



US006236059B1

(12) **United States Patent**
Wolstenholme et al.

(10) **Patent No.:** US 6,236,059 B1
(45) **Date of Patent:** *May 22, 2001

(54) **MEMORY CELL INCORPORATING A CHALCOGENIDE ELEMENT AND METHOD OF MAKING SAME**

(75) Inventors: **Graham R. Wolstenholme; Fernando Gonzalez; Russell C. Zahorik**, all of Boise, ID (US)

(73) Assignee: **Micron Technology, Inc.**, Boise, ID (US)

(*) Notice: This patent issued on a continued prosecution application filed under 37 CFR 1.53(d), and is subject to the twenty year patent term provisions of 35 U.S.C. 154(a)(2).

Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **08/846,725**

(22) Filed: **Apr. 30, 1997**

Related U.S. Application Data

(62) Division of application No. 08/697,341, filed on Aug. 22, 1996, now Pat. No. 5,998,244.

(51) Int. Cl.⁷ **H01L 47/00**

(52) U.S. Cl. **257/3; 257/2; 257/4; 257/5**

(58) Field of Search **257/2, 3, 4, 5, 257/529; 438/95, 98**

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,705,430	*	1/1998	Avanzino et al.	438/618
5,789,277	*	8/1998	Zahorik et al.	438/95
5,831,276	*	11/1998	Gonzalez et al.	257/3
5,841,150	*	11/1998	Gonzalez et al.	257/3

* cited by examiner

Primary Examiner—Steven Loke

Assistant Examiner—Hung Kim Vu

(74) *Attorney, Agent, or Firm*—Fletcher, Yoder & Van Someren

(57) **ABSTRACT**

A memory cell incorporating a chalcogenide element and a method of making same is disclosed. In the method, a doped silicon substrate is provided with two or more polysilicon plugs to form an array of diode memory cells. A layer of silicon nitride is disposed over the plugs. Using a polyspacer process, small pores are formed in the silicon nitride to expose a portion of the polysilicon plugs. A chalcogenide material is disposed in the pores by depositing a layer of chalcogenide material on the silicon nitride layer and planarizing the chalcogenide layer to the silicon nitride layer using CMP. A layer of TiN is next deposited over the plugs, followed by a metallization layer. The TiN and metallization layers are then masked and etched to define memory cell areas.

7 Claims, 12 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3





FIG. 4






FIG. 5




FIG. 6

FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8





FIG. 19






FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14

FIG. 15




FIG. 16




FIG. 17





FIG. 18



MEMORY CELL INCORPORATING A CHALCOGENIDE ELEMENT AND METHOD OF MAKING SAME

This application is a Divisional of application Ser. No. 08/697,341 filed Aug. 22, 1996 U.S. Pat. No. 5,998,244.

BACKGROUND OF THE INVENTION

1. Field of Invention

This invention relates generally to semiconductor circuit devices and methods for making such devices. More particularly, this invention relates to semiconductor memory cells that incorporate a chalcogenide element and to methods for making chalcogenide memory cells.

2. Description of the Related Art

A diode array is a well known memory system used in semiconductor memory devices. The individual diodes in a given array are typically addressed via digit and word lines. In previous diode array memory systems, the individual memory cells were limited to just two memory or logic states: high or low. However, the number of possible logic states for a given memory cell may be increased by connecting a programmable resistor in series with the selected diode. By selectively altering the resistance of the programmable resistor, the diode may be changed to different logic states that correspond to the changed resistance levels. The number of permissible logic states in such systems is limited generally only by the number of different resistance levels that may be reliably set in the programmable resistor.

One possibility for such a programmable resistor is a chalcogenide element. By applying an external stimulus to the chalcogenide element, the internal structure of the chalcogenide material may be modified. The structural modification results in a new resistance level for the chalcogenide material. The chalcogenide material is ovonic in that the observable structural/resistance change exhibited is a variation of the Ovshinsky Effect, and is a function of the current which is applied to the chalcogenide element through the diode.

In the formation of a typical chalcogenide element, a layer of nitride, such as silicon nitride, is disposed over a lower electrode of carbon or TiSi_x . A small pore is formed in the nitride layer, exposing a small area of the lower electrode. A layer of chalcogenide material is deposited on the nitride layer, filling the pore. A layer of carbon is deposited over the chalcogenide layer to form an upper electrode. A TiN layer is disposed over the upper electrode. The chalcogenide layer, upper carbon layer, and TiN layer form a stack that is masked and etched to remove the stack constituents, except in the vicinity of the pore. A passivation layer is placed over the stack and etched to form a contact hole leading to the TiN layer. Finally, a metallization step is performed.

Present techniques for forming the chalcogenide element in a diode array usually involve four separate masking steps: small pore formation, chalcogenide element stack formation, contact layer, and metallization.

There are several disadvantages associated with the present technique for incorporating a chalcogenide element. To begin with, there is an inherent tendency for the chalcogenide stack to dislodge from the nitride layer, causing electrical failure. This lifting problem is due to the rather poor adherence to silicon nitride exhibited by many chalcogenide materials. Second, there are certain difficulties associated with the stack etch step. Due to their physical and chemical nature, the etching of many chalcogenide materials

is presently a process that is difficult to control. Finally, the sheer number of masking steps required make the process relatively uneconomical.

The present invention is directed to overcoming, or at least reducing the effects of, one or more of the foregoing disadvantages.

SUMMARY OF THE INVENTION

In accordance with one aspect of the present invention, a method of forming a forming a chalcogenide element in a memory cell is provided. The method includes the steps of forming a conducting element in a semiconductor substrate and forming a first insulating layer on the semiconductor substrate overlying the conducting element. A pore is formed in the first insulating layer that extends to the conducting element. A layer of chalcogenide material is formed in the pore, and a first conducting layer is formed in contact with the chalcogenide material.

In accordance with another aspect of the present invention, a method of forming a chalcogenide element in a memory cell is provided. The method includes the steps of providing a conducting element in a semiconductor substrate and forming a first insulating layer on the semiconductor substrate overlying the conducting element. A pore is formed in the first insulating layer that extends to the conducting element. A layer of chalcogenide material is formed on the first insulating layer such that a portion of the layer of chalcogenide is disposed in the pore and contacts the conducting element. The portion of the layer of chalcogenide material that is disposed on the first insulating layer is selectively removed by chemical mechanical planarization (CMP). A first conducting layer is formed in contact with the chalcogenide material, and a second conducting layer is formed on the first conducting layer.

In accordance with yet another aspect of the present invention, a method of forming a chalcogenide element in a memory cell is provided. The method includes the steps of providing a semiconductor substrate and providing a conducting element in the semiconductor substrate. A recess is formed in the conducting element. A first insulating layer is formed in the recess. A pore is formed in the first insulating layer that extends to the conducting element. A layer of chalcogenide material is formed in the pore, and a first conducting layer is formed in contact with the chalcogenide material.

In accordance with still another aspect of the present invention, a memory cell is provided. The memory cell includes a semiconductor substrate that has a conducting element disposed therein, and a chalcogenide element. The chalcogenide element is provided by forming a first insulating layer on the semiconductor substrate. A pore is formed in the first insulating layer that extends to the conducting element. A layer of chalcogenide material is formed in the pore, and a first conducting layer is formed in contact with the chalcogenide material.

BRIEF DESCRIPTION OF THE DRAWINGS

Other objects and advantages of the invention will become apparent upon reading the following detailed description and upon reference to the drawings in which:

FIG. 1 depicts the initial stages of a standard process flow for forming a chalcogenide element in a diode array, illustrated in a cross-sectional view.

FIG. 2 depicts the cross-section of FIG. 1 after further processing steps.

FIG. 3 depicts the cross-section of FIG. 2 after further processing steps.

FIG. 4 depicts the cross-section of FIG. 3 after further processing steps.

FIG. 5 depicts the cross-section of FIG. 4 after further processing steps.

FIG. 6 depicts the cross-section of FIG. 5 after further processing steps.

FIG. 7A depicts the initial stages of a process flow for forming a chalcogenide element in a diode array, illustrated in a cross-sectional view.

FIG. 7B depicts the cross-section of FIG. 7A, though with an alternative process flow for forming polysilicon plugs that includes doping the plugs with both p+ and n- dopants.

FIG. 7C depicts the cross-section of FIG. 7A, though with an alternative process flow for forming polysilicon plugs that utilizes a TiN layer deposited on the plugs.

FIG. 7D depicts the cross-section of FIG. 7A, though with an alternative process flow for forming polysilicon plugs that utilizes an oxide layer grown over the plugs.

FIG. 8 depicts the cross-section of FIG. 7A after further processing steps.

FIG. 9 depicts the initial stages of a poly-spacer process for formation of small pores above the polysilicon plugs, illustrated in cross-sectional views.

FIG. 10 depicts the cross-section of FIG. 9 after further processing steps.

FIG. 11 depicts the cross-section of FIG. 10 after further processing steps.

FIG. 12 depicts the cross-section of FIG. 11 after further processing steps.

FIG. 13 depicts the cross-section of FIG. 12 after further processing steps.

FIG. 14 depicts the cross-section of FIG. 13 after further processing steps.

FIG. 15 depicts the cross-section of FIG. 8 after further processing steps.

FIG. 16 depicts the cross-section of FIG. 15 after further processing steps.

FIG. 17 depicts the cross-section of FIG. 16 after further processing steps.

FIG. 18 shows an alternative process for disposing the chalcogenide element in pores that are recessed below the level of the silicon dioxide layer.

FIG. 19 shows another alternative process for disposing the chalcogenide element in pores that are recessed below the level of the silicon dioxide layer.

DETAILED DESCRIPTION OF SPECIFIC EMBODIMENTS

Conventional Process

The embodiments are best described by first considering a common process currently practiced in a CMOS context to form a chalcogenide element. FIGS. 1-6 illustrate cross-sectional views of that existing process. FIG. 1 depicts a substrate 5 prior to the formation of the chalcogenide element. As a result of a number of preliminary processing steps, the substrate 5 includes n- doped regions 7 in the active area of the substrate 5, along with an optional layer of titanium silicide 8, that together function as a buried digit line 10. A relatively thick layer of silicon dioxide 15 overlies the buried digit lines 10. The silicon dioxide 15 has been masked with a contact pattern, not shown, and etched to

create openings in which polycrystalline silicon plugs 20 are formed. A lower electrode 22, in the form of a layer of electrode material, such as carbon, overlies each plug 20. There are shallow p+ regions 24 extending below the plugs 20 as a result of diffusion of p+ material into the substrate 5. Each plug 20 and shallow p+ region 24 forms a diode or memory cell 26 with the digit line 10.

There is a tungsten contact plug 30 disposed in an opening in the silicon dioxide 15. The plug 30 is formed by first depositing a thin layer of titanium and titanium nitride 35 along the sidewalls of the opening and overlying the digit lines 10. Tungsten 40 is then deposited to fill the opening and to overlie the titanium and titanium nitride 35. Following deposition, the titanium and titanium nitride 35 and tungsten 40 are planarized to expose the silicon dioxide 15 and form the contact plug 30.

FIG. 2 depicts the first of four masking steps used to form the chalcogenide element in the existing process. As shown in FIG. 2, a silicon nitride layer 45 of about 300 Å is deposited on the SiO₂ layer 15. The nitride layer 45 is masked, and small pores 50 are formed therein, exposing portions of the lower electrode 22. The pores are typically about 1000 Å wide.

The next masking step involves the formation of the chalcogenide stack. As illustrated in FIG. 3, a layer of a chalcogenide material 55 is deposited on the nitride layer 45, filling the pores 50. An upper electrode 60, in the form of a second carbon layer, is deposited on the chalcogenide layer 55. A conducting layer 65 of TiN is next deposited on the upper electrode 60. Together, the chalcogenide layer 55, the upper electrode 60, and the TiN layer 65 form the chalcogenide stack 70. As shown in FIG. 4, the chalcogenide stack 70 is subsequently masked to define cell areas 75. A stack etch is performed to remove the portions of the chalcogenide stack 70 lateral to the cell areas 75.

As noted above, accurate control of the stack etch may be difficult to achieve in view of the physical and chemical characteristics of the chalcogenide material. If any or all of the layers of the stack 70 are undercut, undesirable voids may form beneath any subsequently deposited passivation layer. Further, unexpected variations in the lateral dimensions of the stack 70 may result in excessive use of die area and necessitate the relaxation of alignment tolerances for the stack 70.

After the stack etch is performed, the positional stability of the chalcogenide stack 70 in the cell areas 75 prior to deposition of additional layers of material is dependent upon the ability of the chalcogenide layer 55 to adhere to the silicon nitride layer 45 at the interface 77 between the two layers 55 and 45, shown in FIG. 4. As noted above, many chalcogenide materials exhibit poor adherence to silicon nitride. This poor adherence may result in the chalcogenide stack 70 in the cell area 75 to lift off of the silicon nitride layer 45, causing failure of the diode 26.

In the third masking step shown in FIG. 5, a passivation layer 80 is formed over the substrate 5 using conventional thin film techniques. The passivation layer 80 is masked and etched to form an opening exposing the TiN layer 65.

The last of the four masking steps is depicted in FIG. 6. A conducting layer 85, which may be metal or polysilicon, is deposited, masked, and etched to remove unwanted metal from either side of the cell areas 75. The metal layer 85 is deposited to contact the TiN layer 65.

Embodiments of the Present Invention

The process flow for a first embodiment of the process of the present invention may be understood by reference to FIGS. 7A–19. FIGS. 7A–19 depict the formation of two chalcogenide elements in a typical diode memory array in a CMOS process. However, it should be understood that NMOS or other process technologies may also be utilized.

FIG. 7A shows a cross-sectional view of a p– substrate **105**. The substrate **105** has been preliminarily processed as generally described above in relation to FIG. 1 to provide n– regions **107** in the active area of the substrate **105**, along with a layer of titanium silicide **108**, that together function as a buried digit line **110**. A relatively thick layer of silicon dioxide **115** overlies the buried digit lines **110**. The silicon dioxide **115** has been masked with a contact pattern, not shown, and etched to create openings in which conducting elements **120**, such as polycrystalline silicon plugs, are formed. The polysilicon plugs **120** are typically doped with p+ dopants, such as boron, gallium, and BF_2 . The p+ dopant may be introduced via ion implantation following plug formation. The dosage may be about 1 to $5\text{E}15$ atoms/ cm^2 , and is advantageously about $2.5\text{E}15$ atoms/ cm^2 , and the energy may be about 50 to 150 KeV, and is advantageously about 100 KeV. Alternatively, the p+ dopant may be introduced by utilizing in situ doped polysilicon with a concentration of about $5\text{E}19$ to $5\text{E}20$ atoms/ cm^2 , and advantageously about $1\text{E}20$ atoms/ cm^2 . In situ doped polysilicon will typically yield a more uniform distribution of p+ dopant in the plugs **120**.

As discussed more fully below, TiSx layers **122** may be laid on top of the plugs **120**. There are shallow p+ regions **124** extending below the plugs **120** as a result of diffusion of p+ material into the substrate **105**. Each plug **120** and shallow p+ region **124** forms a diode **126** of an individual memory cell with the digit line **110**. Together, the diodes **126** form a diode array. The embodiments are described herein in the context of a two diode or memory cell array. However, the discussion is applicable to diode arrays of virtually any size.

In an alternative embodiment shown in FIG. 7B, the plugs **120** may be processed to create a p+ region **128** at an upper portion of the plug **120** and a n– region **129** at a lower portion of the plug **120**. The n– region **129** is formed by doping the plug with n– type dopants, such as phosphorus, antimony, or arsenic at energies and dosages ranging from 35 to 150 KeV and $3\text{E}13$ to $1\text{E}14$ atoms/ cm^2 . The p+ region **128** is, at formed by doping the plug **120** with p+ dopants, such as boron, gallium, gallium, and BF_2 energies and dosages ranging from 35 to 50 KeV and $1\text{E}15$ to $5\text{E}15$ atoms/ cm^2 . Subsequently, a rapid thermal process (RTP) and a hydrogen cycle are performed.

Referring again to FIG. 7A, there is a tungsten contact plug **130** disposed in an opening in the silicon dioxide layer **115**. The plug **130** is formed by first depositing a thin layer of titanium and titanium nitride **135** along the sidewalls of the opening and overlying the digit lines **110**. Tungsten **140** is then deposited to fill the opening and to overlie the titanium and titanium nitride **135**. Following deposition, the titanium and titanium nitride **135** and tungsten **140** are planarized to expose the silicon dioxide **115** and form the contact plug **130**.

After the polysilicon plugs **120** are formed, but prior to subsequent processing steps, such as the formation of the tungsten contact plug **130**, care should be taken to protect the upper surfaces of the plugs **120** from unwanted etchants or the formation of unwanted dielectric layers. For example,

the last etch step used in the poly-spacer process described below will aggressively etch the upper regions of the plugs **120** in the absence of an intervening protective layer. In this regard, there are several possible approaches. For example, as shown in FIG. 7A, a layer of titanium may be deposited to react with the polysilicon in the plugs **120** to form titanium silicide layers **122** that overlie the plugs **120**. The excess titanium may then be planarized to the silicon dioxide layer **115** by CMP as shown. Note that the TiSx layers **122** may be formed via a self-aligned process as shown in FIG. 7A, or alternatively, via a conventional masking step (not shown).

Alternatively, at least two other processes may be used to protect the plugs **120** that eliminate the TiSx layers **122**. In one alternative shown in FIG. 7C, the plugs **120** may be recessed by removing 500 to 1000 Å from the upper portion of the plugs **120** by conventional anisotropic etching techniques. A layer of TiN (not shown) is then deposited over the silicon dioxide layer **115** by PCVD or similar processes to fill the recesses. The layer of TiN layer (not shown) is then planarized by CMP or etching, leaving a protective portion of TiN **144** overlying the polysilicon of each plug **120**. In another alternative described below in conjunction with the description of the poly-spacer process, a TEOS layer (shown as layer **156** in FIGS. 9–13) may be deposited over the plugs **120**, which, when etched, is selective to the polysilicon.

In either of the foregoing alternatives where TiSx formation is eliminated, the polysilicon plugs **120** should be preliminarily protected from reacting with sputtered titanium during formation of the tungsten plug **130**. As shown in FIG. 7D, this may be accomplished by applying a 100–300 Å layer of SiO_2 **142** using low pressure plasma enhanced chemical vapor deposition (LPECVD) or similar techniques over the silicon dioxide layer **115** prior to the formation of the contact hole for the tungsten plug **130** in the SiO_2 layer **115**. The SiO_2 layer **142** acts as a hard mask to prevent the titanium used to form the titanium and titanium nitride layer **135** from reacting with the polysilicon plugs **120** to form TiSx. The layer of SiO_2 may be later removed by CMP or etching if necessary.

In the next phase of the process, small pores are formed in an insulating layer deposited on the substrate **105** using a poly-spacer process. The insulating layer may be silicon nitride or SiO_2 , but is advantageously silicon nitride, and is deposited using conventional thin film techniques. FIG. 8 shows the cross-sectional view of FIG. 7A following deposition of the nitride layer **145** and formation of the small pores **150** therein. Titanium silicide layers **122** have been deposited over the plugs **120**.

The poly-spacer process used to form the pores **150** depicted in FIG. 8 may be understood by reference to FIGS. 9–14. FIG. 9 shows a cross-sectional view of an upper portion of the substrate **105** in the vicinity of the polysilicon plugs **120**. The layer **145** of silicon nitride is first deposited over the SiO_2 layer **115** and TiSi_x layers **122**. A layer **156** of polysilicon is then deposited onto the nitride layer **145**. The layers **145** and **156** are deposited using conventional thin film deposition techniques. The nitride layer **145** may have a substantially uniform thickness ranging from about 50 to 1000 Å, and advantageously it will have a substantially uniform thickness of approximately 500 Å. The nitride layer **145** may be alternatively composed of a dielectric material such as, for example, TEOS oxide **160** or PECVD oxide, but is advantageously composed of silicon nitride. The polysilicon layer **156** may have a substantially uniform thickness ranging from about 1000 to 5000 Å, and advantageously it will have a substantially uniform thickness of approximately

4000 Å. The polysilicon layer 156 may be alternatively composed of TEOS oxide or PECVD oxide, but is typically composed of polysilicon.

FIG. 10 shows the formation of an opening 157 over one of the polysilicon plugs 120. Similar openings will be formed over each polysilicon plug used to form a diode in the memory array. The layers 145 and 156 are etched using conventional anisotropic etching and masking techniques such that the opening 157 extends partially into the layer 145. The etching process may etch material partially from the layer 145 thereby forming a recess in the layer 145. The opening 157 may be formed, for example, as a rectangular channel or as a substantially circular opening in the layers 145 and 156. The opening 157 is typically formed using a conventional circular contact hole mask resulting in a substantially circular opening. The minimum lateral dimension X_1 of the opening 157 may range from about 2500 to 8000 Å, and advantageously it will be approximately 5000 Å. The opening 157 includes a generally horizontal bottom surface 158 and generally vertical side walls 159 at its outer periphery.

A second layer 160 of polysilicon is then deposited onto the layer 156, onto the bottom surface 158 and side walls 159 of the opening 157, using conventional thin film deposition techniques as shown in FIG. 11. The layer 160 may have a substantially uniform thickness ranging from about 500 to 3500 Å, and typically it will have a substantially uniform thickness of approximately 2000 Å. The layer 160 may be alternatively composed of TEOS oxide or PECVD oxide, but is typically composed of polysilicon. In situations where the plugs 120 are not capped with a $TiSi_x$ layer, such as shown in FIG. 8, the layer 160 will usually be TEOS oxide. The layer 160 is then etched using conventional anisotropic etching techniques to form a spacer 161 out of the layer 160 as shown in FIG. 12. The spacer 161 is positioned at the outer periphery of the opening 157 and covers the generally vertical side walls 159. The bottom of the spacer 161 has a lateral thickness substantially equal to the selected thickness of the layer 160 provided the layer 160 conformally coats the layers 145 and 156.

The portion of the layer 145 not covered by the spacer 161 is then etched using conventional anisotropic etching techniques to form the pore 150 (first shown in FIG. 8) in the layer 145 extending to the SiO_2 layer 115 as shown in FIG. 13. The resulting pore 150 may have a minimum lateral dimension ranging from about 500 to 4000 Å, and typically it will have a minimum lateral dimension of approximately 1000 Å. The minimum lateral dimension of the pore 150 is defined by the selected thickness of the layer 160 used in forming the spacer 161. The spacer 161 and layer 156 are then removed using conventional etching techniques as shown in FIG. 14. The disposable spacer 161 thus provides a means of defining the minimum lateral dimension of an ultra-small pore 150 in the layer 145.

In the existing process for forming a chalcogenide element, the next process step would normally entail deposition of the of the chalcogenide layer 55, the second carbon layer 60, and the TiN layer 65 to form the chalcogenide stack 70 as shown in FIG. 3. The chalcogenide stack 70 would then be masked and the stack etch performed to remove the chalcogenide stack 70, except about the cell areas 75 as shown in FIG. 4. However, in the process disclosed herein, a masking step is not used to form the chalcogenide element. Instead, as depicted in FIG. 15, a layer of chalcogenide material 155 is deposited on the nitride layer 145, filling the pores 150 and contacting the polysilicon plug 120. The layer of chalcogenide material is then planarized to the nitride

layer 145. The planarization is advantageously accomplished by CMP, but may be alternatively performed by standard etching techniques.

The deposition of the chalcogenide layer 155 on the nitride layer 145 is accomplished without masking, preferably by sputter deposition. The temperature is preferably about 230° C., but may be between about 25 to 375° C. The pressure is preferably about 4 mTorr, but may be between 2 to 8 mTorr. The power for the sputter process is preferably about 25 Watts, but may be between about 20 to 180 Watts.

Following deposition, the chalcogenide layer 155 is planarized to a thickness of about 500 to 1500 Å by etching or CMP, to remove portions of the chalcogenide layer 155 overlying the nitride layer 145, while at the same time retaining the chalcogenide material in the pore 150. The CMP is selective to the nitride 145. Thus, the CMP action stops when the nitride 145 is exposed.

Typical formulations for the chalcogenide layer 155 include average concentrations of Te in the amorphous state well below 70%, typically below about 60% and ranging in general from as low as about 23% up to about 56% Te, and most preferably to about 48% to 56% Te. Concentrations of Ge are typically above about 15% and range from a low of about 17% to about 44% average, remaining generally below 50% Ge, with the remainder of the principal constituent elements in this class being Sb. The percentages given are atomic percentages which total 100% of the atoms of the constituent elements. In a particularly preferred embodiment, the chalcogenide compositions for these memory cells comprise a Te concentration of about 55%, a Ge concentration of about 22%, and a Sb concentration of about 22%. This class of materials are typically characterized as $Te_aGe_bSb_{100-(a+b)}$, where a is equal to or less than about 70% and preferably between about 60% to about 40%, b is above about 15% and less than 50%, preferably between about 17% to about 44%, and the remainder is Sb.

As shown in FIG. 15, an electrode 163 may be interposed between the chalcogenide material 155 and the polysilicon plugs 120. The electrode 163 may be collimated carbon, titanium-tungsten, or TiN that is deposited as a layer (not shown) over the nitride layer 145, filling the pores 150. The electrode material 163 is deposited via a sputter deposition process utilizing the same parameters disclosed infra for the chalcogenide layer 155 deposition, though with a preferred power of 750 Watts for collimated carbon and about 3 kW for titanium-tungsten or TiN. The electrode material 163 on the nitride layer 145 is then removed, leaving a thin layer of carbon 163 in the pores 150. The removal step may be by conventional etch for collimated carbon, titanium-tungsten, or TiN, or by CMP for either titanium-tungsten or TiN. The remaining thin layer 163 has a thickness of about 200 to 1000 Å. Alternatively, the electrode material 163 may be omitted and the pore 150 filled entirely with chalcogenide material 155.

FIG. 16 is the cross-sectional view of FIG. 15 after further processing steps. As shown in FIG. 16, following the planarization of the chalcogenide layer 155, a TiN layer 165 may be deposited over the chalcogenide layer 155 via CVD or sputter techniques. The TiN layer is preferably about 200 to 1000 Å thick. The array of diodes 126 is then masked and the TiN layer 165, and the silicon nitride layer 145 are etched using common anisotropic techniques to expose the SiO_2 layer on either side of the tungsten plug 130.

In the final masking phase of the process of the present invention shown in FIG. 17, a metal layer 180 is deposited over the substrate 105. The metal layer 180 may be sputtered

aluminum or aluminum-copper alloy, or tungsten applied by CVD, and is preferably about 2000 to 5000 Å thick. The metal layer **180** is then patterned to define cell areas **182** and etched to leave metal overlying the tungsten plug **130** and the cell areas **182**.

In an alternate embodiment of the process depicted in FIGS. **18** and **19**, a chalcogenide element may be disposed on a polysilicon plug **120** below the upper surface of the SiO₂ layer **115**. FIG. **18** depicts the cross-section of FIG. **7A** without TiS_x layers **122** and following further process steps. The polysilicon plug **120** is recessed approximately 1000 Å below the upper surface of the SiO₂. The recess is accomplished by etching the polysilicon plug **120**. Following the etching of the plug **120**, a layer of TiN **185** is deposited on the silicon dioxide layer **115**, filling the recesses over the polysilicon plugs **120**. The layer of TiN (not shown) is then planarized to the SiO₂ layer **115**, preferably by CMP or etching. Following the planarization step, a portion of the TiN layer (not shown) is removed by etching. Typically, about 300 to 500 Å of the TiN layer (not shown) is removed during the etch. A layer of TiN **185** is left over each plug **120**.

FIG. **19** is the cross-sectional view of FIG. **18** following additional process steps. After the TiN layers **185** are formed, a silicon nitride layer **190** is deposited over the silicon dioxide layer **115**, filling the recesses overlying the TiN layers **185**. The nitride layer **190** is then planarized to the SiO₂ layer, preferably by CMP or etching. After the etch, the nitride layer **190** has a thickness of about 500 to 1000 Å. Following the planarization of the nitride layer **190**, a pore **195** may be formed in the nitride layer **190** over each plug **120** using the poly-spacer process described above. Alternatively, the pores **195** may be formed in the overlying nitride layer (not shown) and thus in nitride layers **185** before the overlying nitride layer (not shown) is planarized. Following formation of the pore **195**, the chalcogenide element **200** may be deposited as described above.

Although particular detailed embodiments have been described herein, it should be understood that the invention is not restricted to the details of the disclosed embodiments, and many changes in design, configuration, and dimensions may be possible without departing from the spirit and scope of the invention as defined by the appended claims.

What is claimed is:

1. A memory cell, comprising:

a semiconductor substrate having a conducting element disposed therein; and

a chalcogenide element provided by:

forming a first insulating layer on said semiconductor substrate;

forming a pore in said first insulating layer extending to said conducting element;

forming a layer of chalcogenide material only in said pore; and

forming a first conducting layer in contact with said chalcogenide material.

2. The memory cell of claim 1, wherein said step of forming said layer of chalcogenide material in said pore comprises:

forming a layer of chalcogenide material on said first insulating layer, wherein a portion of said layer of chalcogenide material is disposed in said pore and contacts said conducting element; and

selectively removing said portion of said layer of chalcogenide material that is disposed superadjacent said first insulating layer.

3. The memory cell of claim 2, wherein said step of selectively removing said portion of said layer of chalcogenide material comprises planarizing said layer of chalcogenide material to said first insulating layer by chemical mechanical planarization.

4. The memory cell of claim 1, wherein a layer of titanium silicide is provided between said layer of chalcogenide material and said conductive element.

5. The memory cell of claim 1, wherein a layer of carbon is provided between said layer of chalcogenide material and said conductive element.

6. The memory cell of claim 5, wherein a layer of titanium silicide is provided between said layer of carbon and said conductive element.

7. The memory cell of claim 1, wherein a second conducting layer is provided between said layer of chalcogenide material and said first conducting layer.

* * * * *