



US006260953B1

(12) **United States Patent**
Silverbrook et al.

(10) **Patent No.:** **US 6,260,953 B1**
(45) **Date of Patent:** **Jul. 17, 2001**

(54) **SURFACE BEND ACTUATOR VENTED INK SUPPLY INK JET PRINTING MECHANISM**

(75) Inventors: **Kia Silverbrook; Greg McAvoy**, both of Sydney (AU)

(73) Assignee: **Silverbrook Research Pty Ltd**, Balmain (AU)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/112,820**

(22) Filed: **Jul. 18, 1998**

(30) **Foreign Application Priority Data**

Jul. 15, 1997 (AU) PO7991
Jun. 9, 1998 (AU) PP3985

(51) **Int. Cl.**⁷ **B41J 2/015; B41J 2/135; B41J 2/04**

(52) **U.S. Cl.** **347/54; 347/20; 347/44; 347/47; 347/85**

(58) **Field of Search** **347/20, 44, 54, 347/94, 48, 84, 85**

(56) **References Cited**

FOREIGN PATENT DOCUMENTS

404325257 * 11/1992 (JP) 347/48


* cited by examiner

Primary Examiner—John Barlow
Assistant Examiner—An H. Do

(57) **ABSTRACT**

An ink jet print head includes a nozzle chamber for storage of ink to be ejected from an ink ejection nozzle formed in one wall of the nozzle chamber; and a movable paddle actuator mechanism formed in a first wall of the nozzle chamber, one end of the paddle actuator traversing along a second wall of the nozzle chamber, the second wall being substantially perpendicular to the first wall; the one end further including a flange having a surface abutting the second wall, the movable paddle actuator mechanism being operable to cause the ejection of ink from the ink ejection nozzle with the flange moving substantially tangentially to the second wall.

13 Claims, 8 Drawing Sheets






FIG. 1




FIG. 2




FIG. 3




FIG. 4a





FIG. 4b






FIG. 6



























	Silicon		Sacrificial material		Elastomer
	Boron doped silicon		Cupronickel		Polyimide
	Silicon nitride (Si ₃ N ₄)		CoNiFe or NiFe		Indium tin oxide (ITO)
	CMOS device region		Permanent magnet		PTFE
	Aluminum		Polysilicon		Conductive PTFE
	Glass (SiO ₂)		Titanium Nitride (TiN)		Terfenol-D
	Copper		Titanium boride (TiB ₂)		Shape memory alloy
	Gold		Adhesive		Tantalum
			Resist		Ink

FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17

**SURFACE BEND ACTUATOR VENTED INK
SUPPLY INK JET PRINTING MECHANISM**

**CROSS REFERENCES TO RELATED
APPLICATIONS**

The following Australian provisional patent applications are hereby incorporated by cross-reference. For the purposes of location and identification, US patent applications identified by their US patent application serial numbers (USSN) are listed alongside the Australian applications from which the US patent applications claim the right of priority.

CROSS-REFERENCED AUSTRALIAN PROVISIONAL PATENT APPLICATION NO.	US PATENT/PATENT APPLICATION (CLAIMING RIGHT OF PRIORITY FROM AUSTRALIAN PROVISIONAL APPLICATION)	DOCKET NO.
PO7991	09/113,060	ART01
PO8505	09/113,070	ART02
PO7988	09/113,073	ART03
PO9395	09/112,748	ART04
PO8017	09/112,747	ART06
PO8014	09/112,776	ART07
PO8025	09/112,750	ART08
PO8032	09/112,746	ART09
PO7999	09/112,743	ART10
PO7998	09/112,742	ART11
PO8031	09/112,741	ART12
PO8030	09/112,740	ART13
PO7997	09/112,739	ART15
PO7979	09/113,053	ART16
PO8015	09/112,738	ART17
PO7978	09/113,067	ART18
PO7982	09/113,063	ART19
PO7989	09/113,069	ART20
PO8019	09/112,744	ART21
PO7980	09/113,058	ART22
PO8018	09/112,777	ART24
PO7938	09/113,224	ART25
PO8016	09/112,804	ART26
PO8024	09/112,805	ART27
PO7940	09/113,072	ART28
PO7939	09/112,785	ART29
PO8501	09/112,797	ART30
PO8500	09/112,796	ART31
PO7987	09/113,071	ART32
PO8022	09/112,824	ART33
PO8497	09/113,090	ART34
PO8020	09/112,823	ART38
PO8023	09/113,222	ART39
PO8504	09/112,786	ART42
PO8000	09/113,051	ART43
PO7977	09/112,782	ART44
PO7934	09/113,056	ART45
PO7990	09/113,059	ART46
PO8499	09/113,091	ART47
PO8502	09/112,753	ART48
PO7981	09/113,055	ART50
PO7986	09/113,057	ART51
PO7983	09/113,054	ART52
PO8026	09/112,752	ART53
PO8027	09/112,759	ART54
PO8028	09/112,757	ART56
PO9394	09/112,758	ART57
PO9396	09/113,107	ART58
PO9397	09/112,829	ART59
PO9398	09/112,792	ART60
PO9399	6,106,147	ART61
PO9400	09/112,790	ART62
PO9401	09/112,789	ART63
PO9402	09/112,788	ART64
PO9403	09/112,795	ART65
PO9405	09/112,749	ART66
PP0959	09/112,784	ART68
PP1397	09/112,783	ART69

-continued

CROSS-REFERENCED AUSTRALIAN PROVISIONAL PATENT APPLICATION NO.	US PATENT/PATENT APPLICATION (CLAIMING RIGHT OF PRIORITY FROM AUSTRALIAN PROVISIONAL APPLICATION)	DOCKET NO.
PP2370	09/112,781	DOT01
PP2371	09/113,052	DOT02
PO8003	09/112,834	Fluid01
PO8005	09/113,103	Fluid02
PO9404	09/113,101	Fluid03
PO8066	09/112,751	IJ01
PO8072	09/112,787	IJ02
PO8040	09/112,802	IJ03
PO8071	09/112,803	IJ04
PO8047	09/113,097	IJ05
PO8035	09/113,099	IJ06
PO8044	09/113,084	IJ07
PO8063	09/113,066	IJ08
PO8057	09/112,778	IJ09
PO8056	09/112,779	IJ10
PO8069	09/113,077	IJ11
PO8049	09/113,061	IJ12
PO8036	09/112,818	IJ13
PO8048	09/112,816	IJ14
PO8070	09/112,772	IJ15
PO8067	09/112,819	IJ16
PO8001	09/112,815	IJ17
PO8038	09/113,096	IJ18
PO8033	09/113,068	IJ19
PO8002	09/113,095	IJ20
PO8068	09/112,808	IJ21
PO8062	09/112,809	IJ22
PO8034	09/112,780	IJ23
PO8039	09/113,083	IJ24
PO8041	09/113,121	IJ25
PO8004	09/113,122	IJ26
PO8037	09/112,793	IJ27
PO8043	09/112,794	IJ28
PO8042	09/113,128	IJ29
PO8064	09/113,127	IJ30
PO9389	09/112,756	IJ31
PO9391	09/112,755	IJ32
PP0888	09/112,754	IJ33
PP0891	09/112,811	IJ34
PP0890	09/112,812	IJ35
PP0873	09/112,813	IJ36
PP0993	09/112,814	IJ37
PP0890	09/112,764	IJ38
PP1398	09/112,765	IJ39
PP2592	09/112,767	IJ40
PP2593	09/112,768	IJ41
PP3991	09/112,807	IJ42
PP3987	09/112,806	IJ43
PP3985	09/112,820	IJ44
PP3983	09/112,821	IJ45
PO7935	09/112,822	IJM01
PO7936	09/112,825	IJM02
PO7937	09/112,826	IJM03
PO8061	09/112,827	IJM04
PO8054	09/112,828	IJM05
PO8065	6,071,750	IJM06
PO8055	09/113,108	IJM07
PO8053	09/113,109	IJM08
PO8078	09/113,123	IJM09
PO7933	09/113,114	IJM10
PO7950	09/113,115	IJM11
PO7949	09/113,129	IJM12
PO8060	09/113,124	IJM13
PO8059	09/113,125	IJM14
PO8073	09/113,126	IJM15
PO8076	09/113,119	IJM16
PO8075	09/113,120	IJM17
PO8079	09/113,221	IJM18
PO8050	09/113,116	IJM19
PO8052	09/113,118	IJM20
PO7948	09/113,117	IJM21
PO7951	09/113,113	IJM22
PO8074	09/113,130	IJM23

-continued

CROSS-REFERENCED AUSTRALIAN PROVISIONAL PATENT APPLICATION NO.	US PATENT/PATENT APPLICATION (CLAIMING RIGHT OF PRIORITY FROM AUSTRALIAN PROVISIONAL APPLICATION)	DOCKET NO.
PO7941	09/113,110	IJM24
PO8077	09/113,112	IJM25
PO8058	09/113,087	IJM26
PO8051	09/113,074	IJM27
PO8045	6,110,754	IJM28
PO7952	09/113,088	IJM29
PO8046	09/112,771	IJM30
PO9390	09/112,769	IJM31
PO9392	09/112,770	IJM32
PP0889	09/112,798	IJM35
PP0887	09/112,801	IJM36
PP0882	09/112,800	IJM37
PP0874	09/112,799	IJM38
PP1396	09/113,098	IJM39
PP3989	09/112,833	IJM40
PP2591	09/112,832	IJM41
PP3990	09/112,831	IJM42
PP3986	09/112,830	IJM43
PP3984	09/112,836	IJM44
PP3982	09/112,835	IJM45
PP0895	09/113,102	IR01
PP0870	09/113,106	IR02
PP0869	09/113,105	IR04
PP0887	09/113,104	IR05
PP0885	09/112,810	IR06
PP0884	09/112,766	IR10
PP0886	09/113,085	IR12
PP0871	09/113,086	IR13
PP0876	09/113,094	IR14
PP0877	09/112,760	IR16
PP0878	09/112,773	IR17
PP0879	09/112,774	IR18
PP0883	09/112,775	IR19
PP0880	6,152,619	IR20
PP0881	09/113,092	IR21
PO8006	6,087,638	MEMS02
PO8007	09/113,093	MEMS03
PO8008	09/113,062	MEMS04
PO8010	6,041,600	MEMS05
PO8011	09/113,082	MEMS06
PO7947	6,067,797	MEMS07
PO7944	09/113,080	MEMS09
PO7946	6,044,646	MEMS10
PO9393	09/113,065	MEMS11
PP0875	09/113,078	MEMS12
PP0894	09/113,075	MEMS13

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

Not applicable.

FIELD OF THE INVENTION

The present invention relates to the field of inkjet printing and, in particular, discloses a surface bend actuator vented ink supply ink jet printer.

BACKGROUND OF THE INVENTION

Many different types of printing have been invented, a large number of which are presently in use. The known forms of printers have a variety of methods for marking the print media with a relevant marking media. Commonly used forms of printing include offset printing, laser printing and copying devices, dot matrix type impact printers, thermal paper printers, film recorders, thermal wax printers, dye sublimation printers and ink jet printers both of the drop on demand and continuous flow type. Each type of printer has

its own advantages and problems when considering cost, speed, quality, reliability, simplicity of construction and operation etc.

In recent years, the field of ink jet printing, wherein each individual pixel of ink is derived from one or more ink nozzles has become increasingly popular primarily due to its inexpensive and versatile nature.

Many different techniques of ink jet printing have been invented. For a survey of the field, reference is made to an article by J Moore, "Non-Impact Printing: Introduction and Historical Perspective", Output Hard Copy Devices, Editors R Dubeck and S Sherr, pages 207-220 (1988).

Ink Jet printers themselves come in many different types. The utilization of a continuous stream of ink in ink jet printing appears to date back to at least 1929 wherein U.S. Pat. No. 1,941,001 by Hansell discloses a simple form of continuous stream electro-static ink jet printing.

U.S. Pat. No. 3,596,275 by Sweet also discloses a process of a continuous ink jet printing including the step wherein the ink jet stream is modulated by a high frequency electrostatic field so as to cause drop separation. This technique is still utilized by several manufacturers including Elmjet and Scitex (see also U.S. Pat. No. 3,373,437 by Sweet et al)

Piezoelectric ink jet printers are also one form of commonly utilized ink jet printing device. Piezoelectric systems are disclosed by Kyser et. al. in U.S. Pat. No. 3,946,398 (1970) which utilizes a diaphragm mode of operation, by Zolten in U.S. Pat. No. 3,683,212 (1970) which discloses a squeeze mode of operation of a piezoelectric crystal, Stemme in U.S. Pat. No. 3,747,120 (1972) discloses a bend mode of piezoelectric operation, Howkins in U.S. Pat. No. 4,459,601 discloses a piezoelectric push mode actuation of the ink jet stream and Fischbeck in U.S. Pat. No. 4,584,590 which discloses a shear mode type of piezoelectric transducer element.

Recently, thermal ink jet printing has become an extremely popular form of ink jet printing. The ink jet printing techniques include those disclosed by Endo et al in GB 2007162 (1979) and Vaught et al in U.S. Pat. No. 4,490,728. Both the aforementioned references disclosed ink jet printing techniques which rely upon the activation of an electrothermal actuator which results in the creation of a bubble in a constricted space, such as a nozzle, which thereby causes the ejection of ink from an aperture connected to the confined space onto a relevant print media. Printing devices utilizing the electro-thermal actuator are manufactured by manufacturers such as Canon and Hewlett Packard.

As can be seen from the foregoing, many different types of printing technologies are available. Ideally, a printing technology should have a number of desirable attributes. These include inexpensive construction and operation, high speed operation, safe and continuous long term operation etc. Each technology may have its own advantages and disadvantages in the areas of cost, speed, quality, reliability, power usage, simplicity of construction operation, durability and consumables.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide for an inkjet printing device having a paddle type actuator that further includes a low level of actuation energy.

In accordance with a first aspect of the present invention, there is provided an ink jet nozzle arrangement comprising: a nozzle chamber for storage of ink to be ejected from an ink

ejection nozzle formed in one wall of the nozzle chamber; and a moveable paddle actuator mechanism formed in a first wall of the nozzle chamber, one end of the paddle actuator traversing along a second wall of the nozzle chamber, the second wall being substantially perpendicular to the first wall; the one end further including a flange including a surface abutting the second wall, the movable paddle actuator mechanism being operable to cause the ejection of ink from the ink ejection nozzle with the flange moving substantially tangentially to the second wall.

The arrangement can further include an ink supply channel interconnected to the nozzle chamber for the resupply of ink to the nozzle chamber, the interconnection comprising a slot in a wall of the chamber, the slot being substantially opposite an end of the flange. The slot can be arranged in a corner of a third wall of the chamber and the second wall of the chamber can further form one wall of the ink supply channel.

The arrangement can be formed on a silicon wafer and the ink supply channel can be formed by back etching a back surface of the wafer. The back etching can comprise a plasma etching of the back surface.

The moveable paddle actuator, in being actuated to eject a drop of ink, can constricts the flow of ink into the nozzle chamber.

The arrangement further preferably can include a slot around a substantial portion of the moveable paddle actuator, the slot interconnecting the nozzle chamber with an external ambient atmosphere, the slot being dimensioned to provide for fluid movement during operation of the moveable paddle actuator mechanism so as to minimize the required energy for drop ejection whilst not allowing for the ejection of fluid out of the nozzle chamber.

The movable paddle actuator mechanism preferably can include a thermal actuator for actuation of the mechanism on demand. The thermal actuator can comprise a conductive heater layer between layers of a substantially non-conductive material having a high coefficient of thermal expansion. The conductive heater layer can be arranged in a serpentine form so that, on conductive heating of the conductive heater layer, the conductive heater layer concertinas so as to allow for substantially unhindered expansion of the substantially non-conductive material. The substantially non-conductive material can comprise substantially polytetrafluoroethylene.

The silicon wafer can be initially processed utilizing a CMOS processing system so as to form the electrical circuitry required to operate the ink jet nozzle arrangement on the silicon wafer.

BRIEF DESCRIPTION OF THE DRAWINGS

Notwithstanding any other forms which may fall within the scope of the present invention, preferred forms of the invention will now be described, by way of example only, with reference to the accompanying drawings in which:

FIG. 1 to FIG. 3 are schematic sectional views illustrating the operational principles of the preferred embodiment;

FIG. 4a and FIG. 4b illustrate the operational principles of the thermal actuator of the preferred embodiment;

FIG. 5 is a side perspective view of a single nozzle arrangement of the preferred embodiment;

FIG. 6 illustrates an array view of a portion of a printhead constructed in accordance with the principles of the preferred embodiment.

FIG. 7 provides a legend of the materials indicated in FIGS. 8 to 16; and

FIG. 8 to FIG. 17 illustrate sectional views of the manufacturing steps in one form of construction of an ink jet printhead nozzle.

DESCRIPTION OF PREFERRED AND OTHER EMBODIMENTS

The preferred embodiment of the present invention discloses an inkjet printing device made up of a series of nozzle arrangements. Each nozzle arrangement includes a thermal surface actuator device which includes an L-shaped cross sectional profile and an air breathing edge such that actuation of the paddle actuator results in a drop being ejected from a nozzle utilizing a very low energy level.

Turning initially to FIG. 1 to FIG. 3, there will now be described the operational principles of the preferred embodiment. In FIG. 1, there is illustrated schematically a sectional view of a single nozzle arrangement 1 which includes an ink nozzle chamber 2 containing an ink supply which is resupplied by means of an ink supply channel 3. A nozzle rim 4 is provided, across which a meniscus 5 forms, with a slight bulge when in the quiescent state. A bend actuator device 7 is formed on the top surface of the nozzle chamber and includes a side arm 8 which runs generally parallel to the surface 9 of the nozzle chamber wall so as to form an "air breathing slot" 10 which assists in the low energy actuation of the bend actuator 7. Ideally, the front surface of the bend actuator 7 is hydrophobic such that a meniscus 12 forms between the bend actuator 7 and the surface 9 leaving an air pocket in slot 10.

When it is desired to eject a drop via the nozzle rim 4, the bend actuator 7 is actuated so as to rapidly bend down as illustrated in FIG. 2. The rapid downward movement of the actuator 7 results in a general increase in pressure of the ink within the nozzle chamber 2. This results in an outflow of ink around the nozzle rim 4 and a general bulging of the meniscus 5. The meniscus 12 undergoes a low amount of movement.

The actuator device 7 is then turned off so as to slowly return to its original position as illustrated in FIG. 3. The return of the actuator 7 to its original position results in a reduction in the pressure within the nozzle chamber 2 which results in a general back flow of ink into the nozzle chamber 2. The forward momentum of the ink outside the nozzle chamber in addition to the back flow of ink 15 results in a general necking and breaking off of the drop 14. Surface tension effects then draw further ink into the nozzle chamber via ink supply channel 3. Ink is drawn in the nozzle chamber 3 until the quiescent position of FIG. 1 is again achieved.

The actuator device 7 can be a thermal actuator which is heated by means of passing a current through a conductive core. Preferably, the thermal actuator is provided with a conductive core encased in a material such as polytetrafluoroethylene which has a high level coefficient of expansion. As illustrated in FIG. 4, a conductive core 23 is preferably of a serpentine form and encased within a material 24 having a high coefficient of thermal expansion. Hence, as illustrated in FIG. 4b, on heating of the conductive core 23, the material 24 expands to a greater extent and is therefore caused to bend down in accordance with requirements.

Turning now to FIG. 5, there is illustrated a side perspective view, partly in section, of a single nozzle arrangement when in the state as described with reference to FIG. 2. The nozzle arrangement 1 can be formed in practice on a semiconductor wafer 20 utilizing standard MEMS techniques.

The silicon wafer 20 preferably is processed so as to include a CMOS layer 21 which can include the relevant

electrical circuitry required for the full control of a series of nozzle arrangements **1** formed so as to form a printhead unit. On top of the CMOS layer **21** is formed a glass layer **22** and an actuator **7** which is driven by means of passing a current through a serpentine copper coil **23** which is encased in the upper portions of a polytetrafluoroethylene (PTFE) layer **24**. Upon passing a current through the coil **23**, the coil **23** is heated as is the PTFE layer **24**. PTFE has a very high coefficient of thermal expansion and hence expands rapidly. The coil **23** constructed in a serpentine nature is able to expand substantially with the expansion of the PTFE layer **24**. The PTFE layer **24** includes a lip portion **8** which upon expansion, bends in a scooping motion as previously described. As a result of the scooping motion, the meniscus **5** generally bulges and results in a consequential ejection of a drop of ink. The nozzle chamber **4** is later replenished by means of surface tension effects in drawing ink through an ink supply channel **3** which is etched through the wafer through the utilization of a highly anisotropic silicon trench etcher. Hence, ink can be supplied to the back surface of the wafer and ejected by means of actuation of the actuator **7**. The gap between the side arm **8** and chamber wall **9** allows for a substantial breathing effect which results in a low level of energy being required for drop ejection.

A large number of arrangements **1** of FIG. **5** can be formed together on a wafer with the arrangements being collected into printheads which can be of various sizes in accordance with requirements. Turning now to FIG. **6**, there is illustrated one form of an array **30** which is designed so as to provide three color printing with each color providing two spaced apart rows of nozzle arrangements **34**. The three groupings can comprise groupings **31**, **32** and **33** with each grouping supplied with a separate ink color so as to provide for full color printing capability. Additionally, a series of bond pads e.g. **36** are provided for TAB bonding control signals to the printhead **30**. Obviously, the arrangement **30** of FIG. **6** illustrates only a portion of a printhead which can be of a length as determined by requirements.

One form of detailed manufacturing process which can be used to fabricate monolithic ink jet printheads operating in accordance with the principles taught by the present embodiment can proceed utilizing the following steps:

1. Using a double sided polished wafer **20**, complete drive transistors, data distribution, and timing circuits using a 0.5 micron, one poly, 2 metal CMOS process **21**. Relevant features of the wafer at this step are shown in FIG. **8**. For clarity, these diagrams may not be to scale, and may not represent a cross section though any single plane of the nozzle. FIG. **7** is a key to representations of various materials in these manufacturing diagrams, and those of other cross referenced ink jet configurations.
2. Etch the CMOS oxide layers down to silicon or second level metal using Mask 1. This mask defines the nozzle cavity and the edge of the chips. Relevant features of the wafer at this step are shown in FIG. **8**.
3. Plasma etch the silicon to a depth of 20 microns using the oxide as a mask. This step is shown in FIG. **9**.
4. Deposit 23 microns of sacrificial material **50** and planarize down to oxide using CMP. This step is shown in FIG. **10**.
5. Etch the sacrificial material to a depth of 15 microns using Mask 2. This mask defines the vertical paddle **8** at the end of the actuator. This step is shown in FIG. **11**.
6. Deposit a thin layer (not shown) of a hydrophilic polymer, and treat the surface of this polymer for PTFE adherence.

7. Deposit 1.5 microns of polytetrafluoroethylene (PTFE) **51**.
8. Etch the PTFE and CMOS oxide layers to second level metal using Mask 3. This mask defines the contact vias **52** for the heater electrodes. This step is shown in FIG. **12**.
9. Deposit and pattern 0.5 microns of gold **53** using a lift-off process using Mask 4. This mask defines the heater pattern. This step is shown in FIG. **13**.
10. Deposit 1.5 microns of PTFE **54**.
11. Etch 1 micron of PTFE using Mask 5. This mask defines the nozzle rim **4** and the rim **4** at the edge of the nozzle chamber. This step is shown in FIG. **14**.
12. Etch both layers of PTFE and the thin hydrophilic layer down to the sacrificial layer using Mask 6. This mask defines the gap **10** at the edges of the actuator and paddle. This step is shown in FIG. **15**.
13. Back-etch through the silicon wafer to the sacrificial layer (with, for example, an ASE Advanced Silicon Etcher from Surface Technology Systems) using Mask 7. This mask defines the ink inlets which **3** are etched through the wafer. This step is shown in FIG. **16**.
14. Etch the sacrificial layers. The wafer is also diced by this etch.
15. Mount the printheads in their packaging, which may be a molded plastic former incorporating ink channels which supply the appropriate color ink to the ink inlets at the back of the wafer.
16. Connect the printheads to their interconnect systems. For a low profile connection with minimum disruption of airflow, TAB may be used. Wire bonding may also be used if the printer is to be operated with sufficient clearance to the paper.
17. Fill the completed printheads with ink **55** and test them. A filled nozzle is shown in FIG. **17**.

The presently disclosed ink jet printing technology is potentially suited to a wide range of printing system including: color and monochrome office printers, short run digital printers, high speed digital printers, offset press supplemental printers, low cost scanning printers high speed pagewidth printers, notebook computers with inbuilt pagewidth printers, portable color and monochrome printers, color and monochrome copiers, color and monochrome facsimile machines, combined printer, facsimile and copying machines, label printers, large format plotters, photograph copiers, printers for digital photographic "minilabs", video printers, PHOTO CD (PHOTO CD is a registered trade mark of the Eastman Kodak Company) printers, portable printers for PDAs, wallpaper printers, indoor sign printers, billboard printers, fabric printers, camera printers and fault tolerant commercial printer arrays.

It would be appreciated by a person skilled in the art that numerous variations and/or modifications may be made to the present invention as shown in the specific embodiments without departing from the spirit or scope of the invention as broadly described. The present embodiments are, therefore, to be considered in all respects to be illustrative and not restrictive.

Ink Jet Technologies

The embodiments of the invention use an ink jet printer type device. Of course many different devices could be used. However presently popular ink jet printing technologies are unlikely to be suitable.

The most significant problem with thermal ink jet is power consumption. This is approximately 100 times that

required for high speed, and stems from the energy-inefficient means of drop ejection. This involves the rapid boiling of water to produce a vapor bubble which expels the ink. Water has a very high heat capacity, and must be superheated in thermal ink jet applications. This leads to an efficiency of around 0.02%, from electricity input to drop momentum (and increased surface area) out.

The most significant problem with piezoelectric ink jet is size and cost. Piezoelectric crystals have a very small deflection at reasonable drive voltages, and therefore require a large area for each nozzle. Also, each piezoelectric actuator must be connected to its drive circuit on a separate substrate. This is not a significant problem at the current limit of around 300 nozzles per printhead, but is a major impediment to the fabrication of pagewidth printheads with 19,200 nozzles.

Ideally, the ink jet technologies used meet the stringent requirements of in-camera digital color printing and other high quality, high speed, low cost printing applications. To meet the requirements of digital photography, new ink jet technologies have been created. The target features include:

- low power (less than 10 Watts)
- high resolution capability (1,600 dpi or more)
- photographic quality output
- low manufacturing cost
- small size (pagewidth times minimum cross section)
- high speed (<2 seconds per page).

All of these features can be met or exceeded by the ink jet systems described below with differing levels of difficulty. Forty-five different ink jet technologies have been developed by the Assignee to give a wide range of choices for high volume manufacture. These technologies form part of separate applications assigned to the present Assignee as set out in the table under the heading Cross References to Related Applications.

The ink jet designs shown here are suitable for a wide range of digital printing systems, from battery powered one-time use digital cameras, through to desktop and network printers, and through to commercial printing systems.

For ease of manufacture using standard process equipment, the printhead is designed to be a monolithic 0.5 micron CMOS chip with MEMS post processing. For color photographic applications, the printhead is 100 mm long, with a width which depends upon the ink jet type. The smallest printhead designed is IJ38, which is 0.35 mm wide, giving a chip area of 35 square mm. The printheads each contain 19,200 nozzles plus data and control circuitry.

Ink is supplied to the back of the printhead by injection molded plastic ink channels. The molding requires 50 micron features, which can be created using a lithographically micromachined insert in a standard injection molding tool. Ink flows through holes etched through the wafer to the nozzle chambers fabricated on the front surface of the wafer.

The printhead is connected to the camera circuitry by tape automated bonding.

Tables of Drop on-Demand Ink Jets

Eleven important characteristics of the fundamental operation of individual ink jet nozzles have been identified. These characteristics are largely orthogonal, and so can be elucidated as an eleven dimensional matrix. Most of the eleven axes of this matrix include entries developed by the present assignee.

The following tables form the axes of an eleven dimensional table of ink jet types.

- Actuator mechanism (18 types)
- Basic operation mode (7 types)
- Auxiliary mechanism (8 types)
- Actuator amplification or modification method (17 types)
- Actuator motion (19 types)
- Nozzle refill method (4 types)
- Method of restricting back-flow through inlet (10 types)
- Nozzle clearing method (9 types)
- Nozzle plate construction (9 types)
- Drop ejection direction (5 types)
- Ink type (7 types)

The complete eleven dimensional table represented by these axes contains 36.9 billion possible configurations of ink jet nozzle. While not all of the possible combinations result in a viable ink jet technology, many million configurations are viable. It is clearly impractical to elucidate all of the possible configurations. Instead, certain ink jet types have been investigated in detail. These are designated IJ01 to IJ45 which match the docket numbers in the table under the heading Cross References to Related Applications.

Other ink jet configurations can readily be derived from these forty-five examples by substituting alternative configurations along one or more of the 11 axes. Most of the IJ01 to IJ45 examples can be made into ink jet printheads with characteristics superior to any currently available ink jet technology.

Where there are prior art examples known to the inventor, one or more of these examples are listed in the examples column of the tables below. The IJ01 to IJ45 series are also listed in the examples column. In some cases, a print technology may be listed more than once in a table, where it shares characteristics with more than one entry.

Suitable applications for the ink jet technologies include: Home printers, Office network printers, Short run digital printers, Commercial print systems, Fabric printers, Pocket printers, Internet WWW printers, Video printers, Medical imaging, Wide format printers, Notebook PC printers, Fax machines, Industrial printing systems, Photocopiers, Photographic minilabs etc.

The information associated with the aforementioned 11 dimensional matrix are set out in the following tables.

Description	Advantages	Disvantages	Examples	
ACTUATOR MECHANISM (APPLIED ONLY TO SELECTED INK DROPS)				
Thermal bubble	An electrothermal heater heats the ink to above boiling point, transferring significant heat to the aqueous ink. A bubble	Large force generated Simple construction No moving parts Fast operation	High power Ink carrier limited to water Low efficiency High temperatures	Canon Bubblejet 1979 Endo et al GB patent 2,007,162 Xerox heater-in-pit 1990 Hawkins et al U.S. Pat. No. 4,899,181

-continued

	Description	Advantages	Disadvantages	Examples
	nucleates and quickly forms, expelling the ink. The efficiency of the process is low, with typically less than 0.05% of the electrical energy being transformed into kinetic energy of the drop	Small chip area required for actuator	required High mechanical stress Unusual materials required Large drive transistors Cavitation causes actuator failure Kogation reduces bubble formation Large print heads are difficult to fabricate	Hewlett-Packard TIJ 1982 Vaught et al U.S. Pat. No. 4,490,728
Piezo-electric	A piezoelectric crystal such as lead lanthanum zirconate (PZT) is electrically activated, and either expands, shears, or bends to apply pressure to the ink, ejecting drops.	Low power consumption Many ink types can be used Fast operation High efficiency	Very large area required for actuator Difficult to integrate with electronics High voltage drive transistors required Full pagewidth print heads impractical due to actuator size Requires electrical poling in high field strengths during manufacture	Kyser et al U.S. Pat. No. 3,946,398 Zolton U.S. Pat. No. 3,683,212 1973 Stemme U.S. Pat. No. 3,747,120 Epson Stylus Tektronix IJ04
Electro-strictive	An electric field is used to activate electrostriction in relaxor materials such as lead lanthanum zirconate titanate (PLZT) or lead magnesium niobate (PMN).	Low power consumption Many ink types can be used Low thermal expansion Electric field strength required (approx. 3.4 V/ μm) can be generated without difficulty Does not require electrical poling	Low maximum strain (approx. 0.01%) Large area required for actuator due to low strain Response speed is marginal ($\sim 10 \mu\text{s}$) High voltage drive transistors required Full pagewidth print heads impractical due to actuator size	Seiko Epson, Usui et al JP 253401/96 IJ04
Ferro-electric	An electric field is used to induce a phase transition between the antiferroelectric (AFE) and ferroelectric (FE) phase. Perovskite materials such as tin modified lead lanthanum zirconate titanate (PLZSnT) exhibit large strains of up to 1% associated with the AFE to FE phase transition.	Low power consumption Many ink types can be used Fast operation ($< 1 \mu\text{s}$) Relatively high longitudinal strain High efficiency Electric field strength of around 3 V/ μm can be readily provided	Difficult to integrate with electronics Unusual materials such as PLZSnT are required Actuators require a large area	IJ04
Electro-static plates	Conductive plates are separated by a compressible or fluid dielectric (usually air). Upon application of a voltage, the plates attract each other and displace ink, causing drop ejection. The conductive plates may be in a comb or honeycomb structure, or stacked to increase the surface area and therefore the force.	Low Power consumption Many ink types can be used Fast operation	Difficult to operate electrostatic devices in an aqueous environment The electrostatic actuator will normally need to be separated from the ink Very large area required to achieve high forces High voltage drive transistors may be required Full pagewidth	IJ02, IJ04

-continued

	Description	Advantages	Disadvantages	Examples
Electrostatic pull on ink	A strong electric field is applied to the ink, whereupon electrostatic attraction accelerates the ink towards the print medium	Low current consumption Low temperature	print heads are not competitive due to actuator size High voltage required May be damaged by sparks due to air breakdown Required field strength increases as the drop size decreases High voltage drive transistors required Electrostatic field attracts dust	1989 Saito et al, U.S. Pat. No. 4,799,068 1989 Miura et al, U.S. Pat. No. 4,810,954 Tone-jet
Permanent magnet electro-magnetic	An electromagnet directly attracts a permanent magnet, displacing ink and causing drop ejection. Rare earth magnets with a field strength around 1 Tesla can be used. Examples are: Samarium Cobalt (SaCo) and magnetic materials in the neodymium iron boron family (NdFeB, NdDyFeBNb, NdDyFeB, etc)	Low power consumption Many ink types can be used Fast operation High efficiency Easy extension from single nozzles to pagewidth print heads	Complex fabrication Permanent magnetic material such as Neodymium Iron Boron (NdFeB) required. High local currents required Copper metalization should be used for long electromigration lifetime and low resistivity Pigmented inks are usually infeasible Operating temperature limited to the Curie temperature (around 540 K)	IJ07, IJ10
Soft magnetic core electro-magnetic	A solenoid induced a magnetic field in a soft magnetic core or yoke fabricated from a ferrous material such as electroplated iron alloys such as CoNiFe [1], CoFe, or NiFe alloys. Typically, the soft magnetic material is in two parts, which are normally held apart by a spring. When the solenoid is actuated, the two parts attract, displacing the ink	Low power consumption Many ink types can be used Fast operation High efficiency Easy extension from single nozzles to pagewidth print heads	Complex fabrication Materials not usually present in a CMOS fab such as NiFe, CoNiFe, or CoFe are required High local currents required Copper metalization should be used for long electromigration lifetime and low resistivity Electroplating is required High saturation flux density is required (2.0–2.1 T is achievable with CoNiFe [1])	IJ01, IJ05, IJ08, IJ10, IJ12, IJ14, IJ15, IJ17
Lorenz force	The Lorenz force acting on a current carrying wire in a magnetic field is utilized. This allows the magnetic field to be supplied externally to the print head, for example with rare earth permanent magnets. Only the current carrying wire need be fabricated on the print-	Low power consumption Many ink types can be used Fast operation High efficiency Easy extension from single nozzles to pagewidth print heads	Force acts as a twisting motion Typically, only a quarter of the solenoid length provides force in a useful direction High local currents required Copper metalization should be used for long electromigration lifetime and low resistivity	IJ06, IJ11, IJ13, IJ16

-continued

	Description	Advantages	Disadvantages	Examples
Magnetostriction	head, simplifying materials requirements. The actuator uses the giant magnetostrictive effect of materials such as Terfenol-D (an alloy of terbium, dysprosium and iron developed at the Naval Ordnance Laboratory, hence Ter-Fe-NOL). For best efficiency, the actuator should be pre-stressed to approx. 8 MPa.	Many ink types can be used Fast operation Easy extension from single nozzles to pagewidth print heads High force is available	Pigmented inks are usually infeasible Force acts as a twisting motion Unusual materials such as Terfenol-D are required High local currents required Copper metalization should be used for long electromigration lifetime and low resistivity Pre-stressing may be required	Fischenbeck, U.S. Pat. No. 4,032,929 IJ25
Surface tension reduction	Ink under positive pressure is held in a nozzle by surface tension. The surface tension of the ink is reduced below the bubble threshold, causing the ink to egress from the nozzle.	Low power consumption Simple construction No unusual materials required in fabrication High efficiency Easy extension from single nozzles to pagewidth print heads	Requires supplementary force to effect drop separation Requires special ink surfactants Speed may be limited by surfactant properties	Silverbrook, EP 0771 658 A2 and related patent applications
Viscosity reduction	The ink viscosity is locally reduced to select which drops are to be ejected. A viscosity reduction can be achieved electrothermally with most inks, but special inks can be engineered for a 100:1 viscosity reduction.	Simple construction No unusual materials required in fabrication Easy extension from single nozzles to pagewidth print heads	Requires supplementary force to effect drop separation Requires special ink viscosity properties High speed is difficult to achieve Requires oscillating ink pressure A high temperature difference (typically 80 degrees) is required	Silverbrook, EP 0771 658 A2 and related patent applications
Acoustic	An acoustic wave is generated and focussed upon the drop ejection region.	Can operate without a nozzle plate	Complex drive circuitry Complex fabrication Low efficiency Poor control of drop position Poor control of drop volume	1993 Hadimioglu et al, EUP 550,192 1993 Elrod et al, EUP 572,220
Thermo-elastic bend actuator	An actuator which relies upon differential thermal expansion upon Joule heating is used.	Low power consumption Many ink types can be used Simple planar fabrication Small chip area required for each actuator Fast operation High efficiency CMOS compatible voltages and currents Standard MEMS processes can be used Easy extension from single nozzles to pagewidth print	Efficient aqueous operation requires a thermal insulator on the hot side Corrosion prevention can be difficult Pigmented inks may be infeasible as pigment particles may jam the bend actuator	IJ03, IJ09, IJ17, IJ18, IJ19, IJ20, IJ21, IJ22, IJ23, IJ24, IJ27, IJ28, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34, IJ35, IJ36, IJ37, IJ38, IJ39, IJ40, IJ41

-continued

	Description	Advantages	Disadvantages	Examples
High CTE thermo-elastic actuator	A material with a very high coefficient of thermal expansion (CTE) such as polytetrafluoroethylene (PTFE) is used. As high CTE materials are usually non-conductive, a heater fabricated from a conductive material is incorporated. A 50 μm long PTFE bend actuator with polysilicon heater and 15 mW power input can provide 180 μN force and 10 μm deflection. Actuator motions include: Bend Push Buckle Rotate	heads High force can be generated Three methods of PTFE deposition are under development: chemical vapor deposition (CVD), spin coating, and evaporation PTFE is a candidate for low dielectric constant insulation in ULSI Very low power consumption Many ink types can be used Simple planar fabrication Small chip area required for each actuator Fast operation High efficiency CMOS compatible voltages and currents Easy extension from single nozzles to pagewidth print heads	Requires special material (e.g. PTFE) Requires a PTFE deposition process, which is not yet standard in ULSI fabs PTFE deposition cannot be followed with high temperature (above 350° C.) processing Pigmented inks may be infeasible, as pigment particles may jam the bend actuator	IJ09, IJ17, IJ18, IJ20, IJ21, IJ22, IJ23, IJ24, IJ27, IJ28, IJ29, IJ30, IJ31, IJ42, IJ43, IJ44
Conduct-ive polymer thermo-elastic actuator	A polymer with a high coefficient of thermal expansion (such as PTFE) is doped with conducting substances to increase its conductivity to about 3 orders of magnitude below that of copper. The conducting polymer expands when resistively heated. Examples of conducting dopants include: Carbon nanotubes Metal fibers Conductive polymers such as doped polythiophene Carbon granules	High force can be generated Very low power consumption Many ink types can be used Simple planar fabrication Small chip area required for each actuator Fast operation High efficiency CMOS compatible voltages and currents Easy extension from single nozzles to pagewidth print heads	Requires special materials development (High CTE conductive polymer) Requires a PTFE deposition process, which is not yet standard in ULSI fabs PTFE deposition cannot be followed with high temperature (above 350° C.) processing Evaporation and CVD deposition techniques cannot be used Pigmented inks may be infeasible, as pigment particles may jam the bend actuator	IJ24
Shape memory alloy	A shape memory alloy such as TiNi (also known as Nitinol - Nickel Titanium alloy developed at the Naval Ordnance Laboratory) is thermally switched between its weak martensitic state and its high stiffness austenitic state. The shape of the actuator in its martensitic state is deformed relative to the austenitic shape. The shape change causes ejection of a drop.	High force is available (stresses of hundreds of MPa) Large strain is available (more than 3%) High corrosion resistance Simple construction Easy extension from single nozzles to pagewidth print heads Low voltage operation	Fatigue limits maximum number of cycles Low strain (1%) is required to extend fatigue resistance Cycle rate limited by heat removal Requires unusual materials (TiNi) The latent heat of transformation must be provided High current operation Requires pre-stressing to distort the martensitic state	IJ26
Linear Magnetic	Linear magnetic actuators include the	Linear Magnetic actuators can be	Requires unusual semiconductor	IJ12

-continued

	Description	Advantages	Disvantages	Examples
Actuator	Linear Induction Actuator (LIA), Linear Permanent Magnet Synchronous Actuator (LPMSA), Linear Reluctance Synchronous Actuator (LRSA), Linear Switched Reluctance Actuator (LSRA), and the Linear Stepper Actuator (LSA).	constructed with high thrust, long travel, and high efficiency using planar semiconductor fabrication techniques Long actuator travel is available Medium force is available Low voltage operation	materials such as soft magnetic alloys (e.g. CoNiFe) Some varieties also require permanent magnetic materials such as Neodymium iron boron (NdFeB) Requires complex multi-phase drive circuitry High current operation	
BASIC OPERATION MODE				
Actuator directly pushes ink	This is the simplest mode of operation: the actuator directly supplies sufficient kinetic energy to expel the drop. The drop must have a sufficient velocity to overcome the surface tension.	Simple operation No external fields required Satellite drops can be avoided if drop velocity is less than 4 m/s Can be efficient, depending upon the actuator used	Drop repetition rate is usually limited to around 10 kHz. However, this is not fundamental to the method, but is related to the refill method normally used All of the drop kinetic energy must be provided by the actuator Satellite drops usually form if drop velocity is greater than 4.5 m/s	Thermal ink jet Piezoelectric ink jet IJ01, IJ02, IJ03, IJ04, IJ05, IJ06, IJ07, IJ09, IJ11, IJ12, IJ14, IJ16, IJ20, IJ22, IJ23, IJ24, IJ25, IJ26, IJ27, IJ28, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34, IJ35, IJ36, IJ37, IJ38, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44
Proximity	The drops to be printed are selected by some manner (e.g. thermally induced surface tension reduction of pressurized ink). Selected drops are separated from the ink in the nozzle by contact with the print medium or a transfer roller.	Very simple print head fabrication can be used The drop selection means does not need to provide the energy required to separate the drop from the nozzle	Requires close proximity between the print head and the print media or transfer roller May require two print heads printing alternate rows of the image Monolithic color print heads are difficult	Silverbrook, EP 0771 658 A2 and related patent applications
Electrostatic pull on ink	The drops to be printed are selected by some manner (e.g. thermally induced surface tension reduction of pressurized ink). Selected drops are separated from the ink in the nozzle by a strong electric field.	Very simple print head fabrication can be used The drop selection means does not need to provide the energy required to separate the drop from the nozzle	Requires very high electrostatic field Electrostatic field for small nozzle sizes is above air breakdown Electrostatic field may attract dust	Silverbrook, EP 0771 658 A2 and related patent applications Tone-Jet
Magnetic pull on ink	The drops to be printed are selected by some manner (e.g. thermally induced surface tension reduction of pressurized ink). Selected drops are separated from the ink in the nozzle by a strong magnetic field acting on the magnetic ink.	Very simple print head fabrication can be used The drop selection means does not need to provide the energy required to separate the drop from the nozzle	Requires magnetic ink Ink colors other than black are difficult Requires very high magnetic fields	Silverbrook EP 0741 658 A2 and related patent applications
Shutter	The actuator moves a shutter to block ink flow to the nozzle. The ink pressure is pulsed at a multiple of the drop ejection frequency.	High speed (>50 kHz) operation can be achieved due to reduced refill time Drop timing can be very accurate The actuator	Moving parts are required Requires ink pressure modulator Friction and wear must be considered Stiction is	IJ13, IJ17, IJ21

-continued

	Description	Advantages	Disvantages	Examples
Shuttered grill	energy can be very The actuator moves a shutter to block ink flow through a grill to the nozzle. The shutter movement need only be equal to the width of the grill holes.	possible low Actuators with small travel can be used Actuators with small force can be used High speed (>50 kHz) operation can be achieved	Moving parts are required Requires ink pressure modulator Friction and wear must be considered Stiction is possible	IJ08, IJ15, IJ18, IJ19
Pulsed magnetic pull on ink pusher	A pulsed magnetic field attracts an 'ink pusher' at the drop ejection frequency. An actuator controls a catch, which prevents the ink pusher from moving when a drop is not to be ejected.	Extremely low energy operation is possible No heat dissipation problems	◆Requires an external pulsed magnetic field Requires special materials for both the actuator and the ink pusher Complex construction	IJ10
<u>AUXILLARY MECHANISM (APPLIED TO ALL NOZZLES)</u>				
None	The actuator directly fires the ink drop, and there is no external field or other mechanism required.	Simplicity of construction Simplicity of operation Small physical size	Drop ejection energy must be supplied by individual nozzle actuator	Most ink jets, including piezoelectric and thermal bubble IJ01, IJ02, IJ03, IJ04, IJ05, IJ07, IJ09, IJ11, IJ12, IJ14, IJ20, IJ22, IJ23, IJ24, IJ25, IJ26, IJ27, IJ28, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34, IJ35, IJ36, IJ37, IJ38, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44
Oscillating ink pressure (including acoustic stimulation)	The ink pressure oscillates, providing much of the drop ejection energy. The actuator selects which drops are to be fired be selectively blocking or enabling nozzles. The ink pressure oscillation may be acheived by vibrating the print head, or preferably by an actuator in the ink supply.	Oscillating ink pressure can provide a refill pulse, allowing higher operating speed The actuators may operate with much lower energy Acoustic lenses can be used to focus the sound on the nozzles	Requires external ink pressure oscillator Ink pressure phase and amplitude must be carefully controlled Acoustic reflections in the ink chamber must be designed for	Silverbrook, EP 0771 658 A2 and related patent applications IJ08, IJ13, IJ15, IJ17, IJ18, IJ19, IJ21
Media proximity	The print head is placed in close proximity to the print medium. Selected drops protrude from the print head further than unselected drops, and contact the print medium. The drop soaks into the medium fast enough to cause drop separation.	Low power High accuracy Simple print head construction	Precision assembly required Paper fibers may cause problems Cannot print on rough substrates	Silverbrook, EP 0771 658 A2 and related patent applications
Transfer roller	Drops are printed to a transfer roller instead of straight to the print medium. A transfer roller can also be used for proximity drop separation.	High accuracy Wide range of print substrates can be used Ink can be dried on the transfer roller	Bulky Expensive Complex construction	Silverbrook, EP 0771 658 A2 and related patent applications Tektronix hot melt piezoelectric ink jet Any of the IJ series
Electro-static	An electric field is used to accelerate selected drops towards	Low power Simple print head construction	Field strength required for separation of small	Silverbrook, EP 0771 658 A2 and related patent

-continued

	Description	Advantages	Disadvantages	Examples
	the print medium.		drops is near or above air breakdown	applications Tone-Jet
Direct magnetic field	A magnetic field is used to accelerate selected drops of magnetic ink towards the print medium.	Low power Simple print head construction	Requires magnetic ink Requires strong magnetic field	Silverbrook, EP 0771 658 A2 and related patent applications
Cross magnetic field	The print head is placed in a constant magnetic field. The Lorenz force in a current carrying wire is used to move the actuator.	Does not require magnetic materials to be integrated in the print head manufacturing process	Requires external magnet Current densities may be high, resulting in electromigration problems	IJ06, IJ16
Pulsed magnetic field	A pulsed magnetic field is used to cyclically attract a paddle, which pushes on the ink. A small actuator moves a catch, which selectively prevents the paddle from moving.	Very low power operation is possible Small print head size	Complex print head construction Magnetic materials required in print head	IJ10
<u>ACTUATOR AMPLIFICATION OR MODIFICATION METHOD</u>				
None	No actuator mechanical amplification is used. The actuator directly drives the drop ejection process.	Operational simplicity	Many actuator mechanisms have insufficient travel, or insufficient force, to efficiently drive the drop ejection process	Thermal Bubble Ink jet IJ01, IJ02, IJ06, IJ07, IJ16, IJ25, IJ26
Differential expansion bend actuator	An actuator material expands more on one side than on the other. The expansion may be thermal, piezoelectric, magnetostrictive, or other mechanism. The bend actuator converts a high force low travel actuator mechanism to high travel, lower force mechanism.	Provides greater travel in a reduced print head area	High stresses are involved Care must be taken that the materials do not delaminate Residual bend resulting from high temperature or high stress during formation	Piezoelectric IJ03, IJ09, IJ17, IJ18, IJ19, IJ20, IJ21, IJ22, IJ23, IJ24, IJ27, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34, IJ35, IJ36, IJ37, IJ38, IJ39, IJ42, IJ43, IJ44
Transient bend actuator	A trilayer bend actuator where the two outside layers are identical. This cancels bend due to ambient temperature and residual stress. The actuator only responds to transient heating of one side or the other.	Very good temperature stability High speed, as a new drop can be fired before heat dissipates Cancels residual stress of formation	High stresses are involved Care must be taken that the materials do not delaminate	IJ40, IJ41
Reverse spring	The actuator loads a spring. When the actuator is turned off, the spring releases. This can reverse the force/distance curve of the actuator to make it compatible with the force/time requirements of the drop ejection.	Better coupling to the ink	Fabrication complexity High stress in the spring	IJ05, IJ11
Actuator stack	A series of thin actuators are stacked. This can be appropriate where actuators require high electric field strength, such as electrostatic and piezoelectric actuators.	Increased travel Reduced drive voltage	Increased fabrication complexity Increased possibility of short circuits due to pinholes	Some piezoelectric ink jets IJ04
Multiple	Multiple smaller	Increases the	Actuator forces	IJ12, IJ13, IJ18,

-continued

	Description	Advantages	Disadvantages	Examples
actuators	actuators are used simultaneously to move the ink. Each actuator need provide only a portion of the force required.	force available from an actuator Multiple actuators can be positioned to control ink flow accurately	may not add linearly, reducing efficiency	IJ20, IJ22, IJ28, IJ42, IJ43
Linear Spring	A linear spring is used to transform a motion with small travel and high force into a longer travel, lower force motion.	Matches low travel actuator with higher travel requirements Non-contact method of motion transformation	Requires print head area for the spring	IJ15
Coiled actuator	A bend actuator is coiled to provide greater travel in a reduced chip area.	Increases travel Reduces chip area Planar implementations are relatively easy to fabricate	Actuator forces Generally restricted to planar implementations due to extreme fabrication difficulty in other orientations.	IJ17, IJ21, IJ34, IJ35
Flexure bend actuator	A bend actuator has a small region near the fixture point, which flexes much more readily than the remainder of the actuator. The actuator flexing is effectively converted from an even coiling to an angular bend, resulting in greater travel of the actuator tip.	Simple means of increasing travel of a bend actuator	Care must be taken not to exceed the elastic limit in the flexure area Stress distribution is very uneven Difficult to accurately model with finite element analysis	IJ10, IJ19, IJ33
Catch	The actuator controls a small catch. The catch either enables or disables movement of an ink pusher that is controlled in a bulk manner.	Very low actuator energy Very small actuator size	Complex construction Requires external force Unsuitable for pigmented inks	IJ10
Gears	Gears can be used to increase travel at the expense of duration. Circular gears, rack and pinion, ratchets, and other gearing methods can be used.	Low force, low travel actuators can be used Can be fabricated using standard surface MEMS processes	Moving parts are required Several actuator cycles are required More complex drive electronics Complex construction Friction, friction, and wear are possible	IJ13
Buckle plate	A buckle plate can be used to change a slow actuator into a fast motion. It can also convert a high force, low travel actuator into a high travel, medium force motion.	Very fast movement achievable	Must stay within elastic limits of the materials for long device life High stresses involved Generally high power requirement	S. Hirata et al, "An Ink-jet Head Using Diaphragm Microactuator", Proc. IEEE MEMS, Feb. 1996, pp 418-423. IJ18, IJ27
Tapered magnetic pole	A tapered magnetic pole can increase travel at the expense of force.	Linearized the magnetic force/distance curve	Complex construction	IJ14
Lever	A lever and fulcrum is used to transform a motion with small travel and high force into a motion with longer travel and lower force. The lever can also reverse the direction of travel.	Matches low travel actuator with higher travel requirements Fulcrum area has no linear movement, and can be used for a fluid seal	High stress around the fulcrum	IJ32, IJ36, IJ37
Rotary impeller	The actuator is connected to a rotary impeller. A small angular deflection of the actuator results in	High mechanical advantage The ratio of force to travel of the actuator can be	Complex construction Unsuitable for pigmented inks	IJ28

-continued

	Description	Advantages	Disadvantages	Examples
Acoustic lens	a rotation of the impeller vanes, which push the ink against stationary vanes and out of the nozzle. A refractive or diffractive (e.g. zone plate) acoustic lens is used to concentrate sound waves.	matched to the nozzle requirements by varying the number of impeller vanes No moving parts	Large area required Only relevant for acoustic ink jets	1993 Hadimioglu et al, EUP 550,192 1993 Elrod et al, EUP 572,220
Sharp conductive point	A sharp point is used to concentrate an electrostatic field.	Simple construction	Difficult to fabricate using standard VLSI processes for a surface ejecting ink-jet Only relevant for electrostatic ink jets	Tone-jet
<u>ACTUATOR MOTION</u>				
Volume expansion	The volume of the actuator changes, pushing the ink in all directions.	Simple construction in the case of thermal ink jet	High energy is typically required to achieve volume expansion. This leads to thermal stress, cavitation, and kogation in thermal ink jet implementations	Hewlett-Packard Thermal Ink jet Canon Bubblejet
Linear, normal to chip surface	The actuator moves in a direction normal to the print head surface. The nozzle is typically in the line of movement.	Efficient coupling to ink drops ejected normal to the surface	High fabrication complexity may be required to achieve perpendicular motion	IJ01, IJ02, IJ04, IJ07, IJ11, IJ14
Parallel to chip surface	The actuator moves parallel to the print head surface. Drop ejection may still be normal to the surface.	Suitable for planar fabrication	Fabrication complexity Friction Stiction	IJ12, IJ13, IJ15, IJ33, IJ34, IJ35, IJ36
Membrane push	An actuator with a high force but small area is used to push a stiff membrane that is in contact with the ink.	The effective area of the actuator becomes the membrane area	Fabrication complexity Actuator size Difficulty of integration in a VLSI process	1982 Howkins U.S. Pat. No. 4,459,601
Rotary	The actuator causes the rotation of some element, such a grill or impeller	Rotary levers may be used to increase travel Small chip area requirements	Device complexity May have friction at a pivot point	IJ05, IJ08, IJ13, IJ28
Bend	The actuator bends when energized. This may be due to differential thermal expansion, piezoelectric expansion, magnetostriction, or other form of relative dimensional change.	A very small change in dimensions can be converted to a large motion.	Requires the actuator to be made from at least two distinct layers, or to have a thermal difference across the actuator	1970 Kyser et al U.S. Pat. No. 3,946,398 1973 Stemme U.S. Pat. No. 3,747,120 IJ03, IJ09, IJ10, IJ19, IJ23, IJ24, IJ25, IJ29, IJ30, IJ31, IJ33, IJ34, IJ35
Swivel	The actuator swivels around a central pivot. This motion is suitable where there are opposite forces applied to opposite sides of the paddle, e.g. Lorenz force.	Allows operation where the net linear force on the paddle is zero Small chip area requirements	Inefficient coupling to the ink motion	IJ06
Straighten	The actuator is normally bent, and straightens when energized.	Can be used with shape memory alloys where the austenitic phase is planar	Requires careful balance of stresses to ensure that the quiescent bend is accurate	IJ26, IJ32
Double bend	The actuator bends in one direction when one element is	One actuator can be used to power two nozzles.	Difficult to make the drops ejected by both bend directions	IJ36, IJ37, IJ38

-continued

	Description	Advantages	Disadvantages	Examples
	energized, and bends the other way when another element is energized.	Reduced chip size. Not sensitive to ambient temperature	identical. A small efficiency loss compared to equivalent single bend actuators.	
Shear	Energizing the actuator causes a shear motion in the actuator material.	Can increase the effective travel of piezoelectric actuators	Not readily applicable to other actuator mechanisms	1985 Fishbeck U.S. Pat. No. 4,584,590
Radial constriction	The actuator squeezes an ink reservoir, forcing ink from a constricted nozzle.	Relatively easy to fabricate single nozzles from glass tubing as macroscopic structures	High force required Inefficient Difficult to integrate with VLSI processes	1970 Zoltan U.S. Pat. No. 3,683,212
Coil / uncoil	A coiled actuator uncoils or coils more tightly. The motion of the free end of the actuator ejects the ink.	Easy to fabricate as planar VLSI process Small area required, therefore low cost	Difficult to fabricate for non-planar devices Poor out-of-plane stiffness	IJ17, IJ21, IJ34, IJ35
Bow	The actuator bows (or buckles) in the middle when energized.	Can increase the speed of travel Mechanically rigid	Maximum travel in constrained High force required	IJ16, IJ18, IJ27
Push-Pull	Two actuators control a shutter. One actuator pulls the shutter, and the other pushes it.	The structure is pinned at both ends, so has a high out-of-plane rigidity	Not readily suitable for ink jets which directly push the ink	IJ18
Curl inwards	A set of actuators curl inwards to reduce the volume of ink that they enclose.	Good fluid flow to the region behind the actuator increases efficiency	Design complexity	IJ20, IJ42
Curl outwards	A set of actuators curl outwards, pressurizing ink in a chamber surrounding the actuators, and expelling ink from a nozzle in the chamber.	Relatively simple construction	Relatively large chip area	IJ43
Iris	Multiple vanes enclose a volume of ink. These simultaneously rotate, reducing the volume between the vanes.	High efficiency Small chip area	High fabrication complexity Not suitable for pigmented inks	IJ22
Acoustic vibration	The actuator vibrates at a high frequency.	The actuator can be physically distant from the ink	Large area required for efficient operation at useful frequencies Acoustic coupling and crosstalk Complex drive circuitry Poor control of drop volume and position	1993 Hadimioglu et al, EUP 550,192 1993 Elrod et al, EUP 572,220
None	In various ink jet designs the actuator does not move.	No moving parts	Various other tradeoffs are required to eliminate moving parts	Silverbrook, EP 0771 658 A2 and related patent applications Tone-jet
METHOD OF RESTRICTING BACK-FLOW THROUGH INLET				
Long inlet channel	The inlet channel to the nozzle chamber is made long and relatively narrow, relying on viscous drag to reduce inlet back-flow.	Design simplicity Operational simplicity Reduces crosstalk	Restricts refill rate May result in a relatively large chip area Only partially effective	Thermal ink jet Piezoelectric ink jet IJ42, IJ43
Positive ink pressure	The ink is under a positive pressure, so that in the quiescent state some of the ink drop already protrudes	Drop selection and separation forces can be reduced Fast refill time	Requires a method (such as a nozzle rim or effective hydrophobizing, or	Silverbrook, EP 0771 658 A2 and related patent applications Possible

-continued

	Description	Advantages	Disadvantages	Examples
	from the nozzle. This reduces the pressure in the nozzle chamber which is required to eject a certain volume of ink. The reduction in chamber pressure results in a reduction in ink pushed out through the inlet.		both) to prevent flooding of the ejection surface of the print head.	operation of the following: IJ01-IJ07, IJ09-IJ12, IJ14, IJ16, IJ20, IJ22, IJ23-IJ34, IJ36-IJ41, IJ44
Baffle	One or more baffles are placed in the inlet ink flow. When the actuator is energized, the rapid ink movement creates eddies which restrict the flow through the inlet. The slower refill process is unrestricted, and does not result in eddies.	The refill rate is not as restricted as the long inlet method. Reduces crosstalk	Design complexity May increase fabrication complexity (e.g. Tektronix hot melt Piezoelectric print heads).	HP Thermal Ink Jet Tektronix piezoelectric ink jet
Flexible flap restricts inlet	In this method recently disclosed by Canon, the expanding actuator (bubble) pushes on a flexible flap that restricts the inlet.	Significantly reduces back-flow for edge-shooter thermal ink jet devices	Not applicable to most ink jet configurations Increased fabrication complexity Inelastic deformation of polymer flap results in creep over extended use	Canon
Inlet filter	A filter is located between the ink inlet and the nozzle chamber. The filter has a multitude of small holes or slots, restricting ink flow. The filter also removes, particles which may block the nozzle.	Additional advantage of ink filtration Ink filter may be fabricated with no additional process steps	Restricts refill rate May result in complex construction	IJ04, IJ12, IJ24, IJ27, IJ29, IJ30
Small inlet compared to nozzle	The ink inlet channel to the nozzle chamber has a substantially smaller cross section than that of the nozzle, resulting in easier ink egress out of the nozzle than out of the inlet.	Design simplicity	Restricts refill rate May result in a relatively large chip area Only partially effective	IJ02, IJ37, IJ44
Inlet shutter	A secondary actuator controls the position of a shutter, closing off the ink inlet when the main actuator is energized.	Increases speed of the ink-jet print head operation	Requires separate refill actuator and drive circuit	IJ09
The inlet is located behind the ink-pushing surface	The method avoids the problem of inlet back-flow by arranging the ink-pushing surface of the actuator between the inlet and the nozzle	Back-flow problem is eliminated	Requires careful design to minimize the negative pressure behind the paddle	IJ01, IJ03, IJ05, IJ06, IJ07, IJ10, IJ11, IJ14, IJ16, IJ22, IJ23, IJ25, IJ28, IJ31, IJ32, IJ33, IJ34, IJ35, IJ36, IJ39, IJ40, IJ41
Part of the actuator moves to shut off the inlet	The actuator and a wall of the ink chamber are arranged so that the motion of the actuator closes off the inlet.	Significant reductions in back-flow can be achieved Compact designs possible	Small increase in fabrication complexity	IJ07, IJ20, IJ26, IJ38
Nozzle actuator does not result in ink	In some configurations of ink jet, there is no expansion or movement of an	Ink back-flow problem is eliminated	None related to ink back-flow on actuation	Silverbrook, EP 0771 658 A2 and related patent applications

-continued

	Description	Advantages	Disadvantages	Examples
backflow	actuator which may cause ink back-flow through the inlet.			Valve-jet Tone-jet
<u>NOZZLE CLEARING METHOD</u>				
Normal nozzle firing	All of the nozzles are fired periodically, before the ink has a chance to dry, when not in use the nozzles are sealed (capped) against air. The nozzle firing is usually performed during a special clearing cycle, after first moving the print head to a cleaning station	No added complexity on the print head	May not be sufficient to displace dried ink	Most ink jet systems IJ04, IJ05, IJ06, IJ07, IJ09, IJ10, IJ11, IJ12, IJ14, IJ16, IJ20, IJ22, IJ23, IJ24, IJ25, IJ26, IJ27, IJ28, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34, IJ36, IJ37, IJ38, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44,, IJ45
Extra power to ink heater	In systems which heat the ink, but do not boil it under normal situations, nozzle clearing can be achieved by over-powering the heater and boiling ink at the nozzle.	Can be highly effective if the heater is adjacent to the nozzle	Requires higher drive voltage for clearing May require larger drive transistors	Silverbrook, EP 0771 658 A2 and related patent applications
Rapid succession of actuator pulses	The actuator is fired in rapid succession. In some configurations, this may cause heat build-up at the nozzle which boils the ink, clearing the nozzle. In other situations, it may cause sufficient vibrations to dislodge clogged nozzles.	Does not require extra drive circuits on the print head Can be readily controlled and initiated by digital logic	Effectiveness depends substantially upon the configuration of the ink jet nozzle IJ30, IJ31, IJ32,	May be used with: IJ01, IJ02, IJ03, IJ04, IJ05, IJ06, IJ07, IJ09, IJ10, IJ11, IJ14, IJ16, IJ20, IJ22, IJ23, IJ24, IJ25, IJ27, IJ28, IJ29, IJ33, IJ34, IJ36, IJ37, IJ38, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44, IJ45
Extra power to ink pushing actuator	Where an actuator is not normally driven to the limit of its motion, nozzle clearing may be assisted by providing an enhanced drive signal to the actuator.	A simple solution where applicable	Not suitable where there is a hard limit to actuator movement	May be used with: IJ03, IJ09, IJ16, IJ20, IJ23, IJ24, IJ25, IJ27, IJ29, IJ30, IJ31, IJ32, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44, IJ45
Acoustic resonance	An ultrasonic wave is applied to the ink chamber. This wave is of an appropriate amplitude and frequency to cause sufficient force at the nozzle to clear blockages. This is easiest to achieve if the ultrasonic wave is at a resonant frequency of the ink cavity.	A high nozzle clearing capability can be achieved May be implemented at very low cost in systems which already include acoustic actuators	High implementation cost if system does not already include an acoustic actuator	IJ08, IJ13, IJ15, IJ17, IJ18, IJ19, IJ21
Nozzle clearing plate	A microfabricated plate is pushed against the nozzles. The plate has a post for every nozzle. A post moves through each nozzle, displacing dried ink.	Can clear severely clogged nozzles	Accurate mechanical alignment is required Moving parts are required There is risk of damage to the nozzles Accurate fabrication is required	Silverbrook, EP 0771 658 A2 and related patent applications
Ink pressure	The pressure of the ink is temporarily	May be effective where other	Requires pressure pump or	May be used with all IJ series ink

-continued

	Description	Advantages	Disadvantages	Examples
pulse	increased so that ink streams from all of the nozzles. This may be used in conjunction with actuator energizing.	methods cannot be used	other pressure actuator Expensive Wasteful of ink	jets
Print head wiper	A flexible 'blade' is wiped across the print head surface. The blade is usually fabricated from a flexible polymer, e.g. rubber or synthetic elastomer.	Effective for planar print head surfaces Low cost	Difficult to use if print head surface is non-planar or very fragile Requires mechanical parts Blade can wear out in high volume print systems	Many ink jet systems
Separate ink boiling heater	A separate heater is provided at the nozzle although the normal drop e-ction mechanism does not require it. The heaters do not require individual drive circuits, as many nozzles can be cleared simultaneously, and no imaging is required.	Can be effective where other nozzle clearing methods cannot be used Can be implemented at no additional cost in some ink jet configurations	Fabrication complexity	Can be used with many IJ series ink jets

NOZZLE PLATE CONSTRUCTION

Electro-formed nickel	A nozzle plate is separately fabricated from electroformed nickel, and bonded to the print head chip.	Fabrication simplicity	High temperatures and pressures are required to bond nozzle plate Minimum thickness constraints Differential thermal expansion	Hewlett Packard Thermal Ink jet
Laser ablated or drilled polymer	Individual nozzle holes are ablated by and intense UV laser in a nozzle plate, which is typically a polymer such as polyimide or polysulphone	No masks required Can be quite fast Dome control over nozzle profile is possible Equipment required is relatively low cost	Each hole must be individually formed Special equipment required Slow where there are many thousands of nozzles per print head May produce thin burrs at exit holes	Canon Bubblejet 1988 Sercel et al., SPIE, Vol. 998 Excimer Beam applications, pp. 76-83 1993 Watanabe et al., U.S. Pat. No. 5,208,604
Silicon micro-machined	A separate nozzle plate is micromachined from single crystal silicon, and bonded to the print head wafer.	High accuracy is attainable	Two part construction High cost Requires precision alignment Nozzles may be clogged by adhesive	K. Bean, IEEE Transactions on Electron Devices, Vol. ED-25, No. 10, 1978, pp 1185-1195 Xerox 1990 Hawkins et al., U.S. Pat. No. 4,899,181 1970 Zoltan U.S. Pat No. 3,683,212
Glass capillaries	Fine glass capillaries are drawn from glass tubing. This method has been used for making individual nozzles, but is difficult to use for bulk manufacturing of print heads with thousands of nozzles.	No expensive equipment required Simple to make single nozzles	Very small nozzle sizes are difficult to form Not suited for mass production	
Monolithic, surface micro-machined using VLSI lithographic processes	The nozzle plate is deposited as a layer using standard VLSI deposition techniques. Nozzles are etched in the nozzle plate using VLSI lithography and etching.	High accuracy (<1 μm) Monolithic Low cost Existing processes can be used	Requires sacrificial layer under the nozzle plate to form the nozzle chamber Surface may be fragile to the touch	Silverbrook, EP 0771 658 A2 and related patent applications IJ01, IJ02, IJ04, IJ11, IJ12, IJ17, IJ18, IJ20, IJ22, IJ24, IJ27, IJ28, IJ29, IJ30, IJ31, IJ32, IJ33, IJ34,

-continued

	Description	Advantages	Disadvantages	Examples
Monolithic, etched through substrate	The nozzle plate is a buried etch stop in the wafer. Nozzle chambers are etched in the front of the wafer, and the wafer is thinned from the back thinned from the back side. Nozzles are then etched in the etch stop layer	High accuracy (<1 μm) Monolithic No differential expansion	Requires long etch times Requires a support wafer	IJ36, IJ37, IJ38, IJ39, IJ40, IJ41, IJ42, IJ43, IJ44 IJ03, IJ05, IJ06, IJ07, IJ08, IJ09, IJ10, IJ13, IJ14, IJ15, IJ16, IJ19, IJ21, IJ23, IJ25, IJ26
No nozzle plate	Various methods have been tried to eliminate the nozzles entirely, to prevent nozzle clogging. These include thermal bubble mechanisms and acoustic lens mechanisms	No nozzles to become clogged	Difficult to control drop position accurately Crosstalk problems 1993 Elrod et al	Ricoh 1995 Sekiya et al U.S. Pat. No. 5,412,413 1993 Hadimioglu et al EUP 550,192 EUP 572,220
Trough	Each drop ejector a trough through which a paddle moves. There is no nozzle plate.	Reduced manufacturing complexity Monolithic	Drop firing direction is sensitive to wicking.	IJ35
Nozzle slit instead of individual nozzles	The elimination of nozzle holes and replacement by a slit encompassing many actuator positions reduces nozzle clogging, but increases crosstalk due to ink surface waves	No nozzles to become clogged	Difficult to control drop position accurately Crosstalk problems	1989 Saito et al U.S. Pat. No. 4,799,068
<u>DROP EJECTION DIRECTION</u>				
Edge ('edge shooter')	Ink flow is along the surface of the chip, and ink drops are ejected from the chip edge.	Simple construction No silicon etching required Good heat sinking via substrate Mechanically strong Ease of chip handling	Nozzles limited to edge High resolution is difficult Fast color printing requires one print head per color	Canon Bubblejet 1979 Endo et al GB patent 2,007,162 Xerox heater-in-pit 1990 Hawkins et al U.S. Pat. No. 4,899,181 Tone-jet
Surface ('roof shooter')	Ink flow is along the surface of the chip, and ink drops are ejected from the chip surface, normal to the plane of the chip.	No bulk silicon etching required Silicon can make an effective heat sink Mechanical strength	Maximum ink flow is severely restricted	Hewlett-Packard TIJ 1982 Vaught et al U.S. Pat. No. 4,490,728 IJ02, IJ11, IJ12, IJ20, IJ22
Through chip, forward ('up shooter')	Ink flow is through the chip, and ink drops are ejected from the front surface of the chip.	High ink flow Suitable for pagewidth print heads High nozzle packing density therefore low manufacturing cost	Requires bulk silicon etching	Dilverbrook, EP 0771 658 A2 and related patent applications IJ04, IJ17, IJ18, IJ24, IJ27-IJ45
Through chip, reverse ('down shooter')	Ink flow is through the chip, and ink drops are ejected from the rear surface of the chip.	High ink flow Suitable for pagewidth print heads High nozzle packing density therefore low manufacturing cost	Requires wafer thinning Requires special handling during manufacture	IJ01, IJ03, IJ05, IJ06, IJ07, IJ08 IJ09, IJ10, IJ13, IJ14, IJ15, IJ16, IJ19, IJ21, IJ23, IJ25, IJ26
Through actuator	Ink flow is through the actuator, which is not fabricated as part of the same substrate as the drive transistors.	Suitable for piezoelectric print heads	Pagewidth print heads require several thousand connections to drive circuits	Epson Stylus Tektronix hot melt piezoelectric ink jets

-continued

Description	Advantages	Disadvantages	Examples	
		Cannot be manufactured in standard CMOS fabs Complex assembly required		
		<u>INK TYPE</u>		
Aqueous, dye	Water based ink which typically contains: water, dye, surfactant, humectant, and biocide. Modern ink dyes have high water-fastness, light fastness	Environmentally friendly No odor	Slow drying Corrosive Bleeds on paper May strikethrough Cockles paper	Most existing ink jets All IJ series ink jets Silverbrook, EP 0771 658 A2 and related patent applications
Aqueous, pigment	Water based ink which typically contains: water, pigment, surfactant, humectant, and biocide. Pigments have an advantage in reduced bleed, wicking and strikethrough	Environmentally friendly No odor Reduced bleed Reduced wicking Reduced strikethrough	Slow drying corrosive Pigment may clog nozzles Pigment may clog actuator mechanisms Cockles paper	IJ02, IJ04, IJ21, IJ26, IJ27, IJ30 Silverbrook, EP 0771 658 A2 and related patent applications Piezoelectric ink-jets Thermal ink jets (with significant restrictions)
Methyl Ethyl Ketone (MEK)	MEK is a highly volatile solvent used for industrial printing on difficult surfaces such as aluminum cans.	Very fast drying Prints on various substrates such as metals and plastics	Odorous Flammable	All IJ series ink jets
Alcohol (ethanol, 2-butanol, and others)	Alcohol based inks can be used where the temperatures below the freezing point of water. An example of this is in-camera consumer photographic printing.	Fast drying Operates at sub-freezing temperatures Reduced paper cockle Low cost	Slight odor flammable	All IJ series ink jets
Phase change (hot melt)	The ink is solid at room temperature, and is melted in the print head before jetting. Hot melt inks are usually wax based, with a melting point around 80° C. After jetting the ink freezes almost instantly upon contacting the print medium or a transfer roller.	No drying time-ink instantly freezes on the print medium Almost any print medium can be used No paper cockle occurs No wicking occurs No bleed occurs No strikethrough occurs	High viscosity Printed ink typically has a 'waxy' feel Printed pages may 'block' Ink temperature may be above the curie point of permanent magnets Ink heaters consume power Long warm-up time	Tektronix hot melt piezoelectric ink jets 1989 Nowak U.S. Pat. No. 4,820,346 All IJ series ink jets
Oil	Oil based inks are extensively used in offset printing. They have advantages in improved characteristics on paper (especially no wicking or cockle). Oil soluble dyes and pigments are required.	High solubility medium for some dyes Does not cockle paper Does not wick through paper	High viscosity: this is a significant limitation for use in ink jets, which usually require a low viscosity. Some short chain and multi-branched oils have a sufficiently low viscosity. Slow drying	All IJ series ink jets
Micro-emulsion	A microemulsion is a stable, self forming emulsion of oil, water, and surfactant. The characteristic drop size is less than 100 nm, and is determined by the preferred curvature of the surfactant.	Stops ink bleed High dye solubility Water, oil, and amphiphilic soluble dyes can be used Can stabilize pigment suspensions	Viscosity higher than water Cost is slightly higher than water based ink High surfactant concentration required (around 5%)	All IJ series ink jets

We claim:

1. An ink jet print head comprising:
a nozzle chamber for storage of ink to be ejected from an ink ejection nozzle formed in a first wall of the nozzle chamber; and
a movable paddle actuator mechanism formed in said first wall of said nozzle chamber, one end of said paddle actuator traversing along a second wall of said nozzle chamber, said second wall being substantially perpendicular to said first wall; said one end further having a flange including a surface adjacent said second wall, said movable paddle actuator mechanism being operable to cause ejection of ink from said ink ejection nozzle with said flange moving substantially tangentially to said second wall.
2. An ink jet print head as claimed in claim 1 further comprising an ink supply channel interconnected to said nozzle chamber for supplying ink to said nozzle chamber, said interconnection comprising a slot in a wall of said chamber, said slot being substantially opposite an end of said flange.
3. An ink jet print head as claimed in claim 2 wherein said slot is arranged in a corner of a third wall of said chamber and wherein said second wall of said chamber further forms one wall of said ink supply channel.
4. An ink jet print head as claimed in claim 2 is formed on a silicon wafer.
5. An ink jet print head as claimed in claim 4 wherein said ink supply channel is formed by back etching a back surface of said wafer.
6. An ink jet print head as claimed in claim 5 wherein said back etching comprises a plasma etching of said back surface.

7. An ink jet print head as claimed in claim 4 wherein said silicon wafer is initially processed utilizing a CMOS processing system so as to form an electrical circuit required to operate said ink jet nozzle arrangement on said silicon wafer.
8. An ink jet print head as claimed claim 2 wherein said movable paddle actuator in being actuated to eject a drop of ink, constricts a flow of ink into said nozzle chamber.
9. An ink jet print head as claimed in claim 1 further including a slot around a substantial portion of said movable paddle actuator, said slot interconnecting said nozzle chamber with an external ambient atmosphere, said slot being dimensioned to provide for fluid movement during operation of said movable paddle actuator mechanism while not allowing for the ejection of fluid out of said nozzle chamber.
10. An ink jet print head as claimed in claim 1 wherein said movable paddle actuator mechanism includes a thermal actuator for actuation of said mechanism on demand.
11. An ink jet print head as claimed in claim 10 wherein said thermal actuator comprises a conductive heater layer between layers of a substantially non-conductive material having a high coefficient of thermal expansion.
12. An ink jet print head as claimed in claim 1 wherein said conductive heater layer is arranged in a serpentine form so that, upon conductive heating of said conductive heater layer, said conductive heater layer forms a concertina so as to allow for substantially unhindered expansion of said substantially non-conductive material.
13. An ink jet print head as claimed in claim 10 wherein said substantially non-conductive material comprises substantially polytetrafluoroethylene.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,260,953 B1
DATED : July 17, 2001
INVENTOR(S) : Kia Silverbrook

Page 1 of 1


It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title page,
Item [22] should read -- **Jul. 10, 1998** --.

Signed and Sealed this

Fourteenth Day of May, 2002

Attest:

A handwritten signature in black ink, appearing to read "James E. Rogan", with a horizontal line drawn underneath it.

Attesting Officer

JAMES E. ROGAN
Director of the United States Patent and Trademark Office