



US006346730B1

(12) **United States Patent**
Kitakado et al.

(10) **Patent No.:** **US 6,346,730 B1**
(45) **Date of Patent:** **Feb. 12, 2002**

(54) **LIQUID CRYSTAL DISPLAY DEVICE
HAVING A PIXEL TFT FORMED IN A
DISPLAY REGION AND A DRIVE CIRCUIT
FORMED IN THE PERIPHERY OF THE
DISPLAY REGION ON THE SAME
SUBSTRATE**

5,923,962 A 7/1999 Ohtani et al.
6,166,397 A * 12/2000 Yamazaki et al. 257/59
6,166,414 A * 12/2000 Miyazaki et al. 357/369
6,259,120 B1 * 7/2001 Zhang et al. 257/72

FOREIGN PATENT DOCUMENTS

JP 7-130652 5/1995
JP 2564725 10/1996

OTHER PUBLICATIONS

Hatano et al., "A Novel Self-aligned Gate-overlapped LDD Poly-Si TFT with High Reliability and Performance", IEDM Technical Digest 97, pp. 523-526.

* cited by examiner

Primary Examiner—Ngân V. Ngô

(74) *Attorney, Agent, or Firm*—Eric J. Robinson; Nixon Peabody LLP

(75) **Inventors:** **Hidehito Kitakado; Ritsuko
Kawasaki; Kenji Kasahara**, all of
Kanagawa (JP)

(73) **Assignee:** **Semiconductor Energy Laboratory
Co., Ltd.**, Kanagawa-ken (JP)

(*) **Notice:** Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) **Appl. No.:** **09/541,608**

(22) **Filed:** **Apr. 3, 2000**

(30) Foreign Application Priority Data

Apr. 6, 1999 (JP) 11-099481
Jun. 22, 1999 (JP) 11-176120

(51) **Int. Cl.⁷** **H01L 27/01; H01L 27/12;**
H01L 31/0392

(52) **U.S. Cl.** **257/350; 257/59; 257/72;**
257/344; 257/408; 257/435; 257/296

(58) **Field of Search** 257/59, 72, 350,
257/344, 408, 296, 435

(56) References Cited


U.S. PATENT DOCUMENTS

5,292,675 A 3/1994 Codama
5,323,042 A * 6/1994 Matsumoto 257/350
5,643,826 A 7/1997 Ohtani et al.

(57) ABSTRACT

The present invention provides a semiconductor device in which a bottom-gate TFT or an inverted stagger TFT arranged in each circuit is suitably constructed in conformity with the functionality of the respective circuits, thereby attaining an improvement in the operating efficiency and reliability of the semiconductor device. In the structure, LDD regions in a pixel TFT are arranged so as not to overlap with a channel protection insulating film and to overlap with a gate electrode by at least a portion thereof. LDD regions in an N-channel TFT of a drive circuit is arranged so as not to overlap with a channel protection insulating film and to overlap with a gate electrode by at least a portion thereof. LDD regions in a P-channel TFT of the drive circuit is arranged so as to overlap with a channel protection insulating film and to overlap with the gate electrode.

12 Claims, 13 Drawing Sheets






FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3




FIG. 4




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7A




FIG. 7B




FIG. 8




FIG. 9




FIG. 10




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 11D




FIG. 11E




FIG. 11F




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 13

**LIQUID CRYSTAL DISPLAY DEVICE
HAVING A PIXEL TFT FORMED IN A
DISPLAY REGION AND A DRIVE CIRCUIT
FORMED IN THE PERIPHERY OF THE
DISPLAY REGION ON THE SAME
SUBSTRATE**

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a manufacturing method of a semiconductor device having a circuit in which a thin film transistor (hereinafter referred to as TFT) is formed on a substrate having an insulating surface. More particularly, the present invention is suitable for use in an electro-optical device typically known as a liquid crystal display device having a pixel TFT formed in a display region and a drive circuit formed in the periphery of the display region on the same substrate, and in an electronic equipment mounted with an electro-optical device with this type. Note that throughout the specification of the present invention, the semiconductor device indicates any device utilizing the semiconductor characteristics for functioning, and includes the foregoing electro-optical device and an electronic equipment mounted with the electro-optical device in its category.

2. Description of the Related Art

From the fact that a TFT having an active layer formed of a crystalline silicon film on a substrate having an insulating surface (hereinafter referred as a crystalline silicon TFT) has a high electric field effect mobility, it is possible to form a variety of functional circuits. The above electro-optical device having such functional circuits integrally formed on the same substrate has been developed. As a typical example, the active matrix liquid crystal display device is well known.

In the active matrix liquid crystal device employing the crystalline silicon TFT, a pixel TFT is formed in every pixel of an image display region and a drive circuit is formed in the periphery of the image display region. The drive circuit is composed of a shift resistor circuit, a level shifter circuit, a buffer circuit, a sampling circuit, and the like in which a CMOS circuit as a basic circuit is formed. These circuits are formed on the same substrate, and formed into a unity to complete a display device.

The operating conditions of the pixel TFT and the drive circuit are not necessarily the same. From this, the characteristics that are demanded for a TFT is somewhat different. For example, the pixel TFT is demanded to function as a switch device for applying a voltage to a liquid crystal. The liquid crystal is driven by an a.c., thus a method called frame inverse drive is widely adopted. In this method, for the purpose of maintaining an electric charge of a storage capacitor, the characteristic that is demanded for the pixel TFT was to sufficiently lower an off-current value (a drain current that flows during an off-operation of TFT). On the other hand, since a high drive voltage is applied to the buffer circuit of the drive circuit, it was necessary to raise the voltage-resistance of the TFT so that it will not break when a high voltage is applied. Also, in order to make a current drive ability higher, it was necessary to sufficiently secure an on-current value (a drain current that flows during an on-operation of TFT).

However, the point at issue is that the off-current value of the crystalline silicon TFT easily rises. Moreover, similar to an MOS transistor used in an IC and the like, a deterioration phenomenon such as a drop of the on-current value is observed on the crystalline silicon TFT. This mainly results

from a hot carrier implantation. It has been considered that the hot carrier generated by a high electric field in the vicinity of the drain triggers the deterioration phenomenon.

As a structure of the TFT to reduce the off-current value, an LDD region (Lightly Doped Drain) is known. In this structure, there is provided a region that is added with an impurity element at a low concentration between a channel forming region and a source region or a drain region which is formed by adding an impurity element at a high concentration, and this region is called the LDD region.

For example, Japanese Patent No. 2564725 discloses a method of manufacturing a TFT having an LDD region. In this method, a gate insulating film is formed widely in the direction of a channel width from a gate electrode, and an insulating film thinner than the gate insulating film is further formed beside this gate insulating film. Then by utilizing the difference in the thickness between this insulating film and the gate insulating film, an LDD region is formed in a semiconductor film between the end portion of the gate electrode and a source or drain region.

Moreover, as means for preventing deterioration caused by a hot carrier, a so-called GOLD (Gate-drain Overlapped LDD) structure is known in which the LDD region is arranged so as overlapping the gate electrode via the gate insulating film. With a structure of this kind, the high electric field in the vicinity of a drain is relaxed to prevent hot carrier implantation, which is effective for prevention of the deterioration phenomenon. For example, though a GOLD structure formed by a side wall which is formed of silicon is disclosed by Mutuko Hatano, Hajime Akimoto and Takeshi Sakai, in "IEDM97 TECHNICAL DIGEST, p523-526, 1997," it has been confirmed that an extremely excellent reliability can be achieved when compared with TFTs of other structures.

It had been preferred that the introduction of an impurity element to the semiconductor layer, which is used to form an impurity region such as the LDD region, the source or drain region of the TFT having such a structure, be conducted in a self-aligning manner utilizing the gate electrode and the insulating film for a mask provided on the semiconductor layer. Furthermore, in order to reduce the number of masks, a method (referred as cross dope method in the present invention) has been employed in which once an impurity element of a one conductive type is introduced into the whole surface by utilizing the gate electrode and the insulating film as a mask, an impurity element of a conductive type opposite the one conductive type is introduced into the impurity region of a TFT of either the P-channel TFT or the N-channel TFT at a high concentration.

However, the characteristics being demanded for the pixel TFT and the TFT of the drive circuit such as a shift resistor circuit, or a buffer circuit are not necessarily the same. For example, in the pixel TFT, a large reversal bias (negative voltage in an N-channel TFT) is applied to a gate, whereas the TFT of the drive circuit basically does not operate in the reversal bias state. Also, the operating velocity of the pixel TFT can be $\frac{1}{100}$ of less than that of the TFT of the drive circuit.

The GOLD structure is highly effective in preventing the deterioration of the on-current value, but on the other hand, there arises a problem in that the off-current becomes higher compared with the structure of a normal LDD. Therefore, the GOLD structure was not a preferred structure for applying to the pixel TFT. Contrarily, although the structure of a normal LDD is highly effective in suppressing the off-current value, it has a low effect in relaxing the electric field

in the vicinity of a drain and in preventing deterioration caused by the hot carrier implantation. In this way, in a semiconductor device such as the active matrix liquid crystal display device that has a multiple of integrated circuits of different operating conditions, it was not always desirable to form all the TFTs with the same structure. Such a point of issue like has been revealed as an enhanced characteristic is required for the crystalline silicon TFT in particular, and as the performance demanded of the active matrix liquid crystal display device becomes increased.

Furthermore, although there are several means to decrease the off-current value of the TFT, it was necessary to form a good junction of the channel forming region and the impurity region (LDD region, source region or drain region). In order to do this, the distribution of an impurity element in the interface of the channel forming region and the impurity region that contacts the channel forming region needs to be accurately controlled. However, when the above-mentioned cross dope method is implemented, the distribution of an impurity element in the interface was difficult to control accurately since an impurity element of a one conductive type and an impurity element of a conductive type opposite the one conductive type were introduced into the impurity region of the TFT on one side.

This type of LDD structure is formed by focusing on the characteristic of the N-channel TFT. Many of the P-channel TFTs, which are formed on the same substrate to form the CMOS circuit or the like, were formed as a single drain structure for the purpose of lessening the number of masks as much as possible. In this case, there arises a problem in that since phosphorous (P) for forming an LDD in the N-channel TFT is doped into the source or drain region in the P-channel TFT, a defect is formed in the junction with the channel forming region and the off-current value increases.

SUMMARY OF THE INVENTION

A technique of the present invention is for solving the above problems, and therefore it is an object of the present invention to provide a TFT, which is to be arranged in every circuit of the semiconductor device, having an appropriate structure in accordance with a function of a circuit, to thereby improve operating characteristics and reliability of a semiconductor device.

In order to solve the above problems, according to one aspect of the present invention, there is provided a semiconductor device having a pixel TFT formed in a display region and a TFT of a drive circuit formed in the periphery of the display region on the same substrate, characterized in that: each of the pixel TFT and the TFT of drive circuit has an active layer, an LDD region formed in the active layer, a gate insulating film provided between the active layer and the substrate, and a gate electrode provided between the gate insulating film and the substrate; at least a portion of each LDD region in the pixel TFT or an N-channel TFT of the drive circuit is arranged so as to overlap with the gate electrode; and an LDD region in a P-channel TFT of the drive circuit is arranged so as to overlap with a gate electrode in the P-channel TFT. Also, it is preferable that an LDD region in each of the pixel TFT and the N-channel TFT of the drive circuit is arranged so as not to overlap with a channel protection insulating film, and to overlap with a gate electrode by at least a portion thereof; and an LDD region in a P-channel TFT of the drive circuit is arranged so as to overlap with a channel protection insulating film in the P-channel TFT of the drive circuit, and to overlap with a gate electrode in the P-channel TFT.

Further, according to another aspect of the present invention, a P-channel TFT of the drive circuit has a first impurity region containing therein both an impurity element that gives p-type and an impurity element that gives n-type and a second impurity region containing therein an impurity element that gives p-type, and is characterized in that the second impurity region is formed between the first impurity region and an LDD region in the P-channel TFT of the drive circuit.

This is so constructed that phosphorous that is doped into a source or drain region of a P-channel TFT is not doped into the junction with the channel forming region without increasing the number of masks, attaining a reduction of an off-current value.

A storage capacitor connected to the pixel TFT includes a capacitor wiring formed over the substrate, an insulating film formed on the capacitor wiring, and a semiconductor layer formed on the insulating film. Alternatively, an organic resin film is formed on the pixel TFT, and a capacitor includes a light shielding film formed on the organic resin film, a dielectric film formed closely to the light shielding film, and a pixel electrode connected to the pixel TFT, a portion of which overlaps with the light shielding film.

Moreover, in order to solve the above problems, the present invention provides a method of manufacturing a semiconductor device having a pixel TFT formed in a display region and a TFT of a drive circuit formed in the periphery of the display region on the same substrate, the method comprising the steps of: forming an LDD region in the pixel TFT or an N-channel TFT of the drive circuit at least a portion of which overlaps with a gate electrode; and forming an LDD region in a P-channel TFT of the drive circuit that overlaps a gate electrode in the P-channel TFT. Further, the method may comprises the steps of: forming an LDD region in the pixel TFT and an N-channel TFT of the drive circuit so as not to overlap with a channel protection insulating film, and to overlap with a gate electrode by at least a portion thereof; and forming an LDD region in a P-channel TFT of the drive circuit in a manner so as to overlap with a channel protection insulating film in the P-channel TFT, and to overlap with the gate electrode in the P-channel TFT.

The above method of manufacturing a semiconductor device further comprises the step of: forming a first impurity region containing therein both an impurity element that gives p-type and an impurity element that gives n-type therein and a second impurity region containing therein an impurity element that gives p-type therein in the P-channel TFT of the drive circuit, and the second impurity region is preferably formed between the first impurity region and an LDD region in the P-channel TFT of the drive circuit.

Further, according to another aspect of the present invention, a method of manufacturing a semiconductor device having a pixel TFT formed in a display region and a TFT of a drive circuit formed in the periphery of the display region on the same substrate is characterized in that the method comprises: a first step of forming gate electrodes on a substrate; a second step of forming a gate insulating film on the gate electrodes; a third step of forming semiconductor layers on the gate insulating film; a fourth step of forming channel protection films on the semiconductor layers; a fifth step of introducing an impurity element that gives n-type into the semiconductor layers, and forming LDD regions in an N-channel TFT that does not overlap with the channel protection films; a sixth step of introducing an impurity element that gives n-type into the semiconductor layers, and

forming a source region or a drain region on the N-channel TFT; and a seventh step of introducing an impurity element that gives p-type into one of the semiconductor layers, and forming an LDD region, and a source region or a drain region in the P-channel TFT that overlaps with the channel protection film.

The above method of manufacturing a semiconductor device is characterized by further comprising the steps of: forming a capacitor wiring on the substrate; forming an insulating layer on the capacitor wiring; forming a semiconductor layer on the insulating layer; and forming a storage capacitor connected to the pixel TFT. The method further comprises the steps of: forming an organic resin film on the pixel TFT; forming a light shielding film on the organic resin film; forming a dielectric film on the light shielding film; and forming a pixel electrode connected to the pixel TFT, a portion of which overlaps with the light shielding film; forming a capacitor therefrom. The light shielding film is formed of one or plural kinds of materials selected from aluminum, tantalum, and titanium, and the dielectric film is preferably formed of an oxide of a material which the light shielding film is formed of. Most preferably, this oxide is formed by anodic oxidation.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects of the subject invention will become more fully apparent as the following description is read in light of the attached drawings wherein:

FIGS. 1A–1C are diagrams illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 1;

FIGS. 2A–2C are diagrams illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 1;

FIG. 3 is a diagram illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 1;

FIG. 4 is a diagram illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 2;

FIGS. 5A–5C are diagrams illustrating a manufacturing process of a crystalline semiconductor film of Embodiment 3;

FIGS. 6A–6C are diagrams showing an example of a sectional structure of a storage capacitor of Embodiment 4;

FIGS. 7A–7B are diagrams showing an example of a sectional structure of a storage capacitor of Embodiment 4;

FIG. 8 is a diagram showing a sectional structure of an active matrix liquid crystal display device of Embodiment 7;

FIG. 9 is a perspective view schematically showing an active matrix liquid crystal display device of Embodiment 7;

FIG. 10 is a diagram of the top surface of a pixel of Embodiment 7;

FIGS. 11A–11F are diagrams illustrating examples of a semiconductor device of Embodiment 8;

FIGS. 12A–12C are diagrams illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 6; and

FIG. 13 is a diagram illustrating a manufacturing process of a pixel TFT and a TFT of a drive circuit of Embodiment 6.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hereinafter, preferred embodiment modes of the present invention will be explained in detail as indicated in the following embodiments.

Embodiment 1

A description of a preferred embodiment of the present invention will be given with reference to FIGS. 1A through 3. Here, a description of a method of simultaneously manufacturing a pixel TFT in a display region and a TFT of a drive circuit formed in the periphery of the display region will be explained in detail by following a process.

In FIG. 1A, a low alkali glass substrate or a quartz substrate can be used as a substrate **101**. On the surface of the substrate **101** where a TFT is formed, an insulating film such as a silicon oxide film, a silicon nitride film, or a silicon oxide nitride film can be formed (not shown). Gate electrodes **102** through **104** and a capacitor wiring **105** are formed by employing materials containing an element selected from tantalum (Ta), titanium (Ti), tungsten (W), molybdenum (Mo), and aluminum (Al) or having one of these elements as a main component and are coated by utilizing well-known film formation methods such as sputtering and vacuum evaporation. Then, etching and patterning is carried out so that the end surface is tapered. For example, after forming the Ta film at a thickness of 200 nm by sputtering, and forming a resist mask into a predetermined shape, a plasma etching is performed with mixed gas of CF_4 and O_2 to make a desired shape. Also, a gate electrode can be a two-layer structure (not shown) composed of tantalum nitride (TaN) and Ta, or tungsten nitride (WN) and W. Although not shown in the figures, a gate wiring connected to the gate electrode is formed at the same time.

A gate insulating film **106** is formed of a material having a silicon oxide and silicon nitride as constituents at a thickness of 10 to 200 nm, preferably 50 to 150 nm. For example, a laminated layer formed of a silicon nitride film **106a** made of SiH_4 , NH_3 , and N_2 as raw materials having a thickness of 50 nm having and a silicon oxide nitride film **106b** with a thickness of 75 nm having SiH_4 and N_2O as raw material by plasma CVD can be the gate insulating film. Of course, the gate insulating film **106** can be a single layer made up of a silicon nitride film or a silicon oxide film. Further, in order to obtain a clean surface, it is better to implement plasma hydrogenate before forming the film of the gate insulating film.

Next, the formation of a crystalline semiconductor film that becomes an active layer of a TFT is performed. Silicon is used as the material for the crystalline semiconductor film. First, an amorphous silicon film is formed at a thickness of 20 to 150 nm by a well-known film formation method such as plasma CVD or sputtering so as to be close to the gate insulating film **106**. Although the manufacturing conditions of an amorphous silicon film is not restricted by anything, it is desired that the concentration of impurity elements of oxygen and nitrogen contained in the film be reduced to $5 \times 10^{18} \text{ cm}^{-3}$ or less. Since the gate insulating film and the amorphous silicon film can be formed with the same film formation method, both may be continuously formed. After forming the gate insulating film, contamination on the surface can be prevented by not exposing it in the atmosphere once and characteristic unevenness and fluctuation of a threshold voltage of a TFT manufactured can be reduced. A crystalline silicon film **107** is thereafter formed by employing a well-known crystallization technique. For example, the crystalline silicon film **107** can also be formed by a crystallization method using a catalytic element such as laser crystallization, or thermal crystallization (solid phase crystallization), or by following a technique disclosed in Japanese Patent Application Laid-Open No. Hei 7-130652.

In the region where the N-channel TFT of the crystalline silicon film **107** is formed, boron (B) may be added at a level

of approximately 1×10^{16} to $5 \times 10^{17} \text{ cm}^{-3}$ in order to control a threshold voltage. The adding of boron (B) may be implemented by an ion dope method or may be added at the same time when forming the amorphous silicon film (FIG. 1A).

Next, the adding of an impurity element that gives n-type is performed for the purpose of forming an LDD region in the N-channel TFT. First, a mask insulating film **108** made of a silicon oxide film and a silicon nitride film is formed at a thickness of 100 to 200 nm, typically 120 nm, on the surface of the crystalline silicon film **107**. And a photoresist film is entirely formed on this surface. Thereafter, the photoresist film is exposed using gate electrodes **102** through **104** as masks by an exposure from the back surface of the substrate **101** to thereby form resist masks **109** through **112**. Through this method, resist masks can be formed on the gate electrodes and within the gate electrodes.

Then, an impurity element that gives the n-type is doped via the mask insulating film **108** into the crystalline silicon film underlying it by an ion doping method (an ion implantation method can also be used). In the technical field of semiconductors, applicable impurity elements that give n-type include the elements from the periodic table group **15** such as phosphorous (P), arsenic (As), and antimony (Sb). In this case, phosphorous (P) is used. The concentration of phosphorous (P) added into impurity regions **113** through **118** that are thus formed is preferably in the range of 1×10^{17} to $5 \times 10^{18} \text{ cm}^{-3}$, and here, it is $5 \times 10^{17} \text{ cm}^{-3}$. The present invention expresses the concentration of the impurity element that gives n-type included in the impurity regions **113** through **118** as "n⁻" (FIG. 1B).

Next, the mask insulating film **108** is removed by etching using this resist mask and channel protection films **119** through **122** are formed. For the purpose of conducting a better choice of etching the mask insulating film **108** with respect to the crystalline silicon film **107** as an underlying film, a wet etching method using fluorine solution is adopted here. Of course, dry etching can be implemented, for instance, the insulating film **108** may be etched by using CHF_3 . In any case, the process here is to conduct over-etching so that the channel protection films **119** through **122** can be formed further inside than the end surface of the resist masks **109** through **112** (FIG. 1C).

A process of forming an impurity region to function as a source region or a drain region in the N-channel TFT is performed next. In this process, masks **123** through **125** are formed by a normal exposure method using a resist. Then, the channel protection film **122** on the capacitor wiring **105** is etched and removed by using the thus formed resist masks. Subsequently, impurity regions **126** through **130** into which an impurity element that gives n-type has been added are formed by an ion doping method (an ion implantation method can also be used) on the crystalline silicon film **107**. Here, in the impurity regions **126** through **130**, the impurity element is included at a concentration of $5 \times 10^{20} \text{ cm}^{-3}$, though it can be 1×10^{20} to $1 \times 10^{21} \text{ cm}^{-3}$. The present invention expresses this concentration as "n⁺" (FIG. 2A).

A process of adding an impurity element that gives p-type is performed for the purpose of forming a source region or a drain region in the P-channel TFT of the drive circuit. In the technical field of semiconductors, applicable semiconductor elements that give p-type include the element from the periodic table group **13** such as boron (B), aluminum (Al), and gallium (Ga), and here, boron is used. A mask **131** is formed so that it is positioned on the inside of the channel protection film **119**, and resist masks **132** and **133** are formed

so as to cover the entire region where the N-channel TFTs are formed. Impurity regions **134** through **136** are thereafter formed by an ion doping method (an ion implantation method can also be used) using diborane (B_2H_6). An impurity element is added from the surface of the crystalline silicon film into the impurity regions **135a**, **135b**, **136a** and **136b**. The concentration of boron in the regions is in the range of 1.5×10^{20} to $3 \times 10^{21} \text{ cm}^{-3}$, here it is $2 \times 10^{21} \text{ cm}^{-3}$. The present invention expresses the concentration of the impurity element that gives p-type included in the impurity regions **135a**, **135b**, **136a**, and **136b** as "p³⁰". On the other hand, since the crystalline silicon film is added with an impurity element via the channel protection film **119**, the concentration of boron (B) became 1×10^{16} to $1 \times 10^{18} \text{ cm}^{-3}$ in this impurity region **134**. The present invention expresses the concentration of the impurity element that gives p-type included in the impurity region **134** that is thus formed in this process as "p⁻".

As shown in FIGS. 1B to 2A, the impurity regions **135b** and **136b** are added with phosphorous (P) in the previous process, and therefore a region containing a mixture of boron (B) and phosphorous (P) is formed. However, by adding boron (B) at a concentration of 1.5 to 3 times higher in this process, p-type conductivity can be secured and no influence is inflicted upon the characteristics of the TFT. The present invention indicates these regions as an impurity region "B". Also, the impurity regions **135a** and **136a** at the side of the channel forming region of the impurity regions "B" **135b** and **136b** contain boron (B) only, and the present invention indicates these regions as an impurity region "A". The impurity region **134** overlapping the gate electrode **103** as well as the channel protection film **120** is also formed as a region containing boron (B) only and functions as an LDD region (FIG. 2B).

Respective impurity elements are selectively added into the crystalline silicon film and then etching is carried out on this crystalline silicon film so that it is divided into island-like films. Then a protection insulating film **137**, which will later become a portion of a first interlayer insulating film, is formed. The protection insulating film **137** can be formed of a silicon nitride film, a silicon oxide film, a silicon oxide nitride film, or a lamination film of the combination thereof and may be at a thickness of 100 to 400 nm.

Thereafter, the heat treatment process is carried out for the purpose of activating the impurity elements giving either an n-type or p-type that have been doped at respective concentrations. This process can be carried out by annealing methods such as furnace annealing, laser annealing, or rapid thermal annealing (RTA). Here, activation is carried out by furnace annealing. Heat treatment is performed at 300 to 650° C., preferably 500 to 550° C. in a nitrogenic atmosphere. In this process, heat treatment was performed at 525° C. for 4 hours. Then heat treatment is further performed at 300 to 450° C. for 1 to 12 hours in an atmosphere containing 3 to 100% of hydrogen and then hydrogenation is carried out on the active layer. This process is to terminate the dangling bonds in the active layer by thermally excited hydrogen. As other hydrogenation means, plasma hydrogenation (using hydrogen excited by plasma) can be performed.

When the crystalline silicon film **107**, which becomes the active layer, is fabricated by a crystallization method using a catalytic element from an amorphous silicon film, the amount of catalytic element remaining in the crystalline silicon film **107** is approximately 1×10^{17} to $5 \times 10^{19} \text{ cm}^{-3}$. Of course, there is no problem in completing and operating the TFT in this situation. However, it is more preferable that the residual catalytic element be removed at least from the

channel forming region. One of the means of removing this catalytic element is to utilize the gettering action of phosphorous (P). The concentration of phosphorous (P) necessary in the gettering process is approximately the same as that of impurity region (n^+) formed in FIG. 2B. Through the heat treatment in the activation process that is implemented here, the catalytic element can be gettered from the channel forming region in the N-channel TFT and the P-channel TFT to the impurity regions in the periphery where phosphorous (P) has been doped. As a result, the concentration of the catalytic element in the channel forming region can be made to be $5 \times 10^{17} \text{ cm}^{-3}$ or less. The catalytic element having a concentration of 1×10^{18} to $5 \times 10^{20} \text{ cm}^{-3}$ has segregated to the above impurity region (FIG. 2C).

After completing the activation process, an interlayer insulating film **138** is formed at a thickness of 500 to 1500 nm on the protection insulating film **137**. A first interlayer insulating film is a lamination film formed of the above protection insulating film **137** and the interlayer insulating film **138**. A contact hole that reaches the source region or drain region of the respective TFTs is formed, and then source wirings **139** through **141** and drain wirings **142** and **143** are formed. Although not shown in the figure, this electrode according to the present embodiment is laminated film of a 3-layered structure formed of a 100 nm Ti film, a 300 nm aluminum film containing Ti, and a 150 nm Ti film by sputtering in successions.

The protection insulating film **137** and the interlayer insulating film **138** can be formed of a silicon nitride film, a silicon oxide film or a silicon oxide nitride film, or the like. In any case, it is better that the internal stress of the film be made into the compression stress.

Next, using a silicon nitride film, a silicon oxide film, or a silicon oxide nitride film, a passivation film **144** is formed at a thickness of 50 to 500 nm (typically 100 to 300 nm). If hydrogenation process is carried out in this state, desirable effects can be achieved with respect to an improvement in the characteristics of TFTs. For instance, it is appropriate that heat treatment is performed at 300 to 450° C. in an atmosphere containing 3 to 100% of hydrogen for 1 to 12 hours or similar effects can be obtained if a plasma hydrogenation method employed. Moreover, at the position of forming a contact hole for connecting a pixel electrode to the drain wiring in a later process, an opening portion can be formed in the passivation film **144**.

Then a second interlayer insulating film **145** formed of an organic resin film is formed at about 1 μm of thickness. Polyimide, acryl, polyamide, polyimide-amide, BCB (benzocyclobutene), etc. are applicable as inorganic resin materials. Here, after coating the substrate, the second interlayer insulating film **145** is formed by baking at 300° C. using a type of polyimide that is thermal polymeric. Then, a contact hole that reaches the drain wiring **143** is formed in the second interlayer insulating film **145** and the passivation film **144**, on to which a pixel electrode **146** is provided. If the pixel electrode **146** is used in transmission type liquid crystal display devices, a transparent conductive film can be used. On the other hand, if it is used in reflection type liquid crystal display devices, a metallic film can be used. Here the pixel electrode is used in a transmission type liquid crystal device; therefore an indium tin oxide (ITO) film is formed at a thickness of 100 nm by sputtering. A pixel electrode **190** is the electrode of a neighboring pixel.

Through the above processes, the pixel TFT in a display region and the TFT of the drive circuit in the periphery of the display region can be formed on the same substrate. In the

drive circuit, an N-channel TFT **168** and a P-channel TFT **167** are formed, allowing for a logic circuit structured with a CMOS circuit as the basic circuit. A pixel TFT **169** is an N-channel TFT, and furthermore, from the capacitor wiring **105**, a semiconductor layer **166**, and an insulating layer formed therebetween, a storage capacitor **170** is connected to this pixel TFT **169** (FIG. 3).

A P-channel TFT **167** of the drive circuit has a channel forming region **147**, source regions **150a** and **150b**, drain regions **151a** and **151b**, and LDD regions **148** and **149**. The source region **150b** and the drain region **151b** are formed as the impurity region "B". The concentration of boron (B) in this region is 1.5 to 3 times higher than the concentration of phosphorous (P). On the inside of the impurity region "B", that is, the source region **150a** and the drain region **151a** formed on the side of the channel forming region **147** correspond to the impurity region "A". This impurity region "A" is a region containing only boron at the same concentration as that of the impurity region "B". Further, the LDD regions **148** and **149** overlapping the gate electrode **103** as well as the channel protection film **120** are also formed as regions containing only boron (B). By separating the impurity region "B" from the channel forming region in this way, the reliable junctions between N-channel forming region and the LDD region that comes in contact with the channel forming region, and still further between the LDD region and either the source region or the drain region are attained, enabling the characteristics of the P-channel TFT well retained.

An N-channel TFT **168** of the drive circuit has a channel forming region **152**, a source region **155** and a drain region **156**, and LDD regions **153** and **154**. The pixel TFT **169** has channel forming regions **157** and **158**, source regions or drain regions **163** through **165**, and LDD regions **159** through **162**. The LDD regions in the N-channel TFT of the drive circuit are provided for the principal purpose of relaxing a high electric field in the vicinity of the drain to prevent the deterioration of the on-current value due to hot carrier implantation. Thus, it is appropriate to set the concentration of a suitable impurity element that gives n-type to 5×10^{17} to $5 \times 10^{18} \text{ cm}^{-3}$. On the other hand, the LDD regions in the pixel TFT are provided for the principal purpose of decreasing the off-current value, in which the concentration of the impurity element can be the same as that in the LDD regions in the N-channel TFT of the drive circuit, although it can also be $\frac{1}{2}$ to $\frac{1}{10}$ of that concentration. In FIG. 3, although the pixel TFT **169** is completed as a double-gate structure, it can also be a single-gate structure, or a multi-gate structure provided with a plurality of gate electrodes.

As explained above, according to the present invention, the structure of the TFT constituting each circuit has been optimized in accordance with the specifications demanded by the pixel TFT and the driver circuit, with the result that the operating efficiency and reliability of a semiconductor device can be improved.

Embodiment 2

Referring to FIG. 4, Embodiment 2 is explained by way of example in which a storage capacitor connected to the pixel TFT is provided, as is different from Embodiment 1. The P-channel TFT **167** and the N-channel TFT **168** of the drive circuit and the pixel TFT **169** are manufactured in the same way as in Embodiment 1. The point of difference from Embodiment 1 will be explained hereinbelow.

At least on the top of the pixel TFT, a light shielding film **171** is formed on the second interlayer insulating film **145**.

11

The light shielding film **171** is a film formed of one or a plurality of elements selected from Al, Ti, and Ta or has one of these elements as main components with a thickness of 100 to 300 nm, and is patterned into a predetermined shape. Similar to the second interlayer insulating film, a third interlayer insulating film **172** is formed at a thickness of 0.5 to 1 μm on the light shielding film **171** using an organic resin film. A contact hole that reaches the drain wiring **143** is formed in the third interlayer insulating film **172**, the second interlayer insulating film **145**, and the passivation film **144**, on to which a pixel electrode **173** is then provided. If the pixel electrode **173** is used in transmission type liquid crystal display devices, a transparent conductive film can be used. On the other hand, if it is used in reflection type liquid crystal display devices, a metallic film can be used. Here, since the pixel electrode is used in a transmission type liquid crystal device, an indium tin oxide (ITO) film is formed at a thickness of 100 nm by sputtering. In this way, the storage capacitor **174** connected to the pixel TFT **169** can be formed from the light shielding film **171**, the third interlayer insulating film **172**, and the pixel electrode **173**.

Embodiment 3

A process of forming a crystalline semiconductor film that becomes an active layer of the TFT indicated in embodiments 1 and 2 will be explained in this embodiment with reference to FIGS. 5A–5C. First, gate electrodes **1102** and **1103** are formed at a thickness of 100 to 400 nm on a substrate **1101** (a glass substrate in this embodiment). Each of the gate electrodes is formed of a material containing one or a plurality of elements selected from Al, Ti, Ta, Mo, and W, and is patterned and formed so that the end surface will be taper-like. Although not shown, the gate electrode can also be a laminated structure formed of the above material (s). For instance, it can be a 2-layered structure of tantalum nitride (TaN) and Ta from the substrate side. Further, an oxide can be coated and formed by anodic oxidation and the like on the surface of the gate electrode. A gate insulating film **1104** is formed of a silicon nitride film, a silicon oxide film, or a silicon oxide nitride film at a thickness of 20 to 200 nm, preferably 75 to 125 nm. Then, on the gate insulating film **1104**, a 50 nm thickness of amorphous semiconductor film **1105** (an amorphous silicon film in this embodiment) is formed continuously without being released into the atmosphere.

Thereafter, a water solution containing 10 ppm of catalytic element (nickel in this embodiment) in terms of a weight is coated by a spin coating method to form a catalytic element-contained layer **1106** on the entire surface of the amorphous semiconductor film **1105**. The catalytic elements that are usable in this embodiment include germanium (Ge), iron (Fe), palladium (Pd), tin (Sn), lead (Pb), cobalt (Co), platinum (Pt), copper (Cu), and gold (Au) other than nickel (Ni). According to this embodiment, nickel is added by the spin coating method. Other than the above, means for forming a thin film made of a catalytic element (a nickel film in this embodiment) on the amorphous semiconductor film by a vapor method or sputtering can also be employed. (FIG. 5A)

Before crystallization, heat treatment is performed at 400 to 500° C. for about 1 hour. After eliminating hydrogen from the inside of the film, heat treatment is performed at 500 to 650° C. (preferably at 550 to 570° C.) for 4 to 12 hours (preferably for 4 to 6 hours). In this embodiment, heat treatment is performed at 550° C. for 4 hours and a crystalline semiconductor film **1107** (a crystalline silicon film in this embodiment) is formed. (FIG. 5B)

12

Regarding the active layer **1107** formed in the above manner, by using a catalytic element (here it is nickel) to promote crystallization, a crystalline semiconductor film having excellent crystal qualities can be formed. Moreover, to enhance the crystal qualities, an laser crystallization method can be used together. For instance, an XeF excimer laser light (a wavelength of 308 nm) is used to irradiate the crystalline semiconductor film **1107** fabricated in FIG. 5B with a linear beam at an oscillation frequency of 5 to 50 Hz and at an energy density of 100 to 500 mJ/cm² so as to set the overlap ratio of the linear beam at 80 to 98%. As a result, a crystalline semiconductor film **1108** with further excellent crystal qualities can be formed. (FIG. 5C)

By utilizing the crystalline semiconductor film fabricated in this way on the substrate **1101**, a TFT with good characteristics can be obtained when manufactured by the procedures indicated in embodiments 1 and 2. The characteristics of a TFT can be typically expressed by the electric field effect mobility. Therefore the characteristics of a TFT formed of the crystalline semiconductor film fabricated by the present invention can be obtained in which the electric field effect mobility in the N-channel TFT and the P-channel TFT are 150 to 220 cm²/V·sec and 90 to 120 cm²/V·sec, respectively. Besides, little characteristic deterioration can be observed even if the TFT is operated continuously and excellent characteristics can also be achieved in view of a reliability perspective.

Embodiment 4

In this embodiment, another structure in which a storage capacitor connected to the pixel TFT will be explained with reference to FIGS. 6A to 7B. Here, the processes of forming the storage capacitor shown in FIGS. 6A to 7B are similar with those explained in Embodiment 1. That is, the processes up to the formation of the second interlayer insulating film **145** made of an organic resin film in this embodiment are the same as those in Embodiment 1, and these processes have been described with reference FIGS. 1A to 3. Hence, the explanation in this embodiment will be given focusing on the point of difference with Embodiment 1.

In FIG. 6A, firstly, the second interlayer insulating film **145** is formed by following the process of Embodiment 1, and then a light shielding film **301** is formed of a material containing an element selected from Al, Ta, and Ti. Next, a dielectric film **302** (formed of an oxide from a material which forms the light shielding film) is formed at a thickness of 30 to 150 nm (preferably 50 to 75 nm) on the surface of the light shielding film **301** by anodic oxidation.

When forming the dielectric film **302** by anodic oxidation, first, a tartaric acid ethylene glycol solution of a sufficiently small alkali ion concentration is prepared. This solution is a mixture of 15% of tartaric acid ammonium water solution and ethylene glycol in the proportion of 2:8. Ammonia water is added to this solution and then adjustments are made so that the pH will become 7±0.5. Then, a platinum electrode that becomes a cathode is placed in this solution. The substrate on which the light shielding film **301** is formed is immersed in the solution, and then using the light shielding film **301** as an anode, a direct current is applied thereto at a constant level (several mA to several tens mA). The voltage between the anode and the cathode in the solution is time-varying along with the growth of the oxide, but the voltage is adjusted so that the current may be constant. When the voltage reaches 150 V, the oxidation process is completed without having to maintain the voltage or with the retention time in a range of several seconds to several tens seconds.

In doing this, the dielectric film can be formed without wrapping of the surface where the light shielding film **301** comes in contact with the second interlayer insulating film.

In the present embodiment, a dielectric film is formed only on the surface of the light shielding film, but a vapor phase method such as plasma CVD, thermal CVD, or sputtering can be employed to form the dielectric film. In that case preferably the film thickness is also 30 to 150 nm (preferably 50 to 75 nm). Also, a silicon oxide film, a silicon nitride film, a silicon oxide nitride film, a DLC (diamond like carbon) film, or an organic resin film, or a lamination film combining these can be used as the dielectric film.

A pixel electrode **303** is thereafter formed in the same way as that of embodiment 1. In this way, a storage capacitor **304** can be formed on the region in which the light shielding film **301** overlaps the pixel electrode **303** via the dielectric film **302**.

In the structure of FIG. 6B, after forming the light shielding film **301** and the dielectric film **302** in the same way as that of FIG. 6A, a spacer **305** made of organic resin is formed. A film made of a material selected from polyimide, polyamide, polyimide-amide, acrylic, BCB (benzocyclobutene) can be used as an inorganic resin film. Next, the spacer **305**, the second interlayer insulating film **145**, and the passivation film **143** are etched to form a contact hole, and a pixel electrode **306** is formed of the same material as that of embodiment 1. In this way, a storage capacitor **307** can be formed on the region in which the light shielding film **301** overlaps the pixel electrode **306** via the dielectric film **302**. Providing the spacer **305** can prevent the short circuit that may be generated between the light shielding film **301** and the pixel electrode **306**.

In the structure of FIG. 6C, the light shielding film **301** is formed in the same way as that of FIG. 6A and a spacer **308** made of organic resin is formed so as covering the end portion of the light shielding film **301**. A film made of a material selected from polyimide, polyamide, polyimide-amide, acrylic, BCB (benzocyclobutene) can be used as an inorganic resin film. Next, a dielectric film **309** is formed on the surface of the light shielding film **301** that is exposed by anodic oxidation. No dielectric film is formed in the portion that comes in contact with the spacer **308**. Next, the spacer **308**, the second interlayer insulating film **145**, and the passivation film **143** are etched to form a contact hole, and a pixel electrode **310** is formed of the same material as that of embodiment 1. In this way, a storage capacitor **311** can be formed on the region in which the light shielding film **301** overlaps the pixel electrode **310** via the dielectric film **309**. Providing the spacer **308** can prevent short circuit that may be generated between the light shielding film **301** and the pixel electrode **310**.

In FIG. 7A, the second interlayer insulating film **145** is formed first by following the process in Embodiment 1 and then an insulating film **312** formed of materials such as a silicon oxide film, a silicon nitride film, or a silicon oxide nitride film is formed thereon. A known film formation method is used to form the insulating film **312**, although it is better to use sputtering in particular. Hereinafter, the light shielding film, the dielectric film, and the pixel electrode are formed in the same way as that in FIG. 6A and then a storage capacitor **313** is provided. Providing the insulating film **312** improves adhesion with the underlayer of the light shielding film and the dielectric film can be prevented from wrapping the interface with the underlayer of the light shielding film when the dielectric film is formed by anodic oxidation.

In FIG. 7B, after forming the insulating film and the light shielding film in the same way, the region that is not close

to the light shielding film of the insulating film is removed by etching to form an insulating film **314** so that it overlaps under the light shielding film. Next, a pixel electrode **315** is provided. With this structure, the; adhesion of the light shielding film with the underlayer thereof can be improved and the dielectric film can be prevented from wrapping the interface with the underlayer of the light shielding film can be prevented when the dielectric film is formed by anodic oxidation. Furthermore, the transmission rate of the light through the pixel region in which the light shielding film is formed can be improved.

It is possible to combine the structures shown in FIGS. 7A and 7B with the structures shown in FIGS. 6B and 6C in which a spacer is provided. It is further possible to combine the structures according to the present embodiment shown in FIGS. 6A to 7B with the structures according to embodiment 1 and embodiment 2.

Embodiment 5

In a method of manufacturing a semiconductor device provided with a pixel TFT in a display region shown in Embodiments 1 and 2 and a TFT of a drive circuit formed in the periphery of the display region on the same substrate, a crystalline semiconductor film as an active layer, insulating films such as a gate insulating film, an interlayer insulating film, and an underlying film, and conductive films such as a gate electrode, a source wiring, a drain wiring, and a pixel electrode can all be manufactured by sputtering. The advantage of employing the sputtering method is that when forming a conductive film, the DC (direct current) discharge method can be adopted. Hence, it is applicable for forming a uniform film on a large-area substrate. Further, it is not necessary to use a silane (SiH_4) which needs to be handled with great caution when forming films made of silicon-based materials such as an amorphous silicon film and a silicon nitride film. Thus, safety of operation can be secured. This matter can be utilized as a great merit especially for a production site. Hereinafter, a manufacturing process employing the sputtering method will be explained following the processes of Embodiment 1.

The gate electrodes **102** through **104** and the capacitor wiring **105** in FIG. 1A can be easily formed by the known sputtering method using target materials such as Ta, Ti, W, and Mo. When using compound materials such as W-Mo and Ta-Mo, similarly, it is appropriate to use compounds of target materials. Further, in case of forming TaN and WN, the above can be manufactured by appropriately adding elements such as nitrogen (N_2) and ammonia (NH_3) other than argon (Ar) in a sputtering atmosphere. Also, in addition to argon (Ar), there is a method of controlling the internal stress of a film that is to be manufactured by adding helium (He), krypton (Kr), and xenon (Xe) to the gas for sputtering.

The silicon nitride film **106a** used in the gate insulating film **106** can be formed by using silicon (Si) target and appropriately mixing Ar, N_2 , hydrogen (H_2), and NH_3 , or even by using a target material of silicon nitride, the silicon nitride film can be formed in the same way. Using Si target and appropriately mixing Ar, N_2 , H_2 , and N_2O , the silicon oxide nitride film **106b** can be manufactured by sputtering.

In the same way, Si target is used so that the amorphous silicon film can be manufactured by utilizing Ar and H_2 in sputter gas. Further, if a very small amount of boron (B) is added into the amorphous silicon film, several tens ppm to several thousands ppm of boron (B) can be added into the target in advance or diborane (B_2H_6) can be doped into the sputter gas.

15

A silicon oxide film that is applicable for the channel protection films **119** through **122** can be manufactured by using silicon oxide (or quartz) as the target material and then sputtering Ar or mixed gas of Ar and oxygen (O₂). A silicon nitride film, a silicon oxide film, or a silicon oxide nitride film used for forming the protection insulating film **137**, the interlayer insulating film **138**, the passivation film **144** can be manufactured in the same way as mentioned above.

If Al is used for the source wirings **139** through **141** and the drain wirings **142** and **43**, then about 0.01 to 5 wt % elements such as Ti, Si, scandium (Sc), vanadium (V), or Cu is contained so that hillock can be effectively prevented. Ti, Ta, Al, and the like used for the light shielding film **171** and ITO, ZnO, SnO₂, and the like used for the pixel electrode **146** can all be formed by the known sputtering method.

In this way, other than the second interlayer insulating film **145** and the third interlayer insulating film **172** made of organic resin, any film can be formed by sputtering. Moreover, detailed experiment conditions can be appropriately determined by a user.

Embodiment 6

Another example of the pixel TFT and the TFT of the drive circuit, particularly the P-channel TFT is indicated in this embodiment. First of all, perform the processes of from FIG. 1A to FIG. 2A in the same way as explained in Embodiment 1. The drawing of FIG. 12A corresponds to FIG. 2A. It illustrates a state in which resist masks **1123** through **1125** and impurity regions **1126** through **1130**, doped with an impurity element that gives n-type, are formed.

The forming of the p⁺ region is then carried out as shown in FIG. 12B. A mask **1131** is formed on a channel protection insulating film **1119** so as to be positioned on the inside, and a region in which the N-channel TFT is formed is entirely covered by resist masks **1132** and **1133**. Furthermore, a channel protection film **1119b** having a new shape is formed by performing etching, that is, wet etching is carried out on the channel protection film **1119** using fluorine-based solution so that the end portion of the film **1119** almost coincides with the end portion of the mask **1131**. Thereafter, high concentration impurity regions **1134** through **1136** are formed by ion doping (ion implantation can be used) using diborane (B₂H₆). An impurity element is added into the impurity regions **1134** through **1136** from the surface of the crystalline silicon film.

The range of boron concentration in this region is 1.5×10^{20} to 3×10^{21} cm⁻³, here it is 2×10^{21} cm⁻³. In this specification, the concentration of the impurity element that gives p-type included in the impurity regions **1134** through **1136** formed here is expressed as "p⁺". In this way, by providing the end portion of the high concentration impurity regions in the P-channel TFT that comes in contact with the channel forming region more to the side of the channel forming region than to the end portion of the low concentration impurity regions **1113** and **1114** formed in the previous process, the junction condition in this portion can be made into a good one.

As shown in FIGS. 1B to 2A, the impurity regions **1135** and **1136** are added with phosphorus (P) in the previous process, therefore a region containing a mixture of boron (B) and phosphorus (P) is formed. However, in this process, by adding boron (B) at a concentration of 1.5 to 3 times higher than that of the previous process, p-type conductivity can be secured and no influences are inflicted upon the characteristics of the TFT. In this specification, this region is referred

16

to as impurity region "B". Also, the impurity region **1134** at the side of the channel forming region is a region containing boron (B) only, and this region is referred to as region "A" in this specification.

Respective impurity elements are selectively added into the crystalline silicon film and then etching is carried out on this crystalline silicon film so that it is divided into island-like films. Then a protection insulating film **1137**, which will later become a portion of the first interlayer insulating film, is formed. The protection insulating film **1137** can be formed of a silicon nitride film, a silicon oxide film, a silicon oxide nitride film, or a lamination film of the combination thereof and may be at a thickness of 100 to 400 nm.

Thereafter, the heat treatment process is carried out for the purpose of activating the impurity elements giving either an n-type or p-type that have been added at respective concentrations. When activation is carried out by furnace annealing, heat treatment is performed at 300 to 650° C., preferably 500 to 550° C. in a nitrogenic atmosphere. In this process, heat treatment was performed at 525° C. for 4 hours. When laser annealing is applied, irradiation is conducted by using the excimer laser as a light source, forming the laser light into a linear beam having a width of 100 to 500 μm by an optical system and irradiating the linear beam at the oscillation frequency of from 10 to 100 Hz; the oscillation pulse width of from 20 to 50 nsec (preferably 30 nsec), and the energy density of from 100 to 500 mJ/cm². Another heat treatment is performed at 300 to 450° C. for 1 to 12 hours in an atmosphere containing 3 to 100% of hydrogen to hydrogenate the active layer. This process is to terminate the dangling bonds in the active layer by thermally excited hydrogen. As other hydrogenation means, plasma hydrogenation (using hydrogen excited by plasma) can be performed.

After completing the activation process, an interlayer insulating film **1138** is formed at a thickness of 500 to 1500 nm on the protection insulating film **1137**. A lamination film formed of the above insulating film **1137** and the interlayer insulating film **1138** functions as a first interlayer insulating film. A contact hole that reaches the source region or drain region of the respective TFTs is next formed, and then source wirings **1139** through **1141** and drain wirings **1142** and **1143** are formed. Though not shown, this electrode according to the present embodiment is a laminated film of a three-layered structure consisting of a 100 nm Ti film, a 300 nm aluminum film containing Ti, and a 150 nm Ti film which are formed by sputtering in successions.

The protection insulating film **1137** and the interlayer insulating film **1138** can be formed of a silicon nitride film, a silicon oxide film or a silicon oxide nitride film, or the like. In any case, it is better that the internal stress of the film be made into the compression stress.

Next, using a silicon nitride film, a silicon oxide film, or a silicon oxide nitride film, passivation film **1144** is formed at a thickness of 50 to 500 nm (typically 100 to 300 nm). If hydrogenation process is carried out in this state, desirable effects can be achieved with respect to improving the characteristics of TFTs. For instance, it is better if heat treatment is performed at 300 to 450° C. in an atmosphere containing 3 to 100% of hydrogen for 1 to 12 hours or by employing a plasma hydrogenation method in which similar effects can be obtained. Moreover, an opening may be formed in the passivation film **1144** at a position where a contact hole for connecting a pixel electrode to the drain wiring is to be formed.

Thereafter, a second interlayer insulating film **1145** formed of organic resin is formed at about 1 μm of thickness

in the same way as that of Embodiment 1. Then, a contact hole that reaches the drain wiring **1143** is formed in the second interlayer insulating film **1145** and the passivation film **1144**, thus, a pixel electrode **1146** is provided. If a transmission type liquid crystal display device is to be manufactured, a transparent insulating film is used to form the pixel electrode **1146**. On the other hand, if it is a reflector type liquid crystal display device that is to be manufactured, a metallic film is used. Aimed here is a transmission type liquid crystal device, and therefore an indium tin oxide (ITO) film is formed at a thickness of 100 nm by sputtering. A pixel electrode **1190** is the electrode of a neighboring pixel.

From the above processes, the pixel TFT of a display portion and the TFT of the drive circuit in the periphery of the display portion are formed on the same substrate. In the drive circuit, an N-channel TFT **1168** and a P-channel TFT **1167** are formed, and a logic circuit structured with a CMOS circuit as the basic circuit can be formed. A pixel TFT **1169** is an N-channel TFT, and furthermore, a storage capacitor is formed from the capacitor wiring **105**, a semiconductor layer **1166**, and an insulating film formed therebetween, and is connected to this pixel TFT **1169** (FIG. 3).

A P-channel TFT **1167** of the drive circuit has a channel forming region **1147**, source regions **1148** and **1150** and drain regions **1149** and **1151**, which are formed in high concentration impurity regions. The source region **1150** and the drain region **1151** are formed in the impurity region "B". The concentration of boron (B) in the regions is adjusted to have a concentration 1.5 to 3 times higher than the concentration of phosphorous (P). On the inside of the impurity region "B", that is, the source region **1148** and the drain region **1149** formed on the side of the channel forming region **1147** is the impurity region "A". This impurity region "A" is a region containing only boron in the same concentration as that of the impurity region "B". The structure here is that the entire region "A" overlaps the gate electrode **1102** while on the other hand a portion of the region "B" overlaps the gate electrode **1102**. In this way, by forming the high concentration impurity region in the P-channel TFT from the region "A" and the region "B" from and by forming the region "B" far away from the channel forming region, the junction of the channel forming region and the high concentration impurity region can be a good one.

An N-channel TFT **1168** of the drive circuit has a channel forming region **1152**, a source region **1155** and a drain region **1156**, and LDD regions **1153** and **1154**. The pixel TFT **1169** has channel forming regions **1157** and **1158**, source regions or drain regions **1163** through **1165**, and LDD regions **1159** through **1162**. The LDD regions in the N-channel TFT of the drive circuit are provided with the principal purpose of preventing the deterioration of the on-current value due to hot carrier implantation by relaxing high electric field in the vicinity of the drain. Thus, it is appropriate to make the concentration of a suitable impurity element that gives n-type at 5×10^{17} to $5 \times 10^{18} \text{ cm}^{-3}$. On the other hand, the principal purpose of providing the LDD regions in the pixel TFT is to decrease the off-current value. The concentration of an impurity element in these regions may be the same as those in the LDD regions in the N-channel TFT in the drive circuit, or may be $\frac{1}{2}$ to $\frac{1}{10}$ of that concentration. In FIG. 13, although the pixel TFT **1169** is completed as a double-gate structure, it can also be a single-gate structure, or a multi-gate structure provided with a plurality of gate electrodes without causing any problem.

In a TFT manufactured by the above process, the channel protection insulating film **1119b** and channel protection insulating films **1120** through **1122** can be formed without receiving any damages from ion doping or the like.

Therefore, the characteristics of the TFT are stable. For instance, when a voltage of -1.7 MV is applied to the gate electrode and then leaving it for an hour at 150° C. as a bias thermal stress (BTS) test, hardly any fluctuations can be observed in the threshold voltage, the field effect mobility, the sub-threshold constant, the on-current value, etc. Furthermore, according to the present invention, the operation performance and the reliability of a semiconductor device can be improved by optimizing the structures of the TFTs that compose the pixel TFT circuit and the driver circuit in accordance with the specifications of the respective circuits demand.

Also, regarding the structure of the storage capacitor shown in FIG. 13, it can be formed from the light shielding film, the dielectric film formed on the surface of the light shielding film by anodic oxidation, and the pixel electrode according to embodiment 4 explained with reference to FIGS. 6A to 7B.

Embodiment 7

In this embodiment, processes of manufacturing an active matrix liquid crystal display device from a substrate in which a pixel TFT and a drive circuit are formed are described hereon. As shown in FIG. 8, an orientation film **601** is formed on a substrate in the state shown in FIG. 3 manufactured according to embodiment 1. Normally, polyimide resin is often used as an orientation film in a liquid crystal display device. A light shielding film **603**, a transparent conductive film **604**, and an orientation film **605** are formed on an opposite substrate **602**. After forming the orientation film, a rubbing operation is performed so that the crystal molecules are orientated at a fixed pre-tilt angle. Then using a well-known cell assembling process, the opposite substrate and the other substrate on which the pixel TFT and the drive circuit are formed are stuck together with sealing materials or a spacer (both not shown). Then after injecting a liquid crystal material **606** between the two substrates, the liquid crystal material is completely sealed by a sealing agent (not shown). It is appropriate to use well-known liquid crystal material as the liquid crystal material. The active matrix liquid crystal display device shown in FIG. 8 is completed in this way.

Next, a structure of the active matrix liquid crystal display device will be described with reference to the perspective view of FIG. 9 and to the top view of FIG. 10. It should be noted that the same reference numerals as that of FIGS. 1A to 3 and FIG. 8 are used in FIGS. 9 and 10 in order to correlate the latter with the sectional structural views of the former. Further, the sectional structure along the line A-A' indicated in FIG. 10 corresponds to the cross-sectional view of the pixel TFT **169** and the storage capacitor **170** shown in FIG. 3.

In the perspective view shown in FIG. 9, the structure of the active matrix liquid crystal display comprises a display region **701**, a scanning (gate) line drive circuit **702**, and a signal (source) line drive circuit **703**, which are formed on the glass substrate **101**. The pixel TFT **169** is formed in the display region and the drive circuit formed in the periphery of the display region is structured with a CMOS circuit as the basic circuit. The scanning (gate) line drive circuit **702** and the signal (source) line drive circuit **703** are connected to the pixel TFT in the display region **701** by the gate wiring **104** (denoted by the same reference numeral as the gate electrode, for the wiring **104** is formed by extending the gate electrode and is connected thereto) and the source wiring **141**, respectively. An FPC731 is connected to an external input/output terminal **734**.

FIG. 10 is a top view of almost an entire pixel of the display region **701**. The gate wiring **104** intersects with an

active layer under a not shown gate insulating film via this gate insulating film. And also not shown, the active layer is formed of a source region, a drain region, and an LDD region formed of the n^- region. Further, reference numeral **180** denotes a contact portion of the source wiring **141** and the source region **163**, **181** denotes a contact portion of the drain wiring **143** and the drain region **165**, and **182**, a contact portion of the drain wiring **143** and the pixel electrode **146**. The storage capacitor **170** is formed of a semiconductor layer **166** that comes in contact with the drain region **165** of the pixel TFT **169**, the capacitor wiring **105**, and a region which is formed therebetween and overlaps with the insulating film.

The active matrix liquid crystal display device is explained applying the structure in Embodiment 1, it is also possible to fabricate an active matrix liquid crystal display device freely combined with any of Embodiments 1 to 6.

Embodiment 8

The substrate manufactured by carrying out the present invention and having a pixel TFT and a drive circuit which are formed on the same substrate may be used in various electro-optical display devices (active matrix liquid crystal display devices, active matrix EL display devices, and active matrix EC display devices). In other words, the present invention may be embodied in all kinds of electronic equipment having as display medium those electro-optical display devices incorporated therein.

As such electronic equipment, there are enumerated: video cameras; digital cameras; projectors (rear projectors or front projectors); head mount displays (goggle type displays); navigation systems for vehicles; personal computers; portable telephones; and electronic books. Specific examples thereof are shown in FIG. 11.

FIG. 11A shows a portable telephone that is composed of a main body **9001**, a sound output section **9002**, a sound input section **9003**, a display device **9004**, operation switches **9005**, and an antenna **9006**. The present invention can be applied to the sound output section **9002**, the sound input section **9003**, and the active matrix display device **9004** provided with a display region and a drive circuit that is formed in the periphery thereof.

FIG. 11B shows a video camera that is composed of a main body **9101**, a display device **9102**, a sound input section **9103**, operation switches **9104**, a battery **9105**, and an image receiving section **9106**. The present invention can be applied to the sound input section **9103**, to the active matrix display device **9102** provided with a display region and a drive circuit that is formed in the periphery thereof, and to the image receiving section **9106**.

FIG. 11C shows a mobile computer that is composed of a main body **9201**, a camera section **9202**, an image receiving section **9203**, operation switches **9204**, and a display device **9205**. The present invention can be applied to the image receiving section **9203**, and to the active matrix display device **9205** provided with a display region and a drive circuit that is formed in the periphery thereof.

FIG. 11D shows a goggle type display that is composed of a main body **9301**, display devices **9302**, and arm sections **9303**. The present invention can be applied to the active matrix display device **9302** provided with a display region and a drive circuit that is formed in the periphery thereof. Though not shown, the invention is also applicable to other signal controlling circuit.

FIG. 11E shows a rear type projector that is composed of a main body **9401**, a light source **9402**, a display device **9403**, polarizing beam splitter **9404**, reflectors **9405** and **9406**, and a screen **9407**. The present invention can be applied to the active matrix display device **9403** provided

with a display region and a drive circuit that is formed in the periphery thereof.

FIG. 11F shows a portable electronic book that is composed of a main body **9501**, display devices **9502**, **9503**, a memory medium **9504**, an operation switch **9505** and an antenna **9506**. The book is used to display data stored in a mini-disk (MD) or a DVD, or a data received with the antenna. The display devices **9502**, **9503** are direct-vision type active matrix display devices provided with a display region and a drive circuit that is formed in the periphery thereof, to which the present invention may be applied.

Other than those, though not shown, the present invention may also be applied to display sections of navigation systems for vehicles, image sensors and personal computers. The present invention thus has so wide application range that it is applicable to electronic equipment in any field. Further, the electronic equipment of this embodiment can be realized using a structure formed by combining Embodiments 1 to 7. No limitation is put on how to combine these embodiments.

By implementing the present invention, it is possible to arrange TFTs with appropriate performances that meet the specifications demanded by the functional circuits in the semiconductor device (specifically the electro-optical device in the present invention) formed of a multiple of functional circuits on the same substrate; and a substantial improvement can be made in the operation characteristics and reliability.

More particularly, a bottom-gate TFT or an inverted stagger TFT provided with the LDD regions, by forming as the LDD regions of the pixel TFT, Loff and Lov regions with n^- concentration, the off-current value can be substantially decreased and contributions can be made to the low power consumption of the pixel TFT. Also, by forming, as the LDD regions in the N-channel TFT in the drive circuit, Loff and Lov regions with n^- concentration, the electric current drive performance can be enhanced as well as preventing deterioration caused by hot carrier, and the deterioration of the on-current value can be decreased.

Furthermore, the P-channel TFT of the drive circuit has the impurity region "B" containing both an impurity element that gives p-type and an impurity element that gives n-type therein and has an impurity region "A" containing an impurity element that gives p-type therein. The impurity region "A" is formed between the impurity region "B" and the LDD region in the P-channel TFT in the drive circuit, securing the junction between the channel forming region and the LDD region that comes in contact with the channel forming region, and between the LDD region and either the source region or the drain region become. Therefore, the characteristics of the P-channel TFT can be well retained.

Moreover, the operation performance and reliability of a semiconductor device (specifically an electronic equipment in the present invention) having this type of electro-optical device as a display medium can be improved.

What is claimed is:

1. A semiconductor device comprising:

at least a pixel TFT being formed in a display region over a substrate; and

at least an n-channel TFT and at least a p-channel TFT in a drive circuit each being formed in a periphery of the display region over the substrate;

each of said pixel TFT, and said n-channel and p-channel TFTs in the drive circuit includes:

an active layer,

at least an LDD region being formed in the active layer, a gate insulating film being provided between the active layer and the substrate, and

a gate electrode being provided between the gate insulating film and the substrate,
wherein at least a portion of the LDD region of the pixel TFT is formed so as to overlap with the gate electrode of the pixel TFT,
wherein at least a portion of the LDD region of the n-channel TFT in the drive circuit is formed so as to overlap with the gate electrode of the n-channel TFT in the drive circuit, and
wherein all of the LDD region of the p-channel TFT of the drive circuit is formed so as to overlap with a gate electrode in the p-channel TFT in the drive circuit.

2. A semiconductor device comprising:
at least a pixel TFT being formed in a display region over a substrate;
at least an n-channel TFT and at least a p-channel TFT in a drive circuit each being formed in a periphery of the display region over the substrate,
each of said pixel TFT, and said n-channel and p-channel TFTs in drive circuit includes:
an active layer,
at least an LDD region being formed in the active layer,
a gate insulating film being provided between the active layer and the substrate, and
a gate electrode being provided between the gate insulating film and the substrate,
wherein the LDD region of the pixel TFT is formed so as not to overlap with a channel protection insulating film of the pixel TFT,
wherein a portion of the LDD region of the pixel TFT is formed so as to overlap with the gate electrode of the pixel TFT,
wherein the LDD region of the n-channel TFT in the drive circuit is formed so as not to overlap with a channel protection insulating film of the n-channel TFT in the drive circuit,
wherein a portion of the LDD region of the n-channel TFT in the drive circuit is formed so as to overlap with the gate electrode of the n-channel TFT in the drive circuit,
wherein the LDD region of the p-channel TFT in the drive circuit is formed so as to overlap with a channel protection insulating film of the p-channel TFT in the drive circuit, and
wherein all of the LDD region of the p-channel TFT in the drive circuit is formed so as to overlap with the gate electrode of the p-channel TFT in the drive circuit.

3. A device according to claim 1,
wherein the p-channel TFT in the drive circuit includes:
a first impurity region including both a p-type impurity and an n-type impurity and,
a second impurity region including the p-type impurity, and
wherein the second impurity region is formed between the first impurity region and the LDD region of the p-channel TFT in the drive circuit.

4. A device according to claim 1, further comprising a storage capacitor being connected to the pixel TFT,
said storage capacitor including:
a capacitor wiring formed over the substrate;
an insulating film formed on the capacitor wiring; and
a semiconductor layer being formed on the insulating film.

5. A device according to claim 1, further comprising:
at least an organic resin film being formed over the pixel TFT,

a light shielding film being formed on the organic resin film;
a dielectric film being formed closely to the light shielding film; and
a pixel electrode connected to the pixel TFT, a portion of said pixel electrode being overlapped with the light shielding film
wherein a storage capacitor is formed with the light shielding film, the dielectric film and the portion of the pixel electrode.

6. A device according to claim 5,
wherein the light shielding film comprises at least a material selected from the group consisting of aluminum, tantalum and titanium, and
wherein the dielectric film comprises an oxide of the material.

7. A device according to claim 1,
wherein the semiconductor device is one selected from the group consisting of a cellular phone, a video camera, a mobile computer, a goggle-type display, a projector, a mobile book, a digital camera, a car navigation device, and a personal computer.

8. A device according to claim 2,
wherein the p-channel TFT in the drive circuit includes:
a first impurity region including both a p-type impurity and an n-type impurity and,
a second impurity region including the p-type impurity, and
wherein the second impurity region is formed between the first impurity region and the LDD region of the p-channel TFT in the drive circuit.

9. A device according to claim 2, further comprising a storage capacitor being connected to the pixel TFT,
said storage capacitor including:
a capacitor wiring formed over the substrate;
an insulating film formed on the capacitor wiring; and
a semiconductor layer being formed on the insulating film.

10. A device according to claim 2, further comprising:
at least an organic resin film being formed over the pixel TFT,
a light shielding film being formed on the organic resin film;
a dielectric film being formed closely to the light shielding film; and
a pixel electrode connected to the pixel TFT, a portion of said pixel electrode being overlapped with the light shielding film
wherein a storage capacitor is formed with the light shielding film, the dielectric film and the portion of the pixel electrode.

11. A device according to claim 10,
wherein the light shielding film comprises at least a material selected from the group consisting of aluminum, tantalum and titanium, and
wherein the dielectric film comprises an oxide of the material.

12. A device according to claim 2,
wherein the semiconductor device is one selected from the group consisting of a cellular phone, a video camera, a mobile computer, a goggle-type display, a projector, a mobile book, a digital camera, a car navigation device, and a personal computer.