



US006451077B1

(12) **United States Patent**
Rosenflanz

(10) **Patent No.:** **US 6,451,077 B1**
(45) **Date of Patent:** ***Sep. 17, 2002**

(54) **FUSED ABRASIVE PARTICLES, ABRASIVE ARTICLES, AND METHODS OF MAKING AND USING THE SAME**

(75) Inventor: **Anatoly Z. Rosenflanz**, Maplewood, MN (US)

(73) Assignee: **3M Innovative Properties Company**, St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **09/619,563**

(22) Filed: **Jul. 19, 2000**

Related U.S. Application Data

(63) Continuation-in-part of application No. 09/495,978, filed on Feb. 2, 2000, now abandoned.

(51) **Int. Cl.**⁷ **C09K 3/14**; C04B 35/107; C04B 35/117; C04B 35/111

(52) **U.S. Cl.** **51/309**; 51/307; 51/295; 451/28; 501/126; 501/127; 501/153; 501/87; 501/96.1

(58) **Field of Search** 51/307, 309, 295; 501/126, 127, 153, 154, 105, 87, 96.1; 264/332; 451/28

(56) **References Cited**

U.S. PATENT DOCUMENTS

659,926 A	10/1900	Jacobs
906,339 A	12/1908	Tone
960,712 A	6/1910	Saunders
1,037,999 A	9/1912	Saunders
1,107,011 A	8/1914	Allen
1,149,064 A	8/1915	Kalmus
1,161,620 A	11/1915	Coulter
1,192,709 A	7/1916	Tone
1,240,490 A	9/1917	Saunders et al.
1,247,337 A	11/1917	Saunders et al.
1,257,356 A	2/1918	Hutchins
1,263,708 A	4/1918	Saunders et al.
1,263,709 A	4/1918	Saunders et al.
1,263,710 A	4/1918	Saunders et al.
1,268,532 A	6/1918	Allen
1,268,533 A	6/1918	Allen
1,314,061 A	8/1919	Harrison
1,339,344 A	5/1920	Hutchins
1,402,714 A	1/1922	Brockbank
1,448,586 A	3/1923	Allen
1,910,444 A	5/1933	Nicholson
2,000,857 A	5/1935	Masin
2,424,645 A	7/1947	Baumann, Jr. et al.
2,618,567 A	11/1952	Comstock, 3rd
2,958,593 A	11/1960	Hoover et al.
2,961,296 A	11/1960	Fenerty
3,041,156 A	6/1962	Rowse et al.
3,141,747 A	7/1964	Marshall
3,181,939 A	5/1965	Marshall et al.

3,216,794 A	11/1965	Roschuk
3,377,660 A	4/1968	Marshall et al.
3,498,769 A	3/1970	Coes, Jr.
3,646,713 A	3/1972	Marshall et al.
3,726,621 A	4/1973	Cichy
3,781,172 A	12/1973	Pett et al.
3,792,553 A	2/1974	Schleifer et al.
3,881,282 A	5/1975	Watson
3,891,408 A	6/1975	Rowse et al.
3,893,826 A	7/1975	Quinan et al.
3,916,584 A	11/1975	Howard et al.
3,973,977 A	8/1976	Wilson
3,996,702 A	12/1976	Leahy
4,035,162 A	7/1977	Brothers et al.
4,049,397 A	9/1977	Bockstiegel et al.
4,070,796 A	1/1978	Scott
4,073,096 A	2/1978	Ueltz et al.
4,111,668 A	9/1978	Walker et al.
4,126,429 A	11/1978	Watson
4,140,494 A	2/1979	Coes, Jr.
4,157,898 A	6/1979	Walker et al.
4,194,887 A	3/1980	Ueltz et al.
4,311,489 A	1/1982	Kressner
4,314,827 A	2/1982	Leitheiser et al.
4,341,533 A	7/1982	Daire et al.
RE31,128 E	1/1983	Walker et al.
4,415,510 A	11/1983	Richmond
4,439,845 A	3/1984	Geohegan, Jr. et al.
4,457,767 A	7/1984	Poon et al.
RE31,725 E	11/1984	Walker et al.

(List continued on next page.)

FOREIGN PATENT DOCUMENTS

DE	134 638 A	3/1979
EP	0 480 678 A	4/1992
EP	0 579 281 A1	1/1994
EP	0 647 601 A1	4/1995
EP	0 722 919 A1	7/1996
JP	59 22 7726 A	12/1984
JP	06 040765 A	2/1994
JP	10-208229	2/2000
JP	10-208244	2/2000
WO	WO 00/34201	6/2000

OTHER PUBLICATIONS

“Preliminary data on subsolidus phase equilibria in the La₂O₃-Al₂O₃-Mn₂O₃ and La₂O₃-Al₂O₃-Fe₂O₃ systems”, Hrovat et al., *Journal of Materials Science Letters*, vol. 14, 1995, pp. 265-267 no month.

(List continued on next page.)

Primary Examiner—Michael Marcheschi
(74) *Attorney, Agent, or Firm*—Gregory D. Allen

(57) **ABSTRACT**

Fused abrasive particles comprising at least one eutectic. The fused abrasive particles can be incorporated into abrasive products such as coated abrasives, bonded abrasives, non-woven abrasives, and abrasive brushes.

26 Claims, 27 Drawing Sheets

U.S. PATENT DOCUMENTS

4,518,397 A	5/1985	Leitheiser et al.	5,876,470 A	3/1999	Abrahamson
4,543,107 A	9/1985	Rue	5,902,763 A	5/1999	Waku et al.
4,588,419 A	5/1986	Caul et al.	5,903,951 A	5/1999	Ionta et al.
4,595,663 A *	6/1986	Krohn et al. 501/103	5,954,844 A	9/1999	Law et al.
4,623,364 A	11/1986	Cottringer et al.	5,961,674 A	10/1999	Gagliardi et al.
4,652,275 A	3/1987	Bloecher et al.	5,975,988 A	11/1999	Christianson
4,734,104 A	3/1988	Broberg	5,981,415 A *	11/1999	Waku et al. 501/152
4,737,163 A	4/1988	Larkey			
4,741,743 A	5/1988	Narayanan et al.			
4,744,802 A	5/1988	Schwabel			
4,751,137 A	6/1988	Halg et al.			
4,752,459 A	6/1988	Pepper			
4,770,671 A	9/1988	Monroe et al.			
4,780,268 A	10/1988	Papsi et al.			
4,799,939 A	1/1989	Bloecher et al.			
4,800,685 A	1/1989	Haynes, Jr.			
4,881,951 A	11/1989	Wood et al.			
4,898,587 A	2/1990	Mera			
4,898,597 A	2/1990	Hay et al.			
4,960,441 A	10/1990	Pellow et al.			
4,997,461 A	3/1991	Markhof-Matheny et al.			
5,009,675 A	4/1991	Kunz et al.			
5,011,508 A	4/1991	Wald et al.			
5,013,696 A	5/1991	Greskovich et al.			
5,023,212 A	6/1991	Dubots et al.			
5,038,453 A	8/1991	Kurita et al.			
5,042,991 A	8/1991	Kunz et al.			
5,085,671 A	2/1992	Martin et al.			
5,090,968 A	2/1992	Pellow			
5,094,672 A	3/1992	Giles, Jr. et al.			
5,110,332 A	5/1992	Isaksson			
5,118,326 A	6/1992	Lee et al.			
5,131,926 A	7/1992	Rostoker et al.			
5,139,978 A	8/1992	Wood			
5,143,522 A	9/1992	Gibson et al.			
5,152,917 A	10/1992	Pieper et al.			
5,201,916 A	4/1993	Berg et al.			
5,203,884 A	4/1993	Buchanan et al.			
5,203,886 A	4/1993	Sheldon et al.			
5,227,104 A	7/1993	Bauer			
5,259,147 A	11/1993	Falz et al.			
5,282,875 A	2/1994	Wood et al.			
5,312,789 A	5/1994	Wood			
5,336,280 A	8/1994	Dubots et al.			
5,352,254 A	10/1994	Celikkaya			
5,366,523 A	11/1994	Rowenhorst et al.			
5,372,620 A	12/1994	Rowse et al.			
5,376,470 A	12/1994	Sprouse			
5,378,251 A	1/1995	Culler et al.			
5,417,726 A	5/1995	Stout et al.			
5,427,595 A	6/1995	Pihl et al.			
5,429,647 A	7/1995	Larmie			
5,431,704 A	7/1995	Tamamaki et al.			
5,436,063 A	7/1995	Follett et al.			
5,443,906 A	8/1995	Pihl et al.			
5,496,386 A	3/1996	Broberg et al.			
5,498,269 A	3/1996	Larmie			
5,520,711 A	5/1996	Helmin			
5,547,479 A	8/1996	Conwell et al.			
5,549,962 A	8/1996	Holmes et al.			
5,551,963 A	9/1996	Larmie			
5,593,467 A	1/1997	Monroe			
5,609,706 A	3/1997	Benedict et al.			
5,651,925 A	7/1997	Ashley et al.			
5,665,127 A	9/1997	Moltgen et al.			
5,679,067 A	10/1997	Johnson et al.			
5,725,162 A	3/1998	Garg et al.			
5,738,696 A	4/1998	Wu			
5,782,940 A	7/1998	Jayan et al.			
5,863,308 A	1/1999	Qi et al.			

OTHER PUBLICATIONS

“A New Ceramic Eutectic Composite with High Strength at 1873 K”, Yoshiharu Waku, *Advanced Materials*, vol. 10, No. 8, 1998, pp. 615–617 no month.

“Synthesis of Y–Al Garnet”, Krokhin et al., *Glass and Ceramics*, vol. 55, Nos. 5–6, 1998, pp. 151–152 no month.

“High–temperature strength and thermal stability of a uni-directionally solidified Al₂O₃YAG eutectic composite”, Waku et al. No Date.

“Sapphire matrix composites reinforced with single crystal VAG phases”, Waku et al., *Journal of Materials Science*, vol. 31, 1996, pp. 4663–4670 no month.

“Thermon–Mechanical Stability Of Directionally Solidified Al₂O₃–ZrO₂(Y₂O₃) Eutectic Fibers”, Yang and Zhu, *Scripta Materialia*, vol. 36, No. 8, 1997, pp. 961–966 no month.

“A ductile ceramic eutectic composite with high strength at 1,873 K”, Waku et al., *Nature*, vol. 389, Sep. 1997, pp. 49–52.

“The Liquidus Surface In the Al₂O₃–ZrO₂–Y₂O₃ Phase Diagram”, Lakiza et al., *Powder Metallurgy and Metal Ceramics*, vol. 33, No. 11–12, 1994, pp. 595–597 no month.

“Powder–Material Research Methods And Properties Poly-thermal Sections Of The Al₂O₃–ZrO₂–Y₂O₃ Phase Diagram”, Lakiza et al., *Powder Metallurgy and Metal Ceramics*, vol. 34, No. 11–12, 1995, pp. 655–659 no month.

“Metastable Phase Relationships In The System Al₂O₃–ZrO₂–Y₂O₃”, Lakiz and Lopato, *Powder Metallurgy and Metal Ceramics*, vol. 35, Nos. 11–12, 1996, pp. 621–626 no month.

“Solidus Surface And Phase Equilibria During The Solidification Of Alloys In the Al₂O₃–ZrO₂–Y₂O₃ System”, Lakiza et al., *Powder Metallurgy and Metal Ceramics*, vol. 34, Nos. 1–2, 1995, pp. 64–67 no month.

“Methods Of Investigation Of Properties Of Powder Materials, Interactions In the Al₂O₃–ZrO₂–Y₂O₃ System”, Lakiza et al., *Powder Metallurgy and Metal Ceramics*, vol. 33, Nos. 9–10, 1994, pp. 486–490. no month.

Figs. 311, 346, 350, 354–56, 373, and 716, *Phase Diagrams For Ceramists*, The American Ceramic Society, 1964, pp. 122, 136, 138, 140, 144, 248.

Figs. 2340–44, 2363, 2370, 2374–75, 2382–83, 2385, 2387, 2390, and 2392, *Phase Diagrams For Ceramists, 1969 Supplement*, The American Ceramic Society, 1969, pp. 95–96, 100, 102–103, 105–108 no month.

Figs. 4366–71, 4377–78, 4404–05, 4417, 4426, 4430, 4433, 4437, 4440, 4444, 4457, 4572, and 4602, *Phase Diagrams For Ceramists, 1975 Supplement*, The American Ceramic Society, 1975, pp. 130–132, 135–36, 147, 152, 157, 159–160, 163–164, 172–173, 238, 257 no month.

Figs. 5042, 5211, 5217, 5224, 5228, 5232, 5237, 5239, 5241, 5245, 5251, 5257, 5418, and 5437, *Phase Digrams For Ceramists, vol. IV*, The American Ceramic Society, 1981, pp. 29, 125, 127, 129–131, 133, 135–137, 139, 141, 143, 220, 228 no month.

Fig. 6464, *Phase Diagrams For Ceramists, vol. VI*, The American Ceramic Society, 1981, p. 162 no month.

- Figs. 9262, and 9264, *Phase Diagrams For Ceramists*, vol. IX, *Oxides*, The American Ceramic Society, 1995, pp. 105–106 no month.
- “Phase Equilibria in the Yttrium Oxide–Alumina System”, Toropov et al., *Bulletin of the Academy of Sciences, USSR*, Division of Chemical Science, No. 7, Jul., 1964, pp. 1076–1081, A translation of *Seriya Khimicheskaya*.
- U.S. Patent Application entitled “Fused Al_2O_3 – MgO –Rare Earth Oxide Eutectic Abrasive Particles, Abrasive Articles, And Methods Of Making And Using The Same”, filed Jan. 30, 2001, Rosenflanz having Attorney Docket No. 55353USA8C.005.
- Abstract for “Kinetics of Nonisothermal Sintering of Some Eutectic Oxide Compositions,” I. Yu Volkova et al., 1986 (abstract from Database Chemabs Online! Chemical Abstracts Service, Columbus, Ohio, US). no month.
- “Eutectic Precipitation of the Spinel Solid Solution–Yttrium Aluminum Garnet (YAG) System,” Shuqiang Wang et al., *Journal of the American Ceramic Society*, 1998, vol. 81, No. 1, pp. 263–265 no month.
- “Microstructures of laser-treated Al_2O_3 – ZrO_2 – CeO_2 composites,” Zan–Hwey Chen et al., *Materials Science & Engineering A (Structural Materials: Properties, Microstructure and Processing)*, 1995, vol. A196, No. 1–2, pp. 253–260 no month.
- “Advances in the Grinding Efficiency of Sintered Alumina Abrasives,” Andreas Krell et al., *Journal of the American Ceramic Society*, 1996, vol. 79, No. 3, pp. 763–769 no month.
- “Interface modification for increased fracture toughness in reaction–formed yttrium aluminum garnet/alumina eutectic composites,” Luke N. Brewer et al., 1999, vol. 14, No. 10, pp. 3907–3912 no month.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “China’s Rare Earth Industry In the Doldrums”, Asia Pulse, Jan. 28, 1999, 2 pages.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “China’s Rare Earth Export Quota Set at 45,000 Tons”, Asia Pulse, Jan. 9, 2001, 1 page.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “Elements: China to Impose Quotas on Rare Earth Exports”, Chemical Business NewsBase, Feb. 4, 1999, 1 page.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “Rare Earth Prices and Market Outlook”, Chemical Business NewsBase, May 27, 1999, 2 pages.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “In Asia”, Engineering & Mining Journal, Feb. 28, 2000, 4 pages.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “Rare Earths: An Industry Review and Market Outlook—Part 1”, Chemical Business NewsBase, Dec. 8, 2000, 2 pages.
- Dow Jones Interactive Internet Printout on Jun. 20, 2001 for web address “<http://ptg.djnr.com/ccroot/asp/publib/story.asp>”; “Traders’ View on Chemical Business (Part 2): Rare Earth: Market Confusion Inevitable Due to China’s Unstable Supply”, Chemical Business NewsBase, Aug. 10, 2000, 2 pages.
- “China: Oversupply Puts Rare Earths Projects On Hold”, Industrial Minerals, Aug., 1997, 1 page.
- “Increase in Value of Rare Earth Products Boosts Yixing Xinwei”, W. Yau, South China Morning Post, Apr. 12, 2000, 2 pages.
- “Rare Earth—Market Confusion Inevitable Due to China’s Unstable Supply”, Japan Chemical Week, vol. 41, No. 2080, Jul. 6, 2000, pp. 6–7.
- “Rare Earths Prices Recover Despite China’s Overcapacity”, Louise Rodriguez, America Metal Market, vol. 109, No. 14, Jan. 22, 2001, p. 13.
- “Prices: Minerals”, Asian Ceramics & Glass Jan. 2001, 2 pages.
- “China Rare Earth Information”, China Rare Earth Information Center, vol. 6, No. 4, Aug. 2000, 3 pages.
- “Microstructure and Thermal Stability of $\text{Al}_2\text{O}_3/\text{Y}_3\text{Al}_5\text{O}_{12}$ (YAG) Eutectic Composite Prepared by an Arc Discharge Method”, T. Isobe et al., *J. Ceram. Soc. Jap.*, 109 [1], 2001, pp. 66–70, Abstract in English no month.
- “Divorced Eutectic and Interface Characteristics in a Solidified YAG–Spinel Composite With Spinel–Rich Composition”, S. Wang et al., *J. Mat. Sci.*, 35, 2000, pp. 2757–2761 no month.
- “Processing Microstructure, and Strength of Alumina–YAG Eutectic Polycrystals”, Tai–I1 Mah et al., *J. Am. Ceram. Soc.*, 83, [8], 2000, pp. 2088–2090 no month.
- “Phase Identification of $\text{Al}_2\text{O}_3/\text{RE}_3\text{Al}_5\text{O}_{12}$ and $\text{Al}_2\text{O}_3/\text{RE}_{10}_3$ (RE=Sm–Lu, Y) Eutectics”, *J. Crystal Growth*, 218, 2000, pp. 67–73 no month.
- “Crystallization and Thermal Properties of Al_2O_3 – Y_2O_3 Melts”, S. V. Stankus et al., *J. Crystal Growth*, 167, 1996, pp. 165–170 no month.
- Dialog (R) file 319: Chem Bus NewsBase (c) 2001 Royal Soc Chemistry. Abstract for “China: Oversupply Puts Rare Earths Projects On Hold”, Industrial Minerals n 359, p. 10 no month.
- “Rare–Earth Metals”, J. Hedrick, pp. 61.1–61.6, 1997 no month.
- “Rare–Earth Metal Prices in the USA ca. 1960 to 1994”, J. Hedrick, *J. Alloys and Compounds*, 1997, pp. 471–481 no month.

* cited by examiner




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20




Fig. 21




Fig. 22




Fig. 23




Fig. 24




Fig. 25




Fig. 26




Fig. 27




Fig. 28




Fig. 29




Fig. 30




Fig. 31




Fig. 32




Fig. 33




Fig. 34




Fig. 35




Fig. 36




Fig. 37




Fig. 38




Fig. 39




Fig. 40




Fig. 41




Fig. 42




Fig. 43




Fig. 44




Fig. 45




Fig. 46




Fig. 47




Fig. 48




Fig. 49

FUSED ABRASIVE PARTICLES, ABRASIVE ARTICLES, AND METHODS OF MAKING AND USING THE SAME

This is a continuation-in-part of U.S. Ser. No. 09/495, 978, filed Feb. 2, 2000 abandoned, the disclosure of which is incorporated herein by reference.

FIELD OF THE INVENTION

This invention pertains to fused abrasive particles and methods of making the same. The fused abrasive particles can be incorporated into a variety of abrasive articles, including bonded abrasives, coated abrasives, nonwoven abrasives, and abrasive brushes.

DESCRIPTION OF RELATED ART

There are a variety of abrasive particles (e.g., diamond particles, cubic boron nitride particles, fused abrasive particles, and sintered, ceramic abrasive particles (including sol-gel-derived abrasive particles) known in the art. In some abrading applications, the abrasive particles are used in loose form, while in others the particles are incorporated into abrasive products (e.g., coated abrasive products, bonded abrasive products, non-woven abrasive products, and abrasive brushes). Criteria used in selecting abrasive particles used for a particular abrading application include: abrading life, rate of cut, substrate surface finish, grinding efficiency, and product cost.

From about 1900 to about the mid-1980's, the premier abrasive particles for abrading applications such as those utilizing coated and bonded abrasive products were typically fused abrasive particles. There are two general types of fused abrasive particles: (1) fused alpha alumina abrasive particles (see, e.g., U.S. Pat. No. 1,161,620 (Coulter), U.S. Pat. No. 1,192,709 (Tone), U.S. Pat. No. 1,247,337 (Saunders et al.), U.S. Pat. No. 1,268,533 (Allen), and U.S. Pat. No. 2,424,645 (Baumann et al.)) and (2) fused (sometimes also referred to as "co-fused") alumina-zirconia abrasive particles (see, e.g., U.S. Pat. No. 3,891,408 (Rowse et al.), U.S. Pat. No. 3,781,172 (Pett et al.), U.S. Pat. No. 3,893,826 (Quinan et al.), U.S. Pat. No. 4,126,429 (Watson), U.S. Pat. No. 4,457,767 (Poon et al.), and U.S. Pat. No. 5,143,522 (Gibson et al.)) (also see, e.g., U.S. Pat. No. 5,023,212 (Dubots et. al) and U.S. Pat. No. 5,336,280 (Dubots et. al) which report the certain fused oxynitride abrasive particles). Fused alumina abrasive particles are typically made by charging a furnace with an alumina source such as aluminum ore or bauxite, as well as other desired additives, heating the material above its melting point, cooling the melt to provide a solidified mass, crushing the solidified mass into particles, and then screening and grading the particles to provide the desired abrasive particle size distribution. Fused alumina-zirconia abrasive particles are typically made in a similar manner, except the furnace is charged with both an alumina source and a zirconia source, and the melt is more rapidly cooled than the melt used to make fused alumina abrasive particles. For fused alumina-zirconia abrasive particles, the amount of alumina source is typically about 50–80 percent by weight, and the amount of zirconia, 50–20 percent by weight zirconia. The processes for making the fused alumina and fused alumina abrasive particles may include removal of impurities from the melt prior to the cooling step.

Although fused alpha alumina abrasive particles and fused alumina-zirconia abrasive particles are still widely used in abrading applications (including those utilizing

coated and bonded abrasive products, the premier abrasive particles for many abrading applications since about the mid-1980's are sol-gel-derived alpha alumina particles (see, e.g., U.S. Pat. No. 4,314,827 (Leitheiser et al.), U.S. Pat. No. 4,518,397 (Leitheiser et al.), U.S. Pat. No. 4,623,364 (Cottringer et al.), U.S. Pat. No. 4,744,802 (Schwabel), U.S. Pat. No. 4,770,671 (Monroe et al.), U.S. Pat. No. 4,881,951 (Wood et al.), U.S. Pat. No. 4,960,441 (Pellow et al.), U.S. Pat. No. 5,139,978 (Wood), U.S. Pat. No. 5,201,916 (Berg et al.), U.S. Pat. No. 5,366,523 (Rowenhorst et al.), U.S. Pat. No. 5,429,647 (Larmie), U.S. Pat. No. 5,547,479 (Conwell et al.), U.S. Pat. No. 5,498,269 (Larmie), U.S. Pat. No. 5,551,963 (Larmie), and U.S. Pat. No. 5,725,162 (Garg et al.)).

The sol-gel-derived alpha alumina abrasive particles may have a microstructure made up of very fine alpha alumina crystallites, with or without the presence of secondary phases added. The grinding performance of the sol-gel derived abrasive particles on metal, as measured, for example, by life of abrasive products made with the abrasive particles was dramatically longer than such products made from conventional fused alumina abrasive particles.

Typically, the processes for making sol-gel-derived abrasive particles are more complicated and expensive than the processes for making conventional fused abrasive particles. In general, sol-gel-derived abrasive particles are typically made by preparing a dispersion or sol comprising water, alumina monohydrate (boehmite), and optionally peptizing agent (e.g., an acid such as nitric acid), gelling the dispersion, drying the gelled dispersion, crushing the dried dispersion into particles, screening the particles to provide the desired sized particles, calcining the particles to remove volatiles, sintering the calcined particles at a temperature below the melting point of alumina, and screening and grading the particles to provide the desired abrasive particle size distribution. Frequently a metal oxide modifier(s) is incorporated into the sintered abrasive particles to alter or otherwise modify the physical properties and/or microstructure of the sintered abrasive particles.

There are a variety of abrasive products (also referred to "abrasive articles") known in the art. Typically, abrasive products include binder and abrasive particles secured within the abrasive product by the binder. Examples of abrasive products include: coated abrasive products, bonded abrasive products, nonwoven abrasive products, and abrasive brushes.

Examples of bonded abrasive products include: grinding wheels, cutoff wheels, and honing stones). The main types of bonding systems used to make bonded abrasive products are: resinoid, vitrified, and metal. Resinoid bonded abrasives utilize an organic binder system (e.g., phenolic binder systems) to bond the abrasive particles together to form the shaped mass (see, e.g., U.S. Pat. No. 4,741,743 (Narayanan et al.), U.S. Pat. No. 4,800,685 (Haynes et al.), U.S. Pat. No. 5,038,453 (Narayanan et al.), and U.S. Pat. No. 5,110,332 (Narayanan et al.)). Another major type are vitrified wheels in which a glass binder system is used to bond the abrasive particles together mass (see, e.g., U.S. Pat. No. 4,543,107 (Rue), U.S. Pat. No. 4,898,587 (Hay et al.), U.S. Pat. No. 4,997,461 (Markhoff-Matheny et al.), and U.S. Pat. No. 5,863,308 (Qi et al.)). These glass bonds are usually matured at temperatures between 900° C. to 1300° C. Today vitrified wheels utilize both fused alumina and sol-gel-derived abrasive particles. However, fused alumina-zirconia is generally not incorporated into vitrified wheels due in part to the thermal stability of alumina-zirconia. At the elevated temperatures at which the glass bonds are matured, the physical

properties of alumina-zirconia degrade, leading to a significant decrease in their abrading performance. Metal bonded abrasive products typically utilize sintered or plated metal to bond the abrasive particles.

The abrasive industry continues to desire abrasive particles and abrasive products that are easier to make, cheaper to make, and/or provide performance advantage(s) over conventional abrasive particles and products.

SUMMARY OF THE INVENTION

The present invention provides fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising, on a theoretical oxide basis, Al_2O_3 and at least one other metal oxide, wherein the abrasive particles have a first average microhardness of at least 11 GPa (preferably, at least 12, 13, or 14 GPa, more preferably, at least 15 GPa, and even more preferably, at least 16 GPa, at least 17 GPa, or even at least 18 GPa), wherein the abrasive particles have a second average microhardness after being heated in air at 1000°C . for 4 hours, and wherein the second average microhardness is at least 85% (preferably, at least 90%; more preferably, at least 95%; and even more preferably, at least 100%) of the first average microhardness.

Preferred embodiments according to the present invention include fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising ZrO_2 , on a theoretical oxide basis, Al_2O_3 , and at least one other metal oxide, wherein the abrasive particles have a first average microhardness of at least 11 GPa (preferably, at least 12, 13, or 14 GPa, more preferably, at least 15 GPa, and even more preferably, at least 16 GPa, at least 17 GPa, or even at least 18 GPa), wherein the abrasive particles have a second average microhardness after being heated in air at 100°C . for 4 hours, and wherein the second average microhardness is at least 85% (preferably, at least 90%; more preferably, at least 95%; and even more preferably, at least 100%) of the first average microhardness.

Preferred embodiments according to the present invention also include fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\text{-REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein the abrasive particles have a first average microhardness of at least 11 GPa (preferably, at least 12, 13, or 14 GPa, more preferably, at least 15 GPa, and even more preferably, at least 16 GPa), wherein the abrasive particles have a second average microhardness after being heated in air at 1000°C . for 4 hours, and wherein the second average microhardness is at least 85% (preferably, at least 90%; more preferably, at least 95%; and even more preferably, at least 100%) of the first average microhardness.

Preferred embodiments according to the present invention also include fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\text{-Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein the abrasive particles have a first average microhardness of at least 11 GPa (preferably, at least 12, 13, or 14 GPa, more preferably, at least 15 GPa, and even more preferably, at least 16 GPa), wherein the abrasive particles have a second average microhardness after being heated in air at 1000°C . for 4 hours, and wherein the second average microhardness is at least 85% (preferably, at least 90%; more preferably, at least 95%; and even more preferably, at least 100%) of the first average microhardness.

Preferably, fused, crystalline abrasive particles according to the present invention comprise at least 20, 30, 40, 50, 60, 70, 75, 80, 85, 90, 95, 98, 99, or even 100 percent of the eutectic(s) by volume, based on the total metal oxide, carbide, and/or nitride content, as the case may be, volume of the respective particle. In another aspect, fused, crystalline abrasive particles according to the present invention preferably comprises, on a theoretical oxide basis, at least 30 percent (or even at least 40, 50, 60, 70, or 80 percent) by weight Al_2O_3 , based on the total metal oxide, carbide, and/or nitride content, as the case may be, content the respective particle.

In another aspect, the present invention provides a plurality of particles having a particle size distribution ranging from fine to coarse, wherein at least a portion of the plurality of particles are fused, crystalline abrasive particles according to the present invention.

One method for making fused, crystalline abrasive particles according to the present invention, the method comprises:

- melting at least one Al_2O_3 source and at least one other metal oxide source (typically, at least one reactive Al_2O_3 metal oxide source) to provide a melt; and
- converting the melt to fused, crystalline abrasive particles according to the present invention.

In another method for making fused, crystalline abrasive particles according to the present invention, the method comprises:

- melting at least one Al_2O_3 source and at least one Y_2O_3 source to provide a melt, wherein and at least one source of nitrogen (e.g. AlN) or carbon (e.g. Al_4C_3) is provided in the melt; and
- converting the melt to the fused, crystalline abrasive particles.

In another method for making fused, crystalline abrasive particles according to the present invention, the method comprises:

- melting at least one Al_2O_3 source and at least one REO source to provide a melt, wherein and at least one source of nitrogen (e.g. AlN) or carbon (e.g. Al_4C_3) is provided in the melt; and
- converting the melt to the fused, crystalline abrasive particles.

In this application:

“simple metal oxide” refers to a metal oxide comprised of a one or more of the same metal element and oxygen (e.g., Al_2O_3 , CeO_2 , MgO , SiO_2 , and Y_2O_3);

“complex metal oxide” refers to a metal oxide comprised of two or more different metal elements and oxygen (e.g., $\text{CeAl}_{11}\text{O}_{18}$, $\text{Dy}_3\text{Al}_5\text{O}_{12}$, MgAl_2O_4 , and $\text{Y}_3\text{Al}_5\text{O}_{12}$);

“complex Al_2O_3 .metal oxide” refers to a complex metal oxide comprised of, on a theoretical oxide basis, Al_2O_3 and one or more metal elements other than Al (e.g., $\text{CeAl}_{11}\text{O}_{18}$, $\text{Dy}_3\text{Al}_5\text{O}_{12}$, MgAl_2O_4 , and $\text{Y}_3\text{Al}_5\text{O}_{12}$);

“complex $\text{Al}_2\text{O}_3\text{-Y}_2\text{O}_3$ ” refers to a complex metal oxide comprised of, on a theoretical oxide basis, Al_2O_3 and Y_2O_3 (e.g., $\text{Y}_3\text{Al}_5\text{O}_{12}$);

“complex Al_2O_3 .rare earth oxide” refers to a complex metal oxide comprised of, on a theoretical oxide basis, Al_2O_3 and rare earth oxide (e.g., $\text{CeAl}_{11}\text{O}_{18}$ and $\text{Dy}_3\text{Al}_5\text{O}_{12}$);

“reactive Al_2O_3 metal oxide” refers to a metal oxide other than Al_2O_3 (e.g., Dy_2O_3 or Y_2O_3) that can react with Al_2O_3 to form at least one complex Al_2O_3 .metal oxide;

“rare earth oxides” refer to, on a theoretical oxide basis, CeO_2 , Dy_2O_3 , Er_2O_3 , Eu_2O_3 , Gd_2O_3 , Ho_2O_3 , La_2O_3 , Lu_2O_3 , Nd_2O_3 , Pr_6O_{11} , Sm_2O_3 , Th_4O_7 , Tm_2O_3 , and Yb_2O_3 ;

“REO” means rare earth oxide; and

“particle size” is the longest dimension of a particle.

Fused abrasive particles according to the present invention can be incorporated into various abrasive products such as coated abrasives, bonded abrasives, nonwoven abrasives, and abrasive brushes.

The present invention also provides a method of abrading a surface, the method comprising:

contacting fused abrasive particles according to the present invention with a surface of a workpiece; and moving at least one of the fused abrasive particles according to the present invention or the surface relative to the other to abrade at least a portion of the surface with at least one of the fused abrasive particles according to the present invention.

Preferred fused abrasive particles according to the present invention provide superior grinding performance as compared to current fused abrasive particles. Preferred fused abrasive particles according to the present invention are sufficiently microstructurally and chemically stable to allow them to be used with vitrified bonding systems without the significant decrease in abrading performance of conventional alumina-zirconia abrasive particles used with vitrified bonding systems.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a fragmentary cross-sectional schematic view of a coated abrasive article including fused abrasive particles according to the present invention;

FIG. 2 is a perspective view of a bonded abrasive article including fused abrasive particles according to the present invention;

FIG. 3 is an enlarged schematic view of a nonwoven abrasive article including fused abrasive particles according to the present invention;

FIG. 4 is a schematic of an exemplary portion of interpenetrating phases in a eutectic colony;

FIG. 5 is a Differential thermal analysis (DTA) plot and Thermogravimetric Analysis (TGA) plot of Example 1 fused material;

FIG. 6 is a DTA plot and TGA plot of Comparative Example D fused material;

FIG. 7 is a DTA plot and TGA plot of Comparative Example B abrasive particles;

FIGS. 8 and 9 are scanning electron photomicrographs of polished cross-sections of Examples 1 and 2 fused material, respectively;

FIGS. 10 and 11 are scanning electron photomicrographs of polished cross-sections of Comparative Examples D and B fused material, respectively;

FIGS. 12–14 are scanning electron photomicrographs of polished cross-sections of Comparative Example B abrasive particles after exposure to various heating conditions;

FIG. 15 is a scanning electron photomicrograph of a polished cross-section of Comparative Example D fused material;

FIG. 16 is a scanning electron photomicrographs of polished cross-section of Comparative Example D abrasive particle after exposure to a specified heating condition;

FIGS. 17 and 18 are scanning electron photomicrographs of polished cross-section of Example 3 abrasive particles;

FIGS. 19–30 are scanning electron photomicrographs of polished cross-sections of Example 4–15 abrasive particles, respectively;

FIG. 31 is a DTA plot and TGA plot of Example 10 abrasive particles; and

FIGS. 32–49 are scanning electron photomicrographs of polished cross-sections of Example 16–33 fused material, respectively.

DETAILED DESCRIPTION

Fused Abrasive particles according to the present invention can be made by heating the appropriate metal oxides sources to form a melt, preferably a homogenous melt, and then rapidly cooling the melt to provide a solidified mass. The solidified mass is typically crushed to produce the desired particle size distribution of abrasive particles.

More specifically, fused abrasive particles according to the present invention can be made by charging a furnace with sources of the appropriate raw materials (e.g., depending on the composition of the fused abrasive particles, materials such as metal oxide(s), metal carbides, metal nitrides, metal oxycarbides, and/or metal oxynitrides), and other optional additives (e.g., other metal carbides, nitrides, oxides, metal borides, and processing aids). The raw materials can be added to the furnace, for example, together and melted, or sequentially and melted.

For solidified melt material containing complex metal oxide(s), at least a portion of the metal oxide present in the melted metal oxide sources (i.e., the melt) react to form complex metal oxide(s) during formation process of the solidified material. For example, an Al_2O_3 source and a Y_2O_3 source may react to form $\text{Y}_3\text{Al}_5\text{O}_{12}$ (i.e., $5\text{Al}_2\text{O}_3 + 3\text{Y}_2\text{O}_3 \rightarrow 2\text{Y}_3\text{Al}_5\text{O}_{12}$, or YAlO_3 (i.e., $\text{Al}_2\text{O}_3 + 3\text{Y}_2\text{O}_3 \rightarrow 2\text{YAlO}_3$), or $\text{Y}_4\text{Al}_2\text{O}_9$ (i.e., $\text{Al}_2\text{O}_3 + 2\text{Y}_2\text{O}_3 \rightarrow \text{Y}_4\text{Al}_2\text{O}_9$). Similarly, for example, an Al_2O_3 source and an Er_2O_3 or a Yb_2O_3 source may react to form $\text{Er}_3\text{Al}_5\text{O}_{12}$ and $\text{Yb}_3\text{Al}_5\text{O}_{12}$, respectively. Further, for example, an Al_2O_3 source and a Gd_2O_3 source may react to form GdAlO_3 (i.e., $\text{Al}_2\text{O}_3 + \text{Gd}_2\text{O}_3 \rightarrow 2\text{GdAlO}_3$). Similarly, for example, an Al_2O_3 source and a CeO_2 , Dy_2O_3 , Eu_2O_3 , La_2O_3 , Nd_2O_3 , Pr_2O_3 , or Sm_2O_3 source may react to form CeAlO_3 , $\text{Dy}_3\text{Al}_5\text{O}_{12}$, EuAlO_3 , LaAlO_3 , NdAlO_3 , PrAlO_3 , and SmAlO_3 , respectively. Further, for example, an Al_2O_3 source and a La_2O_3 source may react to form LaAlO_3 (i.e., $\text{Al}_2\text{O}_3 + \text{La}_2\text{O}_3 \rightarrow 2\text{LaAlO}_3$) and $\text{LaAl}_{11}\text{O}_{18}$ (i.e., $11\text{Al}_2\text{O}_3 + \text{La}_2\text{O}_3 \rightarrow 2\text{LaAl}_{11}\text{O}_{18}$). Similarly, for example, an Al_2O_3 source and CeO_2 , Eu_2O_3 , Nd_2O_3 , Pr_2O_3 , or Sm_2O_3 source may react to form $\text{CeAl}_{11}\text{O}_{18}$, $\text{EuAl}_{11}\text{O}_{18}$, $\text{NdAl}_{11}\text{O}_{18}$, $\text{PrAl}_{11}\text{O}_{18}$, and $\text{SmAl}_{11}\text{O}_{18}$, respectively.

Depending upon the relative proportions of Al_2O_3 and Y_2O_3 or rare earth oxide, the resultant solidified material, and ultimately the fused abrasive particles, comprises:

- (a) crystalline Al_2O_3 together with crystalline Al_2O_3 -complex Al_2O_3 -metal oxide (complex Al_2O_3 -metal oxide is, for example, $\text{Y}_3\text{Al}_5\text{O}_{12}$, $\text{Dy}_3\text{Al}_5\text{O}_{12}$, $\text{Er}_3\text{Al}_5\text{O}_{12}$, GdAlO_3 , or $\text{Yb}_3\text{Al}_5\text{O}_{12}$) eutectic;
- (b) Al_2O_3 -complex Al_2O_3 -metal oxide (again complex Al_2O_3 -metal oxide is, for example, $\text{Y}_3\text{Al}_5\text{O}_{12}$, $\text{Dy}_3\text{Al}_5\text{O}_{12}$, $\text{Er}_3\text{Al}_5\text{O}_{12}$, GdAlO_3 , or $\text{Yb}_3\text{Al}_5\text{O}_{12}$) eutectic; and/or
- (c) crystalline complex Al_2O_3 -metal oxide (again, complex Al_2O_3 -metal oxide is, for example, $\text{Y}_3\text{Al}_5\text{O}_{12}$, $\text{Dy}_3\text{Al}_5\text{O}_{12}$, $\text{Er}_3\text{Al}_5\text{O}_{12}$, GdAlO_3 , or $\text{Yb}_3\text{Al}_5\text{O}_{12}$) together with crystalline Al_2O_3 -complex Al_2O_3 -metal oxide (again complex Al_2O_3 -metal oxide is, for

example, $Y_3Al_5O_{12}$, $Dy_3Al_5O_{12}$, $Er_3Al_5O_{12}$, $GdAlO_3$, or $Yb_3Al_5O_{12}$) eutectic.

If Al_2O_3 reacts with Y_2O_3 to form two complex metal oxides, the resulting solidified material, and ultimately the fused abrasive particles, depending upon the relative proportions of Al_2O_3 and Y_2O_3 , comprises:

- (a) first crystalline complex Al_2O_3 .metal oxide (e.g., $Y_3Al_5O_{12}$ or $YAlO_3$) together with first crystalline complex Al_2O_3 .metal oxide (again, e.g., $Y_3Al_5O_{12}$ or $YAlO_3$, respectively)-second, different, crystalline complex Al_2O_3 .metal oxide (e.g., $YAlO_3$ or $Y_4Al_2O_9$, respectively) eutectic;
- (b) first crystalline complex Al_2O_3 .metal oxide (again, e.g., $Y_3Al_5O_{12}$ or $YAlO_3$)-second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $YAlO_3$ or $Y_4Al_2O_9$, respectively) eutectic; and/or
- (c) second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $YAlO_3$ or $Y_4Al_2O_9$) together with first crystalline complex Al_2O_3 .metal oxide (again, e.g., $Y_3Al_5O_{12}$ or $YAlO_3$)-second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $YAlO_3$ or $Y_4Al_2O_9$, respectively) eutectic.

If Al_2O_3 reacts with rare earth oxide to form two complex metal oxides, the resulting solidified material, and ultimately the fused abrasive particles, depending upon the relative proportions of Al_2O_3 and rare earth oxide, comprises:

- (a) first crystalline complex Al_2O_3 , metal oxide (e.g., $CeAlO_3$, $EuAlO_3$, $LaAlO_3$, $NdAlO_3$, $PrAlO_3$, or $SmAlO_3$) together with first crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAlO_3$, $EuAlO_3$, $LaAlO_3$, $NdAlO_3$, $PrAlO_3$, or $SmAlO_3$)-second, different, crystalline complex Al_2O_3 .metal oxide (e.g., $CeAl_{11}O_{18}$, $EuAl_{11}O_{18}$, $LaAl_{11}O_{18}$, $NdAl_{11}O_{18}$, $PrAl_{11}O_{18}$, or $SmAl_{11}O_{18}$, respectively) eutectic;
- (b) first crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAlO_3$, $EuAlO_3$, $LaAlO_3$, $NdAlO_3$, $PrAlO_3$, or $SmAlO_3$)-second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAl_{11}O_{18}$, $EuAl_{11}O_{18}$, $LaAl_{11}O_{18}$, $NdAl_{11}O_{18}$, $PrAl_{11}O_{18}$, or $SmAl_{11}O_{18}$, respectively) eutectic; and/or
- (c) second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAl_{11}O_{18}$, $EuAl_{11}O_{18}$, $LaAl_{11}O_{18}$, $NdAl_{11}O_{18}$, or $SmAl_{11}O_{18}$) together with first crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAlO_3$, $EuAlO_3$, $LaAlO_3$, $NdAlO_3$, $PrAlO_3$, or $SmAlO_3$)-second, different, crystalline complex Al_2O_3 .metal oxide (again, e.g., $CeAl_{11}O_{18}$, $EuAl_{11}O_{18}$, $LaAl_{11}O_{18}$, $NdAl_{11}O_{18}$, $PrAl_{11}O_{18}$, or $SmAl_{11}O_{18}$, respectively) eutectic.

For abrasive particles according to the present invention comprising yttria and nitrides and/or carbides, depending upon the relative proportions of Al_2O_3 , Y_2O_3 , nitrides and/or carbides, the resultant solidified material, and ultimately the fused abrasive particles, may comprise:

- (a) at least one of crystalline aluminum carbide, aluminum oxycarbide, aluminum nitride, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 , metal oxide (complex Al_2O_3 .metal oxide is, for example, $Y_3Al_5O_{12}$) eutectic and at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride);
- (b) at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 .metal oxide (again complex Al_2O_3 .metal oxide is, for example, $Y_3Al_5O_{12}$) eutectic; and/or

- (c) at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 .metal oxide (again complex Al_2O_3 .metal oxide is, for example, $Y_3Al_5O_{12}$) eutectic and crystalline complex Al_2O_3 .metal oxide (again, complex Al_2O_3 .metal oxide is, for example, $Y_3Al_5O_{12}$).

For abrasive particles according to the present invention comprising rare earth oxide and nitrides and/or carbides, depending upon the relative proportions of Al_2O_3 , rare earth oxide, nitrides and/or carbides, the resultant solidified material, and ultimately the fused abrasive particles, may comprise:

- (a) at least one of crystalline aluminum carbide, aluminum oxycarbide, aluminum nitride, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 .metal oxide (complex Al_2O_3 .metal oxide is, for example, $Dy_3Al_5O_{12}$, $Er_3Al_5O_{12}$, $GdAlO_3$, or $Yb_3Al_5O_{12}$) eutectic and at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride);
- (b) at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 .metal oxide (again complex Al_2O_3 .metal oxide is, for example, $Dy_3Al_5O_{12}$, $Er_3Al_5O_{12}$, $GdAlO_3$, or $Yb_3Al_5O_{12}$) eutectic; and/or
- (c) at least one of crystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof (e.g., aluminum oxycarbonitride)-complex Al_2O_3 .metal oxide (again complex Al_2O_3 .metal oxide is, for example, $Dy_3Al_5O_{12}$, $Er_3Al_5O_{12}$, $GdAlO_3$, or $Yb_3Al_5O_{12}$) eutectic and crystalline complex Al_2O_3 .metal oxide (again, complex Al_2O_3 .metal oxide is, for example, $Dy_3Al_5O_{12}$, $Er_3Al_5O_{12}$, $GdAlO_3$, or $Yb_3Al_5O_{12}$).

In addition to the eutectic, some fused abrasive particles according to the present invention may further comprise at least one of oxynitride or oxycarbide of at least one metal selected from the group consisting of Ti, Mg, Ca, Sc, Sr, Ba, Zr, B, and combinations thereof. In another aspect, some fused abrasive particles according to the present invention may further comprise at least one of boride, nitride, oxynitride, carbide, or oxycarbide of at least one of Ti, Mg, Ca, Sc, Sr, Ba, or Zr. In yet another aspect, some fused abrasive particles according to the present invention may further comprise at least one of boron carbide, boron oxycarbide, boron nitride, or boron oxynitride.

It is understood, however, the particular phases formed are dependent upon several factors including the melt composition and solidification conditions. Typically it is preferred that the composition of the melt and the solidification conditions are such that a large portion of the resulting solidified material is occupied by eutectic (i.e., the formulation of the solidified material corresponds to close to eutectic proportions of the various metal oxide phases that present in the material). Although not wanting to be bound by theory, some metastable conditions during formation of the solidified material may lead to the formation of alternative eutectic. For example, if under normal, stable conditions the eutectic that forms is $Al_2O_3/Y_3Al_5O_{12}$, under some metastable conditions $Al_2O_3/YAlO_3$ eutectic may form in place of, or in addition to $Al_2O_3/Y_3Al_5O_{12}$ eutectic.

It is also within the scope of the present invention to substitute a portion of the aluminum and/or other metal cations in the complex Al_2O_3 .metal oxide with other cations.

For example, a portion of the Al cations in a complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ or $\text{Al}_2\text{O}_3\cdot\text{REO}$ may be substituted with at least one cation of an element selected from the group consisting of: Cr, Ti, Sc, Fe, Mg, Ca, Si, Co, and combinations thereof. A portion of the Y cations in a complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ may be substituted with at least one cation of an element selected from the group consisting of: Ce, Dy, Er, Eu, Gd, Ho, La, Lu, Nd, Pr, Sm, Th, Tm, Yb, Fe, Ti, Mn, V, Cr, Co, Ni, Cu, Mg, Ca, Sr, and combinations thereof. A portion of the rare earth cations in a complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ may be substituted with at least one cation of an element selected from the group consisting of: Y, Fe, Ti, Mn, V, Cr, Co, Ni, Cu, Mg, Ca, Sr, and combinations thereof.

Similarly, it is also within the scope of the present invention to substitute a portion of the aluminum cations in alumina. For example, Cr, Ti, Sc, Fe, Mg, Ca, Si, and Co can substitute for aluminum in alumina structure. Similarly, it is also within the scope of the present invention to substitute a portion of the aluminum cations in aluminum oxynitrides, oxycarbides, and/or alumina. For example, Cr, Ti, Sc, Fe, Mg, Ca, Si, and Co can substitute for aluminum in aluminum oxynitrides, oxycarbides, and/or alumina structure. The substitution of cations as described above may affect the properties (e.g. hardness, toughness, strength, thermal conductivity, etc.) of the abrasive particles.

Further, other eutectics will be apparent to those skilled in the art after reviewing the present disclosure. For example, phase diagrams depicting various eutectics, including additional eutectics for systems disclosed herein are known in the art.

Fused abrasive particles according to the present invention containing eutectic typically material are comprised of eutectic colonies. An individual colony contains generally homogeneous microstructural characteristics (e.g., similar size and orientation of crystals of constituent phases within a colony). Typically, impurities, if present, in the fused, crystalline abrasive particles according to the present invention, tend to segregate to colony boundaries, and may be present alone and/or as reaction products (e.g., as a complex $\text{Al}_2\text{O}_3\cdot\text{metal oxide}$) as crystalline and/or amorphous (glass) phase(s).

The constitution of eutectic colony may include: (a) two different simple metal oxides (e.g., an Al_2O_3 phase and a ZrO_2 phase), (b) a simple metal oxide (e.g., an Al_2O_3 phase) and a complex metal oxide (e.g., a GdAlO_3 phase), or (c) a two, different complex metal oxides (e.g., a LaAlO_3 phase and a $\text{LaAl}_{11}\text{O}_{18}$ phase). Examples of possible eutectics for Al_2O_3 and Y_2O_3 include $\text{Al}_2\text{O}_3\text{—Y}_3\text{Al}_5\text{O}_{12}$ eutectic. Example of possible eutectics for Al_2O_3 and complex $\text{Al}_2\text{O}_3\cdot\text{rare earth oxide}$ include $\text{Al}_2\text{O}_3\text{—Dy}_3\text{Al}_5\text{O}_{12}$, $\text{Al}_2\text{O}_3\text{—Er}_3\text{Al}_5\text{O}_{12}$, $\text{Al}_2\text{O}_3\text{—GdAlO}_3$, or $\text{Al}_2\text{O}_3\text{—Yb}_3\text{Al}_5\text{O}_{12}$ eutectics. Example of possible eutectics for two, different complex metal oxide include a $\text{MgAl}_2\text{O}_4\text{—Y}_3\text{Al}_5\text{O}_{12}$ eutectic and $\text{ReAlO}_3\text{—ReAl}_{11}\text{O}_{18}$ eutectics, where $\text{Re}=\text{Ce, Eu, La, Nd, Pr, or Sm}$.

In another aspect, phases making up the eutectic colonies may be (a) single crystals of two different metal oxides (e.g., single crystals of each of Al_2O_3 and $\text{Y}_3\text{Al}_5\text{O}_{12}$, or $\text{Y}_3\text{Al}_5\text{O}_{12}$ and at least one of aluminum oxycarbide, aluminum oxynitride, or a combination thereof), (b) a single crystal of one metal oxide (e.g., single crystal Al_2O_3 , or at least one of aluminum oxycarbide, aluminum oxynitride, or a combination thereof) and a plurality of crystals of a different metal oxide (e.g., polycrystalline $\text{Y}_3\text{Al}_5\text{O}_{12}$), or (c) two different polycrystalline metal oxides (e.g., polycrystalline Al_2O_3 and polycrystalline $\text{Y}_3\text{Al}_5\text{O}_{12}$, or at least one of polycrystalline aluminum oxycarbide, aluminum oxynitride, or a combination thereof and polycrystalline $\text{Y}_3\text{Al}_5\text{O}_{12}$).

The colonies may be in any of a variety of shapes, typically, ranging from essentially spherical to columnar. The composition, phase, and/or microstructure (e.g., crystallinity (i.e., single crystal or polycrystalline) and crystal size) of each colony may be the same or different. The orientation of the crystals inside the colonies may vary from one colony to another. Phases making up a eutectic colony may be present as an interpenetrating network(s). For example, referring to FIG. 4, eutectic colony 150 comprises first crystalline metal oxide phase 151 and second crystalline metal oxide phase 153. The two continuous phases form an entangled, three-dimensional network.

The number of colonies, their sizes and compositions are affected, for example, by the melt composition and solidification conditions. Although not wanting to be bound by theory, it is believed that the closer the melt composition is to the exact eutectic composition, the smaller the number of colonies that are formed. In another aspect, however, it is believed that slow, unidirectional solidification of the melt also tends to minimize the number of colonies formed, while multidirectional solidification with relatively higher cooling rates tends to increase the number of colonies formed. The solidification rate (i.e., cooling rate) of the melt and/or multidirectional solidification of the melt tend to affect the type and/or number of microstructural imperfections (e.g., pores) present in the resulting fused abrasive particles. For example, although not wanting to be bound by theory, relatively rapid solidification (i.e., solidification with relatively high cooling rates) and/or multidirectional solidification tend to lead to an increase in the type and/or number of microstructural imperfections (e.g., pores) present in the resulting fused abrasive particles. Relatively slow solidification, however, tends to lead to an increase in the size of the colonies, and/or crystals present in the solidified material; although it may be possible through slow and controlled cooling, for example, to eliminate formation of colonies. Hence, in selecting the cooling rate and/or degree of multidirectional solidification, there may be a need to increase or decrease the cooling rate to obtain the optimal balance of desirable and undesirable microstructural characteristics associated with the various cooling rates.

Further, for a given composition, the size of the colonies and phases present within the colonies tends to decrease as the cooling rate of the melt increases.

Typically, the eutectic colonies in abrasive particles according to the present invention are, on average, less than 100 micrometers, preferably, less than 50 micrometers, wherein such size for a given colony is the average of the two largest dimensions measured from a polished cross-section of the colony, as viewed with a scanning electron microscope (SEM). Typically, the smallest dimension of the crystalline phases making up the eutectic in a colony, as measured from a polished cross-section of the colony viewed with an SEM, is up to 10 micrometers; preferably, up to 5 micrometers; more preferably, up to 1 micrometer, or even up to 0.5 micrometer.

Some abrasive particles according to the present invention also include primary crystals of at least one of the metal oxide phases making up the eutectic constituent of the abrasive particle. For example, if the eutectic portion is made up of a LaAlO_3 phase and a $\text{LaAl}_{11}\text{O}_{18}$ phase, the microstructure may also include primary crystals of LaAlO_3 , which is believed to occur when the composition of the melt from which the abrasive particles are formed is rich in La_2O_3 (i.e., the melt contains, on a theoretical oxide basis, an excess of La_2O_3 relative to the eutectic); or if the eutectic is made up of a $\text{Yb}_3\text{Al}_5\text{O}_{12}$ phase, and Al_2O_3 , the microstruc-

ture may also include primary crystals of Al_2O_3 , which is believed to occur when the composition of the melt from which the abrasive particles are formed is rich in Al_2O_3 (i.e., the melt contains, on a theoretical oxide basis, an excess of Al_2O_3 relative to the eutectic).

The formation of the primary crystals is believed to result from a deviation from the particular eutectic proportions. The greater the deviation, the larger the overall fraction of primary crystals. The primary crystals may be found in a variety of shapes, typically ranging from rod-like structures to dendritic-like structures. Although not wanting to be bound by theory, it is believed that the presence and/or formation of a primary crystal(s) adjacent to a colony may affect the resulting microstructure of the colony. In some cases it may be advantageous (e.g., for increased abrading performance) to have primary crystals (e.g., primary Al_2O_3 crystals) present in the abrasive particles. It is also believed, however, that the abrading performance of an abrasive particle tends to decrease as the size of the primary crystals increase.

Further, although not wanting to be bound by theory, it is believed that small additions (e.g., less than 5 percent by weight) of metal oxides other than those making up the eutectic may affect colony boundaries, and in turn affect properties (e.g., hardness and toughness) of the abrasive particle.

Sources of (on a theoretical oxide basis) Al_2O_3 for making abrasive particles according to the present invention include those known in the art for making conventional fused alumina and alumina-zirconia abrasive particles. Commercially available Al_2O_3 sources include bauxite (including both natural occurring bauxite and synthetically produced bauxite), calcined bauxite, hydrated aluminas (e.g., boehmite, and gibbsite), Bayer process alumina, aluminum ore, gamma alumina, alpha alumina, aluminum salts, aluminum nitrates, and combinations thereof. The Al_2O_3 source may contain, or only provide, Al_2O_3 . Alternatively, the Al_2O_3 source may contain, or provide Al_2O_3 , as well as one or more metal oxides other than Al_2O_3 (including materials of or containing complex Al_2O_3 -metal oxides (e.g., $\text{Dy}_3\text{Al}_5\text{O}_{12}$, $\text{Y}_3\text{Al}_5\text{O}_{12}$, $\text{CeAl}_{11}\text{O}_{18}$, etc.)).

Preferred metal oxides in addition to the Al_2O_3 (i.e., preferred "metal oxides other than Al_2O_3 ") include Y_2O_3 and rare earth oxide.

Commercially available sources of (on a theoretical oxide basis) Y_2O_3 for making abrasive particles according to the present invention include yttrium oxide powders, yttrium, yttrium-containing ores, and yttrium salts (e.g., yttrium carbonates, nitrates, chlorides, hydroxides, and combinations thereof). The Y_2O_3 source may contain, or only provide, Y_2O_3 . Alternatively, the Y_2O_3 source may contain, or provide Y_2O_3 , as well as one or more metal oxides other than Y_2O_3 (including materials of or containing complex Y_2O_3 -metal oxides (e.g., $\text{Y}_3\text{Al}_5\text{O}_{12}$)).

Commercially available sources of rare earth oxides for making abrasive particles according to the present invention include rare earth oxide powders, rare earth metals, rare earth-containing ores (e.g., bastnasite and monazite), rare earth salts, rare earth nitrates, and rare earth carbonates. The rare earth oxide(s) source may contain, or only provide, rare earth oxide(s). Alternatively, the rare earth oxide(s) source may contain, or provide rare earth oxide(s), as well as one or more metal oxides other than rare earth oxide(s) (including materials of or containing complex rare earth oxide. Other metal oxides (e.g., $\text{Dy}_3\text{Al}_5\text{O}_{12}$, $\text{CeAl}_{11}\text{O}_{18}$, etc.)).

Commercially available sources of metal nitrides and metal carbides for making abrasive particles according to the

present invention include powders and ores comprised of at least one of metal (e.g., aluminum) carbide or nitride and/or at least one other metal other than Al. Other materials containing carbon (e.g., graphite powder) and/or nitrogen (e.g., nitrogen gas) may also be used as a raw materials for making abrasive particles according to the present invention.

The addition of certain metal oxides may alter the crystalline structure or microstructure of the resulting fused abrasive particles. For example, although not wishing to be bound by any theory, it is theorized that certain metal oxides or metal oxide containing compounds (even when used in relatively small amounts, for example, even 0.01 to 5 percent by weight, based on the total metal oxide content of the fused abrasive particle) may be present at the boundaries between the eutectic colonies. The presence of these metal oxides, which may be in the form of reaction products together or with the Al_2O_3 may affect the fracture characteristics and/or microstructure of the fused abrasive particles, and/or may affect the grinding characteristics of the abrasive particles. Certain metal oxides may also act as a processing aid, for example, to increase the density of the fused abrasive particles, by decreasing the size and/or number of pores in the fused abrasive particles. Certain metal oxides may also act as a processing aid, for example, to increase or decrease the effective melting temperature of the melt. Thus certain metal oxides may be added for processing reasons.

Fused abrasive particles according to the present invention typically comprise less than 50 percent by weight (more typically, less than 20 percent by weight; in some cases in the range from 0.01 to 5 percent by weight, in other cases from 0.1 to 1 percent by weight) of metals oxides (on a theoretical oxide basis) other than the eutectic forming metal oxides, based on the total metal oxide content of the respective abrasive particle. Sources of the metal oxides other than Al_2O_3 , Y_2O_3 , and rare earth oxides are also readily commercially available.

Examples of other than Al_2O_3 , Y_2O_3 , rare earth oxides metal oxides include, on a theoretical oxide basis, BaO , CaO , Cr_2O_3 , CoO , Fe_2O_3 , HfO_2 , Li_2O , MgO , MnO , NiO , SiO_2 , TiO_2 , Na_2O , Sc_2O_3 , SrO , V_2O_3 , ZnO , ZrO_2 , and combinations thereof.

Materials for making abrasive particles according to the present invention also include fused abrasive particles (e.g., fused alumina abrasive particles) or other fused material (e.g., fused alumina material) having the same composition or different composition(s), which together with remaining metal oxide, carbide, and nitride sources, as the case may be, provide the desired composition of the fused abrasive particles.

A reducing agent, such as a carbon source may be added to reduce impurities during the melting process. Examples of carbon sources include: coal, graphite, petroleum coke, or the like. Typically, the amount of carbon included in the charge to the furnace is up 5% by weight of the charge; more typically, up to 3% by weight, and more typically, up to 2% by weight. Iron may also be added to the furnace charge to aid in the removal of impurities. The iron can combine with the impurities to make a material that can be removed magnetically, for example, from the melt or crushed solidified material.

It is also within the scope of the present invention to include metal borides, carbides, nitrides, and combinations thereof in the fused, crystalline abrasive particles according to the present invention. Such materials may even be present within (e.g., as inclusions) the eutectic material. Examples of metal borides, carbides, and nitrides may include titanium

diboride, aluminum carbide, aluminum nitride, titanium carbide, titanium nitride, silicon carbide, boron carbide, and boron nitride. Such materials are known in the art, and are commercially available.

The particular selection of metal oxide sources and other additives for making fused abrasive particles according to the present invention typically takes into account, for example, the desired composition and microstructure of the resulting abrasive particles, the desired physical properties (e.g., hardness or toughness) of the resulting abrasive particles, avoiding or minimizing the presence of undesirable impurities, the desired grinding characteristics of the resulting abrasive particles, and/or the particular process (including equipment and any purification of the raw materials before and/or during fusion and/or solidification) being used to prepare the abrasive particles.

The metal oxide sources and other additives can be in any form suitable to the process and equipment being used to make the abrasive particles. The raw materials can be fused using techniques and equipment known in the art for making conventional fused alumina and alumina-zirconia abrasive particles (see, e.g., U.S. Pat. No. 3,781,172 (Pett et al.), U.S. Pat. No. 3,891,408 (Rowse et al.), U.S. Pat. No. 4,035,162 (Brothers et al.), U.S. Pat. No. 4,070,796 (Scott), U.S. Pat. No. 4,073,096 (Ueltz et al.), U.S. Pat. No. 4,126,429 (Watson), U.S. Pat. No. 4,457,767 (Poon et al.), U.S. Pat. No. 5,143,522 (Gibson et al.), and U.S. Pat. No. Re. 31,128 (Walker et al.), the disclosures of which are incorporated herein by reference).

Examples of furnaces for melting the metal oxide sources and other additives include arc furnaces, pig furnaces, arc tapping furnaces, electric furnaces, electric arc furnaces, and gas fired furnaces. Suitable electric furnaces include those in which the electrodes are arranged to create a "kissing arc", wherein the lower tip of the electrodes are not in contact within the molten mass, as well as those in which the electrodes are submerged in the molten mass to provide resistance heating via current passing through the melt.

The furnace may have a lining (sometimes referred to as a "shell" or "skeleton") that covers the inside of the furnace walls. The lining may be made from a material dissimilar to the fused abrasive particle composition. Typically, however it is preferred that the furnace lining is made from a composition or material similar, sometimes nearly identical or identical to the composition of the fused abrasive particle. Thus during processing, if the outer (exposed) surface of the lining melts, the potential contamination of the melt is reduced or minimized.

For some metal oxide sources and other additives, it may also be desirable to preheat feed prior to charging it into the furnace, or otherwise combining it with other metal oxide sources and other additives. For example, if carbonate, nitrate or other salts are used as the metal oxide source, it may be desirable to calcine (e.g., by heating them in air at about 400–1000° C.) such materials prior to adding them with the other metal oxide source materials.

Generally, the metal oxide sources and other additives, if present, are heated to a molten state, and mixed until the melt is homogenous. Typically, the melt is heated to and held at a temperature at least 50° C. (preferably, at least 100° C.) above the melting point of the melt. If the temperature of the melt is too low, the viscosity of the melt may be undesirably too high, making it more difficult to homogenize the various metal oxide sources and other additives making up the melt, or to pour or otherwise transfer the melt from the furnace. If the temperature of the melt is too high temperature, and/or the melt heated for too long, energy will be wasted, and there may be undesirable volatilization of components of the melt as well.

In some cases, it may be desirable, to mix, or otherwise blend the metal oxide sources and other additives (e.g., volatile components (e.g., water or organic solvent) which may assist in forming a homogenous mixture or blend), if present, together prior to forming the melt. For example, particulate metal oxide sources can be milled (e.g., ball milled) to both mix the materials together, as well as reduce the size of the particulate material. Other techniques for mixing or blending the metal oxide sources and other additives, if present, together prior to forming the melt include high shear mixers, paddle mixers, V-blenders, tumblers, and the like. Milling times may range from several minutes to several hours, or even days. Optionally, fugitive materials such as water and organic solvents may be removed from the mixture or blend of metal oxide sources and other additives, for example, by heating, prior to forming the melt. For ease of handling, the metal oxide sources and other additives may also be agglomerated prior to charging them to the furnace.

The atmosphere over the melt may be at atmospheric pressure, a pressure above atmospheric pressure, or a pressure below atmospheric pressure, although a pressure below atmospheric pressure may be preferred in order to reduce the number of pores in the resulting solidified material. The atmosphere over the melt may also be controlled to provide an oxidizing, reducing or inert atmosphere which may affect the melt chemistry.

Reducing conditions during melting may aid in purifying the melt. In addition to, or alternatively to, adding a reducing agent to the melt, suitable reducing conditions may be obtained using carbon electrodes with an electric arc melting furnace. Under suitable reducing conditions, some impurities (e.g., silica, iron oxide, and titania) will convert to their respective molten metallic form, leading to a higher specific gravity for the melt. Such free metal(s) impurities would then tend to sink to the bottom of the furnace.

In another aspect, it may be desired to oxidize free metal present in the melt before the melt is cooled (e.g., before pouring the melt from the furnace). For example, an oxygen lance(s) may be inserted into the melt just prior to pouring the melt from the furnace (see, e.g., U.S. Pat. No. 960,712, the disclosure of which is incorporated herein by reference).

The melt can be cooled using any of a variety of techniques known in the art. Typically the furnace containing the melt is capable of being tilted such that the melt can be poured over or into a heat sink. Generally, the resulting solidified material is larger in size than the desired abrasive particles. Examples of heat sinks include metallic balls (e.g., cast iron or carbon steel balls), metallic rods, metallic plates, metallic rolls, and the like. In some instances, these heat sink materials may be internally cooled (e.g., water-cooled or a suitable refrigerant) to achieve fast cooling rates. The heat sink material may also be pieces of pre-fused abrasive particles (having the same or a different composition being solidified) or other refractory material.

Further with regard to heat sinks, the melt can be cooled by pouring the melt over and in between a plurality of metallic balls. The balls typically range in diameter from about 1 to 50 cm, more typically 5 to 25 cm. The melt may also be cooled using book molds. Suitable book molds consist of a plurality of thin plates (e.g., metallic or graphite plates) that are spaced relatively close together. The plates are usually spaced less than 10 cm apart, typically less than 5 cm, and preferably less than 1 cm apart. The melt may also be poured into graphite or cast iron molds to form slabs. It is generally preferred that such "slabs" be relatively thin so as to achieve faster cooling rates.

The cooling rate is believed to affect the microstructure and physical properties of the solidified material, and thus the fused abrasive particles. Preferably, the melt is rapidly cooled as the size of the crystalline phases of the solidified material generally decreases as the cooling rate increase. Preferred cooling rates are at least 500° C./min.; more preferably, at least 1000° C./min; and even more preferably, at least 1500° C./min. The cooling rate may depend upon several factors including the chemistry of the melt, the melting point of the melt, the type of heat sink, and the heat sink material.

Rapid cooling may also be conducted under controlled atmospheres, such as a reducing, neutral or oxidizing environment to maintain and/or influence the desired crystalline phases, oxidation states, etc. during cooling.

Additional details on cooling a melt can be found, for example, in U.S. Pat. No. Re 31,128 (Walker et al.), U.S. Pat. No. 3,781,172 (Pett et al.), U.S. Pat. No. 4,070,796 (Scott et al.), U.S. Pat. No. 4,194,887 (Ueltz et al.), U.S. Pat. No. 4,415,510 (Richmond), U.S. Pat. No. 4,439,845 (Richmond), and U.S. Pat. No. 5,143,522 (Gibson et al.), the disclosures of which are incorporated herein by reference.

The resulting (solidified) fused material(s) is typically larger in size than that desired for the abrasive particle(s). The fused material can be, and typically is, converted into smaller pieces using crushing and/or comminuting techniques known in the art, including roll crushing, canary milling, jaw crushing, hammer milling, ball milling, jet milling, impact crushing, and the like. In some instances, it is desired to have two or multiple crushing steps. For example after the molten material is solidified, it may be in the form of a relatively large mass structure (e.g., a diameter greater than 5 cm. The first crushing step may involve crushing these relatively large masses or “chunks” to form smaller pieces. This crushing of these chunks may be accomplished with a hammer mill, impact crusher or jaw crusher. These smaller pieces may then be subsequently crushed to produce the desired particle size distribution. In order to produce the desired particle size distribution (sometimes referred to as grit size or grade), it may be necessary to perform multiple crushing steps. In general the crushing conditions are optimized to achieve the desired particle shape(s) and particle size distribution.

The shape of fused abrasive particles according to the present invention depends, for example, on the composition and/or microstructure of the abrasive particles, the geometry in which it was cooled, and the manner in which the solidified material is crushed (i.e., the crushing technique used). In general, where a “blocky” shape is preferred, more energy may be employed to achieve this shape. Conversely, where a “sharp” shape is preferred, less energy may be employed to achieve this shape. The crushing technique may also be changed to achieve different desired shapes. Alternatively, abrasive particles may be directly formed into desired shapes by pouring or forming the melt into a mold.

The shape of the abrasive particles may be measured by various techniques known in the art, including bulk density and aspect ratio. The larger the abrasive particle size, the higher the bulk density due to the increased mass associated with larger particle sizes. Thus, when comparing bulk densities, the comparison should be made on abrasive particles having essentially the same particle size. In general, the larger the bulk density number, the “blockier” the abrasive particle is considered to be. Conversely the smaller the bulk density number, the “sharper” the abrasive particle is considered to be. Another way to measure sharpness is through an aspect ratio. The aspect ratio of a grade 36 for

example, may range from about 1:1 to about 3:1, typically about 1.2:1 to about 2:1.

The bulk density of the abrasive particles can be measured in accordance with ANSI Standard B74.4-1992 (1992), the disclosure of which is incorporated herein by reference. In general, the bulk density is measured by pouring the abrasive particles sample through a funnel so that the abrasive particles traverses through the funnel in a free flowing manner. Immediately underneath the funnel is a collection device (typically a graduated cylinder). A predetermined volume of abrasive particles are collected and then weighed. The bulk density is calculated in terms of weight/volume.

Abrasive particles according to the present invention can be screened and graded using techniques well known in the art, including the use of industry recognized grading standards such as ANSI (American National Standard Institute), FEPA (Federation Europeenne des Fabricants de Produits Abrasifs), and JIS (Japanese Industrial Standard). Abrasive particles according to the present invention may be used in a wide range of particle sizes, typically ranging in size from about 0.1 to about 5000 micrometers, more typically from about 1 to about 2000 micrometers; preferably from about 5 to about 1500 micrometers, more preferably from about 100 to about 1500 micrometers.

In a given particle size distribution, there will be a range of particle sizes, from coarse particles fine particles. In the abrasive art this range is sometimes referred to as a “coarse”, “control” and “fine” fractions. Abrasive particles graded according to industry accepted grading standards specify the particle size distribution for each nominal grade within numerical limits. Such industry accepted grading standards include those known as the American National Standards Institute, Inc. (ANSI) standards, Federation of European Producers of Abrasive Products (FEPA) standards, and Japanese Industrial Standard (JIS) standards. ANSI grade designations (i.e., specified nominal grades) include: ANSI 4, ANSI 6, ANSI 8, ANSI 16, ANSI 24, ANSI 36, ANSI 40, ANSI 50, ANSI 60, ANSI 80, ANSI 100, ANSI 120, ANSI 150, ANSI 180, ANSI 220, ANSI 240, ANSI 280, ANSI 320, ANSI 360, ANSI 400, and ANSI 600. Preferred ANSI grades comprising abrasive particles according to the present invention are ANSI 8–220. FEPA grade designations include P8, P12, P16, P24, P36, P40, P50, P60, P80, P100, P120, P150, P180, P220, P320, P400, P500, P600, P800, P1000, and P1200. Preferred FEPA grades comprising abrasive particles according to the present invention are P12–P220. JIS grade designations include JIS8, JIS12, JIS16, JIS24, JIS36, JIS46, JIS54, JIS60, JIS80, JIS100, JIS150, JIS180, JIS220, JIS240, JIS280, JIS320, JIS360, JIS400, JIS400, JIS600, JIS800, JIS1000, JIS1500, JIS2500, JIS4000, JIS6000, JIS8000, and JIS10,000. Preferred JIS grades comprising abrasive particles according to the present invention are JIS8–220.

After crushing and screening, there will typically be a multitude of different abrasive particle size distributions or grades. These multitudes of grades may not match a manufacturer’s or supplier’s needs at that particular time. To minimize inventory, it is possible to recycle the off demand grades back into the molten mass. This recycling may occur after the crushing step, where the particles are in large chunks or smaller pieces (sometimes referred to as “fines”) that have not been screened to a particular distribution. A charge to the furnace for making fused abrasive particles according to the present invention may consist of anywhere from 0 to 100% by weight recycled fused abrasive particles, typically between 0 to 50% by weight.

Typically, the true density, sometimes referred to as specific gravity, of fused abrasive particles according to the

present invention is typically at least 80% of theoretical density, although abrasive particles with a lower true density may also be useful in abrasive applications. Preferably, the true density of fused abrasive particles according to the present invention is at least 85% of theoretical density, more preferably at least 90% of theoretical density, and even more preferably at least 95% of theoretical density.

Typically, fused abrasive particles according to the present invention may have an average toughness (i.e., resistance to fracture) of at least 2.0 MPa m^{1/2}; preferably at least 2.5 MPa m^{1/2}, more preferably at least 3.0 MPa m^{1/2}, and even more preferably, at least 3.3 MPa m^{1/2}, at least 3.5 MPa m^{1/2}, or even at least 3.8 MPa m^{1/2}.

It is also within the scope of the present invention to provide a surface coating on the fused abrasive particles. Surface coatings are known, for example, to improve the adhesion between the abrasive particles and the binder material in the abrasive article. Such surface coatings are described, for example, in U.S. Pat. No. 1,910,444 (Nicholson), U.S. Pat. No. 3,041,156 (Rowse et al.), U.S. Pat. No. 4,997,461 (Markhoff-Matheny et al.), U.S. Pat. No. 5,009,675 (Kunz et al.), U.S. Pat. No. 5,042,991 (Kunz et al.), and U.S. Pat. No. 5,085,671 (Martin et al.), the disclosures of which are incorporated herein by reference. Further, in some instances, the addition of the coating improves the abrading characteristics of the abrasive particles. Alternatively the surface coating may improve adhesion between the abrasive particle of the invention and the binder.

Likewise after the abrasive particles are produced, it may be further heat-treated to improve its physical properties and/or grinding performance. This heat-treating process may occur in an oxidizing atmosphere. Typically this heat-treating process occurs at a temperature between about 1100° C. to 1600° C., usually between 1200° C. to 1400° C. The time may range from about 1 minute to days, usually between about 5 minutes to 1 hour.

Other suitable preparation techniques for making fused abrasive particles according to the present invention may be apparent to those skilled in the art after reviewing the disclosure herein, as well as, for example, applications having U.S. Ser. Nos. 09/495,978, 09/496,422, 09/496,638, and 09/496,713, each filed on Feb. 2, 2000, and 09/618,876, 09/618,879, 09/619,106, 09/619,191, 09/619,192, 09/619,215, 09/619,289, 09/619,729, 09/619,744, and 09/620,262, each filed on the same date as the instant application, the disclosure of which are all incorporated herein by reference.

Preferred abrasive particles according to the present invention are thermally stable at elevated temperatures, as compared to conventional fused alumina-zirconia materials (including alumina-zirconia abrasive particles available from Norton Company, Worcester, Ma. under the trade designation "NORZON"). When alumina-zirconia eutectic abrasive particles available from Norton Company, Worcester, Mass. under the trade designation "NORZON", are heated in air, for example, to at least about 350° C., typically at least a portion of the zirconia undergoes a tetragonal and/or cubic to monoclinic phase transformation. This phase transformation is usually detrimental to the structural integrity of the alumina-zirconia material because it involves volume changes to the zirconia crystalline phases. Further, such phase transformations have been observed to occur preferentially at the boundaries of eutectic colonies, which thereby tend to weaken the boundaries, and which in turn tend to lead to significant degradation of mechanical properties (i.e., hardness, strength, etc.) of the material. In addition, various impurities, which are typically segregated during solidification of the melt into the eutectic

colonies boundaries may also undergo volumetric structural changes (e.g., due to oxidation), leading to further degradation of mechanical properties (i.e., hardness, strength, etc.) of the material.

By contrast, preferred abrasive particles according to the present invention typically do not exhibit phase transformations of the eutectic phases when heated up to 1000° C. (in some cases even up to 1400° C.) in air, and thus are thermally stable. Although not wishing to be bound by any theory, it is believed that this thermal stability allows such abrasive particle to be incorporated into vitrified bonded abrasives.

The thermal stability of certain preferred abrasive particles according to the present invention may be measured or illustrated using a variety of different techniques, including: Differential Thermal Analysis (DTA), Thermogravimetric Analysis (TGA), X-ray diffraction, hardness measurements, microstructure analysis, color change, and interaction with glass bonds. The thermal stability of the abrasive articles may be dependent, for example, upon the composition, particle chemistry, and processing conditions.

For example, as disclosed above, the fused abrasive particles according to the present invention have a first average microhardness of at least 11 GPa (preferably, at least 12, 13, or 14 GPa, more preferably, at least 15 GPa, and even more preferably, at least 16 GPa, at least 17 GPa, or even at least 18 GPa), wherein the abrasive particles have a second average microhardness after being heated in air at 100° C. for 4 hours, and wherein the second average microhardness is at least 85% (preferably, at least 90%; more preferably, at least 95%; and even more preferably, about 100%) of the first average microhardness (see Example 3 (below) for a more complete description of the test).

The thermal stability of certain preferred abrasive particles according to the present invention may also be observed using Scanning Electron Microscopy (SEM), wherein the average microstructure (e.g., porosity, crystal structure, colony size and crystal size (eutectic crystals, and primary crystals, if present) and integrity of the abrasive particles is examined before and after being heated at 1000° C. in air for 4 hours. The microstructure of certain preferred abrasive particles according to the present invention are essentially the same before and after being heated at 1000° C. in air for 4 hours.

Further, the thermal stability of certain preferred abrasive particles according to the present invention may also be illustrated by comparing the color of the abrasive particles before and after they are heated at 1000° C. in air for 4 hours. The microstructure of preferred abrasive particles according to the present invention is essentially the same before and after being heated at 1000° C. in air for 4 hours.

The thermal stability of certain preferred abrasive particles according to the present invention may also be illustrated by comparing powder XRD result of the abrasive particles before and after they are heated at 1000° C. in air for 4 hours. As discussed above, when alumina-zirconia eutectic material is heated in air, typically at least a portion of the zirconia undergoes a tetragonal and/or cubic to monoclinic phase transformation. The effect of this phase transformation is typically significant enough to be observed via powder XRD. By contrast, the eutectic phases of certain preferred abrasive particles according to the present invention do not exhibit such phase transformations when heated to 1000° C. in air, hence no transformation of the eutectic phases will be observed in the XRD results.

Fused abrasive particles according to the present invention can be used in conventional abrasive products, such as

coated abrasive products, bonded abrasive products (including vitrified, resinoid, and metal bonded grinding wheels, cutoff wheels, mounted points, and honing stones), nonwoven abrasive products, and abrasive brushes. Typically, abrasive products (i.e., abrasive articles) include binder and abrasive particles, at least a portion of which is fused abrasive particles according to the present invention, secured within the abrasive product by the binder. Methods of making such abrasive products and using abrasive products are well known to those skilled in the art. Furthermore, fused abrasive particles according to the present invention can be used in abrasive applications that utilize abrasive particles, such as slurries of abrading compounds (e.g., polishing compounds), milling media, shot blast media, vibratory mill media, and the like.

Coated abrasive products generally include a backing, abrasive particles, and at least one binder to hold the abrasive particles onto the backing. The backing can be any suitable material, including cloth, polymeric film, fibre, nonwoven webs, paper, combinations thereof, and treated versions thereof. The binder can be any suitable binder, including an inorganic or organic binder (including thermally curable resins and radiation curable resins). The abrasive particles can be present in one layer or in two layers of the coated abrasive product.

An example of a coated abrasive product is depicted in FIG. 1. Referring to this figure, coated abrasive product **1** has a backing (substrate) **2** and abrasive layer **3**. Abrasive layer **3** includes fused abrasive particles according to the present invention **4** secured to a major surface of backing **2** by make coat **5** and size coat **6**. In some instances, a supersize coat (not shown) is used.

Bonded abrasive products typically include a shaped mass of abrasive particles held together by an organic, metallic, or vitrified binder. Such shaped mass can be, for example, in the form of a wheel, such as a grinding wheel or cutoff wheel. The diameter of grinding wheels typically is about 1 cm to over 1 meter; the diameter of cut off wheels about 1 cm to over 80 cm (more typically 3 cm to about 50 cm). The cut off wheel thickness is typically about 0.5 mm to about 5 cm, more typically about 0.5 mm to about 2 cm. The shaped mass can also be in the form, for example, of a honing stone, segment, mounted point, disc (e.g. double disc grinder) or other conventional bonded abrasive shape. Bonded abrasive products typically comprise about 3–50% by volume bond material, about 30–90% by volume abrasive particles (or abrasive particle blends), up to 50% by volume additives (including grinding aids), and up to 70% by volume pores, based on the total volume of the bonded abrasive product.

A preferred form is a grinding wheel. Referring to FIG. 2, grinding wheel **10** is depicted, which includes fused abrasive particles according to the present invention **11**, molded in a wheel and mounted on hub **12**.

Nonwoven abrasive products typically include an open porous lofty polymer filament structure having fused abrasive particles according to the present invention distributed throughout the structure and adherently bonded therein by an organic binder. Examples of filaments include polyester fibers, polyamide fibers, and polyaramid fibers. In FIG. 3, a schematic depiction, enlarged about 100×, of a typical nonwoven abrasive product is provided. Such a nonwoven abrasive product comprises fibrous mat **50** as a substrate, onto which fused abrasive particles according to the present invention **52** are adhered by binder **54**.

Useful abrasive brushes include those having a plurality of bristles unitary with a backing (see, e.g., U.S. Pat. No. 5,427,595 (Pihl et al.), U.S. Pat. No. 5,443,906 (Pihl et al.),

U.S. Pat. No. 5,679,067 (Johnson et al.), and U.S. Pat. No. 5,903,951 (Ionta et al.), the disclosure of which is incorporated herein by reference). Preferably, such brushes are made by injection molding a mixture of polymer and abrasive particles.

Suitable organic binders for making abrasive products include thermosetting organic polymers. Examples of suitable thermosetting organic polymers include phenolic resins, urea-formaldehyde resins, melamine-formaldehyde resins, urethane resins, acrylate resins, polyester resins, aminoplast resins having pendant α,β -unsaturated carbonyl groups, epoxy resins, acrylated urethane, acrylated epoxies, and combinations thereof. The binder and/or abrasive product may also include additives such as fibers, lubricants, wetting agents, thixotropic materials, surfactants, pigments, dyes, antistatic agents (e.g., carbon black, vanadium oxide, graphite, etc.), coupling agents (e.g., silanes, titanates, zircoaluminates, etc.), plasticizers, suspending agents, and the like. The amounts of these optional additives are selected to provide the desired properties. The coupling agents can improve adhesion to the abrasive particles and/or filler. The binder chemistry may thermally cured, radiation cured or combinations thereof. Additional details on binder chemistry may be found in U.S. Pat. No. 4,588,419 (Caul et al.), U.S. Pat. No. 4,751,137 (Tumey et al.), and U.S. Pat. No. 5,436,063 (Follett et al.), the disclosures of which are incorporated herein by reference.

More specifically with regard to vitrified bonded abrasives, vitreous bonding materials, which exhibit an amorphous structure and are typically hard, are well known in the art. In some cases, the vitreous bonding material includes crystalline phases. Bonded, vitrified abrasive products according to the present invention may be in the shape of a wheel (including cut off wheels), honing stone, mounted pointed or other conventional bonded abrasive shape. A preferred vitrified bonded abrasive product according to the present invention is a grinding wheel.

Examples of metal oxides that are used to form vitreous bonding materials include: silica, silicates, alumina, soda, calcia, potassia, titania, iron oxide, zinc oxide, lithium oxide, magnesia, boria, aluminum silicate, borosilicate glass, lithium aluminum silicate, combinations thereof, and the like. Typically, vitreous bonding materials can be formed from composition comprising from 10 to 100% glass frit, although more typically the composition comprises 20% to 80% glass frit, or 30% to 70% glass frit. The remaining portion of the vitreous bonding material can be a non-frit material. Alternatively, the vitreous bond may be derived from a non-frit containing composition. Vitreous bonding materials are typically matured at a temperature(s) in the range from about 700° C. to about 1500° C., usually in the range from about 800° C. to about 1300° C., sometimes in the range from about 900° C. to about 1200° C., or even in the range from about 950° C. to about 1100° C. The actual temperature at which the bond is matured depends, for example, on the particular bond chemistry.

Preferred vitrified bonding materials may include those comprising silica, alumina (preferably, at least 10 percent by weight alumina), and boria (preferably, at least 10 percent by weight boria). In most cases the vitrified bonding material further comprise alkali metal oxide(s) (e.g., Na₂O and K₂O) (in some cases at least 10 percent by weight alkali metal oxide(s)).

Binder materials may also contain filler materials or grinding aids, typically in the form of a particulate material. Typically, the particulate materials are inorganic materials. Examples of useful fillers for this invention include: metal

carbonates (e.g., calcium carbonate (e.g., chalk, calcite, marl, travertine, marble and limestone), calcium magnesium carbonate, sodium carbonate, magnesium carbonate), silica (e.g., quartz, glass beads, glass bubbles and glass fibers) silicates (e.g., talc, clays, (montmorillonite) feldspar, mica, calcium silicate, calcium metasilicate, sodium aluminosilicate, sodium silicate) metal sulfates (e.g., calcium sulfate, barium sulfate, sodium sulfate, aluminum sodium sulfate, aluminum sulfate), gypsum, vermiculite, wood flour, aluminum trihydrate, carbon black, metal oxides (e.g., calcium oxide (lime), aluminum oxide, titanium dioxide), and metal sulfites (e.g., calcium sulfite).

In general, the addition of a grinding aid increases the useful life of the abrasive product. A grinding aid is a material that has a significant effect on the chemical and physical processes of abrading, which results in improved performance. Although not wanting to be bound by theory, it is believed that a grinding aid(s) will (a) decrease the friction between the abrasive particles and the workpiece being abraded, (b) prevent the abrasive particles from "capping" (i.e., prevent metal particles from becoming welded to the tops of the abrasive particles), or at least reduce the tendency of abrasive particles to cap, (c) decrease the interface temperature between the abrasive particles and the workpiece, or (d) decreases the grinding forces.

Grinding aids encompass a wide variety of different materials and can be inorganic or organic based. Examples of chemical groups of grinding aids include waxes, organic halide compounds, halide salts and metals and their alloys. The organic halide compounds will typically break down during abrading and release a halogen acid or a gaseous halide compound. Examples of such materials include chlorinated waxes like tetrachloronaphthalene, pentachloronaphthalene, and polyvinyl chloride. Examples of halide salts include sodium chloride, potassium cryolite, sodium cryolite, ammonium cryolite, potassium tetrafluoroborate, sodium tetrafluoroborate, silicon fluorides, potassium chloride, and magnesium chloride. Examples of metals include, tin, lead, bismuth, cobalt, antimony, cadmium, and iron titanium. Other miscellaneous grinding aids include sulfur, organic sulfur compounds, graphite, and metallic sulfides. It is also within the scope of the present invention to use a combination of different grinding aids, and in some instances this may produce a synergistic effect. The preferred grinding aid is cryolite; the most preferred grinding aid is potassium tetrafluoroborate.

Grinding aids can be particularly useful in coated abrasive and bonded abrasive products. In coated abrasive products, grinding aid is typically used in the supersize coat, which is applied over the surface of the abrasive particles. Sometimes, however, the grinding aid is added to the size coat. Typically, the amount of grinding aid incorporated into coated abrasive products are about 50–300 g/m² (preferably, about 80–160 g/m²). In vitrified bonded abrasive products grinding aid is typically impregnated into the pores of the product.

The abrasive products can contain 100% fused abrasive particles according to the present invention, or blends of such abrasive particles with other abrasive particles and/or diluent particles. However, at least about 2% by weight, preferably at least about 5% by weight, and more preferably about 30–100% by weight, of the abrasive particles in the abrasive products should be abrasive particles according to the present invention. In some instances, the abrasive particles according the present invention may be blended with another abrasive particles and/or diluent particles at a ratio between 5 to 75% by weight, about 25 to 75% by weight

about 40 to 60% by weight, or about 50% to 50% by weight (i.e., in equal amounts by weight). Examples of suitable conventional abrasive particles include fused aluminum oxide (including white fused alumina, heat-treated aluminum oxide and brown aluminum oxide), silicon carbide, boron carbide, titanium carbide, diamond, cubic boron nitride, garnet, fused alumina-zirconia, and sol-gel-derived abrasive particles, and the like. The sol-gel-derived abrasive particles may be seeded or non-seeded. Likewise, the sol-gel-derived abrasive particles may be randomly shaped or have a shape associated with them, such as a rod or a triangle. Examples of sol gel abrasive particles include those described U.S. Pat. No. 4,314,827 (Leitheiser et al.), U.S. Pat. No. 4,518,397 (Leitheiser et al.), U.S. Pat. No. 4,623,364 (Cottringer et al.), U.S. Pat. No. 4,744,802 (Schwabel), U.S. Pat. No. 4,770,671 (Monroe et al.), U.S. Pat. No. 4,881,951 (Wood et al.), U.S. Pat. No. 5,011,508 (Wald et al.), U.S. Pat. No. 5,090,968 (Pellow), U.S. Pat. No. 5,139,978 (Wood), U.S. Pat. No. 5,201,916 (Berg et al.), U.S. Pat. No. 5,227,104 (Bauer), U.S. Pat. No. 5,366,523 (Rowenhorst et al.), U.S. Pat. No. 5,429,647 (Larmie), U.S. Pat. No. 5,498,269 (Larmie), and U.S. Pat. No. 5,551,963 (Larmie), the disclosures of which are incorporated herein by reference. Additional details concerning sintered alumina abrasive particles made by using alumina powders as a raw material source can also be found, for example, in U.S. Pat. No. 5,259,147 (Falz), U.S. Pat. No. 5,593,467 (Monroe), and U.S. Pat. No. 5,665,127 (Moltgen), the disclosures of which are incorporated herein by reference. In some instances, blends of abrasive particles may result in an abrasive article that exhibits improved grinding performance in comparison with abrasive articles comprising 100% of either type of abrasive particle.

If there is a blend of abrasive particles, the abrasive particle types forming the blend may be of the same size. Alternatively, the abrasive particle types may be of different particle sizes. For example, the larger sized abrasive particles may be abrasive particles according to the present invention, with the smaller sized particles being another abrasive particle type. Conversely, for example, the smaller sized abrasive particles may be abrasive particles according to the present invention, with the larger sized particles being another abrasive particle type.

Examples of suitable diluent particles include marble, gypsum, flint, silica, iron oxide, aluminum silicate, glass (including glass bubbles and glass beads), alumina bubbles, alumina beads and diluent agglomerates. Fused abrasive particles according to the present invention can also be combined in or with abrasive agglomerates. Abrasive agglomerate particles typically comprise a plurality of abrasive particles, a binder, and optional additives. The binder may be organic and/or inorganic. Abrasive agglomerates may be randomly shape or have a predetermined shape associated with them. The shape may be a block, cylinder, pyramid, coin, square, or the like. Abrasive agglomerate particles typically have particle sizes ranging from about 100 to about 5000 micrometers, typically about 250 to about 2500 micrometers. Additional details regarding abrasive agglomerate particles may be found, for example, in U.S. Pat. No. 4,311,489 (Kressner), U.S. Pat. No. 4,652,275 (Bloecher et al.), U.S. Pat. No. 4,799,939 (Bloecher et al.), U.S. Pat. No. 5,549,962 (Holmes et al.), and U.S. Pat. No. 5,975,988 (Christianson), the disclosures of which are incorporated herein by reference.

The abrasive particles may be uniformly distributed in the abrasive article or concentrated in selected areas or portions of the abrasive article. For example, in a coated abrasive,

there may be two layers of abrasive particles. The first layer comprises abrasive particles other than abrasive particles according to the present invention, and the second (outermost) layer comprises abrasive particles according to the present invention. Likewise in a bonded abrasive, there may be two distinct sections of the grinding wheel. The outermost section may comprise abrasive particles according to the present invention, whereas the innermost section does not. Alternatively, abrasive particles according to the present invention may be uniformly distributed throughout the bonded abrasive article.

Further details regarding coated abrasive products can be found, for example, in U.S. Pat. No. 4,734,104 (Broberg), U.S. Pat. No. 4,737,163 (Larkey), U.S. Pat. No. 5,203,884 (Buchanan et al.), U.S. Pat. No. 5,152,917 (Pieper et al.), U.S. Pat. No. 5,378,251 (Culler et al.), U.S. Pat. No. 5,417,726 (Stout et al.), U.S. Pat. No. 5,436,063 (Follett et al.), U.S. Pat. No. 5,496,386 (Broberg et al.), U.S. Pat. No. 5,609,706 (Benedict et al.), U.S. Pat. No. 5,520,711 (Helmin), U.S. Pat. No. 5,954,844 (Law et al.), U.S. Pat. No. 5,961,674 (Gagliardi et al.), and U.S. Pat. No. 5,975,988 (Christinason), the disclosures of which are incorporated herein by reference. Further details regarding bonded abrasive products can be found, for example, in U.S. Pat. No. 4,543,107 (Rue), U.S. Pat. No. 4,741,743 (Narayanan et al.), U.S. Pat. No. 4,800,685 (Haynes et al.), U.S. Pat. No. 4,898,597 (Hay et al.), U.S. Pat. No. 4,997,461 (Markhoff-Matheny et al.), U.S. Pat. No. 5,038,453 (Narayanan et al.), U.S. Pat. No. 5,110,332 (Narayanan et al.), and U.S. Pat. No. 5,863,308 (Qi et al.) the disclosures of which are incorporated herein by reference. Further, details regarding vitreous bonded abrasives can be found, for example, in U.S. Pat. No. 4,543,107 (Rue), U.S. Pat. No. 4,898,597 (Hay), U.S. Pat. No. 4,997,461 (Markhoff-Matheny et al.), U.S. Pat. No. 5,094,672 (Giles et al.), U.S. Pat. No. 5,118,326 (Sheldon et al.), U.S. Pat. No. 5,131,926 (Sheldon et al.), U.S. Pat. No. 5,203,886 (Sheldon et al.), U.S. Pat. No. 5,282,875 (Wood et al.), U.S. Pat. No. 5,738,696 (Wu et al.), and U.S. Pat. No. 5,863,308 (Qi), the disclosures of which are incorporated herein by reference. Further details regarding nonwoven abrasive products can be found, for example, in U.S. Pat. No. 2,958,593 (Hoover et al.), the disclosure of which is incorporated herein by reference.

Methods for abrading with abrasive particles according to the present invention range from snagging (i.e., high pressure high stock removal) to polishing (e.g., polishing medical implants with coated abrasive belts), wherein the latter is typically done with finer grades (e.g., less ANSI 220 and finer) of abrasive particles. The abrasive particle may also be used in precision abrading applications, such as grinding cam shafts with vitrified bonded wheels. The size of the abrasive particles used for a particular abrading application will be apparent to those skilled in the art.

Abrading with abrasive particles according to the present invention may be done dry or wet. For wet abrading, the liquid may be introduced supplied in the form of a light mist to complete flood. Examples of commonly used liquids include: water, water-soluble oil, organic lubricant, and emulsions. The liquid may serve to reduce the heat associated with abrading and/or act as a lubricant. The liquid may contain minor amounts of additives such as bactericide, antifoaming agents, and the like.

Abrasive particles according to the present invention may be used to abrade workpieces such as aluminum metal, carbon steels, mild steels, tool steels, stainless steel, hardened steel, titanium, glass, ceramics, wood, wood like materials, paint, painted surfaces, organic coated surfaces

and the like. The applied force during abrading typically ranges from about 1 to about 100 kilograms.

EXAMPLES

This invention is further illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention. Various modifications and alterations of the present invention will become apparent to those skilled in the art. All parts and percentages are by weight unless otherwise indicated.

Example 1

A polyethylene bottle was charged with 187.2 grams of alumina powder (obtained under the trade designation "APA-0.5" from Condea Vista, Tucson, Ariz.), 112.9 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 0.6 gram of a dispersing agent (obtained under the trade designation "DURAMAX D-30005" from Rohm and Haas Company, Dear Park, Tex.), and 100.4 grams of distilled water. The powders were present in amounts to provide 78.6 mole % Al_2O_3 and 21.4 mole % Y_2O_3 . About 450 grams of alumina milling media (10 mm diameter; 99.9% alumina; obtained from Union Process, Akron, Ohio.) were added to the bottle, and the mixture was milled for 4 hours to thoroughly mix the ingredients. After the milling, the milling media were removed and the slurry was poured onto a glass ("PYREX") pan where it was dried using a heat-gun held approximately 46 cm (18 inches) above the pan. The pan was slowly oscillated while drying to prevent the settling of the powder prior to complete drying. After drying with the heat-gun, the pan was placed in a drying oven for an additional 30 minutes at 90° C. to more completely dry the material. The dried powder bed was then scored with a spatula and scraped from the pan to form small flakes of material. Each flake weighed about 0.5 to 3 grams. The flakes were calcined in air by heating them to 670° C. at rate of about 1° C./min., and then holding them at 670° C. for 1 hour, after which the power to the furnace power was shut-off, and the furnace allowed to cool back to room temperature.

Several of the calcined flakes were melted in an arc discharge furnace (Model No. 1-VAMF-20-22-45; from Advanced Vacuum Systems, Ayer, Mass.). About 15 grams of the calcined flakes were placed on the chilled copper plate located inside a furnace chamber. The furnace chamber was evacuated and then backfilled with Argon gas at a 260 torr pressure. An arc was struck between an electrode and a plate. The temperatures generated by the arc discharge were high enough to quickly melt the calcined flakes. After melting was complete, the material was maintained in a molten state for about 30 seconds to homogenize the melt. The resultant melt was rapidly cooled by shutting off the arc and allowing the melt to cool on its own. Rapid cooling was ensured by small mass of a sample and a large heat sinking capability of a chilled copper plate. The fused material was removed from the furnace within one minute after the power to the furnace was turned off. Although not wanting to be bound by theory, it is estimated that the cooling rate of the melt on the surface of the water chilled copper plate was 1500° C./min. The fused material was white-green in color.

FIG. 8 is a scanning electron microscope (SEM) photomicrograph of a polished section of fused Example 1 material. The polished section was prepared using conventional mounting and polishing techniques. Polishing was done

using a polisher (obtained from Buehler of Lake Bluff, Ill. under the trade designation "ECOMET 3 TYPE POLISHER-GRINDER"). The sample was polished for about 3 minutes with a diamond wheel, followed by three minutes of polishing with each of 45, 30, 15, 9, and 3 micrometer diamond slurries. The polished sample was coated with a thin layer of gold-palladium and viewed using JEOL SEM (Model JSM 840A). Referring again to FIG. 8, the photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 1 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 1 micrometer.

Example 1 fused material was crushed by using a "Chipmunk" jaw crusher (Type VD, manufactured by BICO Inc., Burbank, Calif.) into (abrasive) particles and graded to retain the -25+30 and -30+35 mesh fractions (USA Standard Testing Sieves). These two mesh fractions were combined to provide a 50/50 blend. Thirty grams of the 50/50 blend of -25+30 and -30+35 mesh fractions were incorporated into a coated abrasive disc. The coated abrasive disc was made according to conventional procedures. The fused abrasive particles were bonded to 17.8 cm diameter, 0.8 mm thick vulcanized fiber backings (having a 2.2 cm diameter center hole) using a conventional calcium carbonate-filled phenolic make resin (48% resole phenolic resin, 52% calcium carbonate, diluted to 81% solids with water and glycol ether) and a conventional cryolite-filled phenolic size resin (32% resole phenolic resin, 2% iron oxide, 66% cryolite, diluted to 78% solids with water and glycol ether). The wet make resin weight was about 185 g/m². Immediately after the make coat was applied, the fused abrasive particles were electrostatically coated. The make resin was precured for 120 minutes at 88° C. Then the cryolite-filled phenolic size coat was coated over the make coat and abrasive particles. The wet size weight was about 850 g/m². The size resin was cured for 12 hours at 99° C. The coated abrasive disc was flexed prior to testing.

The average microhardnesses of Example 1 abrasive particles were measured by mounting loose abrasive particles (about 10 mesh in size) in mounting resin (obtained under the trade designation "EPOMET" from Buehler Ltd., Lake Bluff, Ill.). The resulting cylinder of resin was about 2.5 cm (1 inch) in diameter and about 1.9 cm (0.75 inch) tall. The mounted samples were polished using a conventional grinder/polisher (obtained under the trade designation "EPOMET" from Buehler Ltd.) and conventional diamond slurries with the final polishing step using a 1 micrometer diamond slurry (obtained under the trade designation "METADI" from Buehler Ltd.) to obtain polished cross-sections of the sample.

The microhardness measurements were made using a conventional microhardness tester (obtained under the trade designation "MITUTOYO MVK-VL" from Mitutoyo Corporation, Tokyo, Japan) fitted with a Vickers indenter using a 500-gram indent load. The microhardness measurements were made according to the guidelines stated in ASTM Test Method E384 Test Methods for Microhardness of Materials (1991), the disclosure of which is incorporated herein by reference. The microhardness values were an average of 20 measurements. The average microhardness was 16.2 GPa.

Several Example 1 abrasive particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour,

held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was the same as before heating (i.e., white-green). The average microhardness of the abrasive particles after heating was 16.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Several Example 1 abrasive particles were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was the same as before heating (i.e., white-green). The average microhardness of the abrasive particles after heating was 16.0 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Comparative Example A

The Comparative Example A coated abrasive disc was prepared as described in Example 1 except heat-treated fused alumina abrasive particles (obtained under the trade designation "ALODUR BFRPL" from Triebacher, Villach, Austria) was used in place of the Example 1 fused abrasive particles.

Comparative Example B

The Comparative Example B coated abrasive disc was prepared as described in Example 1 except alumina-zirconia abrasive particles (having a eutectic composition of 53% Al_2O_3 and 47% ZrO_2 ; obtained under the trade designation "NORZON" from Norton Company, Worcester, Mass.) was used in place of the Example 1 fused abrasive particles.

The average microhardness of Comparative Example B abrasive particles was determined, as described above in Example 1, to be 16.0 GPa. The color of the Comparative Example B abrasive particles was gray-navy blue.

Several Comparative Example B abrasive particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was beige. The average microhardness of the abrasive particles after heating was 12.9 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. An SEM photomicrograph a Comparative Example B abrasive particle before heating is shown in FIG. 11. An SEM photomicrograph a Comparative Example B abrasive particle after heating is shown in FIG. 12. The microstructure observed after heating was different than that observed before heating. The differences were observed most predominately at the colony boundaries.

Further powder x-ray diffraction (using a Phillips XRG 3100 x-ray diffractometer with copper K α radiation of 1.54050 Angstrom) was used to qualitatively measure the phases present in Comparative Example B abrasive particles before and after the above described heat-treatment by comparing the peak intensities of 111 of cubic and/or tetragonal reflection at about $2\theta=30$ degrees, to that of 11 $\bar{1}$ of monoclinic reflection at about $2\theta=28$ degrees. For reference see "Phase Analysis in Zirconia Systems," Garvie, R. C. and

Nicholson, P. S., Journal of the American Ceramic Society, vol 55 (6), pp. 303-305, 1972, the disclosure of which is incorporated herein by reference. The samples were ground and -120 mesh powders used for analysis. The unheat-treated Comparative Example B abrasive particles contained both the monoclinic and cubic and/or tetragonal zirconia phases. For the heat-treated sample, a decrease in the cubic and/or tetragonal phase content with a corresponding increase in monoclinic phase content was observed.

Several Comparative Example B abrasive particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was beige. The average microhardness of the abrasive particles after heating was 12.8 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. An SEM photomicrograph a Comparative Example B abrasive particle after heating is shown in FIG. 13. The microstructure observed after heating was different than that observed before heating. The differences, which were greater than those observed for the heat-treatment at 1000° C. for 4 hours, were again observed most predominately at the colony boundaries.

The effect of two vitrified bonding materials on Comparative Example B abrasive particles were evaluated as follows. A first vitrified bond material was prepared by charging a plastic jar (3/8 inches (11.1 cm) in diameter; 3/8 inches (11.1 cm) in height) with 70 parts of a glass frit (37.9% SiO₂, 28.5% B₂O₃, 15.6% Al₂O₃, 13.9% Na₂O, and 4.1% K₂O; obtained under the trade designation "FERRO FRIT 3227" from Ferro Corporation, Cleveland, Ohio.), 27 parts of Kentucky Ball Clay (No 6DC; obtained from Old Hickory Clay Company, Hickory, Ky.), 3.5 parts of Li₂CO₃ (obtained from Alfa Aesar Chemical Company, Ward Hill, Mass.), 3 parts CaSiO₃ (obtained from Alfa Aesar Chemical Company), and 625 grams of 1.3 cm (0.5 inch) diameter plastic coated steel media, and then dry milling the contents at 90 rpm for 7 hours. The composition was formulated to provide a vitrified bond material comprising about 45% SiO₂, about 19% Al₂O₃, about 20% B₂O₃, about 10% Na₂O, about 3% K₂O, about 1.5% Li₂O, and about 1.5% CaO. The dry milled material and Comparative Example B abrasive particles were pressed into a 3.2 cm×0.6 cm (1.25 inch×0.25 inch) pellet. The pellet was heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The pellet was prepared by mixing, in order, 20 parts of Comparative Example B abrasive particles (-20+30 mesh), 0.24 part of hydrolyzed starch (obtained under the trade designation "DEXTRIN" from Aldrich Chemical Company, Milwaukee, Wis.), 0.02 part glycerine (obtained from Aldrich Chemical Company), 0.72 part water, 3.14 parts of the dry milled material, and 0.4 part of hydrolyzed starch ("DEXTRIN"). The pellet was pressed under a load of 2273 kilograms (5000 lbs.). The average microhardness of the abrasive particles after heating in the vitrified bonding material was 13.6 GPa, although some of the Comparative Example B abrasive particles exhibit such severe degradation that microhardness measurements could not be effectively made (portions of the particles were too weak). There was variability in the color of the heat-treated abrasive particles, although the majority of the particles were beige. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. An SEM photomicrograph a Comparative Example B abrasive particle after heating is shown in FIG. 14. The microstruc-

ture observed after heating was different than that observed before heating. The differences, which were greater than those observed for the heat-treatment at 1000° C. for 4 hours, were again observed most predominately at the colony boundaries.

A second vitrified bond material was prepared by charging a plastic jar (4 3/8 inches (11.1 cm) in diameter; 4 3/8 inches (11.1 cm) in height) with 45 parts of Kentucky Ball Clay (No. 6DC; obtained from Old Hickory Clay Company), 28 parts of anhydrous sodium tetraborate (obtained from Alfa Aesar Chemical Company), 25 parts of feldspar (obtained under the trade designation "G-200 Feldspar" from Feldspar Corporation, Atlanta, Ga.), 3.5 parts of Li₂CO₃ (obtained from Alfa Aesar Chemical Company), 2.5 parts of CaSiO₃ (obtained from Alfa Aesar Chemical Company), and 625 grams of 1.3 cm (0.5 inch) diameter plastic coated steel media, and then dry milling the contents at 90 rpm for 7 hours. The composition was formulated to provide a vitrified bond material comprising about 45% SiO₂, about 19% Al₂O₃, about 20% B₂O₃, about 10% Na₂O, about 3% K₂O, about 1.5% Li₂O, and about 1.5% CaO. The dry milled material and Comparative Example B abrasive particles were pressed into a 3.2 cm×0.6 cm (1.25 inch×0.25 inch) pellet. The pellet was heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The pellet was prepared by mixing, in order, 20 parts of Comparative Example B abrasive particles (-20+30 mesh), 0.24 part of hydrolyzed starch ("DEXTRIN"), 0.02 part glycerine (obtained from Aldrich Chemical Company), 0.72 part water, 3.14 parts of the dry milled material, and 0.4 part of hydrolyzed starch ("DEXTRIN"). The pellet was pressed under a load of 2273 kilograms (5000 lbs.). The average microhardness of the abrasive particles after heating in the vitrified bonding material was 13.4 GPa, although some of the Comparative Example B abrasive particles exhibit such severe degradation that microhardness measurements could not be effectively made (portions of the particles were too weak). There was variability in the color of the heat-treated abrasive particles, although the majority of the particles were beige. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was different than that observed before heating. The differences, which were greater than those observed for the heat-treatment at 1000° C. for 4 hours, were again observed most predominately at the colony boundaries.

Comparative Example C

The Comparative Example C coated abrasive disc was prepared as described in Example 1 except sol-gel-derived abrasive particles (commercially available under the trade designation "321 CUBITRON" from the 3M Company, St. Paul, Minn.) was used in place of the Example 1 fused abrasive particles.

Grinding Performance of Example 1 and Comparative Examples A-C

The grinding performance of Example 1 and Comparative Examples A-C coated abrasive discs were evaluated as follows. Each coated abrasive disc was mounted on a beveled aluminum back-up pad, and used to grind the face of a pre-weighed 1.25 cm×18 cm×10 cm 1018 mild steel workpiece. The disc was driven at 5,000 rpm while the portion of the disc overlaying the beveled edge of the back-up pad contacted the workpiece at a load of 8.6

kilograms. Each disc was used to grind individual workpiece in sequence for one-minute intervals. The total cut was the sum of the amount of material removed from the workpieces throughout the test period. The total cut by each sample after 12 minutes of grinding as well as the cut at 12th minute (i.e., the final cut) are reported in Table 1, below.

TABLE 1

Example	Total cut, g	Final cut, g
Comp. A	418	23
Comp. B	621	48
Comp. C	859	75
1	732	56

Example 2

Example 2 fused material and abrasive particles were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 173 grams of alumina powder (“APA-0.5”), 19.3 grams of magnesium oxide powder (obtained under the trade designation “MAGCHEM 10-325” from Martin Marietta Magnesia Specialties, Hunt Valley, Md.), 107.8 grams of yttrium oxide powder obtained from H. C. Starck, Newton, Mass.), 0.6 gram of a dispersing agent (“DURAMAX D-30005”), and 137.4 grams of distilled water, and (b) the powders were present in amounts to provide 64 mole % Al_2O_3 , 18 mole % MgO , and 18 mole % Y_2O_3 . The fused material was white in color.

FIG. 9 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 2 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies are about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 2 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Y}_3\text{Al}_5\text{O}_{12}$, and the dark portions a crystalline Al_2O_3 -rich spinel solid solution phase. The width of these phases observed in the polished section were up to about 2 micrometer.

Comparative Example D

Comparative Example D fused material and abrasive particles were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 149.5 grams of alumina powder (“APA-0.5”), 149.4 grams of yttria-stabilized zirconia oxide powder (with a nominal composition of 94 wt % ZrO_2 (+ HfO_2) and 5.4 wt % Y_2O_3 ; obtained under the trade designation “HSY 3.0” from Zirconia Sales, Inc. of Marietta, Ga.), 0.6 gram of a dispersing agent (“DURAMAX D-30005”), and 136.5 grams of distilled water, and (b) the powders were present in amounts to provide 54.8 mole % Al_2O_3 and 45.2 mole % ZrO_2 . The fused material was white in color.

FIG. 10 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Comparative Example D material. The photomicrograph shows a eutectic derived microstructure comprising a plurality of colonies. The colonies were about 5–40 micrometers in size. Based on powder x-ray diffraction of a portion of Comparative Example D material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline ZrO_2 , and the dark

portions $\alpha\text{-Al}_2\text{O}_3$. The widths of these phases observed in the polished section were up to about 0.5 micrometer.

The average microhardness of Comparative Example D was determined, as described above in Example 1, to be 15.3 GPa.

Several Comparative Example D particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was white. The average microhardness of the abrasive particles after heating was 15.0 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. An SEM photomicrograph Comparative Example D material before heating is shown in FIG. 15. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Further powder x-ray diffraction, as described above for Comparative Example B, was used to qualitatively measure the phases present in Comparative Example D material before and after the above described heat-treatment by comparing the peak intensities of 111 of cubic and/or tetragonal reflection at about $2\theta=30$ degrees, to that of 111 of monoclinic reflection at about $2\theta=28$ degrees. The unheated Comparative Example D material contained predominantly cubic and/or tetragonal zirconia before and after the heat-treatment (i.e., there was no significant difference noted in the x-ray diffraction results).

Several Comparative Example D particles were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was white. The average microhardness of the abrasive particles after heating was 15.0 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was only slightly different than that observed before heating. An SEM photomicrograph Comparative Example D after heating is shown in FIG. 16. There was some cracks observed in the heat-treated material, generally near primary crystals of ZrO_2 .

Differential Thermal Analysis (DTA) And Thermogravimetric Analysis (TGA) of Example 1 and Comparative Example B and D Abrasive Particles/Materials

Differential thermal analysis (DTA) and thermogravimetric analysis (TGA) were conducted for each of Example 1 and Comparative Example B and D abrasive particles/materials. Each material was crushed with a mortar and pestle and screened to retain particles that were in the 400–500 micrometer size range.

DTA/TGA runs were made (using an instrument obtained from Netzsch Instruments, Selb, Germany under the trade designation “NETZSCH STA 409 DTA/TGA”) for each of the screened samples. The amount of each screened sample placed in the 100 microliter Al_2O_3 sample holder was 129.5 micrograms (Example 1), 125.8 micrograms (Comparative Example D), 127.3 micrograms (Comparative Example B), respectively. Each sample was heated in static air at a rate of 10° C./minute from room temperature (about 25° C.) to 1300° C.

Referring to FIG. 5, line 157 is the plotted DTA data for the Example 1 material; line 159, the plotted TGA data.

Referring to FIG. 6, line 177 is the plotted DTA data for the Comparative Example D material; line 179, the plotted TGA data. Referring to FIG. 7, line 187 is the plotted DTA data for the Comparative Example B material; line 189, the plotted TGA data. The change in weight of the sample through the TGA run was, for Example 1, 0.22%; for Comparative Example D, 0.73%; and, for Comparative Example B, 1.16%.

Example 3

Example 3 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 171.6 grams of alumina powder ("APA-0.5"), 83.4 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 45 grams of zirconium oxide powder (with a nominal composition of 100 wt % ZrO_2 (+HfO₂); obtained under the trade designation "DK-2" from Zirconia Sales, Inc. of Marietta, Ga.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 100 grams of distilled water. The fused material was white-red in color.

FIGS. 17 and 18 are scanning electron microscope (SEM) photomicrographs of a polished section (prepared as described in Example 1) of fused Example 3 material. Referring to FIGS. 17 and 18, the photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. Based on powder x-ray diffraction of a portion of Example 3 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline cubic ZrO_2 , the gray portions crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 3 micrometers. Eutectic phases making up the colonies were in a lamellar arrangement. The alumina phases were seen as crystals exhibiting a trigonal shape. The orientation of at least a portion of the lamellar (i.e. orientation of eutectic crystallization) was observed to follow the orientation of the alumina in trigonal outline which was evident by an approximately 120 degree angle at which adjacent lamellar run into each other. While not wishing to be bounded by theory, it is believed that during crystallization of the melt of a composition at or near ternary eutectic, primary alumina crystallized first as a seed in a trigonal shape. The consequent coupled growth of eutectic in the form of lamellar followed, at least initially, the orientation of the seed. A eutectic colony then included alumina seeds of the same orientation (or a single seed) together with the eutectic lamellar growth. Further, it was observed that the colony boundaries did not exhibit phase coarsening as was observed in the binary eutectic (manifested by the significant coarsening of crystals of eutectic phases in an immediate vicinity of colony boundary) of Example 1.

The average microhardness of Example 3 was determined, as described above in Example 1, to be 16.5 GPa.

Several Example 3 particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was white. The average microhardness of the Example 3 particles after heating was 16.7 GPa.

Grinding Performance of Example 3 and Comparative Examples A–C

The grinding performance of Example 3 and Comparative Examples A–C coated abrasive discs were evaluated as

described above for Example 1 and Comparative Examples A–C. The results are reported in Table 2, below.

TABLE 2

Example	Total cut, g	Final cut, g
Comp. A	424	24
Comp. B	614	45
Comp. C	940	79
3	711	58

Example 4

Example 4 fused material and abrasive particles were prepared as described in Example 1, except the polyethylene bottle was charged with 181.7 grams of alumina powder ("APA-0.5"), 88.3 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 30 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 100 grams of distilled water.

FIG. 19 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 4 material. Referring to FIG. 19, the photomicrograph shows a ternary eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 4 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline cubic ZrO_2 , the gray portions crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 5 micrometer. Further, large primary crystals (believed to be Al_2O_3 and $Y_3Al_5O_{12}$), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition.

Example 5

Example 5 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 141.3 grams of alumina powder ("APA-0.5"), 68.7 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 90 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 100 grams of distilled water.

FIG. 20 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 5 material. Referring to FIG. 20, the photomicrograph shows a ternary eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 5 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline cubic ZrO_2 , the gray portions crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 5 micrometers. Further, large primary crystals (believed to be ZrO_2), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition.

Example 6

Example 6 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with

191.8 grams of alumina powder ("APA-0.5"), 93.2 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 15 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 100 grams of distilled water.

FIG. 21 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 6 material. Referring to FIG. 21, the photomicrograph shows a binary eutectic-derived microstructure. Based on powder x-ray diffraction of a portion of Example 6 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline cubic ZrO_2 , the gray portions crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 10 micrometers. Further, large primary crystals (believed to be ZrO_2) were observed between crystals of Al_2O_3 and $Y_3Al_5O_{12}$, indicating that deviation of the composition from an exact eutectic composition is quite large.

Example 7

Example 7 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 201.9 grams of alumina powder ("APA-0.5"), 88.3 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 9.8 grams of neodymium oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 100 grams of distilled water.

FIG. 22 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 7 material. Referring to FIG. 22, the photomicrograph shows a eutectic-derived microstructure. Based on powder x-ray diffraction of a portion of Example 7 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were Nd-rich phase, the gray portions crystalline yttrium aluminum garnet with some yttrium substituted by neodymium, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 10 micrometers.

Example 8

Example 8 fused material was prepared as described in Example 1, except (a) the polyethylene bottle was charged with 201.9 grams of alumina powder ("APA-0.5") and 98.1 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), and (b) the powders were present in amounts to provide 82 mole % Al_2O_3 and 18 mole % Y_2O_3 .

FIG. 23 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 8 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 8 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $Y_3Al_5O_{12}$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 1 micrometer.

Grinding Performance of Example 8 and Comparative Examples A–C

The grinding performance of Example 8 and Comparative Examples A–C coated abrasive discs were evaluated as

described above for Example 1 and Comparative Examples A–C. The results are reported in Table 3, below.

TABLE 3

Example	Total cut, g	Final cut, g
Comp. A	431	25
Comp. B	674	50
Comp. C	933	78
8	787	56

Example 9

Example 9 fused material, abrasive particles, and discs were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 242.5 grams of alumina powder ("APA-0.5"), 257.5 grams of gadolinium oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 150.6 grams of distilled water, and (b) the powders were present in amounts to provide 77 mole % Al_2O_3 and 23 mole % Gd_2O_3 . The fused material was white-yellow in color.

FIG. 24 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 9 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–20 micrometers in size. Based on powder x-ray diffraction of a portion of Example 9 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $GdAlO_3$, and the dark portions $\alpha-Al_2O_3$. The widths of these phases observed in the polished section were up to about 0.7 micrometer. It is also noted that there were many pores observed in the fused material.

Example 10

Example 10 fused material, abrasive particles, and discs were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 145.6 grams of alumina powder ("APA-0.5"), 151.2 grams of lanthanum oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 129.5 grams of distilled water, and (b) the powders were present in amounts to provide 75 mole % Al_2O_3 and 25 mole % La_2O_3 . The fused material was white-red in color; although some of the abrasive particles were redder than others.

FIG. 25 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 10 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. Based on powder x-ray diffraction of a portion of Example 10 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $LaAlO_3$, and the dark portions crystalline $LaAl_{11}O_{18}$. The widths of these phases observed in the polished section were up to about 0.5 micrometer. Further, large primary crystals (believed to be $LaAlO_3$), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a La_2O_3 rich composition.

The average microhardness of Example 10 abrasive particles was determined, as described above in Example 1,

except Example 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 abrasive particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellet. The average microhardness of Example abrasive particles was 15.0 GPa.

Differential thermal analysis (DTA) and thermogravimetric analysis (TGA) were conducted for Example 10 material as described for of Example 1 and Comparative Example B and D abrasive particles/materials. Referring to FIG. 31, line 167 is the plotted DTA data for the Example 10 material; line 169, the plotted TGA data. The change in weight of the sample through the TGA run was 0.22%.

Several Example 10 abrasive particles (together with Example 11 and 12 abrasive particles) were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 10 abrasive particles after heating was the same as before heating (i.e., white-red). The average microhardness of the Example 10 abrasive particles after heating was 14.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 10 abrasive particles after heating was substantially the same as the microstructure observed before heating.

Several Example 10 abrasive particles (together with Example 11 and 12 abrasive particles) were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 10 abrasive particles after heating was the same as before heating (i.e., white-red). The average microhardness of the Example abrasive particles after heating was 14.3 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 10 abrasive particles after heating was substantially the same as the microstructure observed before heating.

The effect of two vitrified bonding materials on Example 10 abrasive particles were evaluated as described for Comparative Example B, except Example 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 abrasive particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellets. The polished cross-sections were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating. The color of the Example 10 abrasive particles after heating with the vitrified bonding material was the same as before heating (i.e., white-red).

Example 11

Example 11 fused material, abrasive particles, and discs were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 143.6 grams of alumina powder ("APA-0.5"), 147.6 grams of neodymium oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 138.5 grams of distilled water, and (b) the powders were present in amounts to provide 75 mole % Al_2O_3 and 25 mole % Nd_2O_3 . The fused material was white-blue in color; although some of the abrasive particles were bluer than others.

FIG. 26 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 11 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 10–40 micrometers in size. Based on powder x-ray diffraction of a portion of Example 11 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline NdAlO_3 , and the dark portions crystalline $\text{NdAl}_{11}\text{O}_{18}$. The widths of these phases observed in the polished section were up to about 0.5 micrometer. Further, large primary crystals (believed to be NdAlO_3), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a Nd_2O_3 rich composition.

The average microhardness of Example 11 abrasive particles was determined, as described above in Example 1, except Example 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 abrasive particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellet. The average microhardness of Example 11 abrasive particles was to be 14.5 GPa.

Several Example 11 abrasive particles (together with Example 10 and 12 abrasive particles) were heated placed in a platinum crucible and heated to 1000° C. at 15 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 11 abrasive particles after heating was the same as before heating (i.e., white-blue). The average microhardness of the Example 11 abrasive particles after heating was 14.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 11 abrasive particles after heating was substantially the same as the microstructure observed before heating.

Several Example 11 abrasive particles (together with Example 10 and 12 abrasive particles) were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 11 abrasive particles after heating was the same as before heating (i.e., white-blue). The average microhardness of the Example 11 abrasive particles after heating was 14.5 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 11 abrasive particles after heating was substantially the same as the microstructure observed before heating.

The effect of two vitrified bonding materials on Example 11 abrasive articles were evaluated as described in Comparative Example B, except 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 abrasive particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellets. The polished cross-sections were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating. The color of the Example 11 abrasive particles after heating with the vitrified bonding material was the same as before heating (i.e., white-blue).

Example 12

A lanthanum carbonate powder (obtained from Aptech Services, LLC, Houston, Tex.; Lot No.: SH99-5-7) was

heated to 900° C. to convert it to lanthanum oxide and some cerium (IV) oxide (manufacturer's conversion specifications were 95% La₂O₃ and 4.19% CeO₂, with a carbonate to oxide yield of 49.85 wt.% metal oxide). Example 12 fused material, abrasive particles, and discs were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 148.6 grams of the lanthanum/cerium oxide powder, 146.4 grams of alumina powder ("APA-0.5"), 0.6 gram of a dispersing agent ("DURAMAX D-30005") and 141.3 grams of distilled water, and (b) the powders were present in amounts to provide 75 mole % Al₂O₃ and mole % La₂O₃/Ce₂O₃. It was observed that the slurry was significantly more viscous as compared to the slurry of Example 10. The fused material was bright orange in color.

FIG. 27 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 12 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–25 micrometers in size. Based on powder x-ray diffraction of a portion of Example 12 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO₃, and the dark portions crystalline LaAl₁₁O₁₈. The widths of these phases observed in the polished section were up to about 0.5 micrometer. Further, large primary crystals (believed to be LaAlO₃), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a La₂O₃ rich composition.

The average microhardness of Example 12 abrasive particles was determined, as described above in Example 1, except Example 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellet. The average microhardness of Example 12 abrasive particles was 14.8 GPa.

Several Example 12 abrasive particles (together with Example 10 and 12 abrasive particles) were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 12 abrasive particles after heating was the same as before heating (i.e., bright orange). The average microhardness of the Example 12 abrasive particles after heating was 14.7 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 12 abrasive particles after heating was substantially the same as the microstructure observed before heating.

Several Example 12 abrasive particles (together with Example 10 and 11 abrasive particles) were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the Example 12 abrasive particles after heating was the same as before heating (i.e., bright orange). The average microhardness of the Example 12 abrasive particles after heating was 14.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 12 abrasive particles after heating was substantially the same as the microstructure observed before heating.

The effect of two vitrified bonding materials on Example 12 abrasive articles were evaluated as described in Comparative Example B, except Example 10, 11, and 12 abrasive particles (i.e., Example 10, 11, and 12 abrasive particles were mixed together; but were distinguishable from each other visually based on color, and under SEM based on composition) were incorporated into the pellets. The polished cross-sections were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating. The average microhardness of the Example 12 abrasive particles after heating in the two vitrified bonding materials was 14.2 GPa and 14.3 GPa, respectively. The color of the Example 12 abrasive particles after heating with each of the two vitrified bonding materials was the same as before heating (i.e., bright orange).

Grinding Performance of Examples 9–12 and Comparative Examples A–C

The grinding performance of Examples 9–12 and Comparative Examples A–C coated abrasive discs were evaluated as described for Example 1 and Comparative Examples A–C. The results are reported in Table 4, below.

TABLE 4

Example	Total cut, g	Final cut, g
Comp. A	418	23
Comp. B	621	48
Comp. C	859	75
9	732	56
10	585	41
11	603	37
12	564	34

Example 13

Example 13 fused material and abrasive particles were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 144.5 grams of alumina powder ("APA-0.5"), 147.4 grams of cerium (IV) oxide (CeO₂) powder, (obtained from Aldrich Chemical Company, Inc., Milwaukee, Wis.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 137.5 grams of distilled water, (b) the powders were present in amounts to provide 75 mole % Al₂O₃ and 25 mole % Ce₂O₃. The fused material was intense yellow-green in color.

FIG. 28 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 13 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. Based on powder x-ray diffraction of a portion of Example 13 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline CeAlO₃ and crystalline CeO₂, and the dark portions crystalline CeAl₁₁O₁₈. The widths of these phases observed in the polished section were up to about 0.5 micrometer. Further, large primary crystals (believed to be CeAlO₃ and/or CeO₂), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a CeAlO₃ and/or CeO₂ rich composition.

Example 14

Example 14 fused material and abrasive particles were prepared as described in Example 1, except (a) the polyeth-

ylene bottle was charged with 146.5 grams of alumina powder ("APA-0.5"), 147.4 grams of dysprosium oxide powder (obtained from Aldrich Chemical Company, Inc., Milwaukee, Wis.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 136.3 grams of distilled water, and (b) the powders were present in amounts to provide 78 mole % Al_2O_3 and 22 mole % Dy_2O_3 . The fused material was white in color.

FIG. 29 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 14 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–20 micrometers in size. Based on powder x-ray diffraction of a portion of Example 14 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Dy}_3\text{Al}_5\text{O}_{12}$, and the dark portions $\alpha\text{-Al}_2\text{O}_3$. The widths of these phases observed in the polished section were up to about 1 micrometer. Primary crystals were not observed.

Example 15

Example 15 fused material and abrasive particles were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 146.3 grams of alumina powder ("APA-0.5"), 148.4 grams of ytterbium oxide powder (obtained from Aldrich Chemical Company, Inc.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 139.6 grams of distilled water, (b) the powders were present in amounts to provide 78.6 mole % Al_2O_3 and 21.4 mole % Yb_2O_3 . The fused material was gray in color.

FIG. 30 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 15 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies are about 5–25 micrometers in size. Based on powder x-ray diffraction of a portion of Example 15 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Yb}_3\text{Al}_5\text{O}_{12}$, and the dark portions $\alpha\text{-Al}_2\text{O}_3$. The width of these phases observed in the polished section were up to about 1 micrometer. Further, large primary crystals (believed to be $\alpha\text{-Al}_2\text{O}_3$), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward an Al_2O_3 rich composition.

Example 16

Example 16 fused material and abrasive particles were prepared as described in Example 1, except the polyethylene bottle was charged with 122.4 grams of alumina powder ("APA-0.5"), 132.6 grams of ytterbium oxide powder (obtained from Aldrich Chemical Company, Inc.), 45 grams of zirconium oxide powder (with a nominal composition of 100 wt % ZrO_2 (+ HfO_2); obtained under the trade designation "DK-2" from Zirconia Sales, Inc. of Marietta, Ga.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 140.2 grams of distilled water. The fused material was white-gray in color.

FIG. 32 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 16 material. The photomicrograph shows a eutectic-derived microstructure comprising a

plurality of colonies. The colonies were about 5–25 micrometers in size. Based on powder x-ray diffraction of a portion of Example 16 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Yb}_3\text{Al}_5\text{O}_{12}$, and the dark portions crystalline $\alpha\text{-Al}_2\text{O}_3$. The shape of ZrO_2 crystallites was not easily discerned on the photomicrograph. The widths of these phases observed in the polished section were up to about 1 micrometer.

Example 17

Example 17 fused material, abrasive particles, and discs were prepared as described in Example 1, except a polyethylene bottle was charged with 127.25 grams of alumina powder ("APA-0.5"), 127.75 grams of gadolinium oxide powder (obtained from Molycorp, Inc.), 45 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 150 grams of distilled water.

FIG. 33 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 17 material. The photomicrograph shows a eutectic-derived microstructure. Based on powder x-ray diffraction of a portion of Example 17 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline GdAlO_3 , and the dark portions $\alpha\text{-Al}_2\text{O}_3$. The shape of ZrO_2 crystallites was not easily discerned on the photomicrograph. The width of the crystals of phases observed in the polished section were up to about 1 micrometer.

Example 18

Example 18 fused material and abrasive particles were prepared as described in Example 1 except the polyethylene bottle was charged with 124.5 grams of alumina powder ("APA-0.5"), 125.3 grams of dysprosium oxide powder (obtained from Aldrich Chemical Company, Inc.), 45 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 140 grams of distilled water.

FIG. 34 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 18 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–15 micrometers in size. Based on powder x-ray diffraction of a portion of Example 18 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Dy}_3\text{Al}_5\text{O}_{12}$, and the dark portions $\alpha\text{-Al}_2\text{O}_3$. The shape of ZrO_2 crystallites was not easily discerned on the photomicrograph. The width of the crystals of phases observed in the polished section were up to about 1 micrometer.

The average microhardness of Example 18 abrasive particles was determined, as described above in Example 1, to be 14.8 GPa.

Several Example 18 abrasive particles were placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The average microhardness of the Example 18 abrasive particles after heating was 15.6 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the

SEM in the secondary electron mode. The microstructure observed for the Example 18 abrasive particles after heating was substantially the same as the microstructure observed before heating.

Example 19

Example 19 fused material and abrasive particles were prepared as described in Example 1, except the polyethylene bottle was charged with 147.9 grams of alumina powder ("APA-0.5"), 137.1 grams of lanthanum oxide powder (obtained from Molycorp, Inc.), 15 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 145 grams of distilled water.

FIG. 35 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 19 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–20 micrometers in size. Based on powder x-ray diffraction of a portion of Example 19 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO_3 , the dark portions crystalline $\text{LaAl}_{11}\text{O}_{18}$, and the gray portions crystalline, monoclinic- ZrO_2 . The widths of these phases observed in the polished section were up to about 1.5 micrometer.

Example 20

Example 20 fused material, abrasive particles, and discs were prepared as described in Example 1, except the polyethylene bottle was charged with 109 grams of alumina powder ("APA-0.5"), 101 grams of lanthanum oxide powder (obtained from Molycorp, Inc.), 90 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 145 grams of distilled water.

FIG. 36 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 20 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. Based on powder x-ray diffraction of a portion of Example 20 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO_3 , the dark portions crystalline $\text{LaAl}_{11}\text{O}_{18}$, and the gray portions $\text{La}_2\text{Zr}_2\text{O}_7$. Further, based on powder x-ray diffraction, the material also contained monoclinic and two variants of cubic ZrO_2 . The shape and location of ZrO_2 crystallites was not easily discerned on the photomicrograph.

The average microhardness of Example 20 abrasive particles was determined, as described above in Example 1, to be 12.0 GPa.

Several Example 20 abrasive particles were also placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The average microhardness of the Example 20 abrasive particles after heating was 11.8 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed for the Example 20 abrasive particles after heating was substantially the same as the microstructure observed before heating.

The grinding performance of Examples 17 and 20, and Comparative Examples A–C coated abrasive discs were

evaluated as described above for Example 1 and Comparative Examples A–C. The results are reported in Table 5, below.

TABLE 5

Example	Total cut, g	Final cut, g
Comp. A	404	21
Comp. B	647	51
Comp. C	952	79
17	669	50
20	611	41

Example 21

Example 21 fused material, abrasive particles, and discs were prepared as described in Example 1, except the polyethylene bottle was charged with 109 grams of alumina powder ("APA-0.5"), 101 grams of lanthanum oxide powder (obtained from Molycorp, Inc.), 9 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 81 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 145 grams of distilled water.

FIG. 37 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 21 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. Based on powder x-ray diffraction of a portion of Example 21 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO_3 , the dark portions crystalline $\text{LaAl}_{11}\text{O}_{18}$, and the gray portions cubic ZrO_2 . The shape and location of ZrO_2 crystallites was not easily discerned on the photomicrograph.

Example 22

Example 22 fused material and abrasive particles were prepared as described in Example 1, except the polyethylene bottle was charged with 117 grams of alumina powder ("APA-0.5"), 93 grams of neodymium oxide powder (obtained from Molycorp, Inc.), 90 grams of zirconium oxide powder ("DK-2"), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 138 grams of distilled water.

FIG. 38 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 22 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. Based on powder x-ray diffraction of a portion of Example 22 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline NdAlO_3 , and the dark portions crystalline $\text{NdAl}_{11}\text{O}_{18}$. The widths of these phases observed in the polished section were up to about 3 micrometers. Further, based on powder x-ray diffraction, the material also contains two variants of cubic ZrO_2 . The shape and location of ZrO_2 crystallites was not easily discerned on the photomicrograph.

Example 23

Example 23 fused material and abrasive particles were prepared as described in Example 1, except the polyethylene bottle was charged with 106.1 grams of alumina powder ("APA-0.5"), 103.9 grams of cerium (IV) oxide (CeO_2)

powder, (obtained from Aldrich Chemical Company, Inc.), 90 grams of zirconium oxide powder ("DK-2") 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 139.5 grams of distilled water.

FIG. 39 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 23 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. Based on powder x-ray diffraction of a portion of Example 23, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline CeAlO_3 , the dark portions crystalline $\text{CeAl}_{11}\text{O}_{18}$, and the gray portions $\text{Ce}_2\text{Zr}_2\text{O}_7$. The widths of these phases observed in the polished section were up to about 5 micrometers. Further, based on powder x-ray diffraction, the material also contained monoclinic and two variants of cubic ZrO_2 . The shape and location of ZrO_2 crystallites was not easily discerned on the photomicrograph. Further, large primary crystals (believed to be CeAlO_3 and/or CeO_2) were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a CeAlO_3 and/or CeO_2 rich composition.

Example 24

Example 24 fused material, abrasive particles, and discs were prepared as described in Example 1, except (a) the polyethylene bottle was charged with 155.6 grams of alumina powder ("APA-0.5"), 144.3 grams of lanthanum oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 0.6 gram of a dispersing agent ("DURAMAX D-30005"), and 130 grams of distilled water, and (b) the powders were present in amounts to provide 77.5 mole % Al_2O_3 and 22.5 mole % La_2O_3 . The fused material was white-red in color; although some of the abrasive particles were redder than others.

FIG. 40 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 24 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. Based on powder x-ray diffraction of a portion of Example 24 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO_3 , and the dark portions crystalline $\text{LaAl}_{11}\text{O}_{18}$. The widths of these phases observed in the polished section were up to about 0.5 micrometer. Further, large primary crystals (believed to be LaAlO_3), present in the form of dendrites, were observed in some areas of the polished cross-section, indicating possible deviation of the composition from an exact eutectic composition toward a La_2O_3 rich composition.

The grinding performance of Example 24 and Comparative Examples A–C coated abrasive discs were evaluated as described above for Example 1 and Comparative Examples A–C. The results are reported in Table 6, below.

TABLE 6

Example	Total Cut, g	Final cut, g
Comp. A	404	21
Comp. B	647	51

TABLE 6-continued

Example	Total Cut, g	Final cut, g
Comp. C	952	79
24	690	52

Example 25

Example 25 fused material, abrasive particles, and discs were prepared as described in Example 1, except the polyethylene bottle was charged with 191.8 grams of alumina powder ("APA-0.5"), 93.2 grams of yttrium oxide powder (obtained from H. C. Starck, Newton, Mass.), 15 grams of aluminum nitride powder (Type F; obtained from Tokuyama Soda Co., Japan), and 150 grams of isopropyl alcohol. The fused material was dark gray in color.

FIG. 41 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 25 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–25 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 25 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Y}_3\text{Al}_5\text{O}_{12}$, and the dark portions $\text{Al}_3\text{O}_3\text{N}$. The widths of these phases observed in the polished section were up to about 1 micrometer.

The average microhardnesses of Example 25 abrasive particles was determined, as described above in Example 1, to be 16.2 GPa.

Several Example 25 abrasive particles were heated placed in a platinum crucible and heated to 100° C. at 50° C./hour, held at 1000° C. for 4 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was the same as before heating (i.e., dark gray). The average microhardness of the abrasive particles after heating was 16.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Several Example 25 abrasive particles were also heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was the same as before heating (i.e., dark gray). The average microhardness of the abrasive particles after heating was 15.8 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Grinding Performance of Example 25 and Comparative Examples A–C

The grinding performance of Example 25 and Comparative Examples A–C coated abrasive discs were evaluated as described for Example 1 and Comparative Examples A–C.

The results are reported in Table 7, below.

TABLE 7

Example	Total cut, g	Final cut, g
Comp. A	414	24
Comp. B	637	50
Comp. C	988	90
25	885	69

Example 26

Example 26 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 199.9 grams of alumina powder ("APA-0.5"), 97.1 grams of yttrium oxide powder (obtained from H. C. Starck), 3 grams of aluminum nitride powder (Type F), and 150 grams of isopropyl alcohol.

FIG. 42 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 26 material. Referring to FIG. 42, the photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 26 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $Y_3Al_5O_{12}$, and the dark portions Al_2O_3 and Al_3O_3N (material was found to contain both of these phases). The widths of these phases observed in the polished section were up to about 3 micrometers.

Example 27

Example 27 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 171.6 grams of alumina powder ("APA-0.5"), 83.4 grams of yttrium oxide powder (obtained from H. C. Starck), 45 grams of aluminum nitride powder (Type F), and 150 grams of isopropyl alcohol.

FIG. 43 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 27 material. Referring to FIG. 43, the photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. FIG. 43 also shows the presence of a third phase in the form of largely spherical inclusions. Based on powder x-ray diffraction of a portion of Example 27 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $Y_3Al_5O_{12}$, and the dark portions Al_3O_3N . The dark inclusions are believed to be AlN phase. The widths of crystals of $Y_3Al_5O_{12}$ and Al_3O_3N phases observed in the polished section were up to about 3 micrometers.

Example 28

Example 28 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 181.7 grams of alumina powder ("APA-0.5"), 88.3 grams of yttrium oxide powder (obtained from Alfa Aesar A Johnson Matthey Company, Ward Hill, Mass.), 30 grams of aluminum carbide powder (obtained from Aldrich Chemical Co., Milwaukee, Wis.), and 150 grams of isopropyl alcohol.

FIG. 44 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 28 material. Referring to FIG. 44, the photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 28 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $Y_3Al_5O_{12}$, and the dark portions Al_2OC . The widths of these phases observed in the polished section were up to about 3 micrometers.

Example 29

Example 29 fused abrasive particles and coated abrasive discs were prepared as described in Example 1, except the polyethylene bottle was charged with 135.3 grams of alumina powder ("APA-0.5"), 143.7 grams of gadolinium oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 21 grams of aluminum nitride powder (Type F), and 150 grams of isopropyl alcohol. The fused material was dark gray in color.

FIG. 45 is a scanning electron microscope (SEM) photomicrograph of a polished section (prepared as described in Example 1) of fused Example 29 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–25 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 29 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $GdAlO_3$, and the dark portions Al_3O_3N . In addition, the presence of Al_2O_3 was also detected by powder x-ray diffraction. The widths of the $GdAlO_3$ and Al_3O_3N phases observed in the polished section were up to about 1 micrometer.

The average microhardnesses of Example 29 abrasive particles was determined, as described above in Example 1, to be 17.2 GPa.

Several Example 29 abrasive particles were heated placed in a platinum crucible and heated to 1000° C. at 50° C./hour, held at 1000° C. for 8 hours (in air), and then cooled to room temperature at about 100° C./hour. The color of the abrasive particles after heating was the same as before heating. The average microhardness of the abrasive particles after heating was 17.1 GPa. The polished cross-sections prepared for the microhardness measurements were examined using the SEM in the secondary electron mode. The microstructure observed after heating was substantially the same as the microstructure observed before heating.

Grinding Performance of Example 29 and Comparative Examples A–C

The grinding performance of Example 29 and Comparative Examples A–C coated abrasive discs were evaluated as described for Example 1 and Comparative Examples A–C. The results are reported in Table 8, below

TABLE 8

Example	Total cut, g	Final cut, g
Comp. A	414	24
Comp. B	637	50
Comp. C	988	90
29	825	50

Example 30

Example 30 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 138.5 grams of alumina powder ("APA-0.5"), 140.5 grams of ytterbium oxide powder (obtained from Aldrich Chemical Company, Inc.), 21 grams of aluminum nitride powder (Type F), and 150 grams of isopropyl alcohol.

FIG. 46 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 30 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 30 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Yb}_3\text{Al}_5\text{O}_{12}$, and the dark portions Al_2O_3 and $\text{Al}_3\text{O}_3\text{N}$ (material was found to contain both of these phases). The widths of these phases observed in the polished section were up to about 2 micrometers.

Example 31

Example 31 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 139 grams of alumina powder ("APA-0.5"), 140 grams of dysprosium oxide powder (obtained from Aldrich Chemical Company Inc.), 21 grams of aluminum nitride powder (Type F), and 150 grams of isopropyl alcohol.

FIG. 47 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 31 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 31 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline $\text{Dy}_3\text{Al}_5\text{O}_{12}$, and the dark portions $\text{Al}_3\text{O}_3\text{N}$. The widths of crystals of $\text{Dy}_3\text{Al}_5\text{O}_{12}$ and $\text{Al}_3\text{O}_3\text{N}$ phases observed in the polished section were up to about 2 micrometers.

Example 32

Example 32 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 135.3 grams of alumina powder ("APA-0.5"), 143.7 grams of gadolinium oxide powder (obtained from Molycorp, Inc., Brea, Calif.), 21 grams of aluminum carbide powder (obtained from Aldrich Chemical Co.), and 150 grams of isopropyl alcohol.

FIG. 48 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 32 material. The photomicrograph shows a eutectic-derived

microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 32 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline GdAlO_3 , and the dark portions Al_2OC and Al_2O_3 (both phases were present according to powder x-ray diffraction). The widths of these phases observed in the polished section were up to about 3 micrometers.

Example 33

Example 33 fused material was prepared as described in Example 1, except the polyethylene bottle was charged with 132.3 grams of alumina powder ("APA-0.5"), 122.7 grams of lanthanum oxide powder (obtained from Molycorp, Inc., Brea Calif.), 45 grams of aluminum nitride powder (Type F) and 150 grams of isopropyl alcohol.

FIG. 49 is an SEM photomicrograph of a polished section (prepared as described in Example 1) of fused Example 33 material. The photomicrograph shows a eutectic-derived microstructure comprising a plurality of colonies. The colonies were about 5–30 micrometers in size. The orientation and morphology of crystals making up the colonies varied from one colony to another. Based on powder x-ray diffraction of a portion of Example 33 material, and examination of the polished sample using SEM in the backscattered mode, it is believed that the white portions in the photomicrograph were crystalline LaAlO_3 and the dark portions $\text{LaAl}_{11}\text{O}_{18}$. FIG. 49 also shows the presence of a third phase in the form of largely spherical inclusions. These inclusions are believed to be AlN phase. The widths of crystals of LaAlO_3 and $\text{LaAl}_{11}\text{O}_{18}$ phases observed in the polished section were up to about 1 micrometer.

Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention, and it should be understood that this invention is not to be unduly limited to the illustrative embodiments set forth herein.

What is claimed is:

1. Fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein said abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

2. The fused, crystalline abrasive particles according to claim 1 comprising at least 50 percent by volume, based on the total metal oxide volume of the respective particle, of said eutectic.

3. The fused, crystalline abrasive particles according to claim 2 comprising, on a theoretical oxide basis, at least 40 percent by weight Al_2O_3 , based on the total metal oxide content the respective particle.

4. The fused, crystalline abrasive particles according to claim 3, wherein said second average microhardness is at least 90% of said first average microhardness.

5. The fused, crystalline abrasive particles according to claim 4, wherein said first average microhardness is at least 14 GPa.

6. Fused, crystalline abrasive particles comprising at least one eutectic, the eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein said abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

7. The fused, crystalline abrasive particles according to claim 6 comprising at least 50 percent by volume, based on the total metal oxide volume of the respective particle, of said eutectic.

8. The fused, crystalline abrasive particles according to claim 7 comprising, on a theoretical oxide basis, at least 40 percent by weight Al_2O_3 , based on the total metal oxide content the respective particle.

9. The fused, crystalline abrasive particles according to claim 8, wherein said second average microhardness is at least 90% of said first average microhardness.

10. The fused, crystalline abrasive particles according to claim 9, wherein said first average microhardness is at least 14 GPa.

11. A plurality of particles having a particle size distribution ranging from fine to coarse, wherein at least a portion of said plurality of particles are fused, crystalline abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

12. A plurality of particles having a particle size distribution ranging from fine to coarse, wherein at least a portion of said plurality of particles are fused, crystalline abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

13. A plurality of abrasive particles having a specified nominal grade, said plurality of abrasive particle having a particle size distribution ranging from fine to coarse, wherein at least a portion of said abrasive particles is a plurality of fused, crystalline abrasive particles, said fused abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

14. A plurality of abrasive particles having a specified nominal grade, said plurality of abrasive particle having a

particle size distribution ranging from fine to coarse, wherein at least a portion of said abrasive particles is a plurality of fused, crystalline abrasive particles, said fused abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

15. An abrasive article comprising a binder and a plurality of abrasive particles, wherein at least a portion of said abrasive particles are fused, crystalline abrasive particles comprising at least one eutectic, said eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

16. An abrasive article comprising a binder and a plurality of abrasive particles, wherein at least a portion of said abrasive particles are fused, crystalline abrasive particles comprising at least one eutectic, said eutectic comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

17. A vitrified bonded abrasive article comprising a plurality of abrasive particles bonded together via vitrified bonding material, wherein at least a portion of said plurality of abrasive particles are fused, crystalline abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{REO}$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

18. A vitrified bonded abrasive article comprising a plurality of abrasive particles bonded together via vitrified bonding material, wherein at least a portion of said plurality of abrasive particles are fused, crystalline abrasive particles comprising at least (i) crystalline, complex $\text{Al}_2\text{O}_3\cdot\text{Y}_2\text{O}_3$ and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness.

19. A method of abrading a surface comprising:
contacting a plurality of abrasive particles comprising at least one eutectic, said eutectic comprising at least (i)

crystalline, complex Al_2O_3 .REO and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al with a surface of a workpiece, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness; and

moving at least one of said plurality of abrasive particles or said surface relative to the other to abrade at least a portion of said surface with at least one of said fused abrasive particles.

20. A method of abrading a surface comprising:

contacting a plurality of abrasive particles comprising at least one eutectic, said eutectic comprising at least (i) crystalline, complex Al_2O_3 . Y_2O_3 and (ii) at least one of aluminoxy-D or M-aluminoxy-D, wherein D is at least one of carbide or nitride, and M is at least one metal cation other than Al with a surface of a workpiece, wherein said abrasive particles have a first average microhardness of at least 11 GPa, wherein the abrasive particles have a second average microhardness after being heated in air at 1000° C. for 4 hours, and wherein said second average microhardness is at least 85% of said first average microhardness; and

moving at least one of said plurality of abrasive particles or said surface relative to the other to abrade at least a portion of said surface with at least one of said fused abrasive particles.

21. The plurality of abrasive particles according to claim 13 wherein said specified nominal grade is selected from the

group consisting of ANSI 16, ANSI 24, ANSI 36, ANSI 40, ANSI 50, ANSI 60, ANSI 80, ANSI 100, ANSI 120, ANSI 150, ANSI 180, ANSI 220, ANSI 240, ANSI 280, ANSI 320, ANSI 360, ANSI 400, and ANSI 600.

22. The plurality of abrasive particles according to claim 13 wherein said specified nominal grade is selected from the group consisting of P16, P24, P36, P40, P50, P60, P80, P100, P120, P150, P180, P220, P320, P400, P500, P600, P800, P1000, and P1200.

23. The plurality of abrasive particles according to claim 13 wherein said specified nominal grade is selected from the group consisting of JIS16, JIS24, JIS36, JIS46, JIS54, JIS60, JIS80, JIS110, JIS150, JIS180, JIS220, JIS240, JIS280, JIS320, JIS360, JIS400, JIS600, JIS800, JIS1000, JIS1500, JIS2500, JIS4000, JIS6000, JIS8000, and JIS10,000.

24. The plurality of abrasive particles according to claim 14 wherein said specified nominal grade is selected from the group consisting of ANSI 16, ANSI 24, ANSI 36, ANSI 40, ANSI 50, ANSI 60, ANSI 80, ANSI 100, ANSI 120, ANSI 150, ANSI 180, ANSI 220, ANSI 240, ANSI 280, ANSI 320, ANSI 360, ANSI 400, and ANSI 600.

25. The plurality of abrasive particles according to claim 14 wherein said specified nominal grade is selected from the group consisting of P16, P24, P36, P40, P50, P60, P80, P100, P120, P150, P180, P220, P320, P400, P500, P600, P800, P1000, and P1200.

26. The plurality of abrasive particles according to claim 14 wherein said specified nominal grade is selected from the group consisting of JIS16, JIS24, JIS36, JIS46, JIS54, JIS60, JIS80, JIS100, JIS150, JIS180, JIS220, JIS240, JIS280, JIS320, JIS360, JIS400, JIS600, JIS800, JIS1000, JIS1500, JIS2500, JIS4000, JIS6000, JIS8000, and JIS10,000.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,451,077 B1
APPLICATION NO. : 09/619563
DATED : September 17, 2002
INVENTOR(S) : Anatoly Z. Rosenflanz

Page 1 of 2

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title Page, item (56), line 12, under Other Publications, "Thermon" should read --Thermo--.

Title Page, item (56) Page 3, line 2, under Other Publications, "IX" should read --XI--.

Title Page, item (56) Page 2, line 26, under Other Publications, "Lakiz and Lopato" should be in regular type.

Col. 3, line 33, "100°" should read --1000°--.

Col. 6, line 41, "o₃" should read --O₃--.

Col. 8, line 56, "to" should read --too--.

Col. 11, line 40, "Dy₃Al₅O₅₁₂" should read --Dy₃Al₅O₁₂--.

Col. 12, line 5, "materials" should read --material--.

Col. 12, line 31, "to⁵" should read --to 5--.

Col. 16, line 25, "particles fine" should read --particles to fine--.

Col. 16, line 48, delete one instance of "JIS400".

Col. 18, line 19, "articles" should read --particles.

Col. 20, line 22, "may thermally" should read --may be thermally--.

Col. 20, line 23, after "thereof" insert --.-- and two spaces.

Col. 21, line 65, "according the" should read --according to the--.

Col. 21, line 66, delete "another" and insert --other--.

Col. 24, line 42, delete "power" following "furnace".

Col. 26, line 60, "K a1" should read --K α1--.

Col. 27, line 28, "3/8" should read --4 3/8-- in both instances.

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,451,077 B1
APPLICATION NO. : 09/619563
DATED : September 17, 2002
INVENTOR(S) : Anatoly Z. Rosenflanz

Page 2 of 2

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Col. 29, line 42, delete "2" and insert --1--.

Col. 35, line 6, insert --10-- following "Example".

Col. 35, line 15, "12abrasive" should read --12 abrasive--.

Col. 35, line 35, insert --10-- following "Example".

Col. 36, line 27, delete "15": preceding "50".

Col. 42, line 34, "LaAl₁₁ 18" should read --LaAl₁₁O₁₈--.

Col. 44, line 38, "100°" should read --1000°--

Col. 52, line 12, "JIS110" should read --JIS100--.

Signed and Sealed this

Twenty-sixth Day of December, 2006

A handwritten signature in black ink on a light gray dotted background. The signature reads "Jon W. Dudas" in a cursive style.

JON W. DUDAS

Director of the United States Patent and Trademark Office