



US006683729B1

(12) **United States Patent**
Schuster

(10) **Patent No.:** **US 6,683,729 B1**
(45) **Date of Patent:** **Jan. 27, 2004**

(54) **OBJECTIVE WITH CRYSTAL LENSES AND PROJECTION EXPOSURE EQUIPMENT FOR MICROLITHOGRAPHY**

(75) Inventor: **Karl-Heinz Schuster**, Königsbronn (DE)

(73) Assignee: **Carl Zeiss**, Heidenheim (DE)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/451,505**

(22) Filed: **Nov. 30, 1999**

(30) **Foreign Application Priority Data**

Nov. 30, 1998	(DE)	198 55 158
Feb. 27, 1999	(DE)	198 08 544
Jun. 29, 1999	(DE)	199 29 701

(51) **Int. Cl.**⁷ **G02B 21/02**; G02B 9/00

(52) **U.S. Cl.** **359/656**; 359/649; 359/754

(58) **Field of Search** 359/642, 754, 359/656, 649

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,701,035	A	10/1987	Hirose	
5,031,977	A	* 7/1991	Gibson	359/766
5,040,882	A	8/1991	Markle	
5,142,409	A	8/1992	Hanzawa et al.	
5,305,138	A	4/1994	Freedenberg et al.	
5,686,728	A	11/1997	Shafer	
5,717,518	A	2/1998	Shafer et al.	
5,781,336	A	7/1998	Coon et al.	
5,815,310	A	9/1998	Williamson	
6,101,047	A	8/2000	Chung et al.	
6,169,627	B1	1/2001	Schuster	
6,195,213	B1	* 2/2001	Omura et al.	359/727
6,243,206	B1	* 6/2001	Wangler	359/621
6,295,508	B1	* 7/2001	Shigematsu	359/766
6,333,781	B1	* 12/2001	Shigematsu	359/766
6,377,338	B1	4/2002	Suenaga	359/727
6,451,462	B1	* 9/2002	Schuster	428/696
6,451,507	B1	* 9/2002	Suenaga et al.	430/311

FOREIGN PATENT DOCUMENTS

DE	222 426 A1	3/1984
DE	222 426 B5	3/1984
DE	197 04936 A1	2/1997
DE	199 22 209	6/1999
DE	199 39 088 A1	8/1999
EP	0 243 950 B1	3/1993
EP	0 809 125 A1	11/1997
EP	0 857 985 A1	6/1998
EP	0 964 307 A2	12/1999
EP	1 037 267 A1	9/2000
WO	WO 98/43135	10/1998
WO	WO 99/25008	5/1999

OTHER PUBLICATIONS

Patentschrift 845 415; Jul. 31, 1952; Ultraviolett durchlässiges optisches System.

European Search Report; EP 99 12 1434; May 31, 2000.

U.S. patent application Ser. No. 60/094579, Shafer et al., filed Jul. 29, 1998.

(1) Mikroelektronik-Fertigung, Lithographie heute und morgen, pp. 57-60.

(2) Vacuum ultraviolet thin films, Applied Optics, Oct. 1990, pp. 4284-4292.

(3) Problemes Poses Par La Conception D'Un Objectif Photoreducteur Fonctionnant en UV, 1984, pp. 281-285.

(4) Performance Evaluation of a Practical 248 nm Wafer Stepper. Walsh et al. 1987, pp. 155-159.

(5) JR 1/1989, pp. 7-9.

* cited by examiner

Primary Examiner—Scott J. Sugarman

(57) **ABSTRACT**

An objective with lenses made of two different crystals, in particular CaF₂ and BaF₂ is particularly suitable as a refractive projection objective for microlithography at 157 nm. Such projection objectives for 193/248 nm with quartz glass and achromatization with CaF₂ are compaction-resistant with BaF₂. Microlithography projection exposure equipment in the 100-200 nm wavelength region include other fluorides and partially catadioptric objectives.

38 Claims, 3 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



**OBJECTIVE WITH CRYSTAL LENSES AND
PROJECTION EXPOSURE EQUIPMENT FOR
MICROLITHOGRAPHY**

**CROSS REFERENCES TO RELATED
APPLICATIONS**

Not applicable.

**STATEMENT REGARDING FEDERALLY
SPONSORED RESEARCH OR DEVELOPMENT**

Not applicable.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The invention relates to an objective with crystal lenses. Such objectives have been known for over a hundred years as Carl Zeiss apochromatic microscope objectives with fluor spar (CaF_2) lenses.

In recent times, refractive projection objectives for microlithography in the DUV at wavelengths of 248 or 193 nm have been constructed, and contain lenses of quartz glass and CaF_2 .

2. Discussion of Relevant Art

An optical system is known from German Democratic Republic Patent DD 222 426 B5, with optical glasses and BaF_2 single crystal as optical media, and can be used for wavelengths of 150 up to 10^4 nm. The embodiment example is a planapochromat for 480–800 nm with several different glasses and BaF_2 .

The choice of materials for UV microlithographic objectives (centered on 248 nm wavelength) is described in G. Roblin, *J. Optics (Paris)*, 15 (1984), pp. 281–285.

The outcome was that only combinations of quartz glass with CaF_2 or LiF are graded as usable.

In U. Behringer, *F+M (Munich)* 107 (1999), 57–60, fluorides such as CaF_2 , MgF_2 and LiF are described as suitable for 157 nm microlithography, with reservations regarding the double refraction of MgF_2 and regarding the handling of LiF.

In K. F. Walsh et al., *SPIE Vol. 774* (1987), 155–159, excimer lasers for wavelengths of 248, 193 and 157 nm are presented, among other things. For 248 nm quartz glass, CaF_2 , BaF_2 , and MgF_2 are named as the only applicable lens materials. For wavelengths below 248 nm, quartz glass is expected to be the only one material which is usable.

A catadioptric 1:1 projection objective for microlithography at 248 nm is described in U.S. Pat. No. 5,031,977, and contains a concave mirror, a quartz glass lens, an LiF lens, and two CaF_2 deflecting prisms. Neither arguments for choice of materials are given nor information on modifications of the special construction.

However, the absorption edge of quartz glass is situated close to 157 nm. CaF_2 still usefully transmits at 157 nm, but has too high a dispersion for a purely CaF_2 objective for microlithography, even for a spectrally narrowed F_2 excimer laser. Heretofore objectives for wavelengths below 193 nm are therefore known only as catadioptric (see German Patent Document DE 196 39 586 A of the same Inventor, and U.S. Prov. Appl. Ser. No. 60/094579 of Jul. 29, 1998) or catoptric (see U.S. Pat. No. 5,686,728) systems. Here U.S. Pat. No. 5,686,728 gives a purely mirror objective for VUV microlithography with a 126 nm, 146 nm, or 157 nm excimer laser, for example.

SUMMARY OF THE INVENTION

The invention has as its object an alternative concept of an objective with a new composition of material which opens up new possibilities of application, particularly in microlithography at low wavelengths.

This object is attained by an objective having a plurality of lenses made of at least two different crystals. This object is also attained by a microlithographic projection objective corrected for illumination with a F_2 excimer laser at 157 nm, wherein the projection objective is purely refractive and comprises a plurality of lenses of a material selected from the group consisting of BaF_2 , SrF_2 , NaF, LiF, and KF. This object is also attained by a projection exposure equipment having a light source including an excimer laser with 100–160 nm wavelength, an illumination system including refractive optical elements comprising one or more fluorides, a reticle positioning and movement system, a projection objective with a plurality of lenses comprising at least two of crystalline materials selected from the group consisting of CaF_2 , BaF_2 , LiF, NaF, SrF_2 , KF and amorphous BeF_2 , and an object positioning and movement system. A process according to the invention for the production of microstructured components provides that a substrate provided with a photosensitive layer is exposed to ultraviolet light by means of a mask and a projection exposure equipment and if necessary after development, the photosensitive layer is structured corresponding to a pattern contained on the mask.

The invention starts from the discovery that novel kinds of objective properties can be provided by the use of two different crystals in an objective. In particular, included in this is the possibility of achromatizing at low wavelengths, at which each known glass, including quartz glass, absorbs strongly. The existing reservations in microlithography against BaF_2 relate to 248 nm and quartz glass as the partner.

Alkali and alkaline earth halides, especially the fluorides, and also other fluorides, are known as optical materials. Their partially difficult properties as materials have however led to their outstanding transmission properties in the deep UV being made use of only in an adjunct manner. It has been shown according to the invention that optical microlithography can be extended down to about 100 nm wavelength with these and similar materials.

A pair of materials for the achromatization of 157 nm optics can be provided for the first time by the pairing of two fluoride crystals, particularly of CaF_2 , BaF_2 , SrF_2 , LiF, NaF, or KF, but also of mixed crystal fluorides. The materials are already known in optical manufacture, as evidenced by the cited state of the art. Barium fluoride, strontium fluoride, or sodium fluoride are preferably used for negative lenses, and indeed only for individual ones, as this can be sufficient. Calcium fluoride then finds application not only for the positive lenses, but also for the remaining negative lenses.

It is particularly advantageous that numerical apertures greater than 0.5 are attained, even at 157 nm. The following example with a numerical aperture of 0.8 reveals this clearly. The advance in resolution of EUV microlithography caused by about 1/10 of the wavelength is thereby partially compensated, since three times the NA is attained. As against 193 nm, the resolution can be nearly halved with 109 nm, since the level of the NA is retained. For the accuracy of processing, the invented technology has dramatic advantages over EUVL caused by tenfold the wavelength.

The stitching process (exposure of the chips by columns) according to an advantageous feature of the invention has

recently been talked about for microlithography at very low wavelengths, and permits image fields of reduced size as rectangles with a moderate aspect ratio and thus makes possible a dramatic reduction in size of the objectives. This in turn dramatically relieves the production problems for the lens crystals.

In a quite different kind of embodiment of the invention, it was surprisingly found that in DUV microlithography with 248 nm or 193 nm, an aging process termed "compaction" occurs in quartz glass during long-term operation; in it, the material becomes densified and consequently the refractive index and the shape of the lens become changed. This of course worsens the imaging power of the objective. Besides compensation by positionable elements, it was known that the most highly loaded image-side lenses concerned can be made of crystal, preferably of CaF_2 , SrF_2 or BaF_2 , which are substantially more stable against UV radiation.

Several embodiment examples of such a use of calcium fluoride lenses are contained in German Patent Application DE 19855157.6 of the Applicant, of the same priority date, which Application is incorporated herein by reference as part of the disclosure of the present Application.

BaF_2 as well as SrF_2 in this reference have the advantage of differing substantially less than CaF_2 from quartz glass in their optical properties (see Roblin, as cited hereinabove)—although this is a disadvantage in the context of achromatization. The design changes of a projection objective on replacing quartz lenses by BaF_2 or SrF_2 lenses near the image are therefore minimal. The projection objective is thus optimized by the use of two crystalline materials: CaF_2 for achromatization, and BaF_2 or SrF_2 against compaction.

For a 157 nm objective, purely refractive and made from one material, accordingly CaF_2 , laser bandwidths of less than 0.1 pm are necessary, depending on the aperture and size of image field.

It cannot be expected that this value can easily be attained on changing from 193 nm to 157 nm. Once again everything is more demanding: permeability of material, layer availability, lattices for the laser components.

According to the invention, a material has been found in BaF_2 which is transparent and isotropic at 157 nm, which has a markedly higher dispersion at 157 nm than does CaF_2 , and which can be supplemented with this for achromatization. BaF_2 first completely absorbs at about 130 nm. The closeness of the absorption edge to 157 nm is responsible for the rapid course of the change in refractive index (strong dispersion) at 157 nm. This similarly holds for other fluorides such as SrF_2 .

Achromatization at 193 nm is established by the combination of CaF_2 and quartz glass. BaF_2 has an only slightly higher dispersion than CaF_2 and is situated uselessly, so to speak, between the dispersion of CaF_2 and quartz glass.

The situation changes for 157 nm, since quartz glass shows increased absorption. According to the general opinion heretofore, there is now no suitable partner for CaF_2 .

This is not the case. The dispersion distance between CaF_2 and BaF_2 at 157 nm is indeed smaller than that between CaF_2 and quartz glass at 193 nm, but a still very good partial achromatization, to a similar level as at 193 nm, e.g., 50% color longitudinal error reduction, is always possible by a moderate use of BaF_2 .

At 193 nm only a partial achromatization is generally carried out, in order to keep the volume of CaF_2 used small, for reasons of cost, availability, and material properties. At 157 nm, it is desired to keep the volume of the partner BaF_2

small, since it has a higher specific weight, and BaF_2 lenses therefore deform more strongly due to gravity.

At 193 nm as much as possible may be made of quartz glass; at 157 nm, as much as possible of CaF_2 . Since the number of positive lenses in refractive lithographic objectives is markedly larger than that of negative lenses, it would be advantageous at 193 nm if quartz glass had a small dispersion. However, the situation is reversed: CaF_2 has the smaller dispersion and cannot, or should not, be used in all the positive lenses. Thus positive lenses are made of quartz glass, which depresses the degree of achromatization.

At 157 nm it is likewise desirable that the preferred material, here CaF_2 , has a smaller dispersion than the partner.

In contrast to 193 nm, this is the case with BaF_2 at 157 nm. Nearly all the lenses, certainly all the positive lenses, can be of the crown, namely CaF_2 . A few negative lenses are made of BaF_2 , or alternatively of SrF_2 , since the same holds qualitatively for this as for BaF_2 .

The above statements of course also hold for lenses in a catadioptric objective, particularly also for refractive partial objectives used therein. The objective according to the invention can also be catadioptric. It is important that lenses, and not only optical auxiliary elements such as deflecting prisms or plane plates consist of crystal.

If lithography is desired with a shorter wavelength than 157 nm and at the same time with very high numerical aperture, a multitude of already known problems is encountered in aggravated form. Firstly, it must be clear that a suitable bandwidth and output power of the light source is only to be expected at excimer laser wavelengths. The spectra of the rare gases indeed emit from about 60 nm, only these are broadband and hence only accessible to purely mirror systems.

Purely mirror systems with a really extended field of between 10 and 26 mm have no aperture greater than $\text{NA}=0.6$ up to now.

Excimer lasers can be operated at the following wavelengths below 157 nm:

NeF	109 nm
Ar ₂	126 nm
ArKr	134 nm
Kr ₂	147 nm.

As regards the question of materials, CaF_2 is a known candidate, with very good transmission for 134 and 147 nm. For 134 and 147 nm, catadioptric lenses exclusively with CaF_2 as the lens material are conceivable, and hence represent nothing new. To obtain refractive objectives with more aperture, such as 0.80/0.85/0.90, the wavelength 147 nm is opened up with the above-mentioned materials system for 157 nm: positive lenses predominantly of CaF_2 , and a few negative lenses of BaF_2 . Since the absorption edge of BaF_2 is situated at about 134.5 nm, 147 nm is still separated from it by about 13 nm. This means an increased absorption, but however makes possible a more relaxed color longitudinal error correction, since BaF_2 at 147 nm now has a stronger dispersion than at 157 nm, and indeed with a higher increase than CaF_2 , since the absorption edge of CaF_2 is situated at 125 nm.

In other words, with equally good bandwidth of the laser of 157 nm and 147 nm, in a purely refractive objective a material pair of CaF_2 and BaF_2 provides a better result as regards color correction. The absorption losses are of course higher.

At 134 nm also, no material pair for achromatization of purely refractive systems was heretofore given. This was found according to the invention in the material pair CaF_2 — SrF_2 . The distance to the absorption edge of SrF_2 at 130 nm has however to be classified as very small. The increased absorption only permits the crystal to appropriately appear in very thin and small negative lenses. Therefore such a system can only be realistic for small image fields, possibly a half field system (stitching).

CaF_2 is also completely excluded at 126 nm, since the distance to the absorption edge is only 1 nm.

There remain as known materials, MgF_2 and LiF . MgF_2 is strongly birefringent at 126 nm and therefore unsuitable. LiF at 126 nm is indeed transparent, but is unsuitable for smaller diameters, since the radiation loading rises and the material is impermissibly changed thereby (transmission and refractive index). Even a catadioptric system does not sufficiently come through without material in the region of the highest aperture (before the image plane). Thus for 126 nm, high aperture lithography objectives with a large field could no longer be constructed.

A further material can now be given according to the invention, especially for the highly loaded small diameter. The configuration at 126 nm consists of a catadioptric lithography objective, which mainly consists of LiF . In the lenses which are loaded with a high light intensity, it consists however of the isotropic amorphous form of BeF_2 . The crystalline form is birefringent, similarly to crystalline quartz. The glassy, solidified form, similarly to quartz glass, is isotropic when similarly produced. Since BeF_2 is markedly more laser-resistant at 126 nm than LiF , it is the suitable material in a few lenses either in the beam waist or several beam waists and/or on the image end of the objective. The small number of BeF_2 lenses is lastly to be sought because BeF_2 has to be classified as a powerful respiratory poison and as a weak contact poison. For the infrared region, there are long established production lines which control the handling of poisonous optical components. It is nevertheless advantageous to restrict the number of BeF_2 lenses to the indispensable ones. Thus a refractive or catadioptric lithography objective is concerned, of at least one crystalline and one vitreous fluoride. BeF_2 has to be produced and worked in the absence of water, since it tends to take up H_2O , and the H_2O immediately blocks the 126 nm wavelength.

Especially low H_2O content BeF_2 production also makes the laser wavelength at 109 nm accessible. Both components in highly pure form, LiF and BeF_2 make a catadioptric objective possible at 109 nm.

Optical materials with high dispersion are conventionally termed flint (glass), and those with low dispersion are termed crown (glass). The following compactly described combinations of materials are proposed according to the above-mentioned for the different DUV through VUV wavelengths.

193 nm:	CaF_2 crown	KF flint
	CaF_2 crown	KF + SiO_2 glass flint
	LiF +, CaF_2 crown	KF flint
	LiF +, CaF_2 crown	KF + SiO_2 glass flint
157 + 147 nm:	CaF_2 and/or LiF crown	NaF , BaF_2 and/or SrF_2 flint
134 nm:	CaF_2 crown	SrF_2 flint
	CaF_2 crown	NaF flint
	LiF crown	SrF_2 flint
	LiF crown	NaF flint
	LiF crown	NaF + SrF_2 flint

where SrF_2 is used for the smaller diameters, since it is more radiation-resistant than NaF .

The above-mentioned systems can have reflections eliminated with thin layer systems of MgF_2 and LaF_3 . For 193 nm, SiO_2 and Al_2O_3 are additionally suitable as antireflection layers.

The possibility of eliminating reflections is an important prerequisite for the attainability of multi-membered refractive objectives, since otherwise about 10% of reflection occurs per lens surface.

Since no antireflection layers are known for 126 and 109 nm, this is another reason why catadioptric systems with fewer (e.g., 3–5) lenses are preferred.

In the case of achromatization with LiF and NaF , a possibility presents itself of dispensing with crystal-gas boundary surfaces, and thus also with antireflection layers or reflection losses.

The thermal conductivity and the thermal expansion of both materials are very similar:

Thermal conductivity	Expansion
LiF 4.01 W/m/K	$37.0 \cdot 10^{-6}/^\circ\text{C}$
NaF 3.75 W/m/K	$36.0 \cdot 10^{-6}/^\circ\text{C}$

Thus a “cemented member” can be produced by wringing, and contains one each of a + and a – lens, or two + lenses and one – lens. Since the refractive indices of the two crystals are very low and elimination of reflections is therefore difficult, this formation of a cemented member is particularly helpful.

The objective could furthermore consist of CaF_2 lenses, as well as individual cemented members of this kind.

Wring members of CaF_2 and BaF_2 are also possible:

Thermal conductivity	Expansion
CaF_2 19.71 W/m/K	$18.8 \cdot 10^{-6}/^\circ\text{C}$
BaF_2 11.72 W/m/K	$18.1 \cdot 10^{-6}/^\circ\text{C}$

It is just the excellent thermal conductivities of the crystals in comparison with glasses that make such wringing appear more reliable, especially when there is different absorption (and thus heating).

As further crystals, the mixed fluoride crystals are above all suitable, among them those with alkali or alkaline earth and other elements, such as tin, zinc, or aluminum. High dispersion and good light resistance at high transmission in the VUV are the selection criteria here, with the avoidance of birefringence.

The above statements naturally also hold for lenses in a catadioptric objective, particularly also for refractive partial objectives used in these. The objective according to the invention can thus also be catadioptric. It is important that lenses, and not only optical auxiliary elements such as deflecting prisms or plane plates, consist of crystal.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention is described in more detail with reference to the drawings, wherein

FIG. 1 shows a lens section of a 157 nm microlithography projection objective with BaF_2 lenses;

FIG. 2 shows a lens section of a 157 nm microlithography projection objective with NaF lenses and aspherics;

FIG. 3 shows a qualitative picture of a projection exposure equipment for microlithography;

FIG. 4 schematically shows a projection objective with a cemented member; and

FIG. 5 schematically shows a catadioptric projection objective.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Table 1 gives the data for the embodiment example shown in the lens section in FIG. 1.

This relates to a microlithography projection objective for the F₂ excimer laser at 157 nm. By the use of CaF₂ and BaF₂ (for lenses 17, 18, 21, 24, 26, 28, 30), it was possible to realize, at a bandwidth of 0.5 pm, an image field of 8.0×13.0 mm², suitable for stitching, a reduction factor of 4.0:1, a distance from the object Ob to the image Im of 1,000 mm, and with both sides telecentric, a numerical aperture of 0.8. A further increase of the numerical aperture is entirely possible. The color longitudinal errors are reduced by a factor of 3 in comparison with a purely CaF₂ objective. It still amounts to CHL (500 pm)=0.095 mm. This factor can be further increased by means of additional CaF₂—BaF₂ lens pairs. The whole RMS error of the wavefront in the image IM is RMS<13 mλ for all image heights, wherein the markedly reduced wavelength serves as the reference dimension λ.

The refractive indices at the main wavelength λ₀=157.63 nm of the F₂ excimer laser and at a 500 pm distance with λ₁=158.13 are:

n ₀ = 1.5584	n ₁ = 1.5571 for CaF ₂
n ₀ = 1.6506	n ₁ = 1.6487 for BaF ₂
n ₀ = 1.5102	n ₁ = 1.5097 for SrF ₂
n ₀ = 1.4781	n ₁ = 1.4474 for LiF
n ₀ = 1.4648	n ₁ = 1.4629 for NaF
n ₀ = 1.5357	n ₁ = 1.5328 for KF

From this an Abbe number (inverse of dispersion) results:

vCaF ₂ = 1219	vBaF ₂ = 874	vSrF ₂ = 392
vLiF = 674	vNaF = 242	vKF = 184

Thus at 157 nm, BaF₂ has a 40% higher dispersion than CaF₂. In comparison, quartz glass at 193 nm has about 54% of the dispersion of CaF₂.

The projection objective according to FIG. 1 and Table 1 has 39 lenses in all, and a plane parallel closure plate P. Seven negative lenses 17, 18, 21, 24, 26, 28 and 30 are made of BaF₂ for achromatization. The construction is in a direct relationship to the design in the above-mentioned Patent Application DE 19855157.6 (the content of which is also incorporated herein by reference, as a part of the present Application).

In the region of the system diaphragm AS, a third waist T₃, not strongly constricted, is formed at the lens 26, following on the already conventional sequence of bulge B₁ to lens 5, waist T₁ at lens 10, bulge B₂ at lens 15, waist T₂ at lens 18, and bulge B₃ at lens 22, and furthermore followed by bulge B₄. The lens group of lenses 20 through 39, with the double bulge B₃, B₄, is particularly highly developed.

Several overcorrecting air spaces, with greater thickness at the middle than at the edge, are provided as substantial correction means in the region of the diaphragm AS between the lenses 23/24, 26/27 and 29/30, 30/31. This construction

limits the lens diameter even at the highest numerical aperture. The lens radii given in Table 1—and corresponding to the respective greatest beam heights—show that the lens diameter is a maximum of 190 mm at the bulge B₄. The lens diameters are also quite uniformly distributed: from lens 13 in the region of the second bulge B₂ through lens 34 near the image IM, all the lens diameters are between 140 and 190 mm.

The negative BaF₂ lenses 21, 24, 26, 28, 30 are arranged in classical +− pairs alternating with positive CaF₂ lenses 22, 23, 25, 27, 29 in the region of the double bulge B₃, B₄, predominantly before the diaphragm AS, and are supplemented by two negative BaF₂ lenses 17, 18 in the region of the second waist T₂. There results a very effective insertion of the second crystal material for achromatization.

The use of two crystal lens materials according to an advantageous feature of the invention results from objective designs starting from, for example, the German Patent Applications DE 19855108.8 and DE 19855157.6, of like filing date, and known from other sources, in that in a DUV objective (300–180 nm) with preponderantly quartz glass lenses and with CaF₂ lenses preponderantly near the diaphragm and serving for achromatization, the lenses nearest the image IM—corresponding to lenses 38, 39, and the like in FIG. 1—of quartz glass or CaF₂ are now replaced by BaF₂ or SrF₂ lenses. The optical properties of BaF₂ and SrF₂ differ only little from those of quartz glass, and require only routine design changes with an optical design program. The plane plate P can of course also be appropriately made of BaF₂. If however, as a closure and protective element, it is often changed in any case, it can also remain quartz glass (in the above-stated wavelength region).

The embodiment of FIG. 2 shows a 157 nm, full field, scanner projection objective based on CaF₂ lenses, which is achromatized by the use of a total of five negative lenses 218, 219, 220, 221; 232, 233, 234, 235; 236, 237; 249, 250; 257, 258 of NaF in both waists, in the diaphragm space, and in the convergent beam path before the image plane.

A total of three aspheric lens surfaces 211, 221, 257, of which two are of NaF, contribute to good correction in a compact, material-saving construction of the objective.

Imaging scale 1:4, image field diameter 27.2 mm for an 8×26 mm full scanner field, and an image-side numerical aperture of NA=0.77 are important characteristics of the objective; its RMS image error over all image heights is below 16 mλ, with a laser bandwidth of Δλ=±2 pm. The chromatic longitudinal aberration for the comparison value Δλ=500 pm is CHL (500 pm)=0.153 mm. The individual geometric data are collected in Table 2. The largest lens diameter used is 246 mm at lenses 247, 248.

The configuring and use of the aspherics here takes place according to the principles of German Patent Application DE 199 22 209.6 of May 14, 1999 by the same Inventor, which is incorporated herein by reference.

The projection exposure equipment for microlithography schematically shown in FIG. 3 includes as the light source 301 an excimer laser, a device 302 for bandwidth reduction (this device can also be integrated into the laser), an illumination system 303 with a homogenizing and field diaphragm device and the like, a mask holder 304 with a positioning and moving device 314. A projection objective 305 according to the invention includes lenses 315, 325 made of different crystals or fluorides. The object is arranged on an object holder 306 with a positioning and moving device 316. In the embodiment as a scanner, the mask holder and the object holder are moved synchronously at speeds

which differ by the imaging scale. Devices, not shown here, of course also belong to the projection exposure equipment, such as control and adjusting systems, autofocus, wafer and mask changing systems, and air conditioning.

FIG. 4 shows an objective 400 with a "cemented member" 401, i.e., a lens group jointed without an air gap and in this deep UV region held together by wringing, since no radiation resistant cement/adhesive is available. As stated above, such members are appropriate with positive LiF and negative NaF lenses, or with BaF₂ and CaF₂. Further lenses 402 in the objective 400 are then made of, e.g., of CaF₂ or another of the above-described materials.

FIG. 5 shows schematically a catadioptric objective according to the invention, such as is proposed for lithography with 126 nm or 109 nm.

The object Ob is imaged on the image plane Im by means of four mirrors M1–M4 and four lenses L1–L4. A lens L1 is united with the mirror M1 to give a Mangin mirror. This facilitates manufacture and reduces reflection losses and disturbances. The lenses L1, L3, L4, in which the pencil of rays has a large cross section and thus a low intensity, are made of LiF. The lens L2 near the image, used for increasing the numerical aperture, is however exposed to concentrated radiation. Amorphous BeF₂ is used here because of its high radiation resistance.

The catadioptric objective should contain only few lenses, i.e. 1–10, because of absorption and the relatively difficult production of the lens materials. Such microlithographic projection objectives are known, e.g. for 193 nm; see U.S. Pat. No. 4,701,035, FIG. 12, and U.S. Pat. No. 5,815,310, FIG. 3, with NA=0.6 and quartz glass as the lens material. Specific embodiments of objectives according to the invention can be derived, starting from such systems, with advance knowledge of the optical properties of the newly given materials.

For the other objective constructions of the invention, the detailed construction can also be derived from existing designs by means of design programs. The refractive index and dispersion of the materials for the respective operating wavelength are to be used for this.

From the "Handbook of Optics", McGraw-Hill 1995, ch. 33, Properties of Crystals and Glasses, p. 33.64, ref. [125], the dispersion curves are known, for example, for

LiF from 100 nm

NaF from 150 nm, with extrapolation from 130 nm

KF from 150 nm, with extrapolation from 130 nm.

Data on the absorption edges of BaF₂, CaF₂, MgF₂, SrF₂ and LiF are found in GB 1,276,700, relating to a bandpass filter at 130 nm. Optical constants of the above-mentioned antireflection layers can be found, e.g., in M. Zukic et al., Applied Optics 29, No. 28, October 1980, pp. 4284–4292.

The literature references given are of course only examples. The exact optical properties can also be obtained by the measurement of samples with a UV spectrometer.

The Abbe numbers for a few fluorides, and of quartz glass for comparison, are given in Table 3a for the wavelengths of the ArF and F₂ excimer lasers.

The quotients of the Abbe numbers derived from these are given in Table 3b for different crown/flint combinations at 157 nm. A large quotient means a strong color error correction with little flint.

According to this, the combination of crown LiF and flint KF would be ideal. The difficult properties of KF (absorption, water sensitivity) however militate against this.

However, with CaF₂ as the crown, only the combination with NaF can compete with the combinations having LiF as crown.

As soon as the production of lenses is possible as well from LiF as it is from CaF₂, objective constructions with LiF as the crown will be preferred, in combination perhaps with BaF₂ or NaF.

The use of crystal lenses according to the invention also provides the same advantages for catadioptric systems in the wavelength region of 100–200 nm.

A projection exposure equipment with an objective according to the invention corresponds, for example, to the constructions known from the stated Patent Applications and other sources, now of course with the objective according to the invention.

For 157 nm systems, there are provided an F₂ excimer laser with a moderate cost for bandwidth limitation, a matched illumination system, e.g. according to German Patent Application DE 19855196, in each case with fluoride and/or mirror optics, or else, e.g., with the objective according to the invention. Mask and wafer positioning and handling systems are used with the projection objective according to the invention for this purpose.

The aspheric lens surfaces are described in the tables with reference to the formula

$$P(h) = \frac{\delta * h^2}{1 + \sqrt{1 - (1 - EX) * \delta_2 * h^2}} + C_1 h^4 + \dots + C_n h^{2n+2} (\delta + 1/R)$$

where P is the pitch height of the aspheric deviation as a function of the height h with respect to the optical axis. C₁ to C_n are the aspheric constants given in the tables. R is the apex radius.

TABLE 1

Element	Radius of Curvature	Thickness	Material	Lens
Ob	∞	8.646		34.52
1	-89.212	4.219	CaF ₂	38.01
	-16234.578	5.440		
2	-264.742	5.333	CaF ₂	43.32
	252.387	7.720		
3	-660.451	17.777	CaF ₂	50.10
	-140.998	.752		
4	1064.631	16.556	CaF ₂	57.46
	-158.471	.750		
5	334.549	20.500	CaF ₂	61.97
	-185.783	.750		
6	123.299	18.438	CaF ₂	60.05
	6416.942	.250		
7	80.830	6.933	CaF ₂	52.10
	59.684	29.393		
8	-270.673	7.923	CaF ₂	45.95
	-138.947	1.854		
9	-4994.395	6.686	CaF ₂	42.27
	100.936	20.795		
10	-77.364	5.536	CaF ₂	38.79
	138.364	18.752		
11	-102.745	16.748	CaF ₂	
	-267.729	7.811		52.63
12	-130.631	24.060	CaF ₂	
	-118.058	.755		63.21
13	-17113.629	30.658	CaF ₂	
	-185.673	.550		77.37
14	-763.483	14.068	CaF ₂	
	-257.169	.450		81.41
15	538.062	17.501	CaF ₂	
	-524.097	.450		83.64
16	225.158	28.126	CaF ₂	82.00
	-455.940	.450		
17	288.200	5.280	BaF ₂	73.64
	116.070	43.999		
18	-136.780	5.899	BaF ₂	
	596.541	30.232		70.04

TABLE 1-continued

Element	Radius of Curvature	Thickness	Material	Lens
19	-126.579	12.715	CaF ₂	5
	-160.434	.450		
20	1476.691	23.253	CaF ₂	77.54
	-252.721	.450		86.85
21	-2817.234	11.778	BaF ₂	10
	231.190	1.794		
22	231.753	53.989	CaF ₂	90.96
	-192.300	.453		93.26
23	362.633	20.787	CaF ₂	88.11
	-787.951	9.876		
24	-299.764	10.937	BaF ₂	86.45
	190.174	.750		
25	183.395	50.343	CaF ₂	83.31
	-174.748	2.226		15
26	-164.440	10.352	BaF ₂	82.14
	168.479	5.874		81.42
27	206.740	50.425	CaF ₂	82.83
	-153.785	1.751		
28	-154.941	8.763	BaF ₂	84.91
	-1457.609	.700		20
29	254.394	43.058	CaF ₂	87.38
AS	Aperture stop	.000		87.38
	-217.033	9.211		
30	-162.604	12.00	BaF ₂	89.88
	-511.982	32.352		
31	-179.731	19.652	CaF ₂	83.87
	-150.853	1.959		25
32	357.035	16.035	CaF ₂	92.29
	2402.661	.935		
33	141.252	27.158	CaF ₂	86.94
	445.801	.751		
34	121.230	20.012	CaF ₂	75.94
	251.005	.750		30
35	89.189	18.534	CaF ₂	62.04
	183.720	7.397		
36	490.596	13.526	CaF ₂	58.00
	255.332	.750		48.00
37	77.348	8.959	CaF ₂	39.69
	53.225	7.818		35
38	115.034	2.770	CaF ₂	30.44
	27.832	1.250		
39	27.548	14.863	CaF ₂	22.66
	193.984	2.347		
P	∞	1.211	CaF ₂	18.16
IM	∞			17.43

TABLE 2

Element	Radius	Thickness	Material
Ob		17.3892	
2	-134.1462	9.9551	CaF ₂
3	-195.6788	.7000	
4	-265.1348	10.3165	CaF ₂
5	-215.7111	.7000	
6	-1188.4145	12.7743	CaF ₂
7	-266.9759	.7000	
8	768.1676	17.0432	CaF ₂
9	-326.8752	.7000	
10	201.9820	20.6243	CaF ₂
11	-1127.2372 A	.7000	
12	194.8406	10.7431	CaF ₂
13	103.5380	29.2205	
14	-439.7364	7.0000	CaF ₂
15	157.9775	22.6930	
16	-211.6271	7.1822	CaF ₂
17	-176.9514	.7259	
18	-205.5616	7.0000	NaF
19	207.9612	36.0232	
20	-119.6353	7.2489	NaF
21	-413.0417 A	10.3726	
22	-218.9613	19.5719	CaF ₂
23	-153.1211	.7433	
24	-1678.0689	38.5556	CaF ₂

TABLE 2-continued

25	-171.3517	14.2594	
26	390.6431	55.0613	CaF ₂
27	-340.4367	1.0036	
28	170.6572	41.3431	CaF ₂
29	2149.7419	.7000	
30	179.2959	13.8028	CaF ₂
31	122.0160	35.7868	
32	-451.7398	7.0000	NaF
33	181.5824	30.6167	
34	-161.3435	7.0000	NaF
35	163.5622	41.2995	
36	-111.4273	7.1203	NaF
37	736.5475	19.4954	
38	-304.5919	18.3054	CaF ₂
39	-195.3438	.7785	
40	-1945.5147	28.2366	CaF ₂
41	-231.5183	.8597	
42	622.3005	42.0816	CaF ₂
43	-517.5539	.0001	
AB		2.8420	
45	856.7969	32.8647	CaF ₂
46	-609.0558	.8543	
47	328.0241	39.3550	CaF ₂
48	-810.7543	33.1869	
49	-246.7339	9.3143	NaF
50	-513.0495	15.0989	
51	-342.1676	18.9964	CaF ₂
52	-240.4190	.9015	
53	142.3229	36.3765	CaF ₂
54	358.3715	2.9965	
55	131.5538	23.5624	CaF ₂
56	257.3044	15.9366	
57	-1240.0410 A	10.0142	NaF
58	269.2267	.7289	
59	113.1907	23.1921	CaF ₂
60	47.2686	2.3140	
61	46.5346	30.1367	CaF ₂
61	354.0845	.158942	
IM			
Aspheric Constants			
21	A 1) -.15637086E+03	2) .14048141E-07	3) .22009617E-11
	4) -.29916689E-16	5) .27054723E-19	6) -.37664501E-23
57	A 1) -.95744229E+00	2) .13628853E-07	3) -.22507210E-11
	4) -.13590312E-16	5) -.18134368E-19	6) .24243733E-23
	7) -.23291310E-27		
	A 1) .00000000E+00	2) .46722013E-08	3) -.80987234E-13
	4) .22189307E-16	5) .16469029E-20	

TABLE 3a

Abbe Numbers		
Wavelength	193.63 nm	157.63 nm
LiF	1344.27	674.56
CaF ₂	1024.36	436.94
SrF ₂	954.39	391.89
BaF ₂	807.43	344.42
SiO ₂	714.96	274.61
NaF	705.92	242.51
KF	648.04	184.19
Definition		
	$\nu_{193} = \frac{n_{193.304} - 1}{n_{193.304} - n_{193.804}}$	
	$\nu_{157} = \frac{n_{157.63} - 1}{n_{157.63} - n_{157.13}}$	

TABLE 3b

Dispersion Comparison 157 nm		
Flint	Crown LiF	Crown CaF ₂
CaF ₂	1.549	—
SrF ₂	1.721	1.115
BaF ₂	1.959	1.269
NaF	2.782	1.802
KF	3.662	2.372

I claim:

1. An objective consisting of:
 - a plurality of lenses comprised of at least two different crystals,
 - a plurality of additional lenses of vitreous material,
 - wherein said vitreous material comprises quartz glass or amorphous BeF₂.
2. A projection objective for microlithography, corrected for illumination with a F₂ excimer laser at 157 nm, wherein said projection objective is purely refractive and consists only of crystal lenses, at least one lens of said crystal lenses comprising a material selected from the group consisting of BaF₂, SrF₂, NaF, LiF, and KF, and at least one CaF₂ lens.
3. The projection objective according to claim 2, including at least one negative lens selected from the group consisting of BaF₂, SrF₂ and NaF.
4. The projection objective according to claim 2, comprising positive lenses of CaF₂ and individual negative lenses of CaF₂.
5. The projection objective according to claim 2, wherein a numerical aperture on an image side of said projection objective is greater than 0.5.
6. The projection objective according to claim 5, wherein said numerical aperture is greater than 0.6.
7. A process for production of microstructured components, comprising exposing a substrate provided with a photosensitive layer via a mask and a projection exposure equipment comprising a 157 nm wavelength ultraviolet light source and a refractive projection objective according to claim 2, and
 - structuring an image on said photosensitive layer corresponding to a pattern contained on said mask.
8. A refractive projection objective for microlithography, corrected for illumination with wavelengths below 360 nm, comprising a plurality of lenses of quartz glass, wherein at least one of two lenses nearest to an image plane of said objective comprises crystal other than CaF₂.
9. The objective according to claim 8, wherein said objective comprises a microlithographic projection objective, corrected for laser illumination with a wavelength below 360 nm, wherein most of said lenses comprise quartz glass, a plurality of positive lenses comprise CaF₂ for achromatization, and at least one lens on an image side of said objective comprises BaF₂, SrF₂ or another fluoride in order to prevent a compaction effect.
10. The objective according to claim 9, wherein said plurality of CaF₂ positive lenses are in the neighborhood of a system diaphragm of said objective.
11. The objective according to claim 9, wherein said plurality of CaF₂ positive lenses are in the neighborhood of a system diaphragm of said objective.
12. A projection objective for microlithography with a working wavelength of 100–180 nm, comprising lenses of at least two materials selected from the group consisting of CaF₂, BaF₂, LiF, NaF, SrF₂, KF, and from amorphous BeF₂.

13. A projection objective for microlithography, comprising a catadioptric objective with a working wavelength of 100–130 nm, having a plurality of lenses of LiF or amorphous BeF₂.

14. An achromatic lens group comprising a plurality of wrung-together lenses of different fluorides.

15. A projection objective comprising at least one achromatic lens group according to claim 14.

16. A process for production of microstructured components, comprising exposing a substrate provided with a photosensitive layer via a mask and a projection exposure equipment comprising a 157 nm wavelength ultraviolet laser light source and a refractive projection objective comprising at least one achromatic lens group according to claim 14, and

structuring an image on said photosensitive layer corresponding to a pattern contained on said mask.

17. An achromatic lens group comprising a plurality of wrung-together lenses of different fluorides, wherein said lenses comprise NaF and LiF or CaF₂ and BaF₂.

18. An objective comprising a plurality of lenses, first lenses of the plurality of lenses being made of a fluoride crystal of a first group consisting of CaF₂, BaF₂, SrF₂, LiF, NaF and KF, second lenses of the plurality of lenses being made of a fluoride crystal of a second group consisting of SrF₂, LiF, NaF and KF.

19. The objective according to claim 18, wherein at least one lens has an aspheric surface.

20. The objective according to claim 18, wherein said lenses have a thin layer comprising an anti-reflection coating of MgF₂ or LaF₃.

21. The objective according to claim 18, comprising a plurality of converging lenses and at least one diverging lens of a material having a refractive index lower than an average refractive index of materials used in converging lenses.

22. A projection exposure equipment for microlithography, comprising:

a light source comprising an excimer laser with 100–160 nm wavelength,

an illumination system comprising refractive optical elements comprising one or more fluorides,

a reticle positioning and movement system,

a projection objective with a plurality of lenses comprising at least two lenses of crystalline materials, one crystalline material selected from a first group comprising CaF₂, BaF₂, LiF, NaF, SrF₂, KF and another crystalline material selected from a second group consisting of LiF, NaF, SrF₂, KF and amorphous BeF₂, and an object positioning and movement system.

23. The projection exposure equipment according to claim 22, wherein said light source comprises an excimer laser with 109, 126, 134, 146 or 157 nm wavelength.

24. A microlithographic projection exposure equipment including a 157 nm light source and a refractive projection objective corrected for a bandwidth provided by a laser and having a finite distance between an object and an image plane comprising a plurality of lenses of at least two different crystals.

25. The projection exposure equipment according to claim 24, that is designed for a stitching process.

26. An objective comprising a plurality of lenses, at least one of said lenses comprising amorphous BeF₂.

27. A projection objective for microlithography, corrected for illumination with a F₂ excimer laser at 157 nm, wherein said projection objective is purely refractive and comprises a plurality of lenses of a material selected from the group consisting of SrF₂, NaF, LiF, and KF.

15

28. The projection objective according to claim 27, further comprising at least one CaF_2 lens.

29. The projection objective according to claim 27, including at least one negative lens selected from the group consisting of BaF_2 , SrF_2 and NaF .

30. The projection objective according to claim 28, comprising positive lenses of CaF_2 and individual negative lenses of CaF_2 .

31. A refractive projection objective for microlithography, corrected for illumination with wavelengths at or below 248 mm, comprising a plurality of lenses of quartz glass, wherein at least one of two lenses nearest to an image plane of said objective comprises crystal.

32. The refractive projection objective according to claim 31, wherein said crystal is selected from the group consisting of CaF_2 , SrF_2 and BaF_2 .

33. An objective comprising:

a plurality of lenses comprised of at least two different crystals,

a plurality of additional lenses of amorphous BeF_2 .

34. A projection objective for microlithography with a working wavelength of 100–180 nm, comprising lenses of at least two materials selected from the group consisting of

16

CaF_2 , BaF_2 , LiF , NaF , SrF_2 , KF , and from amorphous BeF_2 , excluding a combination of CaF_2 and LiF .

35. A projection objective for microlithography with a working wavelength of 100–180 nm, consisting of lenses of at least two materials selected from the group consisting of CaF_2 , BaF_2 , LiF , NaF , SrF_2 , KF , and from amorphous BeF_2 .

36. An objective consisting of a plurality of lenses, first lenses of the plurality of lenses being made of a fluoride crystal of a first group consisting of CaF_2 , BaF_2 , SrF_2 , LiF , NaF and KF , second lenses of the plurality of lenses being made of a fluoride crystal of a second group consisting of SrF_2 , LiF , NaF and KF .

37. An objective comprising a plurality of lenses, first lenses of the plurality of lenses being made of a fluoride crystal of a first group consisting of CaF_2 , BaF_2 , SrF_2 , LiF , NaF and KF , second lenses of the plurality of lenses being made of a fluoride crystal of a second group consisting of SrF_2 , LiF , NaF and KF except the combination of CaF_2 and LiF .

38. The refractive projection objective according to claim 8, wherein said crystal is selected from the group consisting of CaF_2 , SrF_2 and BaF_2 .

* * * * *