



US006800927B2

(12) **United States Patent**
Noble et al.

(10) **Patent No.: US 6,800,927 B2**
(45) **Date of Patent: Oct. 5, 2004**

(54) **MULTIPLE OXIDE THICKNESSES FOR
MERGED MEMORY AND LOGIC
APPLICATIONS**

(75) Inventors: **Wendell P. Noble**, Milton, VT (US);
Leonard Forbes, Corvallis, OR (US)

(73) Assignee: **Micron Technology, Inc.**, Boise, ID
(US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 191 days.

(21) Appl. No.: **10/140,296**

(22) Filed: **May 6, 2002**

(65) **Prior Publication Data**

US 2002/0127797 A1 Sep. 12, 2002

Related U.S. Application Data

(62) Division of application No. 09/386,185, filed on Aug. 31,
1999, now Pat. No. 6,383,871.

(51) **Int. Cl.**⁷ **H01L 29/04**

(52) **U.S. Cl.** **257/628; 257/302; 257/627;**
438/198; 438/270

(58) **Field of Search** 257/301, 302,
257/316, 627, 628; 438/270, 198, 275,
769, 770

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,999,282 A	12/1976	Ono et al.	29/571
4,466,178 A	8/1984	Soclof	29/576 B
4,651,188 A	3/1987	Hayashi et al.	357/38
4,667,215 A	5/1987	Kawamura et al.	357/38
4,768,076 A	8/1988	Aoki et al.	357/42
4,833,516 A	5/1989	Hwang et al.	357/23.6
4,857,986 A	8/1989	Kinugawa	357/42
5,082,795 A	1/1992	Temple	437/41
5,192,680 A *	3/1993	Naruse et al.	257/E21.09
5,196,722 A	3/1993	Bergendahl et al.	257/304

5,364,810 A	11/1994	Kosa et al.	437/52
5,371,383 A	12/1994	Miyata et al.	257/77
5,583,368 A	12/1996	Kenney	257/621
5,770,878 A	6/1998	Beasom	257/330
5,801,089 A	9/1998	Kenney	438/589
5,883,012 A	3/1999	Chiou et al.	438/748
5,888,880 A	3/1999	Gardner et al.	438/424
5,904,543 A	5/1999	Wang	438/444
5,907,170 A	5/1999	Forbes et al.	257/296
5,915,180 A	6/1999	Hara et al.	438/270
5,991,225 A	11/1999	Forbes et al.	365/230.06
5,998,263 A	12/1999	Sekariapuram et al.	438/259
6,015,737 A	1/2000	Tokura et al.	438/270
6,066,869 A	5/2000	Noble et al.	257/296
6,072,209 A	6/2000	Noble et al.	257/296
6,097,065 A	8/2000	Forbes et al.	257/350

(List continued on next page.)

OTHER PUBLICATIONS

Balk, P., "Orientation Dependence of Built-In Surface
Charge on Thermally Oxidized Silicon", *IEEE*, 53, (1965),
pp. 2133-2134.

(List continued on next page.)

Primary Examiner—Kamand Cuneo


Assistant Examiner—Lisa Kilday

(74) *Attorney, Agent, or Firm*—Schwegman, Lundberg,
Woessner & Kluth, P.A.

(57) **ABSTRACT**

Structures are provided for multiple oxide thicknesses on a
single silicon wafer. In particular, structures are provided for
multiple gate oxide thicknesses on a single chip. The chip
can include circuitry including but not limited to the
memory and logic technologies. These structures for mul-
tiple oxide thickness on a single silicon wafer can be used in
conjunction with existing fabrication and processing tech-
niques with minimal or no added complexity. One structure
includes a top layer of SiO₂ on a top surface of a silicon
wafer and a trench layer of SiO₂ on a trench wall of the
silicon wafer. The trench wall of the silicon wafer has a
different order plane-orientation than the top surface. The
thickness of the top layer is different from a thickness of the
trench layer.

29 Claims, 9 Drawing Sheets



U.S. PATENT DOCUMENTS

6,255,684 B1 7/2001 Roesner et al. 257/302
 6,320,215 B1 * 11/2001 Bronner et al. 257/301
 6,358,867 B1 * 3/2002 Tews et al. 257/E21.193
 6,362,494 B1 * 3/2002 Yagi 257/76

OTHER PUBLICATIONS

Carr, W.N., et al., *In: MOS/LSI Design and Application*, McGraw-Hill Book Company, New York, (1972), pp. 37, 49-52.

Crowder, S., et al., "Trade-offs in the Integration of High Performance Devices with Trench Capacitor DRAM", *Dig. Int. Electron Devices Meeting Washington, D.C.*, (Dec. 1997), pp. 45-48.

Deal, B.E., et al., "Characteristics of the Surface-State Charge (Q) of Thermally Oxidized Silicon", *J. Electrochem. Soc.: Solid State Science*, (1967), pp. 266-274.

Hodges, D.A., et al., *In: Analysis and Design of Digital Integrated Circuits, Second Edition*, McGraw-Hill, Inc., New York, (1988), p. 342-344.

Irene, E.A., "The Effects of Trace Amounts of Water on the Thermal Oxidation of Silicon in Oxygen", *Journal of the Electrochemical Society: Solid-State Science and Technology*, (1974), pp. 1613-1616.

Kim, Han-Soo., et al., "The 600V Rating n-ch Trench IGBT with the Low Leakage Current and the High Channel Mobility Using the (101) Oriented Trench Sidewall", *IEEE*, Doc. No. 0-7803-3993-2/97, (1997), 265-268.

King, Y., et al., "Sub-5nm Multiple-Thickness Gate Oxide Technology Using Oxygen Implantation", *IEDM Technical Digest*, (1998), pp. 585-588.

Liu, C.T., et al., "Multiple Gate Oxide Thickness for 2GHz System-on-A-Chip Technologies", *IEDM Technical Digest*, (1998), pp. 589-592.

Peirret, R.F., *Semiconductor Fundamentals, Second Edition*, Modular Series on Solid State Devices, vol. 1, Pierret, R.F., et al., (eds.), Addison-Wesley Publishing Co., Reading, MA, (Apr., 1989), p. 3-13.

Petti, C.J., et al., "Characterization of Surface Mobility on the Sidewalls of Dry-Etched Trenches", *IEEE IEDM '88*, (1988), 104-107.

Sato, T., et al., "Drift-Velocity Saturation of Holes in Si Inversion Layers", *J. Phys. Soc. Japan*, 31(6), (1971), p. 1846.

Shenai, K., "A 55-V, 0.2-microhm-cm² Vertical Trench Power MOSFET", *IEEE Electron Device Letters*, 12, (Mar., 1991), 108-110.

Shenai, K., "Electron Mobilities in MOS Channels Formed Along Anisotropically Dry Etched <110> Silicon Trench Sidewalls", *Electronics Letters*, 27, (Apr. 25, 1991), 715-717.

Theil, J.A., "Deep Trench Fabrication by Si (110) Orientation Dependent Etching", *Journal of Vacuum Science & Technology B: Microelectronics and Nanometer Structures*, Abstract, obtained from <http://ojps.aip.org/>, (Sep., 1995), 1 p.

Togo, M., et al., "Multiple-Thickness Gate Oxide and Dual-Gate Technologies for High Performance Logic-Embedded DRAMs", *IEDM Technical Digest*, (1998), pp. 347-350.

Vitkavage, S.C., et al., "An investigation of Si-SiO₂ interface charges in thermally oxidized (100), (110), (111), and (511) silicon", *J. Appl. Phys.*, 68(10), (1990), pp. 5262-5272.

* cited by examiner




FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2



FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 5




FIG. 6




FIG. 7






FIG. 8



MULTIPLE OXIDE THICKNESSES FOR MERGED MEMORY AND LOGIC APPLICATIONS

RELATED APPLICATIONS

This application is a Divisional of U.S. application Ser. No. 09/386,185, filed Aug. 31, 1999 now U.S. Pat. No. 6,383,871 which is incorporated herein by reference.

FIELD OF THE INVENTION

The present invention relates generally to integrated circuits. In particular, the present invention relates to a method and structure for oxide thicknesses on Metal Oxide Semiconductor Field Effect Transistor (MOSFET) technology for merged memory and logic applications.

BACKGROUND OF THE INVENTION

Typically, memory, e.g., Dynamic Random Access Memory (DRAM), and logic technologies have evolved along separate but parallel paths. In memory technology, for any particular lithography and power supply voltage level generation, the gate oxide thickness is limited by thin oxide reliability due to the stress of voltage boosted word lines. In contrast, for logic technology, thinner gate oxide thicknesses are generally the standard because of the need for high transconductance at lower internal operating voltages. Therefore, efforts to merge the technologies of memory and logic onto a single chip to create a "system on a chip" or other high function memory thus create a dilemma. That is, one is faced with the design choice of either (1) compromising the gate oxide thickness for one and/or both types of devices or (2) assuming the litany of complexities and expenses associated with the growing of two separate types of gate oxides on a single chip.

One current approach has been proposed that does provide a method of fabrication which allows for the scalable gate oxide thicknesses by either implanting Ar^+ or N^+ into a substrate prior to oxidation or implanting O^+ into the substrate after gate deposition. While this approach does facilitate gate oxide scalability when compared to conventional process integration, this technique does not provide a total solution since additional steps as well as expensive process tools are required. Accordingly, more advanced methods are still needed for providing multiple gate oxide thicknesses on a single chip. Desirably these more advanced methods will use existing MOSFET and DRAM processing techniques, thus avoiding any additional complexity in the wafer fabrication process. For these and other reasons there is a need for the present invention.

SUMMARY OF THE INVENTION

The above-mentioned problems with memory and logic technologies and other problems are addressed by the present invention and will be understood by reading and studying the following specification. Structures and methods are described which accord improved benefits for merged memory and logic applications.

Improved methods and structures are provided for multiple oxide thickness on a single silicon wafer. In particular, improved methods and structures are provided for multiple gate oxide thickness on a single chip which includes circuitry encompassing a range of technologies. For example, this range of technologies can include but is not limited to the memory and logic technologies. Moreover, these improved methods and structures for multiple oxide thick-

ness on a single silicon wafer can be used in conjunction with existing fabrication and processing techniques with minimal or no added complexity.

Embodiments of a method for forming a semiconductor device include forming a top layer of SiO_2 (silicon dioxide) on a top surface of a silicon wafer. A trench layer of SiO_2 is also formed on a trench wall of the silicon wafer. The trench wall of the silicon wafer has a different order crystal plane-orientation than the top surface. Additionally, the formation of the top and trench layers of SiO_2 are such that a thickness of the top layer is different from a thickness of the trench layer.

One method of the present invention provides for forming a semiconductor device. Another method includes forming a DRAM that can include a trench capacitor or a stacked capacitor. Moreover, other embodiments provide for forming a Non-Volatile Random Access Memory (NVRAM) device, a flash memory device as well as a programmable logic array. The present invention also includes systems incorporating these different devices and circuits all formed according to the methods provided in this application.

These and other embodiments, aspects, advantages, and features of the present invention will be set forth in part in the description which follows, and in part will become apparent to those skilled in the art by reference to the following description of the invention and referenced drawings or by practice of the invention. The aspects, advantages, and features of the invention are realized and attained by means of the instrumentalities, procedures, and combinations particularly pointed out in the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1A–1C illustrate an embodiment of a process of fabrication of oxide layers on a silicon wafer.

FIG. 2 is a graph that illustrates an oxide thickness vs. time of oxidation for different silicon crystalline plane orientations.

FIGS. 3A–3C illustrate another embodiment of a process of fabrication of oxide layers on a silicon wafer.

FIGS. 4A–4C illustrate an alternate embodiment of a process of fabrication of oxide layers on a silicon wafer.

FIG. 5 is a cross-sectional view of an embodiment of oxide layers on a silicon wafer according to the teachings of the present invention.

FIG. 6 is a perspective view illustrating generally one embodiment of a portion of vertical MOSFETs used in conjunction with embodiments of the present invention.

FIG. 7 is a perspective view illustrating generally another embodiment of a portion of memory used in conjunction with embodiments of the present invention.

FIG. 8 is a perspective view illustrating generally an alternative embodiment of a portion of memory used in conjunction with embodiments of the present invention.

FIG. 9 is a perspective view illustrating an embodiment of a portion of non-volatile memory used in conjunction with embodiments of the present invention.

FIG. 10 is a block diagram which illustrates an embodiment of a system according to teachings of the present invention.

DETAILED DESCRIPTION

In the following detailed description of the invention, reference is made to the accompanying drawings which form a part hereof, and in which is shown, by way of

illustration, specific embodiments in which the invention may be practiced. In the drawings, like numerals describe substantially similar components throughout the several views. These embodiments are described in sufficient detail to enable those skilled in the art to practice the invention. Other embodiments may be utilized and structural, logical, and electrical changes may be made without departing from the scope of the present invention.

The terms wafer and substrate used in the following description include any structure having an exposed surface with which to form the integrated circuit (IC) structure of the invention. The term substrate is understood to include semiconductor wafers. The term substrate is also used to refer to semiconductor structures during processing, and may include other layers that have been fabricated thereupon. Both wafer and substrate include doped and undoped semiconductors, epitaxial semiconductor layers supported by a base semiconductor or insulator, as well as other semiconductor structures well known to one skilled in the art. The term conductor is understood to include semiconductors, and the term insulator is defined to include any material that is less electrically conductive than the materials referred to as conductors. Moreover, the term forming is understood to include growing through thermal oxidation, as is known in the art. The following detailed description is, therefore, not to be taken in a limiting sense, and the scope of the present invention is defined only by the appended claims, along with the full scope of equivalents to which such claims are entitled.

In particular, an illustrative embodiment of the present invention includes a method for forming a semiconductor device. The method includes forming a top layer of SiO_2 on a top surface of a silicon wafer. A trench layer of SiO_2 is also formed on a trench wall of the silicon wafer. Additionally, the trench wall of the silicon wafer has a different order plane-orientation than the top surface. The formation of the top and trench layer of SiO_2 is such that a thickness of the top layer is different from a thickness of the trench layer.

Another embodiment of the present invention includes a method for forming a semiconductor device. This method includes forming a top surface of a silicon wafer with a top crystalline plane orientation. A trench is also formed in the silicon wafer such that a trench wall has a different crystalline plane orientation than the top crystalline plane orientation of the top surface. Moreover, a top oxide layer is thermally grown on the top surface while a trench oxide layer is simultaneously thermally grown on the trench wall during a linear growth period. These two oxide layers are formed such that the top oxide layer has a different thickness than the trench oxide layer.

An alternate method embodiment of the present invention includes forming a DRAM. The method includes forming a top layer of SiO_2 on a top surface of a silicon wafer in which the top surface has a (100) crystal plane and a top thickness. Additionally, a trench layer of SiO_2 is formed on a trench wall of the silicon wafer. This trench wall has a (110) crystal plane. Moreover, the trench layer has a trench thickness that is different from the top thickness of the top surface of the silicon wafer.

Another method embodiment of the present invention includes forming a semiconductor device. The method includes forming a trench in a silicon wafer. In particular, the silicon wafer has a top surface that has a (100) crystal plane. Moreover, the trench has a trench wall that has a (110) crystal plane. The method also includes simultaneously thermally oxidizing the top surface to a top thickness while

oxidizing the trench wall to a trench thickness that is different from the top thickness.

An additional method embodiment of the present invention includes forming a DRAM. This method includes forming a top device on a top surface of a silicon wafer. In particular the top surface has a (100) crystal plane and the top device includes a top gate separated from the (100) crystal plane by a top gate oxide. Moreover, the method includes the formation of a second device on a trench surface in the silicon wafer with the trench surface having a (110) crystal plane. The second device includes a second gate separated from the (110) crystal plane by a second gate oxide. Additionally, formation of the devices is such that a thickness of the top gate oxide is different from a thickness of the second gate oxide.

Another embodiment of the present invention includes a method for forming a stacked capacitor DRAM cell. This method includes forming a top device on a top surface of a silicon wafer. In particular, the top surface has a (100) crystal plane, and the top device includes a top gate separated from the (100) crystal plane by a top gate oxide. The method also includes the formation of a trench in the silicon wafer such that a trench wall of the trench has a (110) crystal plane. A second device is also formed on the trench wall of the trench in which the second device includes a second gate separated from the (110) crystal plane by a second gate oxide. Moreover, the formation of these devices is such that the top gate oxide has a thickness which is different from a thickness of the second gate oxide.

Another method embodiment of the present invention includes forming a Non-Volatile Random Access Memory (NVRAM) device. This method includes forming a top layer of SiO_2 on a top surface of a silicon wafer. The top surface has a (111) crystal plane orientation, and the top layer has a top thickness. Additionally, a trench layer of SiO_2 is formed on a trench wall of the silicon wafer. The trench wall has a (110) crystal plane orientation. Furthermore, the formation of the layers is such that the trench layer has a trench thickness that is different from the top thickness of the top layer.

An alternate method embodiment of the present invention includes forming a flash memory device. The method includes forming a top surface of a silicon wafer with a (111) crystalline plane orientation. A trench in the silicon wafer is also formed in which a trench wall has a (110) crystalline plane orientation. Additionally, a formation of a top oxide layer on the top surface occurs simultaneously with the formation of a trench oxide layer on the trench wall during a linear growth period. Moreover, the formation of the layers is such that the top oxide layer has a different thickness than the trench oxide layer.

A method embodiment of the present invention includes forming a CMOS logic circuit. The method includes forming a top layer of SiO_2 on a top surface of a silicon wafer. The top surface has a (111) crystalline orientation, and the top layer has a top thickness. Additionally, a trench layer of SiO_2 is formed on a trench wall of the silicon wafer. The trench wall has a (110) crystalline orientation and the trench layer has a trench thickness that is different from the top thickness of the top layer.

Another method embodiment of the present invention includes forming a semiconductor device. In particular, this method includes forming a top layer of SiO_2 on a top surface of a silicon wafer. The top surface has a (110) crystalline plane orientation, and the top layer has a top thickness. Moreover, a trench layer of SiO_2 is formed on a trench wall

5

of the silicon wafer. The trench wall has a (311) surface, and the trench layer has a trench thickness that is different from the top thickness of the top layer. Additionally, the formation of the layers of SiO₂ is such that the layers are formed simultaneously during a linear growth period.

An alternate method embodiment of the present invention includes forming a semiconductor device. The method includes forming a top surface of a silicon wafer in which the top surface has a (110) crystalline plane orientation. Additionally, a trench is formed in the silicon wafer, such that a trench wall has a (511) crystalline plane orientation. The method also includes the thermally growth simultaneously of a top oxide layer on the top surface and a trench oxide layer on the trench wall, during a linear growth period, wherein the top oxide layer has a different thickness than the trench oxide layer.

Another method embodiment of the present invention includes forming a programmable logic array. The method includes forming a logic device on a top surface of a silicon wafer in which the top surface has a (100) crystal plane. The logic device includes a logic gate separated from the top surface by a logic gate oxide. The method also includes forming an Electronically Erasable Programmable Read Only Memory (EEPROM) device on a trench wall of the silicon wafer. The trench wall has a different order plane-orientation than the top surface, and the EEPROM device includes an EEPROM gate separated from the trench wall by an EEPROM gate oxide. In one embodiment, the EEPROM gate includes a floating gate for the EEPROM device. Additionally, the logic gate oxide has a thickness which is different from a thickness of the EEPROM gate oxide.

An apparatus embodiment of the present invention includes a semiconductor device. The semiconductor device includes a top device formed on a top surface of a silicon wafer. The top surface has a (110) crystal plane, and the top device has a top gate separated from the (110) crystal plane by a top gate oxide. Moreover, the semiconductor device includes a trench device formed on a trench wall of the silicon wafer. In particular, the trench wall has a (100) crystal plane, and the trench device has a trench gate separated from the trench wall by a trench gate oxide in which a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

Another apparatus embodiment of the present invention includes a DRAM. The DRAM includes a top oxide layer formed on a top surface of a silicon wafer. The top surface has a (110) crystalline orientation, and the top oxide layer has a top oxide thickness. Moreover, the DRAM includes a trench oxide layer formed on a trench wall of the silicon wafer in which the trench wall has a (100) crystalline orientation. Additionally, the trench oxide layer has a trench oxide thickness that is different from the top oxide thickness.

An alternative apparatus embodiment of the present invention includes a semiconductor device. The semiconductor device includes a top surface of a silicon wafer. The top surface has a (110) surface. Moreover, the semiconductor device includes a trench wall in the silicon wafer in which the trench wall has a (511) surface. The semiconductor also includes a top oxide layer on the top surface as well as a trench oxide layer on the trench wall. In particular, the top oxide layer and the trench oxide layer are thermally grown simultaneously during a linear growth period, wherein the top oxide layer has a different thickness than the trench oxide layer.

Another apparatus embodiment of the present invention includes a flash memory device. The flash memory device

6

includes a logic device formed on a top surface of a silicon wafer. The top surface has a (111) crystal plane orientation, and the logic device has a logic gate separated from the top surface by a logic gate oxide. The flash memory device also includes a flash memory cell formed on a trench wall of the silicon wafer, wherein the trench wall has a (110) crystal plane orientation. In particular, the flash memory cell has a flash gate separated from the trench wall by a flash gate oxide, wherein a thickness of the logic gate oxide is different from a thickness of the flash gate oxide.

An alternative apparatus embodiment of the present invention includes a semiconductor device. The semiconductor device includes a top layer of SiO₂ on a top surface of a silicon wafer. Additionally, the semiconductor device includes a trench layer of SiO₂ on a trench wall of the silicon wafer. In particular, the trench wall has a different order plane-orientation than the top surface, and the top layer has a different thickness than the trench layer.

An additional apparatus embodiment of the present invention includes a programmable logic array. The programmable logic array includes a logic device formed on a top surface of a silicon wafer in which the top surface has a (110) crystal plane orientation. Additionally, the logic device has a logic gate separated from the top surface by a logic gate oxide. The programmable logic array also includes an Electronically Erasable Programmable Read Only Memory (EEPROM) device formed on a trench wall of the silicon wafer. The EEPROM device has an EEPROM gate separated from the trench wall by an EEPROM gate oxide. Moreover, the trench wall has a different order plane-orientation than top surface, and a thickness of the logic gate oxide is different from a thickness of the EEPROM gate oxide.

Another apparatus embodiment of the present invention includes an electronic system. The electronic system includes a processor as well as an integrated circuit coupled to the processor. The integrated circuit includes a top device formed on a top surface of a silicon wafer in which the top surface has a (110) crystal plane orientation, and the top device has a top gate separated from the top surface by a top gate oxide. The integrated circuit of the electronic system also includes a trench device formed on a trench wall of the silicon wafer. The trench wall has a (100) crystal plane orientation, and the trench device has a trench gate separated from the trench wall by a trench gate oxide. Moreover, a thickness of the top gate oxide is different from a thickness of the trench gate oxide, and the top gate oxide and the trench gate oxide are thermally grown simultaneously during a linear growth period.

An alternative apparatus embodiment of the present invention includes an electronic system. The electronic system includes a processor as well as a flash memory device. The flash memory device includes a logic device formed on a top surface of a silicon wafer. The top surface has a (111) crystal plane orientation, and the logic device has a logic gate separated from the top surface by a logic gate oxide. The flash memory device of the electronic system also includes a flash memory cell formed on a trench wall of the silicon wafer in which the trench wall has a (110) crystal plane orientation. The flash memory cell has a flash gate separated from the trench wall by a flash gate oxide. In one embodiment, the flash gate includes a floating gate for the flash memory cell. Additionally, a thickness of the flash gate oxide is different from the logic gate oxide.

Another apparatus embodiment of the present invention includes an electronic system. The electronic system

includes a processor as well as a decode circuit. The decode circuit includes a logic circuit formed on a top surface of a silicon wafer in which the top layer has a (110) crystal plane orientation. Additionally, the logic circuit has a logic gate separated from the top layer by a logic gate oxide. The decode circuit of the electronic system includes an EEPROM device formed on a trench wall of the silicon wafer. The EEPROM device has an EEPROM gate separated from the trench wall by an EEPROM gate oxide in which the trench wall has a different order plane-orientation than top surface. Moreover, a thickness of the EEPROM gate oxide is different from a thickness of the logic gate oxide.

FIGS. 1A–1C illustrate an embodiment of a process of fabrication of oxide layers on a silicon wafer according to teachings of the present invention. The sequence can be followed as a method for forming a semiconductor device, as a method for forming a DRAM that can include a trench capacitor or a stacked capacitor, as a method for forming a Non-Volatile Random Access Memory (NVRAM), e.g., a flash memory device, as a method for forming a CMOS logic circuit as well as a method for forming a programmable logic array.

FIG. 1A shows the structure subsequent to the formation of a trench **130** in a silicon wafer **110**, the processing of which is well known in the art. The silicon wafer **110** has a top surface **120**. In one embodiment, the top surface **120** of a silicon wafer **110** is formed with a specific top crystalline plane orientation. In one embodiment, the top surface **120** has a (100) crystalline plane orientation. In another embodiment, the top surface **120** has a (110) crystalline plane orientation. In an additional embodiment, the top surface **120** has a (111) crystalline plane orientation. Other specific top crystalline plane orientations are similarly included which are suited to carry out the embodiments of the present invention. One of ordinary skill in the art will appreciate upon reading this disclosure the top crystalline plane orientations suited to carry out the novel embodiments of the present invention.

FIG. 1B illustrates the structure following the next sequence of processing. A top layer of SiO₂ (silicon dioxide) **140** is formed on the top surface **120** of the silicon wafer **110**. One of ordinary skill in the art will appreciate the masking and etching techniques by which an isolated top layer of SiO₂ **140** can be defined as shown in FIG. 1B. In one embodiment, a thickness (t_{TOP}) of the top layer of SiO₂ **140** is approximately 70 Angstroms. In this embodiment, a width (w_{TOP}) is defined suitable for serving as a gate oxide layer. In one embodiment, the top layer of SiO₂ **140** is defined with a t_{TOP} and a w_{TOP} suitable for use as a gate oxide in logic device applications.

In one embodiment, the top layer of SiO₂ **140** is formed on the top surface **120** through dry oxidization at a temperature of approximately 800° C. In an alternative embodiment, the top layer of SiO₂ **140** is formed on the top surface **120** through wet oxidization at a temperature of approximately 800° C. One of ordinary skill in the art will understand other method embodiments suitable to form the top layer of SiO₂ **140** according to the teachings of the present invention.

FIG. 1C illustrates the structure following the next sequence of processing. A trench layer of SiO₂ **150** is formed on a trench wall **160** of the silicon wafer **110**. According to the teachings of the present invention, the trench wall **160** is formed having a specific crystalline plane orientation different from that of the top surface **120**. In one embodiment,

the trench wall **160** has a different plane orientation than the top surface **120**. For example, when the top surface **120** is formed having a (100) surface, the trench wall **160** is formed having a (110) surface. Other specific crystalline plane orientations of the trench wall are similarly included which are suited to carry out the embodiments of the present invention. One of ordinary skill in the art will appreciate upon reading this disclosure the crystalline plane orientations of the trench wall suited to carry out the novel embodiments of the present invention. Moreover, the crystalline plane orientations of the trench wall **160** are controlled to have a specific orientation in relationship to the crystalline plane orientations of the top surface **120** to achieve the embodiments of the present invention. Upon reading this disclosure, one of ordinary skill in the art will appreciate the manner in which the top surface and the trench wall can be formed to possess this described specific relationship.

According to the teachings of the present invention, the trench layer of SiO₂ **150** is formed in a same linear growth period with the top layer of SiO₂ **140**. Based upon the specific crystalline plane orientations chosen for the top surface **120** and the trench wall **160**, the top layer of SiO₂ **140** will have a resultant or end thickness which is different from the trench layer of SiO₂ **150** formed in a same amount of time. Thus, according to the teachings of the present invention, the thickness (t_{TOP}) of the top layer of SiO₂ **140** is different from a thickness (t_{TR}) of the trench layer of SiO₂ **150**. As explained above in connection with FIG. 1B, the trench layer of SiO₂ **150** can be masked and etched to form a defined trench layer of SiO₂ **150**. In one embodiment, the trench layer of SiO₂ **150** is masked and etched to form or define a gate oxide for a DRAM cell. In another embodiment, the formation of the top layer of SiO₂ **140** and the trench layer of SiO₂ **150** is such that the two layers are formed simultaneously during a linear growth period.

In one embodiment, the formation of the top layer of SiO₂ **140** and the trench layer of SiO₂ **150** is such that the thickness (t_{TR}) of the trench layer of SiO₂ **150** is greater than the thickness (t_{TOP}) of the top layer of SiO₂ **140**. For example, according to the teachings of the present invention, when the top surface **120** is formed with a (100) crystalline plane orientation and the trench wall **160** is formed with a (110) crystalline plane orientation, $t_{TR} > t_{TOP}$. In an alternative embodiment, the formation of the top layer of SiO₂ **140** and the trench layer of SiO₂ **150** is such that the thickness (t_{TR}) of the trench layer of SiO₂ **150** is less than the thickness (t_{TOP}) of the top layer of SiO₂ **140**; all dependent on the chosen crystalline plane orientation for the top surface **120** and the trench wall **160**. In another embodiment, the formation of the top layer of SiO₂ **140** and the trench layer of SiO₂ **150** is such that the thickness (t_{TR}) of the trench layer of SiO₂ **150** is approximately 30% thicker than the thickness (t_{TOP}) of the top layer of SiO₂ **140**. In another embodiment, the thickness (t_{TR}) of the trench layer of SiO₂ **150** is approximately 100 Angstroms. In one embodiment, the trench layer of SiO₂ **150** is a gate oxide of a DRAM cell, which is adapted for use with a DRAM cell having an operating voltage of less than 3.5 volts.

In one embodiment of formation, the trench layer of SiO₂ **150** is formed on the trench wall **160** through dry oxidization at a temperature of approximately 800° C. In an alternative embodiment, the trench layer of SiO₂ **150** is formed on the trench wall **160** through wet oxidization at a temperature of approximately 800° C. One of ordinary skill in the art will understand other method embodiments suitable to form the trench layer of SiO₂ **150** according to the teachings of the present invention.

As illustrated in FIG. 2, forming two specific interrelated crystalline plane orientations in a manner according to the teachings of the present invention facilitates or allows for the realization of different, but specifically designed, oxidation rates upon two different surfaces of the same silicon structure. The graph of FIG. 2 plots the oxide thickness (d_{SiO_2}), expressed in Angstroms, on a silicon substrate versus the allowed time of oxidation (t), shown in minutes. In the graph of FIG. 2, the oxide layers are thermally grown at 800° C. upon a silicon surface having three distinct crystalline plane orientations (i.e., (111), (110) and (100)). FIG. 2 includes plot 202, plot 204 and plot 206. Plot 202 is the graphical plot of oxide thickness vs. time of oxidation to grow an oxide layer on a silicon surface having a (100) crystalline plane orientation. Plot 204 is the graphical plot of oxide thickness vs. time of oxidation to grow an oxide layer on a silicon surface having a (110) crystalline plane orientation. Plot 206 is the graphical plot of oxide thickness vs. time of oxidation to grow an oxide layer on a silicon structure having a (111) crystalline plane orientation. Thus, controlling the specific crystalline plane orientation of different surfaces of the silicon structure advantageously yields different oxidation rates at designed or predicted locations. These different oxidation rates at designed locations over a particular time period, thus, allow for the structuring of gate oxides of differing thickness to accommodate differing technologies (e.g., DRAM and logic technologies) on a single chip or single silicon structure. Hence, designed locations can facilitate the formation of different device structures in a single streamlined process flow.

FIGS. 3A–3C illustrate another embodiment of a process of fabrication of oxide layers on a silicon wafer according to teachings of the present invention. The sequence can be followed as a portion of a method for forming a semiconductor device, a DRAM that can include a trench capacitor or a stacked capacitor, a Non-Volatile Random Access Memory (NVRAM), (e.g., a flash memory device), a CMOS logic circuit as well as a programmable logic array.

FIG. 3A shows the structure after the first sequence of processing. A top surface 310 of a silicon wafer 320 is formed with a top crystalline plane orientation. In one embodiment, the top surface 310 has a (100) crystalline plane orientation. In another embodiment, the top surface 310 has a (110) crystalline plane orientation. In an additional embodiment, the top surface 310 has a (111) crystalline plane orientation. In all of these embodiments, the top crystalline plane orientation is designed to achieve the embodiments of the present invention.

FIG. 3B shows the structure after the next sequence of processing. A trench 330 is formed in the silicon wafer 320 such that a trench wall 340 has a different order plane orientation than the top crystalline plane orientation of the top surface 310. In one embodiment, the trench wall 340 has a (110) crystalline plane orientation. In another embodiment, the trench wall 340 has a (311) crystalline plane orientation. In an additional embodiment, the trench wall 340 has a (511) crystalline plane orientation. However, it is important to appreciate that the crystalline plane orientation of the trench wall 340 is decisively designed in relationship to the crystalline plane orientation of the top surface 310 to achieve the embodiment of the present invention.

FIG. 3C shows the structure after the next sequence of processing. Simultaneously, a top oxide layer 350 is formed on the top surface 310, and a trench oxide layer 360 is formed on the trench wall 340 during a linear growth period, such that the top oxide layer 350 has a thickness (t_{TOP}) that is different from a thickness (t_{TR}) of the trench oxide layer

360. In one embodiment, the top oxide layer 350 and the trench oxide layer 360 are grown on the respective surfaces by thermal oxidation. In one embodiment, the top oxide layer 350 will subsequently be formed into a gate oxide of a logic device. In this embodiment, the top oxide layer 350 has a thickness which is selected for a logic device having an operating voltage of less than 2.5 volts.

In one embodiment, the crystalline plane orientations of the top surface 310 and the trench wall 340 are such that the thickness (t_{TR}) of the trench oxide layer 360 is greater than the thickness (t_{TOP}) of the top oxide layer 350 when formed in a linear time period. In another embodiment, the crystalline plane orientation of the top surface 310 and the trench wall 340 are such that the thickness (t_{TR}) of the trench oxide layer 360 is approximately 30% greater than the thickness (t_{TOP}) of the top oxide layer 350 when formed in a linear time period. In one embodiment, the thickness (t_{TOP}) of the top oxide layer 350 is approximately 70 Angstroms. In one embodiment, the thickness (t_{TR}) of the trench oxide layer 360 is approximately 100 Angstroms.

In one embodiment, the crystalline plane orientation of the trench wall 340 is such that when the trench oxide layer 360 is formed in the linear time period the resulting oxide thickness is suitable for forming a gate oxide of a DRAM cell. In one embodiment, the trench oxide layer 360 is suitably formed to serve as a gate oxide of a DRAM cell having an operating voltage of less than 3.5 volts.

In one embodiment of formation, the top oxide layer 350 and the trench oxide layer 360 are grown on the top surface 310 and the trench wall 340, respectively, through dry oxidization at a temperature of approximately 800° C. In an alternative embodiment, the top oxide layer 350 and the trench oxide layer 360 are grown on the top surface 310 and the trench wall 340, respectively, through wet oxidization at a temperature of approximately 800° C. One of ordinary skill in the art will understand other method embodiments suitable to form the top oxide layer 350 and the trench oxide layer 360 according to the teachings of the present invention.

FIGS. 4A–4C illustrate an embodiment of a process of fabrication of layers of oxide on a silicon wafer according to teachings of the present invention. The sequence can be followed as a method for forming a semiconductor device, as a method for forming a DRAM, as a method for forming a Non-Volatile Random Access Memory (NVRAM), such as a flash memory device, or as a method for forming a CMOS logic circuit as well as a method for forming a programmable logic array.

FIG. 4A shows the structure subsequent to the formation of a trench 430 in a silicon wafer 410, the processing of which is well known in the art. The silicon wafer 410 has a top surface 420. According to the teachings of the present invention, the top surface 420 of the silicon wafer 410 is formed with a specific top crystalline plane orientation. In one embodiment, the top surface 420 has a (100) crystalline plane orientation. In another embodiment, the top surface 420 has a (110) crystalline plane orientation. In an additional embodiment, the top surface 420 has a (111) crystalline plane orientation. Other specific top crystalline plane orientations are similarly included which are suited to carry out the embodiments of the present invention. One of ordinary skill in the art will appreciate upon reading this disclosure the top crystalline plane orientations suited to carry out the novel embodiments of the present invention.

FIG. 4B illustrates the structure following the next sequence of processing. A top device 440 is formed on the top surface 420 of the silicon wafer 410. In one embodiment,

the top device **440** is a logic device. In particular, the top device **440** includes forming a top gate oxide **460**, according to the teachings of the present invention, over a linear time period on the top surface **420**. In one embodiment, the top gate oxide **460** is grown on the top surface **420** by thermal oxidation, as is known in the art. Moreover, a top gate **450** is formed on the top gate oxide **460**. One of ordinary skill in the art will understand upon reading this disclosure the manner in which masking and etching techniques can be employed to form such a logic device. In another embodiment, the top gate oxide **460** has a thickness (t_{TOP}) of approximately 70 Angstroms. In one embodiment, the top gate oxide **460** is formed to accommodate a top device having an operating voltage of less than 2.5 volts.

FIG. **4C** illustrates the structure following the next sequence of processing. According to one embodiment of the present invention, the trench wall **470** has a different plane orientation than the top surface **420** in FIG. **4B**. In one embodiment, the trench wall **470** has a (110) crystalline plane orientation. In another embodiment, the trench wall **470** has a (311) crystalline plane orientation. In an additional embodiment, the trench wall **470** has a (511) crystalline plane orientation. However, it is important to appreciate that the crystalline plane is chosen to be specifically interrelated to the chosen specific crystalline plane orientation of the top surface in order to achieve specific and different gate oxide thicknesses according to teachings of the present invention.

A trench device **480** is formed on a trench wall **470** of a trench **430** in the silicon wafer **410**. The trench device **480** includes forming a trench gate oxide **495**, according to the teachings of the present invention, over a linear time period on the trench wall **470**. In one embodiment, the trench gate oxide **495** is grown on the trench wall **470** by thermal oxidation, as is known in the art. Moreover, a trench gate **490** is formed on the trench gate oxide **495**. One of ordinary skill in the art will understand upon reading this disclosure the manner in which masking and etching techniques can be employed to form such a trench device. In one embodiment, the thickness (t_{TOP}) of the top gate oxide **460** is different from a thickness (t_{TR}) of the trench gate oxide **495**. In one embodiment, the trench device **480** is a DRAM cell. In another embodiment, the top gate oxide **460** and the trench gate oxide **495** are formed simultaneously during a linear growth period (i.e., the oxide is formed over the same length of time). In one embodiment, the thickness (t_{TR}) of the trench gate oxide **495** is thicker than the thickness (t_{TOP}) of the top gate oxide **460**. For example, according to the teachings of the present invention, when the top surface **420** is formed with a crystalline plane orientation of (100) and the trench wall **470** is formed with a crystalline plane orientation of (110), $t_{TR} > t_{TOP}$. In one embodiment, the thickness (t_{TR}) of the trench gate oxide **495** is approximately 30% thicker than the thickness (t_{TOP}) of the top gate oxide **460**. In one embodiment, the thickness (t_{TR}) of the trench gate oxide **495** is approximately 100 Angstroms. In one embodiment, the trench gate oxide **495** is formed to function in the trench device **480** operating with a voltage of less than 3.5 volts.

FIG. **5** is a cross-sectional view of an embodiment of a semiconductor device according to the teachings of the present invention. The semiconductor device of FIG. **5** is constructed in a similar manner according to any one of the methods presented in this application. The semiconductor device includes a top device **520** on a top surface **530** of a silicon wafer **510**. In one embodiment, the top surface **530** is formed with a (100) crystalline plane orientation. In another embodiment, the top surface **530** has a (110) crys-

talline plane orientation. In an additional embodiment, the top surface **530** has a (111) crystalline plane orientation. Other specific top crystalline plane orientation are similarly included which are suited to carry out the embodiments of the present invention. One of ordinary skill in the art will appreciate upon reading this disclosure the top crystalline plane orientations suited to carry out the novel embodiments of the present invention. Additionally, the top device **520** includes a top gate **540** that is separated from the top surface **530** by a top gate oxide **550**. In one embodiment, the top gate oxide **550** is formed to function in a top device **520** operating with a voltage of less than 2.5 volts.

The semiconductor device of FIG. **5** also includes a trench device **560** formed on a trench wall **570** of the silicon wafer **510**. In one embodiment, the trench wall **570** has a different plane orientation than the top surface **530**. In one embodiment, the trench wall **570** has a (110) surface. In another embodiment, the trench wall **570** has a (311) surface. In an additional embodiment, the trench wall **570** has a (511) surface. Other specific crystalline plane orientations of the trench wall **570** are similarly included which are suited to carry out the embodiments of the present invention. One of ordinary skill in the art will appreciate upon reading this disclosure the crystalline plane orientations of the trench wall **570** suited to carry out the novel embodiments of the present invention. Moreover, the trench device **560** has a trench gate **580** separated from the trench wall **570** by a trench gate oxide **590** formed according to the teachings of the present invention.

According to the teachings of the present invention, a thickness (t_{TOP}) of the top gate oxide **550** is different from a thickness (t_{TR}) of the trench gate oxide **590**. In one embodiment, the top gate oxide **550** and the trench gate oxide **590** are such that the thickness (t_{TR}) of the trench gate oxide **590** is thicker than the thickness (t_{TOP}) of the top gate oxide **550**. In another embodiment, the thickness (t_{TR}) of the trench gate oxide **590** is approximately 30% thicker than the thickness (t_{TOP}) of the top gate oxide **550**. In another embodiment, the thickness (t_{TOP}) of the top gate oxide **550** is approximately 70 Angstroms. In another embodiment, the thickness (t_{TR}) of the trench gate oxide **590** is approximately 100 Angstroms.

In one embodiment, the trench device **560** is a portion of a DRAM cell. In one embodiment, the trench gate oxide **590** is formed to function with a trench device **560** having an operating voltage of less than 3.5 volts. In another embodiment, the top gate oxide **550** and the trench gate oxide **590** are thermally grown simultaneously during a linear growth period (i.e., the oxide is formed over the same length of time).

In one embodiment, the trench device **560** is an EEPROM device. In this embodiment, the trench device **560** includes a flash memory device. In one embodiment, the top device **520** is a logic device. In one embodiment, the trench device **560** is included as part of a programmable logic array.

In one embodiment, the top surfaces and trench walls illustrated and described in conjunction with FIGS. **1-5** comprise a portion of the structure necessary for forming vertical transistors formed according to embodiments described in application Ser. No. 08/889,463 entitled "4F² Folded Bit Line DRAM Cell Structure having Buried Bit and Word Lines," filed on Jul. 8, 1997, which is hereby incorporated by reference. In particular, a vertical transistor used in conjunction with embodiments of the present invention is illustrated in FIG. **6**.

FIG. **6** is a perspective view illustrating generally one embodiment of a portion of an array of vertical transistors

formed according to the embodiments of the present invention. Those of ordinary skill in the art will appreciate that FIG. 6 may include other components, including top surface devices (not shown). As shown in FIG. 6, portion of an array of vertical transistors formed according to the teachings of the present invention. The vertical transistors **602a-d** shown in FIG. 6 include vertically oriented access FETs (Field Effect Transistors) **604a-d**.

In the embodiment of FIG. 6, access FETs **604a-d** include an n+ silicon layer formed on the silicon wafer **110** to produce first source/drain regions **612** of access FETs **604a-d**. A p- silicon layer is formed on n+ first source/drain region **612** to form the body region **606** of access FETs **604a-d**. A further n+ silicon layer is formed on p- body region **606** to produce second source/drain region **614** of access FETs **604a-d**. The trench layer surface of each region, **612**, **606** and **614**, is formed with an identical crystalline plane orientation to achieve the embodiments of the present invention.

Conductive segments of a first word line **610** and a second word line **616** provide integrally formed gates for access FETs **604b** and **604c**. The trench layer of SiO₂ **150** includes the trench layer of SiO₂ described and explained above in connection with FIGS. 1-5. The trench layer of SiO₂ **150** is an oxide layer formed between the first word line **610** and/or the second word line **616** and the body regions **606** of access FETs **604b** and **604c**. FIG. 6 also includes the top layer of SiO₂ **140** which includes the top layer of SiO₂ described and explained in detail in connection with FIGS. 1-5.

FIG. 7 is an alternative embodiment of a vertical transistor used in conjunction with embodiments of the present invention. In one embodiment, portions of the trench devices illustrated and described in conjunction with FIGS. 1-5 are vertical transistors of a DRAM cell formed according to embodiments described in application Ser. No. 09/204,072, entitled "Trench DRAM Cell with Vertical Device and Buried Word Lines," filed on Dec. 3, 1998, which is hereby incorporated by reference.

FIG. 7 is a perspective view illustrating generally one embodiment of a vertical transistor formed in conjunction with embodiments of the present invention. Those of ordinary skill in the art will appreciate that FIG. 7 may include other components, including top surface devices (not shown). FIG. 7 illustrates a DRAM cell including a vertically oriented access FET **704** and a capacitor **706**. The vertically oriented access FET **704** includes an n+ silicon layer formed on a silicon wafer **110** to produce a first source/drain region **712**. A p- silicon layer is formed on the first source/drain region **712** to form a body region **714**. Additionally, the vertically oriented access FET **704** includes an n+ silicon layer formed on the p- body region **714** to produce a second source/drain region **716**. In one embodiment, the vertically oriented access FET **704** is formed in semiconductor pillars that extend outwardly from the silicon wafer **110**.

Additionally, FIG. 7 includes conductive segments of a bit line **708**, a portion of which is formed on the second source drain region **716**. FIG. 7 also includes conductive segments of a word line **710** that provide integrally formed gates for the vertically oriented FET **704**. The trench layer of SiO₂ **150** includes the trench layer of SiO₂ described and explained above in connection with FIGS. 1-5. The trench layer of SiO₂ **150** is an oxide layer formed between the word line **710** and the body region **714** of vertically oriented FET **704**. FIG. 7 also includes the top layer of SiO₂ **140** which includes the top layer of SiO₂ described and explained in detail in connection with FIGS. 1-5.

FIG. 8 is an alternative embodiment of vertical transistors used in conjunction with embodiments of the present invention. In one embodiment, portions of the trench devices illustrated and described in conjunction with FIGS. 1-5 are vertical transistors of a DRAM cell formed according to embodiments described in application Ser. No. 08/939,732, entitled "Circuit and Method for an Open Bit Line Memory Cell with a Vertical Transistor and Trench Plate Trench Capacitor," filed on Oct. 6, 1997, which is hereby incorporated by reference.

FIG. 8 is a perspective view illustrating generally one embodiment of a portion of a memory formed in conjunction with embodiments of the present invention. Those of ordinary skill in the art will appreciate that FIG. 8 may include other components, including top surface devices (not shown). FIG. 8 illustrates portions of four trench devices **802a-d** and a storage capacitor plate **804** formed in conjunction with embodiments of the present invention.

The vertical transistors **802a-d** include an n+ silicon layer formed on Silicon On Insulator (SOI) material **806** which has been formed on a silicon wafer **110** to produce a first source/drain region **808**. A p- silicon layer is formed on the first source/drain region **808** to form a body region **810**. Additionally, the trench devices **802a-d** include an n+ silicon layer formed on the p- body region **810** to produce a second source/drain region **812**.

Additionally, FIG. 8 includes conductive segments of bit line wires **814**, a portion of which is formed on the second source drain region **812**. FIG. 8 includes a body contact line **818**. Further, FIG. 8 also includes conductive segments of a word line **816** that provide integrally formed gates for the vertically oriented FETs **802**. The trench layer of SiO₂ **150** includes the trench layer of SiO₂ described and explained above in connection with FIGS. 1-5. The trench layer of SiO₂ **150** is an oxide layer formed between the word line **816** and the body region **810** of trench devices **802a** and **802b**. FIG. 8 also includes the top layer of SiO₂ **140** which includes the top layer of SiO₂ described and explained in detail in connection with FIGS. 1-5.

FIG. 9 is an alternative embodiment of vertical transistors used in conjunction with embodiments of the present invention. In one embodiment, portions of the trench devices illustrated and described in conjunction with FIGS. 1-5 are vertical transistors of a memory cell.

FIG. 9 is a perspective view illustrating generally one embodiment of a portion of a non-volatile memory formed in conjunction with embodiments of the present invention. Those of ordinary skill in the art will appreciate that FIG. 9 may include other components, including top surface devices (not shown). FIG. 9 illustrates portions of a non-volatile memory cell **902** formed in conjunction with embodiments of the present invention. In one embodiment, the non-volatile memory cell **902** is a vertically oriented FET. In one embodiment, the non-volatile memory cell **902** is a portion of an EEPROM, flash memory or NVRAM devices, which include a trench layer of SiO₂ or tunnel oxide layer formed according to the teachings of the present invention.

FIG. 9 includes an n+ silicon layer formed on a silicon wafer **110** to produce a first source/drain region **904**. A p- silicon layer is formed on the first source/drain region **904** to form a body region **906**. Additionally, the non-volatile memory cell **902** include an n+ silicon layer formed on the p- body region **906** to produce a second source/drain region **908**.

Additionally, FIG. 9 includes a floating gate **910** and a control gate **912**. The trench layer of SiO₂ **150** includes the

15

trench layer of SiO₂ formed on a trench surface **914**, described and explained above in connection with FIGS. **1-5**. The trench layer of SiO₂ **150** is an oxide layer formed between the word line floating gate **910** and the body region **906** of the non-volatile memory cell **902**. FIG. **9** also includes the top layer of SiO₂ **140** which includes the top layer of SiO₂ formed on a top surface **120**, described and explained in detail in connection with FIGS. **1-5**.

The device of FIG. **9** encompasses embodiments wherein the crystal planes of the top surface **120** and the trench surface **914** are specifically oriented to allow for a higher oxidation rate for oxides layers grown on the top surface **120**. Accordingly, when oxide layers are grown on both the top surface **120** and the trench surface **914** during a same linear growth period, oxide layers grown on the trench surface **914** are thinner than oxide layers grown on the top surface **120**. In one such embodiment, the top surface **120** has a (110) crystal plane orientation while the trench surface **914** has a (100) crystal plane orientation. In another such embodiment, the top surface **120** has a (111) crystal plane orientation, while the trench surface has a (110) crystal plane orientation. Advantageously, thinner oxides on the trench walls and thicker oxides on top surfaces prove particularly useful in conjunction with EEPROM devices, flash memory devices or other NVRAM devices. In particular, the tunnel oxides along the trench walls used with such devices should be as thin as possible, while the logic devices residing on the top surfaces should have thicker oxides to ensure reliability.

FIG. **10** is a block diagram which illustrates an embodiment of a system **1000** according to teachings of the present invention. The system **1000** includes an integrated circuit **1010**. The integrated circuit **1010** includes the embodiments of top and trench devices formed with specific crystalline plane orientations to facilitate formation of differing gate oxide thicknesses in a streamlined fabrication process flow according to the teachings of the present invention. Additionally, the system **1000** includes a processor **1020** that is operatively coupled to the integrated circuit **1010**. The processor **1020** is coupled to the integrated circuit **1010** through a system bus **1030**. In one embodiment, the processor **1020** and the integrated circuit **1010** are on the same semiconductor chip.

CONCLUSION

Thus, improved methods and structures are provided for multiple oxide thickness on a single silicon wafer. In particular, improved methods and structures are provided for multiple gate oxide thickness on a single chip wherein the chip can include circuitry encompassing a range of technologies including but not limited to the memory and logic technologies. Moreover, these improved methods and structures for multiple oxide thickness on a single silicon wafer can be used in conjunction with existing fabrication and processing techniques with minimal or no added complexity.

Although specific embodiments have been illustrated and described herein, it will be appreciated by those of ordinary skill in the art that any arrangement which is calculated to achieve the same purpose may be substituted for the specific embodiment shown. This application is intended to cover any adaptations or variations of the present invention. It is to be understood that the above description is intended to be illustrative, and not restrictive. Combinations of the above embodiments, and other embodiments will be apparent to those of skill in the art upon reviewing the above description. The scope of the invention includes any other applications in which the above structures and fabrication meth-

16

ods are used. The scope of the invention should be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled.

What is claimed is:

1. A semiconductor device comprising:

a top device formed on a top surface of a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide; and

a trench device formed on a trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

2. The semiconductor device of claim **1**, wherein the top gate oxide thickness is approximately 70 Angstroms.

3. The semiconductor device of claim **1**, wherein the trench gate oxide thickness is approximately 100 Angstroms.

4. The semiconductor device of claim **1**, wherein the top device has an operating voltage of less than 2.5 volts.

5. The semiconductor device of claim **1**, wherein the trench device has an operating voltage of less than 3.5 volts.

6. The semiconductor device of claim **1**, wherein the top device is a logic device.

7. The semiconductor device of claim **1**, wherein the trench device is a DRAM (Dynamic Random Access Memory) cell.

8. A semiconductor device comprising:

a logic device formed on a top surface of a silicon wafer, wherein the top surface has a (111) crystalline plane orientation, the logic device having a logic gate separated from the top surface by a logic gate; and

a flash memory cell formed on a trench wall of the silicon wafer, wherein the trench wall has a (110) crystalline plane orientation, the flash memory cell having a flash gate separated from the trench wall by a flash gate oxide, wherein a thickness of the logic gate oxide is different from a thickness of the flash gate oxide.

9. The semiconductor device of claim **8**, wherein the logic device has an operating voltage of approximately 2.5 volts.

10. The semiconductor device of claim **8**, wherein the flash memory cell has an operating voltage of approximately 3.5 volts.

11. The semiconductor device of claim **8**, wherein the logic gate oxide is approximately 70 Angstroms, and wherein the flash gate oxide is approximately 100 Angstroms.

12. A semiconductor device comprising:

a top device formed on a top surface of a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide, wherein the top gate oxide thickness is approximately 70 Angstroms, and wherein the top device has an operating voltage of less than 2.5 volts; and

a trench device formed on a trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

13. The semiconductor device of claim **12**, wherein the trench gate oxide thickness is approximately 100 Angstroms.

17

14. The semiconductor device of claim 12, wherein the trench device has an operating voltage of less than 3.5 volts.

15. A semiconductor device comprising:

a top device formed on a top surface of a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide; and

a trench device formed on a trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein the trench gate oxide thickness is approximately 100 Angstroms, wherein the trench device has an operating voltage of less than 3.5 volts, and wherein a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

16. The semiconductor device of claim 15, wherein the top device has an operating voltage of less than 2.5 volts.

17. The semiconductor device of claim 1, wherein the trench gate oxide thickness is approximately 30% thicker than the top gate oxide thickness.

18. The semiconductor device of claim 1, wherein the thickness of the trench gate oxide is less than the thickness of the top gate oxide.

19. The semiconductor device of claim 1, wherein the top gate oxide includes a width that is suitable for serving as a gate oxide layer.

20. The semiconductor device of claim 1, wherein the top gate oxide includes a thickness of SiO₂ of approximately 70 Angstroms, and wherein the top gate oxide includes a width that is suitable for serving as a gate oxide layer.

21. The semiconductor device comprising:

a top device formed on a top surface of a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide, and wherein the top gate oxide thickness is approximately 70 Angstroms; and

a trench device formed on the trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein the trench gate oxide thickness is approximately 100 Angstroms, and wherein a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

18

22. The semiconductor device of claim 21, wherein the top device has an operating voltage of less than 2.5 volts, and wherein the trench device has an operating voltage of less than 3.5 volts.

23. A semiconductor device comprising:

a top device formed on a top surface of a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide, wherein the top device is a logic device, and wherein the top device has an operating voltage of less than 2.5 volts; and

a trench device formed on a trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein a thickness of the trench gate oxide is different from a thickness of the top gate oxide.

24. The semiconductor device of claim 23, wherein the top gate oxide thickness is approximately 70 Angstroms.

25. A semiconductor device comprising:

a top device formed on a top surface on a silicon wafer, wherein the top surface has a (110) crystal plane orientation, the top device having a top gate separated from the top surface by a top gate oxide; and

a trench device formed on a trench wall of the silicon wafer, wherein the trench wall has a (100) crystal plane orientation, the trench device having a trench gate separated from the trench wall by a trench gate oxide, wherein the trench device is a DRAM cell, wherein the trench device has an operating voltage of less than 3.5 volts, and wherein a thickness of the top gate oxide is different from a thickness of the trench gate oxide.

26. The semiconductor device of claim 25, wherein the trench gate oxide thickness is approximately 100 Angstroms.

27. The semiconductor device of claim 25, wherein the top device is a logic device, and wherein the top device has an operating voltage of less than 2.5 volts.

28. The semiconductor device of claim 25, wherein the top gate oxide thickness is approximately 70 Angstroms.

29. The semiconductor device of claim 25, wherein the top device is a logic device, wherein the top device has an operating voltage of less than 2.5 volts, and wherein the top gate oxide thickness is approximately 70 Angstroms.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 6,800,927 B2
APPLICATION NO. : 10/140296
DATED : October 5, 2004
INVENTOR(S) : Noble et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On page 2, Togo, M., et al. in Item (56), under "Other Publications", in column 2, line 25, delete "DRAMs" and insert -- DRAMs --, therefor.

On page 2, Vitkavage, S.C., et al. in Item (56), under "Other Publications", in column 2, line 26, delete "SiO2" and insert -- SiO₂ --, therefor.

In column 16, line 35, in Claim 8, after "gate" insert -- oxide --.

In column 17, line 32, in Claim 21, delete "The" and insert -- A --, therefor.

In column 17, line 40, in Claim 21, delete "the" and insert -- a --, therefor.

In column 18, line 17, in Claim 23, delete "trench" and insert -- top --, therefor.

In column 18, line 22, in Claim 23, delete "trench" and insert -- top --, therefor.

Signed and Sealed this

Third Day of April, 2007

A handwritten signature in black ink on a light gray dotted background. The signature reads "Jon W. Dudas" in a cursive style.

JON W. DUDAS

Director of the United States Patent and Trademark Office