

(12) **United States Patent**  
Matsushita et al.

(10) **Patent No.:** **US 6,860,849 B2**  
(45) **Date of Patent:** **Mar. 1, 2005**

(54) **FLEXIBLE TUBE FOR AN ENDOSCOPE**

(75) Inventors: **Minoru Matsushita**, Tokyo (JP);  
**Kikuo Iwasaka**, Tokyo (JP); **Tadashi Kasai**, Tokyo (JP); **Hideo Nanba**, Tokyo (JP)

(73) Assignee: **PENTAX Corporation**, Tokyo (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 192 days.

(21) Appl. No.: **09/848,301**

(22) Filed: **May 4, 2001**

(65) **Prior Publication Data**

US 2002/0010386 A1 Jan. 24, 2002

(30) **Foreign Application Priority Data**

May 8, 2000 (JP) ..... 2000-134922  
May 15, 2000 (JP) ..... 2000-142206  
May 26, 2000 (JP) ..... 2000-156783

(51) **Int. Cl.**<sup>7</sup> ..... **A61B 1/005**

(52) **U.S. Cl.** ..... **600/140**

(58) **Field of Search** ..... 600/139, 140,  
600/121; 604/524, 526, 527

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,690,175 A \* 9/1987 Ouchi et al. .... 600/140  
4,753,222 A \* 6/1988 Morishita ..... 600/140  
4,899,787 A \* 2/1990 Ouchi et al. .... 600/140  
5,217,002 A \* 6/1993 Katsurada et al. .... 600/139  
5,448,988 A \* 9/1995 Watanabe ..... 600/139  
5,876,331 A \* 3/1999 Wu et al. .... 600/139  
5,885,207 A \* 3/1999 Iwasaka ..... 600/139

5,916,147 A \* 6/1999 Boury ..... 600/139  
6,083,152 A \* 7/2000 Strong ..... 600/139  
6,197,014 B1 \* 3/2001 Samson et al. .... 604/524  
6,206,824 B1 \* 3/2001 Ohara et al. .... 600/139  
6,402,687 B1 \* 6/2002 Ouchi ..... 600/139  
6,458,075 B1 \* 10/2002 Sugiyama et al. .... 600/139

**FOREIGN PATENT DOCUMENTS**

JP 2-283346 11/1990  
JP 5-50287 7/1993  
JP 6-98115 12/1994  
JP 2641789 5/1997

**OTHER PUBLICATIONS**

English Language Abstract of JP 2-283346.

\* cited by examiner


*Primary Examiner*—John P. Leubecker


(74) *Attorney, Agent, or Firm*—Greenblum & Bernstein, P.L.C.

(57) **ABSTRACT**

A flexible tube for an endoscope has an elongated tubular core body, and an outer cover which is provided over the core body. The outer cover is composed of an inner layer, an outer layer and at least one intermediate layer. In this flexible tube, any one of the layers is different from one of the other layers in its property. Further, at least one of the layers has a thickness-varying region where the thickness of the layer varies in its longitudinal direction. In addition, the inner layer of the outer cover has projections which are integrally formed on the inner layer so that the projections project into holes and/or the recesses formed on the core body. This structure makes it possible to produce a flexible tube for an endoscope that has high durability, high flexibility and high chemical resistance as well as excellent operationability.

**19 Claims, 15 Drawing Sheets**





# Fig. 1




Fig. 2

Tip ←————→ Base




Fig. 3




Fig. 4




Fig. 5





Fig. 6



**Fig. 7**




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13





Fig. 14

**Fig. 15**

## FLEXIBLE TUBE FOR AN ENDOSCOPE

## BACKGROUND OF THE INVENTION

## 1. Field of the Invention

The present invention relates to a flexible tube for an endoscope.

## 2. Description of the Prior Art

Generally, a flexible tube for an endoscope has a structure which includes a tubular core obtained by covering the outer periphery of a spiral tube with a mesh tube and an outer cover formed of a synthetic resin or the like and provided over the outer periphery of the tubular core.

In endoscopic examination, the flexible tube for an endoscope is inserted along the body cavity to a deep part such as the stomach, duodenum, small intestine, and large intestine. In order to perform the inserting operation easily and reliably, it is necessary for the flexible tube that a push-in force applied to the proximal end (side closer to the operator) of the flexible tube is fully transmitted to its distal end. However, if buckling occurs in the flexible tube, the push-in force can not be fully transmitted to the distal end because the push-in force is partially absorbed by the bent part where the buckling occurs. This means that such a flexible tube for an endoscope can not achieve reliable inserting operation. In order to avoid the occurrence of such buckling, it is necessary for the flexible tube to have sufficient flexibility so that bending is hard to occur. Further, the outer cover must be firmly attached or bonded to the tubular core since buckling is liable to occur at areas where the outer cover is peeled off from the tubular core.

Furthermore, in order to perform the inserting operation reliably, it is also necessary for the flexible tube that a rotational force (that is, a twist) applied to the proximal end thereof is fully transmitted to the distal end thereof. In other words, a flexible tube for an endoscope is also required to have satisfactory rotational followability.

Moreover, a flexible tube for an endoscope is also required to have a relatively high stiffness on the proximal end side (side closer to the operator) and have a flexibility on the distal end side from the viewpoint of the operability and safety of insertion and reduction in the burden on the patient.

Up to now, there are known several flexible tubes for an endoscope which aim to improve the insertion operability in view of the problems described above. One of such flexible tubes is disclosed in Japanese Laid-open Patent Applications No. Hei 5-50287, in which an outer cover of a flexible tube for an endoscope is constructed from a double layer structure comprised of an outer layer made of a material having good elasticity and an inner layer made of a material having good resiliency, thereby improving resiliency of the flexible tube as a whole. Other example of such flexible tube is disclosed in Japanese Patent No. 2641789, in which a distal end side of the flexible tube is made of a soft elastomer and a proximal end side thereof is made of a hard elastomer so that the stiffness varies from the distal end side toward the proximal end side.

However, in these prior arts described in the above, the bonding force between the outer cover and the core has been left out of consideration, so that there is a case that the outer cover is peeled off from the core after repeated use, thus leading to the deterioration in flexibility and resistance to buckling of the flexible tube. In short, there is a problem in the durability of the flexible tube for an endoscope.

Furthermore, although an endoscope must be cleaned and disinfected every time when it is used, in the above prior arts no consideration is given to the chemical resistance of the outer covers. Consequently, in these prior arts, deterioration proceeds during the repeated disinfections, which results in possibility of generation of fine cracks or the like and peeling off of the outer cover from the core.

## SUMMARY OF THE INVENTION

In view of the problems in the prior art described in the above, it is the object of the present invention to provide a flexible tube for an endoscope that possesses various kinds of performances required for a flexible tube for an endoscope, in particular to provide a flexible tube for an endoscope excellent in the operability of insertion, resistance to chemicals and durability.

In order to achieve the above object, the present invention is directed to a flexible tube for an endoscope, comprising:

an elongated tubular core body; and

an outer cover which is provided over the core body, the outer cover having a portion which is formed into a laminate structure composed of at least three layers.

In this invention, it is preferred that the layers of the laminate structure include an inner layer, an outer layer and at least one intermediate layer formed between the inner layer and the outer layer.

Further, in this invention, it is also preferred that the core body has a plurality of holes and/or a plurality of recesses. In this case, it is preferred that the core body includes: a coil that is formed by winding a band-shaped material into a spiral form; and a reticular tube that is formed by weaving a plurality of fine wires together, the reticular tube being provided over the coil. Further, it is also preferred that the inner layer of the outer cover has projections which are integrally formed on the inner layer so that the projections project into the holes and/or the recesses.

Furthermore, in this invention, it is also preferred that at least one of the fine wires forming the reticular tube is coated with a synthetic resin so that a coating of the synthetic resin is provided on the fine wire, in which at least a part of the coating is fused with and bonded to the inner layer of the outer cover.

Moreover, in this invention, it is also preferred that the inner layer of the outer cover contains a material having a compatibility with the synthetic resin of the coating.

Further, in this invention, it is also preferred that the portion of the laminate structure of the outer cover has a substantially uniform thickness over its entire region.

Furthermore, in this invention, it is also preferred that any one of the inner, outer and intermediate layers is different from one of the other layers in its physical property and/or chemical property.

Moreover, in this invention, it is also preferred that any one of the inner, outer and intermediate layers is different from one of the other layers in its hardness.

Moreover, in this invention, it is also preferred that the outer layer of the outer cover contains a material having resistance to chemical.

Moreover, in this invention, it is also preferred that the intermediate layer of the outer cover is formed of a material having higher elasticity than that of the outer layer.

Moreover, in this invention, it is also preferred that the outer layer of the outer cover is formed of a material having higher hardness than that of any one of the inner and intermediate layers.

Moreover, in this invention, it is also preferred that at least a part of the outer layer of the outer cover has higher hardness than that of any of the inner and intermediate layers.

Moreover, in this invention, it is also preferred that the intermediate layer of the outer cover is formed so as to function as cushioning means between the inner layer and the outer layer.

Moreover, in this invention, it is also preferred that at least one of the inner, outer and intermediate layers of the outer cover is formed of a material that contains at least one selected from the group consisting of polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polystyrene-based elastomer, polyamide-based elastomer, fluorine-based elastomer, and fluororubber.

Moreover, in this invention, it is also preferred that each of the inner, outer and intermediate layers of the outer cover is formed of a material that contains at least one selected from the group consisting of polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polystyrene-based elastomer, polyamide-based elastomer, fluorine-based elastomer, and fluororubber.

Further, in this invention, it is also preferred that the outer cover is provided over the core body through an extrusion molding process.

Furthermore, in this invention, it is also preferred that the flexible tube has tip and base ends, and flexibility of the flexible tube increases in a gradual or stepwise manner along the direction from the base end toward the tip end.

Moreover, in this invention, it is also preferred that any one of the layers constituting the portion of the laminate structure of the outer cover is different from one of the other layers in its physical property and/or chemical property.

Moreover, in this invention, it is also preferred that any one of layers constituting the laminate structure of the outer cover is different from one of the other layers in hardness.

Moreover, in this invention, it is also preferred that at least one of the layers constituting the portion of the laminate structure has a thickness-varying region where the thickness of the layer varies in its longitudinal direction.

In this case, it is preferred that the thickness-varying region extends substantially over an entire region of the layer, and within the thickness-varying region the thickness of the layer varies in its longitudinal direction in a gradual or stepwise manner.

Further, it is also preferred that the layer with the thickness-varying region has at least one uniform thickness region which is formed so as to adjoin the thickness-varying region.

Furthermore, it is also preferred that the layer having the thickness-varying region is formed of a material that is different from materials constituting the other layers in its hardness.

Moreover, it is also preferred that each of at least two of the layers constituting the portion of the laminate structure has a thickness-varying region where the thickness of the layer varies in its longitudinal direction.

Moreover, it is also preferred that the outer cover is provided over the core body through an extrusion molding process. In this case, it is preferred that in the extrusion molding process a constituent material for each of the layers is fed at a predetermined feeding rate while the core body is fed at a predetermined feeding speed, in which the thickness of the layer having the thickness-varying region is controlled by adjusting the feeding rate of the material for the layer during the extrusion molding process and/or adjusting the feeding speed of the core body during the extrusion molding process.

Further, in this invention, it is preferred that at least one of the layers constituting the portion of the laminate structure has at least two regions and at least one boundary part

along its longitudinal direction, and one of the regions is contiguous to the other region through the boundary part, in which one of the regions is different from the other regions adjacent thereto in its physical property and/or chemical property.

In this case, it is preferred that one of the regions is formed of a material which is different from that forming the other region adjacent thereto.

Further, it is also preferred that each of at least two of the layers constituting the portion of the laminate structure has at least two regions and at least one boundary part along its longitudinal direction, and one of the regions is contiguous to the other region through the boundary part, in which one of the regions is different from the other region adjacent thereto in its physical property and/or chemical property. In this case, it is preferred that the outer cover is formed such that the boundary part of one layer is not located above or below the boundary part of the other layer in its thickness direction.

Furthermore, it is also preferred that the boundary part is formed as a property-varying part within which the physical property and/or the chemical property of the layer gradually vary in its longitudinal direction. In this case, the boundary part is formed of a mixture of a material constituting one of the regions and a material constituting the other region.

Moreover, it is also preferred that the layer having the boundary part is formed such that the physical property and/or the chemical property within the boundary part vary in its longitudinal direction in a substantially stepwise manner.

Moreover, it is also preferred that in the layer having the at least two regions, one of the regions is different from the other region adjacent thereto in its hardness.

Moreover, it is also preferred that the flexible tube has tip and base ends, and flexibility of the flexible tube increases in a gradual or stepwise manner along the direction from the base end to the tip end.

These and other objects, structures and advantages of the present invention will be apparent more clearly from the following description of the invention based on the examples.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows an overall structure of an endoscope having a first embodiment of a flexible tube according to the present invention;

FIG. 2 is a sectional view which shows apart of the flexible tube in FIG. 1;

FIG. 3 is a sectional view which shows a part of a second embodiment of the flexible tube according to the present invention;

FIG. 4 is a sectional view which shows a part of a third embodiment of the flexible tube according to the present invention;

FIG. 5 is a sectional view which shows a part of a fourth embodiment of the flexible tube according to the present invention;

FIG. 6 is a sectional view which shows a part of a fifth embodiment of the flexible tube according to the present invention;

FIG. 7 is a sectional view which shows a part of a sixth embodiment of the flexible tube according to the present invention;

FIG. 8 is a sectional view which shows a part of a seventh embodiment of the flexible tube according to the present invention;

## 5

FIG. 9 is a sectional view which shows a part of an eighth embodiment of the flexible tube according to the present invention;

FIG. 10 is a sectional view which shows a part of a ninth embodiment of the flexible tube according to the present invention;

FIG. 11 is a sectional view which shows a part of a tenth embodiment of the flexible tube according to the present invention;

FIG. 12 is a sectional view which shows a part of an eleventh embodiment of the flexible tube according to the present invention;

FIG. 13 is an illustration which shows a state where an flexible tube is divided into eight sections;

FIG. 14 is an illustration which shows a state where an flexible tube is divided into ninth sections; and

FIG. 15 is an illustration which shows a state where the bending stiffness in one of the sections shown in FIG. 13 or 14 is measured.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hereinafter, detailed description of the preferred embodiments of a flexible tube for an endoscope according to the present invention will be given with reference to the appended drawings.

##### I. First Embodiment (Flexible Tube 1A)

###### (I-1) Overall Structure of Electronic Endoscope

First, a first embodiment of the flexible tube for an endoscope will be described with reference to FIGS. 1 and 2. FIG. 1 shows an overall structure of an electronic endoscope 10 (electronic scope) having a flexible tube 1A according to the present invention. FIG. 2 is a sectional view which shows a part of the flexible tube 1A of the electronic endoscope 10 in FIG. 1. In FIG. 2, the right-hand side corresponds to the base side (i.e., side closer to an operator), and the left-hand side corresponds to the tip side of the electronic endoscope 10.

In the following, the upper side and the lower side in FIG. 1 will be referred to as "base" and "tip," respectively. Further, the electronic endoscope will be referred to simply as an "endoscope." Furthermore, the flexible tube for an endoscope will be referred to simply as a "flexible tube."

As shown in FIG. 1, the endoscope 10 has an elongated flexible tube (insertion section) 1A designed to be inserted into a body cavity of a living body; a bendable tube 5 provided on a tip end 12 of the flexible tube 1A; an operating section 6 provided on a base end 11 of the flexible tube 1A, which is gripped by an operator during an endoscopic examination to manipulate the endoscope 10; a light guide flexible tube 7 connected at one end thereof to the operating section 6; and a plug 8 provided on the other end of the light guide flexible tube 7.

On the side faces of the operating section 6, there are provided operating knobs 61 and 62. When changing the direction of the bendable tube 5 during the endoscopic examination, the operator turns each of the operating knobs 61 and 62 to pull appropriately wires (not shown) arranged in the flexible tube 1A. In this way, the bendable tube 5 is bent to a desired direction.

The endoscope 10 has an imaging element (CCD) for taking an image of an observation area, which is provided at the tip end of the bendable tube 5. Further, the endoscope 10 has a connector 82 provided on one end of the plug 8. The connector 82 is connected to a light source device which is connected to a monitor (not shown) via a cable.

## 6

In the endoscope 10, the reflected light (which forms an image of the observation area) from the observation area is received by the imaging element. Then, the imaging element outputs an image signal corresponding to the image formed on the imaging element by the reflected light. The image signal is transmitted to the plug 8 via an image signal cable (not shown in the drawing) which extends inside the bendable tube 5, the flexible tube 1A, the operating section 6 and the light guide flexible tube 7. Then, in the light source device, the image signal is subjected to predetermined processing (such as signal processing, image processing, and the like), and then the processed signal is sent to the monitor. In this way, an image (electronic image) taken by the imaging element is displayed on the screen of the monitor.

In the above, the description was given for the case where a flexible tube for an endoscope according to the present invention is applied to an electronic endoscope (electronic type endoscope). However, it is to be noted that a flexible tube of this invention may also be applied to a fiberscope (optical type endoscope).

As shown in FIG. 2, the flexible tube 1A has a core body (structural body) 2 and an outer cover 3 that covers an outer periphery of the core body 2. Further, inside the flexible tube 1A, there is formed a hollow space 24 through which internal elements (such as optical fibers, cables, operation wires, tubular elements, and the like) can be passed.

The core body 2 acts as a reinforcing member for reinforcing the flexible tube 1A, and also acts as a protecting member for protecting the internal elements described above. This core body 2 is constructed from a coil 21 and a reticular tube 22 which covers the outer periphery of the coil 21, so that the core body 2 has an elongated tubular shape. By constructing the core body 2 using the coil 21 and the reticular tube 22, it becomes possible to give the flexible tube 1 torque transmission ability, tracking ability to a body cavity (i.e., bendability), and sufficient mechanical strength.

The coil 21 is formed from a flat metal band. Specifically, this coil 21 is formed by winding the metal band into a spiral form so as to have a uniform diameter with a gap 25 between the adjacent windings. Preferred examples of materials which may be used for the metal band include stainless steel, copper alloys, and the like.

The reticular tube 22 is formed by weaving a plurality of bundles of fine metal wires 23 in a lattice manner so as to have spaces 26 therebetween as shown in FIG. 2. Each of the bundles is formed by arranging a plurality of fine wires side by side. This reticular tube 22 may be formed from nonmetal fibers. Preferred examples of materials which may be used for the fine metal wires 23 include stainless steel, copper alloys and the like. In this invention, it is preferred that at least one of the fine wires (or fibers) constituting the reticular tube 22 is coated with a synthetic resin so that a coating of the synthetic resin is provided thereon.

On the outer periphery of the reticular tube 22, each of the spaces 26 of the reticular tube 22 forms either a recess or hole of the core body 2 depending on its location with respect to the coil 21. Specifically, as shown in FIG. 2, some of the spaces 26 located on the metal band of the coil 21 form recesses of the core body 2, while the other spaces 26 located on the gaps 25 between the adjacent windings form holes of the core body 2. As a result of the structure described above, the core body 2 has a plurality of recesses and holes.

The outer periphery of the core body 2 is covered with the outer cover 3. This outer cover 3 or a portion of the outer cover 3 is formed into a laminate structure which is composed of inner, outer and intermediate layers 31-33.

As will be described below, one of the inner, outer and intermediate layers **31–33** of the outer cover **3** is formed of a material which is different from a material constituting one of the other layers in its physical property or chemical property. Examples of such physical property include stiffness, flexibility, hardness, elongation rate, tensile strength, shearing strength, bending strength and the like. Further, examples of such chemical property include chemical resistance, weather resistance and the like.

#### (I-2) Inner Layer of Outer Cover

The inner layer **31** of the outer cover **3** is formed on the innermost side of the outer cover **3**, and it adheres to the core body **2**. Physical property of the inner layer **31** is substantially homogeneous over its entire region.

On the inner peripheral surface of the inner layer **31**, as shown in FIG. 2, there are integrally formed a plurality of projections (anchoring projections) **4**. Respective projections **4** project into spaces **26** of the core body **2** (i.e., holes and recesses of the core body **2**). As shown in FIG. 2, in the recesses (spaces **26**) of the core body **2**, each of the projections **4** extends to the outer periphery of the coil **21**. Further, in the holes (spaces **26**) of the core body **2**, each of the projections **4** extends into the gap **25** of the coil **21**.

In this invention, it is preferable that the inner layer **31** is made of a material by which formation of the projections **4** can be controlled appropriately, so that appropriate number of projections **4** having appropriate size and shape can be integrally formed on the inner layer **31** as shown in FIG. 2.

By forming the projections **4** as described above, engagements between the projections **4** and the recesses of the core body **2** and between the projections **4** and the holes of the core body **2** are achieved, and therefore the outer cover **3** is firmly fixed with respect to the core body **2** by anchoring effect given by the engagements. Such anchoring effect enables the outer cover **3** to expand and contract sufficiently in conformity with the bending of the core body **2**. Further, due to the anchoring effect, it is possible to maintain a state that the outer cover **3** adheres to the core body **2** even when the flexible tube **1A** is bended. Therefore, by forming the flexible tube in this way, it is possible to give high flexibility to the flexible tube.

Further, the bonding strength between the outer cover **3** and the reticular tube **22** is enhanced by the formation of the projections **4**, so that the peeling off of the outer cover **3** from the reticular tube **22** is prevented even after repeated use of the endoscope. This means that the flexible tube **1A** of this invention can maintain high flexibility even after the endoscope is repeatedly used, that is, the flexible tube has excellent durability.

Further, when the coating of the synthetic resin is given to at least one of the fine wires **23** forming the reticular tube **22** as described above, at least a part of the applied coating (synthetic resin) is fused with and is bonded to the inner layer **31**, thereby providing strong bonding therebetween. In this case, in order to enhance the bonding strength between the fine wires **23** and the inner layer **31**, it is preferable that the inner layer **31** of the outer cover **3** contains a material that has a compatibility with the synthetic resin of the coating.

By using the reticular tube **22** formed from the fine wires with the coating of the synthetic resin as described above, a higher adhesion between the outer cover **3** and the core body **2** is realized. Therefore, by providing the outer cover **3** on the core body **2** having the reticular tube **22** with the coating of the synthetic resin and by forming the projections **4** on the inner layer **31** as described above, it becomes possible to obtain a flexible tube having high flexibility and high

durability. In this connection, it is to be noted this excellent ability is given by the effect of the coating of the synthetic resin provided on the fine wire(s) as well as the effect of the projections **4** described above.

In this invention, a constituent material for the inner layer **31** is not particularly limited. Examples of such material include various resins having elasticity such as polyvinyl chloride, polyolefine (e.g., polyethylene, polypropylene, ethylene-vinylacetate copolymer and the like), polyamide, polyester (e.g., polyethylene terephthalate (PET), polybutylene terephthalate and the like), polyurethane, polystyrene resin, fluoro-based resin (e.g., polytetrafluoroethylene, ethylene-tetrafluoroethylene copolymer and the like), polyimide, and the like; and various elastomers such as polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polyamide-based elastomer, polystyrene-based elastomer, fluorine-based elastomer, silicone rubber, fluororubber, latex rubber, and the like. These can be used alone or as a mixture of two or more thereof. In this invention, a material containing at least one of polyurethane-based elastomer, polyolefin-based elastomer, and polyester-based elastomer is preferably used to form the inner layer **31**, since they can be easily formed into the inner layer with the projections **4** as shown in FIG. 2.

The average thickness of the inner layer **31** (excluding the portions of the projections **4**) is not particularly limited, but the thickness is preferably in the range of 0.05 to 0.8 mm, and more preferably in the range of 0.05 to 0.4 mm.

#### (I-3) Outer Layer of Outer Cover

The outer layer **32** is formed on the outermost side of the outer cover **3**, and has almost homogeneous physical properties over its entire region. In this invention, it is preferable that the outer layer **32** is formed of a material having a resistance to chemicals. By using such a material, it is possible to suppress the degradation of the outer cover **3** due to repeated cleaning and disinfection. Further, it is also possible to suppress deterioration in flexibility caused by the hardening of the outer cover due to repeated cleaning and disinfection. In addition, it is also possible to prevent peeling off of the outer cover **3** from the reticular tube **22** due to cracks or the like caused by repeated cleaning and disinfection.

The outer layer **32** is formed so as to have a relatively high hardness. This prevents the generation of scratches that are liable to produce cracks or the like on the surface of the outer cover **3**. In this invention, it is preferable that the outer layer **32** of the outer cover **33** has higher hardness than that of any one of the inner and intermediate layers **31** and **33** in part or over its entire region.

In this invention, a constituent material for the outer layer **32** is not particularly limited. Examples of such material include various resins having elasticity such as polyvinyl chloride, polyolefine (e.g., polyethylene, polypropylene, ethylene-vinylacetate copolymer and the like), polyamide, polyester (e.g., polyethylene terephthalate (PET), polybutylene terephthalate and the like), polyurethane, polystyrene resin, fluoro-based resin (e.g., polytetrafluoroethylene, ethylene-tetrafluoroethylene copolymer and the like), polyimide, and the like; and various elastomers such as polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polyamide-based elastomer, polystyrene-based elastomer, fluorine-based elastomer, silicone rubber, fluororubber, latex rubber, and the like. These can be used alone or as a mixture of two or more thereof. In this invention, a material containing at least one of polyolefine (e.g., ethylene-vinylacetate copolymer and the like), fluoro-based resin (e.g., polytetrafluoroethylene, ethylene-

tetrafluoroethylene copolymer and the like), polyester-based elastomer, polyolefine-based elastomer, fluorine-based elastomer, silicone rubber and fluororubber is preferably used to form the outer layer **32**, since they have high resistance to chemical.

The thickness of the outer layer **32** is not particularly limited, but the thickness is preferably in the range of 0.05 to 0.8 mm, and more preferably in the range of 0.05 to 0.4 mm.

#### (I-4) Intermediate Layer of Outer Cover

In this invention, it is preferable that the intermediate layer **33** has a higher elasticity than that of the outer layer **32**, and more preferably the intermediate layer **33** has a higher elasticity than that of any one of the inner and outer layers **31** and **32**. With this arrangement, the intermediate layer **33** functions as a cushioning layer (cushioning means) between the inner layer **31** and the outer layer **32**. (In the following, such a function of the intermediate layer **33** is referred to as "cushioning function.") Accordingly, by forming the intermediate layer **33** as described above, it is possible to give higher flexibility to the flexible tube.

Hereinafter, the cushioning function of the intermediate layer **33** is described in more detail. When the flexible tube **1A** is bent by an external force, the high elastic force is generated in the bent intermediate layer **33** through the deformation thereof. The generated elastic force is transmitted effectively to the inner layer **31** and the outer layer **32**, respectively, since the intermediate layer **33** is sandwiched between the inner layer **31** and the outer layer **32** each of which has relatively low elasticity. When the external force has been removed, the bent flexible tube **1A** is restored to its original shape by the high elastic force generated in the bent intermediate layer **33**. In this connection, it is to be noted that the restoration of the flexible tube into its original shape is achieved by the cushioning function of the intermediate layer **33**, and that such a cushioning function gives the flexible tube high flexibility.

In this invention, a constituent material for the intermediate layer **33** is not particularly limited. Examples of such material include various resins having elasticity such as polyvinyl chloride, polyolefine (e.g., polyethylene, polypropylene, ethylene-vinylacetate copolymer), polyamide, polyester (e.g., polyethylene terephthalate (PET), polybutylene terephthalate), polyurethane, polystyrene resin, fluoro-based resin (e.g., polytetrafluoroethylene, ethylene-tetrafluoroethylene copolymer), polyimide, and the like; and various elastomers such as polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polyamide-based elastomer, polystyrene-based elastomer, fluorine-based elastomer, silicone rubber, fluororubber, latex rubber, and the like. These can be used alone or as a mixture of two or more thereof. In this invention, a material containing at least one of low hardness polyurethane-based elastomer, low hardness polyolefine-based elastomer, and low hardness polyester-based elastomer is preferably used to form the intermediate layer **33**, since such elastomers have high elasticity.

Although the intermediate layer **33** in this embodiment is given a single layer structure, it may be given a structure of two or more layers.

The average thickness of the intermediate layer **33** is not particularly limited, but the average thickness is preferably in the range of 0.05 to 0.8 mm, and more preferably in the range of 0.05 to 0.4 mm.

#### (I-5) Outer Cover Having the Layers

In this invention, the average thickness of the outer cover **3** (excluding the portions of the projections **4**) is not par-

ticularly limited, as long as the outer cover **3** can protect the core body **2** and the internal elements arranged in the core body **2** from a fluid (e.g., body fluid) and it does not impair the bendability of the flexible tube. However, the average thickness of the outer cover **3** (excluding the portions of the projections **4**) is preferably in the range of 0.15 to 0.9 mm, and more preferably in the range of 0.3 to 0.8 mm.

In addition, it is preferable that the outer cover **3** (excluding the portions of the projections **4**) has a substantially uniform thickness over its entire region. With this arrangement, it is possible to produce a flexible tube having a substantially uniform diameter over its entire region. When an endoscope having a flexible tube with such an outer cover is used in an endoscopic examination, it is possible for an operator to easily and smoothly insert the insertion section (flexible tube) of the endoscope into a body cavity of a patient, thus making it possible to reduce the burden on the patient during the endoscopic examination.

#### (I-6) Manufacturing Method of Flexible Tube

A method of manufacturing a flexible tube for an endoscope as described in the above is not particularly limited, but it is preferable that the flexible tube of this invention is manufactured by extrusion molding. When such extrusion molding is performed using an extrusion molding machine equipped with a plurality of extrusion ports, it is possible to extrude the inner, outer and intermediate layers **31-33** simultaneously so that the core body **2** is covered with the outer cover **3** having the laminate structure composed of these layers. In this extrusion molding, it is preferable to adjust the feeding amount (i.e., feeding amount per unit time) of constituent material for each layer from each extrusion port while adjusting the feeding speed of the core body **2**. This method makes it is possible to control properly the thickness, shape and property of each layer.

The temperature of the material when performing the extrusion molding is not particularly limited, but the temperature is preferably about 130 to 220° C., and more preferably about 165 to 205° C. Within such a range, the material has an excellent moldability. Therefore, by performing the extrusion molding using the material whose temperature is within the range described above, it becomes possible to improve uniformity of the thickness of the outer cover **3** provided on the core body **2**.

## II. EXAMPLES OF FIRST EMBODIMENT

Next, specific examples of the first embodiment of the present invention will be described below.

### 1. Preparation of Flexible Tube for an Endoscope

#### Example 1a

First, a coil **21** having an outer diameter of 9.9 mm and an inner diameter of 9.6 mm was prepared by winding a band-shaped stainless steel material having a width of 3 mm. Next, stainless steel fine wires **23** at least one of which had been given a coating of a polyamide resin and each of which had a diameter of 0.1 mm were prepared, and then using these fine wires a plurality of bundles of ten fine wires were prepared. These bundles of the ten fine wires **23** were woven together in a lattice manner to obtain a reticular tube **22**. Then, the obtained reticular tube **22** was provided on the prepared coil **21** so that the outer periphery of the coil **21** was covered with the reticular tube **22**. In this way, a core body **2** was prepared.

Next, using an extrusion-molding machine, an outer cover **3** composed of inner, outer and intermediate layers **31-33** was provided on the outer periphery of the core body **2** so

## 11

that the core body **2** was covered with the outer cover **3**. In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. In this connection, it is to be noted that the length of 1.6 m means the length of an available (effective) portion of the flexible tube that can be used for a flexible tube for an endoscope, that is the length of 1.6 m means an available (effective) length of the flexible tube. Therefore, the actually prepared flexible tube had a length more than 1.6 m by including additional portions at the both ends of the available portion of the flexible tube. In this regard, however, it goes without saying that the available length is not limited to 1.6 m mentioned above.

A constituent material used for each of the layers in this Example is shown in the attached Table 1. In addition, the thickness of each of the layers is also shown in Table 1.

## Example 1b

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the thickness of the inner layer **31** was changed as shown in the attached Table 1.

## Example 1c

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the thickness of the intermediate layer **33** was changed as shown in the attached Table 1.

## Example 1d

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the thickness of the outer layer **32** and the material for the outer layer **32** were changed as shown in the attached Table 1.

## Example 1e

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the material for the outer layer **32** was changed as shown in the attached Table 1.

## Comparative Example 1a

A core body **2** was prepared in the same manner as in Example 1a. Then, using an extrusion-molding machine, an outer cover **3** composed of inner and outer layers **31** and **32** was provided on the outer periphery of the core body **2** so that the core body **2** was covered with the outer cover **3**. In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. A constituent material for each layer of the outer cover **3** and the thickness of each layer are shown in the attached Table 1.

## Comparative Example 1b

A flexible tube for an endoscope was prepared in the same manner as in Comparative Example 1a except that the material for the outer layer **32** was changed as shown in the attached Table 1.

## Comparative Example 1c

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the thickness of each of inner and outer layers **31** and **32** and the material for each of the inner and outer layers **31** and **32** were changed as shown in the attached Table 1.

## Comparative Example 1d

A flexible tube for an endoscope was prepared in the same manner as in Example 1a except that the material for each

## 12

of inner and outer layers **31** and **32** was changed as shown in the attached Table 1.

## 2. Observation of the Prepared Flexible Tubes

An observation of the cross-section of the outer cover was carried out for each of the flexible tubes of Examples 1a–1e and Comparative Examples 1a–1d. Through the observation, formation of projections **4** as shown in FIG. **2** was observed in each of the flexible tubes of Examples 1a–1e and Comparative Examples 1a, 1b and 1d, but no formation of projections **4** was observed in the flexible tube of Comparative Example 1c.

## 3. Evaluation of Flexible Tube

## (3-1) Chemical Resistance Test

A chemical resistance test was carried out for each of the flexible tubes of Example 1a–1e and Comparative Example 1a–1d. In this test, 100 L of 10% aqueous solution of iodine held at 25° C. was prepared first, and then each of the prepared flexible tubes was immersed in the aqueous solution for 200 hours. Then, the condition of each flexible tube was evaluated in accordance with the four rankings A–D given below.

Rank A:

No Change in the Appearance; and

No Occurrence of Cracks and Blisters in Outer Cover.

Rank B:

Slight Change in the Appearance; and

Occurrence of Blisters at a Few Spots of Outer Cover.

Rank C:

Large Change in the Appearance; and

Occurrence of Blisters at Many Spots of Outer Cover.

Rank D:

Extremely Large Change in the Appearance; and

Occurrence of a Large Number of Cracks and Blisters on Outer Cover.

The evaluation results in this test are shown in the attached Table 1.

## (3-2) Flexibility Test

A flexibility test was carried out for each of the flexible tubes of Example 1a–1e and Comparative Example 1a–1d. In this test, the flexible tube for an endoscope supported at its both ends was subjected to bending by 90°, and the flexibility in that state was evaluated in accordance with the four rankings A–D given below.

Rank A:

High Flexibility

(A flexible tube of Rank A is considered to be best suited for use as a flexible tube for an endoscope.)

Rank B:

Normal Flexibility

(A flexible tube of Rank B is considered to be suited for use as a flexible tube for an endoscope.)

Rank C:

Low Flexibility

(A flexible tube of Rank C is considered to have problems in use as a flexible tube for an endoscope.)

Rank D:

Almost No Flexibility

(A flexible tube of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The result of the flexibility test is shown in the attached Table 1.

## (3-3) Durability Test

A durability test was carried out for each of the flexible tubes of Examples 1a–1e and Comparative Examples 1a–1d.

In the durability test, each of the flexible tubes was set to a state where the flexible tube was supported at its both ends, and in this state the operation of bending by 90° was repeated 300 times. Then, the degree of change in the flexibility after the repeated operation of bending was examined to evaluate the durability of each flexible tube in accordance with the four rankings A–D given below.

Rank A:

Almost No Change in Flexibility

(A flexible tube of Rank A is considered to have extremely high durability.)

Rank B:

Slight Lowering of Flexibility

(A flexible tube of Rank B is considered to have high durability.)

Rank C:

Large Lowering of Flexibility

(A flexible tube of Rank C is considered to have problems in its durability.)

Rank D:

Extremely Large Lowering of Flexibility; and

Occurrence of cracks and the like at many spots of the outer cover.

(A flexible tube of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The result of the durability test is shown in the attached Table 1.

#### (3-4) Evaluation

The results in the attached Table 1 show that the flexible tube according to the present invention (i.e., Examples 1a–1e) has high chemical resistance and high flexibility as well as high durability. Further, the results in Table 1 also show that conventional flexible tubes (i.e., Comparative Examples 1a–1d) have some drawbacks.

Specifically, the flexible tube of Comparative Example 1a has poor resistance to chemical. This drawback is considered to result from the fact that the outer layer 32 of the outer cover 3 was made of the material with poor chemical resistance. Further, the flexible tube of Comparative Example 1b has poor flexibility. This drawback is considered to result from the fact that both the inner and outer layers 31 and 32 were formed of the materials with relatively high hardness. Furthermore, the flexible tube of Comparative Example 1c has poor flexibility and poor durability. These drawbacks are considered to result from the fact that no projections 4 as shown in FIG. 2 were formed on the inner layer 31. In addition, the flexible tube of Comparative Example 1d has poor durability. This drawback is considered to result from the fact that the inner layer 31 was formed of the material with relatively low hardness and therefore the projections 4 on the inner layer 31 had poor strength.

According to the present invention described above, appropriate materials that are suitable for each of layers of an outer cover 3 are used for preparing an outer cover 3, and the outer cover 3 is provided onto the core body 2 so that each of the layers has appropriate thickness and shape. This structure and the selection of material make it possible to provide a flexible tube for an endoscope that has high durability and high flexibility as well as high chemical resistance.

Further, when a material with high elasticity is used for the intermediate layer of the outer cover, it is possible to give higher flexibility to the flexible tube. In addition, when a material having a high adhesion with the core body is used for the inner layer of the outer cover, it is also possible to give high durability to the flexible tube for an endoscope.

### III. Second Embodiment (Flexible Tube 1B)

Next, a second embodiment of the flexible tube for an endoscope will be described with reference to FIG. 3. FIG. 3 is a sectional view which shows a part of a flexible tube 1B according to the present invention, in which illustration of projections 4 as shown in FIG. 2 is omitted, and structure of a reticular tube 22 is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end 11 shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end 12 shown in FIG. 1. In the following, description of the configurations and features that are the same as those in the above-mentioned first embodiment will be omitted, and description will be given mainly with respect to the configurations and features that are different from those of the first embodiment.

As shown in FIG. 3, an outer cover (or a portion of the outer cover) 3 of the flexible tube 1B has a laminate structure which is composed of inner, outer and intermediate layers 31–33. The inner layer 31 has a smaller thickness at a portion nearer to the tip end 12 of the flexible tube 1B, while each of the outer and inner layers 32 and 33 has a substantially uniform thickness over its entire region. This structure gives the outer cover 3 a stiffness (e.g., bending stiffness) that decreases in the longitudinal direction from the base end 11 toward the tip end 12. By forming the outer cover 3 such that its stiffness varies in the longitudinal direction, it is possible to give a flexible tube flexibility that increases in the longitudinal direction from the base end 11 toward the tip end 12. According to such a flexible tube for an endoscope, since the flexible tube has a higher stiffness in a portion closer to the base end 11, it is possible to fully transmit to the tip end 12 the push-in force and the rotational force applied by the operator. On the other hand, since the flexible tube has high flexibility in a portion closer to the tip end 12, it is also possible to smoothly insert an insertion section (flexible tube) of an endoscope into an internal curved portion of a patient in a safe manner. Therefore, the flexible tube 1B as described above makes it possible for an operator to insert the insertion section with easy manipulation, thus enabling the reduction of the burden on the patient during the endoscopic examination.

In this embodiment, the rate of change in the thickness of the inner layer 31 in the longitudinal direction, that is, the shape of the inner layer 31 is appropriately determined to realize the desired rate of change in the stiffness of the flexible tube in the longitudinal direction. This makes it possible, for example, to produce various kinds of flexible tubes for an endoscope taking into account various shapes of internal portions of a living body, operator's tastes and the like.

Further, in this embodiment, the value of  $T1_{min}/T1_{max}$  is not particularly limited, where the value of " $T1_{min}$ " is given by the thickness of the thinnest part of the inner layer 31, and the value of " $T1_{max}$ " is given by the thickness of the thickest part of the inner layer 31. However, the value of  $T1_{min}/T1_{max}$  is preferably in the range of 0.05 to 0.95, and more preferably in the range of 0.1 to 0.6.

### IV. Third Embodiment (Flexible Tube 1C)

Next, a third embodiment of the flexible tube for an endoscope will be described with reference to FIG. 4. FIG. 4 is a sectional view which shows a part of a flexible tube 1C according to the present invention, in which illustration of projections 4 as shown in FIG. 2 is omitted, and structure of a reticular tube 22 is simply illustrated as a layer. In this

15

figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. 1.

In this embodiment, an outer cover **3** of the flexible tube **1C** has a laminate structure composed of inner, outer and intermediate layers **31–33**. Each of the inner and intermediate layers **31** and **33** has a thickness which gradually varies over its entire region, and the outer layer **32** has a substantially uniform thickness over its entire region.

As shown in FIG. 4, the thickness of the inner layer **31** gradually “decreases” in the direction from the base end **11** toward the tip end **12**. Conversely, the thickness of the intermediate layer **33** gradually “increases” in the direction from the base end **11** toward the tip end **12**. In this embodiment, the intermediate layer **33** is formed of a material having higher elasticity than that of the inner layer **31**.

In this connection, it is to be noted that the thickness of the intermediate layer **33** decreases in the opposite direction to that of the inner layer **31**. Further, it is also to be noted that the total thickness of the inner and intermediate layers **31** and **33** remains substantially uniform over the entire region of the outer cover **3**, and the thickness of the outer cover **3** remains substantially uniform over its entire region, in spite of the fact that the thickness of each of the inner and intermediate layers **31** and **33** varies over its entire region.

In this embodiment, the value of  $T3_{min}/T3_{max}$  is not particularly limited, where the value of “ $T3_{min}$ ” is given by the thickness of the thinnest part of the intermediate layer **33**, and the value of “ $T3_{max}$ ” is given by the thickness of the thickest part of the intermediate layer **33**. However, the value of  $T3_{min}/T3_{max}$  is preferably in the range of 0.05 to 0.95, and more preferably in the range of 0.1 to 0.6.

According to the flexible tube **1C** having the structure described above, in spite of the fact that the total thickness of the outer cover **3** (excluding the portions of the projections **4**) is substantially uniform over its entire region, the ratio of the thickness of the intermediate layer **33** to that of each of the inner and outer layer **31** and **32** becomes larger at a portion closer to the tip end **12**. This structure makes it possible for the flexible tube **1C** to have higher stiffness against tension and bending at a portion closer to the “base” end **11**, and to have higher flexibility at a portion closer to the “tip” end **12**. In other words, this structure makes it possible for the flexible tube **1C** to have flexibility which gradually varies in the longitudinal direction.

According to the flexible tube for an endoscope as described above, since the flexible tube has higher stiffness in a portion closer to the base end **11**, it is possible to fully transmit to the tip end **12** the push-in force and the rotational force applied by the operator. On the other hand, the flexible tube has higher flexibility in a portion closer to the tip end **12**, it is also possible to smoothly insert an insertion section (flexible tube) of an endoscope into an internal curved portion of a patient in a safe manner. Therefore, the flexible tube as described above makes it possible for an operator to insert the insertion section with easy manipulation, thus enabling the reduction of the burden on the patient during the endoscopic examination.

Further, according the flexible tube **1C** of this embodiment, the outer cover **3** is formed such that the thickness of one of the inner and intermediate layers **31** and **33** decreases in the opposite direction to the other layer. This results in that the flexible tube **1C** has a uniform outer diameter over its entire region. When such a flexible tube

16

having a uniform outer diameter is actually used, it is possible to reduce the burden on the patient during endoscopic examination.

#### V. Fourth Embodiment (Flexible Tube ID)

Next, a fourth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 5. FIG. 5 is a sectional view which shows a part of a flexible tube **1D** according to the present invention, in which illustration of projections **4** as shown in FIG. 2 is omitted, and structure of a reticular tube **22** is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. 1. Further, in this figure, the reference numeral “I” indicates a region where a thickness-varying region is formed, and each of the reference numerals “II” and “III” indicates a region where no thickness-varying region is formed. (In this description, a region within which the thickness of a layer increases or decreases is referred to as a “thickness-varying region” of the layer.) In this connection, it is to be noted that the total length of the regions I, II and III corresponds to the length of an outer cover **3** of the flexible tube **1D**.

As shown in FIG. 5, the outer cover **3** of the flexible tube **1D** has a laminate structure composed of inner, outer and intermediate layers **31–33**. Each of the inner and intermediate layers **31** and **33** has a thickness-varying region **34** within the region I, and the outer layer **32** has a substantially uniform thickness over its entire region. The thickness-varying region of each of the inner and intermediate layers **31** and **33** has a relatively small length (e.g., approximately 5 to 80 mm). In this embodiment, the intermediate layer **33** is formed of a material having higher elasticity than that of the inner layer **31**.

The thickness-varying region **34** of the inner layer **31** is formed at a specific portion of this layer (i.e., within the region I), and as shown in FIG. 5 the thickness of this thickness-varying region **34** gradually decreases within the region I in the direction from the base end **11** toward the tip end **12**. Within the regions II and III the inner layer **31** has a substantially uniform thickness, but it has larger thickness within the region III as compared with the thickness within the region II.

Similarly the thickness-varying region **34** of the intermediate layer **33** is also formed within the region I, and as shown in FIG. 5 the thickness of this thickness-varying region **34** gradually decreases within the region I in the direction from the tip end **12** toward the base end **11** (i.e., in the direction opposite to that of the thickness-varying region **34** of the inner layer **31**). Within the regions II and III the intermediate layer **33** has a substantially uniform thickness, but it has larger thickness within the region II as compared with the thickness within the region III.

It is to be noted that in this embodiment the outer cover **3** having the inner, outer and intermediate layers **31–33** is formed so that the thickness-varying regions **34** of the inner and intermediate layers **31** and **33** face (overlap) each other in the thickness direction as shown in FIG. 5. Further, it is also to be noted that the total thickness of the inner and intermediate layers **31** and **33** remains substantially uniform over the entire region of the flexible tube **1D** in spite of the fact that these layers have a thickness-varying region.

According to the flexible tube **1D** having the structure described above, since the intermediate layer **33** is formed of a material having higher elasticity than that of the inner layer

31, the outer cover 3 has a relatively high stiffness (low flexibility) within the region III, while it has a relatively low stiffness (high flexibility) within the region II. In addition, the outer cover 3 has a medium stiffness within the region I where the thickness-varying regions 34 are formed, and the stiffness of this portion varies in the longitudinal direction. The structure described above gives higher stiffness to the base side region (region III) of the flexible tube 1D, while it gives higher flexibility to the tip side region (region II) of the flexible tube 1D. In addition, the structure described above makes it possible to form a flexible tube such that its stiffness (flexibility) varies gradually or stepwise within a portion where a thickness-varying region(s) is formed. According to such a flexible tube, since it has higher stiffness in a portion closer to the base end 11, it is possible to fully transmit to the tip end 12 the push-in force and the rotational force applied by the operator. On the other hand, the flexible tube has high flexibility in a portion closer to the tip end 12, it is also possible to smoothly insert an insertion section (flexible tube) of an endoscope into an internal curved portion of a patient in a safe manner. Therefore, the flexible tube as described above makes it possible for an operator to insert the insertion section with easy manipulation, thus enabling the reduction of the burden on the patient during the endoscopic examination.

Further, according to the flexible tube 1D in this embodiment, the flexible tube 1D has a uniform outer diameter over its entire region in spite of the fact that each of the inner and intermediate layers 31 and 33 has a thickness-varying region 34. Therefore, when such a flexible tube having a uniform outer diameter is used, it is possible to reduce the burden on the patient during endoscopic examination.

#### VI. Fifth Embodiment (Flexible Tube 1E)

Next, a fifth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 6. FIG. 6 is a sectional view which shows a part of a flexible tube 1E according to the present invention, in which illustration of projections 4 as shown in FIG. 2 is omitted, and structure of a reticular tube 22 is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end 11 shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end 12 shown in FIG. 1.

In this embodiment, an outer cover 3 of the flexible tube 1E has a laminate structure composed of inner, outer and intermediate layers 31–33. The inner layer 31 has a substantially uniform thickness over its entire region. The thickness of each of the outer and intermediate layers 32 and 33 varies over the entire region. As shown in FIG. 6, the thickness of the outer layer 32 gradually “decreases” in the direction from the base end 11 toward the tip end 12. Conversely, the thickness of the intermediate layer 33 gradually “increases” in the direction from the base end 11 toward the tip end 12. In this embodiment, the intermediate layer 33 is formed of a material having higher elasticity than that of the outer inner layer 31.

In this connection, it is to be noted that the thickness of the intermediate layer 33 decreases in the opposite direction to that of the outer layer 32. Further, it is also to be noted that the total thickness of the outer and intermediate layers 32 and 33 remains substantially uniform over the entire region of the flexible tube 1E, and the thickness of the outer cover 3 remains substantially uniform over its entire region in spite of the fact that the thickness of each of the outer and intermediate layers 32 and 33 varies over its entire region.

In this embodiment, the value of  $T2_{min}/T2_{max}$  is not particularly limited, where the value of “ $T2_{min}$ ” is given by the thickness of the thinnest part of the outer layer 32, and the value of “ $T2_{max}$ ” is given by the thickness of the thickest part of the outer layer 32. However, the value of  $T2_{min}/T2_{max}$  is preferably in the range of 0.05 to 0.95, and more preferably in the range of 0.1 to 0.6.

According to the flexible tube 1E of this invention, it is possible to achieve the same advantages as those described with respect to the flexible tube 1C (FIG. 4) in the third embodiment.

#### VII. Sixth Embodiment (Flexible Tube 1F)

Next, a sixth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 7. FIG. 7 is a sectional view which shows a part of a flexible tube 1F according to the present invention, in which illustration of projections 4 as shown in FIG. 2 is omitted, and structure of a reticular tube 22 is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end 11 shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end 12 shown in FIG. 1. Further, in this figure, the reference numeral “I” indicates a region where a thickness-varying region is formed, and each of the reference numerals “II” and “III” indicates a region where no thickness-varying region is formed. In this connection, it is to be noted that the total length of the regions I, II and III corresponds to the length of an outer cover 3 of the flexible tube 1F.

As shown in FIG. 7, the outer cover 3 of the flexible tube 1F has a laminate structure composed of inner, outer and intermediate layers 31–33. Each of the outer and intermediate layer 32 and 33 has a thickness-varying region 34 within the region I, and the inner layer 31 has a substantially uniform thickness over its entire region. The thickness-varying region 34 of each of the outer and intermediate layers 32 and 33 has relatively small length (e.g., approximately 5 to 80 mm). In this embodiment, the intermediate layer 33 is formed of a material having higher elasticity than that of the outer layer 32.

The thickness-varying region 34 of the outer layer 32 is formed at a specific portion of this layer (i.e., within the region I), and as shown in FIG. 7 the thickness of this thickness-varying region 34 gradually decreases within the region I in the direction from the base end 11 toward the tip end 12. Within the regions II and III the outer layer 32 has a substantially uniform thickness, but it has larger thickness within the region III as compared with the thickness within the region II.

Similarly the thickness-varying region 34 of the intermediate layer 33 is also formed within the region I, but as shown in FIG. 7 the thickness of this thickness-varying region 34 gradually decreases within the region I in the direction from the tip end 12 toward the tip end 12 (i.e., in the direction opposite to that of the thickness-varying region 34 of the outer layer 32). Within the regions II and III the intermediate layer 33 has a substantially uniform thickness, but it has larger thickness within the region II as compared with the thickness within the region III.

It is to be noted that in this embodiment the outer cover 3 having the inner, outer and intermediate layers 31–33 is formed so that the thickness-varying regions 34 of the outer and intermediate layers 32 and 33 face (overlap) each other in the thickness direction as shown in FIG. 7. Further, it is also to be noted that the total thickness of the outer and intermediate layers 32 and 33 remains substantially uniform

19

over the entire region of the outer cover **3** in spite of the fact that each of the outer and intermediate layers **32** and **33** has a thickness-varying region.

According to the flexible tube **1F** of this invention, it is possible to achieve the same advantages as those described with respect to the flexible tube **1D** in the fourth embodiment.

#### VIII. EXAMPLES OF SECOND-SIXTH EMBODIMENTS

Next, specific examples of the second-sixth embodiments described above will be described below.

##### 1. Preparation of Flexible Tube for an Endoscope

###### Example 2a

First, a coil **21** having an outer diameter of 9.9 mm and an inner diameter of 9.6 mm was prepared by winding a band-shaped stainless steel material having a width of 3 mm. Next, stainless steel fine wires **23** at least one of which had been given a coating of a polyamide resin and each of which had a diameter of 0.1 mm were prepared, and then using these fine wires a plurality of bundles of ten fine wires were prepared. These bundles of the ten fine wires **23** were woven together in a lattice manner to obtain a reticular tube **22**. Then, the obtained reticular tube **22** was provided on the prepared coil **21** so that the outer periphery of the coil **21** was covered with the reticular tube **22**. In this way, a core body **2** was prepared.

Next, using an extrusion-molding machine, an outer cover **3** composed of inner, outer and intermediate layers **31–33** was provided on the outer periphery of the core body **2** so that the core body **2** was covered with the outer cover **3**. (A constituent material used for each of the layers in this Example is as shown in the attached Table 2.) In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. In this connection, it is to be noted that the length of 1.6 m means the length of an available (effective) portion of the flexible tube that can be used for a flexible tube for an endoscope, that is the length of 1.6 m means an available (effective) length of the flexible tube. Therefore, the actually prepared flexible tube had a length more than 1.6 m by including additional portions at the both ends of the available portion of the flexible tube (See FIG. 13). In this regard, however, it goes without saying that the available length is not limited to 1.6 m mentioned above.

In the preparation described above, the outer cover **3** was provided over the core body **2** such that the thickness of the inner layer **31** gradually increases at a constant rate between both ends **11** and **12** of the flexible tube in the direction from the tip end **12** toward base end **11**. Specifically, the inner layer **31** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.05 mm ( $T1_{min}$ ) at the tip end **12** and have a thickness of 0.4 mm ( $T1_{max}$ ) at the base end **11**. In the inner layer **31** of the prepared flexible tube, the  $T1_{min}/T1_{max}$  had a value of 0.125, where the value of " $T1_{min}$ " is given by the thickness of the thinnest part of the inner layer **31**, and the value of " $T1_{max}$ " is given by the thickness of the thickest part of the inner layer **31**.

In addition, the intermediate layer **33** was formed such that its thickness gradually decreases at a constant rate between the both ends **11** and **12** in the direction from the tip end **12** toward base end **11**. Specifically, the intermediate layer **33** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.05 mm ( $T3_{min}$ ) at the base end **11** and have a thickness of 0.4 mm ( $T3_{max}$ ) at the tip end **12**. In the intermediate layer **33** of the prepared

20

flexible tube, the  $T3_{min}/T3_{max}$  had a value of 0.125, where the value of " $T3_{min}$ " is given by the thickness of the thinnest part of the intermediate layer **33**, and the value of " $T3_{max}$ " is given by the thickness of the thickest part of the intermediate layer **33**.

The outer layer **32** of the outer cover **3** was formed over the entire region (length) of the outer cover **3** so as to have a uniform thickness (0.1 mm).

###### Example 2b

A flexible tube for an endoscope was prepared in the same manner as in Example 2a except that the thickness (shape) of each layer of an outer cover **3** was changed as follows.

In the preparation of the flexible tube, the outer cover **3** was provided over the core body **2** such that the thickness of the outer layer **32** gradually increases at a constant rate between both ends **11** and **12** of the flexible tube in the direction from the tip end **12** toward base end **11**. Specifically, the outer layer **32** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.05 mm ( $T2_{min}$ ) at the tip end **12** and have a thickness of 0.4 mm ( $T2_{max}$ ) at the base end **11**. In the inner layer **31** of the prepared flexible tube, the  $T2_{min}/T2_{max}$  had a value of 0.125, where the value of " $T2_{min}$ " is given by the thickness of the thinnest part of the outer layer **32**, and the value of " $T2_{max}$ " is given by the thickness of the thickest part of the outer layer **32**.

In addition, the intermediate layer **33** was formed such that its thickness gradually decreases at a constant rate between the both ends **11** and **12** in the direction from the tip end **12** toward base end **11**. Specifically, the intermediate layer **33** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.05 mm ( $T3_{min}$ ) at the base end **11** and have a thickness of 0.4 mm ( $T3_{max}$ ) at the tip end **12**. In the intermediate layer **33** of the prepared flexible tube, the  $T3_{min}/T3_{max}$  had a value of 0.125, where the value of " $T3_{min}$ " is given by the thickness of the thinnest part of the intermediate layer **33**, and the value of " $T3_{max}$ " is given by the thickness of the thickest part of the intermediate layer **33**.

The inner layer **31** of the outer cover **3** was formed over the entire region (length) of the outer cover **3** so as to have a uniform thickness (0.1 mm).

###### Example 2c

A flexible tube for an endoscope was prepared in the same manner as in Example 2a except that the thickness (shape) of each layer of an outer cover **3** was changed as follows.

In the preparation of the flexible tube, the outer layer **32** of the outer cover **3** was formed such that its thickness increases stepwise in four steps in the direction from the tip end **12** to the base end **11**. Specifically, the outer layer **32** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.05 mm at a first quarter (that is closest to the tip end **12**) of the entire region; have a thickness of 0.15 mm at a second quarter adjacent to the first quarter; have a thickness of 0.25 mm at a third quarter adjacent to the second quarter; and have a thickness of 0.4 mm at a fourth quarter (that is closest to the base end **11**) adjacent to the third quarter. In this outer layer **32**, the tip end **12** had a thickness of 0.05 mm ( $T2_{min}$ ), and the base end **11** had a thickness of 0.4 mm ( $T2_{max}$ ). Thus, the  $T2_{min}/T2_{max}$  had a value of 0.125, where the value of " $T2_{min}$ " was given by the thickness of the thinnest part of the outer layer **32**, and the value of " $T2_{max}$ " was given by the thickness of the thickest part of the outer layer **32**.

## 21

Further, the intermediate layer **33** of the outer cover **3** was formed such that the thickness decreases stepwise in four steps in the direction from the tip end **12** to the base end **11**. Specifically, the intermediate layer **33** had been formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.4 mm at a first quarter (that is closest to the tip end **12**) of the entire region; have a thickness of 0.25 mm at a second quarter adjacent to the first quarter; have a thickness of 0.15 mm at a third quarter adjacent to the second quarter; and have a thickness of 0.05 mm at a fourth quarter (that is closest to the base end **11**) adjacent to the third quarter. In this intermediate layer **33**, the tip end **12** had a thickness of 0.05 mm ( $T3_{min}$ ), and the base end **11** had a thickness of 0.4 mm ( $T3_{max}$ ). Thus, the  $T3_{min}/T3_{max}$  had a value of 0.125, where the value of " $T3_{min}$ " was given by the thickness of the thinnest part of the intermediate layer **33**, and the value of " $T3_{max}$ " was given by the thickness of the thickest part of the intermediate layer **33**.

In addition, the inner layer **31** of the outer cover **3** was formed over the entire region (length) of the outer cover **3** so as to have a uniform thickness (0.1 mm).

## Example 2d

A flexible tube for an endoscope was prepared in the same manner as in Example 2b except that the thickness (shape) of an outer layer **32** of an outer cover **3** was changed as follows, and a constituent material for the outer layer **32** was changed as shown in the attached Table 2.

In the preparation of the flexible tube, the outer cover **3** was provided over the core body **2** such that the thickness of the outer layer **32** gradually increases at a constant rate between the both ends **11** and **12** of the flexible tube in the direction from the tip end **12** toward base end **11**. Specifically, the outer layer **32** was formed over the entire region (length) of the outer cover **3** so as to have a thickness of 0.1 mm ( $T2_{min}$ ) at the tip end **12** and have a thickness of 0.45 mm ( $T2_{max}$ ) at the base end **11**. In the outer layer **32** of the prepared flexible tube, the  $T2_{min}/T2_{max}$  had a value of 0.222, where the value of " $T2_{min}$ " was given by the thickness of the thinnest part of the outer layer **32**, and the value of " $T2_{max}$ " was given by the thickness of the thickest part of the outer layer **32**.

## Example 2e

A flexible tube for an endoscope was prepared in the same manner as in Example 2a except that a material for an outer layer **32** of an outer cover **3** was changed as shown in the attached Table 2.

## Comparative Example 2a

A core body **2** was prepared in the same manner as in Example 2a. Then, using an extrusion-molding machine, an outer cover **3** composed of two layers (i.e., inner and outer layers **31** and **32**) was provided on the outer periphery of the core body **2** so that the core body **2** was covered with the outer cover **3**. In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. A constituent material for each layer of the outer cover **3** is shown in the attached Table 2.

In the preparation of the flexible tube in this embodiment, the inner layer **31** of the outer cover **3** was formed over the entire region (length) of the outer cover **3** so as to have a uniform thickness (0.2 mm). Further, the outer layer **32** of the outer cover **3** was formed over the entire region (length) of the outer cover **3** so as to have a uniform thickness (0.3 mm).

## 22

## Comparative Example 2b

A flexible tube for an endoscope was prepared in the same manner as in Comparative Example 2a except that a material for an outer layer **32** was changed as shown in the attached Table 2.

## Comparative Example 2c

A flexible tube for an endoscope was prepared in the same manner as in Comparative Example 2a except that a material for each of inner and outer layers **31** and **32** was changed as shown in the attached Table 2.

## 2. Observation of the Prepared Flexible Tubes

An observation of the cross-section of the outer cover **3** was carried out for each of the flexible tubes of Examples 2a–2e and Comparative Examples 2a–2c. Through the observation, formation of projections **4** as shown in FIG. 2 was observed in each of the flexible tubes of Examples 2a–2e and Comparative Examples 2a and 2b, but no formation of projections **4** was observed in the flexible tube of Comparative Example 2c.

## 3. Measurement of Rate of Change in Bending Stiffness

The rate of change in the bending stiffness in the longitudinal direction was measured for each of the flexible tubes of Examples 2a–2e.

For each flexible tube, first the flexible tube was divided into eight sections (i.e., first-eighth sections as shown in FIG. 13) which have an equal length (200 mm) in the longitudinal direction, and then the bending stiffness in "each" of the eight sections of the flexible tube was measured according to the following method.

In the measurement, as shown in FIG. 15, first the flexible tube was laid on two supporting-points located a distance L (200 mm) apart so that both ends of one of the sections were supported by the two supporting-points. Then, the magnitude of the pressing force F when the central point of the section was displaced downward by a predetermined distance y (50 mm) was measured and defined as the bending stiffness of each section. Based on the measured value, the rate of change in the bending stiffness in the longitudinal direction of the flexible tube was calculated. The results of the measurement are shown in the attached Table 3.

## 4. Evaluation of Flexible Tube

## (4-1) Insertion (Operationability) Test

An insertion test was carried out for each of the flexible tubes of Examples 2a–2e and Comparative Examples 2a–2c to evaluate operationability (i.e., degree of easiness in insertion operation) of an endoscope with the flexible tube.

Before carrying out the insertion test, endoscopes as shown in FIG. 1 were prepared using the flexible tubes of Examples 2a–2e and Comparative Examples 2a–2c. Further, a living body model having an internal structure similar to an internal portion of a human body was prepared. Then, each of the prepared endoscopes was inserted into the internal portion of the living body model until its tip end (i.e., tip of an bendable tube **5**) reaches a portion corresponding to a large intestine of a human body. In the insertion test, the operationability of the endoscope during the insertion operation was evaluated in accordance with the four rankings A–D given below.

## Rank A:

It is possible to perform insertion operation very smoothly. (A flexible tube of an endoscope of Rank A is considered to be best suited for use as a flexible tube for an endoscope.)

## Rank B:

It is possible to perform insertion operation smoothly. (A flexible tube of an endoscope of Rank B is considered to be suited for use as a flexible tube for an endoscope.)

Rank C:

It takes a relatively long time to complete insertion operation. (A flexible tube of an endoscope of Rank C is considered to have problems for use as a flexible tube for an endoscope.)

Rank D:

It is difficult to complete insertion operation. (A flexible tube of an endoscope of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The results of the insertion test are shown in the attached Table 4.

#### (4-2) Chemical Resistance Test

A chemical resistance test was carried out for each of the flexible tubes of Example 2a–2e and Comparative Example 2a–2c. In the chemical resistance test, 100 L of 10% aqueous solution of iodine held at 25° C. was prepared first, and then each of the prepared flexible tubes was immersed in the aqueous solution for 200 hours. Then, the condition of each flexible tube was evaluated in accordance with the four rankings A–D given below.

Rank A:

No Change in the Appearance; and  
No Occurrence of Cracks and Blisters in Outer Cover.

Rank B:

Slight Change in the Appearance; and  
Occurrence of Blisters at a Few Spots of Outer Cover.

Rank C:

Large Change in the Appearance; and  
Occurrence of Blisters at Many Spots of Outer Cover.

Rank D:

Extremely Large Change in the Appearance; and  
Occurrence of a Large Number of Cracks and Blisters on Outer Cover.

The evaluation result in this test is shown in the attached Table 4.

#### (4-3) Durability Test

A durability test was carried out to examine durability of each of the flexible tubes of Example 2a–2e and Comparative Example 2a–2c. In the durability test, each of the flexible tubes was set to a state where the flexible tube was supported at its both ends, and in this state the operation of bending by 90° was repeated 300 times for each flexible tube. Then, the degree of change in the flexibility after the repeated operation of bending was examined to evaluate the durability of the flexible tube in accordance with the four rankings A–D given below.

Rank A:

Almost No Change in Flexibility  
(A flexible tube of Rank A is considered to have extremely high durability.)

Rank B:

Slight Lowering of Flexibility  
(A flexible tube of Rank B is considered to have high durability.)

Rank C:

Large Lowering of Flexibility  
(A flexible tube of Rank C is considered to have problems in the durability.)

Rank D:

Extremely Large Lowering of Flexibility; and  
Occurrence of cracks and the like at many spots of the outer cover.  
(A flexible tube of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The result of the durability test is shown in the attached Table 4.

#### (4-4) Evaluation

The results in the attached Tables 3 and 4 show that the flexible tube according to the present invention (i.e., Examples 2a–2e) has excellent operationability and high chemical resistance as well as high durability. Further, the results in the attached Table 4 also show that conventional flexible tubes (i.e., Comparative Examples 2a–2c) have some drawbacks.

Specifically, the flexible tube of Comparative Example 2a has poor resistance to chemical. This drawback is considered to result from the fact that the outer layer **32** of the outer cover **3** was formed of the material having poor chemical resistance. Further, the flexible tube of Comparative Example 2b has poor operationability. Furthermore, the flexible tube of Comparative Example 2c has poor durability as well as poor operationability. The poor durability of this flexible tube is considered to result from the fact that no projections **4** as shown in FIG. **2** were formed on the inner layer **31**.

According to the present invention described above, appropriate materials that are for each of layers of an outer cover **3** are used for preparing the outer cover, and the outer cover **3** is provided onto the core body so that each of the layers has appropriate thickness and shape. This structure and the selection of material make it possible to produce a flexible tube for an endoscope that has high durability, high flexibility, and high chemical resistance as well as excellent operationability.

Further, according to the present invention, the outer cover of the flexible tube is formed so that the thickness of at least one of layers constituting the outer cover (laminate structure) varies in the longitudinal direction, for example, gradually or stepwise. This configuration makes it possible for an operator to insert an insertion section (flexible tube) of an endoscope into a body cavity of a living body with easy manipulation.

Furthermore, according to the present invention, a material having high elasticity is used for an intermediate layer of the outer cover. This makes it possible to give high flexibility to a flexible tube, thus enabling the operator to insert an insertion section of an endoscope more easily.

Moreover, according to the present invention, a material having high resistance to chemical is used for an outer layer of the outer cover. This makes it possible to give high chemical resistance to a flexible tube.

In addition, according to the present invention, a material having high adhesion with a core body **2** is used for an inner layer of an outer cover. This makes it possible to give high durability to a flexible tube.

#### IX. Seventh Embodiment (Flexible Tube 1G)

Next, a seventh embodiment of the flexible tube for an endoscope will be described with reference to FIG. **8**. FIG. **8** is a sectional view which shows a part of a flexible tube **1G** according to the present invention, in which illustration of projections **4** as shown in FIG. **2** is omitted, and structure of a reticular tube **22** is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. **1** (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. **1**.

An outer cover **3** of the flexible tube **1G** has a laminate structure composed of inner, outer and intermediate layers **31–33**. The inner and outer layers **31** and **32** have the same structures as those of the flexible tube **1A** in the first

25

embodiment, and this embodiment is different from the first embodiment in the structure of the intermediate layer 33. The structure of the intermediate layer 33 is described below in detail.

The intermediate layer 33 is formed between the inner layer 31 and the outer layer 32. As shown in FIG. 8, this intermediate layer 33 has a first portion (first region) 33a formed at a position closer to the tip end 12, and a second portion (second region) 33b formed at a position closer to the base end 11. The first and second portions 33a and 33b are contiguous to each other through a boundary 34. Specifically, the first portion 33a is formed within a region from the tip end 12 to the boundary 34, and the second portion 33b is formed within a region from the boundary section 34 to the base end 11.

The first portion 33a is different from the second portion 33b in its physical property or chemical property. (Hereinafter, the physical property and chemical property will be referred to simply as "property.") However, the property within each of the first and second portions 33a and 33b is substantially homogeneous. As a result of this structure, the property of the intermediate layer 33 varies substantially stepwise at the boundary 34. Such a difference in the property between the first and second portions 33a and 33b can be obtained by constituting the first and second portions 33a and 33b with different materials.

The lengths of the first and second portions 33a and 33b in the longitudinal direction may differ depending on the type of an endoscope or the like. However, in this invention, it is preferable that the length of the first portion 33a is in the range of about 50 to 1000 mm, and more preferably about 100 to 700 mm. Further, it is preferable that the length of the second portion 33b is in the range of about 50 to 1000 mm, and more preferably 100 to 700 mm.

In addition, in this invention, it is preferable that the first portion 33a is formed of a material having a lower hardness (stiffness) than that of the second portion 33b. With this arrangement, the tip side portion of the outer cover 3 where the first portion 33a is formed has a lower stiffness against tension, bending and the like than that of the base side portion of the outer cover 3 where the second portion 33b is formed. Therefore, by forming the outer cover 3 so as to have two distinct portions (i.e., first and second portion 33a and 33b), it becomes possible to give the tip side region of a flexible tube a higher flexibility than that of the base side region.

According to the flexible tube 1G having the intermediate layer 33 as described, the flexible tube 1G has a high "stiffness" in the portion near the base end 11 (where the second portion 33b is formed) so that a push-in force and the rotational force applied by the operator are sufficiently transmitted to the tip end 12, while it has a high "flexibility" in the portion near the tip end 12 (where the first portion 33a is formed) so that the tip side region of the flexible tube is smoothly inserted into and follows the body cavity having curved form. This structure makes it possible to improve the operationability of the endoscope when inserting the insertion section (flexible tube) into an internal portion of the living body. Accordingly, when an endoscope with the flexible tube having the structure as described above is used during an endoscopic examination, it is possible to reduce burden on a patient, since the operator can safely and smoothly perform the insertion operation.

In this invention, it is preferable the intermediate layer 33 has a higher elasticity than that of the outer layer 32, and more preferably the intermediate layer 33 has a higher

26

elasticity than that of any one of the inner and outer layers 31 and 32. With this arrangement, the intermediate layer 33 functions as a cushioning layer (cushioning means) between the inner layer 31 and the outer layer 32. (In the following, such a function given by the intermediate layer 33 is referred to as "cushioning function.") Accordingly, by forming the intermediate layer 33 as described above, it is possible to give higher flexibility to the flexible tube.

Hereinafter, the cushioning function of the intermediate layer 33 is described in more detail. When the flexible tube 1G is bent by an external force, the high elastic force is generated in the bent intermediate layer 33 through the deformation thereof. The generated elastic force is transmitted effectively to the inner layer 31 and the outer layer 32, respectively, since the intermediate layer 33 is sandwiched between the inner layer 31 and the outer layer 32 each of which has relatively low elasticity. When the external force has been removed, the bent flexible tube 1G is restored to its original shape by the high elastic force generated in the bent intermediate layer 33. In this connection, it is to be noted that the restoration of the flexible tube into its original shape is achieved by the cushioning function of the intermediate layer 33, and that such a cushioning function gives the flexible tube high flexibility.

In this embodiment, a constituent material for the intermediate layer 33 is not particularly limited. Examples of such material include various resins having elasticity such as polyvinyl chloride, polyolefine (e.g., polyethylene, polypropylene, ethylene-vinylacetate copolymer and the like), polyamide, polyester (e.g., polyethylene terephthalate (PET), polybutylene terephthalate and the like), polyurethane, polystyrene resin, fluoro-based resin (e.g., polytetrafluoroethylene, ethylene-tetrafluoroethylene copolymer and the like), polyimide, and the like; and various elastomers such as polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polyamide-based elastomer, polystyrene-based elastomer, fluorine-based elastomer, silicone rubber, fluororubber, latex rubber, and the like. These can be used alone or as a mixture of two or more thereof. In this invention, a material containing at least one of low hardness polyurethane-based elastomer, low hardness polyolefin-based elastomer, and low hardness polyester-based elastomer is preferably used to form the intermediate layer 33, since such elastomers have high elasticity.

Although the intermediate layer 33 in this embodiment is given a single layer construction, it may be given a construction of two or more layers.

In this invention, the average thickness of the intermediate layer 33 is not particularly limited, but the average thickness is preferably in the range of 0.05 to 0.8 mm, and more preferably in the range of 0.05 to 0.4 mm.

#### X. Eighth Embodiment (Flexible Tube 1H)

Next, an eighth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 9. FIG. 9 is a sectional view which shows a part of a flexible tube 1H according to the present invention, in which illustration of projections 4 as shown in FIG. 2 is omitted, and structure of a reticular tube 22 is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end 11 shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end 12 shown in FIG. 1.

As shown in FIG. 9, the outer cover 3 of the flexible tube 1H has a laminate structure composed of inner, outer and

intermediate layers **31–33**. Each of the inner and outer layers **31** and **32** has a substantially uniform thickness over its entire region, and has almost homogeneous property over its entire region. The intermediate layer **33** has a first portion (first region) **33a** formed in a tip side region, and a second portion (second region) **33b** formed in a base side region. The first and second portions **33a** and **33b** of the intermediate layer **33** have different properties. As shown in FIG. 9, the first and second portions **33a** and **33b** are contiguous to each other through a boundary part (property-varying region) **37** formed between the first and second portions **33a** and **33b**, and they are arranged along the longitudinal direction. In this invention, it is preferable that the first portion **33a** is formed of a material having a lower hardness (stiffness) than that of a material constituting the second portion **33b**.

Within the boundary part **37**, its property gradually varies in the longitudinal direction. A tip end portion of the boundary part **37** has substantially the same property as that of the first portion **33a**, while a base end portion of the boundary part **37** has substantially the same property as that of the second portion **33b**.

The boundary part **37** described above is formed through an extrusion molding process. Specifically, a mixture of a constituent material for the first portion **33a** and a constituent material for the second portion **33b** is prepared first, and then the mixture is fed during the extrusion molding while gradually changing the mixing rate of these materials. In this way, the outer cover **3** which has a layer with a boundary part where its property changes gradually in the longitudinal direction is formed. However, the structure of the boundary part **37** is not limited to that as described above. For example, the boundary part **37** maybe formed as a laminated part (composite part) composed of two halves. In this case, a first half is formed of a material having the same property as the first portion **33a** such that its thickness gradually decreases in the direction from the tip side to the base side. Further, a second half is formed of a material having the same property as the second portion **33b** such that its thickness gradually decreases in the direction from the base side to the tip side.

The length in the longitudinal direction of the boundary part **37** is not particularly limited. For example, when the boundary part **37** is formed so as to have a relatively large length, it is possible give a flexible tube a stiffness which varies more gradually in the longitudinal direction. However, in this invention, the length of the boundary part **37** is preferably in the range of 5 to 600 mm, and more preferable in the range of 10 to 400 mm.

By configuring a flexible tube as described above, it is possible to form an intermediate layer so as to have relatively low stiffness in the first portion **33a** located at the tip side, and have relatively high stiffness in the second portion **33b** located at the base side. In addition, it is also possible to form the intermediate layer **33** such that a boundary part (property-varying region) **37** where its property varies gradually along the longitudinal direction is formed between the first and second portions **33a** and **33b**.

According to the flexible tube as described above, due to the formation of the boundary part **37** as well as the homogeneous formation of the inner and outer layers **31** and **32**, the stiffness of the flexible tube **1H** gradually varies within the boundary part **37** and in the vicinity of its both ends. This structure makes it possible to provide a flexible tube whose stiffness (e.g., bending stiffness) varies more gradually along the longitudinal direction as compared with

the flexible tube **1G** (FIG. 8) of the seventh embodiment described above. When an endoscope with the flexible tube having the structure as described above is used during an endoscopic examination, it is possible to reduce burden on a patient, since the operator can more safely and smoothly insert the insertion portion of the endoscope into a body cavity of the patient.

Further, according to the flexible tube **1H** of this embodiment, there is no spot where the stiffness varies abruptly, since the intermediate layer **33** has the boundary part (property-varying region) **37**, and the inner and outer layers **31** and **32** are formed almost homogeneously. Therefore, a push-in force or a rotational force applied by the operator from the base side will not be concentrated at any portion, so that the force can be transmitted sufficiently to the tip end of an endoscope with the flexible tube. In addition, because of the absence of a spot where the stiffness varies abruptly, tendency of the flexible tube to curl or twist will not concentrate at any portion of the flexible tube.

In addition, according to the flexible tube of this embodiment, each of the inner and outer layers **31** and **32** is formed homogeneously over its entire region. This formation makes it possible for the inner layer **31** to have a uniform and high adhesion with the core body **2** over its entire region, and also makes it possible for the outer layer **32** to have uniform and high resistance to chemical over its entire length.

#### XI. Ninth Embodiment (Flexible Tube **1I**)

Next, a ninth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 10. FIG. 10 is a sectional view which shows a part of a flexible tube **1I** according to the present invention, in which illustration of projections **4** as shown in FIG. 2 is omitted, and structure of a reticular tube **22** is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. 1.

As shown in FIG. 10, an outer cover **3** of the flexible tube **1I** has a laminate structure composed of inner, outer and intermediate layers **31–33**. Each of the inner and outer layers **31** and **32** has a substantially uniform thickness and a substantially homogeneous property over its entire region. The intermediate layer **33** has three distinct portions (i.e., first-third portions **33a–33c**). The first portion (first region) **33a** is formed at the tip side, the third portion (third region) **33c** is formed at the base side, and the second portion (second region) **33b** is formed between the first portion **33a** and the third portion **33c**. Each of the first and third portions **33a** and **33c** is different from the second portion **33b** in its property. In this invention, it is preferable that the first portion **33a** is formed of a material having a lower hardness (stiffness) than that of a material constituting the second portion **33b**. Further, it is also preferable that the second portion **33b** is formed of a material having a lower hardness (stiffness) than that of a material constituting the third portion **33c**.

In addition, the intermediate layer **33** has two boundary parts (property-varying regions) **37** which are formed between the first and second portions **33a** and **33b** and between the second and third portions **33b** and **33c**, respectively. Each of the boundary parts **37** has substantially the same structure as that of the intermediate layer **33** of the flexible tube **1H** (FIG. 9) in the eighth embodiment described above, and formed in the same manner as in the eighth embodiment.

In this embodiment, the length of each of the portions of the intermediate layer **33** is not particularly limited. However, it is preferable that the length of the first portion **33a** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 100 to 700 mm. Further, it is preferable that the length of the second portion **33b** is preferably in the range of about 50 to 800 mm, and more preferably in the range of about 100 to 600 mm. Furthermore, it is preferable that the length of the third portion **33c** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 200 to 1000 mm.

According to the flexible tube **1I** having the structure described above, the intermediate layer **33** has a relatively low stiffness in the first portion **33a** located at the tip side, has a relatively high stiffness in the third portion **33c** located at the base side, and has a medium stiffness in the second portion **33b** between the first and second portions **33a** and **33b**. In addition, the stiffness of the intermediate layer **33** gradually varies within each of the boundary parts **37** formed between the first and second portions **33a** and **33b** and between the second and third portions **33b** and **33c**, respectively.

Further, according to the flexible tube **1I** described above, as a result of the formation of the three distinct portions **33a–33c**, the stiffness of the flexible tube **1I** varies along the longitudinal direction in roughly three stages. In addition, as a result of the formation of the two boundary parts (property-varying regions) **37**, the stiffness of the flexible tube **1I** varies more gradually along the longitudinal direction. Accordingly, the stiffness of the flexible tube **1I** in this embodiment varies along the longitudinal direction in a more gradual manner as compared with the flexible tube **1H** (FIG. 9) of the eighth embodiment in which the stiffness varies in roughly “two” stages. Therefore, when an endoscope with the flexible tube **1I** having the structure as described above is used during an endoscopic examination, it is possible to reliably reduce burden on a patient, since the operator can more safely and smoothly insert an insertion portion of an endoscope.

## XII. Tenth Embodiment (Flexible Tube 1J)

Next, a tenth embodiment of the flexible tube for an endoscope will be described with reference to FIG. 11. FIG. 11 is a sectional view which shows a part of a flexible tube **1J** according to the present invention, in which illustration of projections **4** as shown in FIG. 2 is omitted, and structure of a reticular tube **22** is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. 1.

As shown in FIG. 11, an outer cover **3** of the flexible tube **1J** has a laminate structure composed of inner, outer and intermediate layers **31–33**. Each of the inner and intermediate layers **31** and **33** has homogeneous formation and a substantially uniform thickness over its entire region. The outer layer **32** has three distinct portions (i.e., first–third portions **32a–32c**). The first portion (first region) **32a** is formed at the tip side, the third portion (third region) **32c** is formed at the base side, and the second portion (second region) **32b** is formed between the first portion **32a** and the third portion **32c**. Each of the first and third portions **32a** and **32c** is different from the second portion **32b** in its property. In this invention, it is preferable that the first portion **32a** is formed of a material having a lower hardness (stiffness) than

that of a material constituting the second portion **32b**. Further, it is also preferable that the second portion **32b** is formed of a material having a lower hardness (stiffness) than that of a material constituting the third portion **32c**. In addition, in this invention, it is preferable that each of the first–third portions **32a–32c** of the outer layer **32** has high resistance to chemical.

The outer layer **32** has two boundary parts (property-varying regions) **36** which are formed between the first and second portions **32a** and **32b** and between the second and third portions **32b** and **32c**, respectively. Each of the boundary parts **36** has substantially the same structure as that of the intermediate layer **33** of the flexible tube **1H** (FIG. 9) in the eighth embodiment described above, and formed in the same manner as in the eighth embodiment.

In this embodiment, the length of each of the portions of the outer layer **32** is not particularly limited. However, it is preferable that the length of the first portion **32a** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 100 to 700 mm. Further, it is preferable that the length of the second portion **32b** is preferably in the range of about 50 to 800 mm, and more preferably in the range of about 100 to 600 mm. Furthermore, it is preferable that the length of the third portion **32c** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 200 to 1000 mm.

In the flexible tube **1J** having the structure described above, the outer layer **32** has a relatively low stiffness in the first portion **32a** located at the tip side, has a relatively high stiffness in the third portion **32c** located at the base side, and has a medium stiffness in the second portion **32b** between the first and third portions **32a** and **32c**. In addition, the stiffness of the outer layer **32** gradually varies within each of the boundary parts (property-varying regions) **36** formed between the first and second portions **32a** and **32b** and between the second and third portions **32b** and **32c**, respectively. Therefore, according to the flexible tube **1J** described above, it is possible to achieve the same advantages as those described with respect to the flexible tube **1I** (FIG. 10) in the ninth embodiment.

In addition, according to the flexible tube **1J** of this embodiment, each of the inner and intermediate layers **31** and **33** is formed homogeneously over its entire region. This formation makes it possible for the inner layer **31** to have a uniform and high adhesion with the core body **2** over its entire region, and also makes it possible for the intermediate layer **33** to have uniform and high flexibility over its entire length.

## XIII. Eleventh Embodiment (Flexible Tube 1K)

Next, an eleventh embodiment of the flexible tube for an endoscope will be described with reference to FIG. 12. FIG. 12 is a sectional view which shows a part of a flexible tube **1K** according to the present invention, in which illustration of projections **4** as shown in FIG. 2 is omitted, and structure of a reticular tube **22** is simply illustrated as a layer. In this figure, the right-hand side corresponds to the side of the base end **11** shown in FIG. 1 (i.e., side closer to an operator), and the left-hand side corresponds to the side of tip end **12** shown in FIG. 1.

As shown in FIG. 12, an outer cover **3** of the flexible tube **1K** has a laminate structure composed of inner, outer and intermediate layers **31–33**.

The intermediate layer **33** has a substantially uniform thickness over its entire region, and is formed homogeneously over its entire region.

## 31

The outer layer **32** has the same structure as that described with reference to the tenth embodiment shown in FIG. **11**. Specifically, the outer layer **32** has three distinct portions (i.e., first-third portions **32a–32c**). The first portion (first region) **32a** is formed at the tip side, the third portion (third region) **32c** is formed at the base side, and the second portion (second region) **32b** is formed between the first portion **32a** and the third portion **32c**. Each of the first and third portions **32a** and **32c** is different from the second portion **32b** in its property. In this invention, it is preferable that the first portion **32a** is formed of a material having a lower hardness (stiffness) than that of a material constituting the second portion **32b**. Further, it is also preferable that the second portion **32b** is formed of a material having a lower hardness (stiffness) than that of a material constituting the third portion **32c**. In addition, in this invention, it is preferable that each of the first-third portions **32a–32c** of the outer layer **32** has high resistance to chemical.

Further, the outer layer **32** has two boundary parts (property-varying regions) **36** which are formed between the first and second portions **32a** and **32b** and between the second and third portions **32b** and **32c**, respectively. Each of the boundary parts **36** has substantially the same structure as that of the intermediate layer **33** of the flexible tube **1H** (FIG. **9**) in the eighth embodiment described above, and formed in the same manner as in the eighth embodiment.

The inner layer **31** has two distinct portions (i.e., first and second portions **31a** and **31b**). The first portion (first region) **31a** is formed at the tip side, and the second portion (second region) **31b** is formed at the base side. The first portion **31a** is different from the second portion **31b** in its property. In this invention, it is preferable that the first portion **31a** is formed of a material having a lower hardness (stiffness) than that of a material constituting the second portion **31b**. Further, it is also preferable that each of the first and second portions **31a** and **31b** of the inner layer **31** is formed of a material having high adhesion with a core body **2**, that is, a material which are easily formed into a layer with projections **4** as shown in FIG. **2** through extrusion molding.

In addition, the inner layer **31** has a boundary part (property-varying region) **35** which is formed between the first and second portions **31a** and **31b**. The boundary part **35** has substantially the same structure as that of the intermediate layer **33** of the flexible tube **1H** (FIG. **9**) in the eighth embodiment described above, and formed in the same manner as in the eighth embodiment.

In this embodiment, the length of the first and second portions **31a** and **31b** of the inner layer **31** is not particularly limited. However, it is preferable that the length of the first portion **31a** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 500 to 1000 mm. Further, it is preferable that the length of the second portion **31b** is preferably in the range of about 50 to 1000 mm, and more preferably in the range of about 400 to 1000 mm.

According to the flexible tube **1K** having the structure described above, the outer cover **3** of the flexible tube **1K** has different stiffness in the following four regions (1)–(4). (The stiffness of the flexible tube **1K** increases in this order in the longitudinal direction.)

- (1) A region of the outer cover **3** where both the first portion **32a** of the outer layer **32** and the first portion **31a** of the inner layer **31** are formed, and where these portions partly face each other.
- (2) A region of the outer cover **3** where both the second portion **32b** of the outer layer **32** and the first portion **31a**

## 32

of the inner layer **31** are formed, and where these portions partly face each other.

- (3) A region of the outer cover **3** where both the second portion **32b** of the outer layer **32** and the second portion **31b** of the inner layer **31** are formed, and where these portions partly face each other.
- (4) A region of the outer cover **3** where both the third portion **32c** of the outer layer **32** and the second portion **31b** of the inner layer **31** are formed, and where these portions partly face each other.

Therefore, the flexibility of the flexible tube **1K** varies along the longitudinal direction in roughly four stages. Further, as a result of the formation of the boundary parts (property-varying regions) **35** and **36**, the stiffness of the flexible tube varies more gradually along the longitudinal direction. Accordingly, the stiffness of the flexible tube **1K** in this embodiment varies along the longitudinal direction in a more gradual manner as compared with the flexible tube **1I** (FIG. **10**) of the ninth embodiment in which the stiffness varies in roughly “three” stages. Therefore, when an endoscope with the flexible tube having the structure as described above is used during an endoscopic examination, it is possible to reliably reduce burden on a patient, since the operator can more safely and smoothly insert the insertion portion of the endoscope into a body cavity of the patient.

Further, according to the flexible tube **1K** having the structure described above, the outer cover **3** of the flexible tube **1K** is formed such that the boundary part **35** of the inner layer **31** is not located below the boundary parts **36** of the outer layer **32** in the thickness direction. In other words, the outer cover **3** of the flexible tube is formed such that the boundary part **35** of the inner layer **31** and the boundary part **36** of the outer layer **32** are alternately located in the longitudinal direction of the outer cover **3**. This arrangement makes it possible for a flexible tube to have a stiffness that varies more gradually in the longitudinal direction.

## XIV. EXAMPLES OF MODIFICATION

In the above, the flexible tube for an endoscope according to the present invention was described in detail. However, it is to be noted that this invention is not limited to the embodiments described above.

For example, one or more of layers of the outer cover **3** may be formed using materials which contain the same principal material (main polymer) but which are different in molecular weight, the content of additives (e.g., plasticizer), or the like. Alternatively, one or more of layers of the outer cover **3** may also be formed of materials which contain the same components but which are different in density. In this way, it is also possible to form an outer cover **3** such that a layer of the outer cover **3** has distinct portions having different properties.

Further, the structure of each layer of the outer cover **3** is not particularly limited. For example, an outer cover **32** of a flexible tube may be formed such that any one of layers has regions having different properties. Further, an outer cover of a flexible tube may also be formed such that each of two or more of layers has regions having different properties.

Furthermore, the structure of an outer cover **3** described above is not particularly limited. For example, an outer cover of a flexible tube may be formed such that a part of the outer cover has a laminate structure composed of a plurality of layers.

In addition, for example, the flexible tube for an endoscope according to the present invention may be applied to other site of the endoscope such as a flexible tube for a light guide connected to a light source device.

## 33

## XV. EXAMPLES OF SEVENTH-ELEVENTH EMBODIMENTS

Next, specific examples of the seventh-eleventh embodiments of the present invention will be described below.

## 1. Preparation of Flexible Tube for an Endoscope

## Example 3a

First, a coil **21** having an outer diameter of 9.9 mm and an inner diameter of 9.6 mm was prepared by winding a band-shaped stainless steel material having a width of 3 mm. Next, stainless steel fine wires **23** at least one of which had been given a coating of a polyamide resin and each of which had a diameter of 0.1 mm were prepared, and then using these fine wires a plurality of bundles of ten fine wires were prepared. These bundles of the ten fine wires **23** were woven together in a lattice manner to obtain a reticular tube **22**. Then, the obtained reticular tube **22** was provided on the prepared coil **21** so that the outer periphery of the coil **21** was covered with the reticular tube **22**. In this way, a core body **2** was prepared.

Next, using an extrusion-molding machine, an outer cover **3** composed of inner, outer and intermediate layers **31–33** was provided on the outer periphery of the core body **2** so that the core body **2** was covered with the outer cover **3**. In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. In this connection, it is to be noted that the length of 1.6 m means the length of an available (effective) portion of the flexible tube that can be used for a flexible tube for an endoscope, that is the length of 1.6 m means an available (effective) length of the flexible tube. Therefore, the actually prepared flexible tube had a length more than 1.6 m by including additional portions at the both ends of the available portion of the flexible tube (See FIG. 14). In this regard, however, it goes without saying that the available length is not limited to 1.6 m mentioned above.

The details of each of the inner, outer and intermediate layers are as follows.

## &lt;Inner Layer&gt;

The inner layer **31** was formed so as to have a single region with a uniform thickness. The thickness and a constituent material of the inner layer **31** were as follows.

Thickness: 0.2 mm

Material: A medium hardness polyurethane-based elastomer having a hardness of A81. (Hardness was measured in accordance with JIS K 7311.)

## &lt;Outer Layer&gt;

The outer layer **32** was formed so as to have a single region with a uniform thickness. The thickness and a constituent material of the outer layer **32** were as follows.

Thickness: 0.1 mm

Material: A High hardness polyester-based elastomer having a hardness of A92 (Hardness was measured in accordance with JIS K 7311.)

## &lt;Intermediate Layer&gt;

The intermediate layer **33** was formed so as to have a uniform thickness (0.3 mm) and to have first, second and third portions **33a–33c**. The first portion **33a** was formed at the tip side, the second portion **33b** was formed between the first and third portions **33a** and **33c**, and the third portion **33c** was formed at the base side. The first portion **33a** was contiguous to the second portion **33b** through a boundary **34**,

## 34

and the third portion **33c** was contiguous to the second portion **33b** through a boundary **34**. The details of each of the portions **33a–33c** are as follows.

## First Portion

Length: 440 mm

Material: A low hardness polyurethane-based elastomer having a hardness of A68. (Hardness was measured in accordance with JIS K 7311.)

## Second Portion

Length: 530 mm

Material: A medium hardness polyurethane-based elastomer having a hardness of A82. (Hardness was measured in accordance with JIS K 7311.)

## Third Portion

Length: 630 mm

Material: A high hardness polyurethane-based elastomer having a hardness of A90. (Hardness was measured in accordance with JIS K 7311.)

## Example 3b

A flexible tube for an endoscope was prepared in the same manner as in Example 3a except that the configuration of an intermediate layer **33** was changed as follows.

## First Portion

Length: 450 mm

Material: A low hardness polyurethane-based elastomer having a hardness of A68. (Hardness was measured in accordance with JIS K 7311.)

## Second Portion

Length: 300 mm

Material: A medium hardness polyurethane-based elastomer having a hardness of A82. (Hardness was measured in accordance with JIS K 7311.)

## Third Portion

Length: 450 mm

Material: A high hardness polyurethane-based elastomer having a hardness of A90. (Hardness was measured in accordance with JIS K 7311.)

## Boundary Parts

In this Example, two boundary parts **37** each of which had a length of 200 mm were formed in the intermediate layer **33**. One of the boundary part **37** was formed between the first and second portions **33a** and **33b**, and the other boundary part **37** was formed between the second and third portions **33b** and **33c**. Each of the boundary parts **37** was formed through an extrusion molding process so that its property gradually changes in the longitudinal direction. Specifically, first, a mixture of a constituent material for the first portion **33a** and a constituent material for the second portion **33b** was fed in an extrusion molding machine while gradually changing the mixing rate of these materials. Further, a mixture of a constituent material for the second portion **33b** and a constituent material for the third portion **33c** was fed in the extrusion molding machine while gradually changing the mixing rate of these materials.

## Example 3c

A flexible tube for an endoscope was prepared in the same manner as in Example 3a except that the configuration of each of outer and intermediate layer **32** and **33** was changed as follows.

## 35

## &lt;Outer Layer&gt;

In this Example, the outer layer **32** was formed so as to have a uniform thickness (0.1 mm), and so as to have three portions (i.e., first, second and third portions **32a–32c**) and two boundary parts (property-varying regions) **36**. The details of each of the portions **32a–32c** and the boundary parts **36** are as follows.

## First Portion

Length: 450 mm

Material: A low hardness polyolefine-based elastomer having a hardness of A76. (Hardness was measured in accordance with JIS K 7311.)

## Second Portion

Length: 300 mm

Material: A medium hardness polyolefine-based elastomer having a hardness of A85. (Hardness was measured in accordance with JIS K 7311.)

## Third Portion

Length: 450 mm

Material: A high hardness polyolefine-based elastomer having a hardness of A95. (Hardness was measured in accordance with JIS K 7311.)

## Boundary Part

In this Example, each of the boundary parts **36** had a length of 200 mm. One of the boundary part **36** was formed between the first and second portions **32a** and **32b**, and the other boundary part **36** was formed between the second and third portions **32b** and **32c**.

## &lt;Intermediate Layer&gt;

In this Example, the intermediate layer **33** was formed so as to have a single region with a uniform thickness (0.3 mm). A constituent material of the intermediate layer **33** was as follows.

Material: A low hardness polyurethane-based elastomer having a hardness of A78. (Hardness was measured in accordance with JIS K 7311.)

## Example 3d

A flexible tube for an endoscope was prepared in the same manner as in Example 3c except that the configuration of an inner layer **31** of an outer cover **3** was changed as follows.

In this Example, the inner layer **31** was formed so as to have a uniform thickness (0.2 mm), and so as to have two portions (i.e., first and second portions **31a** and **31b**) and a boundary part (property-varying region) **35**. The details of each of the portions **31a** and **31b** and the boundary part **35** are as follows.

## First Portion

Length: 600 mm

Material: A medium hardness polyurethane-based elastomer having a hardness of A82. (Hardness was measured in accordance with JIS K 7311.)

## Second Portion

Length: 600 mm

Material: A high hardness polyurethane-based elastomer having a hardness of A91. (Hardness was measured in accordance with JIS K 7311.)

## Boundary Parts

In this Example, the boundary part **35** having a length of 400 mm was formed between the first and second portions **31a** and **31b**.

## 36

## Comparative Example 3a

A core body **2** was prepared in the same manner as in Example 3a. Then, using an extrusion-molding machine, an outer cover **3** composed of inner and outer layers **31** and **32** was provided on the outer periphery of the core body **2** so that the core body **2** was covered with the outer cover **3**. In this way, a flexible tube for an endoscope with a length of 1.6 m was prepared. The details of each of the layers **31** and **32** of the outer cover **3** are as follows.

## &lt;Inner Layer&gt;

The inner layer **31** was formed so as to have a single region with a uniform thickness. The thickness and a constituent material of the inner layer **31** were as follows.

Thickness: 0.3 mm

Material: A medium hardness polyurethane-based elastomer having a hardness of A81. (Hardness was measured in accordance with JIS K 7311.)

## &lt;Outer Layer&gt;

The outer layer **32** was formed so as to have a single region with a uniform thickness. The thickness and a constituent material of the outer layer **32** were as follows.

Thickness: 0.3 mm

Material: A low hardness polyurethane-based elastomer having a hardness of A68. (Hardness was measured in accordance with JIS K 7311.)

## Comparative Example 3b

A flexible tube for an endoscope was prepared in the same manner as in Comparative Example 3a except that a constituent material for each of inner and outer layers **31** and **32** was changed as follows.

## &lt;Inner Layer&gt;

Material: A medium hardness polyurethane-based elastomer having a hardness of A81. (Hardness was measured in accordance with JIS K 7311.)

## &lt;Outer Layer&gt;

Material: A high hardness polyester-based elastomer having a hardness of A92. (Hardness was measured in accordance with JIS K 7311.)

## Comparative Example 3c

A flexible tube for an endoscope was prepared in the same manner as in Comparative Example 3a except that a constituent material for each of inner and outer layers **31** and **32** was changed as follows.

## &lt;Inner Layer&gt;

Material: A high hardness polyurethane-based elastomer having a hardness of A90. (Hardness was measured in accordance with JIS K 7311.)

## &lt;Outer Layer&gt;

Material: A high hardness polyester-based elastomer having a hardness of A92. (Hardness was measured in accordance with JIS K 7311.)

## 2. Observation of the Prepared Flexible Tubes

An observation of the cross-section of the outer cover was carried out for each of the flexible tubes of Examples 3a–3d and Comparative Examples 3a–3c. Through the observation, formation of projections **4** as shown in FIG. 2 was observed in each of the flexible tubes of Examples 3a–3d and Comparative Examples 3a and 3b, but no formation of projections **4** was observed in the flexible tube of Comparative Example 3c.

### 3. Measurement of Rate of Change in Bending Stiffness

The rate of change in the bending stiffness in the longitudinal direction was measured for each of the flexible tubes of Examples 3a–3d.

For each flexible tube, first the flexible tube was divided into nine sections (i.e., first–ninth sections as shown in FIG. 14) which have an equal length (177 mm) in the longitudinal direction, and then the bending stiffness in “each” of the nine sections of the flexible tube was measured according to the following method.

In the measurement, as shown in FIG. 15, first the flexible tube was laid on two supporting-points located a distance L (177 mm) apart so that both ends of one of the sections were supported by the two supporting-points. Then, the magnitude of the pressing force F when the central point of the section was displaced downward by a predetermined distance y (50 mm) was measured and defined as the bending stiffness of the section. Based on the measured value, the rate of change in the bending stiffness in the longitudinal direction of the flexible tube was calculated. The results of this measurement are shown in the attached Table 5.

### 4. Evaluation of Flexible Tube

#### (4-1) Insertion (Operationability) Test

An insertion test was carried out for each of the flexible tubes of Examples 3a–3d and Comparative Examples 3a–3c to evaluate operationability of an endoscope with the flexible tube during insertion of the endoscope.

Before carrying out the insertion test, endoscopes as shown in FIG. 1 were prepared using the flexible tubes of Examples 3a–3d and Comparative Examples 3a–3c. Further, a living body model having an internal structure similar to an internal portion of a human body was prepared. Then, each of the prepared endoscopes was inserted into the internal portion of the living body model until its tip end (i.e., tip of an bendable tube 5) reaches a portion corresponding to a large intestine of a human body. In the insertion test, the operationability during insertion of the endoscope was evaluated in accordance with the four rankings A–D given below.

Rank A:

It is possible to perform insertion operation very smoothly. (A flexible tube of an endoscope of Rank A is considered to be best suited for use as a flexible tube for an endoscope.)

Rank B:

It is possible to perform insertion operation smoothly. (A flexible tube of an endoscope of Rank B is considered to be suited for use as a flexible tube for an endoscope.)

Rank C:

It takes a relatively long time to complete insertion operation. (A flexible tube of an endoscope of Rank C is considered to have problems for use as a flexible tube for an endoscope.)

Rank D:

It is difficult to complete insertion operation. (A flexible tube of an endoscope of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The results of the insertion test are shown in the attached Table 6.

#### (4-2) Chemical Resistance Test

A chemical resistance test was carried out for each of the flexible tubes of Example 3a–3d and Comparative Example

3a–3c. In this test, 100 L of 10% aqueous solution of iodine held at 25° C. was prepared first, and then each of the prepared flexible tubes was immersed in the aqueous solution for 200 hours. Then, the condition of each flexible tube was evaluated in accordance with the four rankings A–D given below.

Rank A:

No Change in the Appearance; and

No Occurrence of Cracks and Blisters in Outer Cover.

Rank B:

Slight Change in the Appearance; and

Occurrence of Blisters at a Few Spots of Outer Cover.

Rank C:

Large Change in the Appearance; and

Occurrence of Blisters at Many Spots of Outer Cover.

Rank D:

Extremely Large Change in the Appearance; and

Occurrence of a Large Number of Cracks and Blisters on Outer Cover.

The evaluation result in this test is shown in the attached Table 6.

#### (4-3) Durability Test

A durability test was carried out for each of the flexible tubes of Examples 3a–3d and Comparative Examples 3a–3c. In the durability test, each of the flexible tubes was set to a state where the flexible tube was supported at its both ends, and in this state the operation of bending by 90° was repeated 300 times. Then, the degree of change in the flexibility after the repeated operation of bending was examined to evaluate the durability of each flexible tube in accordance with the four rankings A–D given below.

Rank A:

Almost No Change in Flexibility

(A flexible tube of Rank A is considered to have extremely high durability.)

Rank B:

Slight Lowering of Flexibility

(A flexible tube of Rank B is considered to have high durability.)

Rank C:

Large Lowering of Flexibility

(A flexible tube of Rank C is considered to have problems in its durability.)

Rank D:

Extremely Large Lowering of Flexibility; and

Occurrence of cracks and the like at many spots of the outer cover.

(A flexible tube of Rank D is considered to be unsuited for use as a flexible tube for an endoscope.)

The result of the durability test is shown in the attached Table 6.

#### (4-4) Evaluation

The results in the attached Tables 5 and 6 show that the flexible tube according to the present invention (i.e., Examples 3a–3d) has excellent operationability and high chemical resistance as well as high durability. Further, the results in Table 6 also show that conventional flexible tubes (i.e., Comparative Examples 3a–3c) have some drawbacks.

Specifically, the flexible tube of Comparative Example 3a has poor chemical resistance as well as poor operationability. The poor chemical resistance of this flexible tube is

considered to result from the fact that the outer layer of the outer cover is made of the material having poor resistance to chemical. Further, the flexible tube of Comparative Example 3b has poor operationability. Furthermore, the flexible tube of Comparative Example 3c has poor durability as well as poor operationability. The poor durability of this flexible tube is considered to result from the fact that projections 4 as shown in FIG. 2 have not been formed on the inner layer 31.

According to the present invention described above, appropriate materials that are suitable for each of layers of an outer cover are used for preparing the outer cover, and the outer cover is provided onto the core body so that each of the layers has appropriate thickness and shape. This structure and the selection of material make it possible to produce a flexible tube for an endoscope that has high durability, high flexibility and high chemical resistance as well as excellent operationability.

Further, according to the present invention, at least one of layers of an outer cover 3 has at least two distinct portions

In addition, according to the present invention, a material having a high adhesion with a core body is used as a constituent material for an inner layer of the outer cover. This makes it possible to give high durability to a flexible tube.

Finally, it is to be understood that many changes and additions may be made to the embodiments described above without departing from the scope and spirit of the invention as defined in the appended claims.

Further, it is also to be understood that the present disclosure relates to subject matter contained in Japanese Patent Application Nos. 2000-134922, 2000-142206 and 2000-156783 (filed on May 8, 15 and 26, 2000, respectively) which are expressly incorporated herein by reference in its entirety.

TABLE 1

	Inner Layer		Intermediate Layer		Outer Layer		Chemical Resistance	Flexibility	Durability
	Material*	Thickness [mm]	Material*	Thickness [mm]	Material*	Thickness [mm]			
Ex. 1a	M	0.3	L	0.2	H1	0.1	A	A	A
Ex. 1b	M	0.2	L	0.2	H1	0.1	A	A	A
Ex. 1c	M	0.3	L	0.1	H1	0.1	A	A	A
Ex. 1d	M	0.3	L	0.2	H2	0.05	A	A	A
Ex. 1e	M	0.3	L	0.2	H3	0.1	A	A	A
Co. Ex. 1a	M	0.3	—	—	L	0.2	D	C	B
Co. Ex. 1b	M	0.3	—	—	H1	0.2	A	D	B
Co. Ex. 1c	H1	0.2	—	—	M	0.3	C	D	D
Co. Ex. 1d	L	0.3	—	—	H1	0.2	A	C	D

Material M: Medium Hardness Polyurethane-Based Elastomer (Hardness\*: 81)  
Material L: Low Hardness Polyurethane-Based Elastomer (Hardness\*: 68)  
Material H1: High Hardness Polyester-Based Elastomer (Hardness\*: 92)  
Material H2: High Hardness Polyolefine-Based Elastomer (Hardness\*: 91)  
Material H3: High Hardness Polyurethane-Based Elastomer (Hardness\*: 92)  
\*Hardness of the material was measured in accordance with JIS K 7311.

and a boundary part along its longitudinal direction, and one of the portions is contiguous to the other portion through the boundary part. In this layer, one of the portions is different from the other portion adjacent thereto in physical property or chemical property. This configuration makes it possible for a flexible tube to have a stiffness (flexibility) which gradually varies in its longitudinal direction.

According to an endoscope having the flexible tube as described above, since the flexible tube has a higher stiffness in a portion closer to the base end, it is possible to fully transmit to the tip end of the endoscope the push-in force and the rotational force applied by an operator. On the other hand, since the flexible tube has a higher flexibility in a portion closer to the tip end, it is also possible to smoothly insert an insertion section (flexible tube) of the endoscope into an internal curved portion of a patient in a safe manner. Therefore, the flexible tube as described above makes it possible for an operator to insert the insertion section with easy manipulation, thus enabling the reduction of the burden on the patient during the endoscopic examination.

Furthermore, according to the present invention, a material having high elasticity is used as a constituent material for an intermediate layer of the outer cover. This makes it possible to give high flexibility to a flexible tube.

Moreover, according to the present invention, a material having high chemical resistance is used as a constituent material for an outer layer of the outer cover. This makes it possible to give high chemical resistance to a flexible tube.

TABLE 2

	Inner Layer	Intermediate Layer	Outer Layer
Example 2a	Material M	Material L	Material H1
Example 2b	Material M	Material L	Material H1
Example 2c	Material M	Material L	Material H1
Example 2d	Material M	Material L	Material H2
Example 2e	Material M	Material L	Material H3
Co. Example 2a	Material M	—	Material L
Co. Example 2b	Material M	—	Material H1
Co. Example 2c	Material H1	—	Material H2

Material M: Medium Hardness Polyurethane-Based Elastomer (Hardness\*: 81)  
Material L: Low Hardness Polyurethane-Based Elastomer (Hardness\*: 68)  
Material H1: High Hardness Polyester-Based Elastomer (Hardness\*: 92)  
Material H2: High Hardness Polyolefine-Based Elastomer (Hardness\*: 91)  
Material H3: High Hardness Polyurethane-Based Elastomer (Hardness\*: 92)  
\*Hardness of the material was measured in accordance with JIS K 7311.

TABLE 3

	First Section	Second Section	Third Section	Fourth Section	Fifth Section	Sixth Section	Seventh Section	Eighth Section
Example 2a	1	1.1	1.3	1.4	1.5	1.6	1.8	1.9
Example 2b	1	1.2	1.4	1.6	1.8	1.9	2.1	2.3
Example 2c	1	1	1.5	1.5	1.8	1.8	2.2	2.2
Example 2d	1	1.3	1.5	1.7	1.9	2.1	2.3	2.4
Example 2e	1	1.1	1.3	1.4	1.5	1.6	1.8	1.9

TABLE 4

	Operationability	Chemical Resistance	Durability
Example 2a	A	A	A
Example 2b	A	A	A
Example 2c	A	A	A
Example 2d	A	A	A
Example 2e	A	A	A
Co. Example 2a	C	D	B
Co. Example 2b	D	A	B
Co. Example 2c	D	A	D

TABLE 5

	First Section	Second Section	Third Section	Fourth Section	Fifth Section	Sixth Section	Seventh Section	Eighth Section	Ninth Section
Example 3a	1	1.02	1.2	1.2	1.2	1.4	1.4	1.4	1.4
Example 3b	1	1.04	1.11	1.2	1.2	1.3	1.38	1.39	1.4
Example 3c	1	1.03	1.08	1.17	1.18	1.26	1.35	1.36	1.38
Example 3d	1	1.06	1.12	1.19	1.27	1.34	1.38	1.4	1.42

TABLE 6

	Operationability	Chemical Resistance	Durability
Example 3a	A	A	A
Example 3b	A	A	A
Example 3c	A	A	A
Example 3d	A	A	A
Co. Example 3a	C	D	B
Co. Example 3b	D	A	B
Co. Example 3c	D	A	D

What is claimed is:

1. A flexible tube for an endoscope, comprising:

an elongated tubular core body; and

an outer cover which is provided over the core body, the outer cover having a portion which is formed into a laminate structure composed of at least three layers, the layers of the laminate structure including an inner layer,

an outer layer and at least one intermediate layer formed between the inner layer and the outer layer, wherein the intermediate layer of the outer cover has a higher elasticity than the inner and outer layers so that the intermediate layer functions as cushioning between the inner layer and the outer layer.

2. The flexible tube as claimed in claim 1, wherein the core body has a plurality of holes and/or a plurality of recesses.

3. The flexible tube as claimed in claim 2, wherein the inner layer of the outer cover has projections which are integrally formed on the inner layer so that the projections project into the holes and/or the recesses.

4. The flexible tube as claimed in claim 1, wherein the portion of the laminate structure of the outer cover has a substantially uniform thickness over its entire region.

5. The flexible tube as claimed in claim 1, wherein any one of the inner, outer and intermediate layers is different from one of the other layers in its physical property and/or chemical property.

6. The flexible tube as claimed in claim 5, wherein any one of the inner, outer and intermediate layers is different from one of the other layers in its hardness.

7. The flexible tube as claimed in claim 1, wherein the outer layer of the outer cover contains a material having resistance to a chemical.

8. The flexible tube as claimed in claim 1, wherein the intermediate layer of the outer cover is formed of a material having higher elasticity than that of the outer layer.

9. The flexible tube as claimed in claim 1, wherein the outer layer of the outer cover is formed of a material having higher hardness than that of the inner layer or the intermediate layer.

10. The flexible tube as claimed in claim 1, wherein at least a part of the outer layer of the outer cover has higher hardness than that of the inner layer or the intermediate layer.

11. The flexible tube as claimed in claim 1, wherein at least one of the inner, outer and intermediate layers of the outer cover is formed of a material that contains at least one selected from the group consisting of polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polystyrene-based elastomer, polyamide-based elastomer, fluorine-based elastomer, and fluororubber.

12. The flexible tube as claimed in claim 1, wherein each of the inner, outer and intermediate layers of the outer cover

is formed of a material that contains at least one selected from the group consisting of polyurethane-based elastomer, polyester-based elastomer, polyolefine-based elastomer, polystyrene-based elastomer, polyamide-based elastomer, fluorine-based elastomer, and fluororubber.

13. The flexible tube as claimed in claim 1, wherein the outer cover is provided over the core body through an extrusion molding process.

14. The flexible tube as claimed in claim 1, wherein the flexible tube has tip and base ends, and flexibility of the flexible tube increases in a gradual or stepwise manner along the direction from the base end toward the tip end.

15. The flexible tube as claimed in claim 1, wherein any one of the layers constituting the portion of the laminate structure of the outer cover is different from one of the other layers in its physical property and/or chemical property.

16. The flexible tube as claimed in claim 15, wherein any one of layers constituting the laminate structure of the outer cover is different from one of the other layers in hardness.

17. A flexible tube for an endoscope, comprising:  
an elongated tubular core body; and  
an outer cover which is provided over the core body, the outer cover having a portion which is formed into a laminate structure composed of at least three layers, the layers of the laminate structure including an inner layer,

an outer layer and at least one intermediate layer formed between the inner layer and the outer layer, wherein the intermediate layer of the outer cover has a higher elasticity than the inner and outer layers so that the intermediate layer functions as cushioning between the inner layer and the outer layer;

wherein the core body has a plurality of holes and/or a plurality of recesses; and

wherein the core body includes:

a coil that is formed by winding a band-shaped material into a spiral form; and

a reticular tube that is formed by weaving a plurality of fine wires together, the reticular tube being provided over the coil.

18. The flexible tube as claimed in claim 17, wherein at least one of the fine wires forming the reticular tube is coated with a synthetic resin so that a coating of the synthetic resin is provided on the fine wire, in which at least a part of the coating is fused with and bonded to the inner layer of the outer cover.

19. The flexible tube as claimed in claim 18, wherein the inner layer of the outer cover contains a material having a compatibility with the synthetic resin of the coating.

\* \* \* \* \*