



US007056463B2

(12) **United States Patent**
Ohta

(10) **Patent No.:** **US 7,056,463 B2**
(45) **Date of Patent:** **Jun. 6, 2006**

(54) **METHOD OF MANUFACTURING
PRESTRESSED CONCRETE**

(75) Inventor: **Toshiaki Ohta**, Fukuoka (JP)

(73) Assignee: **Japan Science and Technology
Agency**, Saitama (JP)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 144 days.

(21) Appl. No.: **10/478,362**

(22) PCT Filed: **May 17, 2002**

(86) PCT No.: **PCT/JP02/04777**

§ 371 (c)(1),
(2), (4) Date: **Nov. 21, 2003**

(87) PCT Pub. No.: **WO02/094525**

PCT Pub. Date: **Nov. 28, 2002**

(65) **Prior Publication Data**

US 2004/0130063 A1 Jul. 8, 2004

(30) **Foreign Application Priority Data**

May 24, 2001 (JP) 2001-155673

(51) **Int. Cl.**
B28B 5/00 (2006.01)

(52) **U.S. Cl.** 264/228; 264/229; 264/249;
264/274; 264/279; 264/279.1; 156/162; 156/169;
156/172; 52/223.13; 52/223.14

(58) **Field of Classification Search** 264/228,
264/229, 249, 274, 279, 279.1; 156/161,
156/162, 169, 171, 172, 180; 52/223.13,
52/223.14

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,406,270	A *	8/1946	Torell et al.	57/202
3,086,273	A *	4/1963	Welborn	264/228
3,111,569	A *	11/1963	Rubenstein	52/223.14
3,115,727	A *	12/1963	Middendorf	52/223.13
3,190,065	A *	6/1965	Little	57/212
3,290,840	A *	12/1966	Middendorf	52/223.13
3,347,005	A *	10/1967	Preston, Jr.	52/223.14
3,399,437	A *	9/1968	Kelly	425/111
3,422,586	A *	1/1969	Parma	52/223.14
3,513,609	A *	5/1970	Lang	52/223.6
3,837,372	A *	9/1974	Bernot	140/92.2
3,858,991	A *	1/1975	Burtelson	403/194

(Continued)

FOREIGN PATENT DOCUMENTS

JP 04-312659 A * 11/1992

(Continued)

OTHER PUBLICATIONS

English Translation of JP 04-312659 A, Dec. 2004, FLS,
Inc.*


(Continued)

Primary Examiner—Michael P. Colaianni
Assistant Examiner—Patrick Butler
(74) *Attorney, Agent, or Firm*—The Webb Law Firm

(57) **ABSTRACT**

Pre-tension and post-tension processes for the manufacture
of pre-stressed structures in which bonded carbon fiber
cables are provided with burial anchors and temporary
anchors outward of the burial anchors. The burial anchors
are embedded in the structure. The temporary anchors
enable stressing of the carbon fiber cables.

8 Claims, 4 Drawing Sheets



US 7,056,463 B2

Page 2

U.S. PATENT DOCUMENTS

4,121,325 A * 10/1978 Bruinette et al. 24/122.6
4,350,549 A * 9/1982 Frehner 156/161
4,469,756 A * 9/1984 Jungwirth et al. 428/592
4,574,545 A * 3/1986 Reigstad et al. 52/223.6
4,726,163 A * 2/1988 Jacobs 52/223.6
4,849,282 A * 7/1989 Watanabe et al. 428/321.5
4,866,903 A * 9/1989 Ferstay 52/677
5,308,696 A * 5/1994 Hanashita et al. 428/357
5,423,362 A * 6/1995 Knight 249/91
5,540,030 A * 7/1996 Morrow 52/742.13
5,580,642 A * 12/1996 Okamoto et al. 428/212
5,939,003 A * 8/1999 Crigler et al. 264/228
6,082,063 A * 7/2000 Shrive et al. 52/223.13
6,209,279 B1 * 4/2001 Meier et al. 52/649.1

FOREIGN PATENT DOCUMENTS

JP 04-366258 A 12/1992
JP 09-177246 A 7/1997

JP 11-124957 A 5/1999
JP 11-350736 A 12/1999
JP 2000-220254 A 8/2000
JP 2001-311259 A 11/2001

OTHER PUBLICATIONS

English Machine Translation of JP 09-177246 A, Jun. 2005, Japanese Patent Office website.*

English Machine Translation of JP 11-124957 A, Jun. 2005, Japanese Patent Office website.*

English Machine Translation of JP 11-350736 A, Jun. 2005, Japanese Patent Office website.*

English Machine Translation of JP 2000-220254 A, Jun. 2005, Japanese Patent Office website.*

English Machine Translation of JP 2001-311259 A, Jun. 2005, Japanese Patent Office website.*

* cited by examiner

FIG. 1A




FIG. 1B




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7A




FIG. 7B




FIG. 8





FIG. 9



1

**METHOD OF MANUFACTURING
PRESTRESSED CONCRETE**

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a method of manufacturing pre-stressed concrete members, which are reinforced with carbon fiber, useful as pillars, columns, spars, beams or the like of building, civil engineering or offshore structures and so on.

2. Description of the Related Art

Pillar, columns, spars, beams or the like in a building, constructing or engineering field are fabricated from concrete members reinforced with steel rods or fiber-reinforced plastics (FRP). Although the steel rod is a representative reinforcing member, it is heavy and requires a broad work-space for processing and handling the reinforced concrete member. The steel rod shall be stored in a properly controlled atmosphere due to its poor corrosion-resistance. Especially, a post-tension concrete member, which has the structure that steel anchors are embedded in a concrete body at both ends, is significantly damaged in a corrosive atmosphere near a seaside.

Application of thermosetting carbon fibers or fiber cables to pre-stressed concrete members has been researched and developed, aiming at lightening and improved corrosion-resistance of the concrete members. In fact, prepregs, which are prepared by bundling many carbon filaments of 10 μm or less in diameter and impregnating the fiber bundle with a thermosetting primer, are sometimes used as carbon fiber cables. Composite members, which are prepared by forming and curing a woven fiber bundle, are also used for reinforcement of concrete members.

Thermosetting carbon fibers and carbon fiber cables are very expensive due to complicated manufacturing process, so that concrete members reinforced with such fibers or cables can not be used to various fields in point of economical view. Carbon fiber cables are often embedded in a loosed state, resulting in poor fatigue strength of the concrete members. Moreover, steel anchors, which are likely to be damaged in a corrosive atmosphere, are still used for pre-stressed concrete members reinforced with carbon fiber cables. In short, corrosion of the concrete members in a salty atmosphere is not fundamentally dissolved only by use of thermosetting carbon fibers or carbon fiber cables for reinforcement.

SUMMARY OF THE INVENTION

The present invention aims at provision of concrete members, which are reinforced with stretched straight carbon fiber cables, excellent in fatigue strength, corrosion-resistance and mechanical properties. An object of the present invention: is to offer concrete members, which can be installed without steel anchors.

The inventive concrete member is manufactured by either of post-tension and pre-tension processes.

According to a post-tension process, continuous carbon filaments are held parallel to each other and bonded together at proper parts with an adhesive to prepare a straight carbon fiber cable. After burial anchors are attached to both ends of the carbon fiber cable, the carbon fiber cable is inserted in a sheath and set in a molding box. Green concrete is poured in the molding box and steam-aged to a predetermined profile. The sheath is filled with grout under the condition

2

that the carbon fiber cable is stretched by pulling tentative anchors. After the grout is hardened, the carbon fiber cable is released from tension.

According to a pre-tension process, continuous carbon filaments are held parallel to each other and bonded together at proper positions with an adhesive to prepare a straight carbon fiber cable. The carbon fiber cable is processed to a main reinforcing member by attaching burial anchors. Tentative anchors are attached to both ends of the main reinforcing member. The tentative anchors are clamped to an anchor-fixing discs. At least a carbon fiber hoop is wound around a plurality of the straight carbon fiber cables and bonded thereto with an adhesive. The main reinforcing member, which has the carbon fiber hoops fixed to the carbon fiber cables, is set in a molding box. Green concrete is poured in the molding box under the condition that the main reinforcing member is stretched by pulling the tentative anchors. The green concrete is steam-aged to a predetermined profile in the molding box. Thereafter, the main reinforcing member is released from tension.

In any of the post-tension and pre-tension processes, burial anchors are bonded to the carbon fiber cable at its both ends or parts near the ends. The burial anchor is prepared by forming a carbon fiber bundle to a U-shaped profile. The burial anchor may be a part of the carbon fiber cable shaped to a predetermined profile. The U-shaped anchor preferably has a flat bottom perpendicular to a longitudinal direction of the concrete member. The burial anchor is completely buried in a concrete body without such projection as noted in a conventional steel anchor.

A burial anchor, which is bonded to a carbon fiber cable, is a U-shaped carbon fiber cable. It is bonded to a folded end of a carbon fiber bundle extending from an end of the straight carbon fiber cable.

A burial anchor, which is a part of a straight carbon fiber cable, is prepared as follows: A plurality of straight carbon fiber bundles are arranged in a toroidal state each parallel to the other. A banding carbon fiber bundle is wound onto straight parts of the carbon fiber bundles. A cold-setting low-viscosity resin bond is infiltrated to the banded parts and cured, so as to form the burial anchor at both ends of the carbon fiber cable.

A main reinforcing member is formed to a proper length with ease by bonding two or more straight carbon fiber cables. In this case, carbon filaments of each carbon fiber cable are overlaid on and bonded to carbon filaments of the other carbon fiber cable. After each carbon fiber bundle is untied, its filaments are intertwined with filaments of the other carbon fiber bundle and the carbon fiber bundles are firmly bonded together.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is a schematic view illustrating a straight carbon fiber cable, in which carbon fiber bundles are bonded together at predetermined positions along a longitudinal direction.

FIG. 1B is a sectional view illustrating a straight carbon fiber cable impregnated with a cold-setting low-viscosity resin bond.

FIG. 2 is a side view illustrating a bonded joint between two straight carbon fiber cables.

FIG. 3 is a sectional view illustrating a post-tension process, whereby an anchor is bonded to an end of a straight carbon fiber cable.

FIG. 4A is a perspective view illustrating a part of a straight carbon fiber cable, to which a U-shaped carbon fiber anchor is bonded.

FIG. 4B is a side view illustrating the same part of the straight carbon fiber cable.

FIG. 5 is a plan view illustrating a U-shaped carbon fiber anchor, which will be bonded to an end of a straight carbon fiber cable.

FIGS. 6A, 6B, and 6C together comprise a flow chart illustrating formation of a burial anchor at an end of a straight carbon fiber cable.

FIG. 7A is a sectional view illustrating a steel pipe of a tentative anchor, which will be fixed to an end of a carbon fiber cable.

FIG. 7B is a sectional view illustrating the same steel pipe, which has a carbon fiber cable folded and secured therein.

FIG. 8 is a sectional view illustrating attachment of anchors to a carbon fiber multi-cable, which is prepared by uniting two or more straight carbon fiber cables together.

FIG. 9 is a view illustrating a pre-tension process, whereby a pre-stressed concrete member is manufactured, using hooped straight carbon fiber cables.

DETAILED DESCRIPTION OF THE INVENTION

A composite member, which is prepared by impregnating a carbon fiber bundle with a thermosetting primer, forming the prepreg to a predetermined profile and then curing the thermosetting primer, has been used as a carbon fiber cable for a pre-stressed concrete member. The inventive carbon fiber cable is different from the conventional composite member, since it is fabricated without steps of pre-impregnation and thermosetting. Due to omission of pre-impregnation and thermosetting steps, the carbon fiber cable is offered at a low cost.

According to the present invention, carbon filaments are bundled in a state each parallel to the other, and the carbon fiber bundle is formed to a straight carbon fiber cable by application of a certain tension. A cold-setting low-viscosity resin bond is infiltrated into the straight carbon fiber cable and then cured at a temperature of 60° C. or lower during steam-aging concrete. The cold-setting low-viscosity resin bond preferably has a cure temperature of 20±10° C. and viscosity of 700–1000 mPa·sec.

A burial anchor is also prepared from the same straight carbon fiber cable, as follows: The straight carbon fiber cable is bent to a U-shape, and upper parts of the U-shaped carbon fiber cable are coupled with a tendon. A middle part between the coupled parts is straightened, while a bottom of the U-shaped carbon fiber cable is reformed to a flatter and wider profile than the other part. A resin bond is infiltrated into the carbon fiber cable and cured therein. The U-shaped carbon exhibits an elevated anchoring effect due to the flattened bottom, when the anchor is buried in grout hardened in a sheath or a concrete body. The anchor made of the straight carbon fiber cable is also excellent in corrosion-resistance and handled with ease.

A hoop, which is used in a pre-tension process, is also prepared from a straight carbon fiber cable. Two or more straight carbon fiber cables as a main reinforcing member are arranged parallel to each other. A carbon fiber hoop is wound around the straight carbon fiber cables. A cold-setting low-viscosity resin bond is infiltrated into the main rein-

forcing member and the hoop at the crossing points. The hoop is formed at a part of the main reinforcing member by curing the resin bond.

Since straight carbon fiber cables are used as main reinforcing member, burial anchors and hoops, pre-stressed concrete members, which are lightened (e.g. a fourth of a conventional concrete member reinforced with a steel rod by specific gravity) and well resistant to corrosion in a salty atmosphere, are manufactured. Due to excellent corrosion-resistance, the concrete members are easily handled or stored and also installed with good durability.

The other features of the present invention will be clearly understood from the following explanation consulting with drawings attached herewith.

[Preparation of a Straight Carbon Fiber Cable]

Continuous carbon filaments **11** are arranged and stretched in a state parallel to each other, so as to form a straight carbon fiber cable **10**. The carbon filaments **11** are fixed together by a cold-setting resin bond **12** at proper positions along a longitudinal direction, as shown in FIG. 1A. In the case where the carbon fiber cable **10** is used for reinforcement of a pre-stressed concrete member, it is reformed to a tight state and impregnated with a cold-setting low-viscosity resin bond. Each carbon filament **11** is firmly bonded with the other by curing the resin bond, as shown in FIG. 1B. Since the straight carbon fiber cable **10** is prepared by stretching continuous carbon filaments **11** and bonding the filaments **11** together, it is not loosened but improved in fatigue strength as compared with a conventional stranded cable.

Infiltration and curing of the cold-setting resin bond in the straight carbon fiber cable **10** may be performed in a cable-fabricating yard or a pre-stressed concrete member-manufacturing yard. In any case, use of the straight carbon fiber cable **10** remarkably eliminates difficulty on production and handling of a reinforced concrete member, and saves a working space necessary for fabrication and preparation of reinforcing members. Consequently, pre-stressed concrete members are manufactured and installed at a low cost. Moreover, it is possible to automatically on-line control arrangement of reinforcing members and production of pre-stressed concrete members.

Two or more straight carbon fiber cables **10** may be tied each other to a predetermined length suitable for a purpose, as shown in FIG. 2. When the straight carbon fiber cables **10a**, **10b** are tied together, carbon fibers **10f** are preferably wound onto the tied joint for reinforcement.

In the case where two or more straight carbon fiber cables **10a**, **10b** are tied together to, a predetermined length necessary for a practical use, one straight carbon fiber cable **10a** is overlaid on the other straight carbon fiber cable **10b**, a cold-setting resin bond **12** is infiltrated into the overlaid part of the straight carbon fiber cables **10a**, **10b**, and the straight carbon fiber cables **10a**, **10b** are banded together with carbon fibers **10f**. Thereafter, the cold-setting resin bond **12** is cured so as to bond the carbon fibers **10f** to the carbon fiber cables **10a**, **10b**. A fiber bundle of each carbon fiber cables **10a**, **10b** may be untied and intertwined at the joint before infiltration of the cold-setting resin bond **12**, in order to strengthen the tied joint.

[Fixation of a Burial Anchor]

After a straight carbon fiber cable **10** is banded with a ring **31** at its end, carbon fiber bundles **13a**, **13b** are pulled out beyond the ring **31**. Reinforcing members **32** are bonded to the carbon fiber bundles **13a**, **13b** with a resin bond, and one

5

or more U-shaped carbon fiber anchors **33**, **33** are inserted as burial anchors between the carbon fiber bundles **13a**, **13b**. (FIGS. **3**, **4A** and **4B**)

The U-shaped carbon fiber anchor **33** may be untied to separate filaments at jointing ends **33e** in a predetermined length **A**, as shown in FIG. **5**. The separate filaments are intertwined with filaments of the straight carbon fiber bundles **13a**, **13b**, and a resin; bond is infiltrated into the intertwined part, whereby the U-shaped carbon fiber anchors **33** are firmly bonded to the straight carbon fiber bundles **13a**, **13b** by curing the infiltrated resin bond.

The U-shaped carbon fiber anchor **33** preferably has a flattened bottom in order to enlarge its bearing area with respect to grout **22**. The U-shaped carbon fiber anchor **33**, which is preformed to a certain profile by infiltrating a thermosetting resin bond to a part except the jointing ends **33e** and curing the infiltrated resin bond therein, is bonded to a straight carbon fiber cable **10** in a cable-fabricating yard or a pre-stressed concrete-manufacturing yard.

A U-shaped carbon fiber anchor **35**, which is formed from an end part of a straight carbon fiber cable **10**, may be used instead of the separate U-shaped carbon fiber anchor **33**. The integrated U-shaped carbon fiber anchor is fabricated as follows:

Carbon fiber bundles **17** are arranged in a toroidal state each parallel to the other, and expanded at both ends with spacers **34_r**, **34_l**, as shown in FIG. **6(a)**. After the carbon fiber bundles **17** are stretched, a banding carbon fiber bundle **18** is helically wound on and bonded to straight parts of the carbon fiber bundles **17**. As a result, U-shaped carbon fiber anchors **35_r**, **35_l** are formed at both ends of the carbon fiber cable **10**, as shown in FIG. **6(b)**. Carbon fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** are properly attached to the U-shaped carbon fiber anchors **35_r**, **35_l** by winding carbon fiber reinforcing members **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}** thereon, as shown in FIG. **6(c)**. The fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** are used for stretching the main reinforcing member **10**.

The reinforcing members **32**, **37** are made of continuous carbon filaments. The stretching carbon fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** are bonded to the integrated t-shaped carbon fiber anchors **35_r**, **35_l**, by intertwining filaments of the carbon fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** with filaments of the carbon fiber anchors **35_r**, **35_l**, impregnating the intertwined part with a resin bond, and curing the resin bond therein.

A cold-setting low-viscosity resin bond is applied to a surface of the joint, where the U-shaped carbon fiber anchor **33** is bonded to the straight carbon fiber cable **10**, or where the stretching carbon fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** are bonded to the U-shaped carbon fiber anchors **35_r**, **35_l** formed at end parts of the straight carbon fiber cable **10**. The reinforcing members **32**, **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}** are helically wound on the resin bond-applied surface, and then the resin bond is cured so as to firmly integrate the reinforcing members **32**, **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}** with the straight carbon fiber cable **10** and the U-shaped carbon fiber anchors **33**, **35_r**, **35_l**. Each carbon fiber bundle is preferably untied to separate filaments and intertwined together in this case, too.

The bonded joint is strengthened due to presence of the cured resin bond and a tightening force of the reinforcing members **32**, **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}**. In fact, the U-shaped carbon fiber anchor **33** is firmly bonded to the straight carbon fiber cable **10**, or the stretching carbon fiber cables **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}** is firmly bonded to the U-shaped carbon fiber anchors **35_r**, **35_l** formed at end parts of the straight carbon fiber cable **10** by enlarging a contact plane between the carbon fiber filaments, infiltrating a sufficient amount of the resin bond and raising a tightening force of the reinforcing

6

ing member **32**, **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}**. In prior to bonding, each carbon fiber bundle is preferably untied to separate filaments at the joint between the straight carbon fiber cable **10** and the U-shaped carbon fiber anchor **33** or between the integrated U-shaped carbon fiber anchors **35_r**, **35_l** and the stretching carbon fiber cable **36_{1r}**, **36_{1l}**, **36_{2r}**, **36_{2l}**. When the separate carbon fiber filaments are intertwined each other, impregnated with the resin bond and tied with the reinforcing members **32**, **37_{1r}**, **37_{1l}**, **37_{2r}**, **37_{2l}**, the bonded joint is further strengthened due to the cured resin bond in the carbon fiber bundles.

The fabricated straight carbon fiber cable **10** is useful as a stretching cable in a post-tension or pre-tension process for manufacturing a pre-stressed concrete member **20**.

[Post-Tension Process]

In a post-tension process, the U-shaped carbon fiber anchor **33** is bonded to the straight carbon fiber cable **10**, tentative anchors **40a**, **40b** for application of an initial tension are attached to top ends of carbon fiber bundles **13a**, **13b** extending from the straight carbon fiber cable **10**, and then the carbon fiber bundles **13a**, **13b** are inserted in a sheath **21**, which preferably has a tapered inner surface **21t** enlarged toward an opened end, as shown in FIG. **3**.

A reinforcing carbon fiber cable **14** may be helically wound on the straight carbon fiber cable **10** and bonded thereto with a resin bond, in prior to insertion of the carbon fiber bundles **13a**, **13b** in the sheath **21**. Adhesion of grout **22** to the straight carbon fiber cable **10** is improved by the reinforcing carbon fiber cable **14**. However, an unbending post-tension process without using the reinforcing carbon fiber cable **14** is also applicable.

Each tentative anchor **40a**, **40b** has a steel pipe **41**, whose inner diameter becomes larger from one end to the other end, as shown in FIG. **7A**. Each carbon fiber bundle **13a**, **13b** is folded at its top end, the folded part is inserted in the steel pipe **41** from an opened end of a larger diameter. The folded part is overlaid on the straight carbon fiber cable **10** and integrally bonded thereto with a resin bond. Thereafter, the steel pipe **41** is filled with an expansive resin or concrete **42** so as to prevent the folded part of the carbon fiber bundle **13a**, **13b** from dropping off the steel pipe **41**, as shown in FIG. **7B**. The folded part of the carbon fiber bundle **13a**, **13b** may be flattened. Adhesion of the resin or expansive concrete **42** to the folded part of the carbon fiber bundle **13a**, **13b** can be improved by a bonding node **44**, which is formed by winding a reinforcing carbon fiber bundle **43** on the flat folded part, infiltrating and curing the resin bond in the carbon fiber bundles **13a**, **13b** and **43**.

A straight carbon fiber multi-cable **10n** maybe used as a straight carbon fiber cable **10** inserted in a sheath **21**, in order to enhance pre-stress strength. The multi-cable **10n** is also preferably tied with a cold-setting low-viscosity resin bond at proper positions along its longitudinal direction.

In the case where the straight carbon fiber multi-cable **10n** is used, each carbon fiber bundle **13₁**, **13₂** . . . **13_n** extending from the multi-cable **10n** is folded and inserted in the sheath **21**, as shown in FIG. **8**. The carbon fiber bundles **13₁**, **13₂** . . . **13_n** are bridged with a plurality of U-shaped carbon fiber anchors **33₁**, **33₂** . . . **33_n**, and tentative anchors **40₁**, **40₂** . . . **40_n** are attached to the carbon fiber bundles **13₁**, **13₂** . . . **13_n**. The sheath **21**, in which the folded parts of the carbon fiber bundles **13₁**, **13₂** . . . **13_n** are inserted, is located at one side of a molding box. The multi-cable **10n** is straightened by stretching each cable of the multi-cable **10n**.

After the straight carbon fiber cable **10**, to which the U-shaped carbon fiber anchor **33** is fixed, or wherein the

stretching carbon fiber cables 36_{1r} , 36_{1b} , 36_{2r} , 36_{2l} are bonded to the U-shaped carbon fiber anchors 35_r , 35_l formed at end parts of the straight carbon fiber cable **10** (FIGS. **6B** and **6C**), is inserted in the sheath **21**, the straight carbon fiber cable **10** is set in a molding box. Green concrete is poured in the molding box under the condition that the straight carbon fiber cable **10** is stretched by pulling the tentative anchors 40_a , 40_b .

After the poured concrete **23** is hardened to a predetermined profile in the molding box, a hydraulic jack is detached from the molding box without relaxation of the straight carbon fiber cable **10**. Grout **22** is then poured and hardened in the sheath **21**. Thereafter, a tacking tool is unloosed, each carbon fiber bundle 13_a , 13_b is cut off at a position between the tentative anchor 40_a , 40_b and a concrete body **23**. The pre-stressed concrete member **20** is taken out of the molding box and offered for a practical use.

A compression force (i.e. pre-stress), which originates in shrinkage of the straight carbon fiber cable **10** released from a tension, is applied to the pre-stressed concrete member **20** fabricated in this way, since an anchoring effect is realized by the buried carbon fiber anchor **33** and the grout **22** in the sheath **21**.

[Pre-tension Process]

A pre-tension process uses a pre-tension apparatus **50** having anchor-fixing discs **51**, to which tentative anchors 40_1 , $40_2 \dots 40_n$ can be attached with predetermined positional relationship, at both sides, as shown in FIG. **9**. A hydraulic jack **53** is located between each anchor-fixing disc **51** and a bearing wall **52**.

Reinforcing members **32**, U-shaped carbon fiber anchors **33** and so on are bonded to a straight carbon fiber cable **10** by the same way as the post-tension process, except use of main reinforcing members 15_1 , $15_2 \dots 15_n$ made of the straight carbon fiber cable **10** and a hoop **16** made of the straight carbon fiber bundle.

A carbon fiber cable, in which a cold-setting low-viscosity resin bond is preparatively infiltrated and cured, may be used as the straight carbon fiber cable **10** for the main reinforcing members 15_1 , $15_2 \dots 15_n$ and the hoop **16**. Each tentative anchor 40_1 , $40_2 \dots 40_n$ is bonded to a corresponding carbon fiber bundle 13_1 , $13_2 \dots 13_n$, and attached to a predetermined hole of the anchor-fixing disc **51**. A sectional profile of the main reinforcing members 15_1 , $15_2 \dots 15_n$ (in other words, a pre-stressed concrete member **20**) is determined by selection of holes of the anchor-fixing disc **51**, to which the tentative anchor 40_1 , $40_2 \dots 40_n$ are inserted. Each main reinforcing member 15_1 , $15_2 \dots 15_n$ is held parallel to the other, when its both ends are inserted in the holes of the anchor-fixing discs **51**.

The hoop **16** is wound around the main reinforcing members 15_1 , $15_2 \dots 15_n$, which are held with such positional relationship to define a predetermined sectional profile. The hoop **16** is bonded to the main reinforcing members 15_1 , $15_2 \dots 15_n$ at crossing points with a resin bond.

The main reinforcing members 15_1 , $15_2 \dots 15_n$ integrated with the hoop **16** are expanded between the anchor-fixing discs **51**, **51**, and the tentative anchors 40_1 , $40_2 \dots 40_n$ are clamped to the anchor-fixing discs **51**, **51**. After the main reinforcing members 15_1 , $15_2 \dots 15_n$ are set in a molding box **54**, the left-handed anchor-fixing disc **51** is shifted leftwards in FIG. **9** by actuation of the hydraulic jack **53** so as to stretch the main reinforcing members 15_1 , $15_2 \dots 15_n$. Under the condition that the main reinforcing members 15_1 , $15_2 \dots 15_n$ are stretched with a certain tension, green

concrete is poured in the molding box **54** and steam-aged therein. After the concrete is sufficiently hardened, the hydraulic jack **53** is released from a pressure. The main reinforcing members 15_1 , $15_2 \dots 15_n$ are cut off at positions between the concrete body **23** and the tentative anchors 40_1 , $40_2 \dots 40_n$, and the concrete member **20** is separated from the molding box **54**.

The pre-stressed concrete member **20** fabricated in this way is strengthened due to a compression force (i.e. pre-stress) originated in shrinkage of the main reinforcing members 15_1 , $15_2 \dots 15_n$ released from the tension. The bonded joints, where the hoop **16** is bonded to the main reinforcing members 15_1 , $15_2 \dots 15_n$ at a right angle, act as a series of nodes along a longitudinal direction of the main reinforcing members 15_1 , $15_2 \dots 15_n$, so as to firmly integrate the main reinforcing members 15_1 , $15_2 \dots 15_n$ with the concrete body **23** and to realize a dispersion effect of cracks. Consequently, the pre-stressed concrete member **20** is durable over a long term due to mechanical strength of the main reinforcing members 15_1 , $15_2 \dots 15_n$.

INDUSTRIAL APPLICABILITY

According to the present invention, a straight carbon fiber cable is impregnated with a cold-setting low-viscosity resin bond, stretched and molded as such in a concrete body. Arrangement of reinforcing members is fairly simplified in comparison with a conventional process using a composite member pre-cured with a thermosetting resin, and burial anchors are bonded to the straight carbon fiber cable at proper positions with ease. Since the straight carbon fiber cable is straightened by application of a tension and molded in concrete, the pre-stressed concrete member is improved in tensile strength, fatigue properties and crack-resistance. Moreover, carbon fiber cables are bonded as burial anchors to the reinforcing members instead of conventional metal fitting, so that the pre-stressed concrete member exhibits excellent corrosion-resistance even in a salty atmosphere. The pre-stressed concrete member is also handled with safe, since any part is not projected from its surface.

The invention claimed is:

1. A post-tension method for manufacturing a pre-stressed concrete member, which comprises the steps of:
 - holding continuous carbon fiber filaments parallel to each other;
 - preparing a carbon fiber cable by bonding said carbon fiber filaments at positions along a longitudinal direction;
 - bonding or forming burial anchors near both ends of said carbon fiber cable;
 - attaching temporary anchors to both ends of said carbon fiber cable outward of said burial anchors;
 - inserting ends of said carbon fiber cable including said burial anchors in a sheath;
 - setting said carbon fiber cable within said sheath in a molding box;
 - pouring green concrete in said molding box;
 - hardening said poured concrete to a concrete member, in which said carbon fiber is molded;
 - pouring grout in said sheath under the condition that said carbon fiber cable is stretched by pulling said temporary anchors in a longitudinal direction; and
 - releasing said carbon fiber cable from tension after said grout is hardened in said sheath.
2. The method of claim 1, wherein burial anchors are U-shaped carbon fiber bundles bonded to adjacent carbon fiber cables.

9

3. The method of claim 1, wherein the carbon fiber cable is prepared by stretching a plurality of carbon fiber bundles arranged parallel to each other in a continuous loop shape with toroidal-shaped ends spaced by generally straight leg sections, winding bandings on said straight leg sections to form loops at each end of said straight leg sections, infiltrating a resin bond to the carbon fiber cables at the banded positions and curing the resin bond, whereby carbon fiber anchors are integrally formed at both ends of the straight carbon fiber cables.

4. The method of claim 1, wherein the burial anchors have a U-shaped profile with a bottom flattened along a direction perpendicular to the longitudinal direction of the stretched carbon fiber cables.

5. A pre-tension method for manufacturing a pre-stressed concrete member, which comprises the steps of:

holding continuous carbon fiber filaments parallel to each other;

preparing carbon fiber cables by bonding said carbon fiber filaments together at positions along a longitudinal direction;

bonding or forming burial anchors to both ends of said carbon fiber cables;

attaching temporary anchors to said carbon fiber cables extending from both ends of said carbon fiber cable outward of the burial anchors;

fixing said temporary anchors to anchor-fixing discs;

winding a carbon fiber hoop around said carbon fiber cables;

10

bonding said carbon fiber hoop to said carbon fiber cables; setting said carbon fiber cables together with said bonded hoop in a molding box;

pouring green concrete in said molding box under the condition that said carbon fiber cables are stretched in a longitudinal direction;

steam-aging said concrete to a hardened concrete body; and

releasing the carbon cables from tension.

6. The method according to claim 5, wherein the burial anchors are U-shaped carbon fiber bundles bonded to said carbon fiber cables.

7. The method of claim 5, wherein the carbon fiber cables are prepared by stretching a plurality of carbon fiber bundles arranged parallel to each other in a continuous loop shape with toroidal-shaped ends spaced by generally straight leg sections, winding banding on said fiber bundle on straight leg sections of the carbon fiber cables, infiltrating a resin bond to the carbon fiber cables at banded positions and curing the resin bond, whereby carbon fiber anchors are integrally formed at the both ends of said carbon fiber cables.

8. The method of claim 5, wherein the burial anchors have a U-shaped profile with a bottom flattened along a direction perpendicular to the longitudinal direction of the carbon fiber cables.

* * * * *