

(12) **United States Patent**  
**Dong et al.**

(10) **Patent No.:** **US 7,787,729 B2**  
(45) **Date of Patent:** **Aug. 31, 2010**

(54) **SINGLE MODE PROPAGATION IN FIBERS  
AND RODS WITH LARGE LEAKAGE  
CHANNELS**

(75) Inventors: **Liang Dong**, Ann Arbor, MI (US);  
**William Wong**, Ann Arbor, MI (US);  
**Martin E. Fermann**, Dexter, MI (US)

(73) Assignee: **Imra America, Inc.**, Ann Arbor, MI  
(US)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 414 days.

(21) Appl. No.: **11/134,856**

(22) Filed: **May 20, 2005**

(65) **Prior Publication Data**  
US 2006/0263024 A1 Nov. 23, 2006

(51) **Int. Cl.**  
**G02B 6/02** (2006.01)

(52) **U.S. Cl.** ..... **385/123**; 385/124; 385/125;  
385/126; 385/127

(58) **Field of Classification Search** ..... 385/123  
See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,641,917 A	2/1987	Glodis
4,784,486 A	11/1988	Van Wagenen
5,032,001 A	7/1991	Shang
5,121,460 A	6/1992	Tumminelli
5,175,785 A	12/1992	Dabby
5,353,363 A	10/1994	Keck
5,452,394 A	9/1995	Huang
5,521,703 A	5/1996	Mitchell
5,615,673 A	4/1997	Berger et al.
5,742,722 A	4/1998	Imoto
5,802,236 A	9/1998	DiGiovanni
5,818,630 A	10/1998	Fermann et al.
6,072,811 A	6/2000	Fermann et al.

6,236,779 B1	5/2001	Kafka
6,243,522 B1	6/2001	Allan
6,334,017 B1	12/2001	West
6,334,019 B1	12/2001	Birks
6,389,198 B2	5/2002	Kafka

(Continued)

**FOREIGN PATENT DOCUMENTS**

CN	1686884	10/2005
----	---------	---------

(Continued)

**OTHER PUBLICATIONS**

Galvanauskas, *Mode-scalable fiber chirped pulse amplification systems*, IEEE J. Sel. Top. Quantum Electronics, vol. 7, No. 4, pp. 504-517 (2001).

(Continued)

*Primary Examiner*—Charlie Peng

*Assistant Examiner*—Mary A El Shammaa


(74) *Attorney, Agent, or Firm*—Knobbe Martens Olson & Bear LLP

(57)

**ABSTRACT**

Various embodiments include large cores fibers that can propagate few modes or a single mode while introducing loss to higher order modes. Some of these fibers are holey fibers that comprising cladding features such as air-holes. Additional embodiments described herein include holey rods. The rods and fibers may be used in many optical systems including optical amplification systems, lasers, short pulse generators, Q-switched lasers, etc. and may be used for example for micromachining.

**58 Claims, 22 Drawing Sheets**



## U.S. PATENT DOCUMENTS

6,418,258 B1 7/2002 Wang  
 6,444,133 B1 9/2002 Fajardo et al.  
 6,542,681 B2 4/2003 Broeng  
 6,631,234 B1 10/2003 Russell  
 6,652,163 B2 11/2003 Fajardo  
 6,778,732 B1 8/2004 Fermann et al.  
 6,792,188 B2 9/2004 Libori  
 6,795,635 B1 9/2004 Fajardo  
 6,825,974 B2 11/2004 Klinier et al.  
 6,836,607 B2 12/2004 Dejneka et al.  
 6,845,204 B1 1/2005 Broeng  
 6,853,786 B2 2/2005 Russell  
 6,856,742 B2 2/2005 Broeng et al.  
 6,888,992 B2 5/2005 Russell  
 6,892,018 B2 5/2005 Libori et al.  
 6,954,574 B1 10/2005 Russell  
 6,972,894 B2 12/2005 Bjarklev  
 6,987,783 B2 1/2006 Fajardo  
 6,990,282 B2 1/2006 Russell  
 7,054,513 B2 5/2006 Herz  
 7,106,932 B2 9/2006 Birks  
 7,116,875 B2 10/2006 Wadsworth  
 7,136,558 B2 11/2006 Epworth et al.  
 7,155,097 B2 12/2006 Jakobsen  
 7,174,078 B2 2/2007 Libori  
 7,209,619 B2 4/2007 Dong  
 7,221,840 B2 5/2007 Vienne  
 7,224,873 B2 5/2007 Bird  
 7,245,807 B2 7/2007 Mangan  
 7,257,302 B2 8/2007 Fermann  
 7,266,275 B2 9/2007 Hansen  
 7,280,730 B2 10/2007 Dong et al.  
 7,304,309 B2 12/2007 Suhani  
 7,305,164 B2 12/2007 Williams  
 7,321,712 B2 1/2008 Williams  
 7,327,922 B2 2/2008 Skovgaard  
 7,346,249 B2 3/2008 Russell  
 7,349,611 B2 3/2008 Broeng  
 7,414,780 B2 8/2008 Fermann  
 7,418,836 B2 9/2008 Dong  
 7,532,798 B2 5/2009 Williams  
 7,539,382 B2 5/2009 Skovgaard  
 7,590,323 B2 9/2009 Broeng  
 2001/0024546 A1 9/2001 Kafka  
 2002/0181534 A1 12/2002 Hodgson  
 2003/0059185 A1 3/2003 Russell  
 2004/0005127 A1 1/2004 Klinier et al.  
 2004/0033043 A1 2/2004 Monro et al.  
 2004/0052484 A1 3/2004 Broeng et al.  
 2004/0071423 A1 4/2004 Libori et al.  
 2004/0146264 A1 7/2004 Auner  
 2004/0175084 A1 9/2004 Broeng et al.  
 2004/0213302 A1 10/2004 Fermann et al.  
 2004/0228592 A1 11/2004 Gaeta  
 2004/0258381 A1 12/2004 Borrelli  
 2005/0018714 A1 1/2005 Fermann et al.  
 2005/0041702 A1 2/2005 Fermann et al.  
 2005/0069269 A1 3/2005 Libori  
 2005/0105865 A1 5/2005 Fermann et al.  
 2005/0157998 A1 7/2005 Dong  
 2005/0169590 A1 8/2005 Alkeskjold  
 2005/0185908 A1 8/2005 Roberts  
 2005/0226278 A1 10/2005 Gu et al.  
 2005/0232313 A1 10/2005 Fermann  
 2005/0238070 A1 10/2005 Imeshev  
 2005/0276556 A1 12/2005 Williams  
 2006/0005579 A1 1/2006 Jacobsen  
 2006/0067632 A1 3/2006 Broeng  
 2006/0177187 A1 8/2006 Williams  
 2006/0193583 A1 8/2006 Dong et al.  
 2006/0209908 A1 9/2006 Pedersen

2006/0263024 A1 11/2006 Dong et al.  
 2007/0163301 A1 7/2007 Dong et al.  
 2007/0201801 A1 8/2007 Provost  
 2008/0056656 A1 3/2008 Dong

## FOREIGN PATENT DOCUMENTS

DE 60004638 T2 6/2004  
 EP 1043281 10/2000  
 EP 1421420 B1 1/2007  
 FR 2333628 7/1977  
 GB 2103202 2/1983  
 JP 5345632 12/1993  
 JP 6037385 2/1994  
 JP 6298542 10/1994  
 JP 2002116181 4/2002  
 WO WO 9836300 8/1998  
 WO WO 00/16141 3/2000  
 WO WO 00/49435 A1 8/2000  
 WO WO 00/60390 A1 10/2000  
 WO WO 0137008 5/2001  
 WO WO 02/088801 A2 11/2002  
 WO WO 02/101429 A2 12/2002  
 WO WO 03/078338 A2 9/2003  
 WO WO 03/100488 A1 12/2003  
 WO WO 2004/019092 A1 3/2004  
 WO WO 2004/053550 A1 6/2004  
 WO WO 2004/111695 A1 12/2004  
 WO WO 2005/041367 A1 5/2005  
 WO WO 2005/059612 A1 6/2005  
 WO WO 2005054139 6/2005  
 WO WO 2005/091029 A2 9/2005  
 WO WO 2006112071 10/2006

## OTHER PUBLICATIONS

Knight, *Properties of photonic crystal fiber and the effective index model*, J. Opt. Soc. Am. A/vol. 15, No. 3/Mar. 1998 pp. 748-752.  
 Limpert, et al., "High power air-clad large-mode-area photonic crystal fiber laser", Optics Express, vol. 11, pp. 818-823, 2003.  
 Limpert, et al., *High power Q-switched Yb-doped photonic crystal fiber laser producing sub-10 pulses*, Conf. on Advanced Solid State Photonics, paper PD-411, Vienna (2005).  
 Martinez, et al., *(E)ESI determination from mode-field diameter and refractive index profile measurements on single-mode fibers*, IEEE Proceedings V135, pp. 202-210, (1988).  
 Mortenson, *Modal cutoff and the V parameter in photonic crystal fibers*, Optics Letters vol. 28, No. 20 p. 1879-1881, Oct. 15, 2003.  
 N. Deguil-Robin, et al., *Rod-type fiber laser*, Advanced Solid State Photonics, 2005.  
 U.S. Appl. No. 11/091,015, filed Mar. 25, 2005.  
 U.S. Appl. No. 10/844,943, filed May 13, 2004.  
 International Search Report and Written Opinion in International Application No. PCT/US2008/074668 dated Jan. 27, 2009.  
 Knight, et. al., All-silica single-mode optical fiber with photonic crystal cladding, Oct. 1, 1996, vol. 21, No. 19, Optics Letters, pp. 1547-1549.  
 Birks, et. al., Endlessly single-mode photonic crystal fiber, Jul. 1, 1997, vol. 22, No. 13, Optics Letters, pp. 961-963.  
 P. Yeh, et al.: "Theory of Bragg Fiber", J. Opt. Soc. Am., vol. 68, No. 9, Sep. 1978, pp. 1196-1201.  
 R.F. Cregan, et al.: "Single-Mode Photonic Band Gap Guidance of Light in Air", Science, vol. 285, Sep. 1999, pp. 1537-1539.  
 Y. Fink, et al.: "Guiding Optical Light in Air Using an All-Dielectric Structure", Journal of Lightwave Technology, vol. 17, No. 11, Nov. 1999, pp. 2039-2041.  
 G. Ouyang, et al.: "Comparative study of air-core and coaxial Bragg fibers: single-mode transmission and dispersion characteristics", Optics Express, vol. 9, No. 13, 2001, pp. 733-747.  
 G. Ouyang, et al.: "Theoretical study on dispersion compensation in air-core Bragg fibers", Optics Express, vol. 10, No. 17, 2002, pp. 899-908.



- D.G. Ouzounov, et al.: "Generation of Megawatt Optical Solitons in Hollow-Core Photonic Band-Gap Fibers", *Science* vol. 301, Sep. 19, 2003, pp. 1702-1704.
- J. A. Monsoriu, et al., "High-index-core Bragg fibers: dispersion properties", *Optics Express*, vol. 11, No. 12, 2003, pp. 1400-1405.
- G. Bouwmans, et al., "Properties of a hollow-core photonic bandgap fiber at 850 nm wavelength", *Optic Express*, vol. 11, No. 14, 2003, pp. 1613-1620.
- J. Lægsgaard, et al., "Material effect in air-guiding photonic bandgap fibers", *Journal of the Optical Society of America B*, vol. 20, No. 10, 2003, pp. 2046-2051.
- T.D. Engeness, et al., "Dispersion tailoring and compensation by modal interaction in OmniGuide fibers", *Optics Express*, vol. 11, No. 10, 2003, 1175-1196.
- B.J. Mangan, et al., "Low loss (1.7 dB/km) hollow core photonic bandgap fiber", PDP24, Optical Communications Conference, Feb. 2004.
- Smith, et al., "Low-loss hollow-core silica/air photonic bandgap fiber", *Nature*, vol. 424, Aug. 2004, pp. 657-659.
- International Search Report and Written Opinion in International Application No. PCT/US05/00911 dated Jul. 18, 2006.
- International Search Report and Written Opinion in International Application No. PCT/US05/47520 Jan. 23, 2007.
- Bouwmans, et al., "High-power Er:Yb fiber laser with very high numerical aperture pump-cladding waveguide", *Applied Physics Letters*, vol. 83, No. 5, pp. 817-818, Aug. 4, 2003.
- Glas, et al., "Cladding pumped large-mode-area Nd-doped holey fiber laser", *Optics Express*, vol. 10, No. 6, pp. 286-290, Mar. 25, 2002.
- Folkenberg, et al., "Experimental investigation of cutoff phenomena in nonlinear photonic crystal fibers", *Optics Letters*, vol. 28, No. 20, pp. 1882-1884, Oct. 15, 2003.
- K. Furusawa, et al., "Cladding pumped Ytterbium-doped fiber laser with holey inner and outer cladding", *Optics Express*, vol. 9, No. 13, pp. 714-720, Dec. 17, 2001.
- Kuhlmey, et al., "Microstructured Optical Fibers: where's the edge?", *Optics Express*, vol. 10, No. 22, pp. 1285-1290, Nov. 4, 2002.
- Kuhlmey, et al., "Modal cutoff in microstructured optical fibers", *Optics Letters*, vol. 27, No. 19 pp. 1684-1686, Oct. 1, 2002.
- Mortensen, et al., "Improved large-mode-area endlessly single-mode photonic crystal fibers", *Optics Letters*, vol. 28, No. 6, pp. 393-395, Mar. 15, 2003.
- Ranka et al., "Visible continuum generation in air-silica microstructure optical fibers with anomalous dispersion at 800 nm", *Optics Letters*, vol. 25, No. 1, pp. 25-27, Jan. 1, 2000.
- Ranka et al., "Optical properties of high-delta air silica microstructure optical fibers", *Optics Letters*, vol. 25, No. 11, pp. 796-798, Jun. 1, 2000.
- Russell, et al., "Photonic Crystal Fibers", *Science Mag.* vol. 299, pp. 358-362, Jan. 17, 2003.
- Snyder, et al., "Optical Waveguide Theory, Appendix Charts". Chapman and Hall Ltd., 1983.
- W.J. Wadsworth, et al., "High power air-clad photonic crystal fibre laser", *Optics Express*, vol. 11, No. 1, pp. 48-53, Jan. 13, 2003.
- W. Wong, et al., "Breaking the limit of maximum effective area for robust guided single-mode propagation in optical fibers", *Optics Letters*, vol. 30, No. 21, Nov. 1, 2005.
- W. Wong, et al., "Robust Single-Mode Propagation in Optical Fibers with Record Effective Areas", Conference on Lasers and Electro-Optics (CLEO), May 22-27, 2005, CLEO 05 CPDB10.
- J. M. Fini, "Design of solid and microstructure fibers for suppression of higher-order modes," *Optics Express*, vol. 13, No. 9, pp. 3477-3490, May 2, 2005.
- T. Hasegawa, et al., "Hole-assisted lightguide fiber for large anomalous dispersion and low optical loss," *Optics Express*, vol. 9, No. 13, pp. 681-686, Dec. 17, 2001.
- C. J. S. De Matos et al., "All-fiber chirped pulse amplification using highly-dispersive air-core photonic bandgap fiber," *Optics Express* vol. 11, No. 22, Nov. 3, 2003, pp. 2832-2837.
- Office Action issued Jan. 25, 2010 for German Patent Application No. DE 10 2006 023 976.8.




Figure 1A




Figure 1B






Figure 1C






Figure 2A




Figure 2B




Figure 3






Figure 4






Figure 5A




Figure 5B






Figure 6A




Figure 6B




Figure 6C






Figure 6D




Figure 6E




Figure 6F






Figure 7A




Figure 7B




Figure 7C






Figure 7D




Figure 7E




Figure 8A




Figure 8B




Figure 8C






Figure 9




Figure 10




Figure 11




Figure 12




Figure 13






Figure 14A




Figure 14B




Figure 14C




Figure 14D




Figure 14E






Fig. 15A




Fig. 15B




Figure 15C







Figure 15D



230 Figure 15E




Figure 15F




Fig. 16






Figure 17




Figure 18






Fig. 19






300 Figure 20A



306 Figure 20B



100 Figure 21

## 1

# SINGLE MODE PROPAGATION IN FIBERS AND RODS WITH LARGE LEAKAGE CHANNELS

## FIELD OF THE INVENTION

This invention relates to optical fiber and optical rods in general and in particular, to optical fiber and rod waveguides with large core dimensions for single mode propagation and devices and systems that use such fibers and rods such as lasers and amplifiers.

## BACKGROUND

Fiber lasers have demonstrated a great deal of potentials as high power pulse and cw laser sources, especially for applications where high quality, near diffraction-limited beam is required. Such applications include precision machining where well defined beam location is critical and micro-machining and waveguide-writing where a highly focused beam is a useful tool for reaching a threshold power level. The major limitation to the development of fiber lasers with even high peak power is nonlinear effects. The major nonlinear limits are from Raman scattering and self-phase modulation, although Brillouin scattering can also play a role in narrow line-width laser systems. Nonlinear coefficients are low for the silica glass used in most optical fibers. The interaction between the low nonlinear coefficients with high peak intensity in the small fiber core over a sufficient length can, however, still cause severe pulse distortion and loss of energy. Reduction of fiber length is certainly one possible approach. This is, however, limited by the solubility of rare earth ions in the glass host and  $M^2$  value of the multimode pump lasers. The key to the nonlinear problem is therefore optical fibers with large effective mode area while maintaining robust single mode propagation. Such fiber is also required to deliver a single mode beam over distance to the work piece, an important practical attribute in many applications.

Conventional single mode fiber can, in theory, be adapted to provide very large effective mode area. In practice, such a waveguide is so weak that the optical fiber becomes very sensitive to its environment, notably bending effects. Single mode propagation in fibers with few modes was subsequently proposed (see U.S. Pat. No. 5,818,630 for example). The robustness of the single mode propagation can be maintained at reasonable levels in this case especially when care is given to ensure single mode launch, minimization of mode coupling and additional mode filtering. A combination of these techniques has lead to a demonstration of single mode propagation with a mode field diameter (MFD) of  $\sim 30 \mu\text{m}$  (A. Galvanauskas, "Mode-scalable fiber chirped pulse amplification systems", IEEE J. Sel. Top. Quantum Electron., 7, 504 (2001)). Repeated efforts have also been made in the last few years to provide a large effective area solution using the emerging photonic crystal fiber technology. A typical photonic crystal fiber has a regular array of hexagonally placed air holes surrounding a solid core. A photonic crystal fiber supports guided modes in a solid core by providing a composite cladding comprising air holes in a glass background, having a lower effective refractive index than that of the core. To reduce the number of modes in photonic crystal fibers, the state-of-art design employs small air holes with hole-diameter  $d$  to pitch  $A$  ratio of less than 0.1. In this regime, the photonic crystal fiber is very weakly guided leading to high environmental sensitivity. Robust single mode propagation in photonic crystal fibers has been limited to a mode field distribution (MFD) of  $\sim 28 \mu\text{m}$  (High-power air-clad large-

## 2

mode-area photonic crystal fiber laser in Optics Express, vol. 11, pp. 818-823, 2003), a similar level to that of conventional fiber. This is not surprising considering the similarity in principle of the two approaches. The progress towards fibers with large effective area is therefore relatively stagnant in the past 5-7 years, despite the significant progress in fiber lasers.

## SUMMARY

One embodiment of the invention comprises an optical fiber for propagating at least one lower order mode having a wavelength,  $\lambda$ , while limiting propagation of higher order modes having a wavelength,  $\lambda$ , by providing said higher order modes with a higher loss than said at least one lower order mode at said wavelength,  $\lambda$ , said optical fiber comprising: a first cladding region comprising one or more cladding features; and a core region surrounded by the said first cladding region, said cladding features configured to substantially confine propagation of said lower order modes to said core region, said core region having a width of at least about 20 micrometers, wherein said core region is configured to provide a loss for said higher order modes of at least about 0.5 dB.

Another embodiment of the invention comprises an optical fiber for propagating at least one lower order mode having a wavelength,  $\lambda$ , while limiting propagation of higher order modes having a wavelength,  $\lambda$ , by providing said higher order modes with a higher loss than said at least one lower order mode at said wavelength,  $\lambda$ , said optical fiber comprising: a first cladding region comprising one or more cladding features configured to form a partially enclosed region, said partially enclosed region having at least one opening therein formed by one or more spaces in said partially enclosed region, said one or more features having a maximum feature size,  $d$ , and a maximum bridge width,  $a$ , said maximum bridge width in part determining the size of said one or more spaces in said partially enclosed region; and a core region surrounded by the said first cladding region, said cladding features configured to substantially confine propagation of said lower order modes to said core region, wherein said maximum bridge width,  $a$ , and said maximum feature size,  $d$ , have respective values that yield a ratio of  $a/\lambda$  that is at least about 5 and a ratio of  $d/\lambda$ , that is at least about 10 thereby providing an increased effective core size, confinement of said at least one lower order mode, and reduction of said higher order modes.

Another embodiment of the invention comprises a waveguide rod for propagating at least one lower order mode having a wavelength,  $\lambda$ , while limiting propagation of higher order modes having a wavelength,  $\lambda$ , by providing said higher order modes with a higher loss than said at least one lower order mode at said wavelength,  $\lambda$ , said rod comprising: a body comprising material substantially optically transmissive of said wavelength, said body having a width and thickness larger than about  $250 \mu\text{m}$ ; a first cladding region in said body, said first cladding region comprising one or more cladding features configured to form a partially enclosed region, said partially enclosed region having at least one opening therein formed by one or more spaces in said partially enclosed region, said one or more features having a maximum feature size,  $d$ , and a maximum bridge width,  $a$ , said maximum bridge width in part determining the size of said one or more spaces in said partially enclosed region; and a core region in said body, said core region surrounded by the said first cladding region, said cladding features configured to substantially confine propagation of said at least one lower order mode to said core region, wherein said maximum bridge width,  $a$ , and said maximum feature size,  $d$ , have respective values that yield a



ratio of  $a/\lambda$  that is at least about 5 and a ratio of  $d/\lambda$  that is at least about 10 thereby providing an increased effective core size, confinement of said at least one lower order mode, and reduction said higher order modes.

Another embodiment of the invention comprises an optical rod for propagating at least one lower order mode having a wavelength,  $\lambda$ , while limiting propagation of higher order modes having a wavelength,  $\lambda$ , by providing said higher order modes with a higher loss than said at least one lower order mode at said wavelength,  $\lambda$ , said optical rod comprising: a first cladding region comprising one or more cladding features; and a core region surrounded by the said first cladding region, said cladding features configured to substantially confine propagation of said lower order modes to said core region, said core region having a width of at least about 20 micrometers, wherein said core region is configured to provide a loss for said higher order modes of at least about 0.5 dB.

Another embodiment of the invention comprises a hybrid rod structure comprising: a holey waveguide rod portion comprising at least one core region and at least one cladding region, said core region being bounded by air holes surrounding said core region, said air holes further located within the physical extent of said cladding region; and a non-waveguiding portion connected to said holey waveguide rod portion, said air holes extending along most of the length of the holey waveguide and terminating at the non-waveguiding rod portion.

Another embodiment of the invention comprises a holey waveguide rod, comprising: a ceramic or crystalline laser material; at least one core region in said ceramic or crystalline laser material, said core region being bounded by features surrounding said core region; and at least one cladding region in said ceramic or crystalline laser material, said features disposed within the physical extent of said cladding region.

Another embodiment of the invention comprises a holey waveguide rod, comprising: a ceramic or crystalline laser material; at least one core region in said ceramic or crystalline laser material, said core region being bounded by features surrounding said core region; and at least one cladding region in said ceramic or crystalline laser material, said features disposed within the physical extent of said cladding region.

Another embodiment of the invention comprises a method of manufacturing a holey waveguide rod amplifier, comprising: providing a ceramic or crystalline laser material; forming at least one air hole configured to form a core region in said ceramic or crystalline laser material, said core region being bounded by said at least one air hole, said at least one air hole comprising a cladding region in said ceramic or crystalline laser material.

Another embodiment of the invention comprises a waveguide rod amplifier, comprising: a rod having an outside lateral dimension of at least about 250  $\mu\text{m}$  across; at least one cladding region; and at least one doped core region having a numerical aperture less than about 0.04, said core region configured to receive a near diffraction-limited input signal and outputting an amplified near diffraction-limited output beam.

Another embodiment of the invention comprises an optical fiber for propagating at least one lower order modes having a wavelength,  $\lambda$ , while limiting propagation of higher order modes having a wavelength,  $\lambda$ , by providing said higher order modes with a higher loss than said at least one lower order mode at said wavelength,  $\lambda$ , said optical fiber comprising: a cladding; and a core, said core region having a width of at least about 20 micrometers, wherein said fiber is configured such that (i) the at least one lower order mode has no more

than 1.0 db of loss at a bending radius of at 30 centimeters and (ii) said higher order modes have a loss of at least 0.5 dB.

#### BRIEF DESCRIPTION OF DRAWINGS

FIGS. 1A and 1B are side and cross-sectional views schematically illustrating a fiber comprising a core region surrounded by a cladding region comprising a plurality of cladding features comprising air-holes in a hexagonal arrangement.

FIG. 1C is a plot of wavelength versus maximum feature size (normalized by center-to-center hole spacing) showing simulation results for different parameter regimes of operation for single mode propagation for in a fiber with 1 and 2 layers of holes in a hexagonal arrangement.

FIG. 2A is a photograph of a cross-section of a multimode holey fiber fabricated to support a single mode and suppress propagation of higher modes.

FIG. 2B illustrates the measured modal field distribution of the fabricated fiber shown in FIG. 2A and the modal field distribution obtained from simulations.

FIG. 3 is a plot showing the measured loss versus bending radius along two bending planes indicated in the inset, a performance feature of which is much improved compared with conventional large mode area fiber.

FIG. 4 is the plot of wavelength versus maximum hole size (normalized by center-to-center hole spacing) of FIG. 1A schematically showing the single mode operation regime with contour lines of constant bridge width  $a/\lambda$ .

FIG. 5A is a schematic diagram of a generalized fiber.

FIG. 5B is a cross-section of the fiber of FIG. 5A schematically illustrating a core 141 of the fiber 140 defined by features 142, a region 143 that surrounds 142 the features, a glass bridge width,  $a$ , defined as the minimum width of the glass region between the features, and feature size  $d$ , which is defined as the width of the feature facing the core.

FIGS. 6A, 6B, 6C, 6D, 6E and 6F illustrate alternative designs using non-circular feature shapes and arrangements.

FIG. 7A schematically illustrates a design for a polarization maintaining fiber comprising an asymmetrical core.

FIG. 7B schematically illustrates the incorporation of stress elements around the core to create a polarization maintaining fiber.

FIG. 7C is a schematic diagram showing stress elements used in combination with an asymmetrical core and elliptical features.

FIG. 7D schematically illustrates a polarization maintaining fiber design using circular features of varying size.

FIG. 7E schematically illustrates a polarization maintaining fiber design with stress elements in the core.

FIGS. 8A, 8B and 8C illustrate double clad structures for cladding pumped amplifiers and lasers.

FIG. 9 schematically illustrates fundamental mode excitation in the large mode area fiber using a taper at one end of the fiber to reduce the core size so that the fiber is better matched with a single mode or few-mode fiber. (As shown, a lens can also be used as an alternative to a splice).

FIG. 10 schematically illustrates a preferred arrangement where the fiber is coiled so that unwanted higher order modes can be further attenuated by the coils. (A straight section is maintained at the input end and at the exit end).

FIG. 11 schematically illustrates a large mode area fiber comprising a core doped with rare earth ions that is used as in a fiber amplifier or in a laser pumped by a multimode pump source.



## 5

FIG. 12 schematically illustrates an example of how the large mode area fiber can be used in high energy pulse amplification systems.

FIG. 13 schematically illustrates an example of using the large mode area fiber as a delivery fiber for a high power laser system to transport an optical beam to a work piece. (A local lens is used to focus the beam.)

FIG. 14A is a schematic illustration a configuration where a large core fiber is followed by a length of non-waveguiding fiber so that the guided beam can be substantially expanded through diffraction effect before it reaches the glass-air interface.

FIGS. 14B, 14C and 14D schematically illustrate a possible implementation of the design in FIG. 14A by collapsing air holes by heating a length of the fiber.

FIG. 14E schematically illustrates a first double clad fiber spliced to a second fiber having a single cladding.

FIG. 15A schematically illustrates a cross-section of an air-clad holey rod.

FIG. 15B schematically illustrates cross-section of a double clad step index rod.

FIG. 15C is a photograph of a single-clad holey rod.

FIG. 15D is a side view schematically illustrating a monolithic waveguide rod.

FIG. 15E schematically illustrates a cross-section of a waveguide slab comprising air holes.

FIG. 15F schematically illustrates an exemplary curvilinear waveguide.

FIG. 16 schematically illustrates a high power amplifier system comprising a fiber rod and a multimode (MM) pump source.

FIG. 17 schematically illustrates a high power amplifier system utilizing a fiber rod.

FIG. 18 schematically illustrates a cooling arrangement for a waveguide rod.

FIG. 19 schematically illustrates a generic cw laser configuration using an ultra-large mode rod.

FIG. 20A schematically illustrates a generic chirped pulse amplification system for femtosecond (fs) or picosecond (ps) pulses utilizing an ultra-large mode rod.

FIG. 20B schematically illustrates a generic amplification system for nanosecond (ns) pulses utilizing an ultra-large mode rod.

FIG. 21 schematically illustrates a generic Q-switched waveguide rod laser.

#### DETAILED DESCRIPTION OF SOME EMBODIMENTS

Various embodiments of the invention comprise optical waveguides such as large core multimode optical fiber. This multimode optical fiber comprises core and cladding regions. The fiber may comprise a matrix material with a plurality of holes formed therein. See FIGS. 1A and 1B. The plurality of holes are in the cladding region and provide confinement for the core region. The matrix material may comprise, for example, silica glass and the holes may be air holes.

The core may have a lateral dimension such as a width or diameter. Similarly, the optical fiber itself may have a cross-sectional dimension such as width or diameter as well. The holes may have a lateral dimension, e.g., a cross-sectional size or diameter,  $d$ , and an average center-to-center spacing,  $\Lambda$ . Additionally, the holes may be separated by bridges having a bridge width,  $a$ . These bridges may comprise the matrix material or material comprising the cladding region.

Large air holes aid in confinement of light in the core region and are particularly useful for reducing loss induced by bend-

## 6

ing of the fiber. The high contrast air/glass boundary of the large air holes effectively confines fundamental mode or lower order modes on a bend. Bending loss therefore can be effectively reduced by using larger holes. In some embodiments, for example, bending loss of lower order modes (e.g., 1, 3, 5, 10 modes) may be no more than about 1 dB at a bending radius of 30 centimeters or more. This leads to designs with smaller number of larger holes for the reduction of bending loss as discussed in further detail below.

In some embodiments, equivalent hole diameter-to-pitch ratio,  $d/\Lambda$ , may be larger than 0.4 in a structure with holes arranged in a triangular pattern. In other embodiments, the ratio of hole diameter to wavelength  $d/\lambda$  is at least or in excess of about 5. In certain embodiments, values of  $d/\lambda$  (where  $\lambda$  is the light wavelength in vacuum) vary between about 10 to 100 for core diameters up to about 100  $\mu\text{m}$ . The value of  $d/\lambda$  can be even larger (e.g., at least about 100) for larger core size (at least about 100  $\mu\text{m}$ ). Values outside these ranges, however, are possible.

Various embodiments comprise a large core multimode fiber with sufficient built-in mode-filtering to allow robust single mode propagation. Large gaps between the holes provide sufficient leakage channels for higher order modes, which is useful for maintaining single mode propagation.

In particular, the maximum width of the glass bridge,  $a$ , between the holes that define the core can be used as a design parameter for achieving stable single mode propagation. The value,  $a$ , can be normalized to the operating wavelength and the ratio  $a/\lambda$  can be used as a general measurement and design parameter. In one exemplary design to be described below having six circular holes,  $a/\lambda$  varies from about 5 to 40 when core size varies from about 25 to 100  $\mu\text{m}$  at an operating wavelength of  $\sim 1 \mu\text{m}$ , for example. For larger core size beyond about 100  $\mu\text{m}$  core diameter, for example, larger  $a/\lambda$ , (larger than about 100) can be used to create larger leakage channels for the higher order modes. Other values, for example, outside these ranges are possible.

The result of these design features is a fiber with a solid core surrounded by a few large air holes. A large core is provided that can handle high intensities with reduced nonlinearities and reduced damage. Bending loss can be effectively reduced by using larger holes. Larger bridges may be used to introduce leakage loss to suppress higher order modes. Various designs also reduce inter-modal coupling due to high leakage loss of the higher order modes, leading to much improved single mode propagation.

In various embodiments, hole diameter-over-wavelength ratio is excess of about 5. In certain fabricated designs,  $d/\lambda$ , as high as 60 are used leading to a much reduced bending loss. An effective mode area of 1417  $\mu\text{m}^2$ , an equivalent mode field distribution (MFD) of  $\sim 42.5 \mu\text{m}$ , has been demonstrated. Robust single mode propagation has been demonstrated. This technology is expected to have significant impact on the development of high power fiber lasers.

The dimension of the hole facing the fiber core is a particularly relevant dimension. Accordingly, features with larger aspect ratio, e.g. long ellipses, with the long dimension facing the core can be used instead of circular structure. Varying the shape of the hole can provide more flexibility in some designs.

Controlling the bridge width,  $a/\lambda$ , also allows the designer more flexibility in creating fiber designs especially when other constraints need to be considered. Non-circular holes, varying number of holes, non-regularly distributed holes can all be used in a design. In addition, different materials as well as different configurations may also be used as well.



Asymmetrical geometry, for example, either in distribution of holes or/and shape of holes can be used to create polarization maintaining fibers. Stress-inducing elements can be incorporated in holes in an asymmetrical fashion to create polarization maintaining effect as well.

The holes can, in general, be of any shape. Additionally, the holes may be filled with substantially optical transparent materials, for example, having refractive index lower than the rest of the matrix material (which may comprise, e.g., glass). The holes do not have to be uniform. The number of holes can be as low as one.

Rare earth ions, e.g. ytterbium and erbium, can be incorporated into the core to form an active medium. Accordingly, gain can be provided in a fiber when pumped with appropriate pump sources.

A pump guide can be further incorporated around the core region and the features used to define the core. A double clad design may be used. Pump energy can be injected into the pump guide to pump active ions in the doped core. This pump guide may comprise an additional layer around the core region and the features used to define the core. This additional layer may have an effective lower refractive index either by using, e.g., a low index polymer coating or air-hole structures comprising of mainly air and a small amount of glass in some embodiments discussed more fully below. In case of using air hole structures to form the pump cladding, an additional glass layer around the pump cladding may be used to provide structural support. A polymer coating may be used as the outermost layer to provide further protection.

A taper can be formed at one end of the large core to provide a fiber end which is either single mode or has fewer modes. This end having reduced size can be used for either splicing to a single-mode or few-mode fiber or launching light into the fiber. Stable excitation of fundamental mode in the large core fiber can readily be achieved using this type of taper.

The field distribution in a mode in the large core fiber can be modified by bends even when minimum power loss occurs. This effect is due to a combination of weak guidance in the large core and larger stress-induced refractive index change over the much larger core. The optical waveguide is sufficiently modified by bends, which leads to a change in mode field distribution. In various preferred embodiments, however, when the large core fiber is used, both the launching end and exit end are straight to achieve better excitation of the fundamental mode and a desirable output mode profile.

One application of the large mode area fiber is for high power laser delivery. The much reduced nonlinear effect in the large core fiber allows much higher power to be carried by the fiber. The large mode area fiber can also be potentially used as a compressor in a high energy chirped pulse amplification system, where optical pulses are chirped, reducing their peak power in amplifiers, before being compressed back to their original pulse width. This compressor function can also be integrated into an amplifier and/or delivery fiber for some applications. The low nonlinearity of the fiber also allows this large core fiber to support low order solitons with much higher peak power. This feature can be useful in some applications. Accordingly, in some embodiments, the fiber may be coupled to a source of solitons.

In addition to higher order mode filtering, reduction of inter-mode coupling also improves robust single mode propagation in a large core waveguide thereby reducing or minimizing power transfer from the fundamental mode to higher order modes. Increasing the fiber diameter reduces the mode-couplings, which in turn also allows the core diameter in the fiber to be increased (see, e.g., U.S. Pat. No. 5,818,630). In the

extreme case fiber rods are so obtained. Such fiber rods also reduce or minimize mode coupling due to a reduction of micro-bending. Such rod have enough rigidity to maintain their physical shapes. Rods can be deployed in a straight configuration and alternatively, fixed bent configurations when appropriate. Recently, such fiber rods were described by N. Deguil-Robin et al. in "Rod-type fiber laser", Advanced Solid State Photonics, 2005. The fiber rod concept was further developed by Limpert et al., in "High-power Q-switched ytterbium-doped photonic crystal fiber laser producing sub-10 ns pulses" Conf. on Advanced Solid State Photonics, paper PD-1, Vienna (2005).

The design of optimized multi-mode ultra large-core fiber structures may permit near diffraction limited outputs. Suppression of higher order modes may be particularly useful in producing near diffraction limited outputs. These multi-mode ultra large-core fibers may have core diameters, for example, of at least about 15  $\mu\text{m}$  and outside diameters at least about 200  $\mu\text{m}$  to reduce or minimize mode-coupling. Such ultra large core fiber structures can resemble rod structures that are sufficiently rigid so as not allow for any significant bending or coiling (unless pre-bent). Fiber structures based on conventional step-index as well as holey fiber designs can be implemented.

Both step-index as well as holey fiber designs can further incorporate doped core regions to facilitate their use as optical amplifiers or lasers. By incorporating a double cladding into the ultra large core fiber amplifier and laser structures, cladding pumping e.g., with semiconductor laser diode arrays is possible. Alternatively, pump light can be directly coupled into the core region of the ultra large core fiber structure.

The reduction of mode-coupling in such ultra large-core fiber structures further allows direct core pumping with multi-mode laser beams while preserving a near diffraction limited output for the amplified laser mode.

For the specific case of high energy ytterbium amplifiers, multi-mode pump sources based on Nd or also Yb fiber lasers can be implemented. Alternatively, a frequency doubled Tm fiber laser can also be used for core-pumping of an ultra large-core Yb fiber laser. Other configurations and designs are also possible.

Moreover, ultra large-core fiber structures can be combined with taper structures (e.g., at the pump end) to further increase the output peak power from these systems. The taper structures are preferably pumped with near-diffraction limited pump beams, though conventional low brightness pump sources can also be implemented. Alternatively taper structures can also be used to simplify input coupling into these large mode fibers.

Ultra large mode fiber rods can also be designed to follow curvilinear paths to reduce or minimize actual storage space for such structures. Such curvilinear paths can be obtained by gently heating sections of the fiber rod and bending it into a desired shape. Fiber rods formed into curvilinear shapes further allow for the introduction of differential losses between the fundamental and higher order modes.

The construction of laser systems based on three level transitions is further facilitated by the implementation of multi-mode holey or conventional step-index fibers based on ultra-large cores. In case there is competition between three and four energy level systems such as in ytterbium doped fibers, the four-level system often lases first at longer wavelength due to the low inversion required. This is especially true for long ytterbium-doped fiber length, where any emission at the shorter wavelength of the three energy level system is absorbed to pump the four energy system. In a double clad fiber with a large core, where pump can be absorbed over a



short length, a shorter ytterbium-doped fiber can be used and facilitates the laser action from the three energy system. These laser systems may, for example, be used as pump sources for ultra-large core fiber amplifiers and fiber tapers.

Ultra-large core fibers and rods further allow the amplification of ultra-short pulses via the chirped pulse amplification techniques. Ultra-large core fibers and rods also allow Q-switched operation as well as frequency conversion to the UV and IR. Such pulse sources, for example, can generate peak powers of at least about 1 MW and pulse energies of several mJ for pulses with a width of only about 1 ns.

Further the construction of holey large mode waveguides is not limited to fiber materials, holey large mode waveguides can also be constructed in ceramics, plastics and crystalline materials. In some embodiments, these structures are uniformly doped and can be directly core pumped or cladding pumped. Waveguide rods or slabs allow extraction of much larger gains from active materials compared to standard laser rod technology. Undoped waveguide structures based on ceramics, plastics and crystalline materials can also be envisioned.

As used herein, single mode and multimode fiber are defined consistently with the definitions used for traditional non-hole fiber. For traditional fibers, single mode and multimode fiber are generally defined in terms of V number, which is equal to  $\pi$  (numerical aperture) (core diameter)/wavelength for step index fibers. For non-step index fibers, numerical aperture and core diameter can be calculated with the equivalent values for step index fibers [see, e.g., Martinez, F., Husey, C. D., "(E)ESI determination from mode-field diameter and refractive index profile measurements on single-mode fibres" IEEE Proceedings V135, pp. 202-210, (1988)]. For fibers satisfying the relationship  $V < 2.4$ , the power of the fundamental mode is significantly larger than the optical power of the next higher mode. Alternatively, for fibers wherein  $V > 2.4$ , at least the next mode above the fundamental mode can have significant power in comparison to the fundamental mode. Single mode and multimode traditional fibers are accordingly specifically defined by the relationships  $V < 2.4$  and  $V > 2.4$ , respectively.  $V = 2.4$  is the cut-off for the propagation of any mode but the lowest order mode.

In holey fibers, the numerical aperture can be found by the difference in refractive index of core and cladding. However, a core diameter that is the equivalent value for step index fibers is difficult to calculate. Various references [see, e.g., (1) Knight et al, "Properties of photonic crystal fiber and the effective index model" J. Opt. Soc. Am. A Vol. 15, pp. 748-752, (1998), and (2) Mortensen et al "Modal cutoff and the V parameter in photonic crystal fibers" Opt. Lett. Vol. 28, pp. 1879-1881, (2003)] report that if the core diameter is made equal to the pitch or the distance between holes,  $\Lambda$ , then the V for cut off for the propagation of any mode other than the single mode is 2.5 (see, e.g., Knight et al) and  $\pi$  (see, e.g., Mortensen et al). For the various embodiments described herein, whether the V cut-off is 2.405, 2.5 or  $\pi$  is not critical. Various embodiments of holey fiber described herein have a much larger core radius than possible with conventional optical fiber that supports propagation of a single optical mode. Therefore, we will utilize the recent research in this technical area where multimode fiber is defined as where  $V > \pi$  and the core diameter is made equal to the pitch or average pitch to the fiber. Conversely, single mode fiber is defined herein as fiber where  $V < \pi$ .

As described above, holey fiber may be designed to introduce loss for specific modes. The hole size, bridge, and the number of holes may, for example, be selected to induce loss in the propagation of higher order modes in a multimode fiber

where  $V > \pi$ . With a decrease of the number of holes, light in the higher order modes may not be confined to the core and may escape from the fiber. Such loss introduced into multimode fiber  $V > \pi$  is analogous to traditional non-hole multimode fiber having a V number larger than  $\pi$  that include mode filtering provided, for example, by bending the fiber to introduce loss in the propagation of higher order modes. (Mode filters are described in, e.g., U.S. Pat. No. 5,818,630 issued to Fermann et al on Oct. 6, 1998 and entitled "Single-mode Amplifier and Compressors Based on Multi-mode Fibers," which is hereby incorporated herein by reference.) Sufficient bending can be applied to induce losses for each of the modes higher than the fundamental mode such that the fundamental mode is the sole mode that propagates through the bent multimode fiber. Similarly, multimode holey fiber having a V number larger than about  $\pi$  may have a design that introduces loss to higher order modes so that propagation of these higher order modes is attenuated. See, e.g., U.S. patent application Ser. No. 10/844,943 filed May 13, 2004 and entitled "Large Core Holey Fibers" (Attorney Docket No. IMRAA.024A), which is incorporated herein in its entirety.

In various designs discussed below, therefore the maximum size of the cladding features, e.g., air holes, the maximum bridge width, the number of layers (e.g., 1 or 2), may be such that only a few (e.g., 3, 5, 10) lower order modes, or even only a single mode propagates without much loss while higher order modes propagate with much greater loss.

FIGS. 1A and 1B schematically illustrate one embodiment of a holey fiber 500. A cross-section of the fiber shown in FIG. 1A is presented in FIG. 1B where different parameters are defined. As shown, d is hole diameter and  $\Lambda$  is center-to-center hole spacing. Core radius,  $\rho$ , is the distance from the center to the nearest hole-boundary. The values can be normalized to wavelength,  $\lambda$ , the wavelength of light in vacuum.

FIG. 1C is a plot of wavelength versus maximum feature size that illustrates simulation results for different parameter regimes of operation for single mode propagation labeled 502 and 501 for a holey fiber such as shown in FIGS. 1A and 1B with 1 and 2 layers of holes in a hexagonal arrangement. The upper boundaries 503 and 505 of 501 and 502 in FIG. 1C are determined by maximum tolerable loss of the fundamental mode and the lower boundaries 504 and 506 by minimum propagation loss of the second order modes. The plot in FIG. 1C shows that with a reduction of the number of holes from 2 layers to 1 layer,  $d/\Lambda$  moves towards large values for the same core size. The contour lines of constant core diameter  $2\rho$  are shown in lines 507, 508 and 509 for core diameter of 25, 50 and 100  $\mu\text{m}$  respectively. FIG. 1C is computed for straight fibers. For bent fibers as it may be in a practical case, the operation regimes 501 and 502 are moved towards larger  $d/\Lambda$ . In FIG. 1C, 1OM refers to fundamental mode and 2OM second order mode. Core size refers to core diameter  $2\rho$  and equals to  $2\Lambda - d$  in the hexagonal case illustrated in FIG. 1B.

FIG. 2A is a photograph of an exemplary fiber 510 fabricated and tested. In particular, FIG. 2B, 511 shows the measured modal field distribution of the fabricated fiber 510. Also shown in the respective modal field distribution 512 calculated from a model of the fiber 510 shown in FIG. 2A. FIG. 2B also provides a plot 513 and curve 514 that show the measured field profile through the center of the mode along the respective y and x axes, which are delineated in FIG. 2A. FIG. 2B also provides a plot 515 and curve 516 shows the respective modeled field profile. Single mode operation is clearly demonstrated by the distributions. This fiber 510 supports single mode propagation with a measured effective modal area of about 1400  $\mu\text{m}^2$ , which is obtained from taking appropriate integration of the measured mode field distribution in 511.



## 11

FIG. 3 illustrates the measured loss versus bending radius along two bending planes that are indicated in the inset. The bend loss of the fiber was measured by winding the fiber on mandrels of known diameters. Since the cross-section of the fiber lacks rotational symmetry, the dependence of the bend loss on the orientation of the bending plane was investigated. Specifically, as shown in the inset of FIG. 3, a bending plane AA that intersects with two smaller holes is defined. Similarly a bending plane BB that intersects with two thin glass ridges is also defined. The output of the fiber is imaged onto a video camera with an aspheric lens. By monitoring the output beam profile, single mode propagation can be ensured throughout the measurement. The amount of bend loss in decibel per meter is plotted in FIG. 3 as a function of the bend radius in centimeters. Bending along the plane AA introduces less loss in the fiber as compared to bending along the plane BB, which can be explained by the presence of the two small holes helping to better confine the mode. As can be seen in FIG. 3, the amount of bend loss in decibels per unit length as a function of bend radius follows the same functional dependence

$$\left[ = \frac{\alpha}{\sqrt{R_{bend}}} \exp(-\beta R_{bend}) \right]$$

that was developed for conventional optical fibers, where  $R_{bend}$  is the bend radius. The fitting parameters are  $\alpha=3755$  dB·cm<sup>0.5</sup>/m,  $\beta=1.258$  1/cm for bending along the plane AA, and  $\alpha=2.265 \times 10^4$  dB·cm<sup>0.5</sup>/m,  $\beta=1.460$  1/cm for bending along the plane BB.

FIG. 4 shows the same single mode operation regimes plotted in FIG. 1C further including contour lines of constant bridge width,  $a/\lambda$ . Operation regimes 121 and 120 are enclosed by boundaries 124, 125 and 122, 123 are for 1 layer and 2 layers of holes respectively. The contour lines 130, 131, 132, 133, 134 and 135 of constant bridge width are respectively for bridge widths,  $a/\lambda=1, 2, 4, 10, 20$  and 40. For core diameter from about 25 to 100  $\mu\text{m}$ ,  $a/\lambda$  varies from about 5 to 40.

FIGS. 5A and 5B illustrate a generic fiber 140. A Core 141 in fiber 140 is defined by features 142 in a cladding region. Region 143 further surrounds the features 142 in the cladding region. Glass bridge width,  $a$ , is defined as the minimum width of the glass region between holes. Feature size  $d$  is defined as the width of the feature.

FIGS. 6A, 6B, 6C, 6D, 6E, and 6F illustrate alternative designs using non-circular features in various arrangements. FIG. 6A shows a plurality of elliptical holes 151 in a circular arrangement that define a central core region 150. The holes 151 are formed in a matrix material 152. FIG. 6B shows a plurality of differently shaped holes 155 in an irregular arrangement that define a central core region 154. The holes 155 are formed in a matrix material 156. FIG. 6C shows circular holes 158 arranged in a non-circular pattern that define a central core region 157. The holes 158 are formed in a matrix material 159. As used herein, features may comprise holes that include air or are evacuated and, hence, contain vacuum. Additionally, these holes may be filled with another material, for example, different material than the matrix material to form the features. FIGS. 6D, 6E and 6F further described how  $a$  and  $d$  are defined in various designs. The fibers FIGS. 6D and 6E have a pair of holes while the fiber in FIG. 6F has a single hole.

FIG. 7A illustrates a design for a polarization maintaining fiber. Elliptical features 162 surround a generally elliptical or

## 12

rectangular core 161. The use of long ellipses enhances the level of birefringence and reduces bending loss. The features are in a matrix material 163 which surrounds the features. In FIG. 7B, stress elements 164 are used around the core 165 to create a polarization maintaining fiber. The core 165 is further defined by additional features 166. In FIG. 7C, stress elements 168 are used in combination with an asymmetrical core 167 and elliptical features 169. FIG. 7D illustrates a polarization maintaining fiber design with circular features. Two of the features aligned along a plane are reduced in size to provide asymmetry for maintaining polarization. FIG. 7E illustrates a fiber design 400 where stress elements 414 and 415 are introduced in the core 401 defined by six circular features 403 in a hexagonal arrangement. The fiber 400 can be a double clad design by introducing a low refractive index pump cladding 404 surrounding the pump guide 402. An outer layer 405 is also provided.

FIGS. 8A and 8B illustrate a double clad structure for cladding pumped amplifiers and lasers. FIG. 8A illustrates a core 170 defined by the features 171 defining an inner cladding, which is in turn surrounded by outer cladding 172. Pump cladding 173 is a material with a lower refractive index, for example, a polymer coating. However, a second glass with lower refractive index can also be used. FIG. 8B shows another double clad fiber comprising a core 174, which is defined by features 175 defining an inner cladding, and a surrounding outer cladding 176. In FIG. 8B, a pump cladding 177 comprising air holes and thin glass bridges (not shown) is used. A further glass region 178 surrounds the pump cladding 177 to provide mechanical support. Although not shown, thin glass bridges connect the outer cladding region 176 and the glass region 178. A polymer coating surrounding glass region 178, not shown in FIG. 8B, may be also applied to a fiber. In FIG. 8C, the pump cladding 179 is shown to be a rectangular shape. In fact, this pump cladding can take any shape around the pump guide. Accordingly, other configurations are possible.

FIG. 9 illustrates two exemplary configurations for fundamental mode excitation in the large mode area fiber 180. In the first configuration, a taper is made at one end of fiber 180 to reduce its core size so that it is better matched with a single mode or few-mode fiber 181. Light coming from the single mode or few-mode fiber 181 excites substantially only the fundamental mode in the large mode area fiber if good mode matching between the two fibers is achieved with the taper. In a second configuration shown in FIG. 9, a lens 183 is used to launch the fundamental mode into the fiber 180 through the taper 182 as an alternative to a splice.

FIG. 10 illustrates an exemplary arrangement where the fiber is coiled 190 so that any unwanted higher order modes can be further attenuated by the coils. A straight section 191 is maintained at the input end. A straight section 192 is also maintained at the exit end. Modal field distribution can be distorted on bends in the large mode area fiber due to weak guidance and relatively stronger stress-induced refractive index change. The straight sections ensure better coupling into the fundamental mode and thus better launching of a fundamental mode as well as good output mode profile. A lens 193 is shown coupling light into the straight section of the fiber at the input end. The coil 190 can also be used to maintain polarization along the fiber. The birefringence is due to stress optics effects as a result of asymmetry in bend-induced stress. This bend-induced stress is larger in a large core fiber.

FIG. 11 shows a large mode area fiber 200 with a core doped with rare earth ions used in a fiber amplifier or a laser pumped by a multimode pump source. The fiber has straight



## 13

input and output ends **201**, **202** and a coiled section therebetween. A multimode pump **205** is used to pump the amplifier or laser using a coupling lens **204**. Input beam **206** is launched into fiber **200** through a lens **203**. Output **207** is separated by dichroic mirror **208**.

FIG. **12** illustrates an example of how the large mode area fiber can be used in high energy pulse amplification system. Optical pulse from a seed source **210** is stretched in the pulse stretched **211**. Pulse picker **212** reduces the pulse repetition rate. A large core amplifier **213** comprising the large mode area fiber amplifies the pulse and the pulse is then compressed using a pulse compressor **214** close to its original width in output beam **215**.

FIG. **13** illustrates an example of use of the large mode area fiber as a delivery fiber **221** for high power laser system **220** to transport optical beam **222** to work piece **224**. A local lens **223** is used to focus the beam **222**. A positioning system may be used to position the output beam with respect to the work piece. This positioning system may comprise a translation stage, for example, on which the work piece is disposed. Movable optics such as a movable mirror or lens may be used. Other configurations and designs are also possible.

In FIG. **14A**, a fiber **240** comprises a first length comprising a core formed by cladding **241**, followed by a second length without a core. A beam **242** propagates from the first length to the second length where the beam expands in size due to diffraction. The beam **242** is substantially expanded when the beam reaches the fiber end where damage threshold is low. This can prevent end face damage at the output end of an amplifier where power is the highest.

The configuration of FIG. **14A** can also be implemented by splicing the large core fiber with another coreless fiber. This approach is especially useful when the length for expanding the beam **242** is long (e.g., from several centimeters to tens of centimeters long).

FIGS. **14B**, **14C** and **14D** illustrate an implementation of the fiber structure of FIG. **14A**. A fusion splicer was used to collapse holes along a length of the fiber to form the coreless section. FIG. **14B** shows a cross-section of the first length where the holes are present and FIG. **14D** a cross-section of the second length where the holes are collapsed and not thus present.

The first double clad fiber **600** in FIG. **14E** comprises a first cladding **602**, defining a core and a second cladding **603**, defining a pump guide. The first fiber **600** is then spliced to a second fiber **601**. The second fiber **601** has a single cladding **604**, which has a dimension close to that of second cladding **603** in first fiber **600**. The second fiber **601** can be used to expand a beam **605** and may also be used for pump power (not shown in FIG. **14E**) to be launched into second fiber **601**.

As described above, in various preferred embodiments the size of the fiber is large such that the fiber effectively becomes a rod that is rigid. FIG. **15A** comprises an exemplary holey fiber design **250** such as discussed above. The various designs and concepts described herein with reference to fibers are also applicable to rods.

In FIG. **15**, the holey fiber or rod **250** comprises a core region **251** which is preferably index matched to the cladding region **252**. The core region **251** can also have other another index, such as a refractive index lower than cladding region **252**. In various preferred embodiments, the core region **251** is further doped with rare-earth ions such as Yb, Nd, Er or Tm to provide gain. Appropriate glass-forming dopants such as B or F are added to the glass to obtain a doped core area index matched (or with a depressed refractive index compared) to the cladding area **252**. Inside of cladding **252**, a set of air-holes **253** are arranged that define the core region **251**. As

## 14

discussed above, the separation of the center of the air-holes  $\Lambda$  may be close to the diameter of the air-holes  $d$ , e.g.,  $d/\Lambda > 0.4$  to obtain an improved or optimum mode-quality for the fundamental mode. However, other values, for example, ratios of  $d/\Lambda < 0.4$  can also be used. In various preferred embodiments, the fiber can support more than two core modes. Moreover, it can also be desirable to add additional holes to the cladding region **252** to reduce the cladding area. The glass ridges between the air-holes can be at least a few wavelengths in width, i.e. in the range of 5-100  $\mu\text{m}$ , such that pump light from the cladding region **252** penetrates into the core region **251**. Air-cladding region **254** surrounds cladding region **252**. As discussed above, the air-cladding region can comprise an array of very thin glass ridges that are arranged around cladding region **252** and connect to outside cladding region **255**. Cladding region **254** may be designed with a low effective index correspondingly producing a large acceptance angle (or numerical aperture NA) for pump light coupled into cladding region **252**. In various preferred embodiments, the outside diameter of fiber **250** is at least about 250  $\mu\text{m}$  to reduce or minimize mode-coupling.

A simpler fiber rod structure **260** based on a more conventional fiber geometry is shown in FIG. **15B**. The fiber rod **260** in FIG. **15B** comprises a standard rare-earth-doped step-index core gain region **261** and a cladding region **262**. To confine pump light in cladding region **262**, a low index region **263** is further added. Since fiber rods are generally kept straight and mode-coupling is substantially reduced or minimized with a large outside fiber diameter, core NAs in the range from 0.01-0.05 can still be effectively used in the present example. Refractive index variations in the core region are kept to a minimum in various preferred embodiments. To provide a large index difference between cladding regions **262** and **263**, multi-component glasses such as Ta or Sb-doped silica glasses can be used. Such glasses are discussed in Dejneka et al., U.S. Pat. No. 6,836,607. Using such multi-component glasses an effective NA for the pump guiding region of about 0.40 or higher can be obtained.

Hybrid forms of the designs shown in FIG. **15A** and FIG. **15B** can also be employed for ultra large mode fiber rods. For example, an air-cladding **265** can be incorporated into cladding area **262** for the construction of an air-clad conventional step-index fiber.

A photograph of a cross-section of a fiber rod manufactured according to the design principles discussed above is shown in FIG. **15C**. This exemplary fiber rod has a core diameter of 58  $\mu\text{m}$  and a cladding diameter of 270  $\mu\text{m}$ . The air-holes have a diameter of around 40-46  $\mu\text{m}$ . No air-cladding **254** was incorporated. With appropriate launching conditions a fundamental mode with a mode-field diameter of 42  $\mu\text{m}$  could be coupled into this fiber. The fiber was manufactured with the stack and draw technique. Note that this rod further includes holes of different diameter (namely 40 and 46  $\mu\text{m}$ ) along two axes of the fiber so as to induce a degree of form birefringence into the structure. Note that birefringence can further be introduced into the fiber by coiling, allowing for polarization maintaining operation.

The various designs discussed in connection with FIGS. **15A-15C** can be utilized in the rod **101** used in the amplifier and laser systems shown in FIGS. **16**, **17**, and **19**, which will be discussed in more detailed below.

As an example, consider the amplifier system **100** depicted in FIG. **17**. In this system **100** the fiber rod amplifier **101** is connected and preferably fused to a rod amplifier **102**. Fiber rod **101** is constructed with a double clad structure, comprising an outside cladding **103**, an inner cladding **104** and a rare-earth doped core region **105**. In certain embodiments, the



## 15

inner and outside cladding are not doped, though doped cladding structures can also be implemented. The rod structure **102** comprises an unpumped region **106** and a pumped region **107**. This rod structure **102** can be uniformly doped with a gain medium just like a conventional laser rod. Amplifier rods **101** and **102** are pumped with pump sources **108** and **109**, respectively. In certain preferred embodiments, pump source **108** is multi-mode and pump source **109** is single-mode. However, efficient amplifiers can also be constructed based on a single-mode pump source **108**; equally pump source **109** can also be multi-mode.

Appropriate pump sources can be based on near diffraction limited or multi-mode fiber or solid state lasers, as well as beam-shaped semiconductor lasers. Such beam-shaped semiconductor lasers are described, e.g., in U.S. Pat. No. 6,778,732 issued to Fermann et al. Two lenses are used to couple the pump sources into the rod amplifier structures **101** and **102**. Single lenses are shown only for simplicity. More generally, appropriate lens systems can be used for pump coupling. Dichroic beam splitters **110** and **111** are used to combine/separate the pump sources with the input and output signals **112**, **114**, respectively. The input signal **112** is preferably near diffraction limited and injected into fiber rod structure **101**. The direction of the pump light from pump source **109** is denoted with arrow **113**. The output **114** from the whole amplifier system is also denoted with a larger arrow.

A direct comparison can be made with the features of the rod depicted in FIG. 15A and the rod shown in FIG. 17. For example, core region **251** corresponds to core region **105**; cladding region **252** corresponds to cladding region **104** and cladding region **254** corresponds to cladding region **103**. A separate outside cladding region **255** was not shown in FIG. 17. The simple design shown FIG. 15B also has its exact equivalence in the design of fiber rod **101** as shown in FIG. 17.

Optionally, fiber **101** in FIG. 17 (as well as in FIGS. 16 and 19, discussed more fully below) can be surrounded with a polymer jacket or it can be metalized and fixed to a heat sink for efficient thermal heat dissipation. In various preferred embodiments, the air-holes inside fiber **101** are thermally collapsed at the signal input end to avoid end face contamination and to reduce or minimize damage to the structure. Additionally, the signal input end of fiber rod **101** can be tapered down to a smaller diameter to enable single-mode propagation and to facilitate excitation of the fundamental mode in fiber rod **101**.

Several specific examples of different fiber designs and rod designs are presented below.

## FIBER DESIGN EXAMPLE 1

This design includes six air holes arranged in a hexagonal shape as illustrated in FIG. 1A. The center-to-center spacing,  $\Lambda$ , is 40  $\mu\text{m}$ , the hole size 30  $\mu\text{m}$ , yields a core diameter  $2\rho$  of 50  $\mu\text{m}$  for operation at  $\sim 1$   $\mu\text{m}$  wavelength. The bridge width  $a/\lambda$  is 10 and the normalized hole size,  $d/\lambda$ , 30.

## FIBER DESIGN EXAMPLE 2

This design includes six air holes arranged in a hexagonal shape as illustrated in FIG. 1A. The center-to-center spacing,  $\Lambda$ , is 80  $\mu\text{m}$ , the hole size 60  $\mu\text{m}$ , yields a core diameter  $2\rho$  of 100  $\mu\text{m}$  for operation at  $\sim 1$   $\mu\text{m}$  wavelength. The bridge width  $a/\lambda$  is 20 and the normalized hole size,  $d/\lambda$ , 60.

## FIBER DESIGN EXAMPLE 3

This design includes six air holes arranged in a hexagonal shape as illustrated in FIG. 1A. The center-to-center spacing,

## 16

$\Lambda$ , is 160  $\mu\text{m}$ , the hole size 120  $\mu\text{m}$ , yields a core diameter  $2\rho$  of 200  $\mu\text{m}$  for operation at  $\sim 1$   $\mu\text{m}$  wavelength. The bridge width  $a/\lambda$  is 40 and the normalized hole size,  $d/\lambda$ , 120.

## FIBER DESIGN EXAMPLE 4

This design includes six air holes arranged in a hexagonal shape as illustrated in FIG. 1A. The center-to-center spacing,  $\Lambda$ , is 40  $\mu\text{m}$ , the hole size 30  $\mu\text{m}$ , yields a core diameter  $2\rho$  of 50  $\mu\text{m}$  for operation at  $\sim 1$   $\mu\text{m}$  wavelength. The bridge width  $a/\lambda$  is 10 and the normalized hole size,  $d/\lambda$ , 30. Two stress elements comprising boron-doped silica are incorporated in two diagonally opposing air holes to produce a polarization maintaining fiber.

For all the design examples describe herein, the actual fiber cross-sections are usually different from performs due to viscous flow during the fiber drawing process in cases performs are made according to the designs. Frequently, fiber preforms are slightly modified from designs to conform any practical constraints. Also, other sizes and materials may be used. For example, glass other than fused silica, e.g. phosphate, fluoride, telluride, lead silicate, etc., can be used. In fact, phosphate glass may allow higher rare earth doping levels. As discussed above, the air holes can be replaced by one or more materials, for example, glass with lower effective indexes in all design examples. Rare earth ions or a combination of rare earth ions, such as ytterbium, erbium, thulium, neodymium, etc., can be doped in the core region to provide gain. Double clad structure can also be implemented to provide an outer pump guide such as depicted in FIG. 8. Other dimensions and configurations can also be used.

## ROD DESIGN EXAMPLE 1

This design comprise a structure similar to that shown in FIG. 15A. The rod can be constructed from silica glass providing core absorption of 600 dB/m at a wavelength of 980 nm, corresponding to an ytterbium doping level of around 1 weight %. The air-holes can have a diameter of 40  $\mu\text{m}$  and the core diameter (defined as the closest separation between opposite air-holes) can be 50  $\mu\text{m}$ . The inner diameter or air-cladding **254** can have a diameter of 150  $\mu\text{m}$ . The outside diameter can be anywhere in the range from about 250  $\mu\text{m}$  to about 10 mm or even higher. The NA of the air-cladding can be 0.6. Hence a high average cladding absorption of 65 dB/m at a wavelength of 980 nm can be achieved. The main reason for the improvement in cladding absorption is the improved core design of the structure.

## ROD DESIGN EXAMPLE 2

This design comprise a structure similar to that shown in FIG. 15B. Again the rod can be constructed from silica glass providing a core absorption of 600 dB/m at a wavelength of 980 nm. The core diameter can be 50  $\mu\text{m}$  and the inner diameter or the air-cladding **264** can have a diameter of 150  $\mu\text{m}$ . The core NA can be 0.04 and the NA of the air-cladding can be 0.6. Again an average cladding absorption of 65 dB/m at a wavelength of 980 nm can be achieved. An outside fiber diameter of about 250  $\mu\text{m}$  to about 10 mm and larger can be used.

With currently available pump sources, up to about 100 W can be coupled into the above two fiber structures, enabling the generation of amplified average powers at least about 50 W for fiber length less than about 50 cm. Gains of about 30 dB or higher can further be achieved from such fiber structures in lengths less than about 50 cm.



Using such rods in a short pulse amplification system, for an effective mode diameter of about 50  $\mu\text{m}$ , 1 ns long pulses with a pulse energy up to 2.5 mJ can be generated, limited by the bulk damage threshold of silica.

Even higher pulse energies can be generated by using rod-section **102** in FIG. **17**. Mode-expansion in rod-section **102** is governed by diffraction. For a mode diameter,  $\omega$ , of about 50  $\mu\text{m}$ , the Rayleigh range  $R$  can be defined over which diffraction leads to a mode expansion by a factor of  $\sqrt{2}$  as  $R = n\pi\omega^2/2\lambda$ , where  $n$  is the refractive index,  $\lambda$  is the operation wavelength and  $w$  is defined as the diameter between the points where the mode intensity is reduced by a factor of  $1/e$  compared to the intensity at the center of the mode. For a mode diameter,  $\omega$ , of about 50  $\mu\text{m}$  and  $n=1.5$  (for silica glass) at a wavelength of  $\lambda=1 \mu\text{m}$ , the Rayleigh range,  $R$ , is about 6 mm. Ensuring optimum mode overlap between pump source **109** and the output from fiber rod **101**, an increase in mode size by a factor of 4 (from about 50 to 200  $\mu\text{m}$ ) can be obtained in a doped rod **102** of 24 mm length. For a fully inverted rod gain medium **102** made from the same core material as fiber rod **101**, a gain of 2 dB/cm can be achieved at the peak of the ytterbium gain band at 1030 nm. Thus, a 24 mm length rod can increase the maximum pulse energy by around 5 dB. When a high power single mode (SM) pump source **107** is available, the same pump source can be used to pump rod **102** and fiber rod **101**.

An even better situation can be obtained when using a fiber rod with a 100  $\mu\text{m}$  core diameter. In this case, a 42 mm long rod is used to obtain a mode-size of 200  $\mu\text{m}$ . Hence, a gain of 8 dB can be obtained in rod **102**. Eventually, the achievable gain in rod **102** is limited by thermal lensing. However, appropriate designs of fiber rod **101** and rod **102** can ensure a reduced or minimal of mode distortions even for high gain values in rod **102**. Moreover, the thermal lens can itself be used to provide a degree of waveguiding. In addition, gain-guiding effects as discussed in Fermann et al., '630 can be used to improve the mode quality at the output of fiber rod **102**. To minimize thermal distortions due to end effects in rod **102**, an additional undoped rod (not shown) can be fused to the output end rod **102**.

The fiber rod/rod combination may benefit from efficient external convective or conductive cooling. Conductive cooling may provide higher heat dissipation. A possible conductive cooling arrangement is shown in FIG. **18**. Here structure **300** comprises the fiber rod/rod combination **301**, which can be soldered into metal holder **302** in certain embodiments. Metal holder **302** is cooled by 4 water channels **303**, **304**, **305**, **306** arranged centro-symmetrically around rod **301**. More or less water channels can be used. A uniform a temperature profile can be obtained by proper designs. Other configurations are possible.

The use of rod **102** in FIG. **17** for maximization of available pulse energies is purely optional and fiber rod **101** can be used by itself to generate high pulse energies such as shown in FIG. **16** discussed more fully below. When using fiber rod **101** (without rod **102**), small angles (not shown) can be introduced at the fiber ends to avoid parasitic reflections in such structures. Small undoped rods can be fused to fiber rod **101** as end-caps to enable mode-expansion and to increase or maximize the damage threshold of the fiber rod ends.

The achievable gain per unit length in rod **102** can further be optimized by the use of multi-components glasses, such as Bi- or phosphate glasses, ceramic or crystalline materials such as Yb:Y<sub>2</sub>O<sub>3</sub> or Nd:YAG respectively, which can be fused directly to the glass rod. Here Bi- and phosphate glass, Yb:Y<sub>2</sub>O<sub>3</sub> ceramic or Nd:YAG are cited only as examples, and in principle any active gain medium can be used for rod **102**.

Gain media such as Nd:YAG, Nd:YLF or Nd:YVO<sub>4</sub>, Nd:glass, Yb:glass, Nd:KGW, Yb:KGW and Yb:KYW are further examples of structures that can be shaped into fiber rods. These gain media can be uniformly doped.

More generally, such holes can be directly incorporated into uniformly doped glasses, ceramic or crystalline materials such as Bi- and phosphate glasses, Yb:Y<sub>2</sub>O<sub>3</sub> or Nd:YAG and even Ti:Sapphire as well as plastics such as PMMA. Most glasses such as Bi-glasses and phosphate as well as some ceramic materials can be drawn into fibers and the structure as shown in FIG. **15A** can then be simply drawn using the well known stack and draw technique. Alternatively, appropriate holes can be micro-machined into a crystal using precision mechanical drilling, laser ablation, or ultra fast optical pulses. The holes in fiber rods can be much larger compared to holey fibers. To reduce or minimize surface irregularities in the actual hole structure and to increase or maximize the Rayleigh range of the ablating laser, UV pulses can be used.

When employing uniformly doped materials as fiber rods or generally as waveguide rods, the use of direct pumping into the core structure with near diffraction limited pump sources is useful for achieving a good overlap between pump and signal beam.

When creating holes in generic amplifier media, such as glass, plastics, ceramics or crystalline materials, monolithic designs of hybrid versions of waveguide rods can be constructed. The side-view of a such a monolithic hybrid waveguide rod **220** is shown in FIG. **15D**). Waveguide rod **220** comprises a uniformly doped gain material **221** and a propagation region **222**. Propagation region **222** is bounded by symmetrically arranged air holes **223** and **224** (e.g., six large, tightly spaced holes, may be used as shown in FIG. **15A**) on one side (left side of drawing) for modal light confinement, whereas the propagation region is allowed to diffract freely on the opposite side (right side of drawing). The structure can be pumped from the freely propagating region (right side of drawing). The signal is injected into the confined propagation region (left side of drawing). Holes **223** and **224** can be made by mechanical drilling or they can be constructed using laser ablation. In such structures fundamental mode sizes up to about 100  $\mu\text{m}$  or larger can be obtained. To avoid contamination of air-holes **223** and **224**, the input and output end faces are preferably polished and antireflective (AR) coated prior to the introduction of the air-holes. The input and output end faces can also be tilted or wedged (not shown) in order to avoid parasitic reflections in the amplifier.

Since particularly crystalline or ceramic waveguide rods can be quite short due to manufacturing restraints or because the doping level in these structures may be limited due to thermal and efficiency considerations, the signal in such waveguide rods can be multi-passed to increase the achievable gain. Referring back to FIG. **15D**, such waveguide rods operated in a multi-pass configuration are preferably constructed without a freely diffracting region. Standard methods for multi-passes through waveguides incorporating Faraday rotators and polarization beam splitters can be implemented to obtain a double or a quadruple pass through waveguide-rods.

Due to thermal considerations, it can be advantageous to construct waveguide slabs instead of waveguide rods. A generic implementation of a waveguide slab **230** is shown in FIG. **15E**. This slab is wider than it is thick. Exemplary dimensions may range from about a width of 250  $\mu\text{m}$  to 10 mm. Here the core region **231** is derived from a substantially uniformly doped active material **232**, such as a glass, a ceramic, or a crystal. The elongated core structure is defined by eight air-holes. The structure is preferably directly core-



pumped. A predominantly one dimensional heat flow can be obtained by attaching heat sinks and appropriate cooling mechanisms to the top and bottom of slab **230**. Appropriate mode-transforming optics can then also be used to transform the elliptical output beam into a more circular beam as required for many applications. Moreover, cladding pumping can be enabled by surrounding the substrate **232** with a material with a lower refractive index than substrate **232**. To avoid scattering losses due to pump light directed into the air-holes, the air holes in the slab structure can be collapsed down at the pump coupling end.

In order to save storage space for long waveguide rods and to induce a differential loss between the fundamental mode and any higher-order modes, it may be advantageous to coil the rigid structure up into rigid coils or other structures following curvilinear paths. Because of the small bend loss of large mode area holey waveguide rods, curvilinear paths can be introduced without any major performance limitations. Moreover, curvilinear paths are beneficial for a discrimination of the modes within the waveguide, because of the introduction of bend losses for the higher-order modes. An example of a glass or ceramic waveguide rod following a curvilinear path is shown in FIG. **15F**. Even relatively rigid waveguide rods of up to 1 mm (or larger) outside diameter can be formed into arbitrary shapes by gently heating the rods and bending them into the desired shape.

Though the design examples listed up to this point comprised mainly waveguide rod structures with substantially circularly shaped air-holes, for the operation of such waveguides, the exact shape, number, and arrangement, of the air-holes may vary. Designs illustrated in FIGS. **5A**, **5B**, **6A-6F**, **7A-7E** and **8A-8C**, for example, can all be used as a rod structure.

Polarization maintaining operation of waveguide rods can be obtained by constructing these structures in birefringent crystalline materials and exciting a major axis of the crystal. For the case of fiber rods, stress regions can be incorporated into the fibers to enable polarization maintaining operation. Examples of a polarization maintaining fiber rod designs are shown in FIG. **7A-7E**.

Since mode-coupling in fiber rods is greatly reduced, multi-mode (MM) pump sources can be coupled into the core region of the fiber rod with small or minimal effects on the beam quality of the amplifier output beam. Near diffraction limited beam output are possible. Such an arrangement is shown in FIG. **16**. The system is very similar to the one depicted in FIG. **17**. However, rod **102** is eliminated and no separate air-cladding is needed in rod **101**. SM pump **109** is substituted with MM pump **115**. Pump **115** can comprise a few-mode fiber laser or a high brightness semiconductor laser. Also shown is a fiber taper **116** which facilitates excitation of the fundamental mode in fiber rod **101**. Due to the absence of mode-coupling (or very small mode-coupling in fiber rod **101**) the fundamental mode can propagate with minimal distortions in fiber rod **101** despite its MM structure. The MM structure, however, accepts MM pump beams. For example for a 50  $\mu\text{m}$  core diameter fiber rod as depicted in FIG. **15A**, a MM pump beam containing 5-20 modes can be used to pump the core area of fiber rod **101**. For a 100  $\mu\text{m}$  core diameter fiber rod, up to 100 pump modes can be supported. Hence, an efficient brightness converter is obtained with the present configuration.

The structure depicted in FIG. **16** can also be used in conjunction with waveguide rods and slabs as shown in FIG. **15A-15C**. Not all waveguide rods may allow for the incorporation of tapers **116** as shown in FIG. **16**. Hence, particularly

for crystalline waveguide rods and slabs, a non-tapered waveguide **101** may need to be implemented.

The ultra-large core amplifier fibers and rods may be used as an efficient cw fiber laser operating on three-level transitions, such as Nd-fibers operating at about 920 nm, or ytterbium fiber lasers operating at about 980 nm. An exemplary set-up of an efficient Nd fiber laser operating in the range between about 920-940 nm wavelength is shown in FIG. **19**. Fiber rods are not necessary and long-lengths of holey fibers such as shown in FIG. **15A** may be used. Such long lengths of holey fiber can incorporate mode-filters to facilitate cw lasing in the fundamental mode of the holey fiber structure, or lasing in at least the few lowest order modes. Moreover, the fiber can be coiled onto a drum to enable packaging of the device. Even a few-mode cw fiber laser can be used as pump source for a fiber rod as explained with respect to FIG. **16**. System in FIG. **19** is slightly modified in comparison to the system shown in FIG. **16**. The system in FIG. **19** includes a taper **116** as a mode filter and a fiber grating **117** to obtain preferential lasing on the 940 nm lasing transition of Nd fiber when pumping in the 800 nm wavelength region. (See, e.g., Fermann et al. in U.S. Pat. No. 5,818,630). A dichroic mirror **118** is further optionally directly deposited onto the pump coupling end of the fiber **101**. The holes in the pump coupling fiber end can be collapsed and subsequently polished to obtain a smooth end face and to improve or optimize pump coupling efficiency as well as to simplify the deposition of optional mirror **118**. Alternatively the flat polished pump coupling end can be used as a reflective structure.

An exemplary embodiment can comprise a holey fiber with a 60  $\mu\text{m}$  core and a 250  $\mu\text{m}$  cladding diameter. Fiber lengths between 1 to around 30 m can be optimally employed. Even with a standard cladding NA of 0.45 as achievable with polymer clad fibers, greater than about 100 W of pump power can be coupled into the fiber cladding. For a cladding NA of 0.60, pump power up to about 200 W can be coupled into the fiber cladding with conventional high brightness pump sources, enabling the generation of up to 100 W of power near 940 nm. Such near diffraction-limited high power cw sources are ideal for direct core pumping of ytterbium fiber rods in general and specifically uniformly ytterbium doped fiber rods, which do not comprise any undoped cladding region.

Similar design consideration also hold for the design of ytterbium fiber lasers operating at 980 nm, which are even better pump sources for direct core pumping of ytterbium fiber rods. Generally, the ultra-large core fibers as discussed here can be used for the demonstration of lasing on any three-level transition in rare-earth doped fibers.

The waveguide rod amplifiers as discussed here are also advantageous for use as power amplifiers for compact high energy amplification systems for ns, ps, and fs pulses. A generic system for the amplification of fs or ps pulses, based on the chirped pulse amplification technique is shown in FIG. **20A**. System **300** comprises a seed source **301**, an optical gate **302**, a waveguide rod amplifier **303** as well as a pulse compressor **304**. The output from the system and the direction of light propagation is designated with arrow **305**. In some embodiments, seed source **301** may comprise a laser that produces femtosecond or picosecond pulses, a pulse stretcher, and several pre-amplifier stages. Such systems are described in U.S. patent application Ser. No. 10/992,762 Fermann et al, filed Nov. 22, 2004 entitled "All-fiber chirped pulse amplification system" (Docket No. IM-114) which is incorporated herein by reference in its entirety. The optical gate **302** may comprise an optical isolator and an acousto-optic modulator to reduce or minimize any amplified spontaneous emission generated in the seed source from coupling



into waveguide rod amplifier **303**. Compressor **304** may be dispersion matched to the compressor within the seed source to enable the generation of the shortest possible pulses at the output from the system. Some degree of dispersion mismatch between stretcher and compressor is tolerable when exploiting nonlinear pulse propagation of the stretched pulses, particularly when enabling the generation of cubicon pulses; see, U.S. patent application Ser. No. 10/992,762 referenced above. This approach is particularly useful for the generation of femtosecond pulses. The system can be designed to generate cubicon pulses already in seed source **301** or it can also be designed for cubicon pulses formation in waveguide rod amplifier **303**. Cubicon pulse formation may be enabled when injecting highly stretched optical pulses into an amplifier and amplifying them to a peak power that subjects the pulses to significant levels of self-phase modulation. Optional frequency conversion stages can further be implemented downstream from system **305**. When amplifying ps pulses, pulse stretchers as well as compressor **304** can be omitted. Moreover, nonlinear spectral compression as discussed in U.S. patent application Ser. No. 10/927,374, filed Aug. 27, 2004, and entitled "High-energy optical fiber amplifier for ps-ns pulses for advanced material processing applications", (Docket No. IM-105) which is incorporated by reference herein, can be used to obtain near bandwidth-limited ps pulses at the output. Nonlinear spectral compression can be induced into a positive dispersion waveguide rod amplifier by injecting negatively chirped pulses and amplifying the pulses to a peak power that subjects them to significant levels of self-phase modulation. Other configurations are also possible.

A generic nanosecond (ns) pulse amplifier is shown in FIG. 20B. The nanosecond amplifier **306** is very similar to the system **300** shown in FIG. 20A, however, no stretcher and compressor are used. Also shown is an optional frequency conversion element **307** that can typically comprise a nonlinear crystal or an array of nonlinear crystals employed for frequency up- or down-conversion. Nanosecond as well as picosecond type fiber (or rod) amplifiers can further be used as pump sources for optical parametric amplifiers, allowing for the generation of pulses with widths less than about 50 fs and even less than about 10 fs. Such optical parametric amplifier systems are discussed in U.S. patent application Ser. No. 11/091,015 entitled "Optical parametric amplification, optical parametric generation and optical pumping in optical fiber systems" filed Mar. 25, 2005 (Attorney Docket No. IMRAA.026A), which is incorporated herein by reference in its entirety.

When generating ns pulses it is most cost effective to employ active or passive Q-switching. Such a system configuration is shown in FIG. 21. The system **100** is very similar to the system already described with respect to FIG. 16. However, an optical modulator **118** is added in front of one of the cavity mirrors (in this case, the fiber Bragg grating **117**). Two additional lenses **119**, **120** (or more generally a lens system or coupling system) are used to couple light from the tapered fiber rod output end **116** to the mode-filter **117**. A multi-mode fiber rod **101** can be used as the active gain element. Near diffraction-limited operation of the system is obtained by the mode-filtering action of taper **116** in conjunction with fiber Bragg grating **117**. More generally, waveguide rods can also be implemented in this system configuration. Since the pulse energy generated in such systems can exceed a few mJ, a mode-filter based on a spatial filter can be used at one end of the cavity. Alternatively, taper **116** can be eliminated and fiber **117** can be replaced with a single-mode air-holed fiber to provide mode-filtering action. Mode-filtering

can also be obtained by shaping the waveguide rod **101** into a curvilinear form. A mirror can then be incorporated at one end of the air-holed fiber to provide a second reflective structure for the construction of a cavity. Such cavity implementations are not separately shown.

The ultra-large mode fibers and rods as discussed above are particularly suitable for a range of machining and marking applications comprising machining of metals, ceramics, glasses, semiconductors, crystals, biological systems and others just to mention a few examples. Since the above systems allow the generation of pulses with energies up to a few mJ at average powers of tens of W, very high throughput for laser machining becomes possible. The outputs may also be nearly diffraction limited. Such systems may include positioning systems, such as translators for translating the work piece or movable optics (e.g., movable mirrors or lenses, etc.). Other configurations are possible.

Moreover, various embodiments of the invention have been described above. Although this invention has been described with reference to these specific embodiments, the descriptions are intended to be illustrative of the invention and are not intended to be limiting. Various modifications and applications may occur to those skilled in the art without departing from the true spirit and scope of the invention as defined in the appended claims.

What is claimed is:

1. An optical fiber for propagating lower order modes, having order N or less and having a wavelength,  $\lambda$ , while limiting propagation of all higher order modes with order greater than N by providing said all higher order modes with a higher loss than said lower order modes at said wavelength,  $\lambda$ , said optical fiber comprising:

a first cladding region comprising a plurality of lower-index cladding features, each of said plurality of lower-index cladding features having a refractive index lower than a refractive index of said first cladding region, said plurality of lower-index cladding features arranged in no more than two layers; and

a core region surrounded by said first cladding region, said core region substantially surrounded by each layer of said no more than two layers, said plurality of lower-index cladding features configured to substantially confine propagation of said lower order modes to said core region, said core region having a width of at least about 20 micrometers,

wherein said order N is less than or equal to 20, and wherein said core region is configured to provide a loss for said all higher order modes of at least about 0.5 dB.

2. The optical fiber of claim 1, wherein said core region is configured to provide a loss for said all higher order modes of at least about 1 dB.

3. The optical fiber of claim 1, wherein said width of said core region is at least about 40 micrometers.

4. The optical fiber of claim 1, wherein said plurality of lower-index cladding features has a minimum size, d, yielding a ratio of  $d/\lambda$  that is at least about 10.

5. The optical fiber of claim 4, wherein said ratio of  $d/\lambda$  is at least about 20.

6. The optical fiber of claim 1, wherein said plurality of lower-index cladding features are arranged in a single layer.

7. The optical fiber of claim 1, wherein said core and cladding regions are in a substantially optically transmissive main body of said optical fiber, said main body comprising material substantially optically transmissive of said wavelength,  $\lambda$ , said main body having a width and thickness at least about 200  $\mu\text{m}$  so as to reduce mode coupling of said lower order modes to said higher order modes.



## 23

8. The optical fiber of claim 7, wherein said width and thickness of said main body is at least about 500  $\mu\text{m}$ .

9. An optical amplifier comprising an optical fiber according to claim 1, wherein said core region is doped to provide optical gain.

10. A system comprising the optical amplifier of claim 9, wherein output pulse energy is in excess of 1  $\mu\text{J}$ .

11. An optical system for generation of high power solitons comprising the optical fiber of claim 1.

12. A laser system comprising the optical fiber of claim 1, wherein said optical fiber is doped with dopants that provide said optical fiber with gain and said optical fiber is optically coupled to reflective elements that form an optical resonator.

13. A fiber laser according to claim 12, wherein said fiber comprises a Nd doped fiber.

14. A fiber laser according to claim 12, wherein said fiber comprises a ytterbium doped fiber.

15. A chirped pulse amplification system for the amplification of picosecond or femtosecond pulses comprising the optical amplifier of claim 9 and a pulse compressor.

16. A laser micro-machining system comprising the chirped pulse amplification system of claim 15 and a positioning system.

17. An optical fiber according to claim 1, wherein the core and cladding regions comprise polymer materials.

18. The optical fiber of claim 1, wherein said order N is equal to 1.

19. The optical fiber of claim 1, wherein said order N is less than or equal to 3.

20. The optical fiber of claim 1, wherein said order N is less than or equal to 5.

21. The optical fiber of claim 1, wherein said order N is less than or equal to 10.

22. The optical fiber of claim 1, wherein said first cladding is discrete.

23. The chirped-pulse amplification system of claim 15, wherein said compressor comprises a fiber, and wherein said amplifier comprises a portion of a transmission fiber or a portion of said compressor or both.

24. The optical amplifier of claim 9, wherein said amplifier is a pulse amplifier to amplify picosecond, femtosecond, or nanosecond pulses.

25. The laser system of claim 12, further comprising an optical modulator disposed within said resonator to cause active or passive q-switching of said laser.

26. The laser system of claim 12 wherein said laser system is a CW system operating in the fundamental mode or few lowest order modes.

27. The optical fiber of claim 1, wherein at least one layer of said no more than two layers comprises a ring.

28. The optical fiber of claim 1, wherein at least one layer of said no more than two layers comprises two or more of said plurality of lower-index cladding features.

29. The optical fiber of claim 28, wherein said at least one layer comprises six or more of said plurality of lower-index cladding features.

30. The optical fiber of claim 1, wherein said plurality of lower-index cladding features are arranged in two layers.

31. The optical fiber of claim 30, wherein each of said two layers comprises a plurality of lower-index cladding features.

32. An optical rod for propagating lower order modes having order N or less and having a wavelength,  $\lambda$ , while limiting propagation of all higher order modes with order greater than N by providing said all higher order modes with a higher loss than said lower order modes at said wavelength,  $\lambda$ , said optical rod comprising:

## 24

a first cladding region comprising a plurality of lower-index cladding features, each of said plurality of lower-index cladding features having a refractive index lower than a refractive index of said first cladding region, said plurality of lower-index cladding features arranged in no more than two layers; and

a core region surrounded by the said first cladding region, said core region substantially surrounded by each layer of said no more than two layers, said plurality of lower-index cladding features configured to substantially confine propagation of said lower order modes to said core region, said core region having a width of at least about 20 micrometers,

wherein said order N is less than or equal to 20, and

wherein said core region is configured to provide a loss for said all higher order modes of at least about 0.5 dB.

33. The rod of claim 32, wherein said core region is configured to provide a loss for said all higher order modes of at least about 1 dB.

34. The rod of claim 32, wherein said width of said core region is at least about 40 micrometers across.

35. The rod of claim 32, wherein said features have a minimum feature size, d, yielding a ratio of  $d/\lambda$  that is at least about 10.

36. The rod of claim 32, wherein said core and cladding regions are in a substantially optically transmissive main body of said rod, said main body comprising material substantially optically transmissive of said wavelength,  $\lambda$ , said main body having a width and thickness at least about 250  $\mu\text{m}$  so as to reduce mode coupling of said lower order modes to said higher order modes.

37. The optical fiber of claim 32, wherein said order N is equal to 1.

38. The optical fiber of claim 32, wherein said order N is less than or equal to 3.

39. The optical fiber of claim 32, wherein said order N is less than or equal to 5.

40. The optical fiber of claim 32, wherein said order N is less than or equal to 10.

41. The optical fiber of claim 32, wherein said first cladding is discrete.

42. The optical rod of claim 32, wherein at least one layer of said no more than two layers comprises a ring.

43. The optical rod of claim 32, wherein at least one layer of said no more than two layers comprises two or more of said plurality of lower-index cladding features.

44. The optical rod of claim 43, wherein said at least one layer comprises six or more of said plurality of lower-index cladding features.

45. The optical rod of claim 32, wherein said plurality of lower-index cladding features are arranged in a single layer.

46. The optical rod of claim 32, wherein said plurality of lower-index cladding features are arranged in two layers.

47. The optical rod of claim 46, wherein each of said two layers comprises a plurality of lower-index cladding features.

48. An optical fiber for propagating lower order modes having order N or less and having a wavelength,  $\lambda$ , while limiting propagation of all higher order modes with order greater than N by providing said all higher order modes with a higher loss than said lower order modes at said wavelength,  $\lambda$ , said optical fiber comprising:

a cladding further comprising a plurality of lower-index cladding features, each of said plurality of lower-index cladding features having a refractive index lower than a refractive index of said cladding, said plurality of lower-index cladding features arranged in no more than two layers; and

25

a core, said core substantially surrounded by each layer of  
said no more than two layers, said core having a width of  
at least about 20 micrometers,  
wherein said order N is less than or equal to 20, and  
wherein said fiber is configured such that (i) the lower order 5  
modes have no more than 1.0 dB of loss at a bending  
radius of about 30 centimeters and (ii) said all higher  
order modes have a loss of at least 0.5 dB.  
49. The optical fiber of claim 48, wherein said order N is  
equal to 10.  
50. The optical fiber of claim 48, wherein said order N is 10  
equal to 5.  
51. The optical fiber of claim 48, wherein said order N is  
equal to 1.  
52. The optical fiber of claim 51, wherein the fundamental 15  
mode has no more than 0.5 dB of loss at a bending radius of  
10 centimeters.

26

53. The optical fiber of claim 48, wherein at least one layer  
of said no more than two layers comprises a ring.  
54. The optical fiber of claim 48, wherein at least one layer  
of said no more than two layers comprises two or more of said  
plurality of lower-index cladding features.  
55. The optical fiber of claim 53, wherein said at least one  
layer comprises six or more of said plurality of lower-index  
cladding features.  
56. The optical fiber of claim 48, wherein said plurality of  
lower-index cladding features are arranged in a single layer.  
57. The optical fiber of claim 48, wherein said plurality of  
lower-index cladding features are arranged in two layers.  
58. The optical fiber of claim 57, wherein each of said two  
layers comprises a plurality of lower-index cladding features.

\* \* \* \* \*



UNITED STATES PATENT AND TRADEMARK OFFICE  
**CERTIFICATE OF CORRECTION**

PATENT NO. : 7,787,729 B2  
APPLICATION NO. : 11/134856  
DATED : August 31, 2010  
INVENTOR(S) : Dong et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On page 2 in column 2 at line 40, under Other Publications, change “filed” to --field--.

In column 6 at approximately line 34, change “ $a/\lambda$ ,” to -- $a/\lambda$ --.

In column 11 at line 30, change “ $\text{dB.cm}^{0.5}/\text{m}$ ,” to -- $\text{dB.cm}^{0.5}/\text{m}$ --.

In column 11 at line 31, change “ $\text{dB.cm}^{0.5}/\text{m}$ ,” to -- $\text{dB.cm}^{0.5}/\text{m}$ --.

In column 16 at line 5, change “DESIGN” to --DESIGN--.

In column 22 at line 28, In Claim 1, change “ $\lambda$ ,while” to -- $\lambda$ , while--.

Signed and Sealed this  
Nineteenth Day of July, 2011

A handwritten signature in black ink, reading "David J. Kappos". The signature is written in a cursive, flowing style with a large initial "D".

David J. Kappos  
*Director of the United States Patent and Trademark Office*