

US007795685B2

(12) **United States Patent**
Park et al.

(10) **Patent No.:** **US 7,795,685 B2**
(45) **Date of Patent:** **Sep. 14, 2010**

(54) **METHOD OF MANUFACTURING A THIN FILM TRANSISTOR SUBSTRATE AND STRIPPING COMPOSITION**

(75) Inventors: **Hong-Sik Park**, Suwon-si (KR);
Shi-Yul Kim, Yongin-si (KR);
Jong-Hyun Choung, Suwon-si (KR);
Won-Suk Shin, Yongin-si (KR)

(73) Assignee: **Samsung Electronics Co., Ltd.** (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 196 days.

(21) Appl. No.: **11/875,035**

(22) Filed: **Oct. 19, 2007**

(65) **Prior Publication Data**

US 2008/0039354 A1 Feb. 14, 2008

Related U.S. Application Data

(62) Division of application No. 11/215,140, filed on Aug. 30, 2005, now Pat. No. 7,300,827.

(30) **Foreign Application Priority Data**

Aug. 30, 2004 (KR) 2004-68791
May 25, 2005 (KR) 2005-44153

(51) **Int. Cl.**
H01L 23/62 (2006.01)

(52) **U.S. Cl.** **257/359**; 257/213; 257/288;
257/E21.051; 257/E21.229; 257/E21.058;
257/E21.231; 257/E21.411

(58) **Field of Classification Search** 257/359,
257/59, 79, 213, 288, 918
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,986,729	A	11/1999	Yamanaka et al.	
6,440,647	B1 *	8/2002	Yakobson	430/329
6,458,517	B2 *	10/2002	Nohara et al.	430/329
6,924,865	B2	8/2005	Ohta et al.	
7,042,545	B2	5/2006	Byun et al.	
7,300,827	B2 *	11/2007	Park et al.	438/149
7,384,900	B2 *	6/2008	Jo et al.	510/175
2004/0081922	A1 *	4/2004	Ikemoto et al.	430/329
2004/0137379	A1 *	7/2004	Ikemoto	430/331
2005/0078233	A1	4/2005	Lim et al.	
2006/0269849	A1	11/2006	Lee	
2007/0020910	A1	1/2007	Park et al.	
2007/0082432	A1	4/2007	Lee	

FOREIGN PATENT DOCUMENTS

EP 0 647 884 A1 4/1995

* cited by examiner

Primary Examiner—David Nhu

(74) *Attorney, Agent, or Firm*—Cantor Colburn LLP

(57) **ABSTRACT**

A method of manufacturing a thin film transistor substrate includes forming a transistor thin layer pattern, forming a protecting layer, forming a photoresist film, forming a pixel electrode and a conductive layer that are separated from each other, stripping a photoresist pattern to remove the conductive layer using a stripping composition and dissolving the conductive layer. The method of manufacturing a thin film transistor substrate is capable of improving an efficiency of manufacturing process of the thin film transistor substrate. In addition, the stripping composition is recycled.

16 Claims, 9 Drawing Sheets




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13A




FIG. 13B





FIG. 13C



METHOD OF MANUFACTURING A THIN FILM TRANSISTOR SUBSTRATE AND STRIPPING COMPOSITION

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a divisional application of U.S. application Ser. No. 11/215,140 filed on Aug. 30, 2005 and issued as U.S. Pat. No. 7,300,827 on Nov. 27, 2007, which claims priority to Korean Patent Application No. 2004-68791 filed on Aug. 30, 2004, and Korean Patent Application No. 2005-44153 filed on May 25, 2005, and all the benefits accruing therefrom under 35 U.S.C. §119 the contents of which are herein incorporated by reference in their entireties.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a method of manufacturing a thin film transistor substrate and a stripping composition. More particularly, the present invention relates to a method of manufacturing a thin film transistor substrate capable of simplifying a manufacturing process of the thin film transistor substrate and a stripping composition employed for the manufacturing process of the thin film transistor substrate.

2. Description of the Related Art

In general, a display device includes a cathode ray tube type (CRT) display (CRT) device, a liquid crystal display (LCD) device, a plasma display panel (PDP) device, and an organic light emitting display (OLED) device.

Most of the display devices, except for the CRT device, include a thin film transistor substrate having a thin film transistor so as to display images.

In order to simplify the manufacturing process of the thin film transistor substrate to reduce a manufacturing cost, novel technologies have been rapidly developed.

SUMMARY OF THE INVENTION

The present invention provides an exemplary embodiment of a method of manufacturing a thin film transistor substrate capable of simplifying a manufacturing process of the thin film transistor substrate.

The present invention also provides an exemplary embodiment of a stripping composition that is used for the manufacturing process of the thin film transistor and is reusable.

In exemplary embodiments of a method of manufacturing a thin film transistor substrate, a transistor thin layer pattern is disposed on a substrate. A protecting layer is disposed on the transistor thin layer pattern. A photoresist film is disposed on the protecting layer. The photoresist film forms a photoresist pattern on the substrate by a photolithography process. An undercut is generated at a lower portion of the photoresist pattern by the photolithography process. A pixel area is formed on a portion of the substrate by removing the photoresist film. A conductive material is deposited on the photoresist pattern. The conductive material is deposited on the photoresist pattern to form a conductive layer, and the conductive material is deposited on the pixel area to form a pixel electrode. A stripping composition is applied onto the pixel electrode and the photoresist pattern to strip the photoresist pattern, so that the conductive layer formed on the photoresist pattern is separated from the substrate. A used stripping composition containing the conductive layer separated from the substrate is collected and stored in a storage tank. The con-

ductive layer separated from the substrate is completely dissolved in the used stripping composition.

In another exemplary embodiment, the stripping composition includes both a stripping agent for stripping the photoresist and a stripping additive for dissolving the conductive layer.

In another exemplary embodiment, a stripping composition includes a stripping agent for stripping a photoresist and a stripping additive for stripping a conductive layer. The stripping agent for stripping the photoresist includes about 20 percent by weight to about 40 percent by weight of an amine-based compound, about 20 percent by weight to about 50 percent by weight of a protonated glycol-based compound and about 20 percent by weight to about 40 percent by weight of a deprotonated multipolar compound. The stripping additive for stripping the conductive layer includes about 0.5 percent by weight to about 3 percent by weight of a thiol-based compound.

In another exemplary embodiment, the thiol-based compound may include a thio benzoic acid or thiol acid.

In another exemplary embodiment of the method of manufacturing a thin film transistor substrate, the number of masks may decrease, so that the manufacturing process of the thin film transistor may be simplified. Additionally, the stripping composition used for manufacturing the thin film transistor substrate may dissolve the photoresist film, and furthermore the stripping composition may completely dissolve the conductive layer after the photoresist film is dissolved. Advantageously, the stripping composition according to the present invention may be recycled.

In another exemplary embodiment of the method of manufacturing a thin film transistor substrate, a gate line and gate electrode are formed on the substrate substantially perpendicular to each other. A gate insulating layer is formed on the substrate covering the gate line and gate electrode. An amorphous silicon pattern and an n⁺ amorphous silicon pattern are formed on the gate insulating layer. A date line, source electrode and drain electrode are formed on the substrate. The source electrode and the drain electrode are electrically connected to the n⁺ amorphous silicon pattern. The forming of the gate line, the gate electrode, the amorphous silicon pattern, the n⁺ amorphous silicon pattern, the date line, the source electrode and the drain electrode uses multiple masks.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other advantages of the present invention will become readily apparent by reference to the following detailed description when considered in conjunction with the accompanying drawings wherein:

FIG. 1 is a plan view illustrating an exemplary embodiment of a gate line formed on a substrate by an exemplary embodiment of a method of manufacturing a thin film transistor substrate according to the present invention;

FIG. 2 is a cross-sectional view taken along line I-I' in FIG. 1;

FIG. 3 is a plan view of an exemplary embodiment of a channel layer formed on the exemplary embodiment of the gate line in FIG. 1;

FIG. 4 is a cross-sectional view taken along line II-II' in FIG. 3;

FIG. 5 is a plan view of an exemplary embodiment of source and drain electrodes electrically connected to the exemplary embodiments of an n⁺ amorphous silicon pattern in FIG. 3;

3

FIG. 6 is a cross-sectional view taken along line III-III' in FIG. 5;

FIG. 7 is a plan view of an exemplary embodiment of a photoresist pattern formed on an exemplary embodiment of a protecting layer;

FIG. 8 is a cross-sectional view taken along line IV-IV' in FIG. 7;

FIG. 9 is an enlarged view of an exemplary embodiment of portion 'A' in FIG. 8;

FIG. 10 is a cross-sectional view of an exemplary embodiment of a transparent conductive thin layer formed on the exemplary embodiment of a substrate in FIG. 9;

FIG. 11 is a cross-sectional view of an exemplary embodiment of the substrate in FIG. 10 with a part of a photoresist pattern and a conductive layer removed according to an exemplary method of an embodiment of the invention;

FIG. 12 is a cross-sectional view of an exemplary embodiment of a thin film substrate in FIG. 11 without the photoresist pattern and the conductive layer;

FIG. 13A is a picture of a surface of a conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 1;

FIG. 13B is a picture of a surface of a conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 2; and

FIG. 13C is a picture of a surface of a conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 3.

DETAILED DESCRIPTION OF THE INVENTION

The invention is described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the exemplary embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. In the drawings, the size and relative sizes of layers and regions may be exaggerated for clarity.

It will be understood that when an element or layer is referred to as being "on", "connected to" or "coupled to" another element or layer, the element or layer can be directly on, connected or coupled to another element or layer or intervening elements or layers. In contrast, when an element is referred to as being "directly on," "directly connected to" or "directly coupled to" another element or layer, there are no intervening elements or layers present. Like numbers refer to like elements throughout. As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items.

It will be understood that, although the terms first, second, third, etc., may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another region, layer or section. Thus, a first element, component, region, layer or section discussed below could be termed a second element, component, region, layer or section without departing from the teachings of the present invention.

Spatially relative terms, such as "beneath", "below", "lower", "above", "upper" and the like, may be used herein for ease of description to describe the relationship of one element or feature to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially

4

relative terms are intended to encompass different orientations of the device in use or operation, in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as "below" or "beneath" other elements or features would then be oriented "above" the other elements or features. Thus, the exemplary term "below" can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms "a", "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms "comprises" and/or "comprising," when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Embodiments of the invention are described herein with reference to cross-section illustrations that are schematic illustrations of idealized embodiments (and intermediate structures) of the invention. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments of the invention should not be construed as limited to the particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing.

For example, an implanted region illustrated as a rectangle will, typically, have rounded or curved features and/or a gradient of implant concentration at its edges rather than a binary change from implanted to non-implanted region. Likewise, a buried region formed by implantation may result in some implantation in the region between the buried region and the surface through which the implantation takes place. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the actual shape of a region of a device and are not intended to limit the scope of the invention.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

An Exemplary Embodiment of a Method of Manufacturing a Thin Film Transistor Substrate

FIG. 1 is a plan view of an exemplary embodiment of a gate line formed on a substrate by an exemplary embodiment of a method of manufacturing a thin film transistor substrate according to an embodiment of the present invention. FIG. 2 is a cross-sectional view of an exemplary embodiment of the gate line taken along line I-I' in FIG. 1.

Referring to FIGS. 1 and 2, a gate line 110 is formed on a substrate 100 along a first direction, and a gate electrode 112 is formed on the gate line 110 extended along a second direction substantially perpendicular to the first direction. In exemplary embodiments, a conductive gate thin layer entirely formed on the substrate 100 is patterned using a mask to form the gate line 110 and the gate electrode 112. In alternative embodiments, the conductive gate thin layer may include, but

5

is not limited to, aluminum, an aluminum alloy, and the like, as well as combinations including at least one of the foregoing.

A gate insulating layer **114** may be formed on the substrate **100** to cover the gate line **110** and the gate electrode **112** as shown in the exemplary embodiment of FIG. 2.

FIG. 3 is a plan view of an exemplary embodiment of a channel layer formed on the gate line in FIG. 1. FIG. 4 is a cross-sectional view taken along line II-II' in FIG. 3.

Referring to FIGS. 3 and 4, an amorphous silicon thin layer and an n⁺ amorphous silicon thin layer **120** may be sequentially formed on an upper face of the gate insulating layer **114**. The amorphous silicon thin layer and the n⁺ amorphous silicon thin layer **120** may be patterned by a photolithography process using a mask to form an amorphous silicon pattern **122** and an n⁺ amorphous silicon pattern **124** on the gate electrode **112**. The amorphous silicon pattern **122** may be formed on the gate insulating layer **114** corresponding to the gate electrode **112**. A pair of the n⁺ amorphous silicon pattern **124** may be formed on an upper face of the amorphous silicon pattern **122**. In the exemplary embodiment in FIG. 4, the n⁺ amorphous silicon patterns **124** may be spaced apart from each other.

FIG. 5 is a plan view of an exemplary embodiment of source and drain electrodes electrically connected to the n⁺ amorphous silicon pattern in FIG. 3. FIG. 6 is a cross-sectional view taken along line III-III' in FIG. 5.

Referring to FIGS. 5 and 6, after the amorphous silicon pattern **122** and the n⁺ amorphous silicon pattern **124** are formed on the substrate **100**, a source/drain thin layer may be entirely formed on the substrate **100**. In alternative embodiments, the source/drain thin layer may be patterned by the photolithography process using the mask. As a result, a data line **130**, a source electrode **132** and a drain electrode **134** may be formed on the substrate **100**.

The data line **130** may be extended along the second direction, and the source electrode **132** may be extended from the data line **130** along the first direction as shown in FIG. 5. The data line **130** and the source electrode **132** may be substantially perpendicular to each other.

In exemplary embodiments, the source electrode **132** extended from the data line **130** may be electrically connected to one side of the n⁺ amorphous silicon pattern **124**. In alternative embodiments, the drain electrode **134** may be electrically connected to another side of the n⁺ amorphous silicon pattern **124**.

Referring to FIG. 6, a protecting layer **140** may be formed on the substrate **100** to cover the data line **130**, the source electrode **132** and the drain electrode **134**.

As described above, the gate line **110**, the gate electrode **112**, the n⁺ amorphous silicon pattern **124**, the amorphous silicon pattern **122**, the data line **130**, the source electrode **132** and the drain electrode **134** may be formed on the substrate **100** using multiple masks. In alternative embodiments, the gate line **110** and the gate electrode **112** may be formed using one mask. In other alternative embodiments, the n⁺ amorphous silicon pattern **124**, the amorphous silicon pattern **122**, the data line **130**, the source electrode **132** and the drain electrode **134** may be formed using one mask.

FIG. 7 is a plan view of an exemplary embodiment of a photoresist pattern formed on a protecting layer. FIG. 8 is a cross-sectional view taken along line IV-IV' in FIG. 7. FIG. 9 is an enlarged view illustrating an exemplary embodiment of portion 'A' in FIG. 8.

Referring to FIGS. 7 through 9, the photoresist thin layer is entirely formed on the substrate **100**. The photoresist thin layer may be patterned using the mask to form a photoresist

6

pattern **150** on an upper face of the substrate **100**. Reference number **150a** in FIGS. 7 and 8 indicates a pixel area that may be exposed through an area from which the photoresist pattern **150** is removed.

The protecting layer **140** may be patterned using a photoresist pattern **150** as the mask to form a protecting pattern **142** on the substrate **100**. In exemplary embodiments, when the protecting pattern **142** is partially opened or entirely removed, the drain electrode **134** covered by the protecting layer **140** may be exposed as shown in FIG. 8.

When the protecting layer **140** is patterned using the photoresist pattern **150** as the mask, the protecting layer **140** may be isotropically etched by a wet etching. For example, as the protecting layer **140** is isotropically etched by the wet etching, the protecting pattern **142** is more etched than an edge portion of the photoresist pattern **150** to generate an undercut at the protecting pattern **142**. As best shown in the enlarged view of portion 'A' in FIG. 9, reference numeral **142a** denotes the undercut.

In alternative embodiments, when the protecting layer **140** is patterned using the photoresist pattern **150** as the mask, the protecting layer **140** may be anisotropically etched by a dry etching. For example, after the protecting layer **140** is anisotropically etched by the dry etching, the protecting layer **140** may be isotropically etched by the wet etching to generate the undercut **142a** at the protecting pattern **142**.

FIG. 10 is a cross-sectional view of an exemplary embodiment of a transparent conductive thin layer formed on the substrate in FIG. 9.

Referring to FIG. 10, a transparent conductive material is deposited on the substrate **100**. The transparent conductive material may include, but is not limited to, indium zinc oxide (IZO). In alternative embodiments, the transparent conductive material may include amorphous indium tin oxide (a-ITO), indium tin oxide (ITO), and the like, as well as combinations including at least one of the foregoing.

In exemplary embodiments, as the transparent conductive material is formed on the substrate **100**, a conductive layer **160** may be formed on the photoresist pattern **150**. As shown in the exemplary embodiment of FIG. 10, a pixel electrode **170** is formed on the gate insulating layer **114**, and the pixel electrode **170** is electrically separated from the conductive layer **160** since the undercut **142a** is formed between the conductive layer **160** and the pixel electrode **170**.

FIG. 11 is a cross-sectional view of an exemplary embodiment of the substrate in FIG. 10 with a part of a photoresist pattern and a conductive layer removed.

Referring to FIG. 11, after the conductive layer **160** and the pixel electrode **170** are formed on the substrate **100**, a stripping composition **184** may be sprayed on the substrate **100** through, for example, a dispenser **182**.

In exemplary embodiments, the stripping composition **184** may include a stripping agent for the photoresist layer and a stripping additive for the conductive layer. For example, the stripping agent for the photoresist layer may react with the photoresist pattern **150** to remove the photoresist pattern **150**. In alternative embodiments, the stripping additive for the conductive layer may etch the conductive layer **160**.

The stripping composition may include as the stripping agent for the photoresist layer, an amine-based compound, a protonated glycol-based compound, a deprotonated multipolar compound, and the like, as well as any combination including at least one of the foregoing. The stripping additive for the conductive layer may include, but is not limited to a thiol-based compound, an oxalic acid derivative.

The stripping composition will be later described in detail.

In exemplary embodiments, the stripping composition may strip the photoresist pattern **150**, remove the conductive layer **160**, and etch the pixel electrode **170** since the stripping composition may include the stripping agent for the photoresist layer and the stripping additive for the conductive layer.

Referring to FIG. **11**, when the stripping composition **184** is sprayed on the photoresist pattern **150**, the conductive layer **160** and the pixel electrode **170** formed on the photoresist pattern **150**, even the conductive layer **160** and the pixel electrode **170** may be etched by the stripping composition while the photoresist pattern **150** is stripped.

The photoresist pattern **150** may be primarily stripped, and then the conductive layer **160** and the pixel electrode **170** may be etched. Advantageously, stripping time for stripping the photoresist pattern **150** may be properly controlled.

A required time for removing the conductive layer **160**, formed on the photoresist pattern **150**, from the substrate **100** by stripping the photoresist pattern **150** using the stripping composition **184** may be defined as a first time. A required time for completely etching the conductive layer **160** and the pixel electrode **170** using the stripping composition **184** is defined as a second time. The first and second times may be defined by a relationship represented by Formula 1.

$$\frac{\text{The first time}}{\text{The second time}} \quad [\text{Formula 1}],$$

The stripping composition **184** is sprayed on the substrate **100** to separate the conductive layer **160** from the substrate **100** within the first time, so that the pixel electrode **170** is essentially prevented from being damaged by the stripping composition **184**. In exemplary embodiments, the first time may range from about 2 minutes to about 4 minutes when the stripping composition described above is used. In alternative embodiments, the first time may preferably range from about 2.5 minutes to about 3 minutes.

The parts of the conductive layer **160** separated from the substrate **100** after applying the stripping composition **184** are flowed into a storage tank **186** with residual stripping composition **184**. The separated conductive layer **160** that flows into the storage tank **186** with the residual stripping composition **184** may be completely dissolved within the second time. In exemplary embodiments, the second time may range from about 10 minutes to about 30 minutes when the stripping composition **184** described above is used.

In alternative embodiments, when the separated conductive layer **160** is completely dissolved in the storage tank **186**, the stripping composition **184** may be recycled to be provided again to the dispenser **182**. For example, the stripping composition **184** may be repeatedly used in a follow-up process.

In exemplary embodiments, the photoresist pattern **150** may be stripped at a temperature ranging from about 60° C. to about 80° C., and the conductive layer **160** may be dissolved at a temperature ranging from about 60° C. to about 80° C.

FIG. **12** is a cross-sectional view of an exemplary embodiment of a thin film substrate without the photoresist pattern and the conductive layer in FIG. **11**.

Referring to FIG. **12**, the photoresist pattern **150** may be stripped by the stripping composition **184**, and parts of the conductive layer **160** may be separated from the substrate **100** to be flowed into the storage tank **186**. Advantageously, a thin film transistor and the pixel electrode **170** remain on the substrate **100**. In exemplary embodiments, the substrate **100** may be preferably cleaned to effectively prevent the pixel electrode **170** from being damaged by the stripping composition **184** remaining on the substrate **100**.

An Exemplary Embodiment of a Stripping Composition

An exemplary embodiment of a stripping composition will be described in detail hereinafter.

As discussed earlier, the stripping composition may include a stripping agent for a photoresist layer and a stripping additive for a conductive layer. In exemplary embodiments, the stripping agent for the photoresist layer may strip a photoresist pattern, and the stripping additive for the conductive layer may etch the conductive layer. The stripping agent for the photoresist layer may include an amine-based compound, a protonated glycol-based compound, a deprotonated multipolar compound and the like, as well as any combination including at least one of the foregoing. The stripping additive for the conductive layer may include a thiol-based compound.

Examples of the amine-based compound may include, but are not limited to, mono ethanol amine, mono isopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine and the like. These compounds may be used alone or in a mixture thereof.

In exemplary embodiments, when a content of the amine-based compound is less than about 20 percent by weight, the photoresist pattern may not be sufficiently stripped in a period of time. In other exemplary embodiments, when the content of the amine-based compound exceeds about 40 percent by weight, a pixel electrode may be excessively etched and/or be damaged while the photoresist pattern is stripped. Further, when the content of the amine-based compound exceeds about 40 percent by weight, an amount of evaporated stripping composition **184** may increase to change the contents of components in the stripping composition **184**.

In alternative embodiments, where the photoresist pattern may be sufficiently stripped and/or the pixel electrode may not be excessively etched or damaged, the content of the stripping composition ranges from about 20 percent by weight to about 40 percent by weight. In other alternative embodiments, the content of the stripping composition may preferably range from about 25 percent by weight to about 35 percent by weight.

Examples of the protonated glycol-based compound may include, but are not limited to, butyldiglycol, diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol, and the like. These compounds may be used alone or in a mixture thereof.

In exemplary embodiments, when a content of the protonated glycol-based compound is less than about 20 percent by weight, dissolution of the photoresist layer may excessively decrease. In other exemplary embodiments, when the content of the protonated glycol-based compound exceeds about 50 percent by weight, sediment may be generated. In alternative embodiments where the photoresist layer dissolution may not essentially decrease excessively and/or no sediment may effectively be generated, the content of the protonated glycol-based compound may range from about 20 percent by weight to about 50 percent by weight.

Examples of the deprotonated multipolar compound may include, but are not limited to, N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole, and the like. These compounds may be used alone or in a mixture thereof.

In exemplary embodiments, when a content of the deprotonated multipolar compound is less than about 20 percent by weight, stripping time of the photoresist pattern may increase, thereby inducing a damage of the conductive layer. Here, the damage may be caused by thiol-based compound. In other exemplary embodiments, when the content of the deprotonated multipolar compound exceeds about 40 percent by weight, the conductive layer may be etched while etching the photoresist pattern. In alternative embodiments, when the

stripping time of the photoresist pattern may not effectively increase and/or the conductive layer may be essentially undamaged and/or unetched, the content of the deprotonated multipolar compound may range from about 20 percent by weight to about 40 percent by weight. In alternative embodiments, the content of the deprotonated multipolar compound may preferably range from about 25 percent by weight to about 35 percent by weight.

In alternative embodiments, the stripping additive may include a thiol-based compound or an oxalic acid derivative. In other alternative embodiments, the thiol-based compound may be preferable to the oxalic acid derivative. Examples of the thiol-based compound may include, but are not limited to, a thiobenzoic acid, thiol acid, and the like. These compounds may be used alone or in a mixture thereof.

In exemplary embodiments, when a content of the thiol-based compound is less than about 0.5 percent by weight, the conductive layer may not be completely dissolved in the stripping composition, such that recycling of the stripping composition may be difficult. In other exemplary embodiments, when the content of the thiol-based compound exceeds about 3 percent by weight, sediment may be generated in the stripping composition. In alternative embodiments, the content of the thiol-based compound may range from about 0.5 percent by weight to about 3 percent by weight. In other alternative embodiments, when the conductive layer may essentially be dissolved and/or no sediment is effectively generated, the content of the thiol-based compound may preferably range from about 1.5 percent by weight to about 2 percent by weight.

Hereinafter, an exemplary embodiment of the present invention is described in detail with reference to the following examples. The examples are given solely for the purpose of illustration and are not to be construed as limitations of the present invention, as many variations thereof are possible without departing from the spirit and scope of the invention.

EXAMPLES 1 TO 3

About 100 ml of a stripping composition was acquired according to a composition of Table 1.

TABLE 1

Example	Composition (percents by weight)				
	Amine-based compound Monoethanol amine	Protonated glycol-based compound		Deprotonated multipolar compound	Thiol-based compound Thiol
	amine	Butyldiglycol	Ethyleneglycol	N-methyl-2-pyrrolidone	acid
Example 1	30	25	14	30	1
Example 2	30	25	13.5	30	1.5
Example 3	30	25	13	30	2

55

Experiment 1: Estimation of Solvating Power of an IZO Conductive layer

Each of the stripping compositions of Examples 1, 2 and 3 was heated to a temperature of about 70° C., and then the heated stripping compositions were added to an indium zinc oxide (IZO) layer (550 Å) and kept for about 30 minutes. Then, dissolution of the conductive layer was observed.

FIG. 13A is a picture of a surface of the conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 1. FIG. 13B is a picture of a surface of the

conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 2. FIG. 13C is a picture of a surface of the conductive layer dissolved by an exemplary embodiment of a stripping composition of Example 3.

Referring to FIGS. 13A to 13C, the IZO layer is shown completely dissolved within about 30 minutes of the addition of the heated stripping compounds. Advantageously, the stripping composition may completely dissolve the conductive layer within about 30 minutes of a processing time.

Experiment 2: Measuring an Eluted Amount of Indium and Zinc

Each of the stripping compositions of Examples 1 and 3 was sprayed on the thin film transistor substrate after the photoresist pattern was completely stripped. Eluted amounts of indium and zinc were respectively measured. Results are shown in Table 2. The stripping composition of Example 3 was sprayed on the thin film transistor substrate before the photoresist pattern was stripped, then the eluted amounts of indium and zinc were respectively measured. Results are shown in Table 3.

TABLE 2

Metal	Example	After PR stripping		
		3 minutes (ppb)	10 minutes (ppb)	30 minutes (ppb)
Indium	Example 1	16.2	68.9	230.1
	Example 3	20.7	95.2	291.5
Zinc	Example 1	2.4	4.6	9.8
	Example 3	3.4	4.2	15.7

30

35

TABLE 3

Metal	Example	Before PR stripping		
		3 minutes (ppb)	10 minutes (ppb)	30 minutes (ppb)
Indium	Example 3	125.2	206.8	358.2
Zinc	Example 3	11.9	16.4	20.7

60

65

11

Referring to Tables 3 and 4, the eluted amount of the metal after PR stripping shows a difference of about 100 ppb with respect to the eluted amount of the metal before PR stripping. Advantageously, the conductive layer on the photoresist pattern is removed during the PR stripping.

Experiment 3: Variation of Content of Amine

About 1000 ml of PR stripper (commercially available as a trade name of PRS-2000, manufactured by Dong-woo finechem Co., Korea) as a Comparative Example and about 1000 ml of the stripping composition of Example 2 were exhausted by forced exhaust (FE) type. Variation of the content of amine was measured during the exhausting process. Results are shown in Table 4.

TABLE 4

	10 minutes (ml)	20 minutes (ml)	30 minutes (ml)	40 minutes (ml)
Comparative Example	10	20	30	40.5
Example 4	7	10.5	14	15

Referring to Table 4, variation of the content of amine in the stripping composition of Example 4 was lower than variation of the content of amine in the stripper of Comparative Example. Advantageously, the stripping composition according to an exemplary embodiment of the present invention may have an excellent stability.

As discussed above, the exemplary embodiments of a method of manufacturing a thin film transistor substrate may improve an efficiency of manufacturing process for the thin film transistor substrate.

Further, the exemplary embodiments of the stripping composition used for the manufacturing process of thin film transistor substrate discussed above, may dissolve the photoresist and/or the conductive layer. Advantageously, solid components may not remain in the used stripping composition, such that the used stripping composition may be recycled and reused in the process of manufacturing the follow-up thin film transistor substrate. As a further advantage, the stripping composition may have the excellent stability.

What is claimed is:

1. A stripping composition comprising:

a stripping agent for stripping a photoresist layer, the stripping agent comprising:

about 20 percent by weight to about 40 percent by weight of an amine-based compound;

about 20 percent by weight to about 50 percent by weight of a protonated glycol-based compound; and

about 20 percent by weight to about 40 percent by weight of a deprotonated multipolar compound; and

a stripping additive for stripping a conductive layer, the stripping additive comprising about 0.5 percent by weight to about 3 percent by weight of a thiol-based compound.

2. The stripping composition of claim 1, wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing.

3. The stripping composition of claim 1,

wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoet-

12

hoxyethanol amine or any combination including at least one of the foregoing, and

wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing.

4. The stripping composition of claim 1,

wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing,

wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing, and

wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing.

5. The stripping composition of claim 1,

wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing,

wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing,

wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing, and

wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.

6. The stripping composition of claim 1,

wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing,

wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing, and

wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.

7. The stripping composition of claim 1,

wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing, and

wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing.

13

8. The stripping composition of claim 1,
 wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing,
- wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing, and
- wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.
9. The stripping composition of claim 1,
 wherein the amine-based compound comprises monoethanol amine, monoisopropanol amine, methylmethanol amine, ethylethanol amine, dimethanol amine, aminoethoxyethanol amine or any combination including at least one of the foregoing, and
- wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.
10. The stripping composition of claim 1, wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing.
11. The stripping composition of claim 1,
 wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing, and
- wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing.

14

12. The stripping composition of claim 1,
 wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing,
- wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing, and
- wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.
13. The stripping composition of claim 1,
 wherein the protonated glycol-based compound comprises diethyleneglycol methylether, diethyleneglycol ethylether, diethyleneglycol propylether, diethyleneglycol butylether, ethyleneglycol or any combination including at least one of the foregoing, and
- wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.
14. The stripping composition of claim 1, wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing.
15. The stripping composition of claim 1,
 wherein the deprotonated multipolar compound comprises N-methyl-2-pyrrolidone, N,N-dimethyl acetamide, N,N-dimethyl formamide, N,N-dimethyl imidazole or any combination including at least one of the foregoing, and
- wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.
16. The stripping composition of claim 1, wherein the thiol-based compound comprises thio benzoic acid, thiol acid or any combination including at least one of the foregoing.

* * * * *