

#### US007886419B2

# (12) United States Patent

# Huang et al.

# (54) STENT CRIMPING APPARATUS AND METHOD

(75) Inventors: **Bin Huang**, Pleasanton, CA (US); **David** 

C. Gale, San Jose, CA (US); Daniel Castro, Santa Clara, CA (US)

(73) Assignee: Advanced Cardiovascular Systems,

Inc., Santa Clara, CA (US)

(\*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 1113 days.

(21) Appl. No.: 11/489,309

(22) Filed: **Jul. 18, 2006** 

# (65) Prior Publication Data

US 2008/0016668 A1 Jan. 24, 2008

(51) **Int. Cl.** 

**G01M 19/00** (2006.01) B23Q 3/00 (2006.01)

29/283

29/283.5 See application file for complete search history.

# (56) References Cited

### U.S. PATENT DOCUMENTS

3,687,135	$\mathbf{A}$	8/1972	Stroganov et al.
3,839,743	A	10/1974	Schwarcz
3,900,632	A	8/1975	Robinson
4,104,410	A	8/1978	Malecki
4,110,497	A	8/1978	Hoel
4,321,711	A	3/1982	Mano

# (10) Patent No.: US 7,886,419 B2

Feb. 15, 2011

4,346,028	A	8/1982	Griffith
4,596,574	A	6/1986	Urist
4,599,085	A	7/1986	Riess et al.
4,612,009	A	9/1986	Drobnik et al.
4,633,873	A	1/1987	Dumican et al.
4,656,083	A	4/1987	Hoffman et al.
4,718,907	A	1/1988	Karwoski et al.
4,722,335	A	2/1988	Vilasi
4,723,549	A	2/1988	Wholey et al.
4,732,152	A	3/1988	Wallstén et al.
4,733,665	A	3/1988	Palmaz
4,739,762	A	4/1988	Palmaz
4,740,207	A	4/1988	Kreamer
4,743,252	A	5/1988	Martin, Jr. et al.
4,768,507	A	9/1988	Fischell et al.
4,776,337	A	10/1988	Palmaz

(45) **Date of Patent:** 

## (Continued)

## FOREIGN PATENT DOCUMENTS

DE 44 07 079 9/1994

(Continued)

#### OTHER PUBLICATIONS

International Search Report for PCT/US2007/016200, filed Jul. 17, 2007, mailed Nov. 21, 2007, 5 pgs.


(Continued)

Primary Examiner—Essama Omgba (74) Attorney, Agent, or Firm—Suire, Sanders & Dempsey LLP.

# (57) ABSTRACT

A method for crimping a stent onto a balloon includes inflating a balloon with a fluid, sliding a stent over the inflated balloon, crimping the stent onto the balloon, and controlling the pressure inside the balloon below a given value when the stent is being crimped onto the balloon.

# 21 Claims, 3 Drawing Sheets



# US 7,886,419 B2 Page 2

U.S. F	PATENT	DOCUMENTS	5,599,922	A	2/1997	Gryaznov et al.
4.000.000	1/1000		5,605,696	A		Eury et al.
4,800,882 A		Gianturco Tuest al	5,607,442			Fischell et al.
4,816,339 A 4,818,559 A		Tu et al. Hama et al.	5,607,467		3/1997	
4,850,999 A	7/1989		5,618,299			Khosravi et al.
4,877,030 A		Beck et al.	5,629,077			Turnlund et al.
, ,		Lindemann et al.	5,631,135			Gryaznov et al.
, ,		Greco et al.	5,632,771 5,632,840			Boatman et al.
, ,	12/1989		5,637,113			Campbell Tartaglia et al.
4,902,289 A	2/1990		5,649,977			Campbell
4,977,901 A	12/1990	Ofstead	5,667,767			Greff et al.
4,994,298 A	2/1991	Yasuda	5,667,796		9/1997	
5,019,090 A	5/1991	Pinchuk	5,670,558			Onishi et al.
5,028,597 A	7/1991	Kodama et al.	5,693,085			Buirge et al.
5,059,211 A	10/1991	Stack et al.	5,700,286	A		Tartaglia et al.
,		Pryor et al.	5,707,385	A	1/1998	Williams
5,084,065 A		Weldon et al.	5,711,763	A	1/1998	Nonami et al.
5,085,629 A		Goldberg et al.	5,716,981	A	2/1998	Hunter et al.
5,100,429 A		Sinofsky et al.	5,725,549		3/1998	
5,104,410 A		Chowdhary	5,726,297			Gryaznov et al.
5,108,417 A 5,108,755 A		Sawyer Daniels et al.	5,728,751			Patnaik
5,112,457 A		Marchant	5,733,326			Tomonto et al.
5,123,917 A	6/1992		5,733,330		3/1998	
5,147,385 A		Beck et al.	5,733,564			Lehtinen Kunz et el
5,156,623 A		Hakamatsuka et al.	5,733,925 5,741,881			Kunz et al. Patnaik
, ,		Pinchuk et al.	5,756,457			Wang et al.
, ,	11/1992		5,756,476			Epstein et al.
5,163,958 A	11/1992	Pinchuk	5,765,682			Bley et al.
5,167,614 A	12/1992	Tessmann et al.	5,766,204			Porter et al.
5,192,311 A	3/1993	King et al.	5,766,239		6/1998	
5,197,977 A	3/1993	Hoffman, Jr. et al.	5,766,710			Turnlund et al.
5,234,456 A		Silvestrini	5,769,883	A	6/1998	Buscemi et al.
5,234,457 A		Andersen	5,780,807	A	7/1998	Saunders
5,236,447 A		Kubo et al.	5,800,516	A	9/1998	Fine et al.
5,279,594 A		Jackson	5,811,447			Kunz et al.
5,282,860 A		Matsuno et al.	5,824,049			Ragheb et al.
5,289,831 A	3/1994		5,830,178			Jones et al.
5,290,271 A 5,292,321 A	3/1994	Jernberg Lee	5,830,461		11/1998	
5,306,286 A		Stack et al.	5,830,879		11/1998	
5,306,294 A		Winston et al.	5,833,651			Donovan et al.
5,328,471 A		Slepian	5,834,582 5,836,962		11/1998	Sinclair et al.
5,330,500 A	7/1994	<b>-</b>	5,836,965			Jendersee et al.
5,342,348 A		Kaplan	5,837,313			Ding et al.
5,342,395 A	8/1994	Jarrett et al.	5,837,835			Gryaznov et al.
5,342,621 A	8/1994	Eury	5,840,083			Braach-Maksvytis
5,356,433 A	10/1994	Rowland et al.	5,851,508			Greff et al.
5,383,925 A	1/1995	Schmitt	5,853,408		12/1998	Muni
5,385,580 A		Schmitt	5,854,207	A	12/1998	Lee et al.
5,389,106 A	2/1995		5,855,612	A	1/1999	Ohthuki et al.
5,399,666 A	3/1995		5,855,618			Patnaik et al.
5,423,885 A		Williams Wharren et al	5,858,746			Hubbell et al.
5,441,515 A 5,443,458 A		Khosravi et al. Eury et al.	5,865,814		2/1999	
5,443,500 A		Sigwart	5,868,781		2/1999	
5,455,040 A		Marchant	5,873,904			Ragheb et al.
, ,		Berg et al.	5,874,101 5,874,109			Zhong et al. Ducheyne et al.
5,502,158 A		Sinclair et al.	5,874,165			Drumheller
5,514,379 A		Weissleder et al.	5,876,743			Ibsen et al.
5,527,337 A	6/1996	Stack et al.	5,877,263			Patnaik et al.
5,545,408 A	8/1996	Trigg et al.	5,879,713			Roth et al.
5,546,646 A *	8/1996	Williams et al 29/407.08	5,888,533		3/1999	
5,554,120 A		Chen et al.	5,891,192			Murayama et al.
5,556,413 A	9/1996		5,897,955			Drumheller
, ,		Liu et al.	5,906,759		5/1999	Richter
, ,		Haimovich et al.	5,913,871	A	6/1999	Werneth et al.
5,591,199 A		Porter et al.	5,914,182			Drumheller
5,591,607 A		Gryaznov et al.	5,916,870			Lee et al.
5,593,403 A			5,922,005			Richter et al.
5,593,434 A		Williams	5,942,209			Leavitt et al.
5,599,301 A	2/1997	Jacobs et al.	5,948,428	A	9/1999	Lee et al.

# US 7,886,419 B2 Page 3

5,954,744 A		9/1999	Phan et al.	6,312,459	В1	11/2001	Huang et al.
5,957,975 A		9/1999	Lafont et al.	6,327,772	B1	12/2001	Zadno-Azizi et al.
5,965,720 A	1	0/1999	Gryaznov et al.	4,733,665	C2	1/2002	Palmaz
, ,			Conway et al.	6,375,826		4/2002	Wang et al.
•			Solar 606/108	6,379,381			Hossainy et al.
•				,			
,			Whelan et al 623/1.12	6,387,121		5/2002	
5,976,182 A	1	1/1999	Cox	6,388,043	BI	5/2002	Langer et al.
5,980,564 A	1	1/1999	Stinson	6,395,326	B1	5/2002	Castro et al.
5,980,928 A	1	1/1999	Terry	6,409,761	B1	6/2002	Jang
5,980,972 A		1/1999		6,423,092			Datta et al.
5,981,568 A				6,461,632			
, ,				, ,			Gogolewski
5,986,169 A			5	6,464,720			Boatman et al.
5,997,468 A	1	2/1999	Wolff et al.	6,479,565	B1	11/2002	Stanley
6,009,614 A	*	1/2000	Morales 29/516	6,485,512	B1	11/2002	Cheng
6,010,445 A		1/2000	Armini et al.	6,492,615	B1	12/2002	Flanagan
6,015,541 A				6,494,908			Huxel et al.
, ,				, ,			
6,042,875 A			Ding et al.	6,495,156			Wenz et al.
6,048,964 A			Lee et al.	6,511,748			Barrows
6,051,648 A		4/2000	Rhee et al.	6,517,888	B1	2/2003	Weber
6,056,993 A		5/2000	Leidner et al.	6,527,801	B1	3/2003	Dutta
6,060,451 A			DiMaio et al.	6,537,589			Chae et al.
6,063,092 A			Shin 606/108	6,539,607			Fehring et al.
, ,				, ,			
6,066,156 A		5/2000		6,540,777			
6,071,266 A		6/2000	Kelley	6,554,854	Вl	4/2003	Flanagan
6,074,659 A		6/2000	Kunz et al.	6,565,599	B1	5/2003	Hong
6,080,177 A		6/2000	Igaki et al.	6,569,191	B1	5/2003	Hogan
6,080,488 A			Hostettler et al.	6,569,193			Cox et al.
, ,				, ,			
6,083,258 A		7/2000		6,572,672			Yadav et al.
6,093,463 A		7/2000	Thakrar	6,574,851	BI	6/2003	Mirizzi
6,096,070 A		8/2000	Ragheb et al.	6,579,305	B1	6/2003	Lashinski
6,096,525 A		8/2000	Patnaik	6,585,755	B2	7/2003	Jackson et al.
6,099,562 A			Ding et al.	6,592,614			Lenker et al.
, ,				, ,			
6,103,230 A			Billiar et al.	6,592,617			Thompson
6,107,416 A			Patnaik et al.	6,613,072			Lau et al.
6,110,188 A		8/2000	Narciso, Jr.	6,626,939	B1	9/2003	Burnside et al.
6,113,629 A		9/2000	Ken	6,635,269	B1	10/2003	Jennissen
6,117,979 A			Hendriks et al.	, ,			Vallana et al.
6,120,536 A			Ding et al.	, ,			Santini, Jr. et al.
, ,				, ,			,
6,120,904 A			Hostettler et al.	6,664,335			
6,121,027 A		9/2000	Clapper et al.	6,666,214	B2	12/2003	Canham
6,125,523 A	1	0/2000	Brown et al.	6,666,880	B1 *	12/2003	Chiu et al 623/1.11
6,127,173 A	1	0/2000	Eckstein et al.	6,667,049	B2	12/2003	Janas et al.
6,129,761 A			Hubbell	6,669,723			Killion et al.
, ,				, ,			
6,129,928 A			Sarangapani et al.	6,676,697			
6,150,630 A	1	1/2000	Perry et al.	6,679,980	BI	1/2004	Andreacchi
6,153,252 A	1	1/2000	Hossainy et al.	6,689,375	B1	2/2004	Wahlig et al.
4,776,337 A	1	2/2000	Palmaz	6,695,920	B1	2/2004	Pacetti et al.
6,159,951 A	1	2/2000	Karpeisky et al.	6,706,273	B1	3/2004	Roessler
6,160,084 A			Langer et al.	6,709,379			Brandau et al.
, ,				, ,			
6,165,212 A			Dereume et al.	6,719,934			Stinson
6,166,130 A			Rhee et al.	6,719,989			Matsushima et al.
6,169,170 B1		1/2001	Gryaznov et al.	6,720,402	B2	4/2004	Langer et al.
6,171,609 B1		1/2001	Kunz	6,745,445	B2 *	6/2004	Spilka 29/407.08
6,174,330 B1		1/2001	Stinson	6,746,773	B2		Llanos et al.
6,177,523 B1			Reich et al.	6,752,826			Holloway et al.
, ,				, ,			-
6,183,505 B1			Mohn, Jr. et al.	6,753,007			Haggard et al.
6,187,045 B1			Fehring et al.	6,764,505			Hossainy et al.
6,210,715 B1			Starling et al.	6,769,161			Brown et al 29/234
6,224,626 B1		5/2001	Steinke	6,818,063	B1	11/2004	Kerrigan
6,228,845 B1		5/2001	Donovan et al.	6,846,323			Yip et al.
6,240,616 B1		6/2001		,			Schwager et al 623/1.11
6,245,076 B1		6/2001		·			
, ,				·			Rogers et al 606/194
6,245,103 B1		6/2001		, ,			Amis et al.
6,248,344 B1		6/2001	Ylanen et al.	7,563,400	B2 *	7/2009	Wilson et al 264/249
6,251,135 B1		6/2001	Stinson et al.	2001/0044652	$\mathbf{A}1$	11/2001	Moore
6,251,142 B1			Bernacca et al.	2002/0002399			Huxel et al.
6,273,913 B1			Wright et al.				Heublein et al.
, ,							
6,281,262 B1			Shikinami Wana at al	2002/0004101			Ding et al.
6,284,333 B1			Wang et al.	2002/0062148		5/2002	
6,287,332 B1		9/2001	Bolz et al.	2002/0065553	Al	5/2002	
6 6 6 6 7 F 4		9/2001	Heath	2002/0111590	$\mathbf{A}1$	8/2002	Davila et al.
6,290,721 B1						0/0000	
6,290,721 B1 6,293,966 B1		9/2001	Frantzen	2002/0116050	$\mathbf{A}1$	8/2002	Kocur
, ,				2002/0116050 2002/0138133			

2002/01611	14 A1 10/2	002 Gunatillake et al.	WO	WO 00/64506	11/2000
2003/00330		003 Igaki	WO	WO 01/01890	1/2001
2003/00554		003 Schwager et al.	WO	WO 02/30487	4/2002
2003/00563		003 Brown et al.	WO	WO 2004/023985	3/2004
2003/00931	07 A1 5/2	003 Parsonage et al.	VVO	W O 2004/023303	3/2004
2003/01008	65 A1 5/2	003 Santini, Jr. et al.			
2003/01055	18 A1 6/2	003 Dutta		OTHER D	UBLICATIONS
2003/01055	30 A1 6/2	003 Pirhonen		OTTIERT	ODLICATIONS
2003/01710		003 Sanders	U.S. Ar	opl. No. 10/317,435, file	ed Dec. 11, 2002, Hossainy et al.
2003/01874		003 Cully et al.		<del>-</del>	ent mounted on a catheter having opti-
2003/02082		003 Penhasi		•	pabilities, Research Disclosure, Sep.
2003/02098		003 Chun et al.		p. 1159-1162.	
2003/02268 2003/02365		003 Shapovalov et al. 003 Fifer	Ansari,	End-to-end tubal ana	stomosis using an absorbable stent,
2003/02303		003 Filel 004 Spilka	Fertility	y and Sterility, vol. 32(2	2), pp. 197-201 (Aug. 1979).
2004/00930		004 Splika 004 White et al.	Ansari,	Tubal Reanastomosis &	Using Absorbable Stent, International
2004/00980		004 Winte et al.	Journal	of Fertility, vol. 23(4),	pp. 242-243 (1978).
2004/01111		004 Stinson	Bull, Pa	arylene Coating for Me	edical Applications, Medical Product
2004/01279		004 Weber	Manufa	acturing News 18, 1 pg.	(Mar. 1993).
2004/01433		004 Stinson et al.	Casper	et al., Fiber-Reinforcea	d Absorbable Composite for Orthope-
2004/01676	510 A1 8/2	004 Fleming, III	dic Sur	gery, Polymeric Materi	als Science and Engineering, vol. 53
2005/01437	752 A1* 6/2	005 Schwager et al	606/108 pp. 497	<sup>-501</sup> (1985).	
2006/00098	32 A1* 1/2	006 Fisher	623/1.11 Detwei	ler et al., Gastrointes:	tinal Sutureless Anastomosis Using
2006/00473		006 Gale et al.		· ·	the Sliding Absorbable Intraluminal
2006/01428		006 Rizq et al		<b>-</b>	ent of a Stent Placement Device, Jour-
2006/02885		006 Roach et al			1. 9(2), pp. 111-130 (Mar. /Apr. 1996).
2007/00064		007 McNiven et al	55.5 (4.4.5	, ,	bable, Reinforced Ring and an Axially
2007/01297		007 Beach et al	-0/-00		evice for Sutureless Fibrin Glue
2007/02044		007 Knott et al	20/200	•	Journal of Investigative Surgery, vol.
2007/02891 2008/00013		007 Huang et al 008 Kent et al	- \-'/' FT	o. 495-504 (Nov./Dec. 1	
2008/00013		008 Lafont et al	20/516		stomosis of the Small Intestine and the
2009/00888		009 Wang et al	CO1011 1	0	rbable Intraluminal Stent and Fibrin
2009/02085		009 Faucher et al	424/422	ournal of investigative	Surgery, vol. 8(2), pp. 129-140 (Mar.
		009 Wilson et al	(22/1.11	1 am at al Cutumalana Ch	alagustojojam astomu ju Dies Ilsina su
2010/00635		010 Roach et al	622/1.11 Detwei	· ·	olecystojejunostomy in Pigs Using an and Eibrin Glue, Journal of Investi-
			AUSOFU	Surgery, vol. 9(1), pp. 1	· ·
]	FOREIGN PA	ATENT DOCUMENTS	_		Conformal Coatings for Implantable
DE	197 31 021	1/1999		•	sactions on Biomedical Engineering,
DE	197 51 021	1/1999		/IE-27(11), pp. 671-675	
EP	0 108 171	5/1984		· /· II	tion Reactions Combined with Free-
EP	0 144 534	6/1985			Design of Materials for Tissue Engi-
EP	0 364 787	4/1990		0.0	vol. 2, pp. 430-441 (2001).
EP	0 397 500	11/1990			f Glow-Discharge-Polymerized Films
EP	0 464 755	1/1992			ne, J Applied Polymer Sci, vol. 38, pp.
EP	0 493 788	7/1992	55-64 (		, <u>-</u> ,,,
$\mathbf{EP}$	0 554 082	8/1993	Hahn e	t al., Glow Discharge	Polymers as Coatings for Implanted
EP	0 578 998	1/1994		s, ISA, pp. 109-111 (19	
EP	0 604 022	6/1994			Blood Flow Following Small Artery
EP	0 621 017	10/1994		,	Dissolvable Stent, Microsurgery, vol.
EP	0 623 354	11/1994		p. 148-152 (1999).	
EP	0 665 023	8/1995	Kelley	et al., Totally Resorbabl	le High-Strength Composite Material,
EP	0 709 068	5/1996	•		ners, vol. 35, pp. 75-85 (1987).
EP	0 970 711	1/2000	Kubies	et al., Microdomain Str	ructure In polylactide-block-poly(eth-
EP GB	1295570 2 247 696	A2 * 3/2003 3/1992		•	Biomaterials, vol. 21, pp. 529-536
	WO 89/03232	3/1992 4/1989	(2000).	, , ,	
	WO 89/03232 WO 90/01969	3/1990	Kutryk	et al., Coronary Stentin	g: Current Perspectives, a companion
	WO 90/01909 WO 90/04982	5/1990	-	•	Stents, pp. 1-16 (1999).
	WO 90/04982	6/1990	Martin	et al., Enhancing the	biological activity of immobilized
	WO 91/17744	11/1991		· · · · · · · · · · · · · · · · · · ·	ollagen affinity coating, J. Biomed.
	WO 91/17789	11/1991	•	Res., vol. 70A, pp. 10-1	
	WO 92/10218	6/1992	Maudui	it et al., <i>Hydrolytic degr</i>	adation of films prepared from blends
WO	WO 93/06792	4/1993			ght poly(DL-lactic acid)s, J. Biomed.
WO	WO 94/21196	9/1994	Mater.	Res., vol. 30, pp. 201-2	07 (1996).
WO	WO 95/29647	11/1005	Middle	ton et al. Swethetic bi	odegradable polymers as orthopedic

WO

WO

WO

WO

WO

WO

WO

WO 95/29647

WO 98/04415

WO 99/03515

WO 99/15106

WO 99/16386

WO 99/42147

WO 00/12147

11/1995

2/1998

1/1999

4/1999

4/1999

8/1999

3/2000

Middleton et al., Synthetic biodegradable polymers as orthopedic

Muller et al., Advances in Coronary Angioplasty: Endovascular

Nichols et al., Electrical Insulation of Implantable Devices by Com-

posite Polymer Coatings, ISA Transactions, vol. 26(4), pp. 15-18

Stents, Coron. Arter. Dis., vol. 1(4), pp. 438-448 (Jul./Aug. 1990).

devices, Biomaterials, vol. 21, pp. 2335-2346 (2000).

(1987).

Peuster et al., A novel approach to temporary stenting: degradable cardiovascular stents produced from corrodible metal-results 6-18 months after implantation into New Zealand white rabbits, Heart, vol. 86, pp. 563-569 (2001).

Pietrzak et al., *Bioabsorbable Fixation Devices: Status for the Craniomaxillofacial Surgeon*, J. Craniofaxial Surg., vol. 2, pp. 92-96 (1997).

Pietrzak et al., *Bioresorbable implants— practical considerations*, Bone, vol. 19, No. 1, Supplement Jul. 1996, pp. 109S-119S.

Redman, Clinical Experience with Vasovasostomy Utilizing Absorbable Intravasal Stent, Urology, vol. 20(1), pp. 59-61 (Jul. 1982).

Rust et al., The Effect of Absorbable Stenting on Postoperative Stenosis of the Surgically Enlarged Maxillary Sinus Ostia in a Rabbit Animal Model, Archives of Otolaryngology, vol. 122(12) pp. 1395-1397 (Dec. 1996).

Schatz, A View of Vascular Stents, Circulation, vol. 79(2), pp. 445-457 (Feb. 1989).

Schmidt et al., Long-Term Implants of Parylene-C Coated Microelectrodes, Med & Biol Eng & Comp, vol. 26(1), pp. 96-101 (Jan. 1988).

Spagnuolo et al., Gas 1 is induced by VE-cadherin and vascular endothelial growth factor and inhibits endothelial cell apoptosis, Blood, vol. 103, pp. 3005-3012 (2004).

Tamai et al., *Initial and 6-Month Results of Biodegradable Poly-l-Lactic Acid Coronary Stents in Humans*, Circulation, pp. 399-404 (Jul. 25, 2000).

Tsuji et al., *Biodegradable Polymeric Stents*, Current Interventional Cardiology Reports, vol. 3, pp. 10-17 (2001).

Völkel et al., Targeting of immunoliposomes to endothelial cells using a single—chain Fv fragment directed against human endoglin (CD105), Biochimica et Biophysica Acta 1663, pp. 158-166 (2004). von Recum et al., Degradation of polydispersed poly(L-lactic acid) to modulate lactic acid release, Biomaterials, vol. 16, pp. 441-445 (1995).

Yau et al., Modern Size-Exclusion Liquid Chromatography, Wiley-Interscience Publication, IX-XV (1979).

International Search Report for PCT/US2007/014331 filed Jun. 19, 2007, mailed Dec. 28, 2007, 13 pgs.

\* cited by examiner




FIG. 1




FIG. 2




FIG. 3

1

# STENT CRIMPING APPARATUS AND METHOD

#### FIELD OF THE INVENTION

This invention relates to an apparatus for crimping a stent and a method for crimping a stent.

### **BACKGROUND**

A typical stent is a cylindrically shaped device, which holds open and sometimes expands a segment of a blood vessel or other anatomical lumen such as urinary tracts and bile ducts. Stents are often used in the treatment of atherosclerotic stenosis in blood vessels. "Stenosis" refers to a narrowing or constriction of the diameter of a bodily passage or orifice. In such treatments, stents reinforce body vessels and prevent restenosis following angioplasty. "Restenosis" refers to the reoccurrence of stenosis in a blood vessel or heart valve after it has been subjected to angioplasty or valvuloplasty.

A stent is typically composed of scaffolding that includes a pattern or network of interconnecting structural elements often referred to in the art as struts or bar arms. The scaffolding can be formed from wires, tubes, or sheets of material rolled into a cylindrical shape.

In the case of a balloon expandable stent, the stent is mounted on a balloon connected to a catheter. A typical conventional method of mounting the stent on the balloon is 30 a two-step process. First, the stent is compressed or crimped onto the balloon. Second, the compressed or crimped stent is retained or secured on the balloon. The retained stent should have a sufficiently small diameter so that it can be transported through the narrow passages of blood vessels. The stent must 35 be secured on the balloon during delivery until it is deployed at an implant or treatment site within a vessel in the body of a patient. The stent is then expanded by inflating the balloon. "Delivery" refers to introducing and transporting the crimped stent through a bodily lumen to the treatment site in a vessel. "Deployment" corresponds to the expanding of the crimped stent within the lumen at the treatment site. Delivery and deployment of a stent are accomplished by positioning the stent about one end of a catheter, inserting the end of the catheter through the skin into a bodily lumen, advancing the 45 catheter in the bodily lumen to a desired treatment location, inflating the stent at the treatment location, and removing the catheter from the lumen by deflating the balloon.

The stent should be firmly secured to the balloon to avoid detachment of the stent before it is delivered and deployed in the lumen of the patient. Detachment of a stent from the balloon during delivery and deployment can result in medical complications. A lost stent can act as an embolus that can create a thrombosis and require surgical intervention. For this reason, a stent must be securely attached to the catheter. Stent retention is greatly enhanced by protrusion of the balloon into the interstitial spaces or gaps between stent struts.

Stent retention for a polymer stent is especially challenging. Because polymers generally have lower strength than metals, a polymer stent requires wider struts than a metal stent to achieve the same mechanical strength. As a result, a polymer stent has smaller spaces or gaps between adjacent struts, making it more difficult for a balloon to protrude into the spaces to enhance stent retention. Additionally, a polymer stent may have a similar  $T_g$  as the balloon material so that 65 there is a limitation on the use of high temperature to enhance balloon protrusion into stent gaps. When high temperature is

2

used during a crimping process, the stent tends to return to its original dimension and lose its preferred mechanical properties.

#### **SUMMARY**

The present invention overcomes the above disadvantage of the prior art. In an preferred embodiment of the present invention, the balloon may be inflated when the stent is crimped onto the balloon, allowing the balloon to extend into the gaps of the stent to enhance stent retention.

In accordance with one aspect of the invention, a method for crimping a stent onto a balloon includes inflating a balloon with a fluid such as a gas or a liquid, sliding a stent over the inflated balloon, crimping the stent onto the balloon, and controlling the pressure inside the balloon below a given value when the stent is being crimped onto the balloon.

In a preferred embodiment of the invention, the step of controlling includes releasing the fluid inside the balloon when the pressure exceeds the given value so that the pressure inside the balloon does not exceed the given value.

In another preferred embodiment of the invention, the step of releasing includes using a pressure release valve to control the fluid inside the balloon below the given value.

In still another preferred embodiment of the invention, the method includes placing the stent and balloon in a crimper before the stent is crimped onto the balloon.

In a further embodiment of the invention, the method includes soaking the balloon in a solvent to soften the balloon. The solvent may be acetone.

In accordance with another aspect of the invention, a method for crimping a stent onto a balloon includes sliding a stent over a balloon, placing the stent and balloon in a stent crimper, inflating the balloon with a fluid such as a gas or a liquid, crimping the stent onto the balloon, and controlling the pressure inside the balloon below a given value when the stent is being crimped onto the balloon.

In a preferred embodiment of the invention, the method includes reducing the crimper's inner diameter to the outer diameter of the stent before inflating the balloon with the fluid.

In another preferred embodiment of the invention, the step of controlling includes releasing the fluid inside the balloon when the pressure exceeds the given value so that the pressure inside the balloon does not exceed the given value.

In still another preferred embodiment of the invention, the step of releasing includes using a pressure release valve to control the fluid inside the balloon below the given value.

In a further embodiment of the invention, the method includes soaking the balloon in a solvent to soften the balloon. The solvent may be acetone.

In accordance with a further aspect of the invention, a stent crimping apparatus includes means for inflating a balloon with a fluid such as a gas or a liquid, means for crimping the stent onto the balloon, and means for controlling the pressure inside the balloon below a given value when the stent is being crimped onto the balloon.

# BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows a perspective view of a stent.

FIG. 2 shows one apparatus for crimping a stent according to the present invention.

FIG. 3 shows portions of a balloon extending into the gaps of a stent.

#### DETAILED DESCRIPTION OF THE INVENTION

Those of ordinary skill in the art will realize that the following description of the invention is illustrative only and not in any way limiting. Other embodiments of the invention will 5 readily suggest themselves to such skilled persons based on the disclosure herein. All such embodiments are within the scope of this invention.

FIG. 1 illustrates a stent 10 that includes a number of interconnecting structural elements or struts 11. In general, 10 the pattern of the stent struts is designed so that the stent can be radially compressed and expanded. The stent may include portions of struts that are straight or relatively straight, an example being a straight portion designated by reference numeral 12. The stent may also include portions of struts that 15 are bent, such as the portions designated by reference numerals 13, 14, and 15. The bent portions 13, 14, and 15 may bend further when the stent 10 is crimped radially inwardly. The bent portions 13, 14, and 15 may bend less when the stent 10 is expanded radially outwardly.

A stent, as fabricated, is uncrimped and may have an outside diameter that is typically from about 1 mm and to about 4 mm. When the stent is crimped, the structural elements deform allowing the stent to decrease in diameter. The deformation occurs primarily at the bending elements. The balloon, when mounted on a catheter, may have an outside diameter of between about 0.7 mm and 0.8 mm. The outside diameter of a crimped stent may be approximately the same as the outside diameter of the balloon.

In some embodiments, a stent of the present invention may 30 be formed from a tube by laser cutting the pattern of structural elements in the tube. The stent may also be formed by laser cutting a polymeric or metallic sheet, rolling the pattern into the shape of the cylindrical stent, and providing a longitudinal weld to form the stent. Other methods of forming stents are 35 well known and include chemically etching a polymeric or metallic sheet and rolling and then welding it to form the stent. A polymeric or metallic wire may also be coiled to form the stent. The stent may be formed by injection molding of a thermoplastic or reaction injection molding of a thermoset 40 polymeric material. Filaments of the compounded polymer may be extruded or melt spun. These filaments can then be cut, formed into ring elements, welded closed, corrugated to form crowns, and then the crowns welded together by heat or solvent to form the stent. Lastly, hoops or rings may be cut 45 from tubing stock, the tube elements stamped to form crowns, and the crowns connected by welding or laser fusion to form the stent.

A stent can be made from one or more suitable materials. For example, a stent may be made from a metallic material. 50 Alternatively, a stent may be made from a polymeric material. A stent may include a biodegradable material, such as a biodegradable polymer or metal. The biodegradable material may be a pure or substantially pure biodegradable polymer or metal. Alternatively, the biodegradable material may be a 55 mixture of at least two types of biodegradable polymers and metals.

Representative examples of polymers that may be used to fabricate embodiments of stents, or more generally, implantable medical devices include, but are not limited to, poly(N-60 acetylglucosamine) (Chitin), Chitosan, poly(3-hydroxyvalerate), poly(lactide-co-glycolide), poly(3-hydroxybutyrate), poly(4-hydroxybutyrate), poly(3-hydroxybutyrate-co-3-hydroxyvalerate), polyorthoester, polyanhydride, poly(glycolic acid), poly(glycolide), poly(L-lactic acid), poly(L-lactide), 65 poly(D,L-lactic acid), poly(Caprolactone), poly(L-lactide-co-capro-

4

lactone), poly(D,L-lactide-co-caprolactone), poly(glycolideco-caprolactone), poly(trimethylene carbonate), polyester amide, poly(glycolic acid-co-trimethylene carbonate), co-poly(ether-esters) (e.g. PEO/PLA), polyphosphazenes, biomolecules (such as fibrin, fibrinogen, cellulose, starch, collagen, and hyaluronic acid), polyurethanes, silicones, polyesters, polyolefins, polyisobutylene and ethylene-alphaolefin copolymers, acrylic polymers and copolymers, vinyl halide polymers and copolymers (such as polyvinyl chloride), polyvinyl ethers (such as polyvinyl methyl ether), polyvinylidene halides (such as polyvinylidene chloride), polyacrylonitrile, polyvinyl ketones, polyvinyl aromatics (such as polystyrene), polyvinyl esters (such as polyvinyl acetate), acrylonitrile-styrene copolymers, ABS resins, polyamides (such as Nylon 66 and polycaprolactam), polycarbonates, polyoxymethylenes, polyimides, polyethers, polyurethanes, rayon, rayon-triacetate, cellulose acetate, cellulose butyrate, cellulose acetate butyrate, cellophane, cellulose nitrate, cellulose propionate, cellulose ethers, and carboxymethyl cellu-20 lose. Additional representative examples of polymers that may be especially well suited for use in fabricating embodiments of implantable medical devices disclosed herein include ethylene vinyl alcohol copolymer (commonly known by the generic name EVOH or by the trade name EVAL), poly(butyl methacrylate), poly(vinylidene fluoride-cohexafluoropropene) (e.g., SOLEF 21508, available from Solvay Solexis PVDF, Thorofare, N.J.), polyvinylidene fluoride (otherwise known as KYNAR, available from ATOFINA Chemicals, Philadelphia, Pa.), ethylene-vinyl acetate copolymers, poly(vinyl acetate), styrene-isobutylene-styrene triblock copolymers, and polyethylene glycol.

FIG. 2 illustrates one apparatus 20 for crimping a stent 22 according to the present invention. In the present invention, to "crimp" a stent is to compress the stent radially inward to reduce its diameter. The apparatus 20 may include one or more crimping elements 24, a source 26 for pressurized fluid, and a pressure control device 28.

The crimping elements 24 can be used to crimp the stent 22. The crimping elements 24 may be any of the known crimping devices that can move radially to crimp the stent 22. Such crimping elements (or device) are well known in the art and will not be described in detail here.

The pressurized fluid source 26 can be used to supply pressurized fluid, such as pressurized gas or liquid, to inflate a balloon 30, on which the stent 22 is mounted. The balloon 28 may be part of a catheter (not shown). The pressurized fluid source 26 may be any device that can supply pressurized fluid, such as a pump or an accumulator. In the illustrated embodiment, the pressurized fluid source 26 is a pump 26. Preferably, a valve 32 is provided that can shut off the pressurized fluid supplied by the pump 26 to the balloon 30.

The pressure control device 28 may be used to control the pressure inside the balloon 30. For example, the pressure control device 28 may keep the pressure inside of the balloon 30 below a predetermined value. The pressure control device may be any suitable device for achieving this purpose. In the illustrated embodiment, the pressure control device 28 is a pressure relief valve 28.

To crimp the stent 22 on the balloon 30 in accordance with one method of the present invention, the balloon 30 is first inflated using the pressurized fluid supplied by the pump 26 (or any other suitable pressurized fluid source). To soften the balloon 30, the balloon 30 may be soaked in a solvent, such as acetone, for a predetermine period of time. After the stent 22 at a first diameter value has been slid on the inflated balloon 30, the stent 22 and balloon 30 are placed in the stent crimping apparatus 20. Next, the crimping elements 24 may radially

5

compress the stent 22 to reduce the stent's diameter to a second diameter value while the balloon remains inflated. During crimping, the balloon pressure may be kept at or below a first pressure value by the pressure relief valve 28. If the pressure inside the balloon 30 is above the first pressure value, the pressure relief valve 28 opens to discharge the pressurized fluid inside the balloon until the pressure reaches or is below the first pressure value. After the diameter of the stent has been reduced to the second diameter value, the balloon pressure may be kept at the first pressure value for a 10 ing: first period of time. Then the pressure inside the balloon may be released for a second period of time. Next the balloon is inflated again to a second pressure value, and the stent is crimped again until its diameter reaches a third diameter value. The balloon pressure may be kept at the second pres- 15 sure value for a third period of time. Then the pressure inside the balloon may be released, and the stent and balloon may be removed from the stent crimping apparatus 20.

To crimp the stent 22 on the balloon 30 in accordance with another method of the present invention, the stent **22** is first 20 slid on the balloon 30 without the balloon 30 being inflated. To soften the balloon 30, the balloon 30 may be soaked in a solvent, such as acetone, for a predetermine period of time. Then the stent 22 and balloon 30 are placed in the stent crimping apparatus 20. Next the stent 22 may be radially 25 compressed from a first diameter value to a second diameter value while the balloon is not inflated. After the diameter of the stent has been reduced to the second diameter value, the balloon may be inflated to a first pressure value for a first period of time. Then the stent is crimped again until its diameter reaches a third diameter value. The balloon pressure may be kept at the first pressure value for a second period of time. Then the pressure inside the balloon may be released, and the stent and balloon may be removed from the stent crimping apparatus 20.

FIG. 3 shows that after the stent 22 has been crimped onto the balloon 30 using a method of the present invention, portions 34 of the balloon 30 extend into the gaps of the stent 22.

The following are two examples of stent crimping using a method of the present invention.

## Example I

The outer diameter of a pre-crimp stent is 0.135 inches. The balloon is inflated to 39 psi, and the stent is mounted on the balloon. The stent and balloon are placed in a stent crimping apparatus, and the stent is crimped to 0.090 inches while the balloon pressure is kept at 39 psi. Next, the balloon pressure is kept at 39 psi for 20 seconds. Afterwards, the balloon may be deflated for a period of time. The crimper then reduces the outer diameter of the stent to 0.045 inches for 50 seconds without balloon pressure. The balloon is inflated again for 20 seconds under 39 psi. Then the balloon pressure is reduced to zero for 20 seconds. Finally, the stent and balloon are removed from the crimper.

# Example II

The outer diameter of an uncrimped stent is 0.084 inches. 60 The uncrimped stent is placed in a crimper, and the crimper's inner diameter is reduced to 0.084 inches, which is the outer diameter of the uncrimped stent. Next, the balloon is inflated under 30 psi pressure for 20 seconds. The crimper then reduces the outer diameter of the stent to 0.032 inches under 65 30 psi for five seconds and then for 45 seconds without balloon pressure. The balloon is inflated again for 25 seconds

6

under 30 psi. Then the balloon pressure is reduced to zero for 10 seconds. Finally, the stent and balloon are removed from the crimper.

While particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that changes and modifications can be made without departing from this invention in its broader aspects.

What is claimed is:

1. A method for crimping a stent onto a balloon, comprising:

inflating a balloon with a fluid to a first pressure value; sliding a stent at a first diameter over the inflated balloon; crimping the stent to a second diameter that is less than the first diameter onto the balloon;

after crimping the stent to the second diameter, releasing the pressure from inside the balloon so that the balloon is deflated;

inflating the balloon that is deflated to a second pressure value;

crimping the stent to a third diameter that is less than the second diameter after inflating the balloon to the second pressure value; and

controlling the pressure inside the balloon below the first pressure value when crimping to the second diameter and below the second pressure value when crimping to the third diameter.

- 2. The method of claim 1, wherein the step of controlling includes releasing the fluid inside the balloon when the pressure exceeds the first pressure value or second pressure value so that the pressure inside the balloon does not exceed the first pressure value or second pressure value, respectively.
- 3. The method of claim 2, wherein the step of releasing includes using a pressure release valve to control the fluid inside the balloon below the first or second pressure value.
- 4. The method of claim 1, further comprising placing the stent and balloon in a crimper before the stent is crimped to the second diameter onto the balloon.
- 5. The method of claim 1, further comprising soaking the balloon in a solvent to soften the balloon.
  - 6. The method of claim 5, wherein the solvent is acetone.
- 7. The method of claim 1, wherein after crimping the stent to the second diameter, the balloon pressure is kept at the first pressure value for a period of time.
- 8. The method of claim 1, wherein after crimping the stent to the third diameter, the balloon pressure is kept at the second pressure value for a period of time.
- 9. The method of claim 1, further comprising releasing the pressure from the balloon after crimping the stent to the third diameter.
- 10. The method of claim 1, wherein the stent comprises a network of interconnecting struts with gaps between adjacent struts, wherein after the crimping steps the balloon extends into the gaps to enhance stent retention.
- 11. The method of claim 1, wherein the balloon is deflated for a period of time.
  - 12. A method for crimping a stent onto a balloon, comprising:

sliding a stent at a first diameter over a balloon that is not inflated;

placing the stent and balloon that is not inflated in a stent crimper;

crimping the stent to a second diameter that is less than the first diameter while the balloon is not inflated;

inflating the balloon to a pressure value after crimping the stent to the second diameter;

crimping the stent to a third diameter that is less than the second diameter after inflating the balloon; and

7

- controlling the pressure inside the balloon below the pressure value when the stent is being crimped onto the balloon.
- 13. The method of claim 12, further comprising reducing an inner diameter of the crimper to the outer diameter of the 5 stent before inflating the balloon with the fluid.
- 14. The method of claim 12, wherein the step of controlling includes releasing the fluid inside the balloon when the pressure exceeds the pressure value so that the pressure inside the balloon does not exceed the pressure value.
- 15. The method of claim 14, wherein the step of releasing includes using a pressure release valve to control the fluid inside the balloon below the pressure value.
- 16. The method of claim 12, further comprising soaking the balloon in a solvent to soften the balloon.
  - 17. The method of claim 16, wherein the solvent is acetone.

8

- 18. The method of claim 12, wherein after inflating the balloon and before crimping the stent to the third diameter, the balloon pressure is kept at the pressure value for a period of time.
- 19. The method of claim 12, wherein after crimping the stent to the third diameter, the balloon pressure is kept at the pressure value for a period of time.
- 20. The method of claim 12, further comprising releasing the pressure from the balloon after crimping the stent to the third diameter.
  - 21. The method of claim 12, wherein the stent comprises a network of interconnecting struts with gaps between adjacent struts, wherein after the crimping steps the balloon extends into the gaps to enhance stent retention.

\* \* \* \* :