



US007947982B2

(12) **United States Patent**
Takizawa et al.

(10) **Patent No.:** **US 7,947,982 B2**
(45) **Date of Patent:** ***May 24, 2011**

(54) **THIN FILM TRANSISTOR MATRIX DEVICE INCLUDING A PLURALITY OF THIN FILM TRANSISTORS ARRANGED ON THE SUBSTRATE**

(75) Inventors: **Hidaki Takizawa**, Kawasaki (JP); **Shougo Hayashi**, Kawasaki (JP); **Takeshi Kinjo**, Kawasaki (JP); **Makoto Tachibanaki**, Kawasaki (JP); **Kenji Okamoto**, Kawasaki (JP)

(73) Assignee: **Sharp Kabushiki Kaisha**, Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 85 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/489,292**

(22) Filed: **Jun. 22, 2009**

(65) **Prior Publication Data**

US 2009/0256153 A1 Oct. 15, 2009

Related U.S. Application Data

(60) Division of application No. 11/377,754, filed on Mar. 16, 2006, now Pat. No. 7,575,960, which is a division of application No. 10/660,053, filed on Sep. 11, 2003, now Pat. No. 7,075,108, which is a division of application No. 10/080,108, filed on Feb. 21, 2002, now Pat. No. 6,767,754, which is a division of application No. 09/005,176, filed on Jan. 8, 1998, now Pat. No. 6,406,946, which is a continuation of application No. 08/669,272, filed on May 29, 1996, now Pat. No. 5,742,074.

(30) **Foreign Application Priority Data**

May 31, 1995 (JP) 7-134400

(51) **Int. Cl.**
H01L 29/04 (2006.01)

(52) **U.S. Cl.** **257/59**; 257/72; 257/E51.005

(58) **Field of Classification Search** 438/149-151; 257/59, 72, E29.151, E51.005

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,789,889 A 12/1988 Morris et al.
5,012,228 A 4/1991 Masuda et al.

(Continued)

FOREIGN PATENT DOCUMENTS

JP H02-8817 1/1990

(Continued)



Primary Examiner — Khiem D Nguyen

(74) *Attorney, Agent, or Firm* — Greer, Burns & Crain, Ltd.

(57) **ABSTRACT**

A thin film transistor matrix device including an insulating substrate, a plurality of thin film transistors (TFTs) on the insulating substrate, and a plurality of picture element electrodes (connected to the TFTs) on the insulating substrate in a matrix to define an image display region. A first conductor is on the insulating substrate. A first insulating film is on the first conductor, a second conductor is on the first insulating film, and a second insulating film is over the first insulating film and the second conductor. A first contact hole is formed in the first and second insulating films, a second contact hole is formed in the second insulating film, and a conducting connection is formed between the first and second contact holes. The first and second conductors are connected to the conducting connection via the first and second contact holes, respectively, which are both outside the image display region.

14 Claims, 29 Drawing Sheets



US 7,947,982 B2

Page 2

U.S. PATENT DOCUMENTS

5,162,933 A 11/1992 Kakuda et al.
5,182,661 A * 1/1993 Ikeda et al. 349/38
5,247,375 A 9/1993 Mochizuki et al.
5,250,931 A 10/1993 Misawa et al.
5,311,342 A 5/1994 Watanabe
5,335,102 A 8/1994 Kanemori et al.
5,341,012 A 8/1994 Misawa et al.
5,467,210 A 11/1995 Kishigami
5,473,261 A 12/1995 Marumoto et al.
5,483,082 A 1/1996 Takizawa et al.
5,504,348 A 4/1996 Yoshida et al.
5,548,425 A 8/1996 Adachi et al.
5,576,868 A 11/1996 Togashi
5,585,951 A 12/1996 Noda et al. 349/122
5,608,251 A 3/1997 Konuma et al.
5,608,558 A 3/1997 Katsumi
5,621,556 A * 4/1997 Fulks et al. 349/42
5,646,432 A * 7/1997 Iwaki et al. 257/347
5,668,032 A 9/1997 Holmberg et al.
5,670,792 A * 9/1997 Utsugi et al. 257/59

5,703,668 A 12/1997 Shin
5,719,408 A 2/1998 Yamamoto et al.
5,784,133 A 7/1998 Kim et al.
5,852,480 A 12/1998 Yajima et al.
5,900,646 A 5/1999 Takizawa et al.
6,075,580 A 6/2000 Kouchi 349/110
6,515,300 B2 2/2003 den Boer et al.
7,075,108 B2 * 7/2006 Takizawa et al. 257/59

FOREIGN PATENT DOCUMENTS

JP H02-244126 9/1990
JP 2-254421 10/1990
JP H04-221926 8/1992
JP H05-142507 6/1993
JP 5-216062 8/1993
JP H06-130419 5/1994
JP 6-202151 7/1994
JP 6-202153 7/1994
JP 07-244295 9/1995

* cited by examiner

FIG. 2




FIG. 3





FIG. 4






FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 6A

FIG. 6B

FIG. 6C

FIG. 6D

FIG. 7




FIG. 8




FIG. 9





FIG. 11






FIG.12A




FIG.12B




FIG.12C




FIG.12D




FIG. 14




FIG. 15




FIG. 16





FIG. 17






FIG. 18A




FIG. 18B




FIG. 18C




FIG. 18D




FIG. 19A

FIG. 19B

FIG. 19C

FIG.20




FIG.21




FIG.22




FIG.23




FIG. 24




FIG. 25






FIG. 26








FIG.28A

FIG.28B

FIG.28C

FIG.28D





FIG.28E

FIG.28F

FIG.28G

FIG.28H

FIG.29




FIG.30




FIG.31




FIG.32




FIG. 33




FIG. 34





FIG. 35
PRIOR ART



**THIN FILM TRANSISTOR MATRIX DEVICE
INCLUDING A PLURALITY OF THIN FILM
TRANSISTORS ARRANGED ON THE
SUBSTRATE**

This is a divisional of application Ser. No. 11/377,754, filed Mar. 16, 2006, now U.S. Pat. No. 7,575,960, which is a divisional of application Ser. No. 10/660,053, filed Sep. 11, 2003, now U.S. Pat. No. 7,075,108, which is a divisional of application Ser. No. 10/080,108, filed Feb. 21, 2002, now U.S. Pat. No. 6,767,754, which is a divisional of Ser. No. 09/005,176 filed Jan. 8, 1998, now U.S. Pat. No. 6,406,946, which is a continuation of Ser. No. 08/669,272 filed May 29, 1996, now U.S. Pat. No. 5,742,074.

BACKGROUND OF THE INVENTION

The present invention relates to a thin film transistor matrix device and a method for fabricating the same, more specifically a TFT-LCD (TFT matrix-type liquid crystal display device) for use in laptop personal computers and wall TVs, and a method for fabricating the same.

TFT-LCDs have characteristics of thinness and lightness, low electric power consumption, etc. and are expected to have a large market in the future as a display device which will take place of CRTs. To realize TFT panels of high precision, large screens for use in work stations, etc., the aperture ratio is a significant problem for higher image quality. To fabricate inexpensive TFT panels, it is important that the TFT panels have device structures which can be fabricated by the use of photolithography techniques.

A pattern layout of a conventional thin film transistor matrix device is shown in FIG. 35.

An image display region **112** is disposed at the center of a transparent insulating substrate **110**, and a plurality of thin film transistors (not shown) and a plurality of picture element electrodes (not shown) connected to the sources of the respective thin film transistors are arranged in a matrix in the region. The gate electrodes of the thin film transistors are commonly connected to gate bus lines **114a** and **114b** arranged widthwise as viewed in FIG. 35, and the drain electrodes thereof are commonly connected to drain bus lines **116a** and **116b** arranged lengthwise as viewed in FIG. 35.

The plural gate bus lines **114a** and **114b** are separated in odd number-th gate bus lines **114a** which are adjacent to each other, and even number-th gate bus lines **114b** (in this specification, the term "odd number-th lines" is used to refer to the odd numbered lines, namely the first, third, fifth, . . . lines; the term "even number-th lines" is used to refer to the even numbered lines, namely the second, fourth, sixth, . . . lines). The odd number-th gate bus lines **114a** are connected to gate side tab terminals **118a** on the right side as viewed in FIG. 35, and the even number-th gate bus lines **114b** are connected to gate side tab terminals **118b** on the left side as viewed in FIG. 35.

The plural drain bus lines **116** are separated in odd number-th drain bus lines **116a** which are adjacent to each other, and even number-th drain bus lines **116b**. The odd number-th drain bus lines **116a** are connected to drain side tab terminals **120a** on the upper side as viewed in FIG. 35, and the even number-th drain bus lines **116b** are connected to drain side tab terminals **120b** on the lower side as viewed in FIG. 35.

In the thus-structured thin film transistor matrix device, as described above, the gate bus lines **114a**, **114b**, and the drain bus lines **116a**, **116b** are respectively formed by independent conducting layer patterns. As a result problems due to electric stresses, such as electrostatic charges, etc., occur in the pro-

cess for fabricating the thin film transistor and in the process for fabricating the liquid crystal panel, whereby the conducting layer patterns are short-circuited and the characteristics of the thin film transistors, such as threshold values, etc., are changed.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a thin film transistor matrix device and a method for fabricating the same, which is free from occurrence of short-circuit and characteristic changes due to stresses, such as electrostatic charges, etc. and which can be fabricated with high yields.

Another object of the present invention is to provide a thin film transistor matrix device and a method for fabricating the same, which can be inspected with high precision, so that possible defective products can be rejected beforehand.

The above-described objects are achieved by a thin film transistor matrix device comprising: transparent insulating substrate; a plurality of thin film transistors arranged on the transparent insulating substrate in a matrix; a plurality of picture element electrodes arranged on the transparent insulating substrate in a matrix and connected to the sources of the thin film transistors; a plurality of bus lines for commonly connecting the gates or the drains of the thin film transistors; outside terminals formed on a margin of the transparent insulating substrate and opposed to the ends of the bus lines; and connection lines formed in regions inner of the outside terminals and commonly connecting said plurality of bus lines, whereby even when electric stresses due to electrostatic charges are applied in the process for fabricating the thin film transistor matrix device, the device can be fabricated without short-circuit defects and with little characteristic change and high yields.

In the above-described thin film transistor matrix device it is preferable that the connection lines include a plurality of connection lines, said plurality of gate bus lines which are adjacent to each other being respectively commonly connected to said plurality of connection lines, whereby inspection of high precision is possible by applying different voltages to the connection lines, so that defective products can be expelled beforehand.

It is preferable that the above-described thin film transistor matrix device further comprises resistant lines which interconnect said plurality of connection lines and have a higher resistant value than the connection lines.

The above-described objects are achieved by a transparent insulating substrate; a plurality of thin film transistors arranged on the transparent insulating substrate in a matrix; a plurality of picture element electrodes arranged on the transparent insulating substrate in a matrix and connected to the sources of the thin film transistors; a plurality of gate bus lines for commonly connecting the gates of the thin film transistors; a plurality of drain bus lines for commonly connecting the drains of the thin film transistors; first outside terminals formed on a margin of the transparent insulating substrate and opposed to the ends of the gate bus lines; second outside terminals formed on a margin of the transparent insulating substrate and opposed to the ends of the drain bus lines; and gate connection lines formed in an inner region of the second outside terminals and commonly connecting said plurality of drain bus lines, whereby even when electric stresses due to electrostatic charges are applied in the process for fabricating the thin film transistor matrix device, the device can be fabricated without short-circuit defects and with little characteristic change and high yields.

In the above-described thin film transistor matrix device it is preferable that the thin film transistor matrix device further comprises resistant lines for interconnecting the gate connection lines and the drain connection lines, and having a higher resistant value than the gate connection lines and the drain connection lines.

In the above-described thin film transistor matrix device it is preferable that a first gate connection line and a second gate connection line respectively commonly connect said plurality of gate bus lines which are adjacent to each other, and a first drain connection line and a second drain connection line respectively commonly connect said a plurality of gate drain lines which are adjacent to each other.

In the above-described thin film transistor matrix device it is preferable that the thin film transistor matrix device further comprises resistant lines for interconnecting the first and the second gate connection lines, and the first and the second drain connection lines and having a resistant value than said plurality of connection lines, whereby inspection of high precision is possible by applying different voltages to the connection lines, so that defective products can be rejected beforehand

The above-described objects are achieved by the method for fabricating a thin film transistor matrix device comprising: a first step of forming on a transparent insulating substrate a plurality of gate bus lines for commonly connecting the gates of thin film transistors, first outside terminals opposed to ends of the gate bus lines, and a gate connection line formed in a region inner of the first outside terminals for commonly connecting said plurality of gate bus lines; a second step of forming a first insulating film on the entire surface; and a third step of forming on the first insulating film a plurality of drain bus lines for commonly connecting the drains of the thin film transistors, second outside terminals opposed to the ends of the drain bus lines, and a drain connection line formed in a region inner of the second outside terminals for commonly connecting said plurality of drain bus lines.

The above-described objects are achieved by the method for fabricating a thin film transistor matrix device comprising: a first step of forming on a transparent insulating substrate a plurality of gate bus lines for commonly connecting the gates of thin film transistors, first outside terminals opposed to the ends of the gate bus lines, and a first gate connection line for commonly connecting the gate bus lines of one of groups in which adjacent ones of said plurality of gate bus lines are divided; a second step of forming a first insulating film on the entire surface; a third step of forming on the first insulating film a plurality of drain bus lines for commonly connecting the drains of the thin film transistors, second outside terminals opposed to the ends of the drain bus lines, and a first drain connection line for commonly connecting the drain bus lines of one of groups in which adjacent ones of said plurality of drain bus lines are divided; a fourth step of forming a second insulating film on the entire surface; and a fifth step of forming on the second insulating film picture element electrodes, a second gate connection line for commonly connecting the gate bus lines of the other of the groups in which adjacent ones of said plurality of gate bus lines are divided, and a second drain connection line for commonly connecting the drain bus lines of the other of the groups in which adjacent ones of said plurality of drain bus lines are divided.

The above-described objects are achieved by the method for fabricating a thin film transistor matrix device comprising: a first step of forming on a transparent insulating substrate a plurality of gate bus lines for commonly connecting the gates of thin film transistors, first outside terminals opposed to the ends of the gate bus lines, a first gate connection line for

commonly connecting the gate bus lines of one of groups in which adjacent ones of said plurality of gate bus lines are divided, and a first drain connection line for commonly connecting the drain bus lines of one of groups in which adjacent ones of said plurality of drain bus lines are divided; a second step of forming a first insulating film on the entire surface; and a third step forming on the first insulating film said plurality of drain bus lines for commonly connecting the drains of the thin film transistors, second outside terminals opposed to the ends of the drain bus lines; a second drain connection line for commonly connecting the drain bus lines of the other of the groups in which adjacent ones of said plurality of drain bus lines are divided, and a second gate connection line for commonly connecting the gate bus lines of the other of the groups in which adjacent ones of said plurality of gate bus lines are divided.

The above-described objects are achieved by the method for fabricating a thin film transistor matrix device comprising: a first step of forming on a transparent insulating substrate a plurality of gate bus lines for commonly connecting the gates of thin film transistors, first outside terminals opposed to the ends of the gate bus lines, a first gate connection line for commonly connecting the gate bus lines of one of groups in which adjacent ones of said plurality of gate bus lines are divided, and a first drain connection line for commonly connecting the drain bus lines of one of groups in which adjacent ones of said plurality of drain bus lines are divided; a second step of forming a first insulating film on the entire surface; a third step of forming on the first insulating film said plurality of drain bus lines for commonly connecting the drains of the thin film transistors, second outside terminals opposed to the ends of the drain bus lines, a second drain connection line, and a second gate connection line; a fourth step of forming a second insulating film on the entire surface; and a fifth step of forming on the second insulating film picture element electrodes, a first connection line for connecting the drain bus lines of the other of the groups in which adjacent ones of said plurality of drain lines are divided to the second drain connection line, and a second connection line for connecting the gate bus lines of the other of the groups in which adjacent ones of said plurality of gate bus lines are divided to the second gate connection line.

In the above-described method for fabricating a thin film transistor matrix device, it is preferable that the method further comprises a fourth step of forming a second insulating film on the entire surface after the third step; and a fifth step of forming on the second insulating film picture element electrodes, and a resistant line for interconnecting the gate connection lines and the drain connection lines.

In the above-described method for fabricating a thin film transistor matrix device, it is preferable that in the fifth step resistant lines for interconnecting the first and the second gate connection lines and the first and the second drain connection lines are formed.

In the above-described method for fabricating a thin film transistor matrix device, it is preferable that after the fabrication steps are over, the gate bus lines are electrically disconnected from the gate connection lines, and the drain bus lines are electrically disconnected from the drain connection lines.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a plan view of the thin film transistor matrix device according to a first embodiment of the present invention.

FIG. 2 is an enlarged plan view of the thin film transistor matrix device of FIG. 1.

5

FIG. 3 is an enlarged plan view of an image display region of the thin film transistor matrix device of FIG. 1.

FIG. 4 is a sectional view of the thin film transistor matrix device of FIGS. 2 and 3.

FIGS. 5A to 5D are sectional views of the thin film transistor matrix device according to the first embodiment of the present invention at the respective steps of a method for fabricating the same (Part 1).

FIGS. 6A to 6D are sectional views of the thin film transistor matrix device according to the first embodiment of the present invention at the respective steps of a method for fabricating the same (Part 2).

FIG. 7 is a plan view of the thin film transistor matrix device according to a second embodiment of the present invention.

FIG. 8 is an enlarged plan view of the thin film transistor matrix device of FIG. 7.

FIG. 9 is a plan view of the thin film transistor matrix device according to a third embodiment of the present invention.

FIG. 10 is an enlarged plan view of the thin film transistor matrix device of FIG. 9.

FIG. 11 is sectional views of the thin film transistor matrix device of FIG. 10.

FIGS. 12A to 12D are sectional views of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of a first method for fabricating the same (Part 1).

FIGS. 13A to 13D are sectional views of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 2).

FIG. 14 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 1).

FIG. 15 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 2).

FIG. 16 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 3).

FIG. 17 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 4).

FIGS. 18A to 18D are sectional views of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of a second method for fabricating the same (Part 1).

FIGS. 19A to 19C are sectional views of the thin film transistor matrix device according to the third embodiment of the present invention at the respective steps of the second method for fabricating the same (Part 2).

FIG. 20 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at a step of the second method for fabricating the same (Part 1).

FIG. 21 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at a step of the second method for fabricating the same (Part 2).

6

FIG. 22 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at a step of the second method for fabricating the same (Part 3).

FIG. 23 is a plan view of the thin film transistor matrix device according to the third embodiment of the present invention at a step of the second method for fabricating the same (Part 4).

FIG. 24 is a plan view of the thin film transistor matrix device according to a fourth embodiment of the present invention.

FIG. 25 is an enlarged plan view of the thin film transistor matrix device of FIG. 24.

FIG. 26 is sectional views of the thin film transistor matrix device of FIG. 25.

FIGS. 27A to 27D are sectional views of the thin film transistor matrix device according to the fourth embodiment of the present invention at the respective steps of a first method for fabricating the same (Part 1).

FIGS. 28A to 28D are sectional views of the thin film transistor matrix device according to the fourth embodiment of the present invention at the respective steps of the first method for fabricating the same (Part 2).

FIG. 29 is a plan view of the thin film transistor matrix device according to the fourth embodiment of the present invention at a step of the first method for fabricating the same (Part 1).

FIG. 30 is a plan view of the thin film transistor matrix device according to the fourth embodiment of the present invention at a step of the first method for fabricating the same (Part 2).

FIG. 31 is a plan view of the thin film transistor matrix device according to the fourth embodiment of the present invention at a step of the fourth method for fabricating the same (Part 3).

FIG. 32 is a plan view of the thin film transistor matrix device according to the fourth embodiment of the present invention at a step of the fourth method for fabricating the same (Part 4).

FIG. 33 is a plan view of the thin film transistor matrix device according to a fifth embodiment of the present invention.

FIG. 34 is an enlarged plan view of the thin film matrix device of FIG. 33.

FIG. 35 is a plan view of a conventional thin film matrix device.

DETAILED DESCRIPTION OF THE INVENTION

1. A First Embodiment

1.1 Thin film Transistor Matrix Device

The thin film transistor matrix device according to a first embodiment of the present invention will be explained with reference to FIGS. 1 to 6.

FIG. 1 shows a pattern layout of the thin film transistor matrix device according to the present embodiment. FIG. 2 is an enlarged view of a wiring region of the thin film transistor matrix device. FIG. 3 is an enlarged view of an image display region of the thin film transistor matrix device of FIG. 1. FIG. 4 is a sectional view of the thin film transistor matrix device of FIG. 1.

First, with reference to FIG. 1, the general layout of the thin film transistor matrix device according to the present embodiment will be explained.

In the thin film transistor matrix device according to the present embodiment, a gate drive circuit and a drain drive circuit are mounted only on one side of a transparent insulating substrate **10**.

An image display region **12** is provided at the center of the transparent insulating substrate **10**, and a plurality of thin film transistors (not shown) and a plurality of image electrodes (not shown) connected to the sources of the thin film transistors are arranged in a matrix in the region **12**. The gate electrodes of the plural thin film transistors are commonly connected to the gate bus lines **14** which are arranged widthwise as viewed in FIG. 1, and the drain electrodes of the plural thin film transistors are commonly connected to drain bus lines **16** which are arranged lengthwise as viewed in FIG. 1.

The gate bus lines **14** are extended to the left as viewed in FIG. 1 and have bumps **18** formed on the ends thereof. On a margin of the transparent insulating substrate **10** there are formed input terminals **20** which receives signals from the outside. The inner ends of the input terminals **20** and the bumps **18** of the gate bus lines **14** are opposed to each other in IC chip regions **22** where driver IC chips (not shown) are disposed.

A gate connection line **24** which commonly connects with the gate bus lines **14** is longitudinally in the IC chip region **22** between the input terminals **20** and the bumps **18**. The gate connection line **24** and the bumps **18** of the gate bus lines **14** are connected with each other by thin connection lines **26**. The thin connection lines **26** are finally melted off by laser beams to electrically disconnect the gate bus lines **14** from the gate connection line **24**.

The drain bus lines **16** are extended upward as viewed in FIG. 1, and bumps **28** are formed on the ends of the drain bus lines **16**. Input terminals **30** which receive signals from the outside are formed on a margin of the transparent insulating substrate **10**. The inner ends of the input terminals **30** and the bumps **28** of the drain bus lines **16** are opposed to each other in an IC chip region **32** where driver IC chips (not shown) are mounted.

A drain connection line **34** which commonly connects the drain bus lines is extended widthwise as viewed in FIG. 1 in the IC chip region **32** between the input terminals **30** and the bumps **28**. Thin connection lines **36** interconnect the drain connection line **34** and the bumps **28** of the drain bus lines **16**. The thin connection lines **36** are finally melted off by laser beams to electrically disconnect the drain bus lines **14** from the drain connection line **34**.

The gate connection line **24** and the drain connection line **34** are connected with each other by a resistant wire **38** having a higher resistance value than the gate connection line **24** and the drain connection line **34**.

Next, the thin film transistor matrix device according to the present embodiment will be detailed with reference to FIGS. 2 to 4. In FIG. 4, the drawing on the left is a sectional view of the bumps **28** of the drain bus lines **16** along the line A-A' in FIG. 2, the drawing on the right is a sectional view of the bumps **18** of the gate bus lines **14** along the line B-B' in FIG. 2, and the drawing at the center is a sectional view of the thin film transistors and the picture element electrodes along the line C-C' in FIG. 3.

The image display unit **12** of the thin film transistor matrix device will be detailed with reference to the plan view of the image display region of FIG. 3 and the line C-C' sectional view in FIG. 4.

FIG. 3 shows a plane structure of the image display unit **12**. The thin film transistors **40** are disposed at the intersections between the gate bus lines **14** and the drain bus lines **16**. The thin film transistors **40** have the gate electrodes **40g** connected

to the gate bus lines **14**, the drain electrodes **40d** connected to the drain bus lines **16** and the source electrodes **40s** connected to the picture element electrodes **42**. Capacitors **44** are disposed at the centers of the picture element electrodes **42**.

A sectional structure of the image display unit **12** is shown by the C-C' sectional view in FIG. 4. On the transparent insulating substrate **10** there are formed the gate bus lines **14** of a metal layer **46** of, e.g., Al or Cr, and capacitor electrodes **46a** of the capacitors **44**. The gate bus lines **14** and the capacitor electrodes **46a** share the same layer with the gate electrodes **40g**.

On the metal layer **46** there is formed a first insulating film **48** of an SiN film, a two-layer film of an SiO₂ film and an SiN film, or others. The first insulating film **48** shares the same layer with a gate insulating film of the thin film transistors **40**.

On the first insulating film **48** there is formed a semiconductor active layer **50** of, e.g., i-type a-Si. The semiconductor active layer **50** shares the same layer with a channel layer of the thin film transistors **40**. On the semiconductor active layer **50** there are formed the source electrodes **40s** of the metal layer **52** of, e.g., Al, Cl or others, and counter electrodes **52a** of the capacitors **44**.

A second insulating film **54** of, e.g., an SiN film, a two-layer film of an SiO₂ film and an SiN film, or others, is formed on the metal layer **52**. In the second insulating film **54**, contact holes are formed on the source electrodes **40s** and the counter electrodes **52a**.

An transparent electrode film **56** of, e.g., ITO or others, is formed on the second insulating film **54**. The transparent electrode film **56** forms the picture element electrodes **42** and is connected to the source electrodes **40s** and the counter electrodes **52a** through the contact holes.

The bumps **28** of the drain bus lines **16** of the thin film transistor matrix device will be detailed with reference to the plan view of FIG. 2 and the A-A' sectional view in FIG. 4.

The first insulating film **48** is formed on the transparent insulating substrate **10**. The semiconductor active layer **50** and the metal layer **52** are laid on the first insulating film **48**. The second insulating film **53** is formed on the metal layer **52**. Contact holes are formed in the second insulating film **54** on the metal layer **52**. The transparent electrode film **56** is formed on the second insulating film **54**. The transparent electrode film **56** is connected to the metal layer **52** through the contact holes. The bumps **28** are constituted by the transparent electrode film **56** and the metal layer **52**. The drain connection line **34** commonly connecting the drain bus lines **16**, and the thin connection lines **26** share the metal layer **52** with the bumps **28**.

The bumps **18** of the gate bus lines **14** of the thin film transistor matrix device will be explained with reference to the plan view of FIG. 2 and the B-B' sectional view in FIG. 4.

The metal layer **46** is formed on the transparent insulating film **10**. The first insulating film **48** and the second insulating film **54** are formed on the metal layer **46**. Contact holes are formed in the first and the second insulating films **48**, **54** on the metal layer **46**. The transparent electrode film **56** is formed on the second insulating film **54**. The transparent electrode film **56** is connected to the metal layer **46** through the contact holes. The transparent electrode film **56** and the metal layer **46** constitute the bumps **18**. The bumps **18** may be constituted by one of the transparent electrode film **56** and the metal layer **46**. The gate connection line **24** commonly connecting the gate bus lines **14**, and the thin connection lines **26** share the metal layer **46** with the bumps **18**.

A liquid crystal panel is constituted by the above-described thin film transistor matrix device. An opposed substrate (not shown) having a color filter formed thereon is prepared, and a

liquid crystal is sandwiched between the thin film transistor matrix device and the opposed substrate, and the liquid crystal panel is prepared.

A circuit substrate (not shown) for the liquid crystal panel, which includes peripheral circuits, such as a drive circuit, is prepared. The liquid crystal panel and the circuit substrate are connected by a connection line (not shown), such as a flexible cable or others, and a liquid crystal display unit is prepared.

1.2 Method for Fabricating the Thin Film Transistor Matrix Device

Then, the method for fabricating the thin film transistor matrix device according to the present embodiment will be explained with reference to FIGS. 5 and 6. In this method five masks are used.

First, the metal layer 46 of, e.g., Al, Cr or others is formed by sputtering on a transparent insulating substrate 19, such as a glass substrate or others. The metal layer 46 is patterned by the use of a first mask to form the gate bus lines 14, the gate electrodes 42a, the capacitor electrodes 46a, the metal layer 46 of the bumps 18, the gate connection line 24 and the thin connection lines 26 (FIG. 5A).

Then, the first insulating film 48 of an SiN film, a two-layer film of SiO₂ film and SiN film, or others is formed by plasma CVD.

Next, the semiconductor active layer 50 of non-doped i-type a-Si and a protection film (not shown) of an SiO₂ film or an SiN film are continuously formed on the first insulating film 48 by plasma CVD (FIG. 5B). Subsequently all the protection film is etched off except a part thereof on the TFT channel region with a hydrofluoric acid buffer solution or others and by the use of a second mask.

Then, an n⁺-type a-Si layer (not shown) is formed on the entire surface by plasma CVD.

Then, the metal layer 52 of Al, Cr, or others is formed on the n⁺-type a-Si layer by sputtering (FIG. 5C).

Then, by the use of a third mask, the metal layer 52 and the semiconductor active layer 50 are patterned to form the metal layers 52 of the bumps 28, the source electrodes 40s, the counter electrodes 52a, the drain electrodes 40d, drain bus lines 16, the drain connection line 34 and the thin connection lines 26 (FIG. 5D).

Next, the second insulation film 54 of an SiN film, a two-layer film of an SiO₂ film and an SiN film, or others is formed on the entire surface by plasma CVD (FIG. 6A).

Next, by the use of a fourth mask, the second insulation film 54 and the first insulation film 48 are patterned to form the contact holes for the bumps 28, the contact holes for the source electrodes 40s, the contact holes for the counter electrodes 52a, the contact holes for the bumps 18 and the contact hole for the resistant line 38 (FIG. 6B).

Then, the transparent electrode film 56 is formed on the entire surface by sputtering (FIG. 6C).

Next, by the use of a fifth mask, the transparent electrode film 56 is patterned to form the bumps 28, the picture element electrodes 42, the resistant line 38 (FIG. 6D). The resistant line 38 is so patterned that the end of the gate connection line and the end of the drain connection line 34 are connected with each other.

Thus, by the use of 5 masks, the thin film transistor matrix device is fabricated.

According to the present embodiment, the gate bus lines 14 are commonly connected to the gate connection line 24 through the thin connection lines 26, and the drain bus lines 16 are commonly connected to the drain connection line 34 through the thin connection lines 36, whereby in the processes for fabricating the thin film transistors and the liquid

crystal panel, no local charges are present even when electrostatic charges are applied, and electric stresses can be mitigated.

After the fabrication processes in which electrostatic charges, etc. are applied are over, the thin connection lines 26, 36 are melted off by a laser or other to electrically disconnect the gate bus lines 14 from the gate connection line 24 and the drain bus lines 16 from the drain connection line 34.

2. A Second Embodiment

The thin film transistor matrix device according to a second embodiment of the present invention will be explained with reference to FIGS. 7 and 8.

FIG. 7 shows a pattern layout of the thin film transistor matrix device according to the present embodiment. FIG. 8 is an enlarged view of the wiring region of the thin film transistor matrix device of FIG. 7. The same members and members of the same kinds of the thin film transistor matrix device according to the present embodiment as those of the thin film transistor matrix device according to the first embodiment are represented by common reference numerals to simplify or not to repeat their explanation.

The thin film transistor matrix device according to the present embodiment is characterized in that adjacent ones 14a, 14b of a plurality of gate bus lines 14 are respectively commonly connected, and adjacent ones 16a, 16b of a plurality of drain bus lines 16 are respectively commonly connected.

As shown in FIGS. 7 and 8, a plurality of gate bus lines 14 are divided in odd number-th gate bus lines 14a and even number-th gate bus lines.

The odd number-th gate bus lines 14a have bumps 18a formed on the ends on the left side as viewed in FIG. 7 and have the ends on the right side as viewed in FIG. 7 commonly connected to a gate connection line 24a. The gate connection line 24a is extended along the edge of a transparent insulating substrate 10.

The even number-th gate bus lines 14b have the bumps 18b formed on the ends on the left side as viewed in FIG. 7. The bumps 18b are commonly connected to the gate connection line 24b through thin connection lines 26b. The gate connection line 24b is extended longitudinally in an IC chip region 22 between input terminals 20 and the bumps 18b.

Odd number-th drain bus lines 16a have bumps 28a formed on the ends on the upper side as viewed in FIG. 7. The bumps 28a are commonly connected to a drain connection line 34a through thin connection lines 36a. The drain connection line 34a is extended widthwise in the IC chip region 32 between the input terminals 30 and the bumps 28a.

The even number-th drain bus lines 16b have the bumps 29b formed on the end on the upper side as viewed in FIG. 7 and the ends on the lower end commonly connected to a drain connection line 34b. The drain connection line 34b is extended along the lower edge of the transparent insulating substrate 10.

The gate connection lines 24a, 24b and the drain connection lines 34a, 34b are interconnected by resistant lines 38a, 38b, 38c, 38d. The resistant line 38a interconnects the gate connection line 24a and the drain connection line 34a; the resistant line 38b interconnects the gate connection line 24a and the drain connection line 34b; the resistant line 38c interconnects the gate connection line 24b and the drain connection line 34a; and the resistant line 38d interconnects the gate connection line 24b and the drain connection line 34b.

Thus, according to the present embodiment, the gate bus lines 14a, 14b are respectively commonly connected to the

gate connection lines **24a**, **24b**. The drain bus lines **16a**, **16b** are respectively commonly connected to the drain connection lines **34a**, **34b**, whereby in the processes for fabricating the thin film transistors and the liquid crystal panel, no local charges are present even when electrostatic charges are applied, and electric stresses can be mitigated.

For higher inspection precision, a test in which different voltages are applied to adjacent gate bus lines and also to adjacent drain bus lines is preferred to a test in which the same voltage is applied to all the gate bus lines and to all the drain bus lines. According to the present embodiment, adjacent ones **14a**, **14b** of the gate bus lines **14** are respectively commonly connected, and adjacent ones **24a**, **24b** of the drain bus lines **24** are respectively commonly connected, whereby tests of high precision can be conducted even by applying different voltages to adjacent gate bus lines and also to adjacent drain bus lines.

3. A Third Embodiment

3.1 Thin Film Transistor Matrix Device

The thin film transistor matrix device according to a third embodiment of the present invention will be explained with reference to FIGS. **9** to **11**.

FIG. **9** shows a pattern layout of the thin film transistor matrix device according to the present embodiment. FIG. **10** is an enlarged view of the wiring region of the thin film transistor matrix device of FIG. **9**. FIG. **11** is a sectional view of the thin film transistor matrix device of FIG. **9**. The same members or members of the same kinds of the thin film transistor matrix device according to the present embodiment as those of the thin film transistor matrix device according to the first and the second embodiments are represented by common reference numerals to simplify or not to repeat their explanation.

The thin film transistor matrix device according to the present embodiment is characterized in that adjacent ones **14a**, **14b** of a plurality of gate bus lines **14** are respectively commonly connected, and adjacent ones **16a**, **16b** of a plurality of drain bus lines **16** are respectively commonly connected; and gate connection lines **24a**, **24b** which commonly connect respectively the gate bus lines **14a**, **14b** are arranged on the same side of a transparent insulating substrate, and drain connection lines **34a**, **34b** which commonly connect respectively the drain bus lines **16a**, **16b** are arranged on the same side of the transparent insulating substrate **10**.

The plane layout of the thin film transistor matrix device according to the present embodiment will be explained with reference to FIGS. **9** and **10**.

A plurality of gate bus lines **14** are divided in odd number-th gate bus lines **14a** and even number-th gate bus lines **14b** which are adjacent to each other.

Bumps **18a** are formed on the ends of the odd number-th gate bus lines **14a** on the left side as viewed in FIG. **9**. The bumps **18a** are commonly connected to the gate connection line **24a** through thin connection lines **26a** and contact holes **27**.

Bumps **18b** are formed on the ends of the odd number-th gate base lines **14b** on the left side as viewed in FIG. **9**. The bumps **18b** are commonly connected to the gate connection line **24b** through thin connection lines **26**.

The gate connection lines **24a**, **24b** are extended longitudinally through an IC chip **22** between input terminals **20** and the bumps **18a**, **18b**.

Bumps **28a** are formed on the ends of the odd number-th bus lines **16a** on the upper side as viewed in FIG. **9**. The

bumps **28a** are commonly connected to the drain connection line **34a** through thin connection lines **36a** and contact hole **37**.

Bumps **28b** are formed on the ends of the even number-th drain bus lines **16b** on the upper end as viewed in FIG. **9**. The bumps **28b** are commonly connected to the drain connection line **34b** through thin connection lines **36b**.

The drain connection lines **34a**, **34b** are extended transversely through an IC chip region **32** between input terminals **30** and the bumps **28a**, **28b**.

The gate connection lines **24a**, **24b** and the drain connection lines **34a**, **34b** are connected with each other by resistant lines **38a**, **38b**, **38c**, **38d**. The resistant line **38a** interconnects the gate connection line **24a** and the gate connection line **24b**; the resistant line **38b** interconnects the gate connection line **24a** and the drain connection line **34b**; the resistant line **38c** interconnects the gate connection line **24b** and the drain connection line **34a**; and the resistant line **38d** interconnects the drain connection line **34a** and the drain connection line **34b**.

Then, a sectional structure of the thin film transistor matrix device according to the present embodiment will be explained with reference to FIG. **11**.

A sectional structure of the vicinity of the drain connection lines **34a**, **34b** will be explained with reference to the plan view of FIG. **10** and the sectional view along the line A-A'.

A first insulating film **48** is formed on a transparent insulating substrate **10**. On the first insulating film **48**, the thin connection lines **36b** and the drain connection line **34a** are formed of the same layer as a semiconductor active layer **50** and a metal active layer **52**. A second insulating film **54** is formed on the metal layer **52**, and the contact holes **37** are formed on the second insulating film **54**. On the second insulating film **54** the drain connection line **34b** is formed of the same layer as an transparent electrode film. The drain connection line **34b** is connected to the thin connection lines **36b** through the contact holes **37**.

A sectional structure of the vicinity of the gate connection lines **24a**, **24b** will be explained with reference to the plan view of FIG. **10** and the B-B' sectional view of FIG. **11**.

On the transparent insulating substrate **10**, the gate connection line **24b** and the thin connection lines **26a** are formed of the same layer as a metal layer **46**. The first and the second insulating films **48**, **54** are formed on the metal layer **46**. The contact holes **27** are formed in the first and the second insulating films **48**, **54** on the thin connection lines **26a**. The gate connection line **24a** is connected to the thin connection lines **26a** through the contact holes **27**.

3.2 A First Fabrication Method

Then, the method for fabricating the thin film transistor matrix device according to the present embodiment will be explained with reference to FIGS. **12** to **17**. FIGS. **12A-12D** and **13A-13D** are A-A' sectional views and B-B' sectional views of the thin film transistor matrix device at the respective steps of the first fabrication method. FIGS. **14** to **17** are enlarged plan views of the thin film transistor matrix device at the respective fabrication steps.

The thin film transistor matrix device according to the present embodiment has the gate connection lines **24a**, **24b** formed on the layers which are different from each other but can be fabricated by the use of 5 masks as in the first embodiment.

The metal layer **46** of, e.g., Al, Cr or others is formed by sputtering on a transparent insulating substrate **10**, such as a glass substrate or others (FIG. **12A**).

Then, by the use of a first mask, the metal layer **46** is patterned to form the gate bus lines **14a**, **14b**, the gate elec-

trodes **42a**, capacitor electrodes **46**, the gate connection line **24b**, the thin connection lines **26a**, **26b** and input electrodes **20** (FIGS. **12B** and **14**).

Then the first insulating film **48** of an SiN film or a two layer film of an SiO₂ film and an SiN film is formed on the entire surface by plasma CVD.

Then, on the first insulating film, the semiconductor active layer **50** of non-doped i-type a-Si, and a protection layer (not shown) of an SiO₂ film or an SiN film are continuously formed. Subsequently, by the use of a second mask, all the protection film except part thereof in a TFT region is etched off with a hydrofluoric acid buffer solution.

Then, an n⁺-type a-Si layer (not shown) is formed on the entire surface by plasma CVD. Then, the metal layer **52** of Al, Cr or others is formed on the n⁺-type a-Si layer by sputtering (FIG. **12C**).

Then, by the use of a third mask, the metal layer **52** and the semiconductor active layer **50** are patterned to form the source electrodes **40s**, the drain electrodes **40d**, the drain bus lines **16a**, **16b**, the drain connection line **34a**, the thin connection lines **36a**, **36b** and input electrodes **30** (FIGS. **12D** and **15**).

Then, the second insulating film **54** of an SiN film or a two layer film of an SiO₂ film and an SiN film is formed on the entire surface by plasma CVD (FIG. **13A**).

Then, by the use of a fourth mask, the second insulation film **54** and the first insulation film **48** are patterned to form the contact holes **27**, the contact holes **37**, and contact holes for the resistant lines **38** (FIGS. **13B** and **16**).

Then, the transparent electrode film **56** is formed on the entire surface by sputtering (FIGS. **13B** and **16**).

Next, by the use of a fifth mask, the transparent electrode film **56** is patterned to form picture element electrodes **52**, the gate connection line **34b**, and the resistant lines **38a**, **38b**, **38c**, **38d** (FIGS. **13D** and **17**). The resistant lines **38A**, **38B**, **38C**, **38D** are patterned so as to interconnect the ends of the gate connection lines **24a**, **24b**, and the ends of the drain connection lines **34a**, **34b**.

Thus, as in the first embodiment, by the use of only 5 masks, the thin film transistor matrix device according to the present embodiment can be fabricated.

3.3 A Second Fabrication Method

Then, another method for fabricating the thin film transistor matrix device according to the present embodiment will be explained with reference to FIGS. **18** to **23**. FIGS. **18A-18D** and **19A-19C** are respectively A-A' line sectional views and B-B' sectional views of the thin film transistor matrix device at the respective steps of the second fabrication method. FIGS. **20** to **23** are enlarged plan views of the thin film transistor matrix device at the respective steps of the second fabrication method.

In the first fabrication method, the contact hole **27** through which the gate connection line **24a** and the gate connection line **24b** are connected with each other is formed in the first insulating film **48** and the second insulating film **54**. The gate connection line **24a** and the gate connection line **24b** define a too large step therebetween to be well connected with each other.

By the second fabrication method, one mask is added, whereby large steps are not formed between the lines connected with each other through the contact holes. The present embodiment uses 6 masks, which is 1 mask more than the first embodiment.

The metal layer **46** of, e.g., Al, Cr or others is formed on a transparent insulating substrate **10**, such as a glass substrate by sputtering (FIG. **18A**).

Then, the metal layer **46** is patterned by the use of a first mask to form the gate bus lines **14a**, **14b**, the gate electrodes **42a**, the capacitor electrodes **46a**, the drain connection line **34b**, the gate connection line **24b**, the thin connection lines **26a**, **26b** and the input electrodes **20** (FIGS. **18B** and **20**).

Then, the first insulating film **48** of an SiN film, a two-layer film of an SiO₂ film and an SiN film, or others on the entire surface by plasma CVD (FIG. **18C**).

Next, on the first insulating film **48**, the semiconductor active layer **48** of non-doped i-type a-Si and the protection film (not shown) of an SiO₂ film or an SiN film are continuously formed by plasma CVD. Subsequently, by the use of a second mask, all the protection film except a part thereof in the TFT channel region is etched off with a hydrofluoric acid buffer solution.

Then, by the use of an additional mask, the first insulating film **48** is patterned to form the contact holes **37** through which the drain connection line **34b** and the thin connection lines **36b** are connected with each other, and the contact holes **27** through which the thin connection lines **26a** and the gate connection line **24a** are connected with each other (FIGS. **18D** and **21**).

Next, the n⁺-type a-Si layer (not shown) is formed on the entire surface by plasma CVD. Then, the metal layer **52** of Al, Cr or others is formed on the n⁺-type a-Si layer by sputtering (FIG. **19A**).

Then, by the use of a third mask, the metal layer **52** and the semiconductor active layer **50** are patterned to form the source electrodes **40s**, the drain electrodes **40d**, the drain bus lines **16a**, **16b**, the drain connection line **34a**, the thin connection lines **36a**, **36b**, the gate connection line **24a** and the input electrodes **30** (FIGS. **19B** and **22**).

Then, the second insulating film **54** of an SiN film, a two layer film of SiO₂ film and an SiN film, or others is formed on the entire surface by plasma CVD (FIG. **19C**).

Next, by the use of a fourth mask, the second insulating film **54** and the first insulating film **48** are patterned to form the contact holes for the resistant lines **38**.

Next, the transparent electrode film **56** is formed on the entire surface by sputtering.

Then, by the use of a fifth mask, the transparent electrode film **56** is patterned to form the picture element electrodes **42**, and the resistant lines **38a**, **38b**, **38c**, **38d** (FIG. **23**).

Thus, totally 6 masks including the additional mask are used, whereby the gate connection line **24a** and the gate connection line **24b** define a small step therebetween, which enables good connection therebetween.

Thus, according to the present embodiment, the gate bus lines **14a**, **14b** are commonly connected respectively by the gate connection lines **24a**, **24b**, and the drain bus lines **16a**, **16b** are commonly connected respectively by the drain connection lines **34a**, **34b**, whereby in the process for fabricating the thin film transistors and the process for forming a liquid crystal panel, no local charge is present even when electrostatic charges are applied, whereby electric stresses can be mitigated.

For higher inspection precision, a test in which different voltages from each other are applied to the gate bus lines which are adjacent to each other and to the drain bus lines which are adjacent to each other is preferred to a test in which the same voltage is applied to all the gate bus lines and all the drain bus lines. According to the present embodiment, the gate bus lines **14a**, **14b** which are adjacent to each other are respectively commonly connected, and the drain bus lines **24a**, **24b** which are adjacent to each other are respectively commonly connected, whereby different voltages from each

other are applied to the adjacent gate bus lines and the drain bus lines for high precision inspection.

4. A Fourth Embodiment

4.1 Thin Film Transistor Matrix Device

The thin film transistor matrix device according to a fourth embodiment of the present invention will be explained with reference to FIGS. 24 to 26.

FIG. 24 is a view of the pattern layout of the thin film transistor matrix device according to the present embodiment. FIG. 25 is an enlarged view of the wiring region of the thin film transistor matrix device of FIG. 24. FIG. 26 is sectional views of the thin film transistor matrix device of FIG. 24. The same members and members of the same kinds of the present embodiment as the thin film transistor matrix device according to the first to the third embodiments are represented by common reference numerals to simplify or not to repeat their explanation.

In the thin film transistor matrix device according to the present embodiment as well as the third embodiment, gate connection lines 24a, 24b respectively commonly connecting gate bus lines 14a, 14b which are adjacent to each other are arranged on the same side of a transparent insulating substrate 10, and drain connection lines 34a, 34b respectively commonly connecting drain bus lines 16a, 16b are arranged on the same side of the transparent insulating substrate 10, but the present embodiment is different from the third embodiment in the connection structure between the gate bus lines 14a, 14b and the gate connection lines 24a, 24b and that between the drain bus lines 16a, 16b and the drain connection lines 34a, 34b.

First, a layout of the thin film transistor matrix device according to the present embodiment in a plane will be explained with reference to FIGS. 24 and 25.

A plurality of gate bus lines 14 are divided into odd number-th gate bus lines 14a and even number-th gate bus lines 14b which are adjacent to each other.

Bumps 18a are formed on the ends of the odd number-th gate bus lines 14a on the right side as viewed in FIG. 24. The bumps 18a are commonly connected to the gate connection line 24a through thin connection lines 26a, contact holes 27b, a connection line 25 and contact holes 27a.

Bumps 18b are formed on the ends of the even number-th gate bus lines 14b on the left side as viewed in FIG. 24. The bumps 18b are commonly connected to the gate connection line 24b through thin connection lines 26b.

The gate connection lines 24a, 24b are extended longitudinally through an IC chip region 22 between inputs terminals 20 and the bumps 18a, 18b.

Bumps 28a are formed on the ends of the odd number-th drain bus lines 16a on the upper end as viewed in FIG. 24. The bumps 28a are commonly connected to the drain connection line 34a through thin connection lines 36a, contact holes 37b, a connection line 35 and contact holes 37a.

Bumps 28b are formed on the ends of the even number-th drain bus lines 16b on the upper end as viewed in FIG. 24. The bumps 28b are commonly connected to the drain connection line 34b through thin connection lines 36b.

The drain connection lines 34a, 34b are extended longitudinally through an IC chip region 32 between input terminals 30 and the bumps 28a, 28b.

Resistant lines 38a, 38b, 38c, 38d interconnect the gate connection lines 24a, 24b and the drain connection lines 34a, 34b. The resistant line 38a interconnects the gate connection line 24a and the gate connection line 24b; the resistant line 38b interconnects the gate connection line 24a and the drain

connection line 34b; the resistant line 38c interconnects the gate connection line 24b and the drain connection line 34a; and the resistant line 38d interconnects the drain connection line 34a and the drain connection line 34b.

Then, a sectional structure of the thin film transistor matrix device according to the present embodiment will be explained.

A sectional structure of the vicinity of the drain connection lines 34a, 34b will be explained with reference to the plan view of FIG. 25 and the sectional view along the line A-A' in FIG. 26.

On a transparent insulating substrate 10, the drain connection line 34b of the same layer as the metal layer 46 is formed. A first insulating film 48 is formed on the transparent insulating film 10 and the drain connection line 34b. On the first insulating film 48, the thin connection line 36b and the drain connection lines 34a of the same layer as the semiconductor active layer 50 and the metal layer 52. A second insulating film 54 is formed on the metal layer 52. The contact holes 37a are formed in the first and the second insulating films 48, 54 and reach the drain connection line 34b. The contact holes 37b are formed in the second insulating film 54 and reach the thin connection lines 36b. The connection line 35 of the same layer as a transparent electrode film 56 is formed on the second insulating film 54 and interconnects the thin connection lines 36b and the drain connection line 34b through the contact holes 37a, 37b.

A sectional structure of the vicinity of the gate connection lines 24a, 24b will be explained with reference to the plan view of FIG. 25 and a sectional view along the line B-B' in FIG. 26.

On the transparent insulating substrate 10, the gate connection line 24b and the thin connection lines 26a of the same layer as the metal layer 46 are formed. On the metal layer 46, the first insulating film 48 is formed. On the first insulating film 48, the gate connection line 24a of the same layer as the semiconductor active layer 50 and the metal layer S2 is formed. The second insulating film 54 is formed on the first insulating film 48 and the gate connection line 24a. The contact holes 27a are formed in the second insulating film 54 and reach the gate connection line 24a. The contact holes 27b are formed in the first and the second insulating films 48, 54 and reach the thin connection lines 26a. On the second insulating film 54, the connection line 25 of the same layer as the transparent electrode film 56 is formed and interconnects the thin connection lines 26a and the gate connection line 24a through the contact holes 27a, 27b.

4.2 Fabrication Method

Then, the method for fabricating the thin film transistor matrix device according to the present embodiment will be explained with reference to FIGS. 27 to 32. FIGS. 27A-27D and 28A-28D are sectional views of the thin film transistor matrix device according to the present embodiment at the respective step of the fabrication method, which are along the lines A-A' and the line B-B'. FIGS. 29 to 32 are enlarged plan views of the thin film transistor matrix device at the respective steps of the fabrication method.

In the present embodiment, although the gate connection lines 24a, 24b and the drain connection lines 34a, 34b are formed of the different layers, the thin film transistor matrix device according to the present embodiment can be fabricated by the use of only 5 masks as in the first embodiment.

First, the metal layer 46 of, e.g., Al, Cr or others is formed on a transparent insulating substrate 10, such as a glass substrate by sputtering (FIG. 27A).

Next, by the use of a first mask, the metal layer 46 is patterned to form the drain connection line 34b, the gate bus

lines **14a**, **14b**, gate electrodes **42a**, capacitors **46a**, the gate connection line **24b**, the thin connection lines **26a**, **26b**, and input electrodes **20** (FIGS. **27B** and **29**).

The first insulating film **48** of an SiN film, a two-layer film of an SiO₂ film and an SiN film or others is formed on the entire surface by plasma CVD.

Then, on the insulating film **48**, the semiconductor active layer of non-doped i-type a-Si and a protection film (not shown) of an SiO₂ film or an SiN film are continuously formed. Subsequently by the use of a second mask, all the protection film except a part thereof in a TFT channel region is etched off with a hydrogen fluoride buffer solution.

Then, an n⁺-type a-Si film (not shown) is formed on the entire surface by plasma CVD. Then, the metal layer **52** of Al, Cr or others is formed on the n⁺-type a-Si layer by sputtering (FIG. **27C**).

Next, by the use of a third mask, the metal layer **52** and the semiconductor active layer **56** are patterned to form source electrodes **40s**, drain electrodes **40d**, the drain bus lines **16a**, **16b**, the drain connection lines **34a**, the thin connection lines **36a**, **36b**, input electrodes **30**, and the gate connection line **24a** (FIGS. **27D** and **30**).

Then, the second insulating film **54** of an SiN film, a two-layer film of an SiO₂ film and an SiN film or others is formed on the entire surface by plasma CVD (FIG. **28A**).

Next, the second and the first insulating films **54**, **48** are patterned by the use of a fourth mask to form the contact holes **27a**, **27b**, the contact holes **37a**, **37b** and the contact holes for the resistant lines **38** (FIGS. **28B** and **31**).

Then, the transparent electrode film **56** is formed on the entire surface by sputtering (FIG. **28C**).

Then, the transparent electrode film **56** is patterned by the use of a fifth mask to form the connection line **35**, picture element electrodes **42**, the gate connection line **24a**, the drain connection line **34b**, the resistant lines **38a**, **38b**, **38c**, **38d**, and the connection line **25** (FIGS. **28D** and **32**). The resistant lines **38a**, **38b**, **38c**, **38d** are patterned so as to interconnect the ends of the gate connection lines **24a**, **24b** and the ends of the drain connection lines **34a**, **34b**.

Thus, by the use of only 5 masks, the thin film transistor matrix device according to the present embodiment can be fabricated as the first embodiment.

As described above, according to the present embodiment, the gate bus lines **14a**, **14b** are commonly connected to the gate connection lines **24a**, **24b**, and the drain bus lines **16a**, **16b** are commonly connected to the drain connection lines **34a**, **34b**, whereby in the process for fabricating the thin film transistor matrix device and the process for forming a liquid crystal panel, even when electrostatic charges are applied, no local presence of charges, and electric stresses can be mitigated.

For higher inspection precision, a test in which different voltages are applied to adjacent gate bus lines and also to adjacent drain bus lines is preferred to a test in which the same voltage is applied to all the gate bus lines and to all the drain bus lines. According to the present embodiment, adjacent ones **14a**, **14b** of the gate bus lines **14** are respectively commonly connected, and adjacent ones **24a**, **24b** of the drain bus lines **24** are respectively commonly connected, whereby tests of high precision can be conducted even by applying different voltages to adjacent gate bus lines and also to adjacent drain bus lines.

5. A Fifth Embodiment

The thin film transistor matrix device according to a fifth embodiment of the present invention will be explained with reference to FIGS. **33** and **34**.

FIG. **33** is a view of a pattern layout of the thin film transistor matrix device according to the present embodiment. FIG. **34** is an enlarged view of the wiring region of the thin film transistor matrix device of FIG. **33**. The same members or members of the same kinds of the present embodiment as the first to the fourth embodiments are represented by common reference numerals to simplify or not to repeat their explanation.

In the thin film transistor matrix device according to the present embodiment, gate connection lines **24a**, **24b** which respectively commonly connect gate bus lines **14a**, **14b**, and a drive circuit on the gate side are arranged on both sides of a transparent insulating substrate **10**, and drain connection lines **34a**, **34b** which respectively commonly connect drain bus lines **16a**, **16b**, and a drive circuit for the drain side are arranged on both sides of the transparent insulating substrate **10**.

A plurality of gate bus lines **14** are divided into odd number-th gate bus lines **14a** and even number-th gate bus lines **14b**.

Bumps **18a** are formed on the ends of the odd number-th gate bus lines **14a** on the right side as viewed in FIG. **33**. Input terminals **20a** for receiving signals from the outside are formed on the right margin of the transparent insulating substrate **10**. The gate connection line **24a** is extended longitudinally through an IC chip region **22** between the gate connection line **24a**, and the input terminals **20a** and the bumps **18a**.

Bumps **18b** are formed on the ends of the even number-th gate bus lines **14b** on the left side as viewed in FIG. **33**. Input terminals **20b** for receiving signals from the outside are formed on the left margin of the transparent insulating substrate **10**. The gate connection line **24b** is extended longitudinally through an IC chip region **22** between the input terminals **20b** and the bumps **18b**.

Bumps **28a** are formed on the ends of the odd number-th drain bus lines **16a** on the upper side as viewed in FIG. **33**. Input terminals **30a** for receiving signals from the outside are formed on the upper margin of the transparent insulating substrate **10**. The gate connection line **34a** is extended longitudinally through an IC chip region **32** between the input terminals **30a** and the bumps **28a**.

Bumps **28b** are formed on the ends of the even number-th drain bus lines **16b** on the lower end as viewed in FIG. **33**. Input terminals **30b** for receiving signals from the outside are formed on the lower margin of the transparent insulating substrate **10**. The gate connection line **34b** is extended longitudinally through an IC chip region between the input terminals **30b** and the bumps **28b**.

Resistant lines **38a**, **38b**, **38c**, **38d** interconnect the gate connection lines **24a**, **24b** and the drain connection lines **34a**, **34b**. The resistant line **38a** interconnects the gate connection line **24a** and the drain connection line **34a**; the resistant connection line **38b** interconnects the gate connection line **24a** and the drain connection line **34b**; the resistant line **38c** interconnects the gate connection line **24b** and the drain connection line **34a**; and the resistant line **38d** interconnects the gate connection line **24b** and the drain connection line **34b**.

As described above, the gate bus lines **14a**, **14b** are respectively commonly connected to the gate connection lines **24a**, **24b**, and the drain bus lines **16a**, **16b** are respectively commonly connected to the drain connection lines **34a**, **34b**, whereby in the process for fabricating the thin film transistor matrix device and in the process for forming a liquid crystal panel, even when electrostatic charges are applied, there is no local presence of charges, and electric stresses can be mitigated. Furthermore, according to the present embodiment,

19

the gate bus lines **14a**, **14b** which are adjacent to each other are respectively commonly connected to the gate connection lines, and the drain bus lines **24a**, **24b** which are adjacent to each other are respectively commonly connected to the drain connection lines, whereby different voltages are applied to the gate bus lines which are adjacent to each other and to the drain bus lines which are adjacent to each other, whereby inspection of high precision can be conducted.

6. Variations

The present invention is not limited to the above-described embodiments and includes other variations.

For example, in the above-described embodiments, the present invention is applied to inverse-staggered TFT matrix device but is also applicable to devices of other device structures, such as staggered TFT matrix devices.

In the above-described embodiments, the gate bus lines and the drain bus lines are respectively grouped as even-number-th ones and odd number-th ones to be connected to the respective connection lines by group, but the present invention is not limited to this connection mode. The gate bus lines and the drain bus lines may be grouped in other combinations to be commonly connected to the connection lines.

What is claimed is:

1. A thin film transistor matrix device comprising:
 - an insulating substrate;
 - a plurality of thin film transistors arranged on the insulating substrate in a matrix;
 - a plurality of picture element electrodes arranged on the insulating substrate in a matrix to define an image display region, and wherein the picture element electrodes are connected to the thin film transistors;
 - a first conductor formed on the insulating substrate, wherein a portion of the first conductor comprises gate electrodes of the thin film transistors;
 - a first insulating film formed on the first conductor;
 - a second conductor formed on the first insulating film; and
 - a second insulating film formed over the first insulating film and the second conductor;
 - a first contact hole formed, outside the image display region, in the first insulating film and the second insulating film,
 - a second contact hole formed, outside the image display region, in the second insulating film,
 - a conducting connection formed between the first contact hole and the second contact hole,
 - the first conductor is connected to the conducting connection via the first contact hole, and
 - the second conductor is connected to the conducting connection via the second contact hole, and
 - wherein the conducting connection is made of a transparent material,
 - wherein the conducting connection is located in an area between the image display region and an edge of the insulating substrate.
2. The thin film transistor matrix device according to claim 1, wherein the conducting connection is made of a single material.
3. The thin film transistor matrix device according to claim 1, wherein the conducting connection is made of indium tin oxide.
4. The thin film transistor matrix device according to claim 1, wherein the first conductor comprises a plurality of bus lines.
5. The thin film transistor matrix device according to claim 1, wherein the first conductor is made of a single layer.

20

6. The thin film transistor matrix device according to claim 1, wherein the second conductor is made of a single layer.

7. The thin film transistor matrix device according to claim 1, wherein:

said first contact hole is on a first wiring line, where the first conductor comprises the first wiring line; and

said second contact hole is on a second wiring line, where the second conductor comprises the second wiring line.

8. The thin film transistor matrix device according to claim 7, wherein:

said first wiring line extends in a first direction, for at least a portion thereof; and

said second wiring line extends in a second direction, for at least in a portion thereof, and where said second direction is different from said first direction.

9. The thin film transistor matrix device according to claim 8, wherein:

said first direction is a generally widthwise direction; and

said second direction is a generally lengthwise direction.

10. The thin film transistor matrix device according to claim 1, wherein said conducting connection is formed together with and of the same material as pixel electrodes.

11. The thin film transistor matrix device according to claim 1, wherein said second insulating film comprises first and second insulating layers of different insulating materials.

12. The thin film transistor matrix device according to claim 1, wherein the second contact hole is closer to the edge of the insulating substrate than the first contact hole.

13. A liquid crystal display device comprising:

- a thin film transistor matrix device including:
 - an insulating substrate;
 - a plurality of thin film transistors arranged on the insulating substrate in a matrix;
 - a plurality of picture element electrodes arranged on the insulating substrate in a matrix to define an image display region, and wherein the picture element electrodes are connected to the thin film transistors;
 - a first conductor formed on the insulating substrate, wherein a portion of the first conductor comprises gate electrodes of the thin film transistors;
 - a first insulating film formed on the first conductor;
 - a second conductor formed on the first insulating film; and
 - a second insulating film formed over the first insulating film and the second conductor;
 - a first contact hole formed, outside the image display region, in the first insulating film and the second insulating film,
 - a second contact hole formed, outside the image display region, in the second insulating film,
 - a conducting connection formed between the first contact hole and the second contact hole,
 - the first conductor is connected to the conducting connection via the first contact hole, and
 - the second conductor is connected to the conducting connection via the second contact hole, and
 - wherein the conducting connection is made of a transparent material,
 - wherein the conducting connection is located in an area between the image display region and an edge of the insulating substrate.

14. The liquid crystal display device according to claim 13, wherein the second contact hole is closer to the edge of the insulating substrate than the first contact hole.