



US007951900B2

(12) **United States Patent**
Crawford et al.

(10) **Patent No.:** **US 7,951,900 B2**
(45) **Date of Patent:** ***May 31, 2011**

(54) **DIALYSIS FILTER HOUSINGS COMPRISING POLYESTER COMPOSITIONS FORMED FROM 2,2,4,4-TETRAMETHYL-1,3-CYCLOBUTANEDIOL AND 1,4-CYCLOHEXANEDIMETHANOL**

(75) Inventors: **Emmett Dudley Crawford**, Kingsport, TN (US); **David Scott Porter**, Blountville, TN (US); **Gary Wayne Connell**, Church Hill, TN (US)

(73) Assignee: **Eastman Chemical Company**, Kingsport, TN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 656 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **11/390,858**

(22) Filed: **Mar. 28, 2006**

(65) **Prior Publication Data**

US 2006/0286331 A1 Dec. 21, 2006

Related U.S. Application Data

(60) Provisional application No. 60/691,567, filed on Jun. 17, 2005, provisional application No. 60/731,454, filed on Oct. 28, 2005, provisional application No. 60/731,389, filed on Oct. 28, 2005, provisional application No. 60/739,058, filed on Nov. 22, 2005, provisional application No. 60/738,869, filed on Nov. 22, 2005, provisional application No. 60/750,692, filed on Dec. 15, 2005, provisional application No. 60/750,693, filed on Dec. 15, 2005, provisional application No. 60/750,682, filed on Dec. 15, 2005, provisional application No. 60/750,547, filed on Dec. 15, 2005.

(51) **Int. Cl.**

C08G 63/00 (2006.01)
C08L 67/02 (2006.01)

(52) **U.S. Cl.** **528/307; 528/302; 528/304; 528/305; 525/165; 525/173; 525/177; 525/390; 525/397; 525/425; 525/439; 525/444**

(58) **Field of Classification Search** **528/302, 528/304, 305, 307; 525/165, 173, 177, 390, 525/397, 425, 439, 444**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,602,699 A 10/1926 Nightingale
2,160,841 A 6/1939 Dreyfus
2,202,046 A 5/1940 Dreyfus et al.
2,278,537 A 4/1942 Dreyfus et al.
2,720,507 A 10/1955 Caldwell
2,806,064 A 9/1957 McKlveen
2,901,466 A 8/1959 Kibler
2,936,324 A 5/1960 Hasek et al.

3,000,906 A 9/1961 Hasek et al.
3,030,335 A 4/1962 Goldberg
3,062,852 A 11/1962 Martin et al.
3,075,952 A 1/1963 Coover et al.
3,091,600 A 5/1963 Caldwell et al.
3,169,121 A 2/1965 Goldberg et al.
3,190,928 A 6/1965 Elam et al.
3,201,474 A 8/1965 Hasek et al.
3,207,814 A 9/1965 Goldberg et al.
3,218,372 A 11/1965 Okamura et al.
3,227,764 A 1/1966 Martin et al.
3,236,899 A 2/1966 Clark
3,249,652 A 5/1966 Quisenberry
3,259,469 A 7/1966 Painter et al.
3,287,390 A 11/1966 Poos et al.
3,288,854 A 11/1966 Martin
3,312,741 A 4/1967 Martin
3,313,777 A 4/1967 Elam et al.
3,317,466 A 5/1967 Caldwell et al.
3,329,722 A 7/1967 Rylander
3,360,547 A 12/1967 Wilson et al.
3,366,689 A 1/1968 Maeda et al.
3,386,935 A 6/1968 Jackson et al.
3,403,181 A 9/1968 Painter et al.
T858,012 I4 1/1969 Caldwell et al.
3,502,620 A 3/1970 Caldwell
T873,016 I4 4/1970 Gilkey et al.
3,541,059 A 11/1970 Schaper
3,546,177 A 12/1970 Kibler et al.
RE27,682 E 6/1973 Schnell et al.
3,772,405 A 11/1973 Hamb
3,799,953 A 3/1974 Freitag et al.
3,907,754 A 9/1975 Tershansy et al.
3,915,913 A 10/1975 Jackson, Jr. et al.
3,962,189 A 6/1976 Russin et al.
4,001,184 A 1/1977 Scott
4,010,145 A 3/1977 Russin et al.
4,046,933 A 9/1977 Stefanik
4,056,504 A 11/1977 Grundmeier et al.
4,084,889 A 4/1978 Vischer, Jr.
4,125,572 A 11/1978 Scott
4,156,069 A 5/1979 Prevorsek et al.
4,160,383 A 7/1979 Rauschenberger

(Continued)

FOREIGN PATENT DOCUMENTS

BE 615850 4/1962

(Continued)

OTHER PUBLICATIONS

USPTO Office Action dated Apr. 16, 2008 for copending U.S. Appl. No. 11/390,751.

(Continued)

Primary Examiner — Milton I Cano

Assistant Examiner — Gennadiy Mesh

(74) *Attorney, Agent, or Firm* — Betty J. Boshears; Bernard J. Graves, Jr.

(57) **ABSTRACT**

Described are dialysis filter housings comprising polyester compositions comprising polyesters which comprise (a) a dicarboxylic acid component having terephthalic acid residues; optionally, aromatic dicarboxylic acid residues or aliphatic dicarboxylic acid residues or ester residues thereof; 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and 1,4-cyclohexanedimethanol residues.

49 Claims, 3 Drawing Sheets

U.S. PATENT DOCUMENTS							
4,185,009	A	1/1980	Idel et al.	5,681,918	A	10/1997	Adams et al.
4,188,314	A	2/1980	Fox et al.	5,688,874	A	11/1997	Hoffman
4,194,038	A	3/1980	Baker et al.	5,696,176	A	12/1997	Khemani et al.
4,356,299	A	10/1982	Cholod et al.	5,705,575	A	1/1998	Kelsey
4,367,186	A	1/1983	Adelmann et al.	5,783,307	A	7/1998	Fagerburg et al.
4,384,106	A	5/1983	Go et al.	5,804,617	A	9/1998	Hoffman et al.
4,391,954	A	7/1983	Scott	5,814,679	A	9/1998	Eckberg et al.
4,424,140	A	1/1984	Weinberg et al.	5,859,116	A	1/1999	Shih
4,426,512	A	1/1984	Barbee et al.	5,863,622	A	1/1999	Jester
4,427,614	A	1/1984	Barham et al.	5,902,631	A	5/1999	Wang et al.
4,430,484	A	2/1984	Quinn	5,907,026	A	5/1999	Factor et al.
4,431,793	A	2/1984	Rosenquist	5,942,585	A	8/1999	Scott et al.
4,452,933	A	6/1984	McCready	5,955,565	A	9/1999	Morris et al.
4,465,820	A	8/1984	Miller et al.	5,958,539	A	9/1999	Eckart et al.
4,469,861	A	9/1984	Mark et al.	5,958,581	A	9/1999	Khanarian et al.
4,480,086	A	10/1984	O'Neill	5,959,066	A	9/1999	Charbonneau et al.
4,525,504	A	6/1985	Morris et al.	5,962,625	A	10/1999	Yau
4,578,437	A	3/1986	Light et al.	5,977,347	A	11/1999	Shuto et al.
4,749,773	A	6/1988	Weaver et al.	5,989,663	A	11/1999	Morris et al.
4,786,692	A	11/1988	Allen et al.	6,001,910	A	12/1999	Blumenthal et al.
4,816,308	A	3/1989	Shimizu et al.	6,005,059	A	12/1999	Scott et al.
4,826,903	A	5/1989	Weaver et al.	6,011,124	A	1/2000	Scott et al.
4,845,188	A	7/1989	Weaver et al.	6,012,597	A	1/2000	Nishihara et al.
4,880,592	A	11/1989	Martini et al.	6,022,603	A	2/2000	Umeda et al.
4,882,412	A	11/1989	Weaver et al.	6,030,671	A	2/2000	Yang et al.
4,892,922	A	1/1990	Weaver et al.	6,037,424	A	3/2000	Scott et al.
4,892,923	A	1/1990	Weaver et al.	6,043,322	A	3/2000	Scott et al.
4,937,134	A	6/1990	Schrenk et al.	6,044,996	A	4/2000	Carew et al.
4,939,186	A	7/1990	Nelson et al.	6,063,464	A	5/2000	Charbonneau et al.
4,976,057	A	12/1990	Bianchi	6,063,465	A	5/2000	Charbonneau et al.
4,981,898	A	1/1991	Bassett	6,063,495	A	5/2000	Charbonneau et al.
4,985,342	A	1/1991	Muramoto et al.	6,084,019	A	7/2000	Matayabas et al.
5,017,679	A	5/1991	Chang et al.	6,096,854	A	8/2000	Morris et al.
5,017,680	A	5/1991	Sublett	6,114,575	A	9/2000	McMahon et al.
5,034,252	A	7/1991	Nilsson et al.	6,120,477	A	9/2000	Campbell et al.
5,104,450	A	4/1992	Sand et al.	6,126,992	A	10/2000	Khanarian et al.
5,118,760	A	6/1992	Blakely et al.	6,127,492	A	10/2000	Nagashima et al.
5,118,847	A	6/1992	Jackson et al.	6,146,228	A	11/2000	Mougin et al.
5,142,088	A	8/1992	Phelps et al.	6,150,494	A	11/2000	Wang et al.
5,169,994	A	12/1992	Sumner, Jr. et al.	6,183,848	B1	2/2001	Turner et al.
5,183,863	A	2/1993	Nakamura et al.	6,191,209	B1	2/2001	Andrews et al.
5,191,038	A	3/1993	Krabbenhof et al.	6,211,309	B1	4/2001	McIntosh et al.
5,207,967	A	5/1993	Small et al.	6,221,556	B1	4/2001	Gallucci et al.
5,219,510	A	6/1993	Machell et al.	6,225,436	B1	5/2001	Eiffler et al.
5,224,958	A	7/1993	Warunek et al.	6,232,504	B1	5/2001	Barteau et al.
5,239,020	A	8/1993	Morris	6,239,210	B1	5/2001	Kim et al.
5,256,761	A	10/1993	Blount, Jr.	6,255,523	B1	7/2001	Panandiker et al.
5,258,556	A	11/1993	Sumner, Jr. et al.	6,287,656	B1	9/2001	Turner et al.
5,268,219	A	12/1993	Harada et al.	6,307,006	B1	10/2001	Konig et al.
5,288,715	A	2/1994	Machell et al.	6,320,042	B1	11/2001	Michihata et al.
5,288,764	A	2/1994	Rotter et al.	6,323,291	B1	11/2001	Mason et al.
5,292,783	A	3/1994	Buchanan et al.	6,323,304	B1	11/2001	Lemmon et al.
5,310,611	A	5/1994	Okabe et al.	6,342,304	B1	1/2002	Buchanan et al.
5,310,787	A	5/1994	Kutsuwa et al.	6,352,783	B1	3/2002	Fagerburg
5,326,584	A	7/1994	Kamel et al.	6,354,986	B1	3/2002	Hlavinka et al.
5,331,034	A	7/1994	Pfahler et al.	6,359,070	B1	3/2002	Khanarian et al.
5,333,073	A	7/1994	Suzuki	6,406,792	B1	6/2002	Briquet et al.
5,354,791	A	10/1994	Gallucci	6,437,083	B1	8/2002	Brack et al.
5,372,864	A	12/1994	Weaver et al.	6,448,334	B1	9/2002	Verhoogt et al.
5,372,879	A	12/1994	Handa et al.	6,458,468	B1	10/2002	Moskala et al.
5,378,796	A	1/1995	George et al.	6,504,002	B1	1/2003	Karlik et al.
5,382,292	A	1/1995	Conroy et al.	6,559,272	B1	5/2003	Jeon et al.
5,384,377	A	1/1995	Weaver et al.	6,573,328	B2	6/2003	Kropp et al.
5,475,144	A	12/1995	Watson et al.	6,599,994	B2	7/2003	Shelby et al.
5,480,926	A	1/1996	Fagerburg et al.	6,639,067	B1	10/2003	Brinegar et al.
5,486,562	A	1/1996	Borman et al.	6,656,577	B1	12/2003	Adelman et al.
5,489,665	A	2/1996	Yamato et al.	6,669,980	B2	12/2003	Hansen
5,494,992	A	2/1996	Kanno et al.	6,723,768	B2	4/2004	Adams et al.
5,498,668	A	3/1996	Scott	6,733,716	B2	5/2004	Belcher
5,498,688	A	3/1996	Oshino et al.	6,740,377	B2	5/2004	Pecorini et al.
5,506,014	A	4/1996	Minnick	6,773,653	B2	8/2004	Miller et al.
5,523,382	A	6/1996	Beavers et al.	6,818,293	B1	11/2004	Keep et al.
5,534,609	A	7/1996	Lewis et al.	6,818,730	B2	11/2004	Brandenburg et al.
5,633,340	A	5/1997	Hoffman et al.	6,846,440	B2	1/2005	Flynn et al.
5,650,453	A	7/1997	Eckberg et al.	6,846,508	B1	1/2005	Colas et al.
5,654,347	A	8/1997	Khemani et al.	6,896,966	B2	5/2005	Crawford et al.
5,656,715	A	8/1997	Dickerson et al.	6,908,650	B2	6/2005	Odorisio et al.
5,668,243	A	9/1997	Yau et al.	6,914,120	B2	7/2005	Germroth et al.
				7,037,576	B2	5/2006	Willham et al.

7,048,978	B2	5/2006	Tanaka et al.	EP	1 674 496	A1	6/2006
7,053,143	B2	5/2006	Mori et al.	FR	1291273		5/1965
7,122,661	B2	10/2006	Fleche et al.	FR	1432471		2/1966
7,169,880	B2	1/2007	Shelby et al.	FR	1434658		2/1966
7,297,755	B2	11/2007	Shelby et al.	FR	2.112.400		6/1972
7,354,628	B2	4/2008	Steube	GB	962913		7/1964
7,375,154	B2	5/2008	Stafford et al.	GB	1041651		9/1966
7,427,430	B2	9/2008	Rhee et al.	GB	1044015		9/1966
7,468,409	B2	12/2008	Pearson et al.	GB	1047043		11/1966
7,482,397	B2	1/2009	Pearson et al.	GB	1130558		10/1968
2001/0029324	A1	10/2001	Walker et al.	GB	1278284		6/1972
2001/0031805	A1	10/2001	Buhler	GB	1364732		8/1974
2001/0034419	A1	10/2001	Kanayama et al.	GB	2216919	A	10/1989
2001/0044003	A1	11/2001	Gallucci et al.	JP	56-88440	A	12/1979
2002/0055586	A1	5/2002	Dalgewicz, III et al.	JP	03207743		9/1991
2002/0128357	A1	9/2002	Goossens et al.	JP	65-01040		2/1994
2002/0132963	A1	9/2002	Quillen	JP	9-59371	A	4/1997
2002/0137856	A1	9/2002	Andrews et al.	JP	11-222516		8/1999
2002/0198297	A1	12/2002	Odorisio et al.	JP	2001-066701	A	8/1999
2003/0032737	A1	2/2003	Andrews et al.	JP	2000-352620	A	12/2000
2003/0060546	A1	3/2003	Moskala et al.	JP	2001-098086	A	4/2001
2003/0075516	A1	4/2003	Rothman et al.	JP	2001214049		8/2001
2003/0077546	A1	4/2003	Donovan et al.	JP	2004-244497	A	9/2004
2003/0135015	A1	7/2003	Fujimaki et al.	JP	2004-292558	A	10/2004
2003/0139497	A1	7/2003	Odorisio et al.	KR	2003/054611		7/2003
2003/0149177	A1	8/2003	Andrews et al.	WO	WO 01/06981		2/2001
2003/0169514	A1	9/2003	Bourdelais et al.	WO	0185824	A2	11/2001
2003/0187151	A1	10/2003	Adams et al.	WO	WO 02/059207	A2	8/2002
2003/0195295	A1	10/2003	Mahood et al.	WO	2004009146	A1	1/2004
2003/0221716	A1	12/2003	Olson	WO	WO 2004/106988	A2	12/2004
2003/0229181	A1	12/2003	Hariharan et al.	WO	2005007735	A2	1/2005
2004/0022526	A1	2/2004	Kuno et al.	WO	2006025827	A1	3/2006
2004/0063864	A1	4/2004	Adams et al.	WO	WO 2006/127755	A2	11/2006
2004/0101687	A1	5/2004	Crawford et al.	WO	WO 2006/127831	A1	11/2006
2004/0106707	A1	6/2004	Su et al.	WO	2007/053550	A1	5/2007
2004/0106767	A1	6/2004	Simon et al.	WO	2007053549	A1	5/2007
2004/0108623	A1	6/2004	Deeter et al.	WO	WO 2007/053434	A1	5/2007
2004/0138381	A1	7/2004	Blasius et al.	WO	WO 2007/053548	A1	5/2007
2004/0145700	A1	7/2004	Miniutti et al.				
2004/0164279	A1	8/2004	Stevenson et al.				
2004/0202822	A1	10/2004	Bourdelais et al.				
2004/0214984	A1	10/2004	Keep et al.				
2005/0008885	A1	1/2005	Blakely et al.				
2005/0072060	A1	4/2005	Moncho et al.				
2005/0096453	A1	5/2005	Flynn et al.				
2005/0101759	A1	5/2005	Odorisio et al.				
2005/0113556	A1	5/2005	Strand et al.				
2005/0119359	A1	6/2005	Shelby et al.				
2005/0124779	A1	6/2005	Shelby et al.				
2005/0181155	A1	8/2005	Share et al.				
2006/0004151	A1	1/2006	Shaikh et al.				
2006/0094858	A1	5/2006	Turner et al.				
2006/0111481	A1	5/2006	Pearson et al.				
2006/0111519	A1	5/2006	Strand et al.				
2006/0135668	A1	6/2006	Hayes				
2006/0146228	A1	7/2006	Sogo et al.				
2006/0180560	A1	8/2006	Robinson				
2006/0197246	A1	9/2006	Hale et al.				
2006/0199904	A1	9/2006	Hale et al.				
2006/0199919	A1	9/2006	Hale et al.				
2006/0228507	A1	10/2006	Hale et al.				
2006/0234073	A1	10/2006	Hale et al.				
2006/0235167	A1	10/2006	Hale et al.				
2006/0247388	A1	11/2006	Hale et al.				
2006/0270773	A1	11/2006	Hale et al.				
2006/0270806	A1	11/2006	Hale				
2007/0071930	A1	3/2007	Shelby et al.				

FOREIGN PATENT DOCUMENTS

CA	2035149	A1	8/1991
DE	29 21 868	A1	12/1980
DE	197 27 709	A1	6/1997
DE	198 11 773	A1	9/1999
EP	0 039 838	A1	11/1981
EP	0 273 144	A2	5/1987
EP	0 714 764	A2	6/1996
EP	0902052	A1	3/1999
EP	0 930 531	A1	7/1999
EP	1 066 825	A1	1/2001

OTHER PUBLICATIONS

USPTO Office Action dated Apr. 17, 2008 for copending U.S. Appl. No. 11/390,814.

U.S. Appl. No. 11/827,696, filed Jul. 13, 2007, Ryan Thomas Neill, et al.

U.S. Appl. No. 12/091,568, filed Apr. 25, 2008, Emmett Dudley Crawford, et al.

U.S. Appl. No. 12/091,566, filed Apr. 25, 2008, Emmett Dudley Crawford, et al.

U.S. Appl. No. 12/091,570, filed Apr. 25, 2008, Ted Calvin Germroth, et al.

U.S. Appl. No. 12/091,572, filed Apr. 25, 2008, Ted Calvin Germroth, et al.

Copending U.S. Appl. No. 12/294,686, filed Sep. 26, 2008, Ted Calvin Germroth et al.

Copending U.S. Appl. No. 12/294,686, filed Sep. 26, 2008, Ted Calvin Germroth et al.

USPTO Office Action dated Sep. 10, 2008 for copending U.S. Appl. No. 11/390,752.

USPTO Office Action dated Sep. 10, 2008 for copending U.S. Appl. No. 11/390,794.

USPTO Office Action dated Sep. 19, 2008 for copending U.S. Appl. No. 11/391,565.

USPTO Office Action dated Oct. 2, 2008 for copending U.S. Appl. No. 11/390,671.

USPTO Office Action dated Sep. 24, 2008 for copending U.S. Appl. No. 11/390,631.

USPTO Office Action dated Oct. 1, 2008 for copending U.S. Appl. No. 11/390,655.

USPTO Office Action dated Sep. 29, 2008 for copending U.S. Appl. No. 11/391,137.

USPTO Office Action dated Sep. 9, 2008 for copending U.S. Appl. No. 11/391,571.

Chapter 4—*Processing of Plastics in "Plastics Engineering, 3rd ed"*, R.J. Crawford, Butterworth-Heinemann Publisher, 1998, Oxford, England, pp. 245-342.

- Fox equation (T.G. Fox, Session J, Bull. Am. Phys. Soc., 1, 123 (1956)).
- The Technology of Plasticizers*, by J. Kern Sears and Joseph R Darby, published by Society of Plastic Engineers/Wiley and Sons, New York, 1982; pp. 136-139.
- Coleman et al., "Polymer Reviews—A Practical Guide to Polymer Miscibility," *Polymer* 31, pp. 1187-1203 (1990).
- "*Hansen Solubility Parameters, a Users Handbook*", by Charles M. Hansen, Chapter 1, CRC Press, 2000, pp. 1-24.
- Martinez et al., "*Phase Behavior and Mechanical Properties of Injection Molded Poly (Ethylene Terephthalate) / Polyarylate Blends*", *Journal of Applied Polymer Science*, John Wiley and Sons Inc. New York, US, vol. 45, No. 7, Jul. 5, 1992, p. 1135-1143.
- Won Ho Jo et al. : "*Miscibility of poly(ether imide)/poly(ethylene terephthalate) blends*"; *Polymer Bulletin*, Springer, Heidelberg, DE, vol. 33, No. 1, Jun. 1, 1994, p. 113-118 (1994).
- Anonymous: "*Poly (ethylene naphthalenedicarboxylate)/polyetherimide blends*" Research Disclosure, Mason Publications, Hampshire, GB, vol. 283, No. 38, Nov. 1987.
- ASTM D1525—06, *Standard Test Method for Vicat Softening Temperature of Plastics*, Mar. 15, 2006.
- ASTM D648—06, *Standard Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position*, Mar. 15, 2006.
- ASTM D256—06, *Standard Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics*, Mar. 15, 2006.
- ASTM D790—03, *Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials*, Mar. 10, 2003.
- ASTM D638—03, *Standard Test Method for Tensile Properties of Plastics*, Dec. 1, 2003.
- ASTM D3418-03, *Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry*, Dec. 1, 2003.
- Bergen, R.L., Jr., "Stress Cracking of Rigid Thermoplastics," *SPE Journal*, Jun. 1962.
- C.I. Constitution No. 515240.
- C.I. Constitution No. 515245.
- Database WPI, Section Ch, Week 200536, Derwent Publications Ltd., London, GB; AN 2005-355258, XP002396922 & WO 2005-030833 A1 (Kanebo Ltd) Apr. 7, 2005 abstract.
- "*Plastic Additives Handbook*," 5th Edition, 2001, pp. 98-108 and pp. 109-112 (Hanser Gardner Publications, Inc., Cincinnati, OH).
- Shearer, N.H., "T18-Type 1 Polyesters," Mar. 1996, *SPE Annual Technical Conference and Exhibition*, XP009080224.
- U.S. Appl. No. 11/439,062, filed May 23, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/439,340, filed May 23, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/706,476, filed Feb. 14, 2007, Leslie Shane Moody, et al.
- U.S. Appl. No. 11/706,791, filed Feb. 14, 2007, Leslie Shane Moody, et al.
- Brown, R., "Taschenbuch Kunststoff-Additive," 1990, Carl Hanser Verlag Munchen Wiel, XP002455247, pp.361-363.
- USPTO Office Action dated Oct. 29, 2008 for copending U.S. Appl. No. 11/390,955.
- USPTO Office Action dated Nov. 3, 2008 for copending U.S. Appl. No. 11/390,883.
- USPTO Office Action dated Oct. 29, 2008 for copending U.S. Appl. No. 11/390,864.
- USPTO Notice of Allowance dated Nov. 3, 2008 for copending U.S. Appl. No. 11/391,642.
- USPTO Office Action dated Oct. 31, 2008 for copending U.S. Appl. No. 11/391,156.
- USPTO Office Action dated Oct. 30, 2008 for copending U.S. Appl. No. 11/391,495.
- USPTO Office Action dated Nov. 3, 2008 for copending U.S. Appl. No. 11/391,485.
- Copending U.S. Appl. No. 12/254,894, filed Oct. 21, 2008, Gary Michael Stack, et al.
- USPTO Office Action dated Oct. 22, 2008 for copending U.S. Appl. No. 11/391,125.
- USPTO Office Action dated Oct. 20, 2008 for copending U.S. Appl. No. 11/390,672.
- USPTO Office Action dated Oct. 8, 2008 for copending U.S. Appl. No. 11/390,853.
- USPTO Office Action dated Oct. 9, 2008 for copending U.S. Appl. No. 11/391,505.
- USPTO Notice of Allowance dated Oct. 7, 2008 for copending U.S. Appl. No. 11/390,908.
- USPTO Office Action dated Oct. 14, 2008 for copending U.S. Appl. No. 11/390,811.
- USPTO Office Action dated Oct. 22, 2008 for copending U.S. Appl. No. 11/390,750.
- USPTO Office Action dated Oct. 22, 2008 for copending U.S. Appl. No. 11/390,865.
- USPTO Office Action dated Oct. 14, 2008 for copending U.S. Appl. No. 11/390,654.
- USPTO Office Action dated Oct. 20, 2008 for copending U.S. Appl. No. 11/390,836.
- USPTO Office Action dated Jun. 3, 2008 for copending U.S. Appl. No. 11/391,063.
- Chang, S. et al., "Effect of Stabilizers on the Preparation of Poly(ethylene Terephthalate)", *Journal of Polymer Science, Polymer Chemistry Edition*, 1982, vol. 20, pp. 2053-2061, John Wiley & Sons, Inc.
- USPTO Office Action dated Mar. 11, 2008 for copending U.S. Appl. No. 11/391,642.
- USPTO Office Action dated Mar. 24, 2008 for copending U.S. Appl. No. 11/390,908.
- USPTO Office Action dated Apr. 15, 2008 for copending U.S. Appl. No. 11/390,629.
- Copending U.S. Appl. No. 11/588,524, filed Oct. 27, 2006, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 11/588,458, filed Oct. 27, 2006, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 11/588,907, filed Oct. 27, 2006, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 11/588,527, filed Oct. 27, 2006, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 11/588,906, filed Oct. 27, 2006, Ted Calvin Germroth, et al.
- Copending U.S. Appl. No. 11/588,893, filed Oct. 27, 2006, Ted Calvin Germroth, et al.
- Copending U.S. Appl. No. 11/588,554, filed Oct. 27, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/635,434, filed Dec. 7, 2006, Emmett Dudley Crawford.
- U.S. Appl. No. 11/635,433, filed Dec. 7, 2006, Emmett Dudley Crawford.
- Abstract of U.S. Defense Publication T869,015, 869 O.G. 714, Dec. 16, 1969.
- Abstract of U.S. Defense Publication T875,010, 875 O.G. 342, Jun. 9, 1970.
- Chen et al., "The molecular basis for the relationship between the secondary relaxation and mechanical properties of a series of polyester copolymer glasses," *Makromol. Chem.* 32:5944-5955 (1999).
- English language Abstract of JP 02-305816 from Patent Abstracts of Japan, Dec. 19, 1990.
- English language translation of Belgian Patent No. BE 615,850, Apr. 13, 1962.
- English language translation of French Patent No. FR 1,432,471, Feb. 7, 1966.
- English language translation of French Patent No. FR 1,434,658, Feb. 28, 1966.
- U.S. Appl. No. 11/390,555, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,563, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,629, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,630, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,631, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.

- U.S. Appl. No. 11/390,654, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,655, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,671, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,672, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,722, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,750, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,751, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,752, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,773, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,793, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,794, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,809, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/390,811, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,812, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/390,814, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,826, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,827, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,836, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,846, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/390,847, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,853, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,864, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/390,865, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,882, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/390,883, filed Mar. 28, 2006, Thomas Joseph Pecorini, et al.
- U.S. Appl. No. 11/390,908, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/391,063, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,124, filed Mar. 28, 2006, Wesley Raymond Hale, et al.
- U.S. Appl. No. 11/391,125, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,137, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,156, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,485, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,495, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,505, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,565, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,571, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,576, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,642, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- U.S. Appl. No. 11/391,659, filed Mar. 28, 2006, Emmett Dudley Crawford, et al.
- Kelsey: *Macromolecules*, vol. 33, 2000, pp. 5810-5818.
- Gachter, Muller, "Taschenbuch der Kunststoff-Additive," 1990, Carl Hanser Verlag Munchen Wien, XP002450422, pp. 96-97.
- Gachter, Muller, "Kunststoff-Additive," 1990, Carl Hanser Verlag Munchen Wien, XP002449987, pp. 96-99.
- Copending U.S. Appl. No. 12/338,453, filed Dec. 18, 2008, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 12/274,692, filed Nov. 11, 2008, Thomas Joseph Pecorini, et al.
- USPTO Office Action dated Dec. 19, 2008 for copending U.S. Appl. No. 11/390,751.
- USPTO Office Action dated Dec. 31, 2008 for copending U.S. Appl. No. 11/390,827.
- USPTO Office Action dated Dec. 31, 2008 for copending U.S. Appl. No. 11/390,826.
- USPTO Office Action dated Nov. 14, 2008 for copending U.S. Appl. No. 11/390,630.
- USPTO Office Action dated Dec. 19, 2008 for copending U.S. Appl. No. 11/391,576.
- USPTO Office Action dated Dec. 19, 2008 for copending U.S. Appl. No. 11/390,629.
- USPTO Office Action dated Dec. 31, 2008 for copending U.S. Appl. No. 11/390,773.
- USPTO Office Action dated Nov. 14, 2008 for copending U.S. Appl. No. 11/390,882.
- USPTO Office Action dated Dec. 12, 2008 for copending U.S. Appl. No. 11/391,063.
- USPTO Office Action dated Dec. 19, 2008 for copending U.S. Appl. No. 11/390,814.
- USPTO Office Action dated Dec. 31, 2008 for copending U.S. Appl. No. 11/390,722.
- Copending U.S. Appl. No. 12/361,779, filed Jan. 29, 2009, Emmett Dudley Crawford, et al.
- Copending U.S. Appl. No. 12/365,515, filed Feb. 4, 2009, Emmett Dudley Crawford, et al.
- USPTO Office Action dated Jan. 29, 2009 for copending U.S. Appl. No. 11/588,524.
- USPTO Office Action dated Jan. 30, 2009 for copending U.S. Appl. No. 11/588,458.
- USPTO Office Action dated Feb. 2, 2009 for copending U.S. Appl. No. 11/390,853.
- Scheirs, John, et al., "Modern Polyesters: Chemistry and Technology of Polyesters and Copolyesters," *Technology & Engineering*, 2003, p. 287.
- USPTO Office Action dated Jan. 21, 2009 for copending U.S. Appl. No. 11/390,847.
- USPTO Office Action dated Jan. 26, 2009 for copending U.S. Appl. No. 11/588,554.
- USPTO Office Action dated Jan. 26, 2009 for copending U.S. Appl. No. 11/391,659.
- USPTO Office Action dated Feb. 3, 2009 for copending U.S. Appl. No. 11/391,505.
- USPTO Office Action dated Feb. 10, 2009 for copending U.S. Appl. No. 11/390,865.
- USPTO Office Action dated Feb. 12, 2009 for copending U.S. Appl. No. 11/439,062.
- USPTO Office Action dated Feb. 13, 2009 for copending U.S. Appl. No. 11/439,340.
- USPTO Office Action dated Feb. 25, 2009 for copending U.S. Appl. No. 11/588,907.
- USPTO Office Action dated Feb. 25, 2009 for copending U.S. Appl. No. 11/588,527.
- USPTO Office Action dated Feb. 27, 2009 for copending U.S. Appl. No. 11/390,955.
- USPTO Office Action dated Feb. 25, 2009 for copending U.S. Appl. No. 11/588,906.

- USPTO Office Action dated Feb. 25, 2009 for copending U.S. Appl. No. 11/588,883.
- USPTO Office Action dated Mar. 5, 2009 for copending U.S. Appl. No. 11/390,864.
- USPTO Office Action dated Mar. 6, 2009 for copending U.S. Appl. No. 11/391,156.
- USPTO Office Action dated Feb. 25, 2009 for copending U.S. Appl. No. 11/390,811.
- USPTO Office Action dated Feb. 27, 2009 for copending U.S. Appl. No. 11/390,654.
- USPTO Office Action dated Feb. 27, 2009 for copending U.S. Appl. No. 11/390,836.
- USPTO Office Action dated Mar. 13, 2009 for copending U.S. Appl. No. 11/390,883.
- USPTO Office Action dated Mar. 11, 2009 for copending U.S. Appl. No. 11/390,630.
- USPTO Office Action dated Mar. 9, 2009 for copending U.S. Appl. No. 11/391,495.
- USPTO Office Action dated Mar. 9, 2009 for copending U.S. Appl. No. 11/390,750.
- Copending U.S. Appl. No. 12/390,694, filed Feb. 23, 2009, Gary Michael Stack.
- USPTO Office Action dated Apr. 17, 2009 for copending U.S. Appl. No. 11/391,565.
- USPTO Office Action dated Apr. 15, 2009 for copending U.S. Appl. No. 12/091,566.
- USPTO Office Action dated Apr. 17, 2009 for copending U.S. Appl. No. 11/390,671.
- USPTO Office Action dated Apr. 20, 2009 for copending U.S. Appl. No. 11/390,631.
- USPTO Office Action dated Apr. 27, 2009 for copending U.S. Appl. No. 11/390,655.
- USPTO Office Action dated Apr. 27, 2009 for copending U.S. Appl. No. 11/391,137.
- USPTO Office Action dated Apr. 16, 2009 for copending U.S. Appl. No. 12/091,570.
- USPTO Office Action dated Apr. 2, 2009 for copending U.S. Appl. No. 11/390,793.
- USPTO Office Action dated Mar. 31, 2009 for copending U.S. Appl. No. 11/390,563.
- USPTO Notice of Allowance dated Apr. 13, 2009 for copending U.S. Appl. No. 11/391,063.
- USPTO Office Action dated Mar. 16, 2009 for copending U.S. Appl. No. 11/391,485.
- USPTO Office Action dated Mar. 16, 2009 for copending U.S. Appl. No. 11/390,882.
- USPTO Office Action dated Mar. 23, 2009 for copending U.S. Appl. No. 11/390,794.
- USPTO Office Action dated Mar. 23, 2009 for copending U.S. Appl. No. 11/390,752.
- USPTO Office Action dated May 13, 2009 for copending U.S. Appl. No. 12/361,779.
- USPTO Office Action dated May 13, 2009 for copending U.S. Appl. No. 12/365,515.
- USPTO Office Action dated May 21, 2009 for copending U.S. Appl. No. 11/706,476.
- USPTO Office Action dated May 22, 2009 for copending U.S. Appl. No. 11/706,791.
- USPTO Office Action dated May 18, 2009 for copending U.S. Appl. No. 11/391,505.
- USPTO Office Action dated Apr. 14, 2009 for copending U.S. Appl. No. 11/635,434.
- USPTO Office Action dated Apr. 14, 2009 for copending U.S. Appl. No. 11/635,433.
- USPTO Office Action dated May 18, 2009 for copending U.S. Appl. No. 11/390,846.
- New Copending U.S. Appl. No. 12/479,893, filed Jun. 8, 2009, Emmett Dudley Crawford, et al.
- USPTO Office Action dated Jun. 11, 2009 for copending U.S. Appl. No. 11/390,809.
- Shearer, N.H., "T18-Type 1 Polyesters," Mar. 1996, SPE Annual Technical Conference and Exhibition, XP009080224 (correcting data of reference; previously cited in IDS submitted on Jun. 1, 2007).
- USPTO Office Action dated Jul. 2, 2009 for copending U.S. Appl. No. 11/390,827.
- USPTO Office Action dated Aug. 7, 2009 for copending U.S. Appl. No. 11/390,773.
- USPTO Office Action dated Aug. 10, 2009 for copending U.S. Appl. No. 11/390,722.
- USPTO Office Action dated Aug. 27, 2009 for copending U.S. Appl. No. 11/390,826.
- Dixon, E.R. et al., "The Inter-Relation of Some Mechanical Properties with Molecular Weight and Crystallinity in Poly (ethylene terephthalate)," 1968, pp. 464-470, Journal of Materials Science, vol. 3.
- USPTO Office Action dated Sep. 2, 2009 for copending U.S. Appl. No. 11/391,124.
- USPTO Office Action dated Sep. 10, 2009 for copending U.S. Appl. No. 11/390,812.
- USPTO Office Action dated Sep. 14, 2009 for copending U.S. Appl. No. 11/391,576.
- Ellis, Thomas S., "Miscibility of Polyamide Blends: Effects of Configuration," 1995, Polymer, vol. 36, Issue 20, pp. 3919-3926.
- Buschow, K.H.J., "Packaging: Papers for Sacks and Bags," 2001, Encyclopedia of Materials: Science and Technology, vol. 8, Elsevier, pp. 6646-6652.
- Coles, Richard, et al., "Food Packaging Technology," 2003, pp. 194-195 and 224-229, Blackwell Publishing.
- Sajiki, Junko, et al., "Leaching of Bisphenol A (BPA) to Seawater from Polycarbonate Plastic and its Degradation by Reactive Oxygen Species," 2003, Chemosphere, 51, pp. 55-62.
- USPTO Office Action dated Oct. 2, 2009 for copending U.S. Appl. No. 11/588,524.
- USPTO Office Action dated Oct. 7, 2009 for copending U.S. Appl. No. 11/588,458.
- USPTO Office Action dated Sep. 29, 2009 for copending U.S. Appl. No. 11/390,751.
- USPTO Office Action dated Sep. 24, 2009 for copending U.S. Appl. No. 11/588,883.
- USPTO Office Action dated Sep. 28, 2009 for copending U.S. Appl. No. 11/390,847.
- Lobo, Hubert et al, "Handbook of Plastics Analysis," 2003, pp. 20 and 21, Marcel Dekker, Inc.
- USPTO Office Action dated Sep. 29, 2009 for copending U.S. Appl. No. 11/390,629.
- USPTO Office Action dated Sep. 29, 2009 for copending U.S. Appl. No. 11/390,814.
- USPTO Office Action dated Oct. 19, 2009 for copending U.S. Appl. No. 11/390,563.
- USPTO Office Action dated Oct. 20, 2009 for copending U.S. Appl. No. 11/588,907.
- Gupta, V.B. et al., "PET Fibers, Films, and Bottles: Sections 5-7", Handbook of Thermoplastic Polyesters: Homopolymers, Copolymers, Blends, and Composites, 2005, pp. 362-388, Wiley InterScience.
- USPTO Office Action dated Oct. 21, 2009 for copending U.S. Appl. No. 11/391,156.
- USPTO Office Action dated Oct. 22, 2009 for copending U.S. Appl. No. 11/588,906.
- USPTO Office Action dated Nov. 3, 2009 for copending U.S. Appl. No. 11/390,883.
- USPTO Office Action dated Nov. 4, 2009 for copending U.S. Appl. No. 11/390,750.
- USPTO Office Action dated Nov. 4, 2009 for copending U.S. Appl. No. 11/390,864.
- USPTO Office Action dated Nov. 18, 2009 for copending U.S. Appl. No. 11/390,794.
- USPTO Office Action dated Nov. 20, 2009 for copending U.S. Appl. No. 11/391,485.
- USPTO Office Action dated Nov. 20, 2009 for copending U.S. Appl. No. 11/390,882.
- USPTO Office Action dated Nov. 18, 2009 for copending U.S. Appl. No. 11/390,630.
- USPTO Office Action dated Nov. 30, 2009 for copending U.S. Appl. No. 11/391,495.

- Turner, S.R., et al. "Amorphous and Crystalline Polyesters based on 1,4-Cyclohexanedimethanol," Chapter 7, Modern Polyesters: Chemistry and Technology of Polyesters and Copolyesters, Edited by J. Sheirs and T.E. Long, 2003, John Wiley & Sons, Ltd., pp. 267-292.
- USPTO Office Action dated Nov. 17, 2009 for copending U.S. Appl. No. 12/254,894.
- USPTO Office Action dated Dec. 3, 2009 for copending U.S. Appl. No. 11/395,505.
- USPTO Office Action dated Dec. 1, 2009 for copending U.S. Appl. No. 12/091,570.
- USPTO Office Action dated Dec. 4, 2009 for copending U.S. Appl. No. 12/091,566.
- Zipper, Marcus D. et al., "A Free Volume Study of Miscible Polyester Blends," 1995, pp. 127-136, Polymer International, vol. 36.
- "APEC High-Heat Polycarbonate Resin," 2004, Bayer Material Science Product Information; Not Prior Art; Submitted for State of the Art.
- USPTO Notice of Allowance dated Dec. 11, 2009 for copending U.S. Appl. No. 12/365,515.
- USPTO Notice of Allowance dated Dec. 22, 2009 for copending U.S. Appl. No. 12/361,779.
- USPTO Office Action dated Dec. 18, 2009 for copending U.S. Appl. No. 11/390,846.
- USPTO Office Action dated Jan. 7, 2010 for copending U.S. Appl. No. 12/091,568.
- USPTO Office Action dated Jan. 13, 2010 for copending U.S. Appl. No. 11/635,433.
- USPTO Office Action dated Jan. 14, 2010 for copending U.S. Appl. No. 11/390,809.
- USPTO Notice of Allowance dated Jan. 27, 2010 for copending U.S. Appl. No. 11/635,434.
- USPTO Notice of Allowance dated May 26, 2010 for copending U.S. Appl. No. 11/391,495.
- USPTO Office Action dated Mar. 11, 2010 for copending U.S. Appl. No. 11/391,124.
- USPTO Office Action dated Mar. 29, 2010 for copending U.S. Appl. No. 11/390,812.
- USPTO Office Action dated May 6, 2010 for copending U.S. Appl. No. 12/254,894.
- USPTO Notice of Allowance dated Apr. 15, 2010 for copending U.S. Appl. No. 11/391,505.
- New copending U.S. Appl. No. 12/639,324, filed Dec. 16, 2009, Wesley Raymond Hale, et al.
- New copending U.S. Appl. No. 12/724,468, filed Mar. 16, 2010, Emmett Dudley Crawford, et al.
- New copending U.S. Appl. No. 12/724,480, filed Mar. 16, 2010, Emmett Dudley Crawford, et al.
- New copending U.S. Appl. No. 12/724,492, filed Mar. 16, 2010, Emmett Dudley Crawford, et al.
- New copending U.S. Appl. No. 12/784,193, filed May 20, 2010, Emmett Dudley Crawford, et al.
- USPTO Office Action dated Mar. 19, 2010 for copending U.S. Appl. No. 11/588,527.
- USPTO Office Action dated Apr. 21, 2010 for copending U.S. Appl. No. 12/724,468.
- USPTO Office Action dated Apr. 19, 2010 for copending U.S. Appl. No. 12/724,480.
- USPTO Office Action dated Apr. 21, 2010 for copending U.S. Appl. No. 12/724,492.
- USPTO Notice of Allowance dated Mar. 24, 2010 for copending U.S. Appl. No. 11/391,565.
- USPTO Notice of Allowance dated May 13, 2010 for copending U.S. Appl. No. 11/390,629.
- USPTO Notice of Allowance dated May 13, 2010 for copending U.S. Appl. No. 11/390,751.
- USPTO Notice of Allowance dated May 21, 2010 for copending U.S. Appl. No. 11/391,156.
- USPTO Office Action dated Jun. 24, 2010 for copending U.S. Appl. No. 11/390,846.
- USPTO Office Action dated Jul. 8, 2010 for copending U.S. Appl. No. 11/390,809.
- USPTO Notice of Allowance dated Jul. 8, 2010 for copending U.S. Appl. No. 11/390,630.
- USPTO Notice of Allowance dated Jul. 13, 2010 for copending U.S. Appl. No. 11/391,505.
- USPTO Office Action dated Jul. 12, 2010 for copending U.S. Appl. No. 11/390,794.
- USPTO Notice of Allowance dated Jul. 8, 2010 for copending U.S. Appl. No. 11/390,883.
- USPTO Notice of Allowance dated Jun. 24, 2010 for copending U.S. Appl. No. 11/391,576.
- USPTO Office Action dated Jul. 22, 2010 for copending U.S. Appl. No. 12/479,893.
- USPTO Notice of Allowance dated Jul. 22, 2010 for copending U.S. Appl. No. 11/391,485.
- USPTO Notice of Allowance dated Aug. 3, 2010 for copending U.S. Appl. No. 11/390,864.
- USPTO Notice of Allowance dated Aug. 11, 2010 for copending U.S. Appl. No. 11/390,631.
- New copending U.S. Appl. No. 12/853,717, filed Aug. 10, 2010, Emmett Dudley Crawford, et al.
- USPTO Office Action dated Oct. 27, 2010 for copending U.S. Appl. No. 12/294,690.
- USPTO Office Action dated Oct. 5, 2010 for copending U.S. Appl. No. 11/390,655.
- USPTO Office Action dated Oct. 6, 2010 for copending U.S. Appl. No. 11/390,812.
- USPTO Office Action dated Sep. 2, 2010 for copending U.S. Appl. No. 11/391,124.
- USPTO Notice of Allowance dated Sep. 2, 2010 for copending U.S. Appl. No. 11/390,811.
- USPTO Notice of Allowance dated Oct. 14, 2010 for copending U.S. Appl. No. 11/390,722.
- USPTO Notice of Allowance dated Oct. 28, 2010 for copending U.S. Appl. No. 11/390,827.
- New Copending U.S. Appl. No. 12/900,060, filed Oct. 7, 2010, Thomas Joseph Pecorini, et al.
- USPTO Notice of Allowance dated Nov. 4, 2010 for copending U.S. Appl. No. 11/390,955.
- USPTO Notice of Allowance dated Nov. 4, 2010 for copending U.S. Appl. No. 12/724,468.
- USPTO Notice of Allowance dated Nov. 2, 2010 for copending U.S. Appl. No. 12/724,480.
- USPTO Office Action dated Nov. 4, 2010 for copending U.S. Appl. No. 12/294,686.
- USPTO Notice of Allowance dated Nov. 4, 2010 for copending U.S. Appl. No. 11/390,826.
- USPTO Office Action dated Oct. 27, 2010 for copending U.S. Appl. No. 11/390,836.
- USPTO Office Action dated Feb. 2, 2011 for copending U.S. Appl. No. 11/390,655.
- USPTO Office Action dated Jan. 25, 2011 for copending U.S. Appl. No. 12/853,717.
- New Copending U.S. Appl. No. 13/017,352 filed on Jan. 31, 2011, Emmett Dudley Crawford, et al.
- USPTO Notice of Allowance dated Nov. 23, 2010 for copending U.S. Appl. No. 11/390,563.
- New copending U.S. Appl. No. 13/017,069 filed on Jan. 31, 2011, Emmett Dudley Crawford, et al.
- New copending U.S. Appl. No. 12/943,217 filed on Nov. 10, 2010, Emmett Dudley Crawford et al.
- New copending U.S. Appl. No. 13/007,838 filed on Jan. 17, 2011, Emmett Dudley Crawford et al.
- New copending U.S. Appl. No. 13/016,147 filed on Jan. 28, 2011, Emmett Dudley Crawford, et al.
- USPTO Notice of Allowance dated Feb. 18, 2011 for copending U.S. Appl. No. 11/390,809.
- USPTO Notice of Allowance dated Feb. 17, 2011 for copending U.S. Appl. No. 11/390,812.
- USPTO Office Action dated Mar. 17, 2011 for copending U.S. Appl. No. 12/479,893.
- USPTO Office Action dated Feb. 14, 2011 for copending U.S. Appl. No. 12/294,690.
- USPTO Notice of Allowance dated Mar. 17, 2011 for copending U.S. Appl. No. 11/391,137.





Fig. 1

THE EFFECT OF COMONOMER ON
 THE FASTEST CRYSTALLIZATION
 HALFTIMES OF MODIFIED PCT COPOLYESTERS





Fig. 2

THE EFFECT OF COMONOMER ON
 THE BRITTLE-TO-DUCTILE TRANSITION
 TEMPERATURE (T_{bd}) IN A NOTCHED IZOD TEST
 (ASTM D256, 1/8 IN THICK, 10 MIL NOTCH)





Fig. 3

THE EFFECT OF 2,2,4,4-TETRAMETHYL-1,3-CYCLOBUTANEDIOL COMPOSITION ON THE GLASS TRANSITION TEMPERATURE (T_g) OF THE COPOLYESTER

1

**DIALYSIS FILTER HOUSINGS COMPRISING
POLYESTER COMPOSITIONS FORMED
FROM
2,2,4,4-TETRAMETHYL-1,3-CYCLOBUTANEDIOL
AND 1,4-CYCLOHEXANEDIMETHANOL**

CROSS-REFERENCES TO RELATED
APPLICATIONS

This application claims priority under 35 U.S.C. §119(e) to U.S. Provisional Application Ser. No. 60/691,567 filed on Jun. 17, 2005, U.S. Provisional Application Ser. No. 60/731,454 filed on Oct. 28, 2005, U.S. Provisional Application Ser. No. 60/731,389, filed on Oct. 28, 2005, U.S. Provisional Application Ser. No. 60/739,058, filed on Nov. 22, 2005, and U.S. Provisional Application Ser. No. 60/738,869, filed on Nov. 22, 2005, U.S. Provisional Application Ser. No. 60/750,692 filed on Dec. 15, 2005, U.S. Provisional Application Ser. No. 60/750,693, filed on Dec. 15, 2005, U.S. Provisional Application Ser. No. 60/750,682, filed on Dec. 15, 2005, and U.S. Provisional Application Ser. No. 60/750,547, filed on Dec. 15, 2005, all of which are hereby incorporated by this reference in their entireties.

FIELD OF THE INVENTION

The present invention generally relates to dialysis filter housings comprising a polyester compositions made from terephthalic acid, or an ester thereof, or mixtures thereof, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol, having a certain combination of two or more of high impact strengths, high glass transition temperature (T_g), toughness, certain inherent viscosities, low ductile-to-brittle transition temperatures, good color and clarity, low densities, chemical resistance, hydrolytic stability, and long crystallization half-times, which allow them to be easily formed into articles. For example, the dialysis filter housings of the present invention can have a combination of two or more of the following properties: toughness, clarity, chemical resistance, T_g , and hydrolytic stability.

BACKGROUND OF THE INVENTION

Dialysis filter housings can be produced with a variety of plastic materials by a variety of processes, such as injection molding. Polycarbonates are widely used in a variety of molding and extrusion applications.

Poly(1,4-cyclohexylenedimethylene) terephthalate (PCT), a polyester based solely on terephthalic acid or an ester thereof and 1,4-cyclohexanedimethanol, is known in the art and is commercially available. This polyester crystallizes rapidly upon cooling from the melt, making it very difficult to form amorphous articles by methods known in the art such as extrusion, injection molding, and the like. In order to slow down the crystallization rate of PCT, copolyesters can be prepared containing additional dicarboxylic acids or glycols such as isophthalic acid or ethylene glycol. These ethylene glycol-or isophthalic acid-modified PCTs are also known in the art and are commercially available.

One common copolyester used to produce films, sheeting, and molded articles is made from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol. While these copolyesters are useful in many end-use applications, they exhibit deficiencies in properties such as glass transition temperature and impact strength when sufficient modifying ethylene glycol is included in the formulation to provide for long crystallization half-times. For example, copolyesters made

2

from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol with sufficiently long crystallization half-times can provide amorphous products that exhibit what is believed to be undesirably higher ductile-to-brittle transition temperatures and lower glass transition temperatures than the compositions revealed herein.

The polycarbonate of 4,4'-isopropylidenediphenol (bisphenol A polycarbonate) has been used as an alternative for polyesters known in the art and is a well known engineering molding plastic. Bisphenol A polycarbonate is a clear, high-performance plastic having good physical properties such as dimensional stability, high heat resistance, and good impact strength. Although bisphenol-A polycarbonate has many good physical properties, its relatively high melt viscosity leads to poor melt processability and the polycarbonate exhibits poor chemical resistance. It is also difficult to thermoform.

Polymers containing 2,2,4,4-tetramethyl-1,3-cyclobutanediol have also been generally described in the art. Generally, however, these polymers exhibit high inherent viscosities, high melt viscosities and/or high T_g s (glass transition temperatures) such that the equipment used in industry can be insufficient to manufacture or post polymerization process these materials.

Thus, there is a need in the art for dialysis filter housings comprising at least one polymer having a combination of two or more properties, chosen from at least one of the following: toughness, high glass transition temperatures, high impact strength, hydrolytic stability, chemical resistance, long crystallization half-times, low ductile to brittle transition temperatures, good color, and clarity, lower density and/or thermoformability of polyesters while retaining processability on the standard equipment used in the industry.

SUMMARY OF THE INVENTION

It is believed that certain dialysis filter housings comprising polyester compositions formed from terephthalic acid, an ester thereof, or mixtures thereof, 1,4-cyclohexanedimethanol and 2,2,4,4-tetramethyl-1,3-cyclobutanediol with certain monomer compositions, inherent viscosities and/or glass transition temperatures are superior to polyesters known in the art and to polycarbonate with respect to one or more of high impact strengths, hydrolytic stability, toughness, chemical resistance, good color and clarity, long crystallization half-times, low ductile to brittle transition temperatures, lower specific gravity, and thermoformability. These compositions are believed to be similar to polycarbonate in heat resistance and are still processable on the standard industry equipment.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
 - i) 10 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 1 to 90 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

3

wherein the inherent viscosity of the polyester is from 0.1 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 200° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 15 to 70 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 30 to 85 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 160° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 15 to 70 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 30 to 85 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 150° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 15 to 60 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 40 to 85 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

4

wherein the inherent viscosity of the polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 150° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 15 to 90 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 10 to 85 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.1 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 200° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (I) at least one polyester which comprises:
 - (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 10 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 1 to 90 mole % of 1,4-cyclohexanedimethanol residues, and

(II) residues of at least one branching agent; wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.1 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 200° C.

In one aspect, the invention relates to a dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (I) at least one polyester which comprises:
 - (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
 - i) 10 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 1 to 90 mole % of 1,4-cyclohexanedimethanol residues, and

5

(II) at least one thermal stabilizer or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of the polyester is from 0.1 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.; and

wherein the polyester has a Tg of from 100 to 200° C.

In one aspect, the polyester composition contains at least one polycarbonate.

In one aspect, the polyester composition contains no polycarbonate.

In one aspect, the polyesters useful in the invention contain less than 15 mole % ethylene glycol residues, such as, for example, 0.01 to less than 15 mole % ethylene glycol residues.

In one aspect, the polyesters useful in the invention contain no ethylene glycol residues.

In one aspect the polyester compositions useful in the invention contain at least one thermal stabilizer and/or reaction products thereof.

In one aspect, the polyesters useful in the invention contain no branching agent, or alternatively, at least one branching agent is added either prior to or during polymerization of the polyester.

In one aspect, the polyesters useful in the invention contain at least one branching agent without regard to the method or sequence in which it is added.

In one aspect, the polyesters useful in the invention are made from no 1,3-propanediol, or, 1,4-butanediol, either singly or in combination. In other aspects, 1,3-propanediol or 1,4-butanediol, either singly or in combination, may be used in the making of the polyesters useful in this invention.

In one aspect of the invention, the mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is greater than 50 mole % or greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or greater than 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol; wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

In one aspect of the invention, the mole % of the isomers of 2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is from 30 to 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 30 to 70 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, or from 40 to 60 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 40 to 60 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

In one aspect, the polyester compositions are useful in dialysis filter housing(s) including but not limited to, molded articles including but not limited to, injection molded articles.

Also, in one aspect, use of the polyester compositions of the invention minimizes and/or eliminates the drying step prior to melt processing or thermoforming.

In one aspect, certain polyesters useful in the invention can be amorphous or semicrystalline. In one aspect, certain polyesters useful in the invention can have a relatively low crystallinity. Certain polyesters useful in the invention can thus

6

have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a graph showing the effect of comonomer on the fastest crystallization half-times of modified PCT copolyesters.

FIG. 2 is a graph showing the effect of comonomer on the brittle-to-ductile transition temperature (T_{bd}) in a notched Izod impact strength test (ASTM D256, 1/8-in thick, 10-mil notch).

FIG. 3 is a graph showing the effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol composition on the glass transition temperature (Tg) of the copolyester.

DETAILED DESCRIPTION OF THE INVENTION

The present invention may be understood more readily by reference to the following detailed description of certain embodiments of the invention and the working examples.

In accordance with the purpose(s) of this invention, certain embodiments of the invention are described in the Summary of the invention and are further described herein below. Also, other embodiments of the invention are described herein.

It is believed that the polyester(s) and/or polyester composition(s) which are included in the dialysis filter housing(s) of the invention described herein can have a unique combination of two or more physical properties such as high impact strengths, moderate to high glass transition temperatures, chemical resistance, hydrolytic stability, toughness, low ductile-to-brittle transition temperatures, good color and clarity, low densities, long crystallization half-times, and good processability thereby easily permitting them to be formed into articles. In some of the embodiments of the invention, the polyesters have a unique combination of the properties of good impact strength, heat resistance, chemical resistance, density and/or the combination of the properties of good impact strength, heat resistance, and processability and/or the combination of two or more of the described properties, that have never before been believed to be present in dialysis filter housing(s) comprising the polyester compositions which comprise the polyester(s) as disclosed herein.

A "dialysis filter housing," as used herein, refers to a protective casing having a plurality of openings for holding a plurality of hollow fibers or tubing, which can be used for introducing and discharging a dialyzate to a patient. In one embodiment, a cross-sectional area of one opening in the protective casing ranges from 0.001 cm² to less than 50 cm².

In one embodiment, the dialysis filter housing has at least one property chosen from toughness, clarity, chemical resistance, Tg, and hydrolytic stability.

The term "polyester", as used herein, is intended to include "copolyesters" and is understood to mean a synthetic polymer prepared by the reaction of one or more difunctional carboxylic acids and/or multifunctional carboxylic acids with one or more difunctional hydroxyl compounds and/or multifunctional hydroxyl compounds. Typically the difunctional carboxylic acid can be a dicarboxylic acid and the difunctional hydroxyl compound can be a dihydric alcohol such as, for example, glycols. Furthermore, as used in this application, the term "diacid" or "dicarboxylic acid" includes multifunctional acids, such as branching agents. The term "glycol" as used in this application includes, but is not limited to, diols, glycols, and/or multifunctional hydroxyl compounds. Alternatively, the difunctional carboxylic acid may be a hydroxy

carboxylic acid such as, for example, p-hydroxybenzoic acid, and the difunctional hydroxyl compound may be an aromatic nucleus bearing 2 hydroxyl substituents such as, for example, hydroquinone. The term "residue", as used herein, means any organic structure incorporated into a polymer through a polycondensation and/or an esterification reaction from the corresponding monomer. The term "repeating unit", as used herein, means an organic structure having a dicarboxylic acid residue and a diol residue bonded through a carbonyloxy group. Thus, for example, the dicarboxylic acid residues may be derived from a dicarboxylic acid monomer or its associated acid halides, esters, salts, anhydrides, or mixtures thereof. As used herein, therefore, the term dicarboxylic acid is intended to include dicarboxylic acids and any derivative of a dicarboxylic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof, useful in a reaction process with a diol to make polyester. As used herein, the term "terephthalic acid" is intended to include terephthalic acid itself and residues thereof as well as any derivative of terephthalic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof or residues thereof useful in a reaction process with a diol to make polyester.

In one embodiment, terephthalic acid may be used as the starting material. In another embodiment, dimethyl terephthalate may be used as the starting material. In another embodiment, mixtures of terephthalic acid and dimethyl terephthalate may be used as the starting material and/or as an intermediate material.

The polyesters used in the present invention typically can be prepared from dicarboxylic acids and diols which react in substantially equal proportions and are incorporated into the polyester polymer as their corresponding residues. The polyesters of the present invention, therefore, can contain substantially equal molar proportions of acid residues (100 mole %) and diol (and/or multifunctional hydroxyl compounds) residues (100 mole %) such that the total moles of repeating units is equal to 100 mole %. The mole percentages provided in the present disclosure, therefore, may be based on the total moles of acid residues, the total moles of diol residues, or the total moles of repeating units. For example, a polyester containing 30 mole % isophthalic acid, based on the total acid residues, means the polyester contains 30 mole % isophthalic acid residues out of a total of 100 mole % acid residues. Thus, there are 30 moles of isophthalic acid residues among every 100 moles of acid residues. In another example, a polyester containing 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, based on the total diol residues, means the polyester contains 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues out of a total of 100 mole % diol residues. Thus, there are 30 moles of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues among every 100 moles of diol residues.

In other aspects of the invention, the Tg of the polyesters useful in the dialysis filter housing(s) of the invention can be at least one of the following ranges: 100 to 200° C.; 100 to 190° C.; 100 to 180° C.; 100 to 170° C.; 100 to 160° C.; 100 to 155° C.; 100 to 150° C.; 100 to 145° C.; 100 to 140° C.; 100 to 138° C.; 100 to 135° C.; 100 to 130° C.; 100 to 125° C.; 100 to 120° C.; 100 to 115° C.; 100 to 110° C.; 105 to 200° C.; 105 to 190° C.; 105 to 180° C.; 105 to 170° C.; 105 to 160° C.; 105 to 155° C.; 105 to 150° C.; 105 to 145° C.; 105 to 140° C.; 105 to 138° C.; 105 to 135° C.; 105 to 130° C.; 105 to 125° C.; 105 to 120° C.; 105 to 115° C.; 105 to 110° C.; greater than 105 to 125° C.; greater than 105 to 120° C.; greater than 105 to 115° C.; greater than 105 to 110° C.; 110 to 200° C.; 110 to 190° C.; 110 to 180° C.; 110 to 170° C.; 110 to 160° C.; 110 to 155° C.;

110 to 150° C.; 110 to 145° C.; 110 to 140° C.; 110 to 138° C.; 110 to 135° C.; 110 to 130° C.; 110 to 125° C.; 110 to 120° C.; 110 to 115° C.; 115 to 200° C.; 115 to 190° C.; 115 to 180° C.; 115 to 170° C.; 115 to 160° C.; 115 to 155° C.; 115 to 150° C.; 115 to 145° C.; 115 to 140° C.; 115 to 138° C.; 115 to 135° C.; 110 to 130° C.; 115 to 125° C.; 115 to 120° C.; 120 to 200° C.; 120 to 190° C.; 120 to 180° C.; 120 to 170° C.; 120 to 160° C.; 120 to 155° C.; 120 to 150° C.; 120 to 145° C.; 120 to 140° C.; 120 to 138° C.; 120 to 135° C.; 120 to 130° C.; 125 to 200° C.; 125 to 190° C.; 125 to 180° C.; 125 to 170° C.; 125 to 160° C.; 125 to 155° C.; 125 to 150° C.; 125 to 145° C.; 125 to 140° C.; 125 to 138° C.; 125 to 135° C.; 127 to 200° C.; 127 to 190° C.; 127 to 180° C.; 127 to 170° C.; 127 to 160° C.; 127 to 150° C.; 127 to 145° C.; 127 to 140° C.; 127 to 138° C.; 127 to 135° C.; 130 to 200° C.; 130 to 190° C.; 130 to 180° C.; 130 to 170° C.; 130 to 160° C.; 130 to 155° C.; 130 to 150° C.; 130 to 145° C.; 130 to 140° C.; 130 to 138° C.; 130 to 135° C.; 135 to 200° C.; 135 to 190° C.; 135 to 180° C.; 135 to 170° C.; 135 to 160° C.; 135 to 155° C.; 135 to 150° C.; 135 to 145° C.; 135 to 140° C.; 140 to 200° C.; 140 to 190° C.; 140 to 180° C.; 140 to 170° C.; 140 to 160° C.; 140 to 155° C.; 140 to 150° C.; 140 to 145° C.; 148 to 200° C.; 148 to 190° C.; 148 to 180° C.; 148 to 170° C.; 148 to 160° C.; 148 to 155° C.; 148 to 150° C.; 150 to 200° C.; 150 to 190° C.; 150 to 180° C.; 150 to 170° C.; 150 to 160; 155 to 190° C.; 155 to 180° C.; 155 to 170° C.; and 155 to 165° C.

In other aspects of the invention, the glycol component for the polyesters useful in the dialysis filter housing(s) of the invention include but are not limited to at least one of the following combinations of ranges: 10 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 90 mole % 1,4-cyclohexanedimethanol; 10 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 90 mole % 1,4-cyclohexanedimethanol; 10 to less than 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 65 up to 90 mole % 1,4-cyclohexanedimethanol; 10 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 75 to 90 mole % 1,4-cyclohexanedimethanol; 11 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 89 mole % 1,4-cyclohexanedimethanol; 12 to 25 mole % 2,2,4,4-tetramethyl-1,3-

tetramethyl-1,3-cyclobutanediol and 20 to 40 mole % 1,4-cyclohexanedimethanol, 60 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 40 mole % 1,4-cyclohexanedimethanol; and 60 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 40 mole % 1,4-cyclohexanedimethanol.

In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 65 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 35 mole % 1,4-cyclohexanedimethanol, 65 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 35 mole % 1,4-cyclohexanedimethanol; and 65 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 40 mole % 1,4-cyclohexanedimethanol.

In other aspects of the invention, the glycol component for the polyesters useful in the dialysis filter housing(s) of the invention include but are not limited to at least one of the following combinations of ranges: 70 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 30 mole % 1,4-cyclohexanedimethanol, and 70 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 30 mole % 1,4-cyclohexanedimethanol.

In other aspects of the invention, the glycol component for the polyesters useful in the dialysis filter housing(s) of the invention include but are not limited to at least one of the following combinations of ranges: 75 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 25 mole % 1,4-cyclohexanedimethanol, and 75 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 25 mole % 1,4-cyclohexanedimethanol.

In other aspects of the invention, the glycol component for the polyesters useful in the dialysis filter housing(s) of the invention include but are not limited to at least one of the following combinations of ranges: 80 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 20 mole % 1,4-cyclohexanedimethanol, and 80 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 20 mole % 1,4-cyclohexanedimethanol.

In other aspects of the invention, the glycol component for the polyesters useful in the dialysis filter housing(s) of the

invention include but are not limited to at least one of the following combinations of ranges: greater than 45 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to less than 55 mole % 1,4-cyclohexanedimethanol; greater than 45 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to less than 55 mole % 1,4-cyclohexanedimethanol; 46 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 54 mole % 1,4-cyclohexanedimethanol; and 46 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 54 mole % 1,4-cyclohexanedimethanol.

In addition to the diols set forth above, the polyesters useful in the polyester compositions of the dialysis filter housing(s) of the invention may also be made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof. It is contemplated that compositions of the invention made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof can possess at least one of the Tg ranges described herein, at least one of the inherent viscosity ranges described herein, and/or at least one of the glycol or diacid ranges described herein. In addition or in the alternative, the polyesters made from 1,3-propanediol or 1,4-butanediol or mixtures thereof may also be made from 1,4-cyclohexanedimethanol in at least one of the following amounts: from 0.1 to 99 mole %; from 0.1 to 90 mole %; from 0.1 to 80 mole %; from 0.1 to 70 mole %; from 0.1 to 60 mole %; from 0.1 to 50 mole %; from 0.1 to 40 mole %; from 0.1 to 35 mole %; from 0.1 to 30 mole %; from 0.1 to 25 mole %; from 0.1 to 20 mole %; from 0.1 to 15 mole %; from 0.1 to 10 mole %; from 0.1 to 5 mole %; from 1 to 99 mole %; from 1 to 90 mole %, from 1 to 80 mole %; from 1 to 70 mole %; from 1 to 60 mole %; from 1 to 50 mole %; from 1 to 40 mole %; from 1 to 35 mole %; from 1 to 30 mole %; from 1 to 25 mole %; from 1 to 20 mole %; from 1 to 15 mole %; from 1 to 10 mole %; from 1 to 5 mole %; from 5 to 99 mole %, from 5 to 90 mole %, from 5 to 80 mole %; 5 to 70 mole %; from 5 to 60 mole %; from 5 to 50 mole %; from 5 to 40 mole %; from 5 to 35 mole %; from 5 to 30 mole %; from 5 to 25 mole %; from 5 to 20 mole %; and from 5 to 15 mole %; from 5 to 10 mole %; from 10 to 99 mole %; from 10 to 90 mole %; from 10 to 80 mole %; from 10 to 70 mole %; from 10 to 60 mole %; from 10 to 50 mole %; from 10 to 40 mole %; from 10 to 35 mole %; from 10 to 30 mole %; from 10 to 25 mole %; from 10 to 20 mole %; from 10 to 15 mole %; from 20 to 99 mole %; from 20 to 90 mole %; from 20 to 80 mole %; from 20 to 70 mole %; from 20 to 60 mole %; from 20 to 50 mole %; from 20 to 40 mole %; from 20 to 35 mole %; from 20 to 30 mole %; and from 20 to 25 mole %.

For certain embodiments of the invention, the polyesters useful in the invention may exhibit at least one of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.: 0.10 to 1.2 dL/g; 0.10 to 1.1 dL/g; 0.10 to 1 dL/g; 0.10 to less than 1 dL/g; 0.10 to 0.98 dL/g; 0.10 to 0.95 dL/g; 0.10 to 0.90 dL/g; 0.10 to 0.85 dL/g; 0.10 to 0.80 dL/g; 0.10 to 0.75 dL/g; 0.10 to less than 0.75 dL/g; 0.10 to 0.72 dL/g; 0.10 to 0.70 dL/g; 0.10 to less than 0.70 dL/g; 0.10 to 0.68 dL/g; 0.10 to 0.65 dL/g; 0.20 to 1.2 dL/g; 0.20 to 1.1 dL/g; 0.20 to 1 dL/g; 0.20 to less than 1 dL/g; 0.20 to 0.98 dL/g; 0.20 to 0.95 dL/g; 0.20 to 0.90 dL/g; 0.20 to 0.85 dL/g; 0.20 to 0.80 dL/g; 0.20 to 0.75 dL/g; 0.20 to less than 0.75 dL/g; 0.20 to 0.72 dL/g; 0.20 to 0.70 dL/g; 0.20 to less than 0.70 dL/g; 0.20 to 0.68 dL/g; 0.20 to less than 0.68 dL/g; 0.20 to 0.65 dL/g; 0.35 to 1.2 dL/g; 0.35 to 1.1 dL/g; 0.35 to 1 dL/g; 0.35 to less than 1 dL/g; 0.35 to 0.98 dL/g; 0.35 to 0.95 dL/g; 0.35 to 0.90 dL/g; 0.35 to 0.85 dL/g; 0.35 to 0.80 dL/g; 0.35 to 0.75 dL/g; 0.35 to less than 0.75 dL/g; 0.35 to 0.72 dL/g; 0.35 to 0.70 dL/g; 0.35 to less than 0.70 dL/g; 0.35 to 0.68 dL/g; 0.35 to 0.65 dL/g;

0.40 to 1.2 dL/g; 0.40 to 1.1 dL/g; 0.40 to 1 dL/g; 0.40 to less than 1 dL/g; 0.40 to 0.98 dL/g; 0.40 to 0.95 dL/g; 0.40 to 0.90 dL/g; 0.40 to 0.85 dL/g; 0.40 to 0.80 dL/g; 0.40 to 0.75 dL/g; 0.40 to less than 0.75 dL/g; 0.40 to 0.72 dL/g; 0.40 to 0.70 dL/g; 0.40 to less than 0.70 dL/g; 0.40 to 0.68 dL/g; 0.40 to less than 0.68 dL/g; 0.40 to 0.65 dL/g; greater than 0.42 to 1.2 dL/g; greater than 0.42 to 1.1 dL/g; greater than 0.42 to 1 dL/g; greater than 0.42 to less than 1 dL/g; greater than 0.42 to 0.98 dL/g; greater than 0.42 to 0.95 dL/g; greater than 0.42 to 0.90 dL/g; greater than 0.42 to 0.85 dL/g; greater than 0.42 to 0.80 dL/g; greater than 0.42 to 0.75 dL/g; greater than 0.42 to less than 0.75 dL/g; greater than 0.42 to 0.72 dL/g; greater than 0.42 to less than 0.70 dL/g; greater than 0.42 to 0.68 dL/g; greater than 0.42 to less than 0.68 dL/g; and greater than 0.42 to 0.65 dL/g.

For certain embodiments of the invention, the polyesters useful in the invention may exhibit at least one of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.: 0.45 to 1.2 dL/g; 0.45 to 1.1 dL/g; 0.45 to 1 dL/g; 0.45 to 0.98 dL/g; 0.45 to 0.95 dL/g; 0.45 to 0.90 dL/g; 0.45 to 0.85 dL/g; 0.45 to 0.80 dL/g; 0.45 to 0.75 dL/g; 0.45 to less than 0.75 dL/g; 0.45 to 0.72 dL/g; 0.45 to 0.70 dL/g; 0.45 to less than 0.70 dL/g; 0.45 to 0.68 dL/g; 0.45 to less than 0.68 dL/g; 0.45 to 0.65 dL/g; 0.50 to 1.2 dL/g; 0.50 to 1.1 dL/g; 0.50 to 1 dL/g; 0.50 to less than 1 dL/g; 0.50 to 0.98 dL/g; 0.50 to 0.95 dL/g; 0.50 to 0.90 dL/g; 0.50 to 0.85 dL/g; 0.50 to 0.80 dL/g; 0.50 to 0.75 dL/g; 0.50 to less than 0.75 dL/g; 0.50 to 0.72 dL/g; 0.50 to 0.70 dL/g; 0.50 to less than 0.70 dL/g; 0.50 to 0.68 dL/g; 0.50 to less than 0.68 dL/g; 0.50 to 0.65 dL/g; 0.55 to 1.2 dL/g; 0.55 to 1.1 dL/g; 0.55 to 1 dL/g; 0.55 to less than 1 dL/g; 0.55 to 0.98 dL/g; 0.55 to 0.95 dL/g; 0.55 to 0.90 dL/g; 0.55 to 0.85 dL/g; 0.55 to 0.80 dL/g; 0.55 to 0.75 dL/g; 0.55 to less than 0.75 dL/g; 0.55 to 0.72 dL/g; 0.55 to 0.70 dL/g; 0.55 to less than 0.70 dL/g; 0.55 to 0.68 dL/g; 0.55 to less than 0.68 dL/g; 0.55 to 0.65 dL/g; 0.58 to 1.2 dL/g; 0.58 to 1.1 dL/g; 0.58 to 1 dL/g; 0.58 to less than 1 dL/g; 0.58 to 0.98 dL/g; 0.58 to 0.95 dL/g; 0.58 to 0.90 dL/g; 0.58 to 0.85 dL/g; 0.58 to 0.80 dL/g; 0.58 to 0.75 dL/g; 0.58 to less than 0.75 dL/g; 0.58 to 0.72 dL/g; 0.58 to 0.70 dL/g; 0.58 to less than 0.70 dL/g; 0.58 to 0.68 dL/g; 0.58 to less than 0.68 dL/g; 0.58 to 0.65 dL/g; 0.60 to 1.2 dL/g; 0.60 to 1.1 dL/g; 0.60 to 1 dL/g; 0.60 to less than 1 dL/g; 0.60 to 0.98 dL/g; 0.60 to 0.95 dL/g; 0.60 to 0.90 dL/g; 0.60 to 0.85 dL/g; 0.60 to 0.80 dL/g; 0.60 to 0.75 dL/g; 0.60 to less than 0.75 dL/g; 0.60 to 0.72 dL/g; 0.60 to 0.70 dL/g; 0.60 to less than 0.70 dL/g; 0.60 to 0.68 dL/g; 0.60 to less than 0.68 dL/g; 0.60 to 0.65 dL/g; 0.65 to 1.2 dL/g; 0.65 to 1.1 dL/g; 0.65 to 1 dL/g; 0.65 to less than 1 dL/g; 0.65 to 0.98 dL/g; 0.65 to 0.95 dL/g; 0.65 to 0.90 dL/g; 0.65 to 0.85 dL/g; 0.65 to 0.80 dL/g; 0.65 to 0.75 dL/g; 0.65 to less than 0.75 dL/g; 0.65 to 0.72 dL/g; 0.65 to 0.70 dL/g; 0.65 to less than 0.70 dL/g; 0.68 to 1.2 dL/g; 0.68 to 1.1 dL/g; 0.68 to 1 dL/g; 0.68 to less than 1 dL/g; 0.68 to 0.98 dL/g; 0.68 to 0.95 dL/g; 0.68 to 0.90 dL/g; 0.68 to 0.85 dL/g; 0.68 to 0.80 dL/g; 0.68 to 0.75 dL/g; 0.68 to less than 0.75 dL/g; 0.68 to 0.72 dL/g; greater than 0.76 dL/g to 1.2 dL/g; greater than 0.76 dL/g to 1.1 dL/g; greater than 0.76 dL/g to 1 dL/g; greater than 0.76 dL/g to less than 1 dL/g; greater than 0.76 dL/g to 0.98 dL/g; greater than 0.76 dL/g to 0.95 dL/g; greater than 0.76 dL/g to 0.90 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 1.1 dL/g; greater than 0.80 dL/g to 1 dL/g; greater than 0.80 dL/g to less than 1 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 0.98 dL/g; greater than 0.80 dL/g to 0.95 dL/g; greater than 0.80 dL/g to 0.90 dL/g.

It is contemplated that compositions useful in the dialysis filter housing(s) of the invention can possess at least one of the

inherent viscosity ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions useful in the dialysis filter housing(s) of the invention can possess at least one of the Tg ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions useful in the dialysis filter housing(s) of the invention can possess at least one of the Tg ranges described herein, at least one of the inherent viscosity ranges described herein, and at least one of the monomer ranges for the compositions described herein unless otherwise stated.

For the desired polyester, the molar ratio of cis/trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol can vary from the pure form of each or mixtures thereof. In certain embodiments, the molar percentages for cis and/or trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol are greater than 50 mole % cis and less than 50 mole % trans; or greater than 55 mole % cis and less than 45 mole % trans; or 30 to 70 mole % cis and 70 to 30% trans; or 40 to 60 mole % cis and 60 to 40 mole % trans; or 50 to 70 mole % trans and 50 to 30% cis or 50 to 70 mole % cis and 50 to 30% trans; or 60 to 70 mole % cis and 30 to 40 mole % trans; or greater than 70 mole cis and less than 30 mole % trans; wherein the total sum of the mole percentages for cis-and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to 100 mole %. The molar ratio of cis/trans 1,4-cyclohexandimethanol can vary within the range of 50/50 to 0/100, such as between 40/60 to 20/80.

In certain embodiments, terephthalic acid or an ester thereof, such as, for example, dimethyl terephthalate, or a mixture of terephthalic acid and an ester thereof, makes up most or all of the dicarboxylic acid component used to form the polyesters useful in the invention. In certain embodiments, terephthalic acid residues can make up a portion or all of the dicarboxylic acid component used to form the present polyester at a concentration of at least 70 mole %, such as at least 80 mole %, at least 90 mole %, at least 95 mole %, at least 99 mole %, or 100 mole %. In certain embodiments, higher amounts of terephthalic acid can be used in order to produce a higher impact strength polyester. In one embodiment, dimethyl terephthalate is part or all of the dicarboxylic acid component used to make the polyesters useful in the present invention. For the purposes of this disclosure, the terms "terephthalic acid" and "dimethyl terephthalate" are used interchangeably herein. In all embodiments, ranges of from 70 to 100 mole %; or 80 to 100 mole %; or 90 to 100 mole %; or 99 to 100 mole %; or 100 mole % terephthalic acid and/or dimethyl terephthalate and/or mixtures thereof may be used.

In addition to terephthalic acid, the dicarboxylic acid component of the polyester useful in the invention can comprise up to 30 mole %, up to 20 mole %, up to 10 mole %, up to 5 mole %, or up to 1 mole % of one or more modifying aromatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aromatic dicarboxylic acids. Thus, if present, it is contemplated that the amount of one or more modifying aromatic dicarboxylic acids can range from any of these preceding endpoint values including, for example, from 0.01 to 30 mole %, 0.01 to 20 mole %, from 0.01 to 10 mole %, from 0.01 to 5 mole % and from 0.01 to 1 mole. In one embodiment, modifying aromatic dicarboxylic acids that may be used in the present invention include but are not limited to those having up to 20 carbon atoms, and which can be linear, para-oriented, or symmetrical. Examples of modifying aromatic dicarboxylic acids which may be used in this invention include, but are not limited to, isophthalic acid, 4,4'-biphenyldicarboxylic acid, 1,4-, 1,5-, 2,6-, 2,7-naphtha-

lenedicarboxylic acid, and trans-4,4'-stilbenedicarboxylic acid, and esters thereof. In one embodiment, the modifying aromatic dicarboxylic acid is isophthalic acid.

The carboxylic acid component of the polyesters useful in the invention can be further modified with up to 10 mole %, such as up to 5 mole % or up to 1 mole % of one or more aliphatic dicarboxylic acids containing 2-16 carbon atoms, such as, for example, malonic, succinic, glutaric, adipic, pimelic, suberic, azelaic and dodecanedioic dicarboxylic acids. Certain embodiments can also comprise 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying aliphatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aliphatic dicarboxylic acids. Thus, if present, it is contemplated that the amount of one or more modifying aliphatic dicarboxylic acids can range from any of these preceding endpoint values including, for example, from 0.01 to 10 mole % and from 0.1 to 10 mole %. The total mole % of the dicarboxylic acid component is 100 mole %.

Esters of terephthalic acid and the other modifying dicarboxylic acids or their corresponding esters and/or salts may be used instead of the dicarboxylic acids. Suitable examples of dicarboxylic acid esters include, but are not limited to, the dimethyl, diethyl, dipropyl, diisopropyl, dibutyl, and diphenyl esters. In one embodiment, the esters are chosen from at least one of the following: methyl, ethyl, propyl, isopropyl, and phenyl esters.

The 1,4-cyclohexanedimethanol may be cis, trans, or a mixture thereof, for example a cis/trans ratio of 60:40 to 40:60. In another embodiment, the trans-1,4-cyclohexanedimethanol can be present in an amount of 60 to 80 mole %.

The glycol component of the polyester portion of the polyester composition useful in the invention can contain 25 mole % or less of one or more modifying glycols which are not 2,2,4,4-tetramethyl-1,3-cyclobutanediol or 1,4-cyclohexanedimethanol; in one embodiment, the polyesters useful in the invention may contain less than 15 mole % of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 10 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 5 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 3 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 0 mole % modifying glycols. Certain embodiments can also contain 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying glycols. Thus, if present, it is contemplated that the amount of one or more modifying glycols can range from any of these preceding endpoint values including, for example, from 0.01 to 15 mole % and from 0.1 to 10 mole %.

Modifying glycols useful in the polyesters useful in the invention refer to diols other than 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1,4-cyclohexanedimethanol and may contain 2 to 16 carbon atoms. Examples of suitable modifying glycols include, but are not limited to, ethylene glycol, 1,2-propanediol, 1,3-propanediol, neopentyl glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, p-xylene glycol or mixtures thereof. In one embodiment, the modifying glycol is ethylene glycol. In another embodiment, the modifying glycols are 1,3-propanediol and/or 1,4-butanediol. In another embodiment, ethylene glycol is excluded as a modifying diol. In another embodiment, 1,3-propanediol and 1,4-butanediol

are excluded as modifying diols. In another embodiment, 2,2-dimethyl-1,3-propanediol is excluded as a modifying diol.

The polyesters and/or the polycarbonates useful in the polyesters compositions of the invention can comprise from 0 to 10 mole percent, for example, from 0.01 to 5 mole percent, from 0.01 to 1 mole percent, from 0.05 to 5 mole percent, from 0.05 to 1 mole percent, or from 0.1 to 0.7 mole percent, based the total mole percentages of either the diol or diacid residues; respectively, of one or more residues of a branching monomer, also referred to herein as a branching agent, having 3 or more carboxyl substituents, hydroxyl substituents, or a combination thereof. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polyester. The polyester(s) useful in the invention can thus be linear or branched. The polycarbonate can also be linear or branched. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polycarbonate.

Examples of branching monomers include, but are not limited to, multifunctional acids or multifunctional alcohols such as trimellitic acid, trimellitic anhydride, pyromellitic dianhydride, trimethylolpropane, glycerol, pentaerythritol, citric acid, tartaric acid, 3-hydroxyglutaric acid and the like. In one embodiment, the branching monomer residues can comprise 0.1 to 0.7 mole percent of one or more residues chosen from at least one of the following: trimellitic anhydride, pyromellitic dianhydride, glycerol, sorbitol, 1,2,6-hexanetriol, pentaerythritol, trimethylolethane, and/or trimesic acid. The branching monomer may be added to the polyester reaction mixture or blended with the polyester in the form of a concentrate as described, for example, in U.S. Pat. Nos. 5,654,347 and 5,696,176, whose disclosure regarding branching monomers is incorporated herein by reference.

The glass transition temperature (T_g) of the polyesters useful in the invention was determined using a TA DSC 2920 from Thermal Analyst Instrument at a scan rate of 20° C./min.

Because of the long crystallization half-times (e.g., greater than 5 minutes) at 170° C. exhibited by certain polyesters useful in the present invention, it is possible to produce injection molded dialysis filter housing(s). The polyesters of the invention can be amorphous or semicrystalline. In one aspect, certain polyesters useful in the invention can have relatively low crystallinity. Certain polyesters useful in the invention can thus have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

In one embodiment, an "amorphous" polyester can have a crystallization half-time of greater than 5 minutes at 170° C. or greater than 10 minutes at 170° C. or greater than 50 minutes at 170° C. or greater than 100 minutes at 170° C. In one embodiment, of the invention, the crystallization half-times are greater than 1,000 minutes at 170° C. In another embodiment of the invention, the crystallization half-times of the polyesters useful in the invention are greater than 10,000 minutes at 170° C. The crystallization half time of the polyester, as used herein, may be measured using methods well-known to persons of skill in the art. For example, the crystallization half time of the polyester, $t_{1/2}$, can be determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement can be done by exposing the polymers to a temperature, T_{max} , and then cooling it to the desired temperature. The sample can then be held at the desired temperature by a hot stage while transmission measurements are made as a function of time. Initially, the sample

can be visually clear with high light transmission and becomes opaque as the sample crystallizes. The crystallization half-time is the time at which the light transmission is halfway between the initial transmission and the final transmission. T_{max} is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The sample can be heated to T_{max} to condition the sample prior to crystallization half time measurement. The absolute T_{max} temperature is different for each composition. For example PCT can be heated to some temperature greater than 290° C. to melt the crystalline domains.

As shown in Table 1 and FIG. 1 of the Examples, 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers such ethylene glycol and isophthalic acid at increasing the crystallization half-time, i.e., the time required for a polymer to reach half of its maximum crystallinity. By decreasing the crystallization rate of PCT, i.e. increasing the crystallization half-time, amorphous articles based on modified PCT may be fabricated by methods known in the art such as extrusion, injection molding, and the like. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

The polyesters can exhibit an improvement in toughness combined with processability for some of the embodiments of the invention. For example, it is unexpected that lowering the inherent viscosity slightly of the polyesters useful in the invention results in a more processable melt viscosity while retaining good physical properties of the polyesters such as toughness and heat resistance.

Increasing the content of 1,4-cyclohexanedimethanol in a copolyester based on terephthalic acid, ethylene glycol, and 1,4-cyclohexanedimethanol can improve toughness, which can be determined by the brittle-to-ductile transition temperature in a notched Izod impact strength test as measured by ASTM D256. This toughness improvement, by lowering of the brittle-to-ductile transition temperature with 1,4-cyclohexanedimethanol, is believed to occur due to the flexibility and conformational behavior of 1,4-cyclohexanedimethanol in the copolyester. Incorporating 2,2,4,4-tetramethyl-1,3-cyclobutanediol into PCT is believed to improve toughness, by lowering the brittle-to-ductile transition temperature, as shown in Table 2 and FIG. 2 of the Examples. This is unexpected given the rigidity of 2,2,4,4-tetramethyl-1,3-cyclobutanediol.

In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 30,000 poise as measured a 1 radian/second on a rotary melt rheometer at 290° C. In another embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 20,000 poise as measured a 1 radian/second on a rotary melt rheometer at 290° C.

In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 15,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290° C. In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 10,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290° C. In another embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 6,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290° C. Viscosity at rad/sec is related to processability. Typical polymers have viscosities of less than 10,000 poise as measured at 1 radian/second when measured at their processing temperature. Polyesters are typically not processed above 290° C. Polycarbonate is typically processed at 290° C. The viscosity at 1 rad/sec of a typical 12 melt flow rate polycarbonate is 7000 poise at 290° C.

In one embodiment, certain polyesters useful in this invention are visually clear. The term "visually clear" is defined herein as an appreciable absence of cloudiness, haziness, and/or muddiness, when inspected visually. When the polyesters are blended with polycarbonate, including bisphenol A polycarbonates, the blends can be visually clear in one aspect of the invention.

The present polyesters possess one or more of the following properties. In other embodiments, the polyesters useful in the invention may have a yellowness index (ASTM D-1925) of less than 50, such as less than 20.

In one embodiment, polyesters of this invention exhibit superior notched toughness in thick sections. Notched Izod impact strength, as described in ASTM D256, is a common method of measuring toughness. When tested by the Izod method, polymers can exhibit either a complete break failure mode, where the test specimen breaks into two distinct parts, or a partial or no break failure mode, where the test specimen remains as one part. The complete break failure mode is associated with low energy failure. The partial and no break failure modes are associated with high energy failure. A typical thickness used to measure Izod toughness is 1/8". At this thickness, very few polymers are believed to exhibit a partial or no break failure mode, polycarbonate being one notable example. When the thickness of the test specimen is increased to 1/4", however, no commercial amorphous materials exhibit a partial or no break failure mode. In one embodiment, compositions of the present example exhibit a no break failure mode when tested in Izod using a 1/4" thick specimen.

The polyesters useful in the invention can possess one or more of the following properties. In one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 150 J/m (3 ft-lb/in) at 23° C. with a 10-mil notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least (400 J/m) 7.5 ft-lb/in at 23° C. with a 10-mil notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23° C. with a 10-mil notch in a 3.2 mm (1/8-inch) thick bar determined according to ASTM D256. In one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 150 J/m (3 ft-lb/in) at 23° C. with a 10-mil notch in a 6.4 mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least (400 J/m) 7.5 ft-lb/in at 23° C. with a 10-mil notch in a 6.4 mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the film or sheet of the invention exhibit a notched Izod impact strength of at least (534 J/m) 10 ft-lb/in at 23° C. with a 10-mil notch in a 6.4 mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23° C. with a 10-mil notch in a 6.4 mm (1/4-inch) thick bar determined according to ASTM D256.

In another embodiment, certain polyesters useful in the invention can exhibit an increase in notched Izod impact strength when measured at 0° C. of at least 3% or at least 5% or at least 10% or at least 15% as compared to the notched Izod impact strength when measured at -5° C. with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256. In addition, certain other polyesters can also exhibit a retention of notched Izod impact strength within plus or

minus 5% when measured at 0° C. through 30° C. with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256.

In yet another embodiment, certain polyesters useful in the invention can exhibit a retention in notched Izod impact strength with a loss of no more than 70% when measured at 23° C. with a 10-mil notch in a 1/4-inch thick bar determined according to ASTM D256 as compared to notched Izod impact strength for the same polyester when measured at the same temperature with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256.

In one embodiment, the polyesters useful in the invention and/or the polyester compositions of the invention, with or without toners, can have color values L*, a* and b*, which can be determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations are averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They are determined by the L*a*b* color system of the CIE (International Commission on Illumination) (translated), wherein L* represents the lightness coordinate, a* represents the red/green coordinate, and b* represents the yellow/blue coordinate. In certain embodiments, the b* values for the polyesters useful in the invention can be from -10 to less than 10 and the L* values can be from 50 to 90. In other embodiments, the b* values for the polyesters useful in the invention can be present in one of the following ranges: -10 to 9; -10 to 8; -10 to 7; -10 to 6; -10 to 5; -10 to 4; -10 to 3; -10 to 2; from -5 to 9; -5 to 8; -5 to 7; -5 to 6; -5 to 5; -5 to 4; -5 to 3; -5 to 2; 0 to 9; 0 to 8; 0 to 7; 0 to 6; 0 to 5; 0 to 4; 0 to 3; 0 to 2; 1 to 10; 1 to 9; 1 to 8; 1 to 7; 1 to 6; 1 to 5; 1 to 4; 1 to 3; and 1 to 2. In other embodiments, the L* value for the polyesters useful in the invention can be present in one of the following ranges: 50 to 60; 50 to 70; 50 to 80; 50 to 90; 60 to 70; 60 to 80; 60 to 90; 70 to 80; 79 to 90.

In one embodiment, the polyesters useful in the invention exhibit a ductile-to-brittle transition temperature of less than 0° C. based on a 10-mil notch in a 1/8-inch thick bar as defined by ASTM D256.

In one embodiment, the polyesters useful in the invention can exhibit at least one of the following densities: a density of less than 1.3 g/ml at 23° C.; a density of less than 1.2 g/ml at 23° C.; a density of less than 1.18 g/ml at 23° C.; a density of 0.80 to 1.3 g/ml at 23° C.; a density of 0.80 to 1.2 g/ml at 23° C.; a density of 0.80 to less than 1.2 g/ml at 23° C.; a density of 1.0 to 1.3 g/ml at 23° C.; a density of 1.0 to 1.2 g/ml at 23° C.; a density of 1.0 to 1.1 g/ml at 23° C.; a density of 1.13 to 1.3 g/ml at 23° C.; and a density of 1.13 to 1.2 g/ml at 23° C.

In some embodiments, use of the polyester compositions useful in the invention minimizes and/or eliminates the drying step prior to melt processing and/or thermoforming.

The polyester portion of the polyester compositions useful in the invention can be made by processes known from the literature such as, for example, by processes in homogenous solution, by transesterification processes in the melt, and by two phase interfacial processes. Suitable methods include, but are not limited to, the steps of reacting one or more dicarboxylic acids with one or more glycols at a temperature of 100° C. to 315° C. at a pressure of 0.1 to 760 mm Hg for a time sufficient to form a polyester. See U.S. Pat. No. 3,772,405 for methods of producing polyesters, the disclosure regarding such methods is hereby incorporated herein by reference.

In another aspect, the invention relates to dialysis filter housing(s) comprising a polyester produced by a process comprising:

- (I) heating a mixture comprising the monomers useful in any of the polyesters in the invention in the presence of a catalyst at a temperature of 150 to 240° C. for a time sufficient to produce an initial polyester;
- (II) heating the initial polyester of step (I) at a temperature of 240 to 320° C. for 1 to 4 hours; and
- (III) removing any unreacted glycols.

Suitable catalysts for use in this process include, but are not limited to, organo-zinc or tin compounds. The use of this type of catalyst is well known in the art. Examples of catalysts useful in the present invention include, but are not limited to, zinc acetate, butyltin tris-2-ethylhexanoate, dibutyltin diacetate, and dibutyltin oxide. Other catalysts may include, but are not limited to, those based on titanium, zinc, manganese, lithium, germanium, and cobalt. Catalyst amounts can range from 10 ppm to 20,000 ppm or 10 to 10,000 ppm, or 10 to 5000 ppm or 10 to 1000 ppm or 10 to 500 ppm, or 10 to 300 ppm or 10 to 250 based on the catalyst metal and based on the weight of the final polymer. The process can be carried out in either a batch or continuous process.

Typically, step (I) can be carried out until 50% by weight or more of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol has been reacted. Step (I) may be carried out under pressure, ranging from atmospheric pressure to 100 psig. The term "reaction product" as used in connection with any of the catalysts useful in the invention refers to any product of a polycondensation or esterification reaction with the catalyst and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive.

Typically, Step (II) and Step (III) can be conducted at the same time. These steps can be carried out by methods known in the art such as by placing the reaction mixture under a pressure ranging from 0.002 psig to below atmospheric pressure, or by blowing hot nitrogen gas over the mixture.

The invention further relates to a polyester product made by the process described above.

The invention further relates to a polymer blend. The blend comprises:

- (a) 5 to 95 wt % of at least one of the polyesters described above; and
- (b) 5 to 95 wt % of at least one polymeric component.

Suitable examples of polymeric components include, but are not limited to, nylon, polyesters different from those described herein, polyamides such as ZYTEL® from DuPont; polystyrene, polystyrene copolymers, styrene acrylonitrile copolymers, acrylonitrile butadiene styrene copolymers, poly(methylmethacrylate), acrylic copolymers, poly(ether-imides) such as ULTEM® (a poly(ether-imide) from General Electric); polyphenylene oxides such as poly(2,6-dimethylphenylene oxide) or poly(phenylene oxide)/polystyrene blends such as NORYL 1000® (a blend of poly(2,6-dimethylphenylene oxide) and polystyrene resins from General Electric); polyphenylene sulfides; polyphenylene sulfide/sulfones; poly(ester-carbonates); polycarbonates such as LEXAN® (a polycarbonate from General Electric); polysulfones; polysulfone ethers; and poly(ether-ketones) of aromatic dihydroxy compounds; or mixtures of any of the other foregoing polymers. The blends can be prepared by conventional processing techniques known in the art, such as melt blending or solution blending. In one embodiment, the polycarbonate is not present in the polyester composition. If polycarbonate is used in a blend in the polyester compositions useful in the invention, the blends can be visually clear. How-

ever, the polyester compositions useful in the invention also contemplate the exclusion of polycarbonate as well as the inclusion of polycarbonate.

Polycarbonates useful in the invention may be prepared according to known procedures, for example, by reacting the dihydroxyaromatic compound with a carbonate precursor such as phosgene, a haloformate or a carbonate ester, a molecular weight regulator, an acid acceptor and a catalyst. Methods for preparing polycarbonates are known in the art and are described, for example, in U.S. Pat. No. 4,452,933, where the disclosure regarding the preparation of polycarbonates is hereby incorporated by reference herein.

Examples of suitable carbonate precursors include, but are not limited to, carbonyl bromide, carbonyl chloride, or mixtures thereof; diphenyl carbonate; a di(halophenyl)carbonate, e.g., di(trichlorophenyl)carbonate, di(tribromophenyl)carbonate, and the like; di(alkylphenyl)carbonate; e.g. di(tolyl)carbonate; di(naphthyl)carbonate; di(chloronaphthyl)carbonate, or mixtures thereof; and bis-haloformates of dihydric phenols.

Examples of suitable molecular weight regulators include, but are not limited to, phenol, cyclohexanol, methanol, alkylated phenols, such as octylphenol, para-tertiary-butyl-phenol, and the like. In one embodiment, the molecular weight regulator is phenol or an alkylated phenol.

The acid acceptor may be either an organic or an inorganic acid acceptor. A suitable organic acid acceptor can be a tertiary amine and includes, but is not limited to, such materials as pyridine, triethylamine, dimethylaniline, tributylamine, and the like. The inorganic acid acceptor can be either a hydroxide, a carbonate, a bicarbonate, or a phosphate of an alkali or alkaline earth metal.

The catalysts that can be used include, but are not limited to, those that typically aid the polymerization of the monomer with phosgene. Suitable catalysts include, but are not limited to, tertiary amines such as triethylamine, tripropylamine, N,N-dimethylaniline, quaternary ammonium compounds such as, for example, tetraethylammonium bromide, cetyl triethyl ammonium bromide, tetra-n-heptylammonium iodide, tetra-n-propyl ammonium bromide, tetramethyl ammonium chloride, tetra-methyl ammonium hydroxide, tetra-n-butyl ammonium iodide, benzyltrimethyl ammonium chloride and quaternary phosphonium compounds such as, for example, n-butyltriphenyl phosphonium bromide and methyltriphenyl phosphonium bromide.

The polycarbonates useful in the polyester compositions of the invention also may be copolyestercarbonates such as those described in U.S. Pat. Nos. 3,169,121; 3,207,814; 4,194,038; 4,156,069; 4,430,484, 4,465,820, and 4,981,898, the disclosure regarding copolyestercarbonates from each of the U.S. patents is incorporated by reference herein.

Copolyestercarbonates useful in this invention can be available commercially and/or can be prepared by known methods in the art. For example, they can be typically obtained by the reaction of at least one dihydroxyaromatic compound with a mixture of phosgene and at least one dicarboxylic acid chloride, especially isophthaloyl chloride, terephthaloyl chloride, or both.

In addition, the polyester compositions and the polymer blend compositions useful in the dialysis filter housing(s) of this invention may also contain from 0.01 to 25% by weight of the overall composition common additives such as colorants, dyes, mold release agents, flame retardants, plasticizers, nucleating agents, stabilizers, including but not limited to, UV stabilizers, thermal stabilizers and/or reaction products thereof, fillers, and impact modifiers. Examples of typical commercially available impact modifiers well known in the

art and useful in this invention include, but are not limited to, ethylene/propylene terpolymers; functionalized polyolefins, such as those containing methyl acrylate and/or glycidyl methacrylate; styrene-based block copolymeric impact modifiers, and various acrylic core/shell type impact modifiers. Residues of such additives are also contemplated as part of the polyester composition.

The polyesters of the invention can comprise at least one chain extender. Suitable chain extenders include, but are not limited to, multifunctional (including, but not limited to, bifunctional) isocyanates, multifunctional epoxides, including for example, epoxylated novolacs, and phenoxy resins. In certain embodiments, chain extenders may be added at the end of the polymerization process or after the polymerization process. If added after the polymerization process, chain extenders can be incorporated by compounding or by addition during conversion processes such as injection molding or extrusion. The amount of chain extender used can vary depending on the specific monomer composition used and the physical properties desired but is generally about 0.1 percent by weight to about 10 percent by weight, preferably about 0.1 to about 5 percent by weight, based on the total weight of the polyester.

Thermal stabilizers are compounds that stabilize polyesters during polyester manufacture and/or post polymerization, including, but not limited to, phosphorous compounds, including, but not limited to, phosphoric acid, phosphorous acid, phosphonic acid, phosphinic acid, phosphonous acid, and various esters and salts thereof. The esters can be alkyl, branched alkyl, substituted alkyl, difunctional alkyl, alkyl ethers, aryl, and substituted aryl. In one embodiment, the number of ester groups present in the particular phosphorous compound can vary from zero up to the maximum allowable based on the number of hydroxyl groups present on the thermal stabilizer used. The term "thermal stabilizer" is intended to include the reaction product(s) thereof. The term "reaction product" as used in connection with the thermal stabilizers of the invention refers to any product of a polycondensation or esterification reaction between the thermal stabilizer and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive. These can be present in the polyester compositions useful in the invention.

Reinforcing materials may be useful in the compositions of this invention. The reinforcing materials may include, but are not limited to, carbon filaments, silicates, mica, clay, talc, titanium dioxide, Wollastonite, glass flakes, glass beads and fibers, and polymeric fibers and combinations thereof. In one embodiment, the reinforcing materials are glass, such as, fibrous glass filaments, mixtures of glass and talc, glass and mica, and glass and polymeric fibers.

The invention further relates to dialysis filter housing(s) described herein. These dialysis filter housing(s) include, but are not limited to, injection molded dialysis housings. Methods of making dialysis filter housing(s) include, but are not limited to, injection molding.

For the purposes of this disclosure, the term "wt" means "weight".

The following examples further illustrate how the dialysis filter housing(s) of the invention can be made and evaluated, and are intended to be purely exemplary of the invention and are not intended to limit the scope thereof. Unless indicated otherwise, parts are parts by weight, temperature is in degrees C. or is at room temperature, and pressure is at or near atmospheric.

Measurement Methods

The inherent viscosity of the polyesters was determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.

Unless stated otherwise, the glass transition temperature (T_g) was determined using a TA DSC 2920 instrument from Thermal Analyst Instruments at a scan rate of 20° C./min according to ASTM D3418.

The glycol content and the cis/trans ratio of the compositions were determined by proton nuclear magnetic resonance (NMR) spectroscopy. All NMR spectra were recorded on a JEOL Eclipse Plus 600 MHz nuclear magnetic resonance spectrometer using either chloroform-trifluoroacetic acid (70-30 volume/volume) for polymers or, for oligomeric samples, 60/40 (wt/wt) phenol/tetrachloroethane with deuterated chloroform added for lock. Peak assignments for 2,2,4,4-tetramethyl-1,3-cyclobutanediol resonances were made by comparison to model mono- and dibenzoate esters of 2,2,4,4-tetramethyl-1,3-cyclobutanediol. These model compounds closely approximate the resonance positions found in the polymers and oligomers.

The crystallization half-time, $t_{1/2}$, was determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement was done by exposing the polymers to a temperature, T_{max} , and then cooling it to the desired temperature. The sample was then held at the desired temperature by a hot stage while transmission measurements were made as a function of time. Initially, the sample was visually clear with high light transmission and became opaque as the sample crystallized. The crystallization half-time was recorded as the time at which the light transmission was halfway between the initial transmission and the final transmission. T_{max} is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The T_{max} reported in the examples below represents the temperature at which each sample was heated to condition the sample prior to crystallization half time measurement. The T_{max} temperature is dependant on composition and is typically different for each polyester. For example, PCT may need to be heated to some temperature greater than 290° C. to melt the crystalline domains.

Density was determined using a gradient density column at 23° C.

The melt viscosity reported herein was measured by using a Rheometrics Dynamic Analyzer (RDA II). The melt viscosity was measured as a function of shear rate, at frequencies ranging from 1 to 400 rad/sec, at the temperatures reported. The zero shear melt viscosity (η_0) is the melt viscosity at zero shear rate estimated by extrapolating the data by known models in the art. This step is automatically performed by the Rheometrics Dynamic Analyzer (RDA II) software.

The polymers were dried at a temperature ranging from 80 to 100° C. in a vacuum oven for 24 hours and injection molded on a Boy 22S molding machine to give 1/8x1/2x5-inch and 1/4x1/2x5-inch flexure bars. These bars were cut to a length of 2.5 inch and notched down the 1/2 inch width with a 10-mil notch in accordance with ASTM D256. The average Izod impact strength at 23° C. was determined from measurements on 5 specimens.

In addition, 5 specimens were tested at various temperatures using 5° C. increments in order to determine the brittle-to-ductile transition temperature. The brittle-to-ductile tran-

sition temperature is defined as the temperature at which 50% of the specimens fail in a brittle manner as denoted by ASTM D256.

Color values reported herein were determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations were averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They were determined by the L*a*b* color system of the CIE (International Commission on Illumination) (translated), wherein L* represents the lightness coordinate, a* represents the red/green coordinate, and b* represents the yellow/blue coordinate.

In addition, 10-mil films were compression molded using a Carver press at 240° C.

Unless otherwise specified, the cis/trans ratio of the 1,4-cyclohexanedimethanol used in the following examples was approximately 30/70, and could range from 35/65 to 25/75.

Unless otherwise specified, the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol used in the following examples was approximately 50/50.

The following abbreviations apply throughout the working examples and figures:

TPA	Terephthalic acid
DMT	Dimethyl terephthalate
TMCD	2,2,4,4-tetramethyl-1,3-cyclobutanediol
CHDM	1,4-cyclohexanedimethanol
IV	Inherent viscosity
η_0	Zero shear melt viscosity
T_g	Glass transition temperature
T_{bd}	Brittle-to-ductile transition temperature
T_{max}	Conditioning temperature for crystallization half time measurements

Example 1

This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective at reducing the crystallization rate of PCT than ethylene glycol or isophthalic acid. In addition, this example illustrates the benefits of 2,2,4,4-tetramethyl-1,3-cyclobutanediol on the glass transition temperature and density.

A variety of copolyesters were prepared as described below. These copolyesters were all made with 200 ppm dibutyl tin oxide as the catalyst in order to minimize the effect of catalyst type and concentration on nucleation during crystallization studies. The cis/trans ratio of the 1,4-cyclohexanedimethanol was 31/69 while the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol is reported in Table 1

For purposes of this example, the samples had sufficiently similar inherent viscosities thereby effectively eliminating this as a variable in the crystallization rate measurements.

Crystallization half-time measurements from the melt were made at temperatures from 140 to 200° C. at 10° C. increments and are reported in Table 1. The fastest crystallization half-time for each sample was taken as the minimum value of crystallization half-time as a function of temperature, typically occurring around 170 to 180° C. The fastest crystallization half-times for the samples are plotted in FIG. 1 as a function of mole % comonomer modification to PCT.

The data shows that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than ethylene glycol and isophthalic acid at decreasing the crystallization rate (i.e., increasing the

crystallization half-time). In addition, 2,2,4,4-tetramethyl-1,3-cyclobutanediol increases T_g and lowers density.

mol % 1,4-cyclohexanedimethanol residues and 20.2 mol % dimethyl isophthalate residues.

TABLE 1

Example	Comonomer (mol %) ¹	IV (dl/g)	Density (g/ml)	T _g (° C.)	T _{max} (° C.)	Crystallization Half-times (min)						
						at 140° C. (min)	at 150° C. (min)	at 160° C. (min)	at 170° C. (min)	at 180° C. (min)	at 190° C. (min)	at 200° C. (min)
1A	20.2% A ²	0.630	1.198	87.5	290	2.7	2.1	1.3	1.2	0.9	1.1	1.5
1B	19.8% B	0.713	1.219	87.7	290	2.3	2.5	1.7	1.4	1.3	1.4	1.7
1C	20.0% C	0.731	1.188	100.5	290	>180	>60	35.0	23.3	21.7	23.3	25.2
1D	40.2% A ²	0.674	1.198	81.2	260	18.7	20.0	21.3	25.0	34.0	59.9	96.1
1E	34.5% B	0.644	1.234	82.1	260	8.5	8.2	7.3	7.3	8.3	10.0	11.4
1F	40.1% C	0.653	1.172	122.0	260	>10 days	>5 days	>5 days	19204	>5 days	>5 days	>5 days
1G	14.3% D	0.646 ³	1.188	103.0	290	55.0	28.8	11.6	6.8	4.8	5.0	5.5
1H	15.0% E	0.728 ⁴	1.189	99.0	290	25.4	17.1	8.1	5.9	4.3	2.7	5.1

¹The balance of the diol component of the polyesters in Table 1 is 1,4-cyclohexanedimethanol; and the balance of the dicarboxylic acid component of the polyesters in Table 1 is dimethyl terephthalate; if the dicarboxylic acid is not described, it is 100 mole % dimethyl terephthalate.

²100 mole % 1,4-cyclohexanedimethanol.

³A film was pressed from the ground polyester of Example 1G at 240° C. The resulting film had an inherent viscosity value of 0.575 dL/g.

⁴A film was pressed from the ground polyester of Example 1H at 240° C. The resulting film had an inherent viscosity value of 0.0652 dL/g.

where:

A is Isophthalic Acid

B is Ethylene Glycol

C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (approx. 50/50 cis/trans)

D is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (98/2 cis/trans)

E is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (5/95 cis/trans)

As shown in Table 1 and FIG. 1, 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers, such ethylene glycol and isophthalic acid, at increasing the crystallization half-time, i.e., the time required for a polymer to reach half of its maximum crystallinity. By decreasing the crystallization rate of PCT (increasing the crystallization half-time), amorphous articles based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol-modified PCT as described herein may be fabricated by methods known in the art. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

Preparation of the polyesters shown on Table 1 is described below.

Example 1A

This example illustrates the preparation of a copolyester with a target composition of 80 mol % dimethyl terephthalate residues, 20 mol % dimethyl isophthalate residues, and 100 mol % 1,4-cyclohexanedimethanol residues (28/72 cis/trans).

A mixture of 56.63 g of dimethyl terephthalate, 55.2 g of 1,4-cyclohexanedimethanol, 14.16 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210° C. for 5 minutes and then the temperature was gradually increased to 290° C. over 30 minutes. The reaction mixture was held at 290° C. for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.5° C. and an inherent viscosity of 0.63 dl/g. NMR analysis showed that the polymer was composed of 100

Example 1B

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 20 mol % ethylene glycol residues, and 80 mol % 1,4-cyclohexanedimethanol residues (32/68 cis/trans).

A mixture of 77.68 g of dimethyl terephthalate, 50.77 g of 1,4-cyclohexanedimethanol, 27.81 g of ethylene glycol, and 0.0433 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200° C. for 60 minutes and then the temperature was gradually increased to 210° C. over 5 minutes. The reaction mixture was held at 210° C. for 120 minutes and then heated up to 280° C. in 30 minutes. Once at 280° C., vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 10 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.7° C. and an inherent viscosity of 0.71 dl/g. NMR analysis showed that the polymer was composed of 19.8 mol % ethylene glycol residues.

Example 1C

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 80 mol % 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 17.86 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. This

31

polyester was prepared in a manner similar to that described in Example 1A. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 100.5° C. and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 80.5 mol % 1,4-cyclohexanedimethanol residues and 19.5 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Example 1D

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 40 mol % dimethyl isophthalate residues, and 100 mol % 1,4-cyclohexanedimethanol residues (28/72 cis/trans).

A mixture of 42.83 g of dimethyl terephthalate, 55.26 g of 1,4-cyclohexanedimethanol, 28.45 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210° C. for 5 minutes and then the temperature was gradually increased to 290° C. over 30 minutes. The reaction mixture was held at 290° C. for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 81.2° C. and an inherent viscosity of 0.67 dl/g. NMR analysis showed that the polymer was composed of 100 mol % 1,4-cyclohexanedimethanol residues and 40.2 mol % dimethyl isophthalate residues.

Example 1E

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 40 mol % ethylene glycol residues, and 60 mol % 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

A mixture of 81.3 g of dimethyl terephthalate, 42.85 g of 1,4-cyclohexanedimethanol, 34.44 g of ethylene glycol, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200° C. for 60 minutes and then the temperature was gradually increased to 210° C. over 5 minutes. The reaction mixture was held at 210° C. for 120 minutes and then heated up to 280° C. in 30 minutes. Once at 280° C., vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 10 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 82.1° C. and an inherent viscosity of 0.64 dl/g.

32

NMR analysis showed that the polymer was composed of 34.5 mol % ethylene glycol residues.

Example 1F

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 40 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 60 mol % 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

A mixture of 77.4 g of dimethyl terephthalate, 36.9 g of 1,4-cyclohexanedimethanol, 32.5 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210° C. for 3 minutes and then the temperature was gradually increased to 260° C. over 30 minutes. The reaction mixture was held at 260° C. for 120 minutes and then heated up to 290° C. in 30 minutes. Once at 290° C., vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 122° C. and an inherent viscosity of 0.65 dl/g. NMR analysis showed that the polymer was composed of 59.9 mol % 1,4-cyclohexanedimethanol residues and 40.1 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Example 1G

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (98/2 cis/trans), and 80 mol % 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210° C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210° C. for 3 minutes and then the temperature was gradually increased to 260° C. over 30 minutes. The reaction mixture was held at 260° C. for 120 minutes and then heated up to 290° C. in 30 minutes. Once at 290° C., vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes and the stirring speed was reduced to 50 RPM. A pressure of 0.3 mm of Hg was maintained for a total time of 60 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 103° C. and an inherent viscosity of 0.65 dl/g. NMR analysis showed that the polymer was composed

of 85.7 mol % 1,4-cyclohexanedimethanol residues and 14.3 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Example 1H

This example illustrates the preparation of a copolyester with a target composition of 100 mol % dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (5/95 cis/trans), and 80 mol % 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210° C. The stirring speed was set to 200 RPM at the beginning of the experiment. The contents of the flask were heated at 210° C. for 3 minutes and then the temperature was gradually increased to 260° C. over 30 minutes. The reaction mixture was held at 260° C. for 120 minutes and then heated up to 290° C. in 30 minutes. Once at 290° C., vacuum was gradually applied over the next 5 minutes with a set point of 100 mm of Hg and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to a set point of 0.3 mm of Hg over the next 5 minutes and the stirring speed was reduced to 50 RPM. This pressure was maintained for a total time of 60 minutes to remove excess unreacted diols. It was noted that the vacuum system failed to reach the set point mentioned above, but produced enough vacuum to produce a high melt Viscosity, visually clear and

Example 2B was obtained from Eastman Chemical Co. under the trade name Spectar. Example 2C and Example 2D were prepared on a pilot plant scale (each a 15-lb batch) following an adaptation of the procedure described in Example 1A and having the inherent viscosities and glass transition temperatures described in Table 2 below. Example 2C was prepared with a target tin amount of 300 ppm (Dibutyltin Oxide). The final product contained 295 ppm tin. The color values for the polyester of Example 2C were $L^*=77.11$; $a^*=-1.50$; and $b^*=5.79$. Example 2D was prepared with a target tin amount of 300 ppm (Dibutyltin Oxide). The final product contained 307 ppm tin. The color values for the polyester of Example 2D were $L^*=66.72$; $a^*=-1.22$; and $b^*=16.28$.

Materials were injection molded into bars and subsequently notched for Izod testing. The notched Izod impact strengths were obtained as a function of temperature and are also reported in Table 2.

For a given sample, the Izod impact strength undergoes a major transition in a short temperature span. For instance, the Izod impact strength of a copolyester based on 38 mol % ethylene glycol undergoes this transition between 15 and 20° C. This transition temperature is associated with a change in failure mode; brittle/low energy failures at lower temperatures and ductile/high energy failures at higher temperatures. The transition temperature is denoted as the brittle-to-ductile transition temperature, T_{bd} , and is a measure of toughness. T_{bd} is reported in Table 2 and plotted against mol % comonomer in FIG. 2.

The data shows that adding 2,2,4,4-tetramethyl-1,3-cyclobutanediol to PCT lowers T_{bd} and improves the toughness, as compared to ethylene glycol, which increases T_{bd} of PCT.

TABLE 2

Exam- ple	Comon- omer (mol %) ¹	IV (dl/ g)	T_g (° C.)	T_{bd} (° C.)	Notched Izod Impact Energy (ft-lb/in)										
					at -20° C.	at -15° C.	at -10° C.	at -5° C.	at 0° C.	at 5° C.	at 10° C.	at 15° C.	at 20° C.	at 25° C.	at 30° C.
2A	38.0% B	0.68	86	18	NA	NA	NA	1.5	NA	NA	1.5	1.5	32	32	NA
2B	69.0% B	0.69	82	26	NA	NA	NA	NA	NA	NA	2.1	NA	2.4	13.7	28.7
2C	22.0% C	0.66	106	-5	1.5	NA	12	23	23	NA	23	NA	NA	NA	NA
2D	42.8% C	0.60	133	-12	2.5	2.5	11	NA	14	NA	NA	NA	NA	NA	NA

¹The balance of the glycol component of the polyesters in the Table is 1,4-cyclohexanedimethanol. All polymers were prepared from 100 mole % dimethyl terephthalate.

NA = Not available.

where:

B is Ethylene glycol

C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (50/50 cis/trans)

colorless polymer with a glass transition temperature of 99° C. and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 85 mol % 1,4-cyclohexanedimethanol residues and 15 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Example 2

This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol improves the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol).

Copolyesters based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol were prepared as described below. The cis/trans ratio of the 1,4-cyclohexanedimethanol was approximately 31/69 for all samples. Copolyesters based on ethylene glycol and 1,4-cyclohexanedimethanol were commercial polyesters. The copolyester of Example 2A (Estar PCTG 5445) was obtained from Eastman Chemical Co. The copolyester of

Example 3

This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example comprise from 15 to 25 mol % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol were prepared as described below, having the composition and properties shown on Table 3. The balance up to 100 mol % of the diol component of the polyesters in Table 3 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

Materials were injection molded into both 3.2 mm and 6.4 mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23° C. and are reported in Table 3. Density, T_g , and crystallization half-time were measured on the molded bars. Melt viscosity was measured on pellets at 290° C.

TABLE 3

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole %	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2 mm thick bars at 23° C. (J/m)	Notched Izod of 6.4 mm thick bars at 23° C. (J/m)	Specific Gravity (g/mL)	Tg (° C.)	Crystallization Halftime from melt at 170° C. (min)	Melt Viscosity at 1 rad/sec at 290° C. (Poise)
A	15	48.8	0.736	0.707	1069	878	1.184	104	15	5649
B	18	NA	0.728	0.715	980	1039	1.183	108	22	6621
C	20	NA	0.706	0.696	1006	1130	1.182	106	52	6321
D	22	NA	0.732	0.703	959	988	1.178	108	63	7161
E	21	NA	0.715	0.692	932	482	1.179	110	56	6162
F	24	NA	0.708	0.677	976	812	1.180	109	58	6282
G	23	NA	0.650	0.610	647	270	1.182	107	46	3172
H	23	47.9	0.590	0.549	769	274	1.181	106	47	1736
I	23	48.1	0.531	0.516	696	352	1.182	105	19	1292

NA = Not available

Example 3A

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 14.34 lb (45.21 gram-mol) 1,4-cyclohexanedimethanol, and 4.58 lb (14.44 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and at a pressure of 20 psig. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C. and 90 mm of Hg, the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290° C., and the pressure was decreased to <1 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of <1 mm of Hg until the power draw to the agitator no longer increased (70 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.736 dL/g and a Tg of 104° C. NMR analysis showed that the polymer was composed of 85.4 mol % 1,4-cyclohexane-dimethanol residues and 14.6 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L*=78.20, a*=-1.62, and b*=6.23.

Example 3B to Example 3D

The polyesters described in Example 3B to Example 3D were prepared following a procedure similar to the one described for Example 3A. The composition and properties of these polyesters are shown in Table 3.

Example 3E

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the

catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C. and 90 mm of Hg, the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290° C., and the pressure was decreased to <1 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of <1 mm of Hg for 60 minutes. The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.715 dL/g and a Tg of 110° C. X-ray analysis showed that the polyester had 223 ppm tin. NMR analysis showed that the polymer was composed of 78.6 mol % 1,4-cyclohexane-dimethanol residues and 21.4 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L*=76.45, a*=-1.65, and b*=6.47.

Example 3F

The polyester described in Example 3F was prepared following a procedure similar to the one described for Example 3A. The composition and properties of this polyester are shown in Table 3.

Example 3G

The polyester described in Example 3G was prepared following a procedure similar to the one described for Example 3A. The composition and properties of this polyester are shown in Table 3.

Example 3H

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb (19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was car-

37

ried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C. and 90 mm of Hg, the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290° C., and the pressure was decreased to <1 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of <1 mm of Hg for 12 minutes. The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.590 dL/g and a Tg of 106° C. NMR analysis showed that the polymer was composed of 77.1 mol % 1,4-cyclohexane-dimethanol residues and 22.9 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L*=83.27, a*=-1.34, and b*=5.08.

Example 3I

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 12.61 lb (39.77 gram-mol) 1,4-cyclohexanedimethanol, and 6.30 lb

38

of 105° C. NMR analysis showed that the polymer was composed of 76.9 mol % 1,4-cyclohexane-dimethanol residues and 23.1 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L*=80.42, a*=-1.28, and b*=5.13.

Example 4

This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example fall comprise more than 25 to less than 40 mol % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol (31/69 cis/trans) were prepared as described below, having the composition and properties shown on Table 4. The balance up to 100 mol % of the diol component of the polyesters in Table 4 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

Materials were injection molded into both 3.2 mm and 6.4 mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23° C. and are reported in Table 4. Density, Tg, and crystallization halftime were measured on the molded bars. Melt viscosity was measured on pellets at 290° C.

TABLE 4

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole %	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched	Notched	Specific Gravity (g/mL)	Tg (° C.)	Crystallization Halftime from melt at 170° C. (min)	Melt Viscosity at 1 rad/sec at 290° C. (Poise)
					Izod of 3.2 mm thick bars at 23° C. (J/m)	Izod of 6.4 mm thick bars at 23° C. (J/m)				
A	27	47.8	0.714	0.678	877	878	1.178	113	280	8312
B	31	NA	0.667	0.641	807	789	1.174	116	600	6592

NA = Not available

(19.88 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C. and 90 mm of Hg the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290° C., and the pressure was decreased to 4 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of 4 mm of Hg for 30 minutes. The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.531 dL/g and a Tg

Example 4A

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 11.82 lb (37.28 gram-mol) 1,4-cyclohexanedimethanol, and 6.90 lb (21.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C. and 90 mm of Hg, the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290° C., and the pressure was decreased to <1 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of <1 mm of Hg until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel

was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.714 dL/g and a Tg of 113° C. NMR analysis showed that then polymer was composed of 73.3 mol % 1,4-cyclohexane-dimethanol residues and 26.7 mol % 2,2,4,4-tetra methyl-1,3-cyclobutanediol residues.

Example 4B

The polyester of Example 4B was prepared following a procedure similar to the one described for Example 4A. The composition and properties of this polyester are shown in Table 4.

Example 5

This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol % or greater.

Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol were prepared as described below, having the composition and properties shown on Table 5. The balance up to 100 mol % of the diol component of the polyesters in Table 5 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

Materials were injection molded into both 3.2 mm and 6.4 mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23° C. and are reported in Table 5. Density, Tg, and crystallization half-time were measured on the molded bars. Melt viscosity was measured on pellets at 290° C.

TABLE 5

Compilation of various properties for certain polyesters useful in the invention										
Example	TMCD mole %	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2 mm thick bars at 23° C. (J/m)	Notched Izod of 6.4 mm thick bars at 23° C. (J/m)	Specific Gravity (g/mL)	Tg (° C.)	Crystallization Half-time from melt at 170° C. (min)	Melt Viscosity at 1 rad/sec at 290° C. (Poise)
A	44	46.2	0.657	0.626	727	734	1.172	119	NA	9751
B	45	NA	0.626	0.580	748	237	1.167	123	NA	8051
C	45	NA	0.582	0.550	671	262	1.167	125	19782	5835
D	45	NA	0.541	0.493	424	175	1.167	123	NA	3275
E	59	46.6	0.604	0.576	456	311	1.156	139	NA	16537
F	45	47.2	0.475	0.450	128	30	1.169	121	NA	1614

NA = Not available

Example 5A

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and

20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290° C. and the pressure was decreased to 2 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of 2 mm of Hg until the power draw to the agitator no longer increased (80 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.657 dL/g and a Tg of 119° C. NMR analysis showed that the polymer was composed of 56.3 mol % 1,4-cyclohexanedimethanol residues and 43.7 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L*=75.04, a*=-1.82, and b*=6.72.

Example 5B to Example 5D

The polyesters described in Example 5B to Example 5D were prepared following a procedure similar to the one described for Example 5A. The composition and properties of these polyesters are shown in Table 5.

Example 5E

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 6.43 lb (20.28 gram-mol) 1,4-cyclohexanedimethanol, and 12.49 lb (39.37 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20

psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290° C. and the pressure was decreased to 2 mm of Hg. The reaction mixture was held at 290° C. and at a pressure of <1 mm of Hg until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.604 dL/g and a Tg of 139° C. NMR analysis showed that the

41

polymer was composed of 40.8 mol % 1,4-cyclohexanedimethanol residues and 59.2 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: $L^*=80.48$, $a^*=-1.30$, and $b^*=6.82$.

Example 5F

21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250° C. and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250° C. and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270° C. and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270° C.

42

composition of 100 mole % terephthalic acid, 3.5 mole % cyclohexanedimethanol (CHDM) and 96.5 mole % ethylene glycol. The PETG was Eastar 6763 from Eastman Chemical Company, with a nominal composition of 100 mole % terephthalic acid, 31 mole % cyclohexanedimethanol (CHDM) and 69 mole % ethylene glycol. The PCTG was Eastar DN001 from Eastman Chemical Company, with a nominal composition of 100 mole % terephthalic acid, 62 mole % cyclohexanedimethanol (CHDM) and 38 mole % ethylene glycol. The PCTA was Eastar AN001 from Eastman Chemical Company, with a nominal composition of 65 mole % terephthalic acid, 35 mole % isophthalic acid and 100 mole % cyclohexanedimethanol (CHDM). The Polysulfone was Udel 1700 from Solvay, with a nominal composition of 100 mole % bisphenol A residues and 100 mole % 4,4-dichlorosulfonyl sulfone residues. Udel 1700 has a nominal melt flow rate of 6.5 grams/10 minutes measured at 343 C using a 2.16 kg weight. The SAN was Lustran 31 from Lanxess, with a nominal composition of 76 weight % styrene and 24 weight % acrylonitrile. Lustran 31 has a nominal melt flow rate of 7.5 grams/10 minutes measured at 230 C using a 3.8 kg weight. The examples of the invention show improved toughness in 6.4 mm thickness bars compared to all of the other resins.

TABLE 6

Compilation of various properties for certain commercial polymers								
Example	Polymer name	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of		Specific Gravity (g/mL)	Tg (° C.)	Crystallization Halftime from melt (min)
				3.2 mm thick bars at 23° C. (J/m)	6.4 mm thick bars at 23° C. (J/m)			
A	PC	12 MFR	NA	929	108	1.20	146	NA
B	PCTG	0.73	0.696	NB	70	1.23	87	30 at 170° C.
C	PCTA	0.72	0.702	98	59	1.20	87	15 at 150° C.
D	PETG	0.75	0.692	83	59	1.27	80	2500 at 130° C.
E	PET	0.76	0.726	45	48	1.33	78	1.5 at 170° C.
F	SAN	7.5 MFR	NA	21	NA	1.07	-110	NA
G	PSU	6.5 MFR	NA	69	NA	1.24	-190	NA

NA = Not available

and 90 mm of Hg, the agitator speed was decreased to 15 RPM and the pressure was decreased to 4 mm of Hg. When the reaction mixture temperature was 270° C. and the pressure was 4 mm of Hg, the pressure of the pressure vessel was immediately increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.475 dL/g and a Tg of 121° C. NMR analysis showed that the polymer was composed of 55.5 mol % 1,4-cyclohexanedimethanol residues and 44.5 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: $L^*=85.63$, $a^*=-0.88$, and $b^*=4.34$.

Example 6

Comparative Example

This example shows data for comparative materials in Table 6. The PC was Makrolon 2608 from Bayer, with a nominal composition of 100 mole % bisphenol A residues and 100 mole % diphenyl carbonate residues. Makrolon 2608 has a nominal melt flow rate of 20 grams/10 minutes measured at 300 C using a 1.2 kg weight. The PET was Eastar 9921 from Eastman Chemical Company, with a nominal

Example 7

This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example comprise from 15 to 25 mol % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Example 7A to Example 7F

Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. NMR analysis on the 2,2,4,4-tetramethyl-1,3-cyclobutanediol starting material showed a cis/trans ratio of 53/47. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200° C. and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210° C. and these conditions were held for an additional 2 hours. The

43

temperature was raised to 285° C. (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295° C. during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 20 mol %.

Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by ¹H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20° C./min.

Example 7G to Example 7P

These polyesters were prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator, covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777 g (4 moles) of dimethyl terephthalate, 230 g (1.6 moles) of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, 460.8 g (3.2 moles) of cyclohexane dimethanol and 1.12 g of butyltin tris-2-ethylhexanoate (such that there will be 200 ppm tin metal in the final polymer). The heating mantle was set manually to 100% output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260° C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

In the polycondensation reactions, a 500 ml round bottom flask was charged with approximately 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for each example is reported in the following tables.

Camile Sequence for Example 7G and Example 7H

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50

44

-continued

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	290	6	25

Camile Sequence for Example 7M to Example 7P

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	3	25
7	110	290	3	25

Camile Sequence for Example 7J and Example 7K

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	2	25
7	110	290	2	25

Camile Sequence for Example 7I and Example 7L

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	1	25
7	110	290	1	25

The resulting polymers were recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C., catalyst level (Sn) by x-ray fluorescence, and color (L*, a*, b*) by transmission spectroscopy. Polymer composition was obtained by ¹H NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

The table below shows the experimental data for the polyesters of this example. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity. FIG. 3 also shows the dependence of Tg on composition and inherent viscosity.

TABLE 7

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol % TMCD	% cis TMCD	IV (dL/g)	T _g (° C.)	η _o at 260° C. (Poise)	η _o at 275° C. (Poise)	η _o at 290° C. (Poise)
A	20	51.4	0.72	109	11356	19503	5527
B	19.1	51.4	0.60	106	6891	3937	2051
C	19	53.2	0.64	107	8072	4745	2686
D	18.8	54.4	0.70	108	14937	8774	4610
E	17.8	52.4	0.50	103	3563	1225	883
F	17.5	51.9	0.75	107	21160	10877	5256
G	22.8	53.5	0.69	109	NA	NA	NA
H	22.7	52.2	0.68	108	NA	NA	NA
I	23.4	52.4	0.73	111	NA	NA	NA
J	23.3	52.9	0.71	111	NA	NA	NA
K	23.3	52.4	0.74	112	NA	NA	NA
L	23.2	52.5	0.74	112	NA	NA	NA
M	23.1	52.5	0.71	111	NA	NA	NA
N	22.8	52.4	0.73	112	NA	NA	NA
O	22.7	53	0.69	112	NA	NA	NA
P	22.7	52	0.70	111	NA	NA	NA

NA = Not available

Example 8

This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example fall comprise more than 25 to less than 40 mol % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. NMR analysis on the 2,2,4,4-tetramethyl-1,3-cyclobutanediol starting material showed a cis/trans ratio of 53/47. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200° C. and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210° C. and these conditions were held for an additional 2 hours. The temperature was raised to 285° C. (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a

the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295° C. during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 32 mol %.

Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by ¹H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20° C./min.

The table below shows the experimental data for the polyesters of this example. FIG. 3 also shows the dependence of T_g on composition and inherent viscosity. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity.

TABLE 8

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol % TMCD	% cis TMCD	IV (dL/g)	T _g (° C.)	η _o at 260° C. (Poise)	η _o at 275° C. (Poise)	η _o at 290° C. (Poise)
A	32.2	51.9	0.71	118	29685	16074	8522
B	31.6	51.5	0.55	112	5195	2899	2088
C	31.5	50.8	0.62	112	8192	4133	2258
D	30.7	50.7	0.54	111	4345	2434	1154
E	30.3	51.2	0.61	111	7929	4383	2261
F	30.0	51.4	0.74	117	31476	17864	8630
G	29.0	51.5	0.67	112	16322	8787	4355
H	31.1	51.4	0.35	102	NA	NA	NA

NA = Not available

period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete,

Example 9

This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation

of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol % or greater.

Examples A to AC

These polyesters were prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator, covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777 g of dimethyl terephthalate, 375 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, 317 g of cyclohexane dimethanol and 1.12 g of butyltin tris-2-ethylhexanoate (such that there will be 200 ppm tin metal in the final polymer). The heating mantle was set manually to 100% output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260° C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

In the polycondensation reactions, a 500 ml round bottom flask was charged with 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for these examples is reported in the following table, unless otherwise specified below.

Camile Sequence for Polycondensation Reactions

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	290	6	25

Camile Sequence for Examples A, C, R, Y, AB, AC

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	290	6	25

For Examples B, D, F, the same sequence in the preceding table was used, except the time was 80 min in Stage 7. For Examples G and J, the same sequence in the preceding table was used, except the time was 50 min in Stage 7. For Example L, the same sequence in the preceding table was used, except the time was 140 min in Stage 7.

Camile Sequence for Example E

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	300	90	50
6	5	300	7	25
7	110	300	7	25

For Example I, the same sequence in the preceding table was used, except the vacuum was 8 torr in Stages 6 and 7. For Example O, the same sequence in the preceding table was used, except the vacuum was 6 torr in Stages 6 and 7. For Example P, the same sequence in the preceding table was used, except the vacuum was 4 torr in Stages 6 and 7. For Example Q, the same sequence in the preceding table was used, except the vacuum was 5 torr in Stages 6 and 7.

Camile Sequence for Example H

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	280	90	50
6	5	280	5	25
7	110	280	5	25

For Example U and M, the same sequence in the preceding table was used, except the vacuum was 6 torr in Stages 6 and 7. For Example V and X, the same sequence in the preceding table was used, except the vacuum was 6 torr stir rate was 15 rpm in Stages 6 and 7. For Example Z, the same sequence in the preceding table was used, except the stir rate was 15 rpm in Stages 6 and 7.

Camile Sequence for Example K

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	300	90	50
6	5	300	6	15
7	110	300	6	15

For Example M, the same sequence in the preceding table was used, except the vacuum was 8 torr in Stages 6 and 7. For Example N, the same sequence in the preceding table was used, except the vacuum was 7 torr in Stages 6 and 7.

Camile Sequence for Examples S and T

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	5	290	6	25
5	110	290	6	25

The resulting polymers were recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C., catalyst level (Sn) by x-ray fluorescence, and color (L*, a*, b*) by transmission spectroscopy. Polymer composition was obtained by ¹H NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

Examples AD to AK and AT

The polyesters of these examples were prepared as described above for Examples A to AC, except that the target tin amount in the final polymer was 150 ppm for examples AD to AK and AT. The following tables describe the temperature/pressure/stir rate sequences controlled by the Camile software for these examples.

Camile Sequence for Examples AD, AF, and AH

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	400	50
5	110	290	400	50
6	5	290	8	50
7	110	295	8	50

For Example AD, the stirrer was turned to 25 rpm with 95 min left in Stage 7.

Camile Sequence for Example AE

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	10	245	760	0
2	5	245	760	50
3	30	283	760	50
4	3	283	175	50
5	5	283	5	50
6	5	283	1.2	50
7	71	285	1.2	50

For Example AK, the same sequence in the preceding table was used, except the time was 75 min in Stage 7.

Camile Sequence for Example AG

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	10	245	760	0
2	5	245	760	50
3	30	285	760	50
4	3	285	175	50
5	5	285	5	50
6	5	285	4	50
7	220	290	4	50

Camile Sequence for Example AI

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	285	90	50
6	5	285	6	50
7	70	290	6	50

Camile Sequence for Example AJ

Stage	Time (min)	Temp (° C.)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	295	6	25

Examples AL to AS

Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200° C. and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210° C. and these conditions were held for an additional 2 hours. The temperature was raised to 285° C. (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295° C. during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass

was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol %.

Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by ¹H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20° C./min.

The table below shows the experimental data for the polyesters of this example. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity. FIG. 3 also shows the dependence of T_g on composition and inherent viscosity.

TABLE 9

Glass transition temperature as a function of inherent viscosity and composition							
Example	mol % TMCD	% cis TMCD	IV (dL/g)	T _g (° C.)	η _o at 260° C. (Poise)	η _o at 275° C. (Poise)	η _o at 290° C. (Poise)
A	43.9	72.1	0.46	131	NA	NA	NA
B	44.2	36.4	0.49	118	NA	NA	NA
C	44	71.7	0.49	128	NA	NA	NA
D	44.3	36.3	0.51	119	NA	NA	NA
E	46.1	46.8	0.51	125	NA	NA	NA
F	43.6	72.1	0.52	128	NA	NA	NA
G	43.6	72.3	0.54	127	NA	NA	NA
H	46.4	46.4	0.54	127	NA	NA	NA
I	45.7	47.1	0.55	125	NA	NA	NA
J	44.4	35.6	0.55	118	NA	NA	NA
K	45.2	46.8	0.56	124	NA	NA	NA
L	43.8	72.2	0.56	129	NA	NA	NA
M	45.8	46.4	0.56	124	NA	NA	NA
N	45.1	47.0	0.57	125	NA	NA	NA
O	45.2	46.8	0.57	124	NA	NA	NA
P	45	46.7	0.57	125	NA	NA	NA
Q	45.1	47.1	0.58	127	NA	NA	NA
R	44.7	35.4	0.59	123	NA	NA	NA
S	46.1	46.4	0.60	127	NA	NA	NA
T	45.7	46.8	0.60	129	NA	NA	NA
U	46	46.3	0.62	128	NA	NA	NA
V	45.9	46.3	0.62	128	NA	NA	NA
X	45.8	46.1	0.63	128	NA	NA	NA
Y	45.6	50.7	0.63	128	NA	NA	NA
Z	46.2	46.8	0.65	129	NA	NA	NA
AA	45.9	46.2	0.66	128	NA	NA	NA
AB	45.2	46.4	0.66	128	NA	NA	NA
AC	45.1	46.5	0.68	129	NA	NA	NA
AD	46.3	52.4	0.52	NA	NA	NA	NA
AE	45.7	50.9	0.54	NA	NA	NA	NA
AF	46.3	52.6	0.56	NA	NA	NA	NA
AG	46	50.6	0.56	NA	NA	NA	NA
AH	46.5	51.8	0.57	NA	NA	NA	NA
AI	45.6	51.2	0.58	NA	NA	NA	NA
AJ	46	51.9	0.58	NA	NA	NA	NA
AK	45.5	51.2	0.59	NA	NA	NA	NA
AL	45.8	50.1	0.624	125	NA	NA	7696
AM	45.7	49.4	0.619	128	NA	NA	7209
AN	46.2	49.3	0.548	124	NA	NA	2348
AP	45.9	49.5	0.72	128	76600	40260	19110
AQ	46.0	50	0.71	131	68310	32480	17817
AR	46.1	49.6	0.383	117	NA	NA	387
AS	45.6	50.5	0.325	108	NA	NA	NA
AT	47.2	NA	0.48	NA	NA	NA	NA

NA = Not available

This example illustrates the effect of the predominance of the type of 2,2,4,4-tetramethyl-1,3-cyclobutanediol isomer (cis or trans) on the glass transition temperature of the polyester.

Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200° C. and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210° C. and these conditions were held for an additional 2 hours. The temperature was raised to 285° C. (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295° C. during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol %.

Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by ¹H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20° C./min.

The table below shows the experimental data for the polyesters of this Example. The data shows that cis 2,2,4,4-tetramethyl-1,3-cyclobutanediol is approximately twice as effective as trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol at increasing the glass transition temperature for a constant inherent viscosity.

TABLE 10

Effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol cis/trans composition on T _g							
Example	mol % TMCD	IV (dL/g)	T _g (° C.)	η _o at 260° C. (Poise)	η _o at 275° C. (Poise)	η _o at 290° C. (Poise)	% cis TMCD
A	45.8	0.71	119	N.A.	N.A.	N.A.	4.1
B	43.2	0.72	122	N.A.	N.A.	N.A.	22.0
C	46.8	0.57	119	26306	16941	6601	22.8
D	43.0	0.67	125	55060	36747	14410	23.8
E	43.8	0.72	127	101000	62750	25330	24.5
F	45.9	0.533	119	11474	6864	2806	26.4
G	45.0	0.35	107	N.A.	N.A.	N.A.	27.2
H	41.2	0.38	106	1214	757	N.A.	29.0
I	44.7	0.59	123	N.A.	N.A.	N.A.	35.4
J	44.4	0.55	118	N.A.	N.A.	N.A.	35.6
K	44.3	0.51	119	N.A.	N.A.	N.A.	36.3
L	44.0	0.49	128	N.A.	N.A.	N.A.	71.7
M	43.6	0.52	128	N.A.	N.A.	N.A.	72.1

TABLE 10-continued

Effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol cis/trans composition on T_g							
Example	mol % TMCD	IV (dL/g)	T_g ($^{\circ}$ C.)	η_o at 260 $^{\circ}$ C. (Poise)	η_o at 275 $^{\circ}$ C. (Poise)	η_o at 290 $^{\circ}$ C. (Poise)	% cis TMCD
N	43.6	0.54	127	N.A.	N.A.	N.A.	72.3
O	41.5	0.58	133	15419	10253	4252	88.7
P	43.8	0.57	135	16219	10226	4235	89.6
Q	41.0	0.33	120	521	351	2261	90.4
R	43.0	0.56	134	N.A.	N.A.	N.A.	90.6
S	43.0	0.49	132	7055	4620	2120	90.6
T	43.1	0.55	134	12970	8443	3531	91.2
U	45.9	0.52	137	N.A.	N.A.	N.A.	98.1

NA = not available

Example 11

This example illustrates the preparation of a copolyester containing 100 mol % dimethyl terephthalate residues, 55 mol % 1,4-cyclohexanedimethanol residues, and 45 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

A mixture of 97.10 g (0.5 mol) dimethyl terephthalate, 52.46 g (0.36 mol) 1,4-cyclohexanedimethanol, 34.07 g (0.24 mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.0863 g (300 ppm) dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200 $^{\circ}$ C. The contents of the flask were heated at 200 $^{\circ}$ C. for 1 hour and then the temperature was increased to 210 $^{\circ}$ C. The reaction mixture was held at 210 $^{\circ}$ C. for 2 hours and then heated up to 290 $^{\circ}$ C. in 30 minutes. Once at 290 $^{\circ}$ C., a vacuum of 0.01 psig was gradually applied over the next 3 to 5 minutes. Full vacuum (0.01 psig) was maintained for a total time of about 45 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 125 $^{\circ}$ C. and an inherent viscosity of 0.64 dl/g.

Example 12

Comparative Example

This example illustrates that a polyester based on 100% 2,2,4,4-tetramethyl-1,3-cyclobutanediol has a slow crystallization half-time.

A polyester based solely on terephthalic acid and 2,2,4,4-tetramethyl-1,3-cyclobutanediol was prepared in a method similar to the method described in Example 1A with the properties shown on Table 11. This polyester was made with 300 ppm dibutyl tin oxide. The trans/cis ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol was 65/35.

Films were pressed from the ground polymer at 320 $^{\circ}$ C. Crystallization half-time measurements from the melt were made at temperatures from 220 to 250 $^{\circ}$ C. at 10 $^{\circ}$ C. increments and are reported in Table 11. The fastest crystallization half-time for the sample was taken as the minimum value of crystallization half-time as a function of temperature. The fastest crystallization half-time of this polyester is around 1300 minutes. This value contrasts with the fact that the polyester (PCT) based solely on terephthalic acid and 1,4-cyclohexanedimethanol (no comonomer modification) has an extremely short crystallization half-time (<1 min) as shown in FIG. 1.

TABLE 11

Crystallization Half-times (min)							
Comonomer (mol %)	IV (dl/g)	T_g ($^{\circ}$ C.)	T_{max} ($^{\circ}$ C.)	at 220 $^{\circ}$ C. (min)	at 230 $^{\circ}$ C. (min)	at 240 $^{\circ}$ C. (min)	at 250 $^{\circ}$ C. (min)
100 mol % F	0.63	170.0	330	3291	3066	1303	1888

where:

F is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (65/35 Trans/Cis)

It can be clearly seen from a comparison of the data in the above relevant working examples that the polyesters of the present invention offer a definite advantage over the commercially available polyesters with regard to glass transition temperature, density, slow crystallization rate, melt viscosity, and toughness.

The invention has been described in detail with reference to the embodiments disclosed herein, but it will be understood that variations and modifications can be effected within the spirit and scope of the invention.

What is claimed is:

1. A dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
 - i) 20 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 70 to 80 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %;

wherein the inherent viscosity of the polyester is from 0.60 to 0.75 dl/g as determined in 60/40(wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25 $^{\circ}$ C.;

wherein the polyester has a T_g of from 100 to 130 $^{\circ}$ C.; wherein said polyester composition contains no polycarbonate;

wherein the melt viscosity of said polyester is less than 10,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290 $^{\circ}$ C.; and

wherein the polyester has a notched Izod impact strength of at least 7.5 ft-lb/inch at 23 $^{\circ}$ C. according to ASTM D256 with a 10-mil notch in a 1/8 inch thick bar.

2. The dialysis filter housing of claim 1, wherein the inherent viscosity of the polyester is from 0.65 to 0.75 dl/g.

3. The dialysis filter housing of claim 1, wherein the inherent viscosity of the polyester is from 0.60 to 0.70 dl/g.

4. The dialysis filter housing of claim 1, wherein the inherent viscosity of the polyester is from 0.60 to 0.72 dl/g.

5. The dialysis filter housing of claim 1, wherein the polyester has a T_g of 100 to 120 $^{\circ}$ C.

6. The dialysis filter housing of claim 1, wherein the polyester has a T_g of 105 to 125 $^{\circ}$ C.

7. The dialysis filter housing of claim 1, wherein the glycol component of the polyester comprises 20 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and 75 to 80 mole % 1,4-cyclohexanedimethanol residues.

8. The dialysis filter housing of claim 1, wherein the glycol component of the polyester comprises 25 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and 70 to 75 mole % 1,4-cyclohexanedimethanol residues.

9. The dialysis filter housing of claim 1, wherein the dicarboxylic acid component comprises 80 to 100 mole % of terephthalic acid residues.

10. The dialysis filter housing of claim 1, wherein the dicarboxylic acid component comprises 90 to 100 mole % of terephthalic acid residues.

11. The dialysis filter housing of claim 1, wherein the dicarboxylic acid component comprises 95 to 100 mole % of terephthalic acid residues.

12. The dialysis filter housing of claim 1, wherein the polyester comprises from 0.1 to 10 mole % of 1,3-propanediol residues, 1,4-butanediol residues, or mixture thereof.

13. The dialysis filter housing of claim 1, wherein the polyester comprises from 0.01 to 10 mole % of ethylene glycol residues.

14. The dialysis filter housing of claim 1, wherein the 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising greater than 50 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and less than 50 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

15. The dialysis filter housing of claim 1, wherein the 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and less than 45 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

16. The dialysis filter housing of claim 1, wherein the 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues are a mixture comprising greater than 50 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and less than 50 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and the dicarboxylic acid component comprises 80 to 100 mole % of terephthalic acid residues.

17. The dialysis filter housing of claim 1, wherein the polyester composition comprises at least one polymer chosen from poly(etherimides), polyphenylene oxides, poly(phenylene oxide)/polystyrene blends, polystyrene resins, polyphenylene sulfides, polyphenylene sulfide/sulfones, polysulfones; polysulfone ethers, poly(ether-ketones), polyamides, polystyrene, polystyrene copolymers, styrene acrylonitrile copolymers, acrylonitrile butadiene styrene copolymers, poly(methylmethacrylate), or acrylic copolymers.

18. The dialysis filter housing of claim 1, wherein the melt viscosity of the polyester is less than 6,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290° C.

19. The dialysis filter housing of claim 1, wherein the polyester comprises residues of at least one branching agent an amount of 0.01 to 10 weight % based on the total weight of the polyester.

20. The dialysis filter housing of claim 1, wherein the polyester has a crystallization half-time of greater than 100 minutes at 170° C.

21. The dialysis filter housing of claim 1, wherein the polyester has a crystallization half-time of greater than 1,000 minutes at 170° C.

22. The dialysis filter housing of claim 1, wherein the polyester composition has a density of less than 1.2 g/ml at 23° C.

23. The dialysis filter housing of claim 1, wherein the polyester composition comprises at least one thermal stabilizer or a reaction product thereof.

24. The dialysis filter housing of claim 1, wherein the yellowness index of the polyester according to ASTM D-1925 is less than 50.

25. The dialysis filter housing of claim 1, wherein the polyester has a notched Izod impact strength of at least 10 ft-lbs/in at 23° C. according to ASTM D256 with a 10-mil notch in a 1/8-inch thick bar.

26. The dialysis filter housing of claim 1, wherein the polyester has a notched Izod impact strength of at least 10 ft-lbs/in at 23° C. according to ASTM D256 with a 10-mil notch in a 1/4-inch thick bar.

27. The dialysis filter housing of claim 1, wherein the polyester comprises residues of at least one catalyst comprising a tin compound or a reaction product thereof.

28. The dialysis filter housing of claim 1, wherein the dialysis filter housing is a protective casing having a plurality of openings for introducing and/or discharging a dialyzate.

29. The dialysis filter housing of claim 1, wherein the dialysis filter housing is formed by injection molding.

30. A dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
 - i) 20 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 70 to 80 mole % of 1,4-cyclohexanedimethanol residues,
- (c) residues of at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %; wherein the inherent viscosity of the polyester is from 0.60 to 0.75 dL/g as determined in 60/40(wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.;

wherein the polyester has a Tg of from 100 to 130° C.;

wherein said polyester composition contains no polycarbonate;

wherein the melt viscosity of said polyester is less than 10,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290° C.; and

wherein the polyester has a notched Izod impact strength of at least 7.5 ft-lb/inch at 23° C. according to ASTM D256 with a 10-mil notch in a 1/8 inch thick bar.

31. The dialysis filter housing of claim 30, wherein the inherent viscosity of the polyester is from 0.65 to 0.75 dL/g.

32. The dialysis filter housing of claim 30, wherein the inherent viscosity of the polyester is from 0.60 to 0.70 dL/g.

33. The dialysis filter housing of claim 30, wherein the inherent viscosity of the polyester is from 0.60 to 0.72 dL/g.

34. The dialysis filter housing of claim 30, wherein the polyester has a Tg of 100 to 120° C.

35. The dialysis filter housing of claim 32, wherein the polyester has a Tg of 105 to 125° C.

36. The dialysis filter housing of claim 30, wherein the dialysis filter housing is a protective casing having a plurality of openings for introducing and/or discharging a dialyzate.

37. A dialysis filter housing comprising at least one polyester composition comprising at least one polyester, which comprises:

- (a) a dicarboxylic acid component comprising:
 - i) 70 to 100 mole % of terephthalic acid residues;
 - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
 - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
 - i) 20 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
 - ii) 70 to 80 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, the total mole % of the glycol component is 100 mole %;

- (c) at least one thermal stabilizer or a reaction product thereof;

wherein the inherent viscosity of the polyester is from 0.60 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25° C.;

wherein the polyester has a Tg of from 100 to 130° C.;

wherein said polyester composition contains no polycarbonate;

wherein the polyester has a notched Izod impact strength of at least 7.5 ft-lb/inch at 23° C. according to ASTM D256 with a 10-mil notch in a 1/8 inch thick bar; and

wherein the melt viscosity of the polyester is less than 10,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290° C.

38. The dialysis filter housing of claim 37, wherein the inherent viscosity of the polyester is from 0.65 to 0.75 dL/g.

39. The dialysis filter housing of claim 37, wherein the inherent viscosity of the polyester is from 0.60 to 0.72 dL/g.

40. The dialysis filter housing of claim 37, wherein the polyester has a Tg of 100 to 120° C.

41. The dialysis filter housing of claim 37, wherein the dialysis filter housing is a protective casing having a plurality of openings for introducing and/or discharging a dialyzate.

42. The dialysis filter housing of claims 1 or 30, wherein the polyester comprises 20 to 25 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and 75 to 80 mole % of 1,4-cyclohexanedimethanol residues.

43. The dialysis filter housing of claims 1 or 30, wherein the polyester comprises 25 to 30 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and 70 to 75 mole % of 1,4-cyclohexanedimethanol residues.

44. The dialysis filter housing of claim 37 wherein the melt viscosity of the polyester is less than 6,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290° C.

45. The dialysis filter housing of claim 30, wherein the polyester composition comprises residues from at least one branching agent in the amount of 0.01 to 10 mole % based on the total mole percentage of the diacid residues or diol residues.

46. The dialysis filter housing of claim 30, wherein said polyester comprises residues of at least one branching agent in the amount of 0.1 to 0.7 mole % based on the total mole percentage of the diacid residues or diol residues %.

47. The dialysis filter housing of claim 30, wherein said polyester comprises residues of at least one branching agent selected from trimellitic acid, trimellitic anhydride, pyromellitic dianhydride, trimethylolpropane, glycerol, pentaerythritol, citric acid, tartaric acid, or 3-hydroxyglutaric acid.

48. The dialysis filter housing of claim 30, wherein said polyester comprises residues of trimellitic anhydride.

49. The dialysis filter housing of claim 37, wherein said thermal stabilizer comprises at least one ester selected from alkyl, branched alkyl, substituted alkyl, difunctional alkyl, alkyl ethers, aryl, and substituted aryl esters of phosphoric acid, phosphorous acid, phosphonic acid, phosphinic acid, or phosphonous acid.

* * * * *