



US008311245B2

(12) **United States Patent**
Liu

(10) **Patent No.:** **US 8,311,245 B2**
(45) **Date of Patent:** **Nov. 13, 2012**

(54) **THERMOACOUSTIC MODULE,
THERMOACOUSTIC DEVICE, AND METHOD
FOR MAKING THE SAME**

(75) Inventor: **Liang Liu**, Beijing (CN)

(73) Assignee: **Beijing FUNATE Innovation
Technology Co., Ltd.**, Beijing (CN)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 463 days.

(21) Appl. No.: **12/762,488**

(22) Filed: **Apr. 19, 2010**

(65) **Prior Publication Data**

US 2010/0260359 A1 Oct. 14, 2010

Related U.S. Application Data

(63) Continuation of application No. 12/655,415, filed on Dec. 30, 2009.

(30) **Foreign Application Priority Data**

Dec. 30, 2008	(CN)	2008 1 0191731
Dec. 30, 2008	(CN)	2008 1 0191732
Dec. 30, 2008	(CN)	2008 1 0191739
Dec. 30, 2008	(CN)	2008 1 0191740
Jan. 15, 2009	(CN)	2009 1 0000260
Jan. 15, 2009	(CN)	2009 1 0000261
Jan. 15, 2009	(CN)	2009 1 0000262

(51) **Int. Cl.**
H04R 25/00 (2006.01)

(52) **U.S. Cl.** **381/164**; 381/337

(58) **Field of Classification Search** 381/164,
381/337, 338; 367/140; 62/6; 455/550.1;
977/932

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,528,774 A	3/1925	Kranz
3,982,143 A	9/1976	Tamura et al.
4,002,897 A	1/1977	Kleinman et al.
4,045,695 A	8/1977	Itagaki et al.
4,334,321 A	6/1982	Edelman
4,503,564 A	3/1985	Edelman et al.
4,641,377 A	2/1987	Rush et al.
4,689,827 A	8/1987	Gurney, Jr.
4,766,607 A	8/1988	Feldman
5,694,477 A	12/1997	Kole

(Continued)

FOREIGN PATENT DOCUMENTS

CN	2302622	12/1998
----	---------	---------

(Continued)

OTHER PUBLICATIONS

F. Kontomichos et al ., "A thermoacoustic device for sound reproduction", acoustics 08' Paris, Jun. 29-Jul. 4, 2008.

(Continued)

Primary Examiner — Fan Tsang


Assistant Examiner — Phylesha Dabney

(74) *Attorney, Agent, or Firm* — Altis Law Group, Inc.

(57) **ABSTRACT**

A thermoacoustic module includes a substrate, at least one first electrode, at least one second electrode, a sound wave generator, and at least one spacer. The sound wave generator electrically connect to, span between the at least one first electrode and the at least one second electrode. The at least one first electrode and the at least one second electrode are located on the substrate and provide support to the sound wave generator. The at least one spacer is located on the substrate, between the substrate and the sound wave generator. The at least one spacer supports the sound wave generator. An interval is defined between the sound wave generator and the substrate.

20 Claims, 28 Drawing Sheets



US 8,311,245 B2

Page 2

U.S. PATENT DOCUMENTS			JP		
				49-24593	3/1974
				58-9822	1/1983
6,473,625	B1	10/2002	Williams et al.	58-19491	2/1983
6,777,637	B2	8/2004	Nakayama et al.	60-22900	2/1985
6,803,116	B2	10/2004	Ikeda	61-294786	12/1986
6,808,746	B1	10/2004	Dai et al.	1-255398	10/1989
6,921,575	B2	7/2005	Horiuchi et al.	3-147497	6/1991
7,045,108	B2	5/2006	Jiang et al.	4-126489	4/1992
7,130,436	B1	10/2006	Tabata et al.	6-33390	4/1994
7,366,318	B2	4/2008	Nevill	7-282961	10/1995
7,393,428	B2	7/2008	Huang et al.	8-20868	1/1996
7,474,590	B2	1/2009	Watabe et al.	9-105788	4/1997
7,723,684	B1	5/2010	Haddon et al.	11-282473	10/1999
7,799,163	B1	9/2010	Mau et al.	11-300274	11/1999
2001/0005272	A1	6/2001	Buchholz	2001333493	11/2001
2001/0048256	A1	12/2001	Miyazaki et al.	2002-186097	6/2002
2002/0076070	A1	6/2002	Yoshikawa et al.	2002-352940	12/2002
2003/0038925	A1	2/2003	Choi	2002346996	12/2002
2003/0152238	A1	8/2003	Daly	2002542136	12/2002
2003/0165249	A1	9/2003	Higuchi	2003500325	1/2003
2004/0053780	A1	3/2004	Jiang et al.	2003-154312	5/2003
2005/0006801	A1	1/2005	Kinloch et al.	2003198281	7/2003
2005/0036905	A1	2/2005	Gokturk	2003-266399	9/2003
2005/0040371	A1	2/2005	Watanabe et al.	2003-319490	11/2003
2005/0201575	A1	9/2005	Koshida et al.	2003-319491	11/2003
2006/0072770	A1	4/2006	Miyazaki	2003-332266	11/2003
2006/0104451	A1	5/2006	Browning et al.	2003-343867	12/2003
2006/0147081	A1	7/2006	Mango, III et al.	20042103	1/2004
2006/0264717	A1	11/2006	Pesach et al.	2004-107196	4/2004
2007/0145335	A1	6/2007	Anazawa	2004229250	8/2004
2007/0164632	A1	7/2007	Adachi et al.	2005-20315	1/2005
2007/0166223	A1	7/2007	Jiang et al.	2005-51284	2/2005
2007/0176498	A1	8/2007	Sugiura et al.	2005-73197	3/2005
2008/0063860	A1	3/2008	Song et al.	2005-97046	4/2005
2008/0095694	A1	4/2008	Nakayama et al.	2005189322	7/2005
2008/0170982	A1	7/2008	Zhang et al.	2005-235672	9/2005
2008/0248235	A1	10/2008	Feng et al.	2005-318040	11/2005
2008/0260188	A1	10/2008	Kim	2005-534515	11/2005
2008/0299031	A1	12/2008	Liu et al.	2005-341554	12/2005
2009/0016951	A1	1/2009	Kawabata et al.	2005333601	12/2005
2009/0028002	A1	1/2009	Sugiura et al.	2006-93932	4/2006
2009/0045005	A1	2/2009	Byon et al.	2006-180082	7/2006
2009/0085461	A1	4/2009	Feng et al.	2006-202770	8/2006
2009/0096346	A1	4/2009	Liu et al.	2006-217059	8/2006
2009/0096348	A1	4/2009	Liu et al.	2006270041	10/2006
2009/0145686	A1	6/2009	Watabe et al.	2007-24688	2/2007
2009/0153012	A1	6/2009	Liu et al.	2007-54831	3/2007
2009/0167136	A1	7/2009	Liu et al.	2007-167118	7/2007
2009/0167137	A1	7/2009	Liu et al.	2007-174220	7/2007
2009/0196981	A1	8/2009	Liu et al.	2007-187976	7/2007
2009/0232336	A1	9/2009	Pahl	2007-196195	8/2007
2010/0054502	A1	3/2010	Miyachi	2007-228299	9/2007
2010/0054507	A1	3/2010	Oh et al.	2007-527099	9/2007
2010/0086166	A1	4/2010	Jiang et al.	2008-62644	3/2008
2010/0166232	A1	7/2010	Liu et al.	2008-101910	5/2008
2010/0233472	A1	9/2010	Liu et al.	2008-153042	7/2008
2011/0171419	A1	7/2011	Li et al.	2008-163535	7/2008
				2008-269914	11/2008
FOREIGN PATENT DOCUMENTS			JP		
CN	2425468	3/2001		2009-31031	2/2009
CN	1407392	4/2003		2009-91239	4/2009
CN	1443021	9/2003		2009-94074	4/2009
CN	1698400	11/2005		2009-146896	7/2009
CN	2779422	Y 5/2006		2009-146898	7/2009
CN	1787696	6/2006		2009-164125	7/2009
CN	2787870	6/2006		2009-184907	8/2009
CN	2798479	7/2006		2009-184908	8/2009
CN	1821048	8/2006	KR	10-0761548	9/2007
CN	1886820	12/2006	TW	200726290	7/2007
CN	1944829	4/2007	TW	200740976	11/2007
CN	1982209	6/2007	TW	200744399	12/2007
CN	1997243	7/2007	TW	200833862	8/2008
CN	101239712	8/2008	TW	200950569	12/2009
CN	101284662	10/2008	TW	201029481	8/2010
CN	201150134	11/2008	WO	WO0073204	12/2000
CN	101314464	12/2008	WO	WO2004012932	2/2004
CN	101471213	7/2009	WO	WO2005102924	11/2005
CN	101715155	5/2010	WO	WO2005120130	12/2005
CN	101400198	9/2010	WO	WO2007043837	4/2007
			WO	WO2007049496	5/2007

WO	WO2007052928	5/2007
WO	WO2007099975	9/2007
WO	WO2007111107	10/2007
WO	WO2008/029451	3/2008

OTHER PUBLICATIONS

Lin Xiao et al., "Flexible, stretchable, transparent carbon nanotube thin film loudspeakers" vol. 8, No. 12, pp. 4539-4545, 2008.

Silvanus P. Thompson, The Photophone, Nature, Sep. 23, 1880, vol. XXII, No. 569, pp. 481.

Alexander Graham Bell, Selenium and the Photophone, Nature, Sep. 23, 1880, pp. 500-503.

Lee et al., Photosensitization of nonlinear scattering and photoacoustic emission from single-walled carbon nanotubes, Applied Physics Letters, Mar. 13, 2008, 92, 103122.

P.M. Ajayan et al., "Nanotubes in a flash-Ignition and reconstruction", Science, vol. 296, pp. 705, Apr. 26, 2002.

F.Kontomichos et al., "A thermoacoustic device for sound reproduction", acoustics 08 Paris, pp. 4349-4353, Jun. 29-Jul. 4, 2008.

Chen, Huxiong; Diebold, Gerald, "Chemical Generation of Acoustic Waves: A Giant Photoacoustic Effect", Nov. 10, 1995, Science, vol. 270, pp. 963-966.

Amos, S.W.; "Principles of Transistor Circuits"; 2000; Newnes-Butterworth-Heinemann; 9th ed.;p. 114.

Strutt John William, Rayleigh Baron, The Theory of Sound, 1926, pp. 226-235, vol. 2.

Kai Liu, Yinghui Sun, Lei Chen, Chen Feng, Xiaofeng Feng, Kaili Jiang et al., Controlled Growth of Super-Aligned Carbon Nanotube Arrays for Spinning Continuous Unidirectional Sheets with Tunable Physical Properties, Nano Letters, 2008, pp. 700-705, vol. 8, No. 2.

Yang Wei, Kaili Jiang, Xiaofeng Feng, Peng Liu et al., Comparative studies of multiwalled carbon nanotube sheets before and after shrinking, Physical Review B, Jul. 25, 2007, vol. 76, 045423.

William Henry Preece, On Some Thermal Effects of Electric Currents, Proceedings of the Royal Society of London, 1879-1880, pp. 408-411, vol. 30.

J.J.Hopfield, Spectra of Hydrogen, Nitrogen and Oxygen in the Extreme Ultraviolet, Physical Review, 1922, pp. 573-588, vol. 20. <http://www.physorg.com/news123167268.html>, 2010.

P. De Lange, On Thermophones, Proceedings of the Royal Society of London. Series A, Apr. 1, 1915, pp. 239-241, vol. 91, No. 628.

Edward C. Wente, The Thermophone, Physical Review, 1922, pp. 333-345, vol. 19.

Mei Zhang, Shaoli Fang, Anvar A. Zakhidov, Sergey B. Lee et al., Strong, Transparent, Multifunctional, Carbon Nanotube Sheets, Science, Aug. 19, 2005, pp. 1215-1219, vol. 309.

Braun Ferdinand, Notiz uber Thermophonie, Ann. Der Physik, Apr. 1898, pp. 358-360, vol. 65.

Xiaobo Zhang, Kaili Jiang, Chen Feng, Peng Liu et al., Spinning and Processing Continuous Yarns from 4-Inch Wafer Scale Super-Aligned Carbon Nanotube Arrays, Advanced Materials, 2006, pp. 1505-1510, vol. 18.

Kaili Jiang, Qunqing Li, Shoushan Fan, Spinning continuous carbon nanotube yarns, Nature, Oct. 24, 2002, pp. 801, vol. 419.

Swift Gregory W., Thermoacoustic Engines and Refrigerators, Physics Today, Jul. 1995, pp. 22-28, vol. 48.

H.D. Arnold, I.B. Crandall, The Thermophone as a Precision Source of Sound, Physical Review, 1917, pp. 22-38, vol. 10.

W. Yi L.Lu' Zhang Dianlin et al., Linear Specific Heat of Carbon Nanotubes, Physical Review B, Apr. 1, 1999, vol. 59, No. 14, R9015-9018.

Zhuangchun Wu, Zhihong Chen, Xu Du et al., Transparent, Conductive Carbon Nanotube Films, Science, Aug. 27, 2004, pp. 1273-1276, vol. 305.

Lin Xiao, Zhuo Chen, Chen Feng, Liang Liu et al., Flexible, Stretchable, Transparent Carbon Nanotube Thin Film Loudspeakers, Nano Letters, 2008, pp. 4539-4545, vol. 8, No. 12, US.

Lina Zhang, Chen Feng, Zhuo Chen, Liang Liu et al., Superaligned Carbon Nanotube Grid for High Resolution Transmission Electron Microscopy of Nanomaterials, Nano Letters, 2008, pp. 2564-2569, vol. 8, No. 8.

Frank P. Incropera, David P. Dewitt et al., Fundamentals of Heat and Mass Transfer, 6th ed., 2007, pp. A-5, Wiley:Asia.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30A




FIG. 30B




FIG. 30C




FIG. 31A




FIG. 31B




FIG. 31C




FIG. 31D




FIG. 32




FIG. 33




FIG. 34




FIG. 35




FIG. 36




FIG. 37




FIG. 38




FIG. 39




FIG. 40




FIG. 41




FIG. 42




FIG. 43




FIG. 44




FIG. 45




FIG. 46




FIG. 47




FIG. 48




FIG. 49




FIG. 50




FIG. 51




FIG. 52

**THERMOACOUSTIC MODULE,
THERMOACOUSTIC DEVICE, AND METHOD
FOR MAKING THE SAME**

RELATED APPLICATIONS

This application claims all benefits accruing under 35 U.S.C. §119 from China Patent Application No. 200910000260.8, filed on Jan. 15, 2009; 200910000261.2, filed on Jan. 15, 2009; 200910000262.7, Jan. 15, 2009; 200810191732.8, filed on Dec. 30, 2008; 200810191739.X, filed on Dec. 30, 2008; 200810191731.3, filed on Dec. 30, 2008; 200810191740.2, filed on Dec. 30, 2008, in the China Intellectual Property Office. This application is related to copending application Ser. No. 12/655,375, filed on Dec. 30, 2009, entitled, "THERMOACOUSTIC DEVICE". This application is a continuation of U.S. patent application Ser. No. 12/655,415, filed on Dec. 30, 2009, entitled, "THERMOACOUSTIC MODULE, THERMOACOUSTIC DEVICE, AND METHOD FOR MAKING THE SAME".

BACKGROUND

1. Technical Field

The present disclosure relates to acoustic devices and, particularly, to thermoacoustic modules, thermoacoustic devices and method for making the same.

2. Description of Related Art

An acoustic device generally includes an electrical signal output device and a loudspeaker. The electrical signal output device inputs electrical signals into the loudspeaker. The loudspeaker receives the electrical signals and then transforms them into sounds.

There are different types of loudspeakers that can be categorized according by their working principles, such as electro-dynamic loudspeakers, electromagnetic loudspeakers, electrostatic loudspeakers and piezoelectric loudspeakers. However, the various types ultimately use mechanical vibration to produce sound waves, in other words they all achieve "electro-mechanical-acoustic" conversion. Among the various types, the electro-dynamic loudspeakers are most widely used. However, the electro-dynamic loudspeakers are dependent on magnetic fields and often weighty magnets. The structures of the electric-dynamic loudspeakers are complicated. The magnet of the electric-dynamic loudspeakers may interfere or even destroy other electrical devices near the loudspeakers.

Thermoacoustic effect is a conversion of heat to acoustic signals. The thermoacoustic effect is distinct from the mechanism of the conventional loudspeaker, which the pressure waves are created by the mechanical movement of the diaphragm. When signals are inputted into a thermoacoustic element, heating is produced in the thermoacoustic element according to the variations of the signal and/or signal strength. Heat is propagated into surrounding medium. The heating of the medium causes thermal expansion and produces pressure waves in the surrounding medium, resulting in sound wave generation. Such an acoustic effect induced by temperature waves is commonly called "the thermoacoustic effect".

A thermophone based on the thermoacoustic effect was created by H. D. Arnold and I. B. Crandall (H. D. Arnold and I. B. Crandall, "The thermophone as a precision source of sound", Phys. Rev. 10, pp 22-38 (1917)). They used platinum strip with a thickness of 7×10^{-5} cm as a thermoacoustic element. The heat capacity per unit area of the platinum strip with the thickness of 7×10^{-5} cm is 2×10^{-4} J/cm²*K. How-

ever, the thermophone adopting the platinum strip, listened to the open air, sounds extremely weak because the heat capacity per unit area of the platinum strip is too high.

Carbon nanotubes (CNT) are a novel carbonaceous material having extremely small size and extremely large specific surface area. Carbon nanotubes have received a great deal of interest since the early 1990s, and have interesting and potentially useful electrical and mechanical properties, and have been widely used in a plurality of fields. Fan et al. discloses a thermoacoustic device with simpler structure and smaller size, working without the magnet in an article of "Flexible, Stretchable, Transparent Carbon Nanotube Thin Film Loudspeakers", Fan et al., Nano Letters, Vol. 8 (12), 4539-4545 (2008). The thermoacoustic device includes a sound wave generator which is a carbon nanotube film. The carbon nanotube film used in the thermoacoustic device has a large specific surface area, and extremely small heat capacity per unit area that make the sound wave generator emit sound audible to humans. The sound has a wide frequency response range. Accordingly, the thermoacoustic device adopted the carbon nanotube film has a potential to be actually used instead of the loudspeakers in prior art.

However, the carbon nanotube film used in the thermoacoustic device has a small thickness and a large area, and is likely to be damaged by the external forces applied thereon.

What is needed, therefore, is to provide a thermoacoustic device with a protected carbon nanotube film and a high efficiency while maintaining an efficient thermoacoustic effect.

BRIEF DESCRIPTION OF THE DRAWINGS

Many aspects of the embodiments can be better understood with references to the following drawings. The components in the drawings are not necessarily drawn to scale, the emphasis instead being placed upon clearly illustrating the principles of the embodiments. Moreover, in the drawings, like reference numerals designate corresponding parts throughout the several views.

FIG. 1 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 2 is a schematic top plan view of the thermoacoustic module shown in FIG. 1.

FIG. 3 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 4 shows a Scanning Electron Microscope (SEM) image of a drawn carbon nanotube film.

FIG. 5 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 6 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 7 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 8 is a cross-sectional view of the thermoacoustic module shown in FIG. 7.

FIG. 9 is a cross-sectional view of one embodiment of a thermoacoustic module having half-sphere shaped grooves.

FIG. 10 is a cross-sectional view of one embodiment of a thermoacoustic module having V-sphere shaped grooves.

FIG. 11 is a cross-sectional view of one embodiment of a thermoacoustic module having sawtooth shaped grooves.

FIG. 12 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 13 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 14 is a front view of one embodiment of a thermoacoustic module.

FIG. 15 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 16 is a schematic top plan view of the thermoacoustic module shown in FIG. 15.

FIG. 17 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 18 is a cross-sectional view taken along a line 18-18 of the thermoacoustic module shown in FIG. 17.

FIG. 19 is a cross-sectional view taken along a line of 19-19 of the thermoacoustic module shown in FIG. 48.

FIG. 20 is a cross-sectional view taken along a line 20-20 of the thermoacoustic module shown in FIG. 52.

FIG. 21 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 22 is a cross-sectional view taken along a line 22-22 of the thermoacoustic module shown in FIG. 21.

FIG. 23 is a schematic front view of one embodiment of a thermoacoustic module.

FIG. 24 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 25 is a cross-sectional view taken along a line 25-25 of the thermoacoustic module shown in FIG. 24.

FIG. 26 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 27 is a cross-sectional view taken along a line 27-27 of the thermoacoustic module shown in FIG. 26.

FIG. 28 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 29 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIGS. 30A to 30C are cross-sectional views of one screen-printing embodiment for making a thermoacoustic module.

FIGS. 31A to 31D are cross-sectional views of one screen-printing embodiment for making a thermoacoustic module.

FIG. 32 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 33 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 34 is a schematic top plan view of the thermoacoustic module shown in FIG. 33.

FIG. 35 is a cross-sectional view of one embodiment of a thermoacoustic module.

FIG. 36 is an exploded view of one embodiment of a thermoacoustic module.

FIG. 37 is a schematic view of one embodiment of a thermoacoustic device.

FIG. 38 is an exploded view of the thermoacoustic device shown in FIG. 37.

FIG. 39 is a cross-sectional view taken along a line 39-39 of the thermoacoustic module shown in FIG. 37.

FIG. 40 is a cross-sectional view of one embodiment of a thermoacoustic device.

FIG. 41 is a cross-sectional view of one embodiment of a thermoacoustic device.

FIG. 42 is a schematic view of one embodiment of a thermoacoustic device.

FIG. 43 is an exploded view of the thermoacoustic device shown in FIG. 42.

FIG. 44 is a cross-sectional view taken along a line 44-44 of the thermoacoustic device shown in FIG. 42.

FIG. 45 is a partially enlarged view of section 45 of the thermoacoustic device shown in FIG. 44.

FIG. 46 is a cross-sectional view of one embodiment of a thermoacoustic device.

FIG. 47 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 48 is a schematic top plan view of one embodiment of a thermoacoustic module.

FIG. 49 is a schematic view of a carbon nanotube with four layers of conductive material thereon.

FIG. 50 shows an SEM image of a carbon nanotube composite film.

FIG. 51 shows a Transmission Electron Microscope (TEM) image of a carbon nanotube-conductive material composite.

FIG. 52 is a schematic top plan view of one embodiment of a thermoacoustic module.

DETAILED DESCRIPTION

Thermoacoustic Device

A thermoacoustic device in one embodiment comprises of a thermoacoustic module, and the thermoacoustic module comprises of a sound wave generator 204. The sound wave generator 204 is capable of producing sounds by a thermoacoustic effect.

Sound Wave Generator

The sound wave generator 204 has a very small heat capacity per unit area. The heat capacity per unit area of the sound wave generator 204 is less than $2 \times 10^{-4} \text{ J/cm}^2 \cdot \text{K}$. The sound wave generator 204 can be a conductive structure with a small heat capacity per unit area and a small thickness. The sound wave generator 204 can have a large specific surface area for causing the pressure oscillation in the surrounding medium by the temperature waves generated by the sound wave generator 204. The sound wave generator 204 can be a free-standing structure. The term "free-standing" includes, but is not limited to, a structure that does not have to be supported by a substrate and can sustain the weight of it when it is hoisted by a portion thereof without any significant damage to its structural integrity. The suspended part of the sound wave generator 204 will have more sufficient contact with the surrounding medium (e.g., air) to have heat exchange with the surrounding medium from both sides of the sound wave generator 204. The sound wave generator 204 is a thermoacoustic film.

The sound wave generator 204 can be or include a free-standing carbon nanotube structure. The carbon nanotube structure may have a film structure. The thickness of the carbon nanotube structure may range from about 0.5 nanometers to about 1 millimeter. The carbon nanotubes in the carbon nanotube structure are combined by van der Waals attractive force therebetween. The carbon nanotube structure has a large specific surface area (e.g., above $30 \text{ m}^2/\text{g}$). The larger the specific surface area of the carbon nanotube structure, the smaller the heat capacity per unit area will be. The smaller the heat capacity per unit area, the higher the sound pressure level of the sound produced by the sound wave generator 204.

The carbon nanotube structure can include at least one carbon nanotube film.

The carbon nanotube film can be a flocculated carbon nanotube film formed by a flocculating method. The flocculated carbon nanotube film can include a plurality of long, curved, disordered carbon nanotubes entangled with each other. A length of the carbon nanotubes can be greater than 10 centimeters. Further, the flocculated carbon nanotube film can be isotropic. The carbon nanotubes can be substantially uniformly distributed in the carbon nanotube film. The adjacent carbon nanotubes are acted upon by the van der Waals attractive force therebetween, thereby forming an entangled structure with micropores defined therein. It is understood

that the flocculated carbon nanotube film is very porous. Sizes of the micropores can be less than 10 micrometers. The porous nature of the flocculated carbon nanotube film will increase specific surface area of the carbon nanotube structure. The flocculated carbon nanotube film, in some embodiments, will not require the use of structural support due to the carbon nanotubes being entangled and adhered together by van der Waals attractive force therebetween.

The carbon nanotube film can also be a drawn carbon nanotube film formed by drawing a film from a carbon nanotube array that is capable of having a film drawn therefrom. The heat capacity per unit area of the drawn carbon nanotube film can be less than or equal to about 1.7×10^{-6} J/cm²*K. The drawn carbon nanotube film can have a large specific surface area (e.g., above 100 m²/g). In one embodiment, the drawn carbon nanotube film has a specific surface area in the range of about 200 m²/g to about 2600 m²/g. In one embodiment, the drawn carbon nanotube film has a specific weight of about 0.05 g/m².

The thickness of the drawn carbon nanotube film can be in a range from about 0.5 nanometers to about 50 nanometers. When the thickness of the drawn carbon nanotube film is small enough (e.g., smaller than 10 μm), the drawn carbon nanotube film is substantially transparent.

Referring to FIG. 4, the drawn carbon nanotube film includes a plurality of successive and oriented carbon nanotubes joined end-to-end by van der Waals attractive force therebetween. The carbon nanotubes in the drawn carbon nanotube film can be substantially aligned along a single direction and substantially parallel to the surface of the carbon nanotube film. As can be seen in FIG. 4, some variations can occur in the drawn carbon nanotube film. The drawn carbon nanotube film is a free-standing film. The drawn carbon nanotube film can be formed by drawing a film from a carbon nanotube array that is capable of having a carbon nanotube film drawn therefrom.

The carbon nanotube structure can include more than one carbon nanotube films. The carbon nanotube films in the carbon nanotube structure can be coplanar and/or stacked. Coplanar carbon nanotube films can also be stacked one upon other coplanar films. Additionally, an angle can exist between the orientation of carbon nanotubes in adjacent films, stacked and/or coplanar. Adjacent carbon nanotube films can be combined by only the van der Waals attractive force therebetween without the need of an additional adhesive. The number of the layers of the carbon nanotube films is not limited. However, as the stacked number of the carbon nanotube films increases, the specific surface area of the carbon nanotube structure will decrease. A large enough specific surface area (e.g., above 30 m²/g) must be maintained to achieve an acceptable acoustic volume. An angle between the aligned directions of the carbon nanotubes in the two adjacent drawn carbon nanotube films can range from about 0 degrees to about 90 degrees. Spaces are defined between two adjacent carbon nanotubes in the drawn carbon nanotube film. When the angle between the aligned directions of the carbon nanotubes in adjacent drawn carbon nanotube films is larger than 0 degrees, a microporous structure is defined by the carbon nanotubes in the sound wave generator 204. The carbon nanotube structure in an embodiment employing these films will have a plurality of micropores. Stacking the carbon nanotube films will add to the structural integrity of the carbon nanotube structure.

In some embodiments, the sound wave generator 204 is a single drawn carbon nanotube film drawn from the carbon nanotube array. The drawn carbon nanotube film has a thickness of about 50 nanometers, and has a transmittance of visible lights in a range from 67% to 95%.

In other embodiments, the sound wave generator 204 can be or include a free-standing carbon nanotube composite structure. The carbon nanotube composite structure can be formed by depositing at least a conductive layer on the outer surface of the individual carbon nanotubes in the above-described carbon nanotube structure. The carbon nanotubes can be individually coated or partially covered with conductive material. Thereby, the carbon nanotube composite structure can inherit the properties of the carbon nanotube structure such as the large specific surface area, the high transparency, the small heat capacity per unit area. Further, the conductivity of the carbon nanotube composite structure is greater than the pure carbon nanotube structure. Thereby, the driven voltage of the sound wave generator 204 using a coated carbon nanotube composite structure will be decreased. The conductive material can be placed on the carbon nanotubes by using a method of vacuum evaporation, sputtering, chemical vapor deposition (CVD), electroplating, or electroless plating. A microscopic view of the carbon nanotube composite structure formed from a single drawn carbon nanotube film with layers of conductive material thereon is shown in FIGS. 50 and 51.

The material of the conductive material can comprise of iron (Fe), cobalt (Co), nickel (Ni), palladium (Pd), titanium (Ti), copper (Cu), silver (Ag), gold (Au), platinum (Pt), and combinations thereof. The thickness of the layer of conductive material can be ranged from about 1 nanometer to about 100 nanometers. In some embodiments, the thickness of the layer of conductive material can be less than about 20 nanometers. More specifically, referring to FIG. 49, the at least one layer of conductive material 112 can, from inside to outside, include a wetting layer 1122, a transition layer 1124, a conductive layer 1126, and an anti-oxidation layer 1128. The wetting layer 1122 is the innermost layer and contactingly covers the surface of the carbon nanotube 111. The transition layer 1124 enwraps the wetting layer 1122. The conductive layer 1126 enwraps the transition layer 1124. The anti-oxidation layer 1128 enwraps the conductive layer 1126. The wetting layer 1122 wets the carbon nanotubes 111. The transition layer 1124 wets both the wetting layer 1122 and the conductive layer 1126, thus combining the wetting layer 1122 with the conductive layer 1126. The conductive layer 1126 has high conductivity. The anti-oxidation layer 1128 prevents the conductive layer 1126 from being oxidized by exposure to the air and prevents reduction of the conductivity of the carbon nanotube composite film.

In one embodiment, the carbon nanotube structure is a drawn carbon nanotube film, the at least one layer of conductive material 112 comprises a Ni layer located on the outer surface of the carbon nanotube 111 and is used as the wetting layer 1122. An Au layer is located on the Ni layer and used as the conductive layer 1126. The thickness of the Ni layer is about 2 nanometers. The thickness of the Au layer is about 15 nanometers.

The sound wave generator 204 has a small heat capacity per unit area, and a large surface area for causing the pressure oscillation in the surrounding medium by the temperature waves generated by the sound wave generator 204. In use, when electrical or electromagnetic wave signals 250, with variations in the application of the signals and/or strength applied to the sound wave generator 204, repeated heating is produced by the sound wave generator 204 according to the variations of the signals and/or signal strength. Temperature waves, which are propagated into surrounding medium, are obtained. The temperature waves produce pressure waves in the surrounding medium, resulting in sound generation. In this process, it is the thermal expansion and contraction of the

medium in the vicinity of the sound wave generator **204** that produces sound. This is distinct from the mechanism of the conventional loudspeaker, in which the pressure waves are created by the mechanical movement of the diaphragm. There is an “electrical-thermal-sound” conversion when the electrical signals are applied on the sound wave generator **204** through electrodes **206**, **216**; and there is an “optical-thermal-sound” conversion when electromagnetic wave signals **250** emitted from an electromagnetic wave device **240** are applied on the sound wave generator **204**. The conversions of “electrical-thermal-sound” and “optical-thermal-sound” are all belonged to a thermoacoustic principle.

Electrode

The thermoacoustic module can further include at least one first electrode **206** and at least one second electrode **216**. The first electrode **206** and the second electrode **216** are in electrical contact with the sound wave generator **204**, and input electrical signals into the sound wave generator **204**.

The first electrode **206** and the second electrode **216** are made of conductive material. The shape of the first electrode **206** or the second electrode **216** is not limited and can be lamellar, rod, wire, and block among other shapes. A material of the first electrode **206** or the second electrode **216** can be metals, conductive adhesives, carbon nanotubes, and indium tin oxides among other conductive materials. The first electrode **206** and the second electrode **216** can be metal wire or conductive material layers, such as metal layers formed by a sputtering method, or conductive paste layers formed by a method of screen-printing.

The first electrode **206** and the second electrode **216** can be electrically connected to two terminals of an electrical signal input device (such as a MP3 player) by a conductive wire. Thereby, electrical signals output from the electrical signal device can be input into the sound wave generator **204** through the first and second electrodes **206**, **216**.

A conductive adhesive layer can be further provided between the first and second electrodes **206**, **216** and the sound wave generator **204**. The conductive adhesive layer can be applied to a surface of the sound wave generator **204**. The conductive adhesive layer can be used to provide better electrical contact and attachment between the first and second electrodes **206**, **216** and the sound wave generator **204**. In one embodiment, the conductive adhesive layer is a layer of silver paste.

In one embodiment, the sound wave generator **204** is a drawn carbon nanotube film drawn from the carbon nanotube array, and the carbon nanotubes in the carbon nanotube film are aligned along a direction from the first electrode **206** to the second electrode **216**. The first electrode **206** and the second electrode **216** can both have a length greater than or equal to the carbon nanotube film width.

In one embodiment, the thermoacoustic module can include a plurality of alternatively arranged first and second electrodes **206**, **216**. The first electrodes **206** and the second electrodes **216** can be arranged as a staggered manner of +--+-. All the first electrodes **206** are electrically connected together, and all the second electrodes **216** are electrically connected together, whereby the sections of the sound wave generator **204** between the adjacent first electrode **206** and the second electrode **216** are in parallel. An electrical signal is conducted in the sound wave generator **204** from the first electrodes **206** to the second electrodes **216**. By placing the sections in parallel, the resistance of the thermoacoustic module is decreased. Therefore, the driving voltage of the thermoacoustic module can be decreased with the same effect.

The first electrodes **206** and the second electrodes **216** can be substantially parallel to each other with a same distance

between the adjacent first electrode **206** and the second electrode **216**. In some embodiments, the distance between the adjacent first electrode **206** and the second electrode **216** can be in a range from about 1 millimeter to about 3 centimeters.

To connect all the first electrodes **206** together, and connect all the second electrodes **216** together, first conducting member **3210** and second conducting member **3212** can be arranged. Referring to FIG. **47**, all the first electrodes **206** are connected to the first conducting member **3210**. All the second electrodes **216** are connected to the second conducting member **3212**. The sound wave generator **204** is divided by the first and second electrodes **206**, **216** into many sections. The sections of the sound wave generator **204** between the adjacent first electrode **206** and the second electrode **216** are in parallel. An electrical signal is conducted in the sound wave generator **204** from the first electrodes **206** to the second electrodes **216**.

The first conducting member **3210** and the second conducting member **3212** can be made of the same material as the first and second electrodes **206**, **216**, and can be perpendicular to the first and second electrodes **206**, **216**.

Thermoacoustic Device Using Photoacoustic Effect

In one embodiment, when the input signal is electromagnetic wave signal **250**, the signal can be directly incident to the sound wave generator **204** but not through the first and second electrodes **206**, **216**, and the thermoacoustic device works under a photoacoustic effect. The photoacoustic effect is a kind of the thermoacoustic effect and a conversion between light and acoustic signals due to absorption and localized thermal excitation. When rapid pulses of light are incident on a sample of matter, the light can be absorbed and the resulting energy will then be radiated as heat. This heat causes detectable sound signals due to pressure variation in the surrounding (i.e., environmental) medium. Referring to FIG. **14**, a thermoacoustic device according to an embodiment includes a thermoacoustic module **100** and an electromagnetic signal input device which is an electromagnetic wave device **240**.

The thermoacoustic module **100** includes a substrate **202**, and a sound wave generator **204**, but without the first and second electrodes **206**, **216**. In the embodiment shown in FIG. **14**, the substrate **202** has a top surface **230**, and includes at least one recess **208** located on the top surface **230**. The recess **208** defines an opening on the top surface **230**. The sound wave generator **204** is located on the top surface **230** of the substrate **202** and covers the opening of the recess **208**. The sound wave generator **204** includes at least one first region **210**, and at least one second region **220**. Each opening of the at least one recess **208** is covered by one of the first region **210**. The second region **220** of the sound wave generator **204** is in contact with the surface **230** and supported by the substrate **202**.

The electromagnetic wave device **240** is capable of inducing heat energy in the sound wave generator **204** thereby producing a sound by the principle of thermoacoustic.

The electromagnetic wave device **240** can be located apart from the sound wave generator **204**. The electromagnetic wave device **240** can be a laser-producing device, a light source, or an electromagnetic signal generator. The electromagnetic wave device **240** can transmit electromagnetic wave signals **250** (e.g., laser signals and normal light signals) to the sound wave generator **204**.

The average power intensity of the electromagnetic wave signals **250** can be in the range from about $1 \mu\text{W}/\text{mm}^2$ to about $20 \text{W}/\text{mm}^2$. It is to be understood that the average power intensity of the electromagnetic wave signals **250** must be high enough to cause the sound wave generator **204** to heat the

surrounding medium, but not so high that the sound wave generator **204** is damaged. In some embodiments, the electromagnetic signal generator **240** is a pulse laser generator (e.g., an infrared laser diode). In other embodiments, the thermoacoustic device can further include a focusing element such as a lens (not shown). The focusing element focuses the electromagnetic wave signals **250** on the sound wave generator **204**. Thus, the average power intensity of the original electromagnetic wave signals **250** can be lowered.

The incident angle of the electromagnetic wave signals **250** on the sound wave generator **204** is arbitrary. In some embodiments, the electromagnetic wave signal's direction of travel is perpendicular to the surface of the carbon nanotube structure. The distance between the electromagnetic signal generator **240** and the sound wave generator **204** is not limited as long as the electromagnetic wave signal **250** is successfully transmitted to the sound wave generator **204**.

In the embodiment shown in FIG. **14**, the electromagnetic wave device **240** is a laser-producing device. The laser-producing device is located apart from the sound wave generator **204** and faces to the sound wave generator **204**. The laser-producing device can emit a laser. The laser-producing device faces to the sound wave generator **204**. In other embodiments, when the substrate **202** is made of transparent materials, the laser-producing device can be disposed on either side of the substrate **202**. The laser signals produced by the laser-producing device can transmit through the substrate **202** to the sound wave generator **204**.

The thermoacoustic device can further include a modulating device **260** disposed in the transmitting path of the electromagnetic wave signals **250**. The modulating device **260** can include an intensity modulating element and/or a frequency modulating element. The modulating device **260** modulates the intensity and/or the frequency of the electromagnetic wave signals **250** to produce variation in heat. In detail, the modulating device **260** can include an on/off controlling circuit to control the on and off of the electromagnetic wave signal **250**. In other embodiments, the modulating device **260** can directly modulate the intensity of the electromagnetic wave signal **250**. The modulating device **260** and the electromagnetic signal device can be integrated, or spaced from each other. In one embodiment, the modulating device **260** is an electro-optical crystal.

The sound wave generator **204** absorbs the electromagnetic wave signals **250** and converts the electromagnetic energy into heat energy. The heat capacity per unit area of the carbon nanotube structure is extremely small, and thus, the temperature of the carbon nanotube structure can change rapidly with the input electromagnetic wave signals **250** at the substantially same frequency as the electromagnetic wave signals **250**. Thermal waves, which are propagated into surrounding medium, are obtained. Therefore, the surrounding medium, such as ambient air, can be heated at an equal frequency as the input of electromagnetic wave signal **250** to the sound wave generator **204**. The thermal waves produce pressure waves in the surrounding medium, resulting in sound wave generation. In this process, it is the thermal expansion and contraction of the medium in the vicinity of the sound wave generator **204** that produces sound. The operating principle of the sound wave generator **204** is the "optical-thermal-sound" conversion.

Referring to FIG. **23**, in other embodiments, the thermoacoustic module **100** includes a substrate **202**, a plurality of spacers **218**, a sound wave generator **204**. The spacers **218** are located apart from each other on the substrate **202**. The sound wave generator **204** is located on and supported by the spacers **218**. A plurality of spaces are defined between the sound wave

generator **204**, the spacers **218** and the substrate **202**. The sound wave generator **204** includes at least one first region **210**, and at least one second region **220**. The first region **210** is suspended while the second region **220** is in contact with and supported by the spacer **218**.

Substrate

Referring to FIG. **1**, the thermoacoustic module **100** can further include a substrate **202**, the sound wave generator **204** can be disposed on the substrate **202**. The shape, thickness, and size of the substrate **202** is not limited. A top surface **230** of the substrate **202** can be planar or have a curve. A material of the substrate **202** is not limited, and can be a rigid or a flexible material. The resistance of the substrate **202** is greater than the resistance of the sound wave generator **204** to avoid a short through the substrate **202**. The substrate **202** can have a good thermal insulating property, thereby preventing the substrate **202** from absorbing the heat generated by the sound wave generator **204**. The material of the substrate **202** can be selected from suitable materials including, plastics, ceramics, diamond, quartz, glass, resin and wood. In one embodiment, the substrate **202** is glass square board with a thickness of the glass square board is about 20 millimeters and a length of each side of the substrate **202** is about 17 centimeters.

Drawn carbon nanotube film has a large specific surface area, and thus it is adhesive in nature. Therefore, the carbon nanotube film can directly adhere with the top surface **230** of the substrate **202**. Once the carbon nanotube film is adhered to the top surface **230** of the substrate **202**, the carbon nanotube film can be treated with a volatile organic solvent. Specifically, the carbon nanotube film can be treated by applying the organic solvent to the carbon nanotube film to soak the entire surface of the carbon nanotube film. The organic solvent is volatile and can be, for example, ethanol, methanol, acetone, dichloroethane, chloroform, any appropriate mixture thereof. In one embodiment, the organic solvent is ethanol. After being soaked by the organic solvent, carbon nanotube strings will be formed by adjacent carbon nanotubes in the carbon nanotube film, that are able to do so, bundling together, due to the surface tension of the organic solvent when the organic solvent volatilizes. After the organic solvent volatilizes, the contact area of the carbon nanotube film with the top surface **230** of the substrate **202** will increase, and thus, the carbon nanotube film will more firmly adhere to the top surface **230** of the substrate **202**. In another aspect, due to the decrease of the specific surface area via bundling, the mechanical strength and toughness of the carbon nanotube film is increased. Macroscopically, after the organic solvent treatment, the carbon nanotube film will remain an approximately uniform film.

It is to be understood that, though the carbon nanotube film is adhesive in nature, an adhesive can also be used to adhere the carbon nanotube film with the substrate **202**. In one embodiment, an adhesive layer or binder points can be located on the surface of the substrate **202**. The sound wave generator **204** can be adhered on the substrate **202** via the binder layer or binder points. It is to be noted that, the sound wave generator **204** can be fixed on the top surface **230** of the substrate **202** by other means, even if the sound wave generator **204** does not directly contact with the top surface **230** of the substrate **202**.

Referring to FIG. **1**, the substrate **202** can further defines at least one recess **208** through the top surface **230**. By provision of the recess **208**, the sound wave generator **204** is divided into at least one first region **210**, suspended above the recess **208**, and at least one second region **220**, in contact with the top surface **230** of the substrate **202**. There can be more than one first region **210** and/or more than one second region **220**.

11

The first region **210** and the second region **220** both include a plurality of carbon nanotubes. The drawn carbon nanotube film is located on the top surface **230** of the substrate **202** and covers the openings defined by the recesses **208**.

The first region **210** of the sound wave generator **204** is suspended over the recess **208**. Therefore, the carbon nanotube structure in the first region **210** of the sound wave generator **204** can have greater contact and heat exchange with the surrounding medium than the second region **220**. Thus, the electrical-sound transforming efficiency of the thermoacoustic module **100** can be greater than when the entire sound wave generator **204** is in contact with the top surface **230** of the substrate **202**. The second region **220** of the sound wave generator **204** is in contact with the top surface **230**, and supported via the substrate **202**. Therefore, the carbon nanotube structure of the sound wave generator **204** is supported and protected.

According to different materials of the substrate **202**, the recess **208** can be formed by mechanical methods or chemical methods, such as cutting, burnishing, or etching. The substrate **202** having the recess **208** can also be achieved by using a mold with a predetermined shape.

The recess **208** can be a through groove (i.e., the recess **208** goes all the way through the substrate **202**), a through hole, a blind groove (i.e., a depth of the recess **208** is less than a thickness of the substrate **202**), a blind hole.

Referring to FIGS. **1** and **2**, in one embodiment, the recess **208** is a through groove. The opening defined by the recess **208** at the top surface **230** of the substrate **202** can be rectangular, polygon, flat circular, I-shaped, or any other shape. Each one of the first regions **210** covers the opening defined by each one of the recesses **208** on the top surface **230** of the substrate **202**. The recesses **208** can be parallel to each other with a distance $d1$ between every two adjacent recesses **208**. The distance $d1$ can be greater than about 100 microns (μm). In one embodiment, the recesses **208** have rectangular strip shaped openings (shown in FIG. **2**) at the top surface **230** of the substrate **202**, a width of the recess **208** is about 1 millimeter (mm), and the through groove recesses **208** are parallel to each other with a same distance of about 1 mm between every two adjacent through groove recesses **208**.

Referring to FIG. **3**, in one embodiment, each recess **208** is a round through hole. The diameter of the through hole can be about 0.5 μm . A distance $d2$ between two adjacent recesses **208** can be larger than 100 μm . An opening defined by the recess **208** at the top surface **230** of the substrate **202** can be round. It is to be understood that the opening defined by the recess **208** can also have be rectangular, triangle, polygon, flat circular, I-shaped, or any other shape. In other embodiments, the substrate **202** has a top surface **230** and includes at least one recess **208** located on the top surface **230**. The recess **208** has a closed end. Referring to FIGS. **7** and **8**, the recesses **208** can be blind grooves. The opening defined by the blind grooves on the top surface **230** of the substrate **202** can be rectangular, polygon, flat circular, I-shape, or other shape.

In one embodiment, the substrate **202** includes a plurality of blind grooves having rectangular strip shaped openings on the top surface **230** of the substrate **202**. The blind grooves are parallel to each other and located apart from each other for the same distance $d3$. The width of the blind grooves is about 1 millimeter. The distance $d3$ is about 1 millimeter.

When the depth of the blind grooves or holes is greater than about 10 millimeters, the sound waves reflected by the bottom surface of the blind grooves may have a superposition with the original sound waves, which may lead to an interference cancellation. To reduce this impact, the depth of the blind grooves that can be less than about 10 millimeters. In another

12

aspect, when the depth of the blind grooves is less than 10 microns, the heat generated by the sound wave generator **204** would be dissipated insufficiently. To reduce this impact, the depth of the blind grooves and holes can be greater than 10 microns.

Alternatively, the cross-section along a direction perpendicular to the length direction of the blind grooves can be a semicircle **208a** shown in FIG. **9**. Referring to FIG. **10**, the cross-section along the direction perpendicular to the length direction of the blind grooves **1** can be a triangle labeled as **208b**, and the distance $d3$ can be about 1 millimeter. Referring to FIG. **11**, the cross-section along a direction perpendicular to the length direction of the blind grooves **208c** can also be a triangle, while the distance $d3=0$. Therefore, in the embodiment shown in FIG. **11**, the regions of the surface **230** that in contact with the sound wave generator **204** are a plurality of lines. In other embodiments, the regions of the top surface **230** that in contact with the sound wave generator **204** can also be a plurality of points. In summary, the sound wave generator **204** and the top surface **230** of the substrate **202** can be in point-contacts, line-contacts, and/or multiple surface-contacts.

The blind grooves can reflect sound waves produced by the sound wave generator **204**, and increase the sound pressure at the side of the substrate **202** that has the blind grooves. By decreasing the distance between adjacent blind grooves, the first region **210** is increased.

Referring to FIG. **12**, in other embodiments, the opening of the recess **208d** has a spiral shape. Alternatively, the openings of the recess **208e** can have a zigzag shape shown in FIG. **13**. The recesses **208d** can be a through and/or blind groove and/or hole. It is to be understood that the opening can also have other shapes.

In other embodiment, the recesses **208a** can be blind holes as shown in FIG. **9**. The openings defined by the blind holes on the top surface **230** of the substrate **202** can be rectangles, triangles, polygons, flat circulars, I-shapes, or other shapes.

In the embodiment shown in FIGS. **1** to **3** and **7** to **13**, the sound wave generator **204** is located between the electrodes **206**, **216** and the substrate **202**, the first electrode **206** and the second electrode **216** are located on a top surface of the sound wave generator **204**. The first electrode **206** and the second electrode **216** can be metal wires parallel with each other and located on the top surface of the sound wave generator **204**. The first electrode **206** and the second electrode **216** can be fixed to the sound wave generator **204**.

It is to be understood that the first and second electrodes **206**, **216** can also disposed between the substrate **202** and the sound wave generator **204**. Referring to FIG. **5**, in other embodiments, the sound wave generator **204** is located on the top surface **230** and covers the recesses **208** and the electrodes **206**, **216**. In one embodiment, the first electrode **206** and the second electrode **216** are silver paste layers formed on the top surface **230** by a method of screen-printing. Referring to FIG. **6**, in other embodiments, there can also be more than one first electrodes **206** and more than one second electrodes **216** located on the top surface **230** of the substrate **202**, the first electrodes **206** and the second electrodes **216** are arranged as the staggered manner of $+-+-$.

Spacers

The sound wave generator **204** can be disposed on or separated from the substrate **202**. To separate the sound wave generator **204** from the substrate **202**, the thermoacoustic module can further include one or some spacers **218**. The spacer **218** is located on the substrate **202**, and the sound wave generator **204** is located on and partially supported by the spacer **218**. An interval space is defined between the sound

wave generator **204** and the substrate **202**. Thus, the sound wave generator **204** can be sufficiently exposed to the surrounding medium and transmit heat into the surrounding medium, therefore the efficiency of the thermoacoustic module can be greater than having the entire sound wave generator **204** contacting with the top surface **230** of the substrate **202**.

Referring to FIGS. **15** and **16**, in one embodiment, a thermoacoustic module includes a substrate **202**, a first electrode **206**, a second electrode **216**, a spacer **218** and a sound wave generator **204**.

The first electrode **206** and the second electrode **216** are located apart from each other on the substrate **202**. The spacer **218** is located on the substrate **202** between the first electrode **206** and the second electrode **216**. The sound wave generator **204** is located on and supported by the spacer **218** and spaced from the substrate **202**. The sound wave generator **204** has a bottom surface **2042** and a top surface **2044** opposite to the bottom surface **2042**. The spacer **218**, the first electrode **206** and the second electrode **216** are located between the bottom surface **2042** and the substrate **202**.

The electrodes **206**, **216** can also provide structural support for the sound wave generator **204**. A height of the first electrode **206** or the second electrode **216** can range from about 10 microns to about 1 centimeter.

In an embodiment, the first electrode **206** and the second electrode **216** are linear shaped silver paste layers. The linear shaped silver paste layers have a height of about 20 microns. The linear shaped silver paste layers are formed on the substrate **202** via a screen-printing method. The first electrode **206** and the second electrode **216** can be parallel with each other.

The spacer **218** is located on the substrate **202**, between the first electrode **206** and the second electrode **216**. The spacer **218**, first electrode **206** and the second electrode **216** support the sound wave generator **204** and space the sound wave generator **204** from the substrate **202**. An interval space **2101** is defined between the sound wave generator **204** and the substrate **202**. Thus, the sound wave generator **204** can be sufficiently exposed to the surrounding medium and transmit heat into the surrounding medium.

The spacer **218** can be integrated with the substrate **202** or separate from the substrate **202**. The spacer **218** can be attached to the substrate **202** via a binder. The shape of the spacer **218** is not limited and can be dot, lamellar, rod, wire, and block among other shapes. When the spacer **218** has a linear shape such as a rod or a wire, the spacer **218** can parallel to the electrodes **206**, **216**. To increase the contacting area of the carbon nanotube structure of the sound wave generator **204**, the spacer **218** and the sound wave generator **204** can be line-contacts or point-contacts.

A material of the spacer **218** can be conductive materials such as metals, conductive adhesives, and indium tin oxides among other materials. The material of the spacer **218** can also be insulating materials such as glass, ceramic, or resin. A height of the spacer **218** substantially equal to or smaller than the height of the electrodes **206**, **216**. The height of the spacer **218** is in a range from about 10 microns to about 1 centimeter.

In some embodiments, the spacer **218** is a silver paste line being the same as the first electrode **206** and second electrode **216**, formed via a screen-printing method at the same time. The spacer **218** can also be fixed on the substrate **202** by other means, such as by using a binder or a screw.

Additionally, the first and second electrodes **206**, **216** can be formed at the same time as the spacers **218**. In one embodiment, the spacer **218**, the first electrode **206** and the second electrode **216** are parallel with each other, and have the same height of about 20 microns. The sound wave generator **204**

can be planar and be supported by the spacer **218**, the first electrode **206** and the second electrode **216** having the same height.

The sound wave generator **204** is located on the spacer **218**, the first electrode **206** and the second electrode **216** and spaced apart from the substrate **202**. The interval space **2101** is formed via the spacer **218**, the sound wave generator **204**, and the substrate **202**, together with the first electrode **206** or the second electrode **216**. The height of the interval space **2101** is determined by the height of the spacer **218** and first and second electrodes **206**, **216**. In order to prevent the sound wave generator **204** from generating standing wave, thereby maintaining good audio effects, the height of the interval space **2101** between the sound wave generator **204** and the substrate **202** can be in a range of about 10 microns to about 1 centimeter.

In one embodiment, the spacer **218**, the first electrode **206** and the second electrode **216** have a height of about 20 microns, and the height of the interval space **2101** between the sound wave generator **204** and the substrate **202** is about 20 microns.

It is to be understood that, the carbon nanotube structure is flexible. When the distance between the first electrode **206** and the second electrode **216** is large, the middle region of the carbon nanotube structure between the first and second electrodes **206**, **216** may sag and come into contact with the substrate **202**. The spacer **218** can prevent the contact between the carbon nanotube structure and the substrate **202**. Any combination of spacers **218** and electrodes **206**, **216** can be used.

Referring to FIGS. **17** and **18**, in other embodiments, the thermoacoustic module includes a plurality of first electrodes **206**, a plurality of second electrodes **216**, and a plurality of spacers **218**.

The first electrodes **206** and the second electrodes **216** are arranged on the substrate **202** as a staggered manner of $+-+--$. All the first electrodes **206** are connected to the first conducting member **3210**. All the second electrodes **216** are connected to the second conducting member **3212**. The first conducting member **3210** and the second conducting member **3212** can be silver paste lines like the first and second electrodes **206**, **216**, and are perpendicular to the first and second electrodes **206**, **216**. It is to be understood that the first and second conducting member **3210**, **3212**, the first and second electrodes **206**, **216**, and the spacers **218** can be formed on the substrate **202** at the same time by screen-printing a patterned silver paste lines on the top surface **230** of the substrate **202**. The first conducting member **3210** and the second conducting member **3212** can be arranged on the substrate **202** and near the opposite edges of the substrate **202**.

The spacers **218** can be located on the substrate **202** between every adjacent first electrode **206** and second electrode **216** and can be apart from each other for a same distance. A distance between every two adjacent spacers **218** can be in a range from 10 microns to about 3 centimeters.

In one embodiment, as shown in FIGS. **17** and **18**, the thermoacoustic module includes four first electrodes **206**, and four second electrodes **216**. There are two spacers **218** between the adjacent first electrode **206** and the second electrode **216**. The distance between the adjacent spacers **218** is about 7 millimeters, and the distance between the adjacent first electrode **206** and the second electrode **216** is about 2.1 centimeter.

Referring to FIG. **19** and FIG. **48**, alternatively, the sound wave generator **204** can be embedded in spacers **218a** located between the adjacent the first electrode **206** and the second electrode **216**, which means the spacers **218a** extend above a

15

top of the first and second electrodes **206**, **216**. Thus, the sound wave generator **204** can be securely fixed to the substrate **202**. When the spacers **218a** are made of silver paste screen-printed on the substrate **202**, the sound wave generator **204** can be disposed on the silver paste lines before they are cured or solidified. The silver paste can infiltrate through the carbon nanotube structure and thereby extend above the sound wave generator **204**.

Referring to FIG. **20** and FIG. **52**, alternatively, spacers can be sphere shaped (labeled as **218b**). The sound wave generator **204** and the spacers **218b** are in point-contacts. Therefore, the contacting area between the sound wave generator **204** and the spacers **218b** is smaller, and the sound wave generator **204** has a larger contacting area with the surrounding medium. Thus, the efficiency of the thermoacoustic module can be increased.

The first electrodes **206** and the second electrodes **216** can also be supported by the spacers **218**. The first electrodes **206** and the second electrodes **216** can be located on the top surface **2044** of the sound wave generator **204**. The first and second electrodes **206**, **216** can be positioned vertically above the spacers **218**. Each of the first electrodes **206** or second electrodes **216** corresponds to one spacer **218**. The sound wave generator **204** can be secured from the two sides thereof via the electrodes **206**, **216** and the spacers **218**.

In one embodiment as shown in FIGS. **21** and **22**, the thermoacoustic module includes eight spacers **218**, with a height of about 20 microns. The spacers **218** are formed on the substrate **202** via a screen-printing method. The sound wave generator **204** is located on the spacers **218** and adhered to the spacers **218** by a binder, and spaced from the substrate **202**. Four first electrodes **206** and four second electrodes **216** can be located on the top surface **2044** via conductive binder. The first electrodes **206** and the second electrodes **216** can be wires made of stainless steel with a height of about 20 microns.

Referring to FIGS. **24** and **25**, in other embodiments, a thermoacoustic module includes a substrate **202**, a first electrode **206**, a second electrode **216**, a spacer **218** and a sound wave generator **204**. The sound wave generator **204** is separately embedded into the first electrode **206** and the second electrode **216**, and the spacer **218** is located on the substrate **3102** between the first electrode **206** and the second electrode **216**.

The first electrode **206** includes two portions, the upper portion **2062** is on a top surface **2044** of the sound wave generator **204**, the lower portion **2064** is on a bottom surface **2042** of the sound wave generator **204**, to secure the sound wave generator **204** from both sides. The second electrode **216** is similar to the first electrode **206**, and includes the upper portion **2162** and the lower portion **2164**.

A distance from the sound wave generator **204** to the substrate **202** can be in a range from about 10 microns to about 0.5 centimeters.

When the sound wave generator **204** is embedded into the first electrode **206** and the second electrode **216**, the sound wave generator **204** will be very secured and electrically connected with the first and second electrodes **206**, **216**.

Referring to FIGS. **26** and **27**, in other embodiments, when there are a plurality of first electrodes **206** and second electrodes **216**, the first electrodes **206** and the second electrodes **216** are located on the substrate **202** in a staggered manner (e.g. +-+-). The first electrodes **206** and the second electrodes **216** can be parallel to each other with a same distance between the adjacent first electrode **206** and the second electrode **216**. The distance between the adjacent first electrode **206** and the second electrode **216** can be in a range from about

16

1 millimeter to about 2 centimeters. All the first electrodes **206** are electrically connected to the first conducting member **3210**. All the second electrodes **216** are connected to the second conducting member **3212**. The sections of the sound wave generator **204** between the adjacent first electrode **206** and the second electrode **216** are in parallel connection. An electrical signal is conducted in the sound wave generator **204** from the first electrodes **206** to the second electrodes **216**.

The spacers **218** are located on the substrate **202** between every adjacent first electrode **206** and second electrode **216**. The spacers **218** can be the same distance apart. The spacers **218**, the first electrodes **206** and the second electrode **216** can be located on the substrate **202** with a same distance between each other and parallel with each other. A distance between every two adjacent spacers **218** can be in a range from 10 microns to about 1 centimeter.

In one embodiment shown in FIGS. **26** and **27**, the thermoacoustic module includes four first electrodes **206**, and four second electrodes **216**. There are two spacers **218** between the adjacent first electrode **206** and the second electrode **216**. The distance between the adjacent spacers **218** is about 2 millimeters. The distance between the adjacent first electrode **206** and the second electrode **216** is about 6 millimeters. The first electrode **206** includes the upper portion **2062** and the lower portion **2064**. The second electrode **216** includes the upper portion **2162** and the lower portion **2164**. The upper portions **2062**, **2162** and the lower portions **2064**, **2164** clamp the sound wave generator **204** therebetween.

Referring to FIG. **28**, the sound wave generator **204** can also be embedded in and clamped by the spacers **218a**. More particularly, the spacers **218a** can be conductive lines formed from conductive paste, like the electrodes **206**, **216**. Therefore, the electrodes **206**, **216** and the spacers **218a** can be screen printed on the substrate **202** at the same time.

Referring to FIG. **29**, the spacers **218b** can be dot spacers **218b** that have sphere shape while the sound wave generator **204** is embedded in and secured by the first and second electrodes **206**, **216**.

Screen-Printing Method for Making Thermoacoustic Module Referring to FIGS. **30A** to **30C**, the screen-printing method embodiment for making a thermoacoustic module includes:

S11: providing the insulating substrate **202** and the sound wave generator **204**;

S12: screen printing a conductive paste on the top surface **230** of the insulating substrate **202** to form a patterned conductive paste layer **414**;

S13: placing the sound wave generator **204** on the patterned conductive paste layer **414**; and

S14: solidifying the patterned conductive paste layer **414** to form at least the first and second electrodes **206**, **216**.

The step S12 includes the following substeps of:

S121: covering a patterned screen-printing plate on the top surface **230** of the insulating substrate **202**, wherein the patterned screen-printing plate defines patterned openings;

S122: applying the conductive paste through the patterned openings to the top surface **230** of insulating substrate **202**;

S123: removing the patterned screen-printing plate from the insulating substrate **202**.

In step S121, the patterned openings correspond to the patterned conductive paste layer **414** located on the top surface **230** of the insulating substrate **202**. The patterned openings can be designed according to the shapes and positions of the first and second electrodes **206**, **216** and/or spacers **218** and/or the first and second conducting members **3210**, **3212** that needed to be formed on the insulating substrate **202**. The first and second electrodes **206**, **216**, the spacers **218**, and the first and second conducting members **3210**, **3212** can be

screen printed on the substrate **202** at the same time or not. In one embodiment, the patterned screen-printing plate includes eight rectangle openings. The rectangle openings are parallel with each other. Each rectangle opening has a width of 150 microns and a length of 16 centimeters. A distance between every two adjacent rectangle openings is 2 centimeters.

Step **S122** includes the following substeps of:

S1221: applying a conductive paste on the patterned screen-printing plate; and

S1222: forcing the conductive paste into the openings.

The conductive paste may include metal powder, glass powder, and binder. In one embodiment, the conductive paste includes 50% to 90% (by weight) of the metal powder, 2% to 10% (by weight) of the glass powder, and 10% to 40% (by weight) of the binder. The metal powder can be silver powder, gold powder, copper powder, or aluminum powder. The binder can be terpeneol or ethyl cellulose (EC). The conductive paste has a desired degree of viscosity for screen-printing.

In step **S123**, the patterned conductive paste layer **414** is formed on the top surface **230** of the insulating substrate **202**. The patterned conductive paste layer **414** includes a plurality strips or lines. A shape of the strip corresponds to the shape of the opening. In one embodiment, the patterned conductive layer **414** includes eight strips of conductive paste, and each strip of conductive paste has a height in a range from about 5 microns to about 100 microns.

In step **S13**, the sound wave generator **204** is free-standing, and can be laid on the patterned conductive paste layer **414** before the patterned conductive paste layer **414** is cured into solid. However, when the first and second conducting member **3210**, **3212** are screen printed on the substrate **202** together with the electrodes **206**, **216**, and/or the spacers **218**, the first and second conducting member **3210**, **3212** is not covered by the sound wave generator **204**.

The conductive paste can have a viscosity that allows it to infiltrate into the sound wave generator **204**. That is to say, the conductive paste has a suitable viscosity to allow the sound wave generator **204** embedded into the patterned conductive paste layer **414** under action of the gravity or other outer forces. More specifically, the conductive paste can infiltrate in the interspaces defined by the carbon nanotubes in the carbon nanotube structure. In another aspect, the conductive paste can have viscosity and can prevent the sound wave generator **204** from passing through the patterned conductive paste layer **414** to reach the top surface **230** of the substrate **202** before the conductive paste is cured. The viscosity of the conductive paste is not too high and not too low, and thus, the sound wave generator **204** can be embodied into the patterned conductive paste layer **414** and suspended from the insulating substrate **202**. In one embodiment, the patterned conductive paste layer **414** is made of the conductive paste in a colloidal state.

It is to be understood that, for the reason that the sound wave generator **204** is flexible, and when it is embedded in the patterned conductive paste layer **414**, the portion of the sound wave generator **204** between two strips or lines of the patterned conductive paste layer **414** may be curved under the action of gravity, and come into contact with the top surface of the substrate **202**. Therefore, the number of the patterned conductive paste layer **414** should be enough to enable at least above 90% of the area of the sound wave generator **204** is not in contact with the top surface **230** of the substrate **202** and is suspended.

Furthermore, step **S13** can further include pressing the sound wave generator **204** placed on the patterned conductive paste layer **414** by an additional force. The additional force

can be applied by air flow. The step of pressing the sound wave generator **204** can include: providing a blower; blowing the top surface **2044** of the sound wave generator **204** via the blower to cause the conductive paste to infiltrate the sound wave generator **204**. The blowing method can prevent damage to the sound wave generator **204**. The conductive paste can be exposed from the top surface **2044** of the sound wave generator **204**.

In step **S14**, the patterned conductive paste layer **414** can be solidified by different methods (e.g., drying, heating, or UV curing) according to different material of the conductive paste. In one embodiment, the patterned conductive paste layer **414** includes the terpeneol or ethyl cellulose (EC) and can be heated in a heating device. The solidified patterned conductive paste layer **414** becomes the plurality of first and second electrodes **206**, **216** and/or spacers **218** and/or the first and second conducting members **3210**, **3212** on the insulating substrate **202**. The sound wave generator **204** can be embedded in the first and second electrodes **206**, **216** and/or the spacers **218** and suspended from the insulating substrate **412**. However, the sound wave generator **204** does not cover or embedded in the first and second conducting members **3210**, **3212**. In one embodiment, four first electrodes **206** and four second electrode **216** are formed on the insulating substrate **202**, and each electrode **206**, **216** has a width of about 150 microns and a length of about 16 centimeters. A distance between the adjacent first and second electrodes **206**, **216** is about 2 centimeters, and each of the electrode **206**, **216** has a height in a range from about 5 microns to about 100 microns. Further, due to the suspension from the substrate **202**, the sound wave generator **204** can be sufficiently contacted with the surrounding medium, therefore the efficiency of the thermoacoustic module can be increased.

Bonding Layers

Referring to FIG. **32**, the thermoacoustic module can further include conductive bonding layers **524** to secure the sound wave generator **204** on the first and second electrodes **206**, **216** and/or the spacers **218**. The conductive bonding layers **524** can be separately located on the first electrode **206** and/or the second electrode **216** and/or the spacers **218**. The sound wave generator **204** is embedded in the conductive bonding layers **524**, and supported by the first electrode **206** and the second electrode **216**. The conductive bonding layers **524** fix the sound wave generator **204** on the first electrode **206** and the second electrode **216**. The conductive bonding layers **524** can infiltrate into the sound wave generator **204** and may come into contact with the electrodes **206**, **216**. The sound wave generator **204** is electrically connected to the first electrode **206** and the second electrode **216** via the conductive bonding layers **524**.

The conductive bonding layers **524** can be used to provide electrical contact and connection between the first and second electrodes **206**, **216** and the sound wave generator **204**. In one embodiment, the conductive bonding layer **524** is a layer of silver paste. A material of the conductive bonding layers **524** can be a conductive paste and/or a conductive adhesive. The conductive paste or the conductive adhesive can comprise of metal particles, binder and solvent. The metal particles can be gold particles, silver particles, copper particles, or aluminum particles. In one embodiment, the conductive bonding layer **524** is a layer of silver paste.

The silver paste can be coated on the surface of the first electrode **206** and the second electrode **216** to form the two conductive bonding layers **524**. The sound wave generator **204** can be placed on the two conductive bonding layers **524** before the silver paste being solidified. The sound wave generator **204** can comprise of a carbon nanotube structure with

a plurality of interspaces between the adjacent carbon nanotubes. The silver paste can have a desired viscosity before being solidified. Thus, the silver paste can be filled into the interspaces of the carbon nanotube structure. After being solidified, the silver paste is formed into the conductive bonding layers **524**, therefore the sound wave generator **204** is partly embedded into the conductive bonding layers **524**.

In one embodiment, the first electrode **206** and the second electrode **216** are rod-shaped metal electrodes such as metal wires, parallel with each other, and located on the top surface **230** of the substrate **202**. An interval space **P** is defined between the first electrode **206**, the second electrode **216**, the sound wave generator **204** and the substrate **202**. Further, in order to prevent the sound wave generator **204** from generating standing wave, and maintain good audio effects, a distance between the sound wave generator **204** and the substrate **202** can be in a range from about 10 microns to about 1 centimeter.

Referring to FIGS. **33** and **34**, when the thermoacoustic module includes a plurality of first electrodes **206**, and second electrodes **216**, the conductive bonding layers **524** can be arranged on each of the electrodes **206**, **216**. A plurality of interval spaces **P'** can be defined between the first electrode **206**, the second electrode **216**, the sound wave generator **204** and the substrate **202**.

Furthermore, the first electrodes **206** and the second electrodes **216** are alternately and staggered arranged (e.g. +--+). The first electrodes **206** and the second electrodes **216** can be substantially parallel to each other with a same distance between the adjacent first electrode **206** and the second electrode **216**. All the first electrodes **206** are connected to a first conducting member **3210**. All the second electrodes **216** are connected to a second conducting member **3212**. However, the sound wave generator **204** is not located above the first and second conducting member **3210**, **3212**.

In one embodiment, the thermoacoustic module includes four first electrodes **206**, four second electrodes **216**, and eight conductive bonding layers **524**. One conductive bonding layer **524** is located on each one of the first electrodes **206** and the second electrodes **216**. The distance between the adjacent first electrode **206** and the second electrode **216** is about 1.7 centimeters.

Referring to FIG. **35**, a thermoacoustic module includes a plurality of holders **546**. A plurality of interval spaces **P''** is defined between the first electrode **206**, the second electrode **216**, the sound wave generator **204**, the holders **546** and the substrate **202**. The holders **546** are located on the substrate **202** parallel with each other, and spaced from each other for a distance. One of first electrodes **206** and second electrode **216** is located on each one of the holders **546**. There is the holders **546** between each of the first electrodes **206** and the second electrodes **524** and the substrate. A material of the holders **546** can be conductive materials such as metals, conductive adhesives, and indium tin oxides among other materials. The material of the holders **546** can also be insulating materials such as glass, ceramic, or resin. In one embodiment, the holders **546** are made of glass. The spacers **546** are arranged to elevate the first and second electrodes **206**, **216** thereon, thereby increasing the height of the interval spaces **P''** between the sound wave generator **204** and the substrate **202**.

Screen-Printing Method for Making Thermoacoustic Module Including Bonding Layer

Referring to FIGS. **31A** to **31D**, an embodiment for screen-printing a thermoacoustic module includes the following steps of:

S21: providing an insulating substrate **202** and a sound wave generator **204**;

S22: screen printing a conductive paste to a surface of the insulating substrate **202** to form a first patterned conductive paste layer, and solidifying the first patterned conductive paste layer to form at least the plurality of electrodes **206**, **216**;

S23: placing the sound wave generator **204** on the plurality of electrodes **206**, **216**, and screen printing the conductive paste on the sound wave generator **204** to form a second patterned conductive paste layer corresponding to the electrodes **206**, **216**; and

S24: solidifying the second patterned conductive paste layer.

In step **22** the first patterned conductive paste layer is solidified into at least the first and second electrodes **206**, **216** before the sound wave generator **204** is placed thereon. After placing the sound wave generator **204**, the additional conductive paste is applied on the top surface **2044** of the sound wave generator **204** to form the second patterned conductive paste layer at the position above the first and second electrodes **206**, **216**. The second patterned conductive paste layer includes a plurality of strips or lines which correspond to the first and second electrodes **206**, **216**. The conductive paste can infiltrate into the sound wave generator **204** and coat the electrodes **206**, **216**. In step **S24**, the second patterned conductive paste layer is solidified to be a plurality of bonding layers **524**.

It is to be understood that, the spacers **218** can also be formed on the substrate **202** at the same time as the electrodes **206**, **216**. The second patterned conductive paste layer can be screen printed not only at the positions above the electrodes **206**, **216**, but also at the positions above the spacers **218**.

Cover Board

The thermoacoustic module **612** can further include a cover board **610** to cover the sound wave generator **204** thereby protecting the sound wave generator **204** from being damaged. The cover board **610** can have the same shape, structure, and material as that of the substrate **202**. In one embodiment, the cover board **610** is made of glass. The cover board **610** can be located on and supported by two supporters **614**. The cover board **610** can be in partial contact with the sound wave generator **204** or spaced from the sound wave generator **204**.

Referring to the embodiment shown in FIG. **36**, the sound wave generator **204** is located on and supported by the first electrodes **206** and the second electrodes **216**. The cover board **610** is spaced from the substrate **202**. Supporters **614** are located between the cover board **610** and the substrate **202** to separate the cover board **610** from the substrate **202**. The sound wave generator **204**, first electrodes **206** and second electrodes **216** are located between the substrate **202** and the cover board **610**.

The two supporters **614** can be insulating strips and parallel with the first electrodes **206** or the second electrodes **216**. The two supporters **614** are located separately at the two edges of a top surface of the substrate **202**. The two supporters **614** are used for supporting the cover board **610**. A height of the supporters **614** is greater than the height of the first electrodes **206** and the second electrodes **216**. The two supporters **614** can be made of insulating materials, such as glass, ceramic, or resin. In one embodiment, the two supporters **614** are made of polytetrafluoroethylene (PTFE). The cover board **610** is located on and supported by the two supporters **614**.

It is to be understood that, a plurality of spacers can be located between the sound wave generator **204** and the substrate **202**.

Frame

Referring FIG. 37, the thermoacoustic device 1000 can further include two fixing frames 611 to secure the thermoacoustic module. The thermoacoustic module 612 can be fixed between the two fixing frames 611. The two fixing frames 611 can cooperate with each other to fasten the thermoacoustic module 612 therebetween. The two fixing frames 611 can be fixed with each other by bolts, riveting, buckle, scarf, adhesive or any other connection means.

Referring to FIGS. 37 and 38, the two fixing frames 611 can have the same structure, and can have a rectangular shape. In one embodiment, the fixing frame 611 includes four frame members joined end to end to define a rectangle opening 6111. Each frame member has a recess formed along the side adjacent to the opening 6111. The recess can have a stepped configuration. The recesses of the four frame members connect together to define an engaging portion 6112. The engaging portion 6112 is to accommodate and hold the thermoacoustic module 612. A depression 6113 is defined between two adjacent frame members at the corner where the two frame members joined together. Two of the four frame members which are opposite to each other are labeled as 6114 and 6115. The top surface of the frame members 6114 and 6115 facing to the thermoacoustic module 612 can define two heat dissipating grooves 61141, 61151. The heat dissipating grooves 61141, 61151 are used for dissipating the heat produced by the thermoacoustic module 612. Two lead wire channels 61142 are located apart on the top surface of the frame members 6114 at the two sides of the heat dissipating grooves 61141. The lead wire channels 61142 can allow the lead wires go therethrough, thereby connecting the thermoacoustic module 612 to a signal device. It is to be understood that the fixing frames 611 can have other shapes besides the rectangular shape shown in FIG. 37. The shape of the fixing frames 611 can vary according to the shape of the thermoacoustic module. For example, when the thermoacoustic module has a round plate shape, the fixing frames 611 can also have an annular shape accordingly. Additionally, the shape of the thermoacoustic module and the fixing frames 611 need not be similar.

Referring to FIGS. 38 and 39, the two fixing frames 611 can be symmetrically attached together and enclose the thermoacoustic module 612 therebetween. The thermoacoustic module 612 is interposed between the two engaging portions 6112 of the two fixing frames 611. The substrate 202 and the cover board 610 are attached the engaging portions 6112. Two lead wires are separately and electrically connected to the first conducting member 3210 and the second conducting member 3212 through the lead wire channels 61142.

Referring to FIG. 40, in one embodiment, a plurality of spacers 218 can be arranged on the cover board 610 at a position being in alignment with the first or second electrodes 206, 216. More specifically, the spacers 218 are located above the first and second electrodes 206, 216, and sandwich the sound wave generator 204 therebetween.

More specifically, the spacer 218 can be integrated with the cover plate 610 or separated from the cover board 610. The spacer 218 can be fixed on the cover board 610. The shape of the spacer 218 is not limited and can be dot, lamellar, rod, wire, and block among other shapes. When the spacer 218 has a line shape such as a rod or a wire. A material of the spacer 218 can be conductive materials such as metals, conductive adhesives, and indium tin oxides among other materials. The material of the spacer 218 can also be insulating materials such as glass, ceramic, or resin among other materials. The spacers 218 can apply a pressure on the sound wave generator 204.

Referring to FIG. 41, in one embodiment, the location of the second electrodes 216 can be varied, they can be arranged on and mounted the cover board 610 but not on the substrate 202. The first electrodes 206 are located on the substrate 202.

The height of the supporters 614 can be equal to or smaller than the sum of the heights of the first electrode 206, the second electrode 216, and the sound wave generator 204.

Cover Board with Mesh

The cover board 610 can further have a mesh structure defining a plurality of openings therein. Therefore, the cover board 610 has a good sound and thermal transmittance. The cover board 610 is used to protect the sound wave generator 204 from being damaged or destroyed by outer forces. The openings can allow the exchange between the surrounding medium inside and outside of the cover board 610. The openings can be distributed in the cover board 610 orderly or randomly, entirely or partially. The cover board 610 can have a planar shape and/or a curved shape. A material of the cover board 610 can be conductive materials such as metals, or insulating materials such as plastics or resins. The openings of the cover board 610 can be formed by etching a metal plate or drilling a plastic or resin plate. The cover board 610 can also be a braiding or network weaved by metal, plastic, or resin wires. The size of the cover board 610 can be larger than the size of the sound wave generator 204 thereby covering the entire sound wave generator 204. In one embodiment, the size of the cover board 610 is equal to the size of the substrate 202.

Referring to FIGS. 42 to 44, a thermoacoustic device 2000 according to an embodiment includes a thermoacoustic module 612 and a frame 611. The thermoacoustic module 612 is fixed in the frame 611.

Referring to FIG. 43, the cover board 610 has a mesh structure defining a plurality of openings 616 therein. The substrate 202 has a top surface 230 (Shown in FIG. 44).

Referring to FIG. 45, the height h_3 of the supporters 614 is greater than the height h_1 of the first electrode 206 or the second electrode 216, together with the thickness h_2 of the sound wave generator 204, thereby separating the sound wave generator 204 from the cover board 610.

In one embodiment, the cover board 610 is a planar stainless steel mesh, and the openings 616 are distributed in the cover board 610 uniformly and entirely.

Referring to FIG. 42, the frame includes two fixing frames 611. The fixing frames 611 are disposed at the two sides of the thermoacoustic module 612. The two fixing frames 611 can cooperate with each other to fasten the thermoacoustic module 612 therebetween. The two fixing frames 611 can be fixed with each other by bolts, riveting, buckle, scarf, adhesive or any other connection means. It is easy to be understood that the thermoacoustic device 2000 can also include a plurality of first electrodes 206, and a plurality of second electrodes 216. In the embodiment shown in FIG. 46, the thermoacoustic device 2000 includes four first electrodes 206 and four second electrodes 216. The first electrodes 206 and the second electrodes 216 can be arranged on the substrate 202 as a staggered manner of “+--+”.

Depending on the embodiment, certain of the steps of methods described may be removed, others may be added, and the sequence of steps may be altered. It is also to be understood that the description and the claims drawn to a method may include some indication in reference to certain steps. However, the indication used is only to be viewed for identification purposes and not as a suggestion as to an order for the steps.

It is to be understood that the above-described embodiments are intended to illustrate rather than limit the invention. Variations may be made to the embodiments without departing from the spirit of the invention as claimed. Any elements discussed with any embodiment are envisioned to be able to be used with the other embodiments. The above-described embodiments illustrate the scope of the invention but do not restrict the scope of the invention.

What is claimed is:

1. A thermoacoustic module comprising:
a substrate;
at least one first electrode and at least one second electrode located on the substrate;
a sound wave generator spanning between and electrically connected to the at least one first electrode and the at least one second electrode, the sound wave generator having a bottom surface and a top surface, wherein the at least one first electrode and the at least one second electrode provide support to the sound wave generator; and
at least one spacer located on the substrate to provide support to the sound wave generator such that an interval is defined between the sound wave generator and the substrate;
wherein the sound wave generator is capable of generating sound by converting electrical signal into heat, transferring the heat to the medium, and causing a thermoacoustic effect.
2. The thermoacoustic module of claim 1, wherein the at least one first electrode and the at least one second electrode are between the bottom surface of the sound wave generator and the substrate, and connected to the bottom surface of the sound wave generator.
3. The thermoacoustic module of claim 2, wherein the at least one spacer is located between the at least one first electrode and the at least one second electrode.
4. The thermoacoustic module of claim 1, wherein a shape of the at least one spacer is selected from the group consisting of dot, lamellar, rod, wire, block, and combinations thereof.
5. The thermoacoustic module of claim 1, wherein the at least one spacer comprises a plurality of spacers, and the plurality spacers are equidistance apart.
6. The thermoacoustic module of claim 1, wherein the at least one spacer is attached to the substrate via a binder or a screw.
7. The thermoacoustic module of claim 1, wherein the at least one spacer is integrated with the substrate.
8. The thermoacoustic module of claim 1, wherein the at least one spacer is conductive.
9. The thermoacoustic module of claim 1, wherein the sound wave generator is partially embedded in the at least one spacer.
10. The thermoacoustic module of claim 1, wherein the at least one first electrode comprises a plurality of first electrodes, the at least one second electrode comprises a plurality of second electrodes, and the plurality of first electrodes and the plurality of second electrodes are located on the substrate in a staggered manner.
11. The thermoacoustic module of claim 10, wherein the plurality of first electrodes and the plurality of second electrodes are parallel to each other, and adjacent first electrodes and second electrodes equidistant apart.
12. The thermoacoustic module of claim 1, wherein the sound wave generator comprises a carbon nanotube structure, the carbon nanotube structure comprises at least one carbon nanotube film, the at least one carbon nanotube film comprises a plurality of successive carbon nanotubes joined end-to-end by van der Waals attractive force therebetween, the plurality of successive carbon nanotubes in the at least one carbon nanotube film is substantially aligned along a single direction and substantially parallel to a surface of the at least one carbon nanotube film.
13. The thermoacoustic module of claim 1, wherein the sound wave generator comprises a plurality of carbon nano-

tubes substantially aligned along a direction from the at least one first electrode to the at least one second electrode.

14. A thermoacoustic module comprising:
a substrate;
at least one first electrode and at least one second electrode located on the substrate;
a carbon nanotube structure electrically connected to the at least one first electrode and the at least one second electrode; and
a plurality of spacers located between the substrate and the carbon nanotube structure;
wherein the plurality of spacers space the carbon nanotube structure from the substrate, an interval is defined between the carbon nanotube structure and the substrate, the carbon nanotube structure comprises a plurality of carbon nanotubes substantially aligned along a direction from the at least one first electrode to the at least one second electrode;
wherein the sound wave generator is capable of generating sound by converting electrical signal into heat, transferring the heat to the medium, and causing a thermoacoustic effect.
15. The thermoacoustic module of claim 14, wherein the plurality of spacers is insulated from the at least one first electrode and the at least one second electrode.
16. The thermoacoustic module of claim 14, wherein the direction is substantially perpendicular to the at least one first electrode and the at least one second electrode.
17. The thermoacoustic module of claim 14, wherein the at least first electrode and at least second electrode are parallel to each other.
18. The thermoacoustic module of claim 17, wherein the plurality of spacers are linear shaped and parallel to each other.
19. The thermoacoustic module of claim 17, wherein the at least one first electrode and the at least one second electrode are located on a top surface of the carbon nanotube structure, and are positioned vertically above the spacers, each of the at least one first electrode and the at least one second electrode corresponds to one spacer.
20. A thermoacoustic device comprising:
a thermoacoustic module comprising:
a substrate;
at least one first electrode and at least one second electrode located on the substrate;
a sound wave generator spanning between and electrically connected to the at least one first electrode and the at least one second electrode, wherein the at least one first electrode and the at least one second electrode provide support to the sound wave generator; and
at least one spacer located between the substrate and the sound wave generator;
and two fixing frames to secure the thermoacoustic module;
wherein the at least one spacer at least partially supports the sound wave generator, an interval is defined between the sound wave generator and the substrate, the sound wave generator comprises a plurality of carbon nanotubes substantially aligned along a direction from the at least one first electrode to the at least one second electrode;
wherein the sound wave generator is capable of generating sound by converting electrical signal into heat, transferring the heat to the medium, and causing a thermoacoustic effect.