

US008398915B2

(12) **United States Patent**  
**Alkmin et al.**

(10) **Patent No.:** **US 8,398,915 B2**  
(45) **Date of Patent:** **Mar. 19, 2013**

(54) **METHOD FOR MAKING A FIBROUS ARTICLE**

(52) **U.S. Cl.** ..... 264/517; 264/518; 264/119; 264/121  
(58) **Field of Classification Search** ..... None  
See application file for complete search history.

(75) Inventors: **Marco Antonio Alkmin**, São José dos Campos (BR); **Livea Fujita Barbosa**, São José dos Campos (BR); **José Francisco Cau**, São José dos Campos (BR); **Jose Manoel Soares Coutinho**, Quiririm (BR); **Ivair Luiz Duarte**, Jardim Flórida Jacarei (BR); **Reinaldo Lourenço Faria**, São José dos Campos (BR); **Francisco J. V. Hernandez**, São José dos Campos (BR); **Manuela Leonel Martines**, São José dos Campos (BR); **Francisco Antonio Rimoli**, Mogi das Cruzes (BR); **Francisco Savastano Neto**, Taubaté (BR); **Alexandre Teixeira Yamashita**, São José dos Campos (BR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,599,648 A	9/1926	Cochran
1,974,578 A	9/1934	Medoff
2,064,431 A	12/1936	Jurgensen
2,331,355 A	10/1943	Strongson
2,408,508 A	10/1946	Canavan

(Continued)

FOREIGN PATENT DOCUMENTS

DE	2113508 A1	9/1972
EP	249405 A2	12/1987

(Continued)

(73) Assignee: **Johnson & Johnson do Brasil Industria e Comercio Produtos Parafarmaceuticos Ltda. Rodovia** (BR)

OTHER PUBLICATIONS

European Search Report dated Oct. 28, 2011 for corresponding EPA No. 11177496.4.

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 161 days.

*Primary Examiner* — Mary F Theisen

(21) Appl. No.: **12/855,175**

(57) **ABSTRACT**

(22) Filed: **Aug. 12, 2010**


The present invention generally relates to a method and apparatus for a making a formed fibrous article and more specifically to method and apparatus for making a formed fibrous article useful as an absorbent core structure in a disposable sanitary article such as a sanitary napkin, panty liner, diaper or the like. The present invention also relates to a disposable sanitary article including a formed fibrous article according to the present invention as a core structure thereof.

(65) **Prior Publication Data**

US 2012/0037327 A1 Feb. 16, 2012

(51) **Int. Cl.**  
**B27N 3/04** (2006.01)  
**A61F 13/15** (2006.01)

**17 Claims, 11 Drawing Sheets**



U.S. PATENT DOCUMENTS

2,747,575	A	5/1956	Mercer	
2,852,026	A	9/1958	Karr	
2,928,394	A	3/1960	Roberts	
2,973,760	A	3/1961	Dudley	
3,420,234	A	1/1969	Phelps	
3,844,288	A	10/1974	Kiela	
3,897,784	A	8/1975	Fitzgerald	
3,905,372	A	9/1975	Denkinger	
3,906,952	A	9/1975	Zamist	
4,046,147	A	9/1977	Berg	
4,079,739	A	3/1978	Whitehead	
4,152,389	A *	5/1979	Miller .....	264/284
4,490,147	A	12/1984	Pierce et al.	
4,631,062	A	12/1986	Lassen et al.	
4,666,440	A	5/1987	Malfitano	
4,673,402	A	6/1987	Weisman et al.	
4,673,403	A	6/1987	Lassen et al.	
4,758,240	A	7/1988	Glassman	
4,761,258	A *	8/1988	Enloe .....	264/518
4,783,231	A *	11/1988	Raley .....	156/167
4,804,380	A	2/1989	Lassen et al.	
4,848,572	A	7/1989	Herrera	
4,886,632	A *	12/1989	Van Iten et al. ....	264/156
4,904,249	A	2/1990	Miller et al.	
4,935,022	A	6/1990	Lash et al.	
4,988,344	A	1/1991	Reising et al.	
5,127,911	A	7/1992	Baharav	
5,248,309	A	9/1993	Serbiak et al.	
5,269,994	A *	12/1993	Deffenbaugh et al. ....	264/119
5,288,348	A *	2/1994	Modrak .....	156/62.2
5,308,346	A	5/1994	Sneller et al.	
5,383,868	A	1/1995	Hyun	
5,545,156	A	8/1996	Dipalma et al.	
5,591,150	A	1/1997	Olsen et al.	
5,599,337	A	2/1997	McCoy	
5,609,588	A	3/1997	Dipalma et al.	
5,624,423	A	4/1997	Anjur et al.	
5,628,739	A	5/1997	Hsieh et al.	
5,649,916	A	7/1997	Dipalma et al.	
5,702,380	A	12/1997	Walker	
5,730,818	A	3/1998	Isakson	
5,807,362	A	9/1998	Serbiak et al.	
5,833,680	A	11/1998	Hartman	
6,059,763	A	5/2000	Brown	
6,100,442	A	8/2000	Samuelsson et al.	
6,160,197	A	12/2000	Lassen et al.	
6,175,056	B1	1/2001	Carlucci et al.	
6,191,340	B1	2/2001	Carlucci et al.	
6,217,691	B1 *	4/2001	Vair et al. ....	156/176
6,293,931	B1	9/2001	Romare	
6,296,628	B1	10/2001	Mizutani	
6,306,123	B1	10/2001	Salerno et al.	
6,316,688	B1	11/2001	Hammons et al.	
6,350,257	B1	2/2002	Björklund et al.	
6,394,989	B2	5/2002	Mizutani	
6,410,822	B1	6/2002	Mizutani	
6,413,248	B1	7/2002	Mizutani	
6,417,427	B1	7/2002	Roxendal et al.	
6,441,268	B1	8/2002	Edwardsson	
6,482,193	B1	11/2002	Samuelsson et al.	
6,486,379	B1	11/2002	Chen et al.	
6,492,574	B1	12/2002	Chen et al.	
6,503,233	B1	1/2003	Chen et al.	
6,575,948	B1	6/2003	Kashiwagi et al.	
6,610,902	B1	8/2003	Gustafsson et al.	
6,617,490	B1	9/2003	Chen et al.	
6,632,206	B1	10/2003	Onishi et al.	
6,660,903	B1	12/2003	Chen et al.	
6,700,034	B1	3/2004	Lindsay et al.	
6,706,129	B2 *	3/2004	Ando et al. ....	156/62.2
6,764,477	B1	7/2004	Chen et al.	
6,955,667	B1	10/2005	Tanaka et al.	
6,958,430	B1	10/2005	Marinelli	
7,001,167	B2	2/2006	Venturino et al.	
7,122,023	B1	10/2006	Hinoki	
7,323,072	B2 *	1/2008	Engelhart et al. ....	156/73.2
7,368,627	B1	5/2008	Widlund	
7,438,708	B2	10/2008	Kashiwagi et al.	

7,597,690	B2	10/2009	Tanio et al.	
7,621,899	B2	11/2009	Fujikawa et al.	
2001/0021836	A1	9/2001	Kashiwagi	
2001/0029359	A1	10/2001	Carlucci	
2001/0044610	A1	11/2001	Kim et al.	
2002/0026170	A1	2/2002	Samulesson et al.	
2002/0052589	A1	5/2002	Strand	
2002/0055726	A1	5/2002	Costa	
2002/0065497	A1	5/2002	Kolby Falk	
2002/0077617	A1	6/2002	Drevik	
2002/0082576	A1	6/2002	Hansson et al.	
2002/0087133	A1	7/2002	Osterdahl et al.	
2002/0087138	A1	7/2002	Osterdahl et al.	
2002/0156443	A1	10/2002	Drevik et al.	
2002/0156450	A1	10/2002	Drevik et al.	
2002/0165512	A1	11/2002	Drevik et al.	
2002/0165513	A1	11/2002	Drevik et al.	
2002/0188270	A1	12/2002	Edens et al.	
2002/0193758	A1	12/2002	Sandberg	
2003/0018314	A1	1/2003	Nozaki et al.	
2003/0040729	A1	2/2003	Malowaniec et al.	
2003/0055392	A1	3/2003	Tagami et al.	
2003/0088222	A1	5/2003	Yoshimasa et al.	
2003/0125699	A1	7/2003	Drevik et al.	
2003/0125700	A1	7/2003	Drevik	
2003/0125701	A1	7/2003	Widlund	
2003/0130643	A1	7/2003	Drevik et al.	
2003/0144644	A1	7/2003	Murai et al.	
2003/0167047	A1	9/2003	Policappelli	
2004/0254556	A1	12/2004	Brisebois et al.	
2005/0027278	A1	2/2005	Mizutani et al.	
2005/0080391	A1	4/2005	Yoshimasa et al.	
2005/0258576	A1 *	11/2005	Forry et al. ....	264/517
2006/0116653	A1	6/2006	Munakata et al.	
2006/0135930	A1	6/2006	Mizutani et al.	
2006/0142724	A1	6/2006	Watanabe et al.	
2006/0142725	A1	6/2006	Fujikawa et al.	
2006/0259002	A1	11/2006	Parr	
2006/0264878	A1	11/2006	Carstens	
2006/0271008	A1	11/2006	Tanio et al.	
2006/0287635	A1	12/2006	Angel	
2007/0005036	A1	1/2007	Nishikawa et al.	
2008/0065037	A1	3/2008	Konawa	
2008/0119810	A1	5/2008	Kuroda et al.	
2008/0172018	A1	7/2008	Chien	
2008/0275419	A1	11/2008	Standfest	
2008/0281287	A1	11/2008	Marcelo et al.	
2009/0036854	A1	2/2009	Guidotti et al.	
2009/0036858	A1	2/2009	Van Den Bogart et al.	
2009/0157032	A1	6/2009	MacDonald et al.	
2009/0281511	A1	11/2009	Fukae	
2009/0281515	A1	11/2009	Noda et al.	
2010/0030175	A1	2/2010	Konawa	
2010/0036355	A1	2/2010	Håkansson et al.	
2010/0057031	A1	3/2010	Kuroda et al.	
2010/0100067	A1	4/2010	Pugliese, III	

FOREIGN PATENT DOCUMENTS

EP	668066	A2	8/1995
EP	680739	A1	11/1995
EP	733729	A1	3/1996
EP	768070	A1	4/1997
EP	774946	A1	5/1997
EP	472633	B2	11/1999
EP	335252	B1	12/2001
EP	1051956	B1	7/2004
EP	1493415	A3	5/2006
EP	2085504	A1	8/2009
GB	2202554	A	3/1987
JO	4/146748	A	5/1992
JP	2/121664	A	5/1990
JP	8/299383	A	11/1996
JP	10/137290	A	5/1998
JP	10/328232	A	12/1998
JP	11/033054	A	2/1999
JP	11/042250	A	2/1999
JP	11/226051	A	8/1999
JP	11/299827	A	11/1999
JP	2000/189456	A	7/2000


# US 8,398,915 B2


Page 3

---


JP	2001/224626	A	8/2001	WO	WO 97/14390	A1	4/1997
JP	2002/291795	A	10/2002	WO	WO 97/33543	A1	9/1997
JP	2003/062007	A	3/2003	WO	WO 97/40798	A1	11/1997
JP	2003/116909	A	4/2003	WO	WO 98/00083	A1	1/1998
JP	2003/135517	A	5/2003	WO	WO 98/14152	A1	4/1998
JP	2005/237793	A	9/2005	WO	WO 98/22058	A1	5/1998
JP	2005/296024	A	10/2005	WO	WO 98/22060	A1	5/1998
JP	2006/223854	A	8/2006	WO	WO 98/58614	A1	12/1998
JP	2006/239162	A	9/2006	WO	WO 99/55269	A1	11/1999
JP	2006/263205	A	10/2006	WO	WO 00/00121	A1	1/2000
JP	2006/297070	A	11/2006	WO	WO 00/02509	A1	1/2000
JP	2006/297076	A	11/2006	WO	WO 01/17474	A1	3/2001
JP	2007/037660	A	2/2007	WO	WO 01/35887	A1	5/2001
JP	2007/089818	A	4/2007	WO	WO 01/67982	A2	9/2001
JP	2007/089906	A	4/2007	WO	WO 01/97736	A1	12/2001
JP	2007/089907	A	4/2007	WO	WO 02/41817	A1	5/2002
JP	2007/097841	A	4/2007	WO	WO 02/45637	A1	6/2002
JP	2007/135943	A	6/2007	WO	WO 02/47594	A1	6/2002
JP	2007/181725	A	7/2007	WO	WO 02/085269	A1	10/2002
JP	2007/275491	A	10/2007	WO	WO 02/085270	A1	10/2002
JP	2008/080150	A	4/2008	WO	WO 02/087483	A1	11/2002
JP	2008/161256	A	7/2008	WO	WO 02/087484	A1	11/2002
JP	2008/161564	A	7/2008	WO	WO 03/047483	A	6/2003
JP	2008/229032	A	10/2008	WO	WO 03/047484	A1	6/2003
JP	2008/229033	A	10/2008	WO	WO 03/053301	A1	7/2003
JP	2008/295475	A	12/2008	WO	WO 03/055431	A1	7/2003
JP	2009/112590	A	5/2009	WO	WO 03/059222	A1	7/2003
JP	2009/112864	A	5/2009	WO	WO 03/099182	A1	12/2003
JP	2009/195640	A	9/2009	WO	WO 2005/048899	A1	6/2005
JP	2009/207598	A	9/2009	WO	WO 2006/084304	A1	8/2006
WO	WO 90/13278	A1	11/1990	WO	WO 2006/130646	A1	12/2006
WO	WO 91/03999	A1	4/1991	WO	WO 2009/074896	A1	6/2009
WO	WO 96/07379	A1	3/1996	WO	WO 2009/115931	A2	9/2009
WO	WO 97/04730	A2	2/1997	WO	WO 2010/017360	A1	2/2010
WO	WO 97/05840	A1	2/1997				
WO	WO 97/09014	A1	3/1997				
WO	WO 97/09017	A1	3/1997				

\* cited by examiner







**Fig. 2**




**Fig. 3**




**Fig. 4**




**Fig. 5**



**Fig. 6**





**Fig. 7**




**Fig. 8**


**Fig. 9**




**Fig. 10**



**Fig. 11**




**Fig. 12**




**Fig. 13**




**Fig. 14**




**Fig. 15**




**Fig. 16**







**Fig. 17**




**Fig. 18**




**Fig. 19**




**Fig. 20**




**Fig. 21**




**Fig. 22**




**Fig. 23**



**Fig. 24**



**Fig. 25**



**Fig. 26**

**1****METHOD FOR MAKING A FIBROUS ARTICLE**

## FIELD OF THE INVENTION

The present invention generally relates to a method and apparatus for a making a formed fibrous article and more specifically to method and apparatus for making a formed fibrous article useful as an absorbent core structure in a disposable sanitary article such as a sanitary napkin, panty liner, diaper or the like. The present invention also relates to a disposable sanitary article including a formed fibrous article according to the present invention as a core structure thereof.

## BACKGROUND OF THE INVENTION

Various methods for making formed fibrous articles from fibrous materials such as cellulose or the like are well know to those of skill in the art. One common method of manufacturing such formed fibrous articles consists of defiberizing a starting material and then creating an air-entrained stream of the defiberized material. The air-entrained defiberized material may be formed into a formed fibrous article through the use of a porous mold structure subjected to a vacuum to draw the defiberized material into the mold.

It is also known that formed fibrous articles of the type described above may be subjected to calendering processes to alter the mechanical and fluid handling properties of such articles. A calendering process used in the art is commonly referred to as "pin calendering". Pin calendering employs the use of a plurality of pins adapted to compress and densify the article.

A problem associated with pin calendering processes of the type described above is that such processes typically require that a "carrier layer" be used during the pin-calendering step. "Carrier layer" as used herein means any material layer used to support the formed fibrous article, such as a conveyer belt or an adjacent material layer such as rolled nonwoven layer or the like. The use of a carrier layer increases complexity of manufacture. In addition, if the carrier layer is a layer intended to be incorporated into the final product, the inclusion of such layer may increase the cost of the final product and/or undesirably affect the fluid handling characteristics of the product.

In view of the above the inventors of the present invention have discovered, and disclosed herein, a method and apparatus for making a pin-calendered formed fibrous article that does not require the use of a carrier layer. Formed fibrous articles according to the present invention are particularly useful as an absorbent core structure in a disposable sanitary article such as a sanitary napkin, panty liner, diaper or the like.

## SUMMARY OF THE INVENTION

In view of the foregoing, the present invention provides a method for making a formed fibrous article including the steps of forming a formed fibrous article having a three dimensional profile, pin-calendering the fibrous article in a pin calendering station between a first roll and a second roll, wherein the fibrous article is conveyed through a nip defined between the first roll and the second roll without the use of a carrier layer.

**2**

## BRIEF DESCRIPTION OF THE DRAWINGS

Examples of embodiments of the present invention will now be described with reference to the drawings, in which:

5 FIG. 1 is a side elevation view of an apparatus according to the present invention;

FIG. 2 is a detailed perspective view of the forming drum that forms part of the apparatus according to the present invention;

10 FIG. 3 is a sectional view taken along line 3-3 in FIG. 2;

FIG. 4 is a detailed perspective view of a portion of the forming drum shown in FIG. 2;

15 FIG. 5 is a side elevation view of the forming drum and a calendering station that form part of the apparatus according to the present invention;

FIG. 6 is a detailed perspective view of the calendering station shown in FIG. 5, depicting the vacuum roll and calender roll thereof;

20 FIG. 7 is a elevation view of the that portion of the calendering station calender roll circled in FIG. 6;

FIG. 8 is a sectional view taken along line 8-8 in FIG. 6;

FIG. 9 is a detailed perspective view of that portion of the calendering station vacuum roll circled in FIG. 6;

25 FIG. 10 is a perspective view of a formed fibrous article according to the invention after passing through the calendering station;

FIG. 11 is a side elevation view of a pin calendering station that forms part of the apparatus according to the present invention;

30 FIG. 12 is a detailed perspective view of the pin calendering station shown in FIG. 11, depicting the vacuum roll and pin calender roll thereof;

FIG. 13 is a partially exploded perspective view of the pin calendering station pin calender roll;

35 FIG. 14 is a detailed plan view of that portion of the pin calender roll circled in FIG. 13;

FIG. 15 is a sectional view taken along line 15-15 in FIG. 14;

40 FIG. 16 is detailed perspective view of that portion of the pin calender roll circled in FIG. 13;

FIG. 17 is a sectional view taken along line 17-17 in FIG. 11;

45 FIG. 18 is a sectional view taken along line 18-18 in FIG. 12;

FIG. 19 is a side elevation view of a transfer wheel that forms part of the apparatus according to the present invention;

FIG. 20 is a perspective view of the transfer wheel shown in FIG. 19;

50 FIG. 21 is a top plan view of the formed fibrous article after passing through the pin calendering station;

FIG. 22 is a detailed perspective view of that portion of the formed fibrous article circled in FIG. 21;

55 FIG. 23 is a perspective view of an absorbent article according to the present invention with the cover layer and transfer layer thereof partially broken away;

FIG. 24 is a sectional view taken along line 24-24 in FIG. 23; and

FIGS. 25-26 are perspective views of alternate embodiments of absorbent articles according to the present invention.

## DETAILED DESCRIPTION OF THE INVENTION

60 Referring to FIGS. 1-9 and 11-20, there is illustrated a preferred apparatus 10 for making a formed fibrous article 12 according to the method of the present invention.

65 As shown in FIG. 1, the apparatus 10 according to the present invention generally includes a forming drum 14, a

calendering station 16, a pin calendering station 18, and a transfer wheel 20. Certain details of the apparatus 10, such as electrical lines, have been omitted from the figures to simplify the same. However, these features and other basic elements of the apparatus will be clear to those of skill in the art.

The formed fibrous article 12, which is depicted during various stages of the method according to the present invention in FIGS. 3, 5-6, 8, 10, 12 and 18-22, preferably is formed from cellulosic fibers, and in a preferred embodiment of the invention, includes a mixture of cellulosic fibers and superabsorbent polymer. Cellulosic fibers that can be used in the formed fibrous article 12 are well known in the art and include wood pulp, cotton, flax and peat moss. Wood pulp is preferred. Both softwood and hardwood species are useful. Softwood pulps are preferred.

The fibrous article 12 may also contain any superabsorbent polymer (SAP), which are well known in the art. For the purposes of the present invention, the term "superabsorbent polymer" (or "SAP") refers to materials, which are capable of absorbing and retaining at least about 10 times their weight in body fluids under a 0.5 psi pressure. The superabsorbent polymer particles of the invention may be inorganic or organic crosslinked hydrophilic polymers, such as polyvinyl alcohols, polyethylene oxides, crosslinked starches, guar gum, xanthan gum, and the like. The particles may be in the form of a powder, grains, granules, or fibers. Preferred superabsorbent polymer particles for use in the present invention are crosslinked polyacrylates, such as the product offered by Sumitomo Seika Chemicals Co., Ltd. of Osaka, Japan, under the designation of SA70N and products offered by Stockhausen Inc.

The pulp used to form the fibrous article 12 is preferably a bleached softwood pulp, produced by a Kraft process. As shown in FIG. 1, the pulp is provided by the manufacturer as a pulp board 22 in rolled form, the roll identified by the reference numeral 24. The pulp board 22 is conveyed from the roll 24 to a device 26 for grinding the pulp board 22 into fibrous pulp 28. The fibrous pulp 28 is released from the grinding device 26 into a chamber 30 for holding the fibrous pulp 28. The apparatus 10 may further optionally include a device 32 for introducing superabsorbent polymer into the chamber 30 to thereby form a fibrous pulp and superabsorbent mixture. Any conventional device suitable for this purpose, and known to those of skill in the art, may be used for introducing the superabsorbent into the chamber 30.

As best seen in FIG. 3, the chamber 30 has a partially open bottom portion 34 that communicates with the forming drum 14. As seen in FIG. 1, the forming drum 14 includes a hollow cylinder 15 that is structured and arranged to rotate about a fixed axis 17. Any conventional means to rotate the cylinder 15, well known to those of skill in the art, may be used to rotate the cylinder 15. As shown in FIGS. 1-4, the cylinder 15 has a plurality of molds 36 mounted thereto. As the cylinder 15 rotates, each of the molds 36 are sequentially arranged in communication with the open portion 34 of the chamber 30 to thereby receive fibrous pulp 28 from the chamber 30. In FIG. 1, the cylinder 15 rotates in a counterclockwise manner during operation of the apparatus 10.

As shown in FIGS. 1 and 3, the forming drum 14 further includes a vacuum chamber 38 arranged within the interior of the cylinder 15. The vacuum chamber 38 is arranged in a fixed location relative to the rotating cylinder 15 and is operably coupled to a vacuum source (not shown). As best seen in FIG. 4, the mold 36 includes a porous screen 40 structure in the shape of the formed fibrous article 12 to be formed in the mold 36. As the mold 36 passes over the vacuum chamber 38 of the forming drum 14 the vacuum functions to draw the fibrous

pulp 28 from the chamber 30 into the mold 36 by drawing air through the porous screen 40 of the mold 36.

As shown in detail in FIG. 4, the mold 36 includes a nonporous mounting plate portion 42 that surrounds the porous screen 40 portion of the mold 36. The mounting plate portion 42 of the mold 36 is mounted to the periphery 44 of the cylinder 15, thereby enabling each of the molds 36 to rotate with the rotating cylinder 15.

After the mold 36 is rotated under the partially open bottom portion 34 of the chamber 30, the mold 36 is further rotated by the rotating cylinder 15, and as described in further detail below, the fibrous article 12 is then transferred to the calendering station 16.

After formation in the mold 36, the formed fibrous article 12 preferably has a basis weight in the range of between about 200 gsm ( $\text{g/m}^2$ ) to about 400 gsm, a thickness in the range of about 5 mm to about 20 mm, and a density in the range of about 0.01 g/cc to about 0.03 g/cc.

As shown in FIGS. 1 and 5-9 the calendering station 16 generally includes a vacuum roll 42 and an opposed calender roll 44. As best seen in FIG. 6, the vacuum roll 42 is formed from a rotatable cylinder 46 that is rotatable about a fixed axis 48. The calender roll 44 is rotatable about a fixed axis 49. Any conventional means to rotate the cylinder 46, and calender roll 44, well known to those of skill in the art, may be used to rotate cylinder 46 and calender roll 44. The cylinder 46 rotates in a clockwise manner during operation of the apparatus 10, and the calender roll 44 rotates in a counterclockwise manner, as shown in FIG. 1. As best seen in FIGS. 6, 8 and 9, the cylinder 46 includes a plurality of holes 50 that extend from the outer surface 52 of the cylinder 46 to the inner surface 54 of the cylinder 46.

As shown in detail in FIG. 7, the surface 47 of the calender roll 44 includes a recess 53. The recess 53 may take any number of different shapes including generally oval, elliptical, circular or the like. In one preferred embodiment of the invention, as shown in FIG. 7, the recess generally has an oval shape. Preferably, the recess 53 extends over a surface area in range of about 500  $\text{mm}^2$  to about 5000  $\text{mm}^2$ . The recess 53 preferably has a depth in the range of about 2 mm to about 25 mm as measured from the surface 47 of the roll 44 located outside the recess 53. The recess 53 is preferably arranged such that it is longer in the machine direction (md) than in the transverse direction (td). Preferably, the recess 53 has a maximum length, as measured in the machine direction, in the range of about 20 mm to about 120 mm and a maximum width, as measured in the transverse direction, in the range of about 5 mm to about 60 mm.

As shown in FIGS. 5, 6 and 8, the vacuum roll 42 further includes a vacuum chamber 56 arranged within the interior of the cylinder 46. The vacuum chamber 56 is arranged in a fixed location relative to the rotating cylinder 46 and is operably coupled to a vacuum source 57 (FIG. 1). The vacuum chamber 56 is arranged in flow communication with the plurality of holes 50 that extend through the cylinder 46 and thereby draws air through said holes 50.

As shown in FIG. 5, the vacuum chamber 56 is arranged such that its leading edge 58 is substantially aligned with a trailing edge 60 of the vacuum chamber 38 located within cylinder 15 of the forming drum 14. This arrangement of the vacuum chamber 56 relative to location of the vacuum chamber 38 effectuates a transfer of the formed fibrous article 12 from within the mold 36 on the forming drum 14 to the vacuum roll 42.

Once the formed fibrous article 12 has been transferred to the cylinder 46 of the vacuum roll 42 the cylinder 46 rotates the fibrous 12 article until the article 12 passes through the nip



62 formed between the vacuum roll 42 and the calender roll 44. The nip 62 preferably uniformly compresses the fibrous article 12 outside of the area defined by recess 53. The compression of the fibrous article 12 results in a reduction in thickness of the article 12 and a corresponding increase in density in that portion of the fibrous article 12 located outside of the area of the recess 53. In a preferred embodiment of the invention the nip 62 has a distance "d" (i.e. the distance between the surfaces of the opposed rolls) of about 0.9 mm. The distance "d" is identified by the reference symbol "d" in FIG. 8.

As shown in FIG. 10, after passing through the nip 62 the fibrous article 12 generally includes two areas 59 and 61. The first area 59, corresponds to that portion of the article 12 that has been compressed by the rolls 42 and 44 outside of the area of the recess 53. Area 59 preferably extends over a surface area of between about 7000 mm<sup>2</sup> and 14000 mm<sup>2</sup>, has a thickness in the range of about 4 mm to about 12 mm, and a density in the range of about 0.02 g/cc to about 0.1 g/cc. Area 61 of the article 12 is that portion of the article 12 corresponding in location to the recess 53. Area 61 preferably extends over a surface area of between about 1000 mm<sup>2</sup> and 7000 mm<sup>2</sup>, has a thickness in the range of about 10 mm to about 20 mm, and a density in the range of about 0.01 g/cc to about 0.04 g/cc.

It is noted that the fibrous article 12, after passing through the nip 62, has a three dimensional profile. Specifically, area 59 of the fibrous article defines a substantially planar portion of the fibrous article 12 and area 61 extends upwardly from the substantially planar portion thereby defining an upwardly extending hump or raised portion. In one preferred embodiment of the invention, as shown in FIG. 10, area 61 is symmetrically arranged with respect to longitudinally extending central axis 13 of the fibrous article and the transversely extending central axis 19 of the fibrous article 12.

It is noted that the fibrous article 12 has a three dimensional profile yet has a constant basis weight throughout its entire structure. Specifically, planar portion 59 and the raised portion 61 are both formed from a common material composition having a constant basis weight, yet differ in thickness and density. It is also noted that the entire fibrous article 12 is formed from a single material layer.

After the article 12 passes through the nip 62 the article 12 is further rotated in a clockwise direction by the cylinder 46 of the vacuum roll 43, and as will be described in further detail below, transferred to the pin calendering station 18.

As shown in FIGS. 1 and 11-18 the pin calendering station 18 generally includes a vacuum roll 64 and an opposed pin calender roll 65. As best seen in FIG. 12, the vacuum roll 64 is formed from a rotatable cylinder 66 that is rotatable about a fixed axis 68. Any conventional means to rotate the cylinder 66, well known to those of skill in the art, may be used to rotate the cylinder 66. The cylinder 66 rotates in a counter-clockwise direction during operation of the apparatus 10. As shown in FIG. 12, the cylinder 66 includes a plurality of holes 70 that extend from the outer surface 72 of the cylinder 66 to the inner surface 74 of the cylinder 66. In a preferred embodiment of the invention each of the plurality of holes 70 has a diameter of about 1.5 mm and is spaced from an adjacent hole by a distance of about 4 mm (center to center).

As shown in FIGS. 12 and 13 the pin calender roll 65 is structured and arranged to rotate about a fixed axis 67. Any conventional means to rotate the pin calender roll, well known to those of skill in the art, may be used to rotate the roll 65. As shown in FIGS. 13 and 14 the pin calender roll 65 has a roll surface 80 including a first area 69 having plurality of individual pins 78 that extend outwardly from a surface 80 of

the roll 65. As shown in FIG. 13, the first area 69 extends down a central portion of the roll surface 80. In a preferred embodiment of the invention, the first area 69 is structured and arranged to emboss a central region of the fibrous article 12. Alternatively, the first area 69 may be arranged to emboss substantially the entire fibrous article 12.

As best seen in FIG. 14, the surface 80 of the roll 65 is further provided with a first recess 77 and a second recess 79. Each of the first recess 77 and second recess 79 are structured and arranged to correspond in location to area 61 of the fibrous article 12 when the article 12 passes through the nip 92 defined between the vacuum roll 64 and the pin calender roll 65. Preferably each recess 77 and 79 extends over a surface area of between about 260 mm<sup>2</sup> and 1100 mm<sup>2</sup> and has a depth of between about 2 mm and 25 mm.

As shown in FIG. 14, in a preferred embodiment of the invention, each recess 77 and 79 is generally arcuate in shape and generally extends in a machine direction. Each recess 77 and 79 is preferably positioned on the roll 65 so that it is symmetrically arranged with respect to the other recess about the longitudinally extending central axis 13 of the fibrous article and the transversely extending central axis 19 of the fibrous article 12, as the article 12 passes through the through the nip 92 defined between the vacuum roll 64 and the pin calender roll 65.

Recess 77 is separated from recess 79 by a land area 81 that includes a plurality of pins 78. Preferably the land area 81 has a surface area of between about 250 mm<sup>2</sup> and 1000 mm<sup>2</sup>. The land area 81 is connected to the first area 67 by a first smooth roll surface segment 83 and second smooth roll surface segment 85, each of the segments 83 and 85 being preferably free of pins 78.

In preferred embodiments of the invention each of the pins 78 are spaced from an adjacent pin by a distance of about 4 mm (center to center), have height of about 1.5 mm and have an effective contact area of from about 0.8 mm<sup>2</sup> to about 1.2 mm<sup>2</sup>.

As shown in FIGS. 17 and 18, each of the pins 78 are arranged such that they do not overlap with any of the plurality of holes 70 in the cylinder 66 of the vacuum roll 64. This arrangement of the pins 78 relative to the holes 70 insures that no pulp is forced into any of the plurality of holes 70, thereby improving the efficiency of pulp use and the efficiency of the process as a whole.

As shown in FIGS. 11-12 and 17-18, the vacuum roll 64 further includes a vacuum chamber 86 arranged within the interior of the cylinder 66. The vacuum chamber 86 is arranged in a fixed location relative to the rotating cylinder 66 and is operably coupled to the vacuum source 57 (FIG. 1). The vacuum chamber 86 is arranged in flow communication with the plurality of holes 70 that extend through the cylinder 66 and thereby draws air through said holes 70.

As shown in FIG. 11, the vacuum chamber 86 is arranged such that its leading edge 88 is substantially aligned with a trailing edge 90 of the vacuum chamber 56 located within the cylinder 46 of the vacuum roll 42. This arrangement of the vacuum chamber 86 relative to the location of the vacuum chamber 56 effectuates a transfer of the formed fibrous article 12 from the vacuum roll 42 to the vacuum roll 64.

Once the formed fibrous article 12 has been transferred to the cylinder 66 of the vacuum roll 64, the cylinder 66 rotates the formed fibrous article 12 until the article 12 passes through the nip 92 formed by the vacuum roll 64 and the pin calender roll 65.

In a preferred embodiment of the invention the nip 92 has a distance (i.e. the distance between the surfaces of the opposed rolls) of about 0.8 mm. Also in a preferred embodi-

ment of the invention the pin calender roll **65** is heated to a temperature of between about 176° F. to about 212° F. by means of any suitable conventional heating means. It has been found that heating the pin calender roll **65** in this manner helps prevent the formed fibrous article **12** from adhering to the surface of the pin calender roll **65**.

After the article **12** passes through the nip **92** the article **12** is further rotated in a counter clockwise direction by the cylinder **66** of the vacuum roll **64** as shown and, as will be described in further detail below, transferred to the transfer wheel **20**.

As shown in FIG. **19** the transfer wheel **20** comprises a vacuum roll **94** that is formed from a rotatable cylinder **96** that is rotatable about a fixed axis **98**. Any conventional means to rotate the cylinder **96**, well known to those of skill in the art, may be used to rotate the cylinder **96**. The cylinder **96** rotates in a counterclockwise manner during operation of the apparatus **10**, as show in FIG. **1**. As shown in FIG. **20**, the cylinder **96** includes a plurality of holes **100** that extend from the outer surface **102** of the cylinder **96** to the inner surface **104** of the cylinder **96**.

As shown in FIGS. **19** and **20**, the vacuum roll **94** further includes a vacuum chamber **106** arranged within the interior of the cylinder **96**. The vacuum chamber **106** is arranged in a fixed location relative to the rotating cylinder **96** and is operably coupled to the vacuum source **57** (FIG. **1**). The vacuum chamber **106** is arranged in flow communication with the plurality of holes **100** that extend through the cylinder **96** and thereby draw air through said holes **100**.

The transfer wheel **20** further includes a porous conveyor belt **97** that extends around the cylinder **96** and travels with the cylinder **96**, i.e. in a clockwise direction shown in FIG. **20**.

As shown in FIG. **19**, the vacuum chamber **106** is arranged such that its leading edge **108** is substantially aligned with a trailing edge **110** of the vacuum chamber **86** located within the cylinder **66** of the vacuum roll **64**. This arrangement of the vacuum chamber **106** relative to the location of the vacuum chamber **86** effectuates a transfer of the formed fibrous article **12** from the vacuum roll **64** to the vacuum roll **94**. Specifically, formed fibrous article **12** is transferred to the conveyor belt **97** and held in place by the vacuum chamber **106** that functions to draw air through the porous conveyor belt **97** via the holes **100** in the cylinder **96**.

Once the fibrous article **12** is rotated past vacuum chamber **106**, the porous conveyor belt **97** functions to further convey the formed fibrous article **12** in a machine direction. The formed fibrous article **12** may be conveyed in a machine direction for incorporation into a final product structure such as a sanitary napkin, panty liner, incontinence article, diaper or the like.

Referring to FIGS. **21** and **22**, the completed fibrous article **12** generally includes an area **101** that has not been pin embossed, a first arcuate raised area **103**, a second arcuate raised area **105**, a pin embossed region **107** located between the raised area **103** and raised area **105**, and a centrally extending pin embossed area **109** extending along the longitudinally extending central axis **13** of the article **12**. Each of the pin embossed regions **107** and **109** include a plurality of depressions **111** corresponding in location to the pins **78**. Areas **101** and **109** cooperate to define a substantially planar portion of the fibrous article **12** and raised areas **103** and **105** extend upwardly relative to the planar portion of the fibrous article **12**.

After passing through the nip **92** area **101** preferably has a thickness in the range of about 0.8 mm to about 3.5 mm, a

density in the range of about 0.06 g/cc to about 0.5 g/cc, and extends over a surface area of from about 6400 mm<sup>2</sup> and 9400 mm<sup>2</sup>.

After passing through the nip **92** each of area **103** and **105** preferably has a thickness in the range of about 2 mm to about 10 mm and a density in the range of about 0.01 g/cc to about 0.1 g/cc. Each area **103** and **105** preferably extends over a surface area of from about 260 mm<sup>2</sup> and 1100 mm<sup>2</sup>.

After passing through the nip **92** area **107** preferably has a thickness in the range of about 0.2 mm to about 1 mm, a density in the range of about 0.1 g/cc to about 0.9 g/cc in those areas **111** embossed by the pins **78** and a thickness in the range of about 0.8 mm to about 3.5 mm and a density in the range of about 0.06 g/cc to about 0.5 g/cc in those areas outside of areas **111**. Area **107** preferably extends over a surface area of from about 250 mm<sup>2</sup> and 1000 mm<sup>2</sup>.

After passing through the nip **92** area **109** preferably has a thickness in the range of about 0.2 mm to about 1.0 mm and a density in the range of about 0.1 g/cc to about 0.9 g/cc in those areas **111** embossed by the pins **78** and a thickness in the range of about 0.8 mm to about 3.5 mm and a density in the range of about 0.06 g/cc to about 0.5 g/cc in those areas outside of areas **111**. Area **109** preferably extends over a surface area of from about 2400 mm<sup>2</sup> and 7600 mm<sup>2</sup>.

It is noted that although the different areas of the fibrous article **12** differ in density and thickness the fibrous article **12** has a uniform basis weight throughout its entire structure. It is further noted that although fibrous article **12** according to the present invention possesses at least one raised area, i.e. the article **12** possesses a three dimensional profile, the article **12** has a uniform basis weight. Preferred embodiments of the present invention also present the above characteristics while being formed from a uniform material composition. In addition, in preferred embodiments of the present invention, the fibrous article **12** is formed from a single material layer.

It is noted that the formed fibrous article **12** is formed and pin-calendered without the use of any "carrier layer". In addition, is noted that the fibrous article is transferred from the forming drum **14** to the calendering station **16** then to the pin calendering station **18** without the use of any "carrier layer". "Carrier layer" as used herein means any material layer used to support the fibrous article, such as a conveyor belt or an adjacent material layer such a rolled nonwoven layer or the like.

In connection with the various vacuum chambers disclosed herein any suitable vacuum source may be employed. In a preferred embodiment of the invention the vacuum source is an air blower having an air flow of about 2,200 cubic meters per hour.

Reference is made to FIGS. **23-24** which depict a disposable absorbent article **200** in accordance with the present invention. Although disposable absorbent articles according to the present invention will be described herein with reference to a sanitary napkin **200**, other disposable absorbent articles such as panty liners, adult incontinence articles, and diapers are considered within the scope of the present invention. As shown in FIG. **24**, the sanitary napkin **200** includes a liquid permeable cover layer **210**, an optional transfer layer **212**, an absorbent core **214** and a liquid impermeable barrier layer **216**. The absorbent core **214** layer is formed from a formed fibrous article **12** of the type described above.

As shown in FIG. **23**, the absorbent article **200** includes a raised area **213** that extends upwardly from the remaining body facing planar portion **215** of the napkin **200**. Specifically the raised area **213** extends upwardly from a top surface **217** of the planar portion **215**. Preferably, the raised area **213** extends upwardly a distance of about 2 mm to about 10 mm as

measured from the top surface **217** of the planar portion **215** and extends over a surface area of between about 1000 mm<sup>2</sup> and 7000 mm<sup>2</sup>. Preferably, the planar portion **215** extends over an area of between about 7000 mm<sup>2</sup> and 14000 mm<sup>2</sup>.

#### Main Body—Cover Layer

The cover layer **210** may be a relatively low density, bulky, high-loft non-woven web material. The cover layer **210** may be composed of only one type of fiber, such as polyester or polypropylene or it may include a mixture of more than one fiber. The cover may be composed of bi-component or conjugate fibers having a low melting point component and a high melting point component. The fibers may be selected from a variety of natural and synthetic materials such as nylon, polyester, rayon (in combination with other fibers), cotton, acrylic fiber and the like and combinations thereof. Preferably, the cover layer **210** has a basis weight in the range of about 10 gsm to about 75 gsm.

Bi-component fibers may be made up of a polyester layer and a polyethylene sheath. The use of appropriate bi-component materials results in a fusible non-woven fabric. Examples of such fusible fabrics are described in U.S. Pat. No. 4,555,430 issued Nov. 26, 1985 to Chicopee. Using a fusible fabric increases the ease with which the cover layer may be mounted to the absorbent layer(s) of the article and/or to the barrier layer **216**.

The cover layer **210** preferably has a relatively high degree of wettability, although the individual fibers comprising the cover may not be particularly hydrophilic. The cover material should also contain a great number of relatively large pores. This is because the cover layer **210** is intended to take-up body fluid rapidly and transports it away from the body and the point of deposition. Therefore, the cover layer contributes little to the time taken for the napkin **200** to absorb a given quantity of liquid (penetration time).

Advantageously, the fibers that make up the cover layer **210** should not lose their physical properties when they are wetted, in other words they should not collapse or lose their resiliency when subjected to water or body fluid. The cover layer **210** may be treated to allow fluid to pass through it readily. The cover layer **210** also functions to transfer the fluid quickly to the underlying layers of the absorbent article. Thus, the cover layer **210** is advantageously wettable, hydrophilic and porous. When composed of synthetic hydrophobic fibers such as polyester or bi-component fibers, the cover layer **210** may be treated with a surfactant to impart the desired degree of wettability.

In one preferred embodiment of the invention the cover layer **210** is made from a 27 gsm hot through air (HTA) bonded nonwoven material constructed from 100% bico fibers (PE/PET), commercially available from Shalag Industries A.C.S. Ltd., Kibbutz Shamir, Upper Galilee, Israel, under the commercial code STA4ETW27.

Alternatively, the cover layer **210** can also be made of a polymer film having large pores. Because of such high porosity, the film accomplishes the function of quickly transferring body fluid to the underlying layers of the absorbent article. A suitable cover material of this type is commercially found on the Stayfree Dry Max Ultrathin product distributed by McNeil-PPC, Inc.

The cover layer **210** may be embossed to the underlying absorbent layers in order to aid in promoting hydrophilicity by fusing the cover to the adjacent underlying layer. Such fusion may be effected locally, at a plurality of sites or over the entire contact surface of cover layer **210**. Alternatively, the cover layer **210** may be attached to the other layers of the article by other means such as by adhesion.

#### Main Body—Transfer Layer

Adjacent to the cover layer **210** on its inner side and bonded to the cover layer **210** is the optional transfer layer **212**. The transfer layer **212** provides means for receiving body fluid from the cover layer **210** and holding it until the underlying absorbent core **214** has an opportunity to absorb the fluid, and therefore acts as a fluid transfer or acquisition layer. The transfer layer **212** is, preferably, more dense than and has a larger proportion of smaller pores than the cover layer **210**. These attributes allow the transfer layer **212** to contain body fluid and hold it away from the outer side of the cover layer **210**, thereby preventing the fluid from rewetting the cover layer **210** and its surface. However, the transfer layer is, preferably, not so dense as to prevent the passage of the fluid through the layer **212** into the underlying absorbent core **214**.

The transfer layer **212** may be composed of fibrous materials, such as wood pulp, polyester, rayon, flexible foam, or the like, or combinations thereof. The transfer layer **212** may also comprise thermoplastic fibers for the purpose of stabilizing the layer and maintaining its structural integrity. The transfer layer **212** may be treated with surfactant on one or both sides in order to increase its wettability, although generally the transfer layer **212** is relatively hydrophilic and may not require treatment. The transfer layer **212** is preferably bonded or adhered on both sides to the adjacent layers, i.e. the cover layer **210** and the underlying absorbent core **214**.

Examples of suitable materials for the transfer layer **212** are through air bonded pulp sold by Buckeye Technologies of Memphis, Tenn., under the designation VIZORB 3008, which has a basis weight of 110 gsm, VIZORB 3042, which has a basis weight of 100 gsm, and VIZORB 3010, which has a basis weight of 90 gsm.

#### Main Body—Absorbent Core

Referring to FIG. 18, and as discussed above, the absorbent article **200** according to the present invention includes an absorbent core **214**. The absorbent core **214** consists of a formed fibrous article **12** of the type described herein above.

In one preferred embodiment of the invention, the absorbent core **214** is a blend or mixture of cellulosic fibers and superabsorbent disposed therein. Cellulosic fibers that can be used in the absorbent core **214** are well known in the art and include wood pulp, cotton, flax and peat moss. Wood pulp is preferred.

The absorbent core **214** can contain any superabsorbent polymer (SAP), which are well known in the art. For the purposes of the present invention, the term “superabsorbent polymer” (or “SAP”) refers to materials, which are capable of absorbing and retaining at least about 10 times their weight in body fluids under a 0.5 psi pressure. The superabsorbent polymer particles of the invention may be inorganic or organic crosslinked hydrophilic polymers, such as polyvinyl alcohols, polyethylene oxides, crosslinked starches, guar gum, xanthan gum, and the like. The particles may be in the form of a powder, grains, granules, or fibers. Preferred superabsorbent polymer particles for use in the present invention are crosslinked polyacrylates, such as the product offered by Sumitomo Seika Chemicals Co., Ltd. of Osaka, Japan, under the designation of SA70N and products offered by Stockhausen Inc.

The absorbent core **214** preferably has a total basis weight in the range of about 200 gsm to about 400 gsm. In preferred embodiments of the present invention the absorbent core **214** includes about 50%-100% pulp by weight and about 0% to about 50% superabsorbent by weight.

As described above in the description of the method of making the fibrous article **12** set forth above, and in reference to FIGS. 21 and 22, the absorbent core **214** generally includes

an area **101** that has not been pin embossed, a first arcuate raised area **103**, a second arcuate raised area **105**, a pin embossed region **107** located between the raised area **103** and raised area **105**, and a centrally extending pin embossed area **109**. Referring to FIG. **24**, it is noted that the region **107** located between the raised areas **103** and **105** is recessed related to the raised areas. That is, raised areas **103** and **105** have a greater thickness than region **107**.

As shown in FIG. **24**, the first arcuate raised area **103** and the second arcuate raised area **105** of the absorbent core **214** correspond in location, and help define, the raised area **213** of the napkin **200**. However, it is noted that the final shape of the raised area **213** of the napkin **200** is provided by a conventional embossing step (not shown in the figures) and thus the shape of the raised area **213** is not dictated solely by the shape of the first arcuate raised area **103** and the second arcuate raised area **105**. The raised area **213** of the napkin **200** may be formed to have any number of different shapes. For example, two alternate embodiments of the napkin **200a** and **200b** are depicted in FIGS. **25** and **26**. As shown, napkins **200a** and **200b** include raised areas **213** having different shapes than the napkin **200** shown in FIGS. **23** and **24**. Other shapes are also possible. In addition, although the napkin **200** is depicted as having only a single raised area **213** it is possible that the napkin could be provided with a plurality of such raised areas **213**.

All of the articles shown in FIGS. **23-26** use absorbent cores having raised areas **103** and **105** as shown in FIG. **21**, and the final shape of the raised area **213** has been modified merely by using a correspondingly shaped conventional embossing roll to emboss the napkin **200** after the various layers of the napkin **200** have been adhered to one another.

Referring to FIG. **24**, it is noted that the cover layer extends over the first arcuate raised area **103**, the second arcuate raised area **105**, as well as the region **107** located between the raised area **103** and raised area **105**. In this manner, the cover layer **210** generally includes a first portion **221** which is located in body facing planar portion **215** of the napkin **200** and is arranged in abutting surface to surface contact with the transfer layer **212** (or the absorbent core **214** if the transfer layer **212** is omitted), a pair of second regions **223** that are arranged in corresponding location to the arcuate raised areas **103** and **105** of the absorbent core **214**, and a third region **225** that is located between the arcuate raised areas **103** and **105** and is arranged in spaced relationship to the absorbent core **214**.

In one specific example of the invention, the absorbent core **214** consists of a 305 gsm fluff pulp and superabsorbent mixture, the mixture including about 89% fluff pulp by weight, commercially available as Golden Isles Fluff Pulp 420#HD 7% Moisture, from GP Cellulose, Brunswick, Ga., USA, and 11% superabsorbent polymer by weight, commercially available as Aqua Keep SA70N from Sumitomo Seika Chemicals Co., Ltd., Osaka, Japan.

#### Main Body—Barrier Layer

Underlying the absorbent core **214** is a barrier layer **216** comprising liquid-impervious film material so as to prevent liquid that is entrapped in the absorbent core **214** from egressing the sanitary napkin **200** and staining the wearer's undergarment. The barrier layer **216** is preferably made of polymeric film, although it may be made of liquid impervious, air-permeable material such as repellent-treated non-woven or micropore films or foams.

The barrier layer may be breathable, i.e., permits vapor to transpire. Known materials for this purpose include non-woven materials and microporous films in which microporosity is created by, inter alia, stretching an oriented film. Single or multiple layers of permeable films, fabrics, melt-blown materials, and combinations thereof that provide a tortuous

path, and/or whose surface characteristics provide a liquid surface repellent to the penetration of liquids may also be used to provide a breathable backsheets. The cover layer **210** and the barrier layer **216** are joined along their marginal portions so as to form an enclosure or flange seal that maintains the absorbent core **214** captive. The joint may be made by means of adhesives, heat-bonding, ultrasonic bonding, radio frequency sealing, mechanical crimping, and the like and combinations thereof.

In one specific example of the invention, the barrier layer consists of a liquid impermeable 24 gsm polyethylene film commercially available from Clopay do Brasil, Sau Paulo, SP, Brazil.

Positioning adhesive may be applied to a garment facing side of the barrier layer **216** for securing the napkin **200** to the garment during use. The positioning adhesive may be covered with removable release paper so that the positioning adhesive is covered by the removable release paper prior to use.

Absorbent articles of this invention may or may not include wings, flaps or tabs for securing the absorbent article to an undergarment. Wings, also called, among other things, flaps or tabs, and their use in sanitary protection articles is described in U.S. Pat. No. 4,687,478 to Van Tilburg; U.S. Pat. No. 4,589,876 also to Van Tilburg, U.S. Pat. No. 4,900,320 to McCoy, and U.S. Pat. No. 4,608,047 to Mattingly.

The sanitary napkin **200** of the present invention may be applied to the crotch by placing the garment-facing surface against the inside surface of the crotch of the garment. Various methods of attaching absorbent articles may be used. For example, chemical means, e.g., adhesive, and mechanical attachment means, e.g., clips, laces, ties, and interlocking devices, e.g., snaps, buttons, VELCRO (Velcro USA, Inc., Manchester, N.H.), zipper, and the like are examples of the various options available to the artisan.

Adhesive may include pressure sensitive adhesive that is applied as strips, swirls, or waves, and the like. As used herein, the term pressure-sensitive adhesive refers to any releasable adhesive or releasable tenacious means. Suitable adhesive compositions, include, for example, water-based pressure-sensitive adhesives such as acrylate adhesives. Alternatively, the adhesive composition may include adhesives based on the following: emulsion or solvent-borne adhesives of natural or synthetic polyisoprene, styrene-butadiene, or polyacrylate, vinyl acetate copolymer or combinations thereof; hot melt adhesives based on suitable block copolymers—suitable block copolymers for use in the invention include linear or radial co-polymer structures having the formula  $(A-B)_x$  wherein block A is a polyvinylarene block, block B is a poly(monoalkenyl) block, x denotes the number of polymeric arms, and wherein x is an integer greater than or equal to one. Suitable block A polyvinylarenes include, but are not limited to Polystyrene, Polyalpha-methylstyrene, Polyvinyltoluene, and combinations thereof. Suitable Block B poly(monoalkenyl) blocks include, but are not limited to conjugated diene elastomers such as for example polybutadiene or polyisoprene or hydrogenated elastomers such as ethylene butylene or ethylene propylene or polyisobutylene, or combinations thereof. Commercial examples of these types of block copolymers include Kraton™ elastomers from Shell Chemical Company, Vector™ elastomers from Dexco, Solprene™ from Enichem Elastomers and Stereon™ from Firestone Tire & Rubber Co.; hot melt adhesive based on olefin polymers and copolymers where in the olefin polymer is a terpolymer of ethylene and a co-monomers, such as vinyl acetate, acrylic acid, methacrylic acid, ethyl acrylate, methyl acrylate, n-butyl acrylate vinyl silane or maleic anhydride. Commercial examples of these types of polymers include

## 13

Ateva (polymers from AT plastics), Nucrel (polymers from DuPont), Escor (from Exxon Chemical).

Any or all of the cover layer **210**, transfer layer **212**, absorbent core **214**, barrier layer **216**, and adhesive layers may be colored. Such coloring includes, but is not limited to, white, black, red, yellow, blue, orange, green, violet, and mixtures thereof. Color may be imparted according to the present invention through dying, pigmentation, and printing. Colorants used according to the present invention include dyes and inorganic and organic pigments. The dyes include, but are not limited to, anthraquinone dyes (Solvent Red 111, Disperse Violet 1, Solvent Blue 56, and Solvent Green 3), Xanthene dyes (Solvent Green 4, Acid Red 52, Basic Red 1, and Solvent Orange 63), azine dyes (Jet black), and the like. Inorganic pigments include, but are not limited to, titanium dioxide (white), carbon black (black), iron oxides (red, yellow, and brown), chromium oxide (green), ferric ammonium ferrocyanide (blue), and the like.

Organic pigments include, but are not limited to diarylide yellow AAOA (Pigment Yellow 12), diarylide yellow AAOT (Pigment Yellow 14), phthalocyanine blue (Pigment Blue 15), lithol red (Pigment Red 49:1), Red Lake C (Pigment Red), and the like.

The sanitary napkin **200** may include other known materials, layers, and additives, such as, foam, net-like materials, perfumes, medicaments or pharmaceutical agents, moisturizers, odor control agents, and the like. The sanitary napkin **200** can optionally be embossed with decorative designs.

The sanitary napkin **200** may be packaged as unwrapped absorbent articles within a carton, box or bag. The consumer withdraws the ready-to-use article as needed. The sanitary napkin **200** may also be individually packaged (each absorbent article encased within an overwrap).

Also contemplated by the present invention are asymmetrical and symmetrical absorbent articles having parallel longitudinal edges, dog bone- or peanut-shaped, as well as articles having a tapered construction for use with thong-style undergarments.

From the foregoing description, one skilled in the art can ascertain the essential characteristics of this invention, and without departing from the spirit and scope thereof, can make various changes and modifications. Embodiments set forth by way of illustration are not intended as limitations on the variations possible in practicing the present invention.

## EXAMPLES

Specific inventive examples of the present invention, and comparative examples, are described below.

## Inventive Example #1

An example of a sanitary napkin according to the invention was constructed as follows. The body facing cover layer was constructed from a 27 gsm hot through air (HTA) bonded nonwoven material constructed from 100% bico fibers (PE/PET), commercially available from Shalag Industries A.C.S. Ltd., Kibbutz Shamir, Upper Galilee, Israel, under the commercial code STA4ETW27.

A 305 gsm formed fibrous absorbent core was arranged below the cover layer and was formed by the process described herein above with reference to FIGS. 1-21. The absorbent core had a composition of 89% by weight of pulp and 11% by weight of superabsorbent polymer. The pulp was Golden Isles Fluff Pulp 420#HD 7% Moisture, commercially available from GP Cellulose, Brunswick, Ga., USA. The

## 14

superabsorbent polymer was Aqua Keep SA70N commercially available from Sumitomo Seika Chemicals Co., Ltd., Osaka, Japan.

As described above with reference to FIGS. 21-22, the absorbent core (i.e. the formed fibrous article **12**) was formed to include an area **101** that was not been pin embossed, a first arcuate raised area **103**, a second arcuate raised area **105**, a pin embossed region **107** located between the raised area **103** and raised area **105**, and a centrally extending pin embossed area **109** extending along the longitudinally extending central axis of the article **12**, as shown in FIG. 21.

Area **101** had a thickness in the range of about 2 mm, a density of about 0.1 g/cc, and extended over a surface area of 6500 mm<sup>2</sup>.

Area **103** and **105** each had a thickness of 5 mm and a density of about 0.05 g/cc. Each area **103** and **105** extended over a surface area of 557 mm<sup>2</sup>.

Area **107** had a thickness of 0.2 mm and a density of 0.5 g/cc in those areas **111** embossed by the pins **78** and a density of 0.3 g/cc and a thickness of 1 mm in those areas outside of areas **111**. Area **107** extended over a surface area of 504 mm<sup>2</sup>.

Area **109** had a thickness of 0.2 mm and a density of 0.5 g/cc in those areas **111** embossed by the pins **78** and a thickness of 1 mm and a density of 0.3 g/cc in those areas outside of areas **111**. Area **109** extended over a surface area of 4300 mm<sup>2</sup>.

A barrier layer was arranged below the core and was formed from a 24 gsm polyethylene film commercially available from Clipay do Brasil, Sao Paulo, SP, Brazil.

Each of the layers of the sanitary napkin were adhered to one another using a conventional hot melt adhesive. After each of the layers were adhered to one another the sanitary napkin was passed through a conventional embossing process to form a raised area of the type shown in FIG. 23. Thus, the sanitary napkin included a planar portion **215** and a raised area **213** extending upwardly from the planar portion **215** as depicted in FIG. 23. The planar portion **215** extended over an area of 13000 mm<sup>2</sup> and the raised area **213** extended over an area of 2000 mm<sup>2</sup>. The sanitary napkin had a thickness of 2.2 mm in the planar portion **215** and a thickness of 4.7 mm in the raised area **213**.

## Inventive Example #2

An example of a sanitary napkin according to the invention was constructed as follows. The body facing cover layer was constructed from a 27 gsm hot through air (HTA) bonded nonwoven material constructed from 100% bico fibers (PE/PET), commercially available from Shalag Industries A.C.S. Ltd., Kibbutz Shamir, Upper Galilee, Israel, under the commercial code STA4ETW27.

A 305 gsm formed fibrous absorbent core was arranged below the cover layer and was formed by the process described herein above with reference to FIGS. 1-21. The absorbent core had a composition of 89% by weight of pulp and 11% by weight of superabsorbent polymer. The pulp was Golden Isles Fluff Pulp 420#HD 7% Moisture, commercially available from GP Cellulose, Brunswick, Ga., USA. The superabsorbent polymer was Aqua Keep SA70N commercially available from Sumitomo Seika Chemicals Co., Ltd., Osaka, Japan.

As described above with reference to FIGS. 21-22, the absorbent core (i.e. the fibrous article **12**) was formed to include an area **101** that was not been pin embossed, a first arcuate raised area **103**, a second arcuate raised area **105**, a pin embossed region **107** located between the raised area **103** and raised area **105**, and a centrally extending pin embossed area

**109** extending along the longitudinally extending central axis **13** of the article **12**, as shown in FIG. **21**.

Area **101** had a thickness in the range of about 3 mm, a density of about 0.09 g/cc, and extended over a surface area of 6500 mm<sup>2</sup>.

Area **103** and **105** each had a thickness of 6 mm and a density of about 0.04 g/cc. Each area **103** and **105** extended over a surface area of 557 mm<sup>2</sup>.

Area **107** had a thickness of 0.2 mm and a density of 0.5 g/cc in those areas **111** embossed by the pins **78** and a density of 0.3 g/cc and a thickness of 1 mm in those areas outside of areas **111**. Area **107** extended over a surface area of 504 mm<sup>2</sup>.

Area **109** had a thickness of 0.2 mm and a density of 0.5 g/cc in those areas **111** embossed by the pins **78** and a thickness of 1 mm and a density of 0.3 g/cc in those areas outside of areas **111**. Area **109** extended over a surface area of 4300 mm<sup>2</sup>.

Each of the layers of the sanitary napkin were adhered to one another using a conventional hot melt adhesive. After each of the layers were adhered to one another the sanitary napkin was passed through a conventional embossing process to form a raised area of the type shown in FIG. **23**. Thus, the sanitary napkin included a planar portion **215** and a raised area **213** extending upwardly from the planar portion **215** as depicted in FIG. **23**. The planar portion **215** extended over an area of 13000 mm<sup>2</sup> and the raised area **213** extended over an area of 2000 mm<sup>2</sup>. The sanitary napkin had a thickness of 3.3 mm in the planar portion **215** and a thickness of 5.8 mm in the raised area **213**.

#### Comparative Example #1

A comparative example, representative of the prior art, was construed as follows. The body facing cover layer was constructed from a 27 gsm hot through air (HTA) bonded non-woven material constructed from 100% bico fibers (PE/PET), commercially available from Shalag Industries A.C.S. Ltd., Kibbutz Shamir, Upper Galilee, Israel, under the commercial code STA4ETW27.

A 305 gsm fibrous absorbent core was arranged below the cover layer. The absorbent core had a composition of 89% by weight of pulp and 11% by weight of superabsorbent polymer. The pulp was Golden Isles Fluff Pulp 420#HD 7% Moisture, commercially available from GP Cellulose, Brunswick, Ga., USA. The superabsorbent polymer was Aqua Keep SA70N commercially available from Sumitomo Seika Chemicals Co., Ltd., Osaka, Japan. The absorbent core has a uniform thickness along its length of 2.2 mm and a uniform density along its length of 0.1 g/cc.

#### Comparative Example #2

A comparative example, representative of the prior art, was construed as follows. The body facing cover layer was constructed from a 27 gsm hot through air (HTA) bonded non-woven material constructed from 100% bico fibers (PE/PET), commercially available from Shalag Industries A.C.S. Ltd., Kibbutz Shamir, Upper Galilee, Israel, under the commercial code STA4ETW27.

A 305 gsm fibrous absorbent core was arranged below the cover layer. The absorbent core had a composition of 89% by weight of pulp and 11% by weight of superabsorbent polymer. The pulp was Golden Isles Fluff Pulp 420#HD 7% Moisture, commercially available from GP Cellulose, Brunswick, Ga., USA. The superabsorbent polymer was Aqua Keep SA70N commercially available from Sumitomo Seika Chemicals Co., Ltd., Osaka, Japan. The absorbent core has a

uniform thickness along its length of 3.3 mm and a uniform density along its length of 0.09 g/cc.

#### Test Procedures

Absorbent articles according to the present invention provide superior fluid handling characteristics. A number of test procedures are described below that highlight the fluid handling properties of absorbent articles according to the present invention. Prior to conducting any of the described test procedures described below the test product samples should be conditioned for two hours at 21+/-1° C. and 50+/-2% humidity.

#### Procedure for Measuring Fluid Penetration Time

Fluid Penetration Time is measured by placing a product sample to be tested under a Fluid Penetration Test orifice plate. The orifice plate consists of a 7.6 cm x 25.4 cm plate of 1.3 cm thick polycarbonate with an elliptical orifice in its center. The elliptical orifice measures 3.8 cm along its major axis and 1.9 cm along its minor axis. The orifice plate is arranged such that the center of the orifice is aligned with the intersection of the longitudinal and transverse axis of the article, i.e. at the center of the article.

Test fluid was made of the following mixture to simulate bodily fluids: 49.5% of 0.9% sodium chloride solution (VWR catalog #VW 3257-7), 49.05% Glycerin (Emery 917), 1% Phenoxyethanol (Clariant Corporation Phenoxetol™) and 0.45% Sodium Chloride (Baker sodium chloride crystal #9624-05).

A graduated 10 cc syringe containing 7 ml of test fluid is held over the orifice plate such that the exit of the syringe is held approximately 3 inches above the orifice. The syringe is held horizontally, parallel to the surface of the test plate. The fluid is then expelled from the syringe at a rate that allows the fluid to flow in a stream vertical to the test plate into the orifice and a stop watch is started when the fluid first touches the sample to be tested. The stop watch is stopped when a portion of the surface of the sample first becomes visible above the remaining fluid within the orifice. The elapsed time on the stop watch is the Fluid Penetration Time. The average Fluid Penetration Time (FPT) is calculated from taking the average of readings from three product samples.

#### Procedure for Measuring Rewet Potential

The three product samples used for the Fluid Penetration Time (FPT) procedure described above are used for the Rewet Potential test described below.

The rewet potential is a measure of the ability of a napkin or other article to hold liquid within its structure when the napkin contains a relatively large quantity of liquid and is subjected to external mechanical pressure. The rewet potential is determined and defined by the following procedure.

The apparatus for the Rewet Potential test is the same as that set forth above with regard to the FPT test and further includes a quantity of 3 inch x 4 (7.62 cm x 10.16 cm) inch rectangles of Whatman #1 filter paper from (Whatman Inc., Clifton, N.J.) and a weighing machine or balance capable of weighing to an accuracy of +/-0.001 g, a quantity of said Whatman paper, a standard weight of 2.22 kg (4.8 pounds) having dimensions 5.1 cm (2 inches) by 10.2 cm (4.0 inches) by approximately 5.4 cm (2.13 inches) which applies a pressure of 4.14 kPa (0.6 psi) over the 5.1 by 10.2 cm (2 inches by 4 inches) surface.

For purposes of the test procedure set forth herein, the same three product samples used for the fluid penetration test should be used for the rewet potential test. After the test fluid is applied within the orifice plate in the FPT test described above, and as soon as the cover layer of the napkin first appears through the top surface of the fluid, the stop watch is started and an interval of 5 minutes is measured.

After 5 minutes have elapsed, the orifice plate is removed and the napkin is positioned on a hard level surface with the cover layer facing upwards.

A fifteen (15) layer stack of the pre-weighed filter paper is placed on and centered over the wetted area and the standard 2.22 kg weight is placed on top of the filter paper. The filter paper and the weight are arranged over the absorbent article such that they are centered over the area to which the fluid was applied. The filter paper and the weight are arranged such that their longer dimensions are aligned with the longitudinal direction of the product. Immediately after placing the paper and weight on the product, the stopwatch is started and after a 3 minute interval has elapsed the standard weight and filter paper are quickly removed. The wet weight of the filter paper is measured and recorded to the nearest 0.001 grams. The rewet value is then calculated as the difference in grams between the weight of the wet 15 layers of filter paper and the dry 15 layers of filter paper. The average Rewet Potential is calculated from taking the average of readings from three product samples.

#### Procedure for Measuring the Thickness of a Sanitary Article

The apparatus required to measure the thickness of the sanitary napkin is a footed dial (thickness) gauge with stand, available from Ames, with a 2" (5.08 cm) diameter foot at a pressure of 0.07 psig (4.826 hPa) and a readout accurate to 0.001" (0.0254 mm). A digital type apparatus is preferred. If the sanitary napkin sample is individually folded and wrapped, the sample is unwrapped and carefully flattened by hand. The release paper is removed from the product sample and it is repositioned back gently across the positioning adhesive lines so as not to compress the sample, ensuring that the release paper lies flat across the sample. Flaps (if any) are not considered when taking the thickness reading.

The foot of the gauge is raised and the product sample is placed on the anvil such that the foot of the gauge is approximately centered on the location of interest on the product sample. When lowering the foot, care must be taken to prevent the foot dropping onto the product sample or undue force being applied. A load of 0.07 psig (4.826 hPa) is applied to the sample and the read out is allowed to stabilize for approximately 5 seconds. The thickness reading is then taken. This procedure is repeated for three product samples and the average thickness is then calculated.

The measured Fluid Penetration Time, Rewet Potential and Product Thickness of the Inventive Examples and Comparative Examples described above are summarized in the table set forth below.

	Thickness in Raised Area (mm)	Thickness in Planar Portion (mm)	Fluid Penetration Time (s)	Rewet (g)
Inventive Example #1	4.7	2.2	17	0.98
Inventive Example #2	5.8	3.3	11	0.96
Comparative Example #1	NA	2.2	52	0.82
Comparative Example #2	NA	3.3	25	1.43

As shown above, disposable absorbent articles according to the present provide superior fluid handling characteristics.

We claim:

1. A method of making a formed fibrous article comprising the steps of:

forming a formed fibrous article having a three dimensional profile;

pin-calendering the fibrous article in a pin calendering station between a first roll and a second roll, wherein the fibrous article is conveyed through a nip defined between the first roll and the second roll without the use of a carrier layer.

2. The method according to claim 1, wherein the step of forming a formed fibrous article having a three dimensional profile comprises the steps of:

forming a formed fibrous article: and

passing the formed fibrous article through a calendering station to thereby provide the formed fibrous article with the three dimensional profile.

3. The method according to claim 2, wherein the calendering station includes a vacuum roll and an opposed calender roll.

4. The method according to claim 3, wherein a surface of the calender roll includes at least one recess, the recess being structured and arranged to provide the formed fibrous article with the three dimensional profile.

5. The method according to claim 4, wherein the formed fibrous article having a three dimensional profile includes a planar portion and at least one raised portion extending upwardly relative to the planar portion.

6. The method according to claim 5, wherein the planar portion and the raised portion have each has a different thickness and a different density but have a constant basis weight.

7. The method according to claim 6, wherein the step of forming the fibrous article comprises the steps of:

providing fibrous pulp, maintaining the fibrous pulp in a chamber, mounting a mold to a rotating forming drum, rotating the mold on the rotating forming drum until the mold is arranged in communication with the chamber, and drawing the fibrous pulp into the mold to thereby form the fibrous article.

8. The method according to claim 7, wherein the first roll comprises a vacuum roll and the second roll comprises a pin calender roll.

9. The method according to claim 8, wherein a surface of the vacuum roll includes a plurality of holes and the pin calender roll includes a plurality of pins extending outwardly from a surface of the roll.

10. The method according to claim 9, wherein each one of the plurality of pins is arranged such that it does not overlap with any of the plurality of holes.

11. The method according to claim 10, wherein the pin calender roll includes a first area having a plurality the pins extending outwardly from the surface of the roll, a first recess, a second recess, a land area arranged between the first and second recess, the land area including a plurality of the pins extending outwardly from the surface of the roll.

12. The method according to claim 11, wherein the first recess, second recess and land area are structured and arranged to correspond in location to the raised portion of the formed fibrous article when the formed fibrous article passes through the pin calendering station.

13. The method according to claim 12, wherein the fibrous article is formed in the mold and transferred to the calendering station without the use of a carrier layer.

**19**

**14.** The method according to claim **13**, further comprising: transferring the fibrous article from the vacuum roll of the calendering station to the vacuum roll of the pin calendering station.

**15.** The method according to claim **14**, wherein the fibrous article is transferred from the vacuum roll of the calendering station to the vacuum roll of the pin calendering station without the use of a carrier layer.

**20**

**16.** The method according to claim **15**, further comprising transferring the fibrous article from the vacuum roll of the pin calendering station to a transfer wheel.

**17.** The method according to claim **16**, wherein the transfer wheel includes a vacuum roll and a porous conveyor belt that extends around the vacuum roll.

\* \* \* \* \*