

US008540915B2

(12) **United States Patent**  
**Scherer**

(10) **Patent No.:** **US 8,540,915 B2**  
(45) **Date of Patent:** **\*Sep. 24, 2013**

(54) **CONCRETE BLOCK AND METHOD OF MAKING SAME**

(75) Inventor: **Ronald J. Scherer**, Shakopee, MN (US)

(73) Assignee: **Anchor Wall Systems, Inc.**,  
Minnetonka, MN (US)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **13/360,235**

(22) Filed: **Jan. 27, 2012**

(65) **Prior Publication Data**

US 2012/0175808 A1 Jul. 12, 2012

**Related U.S. Application Data**

(63) Continuation of application No. 12/639,732, filed on Dec. 16, 2009, now Pat. No. 8,128,851, which is a continuation of application No. 11/697,067, filed on Apr. 5, 2007, now Pat. No. 7,807,083, which is a continuation of application No. 10/359,525, filed on Feb. 5, 2003, now Pat. No. 7,208,112, which is a continuation-in-part of application No. 10/038,639, filed on Jan. 4, 2002, now Pat. No. 7,140,867.

(51) **Int. Cl.**  
**B28B 3/00** (2006.01)  
**B29C 33/38** (2006.01)  
**G06F 19/00** (2011.01)

(52) **U.S. Cl.**  
USPC ..... **264/219**; 264/236; 264/293; 264/297.9;  
264/314; 264/318; 264/333; 264/334; 700/117;  
700/164; 700/197

(58) **Field of Classification Search**

USPC ..... 264/219, 236, 293, 297.9, 314, 318,  
264/333, 334; 700/117, 164, 197

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

415,773 A 11/1889 Fiske  
799,754 A 9/1905 Petrie

(Continued)

FOREIGN PATENT DOCUMENTS

DE 196 34 499 A1 3/1998  
DE 100 02 390 A1 7/2001

(Continued)

OTHER PUBLICATIONS

Canadian Office Action cited in 2,472,224 mailed Jun. 25, 2009.

(Continued)


*Primary Examiner* — Leo B Tentoni

(74) *Attorney, Agent, or Firm* — Merchant & Gould P.C.

(57) **ABSTRACT**

Molds and processes that permit high-speed, mass production of retaining wall blocks having patterned or other processed front faces, as well as retaining wall blocks formed by such processes. The invention permits the front face of the block to be impressed with a pattern or otherwise directly processed, to allow the formation of pre-determined block front faces, while at the same time facilitating high-speed, high-volume production of blocks. A mirror image of the desired pattern can be created on a stripper shoe by selecting a desired three-dimensional surface from a naturally occurring or man made object and digitally scanning the selected three-dimensional pattern to create scanned data. The scanned data can then be used to machine a face of the stripper shoe that is the mirror image of the selected pattern.

**20 Claims, 19 Drawing Sheets**



(56)

References Cited

U.S. PATENT DOCUMENTS

803,014 A 10/1905 McIlravy  
 813,901 A 2/1906 Leming et al.  
 819,055 A 5/1906 Fisher  
 824,235 A 6/1906 Damon  
 838,278 A 12/1906 Schwartz  
 1,086,975 A 2/1914 Aaronson  
 1,166,312 A 12/1915 Barten  
 1,564,490 A 12/1925 Parkhurst  
 1,574,125 A 2/1926 Sharpe  
 1,596,165 A 8/1926 Evans  
 1,693,852 A 12/1928 McQuain  
 1,776,999 A 9/1930 Jensen  
 1,982,730 A 12/1934 Erkman  
 2,038,205 A 4/1936 Case  
 2,313,363 A 3/1943 Schmitt  
 2,457,368 A 12/1948 Hanson  
 2,517,432 A 8/1950 Hornberger  
 2,682,093 A 6/1954 Clanton  
 2,819,495 A 1/1958 Krausz  
 2,882,689 A 4/1959 Huch et al.  
 3,013,321 A 12/1961 McElroy  
 3,204,316 A 9/1965 Jackson  
 3,277,551 A 10/1966 Sekiguchi  
 3,425,105 A 2/1969 Gulde  
 3,530,553 A 9/1970 Engle et al.  
 3,669,402 A 6/1972 Paulson  
 3,694,128 A 9/1972 Foxen  
 3,702,180 A \* 11/1972 Jones ..... 249/188  
 3,731,899 A 5/1973 Nuzzo  
 3,809,049 A 5/1974 Fletcher et al.  
 3,918,877 A 11/1975 Pickett  
 3,940,229 A 2/1976 Hutton  
 3,981,953 A 9/1976 Haines  
 4,050,864 A 9/1977 Komaki  
 4,063,866 A 12/1977 Lurbiecki  
 4,178,340 A 12/1979 Hyytinen  
 4,272,230 A 6/1981 Abate  
 4,335,549 A 6/1982 Dean, Jr.  
 4,738,059 A 4/1988 Dean, Jr.  
 D298,463 S 11/1988 Forsberg  
 4,784,821 A 11/1988 Leopold  
 4,802,836 A 2/1989 Whissell  
 4,869,660 A 9/1989 Ruckstuhl  
 4,902,211 A 2/1990 Svanholm  
 4,909,717 A 3/1990 Pardo  
 4,920,712 A 5/1990 Dean, Jr.  
 5,002,817 A 3/1991 Jones  
 D317,048 S 5/1991 Forsberg  
 D317,209 S 5/1991 Forsberg  
 D319,885 S 9/1991 Blomquist et al.  
 D321,060 S 10/1991 Blomquist et al.  
 5,056,998 A 10/1991 Goossens  
 5,078,940 A 1/1992 Sayles  
 5,082,438 A 1/1992 Rook et al.  
 5,133,915 A 7/1992 Metten et al.  
 5,183,616 A 2/1993 Hedrick  
 5,249,950 A 10/1993 Woolford  
 D341,215 S 11/1993 Blomquist et al.  
 D350,611 S 9/1994 Scales

D352,789 S 11/1994 Adam  
 5,366,676 A 11/1994 Kobayashi  
 5,435,949 A 7/1995 Hwang  
 D363,787 S 10/1995 Powell  
 5,484,236 A 1/1996 Gravier  
 5,534,214 A 7/1996 Sakamoto et al.  
 5,598,679 A 2/1997 Orton et al.  
 5,651,912 A 7/1997 Mitsumoto et al.  
 D391,376 S 2/1998 Strand et al.  
 5,744,081 A 4/1998 Tanigawa et al.  
 5,756,131 A 5/1998 Suh  
 5,816,749 A 10/1998 Bailey, II  
 5,827,015 A 10/1998 Woolford et al.  
 5,895,624 A \* 4/1999 Reece et al. .... 264/318 X  
 5,942,181 A 8/1999 Rondeau  
 6,159,401 A 12/2000 Hoesch  
 D438,640 S 3/2001 Bolles et al.  
 6,205,728 B1 3/2001 Sutelan  
 6,321,740 B1 11/2001 Scherer et al.  
 6,425,751 B1 7/2002 Bergeron et al.  
 D482,133 S 11/2003 Scherer et al.  
 6,773,642 B1 8/2004 Wardell  
 6,814,906 B2 \* 11/2004 Bergeron et al. .... 264/333 X  
 D511,578 S 11/2005 Mugge et al.  
 D518,578 S 4/2006 Mugge et al.  
 D529,628 S 10/2006 Mugge et al.  
 D532,910 S 11/2006 Mugge et al.  
 7,140,867 B2 11/2006 Scherer et al.  
 D538,946 S 3/2007 Mugge et al.  
 7,208,112 B2 4/2007 Scherer  
 D541,950 S 5/2007 Mugge et al.  
 7,458,800 B2 12/2008 Scherer et al.  
 7,807,083 B2 10/2010 Scherer  
 8,128,851 B2 3/2012 Scherer  
 2003/0182011 A1 9/2003 Scherer  
 2004/0218985 A1 11/2004 Klettenberg et al.

FOREIGN PATENT DOCUMENTS

EP 1 117 021 A2 7/2001  
 GB 944066 12/1963  
 GB 2 232 114 A 12/1990  
 JP 57-135106 8/1982  
 JP 62-182706 11/1987  
 JP 6-50804 7/1994  
 JP 2001-347511 12/2001  
 WO WO 01/53612 A1 7/2001  
 WO WO 03/060251 A1 7/2003

OTHER PUBLICATIONS

Japanese Office Action cited in 2003-560323 mailed Oct. 28, 2008.  
 Japanese Office Action cited in 2006-503140 mailed Jan. 26, 2010.  
 "Kobra Slab Molds: Optimum Slab Production on Big Board Machines, Design and benefits," *KOBRA*, 2 pages (Date Unknown).  
 "Slab Molds, Dream Molds," *KOBRA Formen GmbH*, 2 pages (Date Unknown).  
 Kobra Formen website print out, printed Feb. 13, 2002 from www.kobra-formen.de, 4 pages.  
 Pending claims from U.S. Appl. No. 11/697,067, filed Apr. 5, 2007.  
 Pending claims from U.S. Appl. No. 12/268,145, filed Nov. 10, 2008.

\* cited by examiner







FIG. 2

FIG. 3

FIG. 1

FIG. 3A

FIG. 4





FIG. 5






FIG. 6




FIG. 7





FIG. 8



FIG. 9






FIG. 10A




FIG. 10B




FIG. 10C




FIG. 10D




FIG. 10E




FIG. 10F




FIG. 11



FIG. 12





FIG. 13






FIG. 14A




FIG. 14B



FIG. 14C

1

## CONCRETE BLOCK AND METHOD OF MAKING SAME

### RELATED APPLICATION

This application is a continuation of U.S. patent application Ser. No. 12/639,732, filed Dec. 16, 2009, and issued as U.S. Pat. No. 8,128,851, which is a continuation of application Ser. No. 11/697,067, filed Apr. 5, 2007, issued as U.S. Pat. No. 7,807,083. U.S. application Ser. No. 11/697,067 is a continuation of U.S. application Ser. No. 10/359,525, filed Feb. 5, 2003 and issued as U.S. Pat. No. 7,208,112. U.S. application Ser. No. 10/359,525 is a continuation-in-part of U.S. application Ser. No. 10/038,639, filed Jan. 4, 2002 and issued as U.S. Pat. No. 7,140,867. Each of application Ser. Nos. 2/639,732; 11/697,067; 10/359,525; and 10/038,639 is incorporated by reference herein in their entireties.

### FIELD OF THE INVENTION

The invention relates generally to concrete blocks and the manufacture thereof. More specifically, the invention relates to concrete blocks suitable for use in landscaping applications, such as retaining walls, and manufacturing processes useful in the production of such blocks.

### BACKGROUND OF THE INVENTION

Modern, high speed, automated concrete block plants and concrete paver plants make use of molds that are open at the top and bottom. These molds are mounted in machines which cyclically station a pallet below the mold to close the bottom of the mold, deliver dry cast concrete into the mold through the open top of the mold, densify and compact the concrete by a combination of vibration and pressure, and strip the mold by a relative vertical movement of the mold and the pallet.

Due to the nature of such plants and the equipment used to perform this process, it is difficult to impart a natural appearance to the face of a concrete block, particularly if the block needs to include other features, such as converging side walls, and an integral locator and shear flange(s) formed on the top and/or bottom face of the block. U.S. Pat. No. 5,827,015, which is incorporated herein by reference, discloses such a concrete block suitable for use as a retaining wall block, and the common method for producing such a block in a high speed, automated concrete block plant.

There is demand for a pre-formed concrete unit, particularly a retaining wall block with converging side walls and/or an integral locator and shear flange formed on the top and/or bottom face, and having a more natural appearing face than is achievable by the splitting process described in U.S. Pat. No. 5,827,015, or by the splitting process described in U.S. Pat. No. 6,321,740, which is also incorporated herein by reference. In particular, there is a demand for processes and tooling that will create such blocks with such faces in high-speed, automated fashion on the type of equipment commonly available in a concrete block or concrete paver plant.

### SUMMARY OF THE INVENTION

The invention relates to molds and processes that permit high speed, mass production of concrete units, and, in particular, retaining wall blocks. These molds and processes can be used to create relatively simple decorative front faces on such blocks, similar to the split faces described in U.S. Pat. No. 5,827,015. These molds and processes can also be used to create more complex front faces on such blocks, similar to the

2

split and distressed faces produced by conventional tumbling or hammermill processing, or by the process described in U.S. Pat. No. 6,321,740. These molds and processes can also be used to create unique blocks that have heretofore not been available: retaining wall blocks with converging side walls and/or integral locator and shear flanges and with front faces with significantly more complex faces, including faces with significant detail and relief not heretofore available in dry cast concrete block technology.

In a preferred embodiment, the resulting blocks have patterned front faces that simulate natural stone, as well as upper and lower faces, a rear face, opposed converging side faces, and a flange extending below the lower face. Blocks having this construction, when stacked in multiple courses with other similarly constructed retaining wall blocks, permits construction of serpentine or curved retaining walls that appear to have been constructed with naturally-occurring, rather than man-made, materials.

One aspect of this invention is that a mold made in accordance with the invention is arranged so that the portion of the block that will be the front face when the block is laid is facing the open top of the mold cavity during the molding process. This orientation permits the front face of the block to be formed by the action of a patterned pressure plate ("stripper shoe") in a high-speed, concrete block or paver plant. The stripper shoe can be provided with a very simple pattern, a moderately complex pattern, or a highly detailed, three-dimensional pattern with significant relief, simulating naturally occurring stone. Molding the block in this orientation also makes the block face readily accessible for other processing to affect the appearance of the face, including the application of specially-selected aggregate and/or color pigments to the face.

Another aspect of this invention is that a side wall of the mold has an undercut portion adjacent the open bottom of the mold cavity. This undercut portion cooperates with the pallet that is positioned under the mold to form a subcavity of the mold. In a preferred embodiment, this subcavity forms the locator and shear flange on the surface of the block that will be the bottom of the block as laid.

Another aspect of this invention is that at least one of the side walls of the mold is angled from vertical, to form a side wall of the block as laid that includes a portion that converges toward the opposite side wall as it gets closer to the rear face of the block. This angled mold side wall is moveable, so that it moves into a first position to permit the mold to be filled with dry cast concrete and the concrete to be compacted and densified, and moves into a second position to permit the densified concrete to be stripped from the mold without interference from this mold side wall. In a preferred embodiment, the opposed mold side wall is similarly moveable, so that at least portions of the opposed side walls of the resulting block converge towards each other as they approach the rear of the block.

These and various other advantages and features of novelty which characterize the invention are pointed out with particularity in the claims annexed hereto and forming a part hereof. However, for a better understanding of the invention, its advantages and objects obtained by its use, reference should be made to the drawings which form a further part hereof, and to the accompanying description, in which there is described a preferred embodiment of the invention.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of a retaining wall block according to the present invention, with the block being oriented in the position in which it is formed in the mold.

FIG. 2 is a bottom plan view of the retaining wall block of FIG. 1.

FIG. 3 is a side elevation view of the retaining wall block of FIG. 1.

FIG. 3A is a detailed view of the portion of the retaining wall block contained within the dashed circle in FIG. 3.

FIG. 4 is a front view of a portion of a retaining wall constructed from a plurality of blocks according to the present invention.

FIG. 5 is a flow chart illustrating the process of forming the block of the present invention.

FIG. 6 is a perspective view of a mold assembly having a plurality of mold cavities for forming a plurality of retaining wall blocks of the present invention utilizing the process of the present invention.

FIG. 7 is a top plan view of the mold assembly of FIG. 6.

FIG. 8 is an end view of the mold assembly illustrating one mold cavity with opposed, converging, pivoted side walls.

FIG. 9 is a schematic representation of the side walls that form the upper and lower block faces, the stripper shoe, and the pallet of the mold assembly.

FIGS. 10A, 10B, 10C, 10D, 10E and 10F are digital renditions of representative patterns on the faces of stripper shoes according to the present invention.

FIG. 11 is a perspective view of a representative pattern on the face of a stripper shoe.

FIG. 12 is a flow chart illustrating the process of forming a stripper shoe face of the present invention.

FIG. 13 is a schematic illustration of the temperature control for the stripper shoe.

FIGS. 14A, 14B and 14C are photographs of retaining wall blocks according to the present invention.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

##### Overview

The present invention provides a process for producing a concrete block, as well as a block resulting from the process, and a mold and mold components used to implement the process, in which a pre-determined three-dimensional pattern is impressed into the face of the block, and the front face of the block can be otherwise directly processed or worked so that a pre-determined block front face can be produced in a standard dry cast concrete block or paver machine. Direct processing or working of the front face includes molding, shaping, patterning, impressing, material layering, combinations thereof, and other processes in which the texture, shape, color, appearance, or physical properties of the front face can be directly affected. Further, the process can be implemented using multiple-cavity molds to permit high-speed, high-volume production of the concrete blocks on standard dry cast concrete block or paver equipment. Moreover, use of the inventive process and equipment eliminates the need for a splitting station, and/or a hammermill station, and/or a tumbling station, and the additional equipment and processing costs associated with such additional processing stations.

The blocks produced by the process of the present invention can have a configuration that allows construction of walls, including serpentine or curved retaining walls, by stacking a plurality of blocks, having the same or different pre-determined front faces, in multiple courses, with an automatic set-back and shear resistance between courses.

The preferred embodiment will be described in relation to the impressing of a pre-determined, three-dimensional, rock-like pattern into the front face of a retaining wall block. As a result, the block, and a wall that is constructed from a plurality

of the blocks when stacked into courses, appears to have been constructed with "natural" materials. The process described herein could also be used to construct concrete blocks that are used in the construction of building walls, as well as for concrete bricks, slabs and pavers.

##### Concrete Block

A concrete block 10 according to the present invention is illustrated in FIGS. 1-3. The block 10 comprises a block body having a front face 12, a rear face 14, an upper face 16, a lower face 18, and opposed side faces 20, 22. (Note that the terms front, rear, upper, and lower faces reference the orientation of the faces of the block as placed within a retaining wall and do not necessarily reflect the orientation of the block as it is produced.) The block 10 is formed from a cured, dry cast, no slump concrete. Dry cast, no slump concrete is well known in the art of retaining wall blocks.

The front face 12, as shown in FIGS. 1-3, is provided with a pre-determined three-dimensional pattern. The pattern on the front face 12 is preferably imparted to the front face during molding of the block 10 by the action of a moveable stripper shoe (to be later described) having a pattern that is the mirror image of the front face of the block. FIGS. 14A-C are photos of blocks according to the present invention having patterned front faces.

The pattern that is imparted to the front face 12 can vary depending upon the desired appearance of the front face. Preferably, the pattern simulates natural stone so that the front face 12 appears to be a natural material, rather than a man-made material. The particular stone pattern that is used will be selected based on what is thought to be visually pleasing to users of the blocks. By way of example, the face of the block can be impressed with a pattern that appears to be a single stone, such as river rock. Or the block can be impressed with a pattern that appears to be multiple river rocks in a mortared together pattern. Or the block can be impressed with a pattern that simulates a single piece of quarry rubble, or multiple pieces of field stone, stacked in layers. Endless possibilities are available. By providing stripper shoes with a variety of different patterns, the resulting patterns on the blocks can be varied by changing stripper shoes.

The resulting detail and relief that can be provided on the front face is greater than that which can be provided on a front face of a block that results from conventional splitting techniques, and the tumbling, hammermilling and other distressing techniques previously described. The relief on the patterned front face 12, measured from the lowest point to the highest point, is preferably at least 0.5 inches, and more preferably at least 1.0 inches.

In the preferred embodiment, the front face 12 lies generally in approximately a single plane between the side faces 20, 22, as opposed to the common, three-faceted and curved faces that are frequently seen in split-face retaining wall blocks, although such multi-faceted and curved faces can be easily produced with the present invention. As shown in FIG. 3, the front face 12 is provided with a slight rearward slant, i.e. inclined at an angle  $\alpha$  from the bottom lower face 18 to the upper face 16. Preferably,  $\alpha$  is about 10 degrees. As a result, front and rear faces 12, 14 are separated by a distance  $d_1$  adjacent the lower face 18 and by a distance  $d_2$  adjacent the upper face 16, with  $d_1$  being larger than  $d_2$ . In the preferred embodiment,  $d_1$  is about 7.625 inches and  $d_2$  is about 6.875 inches. The width  $d_3$  is preferably about 12.0 inches. It is also contemplated that the front face 12 between the side faces 20, 22 can be faceted, curved, or combinations thereof. In these embodiments, the front face would also have a slight rearward slant.

## 5

Typically, when retaining wall blocks are stacked into set-back courses to form a wall, a portion of the upper face of each block in the lower course is visible between the front face of each block in the lower course and the front face of each block in the adjacent upper course. The visible portions of the upper faces create the appearance of a ledge. And, in the case of dry cast concrete blocks, this ledge typically has an artificial appearance. By providing a rearward incline angle to the front face **12** of the block **10**, the appearance of the ledge can be reduced or eliminated, thus enhancing the “natural” appearance of the resulting wall.

The front face **12** also includes radiused edges **24a**, **24b** at its junctures with the side faces. The radiused edges **24a**, **24b** are formed by arcuate flanges provided on the stripper shoe. The radius of the edges **24a**, **24b** is preferably about 0.25 inches. The radiused edges **24a**, **24b** shift the contact points between the sides of the block **10** with adjacent blocks in the same course, when a plurality of blocks are laid side-by-side, away from the front face **12**, and result in better contact between the blocks to prevent soil “leakage” between adjacent blocks. If desired, the top and bottom edges at the junctures between the front face **12** and the upper and lower faces **16**, **18** could also be radiused, similar to the radiused edges **24a**, **24b**, by the provision of arcuate flanges on the stripper shoe.

With reference to FIGS. 1-3, the rear face **14** of the block **10** is illustrated as being generally planar between the side faces **20**, **22** and generally perpendicular to the upper and lower faces **16**, **18**. However, it is contemplated that the rear face **14** could deviate from planar, such as by being provided with one or more notches or provided with one or more concavities, while still being within the scope of the invention. The width  $d_4$  of the rear face **14** is preferably about 8.202 inches.

Further, the upper face **16** is illustrated in FIGS. 1-3 as being generally planar, and free of cores intersecting the upper face **16**. When a plurality of blocks **10** is stacked into courses to form a wall structure, the upper face **16** of each block is in a generally parallel relationship to the upper faces **16** of the other blocks.

The lower face **18** of the block **10** is formed so as to be suitable for engaging the upper face **16** of the block(s) in the course below to maintain the generally parallel relationship between the upper faces of the blocks **10** when the blocks are stacked into courses. In the preferred embodiment, as illustrated in FIGS. 1-3, the lower face **18** is generally planar and horizontal so that it is generally parallel to the upper face **16**. However, other lower faces can be used, including a lower face that includes one or more concave portions or one or more channels over portions of the lower face **18**. The distance  $d_6$  between the upper face **16** and the lower face **18** is preferably about 4.0 inches.

In the preferred block **10**, the side faces **20**, **22** are generally vertical and join the upper and lower faces **16**, **18** and join the front and rear faces **12**, **14**, as seen in FIGS. 1-3. At least a portion of each side face **20**, **22** converges toward the opposite side face as the side faces extend toward the rear face **14**. Preferably the entire length of each side face **20**, **22** converges starting from adjacent the front face **18**, with the side faces **20**, **22** being generally planar between the front and rear faces **12**, **14**. However, it is possible that the side faces **20**, **22** could start converging from a location spaced from the front face **12**, in which case the side faces **20**, **22** would comprise a combination of straight, non-converging sections extending from the front face and converging sections leading from the straight sections to the rear face **14**. The converging portion of each side face **20**, **22** preferably converges at an angle  $\beta$  of about 14.5 degrees.

## 6

Alternatively, the block **10** can be provided with only one converging side face or side face portion, with the other side face being substantially perpendicular to the front and rear faces **12**, **14**. A block with at least one converging side face permits serpentine retaining walls to be constructed.

The block **10** also preferably includes a flange **26** that extends below the lower face **18** of the block, as seen in FIGS. 1-3. The flange **26** is designed to abut against the rear face of a block in the course below the block **10** to provide a predetermined set-back from the course below and provide course-to-course shear strength.

With reference to FIG. 3A, it is seen that the flange **26** includes a front surface **28** that engages the rear face of the block(s) in the course below. The flange **26** also includes a bottom surface **30**, a front, bottom edge **32** between the front surface **28** and the bottom surface **30** that is arcuate, and a rear surface **34** that is extension of, and forms a portion of, the rear face **14** of the block. The front surface **28** is preferably angled at an angle  $\gamma$  of about 18 degrees. The angled front surface **28** and the arcuate edge **32** result from corresponding shaped portions of the mold, which construction facilitates filling of the mold with dry cast concrete and release of the flange **26** from the mold.

As shown in FIGS. 1 and 2, the flange **26** extends the entire distance between the side faces **20**, **22**. However, the flange need not extend the entire distance. For example, the flange could extend only a portion of the distance between the side faces, and be spaced from the side faces. Alternatively, two or more flange portions separated from each other by a gap could be used.

With reference to FIG. 3A, the depth  $d_7$  of the flange **26** is preferably about 0.750 inches. This depth defines the resulting set-back of the block relative to the course below. Other flange dimensions could be used, depending upon the amount of desired set-back. The rear surface **34** preferably has a height  $d_8$  of about 0.375 inches.

The concepts described can also be applied to concrete blocks that are used in the construction of building walls, as well as to concrete bricks, slabs and pavers. In these cases, it is contemplated and within the scope of the invention that neither side face of the block or brick would converge, and that the flange would not be present. However, the patterned front face would provide the block or brick a decorative appearance.

## Block Structures

The concrete block **10** of the present invention may be used to build any number of landscape structures. An example of a structure that may be constructed with blocks according to the invention is illustrated in FIG. 4. As illustrated, a retaining wall **40** composed of individual courses **42a-c** of blocks can be constructed. The blocks used in constructing the wall **40** can comprise blocks having identically patterned front faces, or a mixture of blocks with different, but compatibly-patterned faces. The height of the wall **40** will depend upon the number of courses that are used. The construction of retaining walls is well known in the art. A description of a suitable process for constructing the wall **40** is disclosed in U.S. Pat. No. 5,827,015.

As discussed above, the flange **26** on the block **10** provides set-back of the block from the course below. As a result, the course **42b** is set-back from the course **42a**, and the course **42c** is set-back from the course **42b**. Further, as discussed above, the rearward incline of the front face **12** reduces the ledge that is formed between each adjacent course, by reducing the amount of the upper face portion of each block in the lower



course that is visible between the front face of each block in the lower course and the front face of each block in the adjacent upper course.

The retaining wall **40** illustrated in FIG. **4** is straight. However, the preferred block **10** construction with the angled side faces **20**, **22** permits the construction of serpentine or curved retaining walls, such as is disclosed in U.S. Pat. No. 5,827,015.

#### Block Forming Process

An additional aspect of the invention concerns the process for forming the block **10**. With reference to FIG. **5**, an outline of the process is shown. Generally, the process is initiated by mixing the dry cast concrete that will form the block **10**. Dry cast, no slump concrete is well known in the art of retaining wall blocks. The concrete will be chosen so as to satisfy pre-determined strength, water absorption, density, shrinkage, and related criteria for the block so that the block will perform adequately for its intended use. A person having ordinary skill in the art would be able to readily select a material constituency that satisfies the desired block criteria. Further, the procedures and equipment for mixing the constituents of the dry cast concrete are well known in the art.

Once the concrete is mixed, it is transported to a hopper, which holds the concrete near the mold. As discussed below, the mold assembly **50** includes at least one block-forming cavity **56** suitable for forming the preferred block (see FIGS. **6-11**). The cavity **56** is open at its top and bottom. When it is desired to form a block, a pallet is positioned beneath the mold so as to close the bottom of the cavity **56**. The appropriate amount of dry cast concrete from the hopper is then loaded, via one or more feed drawers, into the block-forming cavity through the open top of the cavity **56**. The process and equipment for transporting dry cast concrete and loading a block-forming cavity are well known in the art.

The dry cast concrete in the cavity **56** must next be compacted to densify it. This is accomplished primarily through vibration of the dry cast concrete, in combination with the application of pressure exerted on the mass of dry cast concrete from above. The vibration can be exerted by vibration of the pallet underlying the mold (table vibration), or by vibration of the mold box (mold vibration), or by a combination of both actions. The pressure is exerted by a compression head, discussed below, that carries one or more stripper shoes that contact the mass of dry cast concrete from above. The timing and sequencing of the vibration and compression is variable, and depends upon the characteristics of the dry cast concrete used and the desired results. The selection and application of the appropriate sequencing, timing, and types of vibrational forces, is within the ordinary skill in the art. Generally, these forces contribute to fully filling the cavity **56**, so that there are not undesired voids in the finished block, and to densifying the dry cast concrete so that the finished block will have the desired weight, density, and performance characteristics.

Pressure is exerted by a stripper shoe **94** that is brought down into contact with the top of the dry cast concrete in the cavity **56** to compact the concrete. The stripper shoe **94** acts with the vibration to compact the concrete within the cavity **56** to form a solid, contiguous, pre-cured block. In the preferred embodiment, the stripper shoe also includes a three-dimensional pattern **96** on its face for producing a corresponding pattern on the resulting pre-cured block as the stripper shoe compacts the concrete. Preferably, the portion of the pre-cured block contacted by the patterned shoe face comprises the front face of the block.

After densification, the pre-cured block is discharged from the cavity. Preferably, discharge occurs by lowering the pallet **82** relative to the mold assembly, while further lowering the

stripper shoe **94** through the mold cavity to assist in stripping the pre-cured block from the cavity. The stripper shoe is then raised upwardly out of the mold cavity and the mold is ready to repeat this production cycle.

If the block is to have one or more converging side walls, then corresponding mold side walls, as described in detail below, must be provided in the mold. Such mold side walls must be adapted to move into a first position to permit filling of the mold, and compaction and densification of the dry cast concrete, and must be adapted to move into a second position to permit stripping of the mold without damage to the pre-cured block.

Once the pre-cured block has been completely removed from the cavity, it can be transported away from the mold assembly for subsequent curing. The block may be cured through any means known to those of skill in the art. Examples of curing processes that are suitable for practicing the invention include air curing, autoclaving, and steam curing. Any of these processes for curing the block may be implemented by those of skill in the art.

Once cured, the blocks can be packaged for storage and subsequent shipment to a jobsite, and can then be used with other cured blocks in forming a structure, such as the retaining wall **40** in FIG. **4**.

#### Mold Assembly

The mold assembly **50** according to the present invention that is used to practice the invention is illustrated in FIGS. **6-11**. The mold assembly **50** is made from materials that are able to withstand the pressure that is applied during formation of the pre-cured block, as well as provide sufficient wear life.

The mold assembly **50** is constructed so that the pre-cured block is formed with its front face facing upward, and with its rear face supported on the pallet **82** positioned underneath the mold assembly **50**. This permits pattern impressing or other direct processing to occur on the front face **12** of the block, to allow the formation of pre-determined block front faces. Pre-determined front faces can include front faces having pre-determined patterns and textures, front faces having pre-determined shapes, front faces made from different material(s) than the remainder of the block, and combinations thereof.

Further, the mold assembly **50** is designed so that a pre-cured block, including a block with a lower lip or flange and/or one or more converging side faces, can be discharged through the bottom of the mold assembly.

Referring to FIG. **6**, the mold assembly **50** comprises a mold **52** and a compression head assembly **54** that interacts with the mold **52** as described below. The mold **52** comprises at least one block-forming cavity **56** defined therein. In one preferred embodiment, the mold **52** is sized for use in a standard, "three-at-a-time" American block machine, having a standard pallet size of approximately 18.5 inches by 26.0 inches, which is sized for making three blocks with their upper faces on the pallet. The mold **52** comprises a plurality of generally identical block-forming cavities **56**. FIG. **7** illustrates five block-forming cavities **56** arranged side-by-side, which is possible when making the preferred size blocks on a standard "three-at-a-time" pallet. Of course, larger machines that use larger pallets are in use, and this technology can be used in both larger and smaller machines. The number of possible mold cavities in a single mold depends upon size and/or type of the machine and the size of the pallet. A plurality of block-forming cavities **56** allows increased production of blocks from the single mold **52**.

With reference to FIG. **7**, the cavities **56** are formed by division plates **58**, including a pair of outside division plates, a plurality of inside division plates, and a pair of end liners **60** that are common to each cavity **56**. The use of outside and

inside division plates and end liners to form a block-forming cavity in a mold is known to those of skill in the art. The division plates and end liners form the boundaries of the block cavities and provide the surfaces that are in contact with the pre-cured blocks during block formation, and are thus susceptible to wear. Thus, the division plates and end liners are typically mounted for removal within the mold **52** so that they can be replaced as they wear or if they become damaged. The techniques for mounting division plates and end liners in a mold to form block cavities, and to permit removal of the division plates and end liners, are known to those of skill in the art.

In the preferred embodiment, the division plates **58** form the upper and lower faces **16**, **18** of the blocks **10**, while the end liners **60** form the side faces **20**, **22**. For convenience, the division plates and end liners will hereinafter (including in the claims) be referred to collectively as the side walls of the cavities. Thus, side walls refers to division plates and end liners, as well as to any other similar structure that is used to define the boundaries of a block-forming cavity.

Referring now to FIG. **8**, a portion of a single block-forming cavity **56** is illustrated. The cavity **56** defined by the side walls **58**, **60** has an open top **64** and an open bottom **66**. As shown, the top ends of the side walls **60** (e.g. the end liners) are connected by pivots **62** to suitable surrounding structure of the mold **52** to allow the side walls **60** to pivot between the closed position shown in FIG. **8**, where the side walls **60** converge toward each other, to a retracted position where the side walls **60** are generally vertical and parallel to each other (not shown). In the retracted position, the bottom of the cavity **66** is at least as wide as the top of the mold cavity, which allows the pre-cured block to be discharged through the open bottom. When only a portion of either side face **20**, **22** of the block converges, only a corresponding portion of the side walls **60** will be pivoted. The side wall **58** that forms the lower face of the block **10** is also illustrated in FIG. **8**, while the other side wall **58** that forms the upper face of the block is not shown.

Pivoting of the side walls **60** is required in order to form the preferred block **10**. As discussed above, the block **10** is formed "face-up" in the mold **52** with its converging side faces formed by the side walls **60**. Thus, the converging side walls **60**, when they are angled as illustrated in FIG. **8**, shape the converging side faces **20**, **22** of the pre-cured block. However, the front portion of the pre-cured block is wider than the rear portion of the block. In order to be able to discharge the pre-cured block through the open bottom **66**, the side walls **60** must pivot outward to enable downward movement of the pre-cured block through the open bottom.

Biasing mechanisms **68** are provided to maintain the side walls **60** at the converging position during introduction of the concrete and subsequent compacting of the dry cast concrete, and which allow the side walls **60** to pivot to a vertical position during discharge of the pre-cured block. Preferably, a single biasing mechanism **68** is connected to each side wall **60** that is common to all cavities **56**, so that the movement of each side wall **60** is controlled via a common mechanism (see FIG. **7**). Alternatively, separate biasing mechanisms can be provided for each cavity. The biasing mechanisms **68** are illustrated as comprising air bags, which will be controlled through the use of air or similar gas. Suitable inlet and outlet ports for the air will be provided, as will a source of high pressure air. The use of biasing mechanisms other than air bags is also possible. For example, hydraulic or pneumatic cylinders could be used.

When pressurized with air, the air bags will force the side walls **60** to the position shown in FIG. **8**. When it comes time

to discharge the pre-cured block(s), the pressurized air is vented from the air bags, which allows the side walls **60** to pivot outward under force of the pre-cured block as the pre-cured block is discharged through the open bottom when the pallet is lowered. During block discharge, the side walls **60** remain in contact with the side faces of the pre-cured block. Alternatively, biasing mechanisms, such as coil springs, can be connected to the side walls **60** to force the side walls to the retracted position when the air bags are vented. In this case, as the pallet **82** starts to lower to begin block discharging, the side walls **60** will be forced to the retracted position, and the side walls **60** will not contact the side faces of the block during discharge. After discharge, the side walls **60** are returned to the closed, angled position by re-pressurizing the air bags.

Rather than pivoting the side walls **60**, it is possible to use other mechanisms to permit movement of the side walls **60** to allow discharge of the pre-cured block. For example, the side walls **60** could be mounted so as to slide inwards to the position shown in FIG. **8** and outwards to a position where the bottom of the cavity **56** is at least as wide as the top of the mold cavity. The sliding movements could be implemented using a track system in which the side walls are mounted.

As shown in FIG. **8**, each side wall **60** includes a shaping surface **76** that faces the cavity **56**. The shaping surfaces **76** are substantially planar. The result is the formation of substantially planar side faces **20**, **22** of the block **10**.

Referring now to FIG. **9**, the side walls **58** that form the upper and lower faces **16**, **18** of the block **10** are illustrated. The side walls **58**, which are fixed and not moveable during the molding process, are substantially vertical.

The side wall **58** that forms the upper face **16** (the left side wall **58** in FIG. **9**) includes a shaping surface **78** that faces the cavity **56**. The surface **78** is substantially planar, which results in the formation of a substantially planar upper face **16**.

The side wall **58** that forms the lower face **18** (the right side wall **58** in FIG. **9**) includes an undercut, or "instep," portion **80** at the bottom edge thereof adjacent the open bottom **66**. The undercut portion **80**, in combination with the pallet **82** that is introduced under the mold **52** to temporarily close the open mold bottom **66** during the molding process, defines a flange-forming subcavity of the cavity **56**. The flange-forming subcavity has a shape that results in the formation of the flange **26** on the block **10**.

In particular, the undercut portion **80** includes a shaping surface **84** that forms the front surface **28** of the flange **26**, a shaping surface **86** that forms the bottom surface **30** of the flange, and a shaping surface **88** that forms the edge **32** of the flange **26**. The portion of the flange **26** that is an extension of the rear face **14** is formed by and on the pallet **82**, along with the remainder of the rear face **14**. The shape of the surfaces **84** and **86** facilitate filling of the undercut portion **80** with the concrete during introduction and subsequent compacting of the concrete so that the flange **26** is completely formed, as well as aid in release of the flange **26** from the surfaces **84**, **86** during block discharge.

In the case of a block having a flange on the lower face and no converging side faces, the side walls **60** would be oriented vertically instead of being converging. Further, in the case of a block without a flange on the lower face and with converging side faces, the undercut **80** would not be present. In the case of a block without a flange on the lower face and without converging side faces, the undercut **80** would not be present and the side walls **60** would be oriented vertically.

Returning to FIGS. **6** and **8**, the head assembly **54** is seen to include a compression head **90** in the form of a plate. The head **90** is actuated by an actuating mechanism in a manner known in the art so that the head **90** is moveable vertically up and

## 11

down to bring about compaction of the dry cast concrete in the mold cavities **56** and to assist in stripping the pre-cured blocks from the mold **52**.

Connected to and extending from the bottom of the head **90** is a plurality of stand-offs **92**, one stand-off for each block-forming cavity **56** as shown in FIG. **6**. The stand-offs **92** are spaced from each other, with the longitudinal axis of each stand-off oriented perpendicular to the plane of the head **90** and extending generally centrally through the block-forming cavity **56**.

## Stripper Shoe

A stripper shoe **94**, illustrated in FIGS. **6**, **8**, **9** and **11**, is connected to the end of each stand-off **92**. The stripper shoe **94** is rectangular in shape and is dimensioned so that it may enter the respective cavity **56** through the open top to contact the concrete to compact the concrete, and to travel through the cavity during discharge of the pre-cured block. The dimensions of the stripper shoe **94** are only slightly less than the dimensions of the open top **64** of the cavity **56**, so that the shoe **94** fits into the cavity **56** with little or no spacing between the sides of the shoe **94** and the side walls **58**, **60** defining the cavity. This minimizes escape of concrete between the sides of the shoe **94** and the side walls **58**, **60** during compression, and maximizes the front face area of the block that is contacted by the shoe **94**.

Flanges **98a**, **98b** are formed on opposite ends of the face of the stripper shoe **94**, as best seen in FIG. **11**. The flanges **98a**, **98b** are arcuate to produce the rounded edges **24a**, **24b** on front face **12** of the block. If desired, arcuate flanges can be provided on the two remaining ends of the stripper shoe **94**, in order to produce upper and lower rounded edges on the front face **12**.

As discussed above, a face of the shoe **94** is preferably provided with a pre-determined pattern **96** that is a reverse image of a desired surface or surfaces. As the shoe **94** including the pattern **96** compacts the concrete, the pattern is imparted to the front face of the block. The pattern **96** preferably simulates natural stone, so that the front face of the resulting block simulates natural stone thereby making the block appear more natural and "rock-like." A variety of different patterns **96** can be provided on the shoe **94**, depending upon the appearance of the front face that one wishes to achieve. In addition to, or separate from, the pattern **96**, the face of the shoe **94** can be shaped to achieve a faceted or curved block front face. Indeed, the face of the shoe **94** can be patterned and/or shaped in any manner which one desires in order to achieve a desired appearance of the block front face.

FIGS. **10A-F** and **11** provide examples of patterns **96** that can be provided on the shoe **94**. The patterns **96** simulate naturally occurring objects, such as, for example, natural stone or man made objects. The pattern **96** is preferably machined into the shoe face based upon a pre-determined three-dimensional pattern. An exemplary process for creating the pre-determined pattern **96** on the shoe face follows.

Referring now generally to FIG. **12**, initially, one or more objects are selected. For example, the objects may include one or more natural rocks having surfaces which one considers to be visually pleasing. Other natural or man made objects may also be used.

One or more of the rock surfaces are then scanned using a digital scanning machine. An example of a suitable scanning machine for practicing the invention is the Laser Design Surveyor® 1200 having an RPS 150 head, available from Laser Design Incorporated of Minneapolis, Minn. The Laser Design Surveyor® 1200 has a linear accuracy of 0.0005 inch in the XYZ coordinates, and a resolution of 0.0001 inch. As practiced, data is collected at 256 points for every 0.004 inch

## 12

of the one or more rock surfaces being scanned. The rock surfaces may be scanned at as many angles as necessary to collect data on all surfaces.

Once the scanned data has been collected, various techniques can be used to manipulate the data. Initially, the Laser Design Surveyor® utilizes DataSculpt® software, available from Laser Design, Inc. of Minneapolis, Minn., to generate one or more DataSculpt® point clouds, or data sets including data points positioned in X, Y, and Z coordinates, from the scanned data.

A computer-aided design (CAD) package is then used to trim the point clouds. The point clouds are also sampled to reduce the scanned data to a manageable size, while smoothing the data by removing extraneous points and noise. Next, the data from the point clouds are blended to form a finished point cloud. The finished point cloud is converted to a polygonal mesh, or a three-dimensional rendition of the point cloud using polygonal shapes. The edges of the polygonal mesh are trimmed to form a clean line, and boundaries are applied to form a tight mesh pattern. Using the mesh, grids are applied and converted to a Non-Uniform Rational B-Splines (NURBS) surface.

The resulting digital image is displayed (see, e.g., FIGS. **10A-F**). The user can manipulate the digital image by selecting and modifying one or more points on the digital image in the X, Y, and/or Z directions. Next, the data is scaled and/or trimmed to an overall block dimension, in the illustrated embodiment 3.88 inches by 11.88 inches per print. In addition, the data is modified to meet a 3/4 inch maximum difference in face relief, a 0-10 degree face angle from the lower edge of the face to the upper edge of the face, and a 5-10 degree draft for all interior surfaces of the relief. Next, the complete data file is mirrored to create the reverse image needed to create the stripper shoe **94**. The data can be output in an Initial Graphics Exchange Specification (IGES) format to a CAD system described below.

A CAD system suitable for manipulating the scanned data is the Mastercam® Mill Version 8.1.1, available from CNC Software, Inc. of Tolland, Conn.

The data, in IGES format, is then input into preferably a three axis (or four axis), numerically controlled milling machine for milling of the stripper shoe **94**. The data is converted into toolpaths by the milling machine. Using the toolpaths, the milling machine mills a mirror image of the rock surface into the face of the stripper shoe **94**.

To create the illustrated stripper shoes, the milling machine can perform a series of toolpaths, including: (1) a first toolpath with a 1/2 inch diameter flat bottom endmill doing a parallel pocket at 90 inches per minute (IPM) and 7,000 revolutions per minute (RPM); (2) a second toolpath with a 1/4 inch diameter flat bottom endmill doing a surface contour at 100 IPM and 10,000 RPM; (3) a third toolpath with a 1/4 inch diameter ball endmill doing a 45° surface contour at 100 IPM and 12,000 RPM; and (4) a fourth toolpath with a 1/8 inch diameter ball endmill doing a 45° surface contour at 150 IPM and 14,000 RPM. The number and type of toolpaths may vary based on the complexity of the surface being reproduced.

A suitable milling machine for practicing the invention is the Mikron VCP600 available from Mikron AG Nidau of Nidau, Switzerland.

The result is a pattern milled into the face of the shoe **94** that is a mirror image of the desired pattern of a block. When the shoe **94** including the pattern compacts the concrete used to form the block, the pattern is impressed into the front face of the block. In the illustrated embodiments shown in FIGS.

## 13

10A-F and 11, the resulting three-dimensional pattern has a relief of between about 0.5 inch and about 1.0 inch, preferably no greater than about  $\frac{3}{4}$  inch.

This process can be repeated to produce additional shoes having the same or different face patterns. This is advantageous because the patterned face of each shoe is subject to wear, and the shoe will need to be replaced when the pattern becomes excessively worn. Moreover, multiple shoes can be used for multiple molds. Further, by forming a variety of different pre-determined shoe patterns, a variety of different block front face appearances can be achieved. Other shoe patterns can be formed by combining the scanned surfaces of a plurality of different rocks. Exemplary shoe patterns are illustrated in FIGS. 10A-F and 11.

As discussed above, the resulting detail and relief that is provided on the block front face can be significantly greater than the detail and relief that is provided on the front face of a block that results from conventional splitting techniques, and the other front face distressing techniques discussed above. If desired, the scan data can be manipulated in order to increase or decrease the relief that is milled into the shoe face, which will alter the relief that is ultimately provided on the block front face.

It is known in the art that dry cast concrete may have a tendency to stick to mold surfaces, such as the patterned surface of the stripper shoe 94. Various techniques to enhance the release of the stripper shoe 94 from the dry cast concrete are known, and one or more of them may need to be employed in the practice of this invention. For example, the pattern formed on the stripper shoe has to be designed to enhance, rather than inhibit, release. In this regard, appropriate draft angles have to be employed in the pattern. As noted above, in the illustrated embodiment, a draft angle of  $5^\circ$  is used. The pattern-forming techniques described above permit manipulation of the scanned images to create appropriate draft angles. Release agents, such as a fine mist of oil, can be sprayed onto the stripper shoe between machine cycles. Head vibration can be employed to enhance release. And heat can be applied to the stripper shoe to enhance release. Heating mold components to prevent sticking of dry cast concrete is known in the art. In the present invention, due to the detailed pattern that is to be imparted to the block front face, it is even more important to prevent sticking. In particular, it is important to be able to control the temperature of the shoe so that the temperature can be maintained at selected levels.

Preferably, as shown diagrammatically in FIG. 13, a heater 100 is connected to the shoe 94 for heating the shoe. The heater 100 is controlled by a temperature control unit 102. A thermocouple 104 mounted on the shoe 94 senses the temperature of the shoe, and relays that information to a power control unit 106 that provides electrical power to the control unit 102 and the heater 100. The system is designed such that, when the temperature of the shoe 94 falls below a pre-determined level as sensed by the thermocouple 104, power is provided to the heater 100 to increase the shoe temperature. When the shoe temperature reaches a pre-determined level, as sensed by the thermocouple, the heater 100 is shut off. Thus, the shoe temperature can be maintained at selected levels. Preferably, the control unit 102 is designed to allow selection of the minimum and maximum temperature levels, based on the dry cast concrete that is being used. In the preferred embodiment, the surface temperature of the stripper shoe 94 is maintained between  $120^\circ$  F. and  $130^\circ$  F.

The above specification, examples and data provide a complete description of the manufacture and use of the composition of the invention. Since many embodiments of the inven-

## 14

tion can be made without departing from the spirit and scope of the invention, the invention resides in the claims hereinafter appended.

What is claimed is:

1. A method of making a concrete block having a three-dimensional patterned face;

the method comprising the steps of:

(a) providing a mold having a plurality of side walls defining a mold cavity; the mold including: an open mold top, an open mold bottom closed by a pallet; and a mold surface having a three-dimensional pattern thereon, and a maximum relief, in the three-dimensional pattern, of at least about 0.5 inch;

(i) the mold surface, of the mold provided, having a three-dimensional pattern resulting from: selection of a three-dimensional pattern of one or more existing objects; digital scanning of the selected three-dimensional pattern to create scanned data in XYZ coordinates that is representative of the selected three-dimensional pattern; creation, from the scanned data in the XYZ coordinates, of a digital data set that is representative of a desired three-dimensional patterned face based on the scanned data; and, use of the digital data set to create the mold surface as a mirror image of the desired block face;

(b) introducing dry cast concrete into the mold cavity through the open top of the mold;

(c) molding a pre-cured block by pressing a stripper shoe downwardly through the open top of the mold into the dry cast concrete; the stripper shoe comprising the mold surface having the three-dimensional pattern thereon with a mirror image of the three-dimensional patterned face to form the pre-cured concrete block with the mold surface having the mirror image of the desired block face forming the desired three-dimensional patterned face on the pre-cured block;

(i) the pre-cured concrete block including a rear face opposite the three-dimensional patterned face, an upper face, a lower face opposite the upper face, opposite side faces with at least one side face converging toward the other in extension across the entire distance from adjacent the three-dimensional patterned face thereon to the rear face;

(d) discharging the pre-cured block from the mold cavity onto the pallet; and

(e) curing the pre-cured concrete block.

2. A method of making a concrete block according to claim 1 wherein:

(a) the step of compacting comprises compacting the dry cast concrete, in the mold cavity, while the mold surface, having the mirror image of the desired block face forming the desired three-dimensional patterned face thereon, has a maximum relief of at least 1.0 inch.

3. A process according to claim 1 wherein:

(a) the step of introducing dry cast concrete into the mold cavity includes putting dry cast concrete into a plurality of mold cavities, each of which comprises a plurality of side walls defining a mold cavity having an open mold top and an open mold bottom closed by a pallet, through the open mold top;

(b) the step of molding includes in each mold cavity

(i) a first of the side walls including a first converging side wall portion that is moveably mounted so that it is movable between a first molding position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast concrete is introduced into the mold cavity, and a second dis-

## 15

charging position in which the bottom of the mold cavity is at least wide enough to allow a pre-cured concrete block to be discharged through the bottom of the mold cavity, wherein the first converging side wall portion extends across the entire distance of the mold cavity between two opposed side walls that are adjacent the second side wall; and

(ii) a stripper shoe having a face that comprises a three-dimensional pattern for introduction into the mold cavity through the open top of the mold cavity to press the pattern of the stripper shoe on dry cast concrete contained in the mold cavity to impart a pattern to the front face of a pre-cured concrete block.

4. A process according to claim 3 wherein:

(a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities wherein a side wall includes an undercut adjacent the open mold bottom;

(i) the undercut of each of the mold cavities and a portion of the surface of the pallet defining a flange-forming subcavity;

(b) the step of molding including molding the flange on each pre-cured dry cast concrete block in a flange-forming subcavity of the mold cavity in which the molding is conducted.

5. A process according to claim 4 wherein:

(a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities wherein the remainder of the side wall with the undercut is substantially planar and extends substantially vertically.

6. A process according to claim 3 wherein:

(a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities each of which has a second side wall, opposite the first of the side walls, that includes a second converging side wall portion which is opposite the first converging side wall portion and extends the entire distance across the mold cavity between the two opposed side walls that are adjacent the second of the side walls, and wherein the second converging side wall portion is moveably mounted so that it is movable between a first molding position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast concrete is introduced into the mold cavity, and a second discharging position in which the bottom of the mold cavity is at least wide enough to allow the pre-cured concrete block to be discharged through the bottom of the mold cavity.

7. A process according to claim 6 wherein:

(a) each one of the converging side wall portions is capable of being biased between a second discharging position and a first molding position; and

(b) prior to the step of putting dry cast concrete in the mold cavities, biasing the converging side walls to the first molding position.

8. A process of forming multiple pre-cured dry cast concrete blocks in one cycle of a block machine; the method comprising the steps of:

(a) putting dry cast concrete into a plurality of mold cavities in the block machine, each of the mold cavities having an open top and an open bottom;

(b) molding one pre-cured dry cast concrete block in each of the plurality of mold cavities while compacting the dry cast concrete with a stripper shoe pressing into the

## 16

dry cast concrete through the open top of each of the cavities to form a set of pre-cured dry cast concrete blocks, each block having:

(i) an upwardly facing, patterned, front face having a three-dimensional pattern therein having a relief, measured from the lowest point to the highest point, of at least 0.5 inches;

(A) the front face being formed by a mold surface on the stripper shoe; the mold surface on the provided stripper shoe having a three-dimensional pattern resulting from: a digital creation of the mold surface of a desired block face;

(ii) a generally planar rear face opposite the front face;

(iii) a generally planar upper face free of cores;

(iv) a generally planar lower face opposite and generally parallel to the upper face, the rear face being generally perpendicular to the upper face and the lower face;

(v) opposite generally planar side faces; at least one of the opposite side faces converging toward the other in extension across the entire distance from adjacent the front face having the three-dimensional pattern thereon to adjacent the rear face, the at least one converging side face extending from adjacent the front face at a non-perpendicular angle thereto;

(vi) a flange extending across, and projecting from, the lower face adjacent the rear face; and

(c) discharging one of the plurality of molded pre-cured dry cast concrete blocks from the block machine through the bottom of each of the plurality of mold cavities with the patterned front faces directed upwardly.

9. A process according to claim 8 wherein

(a) the step of molding comprises molding a set of pre-cured dry cast concrete blocks each having each one of the opposite side faces converging toward the other one of the opposite side faces in extension across the entire distance from adjacent the front face having the three-dimensional pattern thereon to adjacent the rear face, each of the converging side faces extending from adjacent the front face at a non-perpendicular angle thereto.

10. A process according to claim 9 wherein:

(a) the step of molding one pre-cured dry cast concrete block includes the mold surface on the provided stripper shoe having a three-dimensional pattern resulting from a digital data set that is representative of a desired three-dimensional patterned face created by digitally scanning a selected three-dimensional pattern to create scanned data in XYZ coordinates that is representative of the selected three-dimensional pattern.

11. A process according to claim 9 wherein:

(a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities wherein a side wall includes an undercut adjacent the open mold bottom; and

(b) wherein the mold assembly includes a pallet having a surface that temporarily closes the entire open bottom of each of the mold cavities;

(i) the undercut of each of the mold cavities and a portion of the surface of the pallet defining a flange-forming subcavity;

(c) the step of molding including molding the flange on each pre-cured dry cast concrete block in a flange-forming subcavity of the mold cavity in which the molding is conducted; and

(d) the step of discharging comprises discharging the pre-cured blocks onto the pallet.

## 17

12. A process according to claim 11 wherein:

- (a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities wherein the remainder of the side wall with the undercut is substantially planar and extends substantially vertically.

13. A process according to claim 11 wherein

- (a) the step of putting dry cast concrete into each one of a plurality of mold cavities comprises putting dry cast concrete into mold cavities each of which has first and second opposed side walls, each of the opposed side walls includes a converging side wall portion which extends the entire distance across the mold cavity, and wherein the first and second converging side wall portions are moveably mounted so that they are movable between a first molding position at an angle with respect to vertical so that the mold cavity is wider at its top than it is at its bottom when dry cast concrete is introduced into the mold cavity, and a second discharging position in which the bottom of the mold cavity is at least wide enough to allow the pre-cured concrete block to be discharged through the bottom of the mold cavity.

14. A process according to claim 13 wherein:

- (a) each one of the converging side wall portions is capable of being biased between a second discharging position and a first molding position; and  
 (b) prior to the step of putting dry cast concrete in the mold cavities, biasing the converging side walls to the first molding position.

15. A process according to claim 14 wherein

- (a) an air bag is connected to each converging side wall portion; and  
 the step of biasing the converging side walls to the first molding position comprises inflating an air bag connected to each converging side wall portion.

## 18

16. A process according to claim 11 wherein

- in each of the plurality of mold cavities, first and second converging side wall portions are each pivotally mounted adjacent an open mold top; and,  
 the step of discharging comprises pivoting the first and second converging side wall portions to discharging positions.

17. A process according to claim 8 wherein:

- (a) the step of putting the dry cast concrete into mold cavities comprises:  
 (i) putting the dry cast concrete into mold cavities, each of which have a side wall that includes an undercut adjacent an open mold bottom; and  
 (ii) putting the dry cast concrete into a block machine including a pallet having a surface that temporarily closes the entire bottom of each of mold cavities; the undercut of each of the mold cavities and a portion of the pallet defining a flange-forming subcavity; the flange-forming subcavity being configured to form the flange on a pre-cured dry cast block formed in that mold cavity.

18. A process according to claim 8 wherein:

- (a) the step of putting dry cast concrete comprises putting dry cast concrete into mold cavities each of which has an open bottom closed by a surface of a pallet; and  
 (b) the step of discharging comprises discharging onto the pallet.

19. A process according to claim 8 wherein:

- (a) the step of molding includes forming at least one upwardly facing patterned face with a pattern that simulates one of: multiple rocks; a single piece of stone; and multiple pieces of stone stacked in layers.

20. A process according to claim 8 wherein:

- (a) the step of molding includes forming at least one upwardly facing patterned face with a pattern having a relief, measured from the lowest point to the highest point, of at least 1.0 inches.

\* \* \* \* \*