

US008647945B2

(12) **United States Patent**  
**Wang et al.**

(10) **Patent No.:** **US 8,647,945 B2**  
(45) **Date of Patent:** **Feb. 11, 2014**

(54) **METHOD OF FORMING SUBSTRATE CONTACT FOR SEMICONDUCTOR ON INSULATOR (SOI) SUBSTRATE**

(75) Inventors: **Geng Wang**, Stormville, NY (US); **Roger A. Booth, Jr.**, Wappingers Falls, NY (US); **Kangguo Cheng**, Guilderland, NY (US); **Joseph Ervin**, New York, NY (US); **Chengwen Pei**, Danbury, CT (US); **Ravi M. Todi**, Poughkeepsie, NY (US)

(73) Assignee: **International Business Machines Corporation**, Armonk, NY (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 363 days.

(21) Appl. No.: **12/959,824**

(22) Filed: **Dec. 3, 2010**

(65) **Prior Publication Data**

US 2012/0139080 A1 Jun. 7, 2012

(51) **Int. Cl.**  
**H01L 21/70** (2006.01)

(52) **U.S. Cl.**  
USPC ..... **438/248**; 438/389; 438/430; 438/524; 438/700; 257/532; 257/E21.532; 257/E21.538; 257/E21.547; 257/E21.548

(58) **Field of Classification Search**  
None  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,549,927 A 10/1985 Goth et al.  
4,924,284 A \* 5/1990 Beyer et al. .... 257/621  
5,217,920 A 6/1993 Mattox et al.  
2006/0261444 A1\* 11/2006 Grivna et al. .... 257/576

\* cited by examiner

*Primary Examiner* — Calvin Lee



*Assistant Examiner* — Abul Kalam

(74) *Attorney, Agent, or Firm* — Scully, Scott, Murphy & Presser, P.C.; Joseph P. Abate, Esq.

(57) **ABSTRACT**

A semiconductor structure is provided that includes a material stack including an epitaxially grown semiconductor layer on a base semiconductor layer, a dielectric layer on the epitaxially grown semiconductor layer, and an upper semiconductor layer present on the dielectric layer. A capacitor is present extending from the upper semiconductor layer through the dielectric layer into contact with the epitaxially grown semiconductor layer. The capacitor includes a node dielectric present on the sidewalls of the trench and an upper electrode filling at least a portion of the trench. A substrate contact is present in a contact trench extending from the upper semiconductor layer through the dielectric layer and the epitaxially semiconductor layer to a doped region of the base semiconductor layer. A substrate contact is also provided that contacts the base semiconductor layer through the sidewall of a trench. Methods for forming the above-described structures are also provided.

**18 Claims, 9 Drawing Sheets**






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14






FIG. 15




FIG. 16



1

**METHOD OF FORMING SUBSTRATE  
CONTACT FOR SEMICONDUCTOR ON  
INSULATOR (SOI) SUBSTRATE**

FIELD OF THE INVENTION

The present disclosure relates to semiconductor devices and interconnects to semiconductor devices.

In bulk semiconductor substrates, the active semiconductor region of a transistor is disposed in a well region of an oppositely doped bulk semiconductor region. In such structure, junction capacitance between the well and the bulk semiconductor region can impact performance. Some micro-electronic devices have active semiconductor regions in a silicon-on-insulator (“SOI”) layer of an SOI substrate. The SOI layer is separated from the main or “bulk” semiconductor region of the substrate by an insulating layer such as a buried oxide (“BOX”) layer or other dielectric layer. The insulating layer improves performance by eliminating junction capacitance between the SOI layer and the bulk semiconductor region.

SUMMARY

In one embodiment, the present disclosure provides a method of forming a contact to base semiconductor layer of a substrate having a semiconductor on insulator (SOI) substrate configuration. The base semiconductor layer is a semiconductor layer of the substrate that is underlying a buried dielectric layer. In one embodiment, a method of forming a semiconductor device is provided that includes providing a material stack on a base semiconductor layer. The material stack may include an epitaxially grown semiconductor layer on the base semiconductor layer, a dielectric layer on the epitaxially grown semiconductor layer, and an upper semiconductor layer present on the dielectric layer. An etch mask may be formed on an upper surface of the upper semiconductor layer. The etch mask includes a contact opening, an isolation opening and a capacitor opening. An etch process in conjunction with the etch mask can provide a contact trench that is in contact with the base semiconductor layer, a isolation trench that is in contact with the base semiconductor layer, and a capacitor trench having a base portion present in the epitaxially grown semiconductor layer. A conformal dielectric may be formed on the contact trench, the isolation trench and the capacitor trench. A portion of the conformal dielectric is removed from a base portion of the contact trench. A dopant region is formed in the base semiconductor layer of the substrate at the base portion of the contact trench. The contact trench, the isolation trench and the capacitor trench may then be filled with a conductive material.

In another aspect of the present disclosure, a semiconductor structure is provided that includes a substrate contact and at least one capacitor. In one embodiment, the semiconductor structure includes a material stack on a base semiconductor layer. The material stack includes an n-type semiconductor layer on the base semiconductor layer, a dielectric layer on the n-type semiconductor layer, and an upper semiconductor layer present on the dielectric. A capacitor may be present in a capacitor trench extending from the upper semiconductor layer through the dielectric layer into contact with the n-type semiconductor layer. The capacitor may include a node dielectric present on the sidewalls of the trench and an upper electrode filling at least a portion of the trench. The substrate contact may be present in a contact trench extending from the

2

upper semiconductor layer through the dielectric layer and the n-type semiconductor layer to a p-type doped region of the base semiconductor layer.

In another embodiment, a method of forming a semiconductor device is provided that includes providing an upper semiconductor layer on a dielectric layer, wherein the dielectric layer is present on a base semiconductor layer, and forming an etch mask on an upper surface of the upper semiconductor layer. The etch mask may include a contact opening having a first width and a capacitor opening having a second width, wherein the first width is of a dimension that is greater than 2 times the value of the second width. A contact trench and a capacitor trench are etched into contact with the base semiconductor layer. A conformal dielectric layer is formed on the contact trench and the capacitor trench. The conformal dielectric layer is recessed within the contact trench and the capacitor trench with an anisotropic etch. A first remaining portion of the conformal dielectric layer that is present in the contact trench is recessed below the upper surface of base semiconductor layer to expose a sidewall portion of the base semiconductor layer within the contact trench. A second remaining portion of the conformal dielectric layer that is present in the capacitor trench is present on an entirety of the sidewalls and base portions of the capacitor trench that is present in the base semiconductor layer. The contact trench and the capacitor trench are filled with a conductive material.

In another aspect, a semiconductor structure is provided that includes a capacitor formed in a semiconductor on insulator (SOI) substrate and a substrate contact to the base semiconductor layer of the semiconductor on insulator (SOI) substrate. In one embodiment, the semiconductor structure includes a semiconductor on insulator (SOI) substrate that includes an upper semiconductor layer, a dielectric layer, and a base semiconductor layer. A substrate contact is present in a first trench extending from an upper surface of the semiconductor layer through the dielectric layer into contact with the base semiconductor layer. The substrate contact includes a conductive fill material that is in direct contact with the base semiconductor layer through a sidewall portion of the trench. The conductive fill of the substrate contact is separated from the base portion of the trench by a conformal dielectric layer. A capacitor is present in a second trench that includes a buried plate, a node dielectric layer and an upper electrode. The node dielectric layer is present on an entirety of the sidewalls and base portions of the second trench that is present in the base semiconductor layer. The node dielectric layer is identical in composition to the conformal dielectric layer.

DESCRIPTION OF THE DRAWINGS

The following detailed description, given by way of example and not intended to limit the disclosure solely thereto, will best be appreciated in conjunction with the accompanying drawings, wherein like reference numerals denote like elements and parts, in which:

FIG. 1 is a side cross-sectional view of an initial structure used in one embodiment of a method of forming a contact to a base semiconductor layer of a semiconductor substrate, in which the initial structure has been etched to provide a contact trench into contact with the base semiconductor layer, an isolation trench into contact with the base semiconductor layer, and a capacitor trench having a base portion present in an epitaxially grown semiconductor layer, in accordance with the present disclosure.

FIG. 2 is a side cross-sectional view depicting forming a block mask over an isolation trench and a capacitor trench, in accordance with one embodiment of the present disclosure.

3

FIG. 3 is a side cross-sectional view depicting forming a dopant region in the base semiconductor layer at the base portion of the contact trench, in accordance with one embodiment of the present disclosure.

FIGS. 4 and 5 are side cross-sectional views depicting filling the contact trench, the isolation trench and the capacitor trench with a conductive material, in accordance with one embodiment of the present disclosure.

FIG. 6 is a side cross-sectional view of forming a conformal metal layer within the contact trench that is depicted in FIG. 2, in accordance with another embodiment in the present disclosure.

FIG. 7 is a side cross-sectional view depicting one embodiment of forming a dopant region in the base semiconductor layer at the base portion of the contact trench that is depicted in FIG. 6.

FIG. 8 is a side-cross sectional view depicting filling the contact trench, the isolation trench and the capacitor trench that are depicted in FIG. 7 with at least one conductive material, in accordance with one embodiment of the present disclosure.

FIG. 9 is a side cross-sectional view of an initial structure used in one embodiment of a method of forming a contact to a semiconductor structure, in which the initial structure has been etched to provide a contact trench into contact with an epitaxially grown semiconductor layer, an isolation trench into contact with the base semiconductor layer, and a capacitor trench having a base portion present in the epitaxially grown semiconductor layer, in accordance with the present disclosure.

FIG. 10 is a side cross-sectional view of removing a conformal dielectric layer from the contact trench that is depicted in FIG. 9, in accordance with one embodiment of the present disclosure.

FIG. 11 is a side-cross sectional view depicting filling the contact trench, the isolation trench and the capacitor trenches that are depicted in FIG. 10 with at least one conductive material, in accordance with one embodiment of the present disclosure.

FIG. 12 is a side cross-sectional view of an initial structure used in one embodiment of a method of forming a contact to the base semiconductor layer of semiconductor on insulator substrate, in which the initial structure includes a pad dielectric stack present on a semiconductor on insulator (SOI) substrate, in accordance with the present disclosure.

FIG. 13 is a side cross-sectional view depicting etching a contact trench and a capacitor trench into contact with the base semiconductor layer of the semiconductor or insulator substrate, in accordance with one embodiment of the present disclosure.

FIG. 14 is a side cross-sectional view depicting forming a doped region in the base semiconductor layer of the substrate adjacent to the contact trench and the capacitor trench, in accordance with one embodiment of the present disclosure.

FIG. 15 is a side cross-sectional view depicting forming a conformal dielectric layer on the contact trench and the capacitor trench, and forming a conformal metal containing layer on the conformal dielectric layer, in accordance with one embodiment of the present disclosure.

FIG. 16 is a side cross-sectional view depicting filling the contact trench and the capacitor trench with a doped semiconductor material, in accordance with one embodiment of the present disclosure.

FIG. 17 is a side cross-sectional view depicting recessing the conformal dielectric layer, the conformal metal containing layer, and the doped semiconductor material within the

4

contact trench and the capacitor trench, in accordance with one embodiment of the present disclosure.

FIG. 18 is a side cross-sectional view depicting filling the contact trench and the capacitor trench with a conductive material, in accordance with one embodiment of the present disclosure.

#### DETAILED DESCRIPTION OF THE INVENTION

Detailed embodiments of the present disclosure are described herein; however, it is to be understood that the disclosed embodiments are merely illustrative of the invention that may be embodied in various forms. In addition, each of the examples given in connection with the various embodiments of the disclosure is intended to be illustrative, and not restrictive. Further, the figures are not necessarily to scale, some features may be exaggerated to show details of particular components. Therefore, specific structural and functional details disclosed herein are not to be interpreted as limiting, but merely as a representative basis for teaching one skilled in the art to variously employ the present invention.

References in the specification to “one embodiment”, “an embodiment”, “an example embodiment”, etc., indicate that the embodiment described may include a particular feature, structure, or characteristic, but every embodiment may not necessarily include the particular feature, structure, or characteristic. Moreover, such phrases are not necessarily referring to the same embodiment. Further, when a particular feature, structure, or characteristic is described in connection with an embodiment, it is submitted that it is within the knowledge of one skilled in the art to affect such feature, structure, or characteristic in connection with other embodiments whether or not explicitly described. For purposes of the description hereinafter, the terms “upper”, “lower”, “right”, “left”, “vertical”, “horizontal”, “top”, “bottom”, and derivatives thereof shall relate to the invention, as it is oriented in the drawing figures. The terms “overlying”, “atop”, “positioned on” or “positioned atop” means that a first element, such as a first structure, is present on a second element, such as a second structure, wherein intervening elements, such as an interface structure, e.g. interface layer, may be present between the first element and the second element. The term “direct contact” means that a first element, such as a first structure, and a second element, such as a second structure, are connected without any intermediary conducting, insulating or semiconductor layers at the interface of the two elements.

FIGS. 1-5 depict one embodiment of a method for forming a contact to the base semiconductor layer 10 of a semiconductor on insulator (SOI) substrate 5. The semiconductor on insulator (SOI) substrate 5 that includes an epitaxially grown semiconductor layer 15 atop a base semiconductor layer 10, and a dielectric layer 20, i.e., buried dielectric layer is present atop the epitaxially grown semiconductor layer 15. In one embodiment, the epitaxially grown semiconductor layer 15 is doped with an n-type dopant and the base semiconductor layer 10 is doped with a p-type dopant. Since the p-type doped region is buried below the dielectric layer 20, it is floating unless a contact is realized to bias the substrate 5 to a specific electrical bias, which is normally ground. When it is floating, the electrical potential in the p-type base semiconductor layer 10 can fluctuate and be affected by n-type epitaxially grown semiconductor region 15 that is locally adjacent to it. This resembles the floating body effect in the upper semiconductor layer of SOI substrates, and can cause leakage and noise issues. In some embodiments, in order to substantially eliminate the negative effects of the floating body, the methods and

structures of the present disclosure provide a contact to the base semiconductor layer **10** of the semiconductor on insulator (SOI) substrate **5**.

FIG. **1** illustrates the results of the initial processing steps that produce a semiconductor on insulator (SOI) substrate **5** that includes an epitaxially grown semiconductor layer **15** that is present between dielectric layer **20** and the base semiconductor layer **10**. The semiconductor on insulator substrate **5** also includes an upper semiconductor layer **25** that is overlying the dielectric layer **20**.

The base semiconductor layer **10** may be composed of any semiconducting material including, but not limited to Si, strained Si, SiC, SiGe, SiGeC, Si alloys, Ge, Ge alloys, GaAs, InAs, and InP, or any combination thereof. In the embodiments that are depicted in FIGS. **1-5** the base semiconductor layer **10** is composed of a silicon containing material. For example, the base semiconductor layer **10** may be composed of silicon having a p-type conductivity type. As used herein, the term “conductivity type” denotes a dopant region being p-type or n-type. The term “p-type” refers to the addition of impurities to an intrinsic semiconductor that creates deficiencies of valence electrons. In a silicon containing material, examples of p-type dopants, i.e., impurities, include but are not limited to: boron, aluminum, gallium and indium. The p-type dopant may be introduced to the base semiconductor layer **10** by ion implantation or by an insitu doping process that is employed while the material of the base semiconductor layer **10** is being formed. The concentration of p-type dopant that is present in the base semiconductor layer **10** is typically greater than  $1 \times 10^{15}$  atoms/cm<sup>3</sup>. In another embodiment, the concentration of the p-type dopant that is present in the base semiconductor layer **10** ranges from  $1 \times 10^{16}$  atoms/cm<sup>3</sup> to  $1 \times 10^{17}$  atoms/cm<sup>3</sup>. The p-type dopant may be boron, but aluminum, gallium and indium may also be employed. In one embodiment, the base semiconductor layer **10** has a thickness ranging from 25  $\mu\text{m}$  to 500  $\mu\text{m}$ . In another embodiment, the first semiconductor layer **4** has a thickness ranging from 50  $\mu\text{m}$  to 100  $\mu\text{m}$ .

The epitaxially grown semiconductor layer **15** is formed on an upper surface of the base semiconductor layer **10**. The epitaxially grown semiconductor layer **15** is composed of any semiconducting material including, but not limited to Si, strained Si, SiC, SiGe, SiGeC, Si alloys, Ge, Ge alloys, GaAs, InAs, and InP, or any combination thereof.

“Epitaxial growth and/or deposition” means the growth of a semiconductor material on a deposition surface of a semiconductor material, in which the semiconductor material being grown has the same crystalline characteristics as the semiconductor material of the deposition surface. Thus, an epitaxial film deposited on a  $\langle 111 \rangle$  crystal surface will take on a  $\langle 111 \rangle$  orientation. If, on the other hand, the wafer surface has an amorphous surface layer, possibly the result of implanting, the depositing atoms have no surface to align to, resulting in the formation of polysilicon instead of single crystal silicon.

A number of different sources may be used for the deposition of epitaxially grown semiconductor layer **15**. Silicon sources for epitaxial growth include silicon tetrachloride, dichlorosilane (SiH<sub>2</sub>Cl<sub>2</sub>), and silane (SiH<sub>4</sub>). The temperature for epitaxial silicon deposition may range from 750° C. to 900° C. Although higher temperature typically results in faster deposition, the faster deposition may result in crystal defects and film cracking.

In the example that is depicted in FIG. **1**, the epitaxially grown semiconductor layer **15** is composed of silicon (Si). In other embodiments, the epitaxially grown semiconductor layer **15** may be composed of silicon germanium (SiGe). In

the embodiments, in which the epitaxially grown semiconductor layer **15** is composed of silicon germanium (SiGe), the Ge content may range from 5% to 50%, by atomic weight %. In another embodiment, the Ge content of the epitaxially grown SiGe may range from 10% to 20%.

In one embodiment, the epitaxially grown semiconductor layer **15** is doped with an n-type conductivity dopant. As used herein, “n-type” refers to the addition of impurities that contribute free electrons to an intrinsic semiconductor, such as antimony, arsenic or phosphorous to a Si-containing material. The n-type dopant may be introduced to the epitaxially grown semiconductor layer **15** during the epitaxial growth process that forms the layer. In one embodiment, in which the epitaxially grown semiconductor layer **15** is doped to provide an n-type conductivity, the dopant may be phosphorus present in a concentration ranging from  $1 \times 10^{18}$  atoms/cm<sup>3</sup> to  $5 \times 10^{21}$  atoms/cm<sup>3</sup>. In one embodiment, in which the epitaxially grown semiconductor layer **15** is doped to provide an n-type conductivity, the dopant may be phosphorus present in a concentration ranging from  $1 \times 10^{19}$  atoms/cm<sup>3</sup> to  $1 \times 10^{20}$  atoms/cm<sup>3</sup>.

The epitaxially grown semiconductor layer **15** may have a thickness that is greater than 1  $\mu\text{m}$ . In one embodiment, the epitaxially grown semiconductor layer **15** has a thickness that ranges from 1  $\mu\text{m}$  to 5  $\mu\text{m}$ . In yet another embodiment, the epitaxially grown semiconductor layer **15** has a thickness that is greater than 3  $\mu\text{m}$ . In one example, the epitaxially grown semiconductor layer **15** has a thickness that is equal to 4.0  $\mu\text{m}$ .

The dielectric layer **20**, i.e., buried dielectric layer, may be an oxide, such as silicon oxide, a nitride, such as silicon nitride, or an oxynitride, such as silicon oxynitride. In one example, the dielectric layer **20** is composed of silicon oxide (SiO<sub>2</sub>). In one embodiment, the dielectric layer **20** has a thickness ranging from 5.0 nm to 400.0 nm. In another embodiment, the dielectric layer **20** has a thickness ranging from 50.0 nm to 200.0 nm.

In one embodiment, the dielectric layer **20** may be deposited or grown prior on the epitaxially grown semiconductor layer **15**. For example, in one embodiment, the dielectric layer **20** may be formed by a deposition process, such as chemical vapor deposition (CVD). Chemical vapor deposition is a deposition process in which a deposited species is formed as a result of a chemical reaction between gaseous reactants at greater than room temperature, wherein solid product of the reaction is deposited on the surface on which a film, coating, or layer of the solid product is to be formed. Variations of CVD processes include, but are not limited to, Atmospheric Pressure CVD (APCVD), Low Pressure CVD (LPCVD), Plasma Enhanced CVD (EPCVD), Metal-Organic CVD (MOCVD) and combinations thereof. In another example, the dielectric layer **20** is formed using a thermal growth process, such as thermal oxidation.

The upper semiconductor layer **25** may be composed of any semiconducting material including, but not limited to, Si, strained Si, SiC, SiGe, SiGeC, Si alloys, Ge, Ge alloys, GaAs, InAs, and InP, or any combination thereof. In one embodiment, the upper semiconductor layer **25** has a thickness ranging from 5.0 nm to 200.0 nm. In another embodiment, the upper semiconductor layer **25** has a thickness ranging from 40.0 nm to 100 nm. In one embodiment, the upper semiconductor layer **25** may be deposited on the dielectric layer **20**. For example, the upper semiconductor layer **25** may be formed by a deposition process, such as chemical vapor deposition (CVD). Variations of CVD processes include, but are not limited to, Atmospheric Pressure CVD (APCVD), Low Pressure CVD (LPCVD), Plasma Enhanced CVD (EPCVD), Metal-Organic CVD (MOCVD) and combinations thereof.

The upper semiconductor layer **25** may also be formed by evaporation, spin-on coating, or chemical solution deposition. In the example that is depicted in FIG. 1, the upper semiconductor layer **25** is composed of silicon.

In addition to the above-described method of forming the semiconductor on insulator (SOI) substrate **5**, the semiconductor on insulator (SOI) substrate **5** may also be formed using wafer-bonding techniques, where adjacent material layers are formed and then joined utilizing glue, adhesive polymer, or direct bonding.

A pad dielectric stack **30** may be formed on the upper surface of the SOI substrate **5**. The pad dielectric stack **30** may include a nitride containing pad dielectric layer **31** that is present on the upper surface of the SOI substrate **5**, and a hard mask dielectric layer **32** that is present on the upper surface of the nitride containing pad dielectric layer **31**. The nitride containing pad dielectric layer **31** may be composed of any nitride containing material, such as silicon nitride ( $\text{Si}_3\text{N}_4$ ) or silicon oxynitride ( $\text{SiO}_x\text{N}_y$ ). The nitride containing pad dielectric layer **31** is typically formed by a deposition process, such as chemical vapor deposition (CVD). The nitride containing pad dielectric layer **31** may have a thickness ranging from 50 nm to 200 nm. In another example, the nitride containing pad dielectric layer **31** has a thickness ranging from 100 nm to 150 nm. The hard mask dielectric layer **32** may be composed of an oxide containing material, such as silicon oxide ( $\text{SiO}_2$ ). The hard mask dielectric layer **32** may also be composed of silicon carbides, silicon nitrides, silicon carbonitrides, silsequioxanes, siloxanes, borosilicate glass (BSG), and boron phosphate silicate glass (BPSG). The hard mask dielectric layer **32** is typically formed by a deposition process, such as chemical vapor deposition (CVD) or spin on deposition. The hard mask dielectric layer **32** may have a thickness ranging from 50 nm to 1000 nm. In another example, the hard mask dielectric layer **32** has a thickness ranging from 300 nm to 500 nm. It is noted that the above-described pad dielectric stack **30** is provided for illustrative purposes only, and is not intended to limit the present disclosure. Any number of material layers and any number of compositions may be employed in the pad dielectric stack **30**, so long as the pad dielectric stack facilitates the selective etch process that provides the contact trench **35**, isolation trench **40** and capacitor trench **45**.

FIG. 1 depicts one embodiment of using the pad dielectric stack **30** as an etch mask to form a contact trench **35**, an isolation trench **40** and a capacitor trench **45** in the semiconductor on insulator (SOI) substrate **5**. The etch process that provides the contact trench **35**, an isolation trench **40** and a capacitor trench **45** may be an anisotropic etch. As used herein, an “anisotropic etch process” denotes a material removal process in which the etch rate in the direction normal to the surface to be etched is higher than in the direction parallel to the surface to be etched. One form of anisotropic etching that is suitable for forming the contact trench **35**, the isolation trench **40** and the capacitor trench **45** is reactive ion etching (RIE). Reactive ion etching (RIE) is a form of plasma etching in which during etching the surface to be etched is exposed to reactive gases in the presence of an RF field. During RIE the surface to be etched takes on a potential that accelerates the reactive species extracted from a plasma toward the surface, in which the chemical etching reaction is taking place in the direction normal to the surface.

Prior to etching the semiconductor on insulator (SOI) substrate **5**, the pad dielectric stack **30** is patterned and etched to provide an etch mask. In one embodiment, a pattern is produced by applying a photoresist (not shown) to the surface to be etched, exposing the photoresist to a pattern of radiation, and then developing the pattern into the photoresist utilizing

a resist developer to provide a photoresist mask (not shown). Once the patterning of the photoresist is completed, the sections of the pad dielectric stack **30** covered by the photoresist are protected, while the exposed portions are removed using a selective etching process that removes the unprotected regions. As used herein, the term “selective” in reference to a material removal process denotes that the rate of material removal for a first material is greater than the rate of removal for at least another material of the structure to which the material removal process is being applied.

For example, in one embodiment, following the formation of the photoresist mask, a selective etch process can remove the exposed portion of the hardmask dielectric layer **32** selective to, i.e., stopping on, the nitride containing pad dielectric layer **31**. Thereafter, the exposed portions of the nitride containing pad dielectric layer **31** may be etched selective to the upper semiconductor layer **25** to provide the etch mask, which is composed of the remaining portions of the pad dielectric stack **30**. The etch mask includes a contact opening **34**, an isolation opening **39** and a capacitor opening **44**.

The capacitor opening **44** has a first width  $W_1$ , the contact opening **34** has a second width  $W_2$ , and the isolation opening **39** has a third width  $W_3$ , wherein the third width  $W_3$  is greater than the second width  $W_2$  and the second width  $W_2$  is greater than the first width  $W_1$ . The second width  $W_2$  of the contact trench can be larger than the third width  $W_3$  of the isolation trench, but it is sufficient for the second width  $W_2$  to be greater than first width  $W_1$ . The first width  $W_1$  of the capacitor opening **44** may range from 0.03  $\mu\text{m}$  to 0.2  $\mu\text{m}$ . In another embodiment, the first width  $W_1$  of the capacitor opening **44** may range from 0.06  $\mu\text{m}$  to 0.1  $\mu\text{m}$ . The second width  $W_2$  of the contact opening **34** may range from 0.10  $\mu\text{m}$  to 0.5  $\mu\text{m}$ . In another embodiment, the second width  $W_2$  of the contact opening **34** may range from 0.2  $\mu\text{m}$  to 0.3  $\mu\text{m}$ . In one example, second width  $W_2$  of the contact opening **34** may be 0.25  $\mu\text{m}$ . The third width  $W_3$  of the isolation opening **39** may range from 0.1  $\mu\text{m}$  to 1.0  $\mu\text{m}$ . In another embodiment, the third width  $W_3$  of the isolation opening **39** may range from 0.2  $\mu\text{m}$  to 0.5  $\mu\text{m}$ .

Following the formation of the etch mask, the semiconductor on insulator (SOI) substrate **5** may be etched to form the contact trench **35**, the isolation trench **40** and the capacitor trench **45**. The etch process may be an anisotropic etch, such as reactive ion etch (RIE). Other anisotropic etch processes that are suitable for forming the contact trench **35**, isolation trench **40** and the capacitor trench **45** include ion beam etching, plasma etching or laser ablation.

The etch process for forming the contact trench **35**, isolation trench **40** and the capacitor trench **45** into the semiconductor on insulator (SOI) substrate **5** may be a multi-stage etch. For example, during the first stage of the etch process, the portions of the upper semiconductor layer **25** that are exposed by the etch mask may be etched using an etch chemistry that is selective to the underlying dielectric layer **20**. Thereafter, the exposed portions of the dielectric layer **20** may be etched using an etch chemistry that is selective to the epitaxially formed semiconductor layer **15**. In a final stage of the etch process, the epitaxially formed semiconductor layer **15** is etched, wherein depending upon the final depth of the trench being formed, the etch may continue into the base semiconductor layer **10**.

The contact trench **35**, isolation trench **40** and the capacitor trench **45** may be formed simultaneously using the same etch mask, i.e., a single etch mask is used to form each of the contact trench **35**, isolation trench **40** and the capacitor trench **45**. By “simultaneously” it is meant that each of the trenches

are formed at the same time, each trench being subjected to the same etch chemistries and the same etch mask.

The capacitor trench **45** has a first depth **D1**, the contact trench **35** has a second depth **D2**, and the isolation trench **40** has a third width **D3**, wherein the third depth **D3** is greater than the second depth **D2** and the second depth **D2** is greater than the first depth **D1**. The first depth **D1** of the capacitor trench **45** may range from 1  $\mu\text{m}$  to 8  $\mu\text{m}$ , as measured from the upper surface of the upper semiconductor layer **25**. In another embodiment, the first depth **D1** of the capacitor trench **45** may range from 2  $\mu\text{m}$  to 4  $\mu\text{m}$ . The second depth **D2** of the contact trench **35** may range from 3  $\mu\text{m}$  to 10  $\mu\text{m}$ . In another embodiment, the second depth **D2** of the contact trench **35** may range from 5  $\mu\text{m}$  to 8  $\mu\text{m}$ . In one embodiment, the sidewall of the capacitor trench **45** may include a taper through the entire depth of the trench beginning from the surface of the semiconductor on insulator (SOI) substrate **5** resulting in a trapezoidal geometry.

The contact trench **35** and the isolation trench **40** are both etched to a depth that contacts the base semiconductor layer **10**. The capacitor trench **45** is etched to a depth that terminates in the epitaxially grown semiconductor layer **15**. In some embodiments, the depth of the contact trench **35**, the isolation trench **40** and the capacitor trench **45** is related to the width of the opening in the etch mask that corresponds to the contact trench **35**, isolation trench **40** and the capacitor trench **45**. More specifically, as the width of the opening in the etch mask is increased, the etch rate of the exposed portions of semiconductor on insulator substrate (SOI) **5** increases. The etch rate increases within increased trench width, because the greater width allows for a greater amount of etchant to reach the surface to be etched than the narrower trench widths. Therefore, the etch process that simultaneously forms the contact trench **35**, the isolation trench **40**, and the capacitor trench **45**, etches the contact trench **35** and the isolation trench **40** to greater depths than the capacitor trench **45**.

In one embodiment, the simultaneous anisotropic etch that provides the contact trench **35**, isolation trench **40** and the capacitor trench **45** relies on aspect ratio dependent etching (ARDE) or RIE lag, where the etch rate is dependent on the dimensions of the trench opening, i.e., smaller trenches etch at a lower rate than larger trenches. In order to promote the directional etch, the etch is designed to facilitate an inhibitor film formation on the sidewall that helps maintain the trench profile and prevent ballooning. This inhibitor film tends to limit available etchant and reaction area to slow down the etch rate and eventually pinch off the smaller trenches earlier than the larger trenches. Additionally, incoming etchant ions have an angular distribution that will lead to a portion of the incoming ions to be captured by the sidewall. In a smaller trench, this ion depletion effect is much more pronounced than in a larger trench, thus reducing the etch rate of smaller trenches. Additionally, etchant ions are consumed by the etching and by-products are produced. So new etchant ions need to be replenished and the by-products need to be removed before further etching can take place. The transport of etchant ions and by-products are obviously more efficient in a larger opening, leading to ARDE. By properly designing the trench opening sizes **W1**, **W2**, and **W3**, the desired trench depths can be achieved for contact trench **35**, isolation trench **40** and the capacitor trench **45** using the same anisotropic etch process.

A conformal dielectric layer **50** may then be formed in the contact trench **35**, the isolation trench **40** and the capacitor trench **45**. The term "conformal" denotes a layer having a thickness that does not deviate from greater than or less than 20% of an average value for the thickness of the layer. The conformal dielectric layer **50** may be composed of any dielec-

tric material. For example, the conformal dielectric layer **50** employed at this stage may be any dielectric material including, but not limited to silicon nitride, silicon oxide, aluminum oxide, zirconium oxide, and hafnium oxide or a combination of dielectric materials. The conformal dielectric layer **50** may be deposited on the sidewall and base portions of the contact trench **35**, the isolation trench **40** and the capacitor trench **45**. The conformal dielectric layer **50** may be simultaneously formed on each of the contact trench **35**, the isolation trench **40** and the capacitor trench **45** using a blanket deposition. In one embodiment, the conformal dielectric layer **50** may be deposited using chemical vapor deposition (CVD) and/or atomic layer deposition (ALD). In another embodiment, the conformal dielectric layer **50** is formed using a growth process, such as thermal oxidation. In one embodiment, the conformal dielectric layer **50** may have a thickness of from 4.0 nm to 10.0 nm. In another embodiment, the conformal dielectric layer of the conformal dielectric layer **50** may have a thickness of from 2.5 nm to 7.0 nm, with a thickness of from 3.0 nm to 5.0 nm being more typical.

FIG. 2 depicts one embodiment of forming a block mask **55** over the isolation trench **40** and a capacitor trench **45**, and removing the conformal dielectric layer **50** from the base portion of the contact trench **35**. In one embodiment, the block mask **55** is formed by a non-conformally deposited material layer **56** that is formed over the capacitor trench **45**, the isolation trench **40**. In one embodiment, the non-conformally deposited material layer **56** is blanket deposited over the capacitor trench **45**, the isolation trench **40** and the contact trench **35**, and is then removed from the contact trench **35** using photolithography and etching. The non-conformal dielectric layer **56** that is deposited over the capacitor trench **45**, the isolation trench **40** and the contact trench **35** does not fill the trenches. The non-conformal dielectric layer **56** caps the capacitor trench **45**, the isolation trench **40** and the contact trench **35** by bridging across the contact opening **34**, the isolation opening **39** and the capacitor opening **44**. Illustrative examples of suitable materials for the non-conformal dielectric layer **56** include, but are not limited to,  $\text{SiO}_2$ , boron phosphor silicate glass (BPSG) oxide, fluorinated  $\text{SiO}_2$ ,  $\text{Si}_3\text{N}_4$ , organic thermoset or thermoplastic dielectrics such as polyimides, polyarylenes, benzocyclobutenes and the like, spun-on glasses including organosilicate glass (OSG), with or without porosity, such as hydrogen silsesquioxane, methyl silsesquioxane, tetraethylorthosilicate (TEOS) and the like, amorphous alloys of Si, O, C and H, or SiCOH, amorphous alloys of Si, O, F and H. In one embodiment, the non-conformal dielectric layer **56** is composed of silicon oxide ( $\text{SiO}_2$ ) that is deposited by high density plasma chemical vapor deposition (HDPCVD).

A photoresist mask **57** can be produced by applying a photoresist layer to the surface of the non-conformal dielectric layer **56**, exposing the photoresist layer to a pattern of radiation, and then developing the pattern into the photoresist layer utilizing resist developer. The remaining portion of the photoresist layer provides the photoresist mask **57** and remains over the non-conformal dielectric layer **56** that is overlying the isolation trench **40** and the capacitor trench **45**.

Alternatively, a hardmask may be substituted for the photoresist mask **57**. Hardmask materials include dielectric systems that may be deposited by chemical vapor deposition (CVD) and related methods. Typically, the hardmask composition includes silicon oxides, silicon carbides, silicon nitrides, silicon carbonitrides, etc. Spin-on dielectrics may also be utilized as a hardmask material including, but not limited to, silsesquioxanes, siloxanes, and boron phosphate silicate glass (BPSG). A block mask comprising a hardmask

## 11

material may be formed by blanket depositing a layer of hardmask material, providing a patterned photoresist atop the layer of hardmask material, and then etching the layer of hardmask material to provide a block mask (not shown) protecting the portion of the non-conformal dielectric layer **56** that is overlying the isolation trench **40** and the capacitor trench **45**.

A selective etch process may remove the exposed portion of the non-conformal dielectric layer **56** that is present over the contact trench **35**, while the portion of the non-conformal dielectric layer **56** that is present over the isolation trench **40** and the capacitor trench **45** is protected by the photoresist mask **57**. The selective etch process may remove the exposed portion of the non-conformal dielectric layer **56** without etching the hard mask dielectric layer **32**. The selective etch process may be an anisotropic etch, such as reactive ion etch.

Still referring to FIG. 2, following removal of the non-conformal dielectric layer **56** from the contact trench **35**, the portion of the conformal dielectric layer **50** that is present at the base of the contact trench **35** is removed to expose the base semiconductor layer **10**. The portion of the conformal dielectric layer **50** that is present at the base of the contact trench **35** may be removed using an anisotropic etch, such as reactive ion etch (RIE). The anisotropic etch that removes the portion of the conformal dielectric layer **50** that is present at the base of the contact trench **35** may also be provided by ion beam etching, plasma etching or laser ablation.

FIG. 3 depicts forming a dopant region **60** in the base semiconductor layer **10** at the base portion of the contact trench **35**. In one embodiment, the dopant region **60** is formed by ion implanting a p-type dopant into the base semiconductor layer **10**. As used herein, "p-type" refers to the addition of trivalent impurities to a semiconductor material that create deficiencies of valence electrons. The p-type conductivity dopant region **60** is produced within Si-containing substrates by doping the base semiconductor layer **10** with elements from group III-A of the Periodic Table of Elements. In one embodiment, a p-type dopant region **60** is formed by implanting dopants of at least one of boron, aluminum or gallium into the base surface of the contact trench **35** in the base semiconductor layer **10**.

In one embodiment, the p-type dopant may be ion implanted into the dopant region **60** using an energy of 0.5 keV to 15.0 keV with a dose of  $1 \times 10^{13}$  atoms/cm<sup>2</sup> to  $1 \times 10^{16}$  atoms/cm<sup>2</sup>. In another embodiment, the p-type dopant may be ion implanted into the dopant region **60** with using an energy of 1 keV to 5 keV with a dose of  $3 \times 10^{14}$  atoms/cm<sup>2</sup> to  $3 \times 10^{15}$  atoms/cm<sup>2</sup>.

The concentration of the p-type dopant that is present in the dopant region **60** is greater than  $1 \times 10^{17}$  atoms/cm<sup>3</sup>. In one embodiment, the concentration of the p-type dopant that is present in the dopant region **60** ranges from  $1 \times 10^{17}$  atoms/cm<sup>3</sup> to  $5 \times 10^{21}$  atoms/cm<sup>3</sup>. In another embodiment, the concentration of the p-type dopant that is present in the dopant region **60** ranges from  $1 \times 10^{19}$  atoms/cm<sup>3</sup> to  $5 \times 10^{20}$  atoms/cm<sup>3</sup>.

The block mask **55** may be removed and a metal nitride layer **65** may be deposited on the sidewalls and base surfaces of the contact trench **35**, the isolation trench **40** and the capacitor trench **45** as depicted in FIG. 4. The block mask **55** may be removed using chemical stripping, oxygen ashing, selective etching, or planarization, e.g., chemical mechanical planarization (CMP).

The metal nitride layer **65** that is present in the contact trench **35**, the isolation trench **40** and the capacitor trench **45** may be composed of titanium nitride (TiN), tantalum nitride (Ta<sub>2</sub>N), tantalum silicon nitride (TaSiN), tungsten nitride

## 12

(WN) or a combination thereof. In one embodiment, the metal nitride layer **65** may have a thickness ranging from 25 Å to 200 Å. In another embodiment, the metal nitride layer **65** has a thickness ranging from 50 Å to 100 Å.

In one embodiment, the metal nitride layer **65** is deposited using a conformal deposition method. The metal nitride layer **65** may be deposited using a physical vapor deposition (PVD) method, such as sputtering. In one embodiment, the sputtering deposition process for forming the metal nitride layer **65** includes applying high-energy particles to strike a solid slab of a metal target material to provide the metal constituent of the metal nitride layer **65**, such as titanium. The high-energy particles physically dislodge metal atoms of target material, which are then deposited on the sidewalls and base surfaces of the contact trench **35**, the isolation trench **40** and the capacitor trench **45**. The source of nitrogen for the metal nitride layer **65** may be provided by nitrogen gas (N<sub>2</sub>). The nitrogen source may be introduced to the sputtering chamber as the sputtered atoms of the metal constituent of the metal nitride layer **65** are migrating towards the deposition surface.

FIG. 5 depicts one embodiment of filling the contact trench **35**, the isolation trench **40** and the capacitor trench **45** with a conductive material **70**. The conductive material **70** may be a doped semiconductor, such as doped polysilicon, or a metal. In the embodiments in which the conductive material is provided by doped polysilicon, the dopant may be an n-type or p-type dopant having a dopant concentration ranging from  $1 \times 10^{18}$  atoms/cm<sup>3</sup> to  $1 \times 10^{20}$  atoms/cm<sup>3</sup>. The conductive material **70** may be deposited using physical vapor deposition (PVD), such as plating or sputtering, or may be deposited using chemical vapor deposition (CVD).

The pad dielectric stack **30** may be removed using a planarization process. Planarization is a material removal process that employs at least mechanical forces, such as frictional media, to produce a planar surface. One example of a planarization method that is suitable for removing the pad dielectric stack is chemical mechanical planarization (CMP). Chemical mechanical planarization (CMP) is a material removal process using both chemical reactions and mechanical forces to remove material and planarize a surface.

In one embodiment, the metal nitride layer **65**, the conformal dielectric layer **50**, and the conductive material **70** that is present within the contact trench **35**, the isolation trench **40** and the capacitor trench **45** is recessed using an anisotropic etch, such as reactive ion etch (RIE). The recessed portion of the conformal dielectric layer **50**, and the conductive material **70** does not extend into the epitaxially grown semiconductor layer **15**. The recessed portion of the conformal dielectric layer **50**, and the conductive material **70** may then be filled with a conductive material to provide a contact **75** to the conductive material **70**. This process allows the capacitor trench **45** to be connected with the upper semiconductor layer **25** in a DRAM application. In another embodiment where DRAM is not present, the recess process may be skipped and material **70** forms the trench fill as well as the top contact to trench fill. In some embodiments, the contact **75** is composed of metal semiconductor alloy, such as a silicide. Silicide formation typically requires depositing a refractory metal, such as Ni or Ti, onto the surface of a Si-containing material, such as a conductive fill composed of doped polysilicon. Following deposition, the structure is then subjected to an annealing step including, but not limited to, rapid thermal annealing. During thermal annealing, the deposited metal reacts with Si forming a metal silicide.

The structures contained within the contact trench **35** provide a substrate contact **100**. The substrate contact **100** extends from the upper semiconductor layer **25** through the



dielectric layer **20** and the n-type epitaxially grown semiconductor layer **15** to a p-type doped region **60** of the base semiconductor layer **10**. The substrate contact **100** substantially suppresses the potential fluctuation and noise in the base semiconductor layer **10**, since the base semiconductor layer **10** can be electrically tied to a fixed potential such as, but not limited to ground at desirable frequency.

The structures contained within the capacitor trench **45** provide a capacitor **110**. The capacitor **110** extends from the upper semiconductor layer **25** through the dielectric layer **20** into contact with the n-type epitaxially grown semiconductor layer **15**. The capacitor **110** is not in direct contact with the base semiconductor layer **10**. A “capacitor” is a structure including two electrically conductive materials separated and insulated from each other by a dielectric for storing a charge. The term “electrode” as used to describe a component of the capacitor **110** represents one of at least two electrically conductive materials of the capacitor **110** that are separated by a node dielectric layer. The electrodes of the capacitor **110** are provided by the metal nitride layer **65**, the conductive fill material **70**, and the portion of the n-type semiconductor layer **15** that is adjacent to the capacitor trench **44**. The metal nitride layer **65** and the conductive fill material **70** provide the upper electrode of the capacitor **110**. The portion of the n-type semiconductor layer **15** that is adjacent to the capacitor trench **44** provides the lower electrode of the capacitor **110**. The “node dielectric layer” is the dielectric layer that is present between the electrodes of the capacitor **110**. The node dielectric layer of the capacitor **110** depicted in FIG. **5** is provided by the non-conformal dielectric layer **50**.

The structures contained in the isolation trench **40** provide an electrical isolation region **105** to isolate region the n-type epitaxially grown semiconductor layer **15** that is surrounding capacitor trench **44** from n-type epitaxially grown semiconductor layer **15** that is surrounding substrate contact trench **34**. A parasitic U-shaped MOSFET is formed where the two regions of n-type epitaxially grown semiconductor layer **15** function as the source and drain, the conformal dielectric layer **50** functions as a gate dielectric and a gate conductor is provided by the metal nitride layer **65** and the conductive fill **70**. The portion of the isolation trench in the base semiconductor layer **10** defines the channel length and a low bias, such as ground, on the isolation trench conductive fill **70** can effectively turn this parasitic MOSFET off and provide isolation. In one embodiment, the isolation trench **39** needs to form an enclosed area to cut off all leakage paths.

FIG. **6** depicts another embodiment of the present disclosure, in which a protective metal layer **80** is formed on the conformal dielectric layer **50** within the contact trench **35** prior to forming the dopant region **60**. The protective metal layer **80** protects the conformal dielectric layer **50** during the processes that expose the base semiconductor layer **10** at the base portion of the contact trench **35** prior to ion implantation to form the dopant region **60**. The protective metal layer **80** is deposited after the conformal dielectric layer **50** has been formed in the contact trench **35**, the isolation trench **40** and the capacitor trench **45**, as depicted in FIG. **1**. Before depositing the protective metal layer **80**, a block mask **85** is formed over the isolation trench **40** and the capacitor trench **45**, wherein the contact trench **35** remains exposed. The block mask **85** is similar to the block mask **55** that is described with reference to FIG. **2**. In one embodiment, a non-conformally deposited material layer **86** is formed over the capacitor trench **45** and the isolation trench **40**. In one embodiment, the non-conformally deposited material layer **86** is blanket deposited over the capacitor trench **45**, the isolation trench **40** and the contact

trench **35**, and is then removed from the contact trench **35** using photolithography and etching, as depicted in FIG. **6**.

The non-conformal dielectric layer **86** that is deposited over the capacitor trench **45**, the isolation trench **40** and the contact trench **35** does not fill the trenches. The non-conformal dielectric layer **86** caps the capacitor trench **45**, the isolation trench **40** and the contact trench **35** by bridging across the contact opening **34**, the isolation opening **39** and the capacitor opening **44**. Illustrative examples of suitable materials for the non-conformal dielectric layer **86** include, but are not limited to, SiO<sub>2</sub>, boron phosphor silicate glass (BPSG) oxide, fluorinated SiO<sub>2</sub>, Si<sub>3</sub>N<sub>4</sub>, organic thermoset or thermoplastic dielectrics such as polyimides, polyarylenes, benzocyclobutenes and the like, spun-on glasses including organosilicate glass (OSG), with or without porosity, such as hydrogen silsesquioxane, methyl silsesquioxane, tetraethylorthosilicate (TEOS) and the like, amorphous alloys of Si, O, C and H, or SiCOH, amorphous alloys of Si, O, F and H. In one embodiment, the non-conformal dielectric layer **86** is composed of silicon oxide (SiO<sub>2</sub>) that is deposited by high density plasma chemical vapor deposition (HDPCVD).

A photoresist mask **87** can be produced by applying a photoresist layer to the surface of the non-conformal dielectric layer **86**, exposing the photoresist layer to a pattern of radiation, and then developing the pattern into the photoresist layer utilizing resist developer. The remaining portion of the photoresist layer remains over the non-conformal dielectric layer **86** that is overlying the isolation trench **40** and the capacitor trench **45**. A selective etch process may remove the exposed portion of the non-conformal dielectric layer **86** that is present over the contact trench **35**, while the portion of the non-conformal dielectric layer **86** that is present over the isolation trench **40** and the capacitor trench **45** is protected by the photoresist mask **87**. The selective etch process may be an anisotropic etch, such as reactive ion etch.

Still referring to FIG. **6**, the protective metal layer **80** may be formed within the contact trench **34** and is obstructed from being formed in the isolation trench **40** and the capacitor trench **45** by the block mask **85**. The protective metal layer **80** may be composed of titanium nitride (TiN), tantalum nitride (TaN), tantalum silicon nitride (TaSiN), tungsten nitride (WN) or a combination thereof.

The protective metal layer **80** is a conformally deposited layer. The protective metal layer **80** may be deposited using physical vapor deposition (PVD), such as sputtering. In one embodiment, the protective metal layer **80** may have a thickness ranging from 25 Å to 200 Å. In another embodiment, the protective metal layer **80** has a thickness ranging from 50 Å to 100 Å.

Following deposition of the protective metal layer **80**, an anisotropic etch may remove the horizontal surfaces of the protective metal layer **80**. For example, the portions of the protective metal layer **80** that are present on the pad dielectric stack **30** and the base of the contact trench **35** may be removed by reactive ion etch. In one embodiment, the etch process that removes the horizontal portions of the protective metal layer **80** is selective to the conformal dielectric layer **50**. Once the protective metal layer **80** that is present at the base portion of the contact trench **35** is removed, the portion of the conformal dielectric layer **50** that is present at the base portion of the contact trench **35** is removed to expose the underlying base semiconductor layer **10**. The exposed portion of the conformal dielectric layer **50** may be removed using an anisotropic etch that is selective to the base semiconductor layer **10**, such as reactive ion etch (RIE). The anisotropic etch that removes the exposed portion of the conformal dielectric layer **50** that

is present at the base of the contact trench **35** may also be provided by ion beam etching, plasma etching or laser ablation.

FIG. 7 depicts forming a dopant region **90** in the base semiconductor layer **10** at the base portion of the contact trench **35**. The dopant region **90** that is depicted in FIG. 7 is similar to the dopant region **60** that is described above with reference to FIG. 4. Therefore, the description of the composition and method of forming the dopant region **60** that is depicted in FIG. 4 is suitable for forming the dopant region **90** that is depicted in FIG. 7.

FIG. 8 depicts one embodiment of filling the contact trench **35**, the isolation trench **40** and the capacitor trenches **45** that are depicted in FIG. 7 with a metal nitride layer **95** and a conductive fill material **96**. In the embodiment that is depicted in FIG. 8, the metal nitride layer **95** is present in direct contact with the protective metal layer **80** on the sidewalls of the contact trench **35** and is present on the exposed portion of base semiconductor layer **10** at the base portion of the contact trench **35**. The metal nitride layer **95** and the conductive fill material **96** that are depicted in FIG. 8 are similar to the metal nitride layer **65** and the conductive fill material **70** that are depicted in FIG. 5. Therefore, the description of the composition and method of forming the metal nitride layer **65** and the conductive fill material **70** that is depicted in FIG. 5 is suitable for forming the metal nitride layer **95** and the conductive fill material **96** that is depicted in FIG. 8.

FIG. 8 also depicts forming contacts **97** composed of metal semiconductor material to at least the conductive fill material **96**. The contacts **97** that are depicted in FIG. 8 are similar to the contacts **75** that are depicted in FIG. 5. Therefore, the description of the composition and method of forming the contacts **75** that are depicted in FIG. 5 is suitable for forming the contacts **97** that are depicted in FIG. 8.

The substrate contact **100a** that is depicted in FIG. 8 is similar to the substrate contact **100** that is depicted in FIG. 5, but further includes a layer of protective metal, i.e., protective metal layer **80** that is present on the sidewall portions of the conformal dielectric layer **50** that is contained within the contact trench **35**. The protective metal layer **80** protects the conformal dielectric layer **50** that is present on the sidewalls of the contact trench **35** during the etch process sequence that exposes the portion of the base semiconductor layer **10** that is implanted to provide the dopant region **90** of the substrate contact **100a**. The electrical isolation region **105a** and the capacitor **110a** that are depicted in FIG. 8 may be identical to the electrical isolation region **105** and the capacitor **110** that are depicted in FIG. 5.

FIGS. 9-11 depict one embodiment of forming a contact **200** to the n-type epitaxially grown semiconductor layer **15**, i.e., n-type epitaxially grown semiconductor layer **15**. The method that is depicted in FIGS. 9-11 may be practiced in combination with or separately from the methods and structures disclosed in FIGS. 1-8. FIG. 9 depicts a substrate **5** that has been etched to provide a contact trench **202** into contact with an epitaxially grown semiconductor layer **15**, an isolation trench **40** into contact with the base semiconductor layer **10**, and a capacitor trench **45** having a base portion present in the epitaxially grown semiconductor layer **15**. The capacitor trench **45** and the isolation trench **40** are similar to the capacitor trench **45** and the isolation trench **40** that are depicted in FIG. 1. The contact trench **202** to the epitaxially grown semiconductor layer **15** that is depicted in FIG. 9 is differentiated from the contact trench **35** that is depicted in FIG. 1, because the contact trench **202** to the epitaxially grown semiconductor layer **15** is not in direct contact with the base semiconductor layer **10**. Referring to FIGS. 1 and 9, the contact trench **202** to

the epitaxially grown semiconductor layer **15** typically has a width **W4** that is less than the width **W2** of the contact trench **35** to the base semiconductor layer **10**. As indicated above, the depth of the trenches may be dependent upon the width of the opening in the etch mask that provides the trenches. Because the contact trench **202** to the epitaxially grown semiconductor layer **15** does not extend to the base semiconductor layer **10**, the width **W4** of the contact trench **202** may be similar to the width **W1** of the capacitor trench **45**, wherein the capacitor trench **45** also does not reach the base semiconductor layer **10**. The width **W4** of the contact trench **202** to the epitaxially grown semiconductor layer **15** is typically less than the width **W3** of the isolation trench **40**.

In one embodiment, the contact trench **202** to the epitaxially grown semiconductor layer **15** has a width **W4** ranging from 0.04  $\mu\text{m}$  to 0.3  $\mu\text{m}$ . In another embodiment, the contact trench **202** has a width **W4** ranging from 0.06  $\mu\text{m}$  to 0.1  $\mu\text{m}$ . In one embodiment, the depth **D4** of the contact trench **202** to the epitaxially grown semiconductor layer **15** ranges from 1  $\mu\text{m}$  to 8  $\mu\text{m}$ . In another embodiment, the depth **D4** of the contact trench **202** to the epitaxially grown semiconductor layer **15** ranges from 2  $\mu\text{m}$  to 4  $\mu\text{m}$ . With the exceptions of the dimensions of the contact trench **202**, the contact trench **202** to the epitaxially grown semiconductor layer **15**, the isolation trench **40** and the capacitor trench **45** are formed using methods and structures similar to those described above with reference to FIG. 1.

FIG. 9 further depicts forming a conformal dielectric layer **50** on the sidewall and base portions of the contact trench **202** to the epitaxially grown semiconductor layer **15**, the isolation trench **40** and the capacitor trench **45**. The conformal dielectric layer **50** that is depicted in FIG. 9 is similar to the conformal dielectric layer **50** that is described above with reference to FIG. 1.

FIG. 10 depicts one embodiment of removing the conformal dielectric layer **50** from the contact trench **202** to the epitaxially grown semiconductor layer **15**. The conformal dielectric layer **50** remains within the isolation trench **40** and the capacitor trench **45**. In one embodiment, prior to removing the conformal dielectric layer **50** from the contact trench **202**, an etch mask **203** is formed over the isolation trench **40** and the capacitor trench **45**, wherein the contact trench **202** to the epitaxially grown semiconductor layer **15** is exposed. The etch mask **203** may be formed from a non-conformally deposited layer **204** to enclose the isolation trench **40** and the capacitor trench **45** in combination with a photoresist mask **205** using deposition, photolithography and etch processes. The etch mask **203**, the non-conformally deposited layer **204** and the photoresist mask **205** that are depicted in FIG. 10 are similar to the block mask **85** that includes the non-conformally deposited material layer **86** and the photoresist mask **87** that is described above with reference to FIG. 6. Therefore, the description of the composition and method of forming the block mask **85** that is depicted in FIG. 6 is suitable for the etch mask **203** that is depicted in FIG. 10.

In one embodiment, following the formation of the etch mask **203**, the conformal dielectric layer **50** is removed from the contact trench **202** to the epitaxially grown semiconductor layer **15**. The conformal dielectric layer **50** may be removed using an anisotropic or isotropic etch that is selective to the epitaxially grown semiconductor layer **15**. In one embodiment, the conformal dielectric layer **50** may be removed from the contact trench **202** using a reactive ion etch (RIE).

FIG. 11 depicts filling the contact trench **202**, the isolation trench **40** and the capacitor trench **45** with at least one conductive material. In one embodiment, a metal nitride layer **206** is formed in each of the contact trench **202**, the isolation

trench **40** and the capacitor trench **45**. The metal nitride layer **206** is formed in direct contact with the epitaxially grown semiconductor layer **15** that provides the base and sidewall surfaces of the contact trench **202**. The metal nitride layer **206** is formed in direct contact with the conformal dielectric layer **50** in the isolation trench **40** and the capacitor trench **45**. A conductive fill material **207** is formed in direct contact with the metal nitride layer **206**. The conductive fill material **207** fills each of the contact trench **202**, the capacitor trench **45** and the isolation trench **40**.

The metal nitride layer **206** and the conductive fill material **207** that are depicted in FIG. **11** are similar to the metal nitride layer **65** and the conductive fill material **70** that are depicted in FIG. **5**. Therefore, the description of the composition and method of forming the metal nitride layer **65** and the conductive fill material **70** that is depicted in FIG. **5** is suitable for forming the metal nitride layer **206** and the conductive fill material **207** that is depicted in FIG. **11**. It should be pointed out that the embodiment is exemplary and for those skillful in the art, by using the block mask scheme described before, if the process sequence is adjusted and if different materials are used, other embodiments can be easily achieved such as an embodiment with the conductive fill material **207** directly in contact with epitaxially grown semiconductor layer **15** of the substrate, thus eliminating any Schottky barrier that may possibly exist between contact trench **202** and the epitaxially grown semiconductor layer **15**.

FIGS. **12-18** depict another embodiment of the present disclosure. Referring to FIG. **18**, in this embodiment, a semiconductor structure **500** is provided that includes a semiconductor on insulator (SOI) substrate **305** comprising an upper semiconductor layer **325**, a dielectric layer **320**, and a base semiconductor layer **310**. A substrate contact **400** is present in a first trench, i.e., contact trench **335**, that extends from an upper surface of the upper semiconductor layer **325** through the dielectric layer **320** into contact with the base semiconductor layer **310**. The substrate contact **400** includes a conductive fill material **370** that is in direct contact with a doped region **355** in the base semiconductor layer **310** with a sidewall portion of the contact trench **335** and is separated from the base portion of the contact trench **335** by a conformal dielectric layer **350**. The semiconductor structure **500** further includes a capacitor **410** present in a second trench, i.e., capacitor trench **345**, that extends from the upper surface of the upper semiconductor layer **325** through the dielectric layer **320** into contact with a doped region **355** within the base semiconductor layer **310**. In one embodiment, the capacitor **410** includes a buried plate, a node dielectric and an upper electrode. The node dielectric (identified by reference number **350**) of the capacitor **410** is present on the entirety of the sidewalls and base portions of the capacitor trench that is present in the base semiconductor layer **310**, and is identical in composition to the conformal dielectric layer **350** that is present in the contact trench **335**.

FIG. **12** depicts one embodiment of an initial structure that may be used to provide the semiconductor structure **500** that is depicted in FIG. **18**. The initial structure may include a semiconductor on insulator (SOI) substrate **305** and a pad dielectric stack **330**. The semiconductor on insulator (SOI) substrate **305** that is depicted in FIG. **12** is similar to the semiconductor on insulator (SOI) substrate **5** that is depicted in FIG. **1**, with the exception that in the embodiment that is depicted in FIGS. **12-18** the semiconductor on insulator (SOI) substrate **305** does not include an epitaxially grown semiconductor layer between the dielectric layer **320** and the base semiconductor layer **310**. The base semiconductor layer **310** that is depicted in FIG. **12** is equivalent to the base semicon-

ductor layer **310** that is described above with reference to FIG. **1**. The dielectric layer **320** that is depicted in FIG. **12** is equivalent to the dielectric layer **20** that is described above with reference to FIG. **1**. The semiconductor on insulator (SOI) substrate **305** further includes an upper semiconductor layer **325** that is in direct contact with the upper surface of the dielectric layer **320**. The upper semiconductor layer **325** that is depicted in FIG. **12** is equivalent to the upper semiconductor layer **25** that is described above with reference to FIG. **1**.

The pad dielectric stack **330** that is depicted in FIG. **12** is similar to the pad dielectric stack **30** that is depicted in FIG. **1**. The pad dielectric stack **330** depicted in FIG. **12** includes an oxide containing pad dielectric layer **329** that is present on the upper surface of the upper semiconductor layer **325**, a nitride containing pad dielectric layer **331** that is present on the upper surface of the oxide containing pad dielectric layer **329**, and a hard mask dielectric layer **332** that is present on the upper surface of the nitride containing pad dielectric layer **331**.

The oxide containing pad dielectric layer **329** may be composed of any oxide material, such as silicon oxide ( $\text{SiO}_2$ ). The oxide containing pad dielectric layer **329** may be formed using deposition methods, such as chemical vapor deposition (CVD), or thermal growth methods, such as thermal oxidation. The oxide containing pad dielectric layer **329** may have a thickness ranging from 50 nm to 200 nm. In another example, the oxide containing pad dielectric layer **329** has a thickness ranging from 100 nm to 150 nm.

The nitride containing pad dielectric layer **331** and the hard mask dielectric layer **332** are equivalent to the nitride containing pad dielectric layer **31** and the hard mask dielectric layer **32** that are described above with reference to FIG. **1**. Therefore, the description of the composition and method of forming the nitride containing pad dielectric layer **31** and the hard mask dielectric layer **32** that are depicted in FIG. **1** are suitable for the nitride containing pad dielectric layer **331** and the hard mask dielectric layer **332** that are depicted in FIG. **12**.

FIG. **13** depicting one embodiment of etching a contact trench **335** and a capacitor trench **345** into contact with the base semiconductor layer **310** of the semiconductor on insulator substrate (SOI) **305**. The contact trench **335** and the capacitor trench **345** are formed using photolithography and etch processes similar to those described for forming the contact trench **35** and the capacitor trench **45** that are depicted in FIG. **1**.

Referring to FIG. **13**, the contact trench **335** and the capacitor trench **345** may be formed simultaneously using the same etch mask, i.e., a single etch mask is used to form each of the contact trench **335** and the capacitor trench **345**. The etching operation may be carried out in a dry etching tool with an inductively coupled plasma for activating the etchant. Halogen-containing gases such as  $\text{CF}_4$ ,  $\text{SF}_6$ ,  $\text{CHF}_3$ ,  $\text{Cl}_2$ ,  $\text{HBr}$ , etc. are generally used as etching gases. In one embodiment, the contact trench **335** is etched to a greater depth into the base semiconductor layer **310** than the capacitor trench **345**. In some embodiments, the depth of the contact trench **335** and the capacitor trench **345** is related to the width of the opening in the etch mask that corresponds to the contact trench **335** and the capacitor trench **345**. More specifically, as the width of the opening in the etch mask is increased the etch rate of the semiconductor on insulator substrate (SOI) **305** increases due to aspect ratio dependent etching (ARDE) phenomena, or RIE lag. As a result, the etch process that simultaneously forms the contact trench **335** and the capacitor trench **345**, etches the contact trench **335** to greater depths into the base semiconductor layer **310** than the capacitor trench **345**.

In one embodiment, the contact trench **335** has a width  $W5$  that is greater than the second width  $W6$  of the capacitor

trench **345**. The first width **W5** of the contact trench **335** may range from 0.1  $\mu\text{m}$  to 1.0  $\mu\text{m}$ . In another embodiment, the first width **W5** of the contact trench **335** may range from 0.2  $\mu\text{m}$  to 0.5  $\mu\text{m}$ . The capacitor trench **345** has a width **W6** that ranges from 0.05  $\mu\text{m}$  to 0.5  $\mu\text{m}$ . In another embodiment, the capacitor trench **345** has a width **W6** that ranges from 0.1  $\mu\text{m}$  to 0.25  $\mu\text{m}$ .

The contact trench **335** has a depth **D5** that is greater than depth **D6** of the capacitor trench **345**. In one embodiment, the contact trench **335** has a depth **D5** that ranges from 2  $\mu\text{m}$  to 10  $\mu\text{m}$ , as measured from the upper surface of the upper semiconductor layer **325**. In another embodiment, the contact trench **335** has a depth **D5** that ranges from 4  $\mu\text{m}$  to 7  $\mu\text{m}$ . In one embodiment, the capacitor trench **345** has a depth **D6** that ranges from 1  $\mu\text{m}$  to 6  $\mu\text{m}$ , as measured from the upper surface of the upper semiconductor layer **325**. In another embodiment, the capacitor trench **345** has a depth **D6** that ranges from 2  $\mu\text{m}$  to 4  $\mu\text{m}$ . It is noted that although FIG. 13 depicts forming two capacitor trenches **345**, it is noted that the present disclosure is not limited to forming only two capacitor trenches **345**, as any number of capacitor trenches **345** may be formed.

FIG. 14 depicts forming first doped region **355a** in the base semiconductor layer **310** of the substrate **305** adjacent to the contact trench **335** and a second doped region **355b** in the base semiconductor layer **310** of the substrate adjacent to the capacitor trench **345**. A doped connecting region **356** of the same dopant type connects the first doped region **355a** that is adjacent to contact trench **335** and the second doped region **355b** that is adjacent to the capacitor trench **345**. The doped connecting region **356** can be formed with a mask and ion implantation. The first doped region **355a** is contacted by the later formed substrate contact **400**. The second doped region **355b** may provide the buried plate electrode of the subsequently formed capacitor **410**. In one embodiment, the first dopant region **355a**, the second doped region **355b** and the doped connecting region **356** are doped to an n-type conductivity. In some examples, the second doped region **355b** may be referred to as an N+ buried plate diffusion region.

In one example, producing an n-type first and second doped region **355a**, **355b** may begin with introducing an n-type dopant source to the sidewalls of the contact trench **335** and the capacitor trench **345**, and then thermally diffusing the dopant into the base semiconductor layer **310** of the semiconductor on insulator substrate **305**. The dopant source to produce the N+ buried plate diffusion region may be introduced by ion-implanting an impurity, such as arsenic (As) or phosphorus (P), into the sidewall of the contact trench **335** and the capacitor trench **345**. Arsenic (As) may be ion-injected into the contact trench **335** and the capacitor trench **345** under the conditions of an accelerating voltage, of about 20 kV, and at a dose of about  $5 \times 10^{15}/\text{cm}^2$ . Depositing a layer of N-type doped material, such as arsenic doped silicate glass, may also form the first and second doped regions **355a**, **355b**. After the impurities are introduced to the sidewalls of the contact trench **335** and the capacitor trench **345**, the semiconductor on insulator (SOI) substrate **305** is then heated in an  $\text{N}_2$  atmosphere at a temperature of about 900° C. for about 30 minutes, thereby diffusing N-type dopants into the base semiconductor layer **310**. In another embodiment, a gaseous doping source, such as  $\text{AsH}_3$  or plasma doping source, may also be used to dope the sidewall of the contact trench **335** and the capacitor trench **345** to form the first and second doped regions **355a**, **355b**.

FIG. 15 depicts one embodiment of forming a conformal dielectric layer **360** on the contact trench **335** and the capacitor trench **345**, and forming a conformal metal containing

layer **365** on the conformal dielectric layer **360**. The conformal dielectric layer **360** is present on the base and sidewall portions of the contact trench **335** and the capacitor trench **345**.

The conformal dielectric layer **360** may be composed of any dielectric material. For example, the conformal dielectric layer **360** employed at this stage may be any dielectric material including, but not limited to silicon nitride, silicon oxide, aluminum oxide, zirconium oxide, and hafnium oxide. The conformal dielectric layer **360** may be deposited on the sidewall and base portions of the contact trench **335** and the capacitor trench **345**. The conformal dielectric layer **360** may be simultaneously formed on each of the contact trench **335** and the capacitor trench **345** using a blanket deposition. In one embodiment, the conformal dielectric layer **360** may be deposited using chemical vapor deposition (CVD) and/or atomic layer deposition (ALD). In another embodiment, the conformal dielectric layer **360** is formed using a growth process, such as thermal oxidation. In one embodiment, the conformal dielectric layer **360** may have a thickness of from 4.0 nm to 10.0 nm. In another embodiment, the conformal dielectric layer **360** may have a thickness of from 2.5 nm to 7.0 nm, with a thickness of from 3.0 nm to 5.0 nm being more typical.

The conformal metal layer **365** that is depicted in FIG. 17 is similar to the conformal metal layer **65** that is depicted in FIG. 4. Therefore, the description of the composition and method of forming the conformal metal layer **65** that is depicted in FIG. 4 is suitable for forming the conformal metal layer **365** that is depicted in FIG. 17.

FIG. 16 depicts one embodiment of filling the contact trench **335** and the capacitor trench **345** with a doped semiconductor material **396**. The doped semiconductor material **396** may be a doped polysilicon. In the embodiments in which the doped semiconductor material **396** is provided by doped polysilicon, the dopant may be an n-type or p-type dopant having a dopant concentration ranging from  $1 \times 10^{18}$  atoms/ $\text{cm}^3$  to  $1 \times 10^{20}$  atoms/ $\text{cm}^3$ . The doped semiconductor material **396** may be deposited using chemical vapor deposition (CVD). The doped semiconductor material **396** may be deposited using a method that encapsulates a void in the lower portion of the capacitor trenches **345**.

FIG. 17 depicts recessing the conformal dielectric layer **360**, the conformal metal layer **365**, and the doped semiconductor material **396** within the contact trench **335** and the capacitor trench **345**. At least a portion of the pad dielectric stack **330** may be removed from the upper surface of the upper semiconductor layer **325** of the semiconductor substrate **305**. The pad dielectric stack **330** may be removed using a planarization process. One example of a planarization method that is suitable for removing the pad dielectric stack **330** is chemical mechanical planarization (CMP). In one example, the planarization method may remove the nitride containing pad dielectric layer **331** and the hard mask dielectric layer **332** stopping on the oxide containing pad dielectric layer **329**.

In one embodiment, the conformal dielectric layer **360**, the conformal metal layer **365**, and the doped semiconductor material **396** is recessed using an anisotropic etch, such as reactive ion etch (RIE). In one example, the conformal dielectric layer **360**, the conformal metal layer **365**, and the doped semiconductor material **396** may be recessed using an etch that is selective to the oxide containing pad dielectric layer **329**.

Referring to FIG. 17, the conformal dielectric layer **360**, the conformal metal containing layer **365**, and the doped semiconductor material **396** in capacitor trench **345** is typically recessed below the interface between the dielectric layer

320 and the upper semiconductor layer 325 to facilitate electrical connection between the upper semiconductor layer 325 and the doped semiconductor material 396. The upper surface of the conformal dielectric layer 360, the conformal metal containing layer 365 and the doped semiconductor material 396 is above the interface of the dielectric layer 320 and the base semiconductor layer 310 to prevent shorting to capacitor plate 355. Because the width W6 of the contact trench 335 is larger than width W5 of the capacitor trench 345, the aspect ratio dependent etching effect provides that the conformal dielectric layer 360, the conformal metal containing layer 365 and the doped semiconductor material 396 that is present in the contact trench 335 is recessed to a greater depth than the conformal dielectric layer 360, the conformal metal containing layer 365 and the doped semiconductor material 396 that is present in the capacitor trench 345. Because the conformal dielectric layer 360, the conformal metal containing layer 365 and the doped semiconductor material 396 that are present in the contact trench 335 are recessed below the upper surface of the base semiconductor layer 310, the subsequent conductive fill 370 will bring conductive fill 370 into direct contact with first doped region 355a that is adjacent to contact trench 335 and form plate contact.

In one embodiment, the material layers that are contained within the contact trench 335 are recessed by a dimension R1 ranging from 100 nm to 400 nm, as measured from the upper surface of the upper semiconductor layer 325. In another embodiment, the material layers that are contained within the contact trench 335 are recessed by a dimension R1 ranging from 200 nm to 300 nm, as measured from the upper surface of the semiconductor layer 325. In one embodiment, the material layers that are contained within the capacitor trench 345 are recessed by a dimension R2 ranging from 100 nm to 300 nm, as measured from the upper surface of the upper semiconductor layer 325. In another embodiment, the material layers that are contained within the capacitor trench 345 are recessed by a dimension R2 ranging from 150 nm to 250 nm, as measured from the upper surface of the semiconductor layer 325.

FIG. 18 depicts filling the contact trench 335 and the capacitor trench 345 with a conductive material 370. The conductive material 370 may be a doped semiconductor, such as doped polysilicon, or a metal. In the embodiments in which the conductive material 370 is provided by doped polysilicon, the dopant may be an n-type or p-type dopant having a dopant concentration ranging from  $1 \times 10^{18}$  atoms/cm<sup>3</sup> to  $1 \times 10^{20}$  atoms/cm<sup>3</sup>. The conductive material 370 may be deposited using physical vapor deposition (PVD), such as plating or sputtering, or may be deposited using chemical vapor deposition (CVD). Following deposition of the conductive fill material 370, a planarization process, such as chemical mechanical planarization, may be employed. The planarization process may remove the oxide containing pad dielectric layer 329. Following removal of the oxide containing pad dielectric layer 329, the upper surface of the conductive material 370 that is present within the contact trench 335 and the capacitor trench 345 may be coplanar with the upper surface of the upper semiconductor layer 325.

The conductive material 370 is the portion of the substrate contact 400 that provides electrical communication to the base semiconductor layer 310 of the semiconductor on insulator (SOI) substrate 5. The conductive material 370 that is present within the contact trench 335 provides electrical contact to the doped plate region of the capacitor trench 345, with the help of the doped connecting region 356.

The capacitor 410, is provided by the second dopant region 355b present about the capacitor trenches 345 and the con-

formal dielectric layer 360, the conformal metal layer 365, and the doped semiconductor material 396 that are contained within the capacitor trench 345. The conformal dielectric layer 360 provides the node dielectric of the capacitor 410. The second doped region 355b provides the lower electrode, e.g., buried plate electrode, of the capacitor 410. The doped semiconductor material 396 and the conformal metal layer 365 provide the upper electrode of the capacitor 410. The conductive material 370 that is present within the capacitor trench 345 provides electrical contact to the upper electrode of the capacitor 410.

FIG. 18 further depicts forming isolation regions 375, e.g., shallow trench isolation (STI) regions, through the upper semiconductor layer 325 into contact with the dielectric layer 320. The isolation regions 375 are positioned to electrically isolate the substrate contact 400 from the capacitors 410. In one embodiment, isolation regions 375 may be employed to isolate adjacent capacitors 410 from one another.

In a DRAM application, access transistors 380 may be formed to the capacitors 410. The access transistors 380 may be field effect transistors. A field effect transistor is a semiconductor device in which output current, i.e., source-drain current, is controlled by the voltage applied to a gate structure. A field effect transistor has three terminals, i.e., a gate structure, a source region (not shown) and a drain region (not shown). The gate structure is a structure used to control output current, i.e., flow of carriers in the channel, of a semiconductor device, such as a field effect transistor, through electrical or magnetic fields. The gate structure is formed on a portion of the upper semiconductor layer 325 that is adjacent to the capacitor trench 345. The channel is the region between the source region and the drain region of a field effect transistor (FET) that becomes conductive when the semiconductor device is turned on. The source region, is a doped region in the transistor, in which majority carriers are flowing into the channel. The drain region is the doped region in transistor located at the end of the channel, in which carriers are flowing out of the semiconductor device through the drain region. The source regions and drain regions are formed within the upper semiconductor layer 325. One of the source regions and drain regions is in electrical communication with the conductive material 370 that is present within the capacitor trench 345. Although not depicted in FIGS. 5, 8 and 11, the above-described access transistors may be employed in combination with the capacitor structures described with reference to FIGS. 5, 8 and 11. In a capacitor application such as decoupling capacitors, access transistors are not needed.

Referring to FIG. 18, metal semiconductor alloy regions 385 may be formed as contact pad to the conductive material 370 that is present in the contact trench 335, and as a contact pad to the source region or drain region of the access transistor 380 that is not in direct electrical communication with the conductive material 370 within the capacitor trench 345. In one embodiment, the metal semiconductor alloy regions 385 may be composed of a silicide, such as nickel silicide, cobalt silicide or tungsten silicide.

A layer of dielectric material (not shown) may be blanket deposited atop the entire semiconductor on insulator (SOI) substrate and planarized. The blanket dielectric may be selected from the group consisting of silicon containing materials such as SiO<sub>2</sub>, Si<sub>3</sub>N<sub>4</sub>, SiO<sub>x</sub>N<sub>y</sub>, SiC, SiCO, SiCOH, and SiCH compounds; the above-mentioned silicon containing materials with some or all of the Si replaced by Ge; carbon-doped oxides; inorganic oxides; inorganic polymers; hybrid polymers; organic polymers such as polyamides or SiLK™; other carbon-containing materials; organo-inorganic materi-

als such as spin-on glasses and silsesquioxane-based materials; and diamond-like carbon (DLC, also known as amorphous hydrogenated carbon, a-C:H). Additional choices for the blanket dielectric include: any of the aforementioned materials in porous form, or in a form that changes during processing to or from being porous and/or permeable to being non-porous and/or non-permeable.

The blanket dielectric may be formed by various methods well known to those skilled in the art, including, but not limited to: spinning from solution, spraying from solution, chemical vapor deposition (CVD), plasma enhanced CVD (PECVD), sputter deposition, reactive sputter deposition, ion-beam deposition, and evaporation.

The deposited dielectric is then patterned and etched to form via holes to the various contact pads **385**. Following via formation interconnects **390** are formed by depositing a conductive metal into the via holes using conventional processing, such as CVD or plating. The conductive metal may include, but is not limited to: tungsten, copper, aluminum, silver, gold, and alloys thereof.

Backside substrate contacts are not suitable in the above-described embodiments, because the backside of the base semiconductor layer is in contact with the packaging layers of the device, which obstruct backside contacts from providing electrical communication to the base semiconductor layer of the substrate.

While the methods and structures disclosed herein have been particularly shown and described with respect to preferred embodiments thereof, it will be understood by those skilled in the art that the foregoing and other changes in forms and details may be made without departing from the spirit and scope of the present disclosure. It is therefore intended that the methods and structures disclosed herein not be limited to the exact forms and details described and illustrated, but fall within the scope of the appended claims.

What is claimed is:

**1.** A method of forming a semiconductor device comprising:

providing a material stack comprising an epitaxially grown semiconductor layer on a base semiconductor layer, a dielectric layer on the epitaxially grown semiconductor layer, and an upper semiconductor layer present on the dielectric layer;

forming an etch mask on an upper surface of the upper semiconductor layer, wherein the etch mask comprises a contact opening, an isolation opening and a capacitor opening;

etching a contact trench into contact with the base semiconductor layer, an isolation trench into contact with the base semiconductor layer, and a capacitor trench having a base portion present in the epitaxially grown semiconductor layer;

forming a conformal dielectric layer on the contact trench, the isolation trench and the capacitor trench;

removing the conformal dielectric layer from a base portion of the contact trench, wherein said removing the conformal dielectric layer comprises forming a block mask over the isolation trench and the capacitor trench, and removing an exposed portion of the conformal dielectric layer that is present at the base portion of the contact trench using an anisotropic etch, wherein the conformal dielectric layer at base portions of the capacitor trench and the isolation trench remain;

forming a dopant region in the base semiconductor layer at the base portion of the contact trench; and

filling the contact trench, the isolation trench and the capacitor trench with a conductive material.

**2.** The method of claim **1**, wherein the epitaxially grown semiconductor layer has a thickness that is greater than 1.0 micron.

**3.** The method of claim **1**, wherein the forming of the etch mask comprises depositing at least one pad nitride layer on the upper semiconductor layer, forming a photoresist mask atop the at least one pad nitride layer, and etching the at least one pad nitride layer to provide the etch mask.

**4.** The method of claim **1**, wherein the capacitor trench has a first width, the contact trench has a second width, and the isolation trench has a third width, wherein the third width is greater than the second width and the second width is greater than the first width.

**5.** The method of claim **1**, wherein the base semiconductor layer is doped with a p-type dopant, and the epitaxially grown semiconductor layer is doped to an n-type dopant.

**6.** The method of claim **1**, wherein the etching comprises an anisotropic etch step.

**7.** The method of claim **1**, wherein the forming of the conformal dielectric layer on the contact trench, the isolation trench and the capacitor trench comprises deposition of a silicon nitride node dielectric layer on sidewalls and base portions of each of the contact trench, the isolation trench and the capacitor trench.

**8.** The method of claim **1**, wherein the forming of the dopant region in the base semiconductor layer at the base portion of the contact trench comprises ion implantation of a p-type dopant into the base semiconductor layer at the base portion of the contact trench.

**9.** The method of claim **1**, wherein the filling the contact trench, the isolation trench and the capacitor trench with a conductive material comprises depositing a conformal layer of metal nitride on sidewalls and base portions of the contact trench, the isolation trench and the capacitor trench, and filling the contact trench, the isolation trench and the capacitor trench with a doped semiconductor or a metal.

**10.** A method of forming a semiconductor device comprising:

providing a material stack comprising an epitaxially grown semiconductor layer on a base semiconductor layer, a dielectric layer on the epitaxially grown semiconductor layer, and an upper semiconductor layer present on the dielectric layer;

forming an etch mask on an upper surface of the upper semiconductor layer, wherein the etch mask comprises a contact opening, an isolation opening and a capacitor opening;

etching a contact trench into contact with the base semiconductor layer, an isolation trench into contact with the base semiconductor layer, and a capacitor trench having a base portion present in the epitaxially grown semiconductor layer;

forming a conformal dielectric layer on the contact trench, the isolation trench and the capacitor trench;

removing the conformal dielectric layer from a base portion of the contact trench;

forming a dopant region in the base semiconductor layer at the base portion of the contact trench; and

filling the contact trench, the isolation trench and the capacitor trench with a conductive material, wherein the filling the contact trench, the isolation trench and the capacitor trench with a conductive material comprises depositing a conformal layer of metal nitride on sidewalls and base portions of the contact trench, the isolation trench and the capacitor trench, and filling the contact trench, the isolation trench and the capacitor trench with a doped semiconductor or a metal.

## 25

11. The method of claim 10, wherein the epitaxially grown semiconductor layer has a thickness that is greater than 1.0 micron.

12. The method of claim 10, wherein the forming of the etch mask comprises depositing at least one pad nitride layer on the upper semiconductor layer, forming a photoresist mask atop the at least one pad nitride layer, and etching the at least one pad nitride layer to provide the etch mask.

13. The method of claim 10, wherein the capacitor trench has a first width, the contact trench has a second width, and the isolation trench has a third width, wherein the third width is greater than the second width and the second width is greater than the first width.

14. The method of claim 10, wherein the base semiconductor layer is doped with a p-type dopant, and the epitaxially grown semiconductor layer is doped to an n-type dopant.

15. The method of claim 10, wherein the etching comprises an anisotropic etch step.

16. The method of claim 10, wherein the forming of the conformal dielectric layer on the contact trench, the isolation

## 26

trench and the capacitor trench comprises deposition of a silicon nitride node dielectric layer on sidewalls and base portions of each of the contact trench, the isolation trench and the capacitor trench.

17. The method of claim 10, wherein the removing of the conformal dielectric layer from the base portion of the contact trench comprises forming a block mask over the isolation trench and the capacitor trench, and removing an exposed portion of the conformal dielectric layer that is present at the base portion of the contact trench using an anisotropic etch, wherein the conformal dielectric layer at base portions of the capacitor trench and the isolation trench remain.

18. The method of claim 10, wherein the forming of the dopant region in the base semiconductor layer at the base portion of the contact trench comprises ion implantation of a p-type dopant into the base semiconductor layer at the base portion of the contact trench.

\* \* \* \* \*