



US008734613B1

(12) **United States Patent**
Frank et al.

(10) **Patent No.:** **US 8,734,613 B1**
(45) **Date of Patent:** **May 27, 2014**

(54) **GLASS FIBER ENHANCED MINERAL WOOL
BASED ACOUSTICAL TILE**

(71) Applicant: **USG Interiors, LLC**, Chicago, IL (US)

(72) Inventors: **William A. Frank**, Lake Villa, IL (US);
Terry Rosenstiel, Vernon Hills, IL (US)

(73) Assignee: **USG Interiors, LLC**, Chicago, IL (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/935,597**

(22) Filed: **Jul. 5, 2013**

(51) **Int. Cl.**

D21H 13/40 (2006.01)
E04B 1/82 (2006.01)
D21J 1/20 (2006.01)
E04B 1/84 (2006.01)
E04B 2/02 (2006.01)

(52) **U.S. Cl.**

CPC . **D21H 13/40** (2013.01); **D21J 1/20** (2013.01);
E04B 1/8409 (2013.01); **E04B 2/02** (2013.01)
USPC **162/145**; 162/156; 162/158; 428/292.4;
428/317.9; 181/284; 181/286

(58) **Field of Classification Search**

CPC C04B 14/22; C04B 14/46; E04B 9/04;
B29C 67/249; B29K 2309/08; B29K 2709/08;
B29K 2995/0002; B32B 2262/101; D21H
13/40; D21J 1/20; B28B 29/0092
USPC 162/145, 152, 156, 158, 164.1, 168.1,
162/175; 428/294.4, 317.9; 181/284, 286,
181/290

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,239,973 A * 3/1966 Hahn et al. 52/144
4,040,213 A 8/1977 Capaul
4,097,209 A * 6/1978 Garrick et al. 425/82.1
4,129,637 A * 12/1978 Kennedy 264/112
4,146,564 A * 3/1979 Garrick et al. 264/516
4,226,674 A 10/1980 Gross et al.
4,847,140 A 7/1989 Jaskowski
5,055,341 A 10/1991 Yamaji et al.
5,071,511 A 12/1991 Pittman
5,148,645 A 9/1992 Lehnert et al.

5,968,629 A 10/1999 Masui et al.
6,284,351 B1 9/2001 Sensenig
6,443,256 B1 * 9/2002 Baig 181/286
6,616,804 B2 9/2003 Foster et al.
6,743,830 B2 * 6/2004 Soane et al. 521/83
6,877,585 B2 * 4/2005 Tinianov 181/290
6,929,091 B2 * 8/2005 Bertagni et al. 181/150
7,294,218 B2 11/2007 Haque et al.
7,547,375 B2 6/2009 Jaffee et al.
7,842,629 B2 11/2010 Jaffee
8,062,565 B2 11/2011 Mueller et al.
2002/0029929 A1 * 3/2002 Tinianov 181/290
2002/0096278 A1 7/2002 Foster et al.
2002/0128352 A1 * 9/2002 Soane et al. 523/200
2002/0139611 A1 * 10/2002 Baig 181/286
2003/0041987 A1 3/2003 Foster et al.
2003/0060113 A1 * 3/2003 Christie et al. 442/364
2004/0050619 A1 3/2004 Bargo, II
2004/0129492 A1 * 7/2004 Bertagni et al. 181/150
2005/0008845 A1 1/2005 Hatanaka et al.
2005/0266757 A1 12/2005 Roekens et al.
2007/0027283 A1 2/2007 Swift et al.
2007/0045892 A1 * 3/2007 Sucech et al. 264/171.13
2007/0060005 A1 3/2007 Yang et al.
2008/0003431 A1 1/2008 Fellingner et al.
2008/0156581 A1 * 7/2008 Englert et al. 181/290
2009/0252941 A1 * 10/2009 Mueller et al. 428/219
2009/0253323 A1 * 10/2009 Mueller et al. 442/150
2010/0101891 A1 4/2010 Kamikawa
2010/0320029 A1 * 12/2010 Cao et al. 181/286
2011/0021101 A1 1/2011 Hawkins et al.
2012/0024625 A1 2/2012 Cao et al.
2012/0161058 A1 * 6/2012 Albarran 252/62
2013/0023174 A1 1/2013 Quinn
2014/0014437 A1 * 1/2014 Wilson 181/290

FOREIGN PATENT DOCUMENTS

GB 2096943 A * 10/1982

* cited by examiner

Primary Examiner — Jose Fortuna

(74) *Attorney, Agent, or Firm* — Pearne & Gordon LLP

(57) **ABSTRACT**

A wet laid basemat for an acoustical ceiling tile comprising on a dry weight basis, 50% or more mineral wool fiber, including shot, less than 9% binder, and between 5 and 20% chopped strand glass fiber, and, optionally, minor amounts of other constituents, whereby the chopped strand glass fibers serve to promote and/or maintain voids in the mat such that the dry basemat has a density of between about 7½ to about 10½ lbs. per cubic foot and an NRC substantially greater than 0.55.

4 Claims, 4 Drawing Sheets




FIG. 1
(PRIOR ART)




FIG. 2




FIG. 3




FIG. 4

1

GLASS FIBER ENHANCED MINERAL WOOL
BASED ACOUSTICAL TILE

BACKGROUND OF THE INVENTION

The invention relates to acoustical tiles particularly suited for use in suspended ceilings.

PRIOR ART

Mineral fiber based ceiling tiles have long been available. Such tiles or panels are conventionally made by water felting dilute aqueous dispersions of mineral wool. In this process, an aqueous slurry of mineral wool, binder and minor quantities of other ingredients, as desired or necessary, is flowed onto a moving foraminous support wire, such as that of a Fourdrinier or Oliver mat forming machine, for dewatering. The slurry may be first dewatered by gravity, and then dewatered by vacuum suction to form a basemat; the wet basemat is then pressed to the desired thickness between rolls or an overhead travelling wire and the support wire to remove additional water. The pressed basemat is then dried in heated drying ovens, and the dried material is cut to the desired dimensions and optionally sanded and/or top coated, or covered with an adhesively attached fiberglass scrim and ultimately painted to produce finished acoustical ceiling tiles or panels.

While water felted mineral wool based acoustical ceiling tiles are relatively economical to produce because of low raw material costs, they exhibit relatively low NRC (noise reduction coefficient) values of about 0.55. It has long been desirable to produce mineral fiber-based acoustical ceiling tiles with improved NRC values.

SUMMARY OF THE INVENTION

The invention provides a mineral wool based water felted acoustical ceiling tile construction that achieves improved NRC values and that can be produced in existing facilities and with conventional processing.

The invention resides in the discovery that ordinary wet used chop strand, WUCS, fiberglass, preferably of certain characteristics, can be substituted in small fractional quantities for mineral fiber in a typical product formulation. The result of the substitution is a surprising increase in loft in the basemat. This loft represents a significant decrease in density and a corresponding increase in porosity and, consequently, sound absorption.

The invention enables the production of relatively low density, relatively thick acoustical panels capable of achieving NRC values substantially greater than 0.55 and up to 0.95 or higher, putting the performance of these tiles at the high end of the spectrum of acoustical tiles.

The body of the inventive panel is characterized by the presence of voids, which are large compared to average interstitial spaces between the composite fibers, distributed randomly throughout the panel body. The voids, by some mechanism not fully understood, are created by the presence of the glass fibers. The population of the voids appears to be proportional to the quantity of glass fibers in the basemat formulation. Fiber length and fiber diameter appear to be additional factors in the successful creation of the voids.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a photomicrograph of a cross-section of an acoustical panel of a standard formulation;

2

FIG. 2 is a photomicrograph of a cross-section of an acoustical tile having a modified formulation including 5% chop strand fiberglass fibers;

FIG. 3 is a photomicrograph of a cross-section of an acoustical tile having a modified formulation including 10% chop strand fiberglass fibers; and

FIG. 4 is photomicrograph of a cross-section of an acoustical tile having a modified formulation including 20% chop strand fiberglass fibers.

DESCRIPTION OF THE PREFERRED
EMBODIMENT

An acoustical tile or panel basemat according to the invention is produced by thoroughly mixing its constituents in a dilute water slurry. The slurry, in a generally conventional process, is distributed over a travelling screen or support wire to form a basemat layer. The layer is drained of water through the screen and by application of a suction vacuum. The mat is then lightly pressed between an overlying roll or travelling screen and the transport screen. Thereafter, the pressed basemat is dried in an oven and cut to a finished rectangular size. The face of the basemat may be finished with conventional techniques such as grinding, laminating and/or painting.

The invention departs from traditional mineral fiber based basemat formulations by substituting chopped strand fiberglass for a fraction of a standard amount of mineral wool fiber. The chopped strand fiberglass can be, for example, of the commercially available wet use chopped strand (WUCS) material.

FIG. 1 shows a cross-section of a part of an acoustical ceiling tile made with a generally conventional mineral fiber based formulation. The table below reflects the constituents of this conventional formula.

TABLE 1

PRIOR ART GENERAL BASEMAT FORMULATION		
		Function
Density	14 to 16.5 lbs. per cubic foot	
Mat Thickness	0.730 inch to 0.780 inch	
Slag Wool Fiber	>75%	Strengthening/Body fiber
Acrylate Polymer	<5%	binder
Starch	<2%	binder
Vinyl Acetate Polymer	<2%	binder
Or Ethylene Acetate Polymer	<2%	binder
Zinc Pyrithione	<2%	antimicrobial agent
Crystalline Silica	<5%	inherent in coating

FIGS. 2-4 show portions of cross sections of acoustical tile basemat with modified formulations. FIG. 2 is illustrative of a formulation containing 5% by weight of chop strand glass fiber, FIG. 3 shows a basemat with a 10% chop strand glass fiber composition, and FIG. 4 shows a cross-section of a basemat with a 20% chop strand glass fiber composition. In the compositions shown in FIGS. 2-4, the chop strand glass fibers are nominally 1/4 inch in length and 16.5 microns in diameter.

Below is a formulation for a mineral fiber based basemat for an acoustical tile embodying the present invention.

TABLE 2

EXEMPLARY BASEMAT FORMULATION OF INVENTION		
		Function
Density	7.5 to 10.5 lbs. per cubic foot	
Mat Thickness	1 inch to 1.5 inch	
Slag Wool Fiber	>50%	Strengthening/Body fiber
Chopped Strand	<25% substitution for Slag Wool	Strengthening/Body/Loft fiber
Acrylate Polymer	<5%	binder
Starch	<2%	binder
Vinyl Acetate Polymer	<2%	binder
Or Ethylene Acetate Polymer	<2%	binder
Zinc Pyrithione	<2%	antimicrobial agent
Crystalline Silica	<5%	inherent in coating

The percentages shown in Tables 1 and 2 are weight percent.

A comparison of FIG. 1 with the remaining FIGS. 2-4 shows the presence of voids in the body of the basemat with the number of voids increasing with the chopped strand glass fiber percent content. The diameter of the fiberglass fibers is substantially greater than the diameter of the mineral fibers. The bulk density, in lbs/cubic foot of a basemat decreases proportionately with the number of voids in a specific volume. As bulk density decreases, as would be expected, the porosity of the basemat increases and its sound absorbing capacity, i.e. NRC rating, increases.

The reason that chopped strand fibers produce, or are at least associated with the occurrence of voids throughout the body of a mineral fiber based basemat is not completely understood. The individual glass fibers appear at least in some instances to hold surrounding mineral fibers out of the space of a void like the bows of an umbrella to draw an analogy. Regardless of how the chopped strand glass fibers create

and/or maintain the voids, the chopped strand glass fibers, in proportion to their mass, decrease bulk density and increase NRC.

During formation of a glass fiber chopped strand containing basemat, increased loft of the wet basemat is experienced before and after it is lightly pressed by a top screen belt or roller before it is carried to a drying oven. The chopped strand fiber preferably can be between nominally 1/4 and 1/2 inch in length and preferably have a diameter between about 13.5 microns to 16.5 microns. The finished panels made in accordance with the invention can have a density of between 7 1/2 to 10 1/2 lbs. per cubic foot and a mat thickness of, for example, 1 inch to 1 1/2 inches.

A basemat typically will have its face or room side covered by a non-woven fiberglass scrim, known in the art, that is adhesively attached and when painted or coated remains air permeable.

It should be evident that this disclosure is by way of example and that various changes may be made by adding, modifying or eliminating details without departing from the fair scope of the teaching contained in this disclosure. The invention is therefore not limited to particular details of this disclosure except to the extent that the following claims are necessarily so limited.

What is claimed is:

1. A wet laid basemat for an acoustical ceiling tile comprising on a dry weight basis, 50% or more mineral wool fiber, including shot, less than 9% binder, and between 5 and 20% chopped strand glass fiber, and, optionally, minor amounts of other constituents, whereby the chopped strand glass fibers serve to promote and/or maintain voids in the basemat such that the basemat has a density of between about 7 1/2 to about 10 1/2 lbs. per cubic foot and an NRC (Noise Reduction Coefficient) substantially greater than 0.55 when dried.

2. A wet laid basemat as set forth in claim 1, wherein the chop strand fibers are nominally between 1/4 inch and 1/2 inch in length.

3. A wet laid basemat as set forth in claim 2, wherein said chop strand fibers have nominal diameters of between 13.5 microns and 16.5 microns.

4. A web laid basemat as set forth in claim 1, having an NRC of about 0.95.

* * * * *