



US00877776B2

(12) **United States Patent**
Wahl et al.

(10) **Patent No.:** **US 8,777,776 B2**
(45) **Date of Patent:** **Jul. 15, 2014**

(54) **GOLF CLUB HEAD HAVING A COMPOSITE FACE INSERT**

(75) Inventors: **Bret H. Wahl**, Escondido, CA (US);
Peter L. Larsen, San Marcos, CA (US);
Chris Schartiger, San Diego, CA (US);
Xinhui Deng, Carlsbad, CA (US);
Bing-Ling Chao, San Diego, CA (US)

(73) Assignee: **Taylor Made Golf Company, Inc.**,
Carlsbad, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 683 days.

(21) Appl. No.: **12/655,082**

(22) Filed: **Dec. 21, 2009**

(65) **Prior Publication Data**
US 2010/0151960 A1 Jun. 17, 2010

Related U.S. Application Data

(63) Continuation-in-part of application No. 12/589,486, filed on Oct. 22, 2009, now Pat. No. 7,871,340, which is a continuation of application No. 11/895,195, filed on Aug. 21, 2007, now Pat. No. 7,628,712, which is a continuation of application No. 10/442,348, filed on May 21, 2003, now Pat. No. 7,267,620.

(51) **Int. Cl.**
A63B 53/04 (2006.01)

(52) **U.S. Cl.**
USPC **473/342; 473/345; 473/350**

(58) **Field of Classification Search**
USPC **473/324–350**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,133,129 A	3/1915	Govan
3,567,228 A	3/1971	Lynn
3,695,618 A	10/1972	Woolley et al.
3,836,153 A	9/1974	Dance, Jr.
3,937,474 A	2/1976	Jepson et al.
4,398,965 A	8/1983	Campau
4,523,759 A	6/1985	Igarashi

(Continued)

FOREIGN PATENT DOCUMENTS

GB	1 201 648	8/1970
GB	2 338 903	1/2000

(Continued)

OTHER PUBLICATIONS

Taylor Made '94/'95 Products—Mid Tour; Mid Tour GF.

(Continued)


Primary Examiner — Alvin Hunter

(74) *Attorney, Agent, or Firm* — Klarquist Sparkman, LLP

(57) **ABSTRACT**

A golf club head having a composite face insert attached to a metallic body is provided. The club head preferably has a volume of at least 200 cc and provides superior durability and club performance. The face insert includes prepreg plies having a fiber areal weight (FAW) of less than 100 g/m². The face insert preferably has a thickness less than 4 mm and a mass at least 10 grams less than an insert of equivalent volume formed of the metallic material of the body of the club head. A metallic cap with a peripheral rim is also provided to protect the ends of the composite material of the face insert. Related methods of manufacturing and alternative materials are disclosed. The resin content of the prepreg plies can be controlled through management of the timing and environment in which the resultant prepreg plies are cured and soaked.

18 Claims, 13 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

4,539,253 A 9/1985 Hirschbuehler et al.
 4,545,580 A 10/1985 Tomita et al.
 4,618,149 A 10/1986 Maxel
 4,740,345 A 4/1988 Nagasaki et al.
 4,792,139 A 12/1988 Nagasaki et al.
 4,793,616 A 12/1988 Fernandez
 4,798,383 A * 1/1989 Nagasaki et al. 473/348
 4,804,188 A 2/1989 McKee et al.
 4,809,978 A 3/1989 Yamaguchi et al.
 4,848,747 A 7/1989 Fujimura et al.
 4,884,812 A * 12/1989 Nagasaki et al. 473/342
 4,928,972 A 5/1990 Nakanishi et al.
 4,964,640 A 10/1990 Nakanishi et al.
 4,995,609 A 2/1991 Parente et al.
 5,007,643 A 4/1991 Okumoto et al.
 5,016,882 A 5/1991 Fujimura et al.
 5,057,353 A * 10/1991 Maranci et al. 428/147
 5,078,397 A * 1/1992 Aizawa 473/342
 5,104,123 A 4/1992 Okitsu et al.
 5,106,094 A 4/1992 Desbiolles et al.
 5,135,227 A 8/1992 Okumoto et al.
 5,176,384 A * 1/1993 Sata et al. 473/329
 5,261,664 A 11/1993 Anderson
 5,271,621 A * 12/1993 Lo 473/345
 5,277,423 A 1/1994 Artus
 5,310,185 A * 5/1994 Viollaz et al. 473/330
 5,312,106 A 5/1994 Cook
 5,344,140 A 9/1994 Anderson
 5,346,216 A 9/1994 Aizawa
 5,348,302 A 9/1994 Sasamoto et al.
 5,377,986 A * 1/1995 Viollaz et al. 473/330
 5,417,419 A 5/1995 Anderson et al.
 5,425,538 A * 6/1995 Vincent et al. 473/342
 5,433,440 A 7/1995 Lin
 5,447,311 A * 9/1995 Viollaz et al. 473/342
 5,465,969 A 11/1995 Cadorniga
 5,472,201 A * 12/1995 Aizawa et al. 473/329
 5,480,153 A 1/1996 Igarashi
 5,494,281 A 2/1996 Chen
 5,499,819 A 3/1996 Nagamoto
 5,505,453 A 4/1996 Mack
 5,518,242 A 5/1996 Mahaffey et al.
 5,529,543 A 6/1996 Beaumont, Sr.
 5,649,873 A 7/1997 Fuller
 5,672,120 A 9/1997 Ramirez et al.
 5,697,855 A 12/1997 Aizawa
 5,720,673 A 2/1998 Anderson
 5,743,813 A 4/1998 Chen et al.
 5,766,092 A 6/1998 Mimeur et al.
 5,774,970 A 7/1998 Huang
 5,827,131 A 10/1998 Mahaffey et al.
 5,830,084 A 11/1998 Kosmatka
 5,906,550 A 5/1999 Kingston
 5,967,903 A 10/1999 Cheng
 5,985,197 A 11/1999 Nelson et al.
 5,993,329 A 11/1999 Shieh
 6,050,904 A 4/2000 Kuo
 6,071,200 A 6/2000 Song
 6,162,133 A 12/2000 Peterson
 6,165,081 A 12/2000 Chou
 6,193,614 B1 2/2001 Sasamoto et al.
 6,248,024 B1 6/2001 Nelson et al.
 6,248,025 B1 6/2001 Murphy et al.
 6,299,547 B1 10/2001 Kosmatka
 6,306,048 B1 10/2001 McCabe et al.
 6,338,683 B1 1/2002 Kosmatka
 6,354,962 B1 * 3/2002 Galloway et al. 473/342
 6,364,789 B1 * 4/2002 Kosmatka 473/329
 6,368,234 B1 * 4/2002 Galloway 473/349
 6,390,932 B1 5/2002 Kosmatka et al.
 6,406,378 B1 6/2002 Murphy et al.
 6,406,381 B2 6/2002 Murphy et al.
 6,435,980 B1 8/2002 Reyes et al.
 6,440,008 B2 8/2002 Murphy et al.
 6,440,011 B1 8/2002 Hocknell et al.

6,582,323 B2 6/2003 Soracco et al.
 6,607,451 B2 8/2003 Kosmatka et al.
 6,648,774 B1 11/2003 Lee
 6,669,576 B1 12/2003 Rice
 6,669,577 B1 12/2003 Hocknell et al.
 6,743,117 B2 6/2004 Gilbert
 6,835,144 B2 12/2004 Best
 6,918,840 B2 7/2005 Stites et al.
 6,921,343 B2 7/2005 Solheim
 6,921,344 B2 7/2005 Gilbert et al.
 6,923,732 B2 8/2005 Stites et al.
 6,991,559 B2 1/2006 Yabu
 7,004,852 B2 2/2006 Billings
 7,022,029 B2 4/2006 Caldwell
 7,140,974 B2 11/2006 Chao et al.
 7,147,571 B2 12/2006 Best et al.
 7,189,165 B2 3/2007 Yamamoto
 7,207,899 B2 4/2007 Imamoto
 7,232,377 B2 6/2007 Gilbert et al.
 7,261,930 B2 * 8/2007 Ellis 428/114
 7,267,620 B2 * 9/2007 Chao et al. 473/342
 7,300,361 B2 11/2007 Stites et al.
 7,303,486 B2 12/2007 Imamoto
 7,316,623 B2 1/2008 Imamoto
 7,357,730 B2 4/2008 Shieh
 7,476,162 B2 1/2009 Stites et al.
 7,481,719 B2 1/2009 Imamoto
 7,628,712 B2 * 12/2009 Chao et al. 473/342
 7,850,546 B2 * 12/2010 Chao et al. 473/342
 7,862,452 B2 * 1/2011 Chao et al. 473/342
 7,874,936 B2 * 1/2011 Chao 473/342
 7,874,937 B2 * 1/2011 Chao 473/342
 7,874,938 B2 * 1/2011 Chao 473/342
 8,163,119 B2 * 4/2012 Chao 156/245
 2001/0055995 A1 12/2001 Cackett et al.
 2002/0065146 A1 5/2002 Kusumoto
 2002/0169034 A1 11/2002 Hocknell et al.
 2003/0036442 A1 2/2003 Chao et al.
 2003/0139227 A1 7/2003 Sugimoto
 2005/0026718 A1 2/2005 Chen
 2005/0075191 A1 4/2005 Bennett
 2007/0049417 A1 3/2007 Shear
 2007/0129162 A1 6/2007 Pan et al.
 2007/0129166 A1 6/2007 Shimazaki et al.
 2007/0155533 A1 7/2007 Solheim et al.
 2007/0293349 A1 12/2007 Chao et al.
 2008/0004134 A1 1/2008 Roach et al.
 2008/0032813 A1 2/2008 Hagood et al.
 2008/0032815 A1 2/2008 Yamamoto
 2008/0058117 A1 3/2008 Roach
 2009/0005191 A1 * 1/2009 Lin 473/331

FOREIGN PATENT DOCUMENTS

JP 60-15145 1/1985
 JP 01-171583 A 7/1989
 JP 4109973 4/1992
 JP 05-007261 2/1993
 JP U-H05-068564 9/1993
 JP 6-23071 2/1994
 JP 6079023 3/1994
 JP 6503490 4/1994
 JP 06-165842 6/1994
 JP 6-205858 7/1994
 JP 07-001958 1/1995
 JP 08257177 A * 10/1996
 JP 9117537 5/1997
 JP 09-176347 7/1997
 JP 09-299519 11/1997
 JP 10-155943 6/1998
 JP 11-137734 5/1999
 JP 11-347155 12/1999
 JP 2001-293112 10/2001
 JP 2001316971 11/2001
 JP 2002315854 10/2002
 JP 2002-331051 11/2002

(56)

References Cited

FOREIGN PATENT DOCUMENTS

JP	2003-024483	1/2003
JP	2003-144590	5/2003
JP	2003138041	5/2003
JP	T-2003-518993	6/2003
JP	2005-218510	8/2005
JP	2006-167033	6/2006
WO	WO2006/017605	2/2006

OTHER PUBLICATIONS

English Translation of the Appeal Board's Questioning, Japanese Application No. 2004-150575, Appeal No. 2008-15208, 4pp. (Nov. 20, 1009).
Japanese Office action (English translation), Japanese App. No. 2005-123040, filed Apr. 21, 2005, 3pp. (Aug. 3, 2010).

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8






FIG. 9






Fig. 11




Fig. 12




Fig. 13A




Fig. 13B




Fig. 14A




Fig. 14B




Fig. 15A




Fig. 15B




Fig. 16




Fig. 17




Fig. 18




Fig. 19

GOLF CLUB HEAD HAVING A COMPOSITE FACE INSERT

CROSS REFERENCE TO RELATED APPLICATION

This application is a continuation-in-part of U.S. patent application Ser. No. 12/589,486, filed Oct. 22, 2009 now U.S. Pat. No. 7,871,340, which is a continuation of U.S. patent application Ser. No. 11/895,195, filed Aug. 21, 2007 (now U.S. Pat. No. 7,628,712), which is a continuation of U.S. patent application Ser. No. 10/442,348, filed May 21, 2003 (now U.S. Pat. No. 7,267,620), which are hereby incorporated herein by reference.

BACKGROUND

The present invention relates generally to golf club heads and, more particularly, to a wood-type golf club head having a composite face insert.

Composite materials have long been recognized for combining many beneficial attributes of various types and are commonly used in golf club heads. Composite materials typically are less dense than other materials used in golf clubs. Thus, the use of composite materials allows for more leeway in how weight is distributed about the club. It is often desirable to locate club weight away from the striking face. Thus, attempts have been made to incorporate composite materials in the club face.

Although such attempts have been generally effective for weight reduction purposes, a number of shortfalls remain, such as durability, impact resistance and overall club performance. For example, prior composite club faces have often suffered from delamination, or peeling apart, of composite layers, greatly reducing the useable life of the club. Delamination is particularly a problem at interface regions between the composite material and other materials of the club head. Such problems have arisen even at relatively low impact levels, hit counts and in benign playing conditions. Attempts to resolve such problems often fail to provide satisfactory club performance, measured by factors such as coefficient of restitution (COR), particularly for wood-type club heads having a volume of at least 300 cc. It should, therefore, be appreciated that there exists a need for a wood-type golf club head having composite material at the club face that is durable, can endure high level impacts and yet provide superior club performance. The present invention fulfills this need and others.

It should, therefore, be appreciated that there exists a need for a wood-type golf club head and an iron-type golf club head having composite material at the club face that is durable, can endure high level impacts and yet provide superior club performance. The present invention fulfills this need and others.

SUMMARY

The invention provides a golf club head having a lightweight face insert attached to a body that is at least partly formed of a metallic material, providing superior durability and club performance. To that end, the face insert comprises prepreg plies having a fiber areal weight (FAW) of less than 100 g/m². The body preferably forms a volume of at least 200 cc. The face insert preferably has a thickness less than 4 mm and has a mass at least 10 grams less than an insert of equivalent volume formed of the metallic material of the body of the

club head. The coefficient of restitution for the club head, measured in accordance to the United States Golf Association Rule 4-1a, is at least 0.79.

In a preferred embodiment of the invention, the face insert further includes a cap with a peripheral rim that is attached to a front surface of the composite region. Also preferably, the thickness of the composite region is about 4.5 mm or less and the metallic cap thickness is about 0.5 mm or less; more preferably the thickness of the composite region is about 3.5 mm or less and the metallic cap thickness is about 0.3 mm or less. The cap preferably comprises a titanium alloy. The face insert may alternatively comprise a layer of textured film co-cured with the plies of low FAW material, in which the layer of textured film forms a front surface of the face insert instead of the metallic cap. The layer of textured film preferably comprises nylon fabric. Without the metallic cap, the mass of the face insert is at least 15 grams less than an insert of equivalent volume formed of the metallic material of the body of the club head.

A preferred method of the present invention advantageously controls the resin content of the low fiber areal weight (FAW) composite material of the golf club face. The steps comprise:

- stacking and cutting a plurality of prepreg plies having a fiber areal weight (FAW) of less than 100 g/m² to form an uncured face insert having substantially a final desired shape, bulge and roll;
- placing the uncured face insert into a tool with an initial temperature T_1 ;
- curing the uncured face insert for about 5 minutes at a first pressure P_1 then initiating heating the tool to a set temperature T_2 greater than or equal to the initial temperature T_1 and curing another 15 minutes at a second pressure P_2 greater than the first pressure P_1 , thus obtaining the cured face insert;
- continue forming the cured face insert at the set temperature and second pressure P_2 for about 30 minutes; and
- soaking the cured face insert for 5 minutes at a third pressure P_3 less than the second pressure P_2 , such that the desired resin content is achieved.

Alternatively, the tool temperature may be immediately raised to a set temperature T_2 upon placement of the composite material therein, this temperature being held substantially constant over the soaking and curing phases. After an initial soaking time of about 5 minutes, the pressure is raised from a first pressure P_1 to a second pressure P_2 greater than the first pressure P_1 . After an additional time of about 15 minutes, the pressure is reduced to about the same value as the first pressure for about another 20 minutes.

For purposes of summarizing the invention and the advantages achieved over the prior art, certain advantages of the invention have been described above. Of course, it is to be understood that not necessarily all such advantages may be achieved in accordance with any particular embodiment of the invention. Thus, for example, those skilled in the art will recognize that the invention may be embodied or carried out in a manner that achieves or optimizes one advantage or group of advantages as taught herein without necessarily achieving other advantages as may be taught or suggested herein.

In one aspect of the present invention, an iron-type golf club a body having a heel portion, a sole portion, a toe portion, a top-line portion, a front portion, a rear portion, and a striking face is described. A cavity is defined by at least a rear surface of the striking face, an interior rear wall surface, and the sole portion. A composite face insert comprising prepreg plies having a fiber areal weight of less than 200 g/m² is also described. The face insert is attached at the front opening of

the body and enclosing the front opening of the body. The thickness of the prepreg plies is within a range of about 1 mm to about 8 mm.

In another aspect of the present invention, an iron-type golf club body having a heel portion, a sole portion, a toe portion, a top-line portion, a front portion, a rear portion, and a striking face. A cavity is described that is defined by at least a rear surface of the striking face, an interior rear wall surface, and the sole portion. A composite face insert is described including prepreg plies having a fiber areal weight less than 100 g/m². The face insert is attached at the front opening of the body and enclosing the front opening of the body. The thickness of the prepreg plies is within a range of about 1 mm to about 8 mm. The golf club head having a coefficient of restitution of at least 0.79.

All of these embodiments are intended to be within the scope of the invention herein disclosed. These and other embodiments of the present invention will become readily apparent to those skilled in the art from the following detailed description of the preferred embodiments having reference to the attached figures, the invention not being limited to any particular preferred embodiment disclosed.

BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments of the present invention will now be described, by way of example only, with reference to the following drawings in which:

FIG. 1 is an exploded view of a club head in accordance with the invention, depicting a composite face insert and a metallic body.

FIG. 2 is a cross-sectional view of the club head of FIG. 1.

FIG. 3 is an exploded view of the composite region of the face insert of FIG. 1 showing the plies comprising the composite region.

FIG. 4 is a close-up view of area A-A of the club head of FIG. 2, depicting a junction of the composite face insert and the body portion.

FIG. 5 is a graph depicting resin viscosity over time during the soaking and curing phases for a preferred method of forming the composite portion of the face insert of FIG. 1.

FIG. 6 is a graph depicting pressure over time during the soaking and curing phases of forming the composite portion of the face insert, corresponding to FIG. 5.

FIG. 7 is a graph depicting temperature over time during the soaking and curing phases of forming the composite portion of the insert, corresponding to FIG. 5.

FIG. 8 is a graph depicting pressure over time during the soaking and curing phases of an alternative method of forming the composite portion of the insert of FIG. 1.

FIG. 9 is a graph depicting temperature over time during the soaking and curing phases of forming the composite portion of the insert, corresponding to FIG. 8.

FIG. 10A illustrates a front view of an embodiment of a golf club head in an address position.

FIG. 10B illustrates a toe-side view of the golf club head shown in FIG. 10A.

FIG. 11 illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to one embodiment.

FIG. 12 illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to another embodiment.

FIG. 13A illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to another embodiment.

FIG. 13B illustrates a detailed view of a lower leading edge zone.

FIG. 14A illustrates an adhesive interface between a face insert and club head body, according to one embodiment.

FIG. 14B illustrates an adhesive interface between a face insert and club head body, according to another embodiment.

FIG. 15A illustrates an engineering gap between a face insert and a club head body, according to another embodiment.

FIG. 15B illustrates a front view of the golf club head shown in FIG. 15A.

FIG. 16 illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to another embodiment.

FIG. 17 illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to another embodiment.

FIG. 18 illustrates a cross-sectional side view of a golf club head taken through an ideal impact location, according to another embodiment.

FIG. 19 illustrates a front view of a golf club head in an address position, according to another embodiment.

DETAILED DESCRIPTION

With reference to the illustrative drawings, and particularly FIGS. 1 and 2, there is shown a golf club head 10 having a metallic body 12 and a face insert 14 comprising a composite region 16 and a metallic cap 18. The face insert 14 is durable and yet lightweight. As a result, weight can be allocated to other areas of the club head 10, enabling the club head's center of gravity to be desirably located farther from the striking face 40 and to further enhance the club head's moment of inertia. The body 12 includes an annular ledge 32 for supporting the face insert 14. In a preferred embodiment, the body 12 is formed by investment casting a titanium alloy. With the face insert 14 in place, the club head 10 preferably defines a volume of at least 200 cc and more preferably a volume of at least 300 cc. The club head 10 has superior durability and club performance, including a coefficient of restitution (COR) of at least 0.79.

With reference to FIG. 3, the composite region 16 of the face insert 14 is configured to have a relatively consistent distribution of reinforcement fibers across a cross section of its thickness to facilitate efficient distribution of impact forces and overall durability. The composite region 16 includes prepreg plies, each ply having a fiber reinforcement and a resin matrix selected to contribute to the club's durability and overall performance. Tests have demonstrated that composite regions formed of prepreg plies having a relatively low fiber areal weight (FAW) provide superior attributes in several areas, such as, impact resistance, durability and overall club performance. More particularly, FAW values below 100 g/m², or preferably 70 g/m² or more preferably 50 g/m², are considered to be particularly effective. Several prepreg plies having a low FAW can be stacked and still have a relatively uniform distribution of fiber across the thickness of the stacked plies. In contrast, at comparable resin content (R/C) levels, stacked plies of prepreg materials having a higher FAW tend to have more significant resin rich regions, particularly at the interfaces of adjacent plies, than stacked plies of lower FAW materials. It is believed that resin rich regions tend to inhibit the efficacy of the fiber reinforcement, particularly since the force resulting from golf ball impact is generally transverse to the orientation of the fibers of the fiber reinforce-

ment. Preferred methods of manufacturing, which aid in reducing resin rich regions, are discussed in detail further below.

Due to the efficiency of prepreg plies of low FAW, the face insert **14** can be relatively thin, preferably less than about 4.5 mm and more preferably less than about 3.5 mm. Thus, use of the face insert **14** results in weight savings of about 10 g to 15 g over a comparable volume of metal used in the body **12** (e.g., Ti-6Al-4V). As mentioned above, this weight can be allocated to other areas of the club, as desired. Moreover, the club head **10** has demonstrated both superior durability and performance. In a durability test, the club head **10** survived over 3000 impacts of a golf ball shot at a velocity of about 44 m/sec. In a performance test of the club's COR, measured in accordance with the United States Golf Association Rule 4-1a, the club head had a COR of about 0.828.

With continued reference to FIG. 3, each prepreg ply of the composite region **16** preferably has a quasi-isotropic fiber reinforcement, and the plies are stacked in a prescribed order and orientation. For convenience of reference, the orientation of the plies is measured from a horizontal axis of the club head's face plane to a line aligned with the fiber orientation of each ply. A first ply **20** of the composite region **16** is oriented at 0 degrees, followed by ten to twelve groups of plies (**22**, **24**, **26**) each having four plies oriented at 0, +45, 90 and -45 degrees, respectively. Thereafter, a ply **28** oriented at 90 degrees precedes the final or innermost ply **30** oriented at 0 degrees. In this embodiment, the first and final plies are formed of a prepreg material reinforced by glass fibers, such as 1080 glass fibers. The remaining plies are formed of prepreg material reinforced by carbon fiber.

A suitable carbon fiber reinforcement comprises a carbon fiber known as "34-700" fiber, available from Grafil, Inc., of Sacramento, Calif., which has a tensile modulus of 234 Gpa (34 Msi) and tensile strength of 4500 Mpa (650 Ksi). Another suitable fiber, also available from Grafil, Inc., is a carbon fiber known as "TR50S" fiber which has a tensile modulus of 240 Gpa (35 Msi) and tensile strength of 4900 Mpa (710 Ksi). Suitable epoxy resins known as Newport 301 and 350 are available from Newport Adhesives & Composites, Inc., of Irvine, Calif.

In a preferred embodiment, the composite region **16** includes prepreg sheets having a quasi-isotropic fiber reinforcement of 34-700 fiber having an areal weight of about 70 g/m² and impregnated with an epoxy resin (e.g., Newport 301) resulting in a resin content (R/C) of about 40%. For convenience of reference, the primary composition of a prepreg sheet can be specified in abbreviated form by identifying its fiber areal weight, type of fiber, e.g., 70 FAW 34-700. The abbreviated form can further identify the resin system and resin content, e.g., 70 FAW 34-700/301, R/C 40%. In a durability test, several plies of this material were configured in a composite region **16** having a thickness of about 3.7 mm. The resulting composite region **16** survived over 3000 impacts of a golf ball shot at a velocity of about 44 m/sec. In another preferred embodiment, the composite region **16** comprises prepreg plies of 50 FAW TR50S/350. This material was tested in a composite region **16** having a thickness of about 3.7 mm and it too survived a similar durability test.

With reference to FIG. 4, the face insert **14** has sufficient structural strength that excessive reinforcement along the interface of the body **12** and the face insert **14** is not required, which further enhances beneficial weight allocation effects. In this embodiment, the body **12** is formed of a titanium alloy, Ti-6Al-4V; however, other suitable material can be used. The face insert **14** is supported by an annular ledge **32** and is secured preferably with an adhesive. The annular ledge **32**

preferably has a thickness of about 1.5 mm and extends inwardly between about 3 mm to about 6 mm. The annular ledge **32** is sufficiently recessed to allow the face insert **14** to sit generally flush with a transition edge **34** of the body. Although, in this embodiment, the annular ledge **32** extends around the periphery of the front opening, it will be appreciated that other embodiments can utilize a plurality of spaced annular ledges, e.g., a plurality of tabs, to support the face insert **14**.

With continued reference to FIG. 4, the metallic cap **18** of the face insert **14** includes a rim **36** about the periphery of the composite region **16**. In a preferred embodiment, the metallic cap **18** may be attached to a front surface of the face insert **14**, wherein the combined thickness of the prepreg plies of the face insert **14** and the metallic cap **18** are no greater than the depth D of the annular ledge **32** at the front opening of the body **12**. The rim **36** covers a side edge **38** of the composite region **16** to further protect against peeling and delamination of the plies. Preferably, the rim **36** has a height substantially the same as the thickness of the face insert **14**. In an alternative embodiment, the rim **36** may comprise a series of segments instead of a continuous cover over the side edge **38** of the composite region **16**. The metallic cap **18** and rim **36** may be formed, for example, by stamping or other methods known to those skilled in the art. A preferred thickness of the metallic cap **18** is less than about 0.5 mm, and more preferably, it is less than about 0.3 mm. However, in embodiments having a face insert **14** without a metallic cap **18**, weight savings of about 15 g can be realized.

Preferably, the thickness of the composite region **16** is about 4.5 mm or less and the thickness of the metallic cap **18** is about 0.5 mm or less. More preferably the thickness of the composite region **16** is about 3.5 mm or less and the thickness of the metallic cap **18** is about 0.3 mm or less. The metallic cap preferably comprises a titanium alloy.

Composite Material Process

The metallic cap **18** defines a striking face **40** having a plurality of grooves **42**. The metallic cap **18** further aids in resisting wear from repeated impacts with golf balls even when covered with sand. Preferably, a bond gap **44** of about 0.05 mm to 0.2 mm, and more preferably about 0.1 mm, is provided for adhesive attachment of the metallic cap **18** to the composite region **16**. In an alternative embodiment, the bond gap **44** may be no greater than 0.2 mm. The metallic cap **18** is preferably formed of Ti-6Al-4V titanium alloy; however, other titanium alloys or other materials having suitable characteristics can be employed. For example, a non-metallic cap, such as a cap comprising injection-molded plastic, having a density less than 5 g/cc and a hardness value of 80 Shore D may be employed.

As mentioned above, it is beneficial to have a composite region **16** that is relatively free of resin rich regions. To that end, fiber reinforcement sheets are impregnated with a controlled amount of resin to achieve a prescribed resin content. This is realized, in part, through management of the timing and environment in which the fiber sheets are cured and soaked.

The plies can be cut at least twice before achieving the desired dimensions. A preferred approach includes cutting plies to a first size, debulking the plies in two compression steps of about two minutes each. Thereafter, the plies are die cut to the desired shape, and compressed a third time; this time using a panel conformed to the desired bulge and roll. The plies are then stacked to a final thickness and compressed a fourth time with the conformed panel for about three minutes. The weight and thickness are measured preferably prior to the curing step.

The plies can be cut at least twice before achieving the desired dimensions. A preferred approach includes cutting plies to a first size and debulking the plies in two compression steps of about two minutes each. Thereafter, the plies are die cut to the desired shape, and compressed a third time using a panel conformed to the desired bulge and roll. The plies are then stacked to a final thickness and compressed a fourth time with the conformed panel for about three minutes. The weight and thickness of the plies are measured preferably prior to the curing step.

FIGS. 5-7 depict an effective soaking and curing profile for impregnating plies 70 FAW 34/700 fiber sheet with Newport 301 resin. Soaking and curing occurs in a tool having upper and lower plates. The tool is pre-layered with a mold release to facilitate removal of the composite material and is pre-heated to an initial temperature (T_1) of about 200° F. The initial soak period is for about 5 minutes, from t_0 to t_1 . During the soak phase, the temperature and pressure remain relatively constant. The pressure (P_1) is at about 15 psi.

An alternative soaking and curing profile is depicted in FIGS. 8 and 9. In this process, the temperature of the tool is initially about 200° F. (T_1) and upon placement of the composite material into the tool, the temperature is increased to about 270° F. (T_2). The temperature is then kept constant. The initial pressure (P_1) is about 20 psi. The initial soak period is for about 5 minutes, from t_0 (0 sec.) to t'_1 . The pressure is then ramped up to about 200 psi (P_2). The post cure phase lasts about 15 minutes (t'_1 to t'_2) and a final soaking/curing cycle is performed at a pressure (P_1) of 20 psi for 20 minutes (t'_2 to t'_3). Composite Face Roughness Treatment

In order to increase the surface roughness of the composite golf club face and to enhance bonding of adhesives used therewith, a layer of textured film can be placed on the material before curing. An example of the textured film is ordinary nylon fabric. Curing conditions do not degrade the fabric and an imprint of the fabric texture is transferred to the composite surface. Tests have shown that adhesion of urethane and epoxy, such as 3M® DP460, to the treated composite surface was greatly improved and superior to adhesion to a metallic surface, such as cast titanium alloy.

In order to increase the surface roughness of the composite region 16 and to enhance bonding of adhesives used therewith, a layer of textured film can be placed on the composite material before curing. An example of the textured film is ordinary nylon fabric. Curing conditions do not degrade the fabric and an imprint of the fabric texture is transferred to the composite surface. Tests have shown that adhesion of urethane and epoxy, such as 3M® DP460, to a composite surface treated in such a fashion was greatly improved and superior to adhesion to a metallic surface, such as cast titanium alloy.

A face insert 14 having increased surface roughness may comprise a layer of textured film co-cured with the plies of low FAW material, in which the layer of textured film forms a front surface of the face insert 14 instead of the metallic cap 18. The layer of textured film preferably comprises nylon fabric. Without the metallic cap 18, the mass of the face insert 14 is at least 15 grams less than a face insert of equivalent volume formed of the metallic material of the body 12 of the club head 10.

Typically, adhesion of the 3M® DP460 adhesive to a cast metallic surface is greater than to an untreated composite surface. Consequently, when the face structure fails on impact, the adhesive peels off the composite surface but remains bonded to the metallic surface. After treating a composite surface as described above, the situation is reversed and the 3M® DP460 peels off the metallic surface but remains bonded to the composite surface.

The enhanced adhesion properties of this treatment contribute to an improved fatigue life for a composite golf club face. In a test, a club head having an untreated face insert 14 and a COR of about 0.847 endured about 250 test shots before significant degradation or failure occurred. In contrast, a similar club head having a treated face insert 14 and a COR of about 0.842 endured over 2000 shots before significant degradation or failure occurred.

Alternatively, the means for applying the composite texture improvement may be incorporated into the mold surface. By doing so, the textured area can be more precisely controlled. For simple face plate joining to the opening of a cast body, the texture can be formed in surfaces where shear and peel are the dominant modes of failure.

It should be appreciated from the foregoing that the present invention provides a club head 10 having a composite face insert 14 attached to a metallic body 12, forming a volume of at least 200 cc and providing superior durability and club performance. To that end, the face insert 14 comprises prepreg plies having a fiber areal weight (FAW) of less than 100 g/m². The face insert 14 preferably has a thickness less than 5 mm and has a mass at least 10 grams less than a face insert of equivalent volume formed of the metallic material of the body 12 of the club head 10. The coefficient of restitution for the club head 10 is preferably at least 0.79.

Alternatively, the face insert 14 may comprise any non-metallic material having a density less than a metallic material of the body 12 along with a metallic cap 18 covering a front surface of the face insert 14 and having a rim 36. For example, the face insert 14 of the present invention may comprise a composite material, such as a fiber-reinforced plastic or a chopped-fiber compound (e.g., bulk molded compound or sheet molded compound), or an injection-molded polymer either alone or in combination with prepreg plies having low FAW. The thickness of the face insert 14 may be substantially constant or it may comprise a variation of at least two thicknesses, one being measured at a geometric center and another measured near a periphery of the face insert 14. In one embodiment, for example, an injection-molded polymer disk may be embedded in a central region of a plurality of low FAW prepreg plies. The total thickness of the face insert 14 may range between about 1 mm and about 8 mm, and preferably between about 2 mm and about 7 mm, more preferably between about 2.5 mm and about 4 mm, and most preferably between about 3 mm and about 4 mm.

In addition, the body 12 of a club head 10 in the present invention may be formed of a metallic material, a non-metallic material or a combination of materials, such as a steel skirt and sole with a composite crown, for example. Also, one or more weights may be located in or on the body 12, as desired, to achieve final performance characteristics for the club head 10.

FIG. 10A illustrates a hollow iron golf club head 1000 including a heel 1002, toe 1004, sole portion 1008, and top line portion 1006. The striking face 1010 includes scoreline grooves 1012 that are designed for impact with the golf ball. The scorelines described in the embodiments herein can be molded into a composite face insert. In some embodiments, the golf club head 1000 body can be a single unitary cast piece that is adhesively attached to a striking face 1010 that is formed separately. In certain embodiments, the striking face 1010 is a composite insert as will be described in further detail below.

FIGS. 10A and 10B also show a center point 1001 being an ideal striking point in the center of the striking face 1010 and respective orthogonal center of gravity (hereinafter, "CG") axes. A CG x-axis 1005, CG y-axis 1007, and CG z-axis 1003

intersect at the center point **1001**. In addition, a CG z-up axis **1009** is defined as an axis perpendicular to the ground plane **1011** and having an origin at the ground plane **1011**. The ground plane **1011** is assumed to be a perfectly flat plane.

In certain embodiments, a desirable CG-x location is between about 5 mm (heel side) and about -5 mm (toe side) along the CG x-axis **1005**. A desirable CG-y location is between about 5 mm to about 20 mm along the CG y-axis **1007** toward the rear portion of the club head. Additionally, a desirable CG-z location is between about 12 mm to about 25 mm along the CG z-up axis **1009**, as previously described.

FIG. **10B** illustrates an elevated toe view of the golf club head **1000** including a back portion **1028**, a front portion **1030**, a sole portion **1008**, a top line portion **1006**, and a striking face **1010**, as previously described. The front surface of the striking face **1010** is contained within a face plane **1025**.

FIG. **11** illustrates a cross-sectional view according to one exemplary embodiment. The club head **1100** includes a back portion **1106**, a top line portion **1104**, a front portion **1102** and a sole portion **1108**. A composite striking face **1112** is located on the front portion **1102** of the body. In other words, the body includes a front opening that receives the composite striking face **1112**. After adhesively attaching the composite face **1112**, an interior cavity **1114** is formed. The club head **1100** back portion **1106** further includes a rear wall having an upper rear wall **1132** and a lower rear wall **1128**, and a sound and vibration dampening badge **1130**. The back portion **1106** also includes a rear protrusion **1124**, an upper edge **1126**, and a sole thickness **1122**.

FIG. **11** further shows the front opening of the club head body having a ledge **1134** extending around an entire periphery of the front opening of the body. It is understood that the ledge **1134** can be continuous or intermittently located around a periphery of the front opening. In one embodiment, the ledge **1134** is perpendicular to a front opening wall **1136**. In one embodiment, the ledge extends inwardly toward a center region of the face by a ledge distance **1118** of about 1 mm to about 5 mm, or about 3 mm to about 4 mm. Similarly, the front opening wall **1136** extends perpendicularly away from a plane of the striking face by a depth distance **1120** between about 1 mm to about 5 mm, or between 3 mm to about 4 mm.

In addition the striking insert **1112** includes a varying thickness and a thickened peripheral portion having a third thickness dimension **1110**. The composite insert **1112** includes a first thickness **1111** at the thinnest region of the striking insert **1112** and a second thickness **1116** located in a central region of the striking insert **1112**. The second thickness **1116** is the thickest dimension within the central region of the striking insert **1112**. In one embodiment, the second thickness **1116** is greater than the first thickness **1111** and less than the third thickness **1110** of the peripheral portion. The third thickness **1110** located in a peripheral portion of the striking insert **1112** is greater than both the second thickness **1116** and the first thickness **1111**. The peripheral region of the striking insert **1112** having the third thickness **1110** is attached to the ledge **1134**.

In one embodiment, the first thickness **1111** can be between about 1.5 mm and about 2.0 mm, with a preferred thickness of about 2 mm or less. The second thickness **1116** can be between about 2 mm and about 3 mm and the third thickness **1110** is between about 3 mm and about 4.5 mm, or preferably about 3.5 mm to about 4.0 mm.

Alternatively, variable thickness configurations or inverted cone configurations can be implemented in the striking face

1112 as discussed in U.S. Pat. Nos. 6,800,038, 6,824,475, 6,904,663, and 6,997,820, all incorporated herein by reference.

In the examples described herein, a composite face insert can have a striking surface area in a range of about 2,700 mm² to about 5,000 mm². The unsupported surface area (surface area on the rear surface of the striking insert that is not engaged with a supporting surface) of the composite face insert can be within a range of about 300 mm² to about 4,000 mm², or preferably 450 mm² to about 3,500 mm². In some embodiments, the unsupported surface area is at least greater than about 2,000 mm². The unsupported surface area is the portion of the composite insert that is defined by the first thickness **1111** and second thickness **1116** excluding the peripheral portion. The composite face thickness can be within a range of about 1 mm to about 8.0 mm, preferably about 2.5 to about 5 mm. In certain embodiments, the composite face thickness is less than about 4.0 mm. In embodiments having a thickened region, the thickened region surface area can range from about 230 mm² to about 2,000 mm².

FIG. **12** illustrates an alternative embodiment of a golf club head **1200** including a front portion **1202**, a rear portion **1206**, a sole portion **1208** and a top line portion **1204**. The club head **1200** includes a front opening located in the front portion **1202**. The club head **1200** further includes a composite striking insert **1216**, a gap cavity **1218**, a back wall **1214**, and a peripheral front opening wall **1210**. The composite striking insert **1216** includes a first thickness **1222**, a second thickness **1220**, and a third thickness **1224**. The third thickness **1224** corresponds to a thickened end portion **1212** of the striking insert **1216**.

The back wall **1214** includes a front engaging surface **1214a** which provides support for the composite insert **1216** to be adhesively attached. The front engaging surface **1214a** and the peripheral front opening wall **1210** create the front opening to receive the composite striking insert **1216**. The front engaging surface **1214a** is offset from the front surface **1230** of the club head by an offset distance **1226**. The offset distance **1226** can be between about 1 mm and about 5 mm or preferably about 4 mm.

The offset distance **1226** is greater than or equal to the third thickness **1224** of the striking insert **1216** to enable the striking insert **1216** to sit within the front opening. The striking insert **1216** is located within the front opening so that the front striking insert **1216** surface is flush with the front portion surface **1230** of the club head body **1200**. The interior gap cavity **1218** is located between the striking insert **1216** and the front engaging surface **1214a** of the back wall **1214** and can be about 0.1 cc to about 20 cc. In one embodiment, the interior cavity is less than about 10 cc.

The interior cavity is entirely defined and surrounded by the striking insert **1216** and the rear back wall **1214** only. The back wall **1214** is in direct adhesive contact with the striking insert **1216** and supports the striking insert **1216**. In other words, the thickened peripheral region **1212** of the striking insert is in direct contact with an interior surface of the back wall **1214**.

It is critical that the central region of the striking insert **1216** is not capable of making direct contact with the back wall **1214** upon impact with the golf ball to avoid unwanted sound and unwanted performance effects. Therefore, a critical distance **1228** of about 1 mm or more is maintained between the front engaging surface **1214a** and a rear surface **1216a** of the striking insert **1216** at a maximum second thickness **1220** location.

FIG. **13A** illustrates another exemplary embodiment according to another alternative embodiment of a golf club

11

head **1300** including a front portion **1302**, a back portion **1306**, a sole portion **1308**, and a top line portion **1304**. The golf club head also includes a badge **1330**, back wall portion **1332**, an interior back wall surface **1328**, a protruding portion **1324**, an upper edge **1326**, a sole thickness **1320**, a ledge **1322**, a front opening wall **1310**, an interior cavity **1334**, and a striking insert **1312**. The ledge **1322** extends a distance **1316** inwardly and the front opening wall **1310** also extends a distance **1318** as previously described.

The striking insert material, of the embodiments described herein, are made of the processes and materials described above but can also be a composite material as described in U.S. patent application Ser. No. 10/831,496 (now U.S. Pat. No. 7,140,974), Ser. Nos. 11/642,310, 11/825,138, 11/998,436, 11/823,638, 12/004,386, 12,004,387, 11/960,609, 11/960,610, and 12/156,947, which are incorporated herein by reference in their entirety. All of the composite inserts described herein can be made according to the processes and composite materials described within the above listed patents and patent applications. For example, in one embodiment, a composite face insert material having a fiber areal weight of less than 200 g/m² is utilized. In another embodiment, a face insert material has a fiber areal weight less than 100 g/m². In yet other embodiments, the face insert material has a fiber areal weight less than 150 g/m².

For example, water jet cutting can be utilized to cut the composite face inserts from a sheet of composite material as described in the patents and patent applications incorporated by reference. In addition, the face insert can be formed by CNC cutting

Some examples of composites that can be used to form the components include, without limitation, glass fiber reinforced polymers (GFRP), carbon fiber reinforced polymers (CFRP), metal matrix composites (MMC), ceramic matrix composites (CMC), and natural composites (e.g., wood composites). The face insert may also be made of a thermoplastic material, as described herein. In certain embodiments, the composite face inserts described herein are made of a material having a density less than about 1.5 g/cc.

FIG. 13A shows a center cross-sectional view of the striking insert **1312** being a constant thickness **1314** (across the face of the striking insert **1312**) and the constant thickness **1314** being between about 3.0 mm to about 5.0 mm, or about 3.5 mm to about 4.5 mm.

FIG. 13B is a detailed view of a lower portion of the golf club head **1300** shown in FIG. 13A. FIG. 13B shows a non-undercut design. Specifically, a lower leading edge zone **1346** of the club head body is completely filled with material and does not include an undercut or gap within the lower leading edge zone **1346** in a transition region between the striking surface of the club face and the sole portion **1308**.

FIG. 13B shows a club face plane **1336** which contains the striking surface and is co-planar with the striking surface. Furthermore, the ledge **1322** includes a front engaging surface **1344** that is contained within a ledge plane **1338**. The club face plane **1336** and the ledge plane **1338** are substantially parallel with respect to one another. A segment **1342** of the sole portion **1308** is located between the face plane **1336** and the ledge plane **1338**.

The lower leading edge zone **1346** is defined by the front opening wall **1310**, the ledge plane **1338**, the club face plane **1336**, and the sole portion segment **1342**. Within the lower leading edge zone **1346**, an undercut or gap is avoided in order to lower the first leading edge groove centerline axis **1348** with respect to the ground **1301**. The leading edge groove centerline axis **1348** is defined as the intersection of a

12

bisecting plane **1352** and the club face plane **1336** at the centerline axis **1348** shown in FIG. 13B.

A low leading edge groove centerline axis **1348** is beneficial in allowing a golfer to make engaging contact with a ball sooner upon impact. In addition, a lower leading edge groove centerline axis **1348** may have additional benefits when a golfer mis-hits a ball by improving the quality of contact between the ball and the leading groove or lowest groove.

A horizontal plane **1350** contains the leading edge groove centerline axis **1348** and is parallel with the ground surface **1301**. The height distance, *h*, between the horizontal plane **1350** of the leading edge groove axis **1348** and the ground surface **1301** is between about 4 mm and about 10 mm. In certain embodiments, the height distance, *h*, is between about 4 mm and about 8 mm or between about 4 mm and about 6 mm.

FIG. 14A illustrates a magnified view **1400** of the junction between a composite face insert **1404** and a ledge **1418**, according to one exemplary embodiment. The composite face insert **1404** includes an end wall **1410** and a rear surface wall **1412**. The composite face insert **1404** is attached to a front opening wall **1408** and front ledge surface **1406** by an adhesive **1414**. The adhesive **1414** is applied over a majority of the interface between the composite face insert **1404** and the front opening wall **1408** and front ledge surface **1406**.

The front ledge surface **1406** intersects with the front opening wall **1408** at a rounded corner location **1416**. The corner **1416** includes a radius of between about 0.1 mm and about 0.5 mm. In certain embodiments, the radius is at least about 0.30 mm or greater. A larger corner **1416** radius will avoid high stress concentrations that may result in material failure of the ledge **1418** after repeated use.

The rear bond gap distance, *x*, is located between the front ledge surface **1406** and the rear surface wall **1412**. The rear bond gap distance, *x*, is measured along an axis that is perpendicular to the face plane toward a rear portion of the club head.

The side bond gap distance **1402** between the end wall **1410** and the front opening wall **1408** is between 0.1 mm and 0.5 mm, or about 0.3 mm or less. In one embodiment, the side bond gap distance **1402** and the rear bond gap distance, *x*, are filled with an adhesive epoxy to attach the composite insert **1404**.

In certain embodiments, the rear bond gap distance, *x*, is equal to or greater than the side bond gap distance **1402**. In some embodiments, the rear bond gap distance, *x*, is in accordance with the following inequality:

$$x \geq 0.2 \text{ mm} \quad \text{Eq. 1}$$

In the above inequality, the side bond gap distance **1402** is set at a distance of about 0.2 mm. If the rear bond gap distance, *x*, follows the inequality of Equation 1 described above, the composite face insert **1404** will be securely attached within the front opening. Without maintaining a rear bond gap distance, *x*, larger than the side bond gap distance **1402**, the composite face insert **1404** may become loose after repeated impacts and bending.

FIG. 14A also shows a metallic cap **1420** which can be implemented in any of the embodiments described herein. The metallic cap **1420** can be made of a material having a density less than 9 g/cc or less than 5 g/cc such as a titanium alloy, CP titanium, or a nickel based alloy. In addition, the metallic cap **1420** can be a Ni—Cr or Co—Ni alloy with a chrome plated layer formed by electro-plating or electro-forming.

FIG. 14B further shows another embodiment similar to FIG. 14A except the metallic cap **1420** is replaced by a

13

polymer or polyurethane front layer **1421** having grooves incorporated thereon. The polymer or polyurethane material can be of the type described in U.S. patent application Ser. No. 11/960,609, already incorporated by reference in its entirety. Both the metallic cap **1420** and polymer or polyurethane layer **1421** cover the entire front surface of the face insert **1404**.

FIG. **15A** illustrates an alternative embodiment **1500** including a composite face insert **1504**, a ledge **1518**, an end wall **1510**, a rear surface wall **1512**, a front opening wall **1508**, front ledge surface **1506**, an adhesive **1514** and a corner **1516**, as previously described. The face insert **1504** can include a metallic cap or polyurethane cover as previously described.

However, the embodiment shown in FIG. **15A** includes an additional step gap **1522** in addition to a side bond gap distance **1502** or bond gap. The side bond gap distance **1502** and the step gap **1522** (measured along an axis parallel to the face plane) create a total engineering gap **1520**. The step gap **1522** is created by a step region **1524**. The step region **1524** and step gap **1522** are present about the entire circumference of the front opening wall **1508**.

As shown, the side bond gap **1502** and step gap **1522** are filled with the adhesive **1514**. The adhesive **1514** in the front portion parallel with the face plane to avoid unwanted bumps or sharp edges on the striking face.

In one embodiment, the total engineering gap **1520** is about 0.5 mm and the side bond gap distance **1502** is about 0.2 mm. As a result, the step gap **1522** is about 0.3 mm. The total engineering gap **1520** can be between about 0.2 mm and about 1 mm or preferably between about 0.2 mm and about 0.8 mm.

The engineering gap **1520** enables the composite face insert **1504** to be attached without maintaining a perfect side bond gap distance **1502** about the entire circumference of the face insert **1504**. For example, the embodiment of FIGS. **14A** and **14B**, without a step gap and engineering gap would require the exact placement of the composite face insert centered within the front opening to achieve a consistent side bond gap distance. An inconsistent side bond gap distance, without an engineering gap, would be clearly seen by the user and would have a negative impact on aesthetic appeal and performance parameters. In other words, the composite face insert without an engineering gap may look off-center to the golfer and negatively impact the golfer's performance.

FIG. **15B** is a front view of a composite face insert with an engineering gap **1520**. The side bond gap distance **1502** and step gap **1522** are also shown. Within the face plane, the engineering gap **1520**, the side bond gap distance **1502**, and the step gap **1522** are measured along an axis that is perpendicular to the end wall **1510** at any given point along the outer peripheral edge of the composite face insert **1504** (within the face plane). The front opening wall **1508** is shown in dashed lines from a front perspective.

The above described engineering gap distance, side bond gap distance and step gap distance can be applied to any of the embodiments described herein. It is understood that the gaps shown in FIG. **15B** are exaggerated for clarity.

FIGS. **16-18** illustrate similar embodiments to FIGS. **11-13B**, having similar features except the club heads are filled with a filler material.

FIG. **16** illustrates a cross sectional view of an alternative embodiment of a golf club head **1600**. The cross section is taken through an ideal striking point in the center of the striking face as previously described.

The club head **1600** includes a front portion **1602**, back portion **1606**, a top line portion **1604**, and a sole portion **1608**.

14

The club head **1600** further includes an upper back wall **1632**, a lower back wall **1628**, a badge **1630**, a sole thickness **1622**, a rear protrusion **1624**, and filler material **1614**. The badge **1630** is positioned above an upper edge **1626** and covers an aperture **1638** used for introducing the plug **1640** and filler material **1614** into the interior cavity of the club head **1600**. The filler material **1614** and plug **1640** can be of the same configuration, material, and keying design as described in U.S. patent application Ser. No. 12/462,198, incorporated by reference herein, in its entirety.

FIG. **16** further shows a front opening wall **1636**, a ledge distance **1618**, a depth distance **1620**, a first thickness **1611**, a second thickness **1616**, a third thickness **1610**, a ledge **1634**, and a composite face insert **1612**, previously described.

In one embodiment, the filler material can be an expandable foam such as Expancel® 920 DU 40 which is an acrylic copolymer encapsulating a blowing agent, such as isopentane. A copolymer is greater than about 75 weight percent of the composition and the blowing agent is about 15-20 weight percent. The unexpanded particle size of the filler material can be between about 2 μm and about 90 μm depending on the context.

In one embodiment, the density of the filler material is between about 0.16 g/cc and about 0.19 g/cc. In certain embodiments, the density of the filler material is in the range of about 0.03 g/cc to about 0.2 g/cc, or about 0.04-0.10 g/cc. The density of the filler material impacts the COR, durability, strength, and filling capacity. In general, a lower density material will have less of an impact on the COR of a club head. The filler material can have a hardness range of about 15-85 Shore OO hardness or about 80 Shore OO hardness or less.

In one embodiment, the filler material is subject to heat for expansion of about 150° C. \pm 10° C. for about 30 minutes. In some embodiments, the expansion of the filler material can begin at about 125° C. to about 140° C. A maximum expansion temperature range can be between about 160° C. to about 190° C. The temperature at which the expansion of the filler material begins is critical in preventing unwanted expansion after the club head is assembled. For example, a filler material that begins expanding at about 120° C. will not cause unwanted expansion when the club is placed in the trunk of a car (where temperatures can reach up to about 83° C.). Thus, a filler material that has a beginning expansion temperature of greater than about 80° C. is preferred.

Some other examples of materials that can be used as a filler material or plug material include, without limitation: viscoelastic elastomers; vinyl copolymers with or without inorganic fillers; polyvinyl acetate with or without mineral fillers such as barium sulfate; acrylics; polyesters; polyurethanes; polyethers; polyamides; polybutadienes; polystyrenes; polyisoprenes; polyethylenes; polyolefins; styrene/isoprene block copolymers; metallized polyesters; metallized acrylics; epoxies; epoxy and graphite composites; natural and synthetic rubbers; piezoelectric ceramics; thermoset and thermoplastic rubbers; foamed polymers; ionomers; low-density fiber glass; bitumen; silicone; and mixtures thereof. The metallized polyesters and acrylics can comprise aluminum as the metal. Commercially available materials include resilient polymeric materials such as Scotchdamp™ from 3M, Sorbothane® from Sorbothane, Inc., DYAD® and GP® from Soundcoat Company Inc., Dynamat® from Dynamat Control of North America, Inc., NoViFlex™ Sylomer® from Pole Star Maritime Group, LLC, Isoplast® from The Dow Chemical Company, and Legetolex™ from Piqua Technologies, Inc. In one embodiment the filler material may have a modulus of elasticity ranging from about 0.001 GPa to about 25 GPa, and

a durometer ranging from about 5 to about 95 on a Shore D scale. In other examples, gels or liquids can be used, and softer materials which are better characterized on a Shore A or other scale can be used. The Shore D hardness on a polymer is measured in accordance with the ASTM (American Society for Testing and Materials) test D2240.

In certain embodiments, the interior cavity of the club head **1600** can include the plug **1640** for absorbing vibration. It is understood, that an embodiment without the plug **1640** is within the scope of the present description.

After the plug **1640** is frictionally engaged in a position, the filler material **1614** can be inserted into the cavity. In certain embodiments, the plug **1640** is a polymeric material.

In one embodiment, the plug **1640** material is a urethane or silicone material having a density of about 0.95 g/cc to about 1.75 g/cc, or about 1 g/cc. The plug **1640** can have a hardness of about 10 to about 70 shore A hardness. In certain embodiments, a shore A hardness of about 40 or less is preferred.

The filler material **1614** can be an expanding foam material that is expanded by a certain amount of heat as previously described. The filler material **1614** expands and fills a relatively large volume, greater than the volume occupied by the plug **1640**.

In some embodiments, the volume of the cavity is between about 1 cc and about 200 cc, or preferably between about 10 cc and about 20 cc. For the purposes of measuring the cavity volume herein, the aperture **1638** is assumed to be removed from the back wall **1632** and an imaginary continuous back wall or substantially planar back wall is utilized to calculate the cavity volume.

In some embodiments, the filler material **1614** occupies about 50% to about 99% of the total club head cavity volume while the plug **1640** occupies between about 0% to about 20% of the total cavity volume. In specific embodiments, the plug **1640** occupies between about 0.1 cc and 1 cc with the remainder of the cavity volume being filled by the filler material **1614**. It is understood that any of the embodiments described herein can be provided without a plug and filler material.

In order to achieve a desirable CG location, the filler material **1614** and plug **1640** must be lightweight. In certain embodiments, the total mass of the filler material **1614** and plug **1640** is less than about 5 g or between about 2 g and about 4 g. In one embodiment, the total weight of the filler material **1614** and the plug **1640** is 10 g or less or about 3 g or less. In certain embodiments, the total weight of the filler material **714** and plug **1640** is less than 2% of the total weight of the club head **1600** (excluding any badges, filler material/plug, and ferrule ring). In other embodiments, the total weight of the filler material **714** and plug **1640** is less than about 10% of the total weight of the club head **1600**.

In some embodiments, the total weight of the filler material **1614** and plug **1640** is between about 1% and about 5% of the total weight of the club head (excluding the badges, filler material/plug, and ferrule ring). Thus, a desirable CG location is still attainable while improving the sound and feel of the golf club head. In certain embodiments, the plug **1640** can weigh about 0.5 g to about 1 g and the filler material **1614** can weigh about 5 grams or less. In some embodiments, the plug **1640** weighs about 0.7 g or less. In other embodiments, the plug **1640** can be equal to or heavier than the total filler material weight.

In yet other embodiments, the filler material **1614** and the plug **1640** have a combined weight of less than 20% of the total club head weight (excluding badges, filler material/plug, and ferrule ring). In one embodiment, the combined weight of the filler material **1614** and plug **1640** is less than 5%.

FIG. **17** illustrates an alternative embodiment of a golf club head **1700** including a front portion **1702**, a rear portion **1706**, a sole portion **1708** and a top line portion **1704**. The club head **1700** includes a front opening located in the front portion **1702**. The club head **1700** further includes a composite striking insert **1716**, filler material **1718**, a back wall **1714**, and a peripheral front opening wall **1710**. It is possible to include a plug, badge, and aperture as described above. The striking insert **1716** includes a first thickness **1722**, a second thickness **1720**, and a third thickness **1724**. A critical distance **1728** having dimensions described above is also present. The peripheral region **1712** is in contact with the front surface of the rear wall **1714**. The front surface of the rear wall **1714** is located at an offset distance **1726**, previously described.

The filler material **1718** can be of the type already described above or can be a thermoplastic elastomer having a density of about 0.9 g/cc to about 1.20 g/cc.

FIG. **18** shows a top line portion **1804**, back portion **1806**, front portion **1802**, sole portion **1808**, back wall portion **1832**, badge **1830**, interior back wall surface **1828**, upper edge **1826**, protruding portion **1824**, ledge **1822**, sole thickness **1820**, offset distance **1818**, ledge distance **1816**, constant face thickness **1814**, front opening wall **1810**, and filler material **1834**, as previously described.

In certain embodiments, the badges and composite face inserts, described herein, can be adhesively attached with epoxy or any known adhesive. For example, an epoxy such as 3M® DP460 can be used. It is possible for the badge **1830** to be mechanically attached to the back portion **1806** of the club head **1800**.

After the hollow iron **1800** is filled with the filler material **1834**, the badge **1830** is adhesively or mechanically attached to the back wall **1832** to cover or occlude the aperture to prevent filler material from leaving the cavity and also to achieve a desired aesthetic and while creating further dampening.

In some embodiments, the COR is greater than about 0.790. Preferably, the COR is at least 0.80 as measured according to the USGA Rules of Golf based on a 160 ft./s ball speed test and the USGA calibration plate. The COR can even be as high as 0.83.

In one embodiment, the body portion is made from 17-4 steel. However another material such as carbon steel (e.g., 1020, 1030, 8620, or 1040 carbon steel), chrome-molybdenum steel (e.g., 4140 Cr—Mo steel), Ni—Cr—Mo steel (e.g., 8620 Ni—Cr—Mo steel), or austenitic stainless steel (e.g., 304, N50, or N60 stainless steel, 410 stainless steel) can be used.

The components of the described components disclosed in the present specification can be formed from any of various suitable metals or metal alloys.

In addition to those noted above, some examples of metals and metal alloys that can be used to form the components of the parts described include, without limitation: titanium alloys (e.g., 3-2.5, 6-4, SP700, 15-3-3-3, 10-2-3, or other alpha/near alpha, alpha-beta, and beta/near beta titanium alloys), aluminum/aluminum alloys (e.g., 3000 series alloys, 5000 series alloys, 6000 series alloys, such as 6061-T6, and 7000 series alloys, such as 7075), magnesium alloys, copper alloys, and nickel alloys.

The body portion can include various features such as weighting elements, cartridges, and/or inserts or applied bodies as used for CG placement, vibration control or damping, or acoustic control or damping. For example, U.S. Pat. No. 6,811,496, incorporated herein by reference in its entirety, discloses the attachment of mass altering pins or cartridge weighting elements.

FIG. 19 shows a golf club head 1900 having a heel 1902, toe portion 1904, sole portion 1908, top line portion 1906, striking face 1910, scoreline grooves 1912, a center point 1901, a CG x-axis 1905, a CG z-axis 1903, a CG z-up axis, a ground plane 1911 as previously described in FIG. 10A.

However, the composite face insert 1916 does not extend across the striking surface to a toe portion 1904 edge 1920 as shown in FIG. 19. The composite face insert 1916 occupies about 50% to about 90% of the front striking surface plane. Subsequently, about 50% to about 10% of the front striking surface plane is comprised of the metallic material similar to the golf club head body.

Including a smaller percentage of composite face insert 1916 striking surface area can result in a significant reduction in manufacturing cost and composite material savings.

At least one advantage of the present invention is that a lightweight composite face insert will provide an improved CG club head location.

In addition, a certain engineering gap can be utilized to reduce the manufacturing time and expense associated with perfectly centering a composite face insert in a front opening of the golf club head.

At least another advantage of the embodiments described above, is that a rear back wall and badge can act to create an enclosed cavity behind the composite face so that the ledge and adhesive material used to bond the face insert to the club body is not visible to the user.

At least another advantage of the embodiments described is that a lightweight filler material arrangement is created allowing the center of gravity of the hollow iron construction to remain low while improving the sound and feel of the club during use.

The embodiments described herein conform with the USGA (United States Golf Association) Rules of Golf and Appendix II, 5c related to the Determination of Groove Conformance (issued in August 2008). For example, clubs having a loft of 25 degrees or higher meets the groove width, groove depth, groove separation, groove consistency, area limitations, and edge radius requirements set forth by the USGA. In the embodiments described herein, less than 50% of measured values of Area/(Width+Separation) are greater than 0.0030 in²/in and no single measured value of Area/(Width+Separation) value for any single groove is greater than 0.0032 in²/in.

With respect to a groove edge radius, the groove edges are in the form of a radius having an effective radius not less than 0.010" as described by the two circles method described in the USGA rules. In addition, the effective radius is not greater than 0.020". In the embodiments described, less than 50% of the upper groove edges or lower groove edges fails the two circles method subject to a 10 degree angular allowance as described in the USGA rules. No single groove edge protrudes more than 0.0003" outside the outer circle.

In view of the many possible embodiments to which the principles of the disclosed invention may be applied, it should be recognized that the illustrated embodiments are only preferred examples of the invention and should not be taken as limiting the scope of the invention. It will be evident that various modifications may be made thereto without departing from the broader spirit and scope of the invention as set forth. The specification and drawings are, accordingly, to be regarded in an illustrative sense rather than a restrictive sense.

We claim:

1. An iron-type golf club head comprising:

a body having a heel portion, a sole portion, a toe portion, a top-line portion, a front portion, a rear portion, and a striking face;

a cavity being defined by at least a rear surface of the striking face, an interior rear wall surface arranged behind the rear surface of the striking face, and the sole portion;

a composite face insert comprising prepreg plies having a fiber areal weight of less than 200 g/m², the face insert being attached at a front opening of the body and enclosing the front opening of the body, wherein the thickness of the prepreg plies is within a range of about 1 mm to about 8 mm; and

wherein the composite face insert includes a front striking surface having a polyurethane layer that is located on a majority of the front striking surface of the composite face insert,

wherein the body includes a lower leading edge zone that is entirely filled with material.

2. The iron-type golf club head of claim 1, wherein the interior rear wall in the rear portion encloses a substantial portion of the rear portion to create a substantially enclosed cavity.

3. The iron-type golf club head of claim 1, wherein the composite face insert includes a front striking surface having a metallic cap layer that is located on a majority of the front striking surface of the composite face insert.

4. The iron-type golf club head of claim 1, wherein a height distance between a horizontal plane of the leading edge groove location and the ground surface is between about 4 mm and about 10 mm.

5. The iron-type golf club head of claim 1, wherein a height distance between a horizontal plane of the leading edge groove location and the ground surface is between about 2 mm and about 6 mm.

6. The iron-type golf club head of claim 1, wherein the composite face insert includes a thickened central region.

7. The iron-type golf club head of claim 1, wherein the coefficient of restitution is at least 0.79.

8. The iron-type golf club head of claim 1, wherein at least one plug is positioned to be in contact with at least a portion of the face insert.

9. The iron-type golf club head of claim 1, wherein at least one plug contacts the inner back wall surface.

10. The iron-type golf club head of claim 1, further comprising an aperture into the enclosed cavity, the aperture being configured to allow the cavity to be filled with a filler material.

11. The iron-type golf club head of claim 10, wherein the filler material is an expanding foam material having a density between about 0.03 g/cc and about 0.2 g/cc.

12. The iron-type golf club head of claim 1, wherein a rear bond gap distance is equal to or greater than a side bond gap distance.

13. The iron-type golf club head of claim 1, wherein a rear bond gap distance is greater than or equal to 0.2 mm.

14. The iron-type golf club head of claim 1, wherein a front ledge surface and front opening wall intersect at a rounded corner location.

15. The iron-type golf club head of claim 1, wherein at least one scoreline is molded into the composite face insert.

16. The iron-type golf club head of claim 1, wherein the composite face insert is formed by water jet cutting.

17. The iron-type golf club head of claim 1, wherein the composite face insert includes prepreg plies having a fiber areal weight of less than 150 g/m².

18. An iron-type golf club head comprising:

a body having a heel portion, a sole portion, a toe portion, a top-line portion, a front portion, a rear portion, and a striking face;

19

a cavity being defined by at least a rear surface of the striking face, an interior rear wall surface substantially facing the rear surface of the striking face, and the sole portion;

a composite face insert comprising prepreg plies having a fiber areal weight less than 100 g/m^2 , the face insert being attached at a front opening of the body and enclosing the front opening of the body, wherein the thickness of the prepreg plies is within a range of about 1 mm to about 8 mm, the golf club head having a coefficient of restitution of at least 0.79.

* * * * *

20