



US008932514B1

(12) **United States Patent**
Yin et al.

(10) **Patent No.:** **US 8,932,514 B1**
(45) **Date of Patent:** **Jan. 13, 2015**

(54) **FRACTURE TOUGHNESS OF GLASS**

(75) Inventors: **Qinghua Yin**, Tempe, AZ (US); **Xiwang Qi**, Scottsdale, AZ (US); **Maximilian A. Biberger**, Scottsdale, AZ (US); **David Leamon**, Gilbert, AZ (US)

(73) Assignee: **SDCmaterials, Inc.**, Tempe, AZ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 489 days.

(21) Appl. No.: **12/962,523**

(22) Filed: **Dec. 7, 2010**

Related U.S. Application Data

(60) Provisional application No. 61/284,329, filed on Dec. 15, 2009.

(51) **Int. Cl.**
B28B 3/02 (2006.01)

(52) **U.S. Cl.**
CPC **B28B 3/025** (2013.01)
USPC **264/603**

(58) **Field of Classification Search**
CPC B28B 3/025
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,021,936 A	11/1935	Johnstone	
2,284,554 A	5/1942	Beyerstedt	
2,419,042 A	4/1947	Todd	202/205
2,519,531 A	8/1950	Worn	230/95
2,562,753 A	7/1951	Trost	241/39
2,689,780 A	9/1954	Rice	23/106
3,001,402 A	9/1961	Koblin	73/421.5

3,042,511 A	7/1962	Reding, Jr.	
3,067,025 A	12/1962	Chisholm	75/84.5
3,145,287 A	8/1964	Siebein et al.	

(Continued)

FOREIGN PATENT DOCUMENTS

DE	34 45 273 A1	6/1986
EP	0 385 742 A1	9/1990

(Continued)

OTHER PUBLICATIONS

Y. Ji, J.A. Yeomans, Processing and mechanical properties of Al₂O₃-5 vol.% Cr nanocomposites, Journal of the European Ceramic Society, vol. 22, Issue 12, Nov. 2002, pp. 1927-1936.*

(Continued)

Primary Examiner — Joseph S Del Sole


Assistant Examiner — Russell Kemmerle, III

(74) *Attorney, Agent, or Firm* — Morrison & Foerster LLP

(57) **ABSTRACT**

A method of making glass is provided. The method comprises preparing a dispersion of a nano-material. A slurry of a glass matrix material is prepared. The nano-dispersion is mixed with the matrix slurry to form a nano-dispersion/slurry mixture. The nano-dispersion/slurry mixture is dried. The nano-dispersion/slurry mixture is pressed into a final manufacture comprising a molecular structure including the nano-material bonded within and uniformly distributed throughout the molecular structure. The manufacture comprises an increased fracture toughness compared with a conventional manufacture produced without bonding the nano-material within the molecular structure. The nano-material has a size on the order of tens of nanometers. The matrix material has a size on the order of several micrometers. Five percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion. Sintering is performed on the final form using a sintering process following the pressing step. The sintering process includes a hot isostatic pressing process.

26 Claims, 2 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

- | | | | | | | | |
|-------------|---------|-----------------------|------------|--------------|---------|---------------------------|------------|
| 3,178,121 A | 4/1965 | Wallace, Jr. | 241/5 | 5,006,163 A | 4/1991 | Benn et al. | |
| 3,179,782 A | 4/1965 | Matvay | | 5,015,863 A | 5/1991 | Takeshima et al. | |
| 3,181,947 A | 5/1965 | Vordahl | | 5,041,713 A | 8/1991 | Weidman | 219/121.51 |
| 3,235,700 A | 2/1966 | Mondain-Monval et al. | | 5,043,548 A | 8/1991 | Whitney et al. | 219/121.84 |
| 3,313,908 A | 4/1967 | Unger et al. | | 5,070,064 A | 12/1991 | Hsu et al. | |
| 3,401,465 A | 9/1968 | Larwill | 34/57 | 5,073,193 A | 12/1991 | Chaklader et al. | 75/346 |
| 3,450,926 A | 6/1969 | Kiernan | | 5,133,190 A | 7/1992 | Abdelmalek | |
| 3,457,788 A | 7/1969 | Miyajima | 73/422 | 5,151,296 A | 9/1992 | Tokunaga | |
| 3,537,513 A | 11/1970 | Austin | 165/70 | 5,157,007 A | 10/1992 | Domesle et al. | 502/66 |
| 3,552,653 A | 1/1971 | Inoue | | 5,192,130 A | 3/1993 | Endo et al. | |
| 3,617,358 A | 11/1971 | Dittrich | | 5,217,746 A | 6/1993 | Lenling et al. | |
| 3,667,111 A | 6/1972 | Chartet | | 5,230,844 A | 7/1993 | Macaire et al. | |
| 3,741,001 A | 6/1973 | Fletcher et al. | 73/28 | 5,233,153 A | 8/1993 | Coats | |
| 3,752,172 A | 8/1973 | Cohen et al. | 137/12 | 5,269,848 A | 12/1993 | Nakagawa | |
| 3,761,360 A | 9/1973 | Auvil et al. | | 5,294,242 A | 3/1994 | Zurecki et al. | |
| 3,774,442 A | 11/1973 | Gustavsson | 73/28 | 5,330,945 A | 7/1994 | Beckmeyer et al. | |
| 3,804,034 A | 4/1974 | Stiglich, Jr. | | 5,338,716 A | 8/1994 | Triplett et al. | |
| 3,830,756 A | 8/1974 | Sanchez et al. | 252/462 | 5,369,241 A | 11/1994 | Taylor et al. | 219/121.47 |
| 3,871,448 A | 3/1975 | Vann et al. | | 5,371,049 A | 12/1994 | Moffett et al. | 501/89 |
| 3,892,882 A | 7/1975 | Guest et al. | 427/34 | 5,372,629 A | 12/1994 | Anderson et al. | 75/332 |
| 3,914,573 A | 10/1975 | Muehlberger | 219/76 | 5,392,797 A | 2/1995 | Welch | 134/108 |
| 3,959,094 A | 5/1976 | Steinberg | | 5,436,080 A | 7/1995 | Inoue et al. | |
| 3,959,420 A | 5/1976 | Geddes et al. | 261/112 | 5,439,865 A | 8/1995 | Abe et al. | 502/333 |
| 3,969,482 A | 7/1976 | Teller | | 5,442,153 A | 8/1995 | Marantz et al. | 219/121.47 |
| 4,008,620 A | 2/1977 | Narato et al. | 73/421.5 A | 5,452,854 A | 9/1995 | Keller | |
| 4,018,388 A | 4/1977 | Andrews | 241/39 | 5,460,701 A | 10/1995 | Parker et al. | |
| 4,021,021 A | 5/1977 | Hall et al. | | 5,464,458 A | 11/1995 | Yamamoto | |
| 4,127,760 A | 11/1978 | Meyer et al. | | 5,485,941 A | 1/1996 | Guyomard et al. | 222/1 |
| 4,139,497 A | 2/1979 | Castor et al. | 252/470 | 5,486,675 A | 1/1996 | Taylor et al. | |
| 4,146,654 A | 3/1979 | Guyonnet | | 5,534,149 A | 7/1996 | Birkenbeil et al. | 210/636 |
| 4,157,316 A | 6/1979 | Thompson et al. | 252/462 | 5,534,270 A | 7/1996 | De Castro | |
| 4,171,288 A | 10/1979 | Keith et al. | 252/462 | 5,543,173 A | 8/1996 | Horn, Jr. et al. | |
| 4,174,298 A | 11/1979 | Antos | 252/441 | 5,553,507 A | 9/1996 | Basch et al. | 73/863.01 |
| 4,189,925 A | 2/1980 | Long | | 5,558,771 A | 9/1996 | Hagen et al. | |
| 4,227,928 A | 10/1980 | Wang | | 5,562,966 A | 10/1996 | Clarke et al. | |
| 4,248,387 A | 2/1981 | Andrews | 241/5 | 5,582,807 A | 12/1996 | Liao et al. | |
| 4,253,917 A | 3/1981 | Wang | | 5,596,973 A | 1/1997 | Grice | |
| 4,260,649 A | 4/1981 | Dension et al. | | 5,611,896 A | 3/1997 | Swanepoel et al. | 204/169 |
| 4,284,609 A | 8/1981 | deVries | 423/242 | 5,630,322 A | 5/1997 | Heilmann et al. | 62/95 |
| 4,315,874 A | 2/1982 | Ushida et al. | | 5,652,304 A | 7/1997 | Calderon et al. | |
| 4,326,492 A | 4/1982 | Leibrand, Sr. et al. | | 5,714,644 A | 2/1998 | Irgang et al. | |
| 4,344,779 A | 8/1982 | Isserlis | | 5,723,027 A | 3/1998 | Serole | |
| 4,369,167 A | 1/1983 | Weir | | 5,723,187 A | 3/1998 | Popoola et al. | |
| 4,388,274 A | 6/1983 | Rourke et al. | 422/177 | 5,726,414 A | 3/1998 | Kitahashi et al. | |
| 4,419,331 A | 12/1983 | Montalvo | | 5,733,662 A | 3/1998 | Bogachek | |
| 4,431,750 A | 2/1984 | McGinnis et al. | 502/329 | 5,749,938 A | 5/1998 | Coombs | 75/332 |
| 4,436,075 A | 3/1984 | Campbell et al. | 123/557 | 5,776,359 A | 7/1998 | Schultz et al. | 252/62.51 |
| 4,440,733 A | 4/1984 | Lawson et al. | | 5,788,738 A | 8/1998 | Pirzada et al. | 75/331 |
| 4,458,138 A | 7/1984 | Adrian et al. | | 5,804,155 A | 9/1998 | Farrauto et al. | |
| 4,459,327 A | 7/1984 | Wang | | 5,811,187 A | 9/1998 | Anderson et al. | 428/403 |
| 4,505,945 A | 3/1985 | Dubust et al. | | 5,837,959 A | 11/1998 | Muehlberger et al. ... | 219/121.47 |
| 4,506,136 A | 3/1985 | Smyth et al. | | 5,851,507 A | 12/1998 | Pirzada et al. | 423/659 |
| 4,513,149 A | 4/1985 | Gray et al. | 564/449 | 5,853,815 A | 12/1998 | Muehlberger | 427/446 |
| 4,523,981 A | 6/1985 | Ang et al. | | 5,858,470 A | 1/1999 | Bernecki et al. | |
| 4,545,872 A | 10/1985 | Sammells et al. | | 5,884,473 A | 3/1999 | Noda et al. | |
| RE32,244 E | 9/1986 | Andersen | | 5,905,000 A | 5/1999 | Yadav et al. | 429/33 |
| 4,609,441 A | 9/1986 | Frese, Jr. et al. | | 5,928,806 A | 7/1999 | Olah et al. | |
| 4,610,857 A | 9/1986 | Ogawa et al. | | 5,935,293 A | 8/1999 | Detering et al. | 75/10.29 |
| 4,616,779 A | 10/1986 | Serrano et al. | | 5,973,289 A | 10/1999 | Read et al. | |
| 4,723,589 A | 2/1988 | Iyer et al. | | 5,989,648 A | 11/1999 | Phillips | 427/456 |
| 4,731,517 A | 3/1988 | Cheney | | 5,993,967 A | 11/1999 | Brotzman, Jr. et al. | 428/407 |
| 4,751,021 A | 6/1988 | Mollon et al. | | 5,993,988 A | 11/1999 | Ohara et al. | 429/40 |
| 4,764,283 A | 8/1988 | Ashbrook et al. | 210/695 | 6,004,620 A | 12/1999 | Camm | |
| 4,765,805 A | 8/1988 | Wahl et al. | | 6,012,647 A | 1/2000 | Ruta et al. | 239/132.1 |
| 4,824,624 A | 4/1989 | Palicka et al. | 264/67 | 6,033,781 A | 3/2000 | Brotzman, Jr. et al. | 428/405 |
| 4,836,084 A | 6/1989 | Vogelesang et al. | | 6,045,765 A | 4/2000 | Nakatsuji et al. | |
| 4,855,505 A | 8/1989 | Koll | 564/398 | 6,059,853 A | 5/2000 | Coombs | 75/332 |
| 4,866,240 A | 9/1989 | Webber | 219/121.47 | 6,066,587 A | 5/2000 | Kurokawa et al. | |
| 4,877,937 A | 10/1989 | Müller | | 6,084,197 A | 7/2000 | Fusaro, Jr. | |
| 4,885,038 A | 12/1989 | Anderson et al. | | 6,093,306 A | 7/2000 | Hanrahan et al. | |
| 4,921,586 A | 5/1990 | Molter | | 6,093,378 A | 7/2000 | Deeba et al. | |
| 4,970,364 A | 11/1990 | Müller | | 6,102,106 A | 8/2000 | Manning et al. | 165/76 |
| 4,982,050 A | 1/1991 | Gammie et al. | | 6,117,376 A | 9/2000 | Merkel | |
| 4,983,555 A | 1/1991 | Roy et al. | 501/120 | 6,140,539 A | 10/2000 | Sander et al. | |
| 4,987,033 A | 1/1991 | Abkowitz et al. | 428/469 | 6,168,694 B1 | 1/2001 | Huang et al. | |
| | | | | 6,190,627 B1 | 2/2001 | Hoke et al. | |
| | | | | 6,213,049 B1 | 4/2001 | Yang | 118/723 |
| | | | | 6,214,195 B1 | 4/2001 | Yadav et al. | 205/334 |
| | | | | 6,228,904 B1 | 5/2001 | Yadav et al. | 523/210 |

(56)

References Cited

U.S. PATENT DOCUMENTS

- | | | | |
|-----------------|---------|---------------------------|------------|
| 6,254,940 B1 | 7/2001 | Pratsinis et al. | 427/562 |
| 6,261,484 B1 | 7/2001 | Phillips et al. | 264/5 |
| 6,267,864 B1 | 7/2001 | Yadav et al. | 205/341 |
| 6,322,756 B1 | 11/2001 | Arno et al. | |
| 6,342,465 B1 | 1/2002 | Klein et al. | 502/339 |
| 6,344,271 B1 | 2/2002 | Yadav et al. | 428/402 |
| 6,362,449 B1 | 3/2002 | Hadidi et al. | |
| 6,379,419 B1 | 4/2002 | Celik et al. | 75/346 |
| 6,387,560 B1 | 5/2002 | Yadav et al. | 429/45 |
| 6,395,214 B1 | 5/2002 | Kear et al. | 264/434 |
| 6,398,843 B1 | 6/2002 | Tarrant | 75/249 |
| 6,399,030 B1 | 6/2002 | Nolan | |
| 6,409,851 B1 | 6/2002 | Sethuram et al. | 148/565 |
| 6,413,781 B1 | 7/2002 | Geis et al. | 436/178 |
| 6,416,818 B1 | 7/2002 | Aikens et al. | 427/383.1 |
| RE37,853 E | 9/2002 | Detering et al. | 75/10.19 |
| 6,444,009 B1 | 9/2002 | Liu et al. | 75/332 |
| 6,475,951 B1 | 11/2002 | Domesle et al. | |
| 6,488,904 B1 | 12/2002 | Cox et al. | |
| 6,506,995 B1 | 1/2003 | Fusaro, Jr. et al. | |
| 6,517,800 B1 | 2/2003 | Cheng et al. | 423/447.1 |
| 6,524,662 B2 | 2/2003 | Jang et al. | 427/535 |
| 6,531,704 B2 | 3/2003 | Yadav et al. | 250/493.1 |
| 6,548,445 B1 | 4/2003 | Buysch et al. | 502/230 |
| 6,554,609 B2 | 4/2003 | Yadav et al. | 432/9 |
| 6,562,304 B1 | 5/2003 | Mizrahi | |
| 6,562,495 B2 | 5/2003 | Yadav et al. | 429/12 |
| 6,569,393 B1 | 5/2003 | Hoke et al. | |
| 6,569,397 B1 | 5/2003 | Yadav et al. | 423/345 |
| 6,569,518 B2 | 5/2003 | Yadav et al. | 428/323 |
| 6,572,672 B2 | 6/2003 | Yadav et al. | 75/343 |
| 6,579,446 B1 | 6/2003 | Teran et al. | |
| 6,596,187 B2 | 7/2003 | Coll et al. | 216/56 |
| 6,603,038 B1 | 8/2003 | Hagemeyer et al. | 560/241.1 |
| 6,607,821 B2 | 8/2003 | Yadav et al. | 428/323 |
| 6,610,355 B2 | 8/2003 | Yadav et al. | 427/115 |
| 6,623,559 B2 | 9/2003 | Huang | 117/87 |
| 6,635,357 B2 | 10/2003 | Moxson et al. | 428/548 |
| 6,641,775 B2 | 11/2003 | Vigliotti et al. | 264/618 |
| 6,652,822 B2 | 11/2003 | Phillips et al. | 423/290 |
| 6,652,967 B2 | 11/2003 | Yadav et al. | 428/403 |
| 6,669,823 B1 | 12/2003 | Sarkas et al. | 204/164 |
| 6,682,002 B2 | 1/2004 | Kyotani | 239/318 |
| 6,689,192 B1 | 2/2004 | Phillips et al. | 75/342 |
| 6,699,398 B1 | 3/2004 | Kim | 216/55 |
| 6,706,097 B2 | 3/2004 | Zornes | 96/153 |
| 6,706,660 B2 | 3/2004 | Park | |
| 6,710,207 B2 | 3/2004 | Bogan, Jr. et al. | 562/549 |
| 6,713,176 B2 | 3/2004 | Yadav et al. | 428/402 |
| 6,716,525 B1 | 4/2004 | Yadav et al. | 428/402 |
| 6,744,006 B2 | 6/2004 | Johnson et al. | |
| 6,746,791 B2 | 6/2004 | Yadav et al. | 429/30 |
| 6,772,584 B2 | 8/2004 | Chun et al. | 60/275 |
| 6,786,950 B2 | 9/2004 | Yadav et al. | 75/346 |
| 6,813,931 B2 | 11/2004 | Yadav et al. | 73/31.05 |
| 6,817,388 B2 | 11/2004 | Tsangaris et al. | 141/82 |
| 6,832,735 B2 | 12/2004 | Yadav et al. | 241/16 |
| 6,838,072 B1 | 1/2005 | Kong et al. | 423/594.2 |
| 6,841,509 B1 | 1/2005 | Hwang et al. | |
| 6,855,410 B2 | 2/2005 | Buckley | |
| 6,855,426 B2 * | 2/2005 | Yadav | 428/403 |
| 6,855,749 B1 | 2/2005 | Yadav et al. | 523/105 |
| 6,858,170 B2 | 2/2005 | Van Thillo et al. | |
| 6,886,545 B1 | 5/2005 | Holm | 123/568.21 |
| 6,891,319 B2 | 5/2005 | Dean et al. | |
| 6,896,958 B1 | 5/2005 | Cayton et al. | 428/323 |
| 6,902,699 B2 | 6/2005 | Fritzemeier et al. | 419/38 |
| 6,916,872 B2 | 7/2005 | Yadav et al. | 524/430 |
| 6,919,065 B2 | 7/2005 | Zhou et al. | |
| 6,919,527 B2 | 7/2005 | Boulos et al. | 219/121.52 |
| 6,933,331 B2 | 8/2005 | Yadav et al. | 523/210 |
| 6,972,115 B1 | 12/2005 | Ballard | |
| 6,986,877 B2 | 1/2006 | Takikawa et al. | 423/447.3 |
| 6,994,837 B2 | 2/2006 | Boulos et al. | 423/613 |
| 7,007,872 B2 | 3/2006 | Yadav et al. | 241/1 |
| 7,022,305 B2 | | | |
| 7,052,777 B2 | | | |
| 7,073,559 B2 | | | |
| 7,074,364 B2 | | | |
| 7,081,267 B2 | | | |
| 7,101,819 B2 | | | |
| 7,147,544 B2 | | | |
| 7,147,894 B2 | | | |
| 7,166,198 B2 | | | |
| 7,166,663 B2 | | | |
| 7,172,649 B2 | | | |
| 7,172,790 B2 | | | |
| 7,178,747 B2 | | | |
| 7,208,126 B2 | | | |
| 7,211,236 B2 | | | |
| 7,217,407 B2 | | | |
| 7,220,398 B2 | | | |
| 7,255,498 B2 | | | |
| 7,265,076 B2 | | | |
| 7,282,167 B2 | | | |
| 7,307,195 B2 | | | |
| 7,323,655 B2 | | | |
| 7,384,447 B2 | | | |
| 7,402,899 B1 | | | |
| 7,417,008 B2 | | | |
| 7,494,527 B2 | | | |
| 7,517,826 B2 | | | |
| 7,534,738 B2 | | | |
| 7,541,012 B2 | | | |
| 7,541,310 B2 | | | |
| 7,557,324 B2 | | | |
| 7,572,315 B2 | | | |
| 7,576,029 B2 | | | |
| 7,576,031 B2 | | | |
| 7,604,843 B1 | | | |
| 7,611,686 B2 | | | |
| 7,615,097 B2 | | | |
| 7,618,919 B2 | | | |
| 7,622,693 B2 | | | |
| 7,632,775 B2 | | | |
| 7,635,218 B1 | | | |
| 7,674,744 B2 | | | |
| 7,678,419 B2 | | | |
| 7,704,369 B2 | | | |
| 7,709,411 B2 | | | |
| 7,709,414 B2 | | | |
| 7,745,367 B2 | | | |
| 7,750,265 B2 | | | |
| 7,759,279 B2 | | | |
| 7,759,281 B2 | | | |
| 7,803,210 B2 | | | |
| 7,842,515 B2 | | | |
| 7,851,405 B2 | | | |
| 7,874,239 B2 | | | |
| 7,875,573 B2 | | | |
| 7,897,127 B2 | | | |
| 7,902,104 B2 | | | |
| 7,905,942 B1 | | | |
| 7,935,655 B2 | | | |
| 8,051,724 B1 | | | |
| 8,076,258 B1 | | | |
| 8,080,494 B2 | | | |
| 8,089,495 B2 | | | |
| 8,129,654 B2 | | | |
| 8,142,619 B2 | | | |
| 8,168,561 B2 | | | |
| 8,173,572 B2 | | | |
| 8,211,392 B2 | | | |
| 8,258,070 B2 | | | |
| 8,278,240 B2 | | | |
| 8,294,060 B2 | | | |
| 8,309,489 B2 | | | |
| 8,349,761 B2 | | | |
| 8,404,611 B2 | | | |
| 8,524,631 B2 | | | |
| 8,557,727 B2 | | | |
| 8,574,408 B2 | | | |
| 8,669,202 B2 | | | |
| 2001/0004009 A1 | | | |
| 4/2006 | | Drumm et al. | |
| 5/2006 | | Brotzman, Jr. et al. | 428/570 |
| 7/2006 | | O'Larey et al. | 164/76.1 |
| 7/2006 | | Jahn et al. | |
| 7/2006 | | Yadav | 427/115 |
| 9/2006 | | Rosenflanz et al. | 501/10 |
| 12/2006 | | Rosenflanz | 451/28 |
| 12/2006 | | Zhou et al. | 427/256 |
| 1/2007 | | Van Der Walt et al. | 204/165 |
| 1/2007 | | Cayton et al. | 524/430 |
| 2/2007 | | Conrad et al. | 106/35 |
| 2/2007 | | Koulik et al. | |
| 2/2007 | | Yadav et al. | 241/23 |
| 4/2007 | | Musick et al. | 423/69 |
| 5/2007 | | Stark et al. | 423/592.1 |
| 5/2007 | | Zhang | 423/610 |
| 5/2007 | | Sutorik et al. | 423/593.1 |
| 8/2007 | | Bush et al. | |
| 9/2007 | | Taguchi et al. | |
| 10/2007 | | Carpenter | |
| 12/2007 | | Polverejan et al. | 585/443 |
| 1/2008 | | Kim | 219/121.43 |
| 6/2008 | | Kodas et al. | 75/332 |
| 7/2008 | | Whiting et al. | |
| 8/2008 | | Richards et al. | 502/306 |
| 2/2009 | | Jurewicz et al. | 75/346 |
| 4/2009 | | Fujdala et al. | |
| 5/2009 | | Fujdala et al. | |
| 6/2009 | | Yeung et al. | 423/245.1 |
| 6/2009 | | Espinoza et al. | |
| 7/2009 | | Nylen et al. | |
| 8/2009 | | Boulos et al. | 75/336 |
| 8/2009 | | Saito et al. | |
| 8/2009 | | Beutel et al. | |
| 10/2009 | | Robinson et al. | |
| 11/2009 | | Alekseeva et al. | 423/276 |
| 11/2009 | | McKechnie et al. | 75/346 |
| 11/2009 | | Shimazu et al. | |
| 11/2009 | | Foret | 219/121.43 |
| 12/2009 | | Zhou et al. | |
| 12/2009 | | Lott | |
| 3/2010 | | Shiratori et al. | |
| 3/2010 | | Kevwitch et al. | |
| 4/2010 | | Olah et al. | |
| 5/2010 | | Zhou et al. | |
| 5/2010 | | Fujdala et al. | |
| 6/2010 | | Fujdala et al. | |
| 7/2010 | | Belashchenko et al. | |
| 7/2010 | | Shiratori et al. | |
| 7/2010 | | Kezuka et al. | |
| 9/2010 | | Sekine et al. | 75/334 |
| 11/2010 | | Zou et al. | |
| 12/2010 | | Wakamatsu et al. | |
| 1/2011 | | Howland | |
| 1/2011 | | Beutel et al. | |
| 3/2011 | | Layman et al. | |
| 3/2011 | | Kalck | |
| 3/2011 | | Layman | |
| 5/2011 | | Tolmachev | |
| 11/2011 | | Layman et al. | |
| 12/2011 | | Biberger | |
| 12/2011 | | Yasuda et al. | |
| 1/2012 | | Keller | |
| 3/2012 | | Lee et al. | |
| 3/2012 | | Layman et al. | |
| 5/2012 | | Virkar | |
| 5/2012 | | Feaviour | |
| 7/2012 | | Grubert et al. | |
| 9/2012 | | Fujdala et al. | |
| 10/2012 | | Tange et al. | |
| 10/2012 | | Mohanty et al. | |
| 11/2012 | | Cuenya et al. | |
| 1/2013 | | Xia et al. | |
| 3/2013 | | Nakamura et al. | |
| 9/2013 | | Biberger | |
| 10/2013 | | Yin et al. | |
| 11/2013 | | Layman | |
| 3/2014 | | Van Den Hoek et al. | |
| 6/2001 | | MacKelvie | |

(56)

References Cited

U.S. PATENT DOCUMENTS

- 2001/0042802 A1 11/2001 Youds 241/5
 2001/0055554 A1 12/2001 Hoke et al.
 2002/0018815 A1 2/2002 Sievers et al. 424/489
 2002/0068026 A1 6/2002 Murrell et al. 422/211
 2002/0071800 A1 6/2002 Hoke et al.
 2002/0079620 A1 6/2002 DuBuis et al. 264/328.14
 2002/0100751 A1 8/2002 Carr
 2002/0102674 A1 8/2002 Anderson 435/174
 2002/0131914 A1 9/2002 Sung
 2002/0143417 A1 10/2002 Ito et al. 700/95
 2002/0168466 A1 11/2002 Tapphorn et al.
 2002/0182735 A1 12/2002 Kibby et al. 436/37
 2002/0183191 A1 12/2002 Faber et al.
 2002/0192129 A1 12/2002 Shamouilian et al.
 2003/0036786 A1 2/2003 Duren et al. 607/96
 2003/0042232 A1 3/2003 Shimazu 219/121.47
 2003/0047617 A1 3/2003 Shanmugham et al.
 2003/0066800 A1 4/2003 Saim et al. 264/5
 2003/0102099 A1 6/2003 Yadav et al.
 2003/0108459 A1 6/2003 Wu et al. 422/186.04
 2003/0110931 A1 6/2003 Aghajanian et al.
 2003/0129098 A1 7/2003 Endo et al.
 2003/0139288 A1 7/2003 Cai et al. 502/303
 2003/0143153 A1 7/2003 Boulos et al.
 2003/0172772 A1 9/2003 Sethuram et al. 501/87
 2003/0223546 A1 12/2003 McGregor et al. 378/143
 2004/0009118 A1 1/2004 Phillips et al. 423/592.1
 2004/0023302 A1 2/2004 Archibald et al. 435/7.1
 2004/0023453 A1 2/2004 Xu et al. 257/369
 2004/0077494 A1 4/2004 LaBarge et al. 502/303
 2004/0103751 A1 6/2004 Joseph et al. 75/10.19
 2004/0109523 A1 6/2004 Singh et al.
 2004/0119064 A1 6/2004 Narayan et al.
 2004/0127586 A1 7/2004 Jin et al. 518/715
 2004/0129222 A1 7/2004 Nylen et al.
 2004/0166036 A1 8/2004 Chen et al.
 2004/0167009 A1 8/2004 Kuntz et al. 501/95.2
 2004/0176246 A1 9/2004 Shirk et al. 502/439
 2004/0208805 A1 10/2004 Fincke et al.
 2004/0213998 A1 10/2004 Hearley et al. 428/402
 2004/0235657 A1 11/2004 Xiao et al.
 2004/0238345 A1 12/2004 Koulik et al.
 2004/0251017 A1 12/2004 Pillion et al. 165/289
 2004/0251241 A1 12/2004 Blutke et al.
 2005/0000321 A1 1/2005 O'Larey et al. 75/952
 2005/0000950 A1 1/2005 Schroder et al. 219/121.59
 2005/0066805 A1 3/2005 Park et al.
 2005/0070431 A1 3/2005 Alvin et al.
 2005/0077034 A1 4/2005 King 165/163
 2005/0097988 A1 5/2005 Kodas et al. 75/332
 2005/0106865 A1 5/2005 Chung et al.
 2005/0133121 A1 6/2005 Subramanian et al.
 2005/0153069 A1 7/2005 Tapphorn et al.
 2005/0163673 A1 7/2005 Johnson et al.
 2005/0199739 A1 9/2005 Kuroda et al. 239/13
 2005/0211018 A1 9/2005 Jurewicz et al.
 2005/0220695 A1 10/2005 Abatzoglou et al. 423/445
 2005/0227864 A1 10/2005 Sutorik et al.
 2005/0233380 A1 10/2005 Pesiri et al. 435/7.1
 2005/0240069 A1 10/2005 Polverejan et al. 585/444
 2005/0258766 A1 11/2005 Kim 315/111.21
 2005/0275143 A1 12/2005 Toth
 2006/0043651 A1 3/2006 Yamamoto et al.
 2006/0051505 A1 3/2006 Kortshagen et al. 427/212
 2006/0068989 A1 3/2006 Ninomiya et al. 502/339
 2006/0094595 A1 5/2006 Labarge 502/325
 2006/0096393 A1 5/2006 Pesiri 73/863.21
 2006/0105910 A1 5/2006 Zhou et al. 502/338
 2006/0108332 A1 5/2006 Belashchenko 219/121.47
 2006/0153728 A1 7/2006 Schoenung et al. 419/32
 2006/0153765 A1 7/2006 Pham-Huu et al. 423/345
 2006/0159596 A1 7/2006 De La Veaux et al. 422/151
 2006/0166809 A1 7/2006 Malek et al.
 2006/0211569 A1 9/2006 Dang et al.
 2006/0213326 A1 9/2006 Gollob et al.
 2006/0222780 A1 10/2006 Gurevich et al.
 2006/0231525 A1 10/2006 Asakawa et al. 216/56
 2007/0044513 A1 3/2007 Kear et al.
 2007/0048206 A1 3/2007 Hung et al. 423/335
 2007/0049484 A1 3/2007 Kear et al.
 2007/0063364 A1 3/2007 Hsiao et al. 264/5
 2007/0084308 A1 4/2007 Nakamura et al. 75/346
 2007/0084834 A1 4/2007 Hanus et al. 219/121.5
 2007/0087934 A1 4/2007 Martens et al. 502/214
 2007/0092768 A1 4/2007 Lee et al.
 2007/0153390 A1 7/2007 Nakamura et al.
 2007/0163385 A1 7/2007 Takahashi et al.
 2007/0173403 A1 7/2007 Koike et al. 502/300
 2007/0178673 A1 8/2007 Gole et al.
 2007/0221404 A1 9/2007 Das et al.
 2007/0253874 A1 11/2007 Foret 422/186.07
 2007/0292321 A1 12/2007 Plischke et al. 422/198
 2008/0006954 A1 1/2008 Yubuta et al.
 2008/0026041 A1 1/2008 Tepper et al.
 2008/0031806 A1 2/2008 Gavenonis et al. 423/608
 2008/0038578 A1 2/2008 Li
 2008/0045405 A1 2/2008 Beutel et al.
 2008/0047261 A1 2/2008 Han et al.
 2008/0057212 A1 3/2008 Dorier et al.
 2008/0064769 A1 3/2008 Sato et al.
 2008/0104735 A1 5/2008 Howland
 2008/0105083 A1 5/2008 Nakamura et al. 75/255
 2008/0116178 A1 5/2008 Weidman 219/121.47
 2008/0125308 A1 5/2008 Furdala et al.
 2008/0125313 A1 5/2008 Furdala et al.
 2008/0138651 A1 6/2008 Doi et al.
 2008/0175936 A1 7/2008 Tokita et al.
 2008/0187714 A1 8/2008 Wakamatsu et al.
 2008/0206562 A1 8/2008 Stucky et al.
 2008/0207858 A1 8/2008 Kowaleski et al.
 2008/0248704 A1 10/2008 Mathis et al.
 2008/0274344 A1 11/2008 Vieth et al. 428/304.4
 2008/0277092 A1 11/2008 Layman et al. 165/281
 2008/0277264 A1 11/2008 Biberger et al.
 2008/0277266 A1 11/2008 Layman et al. 204/157.15
 2008/0277267 A1 11/2008 Biberger et al. 204/157.15
 2008/0277268 A1 11/2008 Layman 204/164
 2008/0277269 A1 11/2008 Layman et al. 423/215.5
 2008/0277270 A1 11/2008 Biberger et al. 204/164
 2008/0277271 A1 11/2008 Layman 422/130
 2008/0280049 A1 11/2008 Kevitch et al. 427/243
 2008/0280751 A1 11/2008 Harutyunyan et al.
 2008/0280756 A1 11/2008 Biberger 502/232
 2008/0283411 A1 11/2008 Eastman et al.
 2008/0283498 A1 11/2008 Yamazaki
 2008/0307960 A1 12/2008 Hendrickson et al.
 2009/0010801 A1 1/2009 Murphy et al. 422/4
 2009/0054230 A1 2/2009 Veeraraghavan et al.
 2009/0081092 A1 3/2009 Yang et al.
 2009/0088585 A1 4/2009 Schammel et al. 562/409
 2009/0092887 A1 4/2009 McGrath et al.
 2009/0098402 A1 4/2009 Kang et al.
 2009/0114568 A1 5/2009 Trevino et al. 208/139
 2009/0162991 A1 6/2009 Beneyton et al.
 2009/0168506 A1 7/2009 Han et al.
 2009/0170242 A1 7/2009 Lin et al.
 2009/0181474 A1 7/2009 Nagai
 2009/0200180 A1 8/2009 Capote et al.
 2009/0208367 A1 8/2009 Calio et al.
 2009/0209408 A1 8/2009 Kitamura et al.
 2009/0223410 A1 9/2009 Jun et al.
 2009/0253037 A1 10/2009 Park et al.
 2009/0274897 A1 11/2009 Kaner et al.
 2009/0274903 A1 11/2009 Addiego 428/337
 2009/0286899 A1 11/2009 Hofmann et al. 522/99
 2009/0324468 A1 12/2009 Golden et al.
 2010/0050868 A1 3/2010 Kuznicki et al.
 2010/0089002 A1 4/2010 Merkel
 2010/0092358 A1 4/2010 Koegel et al.
 2010/0124514 A1 5/2010 Chelluri et al.
 2010/0166629 A1 7/2010 Deeba
 2010/0180581 A1 7/2010 Grubert et al.
 2010/0180582 A1 7/2010 Mueller-Stach et al.
 2010/0186375 A1 7/2010 Kazi et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2010/0240525 A1 9/2010 Golden et al.
 2010/0275781 A1 11/2010 Tsangaris
 2011/0006463 A1 1/2011 Layman
 2011/0030346 A1 2/2011 Neubauer et al.
 2011/0049045 A1 3/2011 Hurt et al.
 2011/0052467 A1 3/2011 Chase et al.
 2011/0143041 A1 6/2011 Layman et al.
 2011/0143915 A1 6/2011 Yin et al.
 2011/0143916 A1 6/2011 Leamon
 2011/0143926 A1 6/2011 Yin et al.
 2011/0143930 A1 6/2011 Yin et al.
 2011/0143933 A1 6/2011 Yin et al.
 2011/0144382 A1 6/2011 Yin et al.
 2011/0152550 A1 6/2011 Grey et al.
 2011/0158871 A1 6/2011 Arnold et al.
 2011/0174604 A1 7/2011 Duesel et al.
 2011/0243808 A1 10/2011 Fossey et al.
 2011/0245073 A1 10/2011 Oljaca et al.
 2011/0247336 A9 10/2011 Farsad et al.
 2011/0305612 A1 12/2011 Müller-Stach et al.
 2012/0023909 A1 2/2012 Lambert et al.
 2012/0045373 A1 2/2012 Bibberger
 2012/0063963 A1 3/2012 Watanabe et al.
 2012/0097033 A1 4/2012 Arnold et al.
 2012/0122660 A1 5/2012 Andersen et al.
 2012/0124974 A1 5/2012 Li et al.
 2012/0171098 A1 7/2012 Hung et al.
 2012/0308467 A1 12/2012 Carpenter et al.
 2012/0313269 A1 12/2012 Kear et al.
 2013/0079216 A1 3/2013 Bibberger et al.
 2013/0213018 A1 8/2013 Yin et al.
 2013/0280528 A1 10/2013 Bibberger
 2013/0281288 A1 10/2013 Bibberger et al.
 2013/0316896 A1 11/2013 Bibberger
 2013/0345047 A1 12/2013 Bibberger et al.
 2014/0018230 A1 1/2014 Yin et al.
 2014/0120355 A1 5/2014 Bibberger
 2014/0128245 A1 5/2014 Yin et al.
 2014/0140909 A1 5/2014 Qi et al.
 2014/0148331 A1 5/2014 Bibberger et al.
 2014/0209451 A1 7/2014 Bibberger et al.

FOREIGN PATENT DOCUMENTS

EP 1 134 302 A1 9/2001
 EP 1 256 378 A2 11/2002
 EP 1 619 168 A1 1/2006
 EP 1 955 765 A1 8/2008
 GB 1 307 941 A 2/1973
 JP 56-146804 11/1981 B22F 9/08
 JP 61-086815 A 5/1986
 JP 62-102827 A 5/1987
 JP 63-214342 A 9/1988
 JP 1-164795 A 6/1989
 JP 05-228361 A 9/1993
 JP 05-324094 A 12/1993
 JP 6-93309 A 4/1994
 JP 6-135797 A 5/1994
 JP 6-272012 A 9/1994
 JP H6-065772 U 9/1994
 JP 7031873 A 2/1995
 JP 07-256116 A 10/1995
 JP 8-158033 A 6/1996
 JP 8-215576 A 8/1996
 JP 10-130810 A 5/1998
 JP 10-249198 A 9/1998
 JP 11-502760 A 3/1999
 JP 2000-220978 A 8/2000
 JP 2002-88486 A 3/2002
 JP 2002-241812 A 8/2002
 JP 2002-336688 A 11/2002
 JP 2003-126694 A 5/2003
 JP 2004-233007 A 8/2004
 JP 2004-249206 A 9/2004

JP 2004-290730 A 10/2004
 JP 2005-503250 A 2/2005
 JP 2005-122621 A 5/2005
 JP 2005-218937 A 8/2005
 JP 2005-342615 A 12/2005
 JP 2006-001779 A 1/2006
 JP 2006-508885 A 3/2006
 JP 2006-87965 A 4/2006
 JP 2006-247446 A 9/2006
 JP 2006-260385 A 9/2006
 JP 2006-326554 A 12/2006
 JP 2007-29859 A 2/2007
 JP 2007-44585 A 2/2007
 JP 2007-46162 A 2/2007
 JP 2007-203129 A 8/2007
 SU 493241 3/1976 B01J 11/22
 TW 200611449 4/2006
 TW 201023207 6/2010
 WO WO-96/28577 A1 9/1996
 WO WO 02/092503 A1 11/2002 C01B 21/064
 WO WO-03/094195 A1 11/2003
 WO WO 2004/052778 A2 6/2004 C01B 13/28
 WO WO-2005/063390 A1 7/2005
 WO WO 2006/079213 A1 8/2006 B01J 2/04
 WO WO-2007/144447 A1 12/2007
 WO WO-2008/130451 A2 10/2008
 WO WO-2008/130451 A3 10/2008
 WO WO-2009/017479 A1 2/2009
 WO WO-2011/081833 A1 7/2011
 WO WO-2012/028695 A2 3/2012
 WO WO-2013/028575 A1 2/2013

OTHER PUBLICATIONS

N. Ünal, F. Kern, M.L. Öveçlü, R. Gadov, Influence of WC particles on the microstructural and mechanical properties of 3 mol% Y2O3 stabilized ZrO2 matrix composites produced by hot pressing, *Journal of the European Ceramic Society*, vol. 31, Issue 13, Nov. 2011, pp. 2267-2275.*
 Rahaman, R. A. *Ceramic Processing and Sintering*, New York. Marcel Decker, 1995. Pages 71-77.*
 K. T. Faber, T. Iwagoshi, A. Ghosh, Toughening by Stress-Induced Microcracking in Two-Phase Ceramics, *J. Am. Ceram. Soc.*, vol. 71, Issue 9, Sep. 1988, pp. C-399-C-401.*
 A. Gutsch et al., "Gas-Phase Production of Nanoparticles", *Kona* No. 20, 2002, pp. 24-37.
 Dr. Heike Mühlheweg et al., "Gas-Phase Reactions—Open Up New Roads to Nanoproducts", *Degussa ScienceNewsletter* No. 08, 2004 pp. 12-16.
 Coating Generation: Vaporization of Particles in Plasma Spraying and Splat Formation, M. Vardelle, A. Vardelle, K-I Ii P. Fauchais, *Universite de Limoges*, 123 Avenue A. Thomas 87000, Limoges, F. , *Pure & Chem*, vol. 68, No. 5, pp. 1093-1099, 1996.
 H. Konrad et al., "Nanostructured Cu-Bi Alloys Prepared by Co-Evaporation in a Continuous Gas Flow," *NanoStructured Materials*, vol. 7, No. 6, 1996, pp. 605-610.
 Kenvin et al. "Supported Catalysts Prepared from Mononuclear Copper Complexes: Catalytic Properties", *Journal of Catalysis*, pp. 81-91, (1992).
 J. Heberlein, "New Approaches in Thermal Plasma Technology", *Pure Appl. Chem.*, vol. 74, No. 3, 2002, pp. 327-335.
 M.Vardelle et al., "Experimental Investigation of Powder Vaporization in Thermal Plasma Jets," *Plasma Chemistry and Plasma Processing*, vol. 11, No. 2, Jun. 1991, pp. 185-201.
 National Aeronautics and Space Administration, "Enthalpy", <http://www.grc.nasa.gov/WWW/K-12/airplane/enthalpy.html>, Nov. 23, 2009, 1 page.
 P. Fauchais et al. "Plasma Spray: Study of the Coating Generation," *Ceramics International*, Elsevier, Amsterdam, NL, vol. 22, No. 4, Jan. 1996, pp. 295-303.
 P. Fauchais et al., "Les Dépôts Par Plasma Thermique," *Revue Generale De L'Electricite*, RGE. Paris, FR, No. 2, Jan. 1993, pp. 7-12.
 P. Fauchais et al, "La Projection Par Plasma: Une Revue," *Annales De Physique*, vol. 14, No. 3, Jun. 1989, pp. 261-310.

(56)

References Cited

OTHER PUBLICATIONS

- T. Yoshida, "The Future of Thermal Plasma Processing for Coating", *Pure & Appl. Chem.*, vol. 66, No. 6, 1994 pp. 1223-1230.
- HANet al., Deformation Mechanisms and Ductility of Nanostructured Al Alloys, *Mat. Res. Soc. Symp. Proc.* vol. 821, Jan. 2004, Material Research Society, http://www.mrs.org/s_mrs/bin.asp?CID=2670&DOC=FILE.PDF, 6 pages.
- Nagai, Yasutaka, et al., "Sintering Inhibition Mechanism of Platinum Supported on Ceria-based Oxide and Pt-oxide-support Interaction," *Journal of Catalysis* 24-2 (2006), pp. 103-109, Jul. 3, 2006, Elsevier.
- Derwent English Abstract for publication No. SU 193241 A, Application No. 1973SU1943286 filed on Jul. 2, 1973, published on Mar. 1, 1976, entitled "Catalyst for Ammonia Synthesis Contains Oxides of Aluminum, Potassium, Calcium, Iron and Nickel Oxide for Increased Activity," 3 pgs.
- Bateman, J. E. et al. (Dec. 17, 1998). "Alkylation of Porous Silicon by Direct Reaction with Alkenes and Alkynes," *Angew. Chem Int. Ed.* 37(19):2683-2685.
- Carrot, G. et al. (Sep. 17, 2002). "Surface-Initiated Ring-Opening Polymerization: A Versatile Method for Nanoparticle Ordering," *Macromolecules* 35(22):8400-8404.
- Chen, H.-S. et al. (Jul. 3, 2001). "On the Photoluminescence of Si Nanoparticles," *Mater. Phys. Mech.* 4:62-66.
- Fojtik, A. et al. (Apr. 29, 1994). "Luminescent Colloidal Silicon Particles," *Chemical Physics Letters* 221:363-367.
- Fojtik, A. (Jan. 13, 2006). "Surface Chemistry of Luminescent Colloidal Silicon Nanoparticles," *J. Phys. Chem. B.* 110(5):1994-1998.
- Hua, F. et al. (Mar. 2006). "Organically Capped Silicon Nanoparticles With Blue Photoluminescence Prepared by Hydrosilylation Followed by Oxidation," *Langmuir* 22(9):4363-4370.
- Jouet, R. J. et al. (Jan. 25, 2005). "Surface Passivation of Bare Aluminum Nanoparticles Using Perfluoroalkyl Carboxylic Acids," *Chem. Mater.* 17(11):2987-2996.
- Kim, N. Y. et al. (Mar. 5, 1997). "Thermal Derivatization of Porous Silicon with Alcohols," *J. Am. Chem. Soc.* 119(9):2297-2298.
- Kwon, Y.-S. et al. (Apr. 30, 2003). "Passivation Process for Superfine Aluminum Powders Obtained by Electrical Explosion of Wires," *Applied Surface Science* 211:57-67.
- Langner, A. et al. (Aug. 25, 2005). "Controlled Silicon Surface Functionalization by Alkene Hydrosilylation," *J. Am. Chem. Soc.* 127(37):12798-12799.
- Li, D. et al. (Apr. 9, 2005). "Environmentally Responsive "Hairy" Nanoparticles: Mixed Homopolymer Brushes on Silica Nanoparticles Synthesized by Living Radical Polymerization Techniques," *J. Am. Chem. Soc.* 127(7):6248-6256.
- Li, X. et al. (May 25, 2004). "Surface Functionalization of Silicon Nanoparticles Produced by Laser-Driven Pyrolysis of Silane Followed by HF-HNO₃ Etching," *Langmuir* 20(11):4720-4727.
- Liao, Y.-C. et al. (Jun. 27, 2006). "Self-Assembly of Organic Monolayers on Aerosolized Silicon Nanoparticles," *J. Am. Chem. Soc.* 128(28):9061-9065.
- Liu, S.-M. et al. (Jan. 13, 2006). "Enhanced Photoluminescence from Si Nano-Organosols by Functionalization With Alkenes and Their Size Evolution," *Chem. Mater.* 18(3):637-642.
- Neiner, D. (Aug. 5, 2006). "Low-Temperature Solution Route to Macroscopic Amounts of Hydrogen Terminated Silicon Nanoparticles," *J. Am. Chem. Soc.* 128:11016-11017.
- Netzer, L. et al. (1983). "A New Approach to Construction of Artificial Monolayer Assemblies," *J. Am. Chem. Soc.* 105(3):674-676.
- "Platinum Group Metals: Annual Review 1996" (Oct. 1997). *Engineering and Mining Journal*, p. 63.
- Sailor, M. J. (1997). "Surface Chemistry of Luminescent Silicon Nanocrystallites," *Adv. Mater.* 9(10):783-793.
- Stiles, A. B. (Jan. 1, 1987). "Manufacture of Carbon-Supported Metal Catalysts," in *Catalyst Supports and Supported Catalysts*, Butterworth Publishers, MA, pp. 125-132.
- Subramanian, S. et al. (1991). "Structure and Activity of Composite Oxide Supported Platinum-Iridium Catalysts," *Applied Catalysts* 74: 65-81.
- Tao, Y.-T. (May 1993). "Structural Comparison of Self-Assembled Monolayers of n-Alkanoic Acids on the surfaces of Silver, Copper, and Aluminum," *J. Am. Chem. Soc.* 115(10):4350-4358.
- Zou, J. et al. (Jun. 4, 2004). "Solution Synthesis of Ultrastable Luminescent Siloxane-Coated Silicon Nanoparticles," *Nano Letters* 4(7):1181-1186.
- U.S. Appl. No. 13/291,983, filed Nov. 8, 2011, for Layman et al.
- U.S. Appl. No. 12/152,084, filed May 9, 2008, for Biberger.
- U.S. Appl. No. 13/028,693, filed Feb. 16, 2011, for Biberger.
- U.S. Appl. No. 12/943,909, filed Nov. 10, 2010, for Layman.
- U.S. Appl. No. 12/152,111, filed May 9, 2008, for Biberger et al.
- U.S. Appl. No. 12/151,830, filed May 8, 2008, for Biberger et al.
- U.S. Appl. No. 12/968,248, filed Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/968,245, filed Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/968,241, filed Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/968,239, filed Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/969,128, filed Dec. 15, 2010, for Biberger.
- U.S. Appl. No. 12/962,463, filed Dec. 7, 2010, for Leaman.
- U.S. Appl. No. 12/961,030, filed Dec. 6, 2010, for Lehman.
- U.S. Appl. No. 12/961,108, filed Dec. 6, 2010, for Lehman.
- U.S. Appl. No. 12/961,200, filed Dec. 6, 2010, for Lehman.
- U.S. Appl. No. 12/968,253, filed Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/968,235, filed on Dec. 14, 2010, for Biberger.
- U.S. Appl. No. 12/969,306, filed Dec. 15, 2010, for Lehman et al.
- U.S. Appl. No. 12/969,447, filed Dec. 15, 2010, for Biberger et al.
- U.S. Appl. No. 12/969,087, filed Dec. 15, 2010, for Biberger.
- U.S. Appl. No. 12/962,533, filed Dec. 7, 2010, for Yin et al.
- U.S. Appl. No. 12/001,643, filed Dec. 11, 2007, for Biberger et al.
- U.S. Appl. No. 12/474,081, filed May 28, 2009, for Biberger et al.
- U.S. Appl. No. 12/001,602, filed Dec. 11, 2007, for Biberger et al.
- U.S. Appl. No. 12/001,644, filed Dec. 11, 2007, for Biberger et al.
- U.S. Appl. No. 12/969,457, filed Nov. 15, 2010, for Leamon et al.
- U.S. Appl. No. 12/969,503, filed Nov. 15, 2010, for Leamon et al.
- U.S. Appl. No. 12/954,813, filed Nov. 26, 2010, for Biberger.
- U.S. Appl. No. 12/954,822, filed Nov. 26, 2010, for Biberger.
- U.S. Appl. No. 13/033,514, filed Feb. 23, 2011, for Biberger et al.
- U.S. Appl. No. 13/589,024, filed Aug. 17, 2012, for Yin et al.
- U.S. Appl. No. 13/801,726, filed Mar. 13, 2013, for Qi et al.
- Babin, A. et al. (1985). "Solvents Used in the Arts," *Center for Safety in the Arts*: 16 pages.
- Chen, W.-J. et al. (Mar. 18, 2008). "Functional Fe₃O₄/TiO₂ Core/Shell Magnetic Nanoparticles as Photokilling Agents for Pathogenic Bacteria," *Small* 4(4): 485-491.
- Gangeri, M. et al. (2009). "Fe and Pt Carbon Nanotubes for the Electrocatalytic Conversion of Carbon Dioxide to Oxygenates," *Catalysis Today* 143: 57-63.
- Luo, J. et al. (2008). "Core/Shell Nanoparticles as Electrocatalysts for Fuel Cell Reactions," *Advanced Materials* 20: 4342-4347.
- Mignard, D. et al. (2003). "Methanol Synthesis from Flue-Gas CO₂ and Renewable Electricity: A Feasibility Study," *International Journal of Hydrogen Energy* 28: 455-464.
- Park, H.-Y. et al. (May 30, 2007). "Fabrication of Magnetic Core@Shell Fe Oxide@Au Nanoparticles for Interfacial Bioactivity and Bio-Separation," *Langmuir* 23: 9050-9056.
- Park, N.-G. et al. (Feb. 17, 2004). "Morphological and Photoelectrochemical Characterization of Core-Shell Nanoparticle Films for Dye-Sensitized Solar Cells: Zn-O Type Shell on SnO₂ and TiO₂ Cores," *Langmuir* 20: 4246-4253.
- "Plasma Spray and Wire Flame Spray Product Group," located at <http://www.processmaterials.com/spray.html>, published by Process Materials, Inc., last accessed Aug. 5, 2013, 2 pages.
- Ahmad, K. et al. (2008). "Hybrid Nanocomposites: A New Route Towards Tougher Alumina Ceramics," *Composites Science and Technology* 68: 1321-1327.
- Chaim, R. et al. (2009). "Densification of Nanocrystalline Y₂O₃ Ceramic Powder by Spark Plasma Sintering," *Journal of European Ceramic Society* 29: 91-98.
- Chau, J. K. H. et al. (2005). "Microwave Plasma Synthesis of Silver Nanopowders," *Materials Letters* 59: 905-908.

(56)

References Cited

OTHER PUBLICATIONS

Das, N. et al. (2001). "Influence of the Metal Function in the "One-Pot" Synthesis of 4-Methyl-2-Pentanone (Methyl Isobutyl Ketone) from Acetone Over Palladium Supported on Mg(Al)O Mixed Oxides Catalysts," *Catalysis Letters* 71(3-4): 181-185.

Lakis, R. E. et al. (1995). "Alumina-Supported Pt-Rh Catalysts: I. Microstructural Characterization," *Journal of Catalysis* 154: 261-275.

Schimpf, S. et al. (2002). "Supported Gold Nanoparticles: In-Depth Catalyst Characterization and Application in Hydrogenation and Oxidation Reactions," *Catalysis Today* 2592: 1-16.

Viswanathan, V. et al. (2006). "Challenges and Advances in Nanocomposite Processing Techniques," *Materials Science and Engineering R* 54: 121-285.

Wan, J. et al. (2005). "Spark Plasma Sintering of Silicon Nitride/Silicon Carbide Nanocomposites with Reduced Additive Amounts," *Scripta Materialia* 53: 663-667.

* cited by examiner




Fig. 1




Fig. 2




Fig. 3

1**FRACTURE TOUGHNESS OF GLASS****CROSS-REFERENCE TO RELATED APPLICATIONS**

This application claims priority to U.S. Provisional Patent Application Ser. No. 61/284,329, filed Dec. 15, 2009 and entitled "MATERIALS PROCESSING," which is hereby incorporated herein by reference in its entirety as if set forth herein.

FIELD OF THE INVENTION

The present invention relates to the field of materials science. More particularly, the present invention relates to glass manufactures and a novel method of making

BACKGROUND

In many applications, glass is utilized because of the desired properties such as transparency and light transmission. Many household products are made of glass and glass has many decorative functions. Glass is also used widely in buildings and automobiles just to name a few more applications. Glass can be reinforced with some kind of particulate matter. Composite glass is desirable since in addition to their high hardness the composite can also possess a greater fracture toughness, which includes the ability to resist fracture. Present methods used to produce composite glass are costly, inefficient and complicated.

Accordingly, it is desirable to create an efficient and inexpensive method to produce glass having improve material characteristics, and especially fracture toughness.

SUMMARY OF THE INVENTION

Other features of the present invention will become apparent from consideration of the following description taken in conjunction with the accompanying drawings.

A first aspect of the present invention is for a method of making glass is provided. The method comprises preparing a dispersion of a nano-material. A slurry of a glass matrix material is prepared. The nano-dispersion is mixed with the matrix slurry to form a nano-dispersion/slurry mixture. In one embodiment, the mixing includes pouring the matrix slurry into the nano-dispersion while agitating. Alternative, the mixing includes pouring the nano-dispersion into the matrix slurry while agitating. The nano-dispersion/slurry mixture is dried. The nano-dispersion/slurry mixture is pressed into a final manufacture comprising a molecular structure including the nano-material bonded within and uniformly distributed throughout the molecular structure. The manufacture comprises an increased fracture toughness compared with a conventional manufacture produced without bonding the nano-material within the molecular structure.

The method includes providing the nano-material with a size on the order of tens of nanometers before the dispersion preparing step. A micron sized matrix material is provided on the order of several micrometers before the slurry preparing step. One percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion. Alternatively, 0.5-10.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion. In yet another alternative, 0.5-20.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion. Sintering is performed on the final form using a sintering process following the pressing step. The sintering process includes a hot isostatic pressing pro-

2

cess. The manufacture includes the nano-material bonded at triple points of the molecular structure. The drying of the nano-dispersion/slurry mixture includes a spray drying process.

Other features of the present invention will become apparent from consideration of the following description taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The novel features of the invention are set forth in the appended claims. However, for purposes of explanation, several embodiments of the invention are set forth in the following figures.

FIG. 1 illustrates a plot of fracture toughness of a glass compared with a metal in accordance with an embodiment of the invention.

FIG. 2 illustrates a partial of a manufacture with improved fracture toughness in accordance with an embodiment of the invention.

FIG. 3 illustrates a method of making a glass with improved fracture toughness in accordance with an embodiment of the invention.

DETAILED DESCRIPTION

In the following description, numerous details and alternatives are set forth for the purpose of explanation. However, one of ordinary skill in the art will realize that the invention can be practiced without the use of these specific details. In other instances, well-known structures and devices are shown in block diagram form in order not to obscure the description of the invention with unnecessary detail.

Turning to FIG. 1, a plot 10 of fracture toughness of a glass compared with a metal is shown in accordance with an embodiment of the invention. Fracture toughness is a term in the field of material science that describes the characteristic of a material that has a crack to resist fracture. More specifically, fracture toughness describes a resistance of a material to a brittle fracture when a crack is present in the material. Brittle fracture occurs when the material exhibits no apparent plastic deformation prior to the fracture, in contrast to a ductile fracture, which is when the material exhibits extensive plastic deformation prior to the fracture. A glass will exhibit a low fracture toughness 12A while a metal will exhibit a significantly higher fracture toughness 12B. A novel method of the invention as described below produces a glass having an increased fracture toughness 12A'.

Hardness is a quality also shown in the plot of FIG. 1. Hardness is a term that describes the characteristic of a solid material to resist deformation. A metal will exhibit a low hardness 14A while a glass will exhibit a significantly higher hardness 14B.

Turning to FIG. 2, a partial of a manufacture 200 with improved fracture toughness is shown in accordance with an embodiment of the invention. The manufacture 200 comprises a composite of a glass matrix material 201 and nanoparticles or nano-material 206. The glass material 201 can comprise any a number of suitable glass materials depending on a particular application. In an exemplary embodiment the glass material 201 comprises a material from a group of silicon dioxide composites. A person of skill will appreciate the many possible oxides capable of combining with silicon dioxide to form the glass material. In one embodiment, the silicon dioxide composite can comprise silicon dioxide combined with a mixture of sodium carbonate, and either calcium carbonate or calcium oxide. In an alternative embodiment, the

silicon dioxide composite can comprise silicon dioxide combined with boric oxide. In yet another embodiment, the silicon dioxide composite can comprise silicon dioxide combined with lead oxide.

Alternatively, the glass material **201** can comprise pure Silica or silicon dioxide (SiO₂). In still another embodiment, the glass material can comprise a metallic glass. Examples of metallic glass alloys include alloys based on zirconium or palladium. The method as described in detail below produces the manufacture **200** in a final form that includes a “granular” or a molecular structure **204** having an amorphous disordered structure propagated throughout the manufacture **200**. The molecular structure **204** comprises an average molecular boundary distance or diameter **208** of one to several micrometers. Preferably, the average molecular diameter **208** equals approximately one micrometer.

The nano-material **206** can comprise any a number of suitable materials that are non-miscible with the glass material **201** depending on a particular application. In an exemplary embodiment, the nano-material **206** can comprise a metallic material or a nano-metal. Examples of suitable metallic materials can include copper, silver and gold. A person of skill can appreciate that other metallic materials can also be suitable for the nano-material **206**. Alternatively, the suitable metallic material can comprise a metallic compound. In an alternative embodiment, the nano-material **206** comprises a material from a group of non-oxide ceramics. Examples of suitable non-oxide ceramics can include titanium carbide or titanium diboride. In yet another embodiment, the nano-material **206** can comprise an oxide ceramic material that is non-miscible with the glass matrix material **201**, for example, alumina and zirconia. A person of skill will appreciate an effect of the nano-material **206** on a refractive index and a transparent quality of the manufacture **200**. Thus the nano-material **206** can be chosen such that refractive indexes of the nano-material **206** and the glass matrix material **201** are equal.

The novel method of the invention produces the manufacture **200** having nanoparticles **206** bonded within the molecular structure **204**. The nanoparticles **206** are bonded within the molecular structure **204** of the glass material **201**. A surface **202** of the manufacture **200** reveals that the nanoparticles **206** are substantially uniformly distributed throughout the molecular structure **204**. Additionally, the manufacture **200** includes the nanoparticles **206** substantially uniformly distributed throughout a three dimensional mass of the manufacture **200**. A novel result of the method includes the nanoparticles **206** substantially uniformly distributed where three or more interfaces intersect or at triple points **210** of the glass material **201**. Preferably, the nanoparticles **206** comprise an average diameter suitable for bonding within the molecular structure **204** of the glass material **201**. In an exemplary embodiment, the nanoparticles **206** have an average diameter of approximately 1 to 40 nm. Preferably, the average diameter of the nanoparticles **206** is 20 nm+/-10 nm.

Turning to FIG. 3, a method is shown for making a glass with improved fracture toughness in accordance with an embodiment of the invention. The method step **310** comprises providing a quantity of nanoparticles **206** which are suitable for bonding with glass material. The nanoparticles **206** preferably comprise an average diameter of 5-15 nm+/-4 nm. The nanoparticles **206** can be in the form of a powder. Any suitable method of providing the nanoparticles **206** known to a person of skill can be used. Such methods can include attrition of some kind. For example, ball milling or feeding micron sized material into a plasma process such as described and claimed in the co-owned and co-pending application Ser. No. 11/110,

341, filed Apr. 19, 2005, and titled “High Throughput Discovery of Materials Through Vapor Phase Synthesis,” which is incorporated herein by reference. The method step **320** comprises providing a quantity of glass matrix material **201**.

The matrix material **201** comprises an average grain diameter of 500-600 nm. Alternatively, the matrix material **201** can comprise an average grain diameter of one micrometer. The matrix material **201** typically comprises a powdered substance. The matrix material **201** can comprise a form of miniature beads or spheres.

The method step **330** comprises preparing a dispersion **332** of the nanoparticles **206** of the step **310**. The dispersion **332** comprises a suspension of the nanoparticles **206** in a suitable liquid or suspension liquid. The nanoparticles **206** can comprise a nano-metal with an average diameter of 5-15 nm+/-4 nm. The nanoparticles **206** can comprise 0.5-20% of the dispersion **332**. Alternatively, the nanoparticles **206** can comprise 0.5-10% of the dispersion **332**. In another alternative, the nanoparticles **206** can comprise approximately 1.0% of the dispersion **332**. In an exemplary embodiment, the suspension liquid comprises water and a surfactant. The surfactant can comprise ten percent of the suspension liquid. Any suitable surfactant can be used. Such surfactants are manufactured by Lubrizol Corporation. In an alternative embodiment, a wetting agent can also be included in the suspension liquid. The wetting agent can be five percent relative to water of the suspension liquid. Alternatively, the suspension liquid comprises an alcohol. Other liquids known to a person of skill can also be utilized. The dispersion **332** comprises a pH suitable for best mixing results with a slurry **342** of the step **340**. In an exemplary embodiment, the pH of the dispersion **332** comprises a base. In another embodiment, the base pH comprises a 7.5 pH.

A feature of the method of the invention contemplates that the dispersion **332** comprises a substantially uniform distribution of the nanoparticles **206** within the liquid. The uniform dispersion **332** facilitates a uniform diameter of the nanoparticles **206** in the suspension and prevents a forming of large aggregations of the nanoparticles **206**. A high concentration of large aggregations of nanoparticles **206** inhibit the desired uniform distribution of the nanoparticles **206** within the molecular structure **204** of the manufacture **200**.

The method step **340** comprises preparing a slurry **342** of the glass matrix material **201** of the step **320**. The slurry **342** preferably comprises a viscous suspension of the glass matrix material **201** in a suitable liquid. The glass matrix material **201** can comprise SiO₂ with an average diameter of 500-600 nm. The glass matrix material **201** can comprise 50% of the slurry **342**. In an exemplary embodiment, the suspension liquid comprises water. Other liquids known to a person of skill can also be utilized. The slurry **342** can include various additives or binders that facilitate a mixing, a drying, a melting and a sintering step described later below. The slurry **342** comprises a pH suitable for best mixing results with the dispersion **332**. In an exemplary embodiment, the pH of the slurry **342** comprises a base. In one embodiment, the base pH comprises an 8.0-9.0 pH. In another embodiment, the base pH comprises an 11.0 pH.

The method step **350** comprises mixing the nano-dispersion **332** with the matrix slurry **342** to form a nano-dispersion/slurry mixture **352**. The mixing of the nano-dispersion/slurry mixture **352** can comprise suitable agitation methods known to a person of skill. The mixing of the nano-dispersion/slurry mixture **352** produces a dispersion of the nanoparticles **206** within the matrix slurry so that the nanoparticles **206** are uniformly distributed throughout the nano-dispersion/slurry mixture **352**. In an exemplary embodiment, the mixing com-

5

prises slowly pouring the slurry 342 into the dispersion 332. Preferably, the nano-dispersion/slurry mixture 352 is sonicated during the pouring of the slurry 342. A sonicating horn can be dipped in the dispersion 332 while pouring the slurry 342. A stir bar can optionally be placed in the dispersion 332 during the pouring of the slurry 342. The stir bar can be used to agitate the nano-dispersion/slurry mixture 352 while pouring the slurry 342. The percentage of the nano-dispersion/slurry mixture 352 that comprises the nano-dispersion 332 can vary between 0.5% to 20%. Alternatively, the nano-dispersion/slurry mixture 352 comprises 0.5% to 10% of the nano-dispersion 332. In another alternative, the nano-dispersion/slurry mixture 352 comprises 0.5% to 3.0% of the nano-dispersion 332.

In an alternative embodiment, the mixing comprises slowly pouring the dispersion 332 into the slurry 342. The nano-dispersion/slurry mixture 352 is sonicated during the pouring of the dispersion 332. A sonicating horn can be dipped in the slurry 342 while pouring the dispersion 332. A stir bar can be placed in the slurry 342 during the pouring of the dispersion 332. The stir bar can be used to agitate the nano-dispersion/slurry mixture 352 while pouring the dispersion 332. Other mixing techniques known to a person of skill the art can be substituted for the mixing and agitation described above.

In one embodiment, the various additives or binders that facilitate mixing, drying and sintering can be added to the slurry 342 before the mixing step of step 350. Alternatively, the additives or binders can be added to the nano-dispersion/slurry mixture 352 after the mixing step 350.

The method step 360 comprises drying the nano-dispersion/slurry mixture 352. In an exemplary embodiment, a spray drying process is utilized to dry the nano-dispersion/slurry mixture 352. The spray drying process comprises loading a spray gun and spraying the nano-dispersion/slurry mixture 352 into a closed compartment, for example, a glove box. The nano-dispersion/slurry mixture 352 is sprayed within the compartment and then allowed to dry. As the drying process proceeds, appreciable amounts of the liquid of the nano-dispersion/slurry mixture 352 evaporate to result in a powdered form or a premanufacture 368. In an alternative embodiment, the method step 360 comprises a freeze drying process. Freeze drying comprises placing the nano-dispersion/slurry mixture 352 into a freeze dryer and allowing the liquid of the nano-dispersion/slurry mixture 352 to evaporate until what results comprises the powdered form or the premanufacture 368.

The process step 365 comprises the premanufacture 368 which is the result of the drying step 360. The premanufacture 368 comprises the nanoparticles 206 uniformly distributed throughout the glass matrix material 201.

The method step 370 comprises a process to make the powdered premanufacture 368 a melt. Making the powdered premanufacture 368 a melt comprises placing the powdered premanufacture 368 of the method step 365 into a mold and pressing the powdered premanufacture 368 to form a molded premanufacture 372. Heat is also applied to the molded premanufacture 372 sufficient to liquify and integrate the nanoparticles 206 with the matrix material 201. A person of skill will choose any suitable method of heating the molded premanufacture 372 to cause liquidisation. The molded premanufacture 372 is allowed to cool.

The method step 380 comprises a process of sintering the molded premanufacture 372. The sintering process comprises using any of a variety of sintering processes. In an exemplary embodiment, the sintering process comprises a hot isostatic pressing (HIP) process. The hot isostatic pressing comprises

6

placing the molded premanufacture 372 into a HIP furnace where the molded premanufacture 372 is heated under pressure. The HIP process facilitates a removal of porosity within the molded premanufacture 372. In an alternative embodiment, a liquid phase sintering process as practiced in the art can be used for the method step 380. In yet another embodiment, a simple hot pressing process as practiced in the art can be used.

Referring back to FIG. 2, a result of the method 300 comprises the manufacture 200 with improved fracture toughness in accordance with an embodiment of the invention. The manufacture 200 comprises a composite of a glass material 201 and nanoparticles or nano-material 206. The novel feature of the method 300 produces the manufacture 200 comprising the nanoparticles 206 uniformly distributed throughout the glass material 201.

While the invention has been described with reference to numerous specific details, one of ordinary skill in the art will recognize that the invention can be embodied in other specific forms without departing from the spirit of the invention. Thus, one of ordinary skill in the art will understand that the invention is not to be limited by the foregoing illustrative details, but rather is to be defined by the appended claims.

25 What is claimed is:

1. A method of making glass comprising:

providing a plasma created nano-material with an average diameter of 1-15 nanometers;

preparing a dispersion of the nano-material;

30 preparing a slurry of a glass matrix material;

mixing the nano-dispersion with the matrix slurry to form a nano-dispersion/slurry mixture;

drying the nano-dispersion/slurry mixture; and

35 pressing the nano-dispersion/slurry mixture into a final manufacture comprising a molecular structure including the nano-material bonded within and uniformly distributed throughout the molecular structure.

2. The method of claim 1, wherein the mixing comprises pouring the slurry into the dispersion while agitating the nano-dispersion/slurry mixture.

3. The method of claim 1, wherein the mixing comprises pouring the dispersion into the slurry while agitating the nano-dispersion/slurry mixture.

4. The method of claim 1, further comprising providing a micron sized matrix material having an average grain size greater than or equal to 1 micrometer before the slurry preparing step.

5. The method of claim 1, wherein one percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

6. The method of claim 1, wherein 0.5-10.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

7. The method of claim 1, wherein 0.5-20.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

8. The method of claim 1, further comprising sintering the final form using a sintering process following the pressing step.

9. The method of claim 8, wherein the sintering process comprises a hot isostatic pressing process.

10. The method of claim 1, wherein the manufacture includes the nano-material bonded at triple points of the molecular structure.

65 11. The method of claim 1, wherein the drying of the nano-dispersion/slurry mixture comprises a spray drying process.

7

12. The method of claim 1, wherein the drying of the nano-dispersion/slurry mixture comprises a freeze drying process.

13. The method of claim 1, wherein the nano-material comprises a non-oxide ceramic material.

14. The method of claim 1, wherein the nano-material comprises an oxide ceramic material that is nonmiscible with the glass matrix material.

15. A method of making glass comprising:

providing a plasma created metallic nano-material with an average diameter of 1-15 nanometers;

preparing a dispersion of the metallic nano-material;

preparing a slurry of a glass matrix material;

mixing the nano-dispersion with the matrix slurry to form a nano-dispersion/slurry mixture;

drying the nano-dispersion/slurry mixture; and

pressing the nano-dispersion/slurry mixture into a final manufacture comprising a molecular structure including the nano-material bonded within and uniformly distributed throughout the molecular structure.

16. The method of claim 15, wherein the mixing comprises pouring the slurry into the dispersion while agitating the nano-dispersion/slurry mixture.

17. The method of claim 15, wherein the mixing comprises pouring the dispersion into the slurry while agitating the nano-dispersion/slurry mixture.

8

18. The method of claim 15, further comprising providing a micron sized matrix material having an average grain size greater than or equal to 1 micrometer before the slurry preparing step.

19. The method of claim 15, wherein one percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

20. The method of claim 15, wherein 0.5-10.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

21. The method of claim 15, wherein 0.5-20.0 percent of the nano-dispersion/slurry mixture comprises the nano-material dispersion.

22. The method of claim 15, further comprising sintering the final form using a sintering process following the pressing step.

23. The method of claim 22, wherein the sintering process comprises a hot isostatic pressing process.

24. The method of claim 15, wherein the manufacture includes the nano-material bonded at triple points of the molecular structure.

25. The method of claim 15, wherein the drying of the nano-dispersion/slurry mixture comprises a spray drying process.

26. The method of claim 15, wherein the drying of the nano-dispersion/slurry mixture comprises a freeze drying process.

* * * * *