



US009050678B2

(12) **United States Patent**
Daniel et al.

(10) **Patent No.:** **US 9,050,678 B2**
(45) **Date of Patent:** **Jun. 9, 2015**

(54) **SYSTEMS, METHODS, AND APPARATUSES FOR MONITORING WELD QUALITY**

(58) **Field of Classification Search**
None
See application file for complete search history.

(71) Applicant: **Lincoln Global, Inc.**, City of Industry, CA (US)

(56) **References Cited**

(72) Inventors: **Joseph A. Daniel**, Sagamore Hills, OH (US); **Bruce J. Chantry**, Solon, OH (US)

U.S. PATENT DOCUMENTS

(73) Assignee: **Lincoln Global, Inc.**, City of Industry, CA (US)

1,159,119	A	11/1915	Springer
D140,630	S	3/1945	Garibay
D142,377	S	9/1945	Dunn
D152,049	S	12/1948	Welch
2,681,969	A	6/1954	Burke
D174,208	S	3/1955	Abidgaard

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(Continued)

(21) Appl. No.: **14/044,995**

CN	201083660	7/2008
CN	101419755	4/2009

(22) Filed: **Oct. 3, 2013**

(Continued)

(65) **Prior Publication Data**

FOREIGN PATENT DOCUMENTS

US 2014/0038143 A1 Feb. 6, 2014

OTHER PUBLICATIONS

SIMFOR / CESOL, "RV-SOLD" Welding Simulator, Technical and Functional Features, 20 pages, no date available.

(Continued)

Related U.S. Application Data

(62) Division of application No. 12/775,729, filed on May 7, 2010, now Pat. No. 8,569,646.

Primary Examiner — David Vu

Assistant Examiner — Cuong B Nguyen

(60) Provisional application No. 61/261,079, filed on Nov. 13, 2009.

(74) *Attorney, Agent, or Firm* — Calfee, Halter and Griswold LLP


(51) **Int. Cl.**
B23K 31/02 (2006.01)
B23K 9/095 (2006.01)
B23K 31/12 (2006.01)
G09B 19/24 (2006.01)

(57) **ABSTRACT**

An arc welder including an integrated monitor is disclosed. The monitor is capable of monitoring variables during a welding process and weighting the variables accordingly, quantifying overall quality of a weld, obtaining and using data indicative of a good weld, improving production and quality control for an automated welding process, teaching proper welding techniques, identifying cost savings for a welding process, and deriving optimal welding settings to be used as pre-sets for different welding processes or applications.

(52) **U.S. Cl.**
 CPC **B23K 9/095** (2013.01); **B23K 9/0953** (2013.01); **B23K 31/12** (2013.01); **B23K 9/0956** (2013.01); **B23K 31/02** (2013.01); **G09B 19/24** (2013.01)

14 Claims, 16 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2,728,838	A	12/1955	Barnes	6,049,059	A	4/2000	Kim
D176,942	S	2/1956	Cross	6,051,805	A	4/2000	Vaidya et al.
2,894,086	A	7/1959	Rizer	6,155,475	A	12/2000	Ekelof et al.
3,035,155	A	5/1962	Hawk	6,155,928	A	12/2000	Burdick
3,059,519	A	10/1962	Stanton	6,236,013	B1	5/2001	Delzenne
3,356,823	A	12/1967	Waters	6,236,017	B1	5/2001	Smartt et al.
3,555,239	A	1/1971	Kerth	6,242,711	B1	6/2001	Cooper
3,621,177	A	11/1971	McPherson et al.	6,271,500	B1	8/2001	Hirayama et al.
3,654,421	A	4/1972	Streetman et al.	6,330,938	B1	12/2001	Herve et al.
3,739,140	A	6/1973	Rotilio	6,330,966	B1	12/2001	Eissfeller
3,866,011	A	2/1975	Cole	6,331,848	B1	12/2001	Stove et al.
3,867,769	A	2/1975	Schow et al.	D456,428	S	4/2002	Aronson et al.
3,904,845	A	9/1975	Minkiewicz	D456,828	S	5/2002	Aronson et al.
D243,459	S	2/1977	Bliss	D461,383	S	8/2002	Blackburn
4,024,371	A	5/1977	Drake	6,441,342	B1	8/2002	Hsu
4,041,615	A	8/1977	Whitehill	6,445,964	B1	9/2002	White et al.
D247,421	S	3/1978	Driscoll	6,506,997	B2	1/2003	Matsuyama
4,124,944	A	11/1978	Blair	6,552,303	B1	4/2003	Blankenship et al.
4,132,014	A	1/1979	Schow	6,560,029	B1	5/2003	Dobbie et al.
4,237,365	A	12/1980	Lambros et al.	6,568,846	B1	5/2003	Cote et al.
4,280,041	A	7/1981	Kiessling et al.	D475,726	S	6/2003	Suga et al.
4,280,137	A	7/1981	Ashida et al.	6,572,379	B1	6/2003	Sears et al.
4,314,125	A	2/1982	Nakamura	6,583,386	B1	6/2003	Ivkovich
4,375,026	A	2/1983	Kearney	6,621,049	B2	9/2003	Suzuki
4,410,787	A	10/1983	Kremers	6,624,388	B1	9/2003	Blankenship et al.
4,429,266	A	1/1984	Traadt	D482,171	S	11/2003	Vui et al.
4,452,589	A	6/1984	Denison	6,647,288	B2	11/2003	Madill et al.
D275,292	S	8/1984	Bouman	6,649,858	B2	11/2003	Wakeman
D277,761	S	2/1985	Korovin et al.	6,655,645	B1	12/2003	Lu et al.
D280,329	S	8/1985	Bouman	6,660,965	B2	12/2003	Simpson
4,611,111	A	9/1986	Baheti et al.	6,697,701	B2	2/2004	Hillen et al.
4,616,326	A	10/1986	Meier et al.	6,697,770	B1	2/2004	Nagetgall
4,629,860	A	12/1986	Lindbom	6,703,585	B2	3/2004	Suzuki
4,677,277	A	6/1987	Cook et al.	6,708,385	B1	3/2004	Lemelson
4,680,014	A	7/1987	Paton	6,710,298	B2	3/2004	Eriksson
4,689,021	A	8/1987	Vasiliev et al.	6,710,299	B2	3/2004	Blankenship et al.
4,707,582	A	11/1987	Beyer	6,715,502	B1	4/2004	Rome et al.
4,716,273	A	12/1987	Paton et al.	D490,347	S	5/2004	Meyers
D297,704	S	9/1988	Bulow	6,734,393	B1	5/2004	Friedl et al.
4,867,685	A	9/1989	Brush et al.	6,744,011	B1	6/2004	Hu et al.
4,877,940	A	10/1989	Bangs et al.	6,750,428	B2	6/2004	Okamoto
4,897,521	A	1/1990	Burr	6,772,802	B2	8/2004	Few
4,907,973	A	3/1990	Hon	6,788,442	B1	9/2004	Potin et al.
4,931,018	A	6/1990	Herbst et al.	6,795,778	B2	9/2004	Dodge et al.
4,998,050	A	3/1991	Nishiyama et al.	6,798,974	B1	9/2004	Nakano et al.
5,061,841	A	10/1991	Richardson	6,857,553	B1	2/2005	Hartman et al.
5,089,914	A	2/1992	Prescott	6,858,817	B2	2/2005	Blankenship et al.
5,192,845	A	3/1993	Kirmsse et al.	D504,449	S	4/2005	Butchko
5,206,472	A	4/1993	Myking et al.	6,920,371	B2	7/2005	Hillen et al.
5,266,930	A	11/1993	Ichikawa et al.	6,940,039	B2	9/2005	Blankenship et al.
5,305,183	A	4/1994	Teynor	7,021,937	B2	4/2006	Simpson et al.
5,320,538	A	6/1994	Baum	7,132,617	B2	11/2006	Lee et al.
5,337,611	A	8/1994	Fleming et al.	7,170,032	B2	1/2007	Flood
5,360,156	A	11/1994	Ishizaka et al.	7,194,447	B2	3/2007	Harvey et al.
5,360,960	A	11/1994	Shirk	7,247,814	B2	7/2007	Ott
5,370,071	A	12/1994	Ackermann	D555,446	S	11/2007	Ibarrondo et al.
D359,296	S	6/1995	Witherspoon	D561,973	S	2/2008	Kinsley et al.
5,424,634	A	6/1995	Goldfarb et al.	7,353,715	B2	4/2008	Myers
5,436,638	A	7/1995	Bolas et al.	7,363,137	B2	4/2008	Brant et al.
5,464,957	A	11/1995	Kidwell	7,375,304	B2	5/2008	Kainec et al.
D365,583	S	12/1995	Viken	7,381,923	B2	6/2008	Gordon et al.
5,562,843	A	10/1996	Yasumoto	7,414,595	B1	8/2008	Muffler
5,670,071	A	9/1997	Ueyama et al.	7,465,230	B2	12/2008	LeMay et al.
5,676,503	A	10/1997	Lang	D587,975	S	3/2009	Aronson et al.
5,676,867	A	10/1997	Van Allen	7,516,022	B2	4/2009	Lee et al.
5,708,253	A	1/1998	Bloch et al.	D602,057	S	10/2009	Osicki
D392,534	S	3/1998	Degen	D606,102	S	12/2009	Bender et al.
5,728,991	A	3/1998	Takada et al.	7,643,890	B1	1/2010	Hillen et al.
5,751,258	A	5/1998	Ferguson et al.	7,687,741	B2	3/2010	Kainec et al.
D396,238	S	7/1998	Schmitt	D614,217	S	4/2010	Peters et al.
5,781,258	A	7/1998	Dabral et al.	D615,573	S	5/2010	Peters et al.
5,823,785	A	10/1998	Matherne, Jr.	D631,074	S	1/2011	Peters et al.
5,835,277	A	11/1998	Hegg	7,874,921	B2	1/2011	Baszucki et al.
5,845,053	A	12/1998	Watanabe	7,970,172	B1	6/2011	Hendrickson
6,008,470	A	12/1999	Zhang	7,991,587	B2	8/2011	Ihn
				8,069,017	B2	11/2011	Hallquist
				8,265,886	B2	9/2012	Bisiauz et al.
				8,274,013	B2	9/2012	Wallace
				8,363,048	B2	1/2013	Gering

(56)

References Cited

U.S. PATENT DOCUMENTS

8,365,603 B2 2/2013 Lesage et al.
 8,569,646 B2 10/2013 Daniel et al.
 8,777,629 B2 7/2014 Kreindl et al.
 2001/0045808 A1 11/2001 Hietmann et al.
 2002/0032553 A1 3/2002 Simpson et al.
 2002/0046999 A1 4/2002 Veikkolainen
 2002/0085843 A1 7/2002 Mann
 2003/0000931 A1 1/2003 Ueda
 2003/0023592 A1 1/2003 Modica et al.
 2003/0025884 A1 2/2003 Hamana et al.
 2003/0111451 A1 6/2003 Blankenship et al.
 2003/0172032 A1 9/2003 Choquet
 2003/0234885 A1 12/2003 Pilu
 2004/0020907 A1 2/2004 Zauner et al.
 2004/0035990 A1 2/2004 Ackeret
 2004/0050824 A1 3/2004 Samler
 2004/0140301 A1 7/2004 Blankenship et al.
 2005/0007504 A1 1/2005 Fergason
 2005/0017152 A1 1/2005 Fergason
 2005/0103766 A1 5/2005 Iizuka et al.
 2005/0103767 A1 5/2005 Kainec et al.
 2005/0109735 A1 5/2005 Flood
 2005/0128186 A1 6/2005 Shahoian et al.
 2005/0133488 A1 6/2005 Blankenship et al.
 2005/0159840 A1 7/2005 Lin et al.
 2005/0189336 A1 9/2005 Ku
 2005/0199602 A1 9/2005 Kaddani et al.
 2005/0230573 A1 10/2005 Ligertwood
 2005/0252897 A1 11/2005 Hsu
 2005/0275913 A1 12/2005 Vesely et al.
 2005/0275914 A1 12/2005 Vesely et al.
 2006/0014130 A1 1/2006 Weinstein
 2006/0136183 A1 6/2006 Choquet
 2006/0163227 A1 7/2006 Hillen et al.
 2006/0169682 A1 8/2006 Kainec et al.
 2006/0173619 A1 8/2006 Brant et al.
 2006/0207980 A1 9/2006 Jacovetty et al.
 2006/0213892 A1 9/2006 Ott
 2006/0214924 A1 9/2006 Kawamoto et al.
 2006/0226137 A1 10/2006 Huismann et al.
 2006/0258447 A1 11/2006 Baszucki et al.
 2007/0034611 A1 2/2007 Drius et al.
 2007/0038400 A1 2/2007 Lee et al.
 2007/0045488 A1 3/2007 Shin
 2007/0088536 A1 4/2007 Ishikawa
 2007/0198117 A1 8/2007 Wajihuddin
 2007/0211026 A1 9/2007 Ohta
 2007/0221797 A1 9/2007 Thompson et al.
 2007/0256503 A1 11/2007 Wong et al.
 2007/0277611 A1 12/2007 Portzgen et al.
 2007/0291035 A1 12/2007 Vesely et al.
 2008/0038702 A1 2/2008 Choquet
 2008/0078811 A1 4/2008 Hillen et al.
 2008/0078812 A1 4/2008 Peters et al.
 2008/0117203 A1 5/2008 Gering
 2008/0128398 A1 6/2008 Schneider
 2008/0135533 A1 6/2008 Ertmer et al.
 2008/0140815 A1 6/2008 Brant et al.
 2008/0149686 A1 6/2008 Daniel et al.
 2008/0203075 A1 8/2008 Feldhausen et al.
 2008/0233550 A1 9/2008 Solomon
 2008/0314887 A1 12/2008 Stoger
 2009/0015585 A1 1/2009 Klusza
 2009/0045183 A1 2/2009 Artelsmair et al.
 2009/0057286 A1 3/2009 Ihara
 2009/0152251 A1 6/2009 Dantinne et al.
 2009/0173726 A1 7/2009 Davidson et al.
 2009/0184098 A1 7/2009 Daniel et al.
 2009/0200281 A1 8/2009 Hampton
 2009/0200282 A1 8/2009 Hampton
 2009/0231423 A1 9/2009 Becker
 2009/0298024 A1* 12/2009 Batzler et al. 434/234
 2009/0325699 A1 12/2009 Delgiannidis
 2010/0012017 A1 1/2010 Miller
 2010/0012637 A1 1/2010 Jaeger

2010/0048273 A1 2/2010 Wallace et al.
 2010/0062405 A1 3/2010 Zboray et al.
 2010/0062406 A1 3/2010 Zboray et al.
 2010/0096373 A1 4/2010 Hillen et al.
 2010/0133247 A1 6/2010 Mazumder et al.
 2010/0133250 A1 6/2010 Sardy et al.
 2010/0176107 A1 7/2010 Bong
 2010/0201803 A1 8/2010 Melikian
 2010/0224610 A1 9/2010 Wallace
 2010/0276396 A1 11/2010 Cooper et al.
 2010/0299101 A1 11/2010 Shimada et al.
 2010/0307249 A1 12/2010 Lesage et al.
 2011/0006047 A1 1/2011 Penrod et al.
 2011/0060568 A1 3/2011 Goldfine et al.
 2011/0091846 A1 4/2011 Kreindl et al.
 2011/0114615 A1 5/2011 Daniel et al.
 2011/0116076 A1 5/2011 Chantry et al.
 2011/0117527 A1 5/2011 Conrardy et al.
 2011/0122495 A1 5/2011 Togashi
 2011/0183304 A1 7/2011 Wallace et al.
 2012/0189993 A1 7/2012 Kindig et al.
 2013/0026150 A1 1/2013 Chantry et al.
 2013/0189657 A1 7/2013 Wallace et al.
 2013/0189658 A1 7/2013 Peters et al.

FOREIGN PATENT DOCUMENTS

CN 201229711 4/2009
 CN 101571887 11/2009
 CN 101587659 11/2009
 DE 2833638 2/1980
 DE 3046634 1/1984
 DE 3244307 5/1984
 DE 3522581 1/1987
 DE 4037879 6/1991
 DE 19615069 10/1997
 DE 19739720 10/1998
 DE 19834205 2/2000
 DE 20009543 8/2001
 DE 102005047204 4/2007
 DE 102010038902 9/2012
 EP 108599 5/1984
 EP 127299 12/1984
 EP 145891 6/1985
 EP 319623 6/1989
 EP 852986 7/1998
 EP 1527852 5/2005
 EP 1905533 4/2008
 ES 2274736 3/2008
 FR 1456780 7/1966
 FR 2827066 1/2003
 FR 2926660 7/2009
 GB 1455972 11/1976
 GB 1511608 5/1978
 GB 2254172 9/1992
 GB 2435838 9/2007
 GB 2454232 6/2009
 JP 2-224877 9/1990
 JP 5-329645 12/1993
 JP 7-047471 2/1995
 JP 7-232270 9/1995
 JP 8-132274 5/1996
 JP 8-150476 6/1996
 JP 8-505091 6/1996
 JP 2000-167666 6/2000
 JP 2001-071140 3/2001
 JP 2003-200372 7/2003
 JP 2003-326362 11/2003
 JP 2006-281270 10/2006
 JP 2007-290025 11/2007
 JP 2009-500178 1/2009
 JP 2009-160636 7/2009
 KR 20090010693 1/2009
 RU 200810801 11/2009
 SU 1038963 8/1983
 WO 98/45078 10/1998
 WO 01/12376 2/2001
 WO 01/43910 6/2001
 WO 01/58400 8/2001

(56)

References Cited

FOREIGN PATENT DOCUMENTS

WO	2005/102230	11/2005
WO	2006/034571	4/2006
WO	2007/039278	4/2007
WO	2009/060231	5/2009
WO	2009/149740	12/2009
WO	2010/000003	1/2010
WO	2010/091493	8/2010
WO	2011/067447	6/2011
WO	2012/143327	10/2012
WO	2013/014202	1/2013
WO	2013/114189	8/2013

OTHER PUBLICATIONS

Training in a virtual environment gives welding students a leg up, retrieved on Apr. 12, 2010 from: <http://www.thefabricator.com/article/arcwelding/virtually-welding>.

Wade, "Human uses of ultrasound: ancient and modern", *Ultrasonics* vol. 38, dated 2000.

Wang et al., "Numerical Analysis of Metal Transfer in Gas Metal Arc Welding," G. Wang, P.G. Huang, and Y.M. Zhang. Departments of Mechanical and Electrical Engineering. University of Kentucky, Dec. 10, 2001.

Wang et al., Study on welder training by means of haptic guidance and virtual reality for arc welding, 2006 IEEE International Conference on Robotics and Biomimetics, ROBIO 2006 ISBN-10: 1424405718, p. 954-958.

White et al., Virtual welder training, 2009 IEEE Virtual Reality Conference, p. 303, 2009.

Office action from U.S. Appl. No. 12/775,729 dated Jul. 19, 2012.

Interview Summary from U.S. Appl. No. 12/775,729 dated Aug. 16, 2012.

Response from U.S. Appl. No. 12/775,729 dated Oct. 15, 2012.

Response from U.S. Appl. No. 12/775,729 dated Oct. 29, 2012.

Notice of Allowance from U.S. Appl. No. 12/775,729 dated Nov. 9, 2012.

Notice of Allowance from U.S. Appl. No. 12/775,729 dated Jun. 24, 2013.

CS Wave, A Virtual learning tool for welding motion, 10 pages, Mar. 14, 2008.

International Search Report and Written Opinion from PCT/IB09/000605 dated Feb. 12, 2010.

International Search Report and Written Opinion from PCT/IB10/02913 dated Apr. 19, 2011.

ASME Definitions, Consumables, Welding Positions, dated Mar. 19, 2001. See <http://www.gowelding.com/wp/asm4.htm>.

Abbas, M., et al.; Code_Aster; Introduction to Code_Aster; User Manual; Booklet U1.0-: Introduction to Code_Aster; Document: U1.02.00; Version 7.4; Jul. 22, 2005.

Bjorn G. Agren; Sensor Integration for Robotic Arc Welding; 1995; vol. 5604C of Dissertations Abstracts International p. 1123; Dissertation Abs Online (Dialog® File 35): © 2012 ProQuest Info& Learning: <http://dialogweb.com/cgi/dwclient?req=1331233317524>; one (1) page; printed Mar. 8, 2012.

Abid, et al., "Numerical simulation to study the effect of tack welds and root gap on welding deformations and residual stresses of a pipe-flange joint" by M. Abid and M. Siddique, Faculty of Mechanical Engineering, GIK Institute of Engineering Sciences and Technology, Topi, NWFP, Pakistan. Available on-line Aug. 25, 2005.

"Penetration in Spot GTA Welds during Centrifugation," D.K. Aidun and S.A. Martin; *Journal of Materials Engineering and Performance* Volumn 7(5) Oct. 1998—597.

Arc+ simulator; http://www.123arc.com/en/depliant_ang.pdf; 2000, 2 pgs.

ARS Electronica Linz GmbH, Fronius, 2 pages, May 18, 1997.

asciencetutor.com, A division of Advanced Science and Automation Corp., VWL (Virtual Welding Lab), 2 pages, 2007.

16th International Shop and Offshore Structures Congress: Aug. 20-25, 2006: Southampton, UK, vol. 2 Specialist Committee V.3

Fabrication Technology Committee Mandate: T Borzecki, G. Bruce, Y.S. Han, M. Heinemann, A Imakita, L. Josefson, W. Nie, D. Olson, F. Roland, and Y. Takeda.

CS Wave, The Virtual Welding Trainer, 6 pages, 2007.

Choquet, Claude; "ARC+: Today's Virtual Reality Solution for Welders" Internet Page, Jan. 1, 2008.

Code Aster (Software) EDF (France), Oct. 2001.

Cooperative Research Program, Virtual Reality Welder Training, Summary Report SR 0512, 4 pages, Jul. 2005.

Desroches, X.; Code-Aster, Note of use for aciculations of welding; Instruction manual U2.03 booklet: Thermomechanical; Document: U2.03.05; Oct. 1, 2003.

Edison Welding Institute, E-Weld Predictor, 3 pages, 2008.

Eduwelding+, Weld Into the Fugure; Online Welding Seminar—A virtual training environment; 123arc.com; 4 pages, 2005.

Eduwelding+, Training Activities with arc+ simulator; Weld Into the Future, Online Welding Simulator—A virtual training environment; 123arc.com; 6 pages, May 2008.

FH Joanneum, Fronius—virtual welding, 2 pages, May 12, 2008.

The Fabricator, Virtual Welding, 4 pages, Mar. 2008.

Fast, K. et al., "Virtual Training for Welding", Mixed and Augmented Reality, 2004, ISMAR 2004, Third IEEE and CM International Symposium on Arlington, VA, Nov. 2-5, 2004.

Garcia-Ellende et al., "Defect Detection in Arc-Welding Processes by Means of the Line-to-Continuum Method and Feature Selection", www.mdpi.com/journal/sensors; *Sensors* 2009, 9, 7753-7770; doi: 10.3390/s91007753.

Juan Vicenete Rosell Gonzales, "RV-Sold: simulator virtual para la formacion de soldadores"; *Deformacion Metalica, Es.* vol. 34, No. 301 Jan. 1, 2008.

Hillis and Steele, Jr.; "Data Parallel Algorithms", *Communications of the ACM*, Dec. 1986, vol. 29, No. 12, p. 1170.

"The influence of fluid flow phenomena on the laser beam welding process"; *International Journal of Heat and Fluid Flow* 23, dated 2002.

The Lincoln Electric Company, CheckPoint Production Monitoring brochure; four pages; http://www.lincolnelectric.com/assets/en_US/products/literature/s232.pdf; Publication S2.32; issue date Feb. 2012.

The Lincoln Electric Company, Production Monitoring brochure, 4 pages, May 2009.

Eric Linholm, John Nickolls, Stuart Oberman, and John Montrym, "NVIDIA Testla: A Unifired Graphics and Computing Architecture", IEEE Computer Society, 2008.

Mahrle, A., et al.; "the influence of fluid flow phenomena on the laser beam welding process" *International Journal of Heat and Fluid Flow* 23 (2002), No. 3, pp. 288-297.

Mavrikios D et al, A prototype virtual reality-based demonstrator for immersive and interactive simulation of welding processes, *International Journal of Computer Integrated manufacturing*, Taylor and Francis, Basingstoke, GB, vol. 19, No. 3, Apr. 1, 2006, pp. 294-300. Mechanisms and Mechanical Devices Source Book, Chironis, Neil Sclater; McGraw Hill; 2nd Addition, 1996.

"Miller Electric MGF Co.; MIG Welding System features weld monitoring software; NewsRoom 2010 (Dialog® File 992); © 2011 Dialog. 2010; <http://www.dialogweb.com/cgi/dwclient?reg=1331233430487>; three (3) pages; printed Mar. 8, 2012."

NSRP ASE, Low-Cost Virtual Reality Welder Training System, 1 Page, 2008.

N. A. Tech., P/NA.3 Process Modeling and Optimization, 11 pages, Jun. 4, 2008.

Virtual Reality Welder Trainer, Session 5: Joining Technologies for Naval Applications: earliest date Jul. 14, 2006 (<http://weayback.archive.org>) by Nancy C. Porter, Edison Welding Institute; J. Allan Cote, General Dynamics Electric Boat; Timothy D. Gifford, VRSim, and Wim Lam, FCS Controls.

Porter, et al., Virtual Reality Training, Paper No. 2005-P19, 14 pages, 2005.

Production Monitoring 2 brochure, four pages, The Lincoln Electric Company, May 2009.

(56)

References Cited

OTHER PUBLICATIONS

Ratnam and Khalid: "Automatic classification of weld defects using simulated data and an MLP neural network." *Insight* vol. 49, No. 3; Mar. 2007.

Russel and Norvig, "Artificial Intelligence: A Modern Approach", Prentice-Hall (Copyright 1995).

"Design and Implementation of a Video Sensor for Closed Loop Control of Back Bead Weld Puddle Width," Robert Schoder, Massachusetts Institute of Technology, Dept. of Mechanical Engineering, May 27, 1983.

Sim Welder, retrieved on Apr. 12, 2010 from: <http://www.simwelder.com>.

Office action from U.S. Appl. No. 14/045,004 dated Jun. 24, 2014.

Office action from U.S. Appl. No. 12/737,313 dated Oct. 3, 2013.

International Search Report and Written Opinion from PCT/US13/001482 dated Dec. 2, 2013.

Wu, Chuansong, "Microcomputer-based welder training simulator", *Computers in Industry*, 20, pp. 321-325 (1992).

ViziTech USA, 2 page web printout dated Mar. 27, 2014 "Changing the Way America Learns".

Office action from U.S. Appl. No. 14/044,986 dated May 12, 2014.

Response from European application No. 10798180.5 dated Feb. 29, 2012.

Office action from European Application No. 10798180.5 dated Jun. 28, 2013.

Response from European Application No. 10798180.5 dated Nov. 8, 2013.

Response from U.S. Appl. No. 12/737,313 dated Feb. 3, 2014.

Notice of Allowance from U.S. Appl. No. 12/737,313 dated Apr. 29, 2014.

Response from U.S. Appl. No. 14/044,986 dated Aug. 4, 2014.

Response from U.S. Appl. No. 14/045,004 dated Aug. 29, 2014.

Notice of Allowance from U.S. Appl. No. 14/044,986 dated Oct. 27, 2014.

Office action from U.S. Appl. No. 14/045,012 dated Oct. 8, 2014.

Notice of Allowance from U.S. Appl. No. 14/045,004 dated Dec. 3, 2014.

Office action from U.S. Appl. No. 14/045,016 dated Dec. 4, 2014.

Response from U.S. Appl. No. 14/045,016 dated Mar. 2, 2015.

Notice of Allowance from U.S. Appl. No. 14/045,012 dated Feb. 18, 2015.

Response from U.S. Appl. No. 14/045,012 dated Jan. 7, 2015.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12

1300
↓




FIG. 13

1400
↓

	1402 WELD CONDITION	1414 FIXED?	1418 \$ COST	1420 TIME COST	1416 WELD SCORE
1404	WIRE COMPOSITION	YES	N/A	N/A	<i>c</i>
1406	WORKPIECE COMPOSITION	YES	N/A	N/A	
1408	SHIELDING GAS FLOW RATE	NO	<i>a</i>	<i>b</i>	
1410	SHIELDING GAS COMPOSITION	YES	N/A	N/A	
1412	WORKPIECE PRE-HEAT TEMPERATURE	YES	N/A	N/A	

FIG. 14A

1400
↓

	1402 WELD CONDITION	1414 FIXED?	1418 \$ COST	1420 TIME COST	1416 WELD SCORE
<u>1404</u>	WIRE COMPOSITION	YES	N/A	N/A	<i>f</i>
<u>1406</u>	WORKPIECE COMPOSITION	YES	N/A	N/A	
<u>1408</u>	SHIELDING GAS FLOW RATE	NO	<i>d</i>	<i>e</i>	
<u>1410</u>	SHIELDING GAS COMPOSITION	YES	N/A	N/A	
<u>1412</u>	WORKPIECE PRE-HEAT TEMPERATURE	YES	N/A	N/A	

FIG. 14B

1500
↙

	PS#	CONDITIONS		WELDER	PROCESS	\$	TIME	SCORE
1516	01	WIRE COMPOSITION	<i>a</i>	M	O	<i>t</i>	<i>v</i>	<i>x</i>
		WORKPIECE COMPOSITION	<i>b</i>					
		SHIELDING GAS FLOW RATE	<i>c</i>					
		SHIELDING GAS COMPOSITION	<i>d</i>					
		WORKPIECE PRE-HEAT TEMPERATURE	<i>e</i>					
1518	02	WIRE COMPOSITION	<i>f</i>	N	P	<i>u</i>	<i>w</i>	<i>y</i>
		WORKPIECE COMPOSITION	<i>b</i>					

•
•
•

FIG. 15

SYSTEMS, METHODS, AND APPARATUSES FOR MONITORING WELD QUALITY

RELATED APPLICATION

The present application is a divisional application of U.S. application Ser. No. 12/775,729, filed May 7, 2010 titled SYSTEMS, METHODS AND APPARATUSES FOR MONITORING WELD QUALITY which is a non-provisional patent application claiming priority/benefit under 35 U.S.C. §119(e) from U.S. Provisional Patent Application No. 61/261,079 filed on Nov. 13, 2009, the entire disclosures of which are both incorporated herein by reference.

FIELD

The general inventive concepts relate to electric arc welding and, more particularly, to systems, methods, and apparatuses for monitoring variables during a welding process and weighting the variables accordingly, quantifying weld quality, obtaining and using data indicative of a good weld, improving production and quality control for an automated welding process, teaching proper welding techniques, identifying cost savings for a welding process, and deriving optimal welding settings to be used as pre-sets for different welding processes or applications.

BACKGROUND

Many different conditions and parameters contribute to the overall quality of a resulting weld. Consequently, manufacturers of electric arc welders have attempted to monitor operation of the welder to determine the quality of the weld and the efficiency of the welder during operation in a manufacturing facility. One attempt to monitor an electric arc welder is illustrated in U.S. Pat. No. 6,051,805 to Vaidya (hereinafter "Vaidya") where a computer or other programmed instrument is employed to monitor average current and the efficiency of the welding operation, which efficiency is expressed as a ratio of the time welding is performed to the total time of the work shift. In accordance with standard technology, this disclosed monitoring system includes a first control circuit which is in the form of a central processing unit with standard accessories such as RAM and EPROM. A second control circuit is connected to the first circuit to input and output information during the monitoring procedure. The monitor gathers information over a period of time which is disclosed as extending over a few hours or up to 999 hours. The monitor determines welding efficiency and monitors time to determine average current and accumulated arc welding time for overall efficiency.

Vaidya discloses a capability of monitoring the current and wire feed speed, as well as gas flow during the welding procedure. All of this information is stored in appropriate memory devices for subsequent retrieval of the operating characteristics of the welder during the welding process. In this way, the productivity of the welder can be measured to calculate cost efficiency and other parameters. Monitoring of the electric arc welder, as suggested in Vaidya, has been attempted by other manufacturers to measure average current during a welding process. However, measuring average current, voltage, wire feed speed or other parameters during a welding process and using this data for recording the performance of the welding operation has not been satisfactory. In the past, monitoring devices have had no pre-knowledge of the parameters being monitored.

Consequently, monitoring of parameters such as current, voltage and even wire feed speed in the past, even using the technology set forth in Vaidya, has been chaotic in response and incapable of determining the actual stability of the electric arc or whether the welding process is above or below desired parameter values. This information must be known for the purpose of rejecting a welding cycle and/or determining the quality of the weld performed during the welding cycle with desired accuracy. In summary, monitoring the operation of an electric arc welder when used for a variety of welding processes has not been satisfactory because there is no prior knowledge which can be used for the purposes of evaluating the welding process during its implementation.

Overcoming these drawbacks, U.S. Pat. No. 6,441,342 to Hsu (hereinafter "Hsu") discloses a monitor and method of monitoring an electric arc welder as the welder performs a selected arc welding process that creates information on the operation of the welder. Accordingly, use of standard, high power computer technology can be used on equally precise and intelligent data generated by the monitor. The monitor and monitoring system of Hsu employs known information during the welding process. The information is fixed and not varying. The monitor concentrates on specific aspects of the welding process to employ prior knowledge which is compared to actual performance. Thus, the stability and acceptable magnitudes or levels of a selected parameter is determined during a specific aspect of the welding process. The weld process is separated into fixed time segments with known desired parameters before monitoring. Then this data can be processed by known computer techniques to evaluate aspects of the weld cycles.

Hsu discloses that the welding process is carried out by an electric arc welder generating a series of rapidly repeating wave shapes. Each wave shape constitutes a weld cycle with a cycle time. Each weld cycle (i.e., wave shape) is created by a known wave shape generator used to control the operation of the welder. These wave shapes are divided into states, such as in a pulse welding process, a state of background current, ramp up, peak current, ramp down, and then back to background current. By dividing the known driving wave shape into states defined as time segments of the generated arc characteristics, any selected one of the states can be monitored. Indeed, many states can be multiplexed. For instance, in the pulse welding process the state related to the peak current can be monitored. Hsu discloses that the state of the welding process is monitored by being read at a high rate preferably exceeding 1.0 kHz. Each of the actual welding parameters, such as current, voltage or even wire feed speed is detected many times during each peak current state of the wave shape used in the pulse welding process. In this manner, the ramp up, ramp down, and background current are ignored during the monitoring process of the peak current state.

Consequently, the peak current is compared with a known peak current. A function of the peak current can be used to detect variations in the actual peak current output from the electric arc welder. In Hsu, a minimum level and a maximum level on the lower and higher side of the command peak current are used to determine the level of the peak current many times during each peak current state of the pulse weld wave shape. Whenever the current exceeds the maximum, or is less than the minimum, this event is counted during each wave shape. The total deviations or events are counted for a weld time (i.e., a time during which a welding process or some significant portion thereof is carried out). If this count is beyond a set number per wave shape or during the weld time, a warning may be given that this particular welding process experienced unwanted weld conditions. Indeed, if the count

exceeds a maximum level the weld is rejected. This same capability is used with a statistical standard deviation program to read the peak current many times during each peak current state of the wave shape to sense the magnitude of the standard deviation. In practice, the standard deviation is the root-mean-square (RMS) deviation calculation by the computer program. In Hsu, the average peak current is calculated and recorded as well as the level conditions and the stability characteristics. The RMS of the current or voltage is also determined for each of the states being monitored, for example, the peak current state of a pulse wave shape. While the peak current level or standard elevation is monitored, the background current stage can be monitored by current level and duration.

Hsu discloses selecting a state in the wave shape and comparing the desired and known command signals for that state to the actual parameters of the welding process during that monitored state. The selection is based on prior knowledge of the waveform generator. For example, at a specific wire feed speed WFS1, the waveform generator is programmed to adjust peak current to control arc length. The "informed" monitor then selects the peak current segment as the monitored state, when welding at this wire feed speed WFS1. At another wire feed speed WFS2, however, the waveform generator is programmed to adjust background time to control arc length (and not peak current). The "informed" monitor then selects the background time as the monitored state and parameter, when welding at this wire feed speed WFS2. In contrast, a posteriori monitor has no idea that at different wire feed speeds, different aspects of the waveform should be monitored to detect arc stability. Monitoring background time at wire feed speed WFS1 or monitoring peak current at wire feed speed WFS2, in this example, would be very ineffective. Thus, Hsu discloses using a time segment of the wave shape for monitoring this segment of the wave shape using prior knowledge of the desired values. This allows actual monitoring of the electric arc welding process and not merely an averaging over the total wave shape.

In Hsu, the monitor is characterized by the use of prior knowledge, as opposed to the normal process of merely reading the output parameters experienced during the welding process. Consequently, the monitoring greatly simplifies the task of detecting normal behavior of a welder when the normal behavior is a function of time and differs during only one aspect of the welding process. The teachings of Hsu are not as applicable to monitoring voltage in a constant voltage process, because the desired level of voltage is a known characteristic during the total weld cycle. However, in other welding processes when both the voltage and current vary during different segments of the wave shape, the method of Hsu gives accurate readings of stability, RMS, standard deviation, average, below minimum and above maximum before the actual parameter being monitored during selected segments of the wave shape.

According to Hsu, the time varying welding processes, such as pulse welding and short circuit welding, are monitored with precise accuracy and not by reading general output information. The monitor is activated at a selected time in each wave form which is the selected state or segment of the wave shape. The monitor compares actual parameters to the desired parameters in the form of command signals directed to a power supply of the welder. In Hsu, monitoring can occur during only specific segments of the wave shape; however, in exceptional events, such as when the arc is extinguished or when there is a short circuit, a computerized subroutine is implemented by either voltage sensing or current sensing to restart the arc and/or correct the short. The subroutines for

these events run parallel to the monitoring program. Consequently, these exceptions do not affect the overall operation of the monitor. These subroutines are constructed as exceptional states or time segments. The parameters or signals within these exceptional states are monitored in a similar fashion as described above.

In Hsu, production information over a calendar time, shift or even by operator can be accumulated for the purposes of evaluating the operation or efficiency of a welder. The monitoring of each weld cycle by monitoring a specific segment or state of the wave shape allows accumulation of undesired events experienced over time. This also allows a trend analysis so that the operator can take corrective actions before the welding process actually produces defective production welds. Trend analysis, defect analysis, accumulated defects, logging of all of these items and related real time monitoring of the electric arc welder allows direct intervention in a timely manner to take preventive actions as opposed to corrective actions.

SUMMARY

The general inventive concepts contemplate systems, methods, and apparatuses for monitoring variables during a welding process and weighting the variables accordingly, quantifying weld quality, and obtaining and using data indicative of a good weld. The weld quality data allows for improvements in production and quality control for an automated welding process, teaching proper welding techniques, identifying cost savings for a welding process, and deriving optimal welding settings to be used as pre-sets for different welding processes or applications. By way of example to illustrate various aspects of the general inventive concepts, several exemplary systems, methods, and are disclosed herein.

A method of monitoring an electric arc welder as the welder performs a selected arc welding process by creating actual welding parameters between an advancing wire and a workpiece, the selected process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes (a) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (b) dividing the wave shapes into states; (c) measuring a selected weld parameter occurring in one of the wave shape states at an interrogation rate over a period of time to obtain a data set for the selected weld parameter; (d) for each period of time, calculating a stability value for the selected weld parameter from the data set; (e) comparing each stability value to an expected stability value to determine if a difference between the stability value and the expected stability value exceeds a predetermined threshold; and (f) if the difference exceeds the threshold, weighting the stability value with a magnitude weight based on the difference, and weighting the stability value with a time contribution weight based on a time contribution of the wave shape state to its wave shape. In this manner, the method can assign multiple weights (e.g., based on a degree/magnitude of deviation and a time contribution of its state) to a measured parameter (i.e., an item in the data set) that constitutes an outlier. In one exemplary embodiment, an outlier is defined as a measured value for a weld parameter that falls outside the limit of three (3) standard deviations away from the mean value of the weld parameter. A monitor, integrated with an arc welder, for performing this exemplary method is also contemplated.

A method of quantifying a weld's quality by monitoring an electric arc welder as the welder performs a selected arc welding process by creating actual welding parameters

5

between an advancing wire and a workpiece, the selected process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes: (a) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (b) dividing the wave shapes into states; (c) measuring a plurality of selected weld parameters occurring in one or more of the states at an interrogation rate over a period of time repeatedly during a weld time; and (d) calculating a plurality of quality parameters for each of the states based on the measurements of the selected weld parameters during the periods of time, wherein the quality parameters represent an overall quality measurement of the weld. A monitor, integrated with an arc welder, for performing this exemplary method is also contemplated.

In one exemplary embodiment, the method also includes: (e) comparing a value of each of the quality parameters calculated for each period of time to a corresponding expected quality parameter value to determine if a difference between the calculated quality parameter value and the expected quality parameter value exceeds a predetermined threshold; and (f) if the difference exceeds the threshold, weighting the calculated quality parameter value with a magnitude weight based on the difference, and weighting the calculated quality parameter value with a time contribution weight based on a time contribution of its state to the wave shape including the state. A monitor, integrated with an arc welder, for performing this exemplary method is also contemplated.

In one exemplary embodiment, the interrogation rate is 120 kHz. In one exemplary embodiment, the period of time is approximately 250 ms.

In one exemplary embodiment, the selected weld parameters include, for each of the states, a count of the measurements taken for each of the selected weld parameters in the period of time, a mean voltage $\overline{voltage}$ in the period of time, a root mean square voltage RMSV in the period of time, a voltage variance V_{var} in the period of time, a mean current $\overline{current}$ in the period of time, a root mean square current RMSI in the period of time, and a current variance I_{var} in the period of time, wherein $\overline{voltage}$ =a sum of voltages measured in the period of time/the count of voltage measurements, wherein

$$RMSV = \sqrt{\frac{\sum_{i=1}^N (voltage_i)^2}{N}},$$

wherein V_{var} =RMSV- $\overline{voltage}$, wherein $\overline{current}$ =a sum of currents measured in the period of time/the count of current measurements, wherein

$$RMSI = \sqrt{\frac{\sum_{i=1}^N (current_i)^2}{N}},$$

and wherein I_{var} =RMSI- $\overline{current}$.

In one exemplary embodiment, the quality parameters include a quality count average QCA for each state calculated as:

6

$$QCA = \frac{\sum_{i=1}^N count_i}{N},$$

wherein N is the total number of weld cycles in a period of time, and wherein $count_i$ refers to a count of the measurements for a specific one of the weld cycles in the period of time.

In one exemplary embodiment, the quality parameters include a quality count standard deviation QCSD for each state calculated as:

$$QCSD = \frac{\sum_{i=1}^N (count_i - QCA)^2}{N - 1}.$$

In one exemplary embodiment, the quality parameters include a quality count standard deviation QCSD for each state calculated as:

$$QCSD = \frac{\sum_{i=1}^N (count_i - QCA)^2}{N}.$$

In one exemplary embodiment, the quality parameters include a quality voltage average QVA for each state calculated as:

$$QVA = \frac{\sum_{i=1}^N voltage_i}{N},$$

wherein N is the total number of weld cycles in the period of time, and wherein $voltage_i$ refers to a voltage measurement for a specific one of the weld cycles in the period of time.

In one exemplary embodiment, the quality parameters include a quality voltage standard deviation QVSD for each state calculated as:

$$QVSD = \frac{\sum_{i=1}^N (voltage_i - QVA)^2}{N - 1}.$$

In one exemplary embodiment, the quality parameters include a quality voltage standard deviation QVSD for each state calculated as:

$$QVSD = \frac{\sum_{i=1}^N (voltage_i - QVA)^2}{N}.$$

In one exemplary embodiment, the quality parameters include a quality current average QIA for each state calculated as:

7

$$QIA = \frac{\sum_{i=1}^N \text{current}_i}{N},$$

wherein N is the total number of weld cycles in the period of time, and wherein current_i refers to a current measurement for a specific one of the weld cycles in the period of time.

In one exemplary embodiment, the quality parameters include a quality current standard deviation QISD for each state calculated as:

$$QISD = \frac{\sum_{i=1}^N (\text{current}_i - QIA)^2}{N - 1}.$$

In one exemplary embodiment, the quality parameters include a quality current standard deviation QISD for each state calculated as:

$$QISD = \frac{\sum_{i=1}^N (\text{current}_i - QIA)^2}{N}.$$

In one exemplary embodiment, the quality parameters include a quality voltage variance average QVVA for each state calculated as:

$$QVVA = \frac{\sum_{i=1}^N V_{\text{vari}}}{N},$$

wherein N is the total number of weld cycles in the period of time.

In one exemplary embodiment, the quality parameters include a quality voltage variance standard deviation QVVSD for each state calculated as:

$$QVVSD = \frac{\sum_{i=1}^N (V_{\text{vari}} - QVVA)^2}{N - 1}.$$

In one exemplary embodiment, the quality parameters include a quality voltage variance standard deviation QVVSD for each state calculated as:

$$QVVSD = \frac{\sum_{i=1}^N (V_{\text{vari}} - QVVA)^2}{N}.$$

In one exemplary embodiment, the quality parameters include a quality current variance average QIVA for each state calculated as:

8

$$QIVA = \frac{\sum_{i=1}^N V_{\text{vari}}}{N},$$

wherein N is the total number of weld cycles in the period of time.

In one exemplary embodiment, the quality parameters include a quality current variance standard deviation QIVSD for each state calculated as:

$$QIVSD = \frac{\sum_{i=1}^N (I_{\text{vari}} - QIVA)^2}{N - 1}.$$

In one exemplary embodiment, the quality parameters include a quality current variance standard deviation QIVSD for each state calculated as:

$$QIVSD = \frac{\sum_{i=1}^N (I_{\text{vari}} - QIVA)^2}{N}.$$

In one exemplary embodiment, the method further includes: (e) using the quality parameters in a metric to evaluate subsequent welds. A monitor, integrated with an arc welder, for performing this exemplary method is also contemplated.

A method of evaluating a plurality of welds performed under substantially the same conditions and according to substantially the same arc welding process by monitoring an electric arc welder as the welder performs the welds according to the arc welding process by creating actual welding parameters between an advancing wire and a workpiece, the selected process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes, during each weld: (a) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (b) dividing the wave shapes into states; (c) measuring a selected weld parameter occurring in one of the states at an interrogation rate over a period of time to obtain a data set for the selected weld parameter; (d) for each period of time, calculating a quality value for the selected weld parameter from the data set; (e) comparing each quality value to an expected quality value to determine if a difference between the quality value and the expected quality value exceeds a predetermined threshold; (f) if the difference exceeds the threshold, weighting the quality value with a magnitude weight based on the difference, and weighting the quality value with a time contribution weight based on a time contribution of the state to its wave shape; and (g) using all of the quality values, including any weighted quality values, obtained during the weld time to determine a quality score for the weld.

In one exemplary embodiment, the method further includes: (h) rejecting the weld if its quality score is within a first predefined range of quality scores; and (i) accepting the weld if its quality score is within a second predefined range of quality scores.

In one exemplary embodiment, the method further includes: (h) permanently associating each weld with its corresponding quality score.

In one exemplary embodiment, the interrogation rate is 120 kHz. In one exemplary embodiment, the period of time is approximately 250 ms.

In one exemplary embodiment, the selected weld parameter is arc current. In one exemplary embodiment, the selected weld parameter is arc voltage.

A method of providing instruction to an individual (i.e., an operator) manually performing an arc welding process using an electric arc welder including an integrated monitor, the welder performing the arc welding process by creating actual welding parameters between an advancing wire and a workpiece, the monitor capable of monitoring the actual welding parameters, and the arc welding process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes: (a) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (b) dividing the wave shapes into states; (c) measuring a selected weld parameter occurring in one of the states at an interrogation rate over a period of time to obtain a data set for the selected weld parameter; (d) for each period of time, calculating a quality value for the selected weld parameter from the data set; (e) comparing each quality value to an expected quality value to determine if a difference between the quality value and the expected quality value exceeds a predetermined threshold; (f) if the difference exceeds the threshold, weighting the quality value with a magnitude weight based on the difference, and weighting the quality value with a time contribution weight based on a time contribution of the state to its wave shape; (g) using the quality value, including any weights, to update a current aggregate quality score for the weld; (h) determining if the current aggregate quality score is within a predefined range of acceptable quality scores during the welding process; and (i) if the current aggregate quality score is outside the predefined range of acceptable quality scores, providing information on corrective action to the operator.

In one exemplary embodiment, the interrogation rate is 120 kHz. In one exemplary embodiment, the period of time is approximately 250 ms.

In one exemplary embodiment, the information is provided visually. In one exemplary embodiment, the information is provided audibly.

In one exemplary embodiment, the information includes a suggested change in a position of the wire relative to the workpiece. In one exemplary embodiment, the information includes a suggested change in a rate of movement of the wire relative to the workpiece.

In one exemplary embodiment, the information is provided to the operator at a predetermined reporting rate. In one exemplary embodiment, the reporting rate is less than 30 seconds. In one exemplary embodiment, the reporting rate is greater than or equal to 30 seconds.

In one exemplary embodiment, the information is provided if recent changes in the current aggregate quality score indicate the current aggregate quality score is likely to move outside the predefined range of acceptable quality scores.

In one exemplary embodiment, the method further includes: (j) if the current aggregate quality score is within the predefined range of acceptable quality scores, providing confirmation to the operator that no corrective action is necessary.

A method of evaluating a plurality of operators performing an arc welding process by monitoring an electric arc welder associated with each of the operators, as each welder is used by its respective operator to perform said arc welding process by creating actual welding parameters between an advancing wire and a workpiece with said arc welding process con-

trolled by command signals to a power supply of said welder, is disclosed. The method includes, for each operator: (a) generating a numerical score indicating a quality measurement of a weld formed according to said arc welding process relative to a predetermined baseline weld; (b) measuring an amount of time said operator spends performing said arc welding process; and (c) associating said numerical score and said welding time with said operator.

In one exemplary embodiment, the numerical score is generated by: (a1) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (a2) dividing said wave shapes into states; (a3) measuring a selected weld parameter occurring in one of said states at an interrogation rate over a period of time to obtain a data set for said selected weld parameter; (a4) for each period of time, calculating a quality value for said selected weld parameter from said data set; (a5) comparing each quality value to an expected quality value to determine if a difference between said quality value and said expected quality value exceeds a predetermined threshold; (a6) if said difference exceeds said threshold, weighting said quality value with a magnitude weight based on said difference, and weighting said quality value with a time contribution weight based on a time contribution of said state to its wave shape; and (a7) using all of said quality values, including any weighted quality values, obtained during said arc welding process to determine said numerical score.

A method of performing a cost-effective analysis for a selected arc welding process, wherein an electric arc welder performs the arc welding process by creating actual welding parameters between an advancing wire and a workpiece, the selected process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes: (a) identifying a plurality of weld conditions capable of affecting overall weld quality; (b) varying one of the weld conditions across a plurality of welds and fixing all remaining weld conditions across the welds; (c) for each of the welds: (i) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time; (ii) dividing the wave shapes into states; (iii) measuring a selected weld parameter occurring in one of the states at an interrogation rate over a period of time to obtain a data set for the selected weld parameter; (iv) for each period of time, calculating a stability value for the selected weld parameter from the data set; (v) comparing each stability value to an expected stability value to determine if a difference between the stability value and the expected stability value exceeds a predetermined threshold; (vi) if the difference exceeds the threshold, weighting the stability value with a magnitude weight based on the difference, and weighting the stability value with a time contribution weight based on a time contribution of the wave shape state to its wave shape; (vii) using the stability values obtained during the weld time, including any weighted stability values, to calculate an overall quality score for the weld; (viii) determining a cost for the weld; and (ix) associating the quality score and the cost with the weld.

In one exemplary embodiment, the weld conditions include one or more of wire characteristics, workpiece characteristics, a shielding gas flow rate, a shielding gas composition, and a workpiece pre-heat temperature.

In one exemplary embodiment, the cost includes monetary expenditures related to producing the weld. In one exemplary embodiment, the cost includes a total time required to complete the weld.

In one exemplary embodiment, the stability value is a standard statistical deviation for the selected weld parameter.

11

In one exemplary embodiment, the interrogation rate is 120 kHz. In one exemplary embodiment, the period of time is approximately 250 ms.

In one exemplary embodiment, the method further includes: (d) outputting the quality score and the cost (or respective averages thereof) associated with each of the welds.

A method of using pre-set welding parameters to obtain a weld having a desired quality, the weld produced by an electric arc welder performing a selected arc welding process by creating actual welding parameters between an advancing wire and a workpiece, the welding process controlled by command signals to a power supply of the welder, according to one exemplary embodiment, is disclosed. The method includes: (a) presenting a plurality of sets of selected weld parameters to a user along with a quality score corresponding to each set, wherein the quality score quantifies an overall quality of a weld previously obtained using the set of selected weld parameters; (b) receiving input from the user as to which of the sets of selected weld parameters to use for performing the welding process; and (c) performing the welding process using the set of selected weld parameters corresponding to the input.

In one exemplary embodiment, a cost associated with performing the welding process using each of the sets of selected weld parameters is presented to the user.

In one exemplary embodiment, the method further includes: (d) receiving input from the user identifying a minimum acceptable quality score; and (e) filtering out all sets of selected weld parameters that correspond to an associated quality score below the minimum acceptable quality score.

In one exemplary embodiment, the method further includes: (d) receiving input from the user identifying a range of acceptable quality scores; and (e) filtering out all sets of selected weld parameters that correspond to an associated quality score outside of the range of acceptable weld quality scores.

Numerous aspects of the general inventive concepts will become readily apparent from the following detailed description of exemplary embodiments, from the claims and from the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The general inventive concepts as well as embodiments and advantages thereof are described below in greater detail, by way of example, with reference to the drawings in which:

FIG. 1 is a combined block diagram and computer flow chart or program illustrating a monitor of an arc welder, according to one exemplary embodiment;

FIG. 2 is a current command graph from a wave generator showing the command wave shape divided into time segments or states of both fixed and variable durations, according to one exemplary embodiment;

FIG. 3 is a current graph of the actual command signals for arc current with the actual arc current parameter superimposed in dashed lines, according to one exemplary embodiment;

FIG. 4 is a block diagram of an aspect of the invention for monitoring signals internal of the welder instead of weld parameters as illustrated in FIGS. 2 and 3, according to one exemplary embodiment;

FIG. 5 is a time based graph illustrating the wave shape, wire feeder command signal and actual wire feeder command signal as experienced in the exemplary embodiment shown in FIG. 4;

12

FIG. 6 is a portion of a parameter curve illustrating a level monitoring feature, according to one exemplary embodiment;

FIG. 7 is a block diagram and computer flow chart or program illustrating processing for stability during a selected state of the wave shape shown in FIGS. 2 and 3, according to one exemplary embodiment;

FIG. 8 is a block diagram and computer flow chart or program to process information from the level monitor stages of the exemplary embodiment shown in FIG. 1;

FIG. 9 is a flowchart illustrating a weighting method for weighting sampled weld data parameters, according to one exemplary embodiment;

FIG. 10 is a diagram of a conceptual production line, according to one exemplary embodiment;

FIG. 11 is a flow chart illustrating a method of instruction, according to one exemplary embodiment;

FIG. 12 is a block diagram illustrating a system for monitoring students, according to one exemplary embodiment.

FIG. 13 is a flow chart illustrating a method of monitoring students, according to one exemplary embodiment.

FIGS. 14A and 14B are tables showing exemplary data used in a cost analysis for a welding process, according to one exemplary embodiment; and

FIG. 15 is a table showing pre-set data associating welding conditions, welders, and welding processes, according to one exemplary embodiment.

DESCRIPTION

While the general inventive concepts are susceptible of embodiment in many different forms, there are shown in the drawings and will be described herein in detail specific embodiments thereof with the understanding that the present disclosure is to be considered as merely an exemplification of the principles of the general inventive concepts. Accordingly, the general inventive concepts are not intended to be limited to the specific embodiments illustrated herein. Furthermore, the disclosures of U.S. Pat. Nos. 5,278,390 and 6,441,342 are incorporated herein by reference, in their entirety, as they may provide background that facilitates a better understanding of particular aspects and/or advancements of the general inventive concepts.

The following are definitions of exemplary terms used throughout the disclosure. Both singular and plural forms of all terms fall within each meaning:

“Logic,” synonymous with “circuit” as used herein includes, but is not limited to, hardware, firmware, software and/or combinations of each to perform a function(s) or an action(s). For example, based on a desired application or needs, logic may include a software controlled microprocessor, discrete logic such as an application specific integrated circuit (ASIC), or other programmed logic device. In some instances, logic could also be fully embodied as software.

“Software” or “computer program” as used herein includes, but is not limited to, one or more computer readable and/or executable instructions that cause a computer or other electronic device to perform functions, actions, and/or behave in a desired manner. The instructions may be embodied in various forms such as routines, algorithms, modules or programs including separate applications or code from dynamically linked libraries. Software may also be implemented in various forms such as a stand-alone program, a function call, a servlet, an applet, instructions stored in a memory, part of an operating system or other type of executable instructions. It will be appreciated by one of ordinary skill in the art that the form of software is dependent on, for example, requirements

of a desired application, the environment it runs on, and/or the desires of a designer/programmer or the like.

“Computer” or “processing unit” as used herein includes, but is not limited to, any programmed or programmable electronic device that can store, retrieve, and process data.

Referring now to the drawings which illustrate various exemplary embodiments of the general inventive concepts and applications employing the general inventive concepts, FIG. 1 shows a block diagram and flow chart or program implemented by a standard onboard computer in electric arc welder 10. For example, welder 10 can be a Power Wave, inverter based electric arc welder sold by The Lincoln Electric Company of Cleveland, Ohio. In accordance with standard technology, welder 10 includes a three phase electrical input L1, L2, L3 directing electrical current to power supply 12. An onboard computerized controller operates the inverter based power supply to create a positive potential at terminal 14 and a negative potential at terminal 16.

Selected arc welding processes are performed by directing a selected previously determined wave shape to the actual welding circuit, shown to have a standard smoothing inductor 18. Welder 10 performs the electric arc welding process between an advancing welding wire 20 from reel 22 driven at a desired rate by feeder 24 operated at the speed of motor 26. Heat of the arc melts wire 20 and workpiece 30 to deposit molten metal from the wire onto the workpiece. To monitor the actual parameters of the welding process, shunt 32 provides output signal I_a from block 34 on line 34a. This signal is representative of the actual arc current at any given time. In a like manner, the voltage between wire 20 and workpiece 30 is sensed by block 36 so the output V_a on line 36a is the instantaneous arc voltage to constitute a second weld parameter. The weld parameters illustrated in FIG. 1 are the actual arc current I_a and the actual arc voltage V_a .

Another parameter controlled for practicing the invention is wire feed speed (WFS), caused by rotation of the motor 26. Consequently, three externally readable welding parameters of the welding process are arc current I_a in line 34a, arc voltage V_a in line 36a and the wire feed speed WFS readable in line 46b, as explained later. The WFS in line 46b is read by tachometer or encoder 46c connected to the drive rolls 24 of the feeder gear box or, alternatively, on a passive wheel attached to the wire. In FIG. 1, the tachometer is shown as driven by the feed rolls. It could also be driven, for example, by the output shaft of motor 26.

The Power Wave electric arc welder includes a wave shape generator to create a series of rapidly repeating wave shapes, each wave shape (e.g., a single sequence of a voltage/current waveform) constituting a weld cycle with a cycle time. These weld cycles are repeated during the welding process to define a weld time. One embodiment of the Power Wave welder 10 is shown in U.S. Pat. No. 5,278,390 to Blankenship wherein the welder controls the individual wave shape to be output by power supply 12 through command line 42 and the speed of motor 26 through command line 44. Command line 44 has a signal which is recognized by the microprocessor on the wire drive control 46 of motor 26 to output the motor voltage drive PWM pulses in line 46a. In practice, the information on line 44 is digital and the command signal on line 46a is analog. Wave shape generator 40 creates digital signals in lines 42, 44 to controlling the desired welding process to be performed by welder 10. The external parameters I_a , V_a and WFS can be read by appropriate monitoring devices.

The wave shape generator 40 divides or segments each of the output wave shapes into a series of time segmented portions or states. In one exemplary embodiment, monitor M is a program loaded into the computer of welder 10, among other

things, to read parameters during one selected segment of the wave shape. The monitor M can be implemented using software, hardware, and combinations thereof, without departing from the spirit and the scope of the general inventive concepts. The portion of the wave shape being monitored is determined by the wave shape generator 40. Indeed, monitor M monitors various time segments or states of the wave shape output by generator 40. In practice, the wave shape generator 40 selects several of the time segments forming the wave shape and outputs the various states into a command interface 70. Consequently, the command interface 70 causes measurement of the parameters during selected time segments of each wave shape output by the generator. Information or data on the command interface 70 includes the state or states being monitored and the particular value or level of the various parameters I_a , V_a , and/or WFS.

Interface 70 of monitor M contains the data recognizing the particular state being processed together with the values for the weld parameters being read. The data in interface 70 is analyzed by level stage 81 to determine the relationship of a parameter on a level basis. The actual parameters are compared with trained or measured parameters during selected states of the wave shape from generator 40. During a particular segment or state of the wave shape, level monitor stage 81 reads the actual parameters in lines 34a, 36a and 46b. These instantaneous values of the actual parameters are stored in internal memory, identified as the report logic 82. The reading of the actual parameters occurs rapidly as indicated by oscillator 84. In one exemplary embodiment, reading of the actual parameters occurs at a rate of 120 kHz for pulse welding. The rate can be adjusted; however, the higher the rate the better the sensitivity of the level measurement. Level monitor 81 also determines a deviation of the actual welding parameters from either a minimum or maximum level. In this manner, not only can the actual values be stored, but data is stored representing deviation of the actual reading of the parameter for a given state as compared to a minimum level or to a maximum level. Report memory or logic 82 records deviation from a set level during a given state of the wave shape, as well as the actual level during the selected state of the wave shape. For a total weld cycle, these readings are accumulated, counted or otherwise processed to determine the quality of the weld and any trends toward weld defects.

In one exemplary embodiment, the readings (e.g., periodically accumulated sets of the readings) are weighted based on a plurality of criteria. The readings can be accumulated, for example, every 250 ms. In one exemplary embodiment, a set is weighted based on a magnitude of its deviation from an expected value (e.g., predetermined threshold, mean value) and a time contribution of its time segment to the corresponding wave shape. Such a weighting method (e.g., the weighting method 900 shown in FIG. 9 and described below) could be implemented, for example, in level monitor stage 81 or any similar or related data processing stage.

Stability monitor stage 91 reads the actual welding parameters on lines 34a, 36a and 46b at a rapid rate determined by oscillator 94. In one exemplary embodiment, reading of the actual parameters occurs at a rate of 120 kHz for pulse welding. Stability monitor stage 91 analyzes the actual weld parameters for standard deviation or absolute deviation during a state of the wave shapes being output. Report memory or logic 92 records this deviation during a given state of the wave shape, as well as the actual value during the selected state of the wave shape. For a total weld cycle, these readings are accumulated, counted or otherwise processed to determine the quality of the welding and any trends toward weld defects.

In one exemplary embodiment, the readings (e.g., periodically accumulated sets of the readings) are weighted based on a plurality of criteria. The readings can be accumulated, for example, every 250 ms. In one exemplary embodiment, a set is weighted based on a magnitude of its deviation from an expected value (e.g., predetermined threshold, mean value) and a time contribution of its time segment to the corresponding wave shape. Such a weighting method (e.g., the weighting method **900** shown in FIG. **9** and described below) could be implemented, for example, in stability monitor stage **91** or any similar or related data processing stage.

A few wave shapes can be skipped when using either monitor stage **81** or monitor stage **91**. In one exemplary embodiment, after a start sequence, all of the wave shapes are monitored for analyzing the actual welding parameters during the various selected states of the wave shape. Several states of a given wave shape in a welding process are monitored and the results are recorded separately for each state to be analyzed for level conformity, trend and stability. When measuring stability, a standard deviation algorithm is used in monitor **M** to evaluate I_a , V_a and/or WFS. This information is available to analyze each of the various segments of the wave shape forming a total weld cycle with a given cycle time. In practice, certain states, such as the peak current during a pulse wave shape are monitored to determine the stability and level deviations of the pulse welding process. In an STT welding process, monitor **M** records short circuit times for each wave shape, since these segments vary in time according to the external conditions of the welding process. Variation in short circuit time informs the welding engineer of adjustments to be implemented.

The series of rapidly repeating wave shapes generated by the standard wave shape generator **40** are divided into time states, as shown in FIGS. **2** and **3**. The output current command wave shape is pulse wave shape **100** with a peak current **102** having a fixed duration of time segment **A** shown in FIG. **3** and a background current **104** with a variable time duration for segment **B** shown in FIG. **3**. The wave shape is divided into segments at times t_1 - t_4 so that the command interface **70** receives the particular state being processed by generator **40** at any given time. As shown in FIG. **3** by the dashed line **110**, the actual arc current from shunt **33** in FIG. **1** deviates from the command current signal of wave shape **100**.

During the selected functional states, such as state **A** or state **B**, the actual arc current I_a is read at a rate determined by oscillator **84** or oscillator **94**. In practice, this is a single software oscillator. Level monitor stage **81** records deviation in the ordinate direction between the actual parameter **110** and the command level of wave shape **100**. During the selected state, stability monitor stage **91** reads the statistical standard deviation of the actual parameter. States **A** and **B** are normally monitored for a pulse welding process. However, the ramp up state between t_1 - t_2 and/or the ramp down state during t_3 - t_4 can be monitored to control or at least read the activity of the actual parameter during these states of the wave shape. As illustrated, the background time segment **B** has a variable time, as shown by the variable time positions of time t_1 . Consequently, the state being monitored can have a fixed time duration or a variable duration. When a variable duration, the state is monitored until the end of the duration. Report logic **82** senses this as a level from one time, i.e. t_4 , to the successive time, i.e. t_1 . As the time t_1 changes with respect to the time t_4 , this time of each wave shape is recorded as a level which is compared to a known time, obtained from interface **70** by selection of the welding mode of generator **40**.

Monitor **M** monitors the actual welding parameters during specific selected states of the wave shapes; however, the

monitor also has programming to operate the computer to determine the stability and/or level characteristics of an internal signal, such as the actual input to motor **26** on line **46a**. Such internal monitoring of the signal on line **46a** is set forth in the flow chart shown in FIG. **4** utilizing the signals shown in FIG. **5**.

The microprocessor in the wire feeder includes a subroutine that is a PID comparing network similar to an error amplifier. This PID comparator is schematically illustrated as block **152** in FIG. **4** having a first input **46b** which is a wire feed speed WFS and a command signal on line **44**. The actual WFS on line **46b** is read by a tachometer or encoder connected to the drive rolls **24** of the feeder gear box or, alternatively, on a passive wheel attached to the wire to read the WFS. The output **156** of the PID is the voltage level at the input of the pulse width modulator **158** which is digitized in the microprocessor of the feeder. The output of the pulse width modulator is the command signal on line **46a** to motor **26** for controlling the wire feed speed of feeder **24**.

In accordance with one exemplary embodiment, monitor **M** includes the process program as schematically illustrated in FIG. **4** wherein the signal on line **156** is read by processing block **160** and the results are output on line **162** to the input of the level monitor stage **81** and/or the stability monitor stage **91**, as previously discussed with respect to the embodiment shown in FIG. **1**. Consequently, an internal signal on line **156** is read at a rapid rate, exceeding 1 kHz, to check the level of this internal signal and/or the stability of this signal.

As illustrated in FIG. **5**, the wave shape **100** for pulse welding extends as a succession of wave shapes from generator **40**. With respect to the wire feed speed, the command signal from generator **40** on line **44** takes the form shown in FIG. **5**. It includes a start ramp up portion **170** and an ending ramp down portion **172**. These two portions cause a drastic increase or decrease in the command signal on line **44**. Between these abnormal command portions of the signal on line **44**, there is a generally level wire feed speed command which is employed for the purposes of testing stability and/or the level deviation of this internal signal on line **156**. In FIG. **5**, the wire acceleration portion **170** is held until the speed is stabilized. This time is also monitored. Other internal signals can be monitored using the same concept as shown in FIGS. **4** and **5**. The level monitor stage determines if the signal on line **156** exceeds the minimum or maximum for a prolonged time. For the wire feeder, this normally indicates a jam in the feeder system.

FIG. **6** shows the concept of a level monitor stage wherein threshold **180** is the maximum parameter level and threshold **182** is the minimum parameter level. When the parameter, illustrated as arc current, exceeds threshold **180** as indicated by transient **184**, there is a recorded event of over current. In a like manner, when the current is less than the minimum level **182**, as shown by transient **186**, there is recorded an under current event. Additionally, these events can be weighted based on a plurality of criteria. In one exemplary embodiment, each event is weighted based on a magnitude of its deviation from an expected value (e.g., predetermined threshold, mean value) and a time contribution of its time segment to the corresponding wave shape. Such a weighting method (e.g., the weighting method **900** shown in FIG. **9** and described below) could be implemented, for example, in level monitor stage **81**, stability monitor stage **91**, or any similar or related data processing stage.

The weighted events are counted or otherwise accumulated periodically to provide the output of the level monitor stage **81** as shown in FIG. **1**. The weighted events can be accumulated, for example, every 250 ms. Consequently, the level

monitor stage **81** detects excursions **184** above a preset threshold and excursions **186** below a preset level. These levels are set by the particular state in the interface **70**. Some states of a wave shape employ the level monitor stage **81** with thresholds and other states of the same wave shape may use the stability monitor stage **91**. Preferably, and in practice, both monitor stages are used for the selected state or states of the wave shape being interrogated by monitor M.

The embodiment shown in FIG. **1** monitors the level and/or stability of actual parameters for internal control signals during a selected state of the wave shape from generator **40** or during the total weld as explained in relationship to the disclosure in FIGS. **4** and **5**. The monitor M in FIG. **1**, as so far explained, provides weighted data for use in analyzing the weld cycle or the total operation of the welder over a work period of time. Various analysis programs are used to process data after the data has been determined and stored. In accordance with one exemplary embodiment, the weighted stability data from monitor stage **91** is analyzed by two programs as shown in FIG. **7**. It is within the skill of the art to analyze the stability data in a variety of computer programs for recording, display and process intervention or evaluation.

As shown in FIG. **7**, analysis program **200** uses the results of monitor stage **91** of monitor M (i.e., the weighted stability values). As an example, the program **200** is operated during monitoring of the time state between times t_2 - t_3 , which is the current peak portion of the wave shape as shown in FIGS. **2** and **3**. Analysis program **200** is shown as a computer flow chart showing two systems employed to analyze the results of the stability stage **91** during the peak current state where the statistical standard deviation of actual current in line **34a** is calculated. In practice, there is a slight delay before the monitor stage **91** makes calculated deviations. The sample select feature to read I_a during state t_2 - t_3 but ignore I_a otherwise is illustrated as sample selector or filter **90a**. This program delay at the start of time segment t_2 - t_3 incorporated in filter **90a** allows the monitor to ignore fluctuations in the current which are experienced during each level shift in the various stages of the output wave shape.

In the programmed flow chart shown in FIG. **7**, the stability output from monitor stage **91** is read by the computer program shown as block **210** which is reset as indicated by the logic on line **210a** at the end of each wave shape determined by the existence of time t_3 . Consequently, the stability of each wave shape is captured by block **210**. This captured stability data is processed in accordance with two separate analysis programs.

The first program includes the pass analysis routine **212**. If the stability for a given wave shape passes the desired threshold set in block **212**, this information is output on line **214**. If the particular wave shape has a stability less than a desired threshold, a logic signal appears in line **216**. Counters **220**, **222** are enabled by the logic on line **224** during each of the weld cycles. Consequently, the stability pass signals for each of the wave shapes during the weld cycle are counted in either counter **220** or counter **222**. Of course, the first portion of each state t_2 - t_3 is ignored to allow the parameter I_a to settle. The results of the two counters are read, stored or otherwise retained as indicated by the read block **220a**, **222a**, respectively. In one exemplary embodiment, if the instability accumulated by counter stage **222** is beyond a desired number, the weld cycle is rejected as indicated by block **226**.

A second analysis implementation of computer program **200** shown in FIG. **7** is illustrated as block **230**. This is a program enabled during the weld cycle. The total instability of the weld cycle accumulating during all wave shapes is analyzed as a total number wherein **100** is the most stable arc.

The output of this stability accumulator and analyzing stage is read, stored or otherwise retained as indicated by block **236**. If the reading stage **234** is below a set stability then the weld cycle is rejected as indicated by block **238**. A person skilled in the art can design other programs for analyzing the results of the monitor M from stability stage **91**. The computer program **200** exhibits two implementations to analyze the obtained weighted stability data. The two implementations can be selectively enabled (either one or the other or both) depending on the nature of the arc stability or weld quality problem the monitor is configured to detect. It is advantageous to read stability in only selected states of the wave shapes, because stability over a variable pulse is not obtainable.

In accordance with another exemplary embodiment, the computer program for analyzing the results of level monitor stage **81** of monitor M (i.e., the weighted read values) is shown in FIG. **8**. In this illustrated embodiment, level analysis program **250** processes the output from monitor level stage **81** in two separate routines, identified as a minimum monitor stage **81a** with filter **80c** and a maximum monitor stage **81b** with filter **80d**. Either one of these stages can be used separately or, in practice, they are combined. Subsection **81a** relates to the determination of transitions **186** shown in FIG. **6** which is an event where the actual parameter is below the threshold minimum **182**. The minimum level on line **202a** from generator **40** is used when stage **81a** is selected by program step **252**. These events are counted by block **254** for each of the weld cycles as indicated. The counter is enabled during the weld cycle by the logic on line **254a**. Counter **254** is a running total of the wave shapes used in a weld cycle. The number of wave shapes is obtained by counting the occurrences of time t_3 from the output of generator **40** as indicated by line **258**. As indicated before, the first part of the state is generally ignored to remove normal inconsistencies at the start of any particular state. Block **260** is the computer flow chart subroutine for dividing the accumulated minimum events **186** from monitor stage **81a** divided by the number N from the counter **256**. This provides an average of minimum transitions during the weld cycle, which is provided to subroutine **262**. The average minimum transitions are read, stored or otherwise output as indicated by block **262a**. If the average is above a certain threshold number provided by the wave generator or by the program step **264**, program routine **266** determines that the weld cycle is unacceptable. If acceptable, no action is taken. However, if the acceptable routine **266** determines that the average is merely approaching the number **264**, a warning signal is provided by block **266a**. Total unacceptability provides a weld reject signal by routine **266b**. A person skilled in the art can devise other computer programs for effecting the analysis of the minimum current deviation or transition of the actual parameter as it relates to a set threshold.

In FIG. **8**, the maximum monitor stage **81b** operates in conjunction with the minimum stage **81a**. The maximum level is on line **202b** from generator **40** and is used when stage **81b** is selected by program **270**. Like data information and programming retains the same numbers. Counter **272** counts the number of events **184** during the state t_2 - t_3 . Subroutine **280** provides the average of events **184** during the various wave shapes formed during the weld cycle. This average in block **282** is read, stored or otherwise used as indicated by block **282a**. In block **286**, the acceptability subroutine is processed wherein the number indicated by block **284** output from generator **40** or otherwise implemented by computer program is compared with the average from block **282** to provide a warning signal as indicated by block **286a** when the

average approaches the set number indicated by block **284**. If the number is reached, a reject subroutine is implemented as indicated by block **286b**.

In practice, stage **81a** and stage **81b** are implemented together and the average of both transitions from blocks **262** and **282** are analyzed by a read, acceptable number to give a warning and/or a rejection of a given weld cycle. Consequently, in practice, minimum level deviations are analyzed, maximum level deviations are analyzed, and total level deviations are analyzed. All of this is accomplished by the computer program as schematically illustrated in FIG. **8**. The level stages **81a**, **81b** output level conditions which are stored and/or displayed as discussed with report logic **82**. The level conditions output by the level stages **81a**, **81b** can be weighted, as discussed herein.

In view of the above, the use of the magnitude and time contribution weights provide a more accurate measure of parameter stability and, thus, overall weld quality. In this manner, an easy to understand numerical value or score can be computed to quantify the overall quality of a weld. In one exemplary embodiment, a weld score between 0-100 or 0%-100% is calculated for a weld based on monitored welding conditions or parameters, such as those monitored by the exemplary embodiment shown in FIG. **1**. Such a weighting method (e.g., the weighting method **900** shown in FIG. **9** and described below) could be implemented, for example, in level monitor stage **81**, stability monitor stage **91**, or any similar or related data processing stage.

A weighting method **900**, according to one exemplary embodiment, is shown in FIG. **9**. The weighting method can be implemented, for example, in the monitor **M**. In an initial step **902** of the weighting method **900**, waves shapes of a weld cycle are divided into a series of time segmented portions or states. Then, in step **904**, weld parameters (e.g., voltage, amperage) corresponding to at least one of the states are sampled at a given rate. In one exemplary embodiment, the sampling rate is 120 kHz. In one exemplary embodiment, the sampling rate is greater than or equal to 120 kHz. In one exemplary embodiment, the sampling rate can be used to generate an interrupt for interrupt service routine (ISR) processing.

The sampled weld parameters are used to calculate weld data. In the exemplary weighting method **900**, the weld data include an execution count, a voltage sum, a voltage squared sum, an amperage sum, and an amperage squared sum. The execution count starts at zero and gets incremented by one for each sampling period (e.g., every 120 kHz). The voltage sum and the amperage sum start at zero and get increased by the sampled voltage and the sampled amperage, respectively, at each sampling period. Similarly, the voltage squared sum and the amperage squared sum start at zero and get increased by the square of the sampled voltage and the square of the sampled amperage, respectively, at each sampling period.

After a predefined sampling period, in step **906**, the sampled weld data is passed on for further processing (as described below), the weld data values are reset to zero, and the sampling process (i.e., step **904**) is repeated. In one exemplary embodiment, the sampling period is 250 ms. Each collection of sampled weld data forms an analysis packet. After further processing of the analysis packet (e.g., every 250 ms), additional weld data is available representing a current weld quality rating for the corresponding state. This additional weld data could be graphed and/or averaged. The average of these ratings over the length of the weld (i.e., the weld cycle) provides an overall quality indicator for the weld.

The further processing of the weld data of each analysis packet that occurs in step **906**, for each of the sampled states,

results in the calculation of additional weld data. The additional weld data include an execution count, a voltage average, a voltage root mean square (RMS), a voltage variance, an amperage average, an amperage RMS, and an amperage variance. The value of the execution count of the additional weld data is copied from the value of the execution count of the weld data. The voltage average is calculated as the voltage sum (from the weld data) divided by the execution count. The voltage RMS is calculated as the square root of the quotient obtained by dividing the voltage squared sum (from the weld data) by the execution count. The voltage variance is calculated as the voltage RMS minus the voltage average. The amperage average is calculated as the amperage sum (from the weld data) divided by the execution count. The amperage RMS is calculated as the square root of the quotient obtained by dividing the amperage squared sum (from the weld data) by the execution count. The amperage variance is calculated as the amperage RMS minus the amperage average.

After step **906**, subsequent processing depends on whether the current weld is a training weld to be used in determining weld quality parameters or a normal weld to be evaluated against such weld quality parameters. Thus, in step **908**, it is determined whether the current weld is a training weld or a normal weld. In one exemplary embodiment, the default condition is that a weld is a normal weld unless otherwise indicated (e.g., by user input).

If the current weld is determined in step **908** to be a training weld, the following additional weld data values are saved for a significant portion of the training weld (e.g., 20-30 seconds): the execution count, the voltage average, the voltage variance, the amperage average, and the amperage variance, whereas the other weld data values and additional weld data values can be disregarded. The significant portion of the training weld is the training period. In one exemplary embodiment, the training period corresponds to at least 80 consecutive analysis packets (i.e., sampling periods).

Thereafter, in step **910**, weld quality parameters are calculated using the additional weld data values saved during the training period. For example, the following weld quality parameters are calculated for each of the sampled states: a quality execution count average, a quality execution count standard deviation, a quality voltage average, a quality voltage standard deviation, a quality amperage average, a quality amperage standard deviation, a quality voltage variance average, a quality voltage variance standard deviation, a quality amperage variance average, and a quality amperage variance standard deviation.

The quality execution count average is calculated as the average of the execution counts from all of the analysis packets processed during the training period. The execution counts could be rounded to integers. The quality execution count standard deviation is calculated as the standard deviation of the execution count from each analysis packet processed during the training period relative to the quality execution count average. The quality voltage average is calculated as the average of the voltage averages from all of the analysis packets processed during the training period. The quality voltage standard deviation is calculated as the standard deviation of the voltage average from each analysis packet processed during the training period relative to the quality voltage average. The quality amperage average is calculated as the average of the amperage averages from all of the analysis packets processed during the training period. The quality amperage standard deviation is calculated as the standard deviation of the amperage average from each analysis packet processed during the training period relative to the quality amperage average. The quality voltage variance average is

calculated as the average of the voltage variances from all of the analysis packets processed during the training period. The quality voltage variance standard deviation is calculated as the standard deviation of the voltage variance from each analysis packet processed during the training period relative to the quality voltage variance. The quality amperage variance average is calculated as the average of the amperage variances from all of the analysis packets processed during the training period. The quality amperage variance standard deviation is calculated as the standard deviation of the amperage variance from each analysis packet processed during the training period relative to the quality amperage variance. As noted above, these quality parameters, when based on delivery of a confirmed good or otherwise acceptable weld, can be used as benchmarks to measure or otherwise rate subsequent welds.

If the current weld is determined in step 908 to be an evaluation weld (i.e., a weld requiring evaluation of its quality), as opposed to a training weld, none of the weld data or additional weld data need be saved. Instead, the results of various quality calculations are obtained and saved. These quality calculations include initially detecting, in step 914, the presence of various outliers. An outlier is a data point or value that is more than a threshold distance from a mean value to which the data point or value contributes. In one exemplary embodiment, an outlier is a value that falls outside the limit of three standard deviations from the mean value.

In the weighting method 900, the outliers sought in step 914 include execution outliers, voltage outliers, voltage variance outliers, amperage outliers, and amperage variance outliers. For each of the monitored states, each of the analysis packets are evaluated to detect the presence of any of these outliers.

If an analysis packet satisfies the following relationship, it is considered an execution outlier: absolute value of (execution count–quality execution count average) $>(3\times$ quality execution count standard deviation). If an analysis packet satisfies the following relationship, it is considered a voltage outlier: absolute value of (voltage average–quality voltage average) $>(3\times$ quality voltage standard deviation). If an analysis packet satisfies the following relationship, it is considered a voltage variance outlier: absolute value of (voltage variance–quality voltage variance average) $>(3\times$ quality voltage variance standard deviation). If an analysis packet satisfies the following relationship, it is considered an amperage outlier: absolute value of (amperage average–quality amperage average) $>(3\times$ quality amperage standard deviation). If an analysis packet satisfies the following relationship, it is considered an amperage variance outlier: absolute value of (amperage variance–quality amperage variance average) $>(3\times$ quality amperage variance standard deviation).

After detection of these outliers, a two-step weighted sum (i.e., from steps 916 and 918) of each outlier is used in calculating a quality indicator for the corresponding analysis packets.

The first step (i.e., step 916) in weighting each of the outliers is determined by the magnitude of the outlier relative to a three standard deviation limit. In general, approximately 0.3% of the data points or values could fall outside the limit of three standard deviations and, thus, be considered an outlier. The weighting of the outlier increases as its value increases above the limit of three standard deviations. The outlier is weighted at a full 100% at four standard deviations and is weighted at a maximum of 200% at five standard deviations. In general, the probability of a fully (i.e., 100%) weighted outlier occurring in a normal data set is 1 in 15,787.

Thus, in step 916, each of the outliers is weighted in accordance with this approach. The weight to be applied to each execution outlier is calculated as the absolute value of (amount above three standard deviation limit/quality execution count standard deviation), with a maximum weight value being 2.0. The weight to be applied to each voltage outlier is calculated as the absolute value of (amount above three standard deviation limit/quality voltage standard deviation), with a maximum weight value being 2.0. The weight to be applied to each voltage variance outlier is calculated as the absolute value of (amount above three standard deviation limit/quality voltage variance standard deviation), with a maximum weight value being 2.0. The weight to be applied to each amperage outlier is calculated as the absolute value of (amount above three standard deviation limit/quality amperage standard deviation), with a maximum weight value being 2.0. The weight to be applied to each amperage variance outlier is calculated as the absolute value of (amount above three standard deviation limit/quality amperage variance standard deviation), with a maximum weight value being 2.0.

The second step (i.e., step 918) in weighting each of the outliers is determined by the execution count of the outlier's state. In particular, the value of each outlier is multiplied by the execution count of the outlier's state, thereby accounting for the time contribution of the state relative to the overall wave shape. In this manner, states that have larger execution counts (i.e., execution times) produce outliers with correspondingly heavier weighting. Consequently, as the execution time for a particular outlier increases, the weight of the outlier will also increase.

The weighting of the outliers, in steps 916 and 918, produce a set of final weighted outliers including final weighted execution outliers, final weighted voltage outliers, final weighted voltage variance outliers, final weighted amperage outliers, and final weighted amperage variance outliers. These final weighted outliers are summed in step 920 to produce a final weighted outlier sum for each analysis packet. Thereafter, determination of a quality indicator for each of the analysis packets is calculated, in step 922, as the quotient obtained by dividing a perfect quality value minus the final weighted outlier sum by the perfect quality value. The perfect quality value is equal to the execution count for the analysis packet multiplied by the number of outlier categories (i.e., in this case five).

Thus, an instantaneous quality indicator (i.e., for the current completed analysis packet) can be determined during the welding process and communicated to the welder or otherwise utilized. In this manner, potential problems can be detected as they occur, i.e., during the welding process, as opposed to only after the weld is complete, when it is likely too late to take any corrective action.

Furthermore, the average of the quality indicators aggregated up to any point of time during the welding process can be averaged to determine a quality indicator of the weld up to that point of time. For example, after the welding process is complete, all of the individual quality indicators can be averaged to obtain an overall quality indicator, score, grade, rating or the like for the completed weld. The overall quality indicator for the weld can be compared against a predetermined quality indicator (e.g., derived from a training weld) that reflects the minimum quality indicator value for an acceptable weld.

In this manner, a quality of a weld can be determine accurately, efficiently, consistently, and/or automatically, in real-time or near real-time. This is particularly advantageous since visible inspection of a weld is not always sufficient to gauge its quality and since an operator might not detect or otherwise

appreciate deviations or other problems during the welding process that can affect overall weld quality.

In some exemplary embodiments, a quality indicator (i.e., a weld score) for a weld is an effective tool for evaluating welds being repetitively produced under substantially the same conditions and according to substantially the same arc welding process, such as during an automated (e.g., robotic) welding process. By calculating instantaneous, periodic, and/or overall weld scores for each weld, an automated quality control process can be adapted for the arc welding process. In particular, a minimum acceptable weld score or range of acceptable weld scores is initially identified as a threshold, according to the weld conditions and the arc welding process. Thereafter, each weld has its (instantaneous, periodic, and/or overall) weld score compared against the threshold to quickly and accurately determine whether the weld should be accepted or rejected. Additionally, by evaluating trends across the weld scores for a production run or set of runs, problems in the production process can be more readily identified, and/or the production process can be more readily optimized.

A conceptual production line **1000** is shown in FIG. **10**, wherein a first weld score **S1 1002**, a second weld score **S2 1004**, and a third weld score **S3 1006** are associated with welds performed on a first workpiece **WP1 1008**, a second workpiece **WP2 1010**, and a third workpiece **WP3 1012**, respectively, by a welder or welding station **1014** including an integrated monitor **M 1016**. One of ordinary skill in the art will appreciate that the different welds could be performed on the same workpiece.

The weld scores are then compared against a predetermined acceptable weld score threshold to determine whether each of the welds should be accepted or rejected. This comparison can be done by the welder/welding station or by a separate device or at a separate location (e.g., an evaluation station **1018**). In one exemplary embodiment, the comparison between the weld score and the threshold is performed manually. In one exemplary embodiment, an automated and manual comparison are performed. In one exemplary embodiment, the weld score is used to determine whether a manual inspection of the corresponding weld is warranted. In one exemplary embodiment, the weld scores are used, at least in part, to determine an overall efficiency of the production line.

In one exemplary embodiment, one or more evaluation stations **1018** are situated along the production line **1000** to measure welds at specified stages of the production process. If an evaluation station **1018** determines that a weld score for a weld meets or exceeds a predetermined acceptable weld score threshold, the evaluation station **1018** accepts the weld by issuing an accept weld command **1020**. In response to the accept weld command **1020**, the workpiece including the acceptable weld is allowed to continue along the production line **1000** for further processing.

Conversely, if the evaluation station **1018** determines that the weld score for the weld falls below a predetermined acceptable weld score threshold, the evaluation station **1018** rejects the weld by issuing a reject weld command **1022**. In response to the reject weld command **1022**, the workpiece including the unacceptable weld is routed off of the production line **1000** or otherwise removed from the production line **1000** (e.g., manually removed). Thereafter, the workpiece having the rejected weld can be subjected to further processing, for example, rehabilitating or otherwise repairing the rejected weld, or recycling the workpiece entirely.

In one exemplary embodiment, each accept weld command **1020** and/or reject weld command **1022** is logged or

otherwise stored for later review and analysis. In this manner, trends relating to the welding process and/or the production process can be more readily identified, which in turn, may make it easier to increase the overall efficiency of the production line utilizing the welding process.

In some exemplary embodiments, quality indicators (i.e., weld scores) computed for welds can be used in an innovative approach to providing instruction or otherwise teaching an operator manually performing an arc welding process. In particular, as the operator is using a welder (e.g., the electric arc welder **10**) to create the weld, instantaneous and/or periodic weld scores are determined for the weld by the welder (e.g., via a monitor **M** of the welder) and are used to provide direct feedback to the operator relating to the current quality of the weld. As noted above, these weld scores are based on weighted, statistical measurements that more accurately reflect weld quality as compared to a mere visual inspection of the weld. In particular, the weld scores are compared against a predetermined acceptable weld score or range of acceptable weld scores to determine whether any corrective action is necessary by the operator. Additionally, the weld scores are evaluated over time to determine whether any trend in moving away from an acceptable weld score (e.g., as evidenced by a continuing reduction in the weld score) is present.

A method of instruction **1100**, according to one exemplary embodiment, is shown in FIG. **11**. The method **1100** begins with an operator starting to perform a welding process in step **1102**.

During the welding process, a weld score is periodically calculated (based on one or more sampled or otherwise measured parameters), in step **1104**, to reflect a current status of the weld. The weld score can be calculated as an instantaneous measurement reflecting the current status of the weld or as an average of several measurements reflecting the status of the weld over a period of time (corresponding to the measurements) during the welding process. In one exemplary embodiment, the weld score is calculated by averaging all of the measurements taken since the welding process started, which reflects a current overall status of the weld.

Next, the weld score is compared to a predetermined threshold weld score in step **1106**. The threshold weld score is a minimum weld score for a good or otherwise acceptable weld status. If the weld score is greater than or equal to the threshold weld score, the current status of the weld is determined to be good in step **1108**. Otherwise, the current status of the weld is determined to be bad in step **1108**.

If the current status of the weld is good, the operator is provided with an indication that the weld is good, in step **1110**, which suggests that the welding process is being performed properly. Thereafter, the current status of the weld is logged, in step **1112**, for later review, analysis, and/or other use. The method of instruction **1100** then continues to monitor the welding process being performed by the operator, as described above.

If the current status of the weld is bad, the operator is provided with an indication that the weld is bad, in step **1114**, which suggests that the welding process is being performed improperly. Thereafter, the current status of the weld is logged, in step **1118**, for later review, analysis, and/or other use. The method of instruction **1100** then continues to monitor the welding process being performed by the operator, as described above.

The aforementioned indications can be provided to the operator in any manner sufficient to inform the operator during the welding process. In one exemplary embodiment, the indication is provided to the operator visually, such as on a

display device integrated with or in close proximity to the welder. In one exemplary embodiment, the instruction is visually displayed on a protective visor or headgear worn by the operator. In one exemplary embodiment, the instruction is provided to the operator audibly, such as through a speaker integrated with or in close proximity to the welder. In one exemplary embodiment, the instruction is audibly played in protective headgear worn by the operator.

In one exemplary embodiment, if the current status of the weld is bad, the operator receives instruction on what corrective action or actions should be taken in step 1116. In one exemplary embodiment, the instruction is provided in real-time during the welding process. The instruction could, for example, involve a suggested change in a position of an electrode (i.e., wire) relative to the workpiece or a suggested change in a rate of movement of the wire relative to the workpiece.

Various devices and techniques could be used to determine possible corrective actions to be taken, such as modeling operator and/or welding conditions during a welding process that results in a verified good weld and using the resulting model data to evaluate other operators carrying out similar welding processes under similar conditions. Artificial intelligence and related simulations could also be used to build such a model. Furthermore, sensors could be used to build such a model.

In one exemplary embodiment, one or more sensors are used to determine aspects of the welding process, for example, a current temperature of the workpiece, a level of shielding gas being delivered, and/or a composition of the shielding gas. In one exemplary embodiment, one or more sensors are used to determine environmental conditions that could affect the welding process, for example, wind conditions and/or humidity conditions. In one exemplary embodiment, one or more sensors are used to determine operator conditions that could affect the welding process, for example, the distance of the operator's hand from the workpiece and/or the angle of the operator's hand from the workpiece. Data from these or other sensors is compared to model data to identify the instruction on what corrective action or actions should be taken by the operator.

In one exemplary embodiment, the corrective action instruction is provided to the operator visually, such as on a display device integrated with or in close proximity to the welder. In one exemplary embodiment, the instruction is visually displayed on a protective visor or headgear worn by the operator. In one exemplary embodiment, the instruction is provided to the operator audibly, such as through a speaker integrated with or in close proximity to the welder. In one exemplary embodiment, the instruction is audibly played in protective headgear worn by the operator.

Thus, the method of instruction 1100 provides real-time feedback to the operator during the welding process, such that the operator readily knows when the weld is moving from a good condition toward a bad condition and when the weld is moving from a bad condition toward a good condition. Furthermore, the method of instruction 1100 can suggest corrective action intended to improve the current (and thus overall) condition of the weld. As changes in the weld condition are often attributable to the actions of the operator, the feedback provided by the method of instruction 1100 (including any suggested corrective action) teaches the operator good welding techniques. Furthermore, good welding techniques of the operator are reinforced by the continued confirmation of a good weld status.

The method of instruction 1100, or aspects thereof, can also readily be adapted or otherwise applied to a simulated

welding process. In one exemplary embodiment, the method of instruction 1100 is applied to a welding simulator utilizing virtual reality technology.

In some exemplary embodiments, a quality indicator (i.e., a weld score) computed for a weld performed by an operator can be used in an innovative approach to certifying the operator with respect to a particular welder, welding process, or welding course, similar to how grades are used in general education. For example, the weld scores (e.g., an overall weld score) calculated in accordance with the method of instruction 1100, or aspects thereof, provide a convenient platform for certifying the operator. The operator must obtain a weld score or scores that exceed predefined threshold weld scores to be certified with respect to the welder, welding process, or welding course. If the operator fails to be certified, the method of instruction 1100 can identify areas that need improvement to the operator. As described herein, additional functionality (e.g., provided by software running in or external to the welder) can be used to measure other parameters that might be useful in certifying the operator. For example, the method of instruction 1100 could be modified to include tracking how much time the operator spent actually welding during the welding process or course. As another example, the method of instruction 1100 could be modified to include tracking the amount of consumables (e.g., wire) used by the operator during the welding process or course.

In addition to being used to certify an operator, the weld scores (and other parameters) can also be used to differentiate one operator from another. For example, notwithstanding that two operators both achieve passing scores and are certified with respect to a particular welder, welding process, or welding course, the scores of the two operators might be vastly different. Accordingly, a certified operator with a much higher score could be chosen over another certified operation having a lower score.

In some exemplary embodiments, quality indicators (i.e., weld scores) computed for welds and other related parameters and information can be used to assist an instructor teaching multiple students a welding technique, process, program, course, or the like. A welding class often includes a theoretical component and a practical component. The theoretical component is generally taught in the form of a lecture, discussion, or demonstration in a classroom or similar setting. Typically, a welding school or other environment for teaching students the practical component of the class will include individual locations such as booths, similar to welding stations in a factory. Each student is assigned to his or her own booth for performing the practical component of the course.

It is rather easy for the instructor to approximate how much time each student spends on the theoretical component of the class, for example, by tracking each student's class attendance and/or participation during discussions relating to the theoretical component. However, it is difficult for the instructor to gauge how much time each student actually spends on the practical component of the class because the instructor cannot be at all of the booths all of the time. For example, the booths may be constructed and/or arranged such that the instructor's line of sight only extends to a single booth at a time, i.e., the booth at which the instructor is currently present. The students at the other booths could be doing something other than welding (e.g., eating, sleeping, talking on the phone) without the instructor knowing. It is also difficult for the instructor to readily determine which of the students would most likely benefit from the instructor's personal attention, at any given time. Thus, the instructor may wind up

devoting time to one student notwithstanding that another student has a greater need for the instructor's personal attention.

A system **1200** for monitoring students learning a welding technique, process, program, course, or the like, such as an arc welding process, according to one exemplary embodiment, is shown in FIG. **12**. The system **1200** includes an area of instruction **1202**, such as a classroom or shop, in which eight booths **1204**, **1206**, **1208**, **1210**, **1212**, **1214**, **1216**, and **1218** are situated. Each of the booths includes a welder. In particular, a first welder **W1 1220** is located in the first booth **1204**, a second welder **W2 1222** is located in the second booth **1206**, a third welder **W3 1224** is located in the third booth **1208**, a fourth welder **W4 1226** is located in the fourth booth **1210**, a fifth welder **W5 1228** is located in the fifth booth **1212**, a sixth welder **W6 1230** is located in the sixth booth **1214**, a seventh welder **W7 1232** is located in the seventh booth **1216**, and an eighth welder **W8 1234** is located in the eighth booth **1218**. Furthermore, a student is assigned to each booth. In particular, a first student **S1 1236** is assigned to work in the first booth **1204**, a second student **S2 1238** is assigned to work in the second booth **1206**, a third student **S3 1240** is assigned to work in the third booth **1208**, a fourth student **S4 1242** is assigned to work in the fourth booth **1210**, a fifth student **S5 1244** is assigned to work in the fifth booth **1212**, a sixth student **S6 1246** is assigned to work in the sixth booth **1214**, a seventh student **S7 1248** is assigned to work in the seventh booth **1216**, and an eighth student **S8 1250** is assigned to work in the eighth booth **1218**.

The area of instruction **1202** is situated such that an instructor **1252** can freely move from one booth to another to interact with the students.

In one exemplary embodiment, each of the welders **W1**, **W2**, **W3**, **W4**, **W5**, **W6**, **W7**, and **W8** includes an integrated monitor **M**, like the welder **10** shown in FIG. **1**. When a student is using a welder to create a weld, instantaneous and/or periodic weld scores are determined for the weld by the welder (via the monitor **M**) and are used to provide direct feedback to the student relating to the current quality of the weld. As described herein, these weld scores are based on weighted, statistical measurements that more accurately reflect weld quality as compared to a mere visual inspection of the weld. In particular, the weld scores are compared against a predetermined acceptable weld score or range of acceptable weld scores (e.g., ascertained from a prior baseline weld) to determine whether any corrective action is necessary by the student. Additionally, the weld scores are evaluated over time to determine whether any trend in moving away from an acceptable weld score (e.g., as evidenced by a continuing reduction in the weld score) is present.

Each of the welders **W1**, **W2**, **W3**, **W4**, **W5**, **W6**, **W7**, and **W8** is in communication with a production monitoring system (PMS) **1254** over a network **1256**. The network **1256** can be a wired or a wireless network. In one exemplary embodiment, the network **1256** is an Ethernet network.

The PMS **1254** can be implemented using software, hardware, and combinations thereof, without departing from the spirit and the scope of the general inventive concepts. In one exemplary embodiment, the PMS **1254** is implemented as software running on a general purpose computer (e.g., a PC) with peripherals such as a display device **1258** and a data store **1260** connected thereto. In one exemplary embodiment, the PMS **1254** could include logic integrated with each of the welders, as in the case of the monitors **M**. As noted above, the PMS **1254** is in data communication with the welders **W1**, **W2**, **W3**, **W4**, **W5**, **W6**, **W7**, and **W8** over the network **1256**.

The PMS **1254** is a weld data collection and monitoring tool that is operable, for example, to collect short-term and long-term welding logs complete with statistics for each recorded weld. The PMS **1254** can also track other production related parameters and conditions, such as wire consumption. In the system **1200**, the PMS **1254** collects data from each of the welders **W1**, **W2**, **W3**, **W4**, **W5**, **W6**, **W7**, and **W8** to determine an amount of time spent by the respective students **S1**, **S2**, **S3**, **S4**, **S5**, **S6**, **S7**, and **S8** in creating the weld. The amount of time spent by each of the students **S1**, **S2**, **S3**, **S4**, **S5**, **S6**, **S7**, and **S8** (i.e., the welding times) can be saved by the PMS **1254** to the data store **1260** for later retrieval and use. Additionally, the PMS **1254** receives the weld scores from each of the welders **W1**, **W2**, **W3**, **W4**, **W5**, **W6**, **W7**, and **W8** over the network **1256**, which can then be saved by the PMS **1254** to the data store **1260** for later retrieval and use. Thus, the PMS **1254** is capable of generating and storing logs of welding times and weld scores for multiple students over multiple evaluation periods, which can be a tremendous resource for the instructor **1252** in teaching and assessing the students.

Additionally, the PMS **1254** can display, in real time, the current welding times for each of the students **S1**, **S2**, **S3**, **S4**, **S5**, **S6**, **S7**, and **S8**, in combination with the current weld scores for each of the students **S1**, **S2**, **S3**, **S4**, **S5**, **S6**, **S7**, and **S8**, on the display device **1258**. In this manner, the instructor **1252**, by observing the display device **1258**, can get an instant and accurate assessment of the current status of each of the students and their respective welds. This allows the instructor **1252** to better proportion his or her time in relation to those students exhibiting the greatest need.

In the system **1200**, the welding times and weld scores can be displayed in any manner, for example, as numerical data and/or as graphical data. In one exemplary embodiment, the PMS **1254** provides a web-based user interface that supports accessing data, viewing data, generating reports, etc. via a web browser.

The system **1200** is readily scalable to accommodate any number of students, as well as multiple instructors.

A method **1300** of monitoring students learning a welding technique, process, program, course, or the like, such as an arc welding process, according to one exemplary embodiment, is shown in FIG. **13**. The method **1300** involves multiple students performing the arc welding process in step **1302**. In one exemplary embodiment, the students perform substantially the same arc welding process under substantially the same conditions and at substantially the same time.

During the arc welding process, a weld score is periodically calculated (based on one or more sampled or otherwise measured parameters) for each student, in step **1304**, to reflect a current status of the student's weld. The weld score can be calculated as an instantaneous measurement reflecting the current status of the student's weld or as an average of several measurements reflecting the status of the student's weld over a period of time (corresponding to the measurements) during the arc welding process. In one exemplary embodiment, the student's weld score is calculated by averaging all of the measurements taken since the arc welding process started, which reflects a current overall status of the student's weld.

During the evaluation period of the method **1300**, an amount of time the each student spends performing the arc welding process (i.e., actually welding) is determined in step **1306**. Operational data collected from the welder of each student can be used to determine the students' welding times.

Each weld score is associated with its corresponding student in step **1308**. Similarly, each welding time is associated with its corresponding student in step **1308**. Identifying infor-

mation (e.g., a serial number) from the welder assigned to each student can be used to associate data collected from and/or generated by the welders (e.g., the weld score, the welding time) with the respective students.

Once the weld scores and welding times are associated with the respective students, this information can be output in any manner in step 1310. For example, a report of all of the students and their respective weld scores and welding times can be output to a display device, such as a monitor. As another example, information on the students and their respective weld scores and welding times can be logged and stored in a data store, such as a disk drive or flash drive, for later retrieval and use. In one exemplary embodiment, the information is output periodically. In one exemplary embodiment, the information is output at the end of the evaluation period.

The weld scores and/or the welding times can also be used to generate additional identifying information for the students. For example, the weld score and/or the welding time for a student can be compared against predetermined thresholds. In this manner, based on the weld score and/or the welding time for a student, a pass or a fail determination can be determined for the weld of the student.

In some exemplary embodiments, weld scores computed for welds can be used in an innovative approach to identifying potential cost savings for a welding process. In one exemplary embodiment, a cost analysis (e.g., cost-effective analysis, cost-benefit analysis) is performed for a welding process based on a series of welds performed according to the welding process. Data 1400 corresponding to exemplary welds, as shown in FIGS. 14A-14B, can be used in performing the cost analysis.

First, a plurality of weld conditions 1402 that affect overall weld quality are selected. For example, in FIGS. 14A and 14B, the weld conditions 1402 include wire characteristics (e.g., wire composition 1404, wire diameter, coating), workpiece characteristics (e.g., workpiece composition 1406, workpiece thickness), a shielding gas flow rate 1408, a shielding gas composition 1410, and/or a workpiece pre-heat temperature 1412. Next, one of these weld conditions 1402 is varied, as indicated at 1414, across the series of welds, while all of the remaining weld conditions 1402 are fixed, as indicated at 1414, across the series of welds.

For each of the welds in the series, a weld score 1416 is also calculated based on the current weld conditions 1402, 1414. The weld score 1416 represents a measure of the overall quality of the weld created under the weld conditions. As noted above, these weld scores are based on weighted, statistical measurements that more accurately reflect weld quality as compared to a mere visual inspection of the weld.

Additionally, for each of the welds in the series, a cost for creating the weld is determined. In one exemplary embodiment, the cost includes monetary expenditures related to producing the weld, represented as a monetary cost 1418 for the weld. In one exemplary embodiment, the cost includes a total time required to complete the weld, represented as a time cost 1420 for the weld. Each weld in the series is associated with its corresponding weld score and cost.

FIGS. 14A and 14B include, respectively, data 1400 for two welds in a series of welds wherein among the weld conditions 1402, the wire composition 1404, the workpiece composition 1406, the shielding gas composition 1410, and the workpiece pre-heat temperature 1412 are fixed, as shown at 1414, across the series of welds, while the shielding gas flow rate 1408 is varied (e.g., incrementally increased or decreased), as shown at 1414, across the series of welds.

For the weld corresponding to FIG. 14A, a monetary cost 1418 of a, a time cost 1420 of b, and a weld score 1416 of c are calculated or otherwise determined. For the weld corresponding to FIG. 14B, a monetary cost 1418 of d, a time cost 1420 of e, and a weld score 1416 of f are calculated or otherwise determined. Thus, if it is determined that $a < d$, $b < e$, and $c = f$, it can be deduced that the shielding gas flow rate 1408 of FIG. 14A is superior to the shielding gas flow rate 1408 of FIG. 14B, since both a cost and time savings are realized without any reduction in overall weld quality by the shielding gas flow rate 1408 of FIG. 14A as compared to the shielding gas flow rate 1408 of FIG. 14B. If it is instead determined that $a < d$, $b \gg e$, and $c = f$, it can be deduced that the shielding gas flow rate 1408 of FIG. 14A provides a cost savings without any reduction in overall weld quality, but at a substantially increased time cost, as compared to the shielding gas flow rate 1408 of FIG. 14B.

In this manner, a user will be able to readily identify the impact the varied weld condition has on overall weld quality in the series and, thus, in the corresponding welding process. In this manner, the user can determine whether varying the weld condition (and in what manner) will allow the user to obtain a more desired weld quality, a more desired cost, or both. Consequently, as more welds are performed and the corresponding data analyzed, the impact of any one or more weld conditions on the overall welding process can be readily determined and evaluated, such that more informed cost saving decisions (e.g., relative to money, time, and quality tradeoffs) can be made.

The cost analysis could be expanded to include additional series of welds, wherein different weld conditions are varied in the different series. In this manner, the user can identify a desired value or setting for a plurality of the weld conditions to achieve a desired outcome (e.g., acceptable weld quality and acceptable cost). These desired values or settings for the weld conditions could then be saved in a profile associated with the welder and the welding process for subsequent retrieval and use for the same welder and welding process, thereby increasing the likelihood that the user will again achieve the desired outcome.

In one exemplary embodiment, a plurality of such profiles (i.e., sets of selected weld parameters and/or weld conditions) are saved, i.e., as pre-sets, such that the profiles can be accessed by a user beginning a welding process. In one exemplary embodiment, a plurality of pre-sets are presented to a user along with a weld score corresponding to each pre-set. Each weld score quantifies an overall quality of a weld previously obtained using the weld parameters and weld conditions associated with the pre-set. As noted above, these weld scores are based on weighted, statistical measurements that more accurately reflect weld quality as compared to a mere visual inspection of the weld. The user can then select one of the pre-sets for performing the welding process, thereby increasing the likelihood that the user will achieve the same or a substantially similar weld as that previously produced using the weld parameters and weld conditions associated with the pre-set. In one exemplary embodiment, a user interface is provided to allow the user to filter out pre-sets that do not match criteria input by the user, for example, filtering out those pre-sets that have an associated weld score below an input threshold.

FIG. 15 shows pre-sets 1500, according to one exemplary embodiment. Each of the pre-sets 1500 includes an identifying pre-set number 1502, a set of weld conditions 1504, welder information 1506, welding process information 1508, a monetary cost 1510, a time cost 1512, and an associated weld score 1514. A first pre-set 1516, having pre-set number

01, is associated with weld conditions **1504** having values a, b, c, d, and e and a welder M. The first pre-set **1516** corresponds to a welding process O. If a user selects the first pre-set **1516** (i.e., pre-set 01) for performing the welding process O with the welder M under the welding conditions a, b, c, d, and e, the user can expect a weld resulting from the welding process O to have a monetary cost of approximately t, a time cost of approximately v, and a weld score of approximately x. The pre-sets **1500** can include additional pre-sets, such as a second pre-set **1518**, associated with different combinations of weld conditions **1504**, welders **1506**, and/or welding processes **1508**.

The above description of specific embodiments has been given by way of example. From the disclosure given, those skilled in the art will not only understand the general inventive concepts and attendant advantages, but will also find apparent various changes and modifications to the structures and methods disclosed. For example, the general inventive concepts are not typically limited to one of a manual welding process or an automated (e.g., robotic) welding process but instead are readily adaptable to either. Furthermore, the general inventive concepts are readily adaptable to different welding processes and techniques (e.g., all variations of arc welding such as Stick and TIG welding). It is sought, therefore, to cover all such changes and modifications as fall within the spirit and scope of the general inventive concepts, as defined by the appended claims, and equivalents thereof.

The invention claimed is:

1. A method of training an operator to perform an arc welding process by providing feedback to said operator during said arc welding process, said method comprising:
 - (a) monitoring an electric arc welder associated with said operator, as said electric arc welder is used by said operator to perform said arc welding process by creating actual welding parameters between an advancing wire and a workpiece with said arc welding process controlled by command signals to a power supply of said electric arc welder;
 - (b) during formation of a weld by said operator according to said arc welding process, periodically generating a numerical score indicating a current quality measurement of said weld, each numerical score generated by:
 - (b1) generating a series of rapidly repeating wave shapes, each wave shape constituting a weld cycle with a cycle time;
 - (b2) dividing said wave shapes into states;
 - (b3) measuring a selected weld parameter occurring in one of said states at an interrogation rate over a period of time to obtain a data set for said selected weld parameter;
 - (b4) for each period of time, calculating a quality value for said selected weld parameter from said data set;
 - (b5) comparing each quality value to an expected quality value to determine if a difference between said quality value and said expected quality value exceeds a predetermined threshold;
 - (b6) if said difference exceeds said threshold, weighting said quality value with a magnitude weight based on said difference, and weighting said quality value with a time contribution weight based on a time contribution of said state to its wave shape; and
 - (b7) using said quality values, including any weighted quality values, obtained during said arc welding process to determine said numerical score; and
 - (c) comparing said current quality measurement to a predetermined threshold weld score, wherein:

- (c1) if said current quality measurement is greater than or equal to said predetermined threshold weld score, indicating to said operator that performance of said arc welding process by said operator is satisfactory; and
 - (c2) if said current quality measurement is less than said predetermined threshold weld score, indicating to said operator that performance of said arc welding process by said operator is unsatisfactory.
2. The method of claim 1, wherein the indication in step (c) is provided to said operator visually.
 3. The method of claim 2, wherein the indication in step (c) is displayed on protective headgear worn by said operator.
 4. The method of claim 1, wherein the indication in step (c) is provided to said operator audibly.
 5. The method of claim 4, wherein the indication in step (c) is output to a speaker in protective headgear worn by said operator.
 6. The method of claim 1, wherein said numerical score generated in step (b) is an instantaneous measurement.
 7. The method of claim 1, wherein said numerical score generated in step (b) is based on a plurality of measurements taken over a period of time.
 8. The method of claim 1, further comprising (d) suggesting corrective action to said operator if performance of said arc welding process by said operator is determined to be unsatisfactory in step (c2).
 9. The method of claim 8, wherein said corrective action is provided to said operator in real time during said arc welding process.
 10. The method of claim 8, wherein said corrective action is provided to said operator visually.
 11. The method of claim 10, wherein said corrective action is displayed on protective headgear worn by said operator.
 12. The method of claim 8, wherein said corrective action is provided to said operator audibly.
 13. The method of claim 12, wherein said corrective action is output to a speaker in protective headgear worn by said operator.
 14. A method of training an operator to perform an arc welding process by providing feedback to said operator during said arc welding process, said method comprising:
 - (a) monitoring an electric arc welder associated with said operator, as said electric arc welder is used by said operator to perform said arc welding process by creating actual welding parameters between an advancing wire and a workpiece with said arc welding process controlled by command signals to a power supply of said electric arc welder;
 - (b) during formation of a weld by said operator according to said arc welding process, periodically generating a numerical score indicating a current quality measurement of said weld; and
 - (c) comparing said current quality measurement to a predetermined threshold weld score, wherein:
 - (c1) if said current quality measurement is greater than or equal to said predetermined threshold weld score, indicating to said operator that performance of said arc welding process by said operator is satisfactory; and
 - (c2) if said current quality measurement is less than said predetermined threshold weld score, indicating to said operator that performance of said arc welding process by said operator is unsatisfactory; and
 - (d) suggesting corrective action to said operator if performance of said arc welding process by said operator is determined to be unsatisfactory in step (c2),

wherein said corrective action is determined based on input from one or more sensors associated with at least one of said operator and said electric arc welder including its surrounding environment.

* * * * *