



US009059045B2

(12) **United States Patent**
Yamazaki et al.

(10) **Patent No.:** **US 9,059,045 B2**
(45) **Date of Patent:** ***Jun. 16, 2015**

(54) **SEMICONDUCTOR DEVICE AND MANUFACTURING METHOD THEREOF**

(71) Applicant: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi-shi, Kanagawa-ken (JP)

(72) Inventors: **Shunpei Yamazaki**, Setagaya (JP); **Hideaki Kuwabara**, Atsugi (JP); **Yasuyuki Arai**, Atsugi (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi-shi, Kanagawa-ken (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **14/082,659**

(22) Filed: **Nov. 18, 2013**

(65) **Prior Publication Data**
US 2014/0218652 A1 Aug. 7, 2014

Related U.S. Application Data

(60) Continuation of application No. 13/488,926, filed on Jun. 5, 2012, now Pat. No. 8,586,988, which is a continuation of application No. 12/789,382, filed on May 27, 2010, now Pat. No. 8,198,630, which is a

(Continued)

(30) **Foreign Application Priority Data**

Mar. 8, 2000 (JP) 2000-064227

(51) **Int. Cl.**
H01L 29/04 (2006.01)
H01L 27/12 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01L 27/1222** (2013.01); **G02F 1/13458** (2013.01); **G02F 1/136204** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC . H01L 21/725; H01L 27/12; H01L 29/66765; H01L 29/4908
USPC 257/57, 59, 72, 300
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,967,981 A 7/1976 Yamazaki
4,458,987 A 7/1984 Sasaki et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0557110 A 8/1993
EP 0629003 A 12/1994

(Continued)

OTHER PUBLICATIONS

Wolf.S et al., Silicon Processing for the VLSI ERA, 1986, vol. 1, pp. 161-175/335, Lattice Press.

(Continued)


Primary Examiner — Quoc Hoang

(74) *Attorney, Agent, or Firm* — Eric J. Robinson; Robinson Intellectual Property Law Office, P.C.

(57) **ABSTRACT**

A TFT is manufactured using at least five photomasks in a conventional liquid crystal display device, and therefore the manufacturing cost is high. By performing the formation of the pixel electrode **127**, the source region **123** and the drain region **124** by using three photomasks in three photolithography steps, a liquid crystal display device prepared with a pixel TFT portion, having a reverse stagger type n-channel TFT, and a storage capacitor can be realized, FIG. 2.

20 Claims, 17 Drawing Sheets



Related U.S. Application Data

continuation of application No. 12/222,687, filed on Aug. 14, 2008, now Pat. No. 7,728,334, which is a continuation-in-part of application No. 11/387,800, filed on Mar. 24, 2006, now Pat. No. 7,414,266, which is a division of application No. 10/852,260, filed on May 25, 2004, now Pat. No. 7,019,329, which is a division of application No. 10/144,067, filed on May 14, 2002, now Pat. No. 6,747,288, which is a division of application No. 09/566,735, filed on May 9, 2000, now Pat. No. 6,387,737.

(51) **Int. Cl.**

G02F 1/1345 (2006.01)
G02F 1/1362 (2006.01)
G02F 1/1368 (2006.01)
H01L 21/67 (2006.01)
H01L 29/66 (2006.01)

(52) **U.S. Cl.**

CPC **G02F1/136286** (2013.01); **G02F 1/1368** (2013.01); **G02F 2001/136231** (2013.01); **G02F 2001/136295** (2013.01); **H01L 21/67161** (2013.01); **H01L 21/67167** (2013.01); **H01L 21/67207** (2013.01); **H01L 21/67225** (2013.01); **H01L 21/67236** (2013.01); **H01L 29/66765** (2013.01); **H01L 27/1288** (2013.01); **H01L 27/124** (2013.01); **H01L 27/1255** (2013.01)

(56)

References Cited

U.S. PATENT DOCUMENTS

4,624,737 A 11/1986 Shimbo
 4,730,903 A 3/1988 Yamazaki et al.
 4,816,885 A 3/1989 Yoshida et al.
 4,914,503 A 4/1990 Shirato et al.
 4,960,719 A 10/1990 Tanaka et al.
 5,005,056 A 4/1991 Motai et al.
 5,028,551 A 7/1991 Dohjo et al.
 5,084,961 A 2/1992 Yoshikawa
 5,151,806 A 9/1992 Kawamoto et al.
 5,181,132 A 1/1993 Shindo et al.
 5,231,039 A 7/1993 Sakono et al.
 5,261,156 A 11/1993 Mase et al.
 5,346,833 A 9/1994 Wu
 5,362,660 A 11/1994 Kwasnick et al.
 5,418,635 A 5/1995 Mitsui et al.
 5,428,250 A 6/1995 Ikeda et al.
 5,459,598 A 10/1995 Carrington
 5,466,617 A 11/1995 Shannon
 5,478,766 A 12/1995 Park et al.
 5,491,352 A 2/1996 Tsuji
 5,532,180 A 7/1996 Boer et al.
 5,539,219 A 7/1996 Boer et al.
 5,561,074 A 10/1996 Koide et al.
 5,561,440 A 10/1996 Kitajima et al.
 5,583,675 A 12/1996 Yamada et al.
 5,622,814 A 4/1997 Miyata et al.
 5,644,147 A 7/1997 Yamazaki et al.
 5,648,662 A 7/1997 Zhang et al.
 5,668,379 A 9/1997 Ono et al.
 5,668,651 A 9/1997 Yamada et al.
 5,684,318 A 11/1997 Ayres et al.
 5,706,064 A 1/1998 Fukunaga et al.
 5,710,612 A 1/1998 Mase
 5,729,312 A 3/1998 Yamagishi et al.
 5,734,177 A 3/1998 Sakamoto
 5,739,549 A 4/1998 Takemura et al.
 5,739,880 A 4/1998 Suzuki et al.
 5,739,882 A 4/1998 Shimizu et al.
 5,739,887 A 4/1998 Ueda et al.
 5,744,820 A 4/1998 Matsushima et al.

5,757,453 A 5/1998 Shin et al.
 5,757,456 A 5/1998 Yamazaki et al.
 5,760,854 A 6/1998 Ono et al.
 5,766,977 A 6/1998 Yamazaki
 5,780,872 A 7/1998 Misawa et al.
 5,793,072 A 8/1998 Kuo
 5,798,812 A 8/1998 Nishiki et al.
 5,804,501 A 9/1998 Kim
 5,811,318 A 9/1998 Kweon
 5,811,328 A 9/1998 Zhang et al.
 5,811,835 A 9/1998 Seiki et al.
 5,811,846 A 9/1998 Miura et al.
 5,818,070 A 10/1998 Yamazaki et al.
 5,821,138 A 10/1998 Yamazaki et al.
 5,821,622 A 10/1998 Tsuji et al.
 5,825,449 A 10/1998 Shin
 5,828,433 A 10/1998 Shin
 5,830,785 A 11/1998 Sanson et al.
 5,831,710 A 11/1998 Colgan et al.
 5,834,327 A 11/1998 Yamazaki et al.
 5,838,400 A 11/1998 Ueda et al.
 5,844,643 A 12/1998 Onishi et al.
 5,847,687 A 12/1998 Hirakata et al.
 5,849,601 A 12/1998 Yamazaki
 5,852,487 A 12/1998 Fujimori et al.
 5,867,233 A 2/1999 Tanaka
 5,872,611 A 2/1999 Hirata et al.
 5,874,326 A 2/1999 Lyu
 5,880,794 A 3/1999 Hwang
 5,888,855 A 3/1999 Nagahisa et al.
 5,889,291 A 3/1999 Koyama et al.
 5,892,562 A 4/1999 Yamazaki et al.
 5,899,547 A 5/1999 Yamazaki et al.
 5,903,326 A 5/1999 Lee
 5,907,380 A 5/1999 Lien
 5,917,564 A 6/1999 Kim et al.
 5,917,567 A 6/1999 Oh et al.
 5,940,154 A 8/1999 Ukita et al.
 5,942,767 A 8/1999 Na et al.
 5,943,559 A 8/1999 Maeda
 5,953,093 A 9/1999 Hirata et al.
 5,959,599 A 9/1999 Hirakata
 5,966,189 A 10/1999 Matsuo
 5,968,850 A 10/1999 Jeong et al.
 5,977,562 A 11/1999 Hirakata et al.
 5,986,724 A 11/1999 Akiyama et al.
 5,990,998 A 11/1999 Park et al.
 5,994,721 A 11/1999 Zhong et al.
 5,995,190 A 11/1999 Nagae et al.
 5,998,229 A 12/1999 Lyu et al.
 5,998,230 A 12/1999 Gee-Sung et al.
 6,008,065 A 12/1999 Lee et al.
 6,008,869 A 12/1999 Oana et al.
 6,020,598 A 2/2000 Yamazaki
 6,025,216 A 2/2000 Ha
 6,025,891 A 2/2000 Kim
 6,025,892 A 2/2000 Kawai et al.
 6,037,017 A 3/2000 Kashiro
 6,038,003 A 3/2000 Kim
 6,054,975 A 4/2000 Kurokawa et al.
 6,055,028 A 4/2000 Nishi et al.
 6,061,112 A 5/2000 Ukita et al.
 6,064,358 A 5/2000 Kitajima et al.
 6,064,456 A 5/2000 Taniguchi et al.
 6,067,141 A 5/2000 Yamada et al.
 6,072,556 A 6/2000 Hirakata et al.
 6,072,557 A 6/2000 Kishimoto
 6,075,257 A 6/2000 Song
 6,097,458 A 8/2000 Tsuda et al.
 6,097,459 A 8/2000 Shimada et al.
 6,097,465 A 8/2000 Hiroki et al.
 6,114,184 A 9/2000 Matsumoto et al.
 6,118,502 A 9/2000 Yamazaki et al.
 6,124,155 A 9/2000 Zhang et al.
 6,124,604 A 9/2000 Koyama et al.
 6,124,606 A 9/2000 Boer et al.
 6,130,443 A 10/2000 Hong et al.
 6,130,729 A 10/2000 Oh et al.
 6,133,977 A 10/2000 Lee et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

6,140,158 A	10/2000	Rhee et al.	6,573,564 B2	6/2003	Yamazaki et al.
6,141,077 A	10/2000	Hirata et al.	6,583,065 B1	6/2003	Williams et al.
6,153,893 A	11/2000	Inoue et al.	6,587,162 B1	7/2003	Kaneko et al.
6,160,600 A	12/2000	Yamazaki et al.	6,599,791 B1	7/2003	Koyama et al.
6,166,396 A	12/2000	Yamazaki	6,600,160 B2 *	7/2003	Kobayashi et al. 250/370.14
6,166,399 A	12/2000	Zhang et al.	6,611,309 B2	8/2003	Park et al.
6,169,593 B1	1/2001	Kanaya et al.	6,617,644 B1	9/2003	Yamazaki et al.
6,172,728 B1	1/2001	Hiraishi	6,617,648 B1	9/2003	Yamazaki et al.
6,177,968 B1	1/2001	Okada et al.	6,621,102 B2	9/2003	Hirakata et al.
6,184,946 B1	2/2001	Ando et al.	6,624,864 B1	9/2003	Kubo et al.
6,188,452 B1	2/2001	Kim et al.	6,630,977 B1	10/2003	Yamazaki et al.
6,190,933 B1	2/2001	Shimabukuro et al.	6,642,074 B2	11/2003	Hong et al.
6,197,625 B1	3/2001	Choi	6,661,488 B1	12/2003	Takeda et al.
6,198,133 B1	3/2001	Yamazaki et al.	6,671,025 B1	12/2003	Ikeda et al.
6,208,390 B1	3/2001	Ejiri et al.	6,697,129 B1	2/2004	Nishi et al.
6,208,395 B1	3/2001	Kanoh et al.	6,709,901 B1	3/2004	Yamazaki et al.
6,215,541 B1	4/2001	Song et al.	6,743,650 B2	6/2004	Hirakata et al.
6,218,219 B1	4/2001	Yamazaki et al.	6,747,288 B2	6/2004	Yamazaki et al.
6,218,221 B1	4/2001	Sah	6,756,258 B2	6/2004	Zhang et al.
6,221,520 B1	4/2001	Takaki et al.	6,762,082 B2	7/2004	Yamazaki et al.
6,222,600 B1	4/2001	Hirano	6,762,813 B1	7/2004	Zhang et al.
6,222,603 B1	4/2001	Sakai et al.	6,771,342 B1	8/2004	Hirakata et al.
6,235,561 B1	5/2001	Seiki et al.	6,774,974 B1	8/2004	Matsuyama
6,239,854 B1	5/2001	Hirakata et al.	6,787,809 B2	9/2004	Hong et al.
6,243,064 B1	6/2001	Hirakata	6,797,548 B2	9/2004	Zhang et al.
6,255,668 B1	7/2001	Kang et al.	6,806,495 B1	10/2004	Yamazaki et al.
6,265,889 B1	7/2001	Tomita et al.	6,806,499 B2	10/2004	Yamazaki et al.
6,266,117 B1	7/2001	Yanagawa et al.	6,806,937 B2	10/2004	Park et al.
6,266,121 B1	7/2001	Shigeta et al.	6,847,064 B2	1/2005	Zhang et al.
6,266,122 B1	7/2001	Kishimoto et al.	6,855,957 B1	2/2005	Yamazaki et al.
6,268,617 B1	7/2001	Hirakata et al.	6,856,360 B1	2/2005	Higuchi et al.
6,271,903 B1	8/2001	Shin et al.	6,856,372 B2	2/2005	Song et al.
6,287,899 B1	9/2001	Park et al.	6,861,670 B1	3/2005	Ohtani et al.
6,297,519 B1	10/2001	Fujikawa et al.	6,873,312 B2	3/2005	Matsueda
6,300,926 B1	10/2001	Yoneya et al.	6,900,084 B1	5/2005	Yamazaki
6,304,243 B1	10/2001	Kondo et al.	6,911,962 B1	6/2005	Hirakata et al.
6,304,305 B1	10/2001	Matsumoto et al.	6,914,655 B2	7/2005	Yamazaki et al.
6,317,185 B1	11/2001	Harano et al.	6,950,168 B2	9/2005	Yamazaki et al.
6,317,187 B1	11/2001	Nakajima et al.	6,985,195 B1	1/2006	Kumagai et al.
6,323,051 B1	11/2001	Shimada	7,016,003 B2	3/2006	Hirakata et al.
6,330,049 B1	12/2001	Kume et al.	7,019,329 B2	3/2006	Yamazaki et al.
6,331,845 B1	12/2001	Kitajima et al.	7,071,037 B2	7/2006	Suzawa et al.
6,331,881 B1	12/2001	Hatano et al.	7,078,255 B2	7/2006	Hong et al.
6,335,213 B1	1/2002	Zhang et al.	7,102,165 B2	9/2006	Yamazaki
6,335,778 B1	1/2002	Kubota et al.	7,102,718 B1	9/2006	Yamazaki et al.
6,339,462 B1	1/2002	Kishimoto et al.	7,115,913 B2	10/2006	Shigeno
6,341,002 B1	1/2002	Shimizu et al.	7,145,173 B2	12/2006	Koyama et al.
6,342,939 B1	1/2002	Hirata et al.	7,166,862 B2	1/2007	Koyama et al.
6,344,888 B2	2/2002	Yasukawa	7,202,497 B2	4/2007	Ohtani et al.
6,359,672 B2	3/2002	Gu et al.	7,235,810 B1	6/2007	Yamazaki et al.
6,362,866 B1	3/2002	Yamazaki et al.	7,259,427 B2	8/2007	Yamazaki et al.
6,365,933 B1	4/2002	Yamazaki et al.	7,279,711 B1	10/2007	Yamazaki et al.
6,368,485 B1	4/2002	Ue et al.	7,317,438 B2	1/2008	Yamazaki et al.
6,384,818 B1	5/2002	Yamazaki et al.	7,323,715 B2	1/2008	Yamazaki
6,387,737 B1	5/2002	Yamazaki et al.	7,403,238 B2	7/2008	Higuchi et al.
6,407,431 B2	6/2002	Yamazaki et al.	7,414,266 B2	8/2008	Yamazaki et al.
6,407,784 B1	6/2002	Kanou et al.	7,507,991 B2	3/2009	Zhang et al.
6,411,358 B2	6/2002	Song et al.	7,511,776 B2	3/2009	Nishi et al.
6,429,057 B1	8/2002	Hong et al.	7,652,294 B2	1/2010	Yamazaki et al.
6,433,842 B1	8/2002	Kaneko et al.	7,656,491 B2	2/2010	Yamazaki et al.
6,437,844 B1	8/2002	Hattori et al.	7,687,325 B2	3/2010	Yamazaki et al.
6,441,399 B1	8/2002	Koyama et al.	7,705,354 B2	4/2010	Yamazaki et al.
6,444,296 B1	9/2002	Sasaki et al.	7,714,975 B1	5/2010	Yamazaki et al.
6,456,269 B2	9/2002	Hirakata	7,728,334 B2	6/2010	Yamazaki et al.
6,462,802 B1	10/2002	Nishimura et al.	7,902,550 B2	3/2011	Yamazaki
6,465,117 B2	10/2002	Takaki et al.	7,923,779 B2	4/2011	Yamazaki et al.
6,465,268 B2	10/2002	Hirakata et al.	7,961,263 B2	6/2011	Song et al.
6,466,289 B1	10/2002	Lee et al.	7,973,312 B2	7/2011	Yamazaki et al.
6,493,050 B1	12/2002	Lien et al.	7,978,292 B2	7/2011	Park et al.
6,498,634 B1	12/2002	Yamazaki et al.	8,198,630 B2 *	6/2012	Yamazaki et al. 257/59
6,519,018 B1	2/2003	Samant et al.	8,586,988 B2 *	11/2013	Yamazaki et al. 257/59
6,528,357 B2	3/2003	Dojo et al.	2001/0045998 A1	11/2001	Nagata et al.
6,529,256 B1	3/2003	Seo	2004/0207789 A1	10/2004	Hirakata et al.
6,531,392 B2	3/2003	Song et al.	2004/0218112 A1	11/2004	Hirakata et al.
6,567,146 B2	5/2003	Hirakata et al.	2004/0257511 A1	12/2004	Song et al.
			2005/0082536 A1	4/2005	Park et al.
			2005/0098894 A1	5/2005	Ohtani et al.
			2006/0081931 A1	4/2006	Yamazaki et al.
			2006/0228821 A1	10/2006	Hong et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2007/0146568 A1 6/2007 Yamazaki et al.
 2008/0315208 A1 12/2008 Yamazaki et al.
 2009/0152551 A1 6/2009 Yamazaki
 2010/0120180 A1 5/2010 Yamazaki et al.
 2010/0171895 A1 7/2010 Yamazaki et al.
 2010/0195013 A1 8/2010 Yamazaki et al.

FOREIGN PATENT DOCUMENTS

EP 0678907 B 10/1995
 EP 0694804 A 1/1996
 EP 1001467 A 5/2000
 EP 1006589 A 6/2000
 EP 1041622 A 10/2000
 JP 58-188684 12/1983
 JP 60-097386 A 5/1985
 JP 61-188967 A 8/1986
 JP 62-131578 A 6/1987
 JP 62-265756 A 11/1987
 JP 63-082405 A 4/1988
 JP 01-210989 A 8/1989
 JP 01-217423 A 8/1989
 JP 02-068524 A 3/1990
 JP 02-077019 A 3/1990
 JP 04-362925 A 12/1992
 JP 05-034717 A 2/1993
 JP 05-119331 A 5/1993
 JP 05-142558 A 6/1993
 JP 05-175500 A 7/1993
 JP 05-232494 A 9/1993
 JP 05-265020 A 10/1993
 JP 05-323371 A 12/1993
 JP 06-045354 A 2/1994
 JP 06-082754 A 3/1994
 JP 06-148683 A 5/1994
 JP 06-194615 A 7/1994
 JP 06-242455 A 9/1994
 JP 06-250210 A 9/1994
 JP 06-268222 A 9/1994
 JP 06-338615 A 12/1994
 JP 07-013196 A 1/1995
 JP 07-120789 A 5/1995
 JP 07-159776 A 6/1995
 JP 07-169967 A 7/1995
 JP 07-191348 A 7/1995
 JP 07-263698 A 10/1995
 JP 07-297407 A 11/1995
 JP 07-318975 A 12/1995
 JP 08-064828 A 3/1996
 JP 08-064829 A 3/1996
 JP 08-087030 A 4/1996
 JP 08-087033 A 4/1996
 JP 08-122806 A 5/1996
 JP 08-240813 A 9/1996
 JP 09-005767 A 1/1997
 JP 09-015621 A 1/1997
 JP 09-054318 A 2/1997
 JP 09-073101 A 3/1997
 JP 09-074257 A 3/1997
 JP 09-090397 A 4/1997

JP 09-120083 A 5/1997
 JP 09-152626 A 6/1997
 JP 09-153618 A 6/1997
 JP 09-160071 A 6/1997
 JP 09-274444 A 10/1997
 JP 10-048651 A 2/1998
 JP 10-048663 A 2/1998
 JP 10-091089 A 4/1998
 JP 10-096944 A 4/1998
 JP 10-123574 A 5/1998
 JP 10-170959 A 6/1998
 JP 10-241464 A 9/1998
 JP 11-024063 A 1/1999
 JP 11-024095 A 1/1999
 JP 11-070610 A 3/1999
 JP 11-109372 A 4/1999
 JP 11-109390 A 4/1999
 JP 11-133455 A 5/1999
 JP 11-160732 A 6/1999
 JP 11-160735 A 6/1999
 JP 11-258596 A 9/1999
 JP 11-258625 A 9/1999
 JP 11-260918 A 9/1999
 JP 11-264998 A 9/1999
 JP 11-271792 A 10/1999
 JP 11-337961 A 12/1999
 JP 11-337976 A 12/1999
 JP 11-337978 A 12/1999
 JP 11-352322 A 12/1999
 JP 2000-002886 A 1/2000
 JP 2000-002892 A 1/2000
 JP 2000-075302 A 3/2000
 JP 2000-111901 A 4/2000
 JP 2000-216396 A 8/2000
 JP 2000-228527 A 8/2000
 JP 2000-341242 A 12/2000
 JP 2000-349301 A 12/2000
 JP 2001-085698 A 3/2001
 JP 2001-257350 A 9/2001
 JP 2004-004680 A 1/2004
 JP 2007-128117 A 5/2007
 JP 2008-146068 A 6/2008
 KR 1996-0000262 B 1/1996
 KR 1997-0024311 A 5/1997
 KR 1998-0072232 A 11/1998
 KR 0161466 B 1/1999
 KR 1999-0011210 A 2/1999
 KR 1999-0063319 A 7/1999
 KR 1999-0074563 A 10/1999
 KR 1999-0075407 A 10/1999
 KR 1999-0077792 A 10/1999
 KR 2000-0004404 A 1/2000
 KR 2000-0033515 A 6/2000
 KR 10-0510439 B 10/2005

OTHER PUBLICATIONS

Nakajima.S et al., Specification U.S. Appl. No. 09/635,945, filed Aug. 10, 2000.
 Wolf.S et al., "Sputter Deposition Equipment," Silicon Processing for the VLSI ERA, 1986, vol. 1 , pp. 359-365, Lattice Press.
 Japanese Office Action (Application No. 2008-062009) Dated Apr. 17, 2012.

* cited by examiner




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 3A




FIG. 3B

FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9A




FIG. 9B




FIG. 10




FIG. 11




FIG. 12




FIG. 13A




FIG. 13B




FIG. 14




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 15D




FIG. 15E




FIG. 15F




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 16D




FIG. 17A




FIG. 17B





FIG. 17C



SEMICONDUCTOR DEVICE AND MANUFACTURING METHOD THEREOF

DETAILED DESCRIPTION OF THE INVENTION

Technical Field to which the Invention Belongs

The present invention relates to a semiconductor device having a circuit comprising a thin film transistor (hereafter referred to as TFT), and to a method of manufacturing thereof. For example, the present invention relates to an electro-optical device, typically a liquid crystal display panel, and to electronic equipment loaded with this type of electro-optical device as a part.

Note that, throughout this specification, semiconductor device denotes a general device which can function by utilizing semiconductor characteristics and that the category of semiconductor devices includes electro-optical devices, semiconductor circuits, and electronic equipment.

In recent years, techniques of structuring a thin film transistor (TFT) by using a semiconductor thin film (with a thickness on the order of several nm to several hundred of nm) formed over a substrate having an insulating surface have been in the spotlight. The thin film transistor is being widely applied in an electronic device such as an IC or an electro-optical device, and in particular, its development as a switching element of an image display device has been proceeding rapidly.

Conventionally, a liquid crystal display device is known as an image display device. Active matrix liquid crystal display devices have come into widespread due to the fact that, compared to passive liquid crystal display devices, a higher precision image can be obtained. By driving pixel electrodes arranged in a matrix state in the active matrix liquid crystal display device, a display pattern is formed on a screen in an active matrix liquid crystal display device. In more detail, by applying a voltage between a selected pixel electrode and an opposing electrode corresponding to the pixel electrode, optical modulation of a liquid crystal layer arranged between the pixel electrode and the opposing electrode is performed, and the optical modulation is recognized as a display pattern by an observer.

The use of this type of active matrix liquid crystal display device is spreading, and along with making the screen size larger, demands for higher precision, higher aperture ratio, and higher reliability are increasing. Further, at the same time, demands are increasing for improving productivity and lowering costs.

Conventionally, an amorphous silicon film is ideally used as an amorphous semiconductor film because of the capability of forming it on a large surface area substrate at a low temperature equal to or less than 300° C. Further, a reversed stagger type (or bottom gate type) TFT having a channel forming region formed by an amorphous semiconductor film is often used.

Problem to be Solved by the Invention

Conventionally, the production costs have been high in order to manufacture a TFT on a substrate with a technique of photolithography using at least 5 photomasks for an active matrix type liquid crystal display device. In order to improve productivity and yield, reducing the number of steps is considered as an effective means.

Specifically, it is necessary to reduce the number of photomasks needed to manufacture the TFT. The photomask is

used in a photolithography technique in order to form a photoresist pattern, which becomes an etching process mask, over the substrate.

By using one photomask, there are applied with steps such as applying resist, pre-baking, exposure, development, and post-baking, and in addition, steps of film deposition and etching, resist peeling, cleaning, and drying are added before and after these steps. Therefore, the entire process becomes complex, which leads to a problem.

Further, static electricity is generated by causes such as friction during manufacturing steps because the substrate is an insulator. Short circuits develop at an intersection portion of wirings formed on the substrate when static electricity is generated, and then deterioration or breakage of the TFT due to static electricity leads to display faults or deterioration of image quality in liquid crystal display devices. In particular, static electricity develops during rubbing in the liquid crystal aligning process performed in the manufacturing steps, and this becomes a problem.

The present invention is for solving such problems, and an object of the present invention is to reduce the number of steps for manufacturing a TFT, and to realize a reduction in the production cost and an improvement in yield for a semiconductor device typified by an active matrix type liquid crystal display device.

Further, an object of the present invention is to provide a structure and a method of manufacturing the structure for resolving the problems of damage to the TFT and deterioration of TFT characteristics due to static electricity.

Means for Solving the Problem

In order to solve the above problems, in the present invention, first, a gate wiring line is formed by a first photomask.

Next, a gate insulating film, a non-doped amorphous silicon film (hereinafter referred to as a-Si film), an amorphous silicon film containing an impurity element to give an n-type conductivity (hereinafter referred to as n⁺a-Si film), and a conductive film are continuously formed.

Next, a gate insulating film, an active layer comprising the a-Si film, a source wiring line (including a source electrode), and a drain electrode are formed through patterning by a second photomask.

Thereafter, after a transparent conductive film is formed, a pixel electrode made of the transparent conductive film is formed by a third photomask, and further, at the same time that a source region and a drain region comprising the n⁺a-Si film are formed, a part of the a-Si film is removed.

By adopting such structure, the number of photomasks used in a photolithography technique can be made three.

Further, the source wiring is covered by a transparent conductive film comprising the same material as the pixel electrode, a structure which protects the entire substrate from external static electricity or the like is used. Furthermore, a structure in which a protecting circuit is formed using the transparent conductive film may also be used. The generation of static electricity due to friction between production equipment and the insulating substrate can be prevented during manufacturing processing by using this type of structure. In particular, the TFTs can be protected from static electricity generated during a liquid crystal alignment process of rubbing performed during manufacturing steps.

A structure of the present invention disclosed in this specification is:

a semiconductor device possessing a gate wiring, a source wiring, and a pixel electrode, having:

the gate wiring **102** formed on an insulating surface;

the insulating film **110** formed on the gate wiring;

the amorphous semiconductor film **122** formed on the insulating film;

the source region **123** and the drain region **124** formed on the amorphous semiconductor film;

the source wiring **125** or the electrode **126** formed on the source region or the drain region; and

the pixel electrode **127** formed on the electrode;

characterized in that:

one end surface of the drain region **124** or the source region **123** reversed corresponds with an end surface of the insulating film **110**, an end of the amorphous semiconductor film **122** and an end surface of the electrode **126**.

Further, another structure of the present invention is:

a semiconductor device possessing a gate wiring, a source wiring, and a pixel electrode, having:

the gate wiring **102** formed on an insulating surface;

the insulating film **110** formed on the gate wiring;

the amorphous semiconductor film **122** formed on the insulating film;

the source region **123** and the drain region **124** formed on the amorphous semiconductor film;

the source wiring **125** or the electrode **126** formed on the source region or the drain region; and

the pixel electrode **127** formed on the electrode;

characterized in that:

one end surface of the drain region **124** or the source region **123** reversed corresponds with an end surface of the insulating film **110**, an end surface of the amorphous semiconductor film **122** and an end surface of the electrode **126**; and

the other end surface of the drain region **124** or the source region **123** reversed corresponds with an end surface of the pixel electrode **127** and the other end surface of the electrode **126**.

Further, each of the above structures is characterized in that the source region and the drain region comprises an amorphous semiconductor film containing an impurity element which imparts n-type conductivity.

Still further, each of the above structures is characterized in that the insulating film, the amorphous semiconductor film, the source region, and the drain region are formed in succession without exposure to the atmosphere.

In addition, each of the above structures is characterized in that the insulating film, the amorphous semiconductor film, the source region, or the drain region is formed by a sputtering method.

Additionally, each of the above structures is, as shown in FIG. 2(D), characterized in that the source region **123** and the drain region **124** are formed by using the same mask as that of the amorphous semiconductor film **122** and the electrode **126**. Moreover, it is characterized in that the source region and the drain region are formed by using the same mask as that of the source wiring **125**.

Further, each of the above structures is, as shown in FIG. 2(D), characterized in that the source region **123** and the drain region **124** are formed by using the same mask as that of the source wiring **125** and the pixel electrode **127**.

In addition, in each of the above structures, by etching process shown in FIG. 2(D), there is provided a structure in which, in the amorphous semiconductor film, the film thickness in a region that contacts with the source region and the drain region is formed thicker than the film thickness in a

region between a region that contacts with the source region and a region that contacts with the drain region, that is, a channel etch type bottom gate structure.

Besides, the structure of the invention for realizing the above construction is a method of fabricating a semiconductor device, characterized by comprising:

a first step of forming a gate wiring line **102** by using a first mask;

a second step of forming an insulating film **104** covering the gate wiring line;

a third step of forming a first amorphous semiconductor film **105** on the insulating film;

a fourth step of forming a second amorphous semiconductor film **106** containing an impurity element to give an n-type conductivity on the first amorphous semiconductor film;

a fifth step of forming a first conductive film **107** on the second amorphous semiconductor film;

a sixth step of forming a wiring line **116** (a source wiring line and an electrode) by selectively removing the insulating film **104**, the first amorphous semiconductor film **105**, the second amorphous semiconductor film **106**, and the first conductive film **107** by using a second mask;

a seventh step of forming a second conductive film **118** being in contact with and overlapping with the wiring line **116** (the source wiring line and the electrode); and

an eighth step of forming a source region **123** and a drain region **124** comprising the second amorphous semiconductor film, and a pixel electrode **127** made of the second conductive film by selectively removing a part of the first amorphous semiconductor film **112**, the second amorphous semiconductor film **114**, the first conductive film **116**, and the second conductive film **118** by using a third mask.

Besides, in the above structure, it is characterized in that formation is continuously made without being exposed to the air from the second step to the fifth step.

Besides, in the above respective structures, it is characterized in that formation is continuously made in the same chamber from the second step to the fifth step.

Besides, in the above respective structures, the insulating film may be formed by a sputtering method or a plasma CVD method.

Besides, in the above respective structures, the first amorphous semiconductor film may be formed by a sputtering method or a plasma CVD method.

Besides, in the above respective structures, the second amorphous semiconductor film may be formed by a sputtering method or a plasma CVD method.

Besides, in the above respective structures, it is characterized in that the second conductive film is a transparent conductive film or a conductive film having reflectivity.

EMBODIMENT MODE OF THE INVENTION

The mode of carrying out the invention will be described below.

FIG. 1 is an example of a plan view of an active matrix substrate of the present invention, and here, for simplification, one pixel structure among a plurality of pixels arranged in matrix form is shown. FIGS. 2 and 3 are views showing a fabricating process.

As shown in FIG. 1, this active matrix substrate includes a plurality of gate wiring lines arranged in parallel with each other, and a plurality of source wiring lines perpendicular to the respective gate wiring lines.

A pixel electrode **127** comprising a transparent conductive film is disposed at a region surrounded by the gate wiring lines and the source wiring lines. Besides, a transparent con-

5

ductive film **128** overlaps with the source wiring line so as not to overlap with the pixel electrode **127**.

Further, a capacitance wiring line **103** is disposed below the pixel electrode **127**, between adjacent two gate wiring lines, and in parallel with the gate wiring line **102**. This capacitance wiring line **103** is provided for every pixel, and forms a storage capacitor with an insulating film **111** shown in FIG. **2(B)** as a dielectric.

Besides, a TFT as a switching element is provided in the vicinity of an intersection of the gate wiring line **102** and the source wiring line **125**. This TFT is a reversed stagger type (or bottom gate type) TFT including a channel formation region comprising a semiconductor film having an amorphous structure (hereinafter referred to as an amorphous semiconductor film).

Besides, in this TFT, a gate electrode (formed integrally with the gate wiring line **102**), a gate insulating film, an a-Si film, a source region and a drain region comprising an n⁺a-Si film, a source electrode (formed integrally with the source wiring line **125**), and an electrode **126** (hereinafter also referred to as a drain electrode) are sequentially formed to be laminated on an insulating substrate.

Besides, the gate insulating film does not exist over the gate wiring line in a region where the gate wiring line does not overlap with the a-Si film.

Thus, the pixel electrode **127** overlapping with the electrode **126** is formed so as not to overlap with the gate wiring line.

Besides, at the intersection of the gate wiring line and the source wiring line, the transparent conductive film at the end portion of the source wiring line is removed so as to prevent shorting. Besides, the end of an electrode **117** is removed so as to prevent shorting between the capacitance wiring line and the pixel electrode.

Besides, under the source wiring line (including the source electrode) and the drain electrode **126**, the gate insulating film, the a-Si film, and the n⁺a-Si film are sequentially formed to be laminated on the insulating substrate.

Besides, the a-Si film in a region between a region that contacts with the source region and a region that contacts with the drain region, is thin as compared with that in the other regions. The film is thin since, when the n⁺a-Si film was separated by etching to form the source region and the drain region, a part of the a-Si film was removed. Besides, by this etching, an end surface of the pixel electrode, an end surface of the drain electrode, and an end surface of the drain region are coincident with each other.

Besides, similarly, an end surface of the transparent conductive film covering the source electrode, an end surface of the source region, and an end surface of the source wiring line are coincident with each other.

The present invention made of the foregoing structure will be described in more detail with embodiments shown below.

[Embodiments]

[Embodiment 1]

An embodiment of the invention are explained using FIGS. **1** to **6** and **9**. The present embodiment shows a method of manufacturing a liquid crystal display device, and a detailed explanation of a method of forming a TFT of a pixel portion on a substrate by a reversed stagger type TFT, and manufacturing a storage capacitor connected to the TFT, is made in accordance with the processes used. Further, a manufacturing process for an input terminal section, formed in an edge portion of the substrate, and for electrically connecting to wirings of circuits formed on other substrates, is shown at the same time in the same figures.

6

In FIG. **2(A)**, a glass substrate, comprising such as barium borosilicate glass or aluminum borosilicate glass, typically Corning Corp. #7059 or #1737, can be used as a substrate **100** having translucency. In addition, a translucent substrate such as a quartz substrate or a plastic substrate can also be used.

Next, after forming a conductive layer on the entire surface of the substrate, a first photolithography process is performed, a resist mask is formed, unnecessary portions are removed by etching, and wirings and electrodes (the gate wiring **102** including a gate electrode, a capacitor wiring **103** and a terminal **101**) are formed. Etching is performed at this time to form a tapered portion in at least an edge portion of the gate electrode **102**. A top view of this stage is shown in FIG. **4**.

It is preferable to form the gate wiring **102** including the gate electrode, the capacitor wiring **103**, and the terminal **101** of the terminal portion from a low resistivity conductive material such as aluminum (Al) or the like, but simple Al has problems such as inferior heat resistance and easy to be corroded, and therefore it is combined with a heat resistant conductive material. One element selected from the group consisting of titanium (Ti), tantalum (Ta), tungsten (W), molybdenum (Mo), chromium (Cr), Neodymium (Nd), or an alloy comprising the above elements, or an alloy film of a combination of the above element, or a nitrated compound comprising the above element is formed as the heat resistant conductive material. Furthermore, forming in combination with a heat resistant conductive material such as Ti, Si, Cr, or Nd, it is preferable because of improved flatness. Further, only such heat resistant conductive film may also be formed, for example, in combination with Mo and W.

In realizing the liquid crystal display device, it is preferable to form the gate electrode and the gate wiring by a combination of a heat resistant conductive material and a low resistivity conductive material. An appropriate combination in this case is explained.

Provided that the screen size is on the order of, or less than, 5 inch diagonal type, a two layer structure of a lamination of a conductive layer (A) comprising a nitride compound of a heat resistant conductive material, and a conductive layer (B) comprising a heat resistant conductive material is used. The conductive layer (B) may comprise an element selected from the group consisting of Al, Ta, Ti, W, Nd, and Cr, or from an alloy of the above elements, or from an alloy film of a combination of the above elements, and the conductive layer (A) comprises a film such as a tantalum nitride (TaN) film, a tungsten nitride (WN) film, or a titanium nitride (TiN) film. For example, it is preferable to use a double layer structure of a lamination of Cr as the conductive layer (A) and Al containing Nd as the conductive layer (B). The conductive layer (A) is given a thickness of 10 to 100 nm (preferably between 20 and 50 nm), and the conductive layer (B) is made with a thickness of 200 to 400 nm (preferably between 250 and 350 nm).

On the other hand, in order to be applied to a large screen, it is preferable to use a three layer structure of a lamination of a conductive layer (A) comprising a heat resistant conductive material, a conductive layer (B) comprising a low resistivity conductive material, and a conductive layer (C) comprising a heat resistant conductive material. The conductive layer (B) comprising the low resistivity conductive material comprises a material comprising aluminum (Al), and in addition to pure Al, Al containing between 0.01 and 5 atomic % of an element such as scandium (Sc), Ti, Nd, or silicon (Si), etc. is used. The conductive layer (C) is effective in preventing generation of hillocks in the Al of the conductive layer (B). The conductive layer (A) is given a thickness of 10 to 100 nm (preferably

between 20 and 50 nm), the conductive layer (B) has 200 to 400 nm thick (preferable between 250 and 350 nm), and the conductive layer (C) is from 10 to 100 nm thick (preferably between 20 and 50 nm) In the present embodiment, the conductive layer (A) comprises a Ti film with a thickness of 50 nm, made by sputtering with a Ti target, the conductive layer (B) comprises an Al film with a thickness of 200 nm, made by sputtering with an Al target, and the conductive layer (C) is a 50 nm thick Ti film, made by sputtering with a Ti target.

An insulating film **104** is formed next on the entire surface. The insulating film **104** is formed using sputtering, and has a film thickness of 50 to 200 nm.

For example, a silicon nitride film is used as the insulating film **104**, and formed to a thickness of 150 nm. Of course, the gate insulating film is not limited to this type of silicon nitride film, and another insulating film such as a silicon oxide film, a silicon oxynitride film, or a tantalum oxide film may also be used, and the gate insulating film may comprise a single layer or a lamination structure comprising these materials. For example, a lamination structure having a silicon nitride film as a lower layer and a silicon oxide film as an upper layer may be used.

Next, an amorphous semiconductor film **105** is formed with a thickness of 50 to 200 nm (preferably between 100 and 150 nm) on the insulating film **104** over the entire surface by using a known method such as plasma CVD or sputtering (not shown in the figure). Typically, an amorphous silicon (a-Si) film is formed with a thickness of 100 nm by sputtering using a silicon target. In addition, it is also possible to apply a microcrystalline semiconductor film, or a compound semiconductor film having an amorphous structure, such as an amorphous silicon germanium film.

An amorphous semiconductor film **106** containing an impurity element imparting n-type is formed next with a thickness of 20 to 80 nm as a semiconductor film **106** which contains an impurity element imparting one conductivity type. The amorphous semiconductor film **106** containing an impurity element imparting n-type is formed on the entire surface by a known method such as plasma CVD or sputtering. Typically it is appropriate to form an n⁺a-Si:H film, and it is deposited by using a silicon target added with phosphorus (P). Alternatively, film deposition may be performed by sputtering using a silicon target in an atmosphere containing phosphorous. In addition, the amorphous semiconductor film **106** containing an impurity element imparting n-type may also comprise a hydrogenated microcrystalline silicon film ($\mu\text{c-Si:H}$).

Next, a conductive metal film **107** is formed by sputtering or vacuum evaporation. Provided that ohmic contact with the n⁺a-Si film **106** can be made, there are no particular limitation on the material of the conductive metal film **107**, and an element selected from the group consisting of Al, Cr, Ta, and Ti, or an alloy comprising the above elements, and an alloy film of a combination of the above elements or the like can be given. Note however that it is necessary to choose a material for the conductive metal film **107** which has a sufficient selective ratio with respect to the terminal and the gate wiring in the later etching process. In the present embodiment, sputtering is used and a Cr film having 300 to 600 thickness is formed as the metal film **107**. (FIG. 2(A))

The insulating film **104**, the amorphous semiconductor film **105**, the semiconductor film **106** containing an impurity element which imparts one conductivity type, and the conductive metal film **107** are all manufactured by a known method, and can be manufactured by plasma CVD or sputtering. The films are formed in succession by sputtering, and suitably changing the target or the sputtering gas in the

present embodiment. The same reaction chamber, or a plurality of reaction chambers, in the sputtering apparatus is used at this time, and it is preferable to laminate these films in succession without exposure to the atmosphere. By thus not exposing the films to the atmosphere, the mixing in of impurities can be prevented.

Next, a second photolithography process is performed, resist masks **108** and **109** are formed, and by removing unnecessary portions by etching, insulating films **110** and **111**, a wiring and an electrode (source wiring) are formed. Wet etching or dry etching is used as the etching process at this time. The insulating film **104**, the amorphous semiconductor film **105**, the semiconductor film **106** containing an impurity element imparting one conductivity type and the conductive metal film **107** are etched in the second photolithography process, and an insulating film **110**, an amorphous semiconductor film **112**, a semiconductor film containing an impurity element imparting one conductivity type **114** and a conductive metal film **116** are formed in the pixel TFT portion. Accordingly the edge surface of the films approximately coincide. Further in the capacitor portion an insulating film **111**, an amorphous semiconductor film **113**, a semiconductor film **115** containing an impurity element imparting one conductivity type and a conductive metal film **117** are formed. Similarly, the edge surface of these films coincide.

Further, in the above second photolithography process, the films are etched away leaving only the terminal **101** in the terminal portion. The insulating film on the gate wiring is also removed by leaving only intersecting portion with other wirings. Accordingly it is necessary to select a material for the terminal **101** and gate wiring that has sufficient selective ratio with respect to that of the insulating film, and it is further necessary to select a material which has a sufficient selective ratio for the materials of the terminal with respect to that of the conductive metal film. That is, it is necessary to choose different materials for the terminal and the gate wiring from that of the conductive metal film. In the present embodiment, the metal film **107** is etched by dry etching using a mixed gas of Cl₂ and O₂, and then the semiconductor film **106** containing an impurity element imparting one conductivity type, the amorphous semiconductor film **105** and the insulating film **104** are selectively removed by changing the reaction gas to a mixed gas of CF₄ and O₂. (FIG. 2(B))

Next, after removing the resist mask **108**, a transparent conductive film **118** is deposited over the entire surface. (FIG. 2(C)) A top view in this state is shown in FIG. 5. Note however, for simplification, the transparent conductive film **118** deposited over the entire surface is not shown in FIG. 5.

The transparent conductive film **118** comprises a material such as indium oxide (In₂O₃) or indium oxide tin oxide alloy (In₂O₃—SnO₂, abbreviated as ITO) using a method such as sputtering or vacuum evaporation. The etching process for this type of material is performed using a solution of hydrochloric acid type. However, a residue is easily generated, particularly in ITO etching, and therefore an indium oxide zinc oxide alloy (In₂O₃—ZnO) may be used in order to improve the etching workability. The indium oxide zinc oxide alloy has superior surface smoothing characteristics, and has superior thermal stability compared to ITO, and therefore even if the electrode **116** comprises an Al film, a corrosion reaction can be prevented. Similarly, zinc oxide (ZnO) is also a suitable material, and in addition, in order to increase the transmittivity of visible light and increase the conductivity, a material such as zinc oxide in which gallium (Ga) is added (ZnO:Ga) can be used.

Resist masks **119**, **120** and **121** are formed next by a third photolithography process. Unnecessary portions are then

removed by etching, forming an amorphous semiconductor film **122**, a source region **123**, a drain region **124**, the source electrode **125**, the drain electrode **126**, and the pixel electrode **127**. (FIG. 2(D))

The third photolithography process patterns the transparent conductive film **118**, and at the same time removes a part of the conductive metal film **116**, the n⁺a-Si film **114** and the amorphous semiconductor film **112** by etching, forming an opening. In the present embodiment, the pixel electrode comprising ITO is selectively removed first by wet etching using a mixed solution of nitric acid and hydrochloric acid, or a ferric chloride solution, and after removing the conductive metal film **116** by wet etching, a part of the n⁺a-Si film **114** and the amorphous semiconductor film **112** are etched by dry etching. Note that wet etching and dry etching are used in the present embodiment, but the operator may perform only dry etching by suitably selecting the reaction gas, and the operator may perform only wet etching by suitably selecting the reaction solution.

Further, the lower portion of the opening reaches the amorphous semiconductor film, and the amorphous semiconductor film **114** is formed having a concave portion. The conductive metal film **116** is separated into the source wiring **125** and the drain electrode **126** by the opening, and the n⁺a-Si:H film **114** is separated into the source region **123** and the drain region **124**. Furthermore, the transparent conductive film **128** contacting the source electrode **125** covers the source wiring, and during subsequent manufacturing processes, especially during a rubbing process, fulfills a role of preventing static electricity from developing. An example of forming the transparent conductive film **128** on the source wiring is shown in the present embodiment, but the transparent conductive film **128** may also be removed during the above etching of the ITO film. In addition, a circuit for protecting from static electricity may be formed by utilizing the above ITO film, in the etching of the ITO film.

Further, though not shown in the figure, it is necessary that the gate wiring have selective ratio with the amorphous semiconductor film and the metal film **116** since the transparent conductive film formed on the gate wiring is selectively removed by the above third photolithography process. Note however the transparent conductive film is partially left in the gate wiring terminal portion.

Resist masks **119** to **121** are next removed. The cross sectional view of this state is shown in FIG. 3(A). Note that FIG. 1 is a top view of one pixel and the cross sections along the A-A' line and the B-B' line correspond to FIG. 3(A) respectively.

Furthermore, FIG. 9(A) shows top views of a gate wiring terminal portion **501** and a source wiring terminal portion **502** in this state. Note that the same symbols are used for area corresponding to those of FIG. 1 to FIG. 3. Further, FIG. 9(B) corresponds to a cross-sectional view taken along the lines E-E' and F-F' in FIG. 9(A). Reference numeral **503** in FIG. 9(A) comprising a transparent conductive film denotes a connecting electrode which functions as an input terminal. In addition, in FIG. 9(B) reference numeral **504** denotes an insulating film (extended from **110**), reference numeral **505** denotes an amorphous semiconductor film (extended from **122**), and reference numeral **506** denotes an n⁺a-Si film (extended from **123**).

Note that a storage capacitor is formed in the capacitor portion between the capacitor wiring **103** and the metal film **117** (or n⁺a-Si film **115** or semiconductor film) with the insulating film **111** as a dielectric.

By thus using three photomasks and performing three photolithography processes, the pixel TFT portion having the

reversed stagger type n-channel type TFT **201** and the storage capacitor **202** can be completed. By placing these in matrix form corresponding to each pixel and thus composing the pixel portion, one substrate can be made in order to manufacture an active matrix liquid crystal display device. For convenience, this type of substrate is referred to as an active matrix substrate throughout this specification.

An alignment film **130** is selectively formed next in only the pixel portion of the active matrix substrate. Screen printing may be used as a method of selectively forming the alignment film **130**, and a method of removal in which a resist mask is formed using a shadow mask after application of the alignment film may also be used. Normally, a polyimide resin is often used in the alignment film of the liquid crystal display element.

Next, a rubbing process is then performed on the alignment film **130**, orienting the liquid crystal elements so as to possess a certain fixed pre-tilt angle.

The active matrix substrate, and an opposing substrate **133** on which an opposing electrode **132**, and an alignment film **131** are formed are next joined together by a sealant while maintaining a gap between the substrates using spacers, after which a liquid crystal material **134** is injected into the space between the active matrix substrate and the opposing substrate. A known material may be applied for the liquid crystal material **134**, and a TN liquid crystal is typically used. After injecting the liquid crystal material, the injecting entrance is sealed by a resin material.

Next, a flexible printed circuit (FPC) is connected to the terminal **101** of the terminal portion. The FPC comprises a copper wiring **137** on an organic resin film **138** such as polyimide, and is connected to the input terminal **129** comprising a transparent conductive film (corresponding to reference numeral **503** of FIG. 9) by an anisotropic conductive adhesive. The anisotropic conductive adhesive comprises an adhesive **135** and particles **136**, with a diameter of several tens to several hundred of μm and having a conductive surface plated by a material such as gold, which are mixed therein. The particles **136** form an electrical connection in this portion by connecting the input terminal **129** and the copper wiring **137**. In addition, in order to increase the mechanical strength of this region, a resin layer **139** is formed. (FIG. 3(B))

FIG. 6 is a diagram explaining the placement of the pixel portion and the terminal portion of the active matrix substrate. A pixel portion **211** is formed on a substrate **210**, gate wirings **208** and source wirings **207** are formed intersecting on the pixel portion, and the n-channel TFT **201** connected to this is formed corresponding to each pixel. The pixel electrode **127** and a storage capacitor **202** are connected to the drain side of the n-channel TFT **201**, and the other terminal of the storage capacitor **202** is connected to a capacitor wiring **209**. The structure of the n-channel TFT **201** and the storage capacitor **202** is the same as that of the n-channel TFT **201** and the storage capacitor **202** shown by FIG. 3(A).

An input terminal portion **205** for inputting a scanning signal is formed in one edge portion of the substrate, and is connected to a gate wiring **208** by a connection wiring **206**. Further, an input terminal portion **203** for inputting an image signal is formed in the other edge portion, and is connected to a source wiring **207** by a connection wiring **204**. A plurality of the gate wiring **208**, the source wiring **207**, and the capacitor wiring **209** are formed in accordance with the pixel density. The number of the wirings is as stated above. Furthermore, an input terminal portion **212** for inputting an image signal and a connection wiring **213** may be formed, and may be connected to the source wiring alternately with the input terminal

11

portion **203**. An arbitrary number of the input terminal portions **203**, **205**, and **212** are formed, which may be suitably determined by the operator.

[Embodiment 2]

FIG. 7 is an example of a method of mounting a liquid crystal display device. The liquid crystal display device has an input terminal portion **302** formed in an edge portion of a substrate **301** on which TFTs are formed, and as shown by embodiment 1, this is formed by a terminal **303** comprising the same material as the gate wiring. An opposing substrate **304** is joined to the substrate **301** by a sealant **305** encapsulating spacers **306**, and in addition, polarizing plates **307** and **308** are formed. This is then fixed to a casing **321** by spacers **322**.

Note that the TFT obtained in Embodiment 1 having an active layer formed by an amorphous semiconductor film has a low electric field effect mobility, and only approximately $1 \text{ cm}^2/\text{Vsec}$ is obtained. Therefore, a driver circuit for performing image display is formed by a LSI chip, and mounted by a TAB (tape automated bonding) method or by a COG (chip on glass) method. In the present embodiment, an example is shown of forming the driver circuit in a LSI chip **313**, and mounting by using the TAB method. A flexible printed circuit (FPC) is used, and the FPC is formed by a copper wiring **310** on an organic resin film **309**, such as polyimide, and is connected to the input terminal **302** by an anisotropic conductive adhesive. The input terminal is a transparent conductive film formed on and contacting the wiring **303**. The anisotropic conductive adhesive is structured by an adhesive **311** and particles **312**, with a diameter of several tens to several hundred of μm and having a conductive surface plated by a material such as gold, which are mixed therein. The particles **312** form an electrical connection in this portion by connecting the input terminal **302** and the copper wiring **310**. In addition, in order to increase the mechanical strength of this region, a resin layer **318** is formed.

The LSI chip **313** is connected to the copper wiring **310** by a bump **314**, and is sealed by a resin material **315**. The copper wiring **310** is then connected to a printed substrate **317** on which other circuits such as a signal processing circuit, an amplifying circuit, and a power supply circuit are formed, through a connecting terminal **316**. A light source **319** and a light conductor **320** are formed on the opposing substrate **304** and used as a back light in the transmitting liquid crystal display device.

[Embodiment 3]

In the present embodiment, an example of forming a protecting film is shown in FIG. 6. Note that the present embodiment is identical to Embodiment 1 till the state of FIG. 2(D), and therefore only points of difference are explained. Further, the same symbols are used for locations corresponding to those in FIG. 2(D).

After first forming through the state of FIG. 2(D) in accordance with Embodiment 1, a thin inorganic insulating film is formed on the entire surface. An inorganic insulating film formed as the thin inorganic insulating film using a silicon oxide film, a silicon nitride film, a silicon oxynitride film, or a tantalum oxide film, and a single layer or a lamination structure comprising these materials may be formed.

A fourth photolithography process is performed next, forming a resist mask, and unnecessary portions are removed by etching, forming an insulating film **402** in the pixel TFT portion, and an inorganic insulating film **401** in the terminal portion. These inorganic insulating films **401** and **402** function as passivation films. Further, the thin inorganic insulating

12

film **401** is removed in the terminal portion by the fourth photolithography process, exposing the terminal **101** of the terminal portion.

The reversed stagger type n-channel type TFT and the storage capacitor, protected by the inorganic insulating film, can thus be completed in the present embodiment by performing the photolithography process using four photomasks four times in total. Thus the pixel portion is structured by arranging these into a matrix state corresponding to each pixel, and one substrate for manufacturing the active matrix liquid crystal display device can be made.

Note that it is possible to freely combine the constitution of the present embodiment with that of Embodiment 1 or Embodiment 2.

[Embodiment 4]

Although Embodiment 1 show an example of laminating an insulating film, an amorphous semiconductor film, an amorphous semiconductor film containing an impurity element which imparts n-type conductivity, and a metal film by sputtering, but the present embodiment shows an example of using plasma CVD to form the films.

The insulating film, the amorphous semiconductor film, and the amorphous semiconductor film containing an impurity element which imparts n-type conductivity are formed by plasma CVD in the present embodiment.

In the present embodiment, a silicon oxynitride film is used as the insulating film, and formed with a thickness of 150 nm by plasma CVD. Plasma CVD may be performed at this point with a power supply frequency of 13 to 70 MHz, preferably between 27 and 60 MHz. By using a power supply frequency of 27 to 60 MHz, a dense insulating film can be formed, and the voltage resistance can be increased as a gate insulating film. Further, a silicon oxynitride film manufactured by adding O_2 to SiH_4 and N_2O has a reduction in fixed electric charge density in the film, and therefore is a material which is preferable for this use. Of course, the gate insulating film is not limited to this type of silicon oxynitride film, and a single layer or a lamination structure using other insulating films such as a silicon oxide film, a silicon nitride film, or a tantalum oxide film may be formed. Further, a lamination structure of a silicon nitride film in a lower layer, and a silicon oxide film in an upper layer may be used.

For example, when using a silicon oxide film, it can be formed by plasma CVD using a mixture of tetraethyl orthosilicate (TEOS) and O_2 , with the reaction pressure set to 40 Pa, a substrate temperature of 250 to 350° C., and discharge at a high frequency (13.56 MHz) power density of 0.5 to 0.8 W/cm^2 . Good characteristics as the gate insulating film can be obtained for the silicon oxide film thus formed by a subsequent thermal anneal at 300 to 400° C.

Typically, a hydrogenated amorphous silicon (a-Si:H) film is formed with a thickness of 100 nm by plasma CVD as the amorphous semiconductor film. At this point, plasma CVD may be performed with a power supply frequency of 13 to 70 MHz, preferably between 27 and 60 MHz, in the plasma CVD apparatus. By using a power frequency of 27 to 60 MHz, it becomes possible to increase the film deposition speed, and the deposited film is preferable because it becomes an a-Si film having a low defect density. In addition, it is also possible to apply a microcrystalline semiconductor film and a compound semiconductor film having an amorphous structure, such as an amorphous silicon germanium film, as the amorphous semiconductor film.

Further, if 100 to 100 k Hz pulse modulation discharge is performed in the plasma CVD film deposition of the insulating film and the amorphous semiconductor film, then particle generation due to the plasma CVD gas phase reaction can be

13

prevented, and pinhole generation in the formed film can also be prevented, and therefore is preferable.

Further, in the present embodiment, an amorphous semiconductor film containing an impurity element which imparts n-type conductivity is formed with a thickness of 20 to 80 nm as a semiconductor film containing a single conductivity type impurity element. For example, an a-Si:H film having n-type may be formed, and in order to do so, phosphine (PH₃) is added at a 0.1 to 5% concentration to silane (SiH₄). Alternatively, a hydrogenated microcrystalline silicon film (μc-Si:H) may also be used as a substitute for the amorphous semiconductor film **106**, containing an impurity element which imparts n-type conductivity.

These films can be formed in succession by appropriately changing the reaction gas. Further, these films can be laminated successively without exposure to the atmosphere at this time by using the same reaction chamber or a plurality of reaction chambers in the plasma CVD apparatus. By thus depositing successively these films without exposing the films to the atmosphere, the mixing in of impurities into the first amorphous semiconductor film can be prevented.

Note that it is possible to combine the present embodiment with Embodiment 2.

[Embodiment 5]

Examples are shown in Embodiment 1 and Embodiment 4 of laminating an insulating film, an amorphous semiconductor film, an n⁺a-Si film, and a metal film, in order and in succession. An example of an apparatus having a plurality of chambers, and used for cases of performing this type of successive film deposition is shown in FIG. **10**.

An outline of an apparatus (successive film deposition system), shown by the present embodiment, is shown in FIG. **10** as seen from above. Reference numerals **10** to **15** in FIG. **10** denote chambers having airtight characteristics. A vacuum evacuation pump and an inert gas introduction system are arranged in each of the chambers.

The chambers denoted by reference numerals **10** and **15** are load-lock chambers for bringing sample (processing substrate) **30** into the system. The chamber denoted by reference numeral **11** is a first chamber for deposition of the insulating film **104**. The chamber denoted by reference numeral **12** is a second chamber for deposition of the amorphous semiconductor film **105**. The chamber denoted by reference numeral **13** is a third chamber for deposition of the amorphous semiconductor film **106** which imparts n-type conductivity. The chamber denoted by reference numeral **14** is a fourth chamber for deposition of the metal film **107**. Further, reference numeral **20** denotes a common chamber for the sample, arranged in common with respect to each chamber.

An example of operation is shown below.

After pulling an initial high vacuum state in all of the chambers at first, a purge state (normal pressure) is made by using an inert gas, nitrogen here. Furthermore, all gate valves **22** to **27** are closed.

First, a cassette **28** loaded with a multiple number of processing substrate is placed into the load-lock chamber **10**. After the cassette is placed inside, a door of the load-lock chamber (not shown in the figure) is closed. In this state, the gate valve **22** is opened and one of the processing substrate **30** is removed from the cassette, and is taken out to the common chamber **20** by a robot arm **21**. Position alignment is performed in the common chamber at this time. Note that a substrate on which the wirings **101**, **102**, and **103** are formed, in accordance with Embodiment 1, is used for the substrate **30**.

The gate valve **22** is then closed, and a gate valve **23** is opened next. The processing substrate **30** is then moved into

14

the first chamber **11**. Film deposition processing is performed within the first chamber at a temperature of 150 to 300° C., and the insulating film **104** is obtained. Note that a film such as a silicon nitride film, a silicon oxide film, a silicon oxynitride film, or a lamination film of these films, can be used as the insulating film. A single layer silicon nitride film is employed in the present embodiment, but a two-layer, three-layer, or higher layer lamination structure film may also be used. Note that a chamber capable of plasma CVD is used here, but a chamber which is capable of sputtering by utilizing a target may also be used.

After completing the deposition of the insulating film, the processing substrate is pulled out into the common chamber by the robot arm, and is then transported to the second chamber **12**. Film deposition is performed within the second chamber at a temperature of 150 to 300° C., similar to that of the first chamber, and the amorphous semiconductor film **105** is obtained by plasma CVD. Note that a film such as a microcrystalline semiconductor film, an amorphous germanium film, an amorphous silicon germanium film, or a lamination film of these films, etc., can be used as the amorphous semiconductor film. Further, a heat treatment process for reducing the concentration of hydrogen may be omitted with a formation temperature of 350 to 500° C. for the amorphous semiconductor film. Note that a chamber capable of plasma CVD is used here, but a chamber which is capable of sputtering by use of a target may also be used.

After completing deposition of the amorphous semiconductor film, the processing substrate is pulled out into the common chamber and then transported to the third chamber **13**. Film deposition process is performed within the third chamber at a temperature of 150 to 300° C., similar to that of the second chamber, and the amorphous semiconductor film **106**, containing an impurity element which imparts n-type conductivity (P or As), is obtained by plasma CVD. Note that a chamber capable of plasma CVD is used here, but a chamber which is capable of sputtering by use of a target may also be used.

After completing deposition of the amorphous semiconductor film containing an impurity element which imparts n-type conductivity, the processing substrate is pulled out into the common chamber, and then is transported to the fourth chamber **14**. The metal film **107** is obtained within the fourth chamber by sputtering using a metallic target.

The processed substrate, on which four layers have thus been formed in succession, is then transported to the load-lock chamber **15** by the robot arm, and is contained in a cassette **29**.

Note that the apparatus shown in FIG. **10** is only one example. Further, it is possible to freely combine the present embodiment with any one of Embodiments 1 to 4.

[Embodiment 6]

In Embodiment 5, an example of successive lamination using a plurality of chambers is shown, but in the present embodiment, a method of successive lamination within one chamber maintained at high vacuum using the apparatus shown in FIG. **11** is employed.

The apparatus system shown in FIG. **11** is used in the present embodiment. In FIG. **11**, reference numeral **40** denotes a processing substrate, reference numeral **50** denotes a common chamber, **44** and **46** denote load-lock chambers, **45** denotes a chamber, and reference numerals **42** and **43** denote cassettes. In order to prevent contamination developing during transport of the substrate, lamination is performed in the same chamber in the present embodiment.

It is possible to freely combine the present embodiment with any one of Embodiments 1 to 4.

Note that, when it is applied to Embodiment 1, a plurality of targets are prepared in the chamber 45, and then the insulating film 104, the amorphous semiconductor film 105, the amorphous semiconductor film 106 containing an impurity element which imparts n-type conductivity, and the metal film 107 may be laminated by changing the reaction gas in order.

Further, when applied to Embodiment 3, the insulating film 104, the amorphous semiconductor film 105, and the amorphous semiconductor film 106 containing an impurity element which imparts n-type conductivity, may be laminated by changing the reaction gas in order.

[Embodiment 7]

In Embodiment 1, an example of forming the n⁺a-Si film by using sputtering is shown, but in the present embodiment, an example of forming it by using plasma CVD is shown. Note that, except for the method of forming the n⁺a-Si film, the present embodiment is identical to Embodiment 1, and therefore only differing points are stated below.

If phosphine (PH₃) is added at a concentration of 0.1 to 5% with respect to silane (SiH₄) as a reaction gas using plasma CVD, then the n⁺a-Si film can be obtained.

[Embodiment 8]

In Embodiment 7, an example of forming the n⁺a-Si film by using plasma CVD is shown, and in the present embodiment, an example of using a microcrystalline semiconductor film containing an impurity element which imparts n-type conductivity is shown.

By setting the deposition temperature from 80 to 300° C., preferably between 140 and 200° C., taking a gas mixture of silane diluted by hydrogen (SiH₄:H₂=1:10 to 100) and phosphine (PH₃) as the reaction gas, setting the gas pressure from 0.1 to 10 Torr, and setting the discharge power from 10 to 300 mW/cm², a microcrystalline silicon film can be obtained. Further phosphorous may be added by plasma doping after film deposition of this microcrystalline silicon film.

[Embodiment 9]

FIG. 12 is a diagram which schematically shows a state of constructing an liquid crystal display device by using the COG method. A pixel region 803, an external input-output terminal 804, and a connection wiring 805 are formed on a first substrate. Regions surrounded by dotted lines denote a region 801 for attaching a scanning line side IC chip, and a region 802 for attaching a data line side IC chip. An opposing electrode 809 is formed on a second substrate 808, and this is joined to the first substrate 800 by using a sealing material 810. A liquid crystal layer 811 is formed inside the sealing material 810 by injecting a liquid crystal. The first substrate and the second substrate are joined with a predetermined gap, and this is set from 3 to 8 μm for a nematic liquid crystal, and from 1 to 4 μm for a smectic liquid crystal.

IC chips 806 and 807 have circuit structures which differ between the data line side and the scanning line side. The IC chips are mounted on the first substrate. An FPC (flexible printed circuit) 812 is attached to the external input-output terminal 804 in order to input power supply and control signals from the outside. In order to increase the adhesion strength of the FPC 812, a reinforcement 813 may be formed. The liquid crystal display device can thus be completed. If an electrical inspection is performed before mounting the IC chips on the first substrate, then the final process yield of the liquid crystal display device can be improved, and the reliability can be increased.

Further, a method such as a method of connection using an anisotropic conductive material or a wire bonding method, can be employed as the method of mounting the IC chips on the first substrate. FIG. 13 shows examples of such. FIG.

13(A) shows an example in which an IC chip 908 is mounted on a first substrate 901 using an anisotropic conductive material. A pixel region 902, a lead wire 906, a connection wiring and an input-output terminal 907 are formed on the first substrate 901. A second substrate is bonded to the first substrate 901 by using a sealing material 904, and a liquid crystal layer 905 is formed therebetween.

Further, an FPC 912 is bonded to one edge of the connection wiring and the input-output terminal 907 by using an anisotropic conductive material. The anisotropic conductive material comprises a resin 915 and conductive particles 914 having a diameter of several tens to several hundred of μm and plated by a material such as Au, and the connection wiring 913 formed with the FPC 912, and the connection wiring and the input-output terminal 907 are electrically connected by the conductive particles 914. The IC chip 908 is also similarly bonded to the first substrate by an anisotropic conductive material. An input-output terminal 909 provided with the IC chip 908 and the lead wire 906 or a connection wiring and the input-output terminal 907 are electrically connected by conductive particles 910 mixed into a resin 911.

Furthermore, as shown by FIG. 13(B), the IC chip may be fixed to the first substrate by an adhesive material 916, and an input-output terminal of a stick driver and a lead wire or a connection wiring may be connected by an Au wire 917. Then, this is all sealed by a resin 918.

The method of mounting the IC chip is not limited to the method based on FIGS. 12 and 13, and it is also possible to use a known method not explained here, such as a COG method, a wire bonding method or a TAB method.

It is possible to freely combine the present embodiment with Embodiment 1.

[Embodiment 10]

In Embodiment 1, a method of manufacturing an active matrix substrate corresponding to a transmission type liquid crystal display device is shown, but in the present embodiment, an example of application to a reflection type liquid crystal display device is shown, using FIG. 14.

First, in the same way as the embodiment 1, steps up to the step shown in FIG. 2(B) are carried out. Then, an interlayer insulating film comprising an organic resin film is formed. Next, a roughening process of the interlayer insulating film is carried out to form an interlayer insulating film 601 having a roughened portion. As the roughening process, a method of applying an organic resin film containing fibers or spacers may be used, a method of formation by partially etching an organic resin film by using a mask may be used, or a method of formation by heating to perform reflow after a photosensitive resin is etched by using a mask to make a cylindrical shape, may be used.

Next, contact holes reaching a source wiring line and a drain electrode are formed in the interlayer insulating film 601 by a third photolithography step. Besides, in order to form a storage capacitor by the same step, at the same time that the contact hole reaching the electrode is formed, the interlayer insulating film on a terminal portion is removed.

Next, a conductive film (Al, Ag, etc.) having reflectivity is formed.

Then, a resist mask pattern is formed by a fourth photolithography step, and a pixel electrode 602 made of the conductive film having the reflectivity is formed by etching. The pixel electrode 602 formed in this way has a roughened portion, can disperse light, and can prevent formation of a mirror surface. At the same time, a lead wiring line 603 reaching a source electrode is formed.

Since subsequent steps are the same as the embodiment 1, they are omitted. In this way, an active matrix substrate cor-

responding to a reflection type liquid crystal display device can be fabricated through four photolithography steps using four photomasks.

Besides, the present embodiment can be combined with the embodiment 2 or the embodiment 3.
[Embodiment 11]

CMOS circuits and pixel portion formed by implementing the present invention can be used in various electro-optical devices (such as an active matrix liquid crystal display device and an active matrix EC display device). Namely, the present invention can be implemented in all electronic appliance in which these electro-optical devices are built into a display portion.

The following can be given as such electronic appliance: a video camera, a digital camera, a projector (rear type or front type), a head-mounted display (goggle type display), a car navigation system, a car stereo, a personal computer, and a portable information terminal (such as a mobile computer, a portable telephone or an electronic book). Examples of these are shown in FIGS. 15, 16 and 17.

FIG. 15(A) is a personal computer, and it includes a main body 2001, an image input portion 2002, a display portion 2003, and a keyboard 2004, etc. The present invention can be applied to the image input portion 2002, the display portion 2003 or other signal driver circuits.

FIG. 15(B) is a video camera, and it includes a main body 2101, a display portion 2102, an audio input portion 2103, operation switches 2104, a battery 2105, and an image receiving portion 2106, etc. The present invention can be applied to the display portion 2102 or other signal driver circuits.

FIG. 15(C) is a mobile computer, and it includes a main body 2201, a camera portion 2202, an image receiving portion 2203, operation switches 2204, and a display portion 2205, etc. The present invention can be applied to the display portion 2205 or other signal driver circuits.

FIG. 15(D) is a goggle type display, and it includes a main body 2301, a display portion 2302, an arm portion 2303, etc. The present invention can be applied to the display portion 2302 or other signal driver circuits.

FIG. 15(E) is a player that uses a recording medium on which a program is recorded (hereafter referred to as a recording medium), and the player includes a main body 2401, a display portion 2402, a speaker portion 2403, a recording medium 2404, and operation switches 2405, etc. Note that this player uses a recording medium such as a DVD (digital versatile disk) or a CD, and the appreciation of music, the appreciation of film, game playing and the Internet can be performed. The present invention can be applied to the display portion 2402 or other signal driver circuits.

FIG. 15(F) is a digital camera, and it includes a main body 2501, a display portion 2502, an eyepiece portion 2503, operation switches 2504, and an image receiving portion (not shown in the figure), etc. The present invention can be applied to the display portion 2502 or other signal driver circuits.

FIG. 16(A) is a front projector, and it includes a projection system 2601, a screen 2602, etc. The present invention can be applied to a liquid crystal display device 2808 which constitutes a part of the projection system 2601, or other signal driver circuits.

FIG. 16(B) is a rear projector, and it includes a main body 2701, a projection system 2702, a mirror 2703, a screen 2704, etc. The present invention can be applied to a liquid crystal display device 2808 which constitutes a part of the projection system 2702 or other signal driver circuits.

Note that FIG. 16(C) is a diagram showing an example of the structure of projection systems 2601 and 2702 of FIGS. 16(A) and 16(B). The projection systems 2601 and 2702

comprise an optical light source system 2801, mirrors 2802 and 2804 to 2806, a dichroic mirror 2803, a prism 2807, a liquid crystal display device 2808, phase differentiating plate 2809 and a projection optical system 2810. The projection optical system 2810 comprises an optical system including a projection lens. The present Embodiment showed a three plate type, but it is not limited to this structure, and it may be for instance a single plate type. Further, the operator may appropriately dispose an optical system such as an optical lens, a film having light polarizing function, a film for adjusting phase difference and an IR film, in the optical path shown by an arrow in the FIG. 16(C).

FIG. 16(D) is a diagram showing an example of the structure of the optical light source system 2801 of FIG. 16(C). In the present embodiment the optical light source system 2801 comprises a reflector 2811, a light source 2812, lens arrays 2813 and 2814, light polarizing conversion element 2815 and a condenser lens 2816. Note that the optical light source system shown in FIG. 16(D) is merely an example and is not specifically limited. For example, the operator may appropriately dispose an optical system such as an optical lens, a film having light polarizing function, a film for adjusting phase difference and an IR film, etc., in the optical light source system.

Provided however, the projectors shown in FIG. 16 show a case of using transmission type electro-optical device and an application example of reflection type electro-optical device is not shown in the figures.

FIG. 17(A) is a portable telephone, and it includes a main body 2901, an audio output portion 2902, an audio input portion 2903, a display portion 2904, operation switches 2905, and an antenna 2906, etc. The present invention can be applied to the audio output portion 2902, the audio input portion 2903, the display portion 2904 or other signal driver circuits.

FIG. 17(B) is a portable book (electronic book), and it includes a main body 3001, display portions 3002 and 3003, a recording medium 3004, operation switches 3005, and an antenna 3006, etc. The present invention can be applied to the display portions 3002 and 3003 or other signal driver circuits.

FIG. 17(C) is a display, and it includes a main body 3101, a support stand 3102, and a display portion 3103, etc. The present invention can be applied to the display portion 3103. The display of the present invention is advantageous for a large size screen in particular, and is advantageous for a display equal to or greater than 10 inches (especially equal to or greater than 30 inches) in diagonal.

The applicable range of the present invention is thus extremely wide, and it is possible to apply the present invention to electronic appliance in all fields. Further, the electronic appliance of the present embodiment can be realized by using a constitution of any combination of embodiments 1 to 10.

Effects of the Invention

With the present invention, a liquid crystal display device prepared with a pixel TFT portion, having a reversed stagger type n-channel TFT, and a storage capacitor can be realized through three photolithography steps using three photomasks.

Further, when forming a protecting film, a liquid crystal display device prepared with a pixel TFT portion, having a reversed stagger type n-channel TFT protected by an inorganic insulating film, and a storage capacitor can be realized through four photolithography steps using four photomasks.

BRIEF DESCRIPTION OF THE DRAWINGS

[FIG. 1] A view showing a top view of the present invention.

[FIGS. 2A-2D] Sectional views showing a fabricating process of an AM-LCD.

[FIGS. 3A and 3B] Sectional views showing the fabricating process of the AM-LCD.

[FIG. 4] A top view showing a fabricating process of an AM-LCD.

[FIG. 5] A top view showing the fabricating process of the AM-LCD.

[FIG. 6] A top view for explaining the arrangement of a pixel portion and an input terminal portion of a liquid crystal display device.

[FIG. 7] A sectional view showing a mounting structure of a liquid crystal display device.

[FIG. 8] A sectional view showing a fabricating process of an AM-LCD.

[FIGS. 9A and 9B] A top view and a sectional view of an input terminal portion.

[FIG. 10] A top view of a fabricating apparatus.

[FIG. 11] A top view of a fabricating apparatus.

[FIG. 12] A view showing the mounting of a liquid crystal display device.

[FIGS. 13A and 13B] Sectional views showing a mounting structure of a liquid crystal display device.

[FIG. 14] A structural sectional view of an active matrix substrate.

[FIGS. 15A-15F] Views showing examples of electronic equipment.

[FIGS. 16A-16D] Views showing examples of electronic equipment.

[FIGS. 17A-17C] Views showing examples of electronic equipment.

What is claimed is:

1. A display device comprising:

a thin film transistor over a substrate, the thin film transistor comprising a gate electrode over the substrate, a gate insulating film over the gate electrode;

a capacitor wiring line over the substrate, wherein the capacitor wiring line comprises a same material as the gate electrode;

a first insulating film over the capacitor wiring line;

a first conductive layer over the first insulating film and electrically connected to a drain of the thin film transistor wherein a capacitor is formed between the capacitor wiring line and the first conductive layer with at least the first insulating film interposed therebetween;

a second insulating film comprising a resin over the thin film transistor and the first conductive layer wherein at least a portion of the second insulating film has a roughened upper surface;

a pixel electrode including a reflective conductive film over the second insulating film and electrically connected to the first conductive layer through a hole in the second insulating film wherein at least a portion of the reflective conductive film has a rough surface due to the roughened upper surface of the second insulating film.

2. The display device according to claim 1, further comprising:

a terminal portion over the substrate, the terminal portion comprising:

a second conductive layer over the substrate, the second conductive layer comprising a same material as the gate electrode of the thin film transistor; and

a third conductive layer over and in electrical contact with the second conductive layer; and

a flexible printed circuit in electrical contact with the terminal portion.

3. The display device according to claim 1, wherein the pixel electrode is in contact with the first conductive layer through a second hole in the second insulating film.

4. The display device according to claim 1, wherein the thin film transistor comprises a silicon film including a channel formation region.

5. The display device according to claim 1, further comprising a liquid crystal material adjacent to the pixel electrode.

6. The display device according to claim 1, wherein the first conductive layer is electrically connected to the drain of the thin film transistor through the pixel electrode.

7. The display device according to claim 1, wherein the reflective conductive film directly contacts the first conductive layer.

8. A display device comprising:

a thin film transistor over a substrate, the thin film transistor comprising a gate electrode over the substrate, a gate insulating film over the gate electrode;

a capacitor wiring line over the substrate, wherein the capacitor wiring line comprises a same material as the gate electrode;

a first insulating film over the capacitor wiring line;

a first conductive layer over the first insulating film and electrically connected to a drain of the thin film transistor, wherein a capacitor is formed between the capacitor wiring line and the first conductive layer with at least the first insulating film interposed therebetween;

a second insulating film comprising a resin over the thin film transistor and the first conductive layer wherein at least a portion of the second insulating film has a roughened upper surface; and

a pixel electrode including a reflective conductive film over the second insulating film and electrically connected to the first conductive layer through a hole in the second insulating film wherein at least a portion of the reflective conductive film has a rough surface due to the roughened upper surface of the second insulating film, wherein the capacitor wiring line and the gate electrode are formed by patterning a first conductive film.

9. The display device according to claim 8, further comprising:

a terminal portion over the substrate, the terminal portion comprising:

a second conductive layer over the substrate, the second conductive layer comprising a same material as the gate electrode of the thin film transistor; and

a third conductive layer over and in electrical contact with the second conductive layer; and

a flexible printed circuit in electrical contact with the terminal portion.

10. The display device according to claim 8, wherein the pixel electrode is in contact with the first conductive layer through a second hole in the second insulating film.

11. The display device according to claim 8, wherein the thin film transistor comprises a silicon film including a channel formation region.

12. The display device according to claim 8, further comprising a liquid crystal material adjacent to the pixel electrode.

13. The display device according to claim 8, wherein the first conductive layer is electrically connected to the drain of the thin film transistor through the pixel electrode.

21

14. The display device according to claim 8, wherein the reflective conductive film directly contacts the first conductive layer.

15. A display device comprising:

- a thin film transistor over a substrate, the thin film transistor comprising a gate electrode over the substrate, a gate insulating film over the gate electrode;
- a gate wiring over the substrate, wherein the gate electrode is electrically connected to the gate wiring;
- a capacitor wiring line over the substrate, wherein the capacitor wiring line extends in parallel with the gate wiring and overlaps with the gate wiring;
- a first insulating film over the capacitor wiring line;
- a first conductive layer over the first insulating film and electrically connected to a drain of the thin film transistor wherein a capacitor is formed between the capacitor wiring line and the first conductive layer with at least the first insulating film interposed therebetween;
- a second insulating film comprising a resin over the thin film transistor and the first conductive layer wherein at least a portion of the second insulating film has a roughened upper surface;
- a pixel electrode including a reflective conductive film over the second insulating film and electrically connected to the first conductive layer through a hole in the second insulating film wherein at least a portion of the reflective

22

conductive film has a rough surface due to the roughened upper surface of the second insulating film.

16. The display device according to claim 15, further comprising:

- a terminal portion over the substrate, the terminal portion comprising:
 - a second conductive layer over the substrate, the second conductive layer comprising a same material as the gate electrode of the thin film transistor; and
 - a third conductive layer over and in electrical contact with the second conductive layer; and
- a flexible printed circuit in electrical contact with the terminal portion.

17. The display device according to claim 15, wherein the pixel electrode is in contact with the first conductive layer through a second hole in the second insulating film.

18. The display device according to claim 15, wherein the thin film transistor comprises a silicon film including a channel formation region.

19. The display device according to claim 15, further comprising a liquid crystal material adjacent to the pixel electrode.

20. The display device according to claim 15, wherein the first conductive layer is electrically connected to the drain of the thin film transistor through the pixel electrode.

* * * * *