

US009201181B2

(12) **United States Patent**
Shimmo et al.

(10) **Patent No.:** **US 9,201,181 B2**
(45) **Date of Patent:** **Dec. 1, 2015**

(54) **INFRARED CUT FILTER AND IMAGING APPARATUS**

USPC 359/350, 355, 356, 359-361, 885, 888,
359/890, 892, 839; 396/275
See application file for complete search history.

(71) Applicant: **Nippon Sheet Glass Company, Limited**, Minato-ku, Tokyo (JP)

(56) **References Cited**

(72) Inventors: **Katsuhide Shimmo**, Minato-ku (JP);
Lei Cai, Minato-ku (JP); **Yoshihiro Takayanagi**, Minato-ku (JP)

U.S. PATENT DOCUMENTS

(73) Assignee: **Nippon Sheet Glass Company, Limited**, Tokyo (JP)

6,104,530 A * 8/2000 Okamura et al. 359/359
6,107,360 A * 8/2000 Kaneko et al. 522/81
2004/0114114 A1 * 6/2004 Yano et al. 353/84
2013/0094075 A1 * 4/2013 Saitoh et al. 359/350

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 22 days.

FOREIGN PATENT DOCUMENTS

JP 2005-338395 A 12/2005
WO WO 2011158635 A1 * 12/2011

(21) Appl. No.: **13/973,240**

* cited by examiner

(22) Filed: **Aug. 22, 2013**

Primary Examiner — Scott J Sugarman
Assistant Examiner — Wen Huang

(65) **Prior Publication Data**

US 2014/0063597 A1 Mar. 6, 2014

(74) *Attorney, Agent, or Firm* — Sughrue Mion, PLLC

(30) **Foreign Application Priority Data**

Sep. 6, 2012 (JP) 2012-195937

(57) **ABSTRACT**

(51) **Int. Cl.**
G02B 5/20 (2006.01)

An infrared cut filter includes: a transparent dielectric substrate; an infrared reflecting layer formed on one surface of the transparent dielectric substrate and configured to reflect infrared light; and an infrared absorbing layer formed on the other surface of the transparent dielectric substrate and configured to absorb infrared light. The infrared absorbing layer is formed of a resin that contains infrared absorbing pigment. The infrared reflecting layer is formed of a dielectric multi-layer film.

(52) **U.S. Cl.**
CPC **G02B 5/208** (2013.01)

(58) **Field of Classification Search**
CPC G02B 5/208; G02B 5/282; G02B 5/223

15 Claims, 34 Drawing Sheets




FIG. 1




FIG. 2




FIG.3




FIG.4




FIG.5

	PIGMENT	SUPPLIER	ATTRIBUTE	AMOUNT OF POWDER ADDED [g.]	SOLVENT	AMOUNT OF SOLVENT ADDED [g.]	AMOUNT OF POWDER ADDED [g.]
FIRST EXEMPLARY EMBODIMENT	CY-10	NIPPON KAYAKU CO., LTD.	CYANINE COMPOUND	0.002			
	NIA-7200H	HAKKOL CHEMICAL COMPANY, LTD.	AZO COMPOUND	0.001	MEK	0.807	0.0545
	IRG-022	NIPPON KAYAKU CO., LTD.	DIIMONIUM COMPOUND	0.003			
SECOND EXEMPLARY EMBODIMENT	SEPC-6	YAMADA CHEMICAL CO., LTD.	PHTHALOCYANINE COPPER COMPLEX	0.002			
	CY40MC	NIPPON KAYAKU CO., LTD.	CYANINE COMPOUND	0.004	MEK	0.807	0.054
	CIR-RL	JAPAN CARLIT CO., LTD.	DIIMONIUM COMPOUND	0.003			
THIRD EXEMPLARY EMBODIMENT	SEPC-6	YAMADA CHEMICAL CO., LTD.	PHTHALOCYANINE COPPER COMPLEX	0.004			
	YND-038	YAMAMOTO CHEMICALS INC.	HETEROAROMATIC COMPOUND	0.002	MEK	0.807	0.0553
	IRG-022	NIPPON KAYAKU CO., LTD.	DIIMONIUM COMPOUND	0.003			

FIG.6A




FIG.6B




FIG.6C




FIG.6D




FIG.6E




FIG.6F




FIG.6G




FIG.6H




FIG.6I




FIG.6J




FIG.6K




FIG.6L




FIG.6M




FIG.7A




FIG.7B




FIG.7C




FIG.7D




FIG.7E




FIG.7F




FIG.7G




FIG.7H




FIG.7I




FIG.7J




FIG.7K




FIG.7L




FIG.7M




FIG.8A




FIG.8B




FIG.8C




FIG.8D




FIG.8E




FIG.8F




FIG.8G




FIG.8H




FIG.8I




FIG.8J




FIG.8K




FIG.8L




FIG.8M




FIG.9

FIRST EXEMPLARY EMBODIMENT

	60	50	40	30	20	10	0	-10	-20	-30	-40	-50	-60
$\lambda_{AT50\%} - \lambda_{RT50\%}$ [nm]													
T_{ave} [%]($\lambda = 400 - 600$ nm)	74.18	76.07	76.28	76.32	76.38	76.33	76.23	76.25	76.14	76.23	72.90	76.14	76.05
$\lambda_{T2\%}$ [nm]	620.5	629.8	639.3	648.5	657.7	666.6	675.3	683.8	692.3	701.0	710.1	718.5	728.6
$\lambda_{T5\%}$ [nm]	613.6	623.1	632.5	641.8	651.0	660.0	668.7	676.9	684.8	692.8	701.2	710.2	719.6
$\lambda_{T50\%}$ [nm]	592.1	601.7	611.1	620.4	628.2	638.1	645.7	647.4	646.1	647.9	648.9	649.4	649.3
$\lambda_{SLOPE} = \lambda_{T50\%} - \lambda_{T2\%} $ [nm]	28.4	28.2	28.1	28.1	29.4	28.5	29.7	36.4	46.2	53.1	61.2	69.1	79.3
$\Delta \lambda_{T50\%}$ [nm]	30.6	30.5	30.3	30.1	29.8	29.5	28.4	22	13.2	8.1	3.5	2.1	1.3

FIG.10

SECOND EXEMPLARY EMBODIMENT

$\lambda_{AT50\%} - \lambda_{RT50\%}$ [nm]	60	50	40	30	20	10	0	-10	-20	-30	-40	-50	-60
T_{ave} [%]($\lambda = 400-600$ nm)	72.41	75.26	76.45	76.49	76.54	76.58	76.50	76.52	76.43	76.36	76.43	76.35	76.23
$\lambda_{T2\%}$ [nm]	615.4	624.8	633.8	642.7	651.8	661.3	670.7	679.8	688.9	697.6	705.5	712.4	719.5
$\lambda_{T5\%}$ [nm]	608.3	617.9	627.3	636.3	645.1	654.3	663.7	672.9	681.7	690.3	698.5	705.7	712.5
$\lambda_{T50\%}$ [nm]	586.9	598.6	606.1	615.6	624.8	633.5	640.7	643.1	642.7	643.1	644.2	644.5	644.4
$\lambda_{SLOPE} = \lambda_{T50\%} - \lambda_{T2\%} $ [nm]	28.4	26.2	27.7	27.1	27.0	27.9	30.0	36.7	46.1	54.4	61.3	68.0	75.1
$\Delta \lambda_{T50\%}$ [nm]	30.1	29.9	29.8	29.8	29.7	29.1	27.2	20.9	12.7	6.8	3.1	1.2	1.2

FIG.11

THIRD EXEMPLARY EMBODIMENT

	60	50	40	30	20	10	0	-10	-20	-30	-40	-50	-60
$\lambda_{AT50\%} - \lambda_{RT50\%} [nm]$													
$T_{ave} [\%] (\lambda = 400 - 600 nm)$	67.83	71.48	74.49	76.36	76.57	76.61	76.67	76.61	76.51	76.54	74.10	76.55	76.51
$\lambda_{T2\%} [nm]$	601.2	610.5	619.8	628.9	637.3	645.6	654.8	664.3	673.8	683.2	692.6	701.1	707.9
$\lambda_{T5\%} [nm]$	594.2	603.7	613.1	622.4	631.3	639.3	647.3	656.3	665.7	674.9	683.9	693.2	701.3
$\lambda_{T50\%} [nm]$	573.1	582.7	592.1	601.3	610.5	619.3	627.3	630.6	630.5	630.3	631.4	631.5	631.5
$\lambda_{SLOPE} = \lambda_{T50\%} - \lambda_{T2\%} [nm]$	28.0	27.8	27.7	27.6	26.8	26.3	27.5	33.7	43.3	52.8	61.2	69.6	76.4
$\Delta \lambda_{T50\%} [nm]$	30.3	30.0	29.6	29.2	29.0	28.9	28.2	23.0	15.0	7.9	3.3	0.9	1.0

FIG.12A




FIG.12B




FIG.13A




FIG.13B




FIG.14A




FIG.14B




FIG.15




FIG.16




FIG.17




FIG. 18




FIG. 19




FIG.20




FIG.21




FIG.22





FIG.23



INFRARED CUT FILTER AND IMAGING APPARATUS

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an infrared cut filter and an imaging apparatus in which an infrared cut filter is used.

2. Description of the Related Art

A semiconductor solid-state imaging device such as a charge coupled device (CCD) or a complementary metal oxide semiconductor (CMOS) is built in imaging apparatus such as digital cameras. The sensitivity of these solid-state imaging devices extends from a visible spectrum range to an infrared spectrum range. For this reason, an infrared cut filter for shielding infrared light is provided between an imaging lens system and a solid-state imaging device in the imaging apparatus. The infrared cut filter enables calibrating the sensitivity of the solid-state imaging device to approximate the spectral sensitivity of human beings.

Infrared cut filters used in the related art include those manufactured by forming an infrared reflecting layer including a dielectric multilayer film on a resin substrate (see, for example, patent document 1).

[patent document 1] JP2005-338395

However, an infrared reflecting layer including a dielectric multilayer has incident angle dependence in which infrared shielding property vary depending on the incident angle. Therefore, the central part of an image capturing light transmitted through the infrared reflecting layer may look different in color from the periphery thereof.

SUMMARY OF THE INVENTION

The present invention addresses the issue and a purpose thereof is to provide an infrared cut filter having favorable infrared shielding property relatively less dependent on the incident angle, and to provide an imaging apparatus in which the infrared cut filter is used.

The infrared cut filter according to at least one embodiment comprises: a transparent dielectric substrate; an infrared reflecting layer formed on one surface of the transparent dielectric substrate and configured to reflect infrared light; and an infrared absorbing layer formed on the other surface of the transparent dielectric substrate and configured to absorb infrared light.

The infrared absorbing layer may be formed of a resin that contains infrared absorbing pigment.

The infrared reflecting layer may be formed of a dielectric multilayer film.

Given that the wavelength that provides the transmittance of 50% of the infrared reflecting layer is $\lambda_{RT50\%}$ nm and the wavelength that provides the transmittance of 50% of the infrared absorbing layer is $\lambda_{AT50\%}$ nm, the infrared reflecting layer and the infrared absorbing layer may be formed such that $\lambda_{AT50\%} < \lambda_{RT50\%}$ is met.

Further, the infrared reflecting layer and the infrared absorbing layer may be formed such that $\lambda_{AT50\%} - \lambda_{RT50\%} \leq -10$ nm is met.

Further, the infrared reflecting layer and the infrared absorbing layer may be formed such that $-50 \text{ nm} \leq \lambda_{AT50\%} - \lambda_{RT50\%}$ is met.

The transparent dielectric substrate may be formed of glass. The infrared reflecting layer may be formed so as to reflect ultraviolet light. A protective layer may be provided on the infrared absorbing layer. The protective layer may have the function of preventing reflection of visible light. The

protective layer may have the function of preventing transmittance of ultraviolet light. A reflection prevention layer for preventing reflection of visible light may be provided on the protective layer. The reflection prevention layer may have the function of preventing transmittance of ultraviolet light. A primer layer may be provided between the transparent dielectric substrate and the infrared absorbing layer.

The infrared reflecting layer may be warped such that the surface opposite to the surface on the side of the transparent dielectric substrate is convex.

Another embodiment of the present invention relates to an imaging apparatus. The imaging apparatus comprises: the infrared cut filter as described above; and an imaging device on which light transmitted through the infrared cut filter is incident.

Optional combinations of the aforementioned constituting elements, and implementations of the invention in the form of methods, apparatuses, and systems may also be practiced as additional modes of the present invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments will now be described, by way of example only, with reference to the accompanying drawings which are meant to be exemplary, not limiting, and wherein like elements are numbered alike in several Figures, in which:

FIG. 1 is a cross sectional view showing the structure of the infrared cut filter according to the embodiment of the present invention;

FIG. 2 shows an exemplary spectral transmittance curve of an infrared reflecting layer according to the first exemplary embodiment including a dielectric multilayer film;

FIG. 3 shows an exemplary spectral transmittance curve of an infrared absorbing layer according to the second exemplary embodiment;

FIG. 4 shows an exemplary spectral transmittance curve of the infrared cut filter according to the embodiment;

FIG. 5 lists the composition of the infrared absorbing layer used in the first through third exemplary embodiments;

FIG. 6A shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 60$ nm;

FIG. 6B shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 50$ nm;

FIG. 6C shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 40$ nm;

FIG. 6D shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 30$ nm;

FIG. 6E shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 20$ nm;

FIG. 6F shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 10$ nm;

FIG. 6G shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 0$ nm;

FIG. 6H shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = -10$ nm;

FIG. 6I shows the spectral transmittance of the infrared cut filter according to the first exemplary embodiment in which $\lambda_{AT50\%} - \lambda_{RT50\%} = -20$ nm;

5

FIG. 17 shows the infrared cut filter according to yet another embodiment of the present invention;

FIG. 18 shows the infrared cut filter according to yet another embodiment of the present invention;

FIG. 19 shows an imaging apparatus in which the infrared cut filter according to the embodiments of the present invention is used;

FIG. 20 shows the spectral transmittance curves obtained when the cut-off wavelength of the infrared reflecting layer is varied;

FIG. 21 shows the spectral transmittance curve of the infrared absorbing layer used in the first exemplary embodiment;

FIG. 22 shows the spectral transmittance curve of the infrared absorbing layer used in the second exemplary embodiment; and

FIG. 23 shows the spectral transmittance curve of the infrared absorbing layer used in the third exemplary embodiment.

DETAILED DESCRIPTION OF THE INVENTION

The invention will now be described by reference to the preferred embodiments. This does not intend to limit the scope of the present invention, but to exemplify the invention.

FIG. 1 is a cross sectional view showing the structure of an infrared cut filter 10 according to an embodiment of the present invention. As shown in FIG. 1, the infrared cut filter 10 includes a transparent dielectric substrate 12, an infrared reflecting layer 14, and an infrared absorbing layer 16. The infrared reflecting layer 14 is formed on one of the surfaces of the transparent dielectric substrate 12. The infrared absorbing layer 16 is formed on the other surface of the transparent dielectric substrate 12.

For example, the infrared cut filter 10 shown in FIG. 1 is provided between the imaging lens system and the imaging device of a digital camera. The infrared cut filter 10 is implemented to receive light via the infrared reflecting layer 14 and emit light from the infrared absorbing layer 16. In other words, the infrared reflecting layer 14 as implemented in the camera faces the imaging lens system and the infrared absorbing layer 16 faces the imaging device.

The transparent dielectric substrate 12 may be a plate of a thickness of about 0.1 mm-0.3 mm. The material forming the transparent dielectric substrate 12 is non-limiting so long as it transmits visible light. For example, the transparent dielectric substrate 12 may be formed of glass. A glass substrate formed of glass is inexpensive and so is favorable in terms of cost. Alternative, a synthetic resin film or a synthetic resin substrate formed of polymethylmethacrylate (PMMA), polyethylene terephthalate (PET), polycarbonate (PC), polyimide (PI), etc. may be used as the transparent dielectric substrate 12.

The infrared reflecting layer 14 is formed on one of the surfaces of the transparent dielectric substrate 12 as described above and functions as a surface on which light is incident. The infrared reflecting layer 14 is configured to transmit visible light and reflect infrared light. The infrared reflecting layer 14 may be formed of a dielectric multilayer film including a stack of a large number of dielectric layers with different refractive indices. The optical property of the dielectric multilayer film such as spectral transmittance property can be designed at will by controlling the refractive index and thickness of each layer. The infrared reflecting layer 14 may be formed by alternately depositing a titanium oxide (TiO₂) layer and a silicon oxide (SiO₂) layer with different refractive indices on the transparent dielectric substrate 12. Other than

6

TiO₂ and SiO₂, a dielectric material such as MgF₂, Al₂O₃, MgO, ZrO₂, Nb₂O₅, and Ta₂O₅ may be used to form the dielectric multilayer film.

The infrared absorbing layer 16 is formed on the other surface of the transparent dielectric substrate 12 as described above and functions as a surface from which light exits. The infrared absorbing layer 16 is configured to transmit visible light and absorb infrared light. The light incident on the infrared cut filter 10 is transmitted through the infrared reflecting layer 14 and the transparent dielectric substrate 12 before being incident on the infrared absorbing layer 16. Therefore, the infrared absorbing layer 16 absorbs infrared light not shielded by the infrared reflecting layer 14 or the transparent dielectric substrate 12.

The infrared absorbing layer 16 may be formed by depositing resin containing infrared absorbing pigment on the transparent dielectric substrate 12. The infrared absorbing layer 16 may be a solid film formed by adding appropriate infrared absorbing pigment in a resin matrix, dissolving or dispersing the pigment, and drying and curing the matrix. Azo compound, diimmonium compound, dithiol metal complex, phthalocyanine compound, cyanine compound, etc. may be used as the infrared absorbing pigment. Alternatively, these compounds may be used in combination thereof. The resin matrix is required to retain the infrared absorbing pigment dissolved or dispersed in the matrix and to be a transparent dielectric material. Polyester, polyacryl, polyolefin, polycarbonate, polycycloolefin, polyvinyl butyral, etc. may be used as the resin matrix. These materials for resin matrix are inexpensive and so are favorable in terms of cost.

A description will now be given of the function of the infrared cut filter 10 according to the embodiment. A description will first be given of the function of the infrared cut filter according comparative embodiments.

FIG. 2 shows the spectral transmittance curve of an infrared cut filter according to the first comparative embodiment in which only an infrared reflecting layer including a dielectric multilayer film is formed on a glass substrate. FIG. 3 shows the spectral transmittance curve of an infrared cut filter according to the second comparative example in which only an infrared absorbing layer including a resin matrix that contains infrared absorbing pigment is formed on a glass substrate.

As shown in FIG. 2, the infrared cut filter according to the first comparative example exhibits dependence on the incident angle, which is characteristic to a dielectric multilayer film. The solid line in FIG. 2 represents the spectral transmittance curve that results when the incident angle is 0°, the broken line represents the spectral transmittance curve that results when the incident angle is 25°, and the chain line represents the spectral transmittance curve that results when the incident angle is 35°. Given that the wavelength that provides the transmittance of 50% is $\lambda_{RT50\%}$, $\lambda_{RT50\%}$ = about 655 nm when the incident angle is 0°. When the incident angle is 25°, $\lambda_{RT50\%}$ = about 637 nm, and, when the incident angle is 35°, $\lambda_{RT50\%}$ = about 625 nm. Thus, when the incident angle changes from 0° to 35° in the infrared cut filter according to the first comparative example, $\lambda_{RT50\%}$ is shifted to the short wavelength side by about 30 nm.

Provided that the infrared cut filter is used with an imaging device, light with a small incident angle (e.g. the incident angle of 0°) on the infrared cut filter enters the central part of the imaging device. Meanwhile, light with a large incident angle (e.g. the incident angle of 25° or 35°) on the infrared cut filter enters the periphery of the imaging device. Therefore, if the infrared cut filter having the infrared shielding property shown in FIG. 2 is used in an imaging apparatus, the spectral

transmittance property (in particular, the spectral property near the wavelength 650 nm) of light entering the imaging device will differ depending on the position on the light-receiving surface of the imaging device. This results in different colors in the central part of an image and in the periphery thereof, thereby adversely affecting color reproducibility.

Unlike the infrared cut filter according to the first comparative example, the shielding property of the infrared cut filter according to the second comparative example is not dependent on the incident angle. However, the spectral transmittance curve of the infrared cut filter according to the second comparative example shows gradual decrease in a transient range where the transmittance changes from relatively high to relatively low. Generally, an infrared cut filter is designed to have a transient range near the wavelength of 600 nm to 700 nm so as not to affect color reproducibility. An infrared cut filter is expected show an abrupt change in the transmittance in this range. Such a property is referred to as “sharp cut-off property”. Therefore, it is impossible to control color reproducibility properly by using the infrared cut filter according to the second comparative example.

We considered the disadvantage associated with the comparative examples and found out that reduction in the dependence of the shielding property on the incident angle and favorable sharp cut-off property can be realized by forming the infrared reflecting layer **14** on one surface of the transparent dielectric substrate **12** and forming the infrared absorbing layer **16** on the other surface.

FIG. 4 shows the spectral transmittance curve of the infrared cut filter **10** according to the embodiment. In FIG. 4 as in FIG. 2, the solid line represents the spectral transmittance curve that results when the incident angle is 0° , the broken line represents the spectral transmittance curve that results when the incident angle is 25° , and the chain line represents the spectral transmittance curve that results when the incident angle is 35° .

The property of the infrared cut filter **10** according to the embodiment is determined by the combination of the optical property of the infrared reflecting layer **14** and the optical property of the infrared absorbing layer **16**. It will be given that the wavelength that provides the transmittance of 50% of the infrared reflecting layer alone, when the incident angle is 0° , is $\lambda_{RT50\%}$ (nm), and the wavelength that provides the transmittance of 50% of the infrared absorbing layer alone is $\lambda_{AT50\%}$ (nm). FIG. 4 shows the spectral transmittance curve of the infrared cut filter **10** in which $\lambda_{AT50\%} = \lambda_{RT50\%} - 20$ nm, namely, in which $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 20 nm.

Given that the wavelength that provides the transmittance of 50% of the infrared cut filter **10** according to the embodiment, when the incident angle is 0° , is $\lambda_{T50\%}$ (nm), $\lambda_{T50\%}$ of the infrared cut filter **10** according to the embodiment is approximately equal to 646 nm when the incident angle is 0° , as shown in FIG. 4. When the incident angle is 25° , $\lambda_{T50\%}$ is approximately equal to 645 nm. When the incident angle is 35° , $\lambda_{T50\%}$ is approximately equal to 633 nm. Thus, $\lambda_{T50\%}$ of the infrared cut filter **10** according to the embodiment is shifted to the short wavelength side by only about 13 nm even when the incident angle changes from 0° to 35° . The dependence of $\lambda_{T50\%}$ on the incident angle is smaller than the dependence of $\lambda_{RT50\%}$ on the incident angle of the first comparative example. Referring also to FIG. 4, change in the incident angle hardly produces any change in the spectral transmittance curve in the range in which the transmittance is higher than 50%. Meanwhile, in the range in which the transmittance is lower than 50%, the spectral transmittance curve shows a difference in response to a change in the incident angle. However, the difference in the spectral transmittance

curve in the range in which the transmittance is lower than 50% hardly presents any problem because the impact on color reproducibility is small.

Further, FIG. 4 shows that the infrared cut filter **10** according to the embodiment has a transient range near the wavelength of 600 nm to 700 nm. The transmittance changes abruptly in this range with the result that a favorable sharp cut-off property is realized.

The optical property of the infrared cut filter **10** according to the embodiment is determined by the combination of the infrared reflecting layer **14** and the infrared absorbing layer **16**. The favorable optical property of the infrared reflecting layer **14** and the infrared absorbing layer **16** will now be discussed.

First, the suitable optical property of the infrared reflecting layer **14** will be discussed. The infrared reflecting layer **14** is designed to pass visible light at least in a band of 400 nm-600 nm and at least reflect infrared light with a wavelength longer than 750 nm so as to achieve the required performance. The wavelength that provides the spectral transmittance of 50% in a transient range between the pass range and the reflection range will be defined as a cut-off wavelength $\lambda_{RT50\%}$. $\lambda_{RT50\%}$ of the infrared reflecting layer **14** depends on the requirement from the spectral sensitivity area of the imaging device and is preferably designed to be near the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer **16**. More preferably, $\lambda_{RT50\%}$ is designed such that $\lambda_{AT50\%} < \lambda_{RT50\%}$.

The infrared reflecting layer **14** is designed so that the transmittance in the visible spectrum range is as high as possible. This is to allow light in the visible spectrum range necessary for imaging to reach the light-receiving surface of the imaging device as much as possible. Meanwhile, the infrared reflecting layer **14** is designed so that the transmittance in the infrared spectrum range is as low as possible. This is to shield light not contributing to imaging or light in a harmful range as much as possible. For example, the infrared reflecting layer **14** preferably has an average spectral transmittance of 90% or greater at least in a visible spectrum range in the wavelength band of 400 nm-600 nm and a spectral transmittance of less than 2% at least in an infrared spectrum range beyond the wavelength of 750 nm.

Further, the spectral transmittance of the infrared reflecting layer **14** preferably exhibits abrupt change in the transient range (referred to as “sharp cut-off property”). This is because, if the sharp cut-off property is lost and the transient range grows excessively, it will be difficult to control color reproducibility. Defining the steepness of the transmittance in the transient range as $\lambda_{RSLOPE} = |\lambda_{RT50\%} - \lambda_{RT2\%}|$ ($\lambda_{RT2\%}$ denotes the wavelength that provides the spectral transmittance of 2%), λ_{RSLOPE} of the infrared reflecting layer **14** is preferably as small as possible. For example, λ_{RSLOPE} is preferably less than 70 nm.

The spectral transmittance curve shown in FIG. 2 shows that the average spectral transmittance is 90% or greater in the visible spectrum range when the incident angle is 0° , 25° , or 35° . The average spectral transmittance in the infrared spectrum range is less than 2%. The spectral transmittance curve shown in FIG. 2 shows that λ_{RSLOPE} is less than 70 nm when the incident angle is 0° , 25° , or 35° . Therefore, the infrared absorbing layer **16** having the spectral transmittance shown in FIG. 2 can be suitably used in the infrared cut filter **10** according to the embodiment.

A description will now be given of the suitable optical property of the infrared absorbing layer **16**. The optical property required of the infrared absorbing layer **16** varies depending on the optical property of the infrared reflecting layer **14** with which the infrared absorbing layer **16** is combined.

In this embodiment, it is preferable that the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer **16** be shorter than the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer **14**, i.e., it is preferable that $\lambda_{AT50\%} < \lambda_{RT50\%}$. By ensuring that the infrared absorbing layer **16** meets this condition, the dependence of the infrared shielding property on the incident angle of the infrared cut filter **10**, namely, the shift amount of the cut-off wavelength $\lambda_{T50\%}$ of the infrared cut filter **10** occurring when the incident angle changes from 0° to 35° can be reduced.

Further, it is preferable that the average transmittance of the infrared absorbing layer **16** in the visible spectrum range be as high as possible. This is because, if the average transmittance in the range of the infrared absorbing layer **16** is small, the amount of light reaching the imaging device will be small. For example, it is preferable that the average transmittance of the infrared absorbing layer **16** in the wavelength 400 nm-600 nm be 80% or greater.

In this embodiment, the spectral transmittance of the infrared absorbing layer **16** in the long wavelength range beyond $\lambda_{RT2\%}$ is not of concern. This is because the average spectral transmittance of the infrared reflecting layer **14** is extremely small in this range so that the overall transmittance in the range of the infrared cut filter **10** is ensured to be low.

In this embodiment, it is preferable that the spectral transmittance curve of the infrared absorbing layer **16** monotonously decrease in the transient range (e.g. 600 nm- $\lambda_{RT2\%}$). This is because it is easy in this way to know the cut-off wavelength $\lambda_{T50\%}$ of the infrared cut filter **10** comprised of the combination of the layers **14** and **16**. Other advantages include easiness and flexibility of setting and easiness of control of color reproducibility.

Discussed below are first through third exemplary embodiments in which are used the infrared reflecting film and the infrared absorbing layer that meet all of the above conditions. Also, a detailed study is made of the relationship between the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer **14** and the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer **16**.

FIG. **5** lists the composition of the infrared absorbing layer used in the first through third exemplary embodiments. The infrared absorbing layer used in the first exemplary embodiment is formed in the following steps. First, methyl ethyl ketone (MEK) is used as a solvent. 0.002/0.807=0.25 wt % of KAYASORB CY-10 (cyanine compound) from NIPPON KAYAKU CO., LTD., 0.001/0.807=0.12 wt % of NIA-7200H (azo compound) from HAKKOL CHEMICAL CO., LTD., 0.003/0.807=0.37 wt % of KAYASORB IRG-022 (diimodium compound) from NIPPON KAYAKU CO., LTD. are added to 0.055% PVB (polyvinyl butyral). After blending, the solution is stirred for 10-15 minutes. The solution is applied evenly on one surface of a glass substrate by flow coating. The glass substrate is left untouched for two hours to dry. The glass substrate is heated for 20 minutes at 140°C . so as to form an infrared absorbing layer. The infrared absorbing layers of the second and third exemplary embodiments are also formed in similar steps, using the pigment shown in FIG. **5**. The spectral transmittance curves of the infrared absorbing film in isolation are shown in FIGS. **21**, **22**, and **23**. The average transmittance in the wavelength 400 nm-600 nm in the first through third exemplary embodiments is 80.4%, 80.6%, and 80.7%, respectively. In a long-wavelength range beyond the wavelength 600 nm, the curve monotonously decreases.

A more suitable condition for the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer **14** and the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer **16** will be

discussed. FIGS. **6A-6M** show the spectral transmittance curves of the infrared cut filter obtained by varying the difference between $\lambda_{AT50\%}$ and $\lambda_{RT50\%}$ in the first exemplary embodiment in units of 10 nm. FIGS. **7A-7M** show the spectral transmittance curves of the infrared cut filter obtained by varying the difference between $\lambda_{AT50\%}$ and $\lambda_{RT50\%}$ in the second exemplary embodiment in units of 10 nm. FIGS. **8A-8M** show the spectral transmittance curves of the infrared cut filter obtained by varying the difference between $\lambda_{AT50\%}$ and $\lambda_{RT50\%}$ in the third exemplary embodiment in units of 10 nm. Referring to FIGS. **6A-6M**, **7A-7M**, and **8A-8M**, the solid line represents the spectral transmittance curve that results when the incident angle is 0° , the broken line represents the spectral transmittance curve that results when the incident angle is 25° , and the chain line represents the spectral transmittance curve that results when the incident angle is 35° . In each of the exemplary embodiments, the difference between $\lambda_{AT50\%}$ and $\lambda_{RT50\%}$ is set by fixing $\lambda_{AT50\%}$ of the infrared absorbing layer **16** and varying the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer **14**, as shown in FIG. **20**. Since the infrared reflecting layer **14** is formed of a dielectric multilayer film, variation in the transient range can be easily implemented by adjusting the film thickness or the number of layers. FIG. **20** shows variation of the spectral transmittance curve of the infrared reflecting layer according to the first exemplary embodiment. The spectral transmittance curve of the infrared reflecting layer according to the second and third exemplary embodiment can be varied similarly.

FIGS. **6A**, **7A**, and **8A** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 60$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 60 nm. FIGS. **6B**, **7B**, and **8B** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 50$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 50 nm. FIGS. **6C**, **7C**, and **8C** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 40$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 40 nm. FIGS. **6D**, **7D**, and **8D** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 30$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 30 nm. FIGS. **6E**, **7E**, and **8E** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 20$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 20 nm. FIGS. **6F**, **7F**, and **8F** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 10$ nm, i.e. $\lambda_{AT50\%}$ is longer than $\lambda_{RT50\%}$ by 10 nm. FIGS. **6G**, **7G**, and **8G** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = 0$ nm, i.e. $\lambda_{AT50\%}$ is equal to $\lambda_{RT50\%}$. FIGS. **6H**, **7H**, and **8H** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = -10$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 10 nm. FIGS. **6I**, **7I**, and **8I** show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%} - \lambda_{RT50\%} = -20$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 20 nm. FIGS. **6J**, **7J**, and **8J** show the spectral transmittance curve of the infrared cut filter according to the first through third

11

exemplary embodiments, respectively, in which $\lambda_{AT50\%}-\lambda_{RT50\%}=-30$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 30 nm. FIGS. 6K, 7K, and 8K show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%}-\lambda_{RT50\%}=-40$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 40 nm. FIGS. 6L, 7L, and 8L show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%}-\lambda_{RT50\%}=-50$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 50 nm. FIGS. 6M, 7M, and 8M show the spectral transmittance curve of the infrared cut filter according to the first through third exemplary embodiments, respectively, in which $\lambda_{AT50\%}-\lambda_{RT50\%}=-60$ nm, i.e. $\lambda_{AT50\%}$ is shorter than $\lambda_{RT50\%}$ by 60 nm. The primary parameters of the spectral transmittance curve of FIGS. 6A-6M (first exemplary embodiment), the spectral transmittance curve of FIGS. 7A-7M (second exemplary embodiment), and the spectral transmittance curve of FIGS. 8A-8M (third exemplary embodiment) are shown in FIGS. 9, 10, and 11, respectively.

For evaluating the spectral transmittance curves shown in FIGS. 6A-6M, 7A-7M, and 8A-8M, we established (1) and (2) below as the property (hereinafter, referred to as “basic property”) primarily required for the infrared cut filter.

(1) average transmittance T_{ave} in the wavelength 400 nm-600 nm > 70%

(2) $\lambda_{SLOPE} = |\lambda_{T50\%} - \lambda_{T2\%}| < 70$ nm (sharp cut-off property)

With regard to the basic property related to the average transmittance T_{ave} indicated in (1), the spectral transmittance curve shown in FIG. 8A obtained when $\lambda_{AT50\%}-\lambda_{RT50\%}=60$ nm does not fulfill the requirement. However, the spectral transmittance curves shown in FIGS. 6A-6M, 7A-7M and 8B-8M meet the basic property of (1).

FIGS. 12A, 13A, and 14A respectively show the relationship in the first through third exemplary embodiments of the difference $\lambda_{AT50\%}-\lambda_{RT50\%}$ between the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer 16 and the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer 14 relative to the steepness $\lambda_{SLOPE} = |\lambda_{T50\%} - \lambda_{T2\%}|$ of the transient range of the spectral transmittance curve. As described above, the steepness (sharp cut-off property) of the spectral transmittance curve of the infrared cut filter in the transient range is preferably as small as possible, and, more specifically, less than 70 nm, as required by the basic property (2) above. Thus, FIGS. 12A, 13A, and 14A show that the condition of $-50 \leq \lambda_{AT50\%} - \lambda_{RT50\%}$ is preferable.

We established (3) below as the property necessary for improvement in the dependence of the infrared shielding property on the incident angle, the primary problem of the present invention. Given that the shift amount in the cut-off wavelength $\lambda_{T50\%}$ obtained when the incident angle changes from 0° to 35° is denoted by $\Delta\lambda_{T50\%}$,

(3) $\Delta\lambda_{T50\%} < 25$ nm

FIGS. 12B, 13B, and 14B respectively show the relationship in the first through third embodiments of the difference $\lambda_{T50\%}-\lambda_{RT50\%}$ between the cut-off wavelength $\lambda_{AT50\%}$ of the infrared absorbing layer 16 and the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer 14 relative to the shift amount $\Delta\lambda_{T50\%}$ of the cut-off wavelength $\lambda_{T50\%}$ occurring when the incident angle changes from 0° to 35° . It is preferable that $\Delta\lambda_{T50\%}$ be less than 25 nm, as required by property (3) above. Thus, FIGS. 12B, 13B, and 14B show that it is preferable that $\lambda_{AT50\%}-\lambda_{RT50\%} \leq -10$ nm.

Based on the foregoing considerations, it is preferable that the difference between the cut-off wavelength $\lambda_{AT50\%}$ of the

12

infrared absorbing layer 16 and the cut-off wavelength $\lambda_{RT50\%}$ of the infrared reflecting layer 14 meet the following condition.

$$-50 \text{ nm} \leq \lambda_{AT50\%} - \lambda_{RT50\%} \leq -10 \text{ nm}$$

By meeting all of the above requirements for property, favorable images can be obtained in which balance is achieved in factors (e.g. transmittance and color quality) contributing to image quality. The requirements for property listed above are by way of example only and can be modified so as to adapt to the property of the imaging device.

Described above is the infrared cut filter 10 according to the embodiment. The embodiment provides the infrared cut filter 10 having favorable infrared shielding property characterized by little dependence on the incident angle, by forming the infrared reflecting layer 14 on one surface of the transparent dielectric substrate 12 and forming the infrared absorbing layer 16 on the other surface.

In the infrared cut filter 10 according to the embodiment, an ordinary glass substrate can be used as the transparent dielectric substrate 12. Since it is not necessary to use fragile glass such as fluorophosphate glass which is not easy to work (e.g. to polish), the substrate can be worked in an ordinary manner (e.g. polished or cut). As a result, the thickness of the substrate can be controlled at will. For example, a thin substrate can be produced.

The property of the infrared cut filter 10 according to the embodiment is determined by the combination of the optical property of the infrared reflecting layer 14 and the optical property of the infrared absorbing layer 16. The optical property of the infrared reflecting layer 14 can be changed easily by adjusting the layer structure of the dielectric multilayer film. Also, the optical property of the infrared absorbing layer 16 can be changed easily by adjusting the type or concentration of infrared absorbing pigment included in the resin matrix or adjusting the thickness of the infrared absorbing layer. If fluorophosphate glass is used in order to impart the substrate with the infrared absorbing capability, change in the infrared absorbing property requires melting of fluorophosphate glass using a furnace, cutting of fluorophosphate glass, polishing of fluorophosphate glass for the purpose of adjusting the thickness, etc. Therefore, it is not easy to change the property. Thus, the infrared cut filter 10 according to the embodiment is also excellent in that the optical property of the infrared cut filter 10 can be changed easily.

The infrared reflecting layer 14 of the infrared cut filter 10 shown in FIG. 1 may be formed to reflect ultraviolet light. By forming the infrared reflecting layer 14 of a dielectric multilayer film, the ultraviolet reflecting function can be provided in the infrared cut filter 10 easily by adjusting the layer structure. The color filter provided in the imaging device may be adversely affected by ultraviolet light in that the life is shortened. Therefore, by removing ultraviolet light in the infrared reflecting layer 14 located in front of the imaging device, such an impact is avoided. By building the ultraviolet reflecting function in the infrared reflecting layer 14, ultraviolet light can be removed before reaching the infrared absorbing layer 16 formed of a resin matrix so that degradation of the infrared absorbing layer 16 can be prevented.

FIG. 15 shows the infrared cut filter 10 according to another embodiment of the present invention. Those components of the infrared cut filter 10 shown in FIG. 15 that are identical or corresponding to components of the infrared cut filter shown in FIG. 1 are represented by the same reference symbols and the description is omitted as appropriate.

The infrared cut filter 10 according to this embodiment differs from the infrared cut filter shown in FIG. 1 in that a

13

protective layer **18** is formed on the infrared absorbing layer **16**. As shown in FIG. **15**, the protective layer **18** is formed on the surface of the infrared absorbing layer **16** opposite to the surface facing the transparent dielectric substrate **12**. In the infrared cut filter according to this embodiment, light exits through the protective layer **18**.

Since the infrared absorbing layer **16** contains infrared absorbing pigment, the layer **16** contains organic components. For this reason, the infrared absorbing layer **16** has relatively low abrasion resistance and humidity resistance. Therefore, by providing on the infrared absorbing layer **16** the protective layer **18** having a different composition from the infrared absorbing layer **16** as in this embodiment, the infrared absorbing layer **16** can be protected.

For example, the protective layer **18** may be a sol-gel hard coating comprising tetraethyl orthosilicate (TEOS) as a main component. The protective layer **18** may be formed by (a) applying a hard coat agent on the infrared absorbing layer **16**, (b) coating the infrared absorbing layer **16** with a sol-gel film, (c) vapor-depositing a dielectric film such as an SiO₂ layer on the infrared absorbing layer **16**. However, the method is non-limiting.

In the infrared cut filter **10** shown in FIG. **15**, the protective layer **18** may be formed to prevent reflection of visible light. By covering the infrared absorbing layer **16** using a material with a refractive index lower than that of the infrared absorbing layer **16**, the protective layer **18** is provided with the function of preventing reflection of visible light. As a result, the visible light transmittance can be improved in the infrared cut filter **10** as a whole. Alternatively, a reflection preventing film formed of a dielectric multilayer film may be deposited on the infrared absorbing layer **16** to form a protective layer **18**.

The protective layer **18** in the infrared cut filter shown in FIG. **15** may be formed to prevent transmittance of ultraviolet light. This prevents ultraviolet light incident, from the light exiting surface, from reaching the imaging device and so prevents degradation of the color filter provided in the imaging device.

FIG. **16** shows the infrared cut filter **10** according to still another embodiment of the present invention. Those components of the infrared cut filter **10** shown in FIG. **16** that are identical or corresponding to components of the infrared cut filter shown in FIGS. **1** and **15** are represented by the same reference symbols and the description is omitted as appropriate.

The infrared cut filter **10** according to this embodiment differs from the infrared cut filter shown in FIG. **15** in that a reflection prevention layer **20** for preventing reflection of visible light is formed on the protective layer **18**. As shown in FIG. **16**, the reflection prevention layer **20** is formed on the surface of the protective layer **18** opposite to the surface facing the infrared absorbing layer **16**. In the infrared cut filter **10** according to this embodiment, light exits through the reflection prevention layer **20**.

Forming the reflection prevention layer **20** on the protective layer **18** as in the infrared cut filter **10** according to this embodiment also facilitates improvement in the visible light transmittance of the infrared cut filter **10** as a whole.

The reflection prevention layer **20** in the infrared cut filter **10** shown in FIG. **16** may be formed to prevent ultraviolet light transmittance. This prevents ultraviolet light incident, from the light exiting surface, from reaching the imaging device and prevents degradation of the color filter provided in the imaging device.

FIG. **17** shows the infrared cut filter **10** according to yet another embodiment of the present invention. Those compo-

14

nents of the infrared cut filter **10** shown in FIG. **17** that are identical or corresponding to components of the infrared cut filter shown in FIG. **1** are represented by the same reference symbols and the description is omitted as appropriate.

The infrared cut filter **10** according to this embodiment differs from the infrared cut filter shown in FIG. **1** in that a primer layer **22** is formed between the transparent dielectric substrate **12** and the infrared absorbing layer **16**. By forming the primer layer **22** between the transparent dielectric substrate **12** and the infrared absorbing layer **16**, adhesion property between the transparent dielectric substrate **12** and the infrared absorbing layer **16** is improved so that the environmental resistance of the infrared cut filter **10** is improved.

FIG. **18** shows the infrared cut filter **10** according to yet another embodiment of the present invention. Those components of the infrared cut filter **10** shown in FIG. **18** that are identical or corresponding to components of the infrared cut filter shown in FIG. **1** are represented by the same reference symbols and the description is omitted as appropriate.

The infrared cut filter **10** according to this embodiment differs from the infrared cut filter shown in FIG. **1** in that the infrared reflecting layer **14** is warped. The infrared reflecting layer **14** is warped such that the surface opposite to the surface on the side of the transparent dielectric substrate **12** is convex. In association with the warp of the infrared reflecting layer **14**, the transparent dielectric substrate **12** and the infrared absorbing layer **16** according to this embodiment are also warped.

As described above, when the infrared cut filter **10** is used in the imaging apparatus, the filter **10** is mounted such that the infrared reflecting layer **14** faces the imaging lens and the infrared absorbing layer **16** faces the imaging device. However, the infrared cut filter **10** is extremely thin and small so that it is not easy to distinguish between the infrared reflecting layer **14** and the infrared absorbing layer **16**. Therefore, warping of the infrared reflecting layer **14** allows the layer **14** to be identified visually. By controlling the stress on the film surface when the dielectric multilayer film is deposited on the transparent dielectric substrate **12**, the degree of warp of the infrared reflecting layer **14** can be adjusted without affecting the optical property.

FIG. **19** shows an imaging apparatus **100** in which the infrared cut filter **10** according to the embodiments of the present invention is used. As shown FIG. **19**, the imaging apparatus **100** includes an imaging lens **102**, the infrared cut filter **10**, and an imaging device **104**. The imaging device **104** may be a semiconductor solid-state imaging device such as a CCD or a CMOS. As shown in FIG. **19**, the infrared cut filter **10** is provided between the imaging lens **102** and the imaging device **104** such that the infrared reflecting layer **14** faces the imaging lens **102** and the infrared absorbing layer **16** faces the imaging device **104**.

As shown in FIG. **19**, light from a subject is condensed by the imaging lens **102**. Infrared light is removed by the infrared cut filter **10**. The resultant light is incident on the imaging device **104**. As shown in FIG. **19**, the light is incident on the infrared cut filter **10** from the imaging lens **102** at various angles of incidence. By using the infrared cut filter **10** according to any of the embodiments, infrared light can be suitably shielded regardless of the incident angle. Therefore, favorable images with high color reproducibility can be captured.

The embodiments as described above are used as the infrared cut filter **10** in the imaging apparatus. Alternatively, the infrared cut filter **10** according to the embodiments can be put to other uses. For example, the infrared cut filter **10** can be used as a heat shielding film for a wind shield glass or a side window of automobiles, or for architectural glass. Still alter-

15

natively, the infrared cut filter **10** can be used as an infrared cut filter for a plasma display panel (PDP).

Described above is an explanation based on an exemplary embodiment. The embodiment is intended to be illustrative only and it will be obvious to those skilled in the art that various modifications to constituting elements and processes could be developed and that such modifications are also within the scope of the present invention.

What is claimed is:

1. An infrared cut filter comprising:

a transparent dielectric substrate;

an infrared reflecting layer formed on one surface of the transparent dielectric substrate and configured to reflect infrared light; and

an infrared absorbing layer formed on the other surface of the transparent dielectric substrate and configured to absorb infrared light, wherein

the infrared absorbing layer is formed of a resin that contains infrared absorbing pigment,

the infrared reflecting layer is formed of a dielectric multilayer film,

given that a wavelength that provides the transmittance of 50% of the infrared reflecting layer, when an incident angle is 0° , is $\lambda_{RT50\%}$ nm and the wavelength that provides the transmittance of 50% of the infrared absorbing layer, when the incident angle is 0° , is $\lambda_{AT50\%}$ nm, the infrared reflecting layer and the infrared absorbing layer are formed such that $\lambda_{AT50\%} - \lambda_{RT50\%} \leq -10$ nm is met,

the infrared reflecting layer and the infrared absorbing layer are formed such that $-50 \text{ nm} \leq \lambda_{AT50\%} - \lambda_{RT50\%}$ is met, and

given that a cut-off wavelength that provides the transmittance of 50% of the infrared cut filter, when the incident angle is 0° , is $\lambda_{T50\%}$ nm and that the shift amount in the cut-off wavelength $\lambda_{T50\%}$ obtained when the incident angle on the infrared cut filter changes from 0° to 35° is denoted by $\Delta\lambda_{T50\%}$, $\Delta\lambda_{T50\%} < 25$ nm.

2. The infrared cut filter according to claim **1**, wherein the transparent dielectric substrate is formed of glass.

3. The infrared cut filter according to claim **1**, wherein the infrared reflecting layer is formed so as to reflect ultraviolet light.

4. The infrared cut filter according to claim **1**, wherein a protective layer is provided on the infrared absorbing layer.

5. The infrared cut filter according to claim **4**, wherein the protective layer has the function of preventing reflection of visible light.

6. The infrared cut filter according to claim **4**, wherein the protective layer has the function of preventing transmittance of ultraviolet light.

7. The infrared cut filter according to claim **4**, wherein a reflection prevention layer for preventing reflection of visible light is provided on the protective layer.

16

8. The infrared cut filter according to claim **7**, wherein the reflection prevention layer has the function of preventing transmittance of ultraviolet light.

9. The infrared cut filter according to claim **1**, wherein a primer layer is provided between the transparent dielectric substrate and the infrared absorbing layer.

10. The infrared cut filter according to claim **1**, wherein the infrared reflecting layer is warped such that the surface opposite to the surface on the side of the transparent dielectric substrate is convex, and warping of the infrared reflecting layer is formed by controlling stress when the dielectric multilayer film is deposited on the transparent dielectric substrate.

11. An imaging apparatus comprising: the infrared cut filter according to claim **1**; and an imaging device on which light transmitted by the infrared cut filter is incident, wherein the infrared absorbing layer is closer to the imaging device than the infrared reflecting layer is.

12. The infrared cut filter according to claim **1**, wherein a minimal value of transmittance less than 15% occurs when the wavelength is 650 nm-750 nm in a spectral transmittance curve of the infrared absorbing layer, and $\lambda_{RT50\%}$ of the infrared reflecting layer is in a wavelength range 600 nm-700 nm.

13. The infrared cut filter according to claim **1**, wherein a thickness of the transparent dielectric substrate is 0.1 mm-0.3 mm.

14. The infrared cut filter according to claim **11**, wherein the infrared reflecting layer is warped such that the surface opposite to the surface on the side of the transparent dielectric substrate is convex, and warping of the infrared reflecting layer is formed by controlling stress when the dielectric multilayer film is deposited on the transparent dielectric substrate.

15. A method of manufacturing the infrared cut filter according to claim **13**, comprising:

preparing a transparent dielectric substrate having a thickness of 0.1 mm-0.3 mm;

forming an infrared reflecting layer on one surface of the transparent dielectric substrate, the infrared reflecting layer having a cut-off wavelength in a wavelength band of 600 nm-700 nm, and an average spectral transmittance of 90% or greater in a wavelength band of 400 nm-600 nm;

adding an infrared absorbing pigment selected from a cyanine compound, a diimmonium compound, a phthalocyanine compound, or an azo compound to produce a PVB resin solution containing the infrared absorbing pigment; and

applying the PVB resin solution on a transparent glass substrate using a flow coating apparatus and drying the transparent glass substrate.

* * * * *