

US009293441B2

(12) **United States Patent**  
**Hoshino et al.**

(10) **Patent No.:** **US 9,293,441 B2**  
(45) **Date of Patent:** **Mar. 22, 2016**

(54) **SEMICONDUCTOR DEVICE AND METHOD OF MANUFACTURING THE SAME**

(75) Inventors: **Masataka Hoshino**, Kanagawa (JP); **Junichi Kasai**, Kanagawa (JP); **Kouichi Meguro**, Kanagawa (JP); **Ryota Fukuyama**, Kanagawa (JP); **Yasuhiro Shinma**, Kanagawa (JP); **Koji Taya**, Kanagawa (JP); **Masanori Onodera**, Kanagawa (JP); **Naomi Masuda**, Kanagawa (JP)

(73) Assignee: **CYPRESS SEMICONDUCTOR CORPORATION**, San Jose, CA (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/252,714**

(22) Filed: **Oct. 4, 2011**

(65) **Prior Publication Data**

US 2012/0025364 A1 Feb. 2, 2012

**Related U.S. Application Data**

(60) Division of application No. 12/556,408, filed on Sep. 9, 2009, now Pat. No. 8,030,179, which is a division of application No. 11/636,155, filed on Dec. 7, 2006, now Pat. No. 7,605,457, which is a continuation-in-part of application No. PCT/JP2005/022646, filed on Dec. 9, 2005.

(51) **Int. Cl.**  
**H01L 23/02** (2006.01)  
**H01L 25/065** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 25/0657** (2013.01); **H01L 25/50** (2013.01); **H01L 23/3128** (2013.01);  
(Continued)

(58) **Field of Classification Search**

CPC ..... H01L 25/0657; H01L 25/50; H01L 2225/06513; H01L 2225/06506; H01L 2225/06551; H01L 2225/06555; H01L 2224/24145; H01L 2224/24146; H01L 2224/24137; H01L 23/3128  
USPC ..... 257/777, 620, 773, E23.145, 686; 438/460

See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

5,466,634 A \* 11/1995 Beilstein et al. .... 438/15  
5,571,754 A \* 11/1996 Bertin et al. .... 438/109

(Continued)

**FOREIGN PATENT DOCUMENTS**

JP 6005665 1/1994  
JP 2001210782 A 8/2001

(Continued)

**OTHER PUBLICATIONS**

International Search Report for International Application No. PCT/JP05/22646 dated Feb. 28, 2006; 2 pages.

(Continued)



*Primary Examiner* — Michael Trinh

(74) *Attorney, Agent, or Firm* — Lowenstein Sandler LLP

(57) **ABSTRACT**

The present invention provides a semiconductor device that includes: stacked semiconductor chips, each semiconductor chip including a semiconductor substrate and a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof; first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on each semiconductor chip. The present invention also provides a method of manufacturing the semiconductor device.

**11 Claims, 14 Drawing Sheets**



- |      |                    |           |  |              |     |         |                          |
|------|--------------------|-----------|--|--------------|-----|---------|--------------------------|
| (51) | <b>Int. Cl.</b>    |           |  |              |     |         |                          |
|      | <i>H01L 25/00</i>  | (2006.01) |  | 6,849,802    | B2  | 2/2005  | Song et al.              |
|      | <i>H01L 23/31</i>  | (2006.01) |  | 6,855,572    | B2  | 2/2005  | Jeung et al.             |
|      | <i>H01L 23/495</i> | (2006.01) |  | 7,180,168    | B2* | 2/2007  | Imai ..... 257/686       |
|      |                    |           |  | 7,253,527    | B2  | 8/2007  | Tanida et al.            |
|      |                    |           |  | 7,312,521    | B2  | 12/2007 | Noma et al.              |
|      |                    |           |  | 7,585,750    | B2  | 9/2009  | Do et al.                |
|      |                    |           |  | 7,605,457    | B2  | 10/2009 | Hoshino et al.           |
|      |                    |           |  | 7,605,616    | B2* | 10/2009 | Shimbayashi ..... 327/77 |
|      |                    |           |  | 7,633,159    | B2  | 12/2009 | Boon et al.              |
|      |                    |           |  | 2003/0080398 | A1  | 5/2003  | Badehi                   |
|      |                    |           |  | 2004/0157410 | A1* | 8/2004  | Yamaguchi ..... 438/460  |
|      |                    |           |  | 2006/0065953 | A1  | 3/2006  | Kim et al.               |

- (52) **U.S. Cl.**  
 CPC . *H01L23/49575* (2013.01); *H01L 2224/32225*  
 (2013.01); *H01L 2224/32245* (2013.01); *H01L*  
*2224/48091* (2013.01); *H01L 2224/48247*  
 (2013.01); *H01L 2225/06506* (2013.01); *H01L*  
*2225/06513* (2013.01); *H01L 2225/06551*  
 (2013.01); *H01L 2225/06555* (2013.01); *H01L*  
*2924/01004* (2013.01); *H01L 2924/01078*  
 (2013.01); *H01L 2924/01079* (2013.01); *H01L*  
*2924/15311* (2013.01)

FOREIGN PATENT DOCUMENTS

JP	2001250906	A	9/2001
JP	2002076167	A	3/2002
JP	2004221372	A	8/2004
JP	2004342861	A	12/2004

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,606,198	A	2/1997	Ono et al.
5,648,684	A	7/1997	Bertin et al.
5,888,884	A	3/1999	Wojnarowski
6,180,506	B1*	1/2001	Sullivan ..... 438/618
6,180,881	B1	1/2001	Isaak
6,335,225	B1*	1/2002	Doan ..... 438/123
6,379,999	B1	4/2002	Tanabe
6,743,696	B2	6/2004	Jeung et al.
6,818,977	B2	11/2004	Poo et al.

OTHER PUBLICATIONS

USPTO Notice of Allowance for U.S. Appl. No. 11/636,155 dated Jun. 4, 2009; 7 pages.  
 USPTO Notice of Allowance for U.S. Appl. No. 12/556,408 dated Apr. 7, 2011; 7 pages.  
 Written Opinion of the International Searching Authority for International Application No. PCT/JP05/22646 dated Feb. 28, 2006; 3 pages.

\* cited by examiner

FIG. 1




FIG. 2




FIG. 3A




FIG. 3B






FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6




FIG. 7A




FIG. 7B






FIG. 8




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12




FIG. 13




FIG. 14




FIG. 15






FIG. 16




FIG. 17





FIG. 18





## 1

**SEMICONDUCTOR DEVICE AND METHOD  
OF MANUFACTURING THE SAME**CROSS-REFERENCES TO RELATED  
APPLICATIONS

This application is a divisional of U.S. patent application Ser. No. 12/556,408, filed on Sep. 9, 2009, entitled "Semiconductor Device and Method of Manufacturing the same," which is a divisional of U.S. patent application Ser. No. 11/636,155, filed on Dec. 7, 2006, entitled "Semiconductor Device and Method of Manufacturing the same," which is a continuation in part of international application number PCT/JP2005/022646, filed on Dec. 9, 2005, which are hereby incorporated herein by reference in their entirety.

## FIELD OF THE INVENTION

The present invention relates to a semiconductor device and a method of manufacturing the semiconductor device, and more particularly, to a semiconductor device that is formed with stacked semiconductor chips and a method of manufacturing the semiconductor device.

## BACKGROUND OF THE INVENTION

In recent years, there has been an increasing demand for smaller semiconductor devices that can be used as non-volatile memory media for portable electronic devices such as portable telephone devices and IC memory cards. In this trend, techniques of efficiently packaging semiconductor chips have been developed. As one of such techniques, there is a method of packaging stacked semiconductor chips.

Japanese Patent Application Publication No. 2004-342861 discloses the following technique (conventional technique 1). Firstly, grooves are formed on the upper face of a semiconductor wafer, and an insulating layer is embedded in the grooves. Through holes having conductors embedded therein are then formed in the insulating layer. The through holes are cut so as to divide the semiconductor wafer into semiconductor chips. The through holes become concavities formed on the side faces of the semiconductor chip, and the conductors formed in the through holes electrically connect the upper face and the lower face of the semiconductor chip.

Japanese Patent Application Publication No. 2004-221372 discloses the following technique (conventional technique 2). Through holes having side walls covered with conductors are formed in a semiconductor wafer. The through holes are cut so as to divide the semiconductor wafer into semiconductor chips. The semiconductor chips are stacked, and metal resin layers are formed in the concavities formed from the through holes in the side faces of the semiconductor chips. The stacked semiconductor chips are electrically connected to one another via the metal resin layers formed in the concavities.

Japanese Patent Application Publication No. 2001-250906 discloses the following technique (conventional technique 3). After semiconductor chips are stacked, wiring patterns are formed on the side faces of the stacked semiconductor chips. The stacked semiconductor chips are electrically connected to one another via the wiring patterns.

As in the conventional technique 1 and the conventional technique 2, however, the following problems are caused in a case where through holes are formed in a semiconductor wafer and are cut to divide the semiconductor wafer into semiconductor chips. Since the conductors that are embedded in the through holes or cover the side walls of the through holes are cut, the conductors are likely to come off when the

## 2

wafer is divided into chips. Also, to form through holes in a semiconductor wafer or an insulating layer, deep etching needs to be performed. This is technologically difficult, and results in higher production costs. In the conventional technique 3, wiring patterns are formed in semiconductor chips after the semiconductor chips are stacked. As a result, the production costs become higher.

## SUMMARY OF THE INVENTION

The present invention has been made in view of the above circumstances and provides a semiconductor device that has metal layers that can be formed on side faces of stacked semiconductor chips at low costs and electrically connect the semiconductor chips to one another. The present invention also provides a method of manufacturing such a semiconductor device.

According to a first aspect of the present invention, there is provided a semiconductor device including: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof, and first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips. The concavities are formed in the first insulating layer. Accordingly, the formation of these concavities is easier than the formation of concavities in a semiconductor substrate. Also, since the first metal layers are formed in the center portions of the concavities, removal of the first metal layers can be prevented when through holes are cut. Thus, a semiconductor device that has second metal layers that electrically connect the semiconductor chips and can be formed at low costs can be provided.

According to another aspect of the present invention, there is provided a semiconductor device including: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces and an upper face of the semiconductor substrate, first metal layers that are provided on side faces and an upper face of the first insulating layer, and a second insulating layer that is provided on upper faces of the first metal layers and side faces of the first insulating layer and has concavities on side faces thereof; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips, the second metal layers being connected to the first metal layers through the concavities. The concavities are formed in the first insulating layer. Accordingly, the formation of these concavities is easier than the formation of concavities in a semiconductor substrate. Also, since the first metal layers are formed in the center portions of the concavities, removal of the first metal layers can be prevented when through holes are cut. Further, electric contact between the upper semiconductor chip of the stacked semiconductor chips and the first metal layers can be prevented. Further, when the second insulating layer is formed, the second insulating layer can be prevented from not covering the first metal layers due to poor accuracy of alignment. Thus, it is possible to provide a semiconductor device that has second metal layers that electrically connect the semiconductor chips and can be formed at low costs.

According to another aspect of the present invention, there is provided a semiconductor device including a package that



has a built-in semiconductor device mounted therein, the built-in semiconductor device being the above-described semiconductor device.

According to another aspect of the present invention, there is provided a method of manufacturing a semiconductor device including: forming first grooves on an upper face of a semiconductor wafer; forming a first insulating layer that covers the upper face of the semiconductor wafer and side faces of the first grooves, and has second grooves that are formed in the first grooves and has concavities on side faces thereof, forming first metal layers on side faces of the concavities; and dividing the semiconductor wafer into a plurality of semiconductor chips by removing a bottom portion of the semiconductor wafer until the removal reaches bottom faces of the second grooves. Through holes are not formed, and accordingly, there is no need to perform the etching for forming through holes. Thus, the production costs can be lowered. Also, the bottom portion of the semiconductor substrate is removed to divide the semiconductor wafer into semiconductor chips, without the dicing of the metal layers. Thus, the first metal layers can be prevented from coming off.

According to another aspect of the present invention, there is provided a method of manufacturing a semiconductor device including: forming first grooves on an upper face of a semiconductor wafer; forming a first insulating layer that covers the upper face of the semiconductor wafer and side faces of the first grooves, and has second grooves that are formed in the first grooves, forming first metal layers on an upper face and side faces of the first insulating layer; forming a second insulating layer that covers the upper face of the first insulating layer and side faces of the second grooves, and has third grooves that are formed in the second grooves and has concavities on side faces thereof, with the first metal layers being exposed through the concavities; and dividing the semiconductor wafer into a plurality of semiconductor chips by removing a bottom portion of the semiconductor wafer until the removal reaches bottom faces of the third grooves. Through holes are not formed, and accordingly, there is no need to perform the etching for forming through holes. Thus, the production costs can be lowered. Also, the bottom portion of the semiconductor substrate is removed to divide the semiconductor wafer into semiconductor chips, without the dicing of the metal layers. Thus, the first metal layers can be prevented from coming off. Further, as the second insulating layer covers the first metal layers except for the portions exposed through the concavities, short-circuiting due to misalignment can be prevented between the first metal layers and the semiconductor substrate located above the first metal layers.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of a semiconductor device in accordance with an embodiment of the present invention;

FIG. 2 is a cross-sectional view of the semiconductor device, taken along the line A-A of FIG. 1, in accordance with an embodiment of the present invention;

FIGS. 3A and 3B are perspective views showing procedures for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIGS. 4A and 4B are perspective views also showing procedures for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIG. 5A is a top view of the semiconductor device during a manufacturing process in accordance with an embodiment of the present invention;

FIG. 5B is a cross-sectional view of the semiconductor device, taken along the line C-C of FIG. 5A, in accordance with an embodiment of the present invention;

FIG. 5C is a cross-sectional view of the semiconductor device, taken along the line D-D of FIG. 5A, in accordance with an embodiment of the present invention;

FIG. 6 is a cross-sectional view showing another procedure for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIGS. 7A and 7B are perspective views also showing procedures for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIG. 8 is a perspective view of a semiconductor device in accordance with an embodiment of the present invention;

FIGS. 9A and 9B are perspective views showing procedures for a semiconductor device in accordance with an embodiment of the present invention;

FIGS. 10A and 10B are perspective views also showing procedures for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIG. 11A is a top view of the semiconductor device during a manufacturing process in accordance with an embodiment of the present invention;

FIG. 11B is a cross-sectional view of the semiconductor device, taken along the line E-E of FIG. 11A, in accordance with an embodiment of the present invention;

FIG. 12 is a cross-sectional view showing a procedure for manufacturing the semiconductor device in accordance with an embodiment of the present invention;

FIG. 13 is a cross-sectional view of a semiconductor device in accordance with an embodiment of the present invention;

FIG. 14 is a cross-sectional view of a semiconductor device in accordance with an embodiment of the present invention; and

FIG. 15 is a cross-sectional view of a semiconductor device in accordance with an embodiment of the present invention.

FIG. 16 illustrates a block diagram of a conventional portable phone, upon which embodiments may be implemented.

FIG. 17 illustrates a block diagram of a computing device, upon which embodiments may be implemented.

FIG. 18 illustrates an exemplary portable multimedia device, or media player, in accordance with various embodiments of the present invention.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

A description will now be given, with reference to the accompanying drawings, of embodiments of the present invention.

#### First Embodiment

A first embodiment is an example of a structure formed with stacked semiconductor chips. FIG. 1 is a perspective view of a semiconductor device in accordance with the first embodiment. FIG. 2 is a cross-sectional view of the semiconductor device, taken along the line A-A of FIG. 1. As shown in FIG. 1, the semiconductor device includes stacked semiconductor chips 10 having circuits formed therein. In the example described in the following, four semiconductor chips 10 are stacked, but the present invention can be applied to any semiconductor device that are formed with more than four or less than four stacked semiconductor chips 10. Pad units 18 are formed on the upper surface of the stack of the semiconductor chips 10. Second metal layers 24 are formed on the side faces of each semiconductor chip 10.



## 5

As shown in FIG. 2, each stacked semiconductor chip 10 includes a semiconductor substrate 12 and a first insulating layer 16 formed on the side faces and the upper face of the semiconductor substrate 12. Pad electrodes 14 are formed on the semiconductor substrate 12. A first metal layer 20 is formed on the first insulating layer 16 and the side faces of the first insulating layer 16. The first metal layer 20 is electrically connected to the pad electrodes 14 in an opening formed in the first insulating layer 16, so as to form the pad units 18. A second insulating layer 22 is provided between each two neighboring semiconductor chips 10. The second insulating layer 22 electrically separates the semiconductor substrate 12 of the upper semiconductor chip 10 from the first metal layer 20 formed on the lower semiconductor chip 10. The second metal layers 24 are provided so as to electrically connect the first metal layers 20 formed on the side faces of the respective semiconductor chips 10.

Referring now to FIGS. 3A through 7B, a method of manufacturing the semiconductor device in accordance with the first embodiment is described. FIGS. 3A through 4B are perspective views of the portion of a semiconductor chip 10 indicated by "B" in FIG. 1, illustrating the procedures for forming the semiconductor chips from semiconductor wafers. Referring first to FIG. 3A, the pad electrodes 14 made of aluminum, for example, are formed on the semiconductor substrate 12 that is a silicon semiconductor wafer. The pad electrodes 14 are electrically connected to a circuit pattern formed on the semiconductor substrate 12. First grooves 40 that contain the scribe lines for dividing the semiconductor substrate 12 into semiconductor chips are formed in the upper face of the semiconductor substrate 12. Each of the first grooves 40 has a depth of 50  $\mu\text{m}$  or greater, for example, and a width of 100  $\mu\text{m}$  or greater, for example. As shown in FIG. 3B, a photosensitive polyimide film 15 is formed to cover the upper face of the semiconductor substrate 12 and the side faces of the first grooves 40 by a spin coat technique, for example. The film thickness of the polyimide film 15 on the semiconductor substrate 12 is about 10  $\mu\text{m}$ , for example.

As shown in FIG. 4A, the photosensitive polyimide film 15 is exposed through a predetermined pattern, so as to form second grooves 42 having concavities 52 in the first grooves 40 and the first insulating layer 16 having openings 50 on the pad electrodes 14. The concavities 52 extend from the upper face of the first insulating layer 16 to the bottom faces of the second grooves 42. The depth of each of the second groove 42 is 50  $\mu\text{m}$  or greater, for example, and the width of each second groove 42 is 20  $\mu\text{m}$  or greater, for example. The depth of each of the concavities 52 is 20  $\mu\text{m}$ , for example. As shown in FIG. 4B, the upper face of the first insulating layer 16 and the center of each concavity 52 are plated with copper, for example, so as to form the first metal layers 20.

FIG. 5A is a top view of the structure in the above situation. FIGS. 5B and 5C are cross-sectional views of the semiconductor chip 10, taken along the lines C-C and D-D of FIG. 5A, respectively. As shown in FIGS. 5A through 5C, the concavities 52 are formed in the second grooves 42 formed in the first insulating layer 16. The first metal layers 20 are formed in the centers of the respective concavities 52. The first metal layers 20 are connected to the pad electrodes 14 formed on the semiconductor substrate 12 through the openings 50.

FIG. 6 is a cross-sectional view of the structure, taken along the line D-D of FIG. 5A. As shown in FIG. 6, polishing is performed on the bottom face of the semiconductor substrate 12 until it reaches the semiconductor grooves 42. At this point, the thickness of the semiconductor substrate 12 is about 50  $\mu\text{m}$ , for example. Since the depth of each of the second grooves 42 is 50  $\mu\text{m}$  or greater, for example, the semiconduc-

## 6

tor substrate 12 is divided by the second grooves 42, so as to produce semiconductor chips 10. The procedure for thinning the semiconductor substrate 12 may be carried out using a technique other than polishing.

FIGS. 7A and 7B are perspective views of the portion B of FIG. 1. As shown in FIG. 7A, the semiconductor chips 10 divided in the manner shown in FIG. 6 are stacked. A second insulating layer 22 is interposed between each two semiconductor chips 10, so that the semiconductor chips 10 are bonded to one another with an adhesive agent. At this point, the concavities 52 in each of the semiconductor chips 10 form the concavity portions 52 extending from the upper face of the uppermost one of the stacked semiconductor chips 10 to the lower face of the lowermost one. The second insulating layers 22 may be formed on the first metal layers 20 before the polishing is performed on the bottom face in FIG. 6.

As shown in FIG. 7B, the concavity portions 52 of the semiconductor chips 10 are squeegeed and filled with silver paste, for example, so as to form the second metal layers 24. With the second metal layers 24, the first metal layers 20 formed in the respective semiconductor chips 10 are electrically connected. Thus, the semiconductor device in accordance with the first embodiment is completed.

In the first embodiment, the stacked semiconductor chips 10 are not necessarily identical semiconductor chips. For example, it is possible to stack semiconductor chips having semiconductor memory devices formed thereon, on semiconductor chips having logic circuits formed thereon. Also, not all the stacked semiconductor chips 10 necessarily have the pad electrodes 14 connected to all the second metal layers 24 formed in the concavity portions 52. Meanwhile, more than one pad electrode 14 may be connected to one second metal layer 24 in one semiconductor chip 10. It is possible to determine which pad electrode(s) 14 of each semiconductor chip 10 is (are) to be connected to the corresponding one(s) of the concavity portions 52, in accordance with which function is to be realized in a stacked semiconductor chips 30. In the first embodiment, each semiconductor chip 10 includes the first insulating layer 16 having the concavities 52, and the first metal layers 20. However, at least one of the stacked semiconductor chips should include the first insulating layer 16 having the concavities 52 formed therein, and the first metal layers 20.

As shown in FIG. 8, second metal layers 24a made of copper may be formed by an electroless plating technique, for example. In a case where the second metal layers are formed by an electroless plating technique, the plating layers formed on the first metal layers 20 each have a reasonable thickness. Accordingly, the plating layers formed on the first metal layers 20 of the semiconductor chips 10 having spaces in between are connected to one another over the first metal layers 20. If the first metal layers 20 of the respective semiconductor chips 10 having spaces in between are not electrically connected, an electroless plating technique is utilized to form the second metal layers 24, so as to connect the first metal layers 20 to one another.

In the semiconductor device in accordance with the first embodiment, each semiconductor chip 10 has the first insulating layer 16 formed on the side faces of the semiconductor substrate 12. The first insulating layer 16 has the concavities 52 formed at regular intervals between the top face and the lower face of the semiconductor chip 10. The first metal layers 20 are formed in the centers of the inner side faces of the concavities 52. In the semiconductor device formed with stacked semiconductor chips 10, the second metal layers 24 that electrically connect the first metal layers 20 formed on



the respective semiconductor chips **10** are formed in the concavities **52** of each semiconductor chip **10**.

The first metal layers **20** and the second metal layers **24** formed on each semiconductor chip **10** are connected, so as to connect the semiconductor chips **10** to one another via the second metal layers **24**. In a case where the concavities **52** are formed in the semiconductor substrate **12** as in the first conventional example, it is necessary to perform etching on the semiconductor substrate **12**. In the first embodiment, on the other hand, the first insulating layer **16** is formed on the side faces of the semiconductor substrate **12**, and the first insulating layer **16** has the concavities **52**. Accordingly, the concavities **52** can be easily formed. The first metal layers **20** are formed in the centers of the inner side faces of the concavities **52**. More specifically, each first metal layer **20** formed on the inner side faces of the concavities **52** extends from the first metal layer **20** formed on the upper face of the first insulating layer **16**. Any first metal layer **20** is not formed in the regions in contact with the second grooves **42**. With the first metal layers **20** being formed in this manner, it is possible to avoid the problem that is observed with the first and second conventional examples that the first metal layers **20** come off when through holes are formed. Further, it is possible to squeegee the concavities **52** with silver paste, so as to readily form the second metal layers **24**, as shown in FIG. 7B. As at least one semiconductor chip **10** among the stacked semiconductor chips **30** includes the first insulating layer **16** having the concavities **52** and the first metal layers **20**, the above described effects can be achieved with the semiconductor chip **10**.

The first insulating layer **16** is provided on the upper face and the side faces of the semiconductor substrate **12**. Accordingly, the first insulating layer **16** can be easily formed through the application of the polyimide film **16** and an exposing and developing process.

Further, the second insulating layer **22** is provided on the first metal layers **20** formed on the upper face of the first insulating layer **16**. With this arrangement, the first metal layers **20** can be prevented from coming into contact with the semiconductor chip **10** located above the subject semiconductor chip **10**. The second insulating layer **22** formed on the first metal layers **20** serves to prevent short-circuiting with the semiconductor chip **10** located above. However, if there is unevenness in the upper face of the subject semiconductor chip **10**, the thermal resistance between the semiconductor chips **10** becomes higher. Therefore, the second insulating layer **22** should preferably cover the entire upper face of each semiconductor chip **10**.

Further, each semiconductor chip **10** has the pad electrodes **14** formed on the upper face of the semiconductor substrate **12**. The first insulating layer **16** has the openings **50** on the respective pad electrodes **14**. The first metal layers **20** are also formed on the upper face of the first insulating layer **16**, and are connected to the pad electrodes **14** through the openings **50**. With this arrangement, the pad electrodes **14** of different semiconductor chips **10** can be connected to one another via the second metal layers **24**.

By the method of manufacturing the semiconductor device in accordance with the first embodiment, the first grooves **40** are formed in the upper face of the semiconductor substrate **12** that is a semiconductor wafer, as shown in FIG. 3A. As shown in FIG. 4A, the first insulating layer **16** that covers the upper face of the semiconductor substrate **12** and the side faces of the first grooves **40** is formed. The first insulating layer **16** also has the second grooves **42** inside the first grooves **40**, and the second grooves **42** have the concavities **52** formed on the side faces thereof. As shown in FIG. 4B, the

first metal layer **20** covers the inner side faces of the concavities **52**. As shown in FIG. 6, polishing is performed on the bottom face of the semiconductor substrate **12** until it reaches the bottom faces of the second grooves **42**, so as to divide the semiconductor substrate **12** into semiconductor chips **10**. By this manufacturing method, there is no need to form through holes. Accordingly, there is no need to perform etching for forming the through holes, and the production costs can be reduced. As the polishing is performed on the lower face of the semiconductor substrate **12**, there is no need to cut the metal layers by a dicing technique to obtain individual semiconductor chips **10**. Thus, the first metal layers **20** can be prevented from coming off.

Also, to form the first insulating layer **16**, the polyimide film **15** (an insulating film) is formed on the upper face of the semiconductor substrate **12** and the side faces of the first grooves **40**, as shown in FIG. 3B. The second grooves **42** having the concavities **52** are then formed in the polyimide film **15**, as shown in FIG. 4A. Through this procedure, the second grooves **42** and the concavities **52** can be easily formed, without the formation of through holes. The insulating film to be the first insulating film is an insulating film other than the polyimide film **15**. In the first embodiment, a predetermined region of the photosensitive polyimide film **15** is exposed to light, so as to form the second grooves **42** and the concavities **52**. However, the second grooves **42** and the concavities **52** may be formed by forming a photoresist on the insulating film to be the first insulating film and then performing etching.

Further, as shown in FIG. 4A, the first insulating layer **16** is formed so as to have the openings **50** on the pad electrodes **14** formed on the semiconductor substrate **12**. As shown in FIG. 4B, the first metal layers **20** are formed on the upper face of the first insulating layer **16**, so that the first metal layers **20** are connected to the pad electrodes **14** through the openings **50**. Through these procedures, the circuits formed on the semiconductor chip **10** can be electrically connected to the second metal layers **24** via the first metal layers **20**.

Further, as shown in FIG. 4B, the first metal layers **20** are formed in the centers of the inner side faces of the concavities **52**. Although the first metal layers **20** may be formed on the entire concavities **52**, the formation of the first metal layers **20** in the centers of the inner side faces of the concavities **52** is advantageous in that the silver paste is stuck on the first metal layers **20** at the time of the squeegee in the first embodiment, so as to prevent the first metal layers from coming off, as shown in FIG. 7B. Also, as shown in FIG. 8, the second metal layers **24** formed by an electroless plating technique can prevent short-circuiting between the plating layer grown from the first metal layers **20** and the first metal layers **20** in the concavities **52**.

Further, as shown in FIG. 7A, more than one semiconductor chips **10** are stacked on one another. As shown in FIG. 7B, the second metal layers **24** are formed in the concavities **52** and are connected to the respective first metal layers **20** of the semiconductor chips **10**. In this manner, the second metal layers **24** to be connected to the first metal layers **20** can be easily formed, as the concavities **52** are filled with the silver paste used for the squeegee.

#### Second Embodiment

A second embodiment is an example of a semiconductor device that has a second insulating layer formed on the first metal layers **20** and the side faces of the first insulating layer, and also has concavities on its side faces. Referring to FIGS. 9A through 12, a method of manufacturing the semiconductor



device in accordance with the second embodiment is described. Like FIG. 3A, FIGS. 9A through 10B are perspective views of the portion B of the semiconductor device. As shown in FIG. 9A, the procedures of the first embodiment illustrated in FIGS. 3A and 3B are carried out. More specifically, the second grooves 42 are formed in the first grooves 40, and the first insulating layer 16 having the openings 50 on the pad electrodes 14 is formed. The width of each of the first grooves 40 is about 100  $\mu\text{m}$ , and the width of each of the second grooves 42 is about 40  $\mu\text{m}$ , for example. The depths of each first groove 40 and each second groove 42 are both 50  $\mu\text{m}$  or greater, for example. The film thickness of the first insulating layer 16 is about 10  $\mu\text{m}$ , for example. As shown in FIG. 9B, the first metal layers 20 are formed on the upper face and the side faces of the first insulating layer 16. The first metal layers 20 are connected to the pad electrodes 14 through the openings 50, so as to form the pad units 18.

As shown in FIG. 10A, a photosensitive polyimide film 27 of 10 about  $\mu\text{m}$ , for example, is applied to the second grooves 42 in such a manner as to cover the upper face of the first insulating layer 16 and the side faces of the second grooves 42. As shown in FIG. 10B, a predetermined region of the polyimide film 27 is exposed and developed. In this manner, third grooves 44 having concavities 54 formed on the inner side faces of the second grooves 42 are formed. The depth of each of the third grooves 44 is 50  $\mu\text{m}$  or greater, for example, and the width of each of the third grooves 44 is about 20  $\mu\text{m}$ , for example. The depth of each of the concavities 54 is about 20  $\mu\text{m}$ , for example.

FIG. 11A is a top view of this structure. FIG. 11B is a cross-sectional view of the structure, taken along the line E-E of FIG. 11A. As shown in FIGS. 11A and 11B, the concavities 54 are formed in such a manner that the first metal layers 20 formed on the upper face and the side faces of the first insulating film 16 are exposed through the centers of the inner side faces of the concavities 54. Since the total width of each third groove 44 (20  $\mu\text{m}$ , for example) and the depth of the concavities on both sides (2 $\times$ 20  $\mu\text{m}$ , for example) is greater than the width of each second groove 42 (40  $\mu\text{m}$ , for example), the first metal layers 20 can be exposed through the inner side faces of the concavities 54.

FIG. 12 is a cross-sectional view of the structure, taken along the line E-E of FIG. 11A. As shown in FIG. 12, polishing is performed on the bottom face of the semiconductor substrate 12 until it reaches the third grooves 44. At this point, the thickness of the semiconductor substrate 12 is 50  $\mu\text{m}$ , for example. Since the depth of each of the third grooves 44 is 50  $\mu\text{m}$  or greater, for example, the semiconductor substrate 12 is divided by the third grooves 44 into the semiconductor chips 10. The same manufacturing procedures as those of the first embodiment illustrated in FIGS. 7A and 7B are then carried out to complete the semiconductor device in accordance with the second embodiment.

Unlike the structure of the first embodiment, the structure of the second embodiment includes a second insulating layer 26 that is formed on the upper faces of the first metal layers 20 and the side faces of the first insulating layer 16, and has the concavities 54 on its side faces. Further, the second metal layers 24 are connected to the first metal layers 20 formed on each semiconductor chip 10 through the concavities 52. By virtue of the second insulating layer 26, electric contact between the semiconductor substrate 12 of the semiconductor chip 10 stacked on the subject semiconductor chip 10 and the first metal layers 20 can be prevented. Also, since the second insulating layer 26 is provided on the side faces of the first insulating layer 16, the second insulating layer 26 is prevented from not covering the first metal layers 20 when the

positioning accuracy in the formation of the second insulating layer 26 is poor. As in the first embodiment, at least one of the stacked semiconductor chips should include the first insulating layer 16 having the concavities 52, the first metal layer 20, and the second insulating layer 26.

By the method of manufacturing the semiconductor device in accordance with the second embodiment, the first grooves 40 are formed on the upper face of the semiconductor substrate 12 that is a semiconductor wafer, as shown in FIG. 9A. The first insulating layer 16 having second grooves 42 formed therein is formed in the first grooves 40, so as to cover the upper face of the semiconductor substrate 12 and the side faces of the first grooves 40. As shown in FIG. 9B, the first metal layers 20 are formed on the upper face of the first insulating layer 16. As shown in FIG. 10B, the third grooves 44 having the concavities 54 formed on the inner side faces of the second grooves 42 are provided to cover the upper face of the first insulating layer 16 and the side faces of the second grooves 42. The second insulating layer 26 is formed in such a manner as to expose the first metal layers 20 through the inner side faces of the concavities 54. As shown in FIG. 12, polishing is performed on the bottom face of the semiconductor substrate 12 until it reaches the bottom faces of the third grooves 44, so as to divide the semiconductor substrate 12 into semiconductor chips 10. In the first embodiment, misalignment might be caused between the second insulating layer 22 and the first metal layers 20. For example, if the second insulating layer 22 does not properly cover the first metal layers 20, short-circuiting is caused between the first metal layers 20 and the semiconductor substrate 12 of the semiconductor chip 10 stacked on the subject semiconductor chip 10. Meanwhile, if a second insulating layer is formed in the concavities 54 of the first insulating layer 16, it is difficult to form the second metal layers 24. In addition to the same effects as those of the first embodiment, the manufacturing method in accordance with the second embodiment can achieve the effect that short-circuiting between the first metal layers 20 and the semiconductor substrate 12 above the first metal layers 20 due to misalignment can be prevented, since the second insulating layer 26 can cover the first metal layers 20 except for the first metal layers 20 exposed through the concavities 54.

Further, as shown in FIG. 10A, to form the second insulating layer 26, the polyimide film 27 (an insulating film) is formed on the first metal layers 20 and the first insulating layer 16. As shown in FIG. 10B, the third grooves 44 having the concavities 54 are formed in the polyimide film 27. Through these procedures, the second grooves 44 and the concavities 54 can be easily formed. The insulating film to be the second insulating film may be an insulating film other than the polyimide film 27. Also, the third grooves 44 and the concavities 54 may be formed by forming a photoresist on the insulating film to be the second insulating film and then performing etching.

### Third Embodiment

Third through fifth embodiments are examples of semiconductor devices each having stacked semiconductor chips (built-in semiconductor devices) mounted in packages. As shown in FIG. 13, the package has a printed board 32 made of glass epoxy resin, and the stacked semiconductor chips 30 of the first or the second embodiment are flip-chip mounted on the printed board 32 with solder balls 33. The solder balls 33 are provided on the pad units 18 of the uppermost semiconductor chip 10 of the first embodiment shown in FIG. 1, for example. Solder balls 31 are provided on the opposite face



## 11

from the semiconductor chips **30** stacked on the printed board **32**. The solder balls **31** and the solder balls **33** are connected with connecting portions (not shown) of the printed board **32**.

## Fourth Embodiment

As shown in FIG. **14**, the package includes a printed board **32** and epoxy resin **35**, and stacked semiconductor chips (built-in semiconductor devices) are face-up mounted on the printed board **32**. The printed board **32** and the semiconductor chips **30** are connected with wires **34**. The wires **34** are connected to the pad units **18** of the uppermost semiconductor chip **10** of the first embodiment shown in FIG. **1**, for example. The stacked semiconductor chips **30** are sealed with the epoxy resin **35**. In the third and fourth embodiments, the stacked semiconductor chips are mounted on the printed board **32**. However, the stacked semiconductor chips may be mounted on a substrate having conductive wires formed on an insulating substrate.

## Fifth Embodiment

As shown in FIG. **15**, the package includes a lead frame **36** and epoxy resin **37**, and stacked semiconductor chips **30** (built-in semiconductor devices) are mounted on the lead frame **36**. The lead frame **36** and the stacked semiconductor chips **30** are connected with wires **38**. The stacked semiconductor chips **30** are resin-sealed with the epoxy resin **37**, for example. As in the third through fifth embodiments, the stacked semiconductor chips **30** (built-in semiconductor devices) of the first or second embodiment may form a semiconductor device mounted in a package.

In the first and second embodiments, the first insulating layer **16** and the second insulating layer **26** are insulating films made of polyimide. However, those insulating layers are not necessarily polyimide films. For example, it is possible to employ an inorganic film such as silicon oxide film, or an organic film. The first metal layers **20** are made of copper and formed by a plating method. However, other metal layers can be employed for the first metal layers **20**. For example, it is possible to employ aluminum or gold. The second metal layers **24** are metal layers formed with silver paste by an electroless plating technique. However, other metal layers may be employed for the second metal layers **24**. For example, it is possible to employ gold or copper.

Embodiments generally relates to semiconductor devices. More particularly, embodiments allow lower-cost semiconductor devices. In one implementation, the various embodiments are applicable to flash memory and devices that utilize flash memory. Flash memory is a form of non-volatile memory that can be electrically erased and reprogrammed. As such, flash memory, in general, is a type of electrically erasable programmable read only memory (EEPROM).

Like Electrically Erasable Programmable Read Only Memory (EEPROM), flash memory is nonvolatile and thus can maintain its contents even without power. However, flash memory is not standard EEPROM. Standard EEPROMs are differentiated from flash memory because they can be erased and reprogrammed on an individual byte or word basis while flash memory can be programmed on a byte or word basis, but is generally erased on a block basis. Although standard EEPROMs may appear to be more versatile, their functionality requires two transistors to hold one bit of data. In contrast, flash memory requires only one transistor to hold one bit of data, which results in a lower cost per bit. As flash memory

## 12

costs far less than EEPROM, it has become the dominant technology wherever a significant amount of non-volatile, solid-state storage is needed.

Exemplary applications of flash memory include digital audio players, digital cameras, digital video recorders, and mobile phones. Flash memory is also used in USB flash drives, which are used for general storage and transfer of data between computers. Also, flash memory is gaining popularity in the gaming market, where low-cost fast-loading memory in the order of a few hundred megabytes is required, such as in game cartridges. Additionally, flash memory is applicable to cellular handsets, smartphones, personal digital assistants, set-top boxes, digital video recorders, networking and telecommunication equipments, printers, computer peripherals, automotive navigation devices, and gaming systems.

As flash memory is a type of non-volatile memory, it does not need power to maintain the information stored in the chip. In addition, flash memory offers fast read access times and better shock resistance than traditional hard disks. These characteristics explain the popularity of flash memory for applications such as storage on battery-powered devices (e.g., cellular phones, mobile phones, IP phones, wireless phones, etc.).

Flash memory stores information in an array of floating gate transistors, called "cells", each of which traditionally stores one bit of information. However, newer flash memory devices, such as MirrorBit® Flash Technology from Spansion Inc., can store more than 1 bit per cell. The MirrorBit cell doubles the intrinsic density of a Flash memory array by storing two physically distinct bits on opposite sides of a memory cell. Each bit serves as a binary bit of data (e.g., either 1 or 0) that is mapped directly to the memory array. Reading or programming one side of a memory cell occurs independently of whatever data is stored on the opposite side of the cell.

With regards to wireless markets, flash memory that utilizes MirrorBit® technology has several key advantages. For example, flash memory that utilizes MirrorBit® technology is capable of burst-mode access as fast as 80 MHz, page access times as fast as 25 ns, simultaneous read-write operation for combined code and data storage, and low standby power (e.g., 1  $\mu$ A).

FIG. **16** shows a block diagram of a conventional portable telephone **2010** (e.g., cell phone, cellular phone, mobile phone, internet protocol phone, wireless phone, etc.), upon which embodiments can be implemented. The cell phone **2010** includes an antenna **2012** coupled to a transmitter **2014** and a receiver **2016**, as well as a microphone **2018**, a speaker **2020**, a keypad **2022**, and a display **2024**. The cell phone **2010** also includes a power supply **2026** and a central processing unit (CPU) **2028**, which may be an embedded controller, conventional microprocessor, or the like. In addition, the cell phone **2010** includes integrated, flash memory **2030**. Flash memory **2030** includes a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof, and first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips. According to various embodiments, it is possible to provide a semiconductor device, such as flash memory, that has metal layers that are formed on the side faces of stacked semiconductor chips, and electrically connect the semiconductor chips. The present invention also provides a method of manu-



facturing such a semiconductor device. As a result, the flash memory **2030** is able to be manufactured at a much lower cost than previous. This decreased cost for the flash memory translates into lower costs for various devices, such as mobile phones, cellular phones, internet protocol phones, and/or wireless phones.

Flash memory comes in two primary varieties, NOR-type flash and NAND-type flash. While the general memory storage transistor is the same for all flash memory, it is the interconnection of the memory cells that differentiates the designs. In a conventional NOR-type flash memory, the memory cell transistors are connected to the bit lines in a parallel configuration, while in a conventional NAND-type flash memory, the memory cell transistors are connected to the bit lines in series. For this reason, NOR-type flash is sometimes referred to as “parallel flash” and NAND-type flash is referred to as “serial flash.”

Traditionally, portable phone (e.g., cell phone) CPUs have needed only a small amount of integrated NOR-type flash memory to operate. However, as portable phones (e.g., cell phone) have become more complex, offering more features and more services (e.g., voice service, text messaging, camera, ring tones, email, multimedia, mobile TV, MP3, location, productivity software, multiplayer games, calendar, and maps.), flash memory requirements have steadily increased. Thus, a less expensive flash memory will render a portable phone more competitive in the telecommunications market.

Also, as mentioned above, flash memory is applicable to a variety of devices other than portable phones. For instance, flash memory can be utilized in personal digital assistants, set-top boxes, digital video recorders, networking and telecommunication equipments, printers, computer peripherals, automotive navigation devices, and gaming systems.

FIG. 17 illustrates a block diagram of a computing device **2100**, upon which embodiments of the present claimed subject matter can be implemented. Although computing device **2100** is shown and described in FIG. 17 as having certain numbers and types of elements, the embodiments are not necessarily limited to the exemplary implementation. That is, computing device **2100** can include elements other than those shown, and can include more than one of the elements that are shown. For example, computing device **2100** can include a greater number of processing units than the one (processing unit **2102**) shown. Similarly, in another example, computing device **2100** can include additional components not shown in FIG. 17.

Also, it is appreciated that the computing device **2100** can be a variety of things. For example, computing device **2100** may be, but is not limited to, a personal desktop computer, a portable notebook computer, a personal digital assistant (PDA), and a gaming system. Flash memory is especially useful with small-form-factor computing devices such as PDAs and portable gaming devices. Flash memory offers several advantages. In one example, flash memory is able to offer fast read access times while at the same time being able to withstand shocks and bumps better than standard hard disks. This is important as small computing devices are often moved around and encounter frequent physical impacts. Also, flash memory is more able than other types of memory to withstand intense physical pressure and/or heat. Thus, portable computing devices are able to be used in a greater range of environmental variables.

In its most basic configuration, computing device **2100** typically includes at least one processing unit **2102** and memory **2104**. Depending on the exact configuration and type of computing device, memory **2104** may be volatile (such as RAM), non-volatile (such as ROM, flash memory, etc.) or

some combination of the two. This most basic configuration of computing device **2100** is illustrated in FIG. 17 by line **2106**. Additionally, device **2100** may also have additional features/functionality. For example, device **2100** may also include additional storage (removable and/or non-removable) including, but not limited to, magnetic or optical disks or tape. In one example, in the context of a gaming system, the removable storage could be a game cartridge receiving component utilized to receive different game cartridges. In another example, in the context of a Digital Versatile Disc (DVD) recorder, the removable storage is a DVD receiving component utilized to receive and read DVDs. Such additional storage is illustrated in FIG. 17 by removable storage **2108** and non-removable storage **2110**. Computer storage media includes volatile and nonvolatile, removable and non-removable media implemented in any method or technology for storage of information such as computer readable instructions, data structures, program modules or other data. Memory **2104**, removable storage **2108** and non-removable storage **2110** are all examples of computer storage media. Computer storage media includes, but is not limited to, RAM, ROM, EEPROM, flash memory **2120** or other memory technology, CD-ROM, digital video disks (DVD) or other optical storage, magnetic cassettes, magnetic tape, magnetic disk storage or other magnetic storage devices, or any other medium which can be used to store the desired information and which can be accessed by device **2100**. Any such computer storage media may be part of device **2100**.

In the present embodiment, the flash memory **2120** comprises: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof, and first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips. According to various embodiments, it is possible to provide a semiconductor device, such as flash memory, that has metal layers that are formed on the side faces of stacked semiconductor chips, and electrically connect the semiconductor chips. The present invention also provides a method of manufacturing such a semiconductor device. As a result, the flash memory **2030** is able to be manufactured at a much lower cost than previous. This decreased cost for the flash memory translates into lower costs for various devices, such as personal digital assistants, set-top boxes, digital video recorders, networking and telecommunication equipments, printers, computer peripherals, automotive navigation devices, gaming systems, mobile phones, cellular phones, internet protocol phones, and/or wireless phones. Further, in one embodiment, the flash memory **2120** utilizes MirrorBit® technology to allow storing of two physically distinct bits on opposite sides of a memory cell.

Device **2100** may also contain communications connection(s) **2112** that allow the device to communicate with other devices. Communications connection(s) **2112** is an example of communication media. Communication media typically embodies computer readable instructions, data structures, program modules or other data in a modulated data signal such as a carrier wave or other transport mechanism and includes any information delivery media. The term “modulated data signal” means a signal that has one or more of its characteristics set or changed in such a manner as to encode information in the signal. By way of example, and not limitation, communication media includes wired media such as a



wired network or direct-wired connection, and wireless media such as acoustic, RF, infrared and other wireless media. The term computer readable media as used herein includes both storage media and communication media.

Device **2100** may also have input device(s) **2114** such as keyboard, mouse, pen, voice input device, game input device (e.g., a joy stick, a game control pad, and/or other types of game input device), touch input device, etc. Output device(s) **2116** such as a display (e.g., a computer monitor and/or a projection system), speakers, printer, network peripherals, etc., may also be included. All these devices are well known in the art and need not be discussed at length here.

Aside from mobile phones and portable computing devices, flash memory is also widely used in portable multimedia devices, such as portable music players. As users would desire a portable multimedia device to have as large a storage capacity as possible, an increase in memory density would be advantageous. Users would also benefit from reduced memory read time and reduced cost.

FIG. **18** shows an exemplary portable multimedia device, or media player, **3100** in accordance with an embodiment of the invention. The media player **3100** includes a processor **3102** that pertains to a microprocessor or controller for controlling the overall operation of the media player **3100**. The media player **3100** stores media data pertaining to media assets in a file system **3104** and a cache **3106**. The file system **3104** is, typically, a storage medium or a plurality of storage media, such as disks, memory cells, and the like. The file system **3104** typically provides high capacity storage capability for the media player **3100**. Also, file system **3104** includes flash memory **3130**. In the present embodiment, the flash memory **3130** comprises: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof, and first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips. According to various embodiments, it is possible to provide a semiconductor device, such as flash memory, that has metal layers that are formed on the side faces of stacked semiconductor chips, and electrically connect the semiconductor chips. The present invention also provides a method of manufacturing such a semiconductor device. As a result, the flash memory **2030** is able to be manufactured at a much lower cost than previous. This decreased cost for the flash memory translates into lower costs for various devices, such as personal digital assistants, set-top boxes, digital video recorders, networking and telecommunication equipments, printers, computer peripherals, automotive navigation devices, gaming systems, mobile phones, cellular phones, internet protocol phones, and/or wireless phones. However, since the access time to the file system **3104** is relatively slow, the media player **3100** can also include a cache **3106**. The cache **3106** is, for example, Random-Access Memory (RAM) provided by semiconductor memory. The relative access time to the cache **3106** is substantially shorter than for the file system **3104**. However, the cache **3106** does not have the large storage capacity of the file system **3104**. Further, the file system **3104**, when active, consumes more power than does the cache **3106**. The power consumption is particularly important when the media player **3100** is a portable media player that is powered by a battery (not shown). The media player **3100** also includes a RAM **3122** and a Read-Only Memory (ROM) **3120**. The ROM **3120** can store programs,

utilities or processes to be executed in a non-volatile manner. The RAM **3122** provides volatile data storage, such as for the cache **3106**.

The media player **3100** also includes a user input device **3108** that allows a user of the media player **3100** to interact with the media player **3100**. For example, the user input device **3108** can take a variety of forms, such as a button, keypad, dial, etc. Still further, the media player **3100** includes a display **3110** (screen display) that can be controlled by the processor **3102** to display information to the user. A data bus **3124** can facilitate data transfer between at least the file system **3104**, the cache **3106**, the processor **3102**, and the CODEC **3112**. The media player **3100** also includes a bus interface **3116** that couples to a data link **3118**. The data link **3118** allows the media player **3100** to couple to a host computer.

In one embodiment, the media player **3100** serves to store a plurality of media assets (e.g., songs, photos, video, etc.) in the file system **3104**. When a user desires to have the media player play/display a particular media item, a list of available media assets is displayed on the display **3110**. Then, using the user input device **3108**, a user can select one of the available media assets. The processor **3102**, upon receiving a selection of a particular media item, supplies the media data (e.g., audio file, graphic file, video file, etc.) for the particular media item to a coder/decoder (CODEC) **3110**. The CODEC **3110** then produces analog output signals for a speaker **3114** or a display **3110**. The speaker **3114** can be a speaker internal to the media player **3100** or external to the media player **3100**. For example, headphones or earphones that connect to the media player **3100** would be considered an external speaker.

In a particular embodiment, the available media assets are arranged in a hierarchical manner based upon a selected number and type of groupings appropriate to the available media assets. For example, in the case where the media player **3100** is an MP3-type media player, the available media assets take the form of MP3 files (each of which corresponds to a digitally encoded song or other audio rendition) stored at least in part in the file system **3104**. The available media assets (or in this case, songs) can be grouped in any manner deemed appropriate. In one arrangement, the songs can be arranged hierarchically as a list of music genres at a first level, a list of artists associated with each genre at a second level, a list of albums for each artist listed in the second level at a third level, while at a fourth level a list of songs for each album listed in the third level, and so on.

Finally, various aspects of the present invention are summarized in the following.

According to a first aspect of the present invention, there is provided a semiconductor device including: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces of the semiconductor substrate and has concavities formed on side faces thereof, and first metal layers that are provided in center portions of inner side faces of the concavities; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips.

In the above-described semiconductor device, the first insulating layer may be provided on an upper face of the semiconductor substrate. The first insulating layer can be easily formed.

In the above-described semiconductor device, the first metal layers may be provided on an upper face of the first insulating layer; and the semiconductor device may further include a second insulating layer that is formed on upper faces



of the first metal layers. Electric contact between the upper semiconductor chip of the stacked semiconductor chips and the first metal layers can be prevented.

According to a second aspect of the present invention, there is provided a semiconductor device including: a plurality of stacked semiconductor chips, at least one of the semiconductor chips including a semiconductor substrate, a first insulating layer that is provided on side faces and an upper face of the semiconductor substrate, first metal layers that are provided on side faces and an upper face of the first insulating layer, and a second insulating layer that is provided on upper faces of the first metal layers and side faces of the first insulating layer and has concavities on side faces thereof; and second metal layers that are provided in the concavities and are connected to the first metal layers formed on the at least one of the semiconductor chips, the second metal layers being connected to the first metal layers through the concavities.

In the above-described semiconductor device, the at least one of the semiconductor chips may include pad electrodes that are provided on the semiconductor substrate; the first insulating layer may have openings that are formed over the pad electrodes; and the first metal layers may be also provided on an upper face of the first insulating layer, and are connected to the pad electrodes through the openings. The pad electrodes of different semiconductor chips can be connected via the second metal layers.

According to a third aspect of the present invention, there is provided a semiconductor device including a package that has a built-in semiconductor device mounted therein, the built-in semiconductor device being the above-described semiconductor device. In the above-described structure, the package may have a substrate; and the built-in semiconductor device may be face-down mounted on the substrate. In the above-described structure, the package may have a substrate; and the built-in semiconductor device may be face-up mounted on the substrate. In the above-described structure, the package may have a lead frame; and the built-in semiconductor device may be sealed with resin.

According to a fourth aspect of the present invention, there is provided a method of manufacturing a semiconductor device including: forming first grooves on an upper face of a semiconductor wafer; forming a first insulating layer that covers the upper face of the semiconductor wafer and side faces of the first grooves, and has second grooves that are formed in the first grooves and has concavities on side faces thereof, forming first metal layers on side faces of the concavities; and dividing the semiconductor wafer into a plurality of semiconductor chips by removing a bottom portion of the semiconductor wafer until the removal reaches bottom faces of the second grooves.

In the above-described method, forming the first insulating layer may include: forming an insulating film on the upper face of the semiconductor wafer; and forming the second grooves that have the concavities formed in the insulating film. The second grooves and the concavities can be easily formed.

In the above-described method, forming the first insulating layer may include: forming the first insulating layer that has openings on pad electrodes formed on the semiconductor wafer; and forming the first metal layers may include forming the first metal layers that are formed on an upper face of the first insulating layer and are connected to the pad electrodes through the openings. The circuits formed on the semiconductor chips and the second metal layers can be electrically connected via the first metal layers.

In the above-described method, forming the first metal layers may include forming the first metal layers on an upper

face of the first insulating layer; and the method may further include forming a second insulating layer on upper faces of the first metal layers. Electric contact between the upper semiconductor chip of the stacked semiconductor chips and the first metal layers can be prevented.

In the above-described method, forming the first metal layers may include forming the first metal layers at center portions of inner side faces of the concavities. The first metal layers can be prevented from coming off.

According to a fifth aspect of the present invention, there is provided a method of manufacturing a semiconductor device including: forming first grooves on an upper face of a semiconductor wafer; forming a first insulating layer that covers the upper face of the semiconductor wafer and side faces of the first grooves, and has second grooves that are formed in the first grooves, forming first metal layers on an upper face and side faces of the first insulating layer; forming a second insulating layer that covers the upper face of the first insulating layer and side faces of the second grooves, and has third grooves that are formed in the second grooves and has concavities on side faces thereof, with the first metal layers being exposed through the concavities; and dividing the semiconductor wafer into a plurality of semiconductor chips by removing a bottom portion of the semiconductor wafer until the removal reaches bottom faces of the third grooves.

In the above-described method, forming the second insulating layer may include: forming an insulating film on the semiconductor wafer; and forming the third grooves that have the concavities formed in the insulating film. The second grooves and the concavities can be easily formed.

The above-described method may further include: stacking a plurality of semiconductor chips that include at least one semiconductor chip divided from the semiconductor wafer; and forming second metal layers in the concavities, the first metal layers being connected to the second metal layers. The second metal layers to be connected to the respective first metal layers can be easily formed by carrying out a squeegee process with silver paste and filling the concavities with the silver paste.

In the above-described method, forming the second metal layers may include forming the second metal layers by an electroless plating technique. The second metal layers can be formed so that the respective first metal layers are connected to the second metal layers.

As described above, the present invention provides a semiconductor device that has metal layers that are formed on the side faces of stacked semiconductor chips at low costs, and electrically connect the semiconductor chips. The present invention also provides a method of manufacturing such a semiconductor device.

Although the preferred embodiments of the present invention have been described so far, the present invention is not limited to the above specific examples, and various changes and modifications may be made to them within the scope of the present invention.

The invention claimed is:

1. A wireless communications device, comprising:
  - a flash memory comprising:
    - a plurality of stacked semiconductor chips, at least one of the semiconductor chips comprising:
      - a semiconductor substrate;
      - a first insulating layer on a top face and side faces of the semiconductor substrate with concavities on side faces thereof, wherein said concavities have planar side surfaces that extend vertically from a first edge at the top face of the semiconductor sub-



19

strate to a second edge at the bottom face of the semiconductor substrate, wherein the first edge is beveled;

first metal layers that are provided in center portions of the concavities in a direction that is orthogonal to a direction of the top face and above the top face in a direction that is parallel to the direction of the top face; and

second metal layers that are provided in the concavities above and contacting the first metal layers and filling the concavities;

a processor;

a communications component;

a transmitter;

a receiver; and

an antenna connected to the transmitter circuit and the receiver circuit.

2. The wireless communications device of claim 1, wherein said flash memory is NAND flash memory.

3. The wireless communications device of claim 1, wherein said flash memory is NOR flash memory.

4. The wireless communications device of claim 1, wherein said flash memory comprises at least one memory cell operable to store more than one bit.

5. A computing device comprising:

a processor;

an input component;

an output component;

a memory comprising:

a volatile memory; and

a flash memory comprising:

a plurality of stacked semiconductor chips, at least one of the semiconductor chips comprising:

a semiconductor substrate;

a first insulating layer on a top face and side faces of the semiconductor substrate with concavities formed on side faces thereof wherein said concavities have planar side surfaces that extend vertically from a first edge at the top face of the semiconductor substrate to a second edge at the bottom face of the semiconductor substrate, wherein the first edge is beveled;

first metal layers in center portions of the concavities in a direction that is orthogonal to a direction

20

of the top face and above the top face in a direction that is parallel to the direction of the top face; and

second metal layers that are provided in the concavities above and contacting the first metal layers and filling the concavities.

6. The computing device of claim 5, wherein said computing device is a personal computer (PC).

7. The computing device of claim 5, wherein said computing device is a personal digital assistant (PDA).

8. The computing device of claim 5, wherein said computing device is a gaming system.

9. A portable media player comprising:

a processor;

a cache;

a user input component;

a coder-decoder component; and

a memory comprising:

a flash memory comprising:

a plurality of stacked semiconductor chips, at least one of the semiconductor chips comprising:

a semiconductor substrate;

a first insulating layer on a top face and side faces of the semiconductor substrate with concavities on side faces thereof wherein said concavities have planar side surfaces that extend vertically from a first edge at the top face of the semiconductor substrate to a second edge at the bottom face of the semiconductor substrate, wherein the first edge is beveled;

first metal layers that are provided in center portions of the concavities in a direction that is orthogonal to a direction of the top face and above the top face in a direction that is parallel to the direction of the top face; and

second metal layers that are provided in the concavities above and contacting the first metal layers and filling the concavities.

10. The portable media player of claim 9, wherein said portable media player is a portable music player.

11. The portable media player of claim 9, wherein said portable media player is a portable video player.

\* \* \* \* \*