

US009449984B2

(12) **United States Patent**
Alsmeier et al.

(10) **Patent No.:** **US 9,449,984 B2**
(45) **Date of Patent:** ***Sep. 20, 2016**

(54) **VERTICAL NAND DEVICE WITH LOW CAPACITANCE AND SILICIDED WORD LINES**

(71) Applicant: **SANDISK TECHNOLOGIES, INC.**,
Plano, TX (US)

(72) Inventors: **Johann Alsmeier**, San Jose, CA (US);
Peter Rabkin, Cupertino, CA (US)

(73) Assignee: **SANDISK TECHNOLOGIES LLC**,
Plano, TX (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **14/465,099**

(22) Filed: **Aug. 21, 2014**

(65) **Prior Publication Data**

US 2014/0361360 A1 Dec. 11, 2014

Related U.S. Application Data

(63) Continuation of application No. 13/443,287, filed on Apr. 10, 2012, now Pat. No. 8,847,302.

(51) **Int. Cl.**
H01L 29/66 (2006.01)
H01L 27/115 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC ... **H01L 27/11582** (2013.01); **H01L 21/28282** (2013.01); **H01L 21/764** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 27/11524
USPC 257/331, 316, 390
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,005,350 B2 2/2006 Walker et al.
7,023,739 B2 4/2006 Chen et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN 0N102237314 A 11/2011
WO WO02/15277 A2 2/2002
WO WO2011/104782 A1 9/2011

OTHER PUBLICATIONS

Jang et al., "Vertical Cell Array Using TCAT (Terabit Cell Array Transistor) Technology for Ultra High Density NAND Flash Memory," 2009 Symposium on VLSI Technology Digest of Technical Papers, pp. 192-193.

(Continued)

Primary Examiner — Phat X Cao


Assistant Examiner — Mohammad M Hoque

(74) *Attorney, Agent, or Firm* — The Marbury Law Group PLLC

(57) **ABSTRACT**

A three dimensional memory device including a substrate and a semiconductor channel. At least one end portion of the semiconductor channel extends substantially perpendicular to a major surface of the substrate. The device also includes at least one charge storage region located adjacent to semiconductor channel and a plurality of control gate electrodes having a strip shape extending substantially parallel to the major surface of the substrate. The plurality of control gate electrodes include at least a first control gate electrode located in a first device level and a second control gate electrode located in a second device level located over the major surface of the substrate and below the first device level. Each of the plurality of control gate electrodes includes a first edge surface which is substantially free of silicide, the first edge surface facing the semiconductor channel and the at least one charge storage region and a silicide located on remaining surfaces of the control gate electrode.

14 Claims, 3 Drawing Sheets



- (51) **Int. Cl.**
H01L 21/28 (2006.01)
H01L 21/764 (2006.01)
H01L 29/792 (2006.01)
H01L 29/49 (2006.01)
H01L 29/51 (2006.01)
- (52) **U.S. Cl.**
CPC **H01L29/4933** (2013.01); **H01L 29/512**
(2013.01); **H01L 29/7926** (2013.01); **H01L**
27/1157 (2013.01)
- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- 7,177,191 B2 2/2007 Fasoli et al.
7,221,588 B2 5/2007 Fasoli et al.
7,233,522 B2 6/2007 Chen et al.
7,514,321 B2 4/2009 Mokhlesi et al.
7,575,973 B2 8/2009 Mokhlesi et al.
7,745,265 B2 6/2010 Mokhlesi et al.
7,808,038 B2 10/2010 Mokhlesi et al.
7,848,145 B2 12/2010 Mokhlesi et al.
7,851,851 B2 12/2010 Mokhlesi et al.
8,008,710 B2 8/2011 Fukuzumi
8,053,829 B2 11/2011 Kang et al.
8,258,033 B2 * 9/2012 Watanabe H01L 27/11582
257/E21.423
8,278,170 B2 * 10/2012 Lee H01L 27/11551
257/E21.645
8,394,716 B2 * 3/2013 Hwang H01L 27/11551
257/315
8,445,347 B2 5/2013 Alsmeier
8,786,003 B2 * 7/2014 Iwase H01L 27/0738
257/316
8,791,523 B2 * 7/2014 Iino H01L 27/1157
257/324
- 2007/0210338 A1 9/2007 Orłowski
2007/0252201 A1 11/2007 Kito et al.
2009/0242967 A1 * 10/2009 Katsumata H01L 21/764
257/324
- 2010/0044778 A1 2/2010 Seol
2010/0112769 A1 5/2010 Son et al.
2010/0120214 A1 5/2010 Park et al.
2010/0148237 A1 * 6/2010 Kito H01L 27/11551
257/315
- 2010/0155810 A1 6/2010 Kim et al.
2010/0155818 A1 6/2010 Cho
2010/0181610 A1 7/2010 Kim et al.
2010/0207195 A1 8/2010 Fukuzumi et al.
2010/0320528 A1 12/2010 Jeong et al.
2011/0076819 A1 3/2011 Kim et al.
2011/0133606 A1 6/2011 Yoshida et al.
2011/0216597 A1 * 9/2011 Higashi G11C 16/04
365/185.18

- 2011/0266606 A1 11/2011 Park et al.
2011/0272755 A1 11/2011 Endo et al.
2012/0001247 A1 1/2012 Alsmeier
2012/0001249 A1 1/2012 Alsmeier
2012/0001250 A1 1/2012 Alsmeier
2012/0001252 A1 1/2012 Alsmeier et al.
2012/0012920 A1 1/2012 Shin et al.
2012/0052674 A1 * 3/2012 Lee H01L 27/11578
438/591
2012/0092926 A1 * 4/2012 Whang H01L 27/11556
365/185.01
2012/0146122 A1 * 6/2012 Whang H01L 29/7889
257/315
2012/0184097 A1 * 7/2012 Chen H01L 27/11286
438/618
2012/0267699 A1 * 10/2012 Kiyotoshi H01L 27/11524
257/319
2012/0280303 A1 * 11/2012 Kiyotoshi H01L 27/11524
257/316
2013/0056816 A1 * 3/2013 Iwase H01L 27/0738
257/316
2013/0083597 A1 4/2013 Nakamura et al.
2013/0130495 A1 5/2013 Higashitani et al.
2013/0264631 A1 10/2013 Alsmeier et al.

OTHER PUBLICATIONS

Katsumata et al., "Pipe-Shaped BiCS Flash Memory with 16 Stacked Layers and Multi-Level-Cell Operation for Ultra High Density Storage Devices," 2009 Symposium on VLSI Technology Digest of Technical Papers, pp. 136-137.
Maeda et al., "Multi-Stacked 1G Cell/Layer Pipe-Shaped BiCS Flash Memory," 2009 Symposium on VLSI Technology Digest of Technical Papers, pp. 22-23.
Endoh et al., "Novel Ultra High Density Memory with a Stacked-Surrounding Gate Transistor (S-SGT) Structured Cell," IEDM Proc. (2001) 33-36.
Tanaka et al., "Bit-Cost Scalable Technology for Low-Cost and Ultrahigh-Density Flash Memory," Toshiba Review, vol. 63, No. 2, 2008, pp. 28-31.
Masahide Kimura, "3D Cells Make Terabit NAND Flash Possible," Nikkei Electronics Asia, Sep. 17, 2009, 6pgs.
International Search Report & Written Opinion, PCT/US2011/042566, Jan. 17, 2012.
Invitation to Pay Additional Fees & Partial International Search Report, PCT/US2011/042566, Sep. 28, 2011.
International Search Report and Written Opinion, International Application No. PCT/US2013/035567, issued Sep. 30, 2013, 6pgs.
International Preliminary Report on Patentability received in connection with international application No. PCT/US2013/035567; mailed Oct. 23, 2014.
Chinese First Office Action for Patent Application No. 2013800150093, dated Apr. 15, 2016, 14 pages.

* cited by examiner




Fig. 1A




Fig. 1B




Fig. 1C




Fig. 1D




Fig. 1E




Fig. 1F




Fig. 2

Fig. 3A




Fig. 3B





Fig. 4

1

VERTICAL NAND DEVICE WITH LOW CAPACITANCE AND SILICIDED WORD LINES

RELATED APPLICATIONS

The instant application is a continuation application of U.S. application Ser. No. 13/443,287 filed on Apr. 12, 2012 and subsequently issued as U.S. Pat. No. 8,847,302 on Sep. 30, 2014.

FIELD

The present invention relates generally to the field of semiconductor devices and specifically to three dimensional vertical NAND strings and other three dimensional devices and methods of making thereof.

BACKGROUND

Three dimensional vertical NAND strings are disclosed in an article by T. Endoh, et. al., titled "Novel Ultra High Density Memory With A Stacked-Surrounding Gate Transistor (S-SGT) Structured Cell", IEDM Proc. (2001) 33-36. However, this NAND string provides only one bit per cell. Furthermore, the active regions of the NAND string is formed by a relatively difficult and time consuming process involving repeated formation of sidewall spacers and etching of a portion of the substrate, which results in a roughly conical active region shape.

SUMMARY

An embodiment relates to a three dimensional memory device including a substrate and a semiconductor channel. At least one end portion of the semiconductor channel extends substantially perpendicular to a major surface of the substrate. The device also includes at least one charge storage region located adjacent to semiconductor channel and a plurality of control gate electrodes having a strip shape extending substantially parallel to the major surface of the substrate. The plurality of control gate electrodes include at least a first control gate electrode located in a first device level and a second control gate electrode located in a second device level located over the major surface of the substrate and below the first device level. Each of the plurality of control gate electrodes includes a first edge surface which is substantially free of silicide, the first edge surface facing the semiconductor channel and the at least one charge storage region and a silicide located on remaining surfaces of the control gate electrode.

Another embodiment relates to a method of making a three dimensional memory device. The method includes providing a plurality of columns extending substantially perpendicular to a major surface of the substrate in which each column includes a core with a semiconductor channel, a first shell with a tunnel dielectric, a second shell with a charge storage material and a third shell with a blocking dielectric. Each column is surrounded by a stack of alternating layers of a first material and a second material over the major surface of the substrate. The first material includes a Group IV semiconductor control gate material. The second material includes a sacrificial material and the stack comprises at least one trench separating a first column from a second column. The method also includes removing the layers of sacrificial material to form air gaps between the layers of semiconductor control gate material and forming a

2

silicide on surfaces of the layers of semiconductor control gate material exposed by removal of the sacrificial material.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is a schematic side cross sectional view illustrating a step in a method of making a three dimensional memory device according to an embodiment.

FIG. 1B is a schematic side cross sectional view illustrating another step in the method of making a three dimensional memory device according to an embodiment.

FIG. 1C is a schematic side cross sectional view illustrating another step in the method of making a three dimensional memory device according to an embodiment.

FIG. 1D is a schematic side cross sectional view illustrating another step in the method of making a three dimensional memory device according to an embodiment.

FIG. 1E is a schematic side cross sectional view illustrating another step in the method of making a three dimensional memory device according to an embodiment.

FIG. 1F is a schematic side cross sectional view illustrating another step in the method of making a three dimensional memory device according to an embodiment.

FIG. 2 is a plan view a memory device according to an embodiment. Also illustrated is a support mask layout used in the method of FIG. 1.

FIG. 3A is a side cross sectional view of a vertical NAND string according to an embodiment.

FIG. 3B is a side cross section of another vertical NAND string according to another embodiment.

FIG. 4 is a plan view of a memory device according to an embodiment.

DETAILED DESCRIPTION

Embodiments include monolithic three dimensional NAND strings and methods of making three dimensional NAND strings. In an embodiment, the NAND string may be formed with a single vertical channel. In one aspect, the vertical channel has a solid, rod shape. In this aspect, the entire channel comprises a semiconductor material. In another aspect, the vertical channel has a hollow cylinder shape. In this aspect, the vertical channel includes a non-semiconductor core surrounded by a semiconductor channel shell. The core may be unfilled or filled with an insulating material, such as silicon oxide or silicon nitride. Alternatively, the NAND string may have a U shape (also known as a "pipe" shape) with two vertical channel wing portions connected with a horizontal channel connecting the wing portions. In one aspect, the U shaped or pipe shaped channel may be solid, as in the solid rod shaped vertical channel NAND. In another aspect, the U shaped or pipe shaped channel may be hollow cylinder shaped, as in the hollow cylinder pipe shaped vertical channel NAND. The U-shaped pipe channel may be filled or unfilled. Separate front side and back side methods for fabricating both single vertical channel and U shaped channel NAND strings are taught in co-pending U.S. patent application Ser. No. 12/827,947, hereby incorporated by reference in its entirety for teaching of the separate front and back side processing methods. Combination front side and back side methods for fabricating both single vertical channel and U shaped channel NAND strings are taught in co-pending U.S. patent application Ser. No. 13/083,775, hereby incorporated by reference in its entirety for teaching combination front side and back side processing methods.

Vertical channel, Bit Cost Scalable (BiCS) NAND memory and U-shaped (i.e., “pipe-shaped”) BiCS (p-BiCS) were developed for ultra high density storage devices. However, earlier BiCS and p-BiCS 3D NAND architectures suffer from relatively high control gate/word line resistances and capacitances. These resistances and capacitances reduce cell efficiency and increase the power consumption of the memory device.

The inventors have discovered that modification of the BiCS and p-BiCS processes allows improved silicidation of the control gates/word lines. The silicidation of the control gates/word lines lowers the resistance of the control gates/word lines, resulting in a decrease in device power consumption and providing an increase in cell efficiency. Additional modification of the BiCS and p-BiCS processes to include air gaps between control gates/word lines in adjacent device levels (i.e., air gaps between vertically separated control gates) lowers the capacitance between the control gates/word lines. This also results in a decrease in device power consumption and increases the cell efficiency.

As used herein, the term “control gate” and “word line” refer to the same electrically conductive entity. A control gate may be considered a portion of a word line located adjacent to and controlling one NAND cell in an array of NAND cells. A word line controls plural NAND cells in the array. Thus, the word line may be considered to be a portion of the electrically conductive entity which connects the control gates. However, it should be understood that the word line and its control gate portions may be formed during the same step and may comprise the same one or more electrically conductive layers as will be described below.

FIGS. 1A-1F illustrate a method of making a three dimensional memory device (e.g., vertical NAND string) according to an embodiment of the invention. In this embodiment, a substrate **100** is provided with a stack of alternating layers of a first material layer **102** and a second material layer **104** formed over the major surface **100a** of the substrate **100**.

The substrate **100** can be any semiconducting substrate known in the art, such as monocrystalline silicon, IV-IV compounds such as silicon-germanium or silicon-germanium-carbon, III-V compounds, II-VI compounds, epitaxial layers over such substrates, or any other semiconducting or non-semiconducting material, such as silicon oxide, glass, plastic, metal or ceramic substrate. The substrate **100** may include integrated circuits fabricated thereon, such as driver circuits for a memory device.

Layers **102** and **104** may be deposited over the substrate **100** by any suitable deposition method, such as sputtering, CVD, PECVD, MBE, etc. Preferably, the first material layer **102** is suitable for use as a control gate. Suitable materials include, but are not limited to, heavily doped Group IV semiconductors, such as silicon (e.g., polysilicon), silicon germanium, silicon carbide, etc. The semiconductor may be p-type or n-type doped and have a doping concentration between 10^{17} cm^{-3} and 10^{21} cm^{-3} .

The second material layer **104** includes a sacrificial material. Any sacrificial material that may be selectively etched compared to the first material may be used. For example, if the first material layer **102** is p-doped polysilicon, the sacrificial materials **104** may be intrinsic polysilicon (i.e., doping below 10^{16} cm^{-3}). Alternatively, the second material layer **104** may comprise a metal or an insulating material (e.g., silicon oxide, silicon nitride, etc.) that may be selectively etched with respect to the first material layer **102**. The stack may be covered with a top layer of insulating material **106**, such as silicon oxide or silicon nitride.

After deposition of the layers **102** and **104**, the stack may be etched to form memory holes **108** and slit trenches **110**. The slit trenches **110** may be filled with a sacrificial material **110A**, such as silicon nitride or another material which can be selectively etched compared to materials of layer **102** and **104**, while the memory cells are formed in the memory holes **108**. For example, the slit trenches **110** may be formed first using lithography and etching, then the trenches **110** may be filled with the sacrificial material **110A**, followed by formation of the memory holes **108** using another lithography and etching step.

In an embodiment, the memory cells **150** (e.g., vertical NAND strings) may be formed with a series of conformal deposition steps of the memory film and channel column portions **151** of the memory cells **150** in the memory holes **108**, as shown in FIG. 1B. Conformal deposition techniques include, but are not limited to, atomic layer deposition (ALD) and chemical vapor deposition (CVD).

For example, as shown in FIG. 2, a layer of blocking dielectric **112** may first be conformally deposited in the memory holes **108**. Next, a layer of charge storage material **114** may be conformally deposited on the layer of blocking dielectric **112** in the memory holes **108**. A layer of tunnel dielectric **116** may then be conformally deposited on the charge storage material **114** in the memory holes **108**. The central portion of the memory hole **108** may then be filled with a semiconductor channel material **118**, such as polysilicon.

The channel **118** material may comprise lightly doped p-type or n-type (i.e., doping below 10^{17} cm^{-3}) semiconductor material (e.g., polysilicon). An n-channel device is preferred since it is easily connected with n+ junctions (i.e., source and drain n+ doped regions having a doping concentration between 10^{17} cm^{-3} and 10^{21} cm^{-3} located at the opposite ends of each channel). However, a p-channel device may also be used. Other semiconductor materials (e.g., SiGe, SiC, Ge, III-V, II-VI, etc.) may also be used.

The blocking dielectric **112** may comprise a silicon oxide layer deposited by conformal atomic layer deposition (ALD) or chemical vapor deposition (CVD). Other high-k dielectric materials, such as hafnium oxide, may be used instead or in addition to silicon oxide. Dielectric **112** may have a thickness of 6 to 20 nm. The charge storage region **114** may comprise a silicon nitride layer deposited by any suitable method, such as ALD, CVD, etc., and have a thickness of 2 to 20 nm. The tunnel dielectric **116** may comprise a relatively thin insulating layer (e.g., 4 to 10 nm thick) of silicon oxide or other suitable material, such as oxynitride, oxide and nitride multi layer stacks, or a high-k dielectric (e.g., hafnium oxide), deposited by any suitable method, such as ALD, CVD.

The result of the conformal depositions is formation of memory cell **150** columns **151** substantially perpendicular to the major surface of the substrate. Each memory cell column **151** includes a semiconductor channel core **118**, a first shell of tunnel dielectric **116**, a second shell of charge storage material **114** and a third shell of blocking dielectric **112**. The blocking dielectric layer, the charge storage material (i.e., the charge trapping layer), and a tunnel dielectric layer extend substantially perpendicular to the major surface **110A** of the substrate **100** between the semiconductor channel **118** and the plurality of control gate electrodes **102**.

In an embodiment, a surface **102D** of the control gate layer **102** directly, physically contacts the blocking dielectric layer **112**, as shown in FIGS. 1F and 2.

In an alternative embodiment, the semiconductor channel core **118** may include an inner core of insulating material

5

surrounded by a shell of semiconductor material. In an alternative configuration, the charge storage material **114** may be formed of a multilayer composite, such as an oxide-nitride-oxide (ONO) multilayer, and/or the blocking dielectric **112** may comprise a tri-layer ONO dielectric, such that the memory film comprises ONO (**112**)-N (**114**)-O (**116**).

As illustrated in FIG. 1C, the top layer of insulating material **106** may then be etched to expose openings **122** in a top layer of semiconducting material **124** to form upper select gates **123**. In an embodiment, the memory cells **150** are configured with vertical pillar channels **118** and the upper select gates **123** are drain select gates. In this configuration, source select gates **125** are formed at the opposite (substrate) end of the vertical channel, as shown in FIG. 3A. Alternatively, the memory cells **150** are configured with U shaped channels **118** and the select gates include respective drain select gates and source select gates **123**, **125** at the upper end of each respective wing portion **118A** of the U shaped channel **118**, as shown in FIG. 3B. The wing portions **118A** are connected by the horizontal channel **118B** located in or on the substrate **100**.

In an embodiment, a support mask **126** may be deposited over the top layer of insulating material **106** after the openings **122** are formed. The support mask **126** provides support to the memory device after the layers of sacrificial materials **110A** and **104** are removed. The support mask **126** may be made of any suitable material, such as an oxide or nitride hard mask material. As shown in FIG. 2, the mask **126** may be a mesh shaped mask which includes clear or open gap portions **126A** surrounded by dark or solid cross bar mesh support portions **126B**.

In the next step, as illustrated in FIG. 1E, the sacrificial material **110A** in the slit trenches **110** may be removed. This removal may be accomplished by selectively etching (e.g., wet etching) the sacrificial material **110A** in the trenches **110** through the gaps **126A** in the mask **126** without etching the other materials or layers in the device. Removing the material **110A** in the trenches **110** exposes the side edges of layers of sacrificial material **104** in the stack.

The layers of sacrificial material **104** may then be removed by selective etching (e.g., wet etching) through the slit trenches **110**, as illustrated in FIG. 1F. This results in terraces of exposed control gate **102** material which are supported by the memory cell columns **151**. The support mask **126** provides additional support to the memory cell columns **151**. The control gates **102** are separated in the vertical direction by the air gaps **104A** where the sacrificial material layers **104** were previously located and in the horizontal direction by the slit trenches **110**.

After formation of the air gaps **104A**, the exposed surfaces of the control gates **102** are silicided to form a silicide layer **128** on the exposed surfaces of the polysilicon control gates **102**. The silicide layer **128** may be formed by conformally depositing a thin layer of metal, such as tungsten, cobalt, nickel or titanium, or a combination of two more of these metals, on the exposed control gate polysilicon material and heating the device to react the thin layer of metal with the control gate material. The metal layer may be formed through the gaps **126A** in the mask **126** and through the trenches **110** and air gaps **104A**. The silicide layer **128** is formed on the upper **102A** and lower **102B** surfaces of the exposed control gates **102** as well as on the exposed face **102C** of the control gate **102** opposite the face **102D** that contacts the charge storage region **112** of the memory device **150**. The upper and lower surfaces **102A**, **102B** of the control gates **102** are positioned substantially parallel to the

6

major surface **100A** of the substrate **100**, while edge surfaces or faces **102C**, **102D** of the control gate **102** are positioned substantially perpendicular to the major surface **100A** of the substrate **100**. The silicide layer **128** is also formed on the side wall of the select gates **123**, **125** exposed in the trenches **122**.

In the completed device, the each memory cell includes a source electrode **130** and a drain electrode **132**. Methods of making the source electrode **130** and a drain electrode **132** are described in co-pending U.S. patent application Ser. Nos. 12/827,947 and 13/083,775, hereby incorporated by reference. In a pillar channel configuration shown in FIG. 3A, the drain electrode **130** may be formed at that top of the vertical memory column **151** and the source electrode **132** may be formed in the substrate **100**. In a U-shaped channel configuration shown in FIG. 3B, both the source and drain electrodes **132**, **130** may be formed contacting the source and drain regions at the top of the wings **118A** of the vertical memory column(s) **151**.

As illustrated in FIGS. 2 and 4, the control gates **102** in adjacent memory cells **150** in a device level may be connected to each other in a strip **134**. The strips **134** connected to a given word line may be combed shaped and strips connected to adjacent word lines may be interdigitated as shown in FIG. 2. As noted above, the strips **134** and individual control gates **102** may be considered portions of the word line rather than discreet elements.

In the embodiment illustrated in FIG. 2, the control gate strips **134** surround a single row of memory cell **150** pillars **151**. Alternatively, as illustrated in FIG. 4, each control gate **102** strip **134** may surround two rows of pillars **151** (i.e., wings **118A**) of adjacent NAND strings (i.e., memory cells) **150**.

In the U-shaped channel configuration of FIG. 3B, the horizontal channel portion **118B** of the U-shaped channel **118** connects adjacent channel wing portions **118A** under the slit trenches **110**, as shown in FIGS. 3B and 4. Thus, the horizontal portion **118B** of the U-shaped channel **118** extends substantially perpendicular to the elongation direction of the strips **134** of control gates **102**. The drain select gates **123** of adjacent memory cells may be connected to each other via a source line while the source select gates **125** of adjacent memory cells may be connected to each other via a bit line (not shown). While the U-shaped NAND strings **150** are illustrated with the control gate strip **134** surrounding two rows of pillars **151** configuration of FIG. 4, it should be understood that the U-shaped NAND strings **150** may also be used with the control gate strip **134** surrounding one row of pillars **151** configuration of FIG. 2.

FIG. 4 illustrates three control gate strips **134A**, **134B** and **134C** located in the same device level. Control gate strip **134B** is located between strips **134A** and **134C**. Control gate strips **134A** and **134C** are electrically connected to the same word line WL, while control gate strip **134B** is electrically connected to a different word line (not shown), such that strip **134B** is interdigitated between strips **134A** and **134C** in the same device level. The strips **134A**, **134B** and **134C** are separated from each other by air gap trenches **110**. A first wing portion **118A** of the semiconductor channel **118** of the NAND string **150** (shown by dashed lines) extends through and is surrounded by strip **134C** (as well as other strips located above and below strip **134C**, such as strip **134D** shown in FIG. 1F). The second wing portion **118A** of the semiconductor channel **118** extends through and is surrounded by strip **134B** (as well as other strips located above and below strip **134B**, such as strip **134E** shown in FIG. 1F). The connecting portion **118B** (shown in dashed lines) of the

7

semiconductor channel **118** is located below the air gap trench **110** which separates the strips.

Although the foregoing refers to particular preferred embodiments, it will be understood that the invention is not so limited. It will occur to those of ordinary skill in the art that various modifications may be made to the disclosed embodiments and that such modifications are intended to be within the scope of the invention. All of the publications, patent applications and patents cited herein are incorporated herein by reference in their entirety.

What is claimed is:

1. A completed three dimensional memory device, comprising:

a substrate;

a semiconductor channel, at least one end portion of the semiconductor channel extending substantially perpendicular to a major surface of the substrate;

at least one charge storage region located adjacent to semiconductor channel; and

a plurality of control gate electrodes having a strip shape extending substantially parallel to the major surface of the substrate, wherein the plurality of control gate electrodes comprise at least a first control gate electrode located in a first device level and a second control gate electrode located in a second device level located over the major surface of the substrate and below the first device level;

wherein each of the plurality of control gate electrodes comprises:

a semiconductor material portion consisting essentially of a p-doped or n-doped Group IV semiconductor material; and

a metal silicide portion composed of a metal silicide of the Group IV semiconductor material and at least one metal,

wherein surfaces of the semiconductor material portion are in contact with the metal silicide portion and the at least one charge storage region,

wherein each vertically neighboring pair of control gate electrodes is spaced by a respective air gap that extends parallel to the major surface of the substrate and is in physical contact with substantially horizontal surfaces of an overlying metal silicide portion and an underlying metal silicide portion

wherein a vertically extending volume extending through the plurality of control gate electrodes is adjoined to the air gaps which comprise a plurality of laterally extending volumes located between each vertically neighboring pair of control gate electrodes to provide a contiguous air gap comprising a single undivided space.

2. The device of claim **1**, wherein:

a first edge surface of each of the plurality of control gate electrodes comprises an edge surface of the semiconductor material portion which contacts the at least one charge storage region;

a second edge surface, a top surface, and a bottom surface of each of the plurality of control gate electrodes are not in contact with the at least one charge storage region; and

the first edge surface and the second edge surface of the plurality of control gate electrodes are positioned substantially perpendicular to the major surface of the substrate.

3. The device of claim **1**, wherein:

the semiconductor channel has a pillar shape having a solid or hollow circular cross section when viewed from above; and

8

the entire pillar-shaped semiconductor channel and the entire at least one charge storage region extend substantially perpendicular to the major surface of the substrate.

4. The device of claim **1**, wherein:

the device comprises a vertical NAND device is located over the substrate;

the electrically conductive layers comprise, or are electrically connected to a respective word line of the vertical NAND device;

the substrate comprises a silicon substrate;

the vertical NAND device comprises an array of monolithic three dimensional NAND strings over the silicon substrate;

at least one memory cell in the first device level of the three dimensional array of NAND strings is located over another memory cell in the second device level of the three dimensional array of NAND strings; and

the silicon substrate contains an integrated circuit comprising a driver circuit for the memory device located thereon.

5. The device of claim **1**, wherein the contiguous air gap extends to a region located above a horizontal plane including a topmost surface of the plurality of control gate electrodes.

6. The device of claim **1**, further comprising a support mask located above the plurality of control gate electrodes, wherein a top surface of the contiguous air gap is a bottom surface of the support mask.

7. The device of claim **6**, wherein the support mask is patterned layer including at least one opening therein.

8. A three dimensional memory device, comprising:

a substrate;

a semiconductor channel, at least one end portion of the semiconductor channel extending substantially perpendicular to a major surface of the substrate;

at least one charge storage region located adjacent to semiconductor channel; and

a plurality of control gate electrodes having a strip shape extending substantially parallel to the major surface of the substrate, wherein the plurality of control gate electrodes comprise at least a first control gate electrode located in a first device level and a second control gate electrode located in a second device level located over the major surface of the substrate and below the first device level;

wherein each of the plurality of control gate electrodes comprises:

a semiconductor material portion composed of a Group IV semiconductor material; and

a metal silicide portion composed of a metal silicide of the Group IV semiconductor material and at least one metal, wherein surfaces of the semiconductor material portion are in contact with the metal silicide portion and the at least one charge storage region,

wherein each vertically neighboring pair of control gate electrodes is spaced by a respective air gap that extends parallel to the major surface of the substrate, and

wherein a vertically extending volume extending through the plurality of control gate electrodes is adjoined to the air gaps to provide a contiguous air gap;

further comprising a support mask located above the plurality of control gate electrodes, wherein a top surface of the contiguous air gap is a bottom surface of the support mask, wherein the support mask is patterned layer including at least one opening therein; and

9

further comprising a plurality of memory cells embedded within the plurality of control gate electrodes, wherein: a first subset of the plurality of memory cells is located underneath a portion of the support mask; and a second subset of the plurality of memory cells is located underneath the at least one opening in the support mask.

9. The device of claim 8, wherein the contiguous air gap vertically extends up to a horizontal plane including a topmost surface the plurality of memory cells.

10. A three dimensional memory device, comprising:

a substrate;

a semiconductor channel, at least one end portion of the semiconductor channel extending substantially perpendicular to a major surface of the substrate;

at least one charge storage region located adjacent to semiconductor channel; and

a plurality of control gate electrodes having a strip share extending substantially parallel to the major surface of the substrate, wherein the plurality of control gate electrodes comprise at least a first control gate electrode located in a first device level and a second control gate electrode located in a second device level located over the major surface of the substrate and below the first device level;

wherein each of the plurality of control gate electrodes comprises:

a semiconductor material portion composed of a Group IV semiconductor material; and

a metal silicide portion composed of a metal silicide of the Group IV semiconductor material and at least one metal, wherein surfaces of the semiconductor material portion are in contact with the metal silicide portion and the at least one charge storage region,

wherein each vertically neighboring pair of control gate electrodes is spaced by a respective air gap that extends parallel to the major surface of the substrate, and

10

wherein a vertically extending volume extending through the plurality of control gate electrodes is adjoined to the air gaps to provide a contiguous air gap;

further comprising a support mask located above the plurality of control gate electrodes, wherein a top surface of the contiguous air gap is a bottom surface of the support mask, wherein the support mask is patterned layer including at least one opening therein; and wherein:

the contiguous air gap is located within a slit trench extending through the plurality of control gate electrodes; and

the at least one opening overlies a region of the slit trench and does not overlie another region of the slit trench.

11. The device of claim 1, wherein sidewalls of the plurality of control gate electrodes are physically exposed to the vertically extending volume.

12. The device of claim 1, further comprising additional air gaps located at a level of an upper select gate that is located above the plurality of control gate electrodes, wherein the additional air gaps are located above a topmost control gate electrode among the plurality of control gate electrodes.

13. The device of claim 12, wherein a portion of the vertically extending volume and the additional air gaps are vertically bounded from above by bottom surfaces of a same support mask.

14. The device of claim 1, further comprising a support mask located above the plurality of control gate electrodes, wherein an upper end portion of the vertically extending volume is bounded by the support mask between a first pair of memory cell columns, and another upper end portion of the vertically extending volume extends through the support mask between a second pair of memory cell columns.

* * * * *