



US009486978B2

(12) **United States Patent**
Chapman et al.

(10) **Patent No.:** **US 9,486,978 B2**
(45) **Date of Patent:** **Nov. 8, 2016**

(54) **SYSTEMS AND METHODS FOR KERFING VENEERS**

26/4045 (2013.01); *B32B 21/042* (2013.01);
B32B 21/13 (2013.01); *B32B 21/14* (2013.01);
B29K 2001/00 (2013.01); *B29L 2009/00*
(2013.01); *B32B 2317/16* (2013.01)

(71) Applicant: **GOODRICH CORPORATION**,
Charlotte, NC (US)

(58) **Field of Classification Search**

(72) Inventors: **Christopher L. Chapman**, Lanesville,
IN (US); **Sayan Rakshit**, Bangalore
(IN); **Tommy R. Hawkins**, Scottsburh,
IN (US); **Satya Swaroop Panda**,
Bangalore (IN)

CPC *B32B 3/263*; *B32B 21/13*; *B32B 21/14*;
B32B 21/042; *B32B 2317/16*; *B32B 1/00*;
B32B 3/30; *B32B 3/28*; *B23K 26/0626*;
B23K 26/00
USPC 428/134, 136, 156, 167, 172, 537.1
See application file for complete search history.

(73) Assignee: **GOODRICH CORPORATION**,
Charlotte, NC (US)

(56) **References Cited**

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 196 days.

U.S. PATENT DOCUMENTS

5,540,025 A * 7/1996 Takehara et al. *B32B 3/30*
428/136

(21) Appl. No.: **14/316,330**

OTHER PUBLICATIONS

(22) Filed: **Jun. 26, 2014**

Office Actions dated Oct. 6, 2015 in French Application No. 15
55888.

(65) **Prior Publication Data**

US 2015/0375343 A1 Dec. 31, 2015

* cited by examiner

(51) **Int. Cl.**

Primary Examiner — Catherine A Simone

B32B 3/26 (2006.01)
B32B 21/14 (2006.01)
B23K 26/40 (2014.01)
B32B 21/04 (2006.01)
B32B 21/13 (2006.01)
B23K 26/36 (2014.01)
B23K 26/06 (2014.01)
B29K 1/00 (2006.01)
B29L 9/00 (2006.01)

(74) *Attorney, Agent, or Firm* — Snell & Wilmer, L.L.P.


(52) **U.S. Cl.**

CPC *B32B 3/263* (2013.01); *B23K 26/0626*
(2013.01); *B23K 26/367* (2013.01); *B23K*

(57) **ABSTRACT**

Systems and methods are disclosed herein for laser kerfed
veneers. A laser may be used to produce kerf lines in thin
veneers. The settings of the laser may be adjusted to adjust
the width and depth of the kerf lines. The width and depth
of the kerf lines may be selected in order to provide
sufficient strength to the veneer while decreasing telegraph-
ing.

6 Claims, 5 Drawing Sheets






FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 3




FIG. 4

1**SYSTEMS AND METHODS FOR KERFING
VENEERS**

FIELD

The present disclosure relates generally to woodworking. More particularly, the present disclosure relates to kerfing veneers.

BACKGROUND

Many applications for wood products call for the wood to be bent or curved. Several methods for bending wood are well known in the art. Wood may be steamed at high temperatures until pliable, and the wood may be bent into a desired shape. The wood may harden in the bent shape as the heat and moisture from the steaming decreases. However, steaming the wood is labor intensive and time consuming. A second method may involve introducing chemicals to plasticize the wood. However, the chemicals can lead to discoloration of the wood and other long-term issues.

A third method for bending wood involves kerfing. During a kerfing process, a saw may make parallel linear partial-thickness cuts in a wood component. The wood may be bent around the kerf lines. However, the tolerance of mechanical kerfing methods may limit the ability of kerfing on thin wood products.

SUMMARY

A method of kerfing a veneer is disclosed. The method may include optimizing settings of a laser to produce a first kerf line having a first depth corresponding to a thickness of a backing ply in the veneer. The method may further include kerfing the first kerf line into the veneer with the laser,

In various embodiments, the method may comprise defocusing the laser. The kerfing may comprise moving the laser across the veneer at a first power. A second kerf line may be kerfed in the veneer at a second power. The second power may be greater than the first power, and a depth of the second kerf line may be greater than the depth of the first kerf line. The veneer may have a thickness of less than 0.015 inches (0.038 cm). The laser may comprise a CO₂ laser in cut mode. The method may comprise kerfing a second kerf line, wherein a separation between the first kerf line and the second kerf line is between 0.003 inches-0.005 inches (0.008 cm-0.013 cm).

A veneer is disclosed. The veneer may comprise a face veneer and a backing coupled to the face veneer. The backing may comprise a first kerf line in the backing. A thickness of the veneer may be less than 0.015 inches (0.033 cm).

In various embodiments, the first kerf line may be formed by a laser. A depth of the first kerf line may be equal to a thickness of a ply of the backing. The backing may comprise a second kerf line, and a depth of the second kerf line may be greater than a depth of the first kerf line. The backing may comprise a second kerf line, and a separation between the first kerf line and the second kerf line may be between 0.003 inches-0.005 inches (0.008 cm-0.013 cm). The veneer may comprise a curve with a radius of less than 2 inches (5.1 cm). The first kerf line may be undetectable in the face veneer.

The foregoing features and elements may be combined in various combinations without exclusivity, unless expressly indicated otherwise. These features and elements as well as the operation thereof will become more apparent in light of the following description and the accompanying drawings. It

2

should be understood, however, the following description and drawings are intended to be exemplary in nature and non-limiting.

BRIEF DESCRIPTION OF THE DRAWINGS

The subject matter of the present disclosure is particularly pointed out and distinctly claimed in the concluding portion of the specification. A more complete understanding of the present disclosure, however, may best be obtained by referring to the detailed description and claims when considered in connection with the drawing figures.

FIG. 1 illustrates a kerfed veneer, in accordance with various embodiments;

FIGS. 2A-2D illustrates cross-sections of various kerf patterns in veneers, in accordance with various embodiments;

FIG. 3 illustrates a veneer having a multi-directional kerf pattern, in accordance with various embodiments; and

FIG. 4 illustrates a flow chart of a process for kerfing a veneer, in accordance with various embodiments.

DETAILED DESCRIPTION

The detailed description of various embodiments herein makes reference to the accompanying drawings, which show various embodiments by way of illustration. While these various embodiments are described in sufficient detail to enable those skilled in the art to practice the disclosure, it should be understood that other embodiments may be realized and that logical, chemical, and mechanical changes may be made without departing from the spirit and scope of the disclosure. Thus, the detailed description herein is presented for purposes of illustration only and not of limitation. For example, the steps recited in any of the method or process descriptions may be executed in any order and are not necessarily limited to the order presented. Furthermore, any reference to singular includes plural embodiments, and any reference to more than one component or step may include a singular embodiment or step. Also, any reference to attached, fixed, connected, or the like may include permanent, removable, temporary, partial, full, and/or any other possible attachment option. Additionally, any reference to without contact (or similar phrases) may also include reduced contact or minimal contact.

Systems and methods are disclosed herein for laser kerfing a wood veneer. A laser may be used to cut kerf lines in the backing of a veneer. The speed, power, and focus of the laser may be adjusted to change the width and depth of the kerf lines. The kerf lines may have varying widths or depths for a single veneer. The veneer may be bent into a curved shape around the kerf lines.

Referring to FIG. 1, a veneer **100** is illustrated according to various embodiments. Veneer **100** may comprise a face veneer **110** and a backing **120**. Face veneer **110** may be a thin slice of decorative wood which is visible in an end-user product. Face veneer **110** may be located at an outer radius of a curved portion of veneer **100**. Face veneer **110** may be coupled to backing **120**. Backing **120** may comprise any type of material used in conjunction with veneers. For example, backing **120** may comprise wood plies, paper, phenolic, or other types of backing materials. In various embodiments, backing **120** may comprise 2 plies of material. However, in various embodiments, backing **120** may comprise any number of plies.

Veneer **100** may comprise kerf lines **130**. Kerf lines **130** may be cut into backing **120**. In various embodiments, kerf

lines **130** may be cut into veneer **100** using a laser. In various embodiments, kerf lines **130** may extend into face veneer **110**. Stated another way, the depth of kerf lines **130** may extend into face veneer **110**. Kerf lines **130** may allow veneer **100** to bend more easily. Material is removed from veneer **100** by kerf lines **130**. Thus, veneer **100** may be bent without compressing, or with less compression of, backing **120**, as well, as less stretching of face veneer **110**.

Referring to FIGS. **2A-2D**, cross-sections of different kerf patterns for a veneer **200** are illustrated according to various embodiments. A kerf pattern may refer to a series of kerf lines. In various embodiments, the kerf pattern may comprise a plurality of straight parallel kerf lines. However, in various embodiments, the kerf lines may be curved, such as sinusoidal or circular. In each sample shown in FIGS. **2A-2D**, the veneer **200** comprises a face veneer **210**, a first backing ply **221** coupled to the face veneer **210**, and a second backing ply **222** coupled to the first backing ply **221**. The face veneer **210**, first backing ply **221**, and second backing ply **222** each have a thickness **T1** of 0.004 inches (0.010 cm), and the veneer **200** had a total thickness **T2** of 0.012 inches (0.030 cm). The depth and pattern of kerfing are controlled to limit the likelihood of telegraphing or cracking of face veneer **210**. Telegraphing refers to impressions that may appear on the veneer face which may correspond to the kerf lines. The telegraphing may be a result of stretching of the face veneer in localized areas during bending of the veneer.

In FIG. **2A**, kerfs **230** were cut into the backing at a depth **D1** of 1 ply, such that depth **D1** is equal to thickness **T1**. The kerfs **230** have a width **W** of 1 ply, and a separation **S** between kerfs was 1 ply. In FIG. **2B**, kerfs **231** were cut into the backing at a depth **D2** of 1.5 plies, such that depth **D2** is equal to 1.5 times **T1**. The kerfs **231** have a width **W** of 1 ply, and a separation **S** between kerfs **231** was 1 ply.

In FIG. **2C**, kerfs **232** were cut in groups of four. The kerfs **232** were cut into the backing at a depth **D2** of 1.5 plies. The kerfs **232** have a width **W** of 1 ply, and a separation **S** between kerfs **232** within a group was 1 ply. A separation **G** between groups was 3.5 plies.

In FIG. **2D**, kerfs **233**, **234**, **235**, **236** were cut in groups of four at varying depths. Each group comprised a first kerf **233** at a depth **D3** of 0.5 plies, a second kerf **234** at a depth **D1** of 1 ply, a third kerf **235** at a depth **D2** of 1.5 plies, and a fourth kerf **236** at a depth **D1** of 1 ply. The kerfs **233**, **234**, **235**, **236** have a width of 1 ply, and a separation between kerfs **233**, **234**, **235**, **236** within a group was 1 ply. A separation **G** between groups was 1 ply. Thus, the kerfs **233**, **234**, **235**, **236** generally followed a wave pattern, in which kerf depth gradually increases and decreases when moving across the kerf pattern. In various embodiments, the kerf pattern may follow a sinusoidal pattern.

In general, as the separation between kerf lines decreased, the strength of the veneer decreased, and the veneer was more likely to crack when the separation was too small. However, as the separation between kerf lines increased, the amount of telegraphing onto the face veneer increased. It was discovered that, for certain veneers, separations between kerf lines of about 0.004 inches (0.010 cm), or about 0.003 inches-0.005 inches (0.008 cm-0.013 cm) provided sufficient veneer strength while minimizing telegraphing.

Referring to FIG. **3**, a veneer **300** having a 2-directional kerf pattern is illustrated according to various embodiments. Kerf patterns comprising parallel kerfs in one direction are generally suitable for bending a veneer around a single axis. However, in various embodiments, it may be desirable to

bend veneers in complex three-dimensional shapes. Veneer **300** may comprise a first series of kerfs **310**, and a second series of kerfs **320** which are perpendicular to the first series of kerfs **310**. In various embodiments, the first series of kerfs **310** may be perpendicular to a grain pattern in the veneer, and the second series of kerfs **320** may be parallel to the grain pattern in the veneer **300**. However, in various embodiments, neither the first series of kerfs **310** nor the second series of kerfs **320** are perpendicular or parallel to the grain pattern in the veneer **300**. Those skilled in the art will recognize that multiple kerf angles may be utilized in a single veneer in order to bend the veneer into complex shapes. In various embodiments, different kerf patterns may be utilized in different directions in the same veneer. For example, the first series of kerfs **310** may have the kerf pattern illustrated in FIG. **2B**, and the second series of kerfs **320** may have the kerf pattern illustrated in FIG. **2D**. Similarly, any given direction may comprise any number of different kerf patterns.

Referring to FIG. **4**, a flowchart **400** of a method for kerfing a veneer is illustrated according to various embodiments. For thicker wood components, saw blades may be used to kerf the components. However, for thin veneers, it may be difficult to mechanically kerf the veneer with the precision necessary to prevent cracking or telegraphing of the veneer.

In various embodiments, a laser may be used to kerf the veneer. In various embodiments, a CO₂ laser may be used, such as a 150 Watt High Speed Engraving laser system manufactured by Kern®. Settings for the laser may be optimized in order to kerf the veneer (step **410**). Optimizing the settings for the laser may comprise adjusting the intensity, focus, and speed of the laser in order to cut kerfs to a desired depth in a particular veneer. In various embodiments, the laser system may have a cut mode and an engrave mode. Using the laser in cut mode may be faster than using the laser in engrave mode to produce the kerf lines. However, in cut mode, the laser is designed to cut through the veneer. In order to produce kerf lines to a desired depth without cutting through the veneer, the speed with which the laser is moved across the veneer may be increased. Additionally, as the power of laser movement is decreased, the depth of the kerf may decrease. Thus, by moving the laser in cut mode at faster speeds than designed by the laser manufacturer, and/or by adjusting the power of the laser, the laser may kerf the backing of the veneer without cutting through the veneer. In various embodiments, the kerfs may be cut at 5 inches per second (13 cm/s), or between 2-10 inches per second (5-25 cm/s).

Additionally, the power and focus of the laser may be adjusted in order to achieve the desired width, and depth of kerf lines. In various embodiments, a desired width of the kerfs was 0.004 inches (0.010 cm). However, the laser system produces kerfs of 0.003 inches (0.008 cm) in width in response to being focused-on the veneer. In various embodiments, the width of the kerf may be adjusted by defocusing the laser. By defocusing the laser, the laser may cut wider kerfs into the veneer, and the focus may be adjusted such that kerfs of 0.004 inches (0.010 cm) in width, or other desired widths, may be produced.

The laser may cut a kerf pattern in the veneer (step **420**). In various embodiments, kerf patterns comprised kerf lines of different depths. The power of the laser may be adjusted to cut different kerf lines at different depths. For example, a first kerf line may be cut at a first depth, such as 0.5 plies, by moving the laser across the veneer at a first power. A second kerf line may then be cut at a second depth, such as

5

1 ply, by moving the laser across the veneer at a second power. In various embodiments, the first power may be 22 watts and the second power may be 30 watts. However, various powers may be used to achieve different depths in different materials. Thus, by altering the power of the laser, kerf lines of different depths may be produced. In various embodiments, kerf patterns that were 3.1 inches (7.9 cm) wide and four feet (120 cm) long were able to be laser cut in less than 23 minutes.

Once the kerf pattern has been cut in the veneer, the veneer may be bent into a desired shape (step 430). In various embodiments, the veneer may be bent to a radius of 2 inches (5.1 cm) or less. In various embodiments, laser kerfing may be used in conjunction with known bending processes. For example, a veneer may be laser kerfed in conjunction with a steaming or chemical treating process in order to bend the veneer. However, in various embodiments, the laser kerfing alone may be sufficient to bend the veneer. Those skilled in the art will recognize that laser kerfed veneers may be used in any industry or application where thin curved veneers are desirable.

Benefits, other advantages, and solutions to problems have been described herein with regard to specific embodiments. Furthermore, the connecting lines shown in the various figures contained herein are intended to represent exemplary functional relationships and/or physical couplings between the various elements. It should be noted that many alternative or additional functional relationships or physical connections may be present in a practical system. However, the benefits, advantages, solutions to problems, and any elements that may cause any benefit, advantage, or solution to occur or become more pronounced are not to be construed as critical, required, or essential features or elements of the disclosure. The scope of the disclosure is accordingly to be limited by nothing other than the appended claims, in which reference to an element in the singular is not intended to mean "one and only one" unless explicitly so stated, but rather "one or more." Moreover, where a phrase similar to "at least one of A, B, or C" is used in the claims, it is intended that the phrase be interpreted to mean that A alone may be present in an embodiment, B alone may be present in an embodiment, C alone may be present in an embodiment, or that any combination of the elements A, B and C may be present in a single embodiment; for example, A and B, A and C, B and C, or A and B and C. Different cross-hatching is used throughout the figures to denote different parts but not necessarily to denote the same or different materials.

Systems, methods and apparatus are provided herein. In the detailed description herein, references to "one embodi-

6

ment", "an embodiment", "various embodiments", etc., indicate that the embodiment described may include a particular feature, structure, or characteristic, but every embodiment may not necessarily include the particular feature, structure, or characteristic. Moreover, such phrases are not necessarily referring to the same embodiment. Further, when a particular feature, structure, or characteristic is described in connection with an embodiment, it is submitted that it is within the knowledge of one skilled in the art to affect such feature, structure, or characteristic in connection with other embodiments whether or not explicitly described. After reading the description, it will be apparent to one skilled in the relevant art(s) how to implement the disclosure in alternative embodiments.

Furthermore, no element, component, or method step in the present disclosure is intended to be dedicated to the public regardless of whether the element, component, or method step is explicitly recited in the claims. No claim element herein is to be construed under the provisions of 35 U.S.C. 112(f) unless the element is expressly recited using the phrase "means for." As used herein, the terms "comprises", "comprising", or any other variation thereof, are intended to cover a non-exclusive inclusion, such that a process, method, article, or apparatus that comprises a list of elements does not include only those elements but may include other elements not expressly listed or inherent to such process, method, article, or apparatus.

The invention claimed is:

1. A veneer comprising:

a face veneer; and

a backing coupled to the face veneer, wherein the backing comprises a first kerf line in the backing;

wherein a thickness of the veneer is less than 0.015 inches,

wherein the veneer comprises a curve with a radius of less than 2 inches.

2. The veneer of claim 1, wherein the first kerf line is formed by a laser.

3. The veneer of claim 1, wherein a depth of the first kerf line is equal to a thickness of a ply of the backing.

4. The veneer of claim 1, wherein the backing comprises a second kerf line, and wherein a depth of the second kerf line is greater than a depth of the first kerf line.

5. The veneer of claim 1, wherein the backing comprises a second kerf line, and wherein a separation between the first kerf line and the second kerf line is between 0.003 inches and 0.005 inches.

6. The veneer of claim 1, wherein the first kerf line is undetectable in the face veneer.

* * * * *