



US009630376B2

(12) **United States Patent**  
**Griess et al.**

(10) **Patent No.:** **US 9,630,376 B2**  
(45) **Date of Patent:** **Apr. 25, 2017**

(54) **COMPOSITE FILLER**

(71) Applicant: **The Boeing Company**, Chicago, IL (US)

(72) Inventors: **Kenneth H. Griess**, Kent, WA (US);  
**Jack J. Esposito**, Auburn, WA (US)

(73) Assignee: **THE BOEING COMPANY**, Chicago, IL (US)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 80 days.

(21) Appl. No.: **14/492,720**

(22) Filed: **Sep. 22, 2014**

(65) **Prior Publication Data**

US 2016/0082694 A1 Mar. 24, 2016

(51) **Int. Cl.**

**B32B 38/04** (2006.01)  
**B32B 5/26** (2006.01)  
**B26F 1/02** (2006.01)  
**B29C 67/00** (2017.01)  
**B29C 70/30** (2006.01)  
**B29L 31/30** (2006.01)  
**B29L 31/00** (2006.01)

(52) **U.S. Cl.**

CPC ..... **B32B 5/26** (2013.01); **B26F 1/02** (2013.01); **B29C 67/0074** (2013.01); **B29C 70/30** (2013.01); **B29C 2793/0072** (2013.01); **B29L 2031/001** (2013.01); **B29L 2031/3076** (2013.01); **B32B 2038/042** (2013.01); **Y10T 156/1075** (2015.01)

(58) **Field of Classification Search**

CPC ..... Y10T 156/1075; Y10T 156/1761; B32B 2038/042

USPC ..... 428/298.1, 300.7; 156/264, 250  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,666,546 A \* 5/1987 Treber ..... B29C 70/228  
156/264  
4,789,594 A \* 12/1988 Stawski ..... B26D 1/02  
156/222  
5,649,349 A 7/1997 Greenway  
6,183,583 B1 \* 2/2001 Duval ..... C04B 35/83  
156/148  
2006/0249868 A1 \* 11/2006 Brown ..... B29C 70/342  
264/163  
2013/0105072 A1 \* 5/2013 Anderson ..... B29C 70/526  
156/264  
2013/0167696 A1 7/2013 Ueno et al.

\* cited by examiner


*Primary Examiner* — Scott W Dodds


(74) *Attorney, Agent, or Firm* — Yee & Associates, P.C.

(57) **ABSTRACT**

A method and apparatus for forming a composite filler is presented. The method comprises cutting a number of layers from a composite material. The method also aligns the number of layers to form a composite filler having a cross-sectional shape. Each of the number of layers has fibers in plane with the cross-sectional shape.

**15 Claims, 15 Drawing Sheets**








FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9






FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19



# 1

## COMPOSITE FILLER

### BACKGROUND INFORMATION

#### 1. Field

The present disclosure generally relates to composite structures and, in particular, to the fabrication of composite structures. Still more particularly, the present disclosure relates to a method and apparatus for producing composite fillers used to fill gaps in composite structures.

#### 2. Background

Aircraft are being designed and manufactured with greater and greater percentages of composite materials. Composite materials are used in aircraft to decrease the weight of the aircraft. This decreased weight improves performance features such as payload capacities and fuel efficiencies. Further, composite materials provide longer service life for various components in an aircraft.

Composite materials are tough, lightweight materials created by combining two or more functional components. For example, a composite material may include reinforcing fibers bound in a polymer resin matrix. The fibers may be unidirectional or may take the form of a woven cloth or fabric. In thermoset composites, fibers and resins are arranged and cured to form a composite material.

When composite structural members are joined together, gaps or voids may be present along bond lines between the members which may need to be filled in order to increase the strength of the bond. For example, in the aircraft industry, composite fuselage stiffeners such as stringers may include a composite filler at the radius bond line between the stringer and a fuselage skin. The composite filler is applied in the form of triangular cross-section strips, sometimes referred to as noodles or fillers, which fill the voids at the bond line. The composite filler may be formed from composite materials such as adhesive or prepreg tape.

These fillers may be prone to cracking. Cracking undesirably reduces the performance of the resulting composite structure. Cracking may be influenced by the material properties of at least one of the composite filler or the composite structural members.

Therefore, it would be desirable to have a method and apparatus that take into account at least some of the issues discussed above, as well as other possible issues. Specifically, one issue is to find a method and apparatus for preventing cracking in composite fillers.

### SUMMARY

An illustrative embodiment of the present disclosure provides a method. The method comprises cutting a number of layers from a composite material. The method also aligns the number of layers to form a composite filler having a cross-sectional shape. Each of the number of layers has fibers in plane with the cross-sectional shape.

Another illustrative embodiment of the present disclosure provides a composite filler. The composite filler comprises a cross-sectional shape and a number of layers of composite material. Each of the number of layers of the composite material has fibers in plane with the cross-sectional shape.

Yet another illustrative embodiment of the present disclosure provides a method. The method comprises cutting a number of layers from a fabric. The method also resin infuses the number of layers to form a number of layers of composite material. The method further aligns the number of layers of composite material to form a composite filler

# 2

having a cross-sectional shape. Each of the number of layers has fibers in plane with the cross-sectional shape.

The features and functions can be achieved independently in various embodiments of the present disclosure or may be combined in yet other embodiments in which further details can be seen with reference to the following description and drawings.

### BRIEF DESCRIPTION OF THE DRAWINGS

The novel features believed characteristic of the illustrative embodiments are set forth in the appended claims. The illustrative embodiments, however, as well as a preferred mode of use, further objectives and features thereof, will best be understood by reference to the following detailed description of an illustrative embodiment of the present disclosure when read in conjunction with the accompanying drawings, wherein:

FIG. 1 is an illustration of an aircraft in which an illustrative embodiment may be implemented;

FIG. 2 is an illustration of an isometric view of a composite filler and a number of composite members in accordance with an illustrative embodiment;

FIG. 3 is an illustration of a front view of a composite filler and a number of composite members in accordance with an illustrative embodiment;

FIG. 4 is an illustration of an isometric view of a hollow punch in accordance with an illustrative embodiment;

FIG. 5 is an illustration of a front view of a hollow punch in accordance with an illustrative embodiment;

FIG. 6 is an illustration of a front view of another hollow punch in accordance with an illustrative embodiment;

FIG. 7 is an illustration of an isometric view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 8 is an illustration of a cross-sectional view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 9 is an illustration of a cross-sectional view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 10 is an illustration of a cross-sectional view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 11 is an illustration of a cross-sectional view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 12 is an illustration of an isometric view of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 13 is an illustration of an isometric view of another example of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 14 is an illustration of an isometric view of yet another example of composite filler forming equipment in accordance with an illustrative embodiment;

FIG. 15 is an illustration of a block diagram of a manufacturing environment in accordance with an illustrative embodiment;

FIG. 16 is an illustration of a flowchart of a process for forming a composite filler in accordance with an illustrative embodiment;

FIG. 17 is an illustration of a flowchart of a process for forming a composite filler in accordance with an illustrative embodiment;

FIG. 18 is an illustration of a block diagram of an aircraft manufacturing and service method in accordance with an illustrative embodiment; and

FIG. 19 is an illustration of a block diagram of an aircraft in which an illustrative embodiment may be implemented.

#### DETAILED DESCRIPTION

The illustrative embodiments recognize and take into account one or more different considerations. The illustrative embodiments recognize and take into account that cracking of a composite filler may result from tensile forces within a filler. These tensile forces may be caused by a differential coefficient of thermal expansion between the different directions within the composite material. Specifically, shrinkage of the composite material may be different along the direction of the fibers in the composite material. The tensile forces may effectively “pull” the filler apart.

The illustrative examples further recognize and take into account that fibers in composite materials do not substantially expand or contract during heating and cooling. Therefore, the illustrative examples recognize and take into account that composite materials do not substantially expand and contract in directions in which the fibers of the composite materials run.

The illustrative examples further recognize and take into account that reducing cracking in composite fillers may improve structural performance. The illustrative examples also recognize and take into account that reducing cracking in composite fillers may reduce cost by reducing instances of rework or replacement of cracked composite fillers.

With reference now to the figures, and in particular, with reference to FIG. 1, an illustration of an aircraft is depicted in which an illustrative embodiment may be implemented. In this illustrative example, aircraft 100 has wing 102 and wing 104 attached to body 106. Aircraft 100 includes engine 108 attached to wing 102 and engine 110 attached to wing 104.

Body 106 has tail section 112. Horizontal stabilizer 114, horizontal stabilizer 116, and vertical stabilizer 118 are attached to tail section 112 of body 106.

Aircraft 100 is an example of an aircraft in which a composite filler may be implemented in accordance with an illustrative embodiment. For example, composite fillers may be placed between stiffeners 120 and composite skin 122 of aircraft 100. FIG. 1 depicts an exposed view of stiffeners 120.

This illustration of aircraft 100 is provided for purposes of illustrating one environment in which the different illustrative embodiments may be implemented. The illustration of aircraft 100 in FIG. 1 is not meant to imply architectural limitations as to the manner in which different illustrative embodiments may be implemented. For example, aircraft 100 is shown as a commercial passenger aircraft. The different illustrative embodiments may be applied to other types of aircraft, such as private passenger aircraft, a rotorcraft, and other suitable types of aircraft.

Turning now to FIG. 2, an illustration of an isometric view of a composite filler and a number of composite members is depicted in accordance with an illustrative embodiment. Specifically, FIG. 2 is an enlarged view of stiffener 202 of stiffeners 120 in section 2-2 of FIG. 1. As depicted, composite filler 204 is placed in gap 206 formed by stiffener 202 and composite skin 122. In this illustrative example, composite filler 204 has a substantially triangular cross-section. Composite skin 122 is a composite member. Stiffener 202 is also a composite member. As depicted,

stiffener 202 is formed by two composite members, composite member 208 and composite member 210. In some illustrative examples, stiffener 202 may instead be more or less than two composite members. In some illustrative examples, stiffener 202 is a composite stringer. In these illustrative examples, the composite stringer may be formed of a single composite member.

Turning now to FIG. 3, an illustration of a front view of a composite filler and a number of composite members is depicted in accordance with an illustrative embodiment. Specifically, FIG. 3 may be a view of stiffener 202, composite filler 204, and composite skin 122 prior to curing from direction 3-3 of FIG. 2.

Composite member 300 has radius 302 and radius 304. Composite member 300 may be an example of stiffener 202 of FIG. 2 as a single composite member. Composite filler 306 is placed in gap 307 formed by composite member 300 and composite member 309. Composite filler 306 has first side 308 and second side 310. First side 308 of composite filler 306 follows radius 302. Second side 310 of composite filler 306 follows radius 304.

Composite filler 306 may be an example of composite filler 204 in FIG. 2. Composite filler 306 has cross-sectional shape 312. Composite filler 306 is formed of a number of layers of a composite material. Composite filler 306 and each of the number of layers have the same cross-sectional shape, cross-sectional shape 312. In this illustrative example, cross-sectional shape 312 is substantially triangular. Each of the number of layers has fibers in plane with cross-sectional shape 312. Further, each layer of the number of layers may be in plane with cross-sectional shape 312. As used herein, “a number of,” when used with reference to items means one or more items. Accordingly, the number of layers may include one or more layers of composite material.

The number of composite layers may have one or more ply orientations. Specifically, the number of composite layers may have at least one of 0 degree plies, +/-10 degree plies, +/-15 degree plies, +/-30 degree plies, +/-45 degree plies, +/-60 degree plies, +/-75 degree plies, or +/-90 degree plies.

As used herein, the phrase “at least one of,” when used with a list of items, means different combinations of one or more of the listed items may be used and only one of each item in the list may be needed. For example, “at least one of item A, item B, or item C” may include, without limitation, item A, item A and item B, or item B. This example also may include item A, item B, and item C or item B and item C. Of course, any combinations of these items may be present. In other examples, “at least one of” may be, for example, without limitation, two of item A; one of item B; and ten of item C; four of item B and seven of item C; or other suitable combinations. The item may be a particular object, thing, or a category. In other words, at least one of means any combination items and number of items may be used from the list but not all of the items in the list are required.

In some illustrative examples, each layer of composite filler 306 may be formed of a composite laminate stack. In some illustrative examples, each layer of composite filler 306 may include multiple plies. In some illustrative examples, each layer of composite filler 306 may include a stack of 0 degree/60 degree/-60 degree plies.

Composite filler 306 has a longitudinal axis that extends into and out of the page. The fibers in the layers of composite filler that are in plane with cross-sectional shape 312 extend orthogonal to the longitudinal axis. As used herein, a first item is orthogonal to a second item when the first item is at

## 5

a ninety degree angle to the second item. Orthogonal may also be referred to as perpendicular. Composite filler **306** may have a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis. The coefficient of thermal expansion may be zero orthogonal to the longitudinal axis because of the fibers extending orthogonal to the longitudinal axis. Composite filler **306** may have a coefficient of thermal expansion of substantially zero orthogonal to each of the sides of cross-sectional shape **312**. In some illustrative examples, when cross-sectional shape **312** is substantially triangular, having zero degree plies, 60 degree plies, and -60 degree plies may cause the coefficient of thermal expansion of substantially zero orthogonal to each of the three sides.

The illustration of composite filler **306** in FIG. 3 is not meant to imply physical or architectural limitations to the manner in which an illustrative embodiment may be implemented. Other components in addition to or in place of the ones illustrated may be used. Some components may be unnecessary. For example, composite filler **306** may have a cross-section that is not substantially triangular.

Turning now to FIG. 4, an illustration of an isometric view of a hollow punch is depicted in accordance with an illustrative embodiment. Hollow punch **400** may be used to cut layers of composite material that may be aligned to form composite filler **306** of FIG. 3. Hollow punch **400** may be a physical embodiment of hollow punch **1550** of FIG. 15.

Hollow punch **400** has first end **402** and second end **404**. First end **402** has opening **406**. Second end **404** has opening **408**. Cross-sectional area **410** of hollow punch **400** at first end **402** is smaller than cross-sectional area **412** of hollow punch **400** at second end **404**. First end **402** has sharp edge **414**.

Sharp edge **414** of hollow punch **400** may be pressed against a composite material to cut the composite material. The cut composite material may travel through hollow punch **400** from first end **402** to second end **404**. The cut composite material may travel through hollow punch **400** as subsequent layers of composite material are cut by sharp edge **414** and travel from first end **402** towards second end **404**.

Hollow punch **400** may be used in conjunction with other components for forming a composite filler. For example, hollow punch **400** may be used with a base. In some illustrative examples, hollow punch **400** may be used with a sleeve. In further illustrative examples, hollow punch **400** may be used with a heater. In yet further illustrative examples, hollow punch **400** may be used with resin injectors.

Turning now to FIG. 5, an illustration of a front view of a hollow punch is depicted in accordance with an illustrative embodiment. View **500** may be a view of hollow punch **400** from direction **5-5** of FIG. 4.

Cross-sectional shape **502** is super-imposed over hollow punch **400**. Cross-sectional shape **502** is a desired cross-sectional shape for a resulting composite filler. In some illustrative examples, cross-sectional shape **502** may be the same as cross-sectional shape **312** of FIG. 3.

As can be seen from view **500**, some additional forming steps may be done to form a resulting composite filler into cross-sectional shape **502** from cross-sectional shape **504** of sharp edge **414**. As can be seen clearly in view **500**, cross-sectional area **410** of first end **402** is smaller than cross-sectional area **412** of second end **404**.

Cross-sectional shape **502** and sharp edge **414** are substantially triangular. Sharp edge **414** has rounded corner **506**

## 6

with radius **508**, rounded corner **510** with radius **512**, and rounded corner **514** with radius **516**.

Turning now to FIG. 6, an illustration of a front view of another hollow punch is depicted in accordance with an illustrative embodiment. Hollow punch **600** may be used to cut layers of composite material that may be aligned to form composite filler **306** of FIG. 3. Hollow punch **600** may be a physical embodiment of hollow punch **1550** of FIG. 15.

Hollow punch **600** has first end **602** and second end **604**. First end **602** has opening **606**. Second end **604** also has an opening, not shown in this view. Cross-sectional area **608** of hollow punch **600** at first end **602** is smaller than cross-sectional area **610** of hollow punch **600** at second end **604**. First end **602** has sharp edge **612**.

Sharp edge **612** of hollow punch **600** may be pressed against a composite material to cut the composite material. The cut composite material may travel through hollow punch **600** from first end **602** to second end **604**. The cut composite material may travel through hollow punch **600** as subsequent layers of composite material are cut by sharp edge **612** and travel from first end **602** towards second end **604**.

As depicted, cross-sectional shape **502** of FIG. 5 is super-imposed over hollow punch **600**. Cross-sectional shape **502** and sharp edge **612** are substantially triangular. Sharp edge **612** has rounded corner **614** with radius **616**, rounded corner **618** with radius **620**, and rounded corner **622** with radius **624**. As can be seen from FIG. 6, radius **616**, radius **620**, and radius **624** are substantially the same. Further, radius **616**, radius **620**, and radius **624** are substantially larger than radius **508**, radius **512**, and radius **516** of FIG. 5. As a result, a composite filler formed using hollow punch **600** may require a greater amount of forming to reach cross-sectional shape **502** than a composite filler formed by hollow punch **400**.

Turning now to FIG. 7, an illustration of an isometric view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. Composite filler forming equipment **700** includes hollow punch **702** and base **704**. Hollow punch **702** may be hollow punch **400** of FIG. 4. Material **706** may be positioned between hollow punch **702** and base **704**. In some illustrative examples, material **706** may be a composite material. In other illustrative examples, material **706** may be a fabric. Base **704** may be formed of at least one of a rigid material and a compliant material. In some illustrative examples, material for base **704** may be selected so that material **706** may be cut with clean edges. In some illustrative examples, material for base **704** may be selected such that a sharp edge of hollow punch **702** remains sharp for a desirable number of cuts.

Hollow punch **702** may be moved in direction **708** to cut material **706**. Hollow punch **702** may cut material **706** by applying pressure to material **706** in direction **708** such that sharp edge **710** of hollow punch **702** cuts through material **706** to contact base **704**. Hollow punch **702** may then be retracted in direction **708**. When hollow punch **702** is retracted, a cut portion of material **706** may remain in hollow punch **702**.

One of composite material **706** and base **704** or hollow punch **702** may move in at least one of direction **712** and direction **714** such that hollow punch **702** is positioned over composite material **706** that can be cut. Afterwards, hollow punch **702** may again be moved in direction **708** to cut material **706** again. This process may be repeated a desired number of times until a composite filler of desired length is formed.

Turning now to FIG. 8, an illustration of a cross-sectional view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. View 800 may be a cross-sectional view of a hollow punch, such as hollow punch 702, along cut 8-8 of FIG. 7. In this illustrative example, hollow punch 802 has resin injector 804 and resin injector 806. Layer 808, layer 810, layer 812, layer 814, layer 816, layer 818, and layer 820 of material 822 traveling within hollow punch 802 in direction 824 from sharp edge 826 to end 828. As layer 808, layer 810, layer 812, layer 814, layer 816, layer 818, and layer 820 of material 822 travel in direction 824, they will eventually encounter sleeve 831. Sleeve 831 will collect layers of material 822 as they exit end 828 of hollow punch 802. Sleeve 831 may allow for better handleability of a resulting composite filler. The resulting composite filler would include sleeve 831 and a number of layers such as layer 808, layer 810, layer 812, layer 814, layer 816, layer 818, and layer 820 of material 822.

Material 822 has number of holes 832 from which layer 808, layer 810, layer 812, and layer 814 were cut. Portion 834 is positioned between two of number of holes 832. Portion 834 is related to a distance traveled by hollow punch 802 in direction 836 between each cut. Specifically, if the distance is increased, portion 834 will increase in width. If the distance is decreased, portion 834 will decrease in width. It is desirable for hollow punch 802 to travel a distance sufficient so that hollow punch 802 cuts a portion of material 822 the same shape as the cross-sectional shape of sharp edge 826. In other words, it is desirable for hollow punch 802 to move sufficiently so that all of sharp edge 826 contacts material 822 so that there is not a hole in the subsequent cut layer.

Turning now to FIG. 9, an illustration of a cross-sectional view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. View 900 depicts hollow punch 802 after having moved in direction 836 and having cut a subsequent layer of material 822. Specifically, layer 902 is now within hollow punch 802. Each of layer 808, layer 810, layer 812, layer 814, layer 816, layer 818, and layer 820 of material 822 have traveled in direction 824 within hollow punch 802 due to layer 902 entering hollow punch 802.

Turning now to FIG. 10, an illustration of a cross-sectional view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. View 1000 depicts hollow punch 802 during resin infusion of layer 808, layer 810, layer 812, layer 814, layer 816, layer 818, layer 820, and layer 902 of material 822. Specifically, in view 1000, resin 1002 has entered hollow punch 802 through resin injector 804 and resin injector 806. Resin 1002 could be selected such that resin 1002 is compatible with fibers of material 822. In some illustrative examples, resin 1002 may wet fibers of material 822 as each subsequent layer passes resin injector 804 and resin injector 806. In some illustrative examples, resin 1002 may wet fibers of material 822 of any layer present within hollow punch 802 when resin is introduced by resin injector 804 and resin injector 806. In some illustrative examples, resin 1002 may wet fibers of material 822 of a number of layers present within hollow punch 802 and near resin injector 804 and resin injector 806 when resin 1002 is introduced by resin injector 804 and resin injector 806. In some illustrative examples, this resin infusion may be done under vacuum.

Vertical position 1004 of resin injector 804 and resin injector 806 may be placed in any desirable location on

hollow punch 802. Vertical position 1004 may be selected such that resin does not flow out of end 828 or leak from sharp edge 826.

Turning now to FIG. 11, an illustration of a cross-sectional view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. In view 1100, hollow punch 1102 cuts layers from material 1104 backed with adhesive 1106. As number of layers 1108 travel in direction 1110 within hollow punch 1102, heat 1112 may be applied to hollow punch 1102. Heat 1112 may bond number of layers 1108 together. As depicted, layers 1108 are alternating layers of material 1104 which may be a dry fiber broad good and adhesive 1106. In some examples, adhesive 1106 may be a resin film. In these examples, heat 1112 may infuse the resin of adhesive 1106 into the fibers of material 1104 and may result in partially cured filler. This partial cure or bonding may provide greater handleability of a resulting composite filler.

The illustration of view 1100 in FIG. 11 is not meant to imply physical or architectural limitations to the manner in which an illustrative embodiment may be implemented. For example, layers 1108 may not be alternating layers. In some illustrative examples, a plurality of layers of material 1104 may be present between layers of adhesive 1106. In other illustrative examples, a plurality of layers of adhesive 1106 may be present between layers of material 1104.

Turning now to FIG. 12, an illustration of an isometric view of composite filler forming equipment is depicted in accordance with an illustrative embodiment. Manufacturing environment 1200 may be a physical embodiment of manufacturing environment 1500. Manufacturing environment 1200 includes hollow punch 1202 and material 1204. Hollow punch 1202 may be used to cut layers out of material 1204 that may be aligned to form composite filler 306 of FIG. 3.

Hollow punch 1202 may be moved in direction 1206 to contact material 1204. After cutting a layer from material 1204, hollow punch 1202 may be moved in at least one of direction 1208 and direction 1210. As depicted, hollow punch 1202 may have started by cutting a layer from composite material 1204 at location 1212. Afterwards, hollow punch 1202 may have moved along direction 1208 to location 1214. After cutting a layer from material 1204 at location 1214, hollow punch 1202 may have moved along direction 1208 again. This process may be repeated along material 1204 until either a desired number of layers have been cut or hollow punch 1202 hits the edge of material 1204. If hollow punch 1202 hits the edge of material 1204, hollow punch 1202 may be moved in direction 1208 until hollow punch 1202 is over a desired location to cut material 1204.

Turning now to FIG. 13, an illustration of an isometric view of another example of composite filler forming equipment is depicted in accordance with an illustrative embodiment. Composite filler forming equipment 1300 may be a physical embodiment of composite filler forming equipment 1504 of FIG. 15. Composite filler forming equipment 1300 includes hollow punch 1302 and base 1304. Hollow punch 1302 and base 1304 may be used to cut out layers of material 1306. In this illustrative example, base 1304 may be rigid. Base 1304 includes recess 1308. Recess 1308 has cross-sectional shape 1310. Cross-sectional shape 1310 is substantially the same as cross-sectional shape 1312 of sharp edge 1314 of hollow punch 1302.

Turning now to FIG. 14, an illustration of an isometric view of yet another example of composite filler forming equipment is depicted in accordance with an illustrative

embodiment. Composite filler forming equipment **1400** may be a physical embodiment of composite filler forming equipment **1504** of FIG. **15**. Composite filler forming equipment **1400** includes solid punch **1402** and plate **1404**. Solid punch **1402** has cross-sectional shape **1406**. Plate **1404** has hole **1408** with cross-sectional shape **1410**. Cross-sectional shape **1406** is substantially the same as cross-sectional shape **1410** but smaller. In other words, cross-sectional shape **1410** may be a larger version of cross-sectional shape **1406**. As a result, solid punch **1402** may enter hole **1408**. The difference in size of cross-sectional shape **1406** and cross-sectional shape **1410** may be selected such that a material placed between solid punch **1402** and plate **1404** has a layer cut from it. The layer has substantially the same shape as cross-sectional shape **1410**. Multiple layers of a material cut using solid punch **1402** and plate **1404** may be aligned to form a composite filler.

Turning now to FIG. **15**, an illustration of a block diagram of a manufacturing environment is depicted in accordance with an illustrative embodiment. Composite filler **306** of FIG. **3** may be formed using manufacturing environment **1500** of FIG. **15**.

Manufacturing environment **1500** comprises composite filler **1502**, composite filler forming equipment **1504**, composite material **1506**, and sleeve material **1508**. Composite filler **1502** may be configured to be placed in gap **1510** formed by composite member **1512**, composite member **1514**, and composite member **1516**.

Composite filler **1502** comprises number of layers of composite material **1518**. Composite filler **1502** has cross-sectional shape **1520**. Cross-sectional shape **1520** may be configured to fit within cross-section **1522** of gap **1510**. In some illustrative examples, cross-sectional shape **1520** may be substantially triangular **1524**. Substantially triangular **1524** cross-sectional shape **1520** has first side **1526**, second side **1528**, and third side **1530**. First side **1526** of composite filler **1502** may contact composite member **1514**. In some illustrative examples, composite member **1514** may have radius **1532**. In these illustrative examples, first side **1526** of composite filler **1502** may follow radius **1532**.

Second side **1528** of composite filler **1502** may contact composite member **1516**. In some illustrative examples, composite member **1516** may have radius **1534**. In these illustrative examples, second side **1528** of composite filler **1502** may follow radius **1534**.

Third side **1530** may contact composite member **1512** of number of composite members **1536**. Number of composite members **1536** includes composite member **1512**, composite member **1514**, and composite member **1516**.

Number of layers of composite material **1518** may be formed from composite material **1506**. Composite material **1506** may include tape **1538** and prepreg sheets **1540**. Number of layers of composite material **1518** may be formed from fabric **1542** which is later infused with resin.

Number of layers of composite material **1518** may be cut from composite material **1506**. Number of layers of composite material **1518** may be aligned to form composite filler **1502**. Number of layers of composite material **1518** may be surrounded with sleeve material **1508** to form composite filler **1502** having sleeve **1544** around number of layers of composite material **1518**.

Sleeve material **1508** may be a flexible woven material. Sleeve material **1508** may be selected based on compatibility with the resin of number of layers of composite material **1518**. Sleeve material **1508** may further be selected based on at least one of weight, strength, or other material properties. For example, sleeve material **1508** may be selected such that

sleeve material **1508** does not undesirably increase the weight of resulting composite filler **1502**.

The weave of sleeve material **1508** may be substantially open. During cure of composite filler **1502**, resin from number of layers of composite material **1518** may flow and fill the holes within the weave of sleeve material **1508**. Sleeve material **1508** may also be referred to as a scrim. In some illustrative examples, sleeve material **1508** may take the form of a nylon or another polymeric material.

Number of layers of composite material **1518** has one or more ply orientations. Specifically, number of layers of composite material **1518** may have at least one of 0 degree plies, +/-10 degree plies, +/-15 degree plies, +/-30 degree plies, +/-45 degree plies, +/-60 degree plies, +/-75 degree plies, or +/-90 degree plies. In some illustrative examples, each layer of number of layers of composite material **1518** may have a single ply orientation. In some illustrative examples, each layer of number of layers of composite material **1518** may have a plurality of ply orientations. In some illustrative examples, a layer in number of layers of composite material **1518** may have a 0 degree/60 degree/-60 degree ply orientation.

Composite filler **1502** has longitudinal axis **1546**. Number of layers of composite material **1518** and composite filler **1502** may each have cross-sectional shape **1520**. Number of layers of composite material **1518** may be aligned such that their cross-sectional shapes are substantially orthogonal to longitudinal axis **1546**.

The degree of expansion divided by the change in temperature for composite filler **1502** is coefficient of thermal expansion **1548**. Composite filler **1502** is formed of composite material **1506** having oriented fibers. Accordingly, coefficient of thermal expansion **1548** may vary based on the direction of measurement. The fibers in number of layers of composite material **1518** that are in plane with cross-sectional shape **1520** extend orthogonal to longitudinal axis **1546**. Composite filler **1502** may have coefficient of thermal expansion **1548** of substantially zero orthogonal to longitudinal axis **1546**. Coefficient of thermal expansion **1548** may be zero orthogonal to longitudinal axis **1546** because of the fibers extending orthogonal to longitudinal axis **1546**. Composite filler **1502** may have coefficient of thermal expansion **1548** of substantially zero orthogonal to each of the sides, first side **1526**, second side **1528**, and third side **1530**, of cross-sectional shape **1520**. In some illustrative examples, when cross-sectional shape **1520** is substantially triangular **1524**, having zero degree plies, 60 degree plies, and -60 degree plies may cause coefficient of thermal expansion **1548** of substantially zero orthogonal to each of the three sides.

Composite filler forming equipment **1504** may cut number of layers of composite material **1518** from at least one of composite material **1506** or fabric **1542**. In some illustrative examples, number of layers of composite material **1518** may be cut by hollow punch **1550** and base **1552**. Hollow punch **1550** has first end **1554**, second end **1556**, and cross-sectional shape **1558**. First end **1554** and second end **1556** have cross-sectional shape **1558**. However, cross-sectional area **1560** of first end **1554** is smaller than cross-sectional area **1562** of second end **1556**.

In some illustrative examples, cross-sectional shape **1558** may be the same or substantially the same as cross-sectional shape **1520**. In other illustrative examples, layers of composite material **1506** or fabric **1542** cut using hollow punch **1550** having cross-sectional shape **1558** may be shaped using composite shaping system **1563**. In these illustrative examples, the layers may be aligned and then shaped using

composite shaping system **1563** such that the layers change from cross-sectional shape **1558** to cross-sectional shape **1520**.

Sharp edge **1564** of first end **1554** may cut at least one of composite material **1506** or fabric **1542** to form layers. The layers may travel from first end **1554** to second end **1556** as additional layers are cut from at least one of composite material **1506** or fabric **1542**. In illustrative examples in which hollow punch **1550** cuts layers from fabric **1542**, these layers may be resin infused using resin injectors **1566** associated with hollow punch **1550**.

Hollow punch **1550** may cut through at least one of composite material **1506** or fabric **1542** to contact base **1552**. Base **1552** may be formed of compliant material **1568**. By forming base **1552** of compliant material **1568**, sharp edge **1564** may be maintained for more repetitions than if sharp edge **1564** contacted base **1552** formed of a rigid material. In some illustrative examples, base **1552** may have recess **1570**. Recess **1570** may have cross-sectional shape **1572** which is substantially similar to cross-sectional shape **1558**. As a result, base **1552** may be formed of a rigid material without undesirably dulling sharp edge **1564**.

Hollow punch **1550** may move towards and away from base **1552** using first movement system **1574**. In some illustrative examples, at least one of hollow punch **1550** or base **1552** may move relative to at least one of composite material **1506** or fabric **1542** using second movement system **1576**. In some illustrative examples, at least one of hollow punch **1550** or base **1552** may move relative to the other using second movement system **1576**.

In some illustrative examples, rather than hollow punch **1550** and base **1552**, composite filler forming equipment **1504** may include solid punch **1578** and plate **1580**. Plate **1580** may have hole **1582**. Solid punch **1578** may interact with hole **1582** such that a layer of material is cut from at least one of composite material **1506** or fabric **1542** and sent through hole **1582**. In some illustrative examples, number of layers of composite material **1518** exit hole **1582**. Sleeve material **1508** may surround number of layers of composite material **1518**.

The illustration of manufacturing environment **1500** in FIG. **15** is not meant to imply physical or architectural limitations to the manner in which an illustrative embodiment may be implemented. Other components in addition to or in place of the ones illustrated may be used. Some components may be unnecessary. Also, the blocks are presented to illustrate some functional components. One or more of these blocks may be combined, divided, or combined and divided into different blocks when implemented in an illustrative embodiment.

For example, manufacturing environment **1500** may not include composite member **1514**. In this example, composite member **1512** and composite member **1516** may form gap **1510**. In other illustrative examples, composite material **1506** may be cut by a different tool. For example, composite filler forming equipment **1504** may take the form of a laser, a knife, or other desirable cutting equipment. In these illustrative examples, each layer may be removed from composite material **1506** after being cut and then may be aligned.

Yet further, in some illustrative examples, composite material **1506** may be associated with an adhesive. In these illustrative examples, a heater may be associated with hollow punch **1550** to heat the adhesive as layers travel through hollow punch **1550**. In these illustrative examples, by heating the adhesive and composite material **1506**, the layers

may be 'B-staged.' Further, by heating the layers of adhesive and composite material **1506**, the layers may have greater handleability.

Turning now to FIG. **16**, an illustration of a flowchart of a process for forming a composite filler is depicted in accordance with an illustrative embodiment. Process **1600** may be used to form composite filler **306** of FIG. **3**. Process **1600** may be used to form composite filler **1502** of FIG. **15**.

Process **1600** begin by cutting a number of layers from a composite material (operation **1602**). The number of layers may be cut from the composite material by composite filler forming equipment such as composite filler forming equipment **1504** of FIG. **15**. In some illustrative examples, this composite filler forming equipment may be a hollow punch and a base. In other illustrative examples, the composite filler forming equipment may be a solid punch and a plate with a hole.

Process **1600** may then align the number of layers to form a composite filler having a cross-sectional shape, each of the number of layers having fibers in plane with the cross-sectional shape (operation **1604**), with the process terminating thereafter. In some illustrative examples, the composite filler and each of the number of layers has the same cross-sectional shape. In some illustrative examples, the cross-sectional shape is substantially triangular.

In some illustrative examples, the composite filler has a longitudinal axis, and the fibers extend orthogonal to the longitudinal axis. In some illustrative examples, the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis. The composite filler may have a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis as the fibers extend orthogonal to the longitudinal axis.

In some illustrative examples, the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to each of the sides of the cross-sectional shape. The coefficient of thermal expansion orthogonal to each of the sides of the cross-sectional shape may be influenced by the direction of fibers within the number of layers of composite material. In some illustrative examples, a number of fibers in the number of layers of composite material may be orthogonal to each of the sides of the cross-sectional shape.

In some illustrative examples, at least one layer of the number of layers of composite material may be a 0 degree/60 degree/-60 degree stack. In other illustrative examples, at least one layer of number of layers of composite material may have a 0 degree/45 degree/-45 degree stack.

Turning now to FIG. **17**, an illustration of a flowchart of a process for forming a composite filler is depicted in accordance with an illustrative embodiment. Process **1700** may be used to form composite filler **306** of FIG. **3**. Process **1700** may be used to form composite filler **1502** of FIG. **15**.

Process **1700** begins by cutting a number of layers from a fabric (operation **1702**). The number of layers may be cut from the fabric by composite filler forming equipment such as composite filler forming equipment **1504** of FIG. **15**. In some illustrative examples, this composite filler forming equipment may be a hollow punch and a base. In other illustrative examples, the composite filler forming equipment may be a solid punch and a plate with a hole.

Process **1700** then resin infuses the number of layers to form a number of layers of composite material (operation **1704**). Resin infusion may be performed through resin injectors associated with a hollow punch.

Process **1700** may then align the number of layers of composite material to form a composite filler having a

cross-sectional shape, each of the number of layers having fibers in plane with the cross-sectional shape (operation **1706**). In some illustrative examples, the composite filler has a longitudinal axis, and the fibers extend orthogonal to the longitudinal axis. In some illustrative examples, the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis.

In some illustrative examples, the composite filler and each of the number of layers has the same cross-sectional shape. The cross-sectional shape may be substantially triangular. In some illustrative examples, the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to each of the sides of the cross-sectional shape.

The coefficient of thermal expansion orthogonal to each of the sides of the cross-sectional shape may be influenced by the direction of fibers within the number of layers of composite material. In some illustrative examples, a number of fibers in the number of layers of composite material may be orthogonal to each of the sides of the cross-sectional shape. In some illustrative examples, at least one layer of number of layers of composite material may be a 0 degree/60 degree/-60 degree stack.

The flowcharts and block diagrams in the different depicted embodiments illustrate the architecture, functionality, and operation of some possible implementations of apparatuses and methods in an illustrative embodiment. In this regard, each block in the flowcharts or block diagrams may represent a module, a segment, a function, and/or a portion of an operation or step.

In some alternative implementations of an illustrative embodiment, the function or functions noted in the blocks may occur out of the order noted in the figures. For example, in some cases, two blocks shown in succession may be executed substantially concurrently, or the blocks may sometimes be performed in the reverse order, depending upon the functionality involved. Also, other blocks may be added in addition to the illustrated blocks in a flowchart or block diagram. Further, some blocks may not be implemented.

For example, at least one of process **1600** and process **1700** may further include surrounding the number of layers of composite material with a sleeve. This sleeve may take the form of a scrim. In some illustrative examples, at least one of process **1600** and process **1700** may further include placing the composite filler within a gap formed by a number of composite members and curing the composite filler.

The illustrative embodiments of the disclosure may be described in the context of aircraft manufacturing and service method **1800** as shown in FIG. **18** and aircraft **1900** as shown in FIG. **19**. Turning first to FIG. **18**, an illustration of a block diagram of an aircraft manufacturing and service method is depicted in accordance with an illustrative embodiment. During pre-production, aircraft manufacturing and service method **1800** may include specification and design **1802** of aircraft **1900** in FIG. **19** and material procurement **1804**.

During production, component and subassembly manufacturing **1806** and system integration **1808** of aircraft **1900** in FIG. **19** takes place. Thereafter, aircraft **1900** in FIG. **19** may go through certification and delivery **1810** in order to be placed in service **1812**. While in service **1812** by a customer, aircraft **1900** in FIG. **19** is scheduled for routine maintenance and service **1814**, which may include modification, reconfiguration, refurbishment, and other maintenance or service.

Each of the processes of aircraft manufacturing and service method **1800** may be performed or carried out by a

system integrator, a third party, and/or an operator. In these examples, the operator may be a customer. For the purposes of this description, a system integrator may include, without limitation, any number of aircraft manufacturers and major-system subcontractors; a third party may include, without limitation, any number of vendors, subcontractors, and suppliers; and an operator may be an airline, a leasing company, a military entity, a service organization, and so on.

With reference now to FIG. **19**, an illustration of a block diagram of an aircraft is depicted in which an illustrative embodiment may be implemented. In this example, aircraft **1900** is produced by aircraft manufacturing and service method **1800** in FIG. **18** and may include airframe **1902** with plurality of systems **1904** and interior **1906**. Examples of systems **1904** include one or more of propulsion system **1908**, electrical system **1910**, hydraulic system **1912**, and environmental system **1919**. Any number of other systems may be included. Although an aerospace example is shown, different illustrative embodiments may be applied to other industries, such as the automotive industry.

Apparatuses and methods embodied herein may be employed during at least one of the stages of aircraft manufacturing and service method **1800** in FIG. **18**. One or more illustrative embodiments may be used during component and subassembly manufacturing **1806**. For example, composite filler **1502** in FIG. **15** may be used during component and subassembly manufacturing **1806**. Further, composite filler **1502** may also be used to perform replacements during maintenance and service **1814**.

Thus, the illustrative embodiments provide a method and apparatus for forming a composite filler. By forming a composite filler having a number of layers with fibers in plane with a cross-section of the composite filler, the composite filler may have a lower likelihood of cracking. Further, the composite filler may have a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis. By having a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis, the composite filler may have a lower likelihood of cracking. Further, the composite filler may have a coefficient of thermal expansion of substantially zero orthogonal to each of the sides of the cross-sectional shape of the composite filler. By having a coefficient of thermal expansion of substantially zero orthogonal to each of the sides of the cross-sectional shape, the composite filler may have a lower likelihood of cracking.

Yet further, by cutting a number of layers from a composite material to form a composite filler having fibers in plane with the cross-sectional shape of the composite filler, manufacturing time of the composite filler may be reduced. Additionally, by cutting a number of layers from a composite material to form a composite filler having fibers in plane with the cross-sectional shape of the composite filler, manufacturing costs of the composite filler may be reduced. Further, by using a sleeve, handling of composite filler may be improved.

The description of the different illustrative embodiments has been presented for purposes of illustration and description, and is not intended to be exhaustive or limited to the embodiments in the form disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art. Further, different illustrative embodiments may provide different features as compared to other illustrative embodiments. The embodiment or embodiments selected are chosen and described in order to best explain the principles of the embodiments, the practical application, and to enable others of ordinary skill in the art to understand the disclosure

## 15

for various embodiments with various modifications as are suited to the particular use contemplated.

What is claimed is:

1. A method comprising:
  - cutting a number of layers from a composite material with a first end of a hollow punch;
  - cutting additional layers of the composite material such that the number of layers of composite material travels through the hollow punch from the first end to a second end of the hollow punch, wherein at least one of the number of layers is retained within the hollow punch as subsequent ones of the layers of composite material are cut with the hollow punch;
  - aligning the number of layers to form a composite filler having a cross-sectional shape, each of the number of layers having fibers in plane with the cross-sectional shape; and
  - removing the composite filler at the second end of the hollow punch as the additional layers of composite material cause the number of layers of composite material travels through the hollow punch.
2. The method of claim 1, wherein the composite filler has a longitudinal axis, and wherein the fibers extend orthogonal to the longitudinal axis.
3. The method of claim 2, wherein the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis.
4. The method of claim 1 further comprising:
  - surrounding the number of layers of the composite material with a sleeve material.
5. The method of claim 1, wherein the cross-sectional shape is substantially triangular.
6. The method of claim 1 further comprising:
  - placing the composite filler within a gap formed at a bond line between a number of composite members; and
  - curing the composite filler.
7. The method of claim 6, wherein the step of curing the composite filler further comprises:
  - co-curing the composite filler with the number of composite members.
8. The method of claim 1, wherein the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to each of sides of the cross-sectional shape.

## 16

9. The method of claim 1, further comprising:
  - receiving the number of layers of the composite material within a sleeve material as the number of layers of composite material exits the second end of the hollow punch.
10. The method of claim 9, wherein the sleeve comprises a scrim.
11. A method comprising:
  - cutting a number of layers from a fabric with a first end of a hollow punch;
  - cutting additional layers of the fabric such that the number of layers travels through the hollow punch from the first end to a second end of the hollow punch, wherein at least one of the number of layers is retained within the hollow punch as subsequent ones of the number of layers of fabric are cut with the hollow punch;
  - resin infusing the number of layers to form a number of layers of composite material;
  - aligning the number of layers of the composite material to form a composite filler having a cross-sectional shape, each of the number of layers having fibers in plane with the cross-sectional shape; and
  - removing the composite filler at the second end of the hollow punch as the additional layers of composite material cause the number of layers of composite material travels through the hollow punch.
12. The method of claim 11, wherein the composite filler has a longitudinal axis, wherein the fibers extend orthogonal to the longitudinal axis, and wherein the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to the longitudinal axis.
13. The method of claim 11 further comprising:
  - surrounding the number of layers of the composite material with a sleeve material.
14. The method of claim 11 further comprising:
  - placing the composite filler within a gap formed by a number of composite members; and
  - curing the composite filler.
15. The method of claim 11, wherein the composite filler has a coefficient of thermal expansion of substantially zero orthogonal to each of sides of the cross-sectional shape.

\* \* \* \* \*