



US009776912B2

(12) **United States Patent**
Ritzberger et al.

(10) **Patent No.:** **US 9,776,912 B2**
(45) **Date of Patent:** **Oct. 3, 2017**

(54) **LITHIUM SILICATE GLASS CERAMIC AND
GLASS WITH DIVALENT METAL OXIDE**

(71) Applicant: **Ivoclar Vivadent AG**, Schaan (LI)
(72) Inventors: **Christian Ritzberger**, Grabs (CH);
Elke Apel, Oberschan (CH); **Wolfram
Höland**, Schaan (LI); **Volker
Rheinberger**, Vaduz (LI)
(73) Assignee: **Ivoclar Vivadent AG**, Schaan (LI)
(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/947,336**

(22) Filed: **Nov. 20, 2015**

(65) **Prior Publication Data**

US 2016/0075593 A1 Mar. 17, 2016

Related U.S. Application Data

(63) Continuation of application No. 14/001,182, filed as
application No. PCT/EP2012/070220 on Oct. 11,
2012, now Pat. No. 9,232,989.

(30) **Foreign Application Priority Data**

Oct. 14, 2011 (EP) 11185335

(51) **Int. Cl.**

C03C 10/04 (2006.01)
C03C 10/00 (2006.01)
C03C 3/095 (2006.01)
C03C 3/097 (2006.01)
C03C 4/00 (2006.01)
A61K 6/02 (2006.01)
A61C 13/00 (2006.01)
A61C 13/083 (2006.01)
C03B 32/02 (2006.01)
A61C 13/08 (2006.01)
C03C 3/076 (2006.01)

(52) **U.S. Cl.**

CPC **C03C 10/0009** (2013.01); **A61C 13/00**
(2013.01); **A61C 13/0022** (2013.01); **A61C**
13/082 (2013.01); **A61C 13/083** (2013.01);
A61K 6/02 (2013.01); **A61K 6/0205** (2013.01);
C03B 32/02 (2013.01); **C03C 3/076** (2013.01);
C03C 3/095 (2013.01); **C03C 3/097** (2013.01);
C03C 4/0021 (2013.01); **C03C 10/00**
(2013.01); **C03C 10/0027** (2013.01); **Y10T**
29/49567 (2015.01)

(58) **Field of Classification Search**

CPC **C03C 10/0045**; **C03C 10/0009**; **C03C**
10/0036; **C03C 3/078**; **C03C 3/087**; **C03C**
3/062
USPC **501/2**, **5**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,006,775 A 10/1961 Chen
3,022,180 A 2/1962 Morrissey et al.
3,161,528 A 12/1964 Eppler
3,252,778 A 5/1966 Goodman et al.
3,804,608 A 4/1974 Gaskell et al.
3,816,704 A 6/1974 Borom et al.
3,977,857 A 8/1976 Mattox
4,155,888 A 5/1979 Mooth
4,189,325 A 2/1980 Barrett et al.
4,414,282 A 11/1983 McCollister et al.
4,473,653 A 9/1984 Rudoi
4,480,044 A 10/1984 McAlinn
4,515,634 A * 5/1985 Wu C03C 4/0021
106/35
4,671,770 A 6/1987 Bell et al.
4,963,707 A 10/1990 Zyokou et al.
4,977,114 A 12/1990 Horinouchi et al.
5,173,454 A 12/1992 Rittler et al.
5,176,961 A 1/1993 Crooker et al.
5,219,799 A 6/1993 Beall et al.
5,432,130 A 7/1995 Rheinberger et al.
5,507,981 A 4/1996 Petticrew et al.
5,618,763 A 4/1997 Frank et al.
5,628,564 A 5/1997 Nenyeyi et al.
5,691,256 A 11/1997 Taguchi et al.
5,698,019 A 12/1997 Frank et al.
5,698,482 A 12/1997 Frank et al.
5,702,514 A 12/1997 Petticrew
5,707,777 A 1/1998 Aoai et al.
5,804,520 A 9/1998 Morinaga et al.
5,872,069 A 2/1999 Abe
5,874,376 A 2/1999 Taguchi et al.
5,925,180 A 7/1999 Frank et al.
5,938,959 A 8/1999 Wang
5,968,856 A 10/1999 Schweiger et al.
6,034,011 A 3/2000 Yamaguchi et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CA 2163792 A1 12/1994
CA 2252660 5/1999
CA 2252660 A1 5/1999
CA 2213390 7/2002
DE 1696473 B1 8/1970
DE 2451121 5/1975
DE 2949619 A1 11/1980
DE 4303458 C1 1/1994
DE 4314817 11/1994
DE 4423793 2/1996
DE 4423794 2/1996
DE 4428839 2/1996

(Continued)

OTHER PUBLICATIONS

<http://en.wikipedia.org/wiki/Nucleation>; Sep. 20, 2012.

(Continued)

Primary Examiner — Noah Wiese
(74) *Attorney, Agent, or Firm* — Ann M. Knab; Thad
McMurray

(57) **ABSTRACT**

Lithium silicate glass ceramics and glasses containing specific oxides of divalent elements are described which crystallize at low temperatures and are suitable in particular as dental materials.

32 Claims, No Drawings

(56)

References Cited

U.S. PATENT DOCUMENTS

6,048,589	A	4/2000	Suzuki	
6,066,584	A	5/2000	Krell et al.	
6,095,682	A	8/2000	Hollander et al.	
6,106,747	A	8/2000	Wohlwend	
6,121,175	A	9/2000	Drescher et al.	
6,157,004	A	12/2000	Bizzio	
6,163,020	A	12/2000	Bartusch et al.	
6,174,827	B1	1/2001	Goto et al.	
6,252,202	B1	6/2001	Zychek	
6,267,595	B1	7/2001	Gratz	
6,270,876	B1	8/2001	Abe et al.	
6,287,121	B1	9/2001	Guiot et al.	
6,342,458	B1	1/2002	Schweiger et al.	
6,376,397	B1	4/2002	Petticrew	
6,420,288	B2	7/2002	Schweiger et al.	
6,441,346	B1	8/2002	Zychek	
6,455,451	B1	9/2002	Brodkin et al.	
6,485,849	B2	11/2002	Petticrew	
6,514,893	B1	2/2003	Schweiger et al.	
6,517,623	B1	2/2003	Brodkin et al.	
6,593,257	B1	7/2003	Nagata et al.	
6,703,332	B2 *	3/2004	Peng C03C 10/0027 428/846.9	
6,802,894	B2	10/2004	Brodkin et al.	
6,818,573	B2	11/2004	Petticrew	
7,162,321	B2	1/2007	Luthardt et al.	
7,316,740	B2	1/2008	Rheinberger et al.	
7,452,836	B2	11/2008	Apel et al.	
7,655,586	B1	2/2010	Brodkin et al.	
7,806,694	B2	10/2010	Brodkin et al.	
7,816,291	B2	10/2010	Schweiger et al.	
7,867,930	B2	1/2011	Apel et al.	
7,867,933	B2	1/2011	Apel et al.	
7,871,948	B2	1/2011	Apel et al.	
7,892,995	B2	2/2011	Castillo	
7,993,137	B2	8/2011	Apel et al.	
8,042,358	B2	10/2011	Schweiger et al.	
8,047,021	B2	11/2011	Schweiger et al.	
8,444,756	B2	5/2013	Schweiger et al.	
2001/0006174	A1	7/2001	Brennan	
2001/0031446	A1	10/2001	Petticrew	
2002/0009600	A1	1/2002	Peng et al.	
2002/0010063	A1	1/2002	Schweiger et al.	
2002/0022563	A1	2/2002	Schweiger et al.	
2002/0031670	A1	3/2002	Goto et al.	
2002/0035025	A1	3/2002	Schweiger et al.	
2002/0160694	A1	10/2002	Wood	
2003/0073563	A1	4/2003	Brodkin et al.	
2004/0182538	A1	9/2004	Lambrecht	
2005/0098064	A1	5/2005	Schweiger et al.	
2005/0127544	A1	6/2005	Brodkin et al.	
2006/0082033	A1	4/2006	Hauptmann et al.	
2006/0139091	A1	6/2006	Fratti	
2006/0257823	A1	11/2006	Pfeiffer et al.	
2006/0257824	A1	11/2006	Pfeiffer et al.	
2007/0023971	A1	2/2007	Saha et al.	
2007/0042889	A1	2/2007	Apel et al.	
2008/0120994	A1	5/2008	Schweiger et al.	
2008/0125303	A1 *	5/2008	Schweiger C03C 10/0027 501/4	
2008/0199823	A1	8/2008	Miller	
2009/0023574	A1	1/2009	Holand et al.	
2009/0038344	A1	2/2009	Apel et al.	
2009/0038508	A1	2/2009	Apel et al.	
2009/0042166	A1	2/2009	Graig et al.	
2009/0256274	A1	10/2009	Castillo	
2009/0258778	A1	10/2009	Castillo	
2010/0083706	A1	4/2010	Castillo	
2011/0009254	A1	1/2011	Schweiger et al.	
2011/0030423	A1	2/2011	Johannes et al.	
2011/0256409	A1	10/2011	Ritzberger et al.	
2012/0094822	A1	4/2012	Castillo et al.	
2012/0148988	A1	6/2012	Castillo et al.	

2012/0248642	A1	10/2012	Ritzberger et al.
2012/0309607	A1	12/2012	Durschang et al.
2014/0141960	A1	5/2014	Borcuch-Laczka et al.

FOREIGN PATENT DOCUMENTS

DE	19647739	3/1998
DE	19725553	12/1998
DE	19725555	12/1998
DE	19750794 A1	6/1999
DE	10031431	1/2002
DE	102007011337	9/2008
EP	231773	8/1987
EP	0536572 A1	4/1993
EP	0626353 A1	11/1994
EP	0536479 B1	9/1995
EP	0827941	3/1998
EP	0916625	5/1999
EP	0817597 B1	9/1999
EP	0774933 B1	12/2000
EP	1127564	8/2001
EP	1152641 A3	11/2001
EP	1505041	2/2005
EP	1688397 A1	8/2006
EP	1688398	8/2006
GB	752243 A	7/1956
GB	2284655 A	6/1995
JP	32-5080	7/1932
JP	S4842814 B1	12/1973
JP	S6272547 A	4/1987
JP	S62182134 A	8/1987
JP	H09208260 A	8/1997
JP	H10212132 A	8/1998
JP	10323354 A	12/1998
JP	11-74418 A	3/1999
JP	2005062832 A	3/2005
JP	5094017 B2	12/2012
WO	9532678 A2	12/1995
WO	0228802 A2	4/2002
WO	2006042046 A2	4/2006
WO	2007028787 A1	3/2007
WO	2008106958	9/2008
WO	2009126317	10/2009
WO	2011/076422	6/2011
WO	2011076422	6/2011
WO	2012143137 A1	10/2012

OTHER PUBLICATIONS

Deubener, J., et al., "Induction time analysis of nucleation and crystal grown in di- and metasilicate glasses", *Journal of Non-Crystalline Solids* 1993, 163, 1-12.

Durschang, Dr. Bernhard, "Report of Results", Fraunhofer Institute for Silicate Research ISC Glass and Mineral Materials, 2015.

McMillan, P.W., et al., "The Structure and Properties of a Lithium Zinc Silicate Glass-Ceramic", *Journal of Material Science*, 1966, I, 269-279.

Borom, M.P., et al., "Strength and Microstructure in Lithium Disilicate Glass Ceramics", *J. Am. Ceram. Soc.*, 1975, 58, 385-391.

Von Clausbruch, et al., "Effect of ZnO on the Crystallization, Microstructure, and Properties of Glass-Ceramics in the SiO₂—Li₂O—K₂O—P₂O₅ System," *Glastech. Ber. Glass. Sci. Technol.* 74(8): 223-229(2001).

Oliveria et al., "Sintering and Crystallization of a GlassPowder in the Li₂O—ZrO₂—SiO₂ System," *J. Amer. Ceramic Soc.* 81(3):777-780 (1998).

Von Clausbruch et al., "Effect of P₂O₅ on the Crystallization and Microstructure of Glass-Ceramics in the SiO₂—Li₂O—Zn—P₂O₅ System," *Glastech. Ber. Glass Sci. Technol.* 74(8): 223-229(2001).

Stokey, S.D., "Chemical Machining of Photosensitive Glass," *Ind. Eng. Chem.* 45:115-118 (1993).

Holand, W. et al., "Glass-ceramic technology", American Chemical Society 2002, Westerville OH, USA.

Holand, W. et al., "Control of nucleation in glass ceramics", *Phil. Trans. Soc. Lond. A* 2003, 361, 575-589.

(56)

References Cited

OTHER PUBLICATIONS

Holand, W. et al., "Principles and phenomena of bioengineering with glass-ceramics of dental restoration", *Journal of the European Ceramic Society* 2007, 27, 1571-1577.

Apel, E., et al., "Influence of ZrO₂ on the crystallization and properties of lithium disilicate glass-ceramics derived from multi-component system", *Journal of European Ceramic Society*, 2007, 27, 1571-1577.

Ivoclar Vivadent Inc., IPS e.max lithium disilicate, 627329, Rev. Feb. 2009.

Giassi, et al., "Injection Moulding of LiO₂—ZrO₂—SiO₂-Al₂O₃ (LZSA) Glass Ceramics," *Glass Technol.*, 45(3), 277-280 (2005).

Jakovac, M., et al., "Measurement of ion elution from dental ceramics," *Journal of the European Ceramic Society*, May 6, 2006, vol. 26, pp. 1695-1700.

Montedo et al., "Low Thermal Expansion Sintered LZSA Glass Ceramics," *American Ceramic Society Bulletin*, vol. 87, No. 7, pp. 34-40, Jul. 2008.

* cited by examiner

**LITHIUM SILICATE GLASS CERAMIC AND
GLASS WITH DIVALENT METAL OXIDE**

CROSS-REFERENCE TO RELATED
APPLICATIONS

This application is a continuation application and claims priority to U.S. application Ser. No. 14/001,182 filed on Aug. 23, 2013, which is the National Stage Application of International patent application PCT/EP2012/070220, filed on Oct. 11, 2012, which claims priority to European patent application No. 11185335.4 filed on Oct. 14, 2011, all the disclosures of which are incorporated herein by reference in their entirety.

The invention relates to lithium silicate glass ceramic and glass which comprise divalent metal oxide selected from MgO, SrO, CaO, BaO, ZnO and mixtures thereof and are particularly suitable for use in dentistry, preferably for the preparation of dental restorations.

Lithium silicate glass ceramics are characterized as a rule by very good mechanical properties, which is why they have been used for a long time in the dental field and there primarily for the preparation of dental crowns and small bridges. The known lithium silicate glass ceramics usually contain as main components SiO₂, Li₂O, Na₂O or K₂O, and nucleating agents such as P₂O₅ as well as additional components such as La₂O₃.

DE 24 51 121 describes lithium disilicate glass ceramics which contain K₂O and Al₂O₃. They are prepared from corresponding nuclei-containing starting glasses which are heated to temperatures of from 850 to 870° C. for the crystallization of lithium disilicate. The purpose for which the glass ceramics are used is not disclosed.

EP 827 941 describes sinterable lithium disilicate glass ceramics for dental purposes, which also contain K₂O or Na₂O in addition to La₂O₃. The lithium disilicate crystal phase is produced at a temperature of 850° C.

Lithium disilicate glass ceramics which likewise contain La₂O₃ as well as K₂O are known from EP 916 625. A heat treatment is carried out at 870° C. for the formation of lithium disilicate.

EP 1 505 041 describes lithium silicate glass ceramics containing K₂O, which, when lithium metasilicate is present as main crystal phase, can be very satisfactorily machined e.g. by means of CAD/CAM processes, in order to then be converted by further heat treatment at temperatures of from 830 to 850° C. into high-strength lithium disilicate glass ceramics.

EP 1 688 398 describes similar K₂O-containing lithium silicate glass ceramics which additionally are substantially free from ZnO. A heat treatment at 830 to 880° C. is applied to them to produce lithium disilicate.

U.S. Pat. No. 5,507,981 describes processes for producing dental restorations and glass ceramics that can be used in these processes. These are in particular lithium disilicate glass ceramics with a low level of Li₂O which usually contain Na₂O or K₂O.

U.S. Pat. No. 6,455,451 relates to lithium disilicate glass ceramics which contain further alkali metal oxides in addition to Li₂O. However, the production of the desired lithium disilicate crystal phase requires high temperatures of from 800 to 1000° C.

WO 2008/106958 discloses lithium disilicate glass ceramics for veneering zirconium oxide ceramics. The glass ceramics contain Na₂O and are produced by heat treatment of nuclei-containing glasses at 800 to 940° C.

WO 2009/126317 describes GeO₂-containing lithium metasilicate glass ceramics which also comprise K₂O. The glass ceramics are processed to form dental products primarily by machining.

WO 2011/076422 relates to lithium disilicate glass ceramics which also contain K₂O in addition to high levels of ZrO₂ or HfO₂. The crystallization of lithium disilicate takes place at high temperatures of from 800 to 1040° C.

The known lithium disilicate glass ceramics have in common that they require heat treatments at more than 800° C. in order to effect the precipitation of lithium disilicate as main crystal phase. A large quantity of energy is therefore necessary to prepare them. Further, in the known glass ceramics the alkali metal oxides, such as in particular K₂O or Na₂O, as well as La₂O₃, are as a rule present as essential components which are apparently required for the production of glass ceramics with the desired properties and in particular the formation of the desired lithium disilicate main crystal phase.

There is therefore a need for lithium silicate glass ceramics during the preparation of which the crystallization of lithium disilicate can be effected at lower temperatures. Further, it should also be possible to prepare them without the alkali metal oxides, such as K₂O or Na₂O, as well as La₂O₃, previously regarded as necessary, and they should be suitable in particular for the preparation of dental restorations primarily in view of their optical and mechanical properties.

This object is achieved by the lithium silicate glass ceramic according to any one of claim 1 to 17 or 20. Also a subject of the invention are the starting glass according to claim 18 or 20, the lithium silicate glass with nuclei according to claim 19 or 20, the process for the preparation of the glass ceramic and the lithium silicate glass with nuclei according to claim 21 or 22 as well as the use according to claim 23 or 24.

The lithium silicate glass ceramic according to the invention is characterized in that it comprises divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O.

The divalent oxide is particularly preferably SrO, as this has a very high X-ray opacity. This is particularly advantageous especially in the use as dental material and in particular as dental restorative material.

It is preferred that the glass ceramic comprises the divalent metal oxide or mixtures thereof in an amount of 0.1 to 15, in particular 2.0 to 12.0 and particularly preferably 2.0 to 8.0 wt.-%.

It is particularly surprising that the formation of the glass ceramic according to the invention with lithium disilicate as main crystal phase is achieved even in the absence of various components regarded as necessary for conventional glass ceramics, such as alkali metal oxides, in particular K₂O, Na₂O, and La₂O₃, and even at very low and thus advantageous crystallization temperatures of from 600 to 750° C. The glass ceramic also has a combination of optical and mechanical properties as well as processing properties that are very advantageous for the use as dental material.

The glass ceramic according to the invention therefore preferably comprises less than 1.0, in particular less than 0.5 wt.-%, preferably less than 0.1 wt.-% K₂O. The glass ceramic is particularly preferably essentially free of K₂O.

Further, a glass ceramic is preferred which comprises K₂O, Na₂O and mixtures thereof in an amount of less than 1.0, in particular less than 0.5 and preferably less than 0.1 wt.-% and particularly preferably which is essentially free of K₂O and Na₂O.

In a further preferred embodiment, the glass ceramic comprises less than 1.0, in particular less than 0.5 and preferably less than 0.1 wt.-% further alkali metal oxide and particularly preferably is essentially free thereof. The term "further alkali metal oxide" refers to alkali metal oxide with the exception of Li_2O .

Further, a glass ceramic which comprises less than 0.1 wt.-% La_2O_3 is preferred. The glass ceramic is particularly preferably essentially free of La_2O_3 .

A glass ceramic is also preferred, which excludes lithium silicate glass ceramic comprising at least 6.1 wt.-% ZrO_2 .

Further, a glass ceramic is also preferred, which excludes lithium silicate glass ceramic comprising at least 8.5 wt.-% transition metal oxide selected from the group consisting of oxides of yttrium, oxides of transition metals with an atomic number of 41 to 79 and mixtures of these oxides.

The glass ceramic according to the invention preferably comprises 55.0 to 85.0, in particular 60.0 to 82.0 and preferably 67.0 to 79.0 wt.-% SiO_2 .

It is also preferred that the glass ceramic comprises 12.5 to 20.0, in particular 15.0 to 17.0 wt.-% Li_2O .

It is further preferred that the molar ratio between SiO_2 and Li_2O is from 1.7 to 3.1, in particular 1.8 to 3.0. It is very surprising that the production of lithium disilicate is achieved within this broad range. Specifically at ratios of less than 2.0 customary materials usually form lithium metasilicate instead of lithium disilicate.

The glass ceramic according to the invention can also comprise a nucleating agent. P_2O_5 is particularly preferably used for this. The glass ceramic preferably comprises 0 to 10.0, in particular 2.0 to 9.0, and preferably 3.0 to 7.5 wt.-% P_2O_5 .

In a further preferred embodiment, the glass ceramic comprises at least one and preferably all of the following components:

Component	wt.-%
SiO_2	67.5 to 79.0
Li_2O	12.5 to 20.0
divalent metal oxide or mixtures	2.0 to 12.0
P_2O_5	0 to 7.0, in particular 3.0 to 7.0
Al_2O_3	0 to 6.0, in particular 3.0 to 6.0.

The glass ceramic according to the invention can moreover also comprise additional components which are selected in particular from oxides of trivalent elements, further oxides of tetravalent elements, further oxides of pentavalent elements, oxides of hexavalent elements, melt accelerators, colourants and fluorescent agents.

Suitable oxides of trivalent elements are in particular Al_2O_3 , Y_2O_3 and Bi_2O_3 and mixtures thereof, and preferably Al_2O_3 .

The term "further oxides of tetravalent elements" refers to oxides of tetravalent elements with the exception of SiO_2 . Examples of suitable further oxides of tetravalent elements are TiO_2 , SnO_2 and GeO_2 , in particular TiO_2 .

The term "further oxides of pentavalent elements" refers to oxides of pentavalent elements with the exception of P_2O_5 . Examples of suitable further oxides of pentavalent elements are Ta_2O_5 and Nb_2O_5 .

Examples of suitable oxides of hexavalent elements are WO_3 and MoO_3 .

A glass ceramic is preferred, which comprises at least one oxide of trivalent elements, at least one further oxide of

tetravalent elements, at least one further oxide of pentavalent elements and/or at least one oxide of hexavalent elements.

Examples of melt accelerators are fluorides.

Examples of colourants and fluorescent agents are oxides of d- and f-elements, such as the oxides of Ti, V, Sc, Mn, Fe, Co, Ta, W, Ce, Pr, Nd, Tb, Er, Dy, Gd, Eu and Yb. Metal colloids, e.g. of Ag, Au and Pd, can also be used as colourants and in addition can also act as nucleating agents. These metal colloids can be formed e.g. by reduction of corresponding oxides, chlorides or nitrates during the melting and crystallization processes. The metal colloids can be present in the glass ceramic in an amount of 0.005 to 0.5 wt.-%.

The term "main crystal phase" used below refers to the crystal phase which has the highest proportion by volume compared with other crystal phases.

In one embodiment, the glass ceramic according to the invention comprises lithium metasilicate as main crystal phase. In particular the glass ceramic comprises more than 5 vol.-%, preferably more than 10 vol.-% and particularly preferably more than 15 vol.-% lithium metasilicate crystals, relative to the total glass ceramic.

In a further particularly preferred embodiment, the glass ceramic comprises lithium disilicate as main crystal phase. In particular, the glass ceramic comprises more than 10 vol.-%, preferably more than 20 vol.-% and particularly preferably more than 30 vol.-% lithium disilicate crystals, relative to the total glass ceramic.

The lithium disilicate glass ceramic according to the invention is characterized by particularly good mechanical properties and can be produced e.g. by heat treatment of the lithium metasilicate glass ceramic according to the invention. However, it can be formed in particular by heat treatment of a corresponding starting glass or of a corresponding lithium silicate glass with nuclei.

It has surprisingly been shown that the lithium disilicate glass ceramic according to the invention has very good mechanical and optical properties and processing properties even in the absence of components regarded as essential for conventional glass ceramics. The combination of its properties even allows it to be used as dental material and in particular as material for the preparation of dental restorations.

The lithium disilicate glass ceramic according to the invention has in particular a fracture toughness, measured as K_{IC} value, of at least $1.9 \text{ MPa}\cdot\text{m}^{0.5}$ and in particular more than about $2.3 \text{ MPa}\cdot\text{m}^{0.5}$. This value was determined using the Vickers method and calculated using Niihara's equation.

The invention also relates to a lithium silicate glass with nuclei that are suitable for forming lithium metasilicate and/or lithium disilicate crystals, wherein the glass comprises the components of the above-described glass ceramics according to the invention. Thus this glass comprises divalent metal oxide selected from MgO , CaO , SrO , BaO , ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li_2O . For preferred embodiments of this glass reference is made to the preferred embodiments described above of the glass ceramics according to the invention.

The glass with nuclei according to the invention can be produced by heat treatment of a correspondingly composed starting glass according to the invention. The lithium metasilicate glass ceramic according to the invention can then be formed by a further heat treatment, and in turn be converted into the lithium disilicate glass ceramic according to the invention by further heat treatment, or the lithium disilicate glass ceramic according to the invention can also preferably be formed directly from the glass with nuclei. The starting

glass, the glass with nuclei and the lithium metasilicate glass ceramic can consequently be regarded as precursors for the production of the high-strength lithium disilicate glass ceramic.

The glass ceramics according to the invention and the glasses according to the invention are present in particular in the form of powders, granulates or blanks, e.g. monolithic blanks, such as platelets, cuboids or cylinders, or powder compacts, in unsintered, partly sintered or dense-sintered form. They can easily be further processed in these forms. They can, however, also be present in the form of dental restorations, such as inlays, onlays, crowns, veneers, facets or abutments.

The invention also relates to a process for the preparation of the glass ceramic according to the invention and the glass with nuclei according to the invention, in which a correspondingly composed starting glass, the glass with nuclei according to the invention or the lithium metasilicate glass ceramic according to the invention is subjected to at least one heat treatment in the range of 450 to 950° C. and in particular 450 to 750° C.

The starting glass according to the invention therefore comprises divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and at least 12.1 wt.-% Li₂O. In addition, it preferably also comprises suitable amounts of SiO₂ and Li₂O, in order to allow the formation of a lithium silicate glass ceramic, and in particular a lithium disilicate glass ceramic. Further, the starting glass can also comprise still further components, such as are given above for the lithium silicate glass ceramic according to the invention. All those embodiments are preferred for the starting glass which are also given as preferred for the glass ceramic.

In the process according to the invention, the glass with nuclei is usually prepared by means of a heat treatment of the starting glass at a temperature of in particular 470 to 560° C. The lithium disilicate glass ceramic according to the invention is then preferably produced from the glass with nuclei through further heat treatment at preferably 600 to 750 and in particular 600 to 720 and particularly preferably 600 to 700° C.

Thus, much lower temperatures are used according to the invention for the crystallization of lithium disilicate than with the conventional lithium disilicate glass ceramics. The energy thus saved represents a clear advantage. Surprisingly, this low crystallization temperature is even possible in the absence of components, such as further alkali metal oxides and La₂O₃, regarded as essential for conventional glass ceramics.

To prepare the starting glass, the procedure is in particular that a mixture of suitable starting materials, such as carbonates, oxides, phosphates and fluorides, is melted at temperatures of in particular from 1300 to 1600° C. for 2 to 10 h. To achieve a particularly high homogeneity, the obtained glass melt is poured into water in order to form a glass granulate, and the obtained granulate is then melted again.

The melt can then be poured into moulds to produce blanks of the starting glass, so-called solid glass blanks or monolithic blanks.

It is also possible to put the melt into water again in order to prepare a granulate. This granulate can then be pressed, after grinding and optionally addition of further components, such as colourants and fluorescent agents, to form a blank, a so-called powder compact.

Finally, the starting glass can also be processed to form a powder after granulation.

The starting glass, e.g. in the form of a solid glass blank, a powder compact or in the form of a powder, is then subjected to at least one heat treatment in the range of 450 to 950° C. It is preferred that a first heat treatment is initially carried out at a temperature in the range of 470 to 560° C. to prepare a glass according to the invention with nuclei which are suitable for forming lithium metasilicate and/or lithium disilicate crystals. This first heat treatment is preferably carried out for a period of 10 min to 120 min and in particular 10 min to 30 min. The glass with nuclei can then preferably be subjected to at least one further heat treatment at a higher temperature and in particular more than 570° C. to effect crystallization of lithium metasilicate or lithium disilicate. This further heat treatment is preferably carried out for a period of 10 min to 120 min, in particular 10 min to 60 min and particularly preferably 10 min to 30 min. To crystallize lithium disilicate, the further heat treatment is usually carried out at 600 to 750, in particular 600 to 720 and preferably 600 to 700° C.

In a preferred embodiment of the process, therefore

(a) the starting glass is subjected to a heat treatment at a temperature of 470 to 560° C. in order to form the glass with nuclei, and

(b) the glass with nuclei is subjected to a heat treatment at a temperature of from 600 to 750° C. in order to form the glass ceramic with lithium disilicate as main crystal phase.

The duration of the heat treatments carried out in (a) and (b) is preferably as given above.

The at least one heat treatment carried out in the process according to the invention can also take place during hot pressing or sintering-on of the glass according to the invention or the glass ceramic according to the invention.

Dental restorations, such as bridges, inlays, onlays, crowns, veneers, facets or abutments, can be prepared from the glass ceramics according to the invention and the glasses according to the invention. The invention therefore also relates to their use for the preparation of dental restorations. It is preferred that the glass ceramic or the glass is shaped into the desired dental restoration by pressing or machining.

The pressing is usually carried out under increased pressure and increased temperature. It is preferred that the pressing is carried out at a temperature of 700 to 1200° C. It is further preferred to carry out the pressing at a pressure of 2 to 10 bar. During pressing, the desired shape change is achieved by viscous flow of the material used. The starting glass according to the invention and in particular the glass with nuclei according to the invention, the lithium metasilicate glass ceramic according to the invention and the lithium disilicate glass ceramic according to the invention can be used for the pressing. The glasses and glass ceramics according to the invention can be used in particular in the form of blanks, e.g. solid blanks or powder compacts, e.g. in unsintered, partly sintered or dense-sintered form.

The machining is usually carried out by material removal processes and in particular by milling and/or grinding. It is particularly preferred that the machining is carried out within the framework of a CAD/CAM process. The starting glass according to the invention, the glass with nuclei according to the invention, the lithium metasilicate glass ceramic according to the invention and the lithium disilicate glass ceramic according to the invention can be used for the machining. The glasses and glass ceramics according to the invention can be used in particular in the form of blanks, e.g. solid blanks or powder compacts, e.g. in unsintered, partly sintered or dense-sintered form. The lithium metasilicate glass ceramic according to the invention and lithium disili-

cate glass ceramic according to the invention are preferably used for the machining. The lithium disilicate glass ceramic can also be used in a not fully crystallized form which was produced by heat treatment at a lower temperature. This has the advantage that an easier machining, and thus the use of simpler equipment for the machining, is possible. After the machining of such a partly crystallized material, it is usually subjected to a heat treatment at a higher temperature and in particular 650 to 750° C. in order to effect further crystallization of lithium disilicate.

In general, after the preparation of the dental restoration shaped as desired by pressing or machining, it can also in particular be heat-treated in order to convert the precursors used, such as starting glass, glass with nuclei or lithium metasilicate glass ceramic, into lithium disilicate glass ceramic or to increase the crystallization of lithium disilicate or to reduce the porosity, e.g. of a porous powder compact used.

However, the glass ceramic according to the invention and the glass according to the invention are also suitable as coating material of e.g. ceramics and glass ceramics. The invention is therefore also directed towards the use of the glass according to the invention or the glass ceramic according to the invention for coating in particular ceramics and glass ceramics.

The invention also relates to a process for coating ceramics and glass ceramics, in which the glass ceramic according to the invention or the glass according to the invention is applied to the ceramic or glass ceramic and is exposed to increased temperature.

This can take place in particular by sintering-on and preferably by pressing-on. With sintering-on, the glass ceramic or the glass is applied to the material to be coated, such as ceramic or glass ceramic, in the usual way, e.g. as powder, and then sintered at increased temperature. With the preferred pressing-on, the glass ceramic according to the invention or the glass according to the invention is pressed on, e.g. in the form of powder compacts or monolithic blanks, at an increased temperature of e.g. 700 to 1200° C., applying pressure, e.g. 2 to 10 bar. The methods described in EP 231 773 and the press furnace disclosed therein can be used in particular for this. A suitable furnace is e.g. the Programat EP 5000 from Ivoclar Vivadent AG, Liechtenstein.

It is preferred that, after conclusion of the coating process, the glass ceramic according to the invention is present with lithium disilicate as main crystal phase, as such glass ceramic has particularly good properties.

Because of the above-described properties of the glass ceramic according to the invention and the glass according to the invention as its precursor, they are suitable in particular for use in dentistry. A subject of the invention is therefore also the use of the glass ceramic according to the invention or the glass according to the invention as a dental material and in particular for the preparation of dental restorations or as a coating material for dental restorations, such as crowns, bridges and abutments.

Finally, the glasses and glass ceramics according to the invention can also be mixed together with other glasses and glass ceramics in order to produce dental materials with properties set as desired. Compositions and in particular dental materials which comprise the glass according to the invention or the glass ceramic according to the invention in combination with at least one other glass and/or one other glass ceramic therefore represent a further subject of the invention. The glass according to the invention or the glass ceramic according to the invention can therefore be used in

particular as main component of an inorganic-inorganic composite or in combination with a plurality of other glasses and/or glass ceramics, wherein the composites or combinations can be used in particular as dental materials. The combinations or composites can particularly preferably be present in the form of sintered blanks. Examples of other glasses and glass ceramics for the preparation of inorganic-inorganic composites and of combinations are disclosed in DE 43 14 817, DE 44 23 793, DE 44 23 794, DE 44 28 839, DE 196 47 739, DE 197 25 553, DE 197 25 555, DE 100 31 431 and DE 10 2007 011 337. These glasses and glass ceramics belong to the silicate, borate, phosphate or aluminosilicate group. Preferred glasses and glass ceramics are of SiO₂—Al₂O₃—K₂O type (with cubic or tetragonal leucite crystals), SiO₂—B₂O₃—Na₂O type, alkali-silicate type, alkali-zinc-silicate type, silicophosphate type, SiO₂—ZrO₂ type and/or lithium-aluminosilicate type (with spodumene crystals). By mixing such glasses or glass ceramics with the glasses and/or glass ceramics according to the invention, for example the coefficient of thermal expansion can be set as desired in a broad range of from 6 to 20·10⁻⁶ K⁻¹.

The invention is explained in more detail below by means of examples.

EXAMPLES

Examples 1 to 17—Composition and Crystal Phases

A total of 17 glasses and glass ceramics according to the invention with the composition given in Table I were prepared by melting corresponding starting glasses followed by heat treatment for controlled nucleation and crystallization.

For this, the starting glasses weighing from 100 to 200 g were first melted from customary raw materials at 1400 to 1500° C., wherein the melting was very easily possible without formation of bubbles or streaks. By pouring the starting glasses into water, glass frits were prepared which were then melted a second time at 1450 to 1550° C. for 1 to 3 h for homogenization.

In the case of Examples 1 to 8 and 10 to 17, the obtained glass melts were then poured into preheated moulds in order to produce glass monoliths. All glass monoliths proved transparent.

In the case of Example 9, the obtained glass melt was cooled to 1400° C. and converted to a finely divided granulate by pouring into water. The granulate was dried and ground to a powder with a particle size of <90 μm. This powder was moistened with some water and pressed to form a powder compact at a pressure of 20 MPa.

The glass monoliths (Examples 1-8 and 10-17) as well as the powder compact (Example 9) were then converted by thermal treatment to glasses and glass ceramics according to the invention. The thermal treatments used for controlled nucleation and controlled crystallization are also given in Table I. The following meanings apply

T_N and t_N Temperature and time used for nucleation

T_C and t_C Temperature and time used for crystallization of lithium disilicate

LS lithium metasilicate

LP lithium orthophosphate

It can be seen that a first heat treatment in the range of 470 to 560° C. resulted in the formation of lithium silicate glasses with nuclei and these glasses crystallized by a further heat treatment already at 600 to 750° C. within only 20 to 30 min to glass ceramics with lithium disilicate as main crystal phase, as was established by X-ray diffraction tests.

The produced lithium disilicate glass ceramics had high fracture toughness values, measured as critical stress intensity factor K_{IC} , of more than $1.9 \text{ MPa}\cdot\text{m}^{0.5}$.

The produced lithium disilicate glass ceramics were able to be very satisfactorily machined in a CAD/CAM process or hot pressed into the form of various dental restorations, which were also provided with a veneer if required.

They were also able to be applied by hot pressing as coatings onto in particular dental restorations, e.g. in order to veneer the latter as desired.

Example 18—Processing Via Powder Compacts

The glass ceramics according to Examples 1, 2, 7 and 12 were ground to powders with an average particle size of $<90 \mu\text{m}$.

In a first variant, the obtained powder was pressed with or without pressing auxiliaries to powder compacts and the latter were partly or densely sintered at temperatures of 800 to 1100°C . and then further processed by machining or by hot pressing to form dental restorations.

In a second variant, the obtained powders were pressed with or without pressing auxiliaries to powder compacts and the latter were then further processed by machining or by hot pressing to form dental restorations. In particular, the dental restorations obtained after the machining were then densely sintered at temperatures of 900 to 1100°C .

With both variants, it was possible to prepare in particular crowns, caps, partial crowns and inlays as well as coatings on dental ceramics and dental glass ceramics.

Example 19—Hot Pressing of Glass with Nuclei

A glass with the composition according to Example 9 was prepared by mixing corresponding raw materials in the form of oxides and carbonates for 30 min in a Turbula mixer and then melting the mixture at 1450°C . for 120 min in a platinum crucible. The melt was poured into water in order to obtain a finely divided glass granulate. This glass granulate was melted again at 1530°C . for 150 min in order to obtain a glass melt with particularly high homogeneity. The temperature was reduced to 1500°C . for 30 min and cylindrical glass blanks with a diameter of 12.5 mm were then prepared by pouring into pre-heated, separable steel moulds or graphite moulds. The obtained glass cylinders were then nucleated at 560°C . and stress-relieved.

The nucleated glass cylinders were then processed by hot pressing at a pressing temperature of 970°C . and a pressing time of 6 min using an EP600 press furnace, Ivoclar Vivadent AG, to form dental restorations, such as inlays, onlays, veneers, partial crowns, crowns, laminating materials and laminates. In each case, lithium disilicate was detected as main crystal phase.

TABLE I

Composition	Example							
	1 wt.-%	2 wt.-%	3 wt.-%	4 wt.-%	5 wt.-%	6 wt.-%	7 wt.-%	8 wt.-%
SiO ₂	73.8	73.8	69.4	68.7	73.8	76.4	73.8	73.8
Li ₂ O	15.3	15.3	19.7	17.0	15.3	12.7	15.3	15.3
P ₂ O ₅	3.4	3.4	3.4	7.0	3.4	3.4	3.4	3.4
Al ₂ O ₃	3.5	—	3.5	3.4	3.5	3.5	—	3.5
ZrO ₂	—	3.5	—	—	—	—	—	—
TiO ₂	—	—	—	—	—	—	3.5	—
MgO	4.0	4.0	4.0	3.9	—	—	—	—
CaO	—	—	—	—	4.0	4.0	4.0	—
SrO	—	—	—	—	—	—	—	4.0
BaO	—	—	—	—	—	—	—	—
ZnO	—	—	—	—	—	—	—	—
CeO ₂	—	—	—	—	—	—	—	—
Tb ₄ O ₇	—	—	—	—	—	—	—	—
Er ₂ O ₃	—	—	—	—	—	—	—	—
SiO ₂ /Li ₂ O molar ratio	2.4	2.4	1.8	2.0	2.4	3.0	2.4	2.4
Optical properties (after pouring)	transparent	transparent	transparent	transparent	transparent	transparent	transparent	transparent
T _g /° C.	464	475	455	461	468	468	469	466
T _N /° C.	480	500	480	480	490	490	490	490
t _N /min.	10	10	10	10	10	10	10	10
T _C /° C.	700	700	700	700	700	700	700	700
t _C /min.	20	20	20	20	20	20	20	20
Main crystal phase _{RT-XRD}	lithium disilicate	lithium disilicate	lithium disilicate	lithium disilicate	lithium disilicate	lithium disilicate	lithium disilicate	lithium disilicate
Other crystal phases	—	LP, quartz	LP, quartz	—	LP	—	LP, quartz	—
K _{IC} /MPa m ^{1/2}	—	—	1.92	—	—	2.41	—	2.08

Composition	Example								
	9 wt.-%	10 wt.-%	11 wt.-%	12 wt.-%	13 wt.-%	14 wt.-%	15 wt.-%	16 wt.-%	17 wt.-%
SiO ₂	75.1	73.8	78.4	75.4	72.9	73.1	72.4	73.3	67.1
Li ₂ O	15.6	15.3	16.3	15.6	15.1	15.2	15.0	15.2	16.7
P ₂ O ₅	—	3.4	3.3	3.4	3.3	3.4	3.2	3.6	4.8
Al ₂ O ₃	3.6	3.5	—	3.6	5.6	4.2	4.1	3.4	—
ZrO ₂	—	—	—	—	—	—	1.5	—	—
TiO ₂	—	—	—	—	—	0.5	0.5	—	—
MgO	—	—	—	—	—	—	—	—	3.8
CaO	—	—	—	2.0	3.1	—	—	4.5	3.8

TABLE I-continued

SrO	4.1	—	—	—	—	—	—	—	3.8
BaO	—	4.0	—	—	—	—	—	—	—
ZnO	—	—	2.0	—	—	3.6	3.3	—	—
CeO ₂	1.0	—	—	—	—	—	—	—	—
Tb ₄ O ₇	0.3	—	—	—	—	—	—	—	—
Er ₂ O ₃	0.3	—	—	—	—	—	—	—	—
SiO ₂ /Li ₂ O molar ratio	2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4	—
Optical properties (after pouring)	transparent	transparent	transparent	transparent	transparent	transparent	transparent	transparent	transparent
T _g /° C.	460	469	461	472	468	474	490	466	445
T _N /° C.	560	490	500	500	500	500	500	490	470
t _N /min.	10	10	10	10	10	10	10	10	10
T _C /° C.	750	700	600	650	650	650	720	700	650
t _C /min.	30	20	20	20	20	20	20	20	20
Main crystal phase _{RT-XRD}	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate	Lithium disilicate
Other crystal phases	Lithium metasilicate, quartz	LS, LP, quartz, Li ₂ O•Al ₂ O ₃ •7.5SiO ₂	—	—	—	—	—	—	LP
K _{IC} /MPa · m ^{1/2}	—	2.37	—	—	—	—	—	—	—

Although preferred embodiments have been depicted and described in detail herein, it will be apparent to those skilled in the relevant art that various modifications, additions, substitutions, and the like can be made without departing from the spirit of the invention and these are therefore considered to be within the scope of the invention as defined in the claims which follow.

The invention claimed is:

1. Lithium silicate glass ceramic which comprises a divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.4 to 3.1.

2. Lithium silicate glass ceramic according to claim 1, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.4 to 3.0.

3. Glass ceramic according to claim 1, which comprises less than 1.0 wt.-% K₂O.

4. Glass ceramic according to claim 1, which comprises less than 1.0 wt.-% K₂O, Na₂O and mixtures thereof.

5. Glass ceramic according to claim 1, which comprises less than 1.0 wt. % alkali metal oxide other than Li₂O.

6. Glass ceramic according to claim 1, which comprises less than 0.1 wt.-% La₂O₃.

7. Glass ceramic according to claim 1, which comprises the divalent metal oxide or mixtures thereof in an amount of from 0.1 to 15 wt.-%.

8. Lithium silicate glass ceramic which comprises SrO and at least 12.1 wt.-% Li₂O, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.2 to 3.1.

9. Lithium silicate glass ceramic according to claim 1, which comprises less than 5.0 wt.-% BaO.

10. Glass ceramic according to claim 1, which comprises 55.0 to 85.0 wt.-% SiO₂.

11. Glass ceramic according to claim 1, which comprises 12.5 to 20.0 wt.-% Li₂O.

12. Glass ceramic according to claim 1, which comprises 0 to 10.0 wt.-% P₂O₅.

13. Glass ceramic according to claim 1, which comprises at least one of the following components:

Component	wt.-%
SiO ₂	67.5 to 79.0
Li ₂ O	12.5 to 20.0
divalent metal oxide or mixtures	2.0 to 12.0
P ₂ O ₅	0 to 7.0
Al ₂ O ₃	0 to 6.0.

14. Glass ceramic according to claim 1, wherein lithium silicate glass ceramic is excluded which comprises at least 6.1 wt.-% ZrO₂.

15. Glass ceramic according to claim 1, wherein lithium silicate glass ceramic is excluded which comprises at least 8.5 wt.-% transition metal oxide selected from the group consisting of oxides of yttrium, oxides of transition metals with an atomic number from 41 to 79 and mixtures of these oxides.

16. Lithium silicate glass ceramic which comprises a divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.2 to 3.1 and which comprises lithium metasilicate as a main crystal phase.

17. Glass ceramic according to claim 16, which comprises more than 5 vol.-% lithium metasilicate crystals.

18. Glass ceramic according to claim 16, which comprises more than 10 vol.-% lithium metasilicate crystals.

19. Glass ceramic according to claim 16, which comprises more than 15 vol.-% lithium metasilicate crystals.

20. Glass ceramic according to claim 1, which comprises lithium disilicate as a main crystal phase.

21. Lithium silicate glass ceramic which comprises a divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.2 to 3.1 and which comprises more than 10 vol.-% lithium disilicate crystals.

22. Glass ceramic according to claim 21, which comprises more than 20 vol.-% lithium disilicate crystals.

23. Glass ceramic according to claim 21, which comprises more than 30 vol.-% lithium disilicate crystals.

24. Lithium silicate glass ceramic according to claim 1, which has lithium disilicate as a main crystal phase and a fracture toughness, measured as K_{IC} value, of at least 1.9 MPa·m^{0.5}.

13

25. Starting glass, which comprises the components of the glass ceramic according to claim 1.

26. Lithium silicate glass with nuclei which are suitable for forming lithium metasilicate and/or lithium disilicate crystals, wherein the glass comprises the components of the glass ceramic according to claim 1.

27. Glass ceramic according to claim 1, wherein the glass ceramic is present in the form of a powder, a granular material, a blank or a dental restoration.

28. Process for the preparation of the glass ceramic according to claim 1, wherein a starting glass, a glass with nuclei or a glass ceramic with lithium metasilicate as a main crystal phase is subjected to at least one heat treatment in the range of from 450 to 950° C.

29. Process for the preparation of a lithium silicate glass ceramic which comprises a divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O and less than 1.0 wt.-% K₂O, wherein

14

(a) a starting glass is subjected to a heat treatment at a temperature of from 470 to 560° C. for a period of from 10 min to 120 min in order to form the glass with nuclei, and

(b) the glass with nuclei is subjected to a heat treatment at a temperature of from 600 to 750° C. in order to form the glass ceramic with lithium disilicate as main crystal phase.

30. Process according to claim 29, wherein the heat treatment in step (b) is carried out for a period of from 10 min to 120 min.

31. A process of using the glass ceramic according to claim 1 as dental material.

32. A process of using a lithium silicate glass ceramic which comprises a divalent metal oxide selected from MgO, CaO, SrO, BaO, ZnO and mixtures thereof and comprises at least 12.1 wt.-% Li₂O, wherein the molar ratio between SiO₂ and Li₂O is in the range of from 2.2 to 3.1, as dental material, wherein the glass ceramic is shaped by pressing or machining to a desired dental restoration.

* * * * *