

US009783718B2

(12) **United States Patent**  
**Stevenson et al.**

(10) **Patent No.:** **US 9,783,718 B2**  
(45) **Date of Patent:** **Oct. 10, 2017**

(54) **SHAPED ABRASIVE PARTICLES AND METHODS OF FORMING SAME**

(71) Applicant: **Saint-Gobain Ceramics & Plastics, Inc.**, Worcester, MA (US)  
(72) Inventors: **Adam J. Stevenson**, Le Thor (FR); **Amin M'Barki**, Cavaillon (FR); **David Louapre**, Paris (FR); **Doruk O. Yener**, Bedford, MA (US); **Jennifer H. Czerepinski**, Framingham, MA (US); **Nabil Nahas**, Boston, MA (US)  
(73) Assignee: **SAINT-GOBAIN CERAMICS & PLASTICS, INC.**, Worcester, MA (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/502,562**

(22) Filed: **Sep. 30, 2014**

(65) **Prior Publication Data**

US 2015/0089881 A1 Apr. 2, 2015

**Related U.S. Application Data**

(60) Provisional application No. 61/884,474, filed on Sep. 30, 2013.

(51) **Int. Cl.**  
**C09K 3/14** (2006.01)  
**C09C 1/68** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **C09K 3/1409** (2013.01)

(58) **Field of Classification Search**  
None  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

345,604 A	7/1886	Semper
1,910,444 A	5/1933	Nicholson
2,049,874 A	8/1936	Sherk
2,148,400 A	2/1939	Crompton, Jr.
2,248,064 A	7/1941	Carlton et al.
2,248,990 A	7/1941	Heany
2,290,877 A	7/1942	Heany
2,318,360 A	5/1943	Benner et al.
2,376,343 A	5/1945	Carlton
2,563,650 A	8/1951	Heinemann et al.
2,880,080 A	3/1959	Rankin et al.
3,041,156 A	6/1962	Rowse et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CA	743715 A	10/1966
CA	2423788 A1	7/2002

(Continued)

OTHER PUBLICATIONS

S. Kumar and J.P. Kruth. "Composites by rapid prototyping technology" *Materials and Design* 31 (2010; available online Aug. 6, 2009) pp. 850-856.\*


(Continued)

*Primary Examiner* — Kaj K Olsen  
*Assistant Examiner* — Ross J Christie  
(74) *Attorney, Agent, or Firm* — Abel Law Group, LLP; Adam Keser

(57) **ABSTRACT**

A method of forming a shaped abrasive particle having a body formed by an additive manufacturing process.

**19 Claims, 12 Drawing Sheets**



(56)

## References Cited

## U.S. PATENT DOCUMENTS

3,067,551 A	12/1962	Maginnis	4,876,226 A	10/1989	Fuentes
3,079,242 A	2/1963	Glasgow	4,881,951 A	11/1989	Wood et al.
3,079,243 A	2/1963	Ueltz	4,917,852 A	4/1990	Poole et al.
3,123,948 A	3/1964	Kistler et al.	4,918,116 A	4/1990	Gardziella et al.
3,141,271 A	7/1964	Fischer et al.	4,925,815 A	5/1990	Tani et al.
3,276,852 A	10/1966	Lemelson	4,930,266 A	6/1990	Calhoun et al.
3,377,660 A	4/1968	Marshall et al.	4,942,011 A	7/1990	Bolt et al.
3,379,543 A	4/1968	Norwalk	4,954,462 A	9/1990	Wood
3,387,957 A	6/1968	Howard	4,960,441 A	10/1990	Pellow et al.
3,454,385 A	7/1969	Amero	4,961,757 A	10/1990	Rhodes et al.
3,477,180 A	11/1969	Robertson, Jr.	4,963,012 A	10/1990	Tracy
3,480,395 A	11/1969	McMullen et al.	4,964,883 A	10/1990	Morris et al.
3,481,723 A	12/1969	Kistler et al.	4,970,057 A	11/1990	Wilkins et al.
3,491,492 A	1/1970	Ueltz	4,997,461 A	3/1991	Markhoff-Matheny et al.
3,495,359 A	2/1970	Smith et al.	5,009,675 A	4/1991	Kunz et al.
3,536,005 A	10/1970	Derrickson	5,009,676 A	4/1991	Rue et al.
3,590,799 A	7/1971	Guuchowicz	5,011,508 A	4/1991	Wald et al.
3,608,050 A	9/1971	Carman et al.	5,011,510 A	4/1991	Hayakawa et al.
3,608,134 A	9/1971	Cook	5,014,468 A	5/1991	Ravipati et al.
3,615,308 A	10/1971	Amero	5,024,795 A	6/1991	Kennedy et al.
3,619,151 A	11/1971	Sheets, Jr. et al.	5,032,304 A	7/1991	Toyota
3,637,360 A	1/1972	Ueltz	5,035,723 A	7/1991	Kalinowski et al.
3,670,467 A	6/1972	Walker	5,035,724 A	7/1991	Pukari et al.
3,672,934 A	6/1972	Larry	5,042,991 A	8/1991	Kunz et al.
3,819,785 A	6/1974	Argyle et al.	5,049,166 A	9/1991	Kirkendall
3,859,407 A	1/1975	Blanding et al.	5,049,645 A	9/1991	Nagaoka et al.
3,874,856 A	4/1975	Leeds	5,053,367 A	10/1991	Newkirk et al.
3,909,991 A	10/1975	Coes, Jr.	5,053,369 A	10/1991	Winkler et al.
3,940,276 A	2/1976	Wilson	5,076,991 A	12/1991	Poole et al.
3,950,148 A	4/1976	Fukuda	5,078,753 A	1/1992	Broberg et al.
3,960,577 A	6/1976	Prochazka	5,081,082 A	1/1992	Hai-Doo et al.
3,977,132 A	8/1976	Sekigawa	5,085,671 A	2/1992	Martin et al.
3,986,885 A	10/1976	Lankard	5,090,968 A	2/1992	Pellow
3,991,527 A	11/1976	Maran	5,094,986 A	3/1992	Matsumoto et al.
4,004,934 A	1/1977	Prochazka	5,098,740 A	3/1992	Tewari
4,037,367 A	7/1977	Kruse	5,103,598 A	4/1992	Kelly
4,045,919 A	9/1977	Moritomo	5,108,963 A	4/1992	Fu et al.
4,055,451 A	10/1977	Cockbain et al.	5,114,438 A	5/1992	Leatherman et al.
4,073,096 A	2/1978	Ueltz et al.	5,120,327 A	6/1992	Dennis
4,114,322 A	9/1978	Greenspan	5,123,935 A	6/1992	Kanamaru et al.
4,150,078 A	4/1979	Miller et al.	5,129,919 A	7/1992	Kalinowski et al.
4,194,887 A	3/1980	Ueltz et al.	5,131,926 A	7/1992	Rostoker et al.
4,252,544 A	2/1981	Takahashi	5,132,984 A	7/1992	Simpson
4,261,706 A	4/1981	Blanding et al.	5,139,978 A	8/1992	Wood
4,286,905 A	9/1981	Samanta	5,152,917 A	10/1992	Pieper et al.
4,304,576 A	12/1981	Hattori et al.	5,160,509 A	11/1992	Carman et al.
4,314,827 A	2/1982	Leitheiser et al.	5,164,744 A	11/1992	Yoshida et al.
4,341,663 A	7/1982	Derleth et al.	5,173,457 A	12/1992	Shorthouse
4,393,021 A	7/1983	Eisenberg et al.	5,178,849 A	1/1993	Bauer
4,452,911 A	6/1984	Eccles et al.	5,180,630 A	1/1993	Giglia
4,457,767 A	7/1984	Poon et al.	5,185,012 A	2/1993	Kelly
4,469,758 A	9/1984	Scott	5,185,299 A	2/1993	Wood et al.
4,505,720 A	3/1985	Gabor et al.	5,190,568 A	3/1993	Tselesin
4,541,842 A	9/1985	Rostoker	5,194,072 A	3/1993	Rue et al.
4,548,617 A	10/1985	Miyatani et al.	5,201,916 A	4/1993	Berg et al.
4,570,048 A	2/1986	Poole	5,203,886 A	4/1993	Sheldon et al.
4,618,349 A	10/1986	Hashimoto et al.	5,213,591 A	5/1993	Celikkaya et al.
4,623,364 A	11/1986	Cottringer et al.	5,215,552 A	6/1993	Sung
4,656,330 A	4/1987	Poole	5,219,462 A	6/1993	Bruxvoort et al.
4,657,754 A	4/1987	Bauer et al.	5,219,806 A	6/1993	Wood
4,659,341 A	4/1987	Ludwig et al.	5,221,294 A	6/1993	Carman et al.
4,678,560 A	7/1987	Stole et al.	5,224,970 A	7/1993	Harakawa et al.
4,711,750 A	12/1987	Scott	5,227,104 A	7/1993	Bauer
4,728,043 A	3/1988	Ersdal et al.	5,244,477 A	9/1993	Rue et al.
4,744,802 A	5/1988	Schwabel	5,244,849 A	9/1993	Roy et al.
4,770,671 A	9/1988	Monroe	5,273,558 A	12/1993	Nelson et al.
4,786,292 A	11/1988	Janz et al.	5,277,702 A	1/1994	Thibault et al.
4,797,139 A	1/1989	Bauer	5,282,875 A	2/1994	Wood
4,797,269 A	1/1989	Bauer et al.	5,288,297 A	2/1994	Ringwood
4,799,939 A	1/1989	Bloecher et al.	5,300,130 A	4/1994	Rostoker
4,829,027 A	5/1989	Cutler et al.	5,304,331 A	4/1994	Leonard et al.
4,832,706 A	5/1989	Yates	5,312,789 A	5/1994	Wood
4,848,041 A	7/1989	Kruschke	5,312,791 A	5/1994	Coblentz et al.
4,858,527 A	8/1989	Masanao	5,366,523 A	11/1994	Rowenhorst et al.
4,863,573 A	9/1989	Moore et al.	5,366,525 A	11/1994	Fujiyama
			5,372,620 A	12/1994	Rowse et al.
			5,373,786 A	12/1994	Umaba
			5,376,598 A	12/1994	Preedy et al.
			5,376,602 A	12/1994	Nilsen



(56)

References Cited

U.S. PATENT DOCUMENTS

5,383,945 A	1/1995	Cottringer et al.	5,885,311 A	3/1999	McCutcheon et al.
5,395,407 A	3/1995	Cottringer et al.	5,893,935 A	4/1999	Wood
5,409,645 A	4/1995	Torre, Jr. et al.	5,902,647 A	5/1999	Venkataramani
5,429,648 A	7/1995	Wu	5,908,477 A	6/1999	Harmer et al.
5,431,967 A	7/1995	Manthiram	5,908,478 A	6/1999	Wood
5,435,816 A	7/1995	Spurgeon et al.	5,919,549 A	7/1999	Van et al.
5,437,754 A	8/1995	Calhoun	5,924,917 A	7/1999	Benedict et al.
5,441,549 A	8/1995	Helmin	5,946,991 A	9/1999	Hoopman
5,443,603 A	8/1995	Kirkendall	5,975,987 A	11/1999	Hoopman et al.
5,447,894 A	9/1995	Yasuoka et al.	5,980,678 A	11/1999	Tselesin
5,453,106 A	9/1995	Roberts	5,984,988 A	11/1999	Berg et al.
5,454,844 A	10/1995	Hibbard et al.	5,989,301 A	11/1999	Laconto, Sr. et al.
5,470,806 A	11/1995	Krstic et al.	5,997,597 A	12/1999	Hagan
5,479,873 A	1/1996	Shintani et al.	6,016,660 A	1/2000	Abramshe
5,482,756 A	1/1996	Berger et al.	6,019,805 A	2/2000	Herron
5,486,496 A	1/1996	Talbert et al.	6,024,824 A	2/2000	Krech
5,496,386 A	3/1996	Broberg et al.	6,027,326 A	2/2000	Cesarano, III et al.
5,500,273 A	3/1996	Holmes et al.	6,048,577 A	4/2000	Garg
5,514,631 A	5/1996	Cottringer et al.	6,053,956 A	4/2000	Wood
5,516,347 A	5/1996	Garg	6,054,093 A	4/2000	Torre, Jr. et al.
5,516,348 A	5/1996	Conwell et al.	6,080,215 A	6/2000	Stubbs et al.
5,523,074 A	6/1996	Takahashi et al.	6,080,216 A	6/2000	Erickson
5,525,100 A	6/1996	Kelly et al.	6,083,622 A	7/2000	Garg et al.
5,527,369 A	6/1996	Garg	6,096,107 A	8/2000	Caracostas et al.
5,543,368 A	8/1996	Talbert et al.	6,110,241 A	8/2000	Sung
5,551,963 A	9/1996	Larmie	6,129,540 A	10/2000	Hoopman et al.
5,560,745 A	10/1996	Roberts	6,136,288 A	10/2000	Bauer et al.
5,567,150 A	10/1996	Conwell et al.	6,146,247 A	11/2000	Nokubi et al.
5,567,214 A	10/1996	Ashley	6,179,887 B1	1/2001	Barber, Jr. et al.
5,567,251 A	10/1996	Peker et al.	6,206,942 B1	3/2001	Wood
5,571,297 A	11/1996	Swei et al.	6,228,134 B1	5/2001	Erickson
5,576,409 A	11/1996	Mackey	6,238,450 B1	5/2001	Garg et al.
5,578,095 A	11/1996	Bland et al.	6,258,137 B1	7/2001	Garg et al.
5,578,222 A	11/1996	Trischuk et al.	6,258,141 B1	7/2001	Sung et al.
5,582,625 A	12/1996	Wright et al.	6,261,682 B1	7/2001	Law
5,584,896 A	12/1996	Broberg et al.	6,264,710 B1	7/2001	Erickson
5,584,897 A	12/1996	Christianson et al.	6,277,160 B1	8/2001	Stubbs et al.
5,591,685 A	1/1997	Mitomo et al.	6,277,161 B1	8/2001	Castro et al.
5,593,468 A	1/1997	Khaund et al.	6,283,997 B1 *	9/2001	Garg ..... A61F 2/28 623/16.11
5,599,493 A	2/1997	Ito et al.	6,284,690 B1	9/2001	Nakahata et al.
5,603,738 A	2/1997	Zeiringer et al.	6,287,353 B1	9/2001	Celikkaya
5,609,706 A	3/1997	Benedict et al.	6,306,007 B1	10/2001	Mori et al.
5,611,829 A	3/1997	Monroe et al.	6,312,324 B1	11/2001	Mitsui et al.
5,618,221 A	4/1997	Furukawa et al.	6,319,108 B1	11/2001	Adefris et al.
5,628,952 A	5/1997	Holmes et al.	6,331,343 B1	12/2001	Perez et al.
5,641,469 A	6/1997	Garg et al.	6,371,842 B1	4/2002	Romero
RE35,570 E	7/1997	Rowenhorst et al.	6,391,812 B1	5/2002	Araki et al.
5,645,619 A	7/1997	Erickson et al.	6,401,795 B1	6/2002	Cesarano, III et al.
5,651,925 A	7/1997	Ashley et al.	6,403,001 B1	6/2002	Hayashi
5,656,217 A	8/1997	Rogers et al.	6,413,286 B1 *	7/2002	Swei ..... B24D 3/28 51/293
5,667,542 A	9/1997	Law et al.	6,451,076 B1	9/2002	Nevoret et al.
5,669,941 A	9/1997	Peterson	6,475,253 B2	11/2002	Culler et al.
5,669,943 A	9/1997	Horton et al.	6,524,681 B1	2/2003	Seitz et al.
5,672,097 A	9/1997	Hoopman	6,531,423 B1	3/2003	Schwetz et al.
5,672,554 A	9/1997	Mohri et al.	6,537,140 B1	3/2003	Miller et al.
5,683,844 A	11/1997	Mammino	6,579,819 B2	6/2003	Hirosaki et al.
5,702,811 A	12/1997	Ho et al.	6,582,623 B1	6/2003	Grumbine et al.
5,725,162 A	3/1998	Garg et al.	6,583,080 B1	6/2003	Rosenflanz
5,736,619 A	4/1998	Kane et al.	6,599,177 B2 *	7/2003	Nevoret ..... B24D 11/008 451/526
5,738,696 A	4/1998	Wu	6,646,019 B2	11/2003	Perez et al.
5,738,697 A	4/1998	Wu et al.	6,652,361 B1	11/2003	Gash et al.
5,751,313 A	5/1998	Miyashita et al.	6,669,745 B2	12/2003	Prichard et al.
5,759,481 A	6/1998	Pujari et al.	6,685,755 B2	2/2004	Ramanath et al.
5,776,214 A	7/1998	Wood	6,696,258 B1	2/2004	Wei
5,779,743 A	7/1998	Wood	6,702,650 B2	3/2004	Adefris
5,785,722 A	7/1998	Garg et al.	6,737,378 B2	5/2004	Hirosaki et al.
5,810,587 A	9/1998	Bruns et al.	6,749,496 B2	6/2004	Mota et al.
5,820,450 A	10/1998	Calhoun	6,755,729 B2	6/2004	Ramanath et al.
5,830,248 A	11/1998	Christianson et al.	6,833,014 B2	12/2004	Welygan et al.
5,840,089 A	11/1998	Chesley et al.	6,843,815 B1	1/2005	Thurber et al.
5,849,646 A	12/1998	Stout et al.	6,846,795 B2	1/2005	Lant et al.
5,855,997 A	1/1999	Amateau	6,878,456 B2	4/2005	Castro et al.
5,863,306 A	1/1999	Wei et al.	6,881,483 B2	4/2005	McArdle et al.
5,866,254 A	2/1999	Peker et al.	6,888,360 B1	5/2005	Connell et al.
5,876,793 A	3/1999	Sherman et al.	6,893,489 B2 *	5/2005	Lem ..... B05D 3/06 106/31.64



(56)	<b>References Cited</b>		2003/0116747 A1*	6/2003	Lem .....	B05D 3/06 427/180
	U.S. PATENT DOCUMENTS		2003/0126800 A1	7/2003	Seth et al.	
			2004/0003895 A1	1/2004	Amano et al.	
6,913,824 B2	7/2005	Culler et al.	2004/0018107 A1*	1/2004	Khoshnevis .....	B22F 3/008 419/6
6,942,561 B2	9/2005	Mota et al.				
6,949,128 B2	9/2005	Annen	2004/0148868 A1	8/2004	Anderson et al.	
6,974,930 B2	12/2005	Jense	2004/0148967 A1	8/2004	Celikkaya et al.	
7,022,179 B1	4/2006	Dry	2004/0202844 A1	10/2004	Wong	
7,044,989 B2	5/2006	Welygan et al.	2004/0224125 A1	11/2004	Yamada et al.	
7,141,522 B2	11/2006	Rosenflanz et al.	2004/0235406 A1	11/2004	Duescher	
7,168,267 B2	1/2007	Rosenflanz et al.	2004/0244675 A1	12/2004	Kishimoto et al.	
7,169,198 B2	1/2007	Moeltgen et al.	2005/0020190 A1	1/2005	Schutz et al.	
7,267,700 B2	9/2007	Collins et al.	2005/0060941 A1	3/2005	Provow et al.	
7,294,158 B2	11/2007	Welygan et al.	2005/0060947 A1	3/2005	McArdle et al.	
7,297,170 B2	11/2007	Welygan et al.	2005/0064805 A1	3/2005	Culler et al.	
7,297,402 B2	11/2007	Evans et al.	2005/0081455 A1	4/2005	Welygan et al.	
7,364,788 B2	4/2008	Kishbaugh et al.	2005/0118939 A1	6/2005	Duescher	
7,373,887 B2	5/2008	Jackson	2005/0132655 A1	6/2005	Anderson et al.	
7,384,437 B2	6/2008	Welygan et al.	2005/0168507 A1*	8/2005	Ide .....	B41J 19/147 347/12
7,488,544 B2	2/2009	Schofalvi et al.				
7,507,268 B2	3/2009	Rosenflanz	2005/0218565 A1	10/2005	DiChiara, Jr.	
7,553,346 B2*	6/2009	Welygan .....	2005/0223649 A1	10/2005	O'Gary et al.	
		B24D 3/002 451/526	2005/0232853 A1	10/2005	Evans et al.	
7,556,558 B2	7/2009	Palmgren	2005/0245179 A1	11/2005	Luedeke	
7,560,062 B2	7/2009	Gould et al.	2005/0255801 A1	11/2005	Pollasky	
7,560,139 B2	7/2009	Thebault et al.	2005/0266221 A1	12/2005	Karam et al.	
7,563,293 B2	7/2009	Rosenflanz	2005/0271795 A1	12/2005	Moini et al.	
7,611,795 B2	11/2009	Aoyama et al.	2005/0284029 A1	12/2005	Bourlier et al.	
7,618,684 B2	11/2009	Nesbitt	2006/0049540 A1	3/2006	Hui et al.	
7,662,735 B2	2/2010	Rosenflanz et al.	2006/0126265 A1	6/2006	Crespi et al.	
7,666,344 B2	2/2010	Schofalvi et al.	2006/0135050 A1	6/2006	Petersen et al.	
7,666,475 B2	2/2010	Morrison	2006/0177488 A1	8/2006	Caruso et al.	
7,669,658 B2	3/2010	Barron et al.	2006/0185256 A1*	8/2006	Nevoret .....	B24D 5/00 51/298
7,670,679 B2	3/2010	Krishna et al.				
7,695,542 B2	4/2010	Drivdahl et al.	2007/0020457 A1	1/2007	Adefris	
7,858,189 B2	12/2010	Wagener et al.	2007/0051355 A1	3/2007	Sung	
7,906,057 B2	3/2011	Zhang et al.	2007/0072527 A1	3/2007	Palmgren	
7,968,147 B2	6/2011	Fang et al.	2007/0074456 A1	4/2007	Orlhac et al.	
7,972,430 B2	7/2011	Millard et al.	2007/0087928 A1	4/2007	Rosenflanz et al.	
8,021,449 B2	9/2011	Seth et al.	2007/0234646 A1	10/2007	Can et al.	
8,034,137 B2	10/2011	Erickson et al.	2008/0006334 A1*	1/2008	Davidson .....	B29C 67/0077 137/571
8,049,136 B2	11/2011	Mase et al.				
8,070,556 B2	12/2011	Kumar et al.	2008/0017053 A1	1/2008	Araumi et al.	
8,123,828 B2	2/2012	Culler et al.	2008/0121124 A1	5/2008	Sato	
8,141,484 B2	3/2012	Ojima et al.	2008/0172951 A1	7/2008	Starling	
8,142,531 B2	3/2012	Adefris et al.	2008/0176075 A1	7/2008	Bauer et al.	
8,142,532 B2	3/2012	Erickson et al.	2008/0179783 A1	7/2008	Liu et al.	
8,142,891 B2	3/2012	Culler et al.	2008/0230951 A1	9/2008	Dannoux et al.	
8,251,774 B2	8/2012	Joseph et al.	2008/0262577 A1	10/2008	Altshuler et al.	
8,256,091 B2	9/2012	Duescher	2008/0286590 A1	11/2008	Besida et al.	
8,440,602 B2	5/2013	Gonzales et al.	2008/0299875 A1	12/2008	Duescher	
8,440,603 B2	5/2013	Gonzales et al.	2009/0016916 A1	1/2009	Rosenzweig et al.	
8,445,422 B2	5/2013	Gonzales et al.	2009/0017736 A1	1/2009	Block et al.	
8,470,759 B2	6/2013	Gonzales et al.	2009/0165394 A1	7/2009	Culler et al.	
8,480,772 B2	7/2013	Welygan et al.	2009/0165661 A1	7/2009	Koenig et al.	
8,628,597 B2	1/2014	Palmgren et al.	2009/0208734 A1	8/2009	Macfie et al.	
8,783,589 B2	7/2014	Hart et al.	2009/0246464 A1	10/2009	Watanabe et al.	
8,852,643 B2	10/2014	Gonzales et al.	2010/0000159 A1	1/2010	Walia et al.	
9,017,439 B2	4/2015	Yener et al.	2010/0003900 A1	1/2010	Sakaguchi et al.	
2001/0027623 A1	10/2001	Rosenflanz	2010/0003904 A1	1/2010	Duescher	
2002/0026752 A1	3/2002	Culler et al.	2010/0040767 A1*	2/2010	Uibel .....	A61C 5/70 427/2.27
2002/0084290 A1*	7/2002	Materna .....				
		B01L 3/0241 222/420	2010/0056816 A1	3/2010	Wallin et al.	
2002/0090891 A1	7/2002	Adefris et al.	2010/0068974 A1	3/2010	Dumm	
2002/0151265 A1	10/2002	Adefris	2010/0146867 A1	6/2010	Boden et al.	
2002/0170236 A1	11/2002	Larson et al.	2010/0151195 A1	6/2010	Culler et al.	
2002/0174935 A1	11/2002	Burdon et al.	2010/0151196 A1	6/2010	Adefris et al.	
2002/0176793 A1*	11/2002	Moussa .....	2010/0151201 A1	6/2010	Erickson et al.	
		B22F 1/0059 419/35	2010/0173167 A1*	7/2010	Vissing .....	B05D 3/06 428/447
2002/0177391 A1	11/2002	Fritz et al.				
2003/0008933 A1	1/2003	Perez et al.	2010/0190424 A1	7/2010	Francois et al.	
2003/0022961 A1	1/2003	Kusaka et al.	2010/0201018 A1	8/2010	Yoshioka et al.	
2003/0029094 A1	2/2003	Moeltgen et al.	2010/0292428 A1	11/2010	Meador et al.	
2003/0085204 A1	5/2003	Lagos	2010/0307067 A1	12/2010	Sigalas et al.	
2003/0099708 A1*	5/2003	Rowe .....	2010/0319269 A1	12/2010	Erickson	
		A61J 3/10 424/469	2010/0321448 A1*	12/2010	Buestgens .....	B41J 2/14 347/68
2003/0109371 A1	6/2003	Pujari et al.				
2003/0110707 A1	6/2003	Rosenflanz et al.				



(56)

References Cited

U.S. PATENT DOCUMENTS

2011/0008604 A1 1/2011 Boylan  
 2011/0111563 A1 5/2011 Yanagi et al.  
 2011/0124483 A1 5/2011 Shah et al.  
 2011/0136659 A1 6/2011 Allen et al.  
 2011/0146509 A1 6/2011 Welygan et al.  
 2011/0160104 A1 6/2011 Wu et al.  
 2011/0244769 A1 10/2011 David et al.  
 2011/0289854 A1 12/2011 Moren et al.  
 2011/0314746 A1 12/2011 Erickson et al.  
 2012/0000135 A1 1/2012 Eilers et al.  
 2012/0055098 A1 3/2012 Ramanath et al.  
 2012/0137597 A1 6/2012 Adefris et al.  
 2012/0144754 A1 6/2012 Culler et al.  
 2012/0144755 A1 6/2012 Erickson et al.  
 2012/0153547 A1 6/2012 Bauer et al.  
 2012/0167481 A1 7/2012 Yener et al.  
 2012/0168979 A1 7/2012 Bauer et al.  
 2012/0227333 A1 9/2012 Adefris et al.  
 2012/0231711 A1 9/2012 Keipert et al.  
 2012/0308837 A1\* 12/2012 Schlechtriemen ..... B28B 1/001  
 428/446  
 2013/0000212 A1 1/2013 Wang et al.  
 2013/0000216 A1 1/2013 Wang et al.  
 2013/0009484 A1 1/2013 Yu  
 2013/0036402 A1 2/2013 Mutisya et al.  
 2013/0045251 A1 2/2013 Cen et al.  
 2013/0067669 A1 3/2013 Gonzales et al.  
 2013/0072417 A1 3/2013 Perez-Prat et al.  
 2013/0074418 A1 3/2013 Panzarella et al.  
 2013/0125477 A1 5/2013 Adefris  
 2013/0180180 A1 7/2013 Yener et al.  
 2013/0186005 A1 7/2013 Kavanaugh  
 2013/0186006 A1 7/2013 Kavanaugh et al.  
 2013/0199105 A1 8/2013 Braun et al.  
 2013/0236725 A1 9/2013 Yener et al.  
 2013/0255162 A1 10/2013 Welygan et al.  
 2013/0267150 A1 10/2013 Seider et al.  
 2013/0283705 A1 10/2013 Fischer et al.  
 2013/0305614 A1 11/2013 Gaeta et al.  
 2013/0337262 A1 12/2013 Bauer et al.  
 2013/0337725 A1 12/2013 Monroe  
 2014/0000176 A1 1/2014 Moren et al.  
 2014/0007518 A1 1/2014 Yener et al.  
 2014/0080393 A1 3/2014 Ludwig  
 2014/0106126 A1 4/2014 Gaeta et al.  
 2014/0182216 A1 7/2014 Panzarella et al.  
 2014/0182217 A1 7/2014 Yener et al.  
 2014/0186585 A1 7/2014 Field, III et al.  
 2014/0250797 A1 9/2014 Yener et al.  
 2014/0290147 A1 10/2014 Seth et al.  
 2014/0352721 A1 12/2014 Gonzales et al.  
 2014/0352722 A1 12/2014 Gonzales et al.  
 2014/0357544 A1 12/2014 Gonzales et al.  
 2014/0378036 A1 12/2014 Cichowlas et al.  
 2015/0000209 A1 1/2015 Louapre et al.  
 2015/0000210 A1 1/2015 Breder et al.  
 2015/0007399 A1 1/2015 Gonzales et al.  
 2015/0007400 A1 1/2015 Gonzales et al.  
 2015/0126098 A1 5/2015 Eilers et al.  
 2015/0128505 A1 5/2015 Wang et al.  
 2015/0183089 A1 7/2015 Iyengar et al.  
 2015/0218430 A1 8/2015 Yener et al.  
 2015/0232727 A1 8/2015 Erickson  
 2015/0291865 A1 10/2015 Breder et al.  
 2015/0291866 A1 10/2015 Arcona et al.  
 2015/0291867 A1 10/2015 Breder et al.  
 2015/0343603 A1 12/2015 Breder et al.  
 2016/0177152 A1 6/2016 Braun  
 2016/0177153 A1 6/2016 Josseaux  
 2016/0177154 A1 6/2016 Josseaux et al.  
 2016/0186028 A1 6/2016 Louapare et al.  
 2016/0214903 A1 7/2016 Humpal et al.  
 2016/0298013 A1 10/2016 Bock et al.  
 2016/0303704 A1 10/2016 Chou et al.  
 2016/0303705 A1 10/2016 Chou et al.

2016/0304760 A1 10/2016 Bock et al.  
 2016/0311081 A1 10/2016 Culler et al.  
 2016/0311084 A1 10/2016 Culler et al.  
 2016/0326416 A1 11/2016 Bauer et al.  
 2016/0340564 A1 11/2016 Louapre et al.  
 2016/0354898 A1 12/2016 Nienaber et al.  
 2016/0362589 A1 12/2016 Bauer et al.  
 2017/0066099 A1 3/2017 Nakamura

FOREIGN PATENT DOCUMENTS

CH 685051 A5 3/1995  
 CN 102123837 B 7/2014  
 DE 102012023688 A1 4/2014  
 DE 202014101739 U1 6/2014  
 DE 202014101741 U1 6/2014  
 DE 102013202204 A1 8/2014  
 DE 102013210158 A1 12/2014  
 DE 102013210716 A1 12/2014  
 DE 102013212598 A1 12/2014  
 DE 102013212622 A1 12/2014  
 DE 102013212634 A1 12/2014  
 DE 102013212639 A1 12/2014  
 DE 102013212644 A1 12/2014  
 DE 102013212653 A1 12/2014  
 DE 102013212654 A1 12/2014  
 DE 102013212661 A1 12/2014  
 DE 102013212666 A1 12/2014  
 DE 102013212677 A1 12/2014  
 DE 102013212680 A1 12/2014  
 DE 102013212687 A1 12/2014  
 DE 102013212690 A1 12/2014  
 DE 102013212700 A1 12/2014  
 DE 102014210836 A1 12/2014  
 EP 0078896 A2 5/1983  
 EP 0152768 A3 9/1987  
 EP 0293163 A2 11/1988  
 EP 0480133 A2 4/1992  
 EP 0652919 A1 5/1995  
 EP 0662110 A1 7/1995  
 EP 0500369 B1 1/1996  
 EP 0609864 B1 11/1996  
 EP 0771769 5/1997  
 EP 0812456 B1 12/1997  
 EP 0651778 B1 5/1998  
 EP 0614861 B1 5/2001  
 EP 0931032 B1 7/2001  
 EP 0833803 8/2001  
 EP 1356152 A2 10/2003  
 EP 1371451 A1 12/2003  
 EP 1383631 B1 1/2004  
 EP 1015181 B1 3/2004  
 EP 1492845 A1 1/2005  
 EP 1851007 A1 11/2007  
 EP 1960157 A1 8/2008  
 EP 2176031 A1 4/2010  
 EP 2184134 A1 5/2010  
 EP 2390056 A2 11/2011  
 EP 1800801 B1 3/2012  
 EP 2537917 A1 12/2012  
 EP 2567784 A1 3/2013  
 EP 2631286 A1 8/2013  
 EP 2692813 A1 2/2014  
 EP 2692814 A1 2/2014  
 EP 2692815 A1 2/2014  
 EP 2692816 A1 2/2014  
 EP 2692817 A1 2/2014  
 EP 2692818 A1 2/2014  
 EP 2692819 A1 2/2014  
 EP 2692820 A1 2/2014  
 EP 2692821 A1 2/2014  
 EP 2719752 A1 4/2014  
 EP 2720676 A1 4/2014  
 EP 2012972 B1 6/2014  
 FR 2354373 A1 1/1978  
 GB 986847 A 3/1965  
 JP 53064890 A 6/1978  
 JP 60-006356 U 1/1985  
 JP 62002946 B 1/1987



(56)

## References Cited

## FOREIGN PATENT DOCUMENTS

JP 63036905 B 7/1988  
 JP 3079277 A 4/1991  
 JP 03-287687 12/1991  
 JP 5285833 A 11/1993  
 JP 6114739 A 4/1994  
 JP 7008474 B2 2/1995  
 JP 10113875 A 5/1998  
 JP 2779252 B2 7/1998  
 JP 10330734 A 12/1998  
 JP H10315142 A 12/1998  
 JP 2957492 B2 10/1999  
 JP 2000091280 A 3/2000  
 JP 2000-336344 A 12/2000  
 JP 3160084 B2 4/2001  
 JP 2001162541 A 6/2001  
 JP 03194269 B2 7/2001  
 JP 2001207160 A 7/2001  
 JP 2002-038131 A 2/2002  
 JP 2003-049158 A 2/2003  
 JP 2004-510873 A 4/2004  
 JP 2004209624 A 7/2004  
 JP 2006159402 A 6/2006  
 JP 2006-192540 A 7/2006  
 JP 2008017305 A 1/2008  
 JP 2008132560 A 6/2008  
 JP 2008194761 A 8/2008  
 JP 5238725 B2 7/2013  
 JP 5238726 B2 7/2013  
 NL 171464 B 11/1982  
 WO 9402559 A1 2/1994  
 WO 95/03370 2/1995  
 WO 95/18192 A1 7/1995  
 WO 9520469 A1 8/1995  
 WO 96/27189 A1 9/1996  
 WO 9714536 A1 4/1997  
 WO 9906500 A1 2/1999  
 WO 99/38817 A1 8/1999  
 WO 9938817 A1 8/1999  
 WO 9954424 A1 10/1999  
 WO 01/14494 A1 3/2001  
 WO 02097150 12/2002  
 WO 03/087236 A1 10/2003  
 WO 2005/080624 A1 9/2005  
 WO 2006/027593 3/2006  
 WO 2006/091519 A1 11/2006  
 WO 2007/041538 A1 4/2007  
 WO 2009085578 A2 7/2009  
 WO 2010/077509 A1 7/2010  
 WO 2010085587 A1 7/2010  
 WO 2010/151201 12/2010  
 WO 2011/068724 A2 6/2011  
 WO 2011068714 A2 6/2011  
 WO 2011087649 A2 7/2011  
 WO 2011/109188 A2 9/2011  
 WO 2011/139562 A2 11/2011  
 WO 2011/149625 A2 12/2011  
 WO 2012/018903 A2 2/2012  
 WO 2012/061016 A1 5/2012  
 WO 2012/061033 A2 5/2012  
 WO 2012/092590 A2 7/2012  
 WO 2012/092605 A2 7/2012  
 WO 2012/112305 A2 8/2012  
 WO 2012/112322 A2 8/2012  
 WO 2012/141905 A2 10/2012  
 WO 2013/003830 A2 1/2013  
 WO 2013/003831 A2 1/2013  
 WO 2013/009484 A2 1/2013  
 WO 2013/036402 A1 3/2013  
 WO 2013/045251 A1 4/2013  
 WO 2013/049239 A1 4/2013  
 WO 2013070576 A2 5/2013  
 WO 2013/102170 A1 7/2013  
 WO 2013/102176 A1 7/2013  
 WO 2013/102177 A1 7/2013  
 WO 2013/106597 A1 7/2013

WO 2013/106602 A1 7/2013  
 WO 2013/151745 A1 10/2013  
 WO 2013/177446 A1 11/2013  
 WO 2013/188038 A1 12/2013  
 WO 2014/005120 A1 1/2014  
 WO 2014/161001 A1 2/2014  
 WO 2014020068 A1 2/2014  
 WO 2014020075 A1 2/2014  
 WO 2014022453 A1 2/2014  
 WO 2014022462 A1 2/2014  
 WO 2014022465 A1 2/2014  
 WO 2014/057273 A1 4/2014  
 WO 2014/062701 A1 4/2014  
 WO 2014/070468 A1 5/2014  
 WO 2014/106173 A1 7/2014  
 WO 2014/106211 A1 7/2014  
 WO 2014/124554 A1 8/2014  
 WO 2014/137972 A1 9/2014  
 WO 2014/140689 A1 9/2014  
 WO 2014/165390 A1 10/2014  
 WO 2014/176108 A1 10/2014  
 WO 2014/206739 A1 12/2014  
 WO 2014/206890 A1 12/2014  
 WO 2014/206967 A1 12/2014  
 WO 2014/209567 A1 12/2014  
 WO 2014/210160 A1 12/2014  
 WO 2014/210442 A1 12/2014  
 WO 2014/210532 A1 12/2014  
 WO 2014/210568 A1 12/2014  
 WO 2015/050781 A1 4/2015  
 WO 2015/073346 A1 5/2015  
 WO 2015/088953 A1 6/2015  
 WO 2015/089527 A1 6/2015  
 WO 2015/089528 A1 6/2015  
 WO 2015/089529 A1 6/2015  
 WO 2015/100018 A1 7/2015  
 WO 2015/100020 A1 7/2015  
 WO 2015/100220 A1 7/2015  
 WO 2015/112379 A1 7/2015  
 WO 2015/130487 A1 9/2015  
 WO 2015/158009 A1 10/2015  
 WO 2015/164211 A1 10/2015  
 WO 2015/165122 A1 11/2015  
 WO 2015/167910 A1 11/2015  
 WO 2015/179335 A1 11/2015  
 WO 2015/180005 A1 12/2015  
 WO 2016/028683 A1 2/2016  
 WO 2016/044158 A1 3/2016  
 WO 2016/064726 A1 4/2016  
 WO 2016/089675 A1 6/2016  
 WO 2016/160357 A1 10/2016  
 WO 2016/161157 A1 10/2016  
 WO 2016/161170 A1 10/2016  
 WO 2016/167967 A1 10/2016  
 WO 2016/196795 A1 12/2016  
 WO 2016/205133 A1 12/2016  
 WO 2016/205267 A1 12/2016  
 WO 2016/210057 A1 12/2016  
 WO 2017/007703 A1 1/2017  
 WO 2017/007714 A1 1/2017  
 WO 2017/062482 A1 4/2017

## OTHER PUBLICATIONS

Jennifer A. Lewis, "Colloidal Processing of Ceramics," J. Am. Ceram. Soc., vol. 83 No. 10, pp. 2341-2359, Oct. 2000.  
 Jennifer A. Lewis, "Direct Ink Writing of 3D Functional Materials," Advanced Functional Materials, 16, pp. 2193-2204, 2006.  
 Kiran Yadav et al., "Shear Reversible Alumina Gels for Direct Writing," J. Am. Ceram. Soc., Manuscript No. 34400, pp. 1-6, Jan. 2014.  
 "Investigation of Shaped Abrasive Particles vol. 1: Review of U.S. Pat. No. 6,054,093 Apr. 25, 2000" © Apr. 2011, 5 pages.  
 Austin, Benson M., "Thick-Film Screen Printing," Solid State Technology, Jun. 1969, pp. 53-58.  
 Avril, Nicholas Joseph, "Manufacturing Glass-fiber Reinforcement for Grinding Wheels," Massachusetts Institute of Technology, 1996, 105 pgs.

(56)

**References Cited**

## OTHER PUBLICATIONS

Bacher, Rudolph J., "High Resolution Thick Film Printing," E.I. du Pont de Nemours & Company, Inc., pp. 576-581, date unknown.

Besse, John R., "Understanding and controlling wheel truing and dressing forces when rotary plunge dressing," *Cutting Tool Engineering*, Jun. 2012, vol. 64, Issue 6, 5 pages.

Brewer, L. et al., *Journal of Materials Research*, 1999, vol. 14, No. 10, pp. 3907-3912.

Ciccotti, M. et al., "Complex dynamics in the peeling of an adhesive tape," *International Journal of Adhesion & Adhesives* 24 (2004) pp. 143-151.

Dupont, "Kevlar Aramid Pulp", Copyright 2011, DuPont, 1 page.

Wu, J. et al., "Friction and Wear Properties of Kevlar Pulp Reinforced Epoxy," Jun. 2006.

J. European Ceramic Society 31, Abstract only (2011) 2073-2081.

Riemer, Dietrich E., "Analytical Engineering Model of the Screen Printing Process: Part II," *Solid State Technology*, Sep. 1988, pp. 85-90.

Miller, L.F., "Paste Transfer in the Screening Process," *Solid State Technology*, Jun. 1969, pp. 46-52.

Morgan, P. et al., "Ceramic Composites of Monazite and Alumina," *J. Am. Ceram. Soc.*, 78, 1995, 1553-63.

Riemer, Dietrich E., "Analytical Engineering Model of the Screen Printing Process: Part I," *Solid State Technology*, Aug. 1988, pp. 107-111.

Winter Catalogue No. 5, Dressing tools, WINTER diamond tools for dressing grinding wheels, 140 pages, Edition 2010.

Badger, Jeffrey, "Evaluation of Triangular, Engineered-Shape Ceramic Abrasive in Cutting Discs," Supplement to the *Welding Journal*, Apr. 2014, vol. 93, pp. 107-s to 115-s.

3M Cubitron II Abrasive Belts Brochure, Shaping the Future, Jan. 2011, 6 pages.

Vanstrum et al., Precisely Shaped Grain (PSG): 3M's Innovation in Abrasive Grain Technology, date unknown, 1 page.

Graf, "Cubitron II: Precision-Shaped Grain (PSG) Turns the Concept of Gear Grinding Upside Down," *gearsolutions.com*, May 2014, pp. 36-44.

DOW Machine Tool Accessories, Grinding & Surface Finishing, [www.lmta.com](http://www.lmta.com), Nov. 2014, 72 pages.

International Search Report and Written Opinion for Application No. PCT/US2014/058378, filed Sep. 30, 2014, 18 pages, Jan. 29, 2015.

European Search Report from EP 14 84 7751, dated Mar. 29, 2017, 1 page.

Lewis et al.; "Direct Ink Writing of Three-Dimensional Ceramic Structures;" *J. Am. Ceram. Soc.*; vol. 89; No. 12; pp. 3599-3609; Dec. 2006.

\* cited by examiner




FIG. 1A




FIG. 1B






FIG. 1C




FIG. 1D




FIG. 1E




FIG. 2






FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8






FIG. 9







**FIG. 10**




**FIG. 11**




**FIG. 12**




**FIG. 13**




**FIG. 14**




**FIG. 15**




**FIG. 16**



**FIG. 17**



**FIG. 18**



**FIG. 19**






FIG. 20




FIG. 21






FIG. 22






FIG. 23










FIG. 26




FIG. 27






FIG. 28




FIG. 29




FIG. 30



## SHAPED ABRASIVE PARTICLES AND METHODS OF FORMING SAME

### CROSS-REFERENCE TO RELATED APPLICATION(S)

This application claims priority under 35 U.S.C. §119(e) to U.S. Patent Application No. 61/884,474 entitled "Shaped Abrasive Particles and Methods of Forming Same," by Doruk O. Yener, filed Sep. 30, 2013, which is assigned to the current assignee hereof and incorporated herein by reference in its entirety.

### BACKGROUND

#### Field of the Disclosure

The following is directed to shaped abrasive particles and, more particularly, to a process of forming shaped abrasive particles using an additive manufacturing process.

#### Description of the Related Art

Abrasive articles incorporating ceramic articles such as abrasive particles are useful for various material removal operations including grinding, finishing, polishing, and the like. Depending upon the type of abrasive material, such abrasive particles can be useful in shaping or grinding various materials in the manufacturing of goods. Certain types of abrasive particles have been formulated to date that have particular geometries, such as triangular shaped abrasive particles and abrasive articles incorporating such objects. See, for example, U.S. Pat. Nos. 5,201,916; 5,366,523; and 5,984,988.

Previously, three basic technologies have been employed to produce abrasive particles having a specified shape, including fusion, sintering, and chemical ceramic. In the fusion process, abrasive particles can be shaped by a chill roll, the face of which may or may not be engraved, a mold into which molten material is poured, or a heat sink material immersed in an aluminum oxide melt. See, for example, U.S. Pat. No. 3,377,660. In sintering processes, abrasive particles can be formed from refractory powders having a particle size of up to 10 micrometers in diameter. Binders can be added to the powders along with a lubricant and a suitable solvent to form a mixture that can be shaped into platelets or rods of various lengths and diameters. See, for example, U.S. Pat. No. 3,079,242. Chemical ceramic technology involves converting a colloidal dispersion or hydro-sol (sometimes called a sol) to a gel or any other physical state that restrains the mobility of the components, drying, and firing to obtain a ceramic material. See, for example, U.S. Pat. Nos. 4,744,802 and 4,848,041.

Rudimentary molding processes have been disclosed as potentially useful in forming limited shaped abrasive particles, such as those disclosed in U.S. Pat. Nos. 5,201,916, 5,366,523, 5,584,896, and U.S. Pat. Publs. 2010/0151195, 2010/0151196. Other processes of forming shaped abrasive particles have been disclosed, see for example, U.S. Pat. Nos. 6,054,093, 6,228,134, 5,009,676, 5,090,968, and 5,409,645.

The industry continues to demand improved abrasive materials and abrasive articles including shaped abrasive particles.

### SUMMARY

According to one aspect, a method of forming a shaped abrasive particle includes having a body formed by an additive manufacturing process.

According to a second aspect, a method includes forming a body of a shaped abrasive particle according to a digital model.

In yet another aspect, a method of forming a fixed abrasive includes forming a plurality of shaped abrasive particles on a substrate, wherein each of the shaped abrasive particles of the plurality of shaped abrasive particles have a body formed by an additive manufacturing process.

According to another aspect, a shaped abrasive particle includes a body having at least one major surface having a self-similar feature.

For still another aspect, a shaped abrasive particle has a body having at least one peripheral ridge extending around at least a portion of a side surface of the body.

In one aspect, a shaped abrasive particle has a body having at least one major surface defining a concave stepped surface.

For another aspect, a shaped abrasive particle has a body having at least one transverse ridge extending along at least two surfaces and an adjoining edge between the at least two surfaces.

According to one aspect, a shaped abrasive particle includes a body having a corner including a plurality of microprotrusions extending from the corner.

For still another aspect, a shaped abrasive particle has a body including a surface comprising a scalloped topography.

According to another aspect, a method of forming a shaped abrasive particle includes using a low pressure injection molding process.

### BRIEF DESCRIPTION OF THE DRAWINGS

The present disclosure may be better understood, and its numerous features and advantages made apparent to those skilled in the art, by referencing the accompanying drawings. Embodiments are illustrated by way of example and are not limited in the accompanying figures.

FIG. 1A includes a perspective view illustration of a method of forming a portion of a shaped abrasive particle in accordance with an embodiment.

FIG. 1B includes an illustration of a system and method of forming a portion of a shaped abrasive particle in accordance with an embodiment.

FIG. 1C includes an illustration of a filling pattern according to an embodiment.

FIG. 1D includes an illustration of filling pattern according to an embodiment.

FIG. 1E includes an illustration of an end of a nozzle according to an embodiment.

FIG. 2 includes a perspective view illustration of an abrasive article including shaped abrasive particles according to an embodiment.

FIG. 3 includes a side view of a shaped abrasive particle and percentage flashing according to an embodiment.

FIG. 4 includes a cross-sectional illustration of a portion of a coated abrasive article according to an embodiment.

FIG. 5 includes a cross-sectional illustration of a portion of a coated abrasive article according to an embodiment.

FIGS. 6-19 include illustrations of shaped abrasive particles according to an embodiment.

FIG. 20 includes a perspective view illustration of a shaped abrasive particle according to an embodiment.

FIG. 21 includes a top view of a major surface of the shaped abrasive particle of FIG. 20.

FIG. 22 includes a top view image of a portion of the shaped abrasive particle of FIG. 20.



FIG. 23 includes a portion of a major surface of the shaped abrasive particle of FIG. 20.

FIG. 24 includes a side view image of a portion of a shaped abrasive particle according to an embodiment.

FIG. 25 includes an image of a portion of a corner of a shaped abrasive particle according to an embodiment herein.

FIG. 26 includes an image of a portion of a surface of a shaped abrasive particle having a scalloped topography according to an embodiment.

FIG. 27 includes a top-down image of a shaped abrasive particle according to an embodiment.

FIG. 28 includes a top-down view of a shaped abrasive particle according to an embodiment.

FIG. 29 includes a side-view image of the shaped abrasive particle of FIG. 28.

FIG. 30 includes an image of a corner of a shaped abrasive particle according to an embodiment.

The use of the same reference symbols in different drawings indicates similar or identical items. Further, skilled artisans appreciate that elements in the figures are illustrated for simplicity and clarity and have not necessarily been drawn to scale. For example, the dimensions of some of the elements in the figures may be exaggerated relative to other elements to help to improve understanding of embodiments of the invention.

#### DETAILED DESCRIPTION

The following is generally directed to a method of forming a shaped abrasive particle utilizing an additive manufacturing process. The shaped abrasive particles can be used in a variety of industries including, but not limited to, automotive, medical, construction, foundry, aerospace, abrasives, and the like. Such shaped abrasive particles may be utilized as free abrasive particles or incorporated into fixed abrasive articles including, for example, coated abrasive articles, bonded abrasive articles, and the like. Various other uses may be derived for the shaped abrasive particles.

In accordance with one aspect, the shaped abrasive particles of the embodiments herein can be formed to have a body formed by an additive manufacturing process. As used herein, an “additive manufacturing process” includes a process, wherein the body of the shaped abrasive particle can be formed by compiling a plurality of portions together in a particular orientation with respect to each other such that, when the plurality is compiled, each of the discrete portions can define at least a portion of the shape of the body. Moreover, in particular instances, the additive manufacturing process can be a template-free process, wherein the material being manipulated to form discrete portions, and ultimately the body itself, need not be placed within a template (e.g., a mold). Rather, the material being manipulated can be deposited in discrete portions, wherein each of the discrete portions has a controlled dimension such that when the plurality is compiled, the body also has a controlled dimension. Therefore, unlike typical molding operations, additive manufacturing processes of the embodiments herein may not necessarily need to incorporate a template that is configured to contain the material being manipulated to form the body.

In particular instances, an additive manufacturing process that is used to form a shaped abrasive particle can be a prototype printing process. In more particular instances, the process of forming the shaped abrasive particle can include a prototype printing of a body of the shaped abrasive particle, where the shaped abrasive particle includes a shaped abrasive particle or a precursor shaped abrasive

particle. In other instances, the additive manufacturing process may include or be considered a laminated object manufacturing process. In the laminated object manufacturing process, individual layers may be formed discretely and joined together to form the body of the shaped abrasive particle.

In accordance with an embodiment, the method of forming a shaped abrasive particle having a body formed by an additive manufacturing process can include deposition of a first print material as a first portion of the body at a first time, and deposition of a second print material as a second portion of the body distinct from the first portion at a second time. It will be understood that the first time can be the same as, or different from, the second time. More particularly, the first print material in some instances may include a solid material, a powder, a solution, a mixture, a liquid, a slurry, a gel, a binder, and any combination thereof. In one particular instance, the first print material can include a sol gel material. For example, the first print material can include a mixture, where the mixture can be a gel formed of a powder material and a liquid, and where the gel can be characterized as a shape-stable material having the ability to substantially hold a given shape even in the green (i.e., unfired) state. In accordance with an embodiment, the gel can be formed of the powder material as an integrated network of discrete particles. In particular instances, the mixture can include a sol-gel material, which may have one or more particulate materials forming a matrix of the mixture. The particulate materials can include any of the materials noted herein, such as the ceramic materials.

The first print material may have a certain content of solid material, liquid material, and additives such that it has suitable rheological characteristics for use with the process detailed herein. That is, in certain instances, the first print material can have a certain viscosity, and more particularly, suitable rheological characteristics that form a dimensionally-stable phase of material that can be formed through the process as noted herein. A dimensionally-stable phase of material can be a material that can be formed to have a particular shape and substantially maintain the shape for at least a portion of the processing subsequent to forming. In certain instances, the shape may be retained throughout subsequent processing, such that the shape initially provided in the forming process is present in the finally-formed object.

The print material, including any print material of the embodiments herein can be a mixture and may have a particular content of an inorganic material, which may be a solid powder material or particulate, such as a ceramic powder material. In accordance with an embodiment, the print material can include a mixture that may include an inorganic material having suitable rheological characteristics that facilitate formation of the body including a shaped abrasive particle. For example, in one embodiment, the first print material can have a solids content of at least about 25 wt %, such as at least about 35 wt %, at least about 36 wt %, or even at least about 38 wt % for the total weight of the mixture. Still, in at least one non-limiting embodiment, the solids content of the first print material can be not greater than about 75 wt %, such as not greater than about 70 wt %, not greater than about 65 wt %, not greater than about 55 wt %, not greater than about 45 wt %, not greater than about 44 wt %, or not greater than about 42 wt %. It will be appreciated that the content of the solids materials in the first print material can be within a range between any of the minimum and maximum percentages noted above, including for example within a range of at least about 25 wt % and not



## 5

greater than about 70 wt %, the least about 35 wt % and not greater than about 55 wt %, or even at least about 36 wt % and not greater than about 45 wt %.

According to one embodiment, the ceramic powder material can include an oxide, a nitride, a carbide, a boride, an oxycarbide, an oxynitride, and a combination thereof. In particular instances, the ceramic material can include alumina. More specifically, the ceramic material may include a boehmite material, which may be a precursor of alpha alumina. The term "boehmite" is generally used herein to denote alumina hydrates including mineral boehmite, typically being  $\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$  and having a water content on the order of 15%, as well as pseudoboehmite, having a water content higher than 15%, such as 20-38% by weight. It is noted that boehmite (including pseudoboehmite) has a particular and identifiable crystal structure, and therefore a unique X-ray diffraction pattern. As such, boehmite is distinguished from other aluminous materials including other hydrated aluminas such as ATH (aluminum trihydroxide), a common precursor material used herein for the fabrication of boehmite particulate materials.

Furthermore, the print material, including any of the print materials of the embodiments herein, may be in the form of a mixture, may have a particular content of liquid material. Some suitable liquids may include water. In accordance with one embodiment, the first print material can be formed to have a liquid content less than the solids content of the mixture. In more particular instances, the first print material can have a liquid content of at least about 25 wt % for the total weight of the mixture. In other instances, the amount of liquid within the first print material can be greater, such as at least about 35 wt %, at least about 45 wt %, at least about 50 wt %, or even at least about 58 wt %. Still, in at least one non-limiting embodiment, the liquid content of the first print material can be not greater than about 75 wt %, such as not greater than about 70 wt %, not greater than about 65 wt %, not greater than about 62 wt %, or even not greater than about 60 wt %. It will be appreciated that the content of the liquid in the first print material can be within a range between any of the minimum and maximum percentages noted above.

Furthermore, to facilitate processing and forming shaped abrasive particles according to embodiments herein, the first print material, can have a particular storage modulus. For example, the first print material can have a storage modulus of at least about  $1 \times 10^4$  Pa, such as at least about  $4 \times 10^4$  Pa, or even at least about  $5 \times 10^4$  Pa. However, in at least one non-limiting embodiment, the first print material may have a storage modulus of not greater than about  $1 \times 10^7$  Pa, such as not greater than about  $2 \times 10^6$  Pa. It will be appreciated that the storage modulus of the first print material can be within a range between any of the minimum and maximum values noted above.

The storage modulus can be measured via a parallel plate system using ARES or AR-G2 rotational rheometers, with Peltier plate temperature control systems. For testing, the first print material can be extruded within a gap between two plates that are set to be approximately 8 mm apart from each other. After extruding the first print material into the gap, the distance between the two plates defining the gap is reduced to 2 mm until the first print material completely fills the gap between the plates. After wiping away excess material, the gap is decreased by 0.1 mm and the test is initiated. The test is an oscillation strain sweep test conducted with instrument settings of a strain range between 0.01% to 100%, at 6.28 rad/s (1 Hz), using 25-mm parallel plate and recording 10 points per decade. Within 1 hour after the test completes, the

## 6

gap is lowered again by 0.1 mm and the test is repeated. The test can be repeated at least 6 times. The first test may differ from the second and third tests. Only the results from the second and third tests for each specimen should be reported.

The print material, which may include a mixture, can be formed to have a particular viscosity to facilitate formation of the body of the shaped abrasive particle having the features of the embodiments herein. For example, the mixture can have a viscosity of at least about  $4 \times 10^3$  Pa s, such as at least about  $5 \times 10^3$  Pa s, at least about  $6 \times 10^3$  Pa s, at least about  $7 \times 10^3$  Pa s, at least about  $7.5 \times 10^3$  Pa s. In another non-limiting embodiment, the mixture can have a viscosity of not greater than about  $20 \times 10^3$  Pa s, such as not greater than about  $18 \times 10^3$  Pa s, not greater than about  $15 \times 10^3$  Pa s, not greater than about  $12 \times 10^3$  Pa s. Still, it will be appreciated that the mixture can have a viscosity within a range including any of the minimum and maximum values noted above, including but not limited to, at least about  $4 \times 10^3$  Pa s and not greater than about  $20 \times 10^3$  Pa s, such as at least about  $5 \times 10^3$  Pa s and not greater than about  $18 \times 10^3$  Pa s, at least about  $6 \times 10^3$  Pa s and not greater than about  $15 \times 10^3$  Pa s. The viscosity can be measured in the same manner as the storage modulus as described above.

Moreover, the first print material, which may be in the form of a mixture, may be formed to have a particular content of organic materials including, for example, organic additives that can be distinct from the liquid to facilitate processing and formation of shaped abrasive particles according to the embodiments herein. Some suitable organic additives can include stabilizers, binders such as fructose, sucrose, lactose, glucose, UV curable resins, and the like.

Notably, the embodiments herein may utilize a first print material that can be distinct from slurries used in conventional forming operations. For example, the content of organic materials within the first print material and, in particular, any of the organic additives noted above, may be a minor amount as compared to other components within the mixture. In at least one embodiment, the first print material can be formed to have not greater than about 30 wt % organic material for the total weight of the first print material. In other instances, the amount of organic materials may be less, such as not greater than about 15 wt %, not greater than about 10 wt %, or even not greater than about 5 wt %. Still, in at least one non-limiting embodiment, the amount of organic materials within the first print material can be at least about 0.01 wt %, such as at least about 0.5 wt % for the total weight of the first print material. It will be appreciated that the amount of organic materials in the first print material can be within a range between any of the minimum and maximum values noted above.

Moreover, the first print material can be formed to have a particular content of acid or base, distinct from the liquid content, to facilitate processing and formation of shaped abrasive articles according to the embodiments herein. Some suitable acids or bases can include nitric acid, sulfuric acid, citric acid, chloric acid, tartaric acid, phosphoric acid, ammonium nitrate, and ammonium citrate. According to one particular embodiment in which a nitric acid additive is used, the first print material can have a pH of less than about 5, and more particularly, can have a pH within a range between about 2 and about 4.

FIG. 1A includes a perspective view illustration of a process of forming a shaped abrasive particle via an additive manufacturing process in accordance with an embodiment. As illustrated, the additive manufacturing process may utilize a deposition assembly 151 configured to have multi-axial movement in at least the X-direction, the Y-direction,



and Z-direction for controlled deposition of a print material **122**. In particular instances, the deposition assembly **151** can have a deposition head **153** configured to provide controlled delivery of a print material to a particular position. Notably, the deposition assembly **151** may provide controlled deposition of a first print material as a first portion of the body at a first time and deposition of a second print material as a second portion of the body that is distinct from the first portion at the second time. Such a process can facilitate the controlled deposition of discrete portions such that the discrete portions are deposited in precise locations with respect to each other and can facilitate formation of a body of a shaped abrasive particle having suitable shape, dimensions, and performance.

In particular instances, the deposition assembly **151** can be configured to deposit a first print material **102** as a first portion **101** of the body of the shaped abrasive particle. In particular, the first portion **101** can define a fraction of the total volume of the body of the shaped abrasive particle. In particular instances, the first portion **101** can have a first portion length (Lfp), a first portion width (Wfp), and a first portion thickness (Tfp). According to one embodiment, Lfp may be greater than or equal to Wfp, Lfp may be greater than or equal to Tfp, and Wfp may be greater than or equal to Tfp. In particular instances, the length of the first portion may define the largest dimension of the first portion **101**, and the width of the first portion **101** may define a dimension extending in a direction generally perpendicular to the length (Lfp) and may define the second largest dimension of the first portion **101**. Moreover, in some embodiments, the thickness (Tfp) of the first portion **101** may define the smallest dimension of the first portion **101**, and may define a dimension extending in a direction perpendicular to either or both of the length (Lfp) and the width (Wfp). It will be appreciated, however, that the first portion **101** can have various shapes as will be defined further herein.

In accordance with an embodiment, the first portion **101** can have a primary aspect ratio (Lfp:Wfp) to facilitate suitable forming of the body of the shaped abrasive particle. For example, the first portion **101** may have a primary aspect ratio (Lfp:Wfp) of at least about 1:1. In other embodiments, the first portion **101** may have a primary aspect ratio that is about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the first portion **101** may have a primary aspect ratio of not greater than about 1000:1.

Furthermore, the first portion **101** may be formed to have a particular secondary aspect ratio, such that the body of the shaped abrasive particle has a desirable shape. For example, the first portion **101** can have a secondary aspect ratio (Lfp:Tfp) of at least about 1:1. In other embodiments, the first portion **101** may have a secondary aspect ratio that is at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the secondary aspect ratio of the first portion **101** may be not greater than about 1000:1.

In yet another embodiment, the first portion **101** may be formed to have a particular tertiary aspect ratio (Wfp:Tfp) to facilitate suitable forming of the body of the shaped abrasive particle. For example, the first portion **101** may have a tertiary aspect ratio (Wfp:Tfp) of at least about 1:1. In other instances, the first portion **101** may have a tertiary aspect ratio of at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. In still another non-limiting embodiment, the first portion **101** can have a tertiary aspect ratio of not greater than about 1000:1.

The dimensions of the first portion **101** of the body of the shaped abrasive particle may be formed to have a particular value to facilitate formation of the body having suitable shape and dimensions. Any of the foregoing dimensions (e.g., Lfp, Wfp, Tfp) of the first portion **101** can have an average dimension of not greater than about 2 mm. In other instances, the average dimension of any one of the first portion length (Lfp), first portion width (Wfp), or first portion thickness (Tfp) can have an average dimension of not greater than about 1 mm, such as not greater than about 900 microns, not greater than about 800 microns, not greater than about 700 microns, not greater than about 600 microns, not greater than about 500 microns, not greater than about 400 microns, not greater than about 300 microns, not greater than about 200 microns, not greater than about 150 microns, not greater than about 140 microns, not greater than about 130 microns, not greater than about 120 microns, not greater than about 110 microns, not greater than about 100 microns, not greater than about 90 microns, not greater than about 80 microns, not greater than about 70 microns, not greater than about 60 microns, or even not greater than about 50 microns. Still, in another non-limiting embodiment, any one of the first portion length (Lfp), the first portion width (Wfp), or the first portion thickness (Tfp) can have an average dimension that is at least about 0.01 microns, such as at least about 0.1 microns, or even at least about 1 micron. It will be appreciated that any one of the first portion length, first portion width, or first portion thickness can have an average dimension within a range between any of the minimum and maximum values noted above.

In another embodiment, the first portion **101** may be deposited to have a particular cross-sectional shape. Deposition of the first portion **101** with a particular cross-sectional shape can facilitate formation of a body of a shaped abrasive particle having a particular, desirable cross-sectional shape and three-dimensional shape. In accordance with an embodiment, the first portion **101** can have substantially any contemplated cross-sectional shape. More particularly, the first portion **101** can have a cross-sectional shape in a plane defined by the first portion length (Lfp) and first portion width (Wfp), such as triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, irregular shaped contours, and any combination thereof. Furthermore, the first portion **101** may be formed to have a particular cross-sectional shape in a plane defined by the first portion length (Lfp) and first portion thickness (Tfp). Such cross-sectional shape can include a shape selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, irregular shaped contours, and any combination thereof.

In at least one embodiment, the first portion **101** may be deposited in the form of a layer. In yet another embodiment, the first portion may be deposited (as shown in FIG. 1A) as an elongated structure, where the length is significantly greater than the thickness or the width. In yet another embodiment, the first portion **101** may be deposited as a discrete droplet. More particularly, the deposition process may be conducted such that it includes depositing a plurality of discrete droplets of a predetermined volume of the first print material **102** to form the first portion **101**. For example, the first portion **101** may be made up of a plurality of first sub-portions that are deposited in a controlled manner to define the dimensions of the first portion **101**.



As further illustrated in FIG. 1A, the process of forming a shaped abrasive particle according to an additive manufacturing process also can include controlled deposition of a second portion **110** including a second print material **112**. In an embodiment, the second print material **112** can include a solid, a solution, a mixture, a liquid, a slurry, a gel, a binder, and a combination thereof. In a particular embodiment, the second print material **112** can be the same as, or different from, the first print material. For example, the second print material **112** can include a sol gel material as described above. The deposition assembly **151** can deposit the second portion **110** in any suitable location including a particular location relative to the first portion **101**. For example, as illustrated in FIG. 1A, the second portion **110** may be deposited in a position to abut at least a portion of the first portion **101**. Such controlled multi-axial movement of the deposition assembly **151** can facilitate both precise deposition of discrete portions including, for example, the first portion **101** and the second portion **110**, as well as controlled and precise deposition of a plurality of portions (and sub-portions) with respect to each other, thus facilitating the compilation of a plurality of portions to form the body of the shaped abrasive particle.

As illustrated, the deposition assembly **151** can be configured to deposit the second print material **112** as the second portion **110** of the body of the shaped abrasive particle. In particular, the second portion **110** can define a fraction of the total volume of the body of the shaped abrasive particle. In particular instances, the second portion **110** can have a second portion length (Lsp), a second portion width (Wsp), and a second portion thickness (Tsp). Notably, according to one aspect, Lsp can be greater than or equal to Wsp, Lsp can be greater than or equal to Tsp, and Wsp can be greater than or equal to Tsp. In particular instances, the length (Lsp) of the second portion **110** may define the largest dimension of the second portion **110**, and the width (Wsp) of the second portion **110** may define a dimension extending in a direction generally perpendicular to the length (Lsp) and may define the second largest dimension in accordance with an embodiment. Finally, in some embodiments, the thickness (Tsp) of the second portion **110** may define generally the smallest dimension of the second portion **110**, and may define a dimension extending in a direction perpendicular to either or both of the length (Lsp) and the width (Wsp). It will be appreciated, however, that the second portion **110** can have various shapes as will be defined further herein.

In accordance with an embodiment, the second portion **110** can have a primary aspect ratio (Lsp:Wsp) that can facilitate formation of a body have a suitable shape and dimensions. For example, the second portion **110** can have a primary aspect ratio (Lsp:Wsp) of at least about 1:1. In other embodiments, the second portion **110** may have a primary aspect ratio that is about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the second portion **110** may have a primary aspect ratio of not greater than about 1000:1.

Furthermore, the second portion **110** may be formed to have a particular secondary aspect ratio, such that the formed body of the shaped abrasive particle has a desirable shape. For example, the second portion **110** can have a secondary aspect ratio (Lsp:Tsp) of at least about 1:1. In other embodiments, the second portion **110** may have a secondary aspect ratio that is at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the secondary aspect ratio of the second portion **110** may be not greater than about 1000:1.

In yet another embodiment, the second portion **110** may be formed to have a particular tertiary aspect ratio (Wsp:Tsp) that can facilitate formation of a body have a suitable shape and dimensions. For example, the second portion **110** can have a tertiary aspect ratio (Wsp:Tsp) of at least about 1:1. In other instances, the second portion **110** may have a tertiary aspect ratio of at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. In still another non-limiting embodiment, the second portion **110** can have a tertiary aspect ratio of not greater than about 1000:1.

The dimensions of the second portion **110** of the body of the shaped abrasive particle may be formed to have a particular value. Any of the foregoing dimensions (e.g., Lsp, Wsp, Tsp) of the second portion **110** can have an average dimension of not greater than about 2 mm. In other instances, the average dimension of any one of the second portion length (Lsp), second portion width (Wsp), or second portion thickness (Tsp) can have an average dimension of not greater than about 1 mm, such as not greater than about 900 microns, not greater than about 800 microns, not greater than about 700 microns, not greater than about 600 microns, not greater than about 500 microns, not greater than about 400 microns, not greater than about 300 microns, not greater than about 200 microns, not greater than about 150 microns, not greater than about 140 microns, not greater than about 130 microns, not greater than about 120 microns, not greater than about 110 microns, not greater than about 100 microns, not greater than about 90 microns, not greater than about 80 microns, not greater than about 70 microns, not greater than about 60 microns, or even not greater than about 50 microns. Still, in another non-limiting embodiment, any one of the second portion length (Lsp), the second portion width (Wsp), or the second portion thickness (Tsp) can have an average dimension that is at least about 0.01 microns, such as at least about 0.1 microns, or even at least about 1 micron. It will be appreciated that any one of the second portion length, second portion width, or second portion thickness can have an average dimension within a range between any of the minimum and maximum values noted above.

In another embodiment, the second portion **110** may be deposited to have a particular cross-sectional shape. Deposition of the second portion **110** with a particular cross-sectional shape can facilitate formation of a body of a shaped abrasive particle having a particular, desirable cross-sectional shape and three-dimensional shape. In accordance with an embodiment, the second portion **110** can have substantially any contemplated cross-sectional shape. More particularly, the second portion **110** can have a cross-sectional shape in a plane defined by the second portion length (Lsp) and second portion width (Wsp), which may be viewed top-down, where the shape is selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, and any combination thereof. Furthermore, the second portion **110** may be formed to have a particular cross-sectional shape in a plane defined by the second portion length (Lsp) and second portion thickness (Tsp), which may be evident in a side-view. Such cross-sectional shape can include a shape selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, and any combination



thereof. Moreover, the second portion **110** may be formed to have a particular cross-sectional shape in a plane defined by the second portion width ( $W_{sp}$ ) and second portion thickness ( $T_{sp}$ ), which may be evident in a side-view. Such cross-sectional shape can include a shape selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, and any combination thereof.

In at least one embodiment, the second portion **110** may be deposited in the form of a layer. In yet another embodiment, the second portion may be deposited (as shown in FIG. 1A) as an elongated structure, where the length is significantly greater than the thickness or the width. In yet another embodiment, the second portion **110** may be deposited as a discrete droplet. More particularly, the deposition process may be conducted such that it includes depositing a plurality of discrete droplets of a predetermined volume of the second print material **112** to form the second portion **110**. For example, the second portion **110** may be made up of a plurality of second sub-portions that are deposited in a controlled manner to define the dimensions of the second portion **110**.

As further illustrated in FIG. 1A, the first portion **101** can have substantially the same cross-sectional shape as the cross-sectional shape of the second portion **110**. However, it will be appreciated that in other embodiments, a plurality of portions may be deposited such that each of the portions can have a different cross-sectional shape with respect to each other. For example, in at least one embodiment, the first portion **101** can be deposited with a first cross-sectional shape with respect to any two dimensions (e.g., length, width, and thickness) of the body of the first portion that can be different than a cross-sectional shape of the second portion **110** with respect to any two dimensions (e.g., length, width, thickness) defining the body of the second portion **110**.

In accordance with some embodiments, the first print material **102** can have a first composition and the second print material **112** can have a second composition. In some instances, the first composition can be substantially the same as the second composition. For example, the first composition and second composition can be essentially the same with respect to each other, such that only a content of impurity materials present in small amounts (e.g., such as less than about 0.1%) may constitute a difference between the first composition and the second composition. Alternatively, in another embodiment, the first composition and second composition can be significantly different with respect to each other.

In at least one embodiment, the first composition can include a material such as an organic material, inorganic material, and a combination thereof. More particularly, the first composition may include a ceramic, a glass, a metal, a polymer, or any combination thereof. In at least one embodiment, the first composition may include a material such as an oxide, a carbide, a nitride, a boride, an oxycarbide, an oxynitride, an oxyboride, and any combination thereof. Notably, in one embodiment, the first composition can include alumina. More particularly, the first composition may include an alumina-based material, such as a hydrated alumina material including, for example, boehmite.

In at least one embodiment, the second composition can include a material such as an organic material, inorganic material, and a combination thereof. More particularly, the

second composition may include a ceramic, a glass, a metal, a polymer, or any combination thereof. In at least one embodiment, the second composition may include a material such as an oxide, a carbide, a nitride, a boride, an oxycarbide, an oxynitride, an oxyboride, and any combination thereof. Notably, in one embodiment, the second composition can include alumina. More particularly, the first composition may include an alumina-based material, such as a hydrated alumina material including, for example, boehmite.

In certain instances, the process of depositing a first print material and second print material (e.g., the first print material **110** and the second print material **112**) can be conducted such that the first print material is deposited at a first time and the second print material is deposited at a second time and the first time and second time are discrete in different time intervals. In such embodiments, the deposition process can be an intermittent process, wherein the deposition process includes the formation of discrete portions during discrete durations of time. In an intermittent process, at least a portion of time passes between the formation of the first portion and the formation of the second portion, wherein there may be no deposition of material.

Still, in other instances, it will be appreciated that the deposition process may be a continuous process. In continuous processes, the deposition process may not necessarily include the deposition of discrete first and second portions at different time intervals. Instead, the deposition process may utilize a continuous extrusion process in which print material can be extruded while the deposition assembly **151** is moving. Moreover, the deposition assembly **151** may be capable of changing the dimension of the portion during the continuous deposition process, thereby facilitating the formation of one or more portions with a variable dimensions (e.g., cross-sectional and three-dimensional dimensions) to facilitate the formation of a body of a shaped abrasive particle having a desirable two-dimensional and three-dimensional shape.

In accordance with another aspect of forming a body of a shaped abrasive particle via an additive manufacturing process, the process can include preferentially modifying one of the first portion **101** and the second portion **110** to join the first portion **101** and the second portion **110** and form a subsection **171** of the body. In a particular embodiment, the process of modifying can include changing a phase of at least one of the first print material **102** and the second print material **112**. For example, modifying can include heating at least one of the first portion **101** and the second portion **110**. More particularly, heating can include joining a part of the first portion **101** to the second portion **110**, such as by fusing at least a part of the first portion **101** to the second portion **110**. Heating also may be accomplished utilizing various techniques including, for example, convection, conduction, and radiation techniques. In one particular embodiment, the process of heating at least one of the first portion **101** and second portion **110** can include impinging electromagnetic radiation on at least a portion of the first portion **110** and/or second portion **110** to facilitate joining a portion of the first portion **101** to the second portion **110**. Suitable types of electromagnetic radiation may be supplied by use of a laser. Still, it will be appreciated that in other instances, the process of heating can include impinging electromagnetic radiation on at least a portion of the second portion to facilitate joining any one of the first portion and second portion.

In other instances, the process of modifying a portion of the body also can include melting, selective laser melting, sintering, selective sintering, direct metal laser sintering,



selective laser sintering, particle beam modification, electron beam melting, fused deposition modeling, curing, and any combination thereof. Any of the foregoing processes can be used on a part or all of any of one or more of the portions to modify the portions.

In another aspect of forming a body of a shaped abrasive particle via an additive manufacturing process, the process of forming a body of a shaped abrasive particle can be conducted according to a digital model. The process of forming a body according to a digital model can include measuring at least a portion of the body and comparing it to a corresponding dimension of the digital model. The process of comparing can be conducted during the forming process or after the forming process is completed for a portion or the entire body. It will be appreciated that the provision of a digital model can facilitate the control of and the deposition process conducted by the deposition assembly 151.

In particular instances, the process of forming a body according to a digital model can further include creating a plurality of digital cross-sections of the digital model. Creation of the plurality of digital cross-sections can facilitate, for example, controlled deposition of one or more portions of the body. For example, in one instance, the process can include depositing a first portion of the body at a first time, where the first portion corresponds to a first cross-section of a plurality of cross-sections of the digital model. Furthermore, the process can include depositing a second portion of the body distinct from the first portion at a second time that is different than the first time. The second portion can correspond to a second cross-section of the plurality of cross-sections of the digital model. Accordingly, it will be appreciated that the plurality of digital cross-sections can be a guide for depositing the plurality of discrete portions, where a single digital cross-section can facilitate the deposition of a discrete first portion and a second digital cross-section can facilitate the deposition of a second discrete portion. Each of the portions may be deposited, and while the deposition assembly 151 is depositing and forming each of the portions, the dimensions of the portions can be measured and compared to a digital model. More particularly, the deposition assembly 151 may be adapted to alter the deposition process based on the comparison of the dimensions of the deposited portion to a corresponding digital model portion.

It also will be appreciated that an additive manufacturing process can include a process of compiling discrete portions including, for example, the first portion 101 and second portion 110, to form a subsection 171. Furthermore, the process may include compiling a plurality of subsections to form the body of the shaped abrasive particle.

In accordance with yet another embodiment, the process of forming the shaped abrasive particle can include a subtractive process. Notably, the subtractive process may be conducted after completing at least some of the additive manufacturing process. More particularly, the subtractive process may be conducted after total completion of the additive manufacturing process. In at least one embodiment, the subtractive process can be conducted after forming a body of a precursor shaped abrasive particle. In certain instances, the subtractive process can include removing at least a portion of the material used to form the precursor shaped abrasive particle. Certain suitable subtractive processes may include, for example, forming at least one opening within a portion of the body, forming at least one aperture that extends through an entire portion of the body, and heating the body to remove a portion of the body, such as by volatilizing at least a portion of the body.

The body of a shaped abrasive particle that has been formed by an additive manufacturing process can include a variety of suitable dimensions. In particular instances, the body can have a body length (Lb), a body width (Wb), and a body thickness (Tb), such as shown in FIG. 6. In one non-limiting embodiment, the length of the body may define the largest dimension of the shaped abrasive particle and the width of the body may define a dimension extending in a direction generally perpendicular to the length and may define the second largest dimension in accordance with an embodiment. Moreover, in some embodiments, the thickness of the body may define the smallest dimension of the shaped abrasive particle, and may define a dimension extending in a direction perpendicular to either or both of the length and the width. In some instances, Lb may be greater than or equal to Wb, and Lb may be greater than or equal to Tb. Yet, in other designs of the shaped abrasive particles, Wb may be greater than or equal to Tb. It will be appreciated, however, that the body can have various shapes as will be defined further herein.

Moreover, reference herein to any dimensional characteristic (e.g., Lb, Wb, Tb) can be reference to a dimension of a single shaped abrasive particle of a batch, a median value, or an average value derived from analysis of a suitable sampling of shaped abrasive particles from a batch. Unless stated explicitly, reference herein to a dimensional characteristic can be considered reference to a median value that is based on a statistically significant value derived from a sample size of a suitable number of articles from a batch of articles. Notably, for certain embodiments herein, the sample size can include at least 10 randomly selected articles from a batch of articles. A batch of articles may be a group of articles that are collected from a single process run. Additionally or alternatively, a batch of articles may include an amount of shaped abrasive particles suitable for forming a commercial grade abrasive product, such as at least about 20 lbs. of particles.

In accordance with an embodiment, the body can have a primary aspect ratio (Lb:Wb) of at least about 1:1. In other embodiments, the body may have a primary aspect ratio that is about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the body may have a primary aspect ratio of not greater than about 1000:1.

Furthermore, the body may be formed to have a particular secondary aspect ratio, such that the shaped abrasive particle has a desirable shape. For example, the body can have a secondary aspect ratio (Lb:Tb) of at least about 1:1. In other embodiments, the body may have a secondary aspect ratio that is at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. Still, in one non-limiting embodiment, the secondary aspect ratio of the body may be not greater than about 1000:1.

In yet another embodiment, the body may be formed to have a particular tertiary aspect ratio (Wb:Tb) of at least about 1:1. In other instances, the body may have a tertiary aspect ratio of at least about 2:1, such as at least about 3:1, at least about 5:1, or even at least about 10:1. In still another non-limiting embodiment, the body can have a tertiary aspect ratio of not greater than about 1000:1.

The dimensions of the body of the shaped abrasive particle may be formed to have a particular value. Any of the foregoing dimensions (e.g., Lb, Wb, Tb) of the body can have an average dimension of at least about 0.1 microns. In other instances, the average dimension of any one of the body length (Lb), body width (Wb), or body thickness (Tb) can have an average dimension of at least about 1 micron,



at least about 10 microns, at least about 50 microns, at least about 100 microns, at least about 150 microns, at least about 200 microns, at least about 400 microns, at least about 600 microns, at least about 800 microns, at least about 1 mm. Still, in another non-limiting embodiment, any one of the body length (Lb), the body width (Wb), or the body thickness (Tb) can have an average dimension that is not greater than about 20 mm, not greater than about 18 mm, not greater than about 16 mm, not greater than about 14 mm, not greater than about 12 mm, not greater than about 10 mm, not greater than about 8 mm, not greater than about 6 mm, or even not greater than about 4 mm. It will be appreciated that any one of the dimensions can have an average dimension within a range between any of the minimum and maximum values noted above.

In another embodiment, the body may be formed to have a particular, desirable cross-sectional shape. For example, the body can have a cross-sectional shape in a plane defined by the body length (Lb) and body width (Wb), where the shape is selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, and any combination thereof. Furthermore, the body may be formed to have a particular cross-sectional shape in a plane defined by the body length (Lb) and the body thickness (Tb). Such cross-sectional shape also can include a shape selected from the group of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, and any combination thereof.

The body also may be formed to have a particular, desirable three-dimensional shape. For example, the body can have a three-dimensional shape selected from the group consisting of a polyhedron, a pyramid, an ellipsoid, a sphere, a prism, a cylinder, a cone, a tetrahedron, a cube, a cuboid, a rhombohedron, a truncated pyramid, a truncated ellipsoid, a truncated sphere, a truncated cone, a pentahedron, a hexahedron, a heptahedron, an octahedron, a nonahedron, a decahedron, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, a volcano shape, a monostatic shape, and a combination thereof. A monostatic shape is a shape with a single stable resting position. Accordingly, shaped abrasive particles having a monostatic shape can be applied to a substrate and consistently be oriented in the same position, as they have only one stable resting position. For example, shaped abrasive particles having a monostatic shape may be suitable when applying the particles to a backing via gravity coating, which may be used in the formation of a coated abrasive product. More particularly, the shaped abrasive particles may be mono-monostatic shapes, which describe three dimensional objects having a shape with only one unstable point of balance. According to one particular embodiment, the shaped abrasive particle may have the shape of a gomboc. In another embodiment, the shaped abrasive particle is a monostatic polyhedron with at least four surfaces.

The additive manufacturing process according to the embodiments herein also may be used to form a plurality of shaped abrasive particles, where each of the shaped abrasive particles of the plurality of shaped abrasive particles have a body having a body length (Lb) a body width (Wb), and a body thickness (Tb) as described above. In accordance with

an embodiment, the plurality of shaped abrasive particles can have at least one of a body length variation of not greater than about 50%, a body width variation of not greater than about 50%, and a body thickness variation of not greater than about 50%.

The body length variation may be described as a standard deviation of body length for a suitable sampling from a plurality of shaped abrasive particles, which can include a plurality of shaped abrasive particles. In an embodiment, the body length variation may be not greater than about 40%, such as not greater than about 30%, not greater than about 20%, not greater than about 10%, or even not greater than about 5%.

Like the body length variation, the body width variation may be a measure of the standard deviation of the width of the body for a suitable sampling of shaped abrasive particles from the plurality of shaped abrasive particles. In accordance with an embodiment, the body width variation may be not greater than about 40%, such as not greater than about 30%, and not greater than about 20%, not greater than about 10%, or even not greater than about 5%.

Furthermore, the body thickness variation may be a standard deviation of body thickness for a suitable sampling of shaped abrasive particles from the plurality of shaped abrasive particles. In accordance with one embodiment, the body thickness variation for the plurality of shaped abrasive particles may be not greater than about 40%, such as not greater than about 30%, not greater than about 20%, not greater than about 10%, or even not greater than about 5%.

In accordance with an embodiment the additive manufacturing process can include forming a body of a shaped abrasive particle by shaping a raw material without the use of a production tool. It will be appreciated that a production tool may refer to a mold or screen having one or more openings configured to contain and form the raw material into the desired final shaped abrasive particle. In accordance with another embodiment, the additive manufacturing process can include forming a body of a shaped abrasive particle by depositing a plurality of discrete portions of raw material in a controlled, non-random manner relative to each other. Still, in at least one embodiment, the additive manufacturing process can include depositing a plurality of portions of the body in a controlled, non-random manner relative to each other into a production tool. That is, in certain instances the additive manufacturing process can include use of a production tool. In at least one manner, the additive manufacturing process is distinct from conventional screen printing and molding processes as the production tool can be filled with a plurality of discrete portions that are placed into the production tool in a controlled-nonrandom manner.

Reference herein to formation of a shape abrasive particle will be understood to include formation of a precursor shaped abrasive particle. That is the additive manufacturing process may form a precursor shaped abrasive particle, which may be a green body or unfinished body that can undergo further processing to form the final shaped abrasive particle. In certain forming processes, the precursor shaped abrasive particle may have essentially the same shape of the final shaped abrasive particle.

In accordance with another embodiment, the additive manufacturing process can include processes such as light photopolymerization, laser powder forming, powder bed fusion, selective laser centering, micro-laser sintering, material extrusion, robocasting, material jetting, sheet lamination, and a combination thereof. In one particular embodiment, the light photopolymerization process can include



stereolithography. Stereolithography can include a process wherein at least one layer of a slurry containing a polymer material can be polymerized during the forming process to form a shaped abrasive particle. More particularly, the stereolithography process can include provision of a mixture, such as a slurry containing a powder raw material and a carrier, and a polymer material that is configured to be polymerized during the forming process of forming the shaped abrasive particle.

In another embodiment the additive manufacturing process can include a laser powder forming process. Laser powder forming can include deposition of a raw material on a target, such as substrate and an impinging radiation, such as from a laser source, at the target and raw material to melt the raw material and form the raw material into at least a portion of a shaped abrasive particle. Notably, the laser powder forming process can include a change of phase of the raw material from a solid state to a liquid state such that a melt is formed prior to formation of at least a portion of the shaped abrasive particle.

The laser powder forming process can utilize a raw material selected from the group of materials such as a metal, a metal alloy, a glass, a ceramic, a polymer, and a combination thereof. In at least one particular embodiment, the shaped abrasive particle formed by the laser powder forming process can include a material such as a metal, a metal alloy, a glass, a ceramic, a ceramic precursor, a polymer, and a combination thereof. The shaped abrasive particles in one embodiment formed by a laser powder forming process can consist essentially of a glass material comprising oxide.

In another instance, the additive manufacturing process can include a selective laser sintering process. Selective laser sintering can include a process wherein radiation is directed to a target. The radiation may be supplied from a laser source. The radiation can be impinged on a target that includes a raw material, and the radiation can change at least a portion of the raw material into a portion of a shaped abrasive particle. In more particular instances, the selective laser sintering process can include impinging radiation from a laser source onto a portion of a bed of raw material and converting a portion of the bed of raw material into a shaped abrasive particle. For example, a portion of the bed of raw material impinged by the radiation can be converted in a manner such that it may undergo a phase change, while other portions of the raw material not subject to the radiation may maintain their original state. In accordance with an embodiment, changing at least a portion of the raw material can include a change in a crystalline structure of the raw material. For example, the bed of raw material may include a boehmite material that is changed by the radiation into an alternative form of alumina, including for example, alpha alumina. In yet another embodiment, changing at least a portion of the raw material can include changing a phases of the raw material, such as changing the raw material subject to the radiation from a solid phase to a liquid phase.

The raw material used in the selective laser sintering operation can include a metal, a metal alloy, a glass, a ceramic, a ceramic precursor, a polymer, and a combination thereof. In one particular embodiment, the raw material can include an oxide material, such as alumina or boehmite. Moreover, the shaped abrasive particle formed by the selective laser sintering process can include a metal, a metal alloy, a glass, a ceramic, a ceramic precursor, a polymer, and a combination thereof. In one particular embodiment, the

shaped abrasive particle formed according to the selective laser sintering process can include an oxide material, such as alumina or boehmite.

And yet another embodiment the additive manufacturing process can include material jetting. A material jetting process can include deposition of discrete droplets of raw material onto a target and coalescence of the discrete droplets into at least a portion of the body of the shape abrasive particle.

According to one alternative process, the shaped abrasive particles can be formed using a low pressure injection molding process. Unlike certain conventional injection molding processes, a molding material, which can include any of the properties of the print material of the embodiments herein directed to an additive manufacturing process, can be injected into a mold in a controlled manner. In particular, during the process, the mold material can be injected into the mold under laminar flow conditions as opposed to turbulent flow conditions. The laminar flow conditions allow for controlled placement of the mold material into the mold according to a filling procedure, which may include selective placement of the mold material into portions of the mold in a particular sequence for a controlled filling procedure. The injection molding process may be combined with one or more processes described herein.

In accordance with one particular embodiment, the additive manufacturing process for forming the shaped abrasive particle can include robocasting. In certain instances, robocasting can include the deposition of a raw material onto a target in the form of discrete portions that are distinct from each other. The portions may be later coalesced through subsequent processing to form the shape abrasive particles. The raw material may be deposited from a nozzle onto a target or substrate in a controlled manner to form the body of the shaped abrasive particle.

In accordance with an embodiment, the process of forming the body via robocasting can include controlling at least one process parameter from the group consisting of a nozzle tip length; a nozzle width; a nozzle aspect ratio, a deposition pressure, a relationship between nozzle width and deposition pressure, a deposition rate, a deposition volume, a relationship between deposition rate and deposition position, a relationship between deposition pressure and deposition position, a shutoff distance, premove delay, a dispense gap, a filling pattern of the print material, a dynamic yield stress ( $\sigma_d$ ) of a print material, a static yield stress ( $\sigma_s$ ) of a print material, a yield stress ratio ( $\sigma_d/\sigma_s$ ) of a print material, and a combination thereof.

In particular instances, the process of forming the body can include deposition or depositing a first print material as the first portion of the body the first time and depositing a second print material as a second portion of the body distinct from the first portion and the second time. FIG. 1B includes an illustration of a portion of a system and method of forming a shaped abrasive particle according to an embodiment. As illustrated, the first deposition assembly **151** can be configured to deposit a first print material **122** and form at least the first portion **141** or the second portion **142**. Certain processes may utilize a second deposition assembly **143** configured to deposit a second print material **147** from a second deposition head (i.e., second nozzle) **144** onto a target to form the first portion **141** or the second portion **142**. In accordance with an embodiment, depositing the first material **122** can include forming the first portion **141** (e.g., in the form of a layer) at a first time and depositing



the second print material **147** as the second portion **142** (e.g., in the form of a layer) overlying the first portion **141**.

In accordance with one embodiment, the first portion **141** can have a first characteristic selected from the group of hardness, porosity, composition, and a combination thereof. Moreover, in another embodiment, the second portion **142** can have a second characteristic selected from the group of hardness, porosity, composition, and a combination thereof. In at least one embodiment, the first characteristic can be different from the second characteristic.

In certain instances, the first print material **122** can have a first composition and the second print material **147** can have a second composition. The first composition and second composition can be significantly different compared to each other. For example, the first and second compositions can differ from each other in terms of primary compositional species, which are distinct from trace amount species that are otherwise undetectable. In particular instances, the first and second compositions can be different from each other based on a difference of at least 2% of one of the primary compositional species in the first and second compositions.

In another embodiment, the second composition can have a different porosity relative to the porosity of the first composition. For example, in one embodiment, the first portion **141** may have a first porosity that is different than a second porosity of the second portion **142**. More particularly, the first portion can have a first porosity that is greater than the second porosity of the second portion **142**. According to at least one embodiment, the body can be formed to have selective porosity in particular portions, which may be suitable to facilitate certain the mechanical properties and abrasive capabilities of the shaped abrasive particle. In certain instances, the body can be formed with one or more portions (e.g., layers) having a select porosity to control the fracture mechanics of the shape abrasive particle.

Any another embodiment, the first print material **122** and the second print material **137** can be deposited in different regions within the body. For example, referring to FIG. 1, the first portion **141** can include the first print material **122** and the second portion **142** can include the second print material **147**. Controlled deposition of the first print material **122** and second print material **137** may be suitable to control the mechanical properties and abrasive characteristics of the shaped abrasive particle. For example, controlled deposition of the first print material **122** and second print material **137** may be suitable to form a shaped abrasive particle having a controlled fracturing behavior. For example, the first print material **122** can have a first composition and the second print material **147** can have a second composition, and the forming process can include selective deposition of the first and second compositions with respect to each other within the body to affect the fracturing behavior of the shaped abrasive particles. For example, in one particular embodiment, the first print material **122** and the second print material **147** can be deposited in alternative layers with respect to each other within a region of the body to form a composite body, which may be configured to control a self-sharpening behavior of the body.

In another embodiment, the first portion **141** can have a first hardness that is distinct from a second hardness associated with the second portion **142**. For example: one embodiment, the first portion **141** and the second portion **142** can have a difference in hardness relative to each other. In certain instances, the first hardness of the first portion **141** can be greater than the second hardness of the second portion **142**. In one particular instance, the first portion **141** and second portion **42** can be deposited in a particular

arrangement relative to each other, which may facilitate improved fracturing behavior and performance of the shaped abrasive particle.

In yet another embodiment, the first print material **122** and second print material **147** can be deposited in different regions of the body to form a composite body including a controlled arrangement of the regions relative to an intended orientation of the shaped abrasive particle in a fixed abrasive article. For example, the first print material **122** and second print material **147** can be arranged within the body such that when the shaped abrasive particle is deployed within a fixed abrasive article (e.g., bonded abrasive, coated abrasive, nonwoven abrasive, etc.) the first print material **122** and the second print material **147** are arranged relative to the intended orientation of the particle in the fixed abrasive. Control of the orientation of the first print material **122** and the second print material **147** within the body of the shaped abrasive particle and relative to the intended orientation of the body in the fixed abrasive may facilitate improved performance of the shaped abrasive particle and the fixed abrasive article.

In certain instances, the forming process can include depositing the first portion **141** having a first volume that is different than a second volume associated with the second portion **142**. For example, as illustrated in FIG. 1B, the first portion **141** can have a first volume that is different than a volume of the second portion **142**. More particularly, in certain instances, the first portion **141** can have a first volume that can be greater than the second volume of the second portion **142**. According to one particular embodiment, the volume of the portions can decrease as the forming process continues, such that the volume of portions formed subsequent to the initial portion decreases relative to the volume of the initial portion.

In accordance with an embodiment, the process of controlled deposition of the first portion and second portion may be suitable to control the size of certain features of the body of the shaped abrasive particle. For example, in at least one embodiment, the first portion **141** can have a first volume that is greater than a second volume of the second portion **142**. In such instances, the first portion **141** may define a central region of the body and the second portion **142** may define at least a portion of a corner of the body. More particularly, the first portion **141** may define a central region of the body and the second portion **142** may define an edge of the body. Notably, it will be appreciated that for certain shaped abrasive particles, it may be desirable to form certain portions of the body using smaller portions, such as the edges and the corners, such that these portions of the body have smaller features and can act as sharp edges or sharp corners. Accordingly, the forming process can include controlled volume deposition at certain portions of the body to facilitate control of the shape and size of certain features, which may facilitate improved performance of the shaped abrasive particle.

As further illustrated in FIG. 1B, the process of forming can include utilization of a first deposition assembly **151**, a first deposition head **153**, and a first print material **122**, that may be deposited from the first deposition assembly **151**. As noted in the embodiments herein, the utilization of a second deposition assembly **143** may facilitate the selective deposition of a second print material **147**, which may be distinct in various manners from the first print material **122** associated with the first deposition assembly **151**. For example, in at least one embodiment, the first portion **141** may be formed by one of the first deposition assembly **151** or the second deposition assembly **143**. As described in embodiments



herein, the process of forming the body can include depositing at least a first print material **122**, from the first deposition head **153** (i.e., nozzle **153**) onto a target, wherein the movement of the nozzle may be controlled by a computer program.

As will be appreciated, in certain forming processes, such as the forming process illustrated in FIGS. 1A and 1B, the process of forming can include controlling a three-dimensional movement of the nozzle configured for deposition of a print material relative to a target. In certain instances, controlling three-dimensional movement can include control of the nozzle in an X-axis, Y-axis, the Z-axis. Furthermore, as illustrated in FIG. 1B, the process may utilize a plurality of nozzles, wherein each nozzle of the plurality of nozzles can be configured to deposit a print material. The process can include control of each of the nozzle the plurality of nozzles and a three-dimensional movement, such as control of the nozzles in an X-axis, Y-axis, and the Z-axis.

In particular instances, the process of forming a body of the shaped abrasive particle having the features described herein may be facilitated by utilization of a nozzle **153** having a particular width **162**. For example, the nozzle **153** can have a width **162** that may be not greater than about 200 microns, such as not greater than about 150 microns, not greater than about 120 microns, not greater than about 100 microns, not greater than about 90 microns, not greater than about 85 microns, not greater than about 80 microns, not greater than about 75 microns, not greater than about 70 microns, not greater than about 65 microns, not greater than about 60 microns, not greater than about 55 microns, not greater than about 50 microns, not greater than about 45 microns, not greater than about 40 microns, not greater than about 35 microns, not greater than about 30 microns, not greater than about 25 microns, not greater than about 20 microns. Still, in at least one non-limiting embodiment, the nozzle **153** may have a width **162** of at least about 0.1 microns, such as at least about 1 microns, or even at least about 10 microns. It will be appreciated that the nozzle **153** can have a width **162** within a range between any of the minimum and maximum values noted above, including for example, within a range between at least about 0.1 microns and not greater than about 500 microns, such as within a range between at least about 0.1 microns and not greater than about 100 microns, or even within a range between at least about 0.1 microns and not greater than about 80 microns.

It will be appreciated that reference herein to a nozzle width **162** can include reference to an interior opening within the nozzle **153**. For example, referring briefly to FIG. 1E, an illustration of an end of a nozzle according to an embodiment is provided. As illustrated, the nozzle **153** can have an opening **155** defining a passage through which the print material can flow and be deposited. The opening **155** can have various two-dimensional shapes, including for example polygon and ellipsoidal. In accordance with one embodiment as illustrated in FIG. 1E, the opening **155** can have a circular two-dimensional shape, and thus the diameter **156** defines the width. As such, reference herein to the width of the nozzle **153**, will be understood to be reference to the width or diameter of the opening **155** depending upon the two-dimensional shape of the opening **155**.

In yet another embodiment, the nozzle **153** can have a tip length **161** defining a longest dimension of the nozzle **153**. Control of the tip length **161** of the nozzle **153** may facilitate improved deposition of the print material, and ultimately formation of features of the body of the shaped abrasive particle. In accordance with an embodiment, the nozzle can

have a tip length **161** of not greater than about 10 mm, such not greater than about 8 mm, not greater than about 6 mm, not greater than about 5 mm, or even not greater than about 4 mm. Still, and another non-limiting embodiment, the nozzle **153** can have a tip length **161** of at least about 0.1 mm, such as at least about 0.2 mm, at least about 0.5 mm, or even at least about 1 mm. It will be appreciated that the tip length **161** of the nozzle **153** can be within a range between any of the minimum maximum values noted above, including for example, a tip length **161** of at least about 0.1 mm and not greater than about 10 mm, such as at least about 0.1 mm and not greater than about 5 mm, or even at least about 0.2 mm and not greater than about 4 mm.

In accordance with one embodiment, the nozzle aspect ratio value (width/tip length) of the nozzle **153** may be controlled to facilitate improved deposition and formation of features of the body of the shaped abrasive particles. For example, the nozzle **153** can have a nozzle aspect ratio value (width/tip length) of not greater than about 0.8, such as not greater than about 0.6, not greater than about 0.5, or even not greater than about 0.4. Still, and another non-limiting embodiment, the nozzle **153** may have a nozzle aspect ratio value of at least about 0.001, such as at least about 0.005, or even at least about 0.008. It will be appreciated that the nozzle **153** can have a nozzle aspect ratio value within a range between any of the minimum and maximum values noted above, including for example, at least about 0.001 and not greater than about 0.8, such as at least about 0.005 and not greater than about 0.5, or even at least about 0.008 and not greater than about 0.4. It will also be appreciated that the second deposition head (i.e., second nozzle **144**) associated with the second deposition assembly **143** can have any of the features described in accordance with the first deposition assembly **151**.

In accordance with an embodiment, the process of forming can include controlling a deposition pressure to facilitate suitable deposition of the first print material and facilitating formation of a body having suitable features for use as a shaped abrasive particle. For example, in at least one embodiment, the deposition pressure can be not greater than about greater than about 5 MPa, such as not greater than about 4.5 MPa, not greater than about 4 MPa, not greater than about 3.5 MPa, not greater than about 3 MPa, not greater than about 2.5 MPa, not greater than about 2 MPa, not greater than about 1.8 MPa, not greater than about 1.5 MPa, not greater than about 1.3 MPa, not greater than about 1 MPa, not greater than about 0.9 MPa, not greater than about 0.8 MPa, or even not greater than about 0.7 MPa. Still, in at least one non-limiting embodiment, the deposition pressure can be at least about 0.005 MPa, such as at least about 0.01 MPa, at least about 0.05 MPa, at least about 0.08 MPa, or even at least about 0.1 MPa. It will be appreciated that the deposition pressure may be within a range between any of the minimum and maximum values noted above, including for example a deposition pressure or at least about 0.05 MPa and not greater than about 5 MPa, such as at least about 0.01 MPa and not greater than about 2 MPa, or even at least about 0.05 MPa and not greater than about 1.5 MPa.

In certain instances, the process of forming the body can include can include controlling the relationship between the nozzle width **162** and the deposition pressure to define a first forming factor (width/deposition pressure) having a value of at least about 0.2 microns/MPa, such as at least about 1 micron/MPa, at least about 2 microns/MPa, at least about 4 microns/MPa, at least about 6 microns/MPa, at least about 8 microns/MPa, at least about 10 microns/MPa, at least about 12 microns/MPa, at least about 14 microns/MPa, or even at



least about 16 microns/MPa. Still, in at least one non-limiting embodiment, the first forming factor can have a value of not greater than about  $1 \times 10^5$  microns/MPa, such as not greater than about  $1 \times 10^4$  microns/MPa, not greater than about 8000 microns/MPa, not greater than about 6000 microns/MPa, not greater than about 5000 microns/MPa, not greater than about 4000 microns/MPa, not greater than about 3000 microns/MPa, not greater than about 2000 microns/MPa, not greater than about 1000 microns/MPa, not greater than about 500 microns/MPa, not greater than about 200 microns/MPa, or even not greater than about 100 microns/MPa. It will be appreciated that the first forming factor can be within a range between any of the minimum and maximum values noted above, including for example, at least about at least about 0.2 microns/MPa and not greater than about  $1 \times 10^5$  microns/MPa, such as at least about 1 micron/MPa and not greater than about 6000 microns/MPa, or even at least about 2 microns/MPa and not greater than about 1000 microns/MPa.

In yet another embodiment, the process of forming the body can include control of the deposition rate that defines the rate at which the nozzle is moved. Suitable control the deposition rate can facilitate suitable formation of the features of the shaped abrasive particles according to the embodiments herein. For example, the forming process can include moving the nozzle a particular deposition rate, such as at least about 0.01 mm/s, at least about 0.05 mm/s, at least about 0.08 mm/s, at least about 0.1 mm/s, at least about 0.3 mm/s, at least about 0.5 mm/s, at least about 0.8 mm/s, at least about 1 mm/s, at least about 1.5 mm/s, at least about 2 mm/s, at least about 2.5 mm/s, at least about 3 mm/s. Still, in another non-limiting embodiment, the process of forming can include moving the nozzle at a deposition rate of not greater about 50 mm/s, such as not great about 30 mm/s, or even not greater than about 20 mm/s. It will be appreciated that the process of forming can include a deposition rate within a range between any of the minimum and maximum values noted above, including for example a deposition rate of at least about 0.01 mm/s and not greater than about 50 mm/s, such as at least about 0.1 mm/s and not greater than about 30 mm/s, or even at least about 1 mm/s and not greater than about 20 mm/s.

In accordance with a particular embodiment, the process of forming can include controlling a deposition volume of one or more print materials to form particular portions of the body of the shaped abrasive particle. For example, the process of forming can include controlling the deposition volume by changing the deposition volume of the print material, depending upon a portion of the body being formed. In at least one embodiment, the forming process can include depositing a smaller volume of material in a region defining a corner of the body as compared to the volume of material deposited in the region defining a major surface of the body. Such deposition procedures may be particularly suitable in the formation of sharp edges or corners which may be particularly suitable for the shaped abrasive particles of the embodiments herein.

The process of depositing controlled volumes can include controlling deposition volume by controlling at least one of a deposition pressure and the deposition rate of the nozzle. Particularly, the process of controlling deposition volume can include controlling a width, length, and height of the portion (e.g., the first portion 141) of the body formed at a first time. Moreover, controlling the deposition volume can further include controlling the width of the deposition nozzle used to form the particular portion. For example, a nozzle having a smaller width may be used to deposit the print

material associated with certain portions of the body (e.g., corners or edges) while a nozzle having a greater nozzle width may be used to deposit a print material associated with other portions, such as the major faces or interior portions of the body.

In still another instance, the process of forming can include controlling the relationship between the deposition rate and the deposition position. In one embodiment, controlling the relationship between deposition rate and deposition position can include changing the deposition rate depending upon the deposition position. More particularly, controlling the relationship between deposition rate and deposition position can include varying the deposition rate to change the size of features in the body. For example, in one embodiment, controlling the relationship between deposition rate and deposition position can include decreasing the deposition rate at a deposition position associated with the corner or edge of the body of the shaped abrasive particle relative to a deposition rate associated with a deposition position at a major surface or an interior portion of the body.

In yet another embodiment, the process of forming can include controlling the relationship between deposition pressure and deposition position. In at least one embodiment, the process of controlling the relationship between deposition pressure and the deposition position can include changing the deposition pressure depending upon the deposition position. In another embodiment, the process of controlling the relationship between the deposition pressure and deposition position can include varying the deposition pressure depending on the deposition pressure to change the features in the body. Particularly, in certain instances, the process of controlling the relationship between the deposition pressure and deposition position can include decreasing the deposition pressure at a deposition position associated with a corner or edge of the body of the shaped abrasive particle relative to a deposition pressure associated with a deposition position at a major surface or interior portion of the body.

In still another embodiment, the process of forming the body can include controlling a premove delay between the initial deposition of the print material from the deposition assembly and the movement of the deposition assembly, including for example, movement of the nozzle from which the print material can be deposited. For example, the premove delay may facilitate suitable formation of the features of the shaped abrasive particle, including those that may utilize certain deposition patterns, such as an outside-in and in-side out filling process. The delay between the initiation of the deposition process and the movement of the deposition assembly can facilitate ensuring that the In at least one embodiment, the process of forming the body can include utilizing a premove delay greater than about 0 seconds, such as at least about 0.1 seconds, or even at least about 0.5 seconds. In still another embodiment, the premove delay may be not greater than about 10 seconds, such as not greater about 8 seconds, not greater than about 6 seconds, or even not greater than about 4 seconds. It will be appreciated that the premove delay may be within a range between any of the minimum maximum values noted above, including for example, at least about 0.1 seconds and not greater than about 10 second, at least about 0.5 seconds and not greater than about 6 seconds.

For at least one embodiment, the process of forming the body can include controlling a shut off distance defining a distance the deposition assembly travels between the time at which pressure is no longer applied to the print material and the print material stops depositing from the deposition assembly. Control of the shutoff distance can facilitate



formation of the features of the shaped abrasive particles of the embodiments herein. The shutoff distance can be less than a dispense gap. In other instances, the shutoff distance can be greater than the dispense gap. According to another embodiment, the shutoff distance can be substantially the same as the dispense gap, such that the value of the dispense gap and the value of the shutoff distance do not vary from each other by more than 5%. In certain instances, the shutoff distance can be not greater than about 2 mm, not greater than about 1 mm, not greater than about 0.5 mm, not greater than about 0.2 mm, or even not greater than about 0.1 mm. In at least one non-limiting embodiment, the shutoff distance can be at least about 0.001 mm. It will be appreciated that the shutoff distance may be within a range between any of the minimum maximum values noted above, including for example, at least about 0.001 mm and not greater than about 1 mm, at least about 0.001 mm and not greater than about 0.2 mm.

The process of forming the body of the shaped abrasive particle can further include controlling a dispense gap **163**. The dispense gap **163** may define a distance between the end of the nozzle **153** and a target **125**, which may be a surface of a substrate or surface of another portion of where the print material is intended to be deposited. It has been noted that control of the dispense gap **163** can facilitate suitable formation of a shaped abrasive particle. In accordance with an embodiment, the dispense gap **163** can have a particular relationship relative to the width **162** of the nozzle **153**. For example, the dispense gap **163** can be not greater than about 10 W, wherein "W" represents the width **162** of the nozzle **153**. In another embodiment, the dispense gap **163** can be not greater than about 9 W, such as not greater than about 8 W, not greater than about 7 W, not greater than about 6 W, not greater than about 5 W, not greater than about 4 W, not greater than about 3 W, not greater than about 2 W, or even not greater than about 1 W. Still, and another in embodiment, the dispense gap **163** can be at least about 0.001 W, such as at least about 0.005 W, at least about 0.01 W, or even at least about 0.1 W. It will be appreciated that the dispense gap **163** can have a value within a range between any of the minimum and maximum values noted above, including for example, at least we spoke 0.001 W and not greater than about 10 W, at least about 0.05 W and not greater than about 5 W, or even at least about 0.01 W and not greater than about 2 W. It will be appreciated that the second deposition assembly **143** and nozzle **144** can be controlled such that the dispense gap associated with the use of the nozzle **144** can have the same features as noted above.

In accordance with another embodiment, the dispense gap **163** may have a particular relationship relative to the thickness "t", wherein "t" represents the average thickness of the portion of the body formed by the print material using the nozzle. For example, the dispense gap **163** associated with the nozzle **153** can be controlled relative to the average thickness "t" of the second portion **142** as formed by the nozzle **153**. In accordance with an embodiment, the dispense gap **163** can be not greater about 10 t, such as not greater than about 9 t, not greater about 8 t, not greater than about 7 t, not greater than about 6 t, not greater than about 5 t, not greater than about 4 t, not greater than about 3 t, not greater than about 2 t, or even not greater than about 1 t. Still, and another non-limiting embodiment, the dispense gap **163** can be at least about 0.001 t, such as at least about 0.05 t, or even at least about 0.01 t. It will be appreciated that the dispense gap **163** can have a value within a range between any of the minimum and maximum values noted above, including for example, at least about 0.001 t and not greater than about 10

t, such as at least about 0.05 t and not greater than about 5 t, or even at least about 0.01 t and not greater than about 2 t.

In at least one embodiment, the process of forming the body can include controlling the dispense gap **163** by varying the dispense gap **163** such that the first print material **122** contacts the target at a suitable distance upon exiting the end of the nozzle **153**. For example, the first print material **122** may exit the end of the nozzle **153** and the terminal and **123** of the first print material **122** may contact the target **125**. In particular instances, controlling the dispense gap **163** can include controlling the height of the end of the nozzle **153** above the target **125**, such that print material can contact the target upon exiting the nozzle **153** without forming a free droplet in the space between the end of the nozzle **153** and the target **125**. It is been noted that for certain types of print material, including those suitable for forming the shaped abrasive particle, the deposition process should be conducted to avoid the formation of free droplets, and during deposition a connection is maintained between the target **125** and the end of the nozzle **153** by the first print material **122**.

Furthermore, suitable formation of the body of the shaped abrasive particle can include controlling the dispense gap by varying the Z-directional distance between the end of the nozzle **153** and the target **125** based upon at least one of the parameters of the group including nozzle tip length **161**, the nozzle width **162**, the deposition pressure, the deposition rate, the deposition volume, the deposition position, the filling pattern of the print material, the dynamic yield stress of the print material, the static yield stress of the print material, the yield stress ratio of the print material, the viscosity of the print material, and a combination thereof. According to one embodiment, the process of forming the body can include controlling the dispense gap **163** by varying the dispense gap based upon the deposition pressure. In other instances, the process s of forming the body can include controlling the dispense gap **163** by varying the dispense gap **163** based upon the deposition position. In still other embodiments, the process of forming may include varying the dispense gap **163** depending on the deposition position, and more particularly, based on the resolution of the feature desired at the particular deposition position. For example, if the material is to be deposited at a position representing a corner or edge of the body of the shaped abrasive particle, the dispense gap **163** may be adjusted, and may be different compared to a dispense gap **163** used to form a major surface or interior portion of the body of the shaped abrasive particle. Furthermore, the process of controlling the dispense gap **163** can include varying the dispense gap **163** to control the volume of material deposited at a deposition position, which may be suitable for formation of certain features of the body, including for example, a corner, an edge, a major surface, or interior portion of the body.

In accordance with an embodiment, the process of forming the body of the shaped abrasive particle using the additive manufacturing process can include controlling a filling pattern that defines the order of forming the portions of the body. The filling pattern and particular process associated with the filling pattern can be selected to form a suitable shaped abrasive particle and may facilitate improved performance of the shaped abrasive particle and fixed abrasives incorporating the shaped abrasive particle. As noted in the embodiments herein, the first portion **141** may be formed into a two-dimensional or three-dimensional shape depending upon the desired shape of the first portion



**141** and the final shape of the shaped abrasive particle. Any one of the portions of the shaped abrasive particle (e.g., the first portion **141**) can be formed in a particular order defined by a filling pattern. The filling pattern can define a deposition process including but not limited to an outside-in filling process, an inside-out filling process, a side-to-side filling process, a bottom-up filling process, and a combination thereof.

For example, referring to FIG. **1C**, a top-down view of a filling pattern for forming a portion of a shaped abrasive particle according to an embodiment is provided. As illustrated, the first portion **181** can be in the form of a layer and may be formed by initiating deposition of the print material at the position **182**. The deposition assembly and the process of depositing the print material may traverse along the path **187** in the direction **184** from the position **182** to the position **183**, where the deposition process is stopped and the first portion **181** is completed. Such a filling pattern can be an outside-in filling process. The outside-in filling process can be characterized by a process that initially forms at least a portion of an outer periphery **185** of the first portion **181** and subsequently forms the interior portion **186**.

In another embodiment, an inside-out filling process may be utilized that can include a process of depositing the print material to initially form an interior region of a portion and subsequently forming the peripheral regions of the portion. For example, referring again to FIG. **1C**, a filling pattern using an inside-out filling process can be undertaken in the opposite direction of the outside-in filling process. The inside-out filling process can initiate deposition at the position **183** and traverse along the path **187** in the direction opposite the direction **184** to the position **182** where the deposition process can be stopped and the first portion **181** is formed. In such an embodiment, the interior portion **186** of the first portion **181** is formed first and the outer periphery **185** of the first portion **181** is formed subsequent to and around the interior portion **186**.

Referring to FIG. **1D**, a side-to-side filling process is illustrated according to an embodiment. In a side-to-side filling process, the deposition assembly can initiate deposition of the print material at position **187**, and move laterally back and forth depositing the print material and stopping at position **188** to form a first portion.

FIG. **1D** can also represent an embodiment of a bottom-up filling process in another embodiment. It will be appreciated that for a bottom-up filling process, the print material can be deposited in a pattern that is based upon formation of one or more overlying layers. For example, in a bottom-up filling process, the deposition assembly may initiate deposition of the print material at position **187** and move back and forth building the structure upon itself in a vertical direction and ending the deposition process at position **188**.

The process of forming the body can include controlling a filling pattern such that a first portion of the body formed at a first time can be formed using a first filling pattern, and a second portion of the body formed a second time, which is distinct from the first time, can be formed using a second filling pattern that is distinct from the first filling pattern. For example, in one particular embodiment, the filling pattern used to form the body can include forming a first portion by an outside-in filling process and a second portion by an inside-out filling process. More particularly, referring again to FIG. **1C**, a first portion **181** in the form of a first layer can be formed by an outside-in forming process and subsequently a second portion can be formed over the first portion **181**. The second portion can be in the form of a layer overlying the first portion **181**, and the second portion can be

formed by an inside-out filling process, wherein deposition can be initiated at a position directly above position **183** and concluded at a position directly above position **182**.

According to a particular embodiment, the print material, which can include a mixture, can have a particular dynamic yield stress ( $\sigma_d$ ) that may facilitate suitable formation of the body of the shaped abrasive particle. For example, the print material may have a dynamic yield stress ( $\sigma_d$ ) of at least about 100 Pa, at least about 120 Pa, at least about 140 Pa, at least about 160 Pa, at least about 180 Pa, at least about 200 Pa. Still, in another non-limiting embodiment, the print material may have a dynamic yield stress ( $\sigma_d$ ) of not greater than about 1500 Pa, not greater than about 1300 Pa, not greater than about 1200 Pa, not greater than about 1100 Pa, not greater than about 1000 Pa. It will be appreciated that the print material can have a dynamic yield stress ( $\sigma_d$ ) within a range between any of the minimum maximum values above, including for example, at least about 100 Pa and not greater than about 1500 Pa, at least about 160 Pa and not greater than about 1200 Pa, or even at least about 200 Pa, and not greater than about 1200 Pa.

The process of forming the body can include controlling at least one process parameter such as the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the dynamic yield stress ( $\sigma_d$ ) of the print material. It will be appreciated that the process can include controlling a combination of the foregoing process parameters based on the dynamic yield stress. Control of one or more process parameters based on the dynamic yield stress may facilitate improved formation of a shaped abrasive particle.

In another embodiment, the print material, which may include a mixture, may have a particular static yield stress ( $\sigma_s$ ) that may facilitate suitable formation of the body of the shaped abrasive particle. For example, the may have a static yield stress ( $\sigma_s$ ) of at least about 180 Pa, such as at least about 200 Pa, at least about 250 Pa, at least about 300 Pa, at least about 350 Pa, at least about 400 Pa, at least about 450 Pa, at least about 500 Pa, at least about 550 Pa, at least about 600 Pa. In another non-limiting embodiment, the static yield stress ( $\sigma_s$ ) can be not greater than about 20,000 Pa, such as not greater than about 18,000 Pa, not greater than about 15,000 Pa, not greater than about 5000 Pa, not greater than about 1000 Pa. It will be appreciated that the print material can have a static yield stress ( $\sigma_s$ ) within a range between any of the minimum and maximum values noted above, including for example, at least about 180 Pa and not greater than about 20,000 Pa, at least about 400 Pa and not greater than about 18,000 Pa, or even at least about 500 Pa and not greater than about 5000 Pa.

The process of forming the body can include controlling at least one process parameter such as the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the static yield stress ( $\sigma_s$ ) of the print material. It will be appreciated that the process can include controlling a combination of the foregoing process parameters based on the static yield stress. Control of one or more process parameters based on the static yield stress may facilitate improved formation of a shaped abrasive particle.

In certain instances, the process of forming the body of the shaped abrasive particle can include forming a print material having a particular relationship between the static yield stress ( $\sigma_s$ ) and the dynamic yield stress ( $\sigma_d$ ). In one embodiment, the print material may be formed such that the



static yield stress is different than the dynamic yield stress. More particularly, the print material may be formed such that it is a shear-thinning print material configured to be suitably extruded from the nozzle and yet have control dimensional stability to avoid significant movement (e.g., slumping) once deposited on the target.

In one embodiment, the print material, which may include a mixture, can have a static yield stress that is greater than the dynamic yield stress that may facilitate formation of the shaped abrasive particle. More particularly, the print material may be formed such that it has a particular yield stress ratio ( $\sigma_d/\sigma_s$ ), such as not greater than about 1, not greater than about 0.99, not greater than about 0.97, not greater than about 0.95, not greater than about 0.9, not greater than about 0.85, not greater than about 0.8, not greater than about 0.75, not greater than about 0.7, not greater than about 0.65, not greater than about 0.6, not greater than about 0.55, or even not greater than about 0.5. Still, in one non-limiting embodiment, the yield stress ratio ( $\sigma_d/\sigma_s$ ) can be at least about 0.01, such as at least about 0.05, at least about 0.08, at least about 0.1, at least about 0.15, at least about 0.2, at least about 0.25, at least about 0.3, at least about 0.35, at least about 0.4, or even at least about 0.45, or even at least 0.5. It will be appreciated that the print material can have a yield stress ratio within a range between any of the minimum and maximum values noted above, including for example, a yield stress ratio of not greater than one and at least about 0.01, such as not greater than about 0.97 and at least about 0.1, or even not greater than about 0.8 and at least about 0.2.

The process of forming the body can include controlling at least one process parameter such as the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the yield stress ratio ( $\sigma_d/\sigma_s$ ) of the print material. It will be appreciated that the process can include controlling a combination of the foregoing process parameters based on the yield stress ratio ( $\sigma_d/\sigma_s$ ). Control of one or more process parameters based on the yield stress ratio ( $\sigma_d/\sigma_s$ ) may facilitate improved formation of a shaped abrasive particle.

In yet another embodiment, the print material may be formed to have a particular viscosity to facilitate formation of the body of the shaped abrasive particle having the features of the embodiments herein. For example, the print material can have a viscosity of at least about  $4 \times 10^3$  Pa s, such as at least about  $5 \times 10^3$  Pa s, at least about  $6 \times 10^3$  Pa s, at least about  $7 \times 10^3$  Pa s, at least about  $7.5 \times 10^3$  Pa s. In another non-limiting embodiment, the print material can have a viscosity of not greater than about  $20 \times 10^3$  Pa s, such as not greater than about  $18 \times 10^3$  Pa s, not greater than about  $15 \times 10^3$  Pa s, or even not greater than about  $12 \times 10^3$  Pa s. Still, it will be appreciated that the print material can have a viscosity within a range including any of the minimum and maximum values noted above, including but not limited to, at least about  $4 \times 10^3$  Pa s and not greater than about  $20 \times 10^3$  Pa s, such as at least about  $5 \times 10^3$  Pa s and not greater than about  $18 \times 10^3$  Pa s, at least about  $6 \times 10^3$  Pa s and not greater than about  $15 \times 10^3$  Pa s. For those print materials that are shear-thinning or otherwise non-Newtonian materials, the above viscosity values may be an apparent viscosity. The viscosity can be measured by incrementally decreasing a shear rate from  $100 \text{ s}^{-1}$  to  $2 \text{ s}^{-1}$  without pre-shearing the print material using a parallel plate rheometer.

The process of forming the body can include controlling at least one process parameter such as the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition

position, and the filling pattern of the print material based on the viscosity of the print material. It will be appreciated that the process can include controlling a combination of the foregoing process parameters based on the viscosity. Control of one or more process parameters based on the viscosity may facilitate improved formation of a shaped abrasive particle.

It will be appreciated that any of the forming processes herein can be combined with other processes, including conventional processes of printing, spraying, deposition, casting, molding, and the like. In certain instances, the additive manufacturing process may be used to form a preform of the body of the shaped abrasive particle. The preform can be a skeleton of the body, such as an outer portion or an inner portion that is first created, and processed further through one or more other processes to create the shaped abrasive particle. For example, in at least one embodiment, an additive manufacturing process may be used to form an exterior portion of the body, such as the peripheral walls of the body. After forming the exterior portion, a subsequent operation may be utilized to form an interior portion of the body, including for example, a separate forming process (e.g., a filling process) using the same material or a different material used in the additive manufacturing process used to form the exterior portion. One suitable forming process to form the interior portion can include a spraying process or printing process. The two step process of forming the different portions of the body may facilitate efficient processing over a process relying only on an additive manufacturing process to form the entire body of the shaped abrasive particle. It will be appreciated that the above example is non-limiting and other two-step processes including the additive manufacturing process may be used. It is envisioned that one may form an interior portion of the body using the additive manufacturing process and forming an exterior portion of the body using a different process than the additive manufacturing process.

The shaped abrasive particle formed by an additive manufacturing process as defined herein can include a variety of other suitable dimensions and features. In an embodiment, the body of the shaped abrasive particle includes a first major surface, a second major surface, and at least one side surface extending between the first major surface and the second major surface.

The bodies of the shaped abrasive particles can have a percent flashing that may facilitate improved performance. Notably, the flashing defines an area of the body as viewed along one side, wherein the flashing extends from a side surface of the body **301** within the boxes **302** and **303**, as illustrated in FIG. 3. The flashing can represent tapered regions proximate to the upper surface **303** and bottom surface **304** of the body **301**. The flashing can be measured as the percentage of area of the body **301** along the side surface contained within a box extending between an innermost point of the side surface (e.g., **321**) and an outermost point (e.g., **322**) on the side surface of the body **301**. In one particular instance, the body **301** can have a particular content of flashing, which can be the percentage of area of the body **301** contained within the boxes **302** and **303** compared to the total area of the body **301** contained within boxes **302**, **303**, and **304**. The flashing can represent tapered regions proximate to first and second major surfaces of the body. The flashing can be measured as the percentage of area of the body along the side surface contained within a box extending between an innermost point of the side surface and an outermost point on the side surface of the body.



In one particular instance, the body can have a particular content of flashing, which can be the percentage of area of the body within the tapered regions compared to the total area of the body. According to one embodiment, the percent flashing (f) of the body can be at least about 1%. In another embodiment, the percent flashing can be greater, such as at least about 2%, at least about 3%, at least about 5%, at least about 8%, at least about 10%, at least about 12%, such as at least about 15%, at least about 18%, or even at least about 20%. Still, in a non-limiting embodiment, the percent flashing of the body 301 can be controlled and may be not greater than about 45%, such as not greater than about 40%, not greater than about 35%, not greater than about 30%, not greater than about 25%, not greater than about 20%, not greater than about 18%, not greater than about 15%, not greater than about 12%, not greater than about 10%, not greater than about 8%, not greater than about 6%, or even not greater than about 4%. In a particular embodiment, the body can be essentially free of flashing. It will be appreciated that the percent flashing of the body can be within a range between any of the above minimum and maximum percentages. Moreover, it will be appreciated that the above flashing percentages can be representative of an average flashing percentage or a median flashing percentage for a batch of shaped abrasive particles.

The shaped abrasive particles of the embodiments herein can be formed such that the body includes a crystalline material, and more particularly, a polycrystalline material. Notably, the polycrystalline material can include grains. In one embodiment, the body can be essentially free of an organic material including, for example, a binder. More particularly, the body can consist essentially of a polycrystalline material.

In one aspect, the body of the shaped abrasive particle can be an agglomerate including a plurality of particles, grit, and/or grains bonded to each other to form the body. Suitable grains can include nitrides, oxides, carbides, borides, oxynitrides, oxyborides, diamond, and a combination thereof. In particular instances, the grains can include an oxide compound or complex, such as aluminum oxide, zirconium oxide, titanium oxide, yttrium oxide, chromium oxide, strontium oxide, silicon oxide, and a combination thereof. In one particular instance, the ceramic article is formed such that the grains forming the body include alumina, and more particularly, may consist essentially of alumina. In another instance, the body of the ceramic article can consist essentially of alumina. Moreover, in particular instances, the body of the shaped abrasive particle can be formed from a seeded sol gel.

In an embodiment, the body can include a polycrystalline material. The grains (e.g., crystallites) contained within the body may have an average grain size that is generally not greater than about 100 microns. In other embodiments, the average grain size can be less, such as not greater than about 80 microns, not greater than about 50 microns, not greater than about 30 microns, not greater than about 20 microns, not greater than about 10 microns, or even not greater than about 1 micron. Still, the average grain size of the grains contained within the body can be at least about 0.01 microns, such as at least about 0.05 microns, such as at least about 0.08 microns, at least about 0.1 microns, or even at least about 0.5 microns. It will be appreciated that the grains can have an average grain size within a range between any of the minimum and maximum values noted above.

In accordance with certain embodiments, the shaped abrasive particle can be a composite article including at least two different types of grains within the body. It will be

appreciated that different types of grains are grains having different compositions with regard to each other. For example, the body can be formed such that it includes at least two different types of grains, wherein the two different types of grains can be nitrides, oxides, carbides, borides, oxynitrides, oxyborides, diamond, and a combination thereof.

In some embodiments, the body of the ceramic article can include a variety of suitable additives. For example, the additive can include an oxide. In a particular embodiment, the additive can include a metal element, such as a rare-earth element. In another particular embodiment, the additive can include a dopant material. For example, the dopant material can include an element or compound selected from the group consisting of an alkali element, an alkaline earth element, a rare-earth element, a transition metal element, and a combination thereof. In yet another embodiment, the dopant material can include an element selected from the group consisting of hafnium, zirconium, niobium, tantalum, molybdenum, vanadium, lithium, sodium, potassium, magnesium, calcium, strontium, barium, scandium, yttrium, lanthanum, cesium, praseodymium, chromium, cobalt, iron, germanium, manganese, nickel, titanium, zinc, and a combination thereof.

According to a particular embodiment, the forming process can form precursor shaped abrasive particles. The precursor shaped abrasive particles may undergo further processing to form shaped abrasive particles. Such further processing can include, but need not be limited to, drying, heating, evolving, volatilizing, sintering, doping, drying, curing, reacting, radiating, mixing, stirring, agitating, calcining, comminuting, sieving, sorting, shaping, and a combination thereof.

Drying may include removal of a particular content of material, including volatiles, such as water. In accordance with an embodiment, the drying process can be conducted at a drying temperature of not greater than about 300° C., such as not greater than about 280° C., or even not greater than about 250° C. Still, in one non-limiting embodiment, the drying process may be conducted at a drying temperature of at least about 50° C. It will be appreciated that the drying temperature may be within a range between any of the minimum and maximum temperatures noted above. Furthermore, the drying process may be conducted for a particular duration. For example, the drying process may be not greater than about six hours.

The process of forming the precursor shaped abrasive particle to a finally-formed shaped abrasive particle may further comprise a sintering process. Sintering of the precursor shaped abrasive particle may be utilized to densify the article, which is generally in a green state as the precursor shaped abrasive particle. In a particular instance, the sintering process can facilitate the formation of a high-temperature phase of the ceramic material. For example, in one embodiment, the precursor shaped abrasive particle may be sintered such that a high-temperature phase of the material is formed, including for example, alpha alumina. According to one particular embodiment, the shaped abrasive particle can be a shaped abrasive particle having at least about 90 wt % alpha alumina for the total weight of the particle. In a more particular instance, the content of alpha alumina may be greater such that the shaped abrasive particle may consist essentially of alpha alumina.

In accordance with another aspect, a method of forming a fixed abrasive article including shaped abrasive particles formed through the additive manufacturing process can also be accomplished. For example, the process of forming a



fixed abrasive article can include forming a plurality of shaped abrasive particles on a substrate, where each of the shaped abrasive particles of the plurality of shaped abrasive particles have a body formed by an additive manufacturing process. It will be appreciated that the fixed abrasive article may include a bonded abrasive article, a coated abrasive article, and the like. It will further be appreciated that the substrate can include, for example, a backing.

In at least one embodiment, the forming process can be conducted such that the shaped abrasive particles are formed directly overlying the substrate. For example, in accordance with an embodiment, a perspective view illustration of a fixed abrasive article including shaped abrasive particles overlying the substrate is provided in FIG. 2. As illustrated, the fixed abrasive article **200** can include a first shaped abrasive particle **201** overlying a substrate **204** and a second shaped abrasive particle **211** overlying the substrate **204**.

It will be appreciated that the process of forming a shaped abrasive particle as part of a fixed abrasive article can include any of the processes described herein in other embodiments. For example, as indicated herein, the body of each of the shaped abrasive particles **201** and **211** of the plurality of shaped abrasive particles can be formed according to a digital model. As further illustrated, and described herein, each of the shaped abrasive particles **201** and **211** can have bodies formed from a plurality of portions **203**, which may be discrete from each other, or may have undergone further processing (e.g., modifying) to join the portions together to form each of the bodies of the shaped abrasive particles **201** and **211**.

As described in the embodiments herein, the additive manufacturing process of forming the body according to a digital model can include depositing a first print material as a first portion of the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles at a first time. Furthermore, the process can include depositing a second print material as a second portion of the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles at a second time that is different than the first time. In a particular embodiment, the additive manufacturing process also can include preferentially modifying one of the first portion and the second portion to join the first portion and the second portion and form a subsection of the body of the shaped abrasive particle.

In accordance with a particular embodiment, the forming process can be conducted directly on at least a portion of a bonding layer **231**, which may be overlying the substrate. The bonding layer **231** can include a material such as an inorganic material, a vitreous material, a crystalline material, an organic material, a resin material, a metal material, a metal alloy, and a combination thereof. The bonding layer may be a continuous layer or material or may be a discontinuous layer of material having discrete bonding regions separated by gaps, wherein essentially no bonding material is present. The process of forming can include selectively forming shaped abrasive particles in regions corresponding to the discrete bonding regions, such that each discrete bonding region has one or more shaped abrasive particles contained therein.

In some embodiments of the forming process, the substrate **204** may be translated through a forming zone. In the forming zone, at least one shaped abrasive particle of the plurality of shaped abrasive particles can be formed overlying the substrate. In particular instances, the translation of the substrate **204** can include a stepped translation process, wherein the substrate **204** may be translated a certain distance and stopped to allow the formation of the shaped

abrasive particle to occur. After a shaped abrasive particle is suitably formed overlying the substrate **204**, the stepped translation process can continue by translating the substrate **204** in a desirable direction by a known distance again and stopping again to facilitate the formation of another shaped abrasive particle at a particular location on substrate **204**. In one embodiment, as shown in FIG. 2, the substrate **204** may be translated to a first position defined by the position of the shaped abrasive particle **211**, wherein at a first time the shaped abrasive particle **211** can be formed by an additive manufacturing process. After suitable formation of the shaped abrasive particle **211**, the substrate **204** may be translated in a direction to a position identified by the position of the shaped abrasive particle **201** overlying the substrate **204**. At that point, the substrate **204** may be stopped to allow the formation of the shaped abrasive particle **201** at the location provided in FIG. 2.

As such, a plurality of shaped abrasive particles can be formed at predetermined locations on the substrate **204**. Notably, in certain instances, the formation of the fixed abrasive article **200** can be conducted such that each of the shaped abrasive particles can be placed on the backing, and such placement can be conducted simultaneously with the formation of the body of each of the shaped abrasive particles.

Furthermore, it will be appreciated that such a process of forming a fixed abrasive article also can include orienting each of the shaped abrasive particles of the plurality of the shaped abrasive particles relative to the substrate. Such orienting can facilitate the controlled orientation of each of the shaped abrasive particles relative to each other as well as relative to the substrate **204**. For example, the process of forming the body of a shaped abrasive particle can be conducted simultaneously with the process of orienting the shaped abrasive particle relative to the substrate **204**.

In more particular instances, each shaped abrasive particle may be formed in a manner such that it has a controlled orientation with respect to a vertical orientation, a rotational orientation, a flat orientation, or a side orientation. In the flat orientation, a bottom surface of a shaped abrasive particle can be closest to a surface of the substrate **204** (e.g., a backing) and an upper surface of the shaped abrasive particle can be directed away from the substrate **204** and configured to conduct initial engagement with a workpiece. Note herein that vertical orientation can refer to the orientation of the particles as viewed in a plane perpendicular to the belt, whereas rotational orientation refers to the orientation of a shaped abrasive particle as viewed in a plane parallel to the belt.

Turning briefly to FIG. 4, a coated abrasive article is illustrated including shaped abrasive particles in a particular orientation relative to the substrate. For example, the coated abrasive article **400** can include a substrate **401** (i.e., a backing) and at least one adhesive layer overlying a surface of the substrate **401**. The adhesive layer can include a make coat **403** and/or a size coat **404**. The coated abrasive **400** can include abrasive particulate material **410**, which can include shaped abrasive particles **405** of the embodiments herein and a second type of abrasive particulate material **407** in the form of diluent abrasive particles having a random shape, which may not necessarily be shaped abrasive particles. The make coat **403** can be overlying the surface of the substrate **401** and surrounding at least a portion of the shaped abrasive particles **405** and second type of abrasive particulate material **407**. The size coat **404** can be overlying and bonded to the shaped abrasive particles **405** and second type of abrasive particulate material **407** and the make coat **403**.



According to one embodiment, the shaped abrasive particles **405** herein can be oriented in a predetermined orientation relative to each other and the substrate **401**. As illustrated in FIG. **4**, the shaped abrasive particles **405** can be oriented in a flat orientation relative to the substrate **401**. In the flat orientation, the bottom surface **414** of the shaped abrasive particles can be closest to a surface of the substrate **401** (i.e., the backing) and the upper surface **413** of the shaped abrasive particles **405** can be directed away from the substrate **401** and configured to conduct initial engagement with a workpiece.

According to another embodiment, the shaped abrasive particles **505** can be placed on a substrate **501** in a predetermined side orientation, such as that shown in FIG. **5**. In particular instances, a majority of the shaped abrasive particles **505** of the total content of shaped abrasive particles **505** on the abrasive article **500** can have a predetermined side orientation. In the side orientation, the bottom surface **414** of the shaped abrasive particles **505** can be spaced away and angled relative to the surface of the substrate **501**. In particular instances, the bottom surface **414** can form an obtuse angle (A) relative to the surface of the substrate **501**. Moreover, the upper surface **513** can be spaced away and angled relative to the surface of the substrate **501**, which in particular instances, may define a generally acute angle (B). In a side orientation, a side surface **416** of the shaped abrasive particle can be closest to the surface of the substrate **501**, and more particularly, may be in direct contact with a surface of the substrate **501**.

According to another embodiment, one or more shaped abrasive particles can be placed on a substrate in a predetermined side orientation. In particular instances, a majority of the shaped abrasive particles of the plurality of shaped abrasive particles on the abrasive article can have a predetermined side orientation. In the side orientation, a bottom surface of the shaped abrasive particle can be spaced away and angled relative to the surface of the substrate **204**. In particular instances, the bottom surface can form an obtuse angle relative to the surface of the substrate **204**. Moreover, the upper surface of the shaped abrasive particle is spaced away and angled relative to the surface of the substrate **204**, which in particular instances, may define a generally acute angle. In a side orientation, one or more side surfaces of the shaped abrasive particle can be closest to the surface of the substrate **204**, and more particularly, may be in direct contact with a surface of the substrate **204**.

For certain fixed abrasive articles herein, at least about 55% of the plurality of shaped abrasive particles on the fixed abrasive article **200** can be oriented in a side orientation. Still, the percentage may be greater, such as at least about 60%, at least about 65%, at least about 70%, at least about 75%, at least about 77%, at least about 80%, at least about 81%, or even at least about 82%. And for one non-limiting embodiment, a fixed abrasive article **200** may be formed using the shaped abrasive particles herein, wherein not greater than about 99% of the plurality of shaped abrasive particles are oriented in a side orientation.

Furthermore, the abrasive articles made with the shaped abrasive particles formed by the additive manufacturing processes described herein can utilize various contents of the shaped abrasive particles. For example, the fixed abrasive articles can be coated abrasive articles including a single layer of the shaped abrasive particles in an open coat configuration or a closed coat configuration. For example, the plurality of shaped abrasive particles can define an open coat abrasive product having a coating density of shaped abrasive particles of not greater than about 70 particles/cm<sup>2</sup>.

In other instances, the density of shaped abrasive particles per square centimeter of the open coat abrasive article may be not greater than about 65 particles/cm<sup>2</sup>, such as not greater than about 60 particles/cm<sup>2</sup>, not greater than about 55 particles/cm<sup>2</sup>, or even not greater than about 50 particles/cm<sup>2</sup>. Still, in one non-limiting embodiment, the density of the open coat coated abrasive using the shaped abrasive particles herein can be at least about 5 particles/cm<sup>2</sup>, or even at least about 10 particles/cm<sup>2</sup>. It will be appreciated that the density of shaped abrasive particles per square centimeter of an open coat coated abrasive article can be within a range between any of the above minimum and maximum values.

In an alternative embodiment, the plurality of shaped abrasive particles can define a closed coat abrasive product having a coating density of shaped abrasive particles of at least about 75 particles/cm<sup>2</sup>, such as at least about 80 particles/cm<sup>2</sup>, at least about 85 particles/cm<sup>2</sup>, at least about 90 particles/cm<sup>2</sup>, at least about 100 particles/cm<sup>2</sup>. Still, in one non-limiting embodiment, the density of the closed coat coated abrasive using the shaped abrasive particle herein can be not greater than about 500 particles/cm<sup>2</sup>. It will be appreciated that the density of shaped abrasive particles per square centimeter of the closed coat abrasive article can be within a range between any of the above minimum and maximum values.

The substrate of the fixed abrasive articles described herein can include a variety of suitable materials, including an organic material such as polymers, an inorganic material, such as metal, glass, ceramic, and a combination thereof. In certain instances, the substrate can include a woven material. However, the substrate may be made of a non-woven material. In another embodiment, the substrate can include a material selected from the group consisting of cloth, paper, film, fabric, fleeced fabric, vulcanized fiber, woven material, non-woven material, webbing, polymer, resin, phenolic resin, phenolic-latex resin, epoxy resin, polyester resin, urea formaldehyde resin, polyester, polyurethane, polypropylene, polyimides, and a combination thereof.

In certain situations, the shaped abrasive particles may be placed on a first substrate, which facilitates further processing of the shaped abrasive particles, such as drying, heating, and sintering. The substrate may be a permanent article. However, in other instances, the substrate may be a sacrificial article, that can be partially or completely destroyed during further processing of the shaped abrasive particles. The first substrate may be combined with a second substrate after processing of the shaped abrasive particles, for later forming the abrasive article. For example, in instances using a permanent first substrate, the first substrate may be combined with the second substrate to form a composite substrate that is used in the finally-formed fixed abrasive article. In still other instances where a sacrificial substrate is used, the placement and orientation of the shaped abrasive particles on the first substrate may be substantially maintained through the forming process, even though the first substrate is partially or completely removed. The finally-formed shaped abrasive particles may be combined with a second substrate while maintaining their placement and orientation to facilitate formation of the finally-formed abrasive article.

In some embodiments, the substrate of the fixed abrasive articles also can include a suitable additive or additives. For example, the substrate can include an additive chosen from the group consisting of catalysts, coupling agents, curants, anti-static agents, suspending agents, anti-loading agents, lubricants, wetting agents, dyes, fillers, viscosity modifiers, dispersants, defoamers, and grinding agents.



The fixed abrasive articles described herein, in addition to including a substrate (e.g., a backing), can include at least one adhesive layer, such as a bonding layer, overlying a surface of the substrate. The adhesive layer can include a make coat. A polymer formulation may be used to form any of a variety of layers of the abrasive article such as, for example, a frontfill, a pre-size, the make coat, the size coat, and/or a supersize coat. When used to form the frontfill, the polymer formulation generally includes a polymer resin, fibrillated fibers (preferably in the form of pulp), filler material, and other optional additives. Suitable formulations for some frontfill embodiments can include material such as a phenolic resin, wollastonite filler, defoamer, surfactant, a fibrillated fiber, and a balance of water. Suitable polymeric resin materials include curable resins selected from thermally curable resins including phenolic resins, urea/formaldehyde resins, phenolic/latex resins, as well as combinations of such resins. Other suitable polymeric resin materials may also include radiation curable resins, such as those resins curable using electron beam, UV radiation, or visible light, such as epoxy resins, acrylated oligomers of acrylated epoxy resins, polyester resins, acrylated urethanes and polyester acrylates and acrylated monomers including monoacrylated, multiacrylated monomers. The formulation can also comprise a nonreactive thermoplastic resin binder which can enhance the self-sharpening characteristics of the deposited abrasive composites by enhancing the erodability. Examples of such thermoplastic resin include polypropylene glycol, polyethylene glycol, and polyoxypropylene-polyoxyethene block copolymer, etc. Use of a frontfill on the substrate can improve the uniformity of the surface, for suitable application of the make coat and improved application and orientation of shaped abrasive particles in a predetermined orientation.

The abrasive article also can include abrasive particulate material, which can include shaped abrasive particles of the embodiments herein and a second type of abrasive particulate material in the form of diluent abrasive particles having a random shape, which may not necessarily be shaped abrasive particles. In an embodiment, the make coat can be overlying the surface of the substrate and surrounding at least a portion of the shaped abrasive particles and second type of abrasive particulate material. In another embodiment, the make coat can be bonded directly to at least a portion of the substrate. The make coat can include a variety of suitable materials including, for example, an organic material, a polymeric material, or a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

The adhesive layer also can include a size coat. The size coat can be overlying at least a portion of the plurality of shaped abrasive particles described herein, as well as any second type of abrasive particulate material and the make coat. The size coat also can be bonded directly to at least a portion of the plurality of shaped abrasive particles. Like the make coat, the size coat can include a variety of suitable materials including, for example, an organic material, a polymeric material, or a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

The fixed abrasive articles, including the shaped abrasive particles and the additive manufacturing processes used to form the shaped abrasive particles as described herein represent a departure from and improvement over conventional fixed abrasive articles. While many processes of forming shaped abrasive particles, including shaped abrasive particles, rely primarily on templating and/or subtractive processes (e.g., molding, screen printing, etc.), the processes disclosed in the embodiments herein include a forming process for forming shaped abrasive particles using an additive manufacturing process. Moreover, the processes may further utilize a digital model, which can be used to analyze, compare, and adapt the forming process, which may facilitate improved dimensional uniformity, shape, placement, and ultimately performance of the article utilizing the shaped abrasive particles.

While it will be appreciated that the shaped abrasive particles of the embodiments can have any suitable shape, FIGS. 6 through 19 provide illustrations of some exemplary, non-limiting shaped abrasive particles that may be made according to the embodiments herein.

In particular, in one embodiment provided in FIG. 18, the shaped abrasive particle 1800 can include a body 1801 including a first layer 1802 and a second layer 1803 overlying the first layer 1802. According to an embodiment, the body 1801 can have layers 1802 and 1803 that are arranged in a stepped configuration relative to each other. A stepped configuration can be characterized by at least one plateau region 1820 on a surface 1810 of the first layer 1802 between a side surface 1804 of the first layer 1802 and a side surface 1805 of the second layer 1803. The size and shape of the plateau region 1820 may be controlled or predetermined by one or more processing parameters and may facilitate an improved deployment of the abrasive particles into an abrasive article and performance of the abrasive article.

In one embodiment, the plateau region 1802 can have a lateral distance 1821, which can be defined as the greatest distance between an edge 1807 between the upper surface 1810 of the first layer 1802 and a side surface 1804 of the first layer to the side surface 1805 of the second layer. Analysis of the lateral distance 1821 may be facilitated by a top-view image of the body 1801, such as shown in FIG. 19. As illustrated, the lateral distance 1821 can be the greatest distance of the plateau region 1802. In one embodiment, the lateral distance 1821 may have a length that is less than the length 1810 of the first layer 1802 (i.e., larger layer). In particular, the lateral distance 1821 can be not greater than about 90%, such as not greater than about 80%, not greater than about 70%, not greater than about 60%, not greater than about 50%, not greater than about 40%, not greater than about 30%, or even not greater than about 20% of the length 1810 of the first layer 1802 of the body 1801. Still, in one non-limiting embodiment, the lateral distance 1821 can have a length that is at least about 2%, at least about 5%, at least about 8%, at least about 10%, at least about 20%, at least about 25%, at least about 30%, or even at least about 50% of the length of the first layer 1802 of the body 1801. It will be appreciated that the lateral distance 1821 can have a length within a range between any of the minimum and maximum percentages noted above.

The second layer 1803 can have a particular length 1809, which is the longest dimension of a side, such as shown in FIG. 19, relative to a length 1810 of the first layer 1802 that may facilitate improved deployment of the abrasive particles into an abrasive article and/or performance of the abrasive article. For example, the length 1809 of the second layer



**1803** can be not greater than about 90%, such as not greater than about 80%, not greater than about 70%, not greater than about 60%, not greater than about 50%, not greater than about 40%, not greater than about 30%, or even not greater than about 20% of the length **1810** of the first layer **1802** of the body **1801**. Still, in one non-limiting embodiment, the second layer **1803** can have a length **1809** that can be at least about 2%, at least about 10%, at least about 20%, at least about 30%, at least about 40%, at least about 50%, at least about 60%, or even at least about 70% of the length **1810** of the first layer **1802** of the body **1801**. It will be appreciated that the length **1809** of the second layer **1803** relative to the length **1810** of the first layer **1802** can be within a range between any of the minimum and maximum percentages noted above.

The foregoing shaped abrasive particle of FIGS. **18** and **19** can be formed using the additive manufacturing process according to the embodiments herein. Moreover, it is contemplated that the organization of the layers can be different than as illustrated. The body may include any combination of layers of different dimensions and/or shapes in any organization relative to each other.

Moreover, coated abrasive articles have been described in detail herein, but it will be appreciated that the shaped abrasive particles of the embodiments may be employed in bonded abrasive articles. Bonded abrasive articles can take various shapes including wheels, discs, cups, segments, and the like generally consisting of composites having abrasive grains contained within a three-dimensional bond matrix. Additionally, the bonded abrasive tools can include some volume percentage of porosity.

Some suitable materials for use as the bond material can include metal materials, polymer materials (e.g., resin), vitreous or amorphous phase materials, crystalline phase materials, and a combination thereof.

Bonded abrasive articles are typically formed from an initial mixture including the bond material or a precursor of the bond material, the abrasive particles (e.g., shaped abrasive particles, diluent particles, combination of different types of abrasive particles, etc.), and fillers (e.g., active fillers, grinding aids, pore formers, mixing aids, reinforcing agents, etc.). The mixture can be formed into a green body (i.e., unfinished body) using various techniques, including but not limited to, molding, pressing, extruding, depositing, casting, infiltrating, and a combination thereof. The green body may undergo further processing to aid formation of the final-formed bonded abrasive body. The processing may depend on the composition of the mixture, but can include processes such as drying, curing, radiating, heating, crystallizing, re-crystallizing, sintering, pressing, decomposition, dissolution, and a combination thereof.

The final-formed bonded abrasive article may have various contents of the components (i.e., abrasive particles, bond material, filler, and porosity) depending on the intended end use. For example, in certain instances, the final-formed bonded abrasive article can have a porosity of at least about 5 vol % of the total volume of the bonded abrasive article. In other embodiments, the porosity can be greater, such as on the order of at least about 15 vol %, at least 25 vol %, at least about 25 vol %, at least about 50 vol %, or even at least about 60 vol %. Particular embodiments may utilize a range of porosity between about 5 vol % and about 75 vol % of the total volume of the bonded abrasive article.

Moreover, the final-formed bonded abrasive may have a content of bond material of at least about 10 vol % for the total volume of the bonded abrasive body. In other instances, the body can include at least about 30 vol %, such as at least

about 40 vol %, at least about 50 vol % or even at least about 60 vol % bond material for the total volume of the body of the bonded abrasive article. Certain embodiments may utilize a range of bond material between about 10 vol % and about 90 vol %, such as between about 10 vol % and about 80 vol %, or even between about 20 vol % and about 70 vol % of the total volume of the bonded abrasive article.

The final-formed bonded abrasive may have a content of abrasive particles of at least about 10 vol % for the total volume of the bonded abrasive body. In other instances, the body can include at least about 30 vol %, such as at least about 40 vol %, at least about 50 vol % or even at least about 60 vol % abrasive particles for the total volume of the body of the bonded abrasive article. In other examples, the abrasive article may utilize a range of abrasive particles between about 10 vol % and about 90 vol %, such as between about 10 vol % and about 80 vol %, or even between about 20 vol % and about 70 vol % of the total volume of the bonded abrasive article.

Certain features, for clarity, described herein in the context of separate embodiments, may also be provided in combination in a single embodiment. Conversely, various features that are, for brevity, described in the context of a single embodiment, may also be provided separately or in any subcombination. Further, reference to values stated in ranges includes each and every value within that range.

In accordance with one aspect, the shaped abrasive particles of the embodiments herein can have bodies including various features facilitated by the additive manufacturing process. For example, in one embodiment the shaped abrasive particle may have a body having at least one major surface having a self-similar feature. FIG. **20** includes a perspective view illustration of a shaped abrasive particle according to an embodiment. As illustrated, the shaped abrasive particle **2000** can include a body **2001** having an upper major surface **2002**, a lower major surface **2004**, and side surfaces **2005**, **2006**, and **2007** extending between the major surfaces **2002** and **2004**. FIG. **21** includes a top view of a major surface of the shaped abrasive particle **2000** of FIG. **20**.

As illustrated, and in accordance with an embodiment, the major surface **2002** of the shaped abrasive particle **2000** can have a self-similar feature **2003**. A self-similar feature **2003** can be an arrangement of features on a surface of the body of the shaped abrasive particle, such as a major surface of the body. The self-similar feature can include one or more features that can be arranged relative to each other, such as in a particular distribution, such as features arranged in a pattern relative to each other. The self-similar feature **2003** can include a plurality of shapes disposed on the major surface **2002** of the body **2001**. In more particular instances, the self-similar feature **2003** can include a plurality of two-dimensional shapes nested within each other on the major surface **2002**. For example, in the embodiment illustrated in FIGS. **20** and **21**, the self-similar feature **2003** can include a plurality of two-dimensional triangular shapes patterned on the surface, and distributed relative to each other in a nested arrangement, including the plurality of triangles **2009** and **2010**.

In another embodiment, the self-similar feature can include arrangement of two-dimensional shapes at the major surface of the body of the shaped abrasive particle wherein the arrangement of the two-dimensional shapes are substantially the same two-dimensional shape as the two-dimensional shape defined by a periphery of the major surface. For example, referring to the embodiments of FIGS. **20** and **21**, the triangles **2009** and **2010** can have substantially the same



two-dimensional shape as the two-dimensional shape of the periphery **2012** of the upper major surface **2002** of the shaped abrasive particle **2000**. It will be appreciated that while the embodiments of FIGS. **20** and **21** illustrate a shaped abrasive particle having a generally triangular two-dimensional shape, other two-dimensional shapes may be formed using the additive manufacturing process. For example, the body of the shaped abrasive particle can include a two-dimensional shape from the group including a regular polygons, irregular regular polygons, irregular shapes, triangles, quadrilaterals, rectangles, trapezoid, pentagons, hexagons, heptagons, octagons, ellipses, Greek alphabet letters, Latin enough alphabet characters, Russian alphabet characters, Kanji characters, and a combination thereof.

Referring to FIG. **22**, a top view image of a portion of the shaped abrasive particle of FIG. **20** is provided. The shaped abrasive particle **2000** can include a corner **2201** which when viewed top-down can define a particular radius of curvature. Notably, the corner **2201** can have an arcuate contour **2202** to which a best-fit circle **2203** may be fit. The best-fit circle **2203** may have a radius **2204** that can define the corner roundness of the corner **2201**. The best fit circle may be fit and the radius evaluated using a suitable form of imaging and magnification, such as provided in FIG. **22**. Suitable software, such as ImageJ may be used.

In one embodiment, the body of a shaped abrasive particle can have a particular corner roundness that may facilitate use in abrasive operations. For example, the shaped abrasive particle can have a body having a corner roundness of not greater than about 250 microns, such as not greater than about 220 microns, not greater than about 200 microns, not greater than about 180 microns, not greater than about 160 microns, not greater than about 140 microns, not greater than about 120 microns, not greater than about 100 microns, not greater than about 90 microns, not greater than about 80 microns, not greater than about 70 microns, not greater than about 60 microns, not greater than about 50 microns, not greater than about 40 microns, not greater than about 30 microns, or even not greater than about 20 microns. In one non-limiting embodiment, the body of the shaped abrasive particle can have a corner roundness of at least about 0.1 microns, such as at least about 0.5 microns. It will be appreciated that the body can have a corner roundness within a range including any of the minimum and maximum values noted above, including for example at least about 0.1 microns and not greater than about 250 microns, such as at least about 0.1 microns and not greater than about 100 microns, or even at least about 0.5  $\mu\text{m}$  and not greater than about 80 microns.

In accordance with another embodiment, the shaped abrasive particle can have at least one major surface defining a concave, stepped surface. For example, referring to FIG. **23** a portion of a major surface of the shaped abrasive particle of FIG. **20** is provided. As provided, the major surface **2002** can have a concave, stepped surface, which may be defined by a plurality of step features **2301** extending along at least a portion of the length of the body **2001**. In a particular embodiment, the concave, stepped surface can define a thickness at a midpoint **2302** that is less than a thickness (t) of the body at an edge. It will be appreciated that the thickness (t) can extend in a direction perpendicular to the major surface **2002** of the body **2001** along the side surface **2005**. In accordance with a particular embodiment, the concave, stepped surface can include step features **2301** including a plurality of flats **2304** and risers **2305**, were in the flats extend substantially parallel to the plane of the

major surface **2002** and the risers **2305** extend substantially perpendicular to the plane of the major surface **2002**. Moreover, the risers **2305** extend substantially perpendicular to the flats **2304**.

In accordance with an embodiment, the step features **2301** of the concave, stepped surface, can include flats **2304** defining a particular average width relative to the length (l) of the body **2001**. For example, the flats **2304** can have an average width (wf) that is not greater than about 0.8 (l), wherein "l" defines the length or longest dimension of the body **2001** (see. FIG. **21**) extending along one side of the major surface **2002**. In another embodiment, the flats **2304** can have an average width (wf) that can be not greater than about 0.5 (l), such as not greater than about 0.4 (l), not greater than about 0.3 (l), not greater than about 0.2 (l), not greater than about 0.1 (l), not greater than about 0.09 (l), not greater than about 0.08 (l). In still one non-limiting embodiment, the flats **2304** can have an average width (wf) that can be at least about 0.001 (l), such as at least about 0.005 (l), at least about 0.01 (l). It will be appreciated that the flats **2304** can have an average width (wf) within a range between any of the minimum and maximum values noted above, including for example, within a range including at least about 0.001 (l) and not greater than about 0.8 (l), such as at least about 0.005 (l) and not greater than about 0.4 (l), or even at least about 0.01 (l) and not greater than about 0.2 (l).

In another embodiment, the risers **2305** can have an average height (hr) extending in a direction substantially perpendicular to the plane of the major surface **2002** that can be formed to have a particular relationship to the length (l) of the body **2001** of the shaped abrasive particle **2000**. For example, the average height (hr) of the risers can be not great about 0.2 (l), wherein "l" defines the length of the body **2001**. In another embodiment, the risers **2305** can have an average height (hr) not greater than about 0.15 (l), such as not greater than about 0.1 (l), not greater than about 0.05 (l), or even not greater than about 0.02 (l). In at least one non-limiting embodiment, the risers **2305** can have an average height (hr) of at least about 0.0001 (l), such as at least about 0.0005 (l). It will be appreciated that the risers **2305** can have an average height (hr) that is within a range including any of the minimum and maximum values noted above, including for example, at least about 0.0001 (l) and not greater than about 0.2 (l), or at least about 0.0005 (l) and not greater than about 0.1 (l).

Still another embodiment, the step features **2301** including the flats **2304** and risers **2305** may be formed to have a certain relationship relative to each other that may facilitate improved performance of the shaped abrasive particle and associated abrasive article. For example, the flats **2304** may have a particular average width (wr) that is greater than the average height (hr) of the risers **2305**. In more particular instances, the average height (hr) of the risers **2305** can be not greater than about 0.95 (wf). According to another embodiment, the average height (hr) of the risers **2305** can be not greater than about 0.9 (wf), such as not greater than about 0.8 (wf), not greater than about 0.7 (wf), not greater than about 0.5 (wf), not greater than about 0.3 (wf), not greater than about 0.2 (wf), not greater than about 0.1 (wf). In one non-limiting embodiment, the average height (hr) of the risers **2305** can be at least about 0.0001 (wf), such as at least about 0.001 (wf). It will be appreciated that the average height (hr) of the risers **2305** can be within a range including any of the minimum and maximum values noted above, including for example, at least about 0.0001 (wf) and not greater than about 0.95 (wf), or even at least about 0.001 (wf) and not greater than about 0.2 (wf).



Formation of the concave, stepped surface including step features **2301** can be facilitated by control of the filling pattern used to form the upper surface **2002** of the body **2001**. It will be appreciated that in other instances, alternative filling patterns may be used to form alternative features in one or more major surfaces of the body **2001**. For example, in one embodiment the upper surface for at least one major surface of the body **2001** can have a convex, stepped surface. A convex, stepped surface may have a thickness at a midpoint **2302** that is greater than a thickness of the body at an edge. As such, such a convex, stepped surface may include stepped features, wherein the thickness of the body decreases moving from the midpoint **2302** to the edge **2303**. Such a feature may be facilitated by formation of the upper surface utilizing a particular filling pattern, including for example, an inside-out filling process, wherein the material at the midpoint **2302** is deposited before the material at the edge **2303**.

In another embodiment, certain shaped abrasive particles formed according to the methods described herein can include a body that has at least one peripheral ridge extending around at least a portion of a side surface of the body. FIG. **24** includes a side view image of a portion of a shaped abrasive particle according to an embodiment. As provided, the shaped abrasive particle **2400** can include a body **2401** including a first major surface **2402**, a second major surface **2403** opposite the first major surface **2402**, and side surfaces **2404** and **2405** extending between the first major surface **2402** and second major surface **2403**. As further illustrated, the side surfaces **2404** and **2405** can include at least one peripheral ridge **2407** extending around at least a portion of the side surfaces **2404** and **2405** of the body **2401**. In certain instances, the one or more peripheral ridges **2407** can extend around the majority of the side surfaces **2404** and **2405** of the body **2401**. For certain embodiments, the one or more peripheral ridges **2407** can extend around the entire peripheral length of the side surfaces **2404** and **2405** of the body **2401**. As further illustrated, the at least one peripheral ridge **2407** can extend in a direction generally perpendicular to the thickness (*t*) of the body and substantially parallel to the planes defined by the first major surface **2402** and second major surface **2403**.

Furthermore, in at least another embodiment at least one of the peripheral ridges **2407** can extend around the entire side surface of the body **2401** without intersecting one or more major surfaces, including for example, the first major surface **2402** and/or the second major surface **2403**. As illustrated in FIG. **24**, at least one of the peripheral ridges **2407** can extend along at least two side surfaces **2404** and **2405** and an adjoining edge **2408** extending between the side surfaces **2404** and **2405**.

For certain shaped abrasive particles of the embodiments herein, the peripheral ridges **2407** can be separated by protrusions **2406**. In particular, each pair of peripheral ridges **2407** can be separated by at least one protrusion of the group of protrusions **2406**. Notably, the protrusions **2406** can each have a thickness that is less than the total thickness (*t*) of the body **2401**.

In one embodiment, the at least one peripheral ridge **2407** can have a depth (*dr*) that extends from an upper surface into the body and having a particular relationship relative to the thickness (*t*) of the body **2401**. For example, the at least one peripheral ridge **2407** can have a depth (*dr*) that is not greater than about 0.8 (*t*), wherein "*t*" is a thickness of the body. Still, the at least one peripheral ridge **2407** can have a depth (*dr*) that is not greater than about 0.7 (*t*), such as not greater than about 0.6 (*t*), not greater than about 0.5 (*t*), not greater

than about 0.4 (*t*), not greater than about 0.3 (*t*), not greater than about 0.2 (*t*), not greater than about 0.18 (*t*), not greater than about 0.16 (*t*), not greater than about 0.15 (*t*), not greater than about 0.14 (*t*), not greater than about 0.12 (*t*), not greater than about 0.1 (*t*), not greater than about 0.09 (*t*), not greater than about 0.08 (*t*), not greater than about 0.07 (*t*), not greater than about 0.06 (*t*), or even not greater than about 0.05 (*t*). In one non-limiting embodiment, the at least one peripheral ridge **2407** can have a depth (*dr*) that is at least about 0.001 (*t*), such as at least about 0.01 (*t*). It will be appreciated that the depth (*dr*) of the at least one peripheral ridge **2407** can be within a range including any of the minimum and maximum values noted above, including for example a depth (*dr*) of at least about 0.001 (*t*) and not greater than about 0.8 (*t*), such as at least about 0.001 (*t*) and not greater than about 0.5 (*t*), or even at least about 0.001 (*t*) and not greater than about 0.1 (*t*). Furthermore, it will be appreciated that reference herein to the at least one peripheral ridge having a depth (*dr*) can also refer to an average depth of the plurality of peripheral ridges **2407**. Moreover, the average depth of the plurality of peripheral ridges **2407** can have the same relationship relative to the average thickness (*t*) of the body **2401** as described above.

At least one embodiment, shaped abrasive particles of the embodiments herein can include at least one transverse ridge that can extend over at least two surfaces and an adjoining edge between the at least two surfaces. Referring again to FIG. **24**, the at least one peripheral ridge **2407** can be in the form of a transverse ridge that extends over the first side surface **2404**, second side surface **2405**, and the adjoining edge **2408** between the first side surface **2404** and the second side surface **2405**. In more particular instances, a transverse ridge can extend over at least three surfaces in at least two adjoining edges between the at least three surfaces. For example, in the instance of a shaped abrasive particle having a triangular two-dimensional shape as viewed top-down, a transverse ridge can extend around the side surfaces between the major surfaces such that the transverse ridge extends over all three side surfaces and at least two of the adjoining edges between the at least three surfaces. It will be appreciated that the transverse ridges can extend around the entire periphery of the side surfaces of the body, which may include more than three side surfaces in the case of a body having other two-dimensional shapes as viewed top down (e.g., a rectangular two-dimensional shape with four side surfaces and four adjoining edges).

In another embodiment, the body of the shaped abrasive particle can include a plurality of transverse ridges **2407**, wherein each of the transverse ridges of the plurality of transverse ridges **2407** extend parallel to each other around at least a portion of the periphery of the body **2401**. In another embodiment, at least one of the transverse ridges of the plurality of transverse ridges can have a different length relative to each other. It will be appreciated that the length is a measure of the longest dimension of the transverse ridge. For example, in the embodiment of FIG. **24**, the transverse ridges **2407** can have lengths extending perpendicular to the thickness "*t*" of the body **2401**. However, it will be appreciated that some of the transverse ridges **2407** may have lengths that differ from others, such that at least one of the transverse ridges **2407** has a length that is greater than or less than a length of another transverse ridge. According to a particular embodiment, each of the transverse ridges **2407** of the plurality transverse ridges can have different lengths relative to each other.

In yet another aspect, the shaped abrasive particles of the embodiments herein may include a body having at least one



corner that includes a plurality of micro-protrusions extending from the corner. The formation of a body having at least one corner with the micro-protrusions may facilitate improved abrasive performance. FIG. 25 includes an image of a portion of a corner of a shaped abrasive particle according to an embodiment herein. The shaped abrasive particle 2500 can include a body 2501 having a corner 2502 that can include a plurality of micro-protrusions 2503 extending from the corner 2502. In accordance with an embodiment, the micro-protrusions 2503 can define a plurality of discrete corner protrusions 2504, 2505, 2506, and 2507 (2504-2507) separated by a plurality of ridges 2508. In accordance with one embodiment, the plurality of discrete corner protrusions 2504-2507 can have different shapes relative to each other. For example, the discrete protrusion 2504 is extending further in a lateral direction from the corner 2502 relative to the discrete corner protrusion 2505.

Furthermore, the discrete corner protrusion 2504-2507 can have different corner contours relative to each other. For example, the discrete corner protrusion 2504 as viewed top-down can have a sharper corner roundness relative to the other discrete corner protrusion 2505, 2506 and 2507. In certain instances, each of the discrete corner protrusions 2504-2507 can have different corner roundness values relative to each other. In yet another embodiment, the micro-protrusions 2503 associate with the corner 2502 can define a plurality of discrete corner protrusion 2504 and 2507, which may have different contours relative to each other. In one particular embodiment, the corner 2502 can have a different corner roundness values at the upper surface 2510 defined by the discrete corner protrusion 2507 relative to the average corner roundness of the corner at the bottom surface 2511 defined by the discrete corner protrusion 2504.

In another embodiment, the particular feature of the micro-protrusions 2503 can include a plurality of discrete corner protrusions 2504-2507, wherein at least two of the discrete corner protrusions can define a step having a lateral shift relative to each other. For example, the discrete corner protrusion 2504 can extend further from the body 2501 relative to the discrete corner protrusion 2505 and define a lateral shift 2509 between the outermost peripheral edge of the discrete corner protrusion 2504 relative to the outermost peripheral edge of the discrete corner protrusion 2505.

In accordance with another embodiment, the corner 2502 including the micro-protrusions 2503 can define a serrated edge in accordance with one embodiment. The micro-protrusions 2503 can define a serrated contour along the edge 2513 extending between the first major surface 2510 and the second major surface 2511. More particularly, the formation of discrete corner protrusions 2504-2507 separated by ridges 2508 can give the edge 2513 a serrated contour that may facilitate improved abrasive capabilities.

In yet another aspect, the shaped abrasive particles of the embodiments herein can include a body having a scalloped topography defining a plurality of curved protrusions having ridges extending between the curve protrusions. In one embodiment, FIG. 26 includes an image of a portion of a surface of a shaped abrasive particle having a scalloped topography. As illustrated, the body 2601 can include a portion including a scalloped topography 2602. The scalloped topography 2602 can include a plurality of curved protrusions 2603 having ridges 2604 extending between the curve protrusions 2603. In accordance with one embodiment, the scalloped topography 2602 can extend over a majority of an entire surface of the body 2601. In certain instances, the scalloped topography 2602 can extend over an entire surface of one surface (e.g., side surface or major

surface) of the body of the shaped abrasive particle. In yet another design, the scalloped topography 2602 can extend over a majority of the entire side surface area of the body 2601 of the shaped abrasive particle. Still in at least one embodiment, the scalloped topography 2602 can extend over the entire surface area of the body 2601 of the shaped abrasive particle.

The scalloped topography 2602 can include curve protrusions 2603 defining arcuate portions of the external surface of the body extending between ridges 2604. In one particular embodiment, the curve protrusions 2603 can be in the form of each elongated protrusions, wherein each protrusion has a length (l), width (w), and a height (h), wherein each protrusion can have an arcuate contour in the direction of the width and the height. For example, as illustrated in the embodiment of FIG. 26, the curve protrusions 2603 can be an elongated protrusion 2605 having a length 2606, a width of 2607, and a height 2608. As will be appreciated the length 2606 can define the longest dimension of the elongated protrusion 2605, the width 2607 can extend in a direction substantially perpendicular to the length 2606, and in particular, can extend for the distance between adjacent ridges on either side of the elongated protrusion 2605. The elongated protrusion 2605 can further include a height 2608 that can define the greatest distance the elongated protrusion 2605 extends in a direction perpendicular to the plane defined by the length 2606 and width 2607. The height 2608 may further be defined the distance between the highest point on the elongated protrusion 2605 and lowest point, which may be associated with a ridge adjacent either side of the elongated protrusion 2605.

In at least one embodiment, the elongated protrusion 2605 can have a length 2606 extending in substantially the same direction as the length of the body 2601 of the shaped abrasive particle. In accordance with one embodiment the length of at least one elongated protrusion 2605 can be at least about 0.8 (l) where "l" is the length of the body 2601 of the shaped abrasive particle. In other instances, the length of the elongated protrusion 2605 can be at least 0.9 (l), or even at least about 1 (l), such that the length of the elongated protrusion 2605 is equivalent to the length of the body 2601. It will be appreciated that reference to the length of the elongated protrusion 2605 can include reference to an average length of a plurality of elongated protrusions, and the average length can have the same relationship relative to the length of the body as described above.

The elongated protrusions can be formed to have a particular relationship of width 2607 relative to the height 2608. For example, on one or more of the plurality of elongated protrusions, including for example, the elongated protrusion 2605 can have a height 2608 that is less than the width 2607. It will be appreciated that the body 2601 can include a plurality of elongated protrusion, which can define an average width and average height, and reference herein to a width or height can also include reference to an average width or average height for a plurality of elongated protrusions. The average height (hep) of the plurality of elongated protrusions 2603 can be not greater than about 0.9 (wep), wherein "wep" represents the average width of the elongated protrusions, such as not greater than about 0.8 (wep), not greater than about 0.7 (wep), not greater than about 0.6 (wep), not greater than about 0.5 (wep), not greater than about 0.4 (wep), not greater than about 0.3 (wep), not greater than about 0.2 (wep), or even not greater than about 0.1 (wep). Still, in at least one embodiment, the plurality of elongated protrusions can have an average height (hep) that is at least about 0.001 (wep), or even at least about 0.1 (wep).



It will be appreciated that the average height (hep) of the plurality of elongated protrusions can be within a range including any of the minimum and maximum values above, including for example, at least about 0.001 (wep) and not greater than about 0.9 (wep), or at least about 0.001 (wep) and not greater than about 0.5 (wep).

In accordance with one embodiment, the average height of the plurality of elongated protrusions **2603** can be not greater than about 500 microns, such as not greater than about 400 microns, not greater than about 300 microns, not greater than about 250 microns, not greater than about 200 microns, not greater than about 150 microns, not greater than about 100 microns, not greater than about 90 microns, not greater than about 30 microns, or even not greater than about 50 microns. Still, in one non-limiting embodiment, the average height of the plurality of elongated protrusions **2603** can be at least about 0.01 microns, at least about 0.1 microns, or even at least about 1 micron. It will be appreciated that the average height of the plurality of elongated protrusions **2603** can be within range including any of the minimum and maximum values noted above, including for example, at least about 0.1 microns and not greater than about 200 microns, such as at least about 0.1 microns and not than about 100 microns.

In accordance with another embodiment, the plurality of elongated protrusions **2603** can have an average width that is less than the average length of the body. In certain instances, the plurality of elongated protrusions may have a particular relationship to the average width relative to the length of the body **2601** of the shaped abrasive particle. For example, the average width of the plurality of elongated protrusions can be not greater than about 0.9 (l), such as not greater than about 0.8 (l), not greater than about 0.7 (l), not greater than about 0.6 (l), not greater than about 0.5 (l), not greater than about 0.4 (l), not greater than about 0.3 (l), not greater than about 0.2 (l), or even not greater than about 0.1 (l). Still, in at least one non-limiting embodiment, the average width of the plurality of elongate protrusions can be at least 0.001 (l), or at least the 0.01 (l). It will be appreciated that the average width can be within range including any of the minimum and maximum values noted above, including for example, at least about 0.001 (l) and not greater than about 0.9 (l), such as at least about 0.01 (l) and not greater than about 0.5 (l).

In certain instances, the plurality of elongated protrusions can have an average width that is not greater than about 500 microns, such as not greater than about 400 microns, not greater than about 300 microns, not greater than about 250 microns, or even not greater than about 200 microns. Still, in at least one non-limiting embodiment, the average width of the plurality of elongate protrusions can be at least about 0.01 microns, at least about 0.1 microns, or even at least about 1 micron. It will be appreciated that the plurality of elongated protrusions can have an average width within a range including any of the minimum and maximum values noted above, including for example, at least about 0.01 microns and not greater than about 500 microns, such as at least about 0.01 microns and not greater than about 300 microns.

As further illustrated in FIG. **26**, the scalloped topography **2602** may facilitate formation of sides and edges of the shaped abrasive particle having a non-linear feature which may beneficially affect the abrasive properties of the shaped abrasive particles. For example, the scalloped topography may facilitate improved fracture mechanics of the shaped abrasive particle. In at least one particular embodiment, scalloped topography **2602** can intersect an edge defining at

least one corner of the body. For example, referring again to FIG. **25**, the side surface **2514** between the major surfaces **2510** and **2511** can have a scalloped topography that intersects the corner **2502** and defines a serrated contour along the length of the edge **2513**. Formation of a serrated edge **2513** may facilitate improved abrasive capabilities of the shaped abrasive particle.

In accordance with an embodiment, the body of the shaped abrasive particle can include at least four major surfaces joined together at common edges. In certain instances, the four major surfaces can have substantially the same surface area relative to each other. More specifically, the body may include a tetrahedral shape.

FIG. **27** includes a top-down image of a shaped abrasive particle according to the embodiment. FIG. **27** includes a shaped abrasive particle including a bottom surface **2702**, three major side surfaces **2703**, **2704**, and **2705** joined to the bottom surface **2702** along common edges defined by the peripheral surface of the bottom surface **2702**. As further provided in FIG. **27**, the body **2701** of the shaped abrasive particle includes an upper surface **2706**. The upper surface **2706** can include a peripheral surface **2708** having a generally planar contour. Accordingly, the body **2701** can represent a truncated tetrahedral shaped abrasive particle, and more specifically, a volcano shape shaped abrasive particle.

The body **2701** can include an opening **2709**, which may be in the form of a blind opening or depression extending into the body at the upper surface **2706**. In one particular embodiment, the upper surface **2706** can have a concave, stepped surface defined by the peripheral surface **2708** and a first stepped surface **2711** having a substantially planar region (e.g., a flat) in the form of a triangular area. The first stepped surface **2711** can define a step disposed in the opening **2709**. The first stepped surface **2711** can be recessed into the opening **2709** below the peripheral surface **2708**. The concave, stepped surface can also include a second stepped surface **2712** having a substantially planar region, which may be in the form of a triangular area, and recessed into the opening **2709** below the planar peripheral surface **2708** and the first stepped surface **2711**. The concave, stepped surface can also include a riser **2713** between the first stepped surface **2711** and the peripheral surface **2708**. The concave, stepped surface may also include a riser **2714** between the second stepped surface **2712** and the first stepped surface **2713**. In particular embodiments having an opening **2709** in the upper surface **2706**, the shaped abrasive particle may define a volcano shape shaped abrasive particle, wherein the midpoint **2710** of the opening **2709** is recessed into the body away from the planar peripheral surface **2708**.

As also provided in FIG. **27**, the body **2701** can be formed of a plurality of portions, including for example, portion **2721** defining the peripheral surface of the bottom surface **2702** and portion **2722** overlying the first portion **2721**. The body can further include a plurality of overlying portions above the portions **2721** and **2722**. As illustrated, the portions **2721** and **2722** can be in the form of triangular layers as viewed top-down in FIG. **27**. Moreover, as illustrated, the layers can facilitate the formation of edges **2731**, **2732**, and **2733** between the major surface **2703**, **2704**, and **2705** and extending from the upper surface **2707** to the bottom surface **2702** having micro-protrusions. The micro-protrusions can define a serrated contour along the edges **2731**, **2732**, and **2733**.

Moreover, the major surfaces **2703**, **2704**, and **2705** can have a plurality of elongated protrusions **2741** extending around the periphery of the surfaces. The body **2701** can also include a plurality of transverse ridges **2742** extending around



the major surfaces **2703**, **2704**, and **2705** and adjoining edges **2731**, **2732**, and **2733**. Looking top-down as provided in FIG. **27**, the major surfaces **2703**, **2704**, and **2705** can also have a scalloped topography defining a plurality of arcuate protrusions **241** separated by the plurality of transverse ridges **2742**.

FIG. **28** includes a top-down view of a shaped abrasive particle according to an embodiment. As provided, the body **2801** of the shaped abrasive particle can include a bottom surface **2802** and major side surfaces **2803**, **2804**, and **2805** joined to the bottom surface **2802** at the peripheral surface **2806** of the bottom surface **2802**. The body **2801** can further include corners **2811**, **2812**, **2813**, and **2814** joined by the edges **2821**, **2822**, and **2823** such that the body forms a tetrahedral shape. Unlike the shaped abrasive particle of FIG. **27**, the body **2801** of the shaped abrasive particle of FIG. **28** is not a truncated pyramid, but includes the four corners **2811**, **2812**, **2813**, and **2814**. Notably, the corners **2811**, **2812**, and **2813** can be defined by a first portion **2831** of the body and the corner **2814** can be defined by a second portion **2832** formed at a second time and distinct from the portion **2831**. In at least one embodiment, the corners **2811**, **2812**, and **2813** can have substantially the same corner roundness value and the corner **2814** can have a corner roundness value that is different than the corner roundness values of the corners **2811**, **2812**, and **2813**. In at least one embodiment, the corner **2814** can have a corner roundness value that is greater than the corner roundness values of the corners **2811**, **2812**, and **2813**. In still another embodiment, the corner **2814** can have a corner roundness value that is less than the corner roundness values of the corners **2811**, **2812**, and **2813**. FIG. **29** includes a side-view image of the shaped abrasive particle of FIG. **28**. It will be appreciated that the shaped abrasive body particles of the embodiments herein can include bodies having various three-dimensional shapes as described herein, and are not to be interpreted as limited to those embodiments illustrated or depicted.

Without wishing to be tied to a particular theory, it is thought that one or more features of the embodiments herein can facilitate formation of shaped abrasive particles having improved abrasive properties. In certain instances, it has been noted that the shaped abrasive particles can have unique fracturing behavior, wherein during abrasive operations regions of the portions making up the body of the shaped abrasive particle may be selectively removed, which may expose sharper portions, thus exhibiting a self-sharpening behavior. FIG. **30** includes an image of a corner of a shaped abrasive particle according to an embodiment. As provided, certain region **3002** of a portion **3003** of the body **3001** of the shaped abrasive particle have been removed during an abrasive operation to expose an unused region **3005** of another portion **3006** of the body **3001**, which has a sharp corner and may facilitate continued abrasive operations.

#### Items

Item 1. A method of forming a shaped abrasive particle having a body formed by an additive manufacturing process.

Item 2. A method comprising forming a body of a shaped abrasive particle according to a digital model.

Item 3. The method of any one of items 1 and 2, wherein the additive manufacturing process includes forming a body of a shaped abrasive particle by shaping a raw material without use of a production tool.

Item 4. The method of any one of items 1 and 2, wherein the additive manufacturing process includes forming a body

of a shaped abrasive particle by depositing a plurality of discrete portions in a controlled, non-random manner relative to each other.

Item 5. The method of item 4, wherein depositing a plurality of portions of the body in a controlled, non-random manner relative to each other includes deposition of the plurality of portions into a production tool.

Item 6. The method of any one of items 1 and 2, wherein the method comprises at least one process selected from the group consisting of layer additive method, light photopolymerization, laser powder forming, powder bed fusion, selective laser sintering, micro-laser sintering, material extrusion robocasting, material jetting, sheet lamination, and a combination thereof.

Item 7. The method of item 6, wherein light photopolymerization includes stereolithography, wherein stereolithography includes depositing at least one layer of a slurry containing a polymer material that is polymerized during the forming process to form a shaped abrasive particle.

Item 8. The method of item 6, wherein laser powder forming includes depositing a raw material on a target and impinging radiation from a laser source on the target to melt the raw material and form the raw material into a shaped abrasive particle.

Item 9. The method of item 8, wherein the shaped abrasive particle comprises a material selected from the group consisting of a metal, metal alloy, glass, ceramic, polymer, and a combination thereof.

Item 10. The method of item 9, wherein the shaped abrasive particle consists essentially of a glass material comprising an oxide.

Item 11. The method of item 6, wherein selective laser sintering includes impinging radiation from a laser source on a target including a raw material and changing at least a portion of one of the phases of the raw material into a shaped abrasive particle.

Item 12. The method of item 11, wherein selective laser sintering includes impinging radiation from a laser source on a select portion of a bed of raw material and converting a portion of the bed of raw material into a shaped abrasive particle.

Item 13. The method of item 11, wherein changing at least a portion of one of the phases of the raw material includes a change in crystalline structure of the raw material.

Item 14. The method of item 11, wherein changing at least a portion of one of the phases of the raw material includes a change from a solid phase to a liquid phase of the raw material.

Item 15. The method of item 11, wherein changing at least a portion of one of the phases of the raw material includes sintering of the raw material.

Item 16. The method of item 11, wherein the shaped abrasive particle comprises a material selected from the group consisting of a metal, metal alloy, glass, ceramic, polymer and a combination thereof.

Item 17. The method of item 6, wherein material jetting includes deposition of discrete droplets of raw material on a target and coalescence of the discrete droplets into a body to form a shaped abrasive particle.

Item 18. The method of item 6, wherein material jetting includes depositing a plurality of discrete droplets into production tool in a controlled, non-random arrangement to form a shaped abrasive particle.

Item 19. The method of any one of items 1 and 2, wherein forming the body comprises controlling at least one process parameter selected from the group consisting of: a nozzle tip length; a nozzle width; a nozzle aspect ratio; a deposition



pressure; a relationship between nozzle width and deposition pressure; a deposition rate; a deposition volume, a relationship between deposition rate and deposition position; a relationship between deposition pressure and deposition position; a shutoff distance; a premove delay; a dispense gap; a filling pattern of the print material; a dynamic yield stress ( $\sigma_d$ ) of a print material; a static yield stress ( $\sigma_s$ ) of a print material; a yield stress ratio ( $\sigma_d/\sigma_s$ ) of a print material; a viscosity of the print material; and a combination thereof.

Item 20. The method of item 19, further comprising: depositing a first print material as a first portion of the body at a first time; and depositing a second print material as a second portion of the body distinct from the first portion at a second time.

Item 21. The method of item 20, wherein the first print material has a first composition and the second print material comprises a second composition.

Item 22. The method of item 21, wherein the first composition and the second composition are significantly different compared to each other.

Item 23. The method of item 21, wherein the second composition has a difference in porosity relative to the first composition.

Item 24. The method of item 21, wherein the first print material and second print material are deposited at different regions within the body and configured to affect the fracturing behavior of the shaped abrasive particle.

Item 25. The method of item 21, wherein the first print material and second print material are deposited in alternative layers within a region of the body forming a composite material configured to control a self-sharpening behavior of the body.

Item 26. The method of item 21, wherein the first print material and second print material are deposited in different regions of the body forming a composite material including a controlled arrangement of the regions relative to an intended orientation of the shaped abrasive particle in a fixed abrasive article.

Item 27. The method of item 20, wherein depositing the first print material comprises forming a first layer of the body at a first time and depositing the second print material comprises forming a second layer of the body overlying the first layer.

Item 28. The method of item 20, wherein the first portion can have a first characteristic selected from the group consisting of hardness, porosity, composition, and a combination thereof, and the second portion can have a second characteristic selected from the group consisting of hardness, porosity, composition, and a combination thereof, and wherein the first characteristic can be different from the second characteristic.

Item 29. The method of item 28, wherein the first portion can have a first porosity that is greater than a second porosity of the second portion, and wherein the first portion and the second portion are deposited in an arrangement relative to each other within the body forming a composite material configured to affect the fracturing behavior of the shaped abrasive particle.

Item 30. The method of item 28, wherein the first portion can have a first hardness that is greater than a second hardness of the second portion, and wherein the first portion and the second portion are deposited in an arrangement relative to each other within the body forming a composite material configured to affect the fracturing behavior of the shaped abrasive particle.

Item 31. The method of item 20, wherein the first portion can have a first volume that is greater than a second volume of the second portion.

Item 32. The method of item 31, wherein the first portion can define a central region of the body and the second portion can define an edge of the body.

Item 33. The method of item 31, wherein the first portion can define a central region of the body and the second portion can define a corner of the body.

Item 34. The method of item 19, wherein the method of forming the body further comprises depositing a print material from a nozzle onto a substrate, wherein the movement of the nozzle is controlled by a computer program.

Item 35. The method of item 34, wherein the nozzle comprises a nozzle width not greater than about 200 microns or not greater than about 100 microns or not greater than about 90 microns or not greater than about 85 microns or not greater than about 80 microns or not greater than about 75 microns or not greater than about 70 microns or not greater than about 65 microns or not greater than about 60 microns or not greater than about 55 microns or not greater than about 50 microns or not greater than about 45 microns or not greater than about 40 microns or not greater than about 35 microns or not greater than about 30 microns or not greater than about 25 microns or not greater than about 20 microns.

Item 36. The method of item 34, wherein the nozzle comprises a width of at least about 0.1 microns or at least about 1 micron or at least about 10 microns.

Item 37. The method of item 19, wherein the nozzle comprises a tip length of not greater than about 10 mm or not greater than about 8 mm or not greater than about 6 mm or not greater than about 5 mm or not greater than about 4 mm.

Item 38. The method of item 19, wherein the nozzle comprises a tip length of at least about 0.1 mm or at least about 0.2 mm or at least about 0.5 mm or at least about 1 mm.

Item 39. The method of item 19, wherein the nozzle comprises an aspect ratio value (width/tip length) of not greater than about 0.8 or not greater than about 0.6 or not greater than about 0.5 or not greater than about 0.4.

Item 40. The method of item 19, wherein the nozzle comprises an aspect ratio value (width/tip length) of at least about 0.001 or at least about 0.005 or at least about 0.008.

Item 41. The method of item 19, wherein the deposition pressure is not greater than about 5 MPa or not greater than about 4.5 MPa or not greater than about 4 MPa or not greater than about 3.5 MPa or not greater than about 3 MPa or not greater than about 2.5 MPa or not greater than about 2 MPa or not greater than about 1.8 MPa or not greater than about 1.5 MPa or not greater than about 1.3 MPa or not greater than about 1 MPa or not greater than about 0.9 MPa or not greater than about 0.8 MPa or not greater than about 0.7 MPa.

Item 42. The method of item 19, wherein the deposition pressure is at least about 0.005 MPa or at least about 0.01 MPa or at least about 0.05 MPa or at least about 0.08 MPa or at least about 0.1 MPa.

Item 43. The method of item 19, wherein the relationship between nozzle width and deposition pressure (width/pressure) defines a first forming factor having a value of at least about 0.2 microns/MPa or at least about 1 micron/MPa or at least about 2 microns/MPa or at least about 4 microns/MPa or at least about 6 microns/MPa or at least about 8 microns/MPa or at least about 10 microns/MPa or at least about 12 microns/MPa or at least about 14 microns/MPa or at least about 16 microns/MPa.



Item 44. The method of item 19, wherein the relationship between nozzle width and deposition pressure (width/pressure) defines a first forming factor having a value of not greater than about  $1 \times 10^5$  microns/MPa or not greater than about  $1 \times 10^4$  microns/MPa or not greater than about 8000 microns/MPa or not greater than about 6000 microns/MPa or not greater than about 5000 microns/MPa or not greater than about 4000 microns/MPa or not greater than about 3000 microns/MPa or not greater than about 2000 microns/MPa or not greater than about 1000 microns/MPa or not greater than about 500 microns/MPa or not greater than about 200 microns/MPa or not greater than about 100 microns/MPa.

Item 45. The method of item 19, wherein forming comprises moving the nozzle at a deposition rate of at least about 0.01 mm/s or at least about 0.05 mm/s or, at least about 0.08 mm/s or at least about 0.1 mm/s or at least about 0.3 mm/s or at least about 0.5 mm/s or at least about 0.8 mm/s or at least about 1 mm/s or at least about 1.5 mm/s or at least about 2 mm/s or at least about 2.5 mm/s or at least about 3 mm/s.

Item 46. The method of item 19, wherein forming comprises moving the nozzle at a deposition rate of not greater than about 50 mm/s or not greater than about 30 mm/s or not greater than about 20 mm/s.

Item 47. The method of item 19, wherein forming comprises controlling a deposition volume of a print material to define a portion of the body.

Item 48. The method of item 47, wherein controlling the deposition volume comprises changing the deposition volume of the print material depending upon the portion of the body being formed.

Item 49. The method of item 47, wherein forming comprises depositing a smaller volume of material at a region defining a corner of the body as compared to a region defining a major surface of the body.

Item 50. The method of item 47, wherein controlling the deposition volume includes controlling a deposition pressure and deposition rate of the nozzle.

Item 51. The method of item 50, wherein controlling the deposition volume includes controlling a width, length, and height of a first portion of the body formed at a first time.

Item 52. The method of item 19, wherein forming comprises controlling the relationship between deposition rate and deposition position.

Item 53. The method of item 52, wherein controlling the relationship between deposition rate and deposition position includes changing the deposition rate depending upon the deposition position.

Item 54. The method of item 52, wherein controlling the relationship between deposition rate and deposition position includes decreasing the deposition rate at a deposition position associated with a corner of the body of the shaped abrasive particle relative to a deposition rate associated with a deposition position at a major surface of the body.

Item 55. The method of item 52, wherein controlling the relationship between deposition rate and deposition position includes varying the deposition rate to change the size of features in the body depending on the deposition position.

Item 56. The method of item 19, wherein forming comprises controlling the relationship between the deposition pressure and the deposition position.

Item 57. The method of item 56, wherein controlling the relationship between the deposition pressure and the deposition position includes changing the deposition pressure depending upon the deposition position.

Item 58. The method of item 56, wherein controlling the relationship between the deposition pressure and the depo-

sition position includes decreasing the deposition pressure at a deposition position associated with a corner of the body of the shaped abrasive particle relative to a deposition pressure associated with a deposition position at a major surface of the body.

Item 59. The method of item 56, wherein controlling the relationship between the deposition pressure and the deposition position includes varying the deposition pressure to change the size of features in the body depending on the deposition position.

Item 60. The method of item 19, wherein forming a body further comprises controlling a premove delay between a beginning of deposition of the print material and movement of a nozzle for depositing the print material.

Item 61. The method of item 60, wherein the premove delay is greater than 0 seconds.

Item 62. The method of item 60, wherein the premove delay is not greater than about 10 seconds.

Item 63. The method of item 19, wherein forming a body further comprises controlling a shutoff distance defining the distance a nozzle moves after turning the pressure off to the print material.

Item 64. The method of item 19, wherein the shutoff distance is less than a dispense gap.

Item 65. The method of item 19, wherein the shutoff distance is greater than a dispense gap.

Item 66. The method of item 19, wherein the shutoff distance is substantially equal to a dispense gap.

Item 67. The method of item 19, wherein forming comprises controlling a dispense gap defining a distance between the nozzle and target.

Item 68. The method of item 67, wherein the dispense gap is not greater than about 10 W, wherein "W" represents the width of the nozzle, wherein the dispense gap is not greater than about 9 W or not greater than about 8 W or not greater than about 7 W or not greater than about 6 W or not greater than about 5 W or not greater than about 4 W or not greater than about 3 W or not greater than about 2 W or not greater than about 1 W.

Item 69. The method of item 67, wherein the dispense gap is at least about 0.001 W, wherein "W" represents the width of the nozzle, wherein the dispense gap is at least about 0.005 W or at least about 0.01 W or at least about 0.1 W.

Item 70. The method of item 67, wherein the dispense gap is not greater about 10 t, wherein "t" represents the thickness of the print material, wherein the dispense gap is not greater than about 9 t or not greater than about 8 t or not greater than about 7 t or not greater than about 6 t or not greater than about 5 t or not greater than about 4 t or not greater than about 3 t or not greater than about 2 t or not greater than about 1 t.

Item 71. The method of item 67, wherein the dispense gap is at least about 0.001 t, wherein "t" represents the thickness of the print material, wherein the dispense gap is at least about 0.005 t or at least about 0.01 t.

Item 72. The method of item 67, wherein controlling the dispense gap includes varying the dispense gap such that the print material contacts the target immediately upon exiting the nozzle.

Item 73. The method of item 67, wherein controlling the dispense gap includes controlling the height of the nozzle above the target such that the print material contacts the target upon exiting the nozzle without forming a free droplet in the space between the nozzle and target.

Item 74. The method of item 67, wherein controlling the dispense gap includes varying the Z-directional distance between the nozzle and the target based upon at least one of



the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, the filling pattern of the print material, the dynamic yield stress ( $\sigma_d$ ) of the print material, the static yield stress ( $\sigma_s$ ) of the print material, the yield stress ratio ( $\sigma_d/\sigma_s$ ) of the print material, the viscosity of the print material, and a combination thereof.

Item 75. The method of item 67, wherein controlling the dispense gap includes varying the dispense gap based on the deposition position.

Item 76. The method of item 67, wherein controlling the dispense gap includes varying the dispense gap to alter the volume of material deposited at a deposition position.

Item 77. The method of item 19, wherein forming further comprises controlling the filling pattern that defines the order of forming a first portion of the body at a first time and a second portion of the body at a second time.

Item 78. The method of item 77, wherein the filling pattern defines an deposition process selected from the group consisting of an outside-in filling process, an inside-out filling process, a side-to-side filling process, bottom-up filling process, and a combination thereof.

Item 79. The method of item 77, wherein controlling the filling pattern includes forming a first portion of the body at a first time using a first filling pattern and a second portion of the body at a second time using a second filling pattern, wherein the first filling pattern is different from the second filling pattern.

Item 80. The method of item 77, wherein the filling pattern includes forming a first layer by an outside-in filling process and a second layer overlying the first layer by an inside-out filling process.

Item 81. The method of item 19, wherein the print material can include a mixture comprising an inorganic material in a content of at least about 25 wt % for a total weight of the mixture or at least about 35 wt % or at least about 36 wt % or and not greater than about 75 wt % or not greater than about 70 wt % or not greater than about 65 wt % or not greater than about 55 wt % or not greater than about 45 wt % or not greater than about 44 wt %.

Item 82. The method of item 81, wherein the mixture comprises a sol-gel.

Item 83. The method of item 81, wherein the inorganic material comprises a ceramic.

Item 84. The method of item 81, wherein the inorganic material comprises a material selected from the group consisting of oxides, carbides, nitrides, borides, oxycarbides, oxynitrides, oxyborides, carbon-based materials, and a combination thereof.

Item 85. The method of item 81, wherein the inorganic material comprises alumina.

Item 86. The method of item 81, wherein the inorganic material comprises boehmite.

Item 87. The method of item 81, wherein the mixture comprises nitric acid.

Item 88. The method of item 81, wherein the mixture comprises water.

Item 89. The method of item 81, wherein the mixture comprises a dynamic yield stress ( $\sigma_d$ ) of at least about 100 Pa or at least about 120 Pa or at least about 140 Pa or at least about 160 Pa or at least about 180 Pa or at least about 200 Pa.

Item 90. The method of item 81, wherein the mixture comprises a dynamic yield stress ( $\sigma_d$ ) of not greater than about 1500 Pa or not greater than about 1300 Pa or not greater than about 1200 Pa or not greater than about 1100 Pa or not greater than about 1000 Pa.

Item 91. The method of item 81, wherein forming comprises controlling at least one of the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the dynamic yield stress ( $\sigma_d$ ) of the print material.

Item 92. The method of item 81, wherein the mixture comprises a static yield stress ( $\sigma_s$ ) of at least about 180 Pa or at least about 200 Pa or at least about 250 Pa or at least about 300 Pa or at least about 350 Pa or at least about 400 Pa or at least about 450 Pa or at least about 500 Pa or at least about 550 Pa or at least about 600 Pa.

Item 93. The method of item 81, wherein the mixture comprises a static yield stress ( $\sigma_s$ ) of not greater than about 20000 Pa or not greater than about 18000 Pa or not greater than about 15000 Pa or not greater than about 5000 Pa or not greater than about 1000 Pa.

Item 94. The method of item 81, wherein the mixture comprises a static yield stress ( $\sigma_s$ ) different than the dynamic yield stress ( $\sigma_d$ ).

Item 95. The method of item 81, wherein the mixture comprises a static yield stress ( $\sigma_s$ ) greater than the dynamic yield stress ( $\sigma_d$ ).

Item 96. The method of item 81, wherein the mixture comprises a yield stress ratio ( $\sigma_d/\sigma_s$ ) of not greater than about 1 or not greater than about 0.99 or not greater than about 0.97 or not greater than about 0.95 or not greater than about 0.9 or not greater than about 0.85 or not greater than about 0.8 or not greater than about 0.75 or not greater than about 0.7 or not greater than about 0.65 or not greater than about 0.6 or not greater than about 0.55 or not greater than about 0.5.

Item 97. The method of item 81, wherein forming comprises controlling at least one of the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the static yield stress ( $\sigma_s$ ) of the print material.

Item 98. The method of item 81, wherein the mixture comprises a yield stress ratio ( $\sigma_d/\sigma_s$ ) of at least about 0.01 or at least about 0.05 or at least about 0.08 or at least about 0.1 or at least about 0.15 or at least about 0.2 or at least about 0.25 or at least about 0.3 or at least about 0.35 or at least about 0.4 or at least about 0.45 or at least about 0.5.

Item 99. The method of item 81, wherein forming comprises controlling at least one of the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the yield stress ratio ( $\sigma_d/\sigma_s$ ) of the print material.

Item 100. The method of item 81, wherein the mixture is a shear thinning material.

Item 101. The method of item 81, wherein the mixture comprises a viscosity of at least about  $4 \times 10^3$  Pa s or at least about  $5 \times 10^3$  Pa s or at least about  $6 \times 10^3$  Pa s or at least about  $7 \times 10^3$  Pa s or at least about  $7.5 \times 10^3$  Pa s.

Item 102. The method of item 81, wherein the mixture comprises a viscosity of not greater than about  $20 \times 10^3$  Pa s or such as not greater than about  $18 \times 10^3$  Pa s or not greater than about  $15 \times 10^3$  Pa s or not greater than about  $12 \times 10^3$  Pa s.

Item 103. The method of item 81, wherein forming comprises controlling at least one of the dispense gap, the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, and the filling pattern of the print material based on the viscosity of the print material.



Item 104. The method of any one of items 1 and 2, wherein forming further comprises controlling a three-dimensional movement of a nozzle configured for deposition of a print material, wherein controlling the three-dimensional movement includes control of the nozzle in an X-axis, a Y-axis, and a Z-axis.

Item 105. The method of any one of items 1 and 2, wherein forming further comprises control of a plurality of nozzles, wherein each nozzle of the plurality of nozzles can be configured to deposit a print material and control of the plurality of nozzles includes control of three-dimensional movement of each nozzle in an X-axis, a Y-axis, and a Z-axis.

Item 106. The method of any one of items 1 and 2, further comprising: depositing a first print material as a first portion of the body at a first time; and depositing a second print material as a second portion of the body distinct from the first portion at a second time.

Item 107. The method of item 106, wherein the first time is different than the second time.

Item 108. The method of item 106, wherein the first print material comprises a material selected from the group consisting of a solid, a powder, a solution, a mixture, a liquid, a slurry, a gel, a binder, and a combination thereof.

Item 109. The method of item 106, further comprising preferentially modifying one of the first portion and second portion to join the first portion and second portion and form a subsection of the body.

Item 110. The method of item 109, wherein modifying comprises changing a phase of at least one of the first print material and the second print material.

Item 111. The method of item 109, wherein modifying comprises heating at least one of the first portion and second portion.

Item 112. The method of item 111, wherein heating comprises fusing the first portion to the second portion.

Item 113. The method of item 111, wherein heating comprises joining the first portion to the second portion.

Item 114. The method of item 111, wherein heating comprises impinging electromagnetic radiation on at least a portion of the first portion.

Item 115. The method of item 111, wherein heating comprises impinging electromagnetic radiation on at least a portion of the second portion.

Item 116. The method of item 106, wherein depositing comprises depositing a plurality of discrete droplets of a predetermined volume of the first print material to form the first portion.

Item 117. The method of item 106, wherein depositing comprises depositing a plurality of discrete droplets of a predetermined volume of the second print material to form the second portion.

Item 118. The method of item 106, wherein the first portion comprises a first portion length (Lfp), a first portion width (Wfp), and a first portion thickness (Tfp), and wherein  $Lfp \geq Wfp$ ,  $Lfp \geq Tfp$ , and  $Wfp \geq Tfp$ .

Item 119. The method of item 118, wherein the first portion comprises a primary aspect ratio (Lfp:Wfp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 120. The method of item 118, wherein the first portion comprises a secondary aspect ratio (Lfp:Tfp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 121. The method of item 118, wherein the first portion comprises a tertiary aspect ratio (Wfp:Tfp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 122. The method of item 118, wherein at least one of the first portion length (Lfp), the first portion width (Wfp), and the first portion thickness (Tfp) has an average dimension of not greater than about 2 mm or such as not greater than about 1 mm or not greater than about 900 microns or not greater than about 800 microns or not greater than about 700 microns or not greater than about 600 microns or not greater than about 500 microns or not greater than about 400 microns or not greater than about 300 microns or not greater than about 200 microns or not greater than about 150 microns or not greater than about 140 microns or not greater than about 130 microns or not greater than about 120 microns or not greater than about 110 microns or not greater than about 100 microns or not greater than about 90 microns or not greater than about 80 microns or not greater than about 70 microns or not greater than about 60 microns or not greater than about 50 microns, and at least about 0.01 microns or at least about 0.1 microns or at least about 1 micron.

Item 123. The method of item 118, wherein the first portion comprises a cross-sectional shape in a plane defined by the first portion length (Lfp) and the first portion width (Wfp) selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoidal, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 124. The method of item 118, wherein the first portion comprises a cross-sectional shape in a plane defined by the first portion length (Lfp) and the first portion thickness (Tfp) selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoidal, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 125. The method of item 118, wherein the first portion is in the form of layer.

Item 126. The method of item 106, wherein the second portion comprises a second portion length (Lsp), a second portion width (Wsp), and a second portion thickness (Tsp), and wherein  $Lsp \geq Wsp$ ,  $Lsp \geq Tsp$ , and  $Wsp \geq Tsp$ .

Item 127. The method of item 126, wherein the second portion comprises a primary aspect ratio (Lsp:Wsp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 128. The method of item 126, wherein the second portion comprises a secondary aspect ratio (Lsp:Tsp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 129. The method of item 126, wherein the second portion comprises a tertiary aspect ratio (Wsp:Tsp) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 130. The method of item 126, wherein at least one of the second portion length (Lsp), the second portion width (Wsp), and the second portion thickness (Tsp) has an average dimension of not greater than about 2 mm or such as not greater than about 1 mm or not greater than about 900 microns or not greater than about 800 microns or not greater



than about 700 microns or not greater than about 600 microns or not greater than about 500 microns or not greater than about 400 microns or not greater than about 300 microns or not greater than about 200 microns or not greater than about 150 microns or not greater than about 140 microns or not greater than about 130 microns or not greater than about 120 microns or not greater than about 110 microns or not greater than about 100 microns or not greater than about 90 microns or not greater than about 80 microns or not greater than about 70 microns or not greater than about 60 microns or not greater than about 50 microns, and at least about 0.01 microns or at least about 0.1 microns or at least about 1 micron.

Item 131. The method of item 126, wherein the second portion comprises a cross-sectional shape in a plane defined by the second portion length (Lsp) and the second portion width (Wsp) selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoidal, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 132. The method of item 126, wherein the second portion comprises a cross-sectional shape in a plane defined by the second portion length (Lsp) and the second portion thickness (Tsp) selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoidal, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 133. The method of item 126, wherein the first portion comprises a cross-sectional shape different than a cross-sectional shape of the second portion.

Item 134. The method of item 126, wherein the first portion comprises a cross-sectional shape substantially the same as a cross-sectional shape of the second portion.

Item 135. The method of item 106, wherein the first print material comprises a first composition and the second print material comprises a second composition.

Item 136. The method of item 135, wherein the first composition and the second composition are essentially the same with respect to each other.

Item 137. The method of item 135, wherein the first composition and the second composition are significantly different with respect to each other.

Item 138. The method of item 135, wherein the first composition comprises a material selected from the group consisting of organic material, inorganic material, and a combination thereof.

Item 139. The method of item 135, wherein the first composition comprises a material selected from the group consisting of a ceramic, a glass, a metal, a polymer, and a combination thereof.

Item 140. The method of item 135, wherein the first composition comprises a material selected from the group consisting of an oxide, a carbide, a nitride, a boride, an oxycarbide, oxynitride, oxyboride, and a combination thereof.

Item 141. The method of item 135, wherein the first composition comprises alumina.

Item 142. The method of item 135, wherein the second composition comprises a material selected from the group consisting of organic material, inorganic material, and a combination thereof.

Item 143. The method of item 135, wherein the second composition comprises a material selected from the group consisting of a ceramic, a glass, a metal, a polymer, and a combination thereof.

Item 144. The method of item 135, wherein the second composition comprises a material selected from the group consisting of an oxide, a carbide, a nitride, a boride, an oxycarbide, oxynitride, oxyboride, and a combination thereof.

Item 145. The method of item 135, wherein the second composition comprises alumina.

Item 146. The method of item 106, wherein the second print material includes a solid, a powder, a solution, a mixture, a liquid, a slurry, a gel, a binder, and a combination thereof.

Item 147. The method of item 1, further comprising forming the body according to a digital model.

Item 148. The method of any one of items 2 and 147, further comprising comparing at least a portion of the body to the digital model.

Item 149. The method of item 148, wherein comparing includes measuring at least a portion of the body and comparing it to a corresponding dimension of the digital model.

Item 150. The method of item 148, wherein comparing is conducted during forming.

Item 151. The method of item 148, wherein comparing is conducted after forming.

Item 152. The method of any one of items 2 and 147, further comprising creating a plurality of digital cross-sections of the digital model.

Item 153. The method of item 152, further comprising: depositing a first portion of the body at a first time, the first portion corresponding to a first cross-section of the plurality of cross-sections of the digital model; depositing a second portion of the body distinct from the first portion at a second time different than the first time, the second portion corresponding to a second cross-section of the plurality of cross-sections of the digital model.

Item 154. The method of item 152, further comprising using the plurality of digital cross-sections as a guide for depositing a plurality of discrete portions.

Item 155. The method of item 1, wherein the additive manufacturing process defines a process of compiling discrete portions to form a sub-portion.

Item 156. The method of item 155, further comprising compiling a plurality of sub-portions to form the body of the shaped abrasive particle.

Item 157. The method of any one of items 1 and 2, further comprising a subtractive process.

Item 158. The method of item 157, wherein the subtractive process is conducted after forming a body of a precursor shaped abrasive particle.

Item 159. The method of item 157, wherein the subtractive process includes removing at least a portion of the material used to form a precursor shaped abrasive particle.

Item 160. The method of item 157, wherein the subtractive process includes forming at least one opening within a portion of the body.

Item 161. The method of item 157, wherein the subtractive process includes forming an aperture through a portion of the body.

Item 162. The method of item 157, wherein the subtractive process includes heating to remove a portion of the body.

Item 163. The method of item 162, wherein heating comprises volatilizing at least a portion of the body.

Item 164. The method of any one of items 1 and 2, further comprising at least one process of modifying a portion of the body including melting, selective laser melting, sintering, selective sintering, direct metal laser sintering, selective



laser sintering, particle beam modification, electron beam melting, fused deposition modeling, curing, and a combination thereof.

Item 165. The method of any one of items 1 and 2, wherein forming comprises prototype printing of the body of the shaped abrasive particle.

Item 166. The method of any one of items 1 and 2, wherein forming comprises laminated object manufacturing.

Item 167. The method of any one of items 1 and 2, wherein the body comprises a three-dimensional shape including a body length (Lb), a body width (Wb), and a body thickness (Tb), and wherein  $Lb \geq Wb$ ,  $Lb \geq Tb$ , and  $Wb \geq Tb$ .

Item 168. The method of item 167, wherein the body comprises a primary aspect ratio (Lb:Wb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 169. The method of item 167, wherein the body comprises a secondary aspect ratio (Lb:Tb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 170. The method of item 167, wherein the body comprises a tertiary aspect ratio (Wb:Tb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 171. The method of item 167, wherein at least one of the body length (Lb), the body width (Wb), and the body thickness (Tb) has an average dimension of at least about 0.1 microns or at least about 1 micron or at least about 10 microns or at least about 50 microns or at least about 100 microns or at least about 150 microns or at least about 200 microns or at least about 400 microns or at least about 600 microns or at least about 800 microns or at least about 1 mm, and not greater than about 20 mm or not greater than about 18 mm or not greater than about 16 mm or not greater than about 14 mm or not greater than about 12 mm or not greater than about 10 mm or not greater than about 8 mm or not greater than about 6 mm or not greater than about 4 mm.

Item 172. The method of item 167, wherein the body comprises a cross-sectional shape in a plane defined by the body length and the body width selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 173. The method of item 167, wherein the body comprises a cross-sectional shape in a plane defined by the body length and the body thickness selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 174. The method of any one of items 1 and 2, wherein the body comprises a three-dimensional shape selected from the group consisting of a polyhedron, a pyramid, an ellipsoid, a sphere, a prism, a cylinder, a cone, a tetrahedron, a cube, a cuboid, a rhombohedron, a truncated pyramid, a truncated ellipsoid, a truncated sphere, a truncated cone, a pentahedron, a hexahedron, a heptahedron, an octahedron, a nonahedron, a decahedron, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 175. The method of any one of items 1 and 2, further comprising forming a plurality of shaped abrasive particles, wherein each of the shaped abrasive particles of the plurality of shaped abrasive particles have a body having a body length (Lb), a body width (Wb), and a body thickness (Tb).

Item 176. The method of item 175, wherein the plurality of shaped abrasive particles have at least one of: a body length variation of not greater than about 50%; a body width variation of not greater than about 50%; and a body thickness variation of not greater than about 50%.

Item 177. The method of any one of items 1 and 2, wherein the body has a first major surface, a second major surface, and at least one side surface extending between the first major surface and the second major surface.

Item 178. The method of any one of items 1 and 2, wherein the body comprises a percent flashing not greater than about 40% or not greater than about 20% or not greater than about 10% or not greater than about 4%, wherein the body is essentially free of flashing.

Item 179. The method of any one of items 1 and 2, wherein the body is essentially free of a binder, wherein the body is essentially free of an organic material.

Item 180. The method of any one of items 1 and 2, wherein the body comprises a polycrystalline material, wherein the polycrystalline material comprises grains, wherein the grains are selected from the group of materials consisting of nitrides, oxides, carbides, borides, oxynitrides, diamond, and a combination thereof, wherein the grains comprise an oxide selected from the group of oxides consisting of aluminum oxide, zirconium oxide, titanium oxide, yttrium oxide, chromium oxide, strontium oxide, silicon oxide, and a combination thereof, wherein the grains comprise alumina, wherein the grains consist essentially of alumina.

Item 181. The method of any one of items 1 and 2, wherein the body consists essentially of alumina.

Item 182. The method of any one of items 1 and 2, wherein the body is formed from a seeded sol gel.

Item 183. The method of any one of items 1 and 2, wherein the body comprises a polycrystalline material having an average grain size not greater than about 1 micron.

Item 184. The method of any one of items 1 and 2, wherein the body is a composite comprising at least about 2 different types of compositions.

Item 185. The method of any one of items 1 and 2, wherein the body comprises an additive, wherein the additive comprises an oxide, wherein the additive comprises a metal element, wherein the additive comprises a rare-earth element.

Item 186. The method of item 185, wherein the additive comprises a dopant material, wherein the dopant material includes an element selected from the group consisting of an alkali element, an alkaline earth element, a rare earth element, a transition metal element, and a combination thereof, wherein the dopant material comprises an element selected from the group consisting of hafnium, zirconium, niobium, tantalum, molybdenum, vanadium, lithium, sodium, potassium, magnesium, calcium, strontium, barium, scandium, yttrium, lanthanum, cesium, praseodymium, chromium, cobalt, iron, germanium, manganese, nickel, titanium, zinc, and a combination thereof.

Item 187. A method of forming a fixed abrasive comprising: forming a plurality of shaped abrasive particles on a substrate, wherein each of the shaped abrasive particles of the plurality of shaped abrasive particles have a body formed by an additive manufacturing process.

Item 188. The method of item 187, wherein forming is conducted directly overlying the substrate.

Item 189. The method of item 187, wherein forming is conducted directly on at least a portion of a bonding layer overlying the substrate, wherein the bonding layer comprises a material selected from the group consisting of an



inorganic material, a vitreous material, a crystalline material, an organic material, a resin material, a metal material, a metal alloy, and a combination thereof.

Item 190. The method of item 187, wherein the substrate is translated through a forming zone, wherein in the forming zone at least one shaped abrasive particle of the plurality of shaped abrasive particles is formed overlying the substrate.

Item 191. The method of item 187, wherein translation includes a stepped translation process.

Item 192. The method of item 187, wherein the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles is formed according to a digital model.

Item 193. The method of item 187, wherein the additive manufacturing process comprises: depositing a first print material as a first portion of the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles at a first time; and depositing a second print material as a second portion of the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles at a second time different than the first time.

Item 194. The method of item 193, further comprising preferentially modifying one of the first portion and second portion to join the first portion and second portion and form a subsection of the body of the shaped abrasive particle.

Item 195. The method of item 187, wherein the plurality of shaped abrasive particles are formed at a predetermined location on the substrate.

Item 196. The method of item 187, further comprising placing each of the shaped abrasive particles of the plurality of shaped abrasive particles on the substrate, wherein the placing is conducted simultaneously with forming the body of each of the shaped abrasive particles of the plurality of shaped abrasive particles.

Item 197. The method of item 187, further comprising orienting each of the shaped abrasive particles of the plurality of shaped abrasive particles relative to the substrate.

Item 198. The method of item 197, wherein orienting and forming are conducted simultaneously.

Item 199. The method of item 187, wherein at least about 55% of the plurality of shaped abrasive particles are oriented in a side orientation.

Item 200. The method of item 187, wherein the plurality of shaped abrasive particles define an open coat, wherein the plurality of shaped abrasive particles of the first portion define a closed coat, wherein the open coat comprises a coating density of not greater than about 70 particles/cm<sup>2</sup>.

Item 201. The method of item 187, wherein the substrate comprises a woven material, wherein the substrate comprises a non-woven material, wherein the substrate comprises an organic material, wherein the substrate comprises a polymer, wherein the substrate comprises a material selected from the group consisting of cloth, paper, film, fabric, fleeced fabric, vulcanized fiber, woven material, non-woven material, webbing, polymer, resin, phenolic resin, phenolic-latex resin, epoxy resin, polyester resin, urea formaldehyde resin, polyester, polyurethane, polypropylene, polyimides, and a combination thereof.

Item 202. The method of item 187, wherein the substrate comprises an additive chosen from the group consisting of catalysts, coupling agents, curants, anti-static agents, suspending agents, anti-loading agents, lubricants, wetting agents, dyes, fillers, viscosity modifiers, dispersants, defoamers, and grinding agents.

Item 203. The method of item 187, further comprising an adhesive layer overlying the substrate, wherein the adhesive layer comprises a make coat, wherein the make coat overlies

the substrate, wherein the make coat is bonded directly to a portion of the substrate, wherein the make coat comprises an organic material, wherein the make coat comprises a polymeric material, wherein the make coat comprises a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

Item 204. The method of item 203, wherein the adhesive layer comprises a size coat, wherein the size coat overlies a portion of the plurality of shaped abrasive particles, wherein the size coat overlies a make coat, wherein the size coat is bonded directly to a portion of the plurality of shaped abrasive particles, wherein the size coat comprises an organic material, wherein the size coat comprises a polymeric material, wherein the size coat comprises a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

Item 205. A shaped abrasive particle comprising a body having at least one major surface having a self-similar feature.

Item 206. A shaped abrasive particle comprising a body having at least one peripheral ridge extending around at least a portion of a side surface of the body.

Item 207. A shaped abrasive particle comprising a body having at least one major surface defining a concave stepped surface.

Item 208. A shaped abrasive particle comprising a body having at least one transverse ridge extending along at least two surfaces and an adjoining edge between the at least two surfaces.

Item 209. A shaped abrasive particle comprising a body having a corner including a plurality of microprotrusions extending from the corner.

Item 210. A shaped abrasive particle comprising a body including a surface comprising a scalloped topography.

Item 211. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein body comprises a corner roundness of not greater than about 250 microns or not greater than about 220 microns or not greater than about 200 microns or not greater than about 180 microns or not greater than about 160 microns or not greater than about 140 microns or not greater than about 120 microns or not greater than about 100 microns or not greater than about 90 microns or not greater than about 80 microns or not greater than about 70 microns or not greater than about 60 microns or not greater than about 50 microns or not greater than about 40 microns or not greater than about 30 microns or not greater than about 20 microns.

Item 212. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210, wherein body comprises a corner roundness of at least about 0.1 microns or at least about 0.5 microns.

Item 213. The shaped abrasive particle of any one of items 206, 207, 208, 209, and 210, wherein the body comprises a major surface including a self-similar feature.

Item 214. The shaped abrasive particle of any one of items 205 and 213, wherein the self-similar feature comprises an arrangement of two-dimensional shapes having substantially the same two-dimensional shape of the periphery of the major surface.

Item 215. The shaped abrasive particle of any one of items 205 and 213, wherein the major surface has a two-dimen-



sional shape selected from the group consisting of regular polygons, irregular polygons, irregular shapes, triangles, quadrilaterals, rectangles, trapezoids, pentagons, hexagons, heptagons, octagons, ellipses, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 216. The shaped abrasive particle of any one of items 205 and 213, wherein the major surface comprises a triangular two-dimensional shape.

Item 217. The shaped abrasive particle of any one of items 205 and 213, wherein the self-similar feature comprises a plurality of triangular two-dimensional shapes nested within each other.

Item 218. The shaped abrasive particle of any one of items 205, 207, 208, 209, and 210, wherein the body has at least one peripheral ridge extending around at least a portion of a side surface of the body.

Item 219. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge extends around a majority of the side surface of the body.

Item 220. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge extends around an entire side surface of the body.

Item 221. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge extends around the side surface of the body without intersecting a major surface.

Item 222. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge intersects at least two surfaces and an edge of the body.

Item 223. The shaped abrasive particle of any one of items 206 and 218, wherein the body comprises a length (l), a width (w), and a thickness (t), wherein  $l \geq w \geq t$ , and the at least one peripheral ridge extends peripherally around a side surface of the body extending between major surfaces.

Item 224. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge comprises a depth that is not greater than about 0.8 t, wherein "t" is a thickness of the body, not greater than about 0.7 t or not greater than about 0.6 t or not greater than about 0.5 t or not greater than about 0.4 t or not greater than about 0.3 t or not greater than about 0.2 t or not greater than about 0.18 t or not greater than about 0.16 t or not greater than about 0.15 t or not greater than about 0.14 t or not greater than about 0.12 t or not greater than about 0.1 t or not greater than about 0.09 t or not greater than about 0.08 t or not greater than about 0.07 t or not greater than about 0.06 t or not greater than about 0.05 t.

Item 225. The shaped abrasive particle of any one of items 206 and 218, wherein the at least one peripheral ridge comprises a depth that is at least about 0.001 t, wherein "t" is a thickness of the body, at least about 0.01 t.

Item 226. The shaped abrasive particle of any one of items 205, 206, 208, 209, and 210, wherein the body has at least one major surface defining a concave, stepped surface.

Item 227. The shaped abrasive particle of any one of items 207 and 226, wherein the concave stepped surface defines a thickness at the midpoint of the major surface that is less than a thickness of the body at an edge.

Item 228. The shaped abrasive particle of any one of items 207 and 226, wherein concave stepped surface comprises a plurality of flats and risers, wherein the flats extend substantially parallel to the plane of the major surface and the risers extend substantially perpendicular to the plane of the major surface.

Item 229. The shaped abrasive particle of item 228, wherein the flats have an average width (wf) that is not

greater than about 0.8 (l), wherein "1" defines a length of the body, not greater than about 0.5 (l) or not greater than about 0.4 (l) or not greater than about 0.3 (l) or not greater than about 0.2 (l) or not greater than about 0.1 (l) or not greater than about 0.09 (l) or not greater than about 0.08 (l).

Item 230. The shaped abrasive particle of item 228, wherein the flats have an average width (wf) that is at least about 0.001 (l), wherein "1" defines a length of the body, at least about 0.005 (l) or at least about 0.01 (l).

Item 231. The shaped abrasive particle of item 228, wherein the risers have an average height (hr) that is not greater than about 0.2 (l), wherein "1" defines a length of the body, not greater than about 0.15 (l) or not greater than about 0.1 (l) or not greater than about 0.05 (l) or not greater than about 0.02 (l).

Item 232. The shaped abrasive particle of item 228, wherein the risers have an average height (hr) that is at least about 0.0001 (l) wherein "1" defines a length of the body, at least about 0.0005 (l).

Item 233. The shaped abrasive particle of item 228, wherein the flats have an average width that is greater than an average height of the risers, wherein the average height of the risers (hr) is not greater than about 0.95 (wf), wherein "wf" defines an average width of the flats, not greater than about 0.9 (wf) or not greater than about 0.8 (wf) or not greater than about 0.7 (wf) or not greater than about 0.5 (wf) or not greater than about 0.3 (wf) or not greater than about 0.2 (wf) or not greater than about 0.1 (wf).

Item 234. The shaped abrasive particle of item 228, wherein the average height of the risers is at least about 0.0001 (wf), wherein "wf" defines an average width of the flats, at least about 0.001 (wf).

Item 235. The shaped abrasive particle of any one of items 205, 206, 208, 209, and 210, wherein the body has at least one major surface defining a convex, stepped surface defining a thickness at the midpoint of the major surface that is greater than a thickness of the body at an edge.

Item 236. The shaped abrasive particle of any one of items 205, 206, 207, 209, and 210, wherein the body comprises at least one transverse ridge extending along at least two surfaces and an adjoining edge between the at least two surfaces.

Item 237. The shaped abrasive particle of any one of items 208 and 236, wherein the at least one transverse ridge extends over at least three surfaces and at least two adjoining edges between the at least three surfaces.

Item 238. The shaped abrasive particle of any one of items 208 and 236, wherein the body comprises a plurality of transverse ridges, each of the transverse ridges of the plurality of transverse ridges extending parallel to each other around at least a portion of the periphery of the body.

Item 239. The shaped abrasive particle of item 238, wherein at least one of the transverse ridges of the plurality of transverse ridges has a different length relative to another transverse ridge of the plurality of transverse ridges.

Item 240. The shaped abrasive particle of item 238, wherein each of the transverse ridges of the plurality of transverse ridges have different lengths relative to each other.

Item 241. The shaped abrasive particle of any one of items 205, 206, 207, 208, and 210, wherein the body comprises a corner including a plurality of microprotrusions extending from the corner.

Item 242. The shaped abrasive particle of any one of items 209 and 241, wherein the microprotrusions define a plurality of discrete corner protrusions separated by a plurality of ridges.



Item 243. The shaped abrasive particle of item 242, wherein the plurality of discrete corner protrusions have a plurality of different contours relative to each other.

Item 244. The shaped abrasive particle of item 242, wherein at least two discrete corner protrusions have a different corner radius relative to each other.

Item 245. The shaped abrasive particle of item 242, wherein at least two discrete corner protrusions define a step having a lateral shift relative to each other.

Item 246. The shaped abrasive particle of any one of items 209 and 241, wherein the corner roundness at an upper surface is different than a corner roundness at a bottom surface, and wherein the upper surface has a lower surface area than the bottom surface.

Item 247. The shaped abrasive particle of any one of items 209 and 241, wherein the microprotrusions define a serrated edge.

Item 248. The shaped abrasive particle of any one of items 205, 206, 207, 208, and 209, wherein the body has a surface comprising a scalloped topography.

Item 249. The shaped abrasive particle of any one of items 210 and 248, wherein the scalloped topography extends over a majority of a surface area of at least one surface of the body.

Item 250. The shaped abrasive particle of any one of items 210 and 248, wherein the scalloped topography extends over a majority of an entire surface area of at least one surface of the body.

Item 251. The shaped abrasive particle of any one of items 210 and 248, wherein the scalloped topography defines a plurality of curved protrusions having ridges extending between the curved protrusions.

Item 252. The shaped abrasive particle of any one of items 210 and 248, wherein the scalloped topography includes a plurality of elongated protrusions, each protrusion having a length, a width, and a height, wherein each protrusion has an arcuate contour extending in the direction of the width and the height.

Item 253. The shaped abrasive particle of item 252, wherein the length of each elongated protrusion extends substantially in the direction of a length of the body.

Item 254. The shaped abrasive particle of item 252, wherein the length of at least one elongated protrusion is at least about 0.8 (l), wherein "l" is the length of the body, at least about 0.9 (l) or at least about 1 (l).

Item 255. The shaped abrasive particle of item 252, wherein the plurality of elongated protrusions have an average height that is less than the average width (wep), wherein the average height of the plurality of elongated protrusion is not greater than about 0.9 (wep) or not greater than about 0.8 (wep) or not greater than about 0.7 (wep) or not greater than about 0.6 (wep) or not greater than about 0.5 (wep) or not greater than about 0.4 (wep) or not greater than about 0.3 (wep) or not greater than about 0.2 (wep) or not greater than about 0.1 (wep).

Item 256. The shaped abrasive particle of item 255, wherein the average height of the plurality of elongated protrusions is not greater than about 500 microns or not greater than about 400 microns or not greater than about 300 microns or not greater than about 250 microns or not greater than about 200 microns or not greater than about 150 microns or not greater than about 100 microns or not greater than about 90 microns or not greater than about 70 microns or not greater than about 50 microns.

Item 257. The shaped abrasive particle of item 252, wherein the plurality of elongated protrusions comprises an average width that is less than the average length.

Item 258. The shaped abrasive particle of item 252, wherein plurality of elongated protrusions have an average width that is less than the length (l) of the body, wherein the average width of the plurality of elongated protrusion is not greater than about 0.9 (l) or not greater than about 0.8 (l) or not greater than about 0.7 (l) or not greater than about 0.6 (l) or not greater than about 0.5 (l) or not greater than about 0.4 (l) or not greater than about 0.3 (l) or not greater than about 0.2 (l) or not greater than about 0.1 (l).

Item 259. The shaped abrasive particle of item 252, wherein the average width of the plurality of elongated protrusion is at least about 0.001 (l) or at least about 0.01 (l).

Item 260. The shaped abrasive particle of item 252, wherein the average width of the plurality of elongated protrusions is not greater than about 500 microns or not greater than about 400 microns or not greater than about 300 microns or not greater than about 250 microns or not greater than about 200 microns.

Item 261. The shaped abrasive particle of any one of items 210 and 248, wherein the scalloped topography intersects an edge defining at least one corner of the body and defines an edge having a serrated contour along the length of the edge.

Item 262. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises at least 4 major surfaces joined together at common edges.

Item 263. The shaped abrasive particle of item 262, wherein the at least 4 major surfaces have substantially the same surface area.

Item 264. The shaped abrasive particle of item 262, wherein the body comprises a tetrahedral shape.

Item 265. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises a three-dimensional shape selected from the group consisting of a polyhedron, a pyramid, an ellipsoid, a sphere, a prism, a cylinder, a cone, a tetrahedron, a cube, a cuboid, a rhomohedron, a truncated pyramid, a truncated ellipsoid, a truncated sphere, a truncated cone, a pentahedron, a hexahedron, a heptahedron, an octahedron, a nonahedron, a decahedron, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, a volcano shape, monostatic shape, and a combination thereof.

Item 266. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises a three-dimensional shape including a body length (Lb), a body width (Wb), and a body thickness (Tb), and wherein  $Lb > Wb$ ,  $Lb > Tb$ , and  $Wb > Tb$ .

Item 267. The shaped abrasive particle of item 266, wherein the body comprises a primary aspect ratio (Lb:Wb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 268. The shaped abrasive particle of item 266, wherein the body comprises a secondary aspect ratio (Lb:Tb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 269. The shaped abrasive particle of item 266, wherein the body comprises a tertiary aspect ratio (Wb:Tb) of at least about 1:1 or at least about 2:1 or at least about 3:1 or at least about 5:1 or at least about 10:1, and not greater than about 1000:1.

Item 270. The shaped abrasive particle of item 266, wherein the body comprises a cross-sectional shape in a plane defined by the body length and the body width selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal,



octagonal, ellipsoids, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 271. The shaped abrasive particle of item 266, wherein the body comprises a cross-sectional shape in a plane defined by the body length and the body thickness selected from the group consisting of triangular, quadrilateral, rectangular, trapezoidal, pentagonal, hexagonal, heptagonal, octagonal, ellipsoids, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, and a combination thereof.

Item 272. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body is essentially free of a binder, wherein the body is essentially free of an organic material.

Item 273. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises a polycrystalline material, wherein the polycrystalline material comprises grains, wherein the grains are selected from the group of materials consisting of nitrides, oxides, carbides, borides, oxynitrides, diamond, and a combination thereof, wherein the grains comprise an oxide selected from the group of oxides consisting of aluminum oxide, zirconium oxide, titanium oxide, yttrium oxide, chromium oxide, strontium oxide, silicon oxide, and a combination thereof, wherein the grains comprise alumina, wherein the grains consist essentially of alumina.

Item 274. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body is formed from a seeded sol gel.

Item 275. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises a polycrystalline material having an average grain size not greater than about 1 micron.

Item 276. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body is a composite comprising at least about 2 different types of compositions.

Item 277. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body comprises an additive, wherein the additive comprises an oxide, wherein the additive comprises a metal element, wherein the additive comprises a rare-earth element.

Item 278. The shaped abrasive particle of item 277, wherein the additive comprises a dopant material, wherein the dopant material includes an element selected from the group consisting of an alkali element, an alkaline earth element, a rare earth element, a transition metal element, and a combination thereof, wherein the dopant material comprises an element selected from the group consisting of hafnium, zirconium, niobium, tantalum, molybdenum, vanadium, lithium, sodium, potassium, magnesium, calcium, strontium, barium, scandium, yttrium, lanthanum, cesium, praseodymium, chromium, cobalt, iron, germanium, manganese, nickel, titanium, zinc, and a combination thereof.

Item 279. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the body is coupled to a substrate as part of a fixed abrasive, wherein the fixed abrasive article is selected from the group consisting of a bonded abrasive article, a coated abrasive article, and a combination thereof.

Item 280. The shaped abrasive particle of item 279 wherein the substrate is a backing, wherein the backing comprises a woven material, wherein the backing comprises a non-woven material, wherein the backing comprises an organic material, wherein the backing comprises a polymer, wherein the backing comprises a material selected from the

group consisting of cloth, paper, film, fabric, fleeced fabric, vulcanized fiber, woven material, non-woven material, webbing, polymer, resin, phenolic resin, phenolic-latex resin, epoxy resin, polyester resin, urea formaldehyde resin, polyester, polyurethane, polypropylene, polyimides, and a combination thereof.

Item 281. The shaped abrasive particle of item 280, wherein the backing comprises an additive selected from the group consisting of catalysts, coupling agents, curants, anti-static agents, suspending agents, anti-loading agents, lubricants, wetting agents, dyes, fillers, viscosity modifiers, dispersants, defoamers, and grinding agents.

Item 282. The shaped abrasive particle of item 280, further comprising an adhesive layer overlying the backing, wherein the adhesive layer comprises a make coat, wherein the make coat overlies the backing, wherein the make coat is bonded directly to a portion of the backing, wherein the make coat comprises an organic material, wherein the make coat comprises a polymeric material, wherein the make coat comprises a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

Item 283. The shaped abrasive particle of item 282, wherein the adhesive layer comprises a size coat, wherein the size coat overlies a portion of the plurality of shaped abrasive particles, wherein the size coat overlies a make coat, wherein the size coat is bonded directly to a portion of the plurality of shaped abrasive particles, wherein the size coat comprises an organic material, wherein the size coat comprises a polymeric material, wherein the size coat comprises a material selected from the group consisting of polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, polyvinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and a combination thereof.

Item 284. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the shaped abrasive particle is part of a plurality of a first type of shaped abrasive particles, wherein a majority of the first type of shaped abrasive particles are coupled to a backing in an open coat, wherein the open coat comprises a coating density of not greater than about 70 particles/cm<sup>2</sup> or not greater than about 65 particles/cm<sup>2</sup> or not greater than about 60 particles/cm<sup>2</sup> or not greater than about 55 particles/cm<sup>2</sup> or not greater than about 50 particles/cm<sup>2</sup> or at least about 5 particles/cm<sup>2</sup> or at least about 10 particles/cm<sup>2</sup>.

Item 285. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the shaped abrasive particle is part of a plurality of a first type of shaped abrasive particles, wherein a majority of the first type of shaped abrasive particles are coupled to a backing in a closed coat, wherein having a closed coat of the blend of shaped abrasive particles on a backing, wherein the closed coat comprises a coating density of at least about 75 particles/cm<sup>2</sup> or at least about 80 particles/cm<sup>2</sup> or at least about 85 particles/cm<sup>2</sup> or at least about 90 particles/cm<sup>2</sup> or at least about 100 particles/cm<sup>2</sup>.

Item 286. The shaped abrasive particle of any one of items 205, 206, 207, 208, 209, and 210 wherein the shaped abrasive particle is part of a blend including a plurality of a first type of shaped abrasive particles and a third type of abrasive particle, wherein the third type of abrasive particle comprises a shaped abrasive particle, wherein the third type



of abrasive particle comprises a diluent type of abrasive particle, wherein the diluent type of abrasive particle comprises an irregular shape.

Item 287. The shaped abrasive particle of item 286, wherein the blend of abrasive particles comprises a plurality of shaped abrasive particles, and wherein each shaped abrasive particle of the plurality of shaped abrasive particles is arranged in a controlled orientation relative to a backing, the controlled orientation including at least one of a predetermined rotational orientation, a predetermined lateral orientation, and a predetermined longitudinal orientation.

Item 288. A method of forming a shaped abrasive particle using a low pressure injection molding process.

Item 289. The method of item 288, wherein the low pressure injection molding includes filling a mold with a mold material using laminar flow conditions.

Item 290. The method of item 288, wherein the laminar flow conditions are based on at least one of a rheology of the mold material, the shape of the mold, mold material, and a combination thereof.

## EXAMPLES

### Example 1

A print material was made by creating a mixture including 39 wt % boehmite and alpha alumina seeds in water. Nitric acid was added to adjust the pH of the mixture to 4. The print material was then transferred to a container, de-aired using a vacuum pump, and aged at room temperature for up to 30 days or until the rheological properties were sufficient for printing. The print material was then loaded into a deposition assembly of a robocasting unit, commercially available as EFD Nordson® Ultra TT 525 having a Tungsten Palm OS® controller and EFD 1.2 software. The deposition assembly includes a nozzle having a nozzle width of 100  $\mu\text{m}$ , a nozzle tip length of approximately 6.35 mm or 3 mm. The print material had a static yield stress of approximately 750 Pa, a dynamic yield stress of approximately 450 Pa. The print material was a shear thinning mixture with an apparent viscosity of 9000 Pa s at a shear rate of 100  $\text{s}^{-1}$ .

The height of the nozzle and the tactile height sensor were carefully adjusted so that the height measurements used by the printer were accurate. An initial line of print material was deposited to expel air and adjust the deposition pressure, deposition rate, deposition volume, and dispense gap. Certain process parameters such as the deposition rate, deposition pressure, and dispense gap were evaluated and adjusted based on the rheological characteristics of the print material until the printed line had approximately the same width as the nozzle width. The pressure was approximately 0.5 MPa (70 psi), the deposition rate was approximately 3 mm/s, and the dispense gap was approximately 100  $\mu\text{m}$ .

A program for forming a shaped abrasive particle having a triangular shape including deposition of 6 layers of the same size was loaded onto the controller. The filling pattern included deposition of a first layer having a triangular two-dimensional shape using an outside-in “escargot” process. The premove delay was 0.1 seconds. A second layer was then formed overlying the first layer. The nozzle was moved vertically upward 100  $\mu\text{m}$  above the stop position of the first layer. The second layer was then formed having a triangular two-dimensional shape and was formed using a filling pattern based on an inside-out process. The premove delay was 0.3 seconds. Four additional layers were formed on top of each other using the alternating outside-in and inside-out process until 6 layers were formed.

The body was dried in ambient conditions and sintered at approximately 1250° C. for 90 minutes. The shaped abrasive particle of FIG. 20 is representative of the shaped abrasive particle formed according to Example 1.

### Example 2

A tetrahedral or pyramidal shaped abrasive particle was formed using the same print material of Example 1. The robocasting parameters were the same as Example 1 except that the nozzle width was 150 microns and the nozzle length was approximately 6.35 mm. Moreover, the filling process was essentially the same as Example 1, except that the premove delay was 0.2 seconds for layers formed using an inside-out filling process, and each of the layers got successively smaller in size as the pyramidal shape was formed. The shaped abrasive particles were dried in ambient conditions and sintered at approximately 1250° C. for 90 minutes. The shaped abrasive particle of FIGS. 28 and 29 is representative of a shaped abrasive particle formed according to Example 2.

### Example 3

A volcano-shape, shaped abrasive particle was formed using the same print material of Example 2, except that the filling process is changed for a final grouping of the layers, such as about the last 3 layers. The filling pattern uses an alternating outside-in and inside-out filling process as described in Example 2, except that the final group of layers were deposited around the periphery of the shape, but did not deposit the print material fully into the interior of the body to create the opening and volcano-shape. The shaped abrasive particles were dried in ambient conditions and sintered at approximately 1250° C. for 90 minutes. The shaped abrasive particle of FIG. 27 is representative of a shaped abrasive particle formed according to Example 3 including the opening 2709.

Certain references have demonstrated the formation of various objects on a centimeter scale by certain additive manufacturing techniques. However, these references are not directed to the formation of shaped abrasive particles having the features of the shaped abrasive particles of the embodiments herein making them suitable for use as abrasives. Moreover, formation of shaped abrasive particles having the features and dimensions of the embodiments herein, which makes them suitable for their intended purpose, requires knowledge that is not readily available from references disclosing formation of articles on a centimeter scale. The knowledge needed to migrate from centimeter scale technology to millimeter or micron sized technology is non-trivial and was the result of significant research. Benefits, other advantages, and solutions to problems have been described above with regard to specific embodiments. However, the benefits, advantages, solutions to problems, and any feature(s) that may cause any benefit, advantage, or solution to occur or become more pronounced are not to be construed as a critical, required, or essential feature of any or all the items.

The shaped abrasive particles of the embodiments herein are suitable for use in fixed abrasive articles, which may be used to create products in various industries including metal working and fabrication industries, the automotive industry, building and construction materials, and the like.

The specification and illustrations of the embodiments described herein are intended to provide a general understanding of the structure of the various embodiments. The



specification and illustrations are not intended to serve as an exhaustive and comprehensive description of all of the elements and features of apparatus and systems that use the structures or methods described herein. Separate embodiments may also be provided in combination in a single embodiment, and conversely, various features that are, for brevity, described in the context of a single embodiment, may also be provided separately or in any subcombination. Further, reference to values stated in ranges includes each and every value within that range. Many other embodiments may be apparent to skilled artisans only after reading this specification. Other embodiments may be used and derived from the disclosure, such that a structural substitution, logical substitution, or another change may be made without departing from the scope of the disclosure. Accordingly, the disclosure is to be regarded as illustrative rather than restrictive.

The foregoing description in combination with the figures is provided to assist in understanding the teachings disclosed herein. The following discussion will focus on specific implementations and embodiments of the teachings. This focus is provided to assist in describing the teachings and should not be interpreted as a limitation on the scope or applicability of the teachings. However, other teachings can certainly be used in this application.

As used herein, the terms “comprises,” “comprising,” “includes,” “including,” “has,” “having” or any other variation thereof, are intended to cover a non-exclusive inclusion. For example, a method, article, or apparatus that comprises a list of features is not necessarily limited only to those features but may include other features not expressly listed or inherent to such method, article, or apparatus. Further, unless expressly stated to the contrary, “or” refers to an inclusive-or and not to an exclusive-or. For example, a condition A or B is satisfied by any one of the following: A is true (or present) and B is false (or not present), A is false (or not present) and B is true (or present), and both A and B are true (or present).

Also, the use of “a” or “an” is employed to describe elements and components described herein. This is done merely for convenience and to give a general sense of the scope of the invention. This description should be read to include one or at least one and the singular also includes the plural, or vice versa, unless it is clear that it is meant otherwise. For example, when a single item is described herein, more than one item may be used in place of a single item. Similarly, where more than one item is described herein, a single item may be substituted for that more than one item.

Unless otherwise defined, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. The materials, methods, and examples are illustrative only and not intended to be limiting. To the extent not described herein, many details regarding specific materials and processing acts are conventional and may be found in reference books and other sources within the structural arts and corresponding manufacturing arts.

What is claimed is:

1. A method of forming a shaped abrasive particle having a body, the method comprising:  
 depositing a print material from a nozzle to a target using an additive manufacturing process to form the body of the shaped abrasive particle, wherein the print material comprises a viscosity of at least about  $4 \times 10^3$  Pa s; and  
 controlling a dispense gap defining a distance between the nozzle and the target, wherein the dispense gap is not

greater than about 10 W, wherein “W” represents the width of the nozzle, and wherein controlling the dispense gap includes varying a Z-directional distance between the nozzle and the target based upon at least one of the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, the filling pattern of the print material, the dynamic yield stress ( $\sigma_d$ ) of the print material, the static yield stress ( $\sigma_s$ ) of the print material, the yield stress ratio ( $\sigma_d/\sigma_s$ ) of the print material, and the viscosity of the print material.

2. The method of claim 1, wherein the additive manufacturing process includes forming the body by shaping the print material without use of a production tool.

3. The method of claim 1, wherein depositing the print material comprises depositing a plurality of discrete portions of the print material in a controlled, non-random manner relative to each other.

4. The method of claim 3, wherein depositing a plurality of discrete portions of the body in a controlled, non-random manner relative to each other includes deposition of the plurality of portions into a production tool.

5. The method of claim 1, wherein the additive manufacturing process comprises at least one process selected from the group consisting of layer additive method, light photopolymerization, laser powder forming, powder bed fusion, selective laser sintering, micro-laser sintering, material extrusion robocasting, material jetting, and sheet lamination.

6. The method of claim 1, wherein depositing the print material comprises:

depositing a first print material as a first portion of the body at a first time; and

depositing a second print material as a second portion of the body distinct from the first portion at a second time.

7. The method of claim 6, wherein the first portion has a different hardness, porosity, composition, or combination thereof than the second portion.

8. The method of claim 1, wherein the nozzle comprises a nozzle width not greater than about 100 microns, a tip length of not greater than about 10 mm, and an aspect ratio value (width/tip length) of not greater than about 0.8.

9. The method of claim 1, wherein the body comprises a corner roundness of not greater than about 100 microns.

10. A method of forming a shaped abrasive particle having a body, wherein forming the body comprises:

depositing a print material from a nozzle to a target using an additive manufacturing process, wherein the additive manufacturing process includes depositing a plurality of discrete portions of print material in a controlled, non-random manner relative to each other in a filling pattern, and wherein the print material comprises a viscosity of at least about  $4 \times 10^{-3}$  Pa·s; and

controlling a dispense gap defining a distance between the nozzle and the target wherein the dispense gap is not greater than about 10 W, wherein “W” represents the width of the nozzle,

wherein depositing the print material comprises depositing a first print material as a first portion of the body at a first time; and depositing a second print material as a second portion of the body distinct from the first portion at a second time; and

wherein depositing the print material comprises using an outside-in filling process, an inside-out filling process, a side-to-side filling process, a bottom-up filling process, or a combination thereof.



75

11. The method of claim 10, wherein the additive manufacturing process includes forming a body of a shaped abrasive particle by shaping a raw material without use of a production tool.

12. The method of claim 10, wherein the additive manufacturing process includes forming a body of a shaped abrasive particle by depositing a plurality of discrete portions in a controlled, non-random manner relative to each other.

13. The method of claim 12, wherein depositing a plurality of discrete portions of the body in a controlled, non-random manner relative to each other includes deposition of the plurality of portions into a production tool.

14. The method of claim 10, wherein the additive manufacturing process comprises at least one process selected from the group consisting of layer additive method, light photopolymerization, laser powder forming, powder bed fusion, selective laser sintering, micro-laser sintering, material extrusion robocasting, material jetting, sheet lamination, and a combination thereof.

15. The method of claim 10, wherein the first portion can have a hardness, a porosity, a composition, or a combination thereof different than the second portion.

16. The method of claim 10, wherein the method of forming the body further comprises depositing the print material from a nozzle, wherein the movement of the nozzle is controlled by a computer program and the nozzle comprises a nozzle width not greater than about 100 microns, a tip length of not greater than about 10 mm, and an aspect ratio value (width/tip length) of not greater than about 0.8.

17. The method of claim 10, wherein controlling the dispense gap includes varying a Z-directional distance

76

between the nozzle and the target based upon at least one of the nozzle tip length, the nozzle width, the deposition pressure, the deposition rate, the deposition volume, the deposition position, the filling pattern of the print material, the dynamic yield stress ( $\sigma_d$ ) of the print material, the static yield stress ( $\sigma_s$ ) of the print material, the yield stress ratio ( $\sigma_d/\sigma_s$ ) of the print material, the viscosity of the print material, and a combination thereof.

18. The method of claim 10, wherein the body comprises a corner roundness of not greater than about 100 microns.

19. A method of forming a shaped abrasive particle having a body, the method comprising:

depositing a print material from a nozzle to a target using an additive manufacturing process to form the body of the shaped abrasive particle, wherein depositing the print material comprises depositing a plurality of discrete portions of the print material in a controlled, non-random manner relative to each other, and wherein the print material comprises a viscosity of at least about  $4 \times 10^3$  Pa s; and

controlling a dispense gap defining a distance between the nozzle and the target, wherein the dispense gap is not greater than about 10 W, wherein "W" represents the width of the nozzle;

wherein the nozzle comprises a nozzle width not greater than about 100 microns, a tip length of not greater than about 10 mm, and an aspect ratio value (width/tip length) of not greater than about 0.8; and

wherein the body comprises a corner roundness of not greater than about 100 microns.

\* \* \* \* \*