



US009854870B2

(12) **United States Patent**
Hensley et al.

(10) **Patent No.:** **US 9,854,870 B2**
(45) **Date of Patent:** ***Jan. 2, 2018**

(54) **METHOD OF MANUFACTURING A
BLADDER ELEMENT WITH AN
IMPRESSION OF ETCHED AREA OF MOLD
ASSEMBLY AND ARTICLE HAVING
BLADDER ELEMENT WITH IMPRESSION**

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,151,314 A 10/1935 Burger
3,591,402 A 7/1971 Blackfan
(Continued)

FOREIGN PATENT DOCUMENTS

CA 1111222 A 10/1981
DE 243211 A1 2/1987
(Continued)

OTHER PUBLICATIONS

American Society for Testing and Materials (ASTM) Standard D1003-00, Standard Test Method for Haze and Luminous Transmittance of Transparent Plastics, Jul. 2000, Book of Standards vol. 08.01, ASTM International, Pennsylvania, USA.

(Continued)

Primary Examiner — Shamim Ahmed

(74) *Attorney, Agent, or Firm* — Quinn IP Law

(57) **ABSTRACT**

A method of manufacturing an article includes disposing polymeric material in a mold assembly that has a mold surface that has an etched area. The method further comprises forming a fluid-filled bladder element at least partially by conforming the polymeric material to the mold surface, thereby imparting an impression of the etched area on a surface of the bladder element. The method includes assembling the bladder element in the article so that a first portion of the bladder element with the impression of the etched area is exposed to view, and a second portion of the bladder element is blocked from view by the article. An article comprises the bladder element with the etched area.

21 Claims, 7 Drawing Sheets

(71) Applicant: **NIKE, Inc.**, Beaverton, OR (US)

(72) Inventors: **Taryn Hensley**, Beaverton, OR (US);
Dervin A. James, Hillsboro, OR (US)

(73) Assignee: **NIKE, Inc.**, Beaverton, OR (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **15/093,090**

(22) Filed: **Apr. 7, 2016**

(65) **Prior Publication Data**


US 2016/0295965 A1 Oct. 13, 2016

Related U.S. Application Data

(60) Provisional application No. 62/144,571, filed on Apr. 8, 2015.

(51) **Int. Cl.**
A43B 13/20 (2006.01)
A43B 1/00 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC *A43B 13/20* (2013.01); *A43B 1/0072* (2013.01); *A43B 3/0078* (2013.01); *A43B 13/12* (2013.01);
(Continued)



(51)	Int. Cl. <i>B29C 33/42</i> (2006.01) <i>A43B 3/00</i> (2006.01) <i>A43B 23/24</i> (2006.01) <i>B29D 35/12</i> (2010.01) <i>B29D 35/14</i> (2010.01) <i>A43B 13/12</i> (2006.01) <i>B29C 33/38</i> (2006.01) <i>B29K 23/00</i> (2006.01) <i>B29K 75/00</i> (2006.01)	2004/0071936 A1* 4/2004 Martelli B29C 33/42 428/141 2005/0023185 A1 2/2005 Ramet 2006/0017200 A1 1/2006 Cundiff et al. 2007/0000605 A1 1/2007 Millette et al. 2007/0294832 A1 12/2007 Shiao 2008/0110047 A1 5/2008 White et al. 2008/0261016 A1 10/2008 Tamada et al. 2009/0013557 A1 1/2009 Rudy 2009/0045542 A1 2/2009 Borchert et al. 2013/0068378 A1 3/2013 Dua et al. 2014/0202033 A1 7/2014 Connell et al. 2014/0259749 A1 9/2014 Taylor et al. 2015/0351499 A1 12/2015 James 2016/0295963 A1 10/2016 Chang et al. 2016/0295964 A1 10/2016 Hensley et al. 2016/0295966 A1 10/2016 Hensley et al.
(52)	U.S. Cl. CPC <i>A43B 13/203</i> (2013.01); <i>A43B 23/24</i> (2013.01); <i>B29C 33/3842</i> (2013.01); <i>B29C</i> <i>33/42</i> (2013.01); <i>B29D 35/122</i> (2013.01); <i>B29D 35/128</i> (2013.01); <i>B29D 35/142</i> (2013.01); <i>B29D 35/148</i> (2013.01); <i>B29K</i> <i>2023/086</i> (2013.01); <i>B29K 2075/00</i> (2013.01); <i>B29K 2995/0067</i> (2013.01)	

FOREIGN PATENT DOCUMENTS

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,183,156 A	1/1980	Rudy	
4,219,945 A	9/1980	Rudy	
4,936,029 A	6/1990	Rudy	
5,042,176 A	8/1991	Rudy	
5,393,372 A	2/1995	Ammon	
5,572,804 A	11/1996	Skaja et al.	
5,580,410 A	12/1996	Johnston	
5,713,141 A	2/1998	Mitchell et al.	
5,735,776 A	4/1998	Swezey et al.	
5,802,739 A	9/1998	Potter et al.	
5,815,950 A	10/1998	Wang	
5,885,515 A	3/1999	Hudkins	
5,952,065 A	9/1999	Mitchell et al.	
6,009,637 A	1/2000	Pavone	
6,013,340 A	1/2000	Bonk et al.	
6,060,144 A	5/2000	Kimura et al.	
6,082,025 A	7/2000	Bonk et al.	
6,099,789 A	8/2000	Sumi	
6,127,026 A	10/2000	Bonk et al.	
6,164,729 A	12/2000	Dibenedetto et al.	
6,203,868 B1	3/2001	Bonk et al.	
6,299,962 B1*	10/2001	Davis A43B 23/0255 12/142 P	
6,321,465 B1	11/2001	Bonk et al.	
6,361,840 B2	3/2002	Nelson et al.	
6,402,879 B1	6/2002	Tawney et al.	
6,451,417 B1	9/2002	Sumi et al.	
6,544,634 B1	4/2003	Abrams et al.	
6,547,703 B1	4/2003	Swezey et al.	
6,571,490 B2	6/2003	Tawney et al.	
6,632,858 B1	10/2003	Pears et al.	
6,944,973 B2	9/2005	Goodwin	
6,998,005 B2	2/2006	Magee et al.	
7,073,276 B2	7/2006	Swigart	
7,131,218 B2	11/2006	Schindler	
7,152,343 B2	12/2006	Whatley	
7,178,267 B2	2/2007	Skaja et al.	
7,401,369 B2	7/2008	White et al.	
7,449,087 B2	11/2008	Odajima et al.	
7,622,014 B2	11/2009	Millette et al.	
7,622,066 B2	11/2009	Brustad et al.	
8,574,387 B2	11/2013	Hull et al.	
8,850,719 B2	10/2014	Hawkinson et al.	
9,198,477 B2	12/2015	Davis et al.	
2003/0151168 A1	8/2003	Gohl et al.	

DE	4038077 A1	6/1992
GB	1215135 A	12/1970
GB	1265142 A	3/1972
GB	1308776 A	3/1973
GB	2330551 A	4/1999
GB	2381492 A	5/2003
JP	S57174215 A	10/1982
JP	S57178724 A	11/1982
JP	S57185120 A	11/1982
JP	S6116830 A	1/1986
JP	S61146508 A	7/1986
JP	S6232023 A	2/1987
JP	S62280022 A	12/1987
JP	S631521 A	1/1988
JP	S6354230 A	3/1988
JP	S63212528 A	9/1988
JP	S63249615 A	10/1988
JP	S63252718 A	10/1988
JP	S6434719 A	2/1989
JP	H0218025 A	1/1990
JP	H0218026 A	1/1990
JP	H0263717 A	3/1990
JP	H04187418 A	7/1992
JP	H04331127 A	11/1992
JP	H08294957 A	11/1996
JP	H08323849 A	12/1996
JP	H0911324 A	1/1997
JP	H0939078 A	2/1997
JP	H0948063 A	2/1997
JP	H0957826 A	3/1997
JP	H10156927 A	6/1998
JP	H10217320 A	8/1998
JP	2003145612 A	5/2003
JP	2004009304 A	1/2004
JP	2004291647 A	10/2004
JP	2005103965 A	4/2005
JP	2005280250 A	10/2005
JP	2006015760 A	1/2006
JP	2008109501 A	5/2008
RU	2004447 C1	12/1993
WO	2010039826 A2	4/2010

OTHER PUBLICATIONS

Nike Air Max 2015, Nov. 19, 2014; <https://web.archive.org/web/20141119223217/http://news.nike.com/news/nike-air-max-2015-soft-cushioning-dynamic-fit-and-bold-design> [retrieved on Jul. 20, 2016].

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8





FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18

1

**METHOD OF MANUFACTURING A
BLADDER ELEMENT WITH AN
IMPRESSION OF ETCHED AREA OF MOLD
ASSEMBLY AND ARTICLE HAVING
BLADDER ELEMENT WITH IMPRESSION**

CROSS-REFERENCE TO RELATED
APPLICATION

This application claims the benefit of U.S. Provisional Application No. 62/144,571 filed Apr. 8, 2015, which is hereby incorporated by reference in its entirety.

TECHNICAL FIELD

The present teachings generally include an article that comprises a bladder element having a surface with an impression, and a method of manufacturing the bladder element from a mold assembly with an etched area.

BACKGROUND

Clothing, an accessory, and/or athletic wear are often a source of expression for the wearer. The clothing, accessory, and/or athletic wear may provide an association with a team, coordinate with another item, or provide the owner or user with an attractive or customized item.

Footwear typically includes a sole configured to be located under a wearer's foot to space the foot away from the ground or floor surface. Footwear sometimes utilizes polyurethane foam or other resilient materials in the sole to provide cushioning

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic illustration in perspective view of a first embodiment of a bladder element having polymeric sheets with impressions and an etched feature.

FIG. 2 is a schematic illustration in fragmentary view of a portion of colored medium applied to one of the polymeric sheets of FIG. 1.

FIG. 3 is a schematic illustration in bottom view of the bladder element of FIG. 1 showing another impression.

FIG. 4 is a schematic illustration in fragmentary cross-sectional view of the article of bladder element of FIG. 1 taken at lines 4-4 in FIG. 1.

FIG. 5 is a schematic illustration in plan view of a mold half of a mold assembly for forming the bladder element of FIG. 1.

FIG. 6 is a schematic illustration in cross-sectional view of the mold half of FIG. 5 taken at lines 6-6 in FIG. 5.

FIG. 7 is a schematic illustration in cross-sectional view of another mold half of the mold assembly taken at lines 7-7 in FIG. 8.

FIG. 8 is a schematic illustration in plan view of the mold half of FIG. 7.

FIG. 9 is a schematic illustration in fragmentary cross-sectional view of the article of footwear of FIG. 14 taken at lines 9-9 in FIG. 14.

FIG. 10 is a schematic illustration in fragmentary cross-sectional view of an outer layer of the polymeric sheet shown in FIG. 9 with the etched feature.

FIG. 11 is a schematic illustration in fragmentary cross-sectional view of an alternative embodiment of an outer layer of the polymeric sheet of FIG. 9 with an alternative impression.

2

FIG. 12 is a schematic illustration in plan view of a second polymeric sheet used to form the bladder element of FIG. 1, showing an image applied with a colored medium.

FIG. 13 is a schematic illustration in plan view of a first polymeric sheet used to form the bladder element of FIG. 1, showing images applied with a colored medium, and an etched feature.

FIG. 14 is a schematic side view illustration of an article of footwear having a sole assembly with the bladder element of FIG. 1 secured to the sole assembly.

FIG. 15 is a schematic top view illustration of the article of footwear of FIG. 14.

FIG. 16 is a schematic bottom view illustration of the article of footwear of FIG. 14 having a first embodiment of an outsole.

FIG. 17 is a schematic bottom view illustration of the article of footwear of FIG. 14 having an alternative embodiment of an outsole.

FIG. 18 is a flow diagram illustrating a method of manufacturing an article such as the article of footwear of FIG. 14.

DESCRIPTION

A method of manufacturing an article includes disposing polymeric material in a mold assembly that has a mold surface. The mold surface has an etched area. The method further comprises forming a fluid-filled bladder element at least partially by conforming the polymeric material to the mold surface. The conforming imparts an impression of the etched area on a surface of the fluid-filled bladder element. The method includes assembling the fluid-filled bladder element in the article so that a first portion of the fluid-filled bladder element with the impression of the etched area is exposed to view, and a second portion of the fluid-filled bladder element is blocked from view by the article. The fluid-filled bladder element has a sealable internal cavity that retains fluid.

The article may have an opening, and the impression may be aligned with the opening, and exposed to view through the opening. For example, the article may be an article of footwear having a sole assembly and an upper, with the opening in one of the sole assembly and the upper. Assembling the fluid-filled bladder element in the article may comprise securing the fluid-filled bladder element to the sole assembly so that the impression is aligned with the opening and exposed to view through the opening. For example, the opening may be in a midsole or an outsole of the sole assembly. In an embodiment, the method may comprise securing an outsole, at least one portion of which is substantially transparent, to the fluid-filled bladder element so that the at least one portion of the outsole that is substantially transparent is aligned with the impression, and the impression is exposed to view through the at least one portion of the outsole that is substantially transparent.

The method may comprise etching the etched area in the mold surface by at least one of laser etching, mechanical etching, or chemical etching prior to conforming the polymeric material to the mold surface and imparting the impression. In some embodiments, the method may include applying a colored medium to the first polymeric sheet prior to imparting the impression, and disposing the polymeric material in the mold assembly may comprise positioning the first polymeric sheet in the mold assembly so that the impression of the etched area is adjacent to or on the colored medium on the first polymeric sheet. In other embodiments, a colored medium may be applied to the bladder element after it is

formed. The impression may comprise at least one of a protrusion from or a recess in the surface of the bladder element. In one embodiment, a substantially transparent topcoat may be secured to the fluid-filled bladder element over the impression to protect the impression from damage and abrasion.

Etching of the etched area may be controlled in various ways to enable fluid retention in the internal cavity of the fluid-filled bladder element. For example, etching the etched area may be controlled so that the impression has a maximum depth into the first polymeric sheet of not more than about one-half of a first thickness of the first polymeric sheet. For example, if chemical etching is used, a depth of etching in the mold surface may be controlled at increments of 0.008 to 0.015 inches. In some embodiments, the first polymeric sheet comprises a gas barrier polymer. Etching the etched area may be controlled so that the gas barrier polymer is not compromised by the impression. As used herein, the gas barrier polymer is not compromised by the impression if the fluid retention ability of the fluid-filled bladder element is not decreased due to the etching. In other words, the gas transmission rate of the fluid-filled bladder element does not decrease due to the impression.

The method may further comprise polishing a first region of the mold surface to a first average surface roughness, wherein a second region of the mold surface has a second average surface roughness. The etched area is at least partially in at least one of the first region or the second region. The first average surface roughness may be at least ten percent greater than or at least ten percent less than the second average surface roughness. The surface of the fluid-filled bladder element has a first area corresponding with the first region of the mold surface and a second area corresponding with the second region of the mold surface.

The method may further comprise treating the surface of the fluid-filled bladder element to achieve at least one of a predetermined level of opacity, transparency, or luster of the fluid-filled bladder element. Treating the surface of the fluid-filled bladder element may be by at least one of heating the surface of the fluid-filled bladder element or applying a softening agent to the surface of the fluid-filled bladder element.

Conforming the polymeric material to the mold surface may be by any or all of blow-molding, compression forming, vacuum forming, or thermoforming. Additionally, the etched area may be at least partially on a curved portion of the mold surface so that the at least a portion of the surface of the fluid-filled bladder element with the impression of the etched area is a corresponding curved portion of the fluid-filled bladder element.

The method may further comprise inflating the bladder element by filling the sealable internal cavity with a fluid, and then sealing the sealable internal cavity so that the fluid is retained in the sealable internal cavity. In one embodiment, the fluid is a gas at or above ambient pressure. The fluid-filled bladder element may have a gas transmission rate for nitrogen of less than 10 cubic centimeters per square meter per atmosphere per day, or of less than 1 cubic centimeter per square meter per atmosphere per day.

The fluid-filled bladder element may be formed from various polymeric materials enabling fluid retention and the gas transmission rate as described. For example, the polymeric material may comprise at least a first polymeric sheet that comprises a thermoplastic polymeric material. In one embodiment, the thermoplastic polymeric material may be a thermoplastic polyurethane (TPU). In one embodiment, the TPU is present on at least an outer surface of the first

polymeric sheet. The first polymeric sheet may comprise a multi-layer polymeric sheet. The multi-layer polymeric sheet may be a laminate membrane that comprises at least a first layer comprising the TPU, and at least a second layer comprising a gas barrier polymer. The gas barrier polymer may comprise an ethylene-vinyl alcohol copolymer. In one embodiment, the at least a first layer consists essentially of the TPU, and the at least a second layer consists essentially of the ethylene-vinyl alcohol copolymer.

The method may include forming a peripheral seam in the bladder element by bonding in the mold assembly. The peripheral seam at least partially seals the sealable internal cavity in the bladder element. The peripheral seam is spaced apart from the impression. The method may include assembling the peripheral bladder element in the article so that the impression is at least partially aligned with the opening in the article. Furthermore, the peripheral seam may be covered by the article.

Optionally, in addition to the impression on the first polymeric sheet, the method may include etching an etched feature on the first polymeric sheet prior to disposing the polymeric material on the mold assembly or after the bladder element is formed. Etching of the etched feature is controlled so that a gas barrier layer of the first polymeric sheet is not compromised by the etching. Furthermore, the etched feature may be at least partially aligned with the etched area of the mold assembly during disposing of the first polymeric sheet in the mold assembly so that the impression of the etched area is at least partially on the etched feature. The surface of the bladder element having the impression may be an outer surface. The etched feature may be on one of the outer surface or an inner surface of the bladder element. The method may further comprise applying a colored medium to the first polymeric sheet before or after the bladder element is formed, in which case at least one of the etched feature and the impression may be adjacent to or on the colored medium on the first polymeric sheet.

Within the scope of the present teachings, an article comprises a fluid-filled bladder element including a polymeric material that has a surface with an impression thereon. The fluid-filled bladder element has a sealable internal cavity that retains fluid. A first portion of the fluid-filled bladder element with the impression is exposed to view, and a second portion of the fluid-filled bladder element is blocked from view by the article. Stated differently, the impression is at least partially aligned with the opening and exposed to view through the opening.

The fluid-filled bladder element may be manufactured by disposing the polymeric material in a mold assembly, and then conforming the polymeric material to a mold surface of the mold assembly to at least partially form the fluid-filled bladder element, thereby imparting the impression of the etched area onto the surface of the fluid-filled bladder element. The etched area of the mold surface may be etched on the mold surface by at least one of laser etching, mechanical etching, or chemical etching.

The surface of the fluid-filled bladder element may have a first area corresponding with a first region of the mold surface and a second area corresponding with a second region of the mold surface. The impression is in at least one of the first area and the second area. The first region of the mold surface has a first average surface roughness and the second region of the mold surface has a second average surface roughness. The first average surface roughness is at least ten percent greater than or at least ten percent less than the second average surface roughness.

5

The polymeric material may be conformed to the mold surface by at least one of blow-molding, compression forming, vacuum forming, or thermoforming the polymeric material. The polymeric material may include a first polymeric sheet, and the article may further comprise a colored medium applied to the first polymeric sheet. The impression of the etched area may be adjacent to or on the colored medium on the first polymeric sheet. In one embodiment, the portion of the surface of the fluid-filled bladder element with the impression of the etched area is a curved portion of the fluid-filled bladder element that corresponds with the curved portion of the mold surface.

In one embodiment of the article, the fluid-filled bladder element has a seam that at least partially seals the sealable internal cavity. The impression is spaced apart from the peripheral seam. The peripheral seam may be covered by and blocked from view by the article.

As described with respect to the method, the polymeric material used to form the fluid-filled bladder element of the article may comprise a thermoplastic polymeric material. In one embodiment, the thermoplastic polymeric material may be a thermoplastic polyurethane (TPU). In one embodiment, the polymeric material includes a first polymeric sheet, and the TPU is present on at least an outer surface of the first polymeric sheet. The first polymeric sheet may comprise a multi-layer polymeric sheet. The multi-layer polymeric sheet may be a laminate membrane that comprises at least a first layer comprising the TPU, and at least a second layer comprising a gas barrier polymer. The gas barrier polymer may comprise an ethylene-vinyl alcohol copolymer. In one embodiment, the at least a first layer consists essentially of the TPU, and the at least a second layer consists essentially of the ethylene-vinyl alcohol copolymer. Additionally, in one embodiment, the fluid-filled bladder element may have a gas transmission rate for nitrogen of less than 10 cubic centimeters per square meter per atmosphere per day, or of less than 1 cubic centimeter per square meter per atmosphere per day. The sealable internal cavity may be filled with a gas at or above ambient pressure.

In various embodiments, the impression may comprise at least one of a protrusion from or a recess in the surface of the fluid-filled bladder element. For example, the polymeric material may comprise a first polymeric sheet that has a first thickness. The impression may have a maximum depth into the first polymeric sheet of not more than about one-half of the first thickness. For example, when the first polymeric sheet comprises a gas barrier layer, the maximum depth of the impression does not compromise the gas barrier layer. A substantially transparent topcoat may be secured to the fluid-filled bladder element over the impression.

In one embodiment, the surface of the fluid-filled bladder element has a treated area with at least one of a predetermined level of opacity, transparency, or luster. The polymeric material may comprise at least a first polymeric sheet, and a feature may be etched on the first polymeric sheet. The feature may be at least partially aligned with the impression. The surface of the fluid-filled bladder element having the impression may be an outer surface, and the feature may be on one of the outer surface or an inner surface of the bladder element. A colored medium may be applied to the first polymeric sheet, and at least one of the feature or the impression may be adjacent to or on the colored medium on the first polymeric sheet.

The above features and advantages and other features and advantages of the present teachings are readily apparent from the following detailed description of the modes for

6

carrying out the present teachings when taken in connection with the accompanying drawings.

“A,” “an,” “the,” “at least one,” and “one or more” are used interchangeably to indicate that at least one of the items is present. A plurality of such items may be present unless the context clearly indicates otherwise. All numerical values of parameters (e.g., of quantities or conditions) in this specification, unless otherwise indicated expressly or clearly in view of the context, including the appended claims, are to be understood as being modified in all instances by the term “about” whether or not “about” actually appears before the numerical value. “About” indicates that the stated numerical value allows some slight imprecision (with some approach to exactness in the value; approximately or reasonably close to the value; nearly). If the imprecision provided by “about” is not otherwise understood in the art with this ordinary meaning, then “about” as used herein indicates at least variations that may arise from ordinary methods of measuring and using such parameters. In addition, a disclosure of a range is to be understood as specifically disclosing all values and further divided ranges within the range. All references referred to are incorporated herein in their entirety.

The terms “comprising,” “including,” and “having” are inclusive and therefore specify the presence of stated features, steps, operations, elements, or components, but do not preclude the presence or addition of one or more other features, steps, operations, elements, or components. Orders of steps, processes, and operations may be altered when possible, and additional or alternative steps may be employed. As used in this specification, the term “or” includes any one and all combinations of the associated listed items. The term “any of” is understood to include any possible combination of referenced items, including “any one of” the referenced items. The term “any of” is understood to include any possible combination of referenced claims of the appended claims, including “any one of” the referenced claims.

Those having ordinary skill in the art will recognize that terms such as “above,” “below,” “upward,” “downward,” “top,” “bottom,” etc., are used descriptively relative to the figures, and do not represent limitations on the scope of the invention, as defined by the claims.

Referring to the drawings, wherein like reference numbers refer to like components throughout the several views, FIGS. 1 and 2 show a fluid-filled bladder element 10 that has impressions 12B, 12C, 12D imparted thereon. As further explained herein, the impressions 12B, 12C, 12D are imparted from etched features of a mold assembly 32A, 32B, and because at least a portion of the fluid-filled bladder element 10 is substantially transparent, the impressions 12B, 12C, 12D can be viewed from an exterior of the fluid-filled bladder element 10 when the fluid-filled bladder element 10 is assembled in an article, such as the article of footwear 18 of FIG. 9. In the embodiment shown, the entire bladder element 10 is a substantially transparent polymeric material, and is formed from a first polymeric sheet 20 and a second polymeric sheet 22.

As used herein, a “fluid” includes a gas, including air, an inert gas such as nitrogen, or another gas. Accordingly, “fluid-filled” includes “gas-filled”. As used herein, a component is “substantially transparent” if it has a luminous transmittance (i.e., a percentage of incident light that is transmitted) of at least 80 percent and haze (i.e., percentage of transmitted light that is scattered) of not more than 56 percent. The various materials used for the bladder element 10, and other embodiments of bladder elements discussed

herein, may be substantially transparent. Those skilled in the art will readily understand a variety of methods to determine luminous transmittance and haze of an object, such as the bladder element **10**. For example, the luminous transmittance and haze of the bladder element **10** can be determined according to American Society for Testing and Materials (ASTM) Standard D1003-00, Standard Test Method for Haze and Luminous Transmittance of Transparent Plastics. Additionally, in some embodiments, the bladder element **10** may have a tinted color.

Optionally, as further described herein, a colored medium **46** is aligned with and is adjacent to or on the impressions **12B** and **12C**. The colored medium **46** can be ink or paint, and may include reflective particles **48**, as shown in the close-up view of FIG. 2. As indicated in the close-up view in FIG. 2, the colored medium **46** is an ink as a base and has reflective particles **48**. The reflective particles **48** allow for light to be cast back towards its source. The reflective particles **48** may also allow light to be scattered. In such embodiments, this provides a safety feature for low-light or full-light environments. The reflective particles **48** can be metal flakes or may include a phosphorescent material so that the reflective particles are a “glow-in-the-dark” material. In embodiments with reflective particles **48**, a curved portion **60** of the inflated bladder element **10**, discussed with respect to FIG. 9, facilitates reflecting of the light by the reflective particles **48**. For example, during a normal gait, a foot on which the article of footwear **18** is worn is repeatedly lifted and planted. The motion of the normal gait creates an additional “flash” of reflected light from the reflective particles **48** and makes the article of footwear **18** more noticeable.

Optionally, an etched feature **12A** can be etched on the bladder element **10**. Etched feature **12A**, shown in FIG. 1, is etched on the first polymeric sheet **20**, impressions **12C** and **12D** are imparted on the first polymeric sheet **20**, and the impression **12B** is imparted on the second polymeric sheet **22**, as shown in FIG. 3. In an embodiment in which the colored medium **46** is an ink, applying the colored medium **46** to the bladder element **10** may be by printing the ink on the first polymeric sheet **20** prior to or after imparting the impressions **12C** and **12D** and etching the etched feature **12A**, and printing the ink on the second polymeric sheet **22** prior to or after imparting the impression **12B**. Exemplary printing techniques include direct and indirect printing techniques.

The first polymeric sheet **20** and the second polymeric sheet **22** are secured to one another so that the bladder element **10** defines a sealable internal cavity **23**. As explained herein, the materials of the first polymeric sheet **20** and the second polymeric sheet **22**, as well as the construction of the bladder element **10** are configured so that the bladder element **10** is capable of retaining fluid in the sealable internal cavity **23** when the sealable internal cavity **23** is sealed. For example, the sealable internal cavity **23** may be filled with a gas at or above ambient pressure.

The etched feature **12A** is aligned with and adjacent to colored medium **46** applied to the first polymeric sheet **20**. The impression **12C** is also shown aligned with and on the colored medium **46** applied to the first polymeric sheet **20**. The impression **12B** is aligned with the colored medium applied to the second polymeric sheet **22**. As best shown in FIG. 1, a portion of the impression **12B** is on the colored medium **46**, and a portion of the impression **12B** is adjacent to the colored medium **46** applied to the second polymeric sheet **22**. FIG. 12 shows an embodiment in which the colored medium **46** is applied on an outer surface **41** of the

second polymeric sheet **22** as a star-shaped image in the embodiment shown prior to formation of the bladder element **10**. FIG. 13 shows an embodiment in which the colored medium **46** is applied on an outer surface **40** of the first polymeric sheet **20** as an image of the number one and a number sign in the embodiment shown prior to formation of the bladder element **10**.

The bladder element **10** with etched feature **12A** and impressions **12B**, **12C**, **12D** is included in a sole assembly **16** of an article of footwear **18**. As shown in FIG. 14, the article of footwear **18** is an athletic shoe, and the bladder element **10** is a cushioning element. In other embodiments, the sole assembly **16** could be for an article of footwear that is a dress shoe, a work shoe, a sandal, a slipper, a boot, or any other category of footwear. Alternatively, the fluid-filled bladder element **10** could be used as a cushioning element in another article, such as but not limited to a shoulder strap, a backpack, a shoulder pad, a glove, an elbow pad, a knee pad, a shin guard, or other apparel, or a sports ball.

FIG. 4 shows that the impression **12B** is a protrusion in the outer surface **41** of the second polymeric sheet **22** in the shape of a star. Impressions **12C** and **12D** are imparted on the outer surface **40** of the first polymeric sheet **20**. When the bladder element **10** is formed, the impression **12C** is on a bottom surface **53**, which is part of the outer surface **40**. In the embodiment shown, the impression **12B** is a star shape. In the embodiment shown, the impression **12C** includes the number one and the number sign. For example, the impression **12C** may be a player number. The impression **12C** is a recess in the outer surface **40** of the first polymeric sheet **20**. The impression **12D** is a series of protrusions in the form of elongated stripes on the outer surface **40**. In the embodiment shown in FIG. 1, the etched feature **12A** is a diamond pattern.

As shown in FIG. 3, even though the impression **12B** is on the second polymeric sheet **22**, it can be viewed from an exterior of the bladder element **10** through the first polymeric sheet **20** (i.e., is exposed to view through the first polymeric sheet **20**) due to the substantially transparent nature of the first and second polymeric sheets **20**, **22**. In another embodiment, the bladder element **10** may be formed from a single polymeric sheet or may be formed from substantially transparent polymeric material not in sheet form.

The fluid-filled bladder element **10** can be formed from a variety of polymeric materials. In an embodiment shown and described at least with respect to FIGS. 1-3, the bladder element **10** can be formed from any of various polymeric materials that can retain a fluid at a predetermined pressure, including a fluid that is a gas, such as air, nitrogen, or another gas. For example, the bladder element **10** can be thermoplastic polymeric material. The bladder element **10** can be a urethane, polyurethane, polyester, polyester polyurethane, and/or polyether polyurethane. Moreover, the bladder element **10** can be formed of layers of different materials. FIG. 9, which is a close-up fragmentary cross-sectional portion of the bladder element **10** in an article of footwear **18** taken at lines 9-9 in FIG. 14, shows that the first polymeric sheet **20** is a laminate membrane formed from thin films having one or more first layers **24** that comprise thermoplastic polyurethane layers **24** and that alternate with one or more second layers **26**, also referred to herein as barrier layers, gas barrier polymers, or gas barrier layers, that comprise a copolymer of ethylene and vinyl alcohol (EVOH) that is impermeable to the pressurized fluid contained therein as disclosed in U.S. Pat. No. 6,082,025 to Bonk et al., which is incorporated by reference in its entirety. The second polymeric sheet **22** may

be formed from the same materials shown and described in FIG. 9 with respect to the first polymeric sheet 20. The first layer 24 may be arranged to form an outer surface of the first polymeric sheet 20. That is, the outermost first layer 24 shown in FIG. 9 may be a portion of the outer surface 40 of the bladder element 10. The bladder element 10 may also be formed from a material that includes alternating layers of thermoplastic polyurethane and ethylene-vinyl alcohol copolymer, as disclosed in U.S. Pat. Nos. 5,713,141 and 5,952,065 to Mitchell et al. which are incorporated by reference in their entireties. Alternatively, the layers may include ethylene-vinyl alcohol copolymer, thermoplastic polyurethane, and a regrind material of the ethylene-vinyl alcohol copolymer and thermoplastic polyurethane. The bladder element 10 may also be a flexible microlayer membrane that includes alternating layers of a gas barrier polymer material such as second layers 26 and an elastomeric material such as first layers 24, as disclosed in U.S. Pat. Nos. 6,082,025 and 6,127,026 to Bonk et al. which are incorporated by reference in their entireties. Additional suitable materials for the bladder element 10 are disclosed in U.S. Pat. Nos. 4,183,156 and 4,219,945 to Rudy which are incorporated by reference in their entireties. Further suitable materials for the bladder element 10 include thermoplastic films containing a crystalline material, as disclosed in U.S. Pat. Nos. 4,936,029 and 5,042,176 to Rudy, and polyurethane including a polyester polyol, as disclosed in U.S. Pat. Nos. 6,013,340, 6,203,868, and 6,321,465 to Bonk et al. which are incorporated by reference in their entireties. In selecting materials for the bladder element 10, engineering properties such as tensile strength, stretch properties, fatigue characteristics, dynamic modulus, and loss tangent can be considered. The thicknesses of the first and second polymeric sheets 20, 22 of materials used to form the bladder element 10 can be selected to provide these characteristics. For example, in various embodiments, the bladder element 10 may have a Shore A hardness of about 20 to about 100 when inflated.

As further explained herein, the first and second polymeric sheets 20, 22 used to form the bladder element 10 may be treated or processed, and/or have properties specifically selected to enable the etched feature 12A and the impressions 12B, 12C and 12D to be lasting and aesthetically pleasing while protecting the ability of the bladder element 10 to sealingly retain the fluid.

In various embodiments, the etched feature 12A may comprise at least one of a protrusion from or a recess in the surface of the bladder element 10. For example, FIG. 10 shows a series of recesses 33A arranged to form the diamond pattern of the etched feature 12A. The recesses 33A are generally triangular grooves in cross section, as shown in FIG. 10, and may be made by removing some of the material of the outermost layer 24 of first polymeric sheet 20 during the etching process. FIG. 10 also shows the protruding impression 12D on the etched feature 12A. FIG. 11 shows an alternative etching pattern to create an alternative etched feature 12AA that can be used in place of etched feature 12A. The etched feature 12AA forms the diamond pattern by a series of protrusions 33B that are arranged by displacing some of the material of the outermost layer 26 from recesses 33C to protrusions 33B during the etching process. FIG. 11 shows the protruding impression 12D on the etched feature 12AA.

As shown in FIG. 9, the first polymeric sheet 20 has a first thickness T1. In an embodiment in which the first polymeric sheet 20 comprises a gas barrier polymer, such as in an embodiment in which the second layers 26 are a gas barrier

polymer, a maximum depth of the etched feature 12A in the first polymeric sheet 20 is controlled so that the gas barrier polymer of layers 26 is not compromised. A maximum depth D into the first polymeric sheet 20 of the etched feature 12A is much less than a thickness T1 of the first polymeric sheet 20 and is less than the thickness of the outermost one of the first layers 24. The maximum depth D could range up to about one-half of the thickness T1 of the first polymeric sheet 20, as the innermost layer 26A of the gas barrier layers 26 would still be intact, enabling a desired maximum gas transmission rate. For example, the bladder element 10 may have a gas transmission rate for nitrogen of less than 10 cubic centimeters per square meter per atmosphere per day, or of less than 1 cubic centimeter per square meter per atmosphere per day. In various embodiments, by way of non-limiting example, the depth of the etched feature 12A may be from 73 micrometers to 270 micrometers.

In certain embodiments, a protective coating layer 15, also referred to as a topcoat or barrier and shown in FIGS. 1 and 4 with respect to impression 12B, can be placed on and secured to the bladder element 10 over one or more of the impressions 12B, 12C, 12D or etched feature 12A to protect the impressions 12B, 12C, 12D or etched feature 12A. Exemplary materials for a coating layer include polymers or prepolymers such as polyurethane, polytetrafluorethylene, polypropylene, polycarbonate, and the like, as non-limiting examples.

The bladder element 10 may be manufactured using a mold assembly 32A, 32B that includes a first mold half 32A of FIGS. 7 and 8, and a second mold half 32B of FIGS. 5 and 6. The first mold half 32A has a cavity portion 36A with a mold surface 34A. Referring to FIGS. 7 and 8, the mold surface 34A has an etched area 37, which in the embodiment shown is a protrusion in the shape of a reverse (i.e., mirror image) of the number one and the number sign that are imparted as the impression 12C. When the first polymeric sheet 20 is conformed to the mold surface 34A during forming of the bladder element 10 as discussed herein, the impression 12C of the etched area 37 is imparted on the outer surface 40 of the bladder element 10. The material of the first polymeric sheet 20 is displaced by the protruding etched area 37 so that the impression 12C is a recess in the first polymeric sheet 20.

Referring to FIG. 4, a maximum depth D1 of the impression 12C in the first polymeric sheet 20 is controlled so that the gas barrier polymer of layers 26 shown in FIG. 9 are not compromised. For example, referring to FIG. 7, the etching of the mold surface 34A is controlled to provide a maximum height H1 of the protrusion of the etched area 37, with the maximum height H1 equaling the maximum depth D1. In one embodiment, if chemical etching is used, a depth of etching in the mold surface 34A may be controlled at increments of 0.008 to 0.015 inches. Referring to FIG. 4, the maximum depth D1 into the first polymeric sheet 20 of the impression 12C is much less than a thickness T1 of the first polymeric sheet 20. The maximum depth D1 could range up to about one-half of the thickness T1 of the first polymeric sheet 20, as the innermost layer 26A of the gas barrier layers 26 (shown in FIG. 9) would still be intact, enabling a desired maximum gas transmission rate.

The mold surface 34A also has an etched area 31A, which in the embodiment shown is a series of diagonal, etched grooves 39A. The etched grooves 39A are recessed in the mold surface 34A. When the first polymeric sheet 20 is conformed to the mold surface 34A during forming of the bladder element 10, the impression 12D of the etched area 31A is imparted onto the outer surface 40 of the bladder

11

element 10. The material of the first polymeric sheet 20 fills the etched grooves 39A of the mold half 32A during forming of the bladder element 10, creating the impression 12D. The impression 12D this is a protrusion from the first polymeric sheet 20. The etched feature 12A on the first polymeric sheet 20 at least partially aligns with the impression 12D, as shown in FIGS. 1 and 14.

The mold surface 34B also has an etched area 31B, which in the embodiment shown is an outline of a star shape. The etched area 31B is recessed in the mold surface 34B. When the second polymeric sheet 22 is conformed to the mold surface 34B during forming of the bladder element 10, the impression 12B of the etched area 31B is imparted onto the outer surface 41 of the bladder element 10. The material of the second polymeric sheet 22 fills the etched area 31B of the mold half 32B during forming of the bladder element 10, creating the impression 12B. The colored medium 46 on the second polymeric sheet 22 at least partially aligns with the impression 12B, as shown in FIGS. 1 and 15.

Although the etched feature 12A is shown on the outer surface 40, the etched feature 12A may instead be on an inner surface of the bladder element 10 by etching the etched feature 12A on an opposite side of the first polymeric sheet 20. FIG. 14 also illustrates that the etched feature 12A and/or the impression 12D can be configured in one embodiment to be adjacent to or on the colored medium 46 on the first polymeric sheet 20.

The bladder element 10 may be manufactured by first disposing the first polymeric sheet 20 in a mold assembly 32A, 32B that includes a first mold half 32A of FIGS. 7 and 8, and a second mold half 32B of FIGS. 5 and 6. The second polymeric sheet 22 is placed on the first polymeric sheet 20. The polymeric sheets 20, 22 are shown for purposes of illustration on the first mold half 32A, although not shown in the plan view of FIG. 8 for purposes of clarity. The polymeric sheets 20, 22 lay over the mold cavity 36A of FIG. 8 when placed on the first mold half 32A as shown in FIG. 7. The mold assembly 32A, 32B is then closed by placing the mold halves 32A, 32B together, with the second mold half 32B on first mold half 32A and the first and second polymeric sheets 20, 22 between the mold halves 32A, 32B.

The first polymeric sheet 20 is then conformed to the mold surface 34A and the second polymeric sheet 22 is conformed to the mold surface 34B to at least partially form the bladder element 10 with the sealable internal cavity 23. Conforming the first and second polymeric sheets 20, 22 to the mold surfaces 34A, 34B may be, for example, by vacuum forming with a vacuum applied through the openings, also referred to as vacuum ports 35 (only some of which are indicated with the reference number) and/or by thermoforming. The first and second polymeric sheets 20, 22 conform to the etched area 37, 31A, respectively, imparting impression 12B onto the outer surface 41 of the second polymeric sheet 22, and the impressions 12C and 12D of the etched areas 37, 31A onto the outer surface 40 of the first polymeric sheet 20. The etched feature 12A and impressions 12C, 12D are on the outer surface 40 of the bladder element 10.

The etched feature 12A may be etched on the outer surface 40 of the first polymeric sheet 20 by at least one of laser etching or mechanical etching. Laser etching can be carried out with a laser etching machine that uses a computer controlled laser. The laser moves according to a predetermined pattern and at predetermined depths pursuant to a stored software algorithm to create the etched feature 12A. Mechanical etching can be accomplished using a tool head that contacts the surface 40 of the first polymeric sheet 20 to etch the etched feature 12A. A mechanical etching machine

12

can be used so that the tool head is also computer controlled to move according to a predetermined pattern and at predetermined depths pursuant to a stored software algorithm to create the etched feature 12A.

With reference to FIG. 1, the first polymeric sheet 20 is bonded to the second polymeric sheet 22 to form a peripheral seam 28 around a periphery of the bladder element 10. The peripheral seam 28 partially seals the internal cavity 23 of the bladder element 10, and the internal cavity 23 is completely sealed once a fill tube or other filling mechanism formed with the bladder element 10 is plugged. The fill tube is formed at mating recesses 38A, 38B of the mold assembly 32A, 32B as described with respect to FIGS. 5-8, and is subsequently trimmed from the bladder element 10 after being used to inflate the internal cavity 23 and after being plugged. The peripheral seam 28 may also help the bladder element 10 retain its shape. The first and second polymeric sheets 20, 22 can be bonded to one another with or without the use of an adhesive and by thermal bonding during thermoforming, compression forming, radio frequency (RF) welding in the mold assembly 32A, 32B as shown in FIGS. 6 and 7.

Referring to FIG. 8, to form the bladder element 10 in the mold assembly 32A, 32B, either before or after the etched feature 12A is etched on the first polymeric sheet 20, the first polymeric sheet 20 is laid on the first mold half 32A, across the mold cavity portion 36A so that the colored medium 46 shown in FIG. 13 is aligned with the etched area 37. The second polymeric sheet 22 is then placed on the first polymeric sheet 20 so that the colored medium 46 shown in FIG. 12 is aligned with the impression 12B. Alternatively, colored medium 46 could be applied after the bladder element 10 is formed. Both the first and the second polymeric sheets 20, 22 are in their original, generally flat form when initially placed on the first mold half 32A. After the first and second polymeric sheets 20, 22 are placed on the first mold half 32A, the mold assembly 32A, 32B is closed. Alternatively, if polymeric material not in the form of sheets is used, the material could be placed in the mold cavity portion 36A prior to closing the mold assembly 32A, 32B.

A forming process is then used to shape the first and second polymeric sheets 20, 22 to the mold halves 32A, 32B, such as by the use of temperature and pressure control. For example, the forming process may include any or all of thermoforming, vacuum forming, compression forming, or radio frequency (RF) welding. Vacuum ports 35 are shown extending through the mold halves 32A, 32B, and a vacuum may be applied through the ports 35 to pull the first and second polymeric sheets 20, 22 against the mold surfaces 34A, 34B in the mold halves 32A, 32B. Only some of the many like vacuum ports 35 are numbered in FIGS. 5 and 8. The first and second polymeric sheets 20, 22 may be heated by the mold assembly 32A, 32B during the forming process. Additionally, a fill tube may be formed by the first and second polymeric sheets 20, 22 at the recesses 38A, 38B in the mold halves 32A, 32B. The recesses 38A, 38B mate when the mold assembly 32A, 32B is closed. The portion of the first and second polymeric sheets 20, 22 surrounding the mold cavity portions 36A, 36B are bonded to one another by any or all of thermal bonding during thermoforming, radio frequency welding, or compression forming through pressure applied by the mold halves 32A, 32B or by a separate machine after removal from the mold halves 32A, 32B.

After the first and second polymeric sheets 20, 22 are formed to the contours of the mold assembly 32A, 32B in the mold cavity portions 36A, 36B and, if heated, sufficiently cooled, the mold halves 32A, 32B are then separated, and

excess material of the first and second polymeric sheets **20**, **22** around the periphery of the seam **28** is trimmed. The fill tube formed at the recesses **38A**, **38B** may be used to inflate the bladder element **10** with gas at or above ambient pressure, and then the fill tube may be plugged and trimmed so that the bladder element **10** is in its final, formed state.

As best shown in FIGS. **1**, **9** and **14**, at least the etched feature **12A** and a portion of the impression **12D** are on a curved portion **60** of the outer surface **40** of the bladder element **10**. The etched feature **12A** and the impressions **12B**, **12C** and **12D** are each spaced apart from the peripheral seam **28** on the formed bladder element **10** due to the initial placement of the etched areas **37**, **31A**, **31B** in the mold assembly **32A**, **32B** away from a perimeter **66A**, **66B** of the mold cavity portions **36A**, **36B**. The etched feature **12A** is etched on the first polymeric sheet **20** so that it is also spaced apart from the peripheral seam **28**.

The surface **40** of the bladder element **10** may have at least one of a predetermined level of opacity, transparency or luster achieved by treating the surface **40** of the bladder element **10** by at least one of heating or applying a softening agent. For example, with reference to FIG. **3**, a first area **61** of the outer surface **40** of the bladder element **10** is the area both including the number one of the impression **12C** and within the number one. The impression **12C** is on the first area **61**. The first area **61** has a first predetermined level of opacity, transparency or luster. A second area **63** of the surface **40** of the bladder element **10** is the area surrounding and not within the impression **12C**, and has a second predetermined level of opacity, transparency or luster that is different than the first predetermined level, such as at least ten percent greater than or at least ten percent less than the first predetermined level of opacity, transparency or luster.

The second area **63** may achieve a predetermined level of opacity, transparency, or luster by heating the entire bladder element **10**, such as after formation and/or while in the mold assembly **32A**, **32B**. The first area **61** may be made more lustrous than the second area **63** such as by applying a softening agent only to the first area **61**.

The surface roughness of the mold surfaces **34A**, **34B** can also affect the opacity, transparency, and luster of the bladder element **10**. Alternatively, or in addition to treating the bladder element **10**, a region of either or both of the mold surfaces **34A**, **34B** can be polished to a predetermined surface roughness to help achieve the predetermined level of opacity, transparency or luster of the bladder element **10**. For example, with reference to FIG. **8**, a first region **84** of the mold surface **34A** can be polished to a first average surface roughness. The first region **84** has a perimeter **86** shown in phantom. A second region **88** of the mold surface **34A** is the region outside of the perimeter **86**, surrounding the first region **84**. The second region **88** has a second average surface roughness that can be obtained by polishing, or can be obtained simply by the casting or machining of the mold half **32A**. Polishing can be by sandblasting, such as at 0.001 inch increments. The etched area **37** is shown with the first region **84**. The etched area **31A** is partially in the first region **84** and partially in the second region **88**. The polishing of the first region **84** results in a first average surface roughness of the mold surface **34A** in the first region **84** which is at least ten percent greater than or at least ten percent less than the second average surface roughness in the second region **88**, as may be accomplished by the material selected and used to polish the surface **34A**. The surface **40** of the bladder element **10** has a first area **90** with a perimeter **92** as shown in FIG. **3**. The first area **90** corresponds with the first region **84** of the mold surface **34A**. The surface **40** of the bladder

element **10** also has a second area **94** that corresponds with the second region **88** of the mold surface **34A**. The first area **90** and the second area **94** may differ in opacity, transparency, or luster as a result of the difference in polishing between the regions **84**, **88**. For example, the level of transparency and the level of haze may be measured as described herein, such as by using the American Society for Testing and Materials (ASTM) Standard D1003-00, Standard Test Method for Haze and Luminous Transmittance of Transparent Plastics.

With reference to FIG. **14**, the bladder element **10** can be secured in the sole assembly **16** such as by bonding to a midsole **70** of the sole assembly **16**. For example, the bladder element **10** can be bonded with adhesive to the formed midsole **70**. Alternatively, the bladder element **10** can be placed in a midsole mold assembly (not shown), and the midsole **70** may be formed around the bladder element **10**, such as by injecting foam into the midsole mold assembly. In still other embodiments, the bladder element **10** is secured to the sole assembly **16** by an interference fit. In some embodiments, the bladder element **10** serves as at least a portion of a midsole, an outsole, or both. In all such embodiments, because the etched feature **12A** and the impressions **12B**, **12C**, and **12D** are spaced apart from the peripheral seam **28**, the bladder element **10** can be assembled in the article of footwear **18** so that the etched feature **12A** and the impressions **12B**, **12C**, and **12D** are aligned with and exposed to view through the openings in the sole assembly **16** and/or in a footwear upper extending over the sole assembly **16**, such as represented by an insole or sockliner **73** as described herein, while the seam **28** can be covered by and blocked from view by the article of footwear **18**. For example, as shown in FIG. **14**, the midsole **70** is formed with an opening **72A**. The etched feature **12A** is positioned at the opening **72A** so that it is exposed at the exterior of the article of footwear **18**, while the seam **28** is covered by the midsole **70** and is not exposed at the opening **72A**. Stated differently, a first portion of the bladder element **10** including the etched feature **12A** is aligned with the opening **72A** and exposed to view through the opening **72A** (i.e., such as from a viewpoint of a side view as in FIG. **14**). A second portion of the bladder element (i.e., the portion indicated with hidden lines in FIG. **14**) is covered by and blocked from view by the midsole **70**.

In another example, as shown in FIG. **15**, the sockliner **73** also has an opening **72B** and the bladder element **10** is secured to the sole assembly **16** so that the sole assembly **16** and the sockliner **73** do not cover the impression **12B**, and a first portion of the bladder element **10** with the impression **12B** is exposed to view through the opening **72B**, with the impression **12B** aligned with the opening **72B**. A second portion of the bladder element **10**, including the peripheral seam **28**, is not exposed at the opening **72B**, but is covered by and blocked from view at least by the sockliner **73** (i.e., from the viewpoint of FIG. **15**).

As is apparent in FIG. **16**, the sole assembly **16** does not cover at least the impression **12C**. The sole assembly **16** includes an outsole **76A** secured to a lower surface **75** of the midsole **70** as also shown in FIG. **14**. In one embodiment, the outsole **76A** has an opening **72C** that is aligned with the impression **12C** so that the impression **12C** is exposed at the exterior of the article of footwear **18** and may be viewed from a viewpoint looking at a bottom of the footwear **18**, such as when a wearer of the article of footwear **18** lifts a heel portion **74** of the article of footwear **18**. A second portion of the bladder element **10**, represented by hidden

lines in FIG. 16, is covered by the outsole 76A and blocked from view by the outsole 76A.

The outsole 76A is shown with tread elements 78A having bottom surfaces that form a ground contact surface of the article of footwear 18. The tread elements 78A can have various alternative shapes and can be arranged in various alternative arrangements. The outsole 76A shows grooves 81 formed in the outsole 76A.

FIG. 17 shows an alternative embodiment of an outsole 76B secured to the midsole 70 of FIG. 14 and to the bladder element 10. The outsole 76B has at least a portion 80, bounded by phantom lines, that is substantially transparent. The substantially transparent portion 80 is aligned with the impression 12C so that the impression 12C is exposed to view at an exterior of an article of footwear 18A, and may be viewed, such as when a wearer lifts the heel portion 74 of the article of footwear 18A. A remaining portion 82 of the outsole 76B, not bounded by the phantom lines, can also be substantially transparent. In the embodiment shown, the entire outsole 76B is substantially transparent. Alternatively, the remaining portion 82 could be opaque or not substantially transparent. The outsole 76B shows grooves 81 formed in the outsole 76B and a different arrangement of tread elements 78B. The article of footwear 18A has a different outsole 76B than the article of footwear 18, but is otherwise the same as the article of footwear 18.

Referring to FIG. 18, a method 100 of manufacturing an article, such as the article of footwear 18, is described with respect to the bladder element 10 of FIGS. 1-4, the mold assembly 32A, 32B of FIGS. 5-8, and the article of footwear 18 of FIG. 14. The method 100 may begin with step 102, etching any or all of the etched areas 37, 31A in the mold surface 34A by at least one of laser etching, mechanical etching, or chemical etching. Step 102 may also include etching the etched area 31B in the mold surface 36B. Etching of the etched area 37, 31A, and/or 31B in step 102 may be controlled in various ways to enable fluid retention in the internal cavity 23 of bladder element 10. For example, step 102 may include sub-step 104, controlling the etching of the etched area 37 so that the impression 12C has a maximum depth D1 into the first polymeric sheet 20 of not more than about one-half of a first thickness T1 of the first polymeric sheet 20, as discussed with respect to FIG. 4. In some embodiments, the first polymeric sheet 20 comprises a gas barrier polymer. Etching the etched area 37 may be controlled in sub-step 104 so that the gas barrier polymer is not compromised by the impression 12C.

The method 100 may further comprise step 106, polishing the first region 84 of the mold surface 34A to a first average surface roughness, wherein the second region 88 of the mold surface 34A has a second average surface roughness. The etched area 37 and/or the etched area 31A is at least partially in at least one of the first region 84 or the second region 88, as shown in FIG. 8. The first average surface roughness may be at least ten percent greater than or at least ten percent less than the second average surface roughness. The surface 40 of the bladder element 10 includes the first area 90 corresponding with the first region 84 of the mold surface 34A and the second area 94 corresponding with the second region 88 of the mold surface 34A, as discussed with respect to FIG. 3. Step 106 may occur prior to or after step 102. The mold surface 34B may also be polished in a similar manner.

In some embodiments, the method 100 may include step 108, applying a colored medium 46 to the first polymeric sheet 20, such as to create the shape of the number one and the number sign, as shown in FIG. 13, that will be aligned with the etched feature 12C. The colored medium 46 may

also be applied to the first polymeric sheet 20 to create a diamond pattern as shown in FIG. 13, and the etched feature 12A may be etched to be adjacent to or on the colored medium 46 on the first polymeric sheet 20. The colored medium 46 may also be applied to the second polymeric sheet 22 to create a star pattern that will be aligned with the impression 12B. It is to be understood that the colored medium 46 could be of different colors or materials at the different areas of application on the first and second polymeric sheets 20, 22.

In some embodiments, the method 100 may include step 110, etching the etched feature 12A on the surface 40 of the first polymeric sheet 20 by at least one of laser etching or mechanical etching. The etched feature 12A may be etched to be adjacent to or on the colored medium 46 on the first polymeric sheet 20. Step 102, including sub-step 104, step 106, step 108, and step 110 can be performed in any order. In some embodiments of the method 100, the first and second polymeric sheets 20, 22 may be obtained with the colored medium 46 already applied thereon, or with the etched feature 12A already etched thereon, in which case steps 108 and 110 are not performed. In still other embodiments, steps 108 and/or 110 may be performed after the bladder element 10 is formed, i.e., after step 132.

The method 100 further comprises step 112, disposing a first polymeric sheet 20 in a mold assembly 32A, 32B. The first polymeric sheet 20 may be disposed in the mold assembly 32A, 32B so that the surface 40 of the first polymeric sheet 20 with the etched feature 12A will be on one of an inner surface or an outer surface of the bladder element 10. In the embodiment shown, the surface 40 is an outer surface of the bladder element 10. In an embodiment in which a colored medium 46 is applied to the first polymeric sheet in step 108, disposing the first polymeric sheet 20 in step 112 may include sub-step 114, aligning the colored medium 46 with the etched area 31A so that the impression 12C will be on or adjacent to the colored medium 46. Similarly, the colored medium 46 on the second polymeric sheet 22 can be aligned with the etched area 31B so that the impression 12B will be on or adjacent to the colored medium 46.

In an embodiment in which the mold assembly 32A, 32B includes a mold surface 34A with an etched area 31A, the method 100 also includes step 116, aligning the etched feature 12A with the etched area 31A so that the impression 12D of the etched area 31A will be adjacent to or on the etched feature 12A, as shown in FIGS. 1, 2 and 14.

After disposing the polymeric material in the mold assembly 32A, 32B, the method 100 further comprises step 118, conforming the polymeric material to the mold surfaces 34A and 34B to form a bladder element 10 with a sealable internal cavity 23. Conforming the polymeric material, such as the first polymeric sheet 20, to the mold surface 34A imparts the impression 12C of the etched area 37 and the impression 12D of the etched area 31A onto the surface 40 of the bladder element 10. Conforming the polymeric material, such as the second polymeric sheet 22, to the mold surface 34B imparts the impression 12B of the etched area 31B onto the surface 41 of the second polymeric sheet 22. Conforming the polymeric material, such as the first and second polymeric sheets 20, 22 to the mold surface 34A and the mold surface 34B may be by any or all of blow molding in sub-step 120, compression forming in sub-step 122, vacuum forming in sub-step 124, or thermoforming in sub-step 126. In other words some or all of the sub-steps

120, 122, 124, and 126 may be performed. For example, if the polymeric material is in other than sheet form, blow molding may be used.

The method 100 may further comprise step 128, forming a peripheral seam 28 in the bladder element 10 that at least partially seals the internal cavity 23. Forming the peripheral seam 28 in step 128 may be by compression forming the first polymeric sheet 20 to the second polymeric sheet 22, such as during step 122 while the sheet 20 is conformed to the mold surface 34A, by radio frequency (RF) welding, and/or by the use of adhesives. Forming the bladder element 10 in step 128 is accomplished so that the first and second polymeric sheets 20, 22 are bonded at the peripheral seam 28, at least a portion of the etched feature 12A and the impressions 12B, 12C and 12D are spaced apart from the peripheral seam 28. Additionally, disposing the first polymeric sheet 20 in the mold assembly 32A, 32B may be so that the etched feature 12A and a portion of the impression 12D is at least partially on a curved portion 60 of the bladder element 10 corresponding to a curved portion 45 of the mold surface 34A indicated in FIG. 8. In other words, in step 108, the first polymeric sheet 20 is disposed on the first mold surface 34A, so that the etched feature 12A and a portion of the impression 12D will be on the curved portion 60 of the bladder element 10 when the bladder element 10 is formed.

The method 100 may further comprise step 130, inflating the bladder element 10 by filling the sealable internal cavity 23 with a fluid, and then sealing the sealable internal cavity 23 in step 132 so that the fluid is retained in the sealable internal cavity 23. In one embodiment, the fluid is a gas at or above ambient pressure. The bladder element 10 may have a gas transmission rate for nitrogen of less than 10 cubic centimeters per square meter per atmosphere per day, or of less than 1 cubic centimeter per square meter per atmosphere per day.

In one embodiment, a substantially transparent topcoat 15 may be secured over the impression 12B in step 134, such as to protect the impression 12B from abrasion. Although described with respect to the impression 12B, the topcoat 15 may be secured over any or all of the impressions 12B, 12C, or 12D and/or over the etched feature 12A.

The method 100 may further comprise step 136, treating the surface 40 and/or 41 of the bladder element 10 to achieve at least one of a predetermined level of opacity, transparency, or luster of the bladder element 10. This treatment may occur after conforming the first polymeric sheet 20 to the mold surface 34A and the second polymeric sheet 22 to the mold surface 34B to at least partially form the bladder element 10. For example, treating the surface 40, 41 of the bladder element 10 may be by at least one of heating the surface 40, 41 of the bladder element 10, such as while the bladder element is in the mold assembly 32A, 32B, or by applying a softening agent to the surface 40, 41 of the bladder element 10. As previously discussed, in some embodiments, the first area 61 of the surface 40 of the bladder element 10 may be treated to achieve a first predetermined level of opacity, transparency, or luster. The second area 63 of the surface 40 of the bladder element 10 may have a second predetermined level of opacity, transparency, or luster that is at least ten percent greater than or at least ten percent less than that of the first predetermined level of opacity, transparency, or luster. The impression 12C is on the first area 61 of the surface 40 of the bladder element 10, and the impression 12D is on both the first area 61 and the second area 63 of the surface 40 of the bladder element 10. The surface 41 of the second polymeric sheet 22 of the bladder element 10 could be treated in a similar manner to

achieve at least one of a predetermined level of opacity, transparency, or luster of a first area 90 of the surface 41 that is different than a second predetermined level of opacity, transparency or luster of a second area 94 of the surface 41, with the impression 12B in one of the first area 90 or the second area 94 of the surface 41.

After any cooling period that may be provided, the mold assembly 32A, 32B is opened, and the bladder element 10 is removed from the mold assembly 32A, 32B. The bladder element 10 with the etched feature 12A and the impressions 12B, 12C, and 12D is now complete. Optionally, if the same entity carrying out steps 102-136 also assembles the bladder element 10 in an article such as the article of footwear 18, then the method 100 can proceed with steps 138, 140 and 142. In step 138, the fluid-filled bladder element 10 is assembled in the sole assembly 16 of the article of footwear 18. Assembling the bladder element 10 in the article of footwear 18 may include sub-step 140, securing the bladder element 10 to the midsole 70. In various embodiments, securing the bladder element 10 to the midsole 70 can be accomplished with adhesive or by forming the midsole 70 around the bladder element 10 in a midsole mold assembly (not shown). In all such embodiments, the bladder element 10 may be assembled in the article of footwear 18 so that the peripheral seam 28 and the second portion of the bladder element 10 are covered by and blocked from view by the article of footwear 18, and the impressions 12B, 12C, and 12D, as well as etched feature 12A, if included, are exposed to view through openings such as opening 72A in the midsole 70 and opening 72B in the sockliner 73, as described with respect to the embodiment of FIGS. 9 and 14. In other words, the etched feature 12A and a portion of the impression 12D are aligned with the opening 72A so that the etched feature 12A and impression 12D are exposed to view and can be viewed through the opening 72A from an exterior of the article of footwear 18. Similarly, the impression 12B is aligned with the opening 72B so that the impression 12B is exposed to view and can be viewed through the opening 72B from an exterior of the article of footwear 18.

Next, in step 142, an outsole can be secured to the midsole 70. If outsole 76A of FIG. 16 is used, the opening 72C is aligned with the impression 12C and with a portion of impression 12D. The impression 12B can also be viewed through the substantially transparent bladder element 10 at the opening 72C. If outsole 76B of FIG. 17 is used, the substantially transparent portion 80 of the outsole 76B is aligned with the impression 12C and with a portion of the impression 12D so that the impressions 12C, 12D are exposed to view through the substantially transparent portion of the outsole 76B. As discussed above, the entire outsole 76B may be substantially transparent.

While several modes for carrying out the many aspects of the present teachings have been described in detail, those familiar with the art to which these teachings relate will recognize various alternative aspects for practicing the present teachings that are within the scope of the appended claims. It is intended that all matter contained in the above description or shown in the accompanying drawings shall be interpreted as illustrative only and not as limiting.

The invention claimed is:

1. A method of manufacturing an article of footwear having a sole assembly with a midsole and an outsole, and having an upper, the method comprising:
 - disposing a first polymeric sheet in a mold assembly that has a mold surface; wherein the mold surface has an etched area;

19

forming a fluid-filled bladder element at least partially by conforming the first polymeric sheet to the mold surface; wherein said conforming imparts an impression of the etched area on a surface of the first polymeric sheet; and

5 assembling the fluid-filled bladder element in the midsole so that a first portion of the fluid-filled bladder element with the impression of the etched area is exposed to view through an opening in one of the midsole, the outsole, and the upper, and a second portion of the fluid-filled bladder element is blocked from view by

10 said one of the midsole, the outsole, and the upper; wherein the fluid-filled bladder element has a sealable internal cavity that retains fluid.

2. The method of claim 1, wherein: said assembling the fluid-filled bladder element includes aligning the impression of the etched area with the opening so that the impression of the etched area is exposed to view through the opening.

3. The method of claim 2, wherein: said assembling includes securing the fluid-filled bladder element to the sole assembly.

4. The method of claim 3, wherein: the opening is in the midsole or the outsole.

5. The method of claim 1, wherein: at least a portion of the outsole is substantially transparent; and

said assembling comprises securing the outsole to the fluid-filled bladder element so that the impression of the etched area is exposed to view through the portion

30 of the outsole that is substantially transparent.

6. The method of claim 1, wherein: the fluid-filled bladder element further includes a second polymeric sheet; and

said forming the fluid-filled bladder element includes:

35 bonding the first polymeric sheet to the second polymeric sheet at a peripheral seam so that the first polymeric sheet and the second polymeric sheet together define the internal cavity sealed at the peripheral seam; and

said assembling the fluid-filled bladder element in the midsole includes covering the peripheral seam with the midsole so that the peripheral seam is blocked from view by the midsole.

7. The method of claim 1, further comprising: prior to said forming the fluid-filled bladder element, etching the etched area in the mold surface by at least one of laser etching, mechanical etching, or chemical etching.

8. The method of claim 1 wherein the impression of the etched area comprises a recess in the surface of the fluid-filled bladder element.

9. The method of claim 1, wherein the first polymeric sheet has a first thickness; and

55 the impression of the etched area has a maximum depth into the first polymeric sheet of not more than about one-half of the first thickness.

10. The method of claim 1, further comprising: polishing a first region of the mold surface to a first average surface roughness; wherein:

60 a second region of the mold surface has a second average surface roughness; the etched area is at least partially in at least one of the first region or the second region; the first average surface roughness is at least ten percent greater than or at least ten percent less than the second average surface roughness; and

20

the surface of the fluid-filled bladder element has a first area corresponding with the first region of the mold surface and a second area corresponding with the second region of the mold surface.

11. The method of claim 1, wherein: the mold surface has a curved portion; the fluid-filled bladder element has a curved portion corresponding with the curved portion of the mold surface; and

10 said disposing the first polymeric sheet in the mold assembly is so that the impression of the etched area is on the curved portion of the fluid-filled bladder element.

12. The method of claim 1, further comprising: etching an etched feature on the first polymeric sheet; and at least partially aligning the etched feature with the etched area of the mold assembly during said disposing the first polymeric sheet in the mold assembly so that the impression of the etched area is imparted at least partially on the etched feature.

13. The method of claim 12, wherein the surface of the bladder element having the impression of the etched area is an outer surface; and wherein the etched feature is on one of

25 the outer surface or an inner surface of the bladder element.

14. The method of claim 1 further comprising: prior to said assembling the fluid-filled bladder element in the article, filling the sealable internal cavity with fluid; and

30 sealing the sealable internal cavity so that the fluid is retained in the sealable internal cavity; wherein the fluid is a gas at or above ambient pressure.

15. The method of claim 1, further comprising: securing a topcoat to the fluid-filled bladder element over the impression of the etched area; and wherein the topcoat is substantially transparent so that the impression of the etched area is exposed to view through the topcoat.

16. The method of claim 1, wherein: the first polymeric sheet; comprises a thermoplastic polyurethane (TPU); and the TPU is present on at least an outer surface of the first polymeric sheet.

17. The method of claim 16, wherein the first polymeric sheet comprises a multi-layer polymeric sheet that is a laminate membrane having:

45 at least a first layer comprising the TPU; and at least a second layer comprising a gas barrier polymer.

18. The method of claim 17, wherein the gas barrier polymer is an ethylene-vinyl alcohol copolymer.

19. A method of manufacturing an article of footwear having a sole assembly with a midsole and an outsole, and having an upper, the method comprising:

50 disposing a first polymeric sheet in a mold assembly that has a mold surface; wherein the mold surface has an etched area;

forming a fluid-filled bladder element at least partially by conforming the first polymeric sheet to the mold surface; wherein said conforming imparts an impression of the etched area on a surface of the first polymeric sheet; assembling the fluid-filled bladder element in the midsole so that a first portion of the fluid-filled bladder element with the impression of the etched area is exposed to view through an opening in one of the midsole, the outsole, and the upper, and a second portion of the fluid-filled bladder element is blocked from view by

60 said one of the midsole, the outsole, and the upper;

21

wherein the fluid-filled bladder element has a sealable internal cavity that retains fluid; and
 after said conforming the first polymeric sheet to the mold surface to at least partially form the fluid-filled bladder element, treating the surface of the fluid-filled bladder element to achieve at least one of a predetermined level of opacity, transparency, or luster of the fluid-filled bladder element.

20. The method of claim **19**, wherein said treating is by at least one of heating the surface of the fluid-filled bladder element or applying a softening agent to the surface of the fluid-filled bladder element.

21. A method of manufacturing an article of footwear having a sole assembly with a midsole and an outsole, and having an upper, the method comprising:

disposing a first polymeric sheet and a second polymeric sheet in a mold assembly that has a mold surface; wherein the mold surface has an etched area;

forming a fluid-filled bladder element at least partially by conforming the first polymeric sheet to the mold sur-

22

face; wherein said conforming imparts an impression of the etched area on a surface of the first polymeric sheet; assembling the fluid-filled bladder element in the midsole so that a first portion of the fluid-filled bladder element with the impression of the etched area is exposed to view through an opening in one of the midsole, the outsole, and the upper, and a second portion of the fluid-filled bladder element is blocked from view by said one of the midsole, the outsole, and the upper; wherein the first polymeric sheet and the second polymeric sheet define a sealed internal cavity that retains fluid; and

wherein said conforming the first polymeric sheet to the mold surface comprises at least one of compression forming the first polymeric sheet, vacuum forming the first polymeric sheet, or thermoforming the first polymeric sheet.

* * * * *