

US009862512B2

(12) **United States Patent**
Jons

(10) **Patent No.:** **US 9,862,512 B2**
(45) **Date of Patent:** **Jan. 9, 2018**

(54) **METHOD FOR SEALING A FOOD STORAGE BAG**

(71) Applicant: **Carolyn Kay Jons**, Eden Prairie, MN (US)

(72) Inventor: **Carolyn Kay Jons**, Eden Prairie, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 424 days.

(21) Appl. No.: **14/714,329**

(22) Filed: **May 17, 2015**

(65) **Prior Publication Data**

US 2016/0332762 A1 Nov. 17, 2016

(51) **Int. Cl.**

B65B 51/10 (2006.01)
B65D 33/25 (2006.01)
B65B 7/06 (2006.01)
B65D 81/26 (2006.01)

(52) **U.S. Cl.**

CPC **B65B 51/10** (2013.01); **B65B 7/06** (2013.01); **B65D 33/25** (2013.01); **B65D 81/268** (2013.01); **B65B 2051/105** (2013.01)

(58) **Field of Classification Search**

CPC B65B 51/10; B65B 7/06; B65B 7/164; B65B 2051/105
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,521,031 A * 7/1970 Guenter B65B 51/10
219/243
4,630,429 A * 12/1986 Christine B29C 65/18
156/515

4,856,260 A * 8/1989 Woo B29C 65/18
156/583.1
5,324,233 A * 6/1994 Owensby B29C 65/18
493/190
5,630,308 A * 5/1997 Guckenberger B23K 26/067
53/412
5,894,929 A * 4/1999 Kai B65D 81/2023
206/524.8
6,312,742 B1 * 11/2001 Wood B65B 7/06
383/111
6,392,198 B1 * 5/2002 Yao B29C 65/228
156/579
9,561,889 B2 * 2/2017 Dayrit B32B 27/20
2003/0024847 A1 * 2/2003 Malaspina B65D 33/01
206/524.8
2014/0270581 A1 * 9/2014 Jons B65D 33/25
383/37


* cited by examiner


Primary Examiner — Christopher Harmon

(57) **ABSTRACT**

A method for sealing a food storage bag includes providing a bag with walls formed of two facing sheets, at least one of the facing sheets is a multilayer sheet having an inner layer of polymer enabling the facing sheets to be joined by melt sealing at less than 95° C.; providing a sealing device comprising an elongated bar with thermal conductivity greater than 5 W/(m K) and an insulating component affixed to the bar having a thermal conductivity less than 1 W/(m K); placing the sealing device into water; warming the bar to between 50° C. and 100° C.; removing the warmed bar from water; handling the sealing device by the insulating component; and pressing the warmed bar against a wall of the storage bag to join facing sheets. In one embodiment, a machine-readable image on the bag points to a video on the Internet that illustrates the sealing process.

12 Claims, 3 Drawing Sheets










Fig. 4



1

METHOD FOR SEALING A FOOD STORAGE BAG

CROSS REFERENCE TO RELATED APPLICATION

This application is a continuation of and claims priority from U.S. application Ser. No. 13/829,649, filed on Mar. 14, 2013, the entire contents of which is incorporated herein by reference.

FIELD OF INVENTION

The present invention generally relates to a flexible bag for food storage, a device for sealing the storage bag, and a process for sealing a food storage bag with the device. The invention further relates to their use.

BACKGROUND OF INVENTION

In both United States and the United Kingdom, separate studies have indicated that about a third of all food purchased is wasted. At the household level, the largest contributor (>20%) to this food waste is fruits and vegetables. The most common reason given for this disposal was that the fruits and vegetables were moldy or slimy. This invention is aimed at improving the situation by enabling an improved food storage method.

Both inside and outside refrigerators, flexible storage bags are commonly used by consumers to store food. Plastic bags are available to the public in many stores and are most usually sold by the box. A variety of designs for sealable plastic bags have been contemplated, but the most common seals are interlocking slide devices (e.g. U.S. Pat. No. 2,558,367; U.S. Pat. No. 4,186,786). In 1957, a 5th grader name Robert Lejeune won a National Science Fair competition by demonstrating that sealable pouches, similar to Ziploc™ bags and sold as pencil cases at the time, retarded food spoilage in some cases. This present invention also results from a Science Fair project, this time demonstrating a new bag design that prevents mold growth.

With food and many other items negatively impacted by storage in oxygen, prolonged useful life would be possible if the presence of air were avoided. For this purpose, vacuum storage bags (e.g. U.S. Pat. No. 6,883,665, U.S. Pat. No. 7,290,660) and associated equipment for sealing these bags are sold. However, commercial devices for vacuum sealing in the home are fairly expensive and take up space. Further, residual air remaining in bags can negatively impact storage results. Also, the vacuum associated with remaining spaces between food provides a driving force to encourage air to enter through small leaks. Finally, vacuum storage is less desirable for food that is readily deformable under pressure. For example, raspberries may become in large part juice due to pressure exerted upon them.

Another approach to prolong food storage is removal of just oxygen. For this purpose, commercial oxygen absorption packets (e.g. U.S. Pat. No. 4,332,845) have been available for years. However, it seems that adoption of this technology has been limited by several factors. First, oxygen absorption packets are not typically sold in stores where food is present. For this purpose, convenient packaging with a long shelf life is needed. Related to this, oxygen absorption packets would need to be packaged in small numbers, as the common practice of including 20-50 in a common oxygen-isolating package requires consumers to either use all at once or undertake inconvenient steps to store the remainder.

2

Further, an oxygen-impermeable container of appropriate size is necessary. Finally, significant adoption will require the product to be both easy to use and easy to understand.

To address these issues, co-pending US 2014/0270581 describes a new, easy-to-use, flexible bag design. This application provides a new method for sealing a bag. It is hoped that this invention can provide consumers with a more convenient method to prevent mold growth and keep food fresh longer.

SUMMARY OF INVENTION

A method for sealing flexible bags for food storage includes providing a bag with walls formed of two facing sheets that are joined together along three adjacent edges to form a rectangular pouch, at least one of the facing sheets is a multilayer sheet having an inner layer of polymer enabling the facing sheets to be joined by melt sealing at less than 95° C.; providing a sealing device comprising an elongated bar with thermal conductivity greater than 5 W/(m K) and an insulating component affixed to the elongated bar having a thermal conductivity less than 1 W/(m K); placing the sealing device into water; warming the elongated bar to a temperature of between 50° C. and 100° C.; removing the warmed bar from the water; handling the sealing device by the insulating component; and pressing the warmed elongated bar against a wall of the storage bag to join facing sheets by melt sealing and to create a storage region that is isolated from air surrounding the storage bag.

The invention also includes a package comprising a plurality of bags and a sealing device appropriate for this purpose. In another embodiment, a wall of the bag includes a machine-readable image, directing a computer or phone to a video on the Internet that shows both opening the frangible seal and re-sealing the bag at a separate location to isolate the storage region from air surrounding the bag.

BRIEF DESCRIPTION OF DRAWINGS

The invention and its various embodiments may be better understood by reference to the detailed description and accompanying figures. Within these sections, like reference numerals refer to like elements.

FIG. 1 is a drawing of one embodiment of the flexible bag.

FIG. 2 is a cross section of a flexible bag embodiment with a frangible seal.

FIG. 3 is a cross section of a flexible bag embodiment after the frangible seal has been opened and the consumer implementable sealing mechanism has been sealed.

FIG. 4 is a perspective drawing of a heat sealing device.

DETAILED DESCRIPTION

Mold can't grow without the presence of oxygen. For this reason the flexible bag of this invention includes an oxygen remover. As described in different references (e.g. U.S. Pat. No. 4,524,015; U.S. Pat. No. 5,028,578; U.S. Pat. No. 5,143,763; U.S. Pat. No. 8,221,647; US 2007/0212461 A1; US 2012/0128532A1) a large variety of oxygen removing materials are known. In a preferred embodiment, the oxygen remover includes a high surface area iron powder that can react in air to remove oxygen (e.g. $2\text{Fe}_2+3\text{O}_2\rightarrow 2\text{Fe}_2\text{O}_3$). The remover preferably includes iron particles of less than 100 microns average size. The oxygen remover may also include other materials, such as silica gel or clay for water storage, activated carbon for odor reduction, and sodium chloride or acid for increasing the oxidation rate of iron.

The flexible bag of this invention is preferably sufficient to store between than 0.4 L and 8 L of oxygen-sensitive material (e.g. perishable food), roughly corresponding to sizes between common sandwich bags and two gallons. However, the invention could be used with smaller and larger volumes as well. Preferably, the oxygen remover is of sufficient capacity to remove oxygen from the largest fillable volume of the bag, allow for a 10 minute (or even 30 minute) exposure during loading, and account for leakage through side walls and seals over a year's time. The oxygen remover is preferably sized to lose more than 25%, or even 50%, of its capacity if it were stored for five years. Similarly, the oxygen remover is preferably sized to lose 25%, or even 50%, of its capacity if it were exposed for two hours of loading time.

An embodiment of the flexible bag of this invention is illustrated in FIG. 1. The bag 10 is made from two facing, flexible sheets 12 that form the walls 13 of the bag. The two facing sheets are joined together (e.g. by a fold 14, an adhesive, or melt seal 16), along three adjacent edges 18 to form a rectangular pouch 20 with opening 22 at the top. These facing sheets have an oxygen transmission rate at 25° C. of less than 10 cm³/m²/day, more preferably less than 5 cm³/m²/day, or even less than 2 cm³/m²/day. The oxygen transmission rate depends on both material type and thickness, so many available sheets have this property. However, preferred polymeric materials that contribute to low oxygen permeability include ethylene vinyl alcohol copolymer (EVOH), polyacrylonitrile (PAN), polyvinyl acetate (PVA), and Saran™. Composites sheets can also incorporate a metal or metal oxide layer that inhibits oxygen permeability.

At least one, and preferably both, of the facing sheets 12 is a multilayer sheet. The inner layer facilitates heat sealing and joining to another facing sheet. The inner layer includes a polymer with relatively low melting point compared to other layers of the facing sheets, enabling the two facing sheets to be joined during manufacture or later by an end-user. A preferred multilayer sheet has an inner layer of lower temperature polymer enabling the consumer to join facing sheets by melt sealing at a temperature of less than 95° C. Preferably, the consumer could use less than 100 psi, 60 psi, or even 20 psi to seal the bag. (Preferably, the multilayer sheets can be sealed at a temperature between 50° C. and 95° C., but they do not enable melt sealing by the consumer below 50° C.) The multilayer sheet also includes other layers contributing more to strength and/or low oxygen permeability. In a preferred embodiment, both facing sheets include a coating or intermediate layer that is a metal or metal oxide layer.

The two facing sheets 12 may be of any thickness. A conventional plastic bag (e.g. Ziploc™ sandwich bag) has polyethylene thickness of about 2 mil (0.05 mm). However, for sealing and handling a bag containing a weighty oxygen removing component, the inventor has found that the preferred sheet thickness is greater than 3 mil (>0.076 mm).

The pouch 20 is separated into inner 30 and outer 32 sections by a frangible seal 34 affixing the two facing sheets. A "frangible" seal means one that it is breakable during opening. The inner section 30 of the pouch contains both an oxygen remover 40 and a storage region 42 with a fillable volume between 0.35 L and 8.5 L. A water impermeable membrane 44 with high oxygen permeability separates the oxygen remover 40 from materials in the storage region 42. As used herein, "water impermeable" refers to the fact that liquid water does not pass at a pressure differential of 1 bar. The membrane preferably has an oxygen transmission rate of more than 2000 cm³/m²/day, more preferably more than

10,000 cm³/m²/day, at 25° C. Polymers with relatively high oxygen permeability coefficients include poly(propylene), low density poly(ethylene), Teflon, natural rubber and silicone rubber, but a variety of materials may be used depending on thickness. Additionally, the water impermeable membrane 44 may have small pores and be hydrophobic or oleophobic, so that liquid does not pass through at low (<1 bar) pressure. More preferably, the impermeable membrane 44 may be a non-porous film with high gas permeation, as described for instance in U.S. Pat. No. 6,680,113 or as used in the 3M Tegaderm product. BASF's Styrolux® (styrene-butadiene copolymer) is another film with high oxygen permeability.

The frangible seal 34 initially isolates the oxygen remover 40 and storage region 42 within the pouch from air outside the pouch. The initially closed frangible seal is integral with the bag, by which it means that the seal is not optionally added or made closed. Rather, the closed seal is manufactured into the bag. Because this integral closed seal is formed at approximately the same time as seals along edges 18 of the bag 10, the capacity of the incorporated oxygen remover 40 is kept high. In the intended use, this integral, frangible seal 34 ensures long shelf-life (e.g. in the store) for the oxygen remover 40 prior to breaking the seal by the consumer. The frangible seal must be opened to allow food or other items to be placed within the storage region of the bag. After the initial integral closed frangible seal 34 of this invention is opened, it is not re-sealable to equivalent performance by the consumer.

There are many ways to create a frangible seal. Illustrative of one preferred seal type is a common potato chip bag, which includes a frangible seal that is opened by the consumer. These seals are often made by a process of optimally applying heat and pressure to a polymer for a specific amount of time. Increasing any of the three factors (heat, pressure, time) may lead to greater strength. In this embodiment, the seal type is not re-sealable by the consumer. One advantage of this type of frangible seal is that it is less likely to contact food in an intimate and undesired manner. Alternatively, other preferred frangible seals within scope of this invention can retain some ability to re-join the two facing sheet surfaces after opening, but the seal is no longer able to prevent oxygen passage to the same degree as the initial integral closed seal. Although this embodiment has increased oxygen passage after seal breakage, retaining some of the ability to join two facing surfaces can assist in positioning the two facing sheets to allow making other seals between them (to be described later) more facile.

In addition to the type of seal, oxygen transmission through the integral frangible seal 34 can depend on the seal's dimensions (e.g. length, thickness, and width). Preferably, the frangible seal allows oxygen passage of less than 0.5 cm³/day, more preferably less than 0.1 cm³/day, so that capacity of the oxygen remover is not overly degraded within a year's storage time. The bag's frangible seal preferably opens with a force of less than 20 N.

In addition to the oxygen remover 40, storage region 42, and impermeable membrane 44, the inner section 30 of the pouch 20 may contain an oxygen indicator 50. For example, the presence of oxygen may be indicated by a chemical reaction, such as using the chemistry described in patent application US 2008/0070307A1. However, in this bag 10, it desirable that chemicals within the oxygen indicator 50 be isolated from the storage region by an isolating membrane 52 which may be the same as the aforementioned water impermeable membrane 44. Preferably, passage of gas between an oxygen indicator 50 and the bag's oxygen

5

remover **40** requires passage through at least two water impermeable membranes **44,52**. The isolating membrane **52** separating the indicator **50** from the storage region **42** preferably has a transmission rate of at least $2000 \text{ cm}^3/\text{m}^2/\text{day}$, or more preferably at least $10000 \text{ cm}^3/\text{m}^2/\text{day}$. This membrane

preferably has greater oxygen transmission than the water impermeable membrane separating the oxygen remover from the storage region. The invention preferably includes a consumer implementable sealing mechanism **60**, different from the frangible seal **34**, that is capable of isolating the storage region **42** from air outside the bag **10**. In the intended use, this consumer sealing mechanism **60** is closed by the consumer following the placement of food or other items within the storage region of the bag. This sealing mechanism **60** is capable of being sealed at a temperature of less than 25°C . So that open time for the bag is minimized, operation of this consumer implementable sealing mechanism **60** is quick and requires no additional tools. To maximize space available for food storage and assist in opening the frangible seal **34**, the consumer sealing mechanism **60** is preferably located within the outer section **32** of the pouch **20**, as defined by the frangible seal **34**. In this case, the sealing mechanism **60** is capable of isolating the storage region and at least a part of the outer section **42** from air surrounding the bag **10**.

The consumer implementable sealing mechanism **60** can take many forms. In preferred configurations, the sealing mechanism includes an adhesive (e.g. U.S. Pat. No. 7,290,660; US 2008/0044144A1) that limits air passage. FIG. 2 illustrates an embodiment that includes a folded tab **62** coated with adhesive **64** on one surface **66**. FIG. 3 illustrates the same bag after breaking the frangible seal **34** and closing the consumer implementable sealing mechanism **60** with the foldable tab **62** having adhesive **64**. To improve its effectiveness, the adhesive coated surface is preferably affixed to a removable protective layer **68**. To avoid wrinkles during sealing, the inventor has found it advantageous that the foldable tab **62** comprises a rigid region **70** with greater stiffness than the average stiffness of the walls **13** of the bag. In one embodiment, rigid regions **70,70'** of greater stiffness are on both sides of a fold line **72**. The stiffness (force/deformation) for a foldable tab region may be more than twice or more than four times that for one of the sheets making up a wall **13**. Improved sealing without wrinkles may further be achieved by constructing the bag with an increased thickness or mass per unit area in the region of a foldable seal.

Another aspect of this invention is a process for sealing flexible bags **10** containing an oxygen remover **40** that includes submerging a sealing device **90** in hot water, removing the sealing device **90** from water, and pressing the warmed sealing device **90** against the bag **10** to join facing sheets **12,12'**. For this purpose, it is preferred that the sealing device **90** contains a metal bar **92**. It is also preferred that the storage bag has walls **13** with oxygen transmission rate at 25°C . of less than $10 \text{ cm}^3/\text{m}^2/\text{day}$, more preferably less than $5 \text{ cm}^3/\text{m}^2/\text{day}$, or even less than $2 \text{ cm}^3/\text{m}^2/\text{day}$.

At least one of the walls **13** comprises a multilayer sheet **12** having an inner layer of polymer enabling the facing sheets of the bag to be joined by melt sealing at less than 95°C .

Currently, vacuum sealers are commonly used to join facing sheets of heat-meltable bags by heat sealing. A typical vacuum sealer marketed for household use (Food Saver© V2222) comprises a 30 cm long sealing section heated by electricity. Another similar unit for this purpose is the Frigidaire Vacuum Sealer© (Model # 5304454102). The

6

actual temperature attained by heating elements for these vacuum sealers has not been determined by the inventor, but it has been found by the inventor that bags sold with these vacuum sealer do not seal by pressing of a metal bar heated in boiling water. Similarly, a collection of other bags sold for food storage were similarly found to not seal using a metal bar heated in boiling water. The inventor has found that layers of 3M Scotchpac™ HB-P 69731 Translucent High Barrier Film are able to be joined and sealed by this method. The film product contains a ceramic metal oxide coating that inhibit oxygen passage and a 0.5 mil ethylene vinyl acetate (EVA) copolymer later on one surface to enable sealing.

The inventor has identified several properties of a preferred sealing device. The sealing device includes an elongated bar **92** with a continuous sealing section **94** that extends tangent to a plane over a length between 5 and 25 cm. In use, this flat, continuous sealing section **94** contacts the plastic film and creates a continuous seal between two adjacent sheets **12**. The elongated bar has high (>5 , or even $>20 \text{ W}/(\text{m K})$) thermal conductivity. The volumetric heat capacity of the bar is preferably greater than $2 \text{ J}/(\text{cm}^3 \text{ K})$. The mass of the elongated bar is preferably at least 0.5 g per cm of length. In this way, stored thermal energy within the bar **92** can be a source for heat during multiple sealing operations. Another component of the sealing device is made of a material (e.g. wood, plastic) with much lower ($<1 \text{ W}/(\text{m K})$) thermal conductivity. This lower thermal conductivity component **96** may be positioned at the ends or be located across one side of the elongated bar **92**, so that the bar can be more readily held and the continuous sealing section **94** can be pressed at elevated temperature against the bag **10** by the consumer. In one embodiment, the bar also includes a flexible piece **98** (e.g. string, thread, cord) that can extend several centimeters ($>5 \text{ cm}$) from one end of the sealing device, allowing the consumer to more easily remove the device from the hot water, while not extending the overall length of the sealing device in storage.

The length of the sealing device is important. If the sealing device **90** has a flexible piece **98** or adjustable piece, the sealing device **90** may have a minimum length **100** different from the maximum length. So as to minimize storage space when not in use, preferred embodiments of a sealing device have a minimum length **100** of the sealing device **90** that is not more than 20% greater, more preferably not more than 10% greater, than the length **102** of the continuous sealing section **94** of a metal bar **92** that contacts the plastic sheet. Although many seal lengths required for bags will be greater than 25 cm, some preferred embodiments will have a length **102** of the continuous sealing section **94** of a metal bar **92** that is less than 15 cm. In this way, the metal bar can be more easily submerged in water using standard microwavable mugs or cups, in the way many modern consumers are accustomed to heating water. In one embodiment, the length **102** of the continuous sealing section **94** of a metal bar **92** is between 7 and 15 cm in length, more preferably between 8 and 13 cm.

Bags for food storage are typically sold by the box, with a large number of bags within each box. Another aspect of this invention is a package (e.g. box or bag) that comprises at least four, or even at least ten, storage bags **10** and a sealing device **90** as described above. Appropriate storage bags are made of flexible sheets **12** with low oxygen transmission rate (less than $10 \text{ cm}^3/\text{m}^2/\text{day}$, $5 \text{ cm}^3/\text{m}^2/\text{day}$, or even less than $2 \text{ cm}^3/\text{m}^2/\text{day}$), and at least one of the facing sheets is a multilayer sheet having an inner layer of polymer enabling the facing sheets to be joined by melt sealing at less than 95°C . Preferably, the minimal length **100** of the sealing

device **90** is less than the largest diagonal of the bag. More preferably, the sealing device is not longer than longest edge dimension of the bag. Most preferably, the length **102** of the continuous sealing section **94** of a metal bar is greater than half the width of the bag opening. In this way, a bag may be sealed by two successive heat sealing operations.

From the perspective of the average consumer, a bag containing an oxygen remover would be new and potentially confusing. Use of the bag may involve different and unfamiliar ways to open the bag, load material within the storage region, or seal the oxygen remover and contents within the bag. Consequently, in another embodiment, at least one of the walls **13** of a flexible bag for food storage includes on it a machine-readable image **110** directing a computer or phone to a video on the Internet that shows how to open or seal the bag. The video may show opening a frangible seal **34** or closing the bag **10** using any of the procedures previously mentioned. Both opening and closing actions may be shown in the video.

The image **110** is preferably a multi-dimensional visual code that is machine-readable. Most preferably, the image is a QR code (abbreviated from Quick Response Code), a type of matrix barcode. QR codes descriptions and different uses for these are include in patent applications US 2006/0082475A1, US 2011/0085732A1, US 2012/0280031A1, US 2012/0291647A1, US 2013/0035787A1, and US 2013/0036162A1. Alternatively, other multi-dimensional visual codes include Codablock, Ezcode, DataGlyphs, MixiCode, ShotCode, and Aztec Code. Preferably, the image **110** directs a device with appropriate hardware and software to a video that demonstrates use of the bag **10**. This may be done by embedding within the machine-readable visual code a direct link to the video or to a URL containing a link to the video. Appropriate devices (e.g. smart phones and computer systems) are becoming common, and include a camera, display means, and Internet connection. Examples of appropriate software include NeoReader, BeeTagg, RedLaser, QuickMark, i-nigma, and Kayawa Reader.

For best results, using the inventive bag to prevent oxygen passage may be an exacting process, such that it may be more effective to show than describe. In one embodiment, the video may show the steps of re-sealing the bag with a consumer implementable sealing mechanism **60** that isolates the storage region **42** and at least a part of the outer section **32** from air surrounding the bag **10**. For instance, in the case of the folded tab **62** consumer seal in FIGS. **2** and **3**, the video may show sealing the bag by removal of the protective layer **68** to expose adhesive **64** on a surface **66**, and then folding a section of the tab **62** over one of the two facing sheets **12**. The video may further show how to avoid wrinkles (such as by sealing from the center to the periphery). In the case of forming a seal by a low temperature melt process, the video may show heating water in a cup, placing a sealing device **90** in the water to warm a metal bar **92**, removing the sealing device **90** by handling it by a component **96** of material having low thermal conductivity, and applying pressure to the warm bar **92** and at least one multilayer sheet **12**, such that facing sheets are joined together.

It is preferred that a plurality of bags (at least four bags, preferably at least 10, or even at least 100 bags) are sold in a package (e.g. a box or bag), and each bag may also include on its wall **13** an individual identifier. In one embodiment, a machine readable image **110** is different for each bag **10** within a package. In this way, software loaded on a phone or computer (including those computers within cameras, refrigerators, or other devices made capable of reading the image)

may record and make retrievable information assigned to individual bags and/or their contents. The same image or a different machine readable image on the bag may also link to a video, as described above.

Examples below are intended to be instructive but not to limit the scope of this invention. The entire subject matter of each of the previously cited references is incorporated herein by reference.

EXAMPLES

Example 1

One embodiment of the flexible bag may be created as follows. The walls of the bag are made from a 15 cm (6 inch) wide by 60 cm (24 inch) long sheet of Scotchpac™ HB-P 69731 Translucent High Barrier Film. 3M has published that this material is a multilayer laminate of 0.08 mm (3.1 mil) polyester (PET) with a 0.01 mm (0.5 mil) heat sealable ethylene vinyl acetate (EVA) copolymer inner layer. According to the 3M product page, a ceramic oxide coating (AlO) results in an oxygen transmittance by ASTM D 3985 of 1.3 cm³/m²/day.

Several items are affixed to the inner layer of the multilayer sheet as follows: A piece of opaque paper (e.g. 8 cm×8 cm) is adhered to the inner surface of the multilayer sheet, approximately 15 cm from the top edge. The paper contains written instructions and a QR code that links to a video. An iron powder mixture extracted from an AGELESS® (ZPT 500) absorption packet is spread on top of the paper. A 10"×10 cm strip of 3M Tegaderm membrane with adhesive backing is used to hold the iron powder in place against the opaque paper and multilayer sheet. In preparation for forming the frangible seal, an adhesive layer is applied in a line across the sheet width to the inner surface (EVA) of the multilayer sheet at a location approximately 5 cm from the top edge. The consumer implementable seal is created by adhering two aligned pieces of a relatively rigid clear plastic near the top edge of the multilayer sheet, and then applying a backed adhesive to the top most piece.

The long multilayer sheet is folded over itself to result in two facing multilayer sheets, with the EVA copolymer layers facing inward. The location of the fold is selected to cause the adhesive section of the resulting foldable tab to partially overlap both facing sheets. The adhesive layer applied in a line at 5 cm from the top edge is put under pressure to join and seal both sheets, forming the frangible seal. Using a Food Saver© V2222 vacuum sealer (without vacuum), facing sheets are thermally sealed together along their outer long edges (including over the line of applied adhesive). Through these side seals and the frangible seal, the oxygen remover is isolated from air surrounding the bag.

While this description provides a workable bag, one skilled in the art will recognize that many variations are possible and are within the scope of this invention.

Example 2

An experiment compared five bags having approximately the construction described above to five commercial freezer zippered bags having similar volume. An Ageless© oxygen removal packet was placed in commercial bags and the constructed bags of this invention were made with the iron-based, oxygen removing mixture from identical packets. Sheets of 3M Petrifilm were inoculated with a uniform solution containing mold spores taken from blueberries, placed in petri dishes to create a repeatable volume of

9

“empty” air, and sealed inside the constructed and commercial bags. After one week, the samples sealed inside of the commercial freezer bag had a large (and undetermined) number of mold colonies, whereas no mold colonies were observed on 3M Petrifilm within the constructed bags.

Example 3

Bags were constructed as above, except that the inoculated Petrifilm container was built into the bag’s storage region. In this way, the integrity of the frangible seal could be tested. This experiment relates to the shelf life one might expect for a product. While tests will need to be done in the future for longer times, after the last observation at 115 days, no mold growth was observed in samples.

Example 4

Bags were constructed as above. Strawberries and cheese were placed in these bags and in commercial zippered bags of the same size. Strawberries stored in commercial bags showed evidence of significant mold growth after four days. Cheese stored in commercial bags showed significant mold after six days. After twice as long, in each case, no mold was observed for food in the constructed bag. The experiment was terminated at that point, as the appearance of food items within the constructed bags had begun to lessened due to other aspects (weeping for un-refrigerated cheese and moisture-loss for strawberries).

The invention claimed is:

1. A method of sealing a food storage bag comprising the steps of

- a) providing a flexible storage bag comprising two facing sheets forming the walls, the two facing sheets joined together along three adjacent edges to form a rectangular pouch with an opening at one end, at least one of the facing sheets is a multilayer sheet having an inner layer of polymer suitable to be joined by melt sealing at less than 95° C. to its facing sheet;
- b) providing a sealing device comprising an elongated bar with thermal conductivity greater than 5 W/(m K) and an insulating component affixed to the elongated bar having a thermal conductivity less than 1 W/(m K), wherein the elongated bar has a continuous sealing section that extends tangent to a plane over a length between 5 and 25 cm;
- c) placing the sealing device into water;
- d) warming the elongated bar to a temperature of between 50° C. and 100° C.;
- e) removing the warmed bar from the water;
- f) handling the sealing device by the insulating component; and

10

g) pressing the warmed elongated bar against a wall of the storage bag to join facing sheets by melt sealing and to create a storage region that is isolated from air surrounding the storage bag.

2. The method of claim 1, wherein the length of the continuous sealing section of the elongated bar is greater than half the width of the opening.

3. The method of claim 1, wherein the length of the sealing device is less than the length of the largest diagonal of the storage bag.

4. The method of claim 3, wherein the length of the sealing device is not longer than the longest edge of the storage bag.

5. The method of claim 1, wherein the sealing device further includes a flexible piece extending from one end of the sealing device, the flexible piece is suitable for allowing the consumer to more easily remove the device from the hot water.

6. The method of claim 1, wherein the water is contained within a microwavable cup or mug, and the continuous sealing section of the elongated bar is less than 15 cm.

7. The method of claim 1, wherein the length of the continuous sealing section of the elongated bar is between 7 and 15 cm in length.

8. The method of claim 1, wherein the length of the continuous sealing section of the elongated bar is between 8 and 13 cm in length.

9. The method of claim 1, wherein the facing sheets have an oxygen transmission rate at 25° C. of less than 10 cm³/m²/day.

10. The method of claim 9, wherein the pouch is separated into inner and outer sections by a frangible seal affixing the two facing sheets, and the inner section contains an oxygen remover and a water impermeable membrane with oxygen transmission rate at 25° C. of more than 2000 cm³/m²/day, the membrane separating the oxygen remover from a storage region within the pouch; wherein prior to joining facing sheets by melt sealing, the method further comprises opening the frangible seal that initially isolates the oxygen remover from air outside the pouch.

11. The method of claim 1, wherein at least one wall of the storage bag contains a machine-readable image that is a multi-dimensional visual code suitable to direct a computer or phone having camera, display, internet connection, and appropriate software to read the image, to a video on the Internet that shows sealing the storage bag with the sealing device.

12. The method of claim 1, wherein at least one wall of the storage bag contains a QR code.

* * * * *