



US009914864B2

(12) **United States Patent**
Josseaux et al.

(10) **Patent No.:** **US 9,914,864 B2**
(45) **Date of Patent:** **Mar. 13, 2018**

(54) **SHAPED ABRASIVE PARTICLES AND METHOD OF FORMING SAME**

(58) **Field of Classification Search**
USPC 51/295, 293, 307, 309
See application file for complete search history.

(71) Applicant: **Saint-Gobain Ceramics & Plastics, Inc.**, Worcester, MA (US)

(56) **References Cited**

(72) Inventors: **Frederic Josseaux**, Worcester, MA (US); **David F. Louapre**, Paris (FR)

U.S. PATENT DOCUMENTS

(73) Assignee: **SAINT-GOBAIN CERAMICS & PLASTICS, INC.**, Worcester, MA (US)

345,604 A	7/1886	Semper
1,910,444 A	5/1933	Nicholson
2,049,874 A	8/1936	Sherk
2,148,400 A	2/1939	Crompton, Jr.
2,248,064 A	7/1941	Carlton et al.
2,248,990 A	7/1941	Heany
2,290,877 A	7/1942	Heany
2,318,360 A	5/1943	Benner et al.
2,376,343 A	5/1945	Carlton

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(Continued)

(21) Appl. No.: **14/757,688**

(22) Filed: **Dec. 23, 2015**

FOREIGN PATENT DOCUMENTS

(65) **Prior Publication Data**

CA	743715 A	10/1966
CA	2423788 A1	7/2002

US 2016/0177154 A1 Jun. 23, 2016

(Continued)

Related U.S. Application Data

OTHER PUBLICATIONS

(63) Continuation of application No. 14/581,220, filed on Dec. 23, 2014, now Pat. No. 9,707,529.

International Search Report for Application No. PCT/US2015/000190, dated Apr. 1, 2016, 1 page.

(60) Provisional application No. 62/141,181, filed on Mar. 31, 2015.

(Continued)

(51) **Int. Cl.**

Primary Examiner — James McDonough

B24D 3/00	(2006.01)
B24D 11/00	(2006.01)
B24D 18/00	(2006.01)
C09K 3/14	(2006.01)
B24B 1/00	(2006.01)
B24D 3/02	(2006.01)
B01J 2/26	(2006.01)
B01J 2/20	(2006.01)

(74) *Attorney, Agent, or Firm* — Abel Law Group, LLP; Adam Keser


(52) **U.S. Cl.**

CPC **C09K 3/1409** (2013.01); **B01J 2/20** (2013.01); **B01J 2/26** (2013.01)

(57) **ABSTRACT**

An abrasive particle including a shaped abrasive particle including a body having a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle.

23 Claims, 16 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

			4,848,041 A	7/1989	Kruschke	
			4,858,527 A	8/1989	Masanao	
			4,860,721 A *	8/1989	Matsuda	B24D 5/12 125/15
2,563,650 A	8/1951	Heinemann et al.	4,863,573 A	9/1989	Moore et al.	
2,880,080 A	3/1959	Rankin et al.	4,876,226 A	10/1989	Fuentes	
3,041,156 A	6/1962	Rowse et al.	4,881,951 A	11/1989	Wood et al.	
3,067,551 A	12/1962	Maginnis	4,917,852 A	4/1990	Poole et al.	
3,079,242 A	2/1963	Glasgow	4,918,116 A	4/1990	Gardziella et al.	
3,079,243 A	2/1963	Ueltz	4,925,815 A	5/1990	Tani et al.	
3,123,948 A	3/1964	Kistler et al.	4,930,266 A	6/1990	Calhoun et al.	
3,141,271 A	7/1964	Fischer et al.	4,942,011 A	7/1990	Bolt et al.	
3,276,852 A	10/1966	Lemelson	4,954,462 A	9/1990	Wood	
3,377,660 A	4/1968	Marshall et al.	4,960,441 A	10/1990	Pellow et al.	
3,379,543 A	4/1968	Norwalk	4,961,757 A	10/1990	Rhodes et al.	
3,387,957 A	6/1968	Howard	4,963,012 A	10/1990	Tracy	
3,454,385 A	7/1969	Amero	4,964,883 A	10/1990	Morris et al.	
3,477,180 A	11/1969	Robertson, Jr.	4,970,057 A	11/1990	Wilkens et al.	
3,480,395 A	11/1969	McMullen et al.	4,997,461 A	3/1991	Markhoff-Matheny et al.	
3,481,723 A	12/1969	Kistler et al.	5,009,675 A	4/1991	Kunz et al.	
3,491,492 A	1/1970	Ueltz	5,009,676 A	4/1991	Rue et al.	
3,495,359 A	2/1970	Smith et al.	5,011,508 A	4/1991	Wald et al.	
3,536,005 A	10/1970	Derrickson	5,011,510 A	4/1991	Hayakawa et al.	
3,590,799 A	7/1971	Guuchowicz	5,014,468 A	5/1991	Ravipati et al.	
3,608,050 A	9/1971	Carman et al.	5,024,795 A	6/1991	Kennedy et al.	
3,608,134 A	9/1971	Cook	5,032,304 A	7/1991	Toyota	
3,615,308 A	10/1971	Amero	5,035,723 A	7/1991	Kalinowski et al.	
3,619,151 A	11/1971	Sheets, Jr. et al.	5,035,724 A	7/1991	Pukari et al.	
3,637,360 A	1/1972	Ueltz	5,042,991 A	8/1991	Kunz et al.	
3,670,467 A	6/1972	Walker	5,049,166 A	9/1991	Kirkendall	
3,672,934 A	6/1972	Larry	5,049,645 A	9/1991	Nagaoka et al.	
3,819,785 A	6/1974	Argyle et al.	5,053,367 A	10/1991	Newkirk et al.	
3,859,407 A	1/1975	Blanding et al.	5,053,369 A	10/1991	Winkler et al.	
3,874,856 A	4/1975	Leeds	5,076,991 A	12/1991	Poole et al.	
3,909,991 A	10/1975	Coes, Jr.	5,078,753 A	1/1992	Broberg et al.	
3,940,276 A	2/1976	Wilson	5,081,082 A	1/1992	Hai-Doo et al.	
3,950,148 A	4/1976	Fukuda	5,085,671 A	2/1992	Martin et al.	
3,960,577 A	6/1976	Prochazka	5,090,968 A	2/1992	Pellow	
3,977,132 A	8/1976	Sekigawa	5,094,986 A	3/1992	Matsumoto et al.	
3,986,885 A	10/1976	Lankard	5,098,740 A	3/1992	Tewari	
3,991,527 A	11/1976	Maran	5,103,598 A	4/1992	Kelly	
4,004,934 A	1/1977	Prochazka	5,108,963 A	4/1992	Fu et al.	
4,037,367 A	7/1977	Kruse	5,114,438 A	5/1992	Leatherman et al.	
4,045,919 A	9/1977	Moritomo	5,120,327 A	6/1992	Dennis	
4,055,451 A	10/1977	Cockbain et al.	5,123,935 A	6/1992	Kanamaru et al.	
4,073,096 A	2/1978	Ueltz et al.	5,129,919 A	7/1992	Kalinowski et al.	
4,114,322 A	9/1978	Greenspan	5,131,926 A	7/1992	Rostoker et al.	
4,150,078 A	4/1979	Miller et al.	5,132,984 A	7/1992	Simpson	
4,194,887 A	3/1980	Ueltz et al.	5,139,978 A	8/1992	Wood	
4,252,544 A	2/1981	Takahashi	5,152,917 A	10/1992	Pieper et al.	
4,261,706 A	4/1981	Blanding et al.	5,160,509 A	11/1992	Carman et al.	
4,286,905 A	9/1981	Samanta	5,164,744 A	11/1992	Yoshida et al.	
4,304,576 A	12/1981	Hattori et al.	5,173,457 A	12/1992	Shorthouse	
4,314,827 A	2/1982	Leitheiser et al.	5,178,849 A	1/1993	Bauer	
4,341,663 A	7/1982	Derleth et al.	5,180,630 A	1/1993	Giglia	
4,393,021 A	7/1983	Eisenberg et al.	5,185,012 A	2/1993	Kelly	
4,452,911 A	6/1984	Eccles et al.	5,185,299 A	2/1993	Wood et al.	
4,457,767 A	7/1984	Poon et al.	5,190,568 A	3/1993	Tselesin	
4,469,758 A	9/1984	Scott	5,194,072 A	3/1993	Rue et al.	
4,505,720 A	3/1985	Gabor et al.	5,201,916 A *	4/1993	Berg	B24D 3/14 264/6
4,541,842 A	7/1985	Rostoker				
4,548,617 A	10/1985	Miyatani et al.	5,203,886 A	4/1993	Sheldon et al.	
4,570,048 A	2/1986	Poole	5,213,591 A	5/1993	Celikkaya et al.	
4,618,349 A	10/1986	Hashimoto et al.	5,215,552 A	6/1993	Sung	
4,623,364 A	11/1986	Cottringer et al.	5,219,462 A	6/1993	Bruxvoort et al.	
4,656,330 A	4/1987	Poole	5,219,806 A	6/1993	Wood	
4,657,754 A	4/1987	Bauer et al.	5,221,294 A	6/1993	Carman et al.	
4,659,341 A	4/1987	Ludwig et al.	5,224,970 A	7/1993	Harakawa et al.	
4,678,560 A	7/1987	Stole	5,227,104 A	7/1993	Bauer	
4,711,750 A	12/1987	Scott	5,244,477 A *	9/1993	Rue	C04B 35/1115 51/293
4,728,043 A	3/1988	Ersdal et al.				
4,744,802 A	5/1988	Schwabel	5,244,849 A	9/1993	Roy et al.	
4,770,671 A	9/1988	Monroe	5,273,558 A	12/1993	Nelson et al.	
4,786,292 A	11/1988	Janz et al.	5,277,702 A	1/1994	Thibault et al.	
4,797,139 A	1/1989	Bauer	5,282,875 A	2/1994	Wood	
4,797,269 A	1/1989	Bauer et al.	5,288,297 A	2/1994	Ringwood	
4,799,939 A	1/1989	Bloecher et al.	5,300,130 A	4/1994	Rostoker	
4,829,027 A	5/1989	Cutler et al.	5,304,331 A	4/1994	Leonard et al.	
4,832,706 A	5/1989	Yates	5,312,789 A	5/1994	Wood	

(56)

References Cited

U.S. PATENT DOCUMENTS

5,312,791 A	5/1994	Coblentz et al.	5,830,248 A	11/1998	Christianson et al.
5,366,523 A	11/1994	Rowenhorst et al.	5,840,089 A	11/1998	Chesley et al.
5,366,525 A	11/1994	Fujiyama	5,849,646 A	12/1998	Stout et al.
5,372,620 A	12/1994	Rowse et al.	5,855,997 A	1/1999	Amateau
5,373,786 A	12/1994	Umaba	5,863,306 A	1/1999	Wei et al.
5,376,598 A	12/1994	Preedy et al.	5,866,254 A	2/1999	Peker et al.
5,376,602 A	12/1994	Nilsen	5,876,793 A	3/1999	Sherman et al.
5,383,945 A	1/1995	Cottringer et al.	5,885,311 A	3/1999	McCutcheon et al.
5,395,407 A	3/1995	Cottringer et al.	5,893,935 A	4/1999	Wood
5,409,645 A	4/1995	Torre, Jr. et al.	5,902,647 A	5/1999	Venkataramani
5,429,648 A	7/1995	Wu	5,908,477 A	6/1999	Harmer et al.
5,431,967 A	7/1995	Manthiram	5,908,478 A	6/1999	Wood
5,435,816 A	7/1995	Spurgeon et al.	5,919,549 A	7/1999	Van et al.
5,437,754 A	8/1995	Calhoun	5,924,917 A	7/1999	Benedict et al.
5,441,549 A	8/1995	Helmin	5,946,991 A	9/1999	Hoopman
5,443,603 A	8/1995	Kirkendall	5,975,987 A	11/1999	Hoopman et al.
5,447,894 A	9/1995	Yasuoka et al.	5,980,678 A	11/1999	Tselesin
5,453,106 A	9/1995	Roberts	5,984,988 A	11/1999	Berg et al.
5,454,844 A	10/1995	Hibbard et al.	5,989,301 A	11/1999	Laconto, Sr. et al.
5,470,806 A	11/1995	Krstic et al.	5,997,597 A	12/1999	Hagan
5,479,873 A	1/1996	Shintani et al.	6,016,660 A	1/2000	Abramshe
5,482,756 A	1/1996	Berger et al.	6,019,805 A	2/2000	Herron
5,486,496 A	1/1996	Talbert et al.	6,024,824 A	2/2000	Krech
5,496,386 A	3/1996	Broberg et al.	6,027,326 A	2/2000	Cesarano, III et al.
5,500,273 A	3/1996	Holmes et al.	6,048,577 A	4/2000	Garg
5,514,631 A	5/1996	Cottringer et al.	6,053,956 A	4/2000	Wood
5,516,347 A	5/1996	Garg	6,054,093 A	4/2000	Torre, Jr. et al.
5,516,348 A	5/1996	Conwell et al.	6,080,215 A	6/2000	Stubbs et al.
5,523,074 A	6/1996	Takahashi et al.	6,080,216 A	6/2000	Erickson
5,525,100 A	6/1996	Kelly et al.	6,083,622 A	7/2000	Garg et al.
5,527,369 A	6/1996	Garg	6,096,107 A	8/2000	Caracostas et al.
5,543,368 A	8/1996	Talbert et al.	6,110,241 A	8/2000	Sung
5,551,963 A	9/1996	Larmie	6,129,540 A	10/2000	Hoopman et al.
5,560,745 A	10/1996	Roberts	6,136,288 A	10/2000	Bauer et al.
5,567,150 A	10/1996	Conwell et al.	6,146,247 A	11/2000	Nokubi et al.
5,567,214 A	10/1996	Ashley	6,179,887 B1	1/2001	Barber, Jr. et al.
5,567,251 A	10/1996	Peker et al.	6,206,942 B1	3/2001	Wood
5,571,297 A	11/1996	Swei et al.	6,228,134 B1	5/2001	Erickson
5,576,409 A	11/1996	Mackey	6,238,450 B1	5/2001	Garg et al.
5,578,095 A	11/1996	Bland et al.	6,258,137 B1	7/2001	Garg et al.
5,578,222 A	11/1996	Trischuk et al.	6,258,141 B1	7/2001	Sung et al.
5,582,625 A	12/1996	Wright et al.	6,261,682 B1	7/2001	Law
5,584,896 A	12/1996	Broberg et al.	6,264,710 B1	7/2001	Erickson
5,584,897 A	12/1996	Christianson et al.	6,277,160 B1	8/2001	Stubbs et al.
5,591,685 A	1/1997	Mitomo et al.	6,277,161 B1	8/2001	Castro et al.
5,593,468 A	1/1997	Khaund et al.	6,283,997 B1	9/2001	Garg et al.
5,599,493 A	2/1997	Ito et al.	6,284,690 B1	9/2001	Nakahata et al.
5,603,738 A	2/1997	Zeiringer et al.	6,287,353 B1	9/2001	Celikkaya
5,609,706 A	3/1997	Benedict et al.	6,306,007 B1	10/2001	Mori et al.
5,611,829 A	3/1997	Monroe et al.	6,312,324 B1	11/2001	Mitsui et al.
5,618,221 A	4/1997	Furukawa et al.	6,319,108 B1	11/2001	Adefris et al.
5,628,952 A	5/1997	Holmes et al.	6,331,343 B1	12/2001	Perez et al.
5,641,469 A	6/1997	Garg et al.	6,371,842 B1	4/2002	Romero
RE35,570 E	7/1997	Rowenhorst et al.	6,391,812 B1	5/2002	Araki et al.
5,645,619 A	7/1997	Erickson et al.	6,401,795 B1	6/2002	Cesarano, III et al.
5,651,925 A	7/1997	Ashley et al.	6,403,001 B1	6/2002	Hayashi
5,656,217 A	8/1997	Rogers et al.	6,413,286 B1	7/2002	Swei et al.
5,667,542 A	9/1997	Law et al.	6,451,076 B1	9/2002	Nevoret et al.
5,669,941 A	9/1997	Peterson	6,475,253 B2	11/2002	Culler et al.
5,669,943 A	9/1997	Horton et al.	6,524,681 B1	2/2003	Seitz et al.
5,672,097 A	9/1997	Hoopman	6,531,423 B1	3/2003	Schwetz et al.
5,672,554 A	9/1997	Mohri et al.	6,537,140 B1	3/2003	Miller et al.
5,683,844 A	11/1997	Mammino	6,579,819 B2	6/2003	Hirosaki et al.
5,702,811 A	12/1997	Ho et al.	6,582,623 B1	6/2003	Grumbine et al.
5,725,162 A	3/1998	Garg et al.	6,583,080 B1	6/2003	Rosenflanz
5,736,619 A	4/1998	Kane et al.	6,599,177 B2	7/2003	Nevoret et al.
5,738,696 A	4/1998	Wu	6,613,113 B2	9/2003	Minick et al.
5,738,697 A	4/1998	Wu et al.	6,646,019 B2	11/2003	Perez et al.
5,751,313 A	5/1998	Miyashita et al.	6,652,361 B1	11/2003	Gash et al.
5,759,481 A	6/1998	Pujari et al.	6,669,745 B2	12/2003	Prichard et al.
5,776,214 A	7/1998	Wood	6,685,755 B2	2/2004	Ramanath et al.
5,779,743 A	7/1998	Wood	6,696,258 B1	2/2004	Wei
5,785,722 A	7/1998	Garg et al.	6,702,650 B2	3/2004	Adefris
5,810,587 A	9/1998	Bruns et al.	6,737,378 B2	5/2004	Hirosaki et al.
5,820,450 A	10/1998	Calhoun	6,749,496 B2	6/2004	Mota et al.
			6,755,729 B2	6/2004	Ramanath et al.
			6,833,014 B2	12/2004	Welygan et al.
			6,843,815 B1	1/2005	Thurber et al.
			6,846,795 B2	1/2005	Lant et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

6,878,456 B2	4/2005	Castro et al.	2004/0224125 A1	11/2004	Yamada et al.
6,881,483 B2	4/2005	McArdle et al.	2004/0235406 A1	11/2004	Duescher
6,888,360 B1	5/2005	Connell et al.	2004/0244675 A1	12/2004	Kishimoto et al.
6,913,824 B2	7/2005	Culler et al.	2005/0020190 A1	1/2005	Schutz et al.
6,942,561 B2	9/2005	Mota et al.	2005/0060941 A1	3/2005	Provow et al.
6,949,128 B2	9/2005	Annen	2005/0060947 A1	3/2005	McArdle et al.
6,974,930 B2	12/2005	Jense	2005/0064805 A1	3/2005	Culler et al.
7,022,179 B1	4/2006	Dry	2005/0081455 A1	4/2005	Welygan et al.
7,044,989 B2	5/2006	Welygan et al.	2005/0118939 A1	6/2005	Duescher
7,141,522 B2	11/2006	Rosenflanz et al.	2005/0132655 A1	6/2005	Anderson et al.
7,168,267 B2	1/2007	Rosenflanz et al.	2005/0218565 A1	10/2005	DiChiara, Jr.
7,169,198 B2	1/2007	Moeltgen et al.	2005/0223649 A1	10/2005	O'Gary et al.
7,267,700 B2	9/2007	Collins et al.	2005/0232853 A1	10/2005	Evans et al.
7,294,158 B2	11/2007	Welygan et al.	2005/0245179 A1	11/2005	Luedeke
7,297,170 B2	11/2007	Welygan et al.	2005/0255801 A1	11/2005	Pollasky
7,297,402 B2	11/2007	Evans et al.	2005/0266221 A1	12/2005	Karam et al.
7,364,788 B2	4/2008	Kishbaugh et al.	2005/0271795 A1	12/2005	Moini et al.
7,373,887 B2	5/2008	Jackson	2005/0284029 A1	12/2005	Bourlier et al.
7,384,437 B2	6/2008	Welygan et al.	2006/0049540 A1	3/2006	Hui et al.
7,488,544 B2	2/2009	Schofalvi et al.	2006/0126265 A1	6/2006	Crespi et al.
7,507,268 B2	3/2009	Rosenflanz	2006/0135050 A1	6/2006	Petersen et al.
7,553,346 B2	6/2009	Welygan et al.	2006/0177488 A1	8/2006	Caruso et al.
7,556,558 B2	7/2009	Palmgren	2006/0185256 A1	8/2006	Nevoret et al.
7,560,062 B2	7/2009	Gould et al.	2007/0020457 A1	1/2007	Adefris
7,560,139 B2	7/2009	Thebault et al.	2007/0051355 A1	3/2007	Sung
7,563,293 B2	7/2009	Rosenflanz	2007/0072527 A1	3/2007	Palmgren
7,611,795 B2	11/2009	Aoyama et al.	2007/0074456 A1	4/2007	Orlhac et al.
7,618,684 B2	11/2009	Nesbitt	2007/0087928 A1	4/2007	Rosenflanz et al.
7,662,735 B2	2/2010	Rosenflanz et al.	2007/0234646 A1	10/2007	Can et al.
7,666,344 B2	2/2010	Schofalvi et al.	2008/0017053 A1	1/2008	Araumi et al.
7,666,475 B2	2/2010	Morrison	2008/0121124 A1	5/2008	Sato
7,669,658 B2	3/2010	Barron et al.	2008/0172951 A1	7/2008	Starling
7,670,679 B2	3/2010	Krishna et al.	2008/0176075 A1	7/2008	Bauer et al.
7,695,542 B2	4/2010	Drivdahl et al.	2008/0179783 A1	7/2008	Liu et al.
7,858,189 B2	12/2010	Wagener et al.	2008/0230951 A1	9/2008	Dannoux et al.
7,906,057 B2	3/2011	Zhang	2008/0262577 A1	10/2008	Altshuler et al.
7,968,147 B2	6/2011	Fang et al.	2008/0286590 A1	11/2008	Besida et al.
7,972,430 B2	7/2011	Millard et al.	2008/0299875 A1	12/2008	Duescher
8,021,449 B2	9/2011	Seth et al.	2009/0016916 A1	1/2009	Rosenzweig et al.
8,034,137 B2	10/2011	Erickson et al.	2009/0017736 A1	1/2009	Block et al.
8,049,136 B2	11/2011	Mase et al.	2009/0165394 A1	7/2009	Culler et al.
8,070,556 B2	12/2011	Kumar et al.	2009/0165661 A1	7/2009	Koenig et al.
8,123,828 B2	2/2012	Culler et al.	2009/0208734 A1	8/2009	Macfie et al.
8,141,484 B2	3/2012	Ojima et al.	2009/0246464 A1	10/2009	Watanabe et al.
8,142,531 B2	3/2012	Adefris et al.	2010/0000159 A1	1/2010	Walia et al.
8,142,532 B2	3/2012	Erickson et al.	2010/0003900 A1	1/2010	Sakaguchi et al.
8,142,891 B2	3/2012	Culler et al.	2010/0003904 A1	1/2010	Duescher
8,251,774 B2	8/2012	Joseph et al.	2010/0040767 A1	2/2010	Uibel et al.
8,256,091 B2	9/2012	Duescher	2010/0056816 A1	3/2010	Wallin et al.
8,440,602 B2	5/2013	Gonzales et al.	2010/0068974 A1	3/2010	Dumm
8,440,603 B2	5/2013	Gonzales et al.	2010/0146867 A1	6/2010	Boden et al.
8,445,422 B2	5/2013	Gonzales et al.	2010/0151195 A1	6/2010	Culler et al.
8,470,759 B2	6/2013	Gonzales et al.	2010/0151196 A1	6/2010	Adefris et al.
8,480,772 B2	7/2013	Welygan et al.	2010/0151201 A1	6/2010	Erickson et al.
8,628,597 B2	1/2014	Palmgren et al.	2010/0190424 A1	7/2010	Francois et al.
8,783,589 B2	7/2014	Hart et al.	2010/0201018 A1	8/2010	Yoshioka et al.
8,852,643 B2	10/2014	Gonzales et al.	2010/0292428 A1	11/2010	Meador et al.
9,017,439 B2	4/2015	Yener et al.	2010/0307067 A1	12/2010	Sigalas et al.
2001/0027623 A1	10/2001	Rosenflanz	2010/0319269 A1	12/2010	Erickson
2002/0026752 A1	3/2002	Culler et al.	2011/0008604 A1	1/2011	Boylan
2002/0151265 A1	10/2002	Adefris	2011/0023376 A1	2/2011	Linnenbrink
2002/0170236 A1	11/2002	Larson et al.	2011/0111563 A1	5/2011	Yanagi et al.
2002/0174935 A1	11/2002	Burdon et al.	2011/0124483 A1	5/2011	Shah et al.
2002/0177391 A1	11/2002	Fritz et al.	2011/0136659 A1	6/2011	Allen et al.
2003/0008933 A1	1/2003	Perez et al.	2011/0146509 A1	6/2011	Welygan et al.
2003/0022961 A1	1/2003	Kusaka et al.	2011/0160104 A1	6/2011	Wu et al.
2003/0029094 A1	2/2003	Moeltgen et al.	2011/0244769 A1	10/2011	David et al.
2003/0085204 A1	5/2003	Lagos	2011/0289854 A1	12/2011	Moren et al.
2003/0109371 A1	6/2003	Pujari et al.	2011/0314746 A1	12/2011	Erickson et al.
2003/0110707 A1	6/2003	Rosenflanz et al.	2012/0000135 A1	1/2012	Eilers et al.
2003/0126800 A1	7/2003	Seth et al.	2012/0055098 A1	3/2012	Ramanath et al.
2004/0003895 A1	1/2004	Amano et al.	2012/0137597 A1	6/2012	Adefris et al.
2004/0148868 A1	8/2004	Anderson et al.	2012/0144754 A1	6/2012	Culler et al.
2004/0148967 A1	8/2004	Celikkaya et al.	2012/0144755 A1	6/2012	Erickson et al.
2004/0202844 A1	10/2004	Wong	2012/0153547 A1	6/2012	Bauer et al.
			2012/0167481 A1	7/2012	Yener et al.
			2012/0168979 A1	7/2012	Bauer et al.
			2012/0227333 A1	9/2012	Adefris et al.
			2012/0231711 A1	9/2012	Keipert et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2012/0308837 A1 12/2012 Schlechtriemen et al.
 2013/0000212 A1 1/2013 Wang et al.
 2013/0000216 A1 1/2013 Wang et al.
 2013/0009484 A1 1/2013 Yu
 2013/0036402 A1 2/2013 Mutisya et al.
 2013/0045251 A1 2/2013 Cen et al.
 2013/0067669 A1 3/2013 Gonzales et al.
 2013/0072417 A1 3/2013 Perez-Prat et al.
 2013/0074418 A1 3/2013 Panzarella et al.
 2013/0125477 A1 5/2013 Adefris
 2013/0180180 A1 7/2013 Yener et al.
 2013/0186005 A1 7/2013 Kavanaugh
 2013/0186006 A1 7/2013 Kavanaugh et al.
 2013/0199105 A1 8/2013 Braun et al.
 2013/0236725 A1 9/2013 Yener et al.
 2013/0255162 A1 10/2013 Welygan et al.
 2013/0267150 A1 10/2013 Seider et al.
 2013/0283705 A1 10/2013 Fischer et al.
 2013/0305614 A1 11/2013 Gaeta et al.
 2013/0337262 A1 12/2013 Bauer et al.
 2013/0337725 A1 12/2013 Monroe
 2014/0000176 A1 1/2014 Moren et al.
 2014/0007518 A1 1/2014 Yener et al.
 2014/0080393 A1 3/2014 Ludwig
 2014/0106126 A1 4/2014 Gaeta et al.
 2014/0182216 A1 7/2014 Panzarella et al.
 2014/0182217 A1 7/2014 Yener et al.
 2014/0186585 A1 7/2014 Field, III et al.
 2014/0250797 A1 9/2014 Yener et al.
 2014/0290147 A1 10/2014 Seth et al.
 2014/0352721 A1 12/2014 Gonzales et al.
 2014/0352722 A1 12/2014 Gonzales et al.
 2014/0357544 A1 12/2014 Gonzales et al.
 2014/0378036 A1 12/2014 Cichowlas et al.
 2015/0000209 A1 1/2015 Louapre et al.
 2015/0000210 A1 1/2015 Breder et al.
 2015/0007399 A1 1/2015 Gonzales et al.
 2015/0007400 A1 1/2015 Gonzales et al.
 2015/0089881 A1 4/2015 Stevenson et al.
 2015/0126098 A1 5/2015 Eilers et al.
 2015/0128505 A1 5/2015 Wang et al.
 2015/0183089 A1 7/2015 Iyengar et al.
 2015/0218430 A1 8/2015 Yener et al.
 2015/0232727 A1 8/2015 Erickson
 2015/0291865 A1 10/2015 Breder et al.
 2015/0291866 A1 10/2015 Arcona et al.
 2015/0291867 A1 10/2015 Breder et al.
 2015/0343603 A1 12/2015 Breder et al.
 2016/0177152 A1 6/2016 Braun
 2016/0177153 A1 6/2016 Josseaux
 2016/0177154 A1 6/2016 Josseaux et al.
 2016/0186028 A1 6/2016 Louapare et al.
 2016/0214903 A1 7/2016 Humpal et al.
 2016/0298013 A1 10/2016 Bock et al.
 2016/0303704 A1 10/2016 Chou et al.
 2016/0303705 A1 10/2016 Chou et al.
 2016/0304760 A1 10/2016 Bock et al.
 2016/0311081 A1 10/2016 Culler et al.
 2016/0311084 A1 10/2016 Culler et al.
 2016/0340564 A1 11/2016 Louapre et al.
 2016/0354898 A1 12/2016 Nienaber et al.
 2016/0362589 A1 12/2016 Bauer et al.
 2017/0066099 A1 3/2017 Nakamura
 2017/0114260 A1 4/2017 Bock et al.
 2017/0129075 A1 5/2017 Thurber et al.

FOREIGN PATENT DOCUMENTS

CH 685051 A5 3/1995
 CN 102123837 B 7/2014
 DE 102012023688 A1 4/2014
 DE 202014101739 U1 6/2014
 DE 202014101741 U1 6/2014
 DE 102013202204 A1 8/2014
 DE 102013210158 A1 12/2014

DE 102013210716 A1 12/2014
 DE 102013212598 A1 12/2014
 DE 102013212622 A1 12/2014
 DE 102013212634 A1 12/2014
 DE 102013212639 A1 12/2014
 DE 102013212644 A1 12/2014
 DE 102013212653 A1 12/2014
 DE 102013212654 A1 12/2014
 DE 102013212661 A1 12/2014
 DE 102013212666 A1 12/2014
 DE 102013212677 A1 12/2014
 DE 102013212680 A1 12/2014
 DE 102013212687 A1 12/2014
 DE 102013212690 A1 12/2014
 DE 102013212700 A1 12/2014
 DE 102014210836 A1 12/2014
 EP 0046374 A2 2/1982
 EP 0078896 A2 5/1983
 EP 0152768 A3 9/1987
 EP 0293163 A2 11/1988
 EP 0480133 A2 4/1992
 EP 0652919 A1 5/1995
 EP 0662110 A1 7/1995
 EP 0500369 B1 1/1996
 EP 0609864 B1 11/1996
 EP 0771769 5/1997
 EP 0812456 B1 12/1997
 EP 0651778 B1 5/1998
 EP 0614861 B1 5/2001
 EP 0931032 B3 7/2001
 EP 0833803 8/2001
 EP 1356152 A2 10/2003
 EP 1371451 A1 12/2003
 EP 1383631 B1 1/2004
 EP 1015181 B1 3/2004
 EP 1492845 A1 1/2005
 EP 1851007 A1 11/2007
 EP 1960157 A1 8/2008
 EP 2176031 A1 4/2010
 EP 2184134 A1 5/2010
 EP 2390056 A2 11/2011
 EP 1800801 B1 3/2012
 EP 2537917 A1 12/2012
 EP 2567784 A1 3/2013
 EP 2631286 A1 8/2013
 EP 2692813 A1 2/2014
 EP 2692814 A1 2/2014
 EP 2692815 A1 2/2014
 EP 2692816 A1 2/2014
 EP 2692817 A1 2/2014
 EP 2692818 A1 2/2014
 EP 2692819 A1 2/2014
 EP 2692820 A1 2/2014
 EP 2692821 A1 2/2014
 EP 2719752 A1 4/2014
 EP 2720676 A1 4/2014
 EP 2012972 B1 6/2014
 FR 2354373 A1 1/1978
 GB 986847 a 3/1965
 JP 53064890 A 6/1978
 JP 60-006356 U 1/1985
 JP 62002946 B 1/1987
 JP 63036905 B 7/1988
 JP 3079277 A 4/1991
 JP 03-287687 12/1991
 JP 5285833 A 11/1993
 JP 6114739 A 4/1994
 JP 7008474 B2 2/1995
 JP 10113875 A 5/1998
 JP 2779252 B2 7/1998
 JP 10330734 A 12/1998
 JP H10315142 A 12/1998
 JP 2957492 B2 10/1999
 JP 2000091280 A 3/2000
 JP 2000-336344 A 12/2000
 JP 3160084 B2 4/2001
 JP 2001162541 A 6/2001
 JP 03194269 B2 7/2001
 JP 2001207160 A 7/2001

(56)

References Cited

FOREIGN PATENT DOCUMENTS

JP 2002-038131 A 2/2002
 JP 2003-049158 A 2/2003
 JP 2004-510873 A 4/2004
 JP 2004209624 A 7/2004
 JP 2006159402 A 6/2006
 JP 2006-192540 A 7/2006
 JP 2008194761 A 8/2008
 JP 5238725 B2 7/2013
 JP 5238726 B2 7/2013
 NL 171464 B 11/1982
 WO 1994002559 A1 2/1994
 WO 95/01241 A1 1/1995
 WO 95/03370 2/1995
 WO 95/18192 A1 7/1995
 WO 1995020469 A1 8/1995
 WO 96/27189 A1 9/1996
 WO 1997014536 A1 4/1997
 WO 1999006500 A1 2/1999
 WO 99/38817 A1 8/1999
 WO 1999038817 A1 8/1999
 WO 9954424 A1 10/1999
 WO 01/14494 A1 3/2001
 WO 2002097150 12/2002
 WO 03/087236 A1 10/2003
 WO 2005/080624 A1 9/2005
 WO 2006/027593 3/2006
 WO 2007/041538 A1 4/2007
 WO 2009085578 A2 7/2009
 WO 2010/077509 A1 7/2010
 WO 2010085587 A1 7/2010
 WO 2010/151201 12/2010
 WO 2011/068724 A2 6/2011
 WO 2011068714 A2 6/2011
 WO 2011087649 A2 7/2011
 WO 2011/109188 A2 9/2011
 WO 2011/139562 A2 11/2011
 WO 2011/149625 A2 12/2011
 WO 2012/018903 A2 2/2012
 WO 2012/061016 A1 5/2012
 WO 2012/061033 A2 5/2012
 WO 2012/092590 A2 7/2012
 WO 2012/092605 A2 7/2012
 WO 2012/112305 A2 8/2012
 WO 2012/112322 A2 8/2012
 WO 2012/141905 A2 10/2012
 WO 2013/003830 A2 1/2013
 WO 2013/003831 A2 1/2013
 WO 2013/009484 A2 1/2013
 WO 2013/036402 A1 3/2013
 WO 2013/045251 A1 4/2013
 WO 2013/049239 A1 4/2013
 WO 2013070576 A2 5/2013
 WO 2013/102170 A1 7/2013
 WO 2013/102176 A1 7/2013
 WO 2013/102177 A1 7/2013
 WO 2013/106597 A1 7/2013
 WO 2013/106602 A1 7/2013
 WO 2013/151745 A1 10/2013
 WO 2013/177446 A1 11/2013
 WO 2013/188038 A1 12/2013
 WO 2014/005120 A1 1/2014
 WO 2014/161001 A1 2/2014
 WO 2014020068 A1 2/2014
 WO 2014020075 A1 2/2014
 WO 2014022453 A1 2/2014
 WO 2014022462 A1 2/2014
 WO 2014022465 A1 2/2014
 WO 2014/057273 A1 4/2014
 WO 2014/062701 A1 4/2014
 WO 2014/070468 A1 5/2014
 WO 2014/106173 A1 7/2014
 WO 2014/106211 A1 7/2014
 WO 2014/124554 A1 8/2014
 WO 2014/137972 A1 9/2014
 WO 2014/140689 A1 9/2014

WO 2014/165390 A1 10/2014
 WO 2014/176108 A1 10/2014
 WO 2014/206739 A1 12/2014
 WO 2014/206890 A1 12/2014
 WO 2014/206967 A1 12/2014
 WO 2014/209567 A1 12/2014
 WO 2014/210160 A1 12/2014
 WO 2014/210442 A1 12/2014
 WO 2014/210532 A1 12/2014
 WO 2014/210568 A1 12/2014
 WO 2015/050781 A1 4/2015
 WO 2015/073346 A1 5/2015
 WO 2015/088953 A1 6/2015
 WO 2015/089527 A1 6/2015
 WO 2015/089528 A1 6/2015
 WO 2015/089529 A1 6/2015
 WO 2015/100018 A1 7/2015
 WO 2015/100020 A1 7/2015
 WO 2015/100220 A1 7/2015
 WO 2015/112379 A1 7/2015
 WO 2015/130487 A1 9/2015
 WO 2015/158009 A1 10/2015
 WO 2015/164211 A1 10/2015
 WO 2015/165122 A1 11/2015
 WO 2015/167910 A1 11/2015
 WO 2015/179335 A1 11/2015
 WO 2015/180005 A1 12/2015
 WO 2016/028683 A1 2/2016
 WO 2016/044158 A1 3/2016
 WO 2016/064726 A1 4/2016
 WO 2016/089675 A1 6/2016
 WO 2016/160357 A1 10/2016
 WO 2016/161157 A1 10/2016
 WO 2016/161170 A1 10/2016
 WO 2016/167967 A1 10/2016
 WO 2016/196795 A1 12/2016
 WO 2016/205133 A1 12/2016
 WO 2016/205267 A1 12/2016
 WO 2016/210057 A1 12/2016
 WO 2017/007703 A1 1/2017
 WO 2017/007714 A1 1/2017
 WO 2017/062482 A1 4/2017
 WO 2017/083249 A1 5/2017
 WO 2017/083255 A1 5/2017
 WO 2017/151498 A1 9/2017

OTHER PUBLICATIONS

“Investigation of Shaped Abrasive Particles vol. 1: Review of U.S. Pat. No. 6,054,093 Apr. 25, 2000” © Apr. 2011, 5 pages.
 Austin, Benson M., “Thick-Film Screen Printing,” Solid State Technology, Jun. 1969, pp. 53-58.
 Avril, Nicholas Joseph, “Manufacturing Glass-fiber Reinforcement for Grinding Wheels,” Massachusetts Institute of Technology, 1996, 105 pgs.
 Bacher, Rudolph J., “High Resolution Thick Film Printing,” E.I. du Pont de Nemours & Company, Inc., pp. 576-581, date unknown.
 Besse, John R., “Understanding and controlling wheel truing and dressing forces when rotary plunge dressing,” Cutting Tool Engineering, Jun. 2012, vol. 64, Issue 6, 5 pages.
 Brewer, L. et al., Journal of Materials Research, 1999, vol. 14, No. 10, pp. 3907-3912.
 Ciccotti, M. et al., “Complex dynamics in the peeling of an adhesive tape,” International Journal of Adhesion & Adhesives 24 (2004) pp. 143-151.
 Dupont, “Kevlar Aramid Pulp”, Copyright 2011, DuPont, 1 page.
 Wu, J. et al., Friction and Wear Properties of Kevlar Pulp Reinforced Epoxy.
 J. European Ceramic Society 31, Abstract only (2011) 2073-2081.
 Riemer, Dietrich E., “Analytical Engineering Model of the Screen Printing Process: Part II,” Solid State Technology, Sep. 1988, pp. 85-90.
 Miller, L.F., “Paste Transfer in the Screening Process,” Solid State Technology, Jun. 1969, pp. 46-52.
 Morgan, P. et al., “Ceramic Composites of Monazite and Alumina,” J. Am. Ceram. Soc., 78, 1995, 1553-63.

(56)

References Cited

OTHER PUBLICATIONS

Riemer, Dietrich E., "Analytical Engineering Model of the Screen Printing Process: Part I," *Solid State Technology*, Aug. 1988, pp. 107-111.

Winter Catalogue No. 5, Dressing tools, WINTER diamond tools for dressing grinding wheels, 140 pages.

Badger, Jeffrey, "Evaluation of Triangular, Engineered-Shape Ceramic Abrasive in Cutting Discs," *Supplement to the Welding Journal*, Apr. 2014, vol. 93, pp. 107-s to 115-s.

3M Cubitron II Abrasive Belts Brochure, *Shaping the Future*, Jan. 2011, 6 pages.

Vanstrum et al., *Precisely Shaped Grain (PSG): 3M's Innovation in Abrasive Grain Technology*, date unknown, 1 page.

Graf, "Cubitron II: Precision-Shaped Grain (PSG) Turns the Concept of Gear Grinding Upside Down," *gearsolutions.com*, May 2014, pp. 36-44.

Dow Machine Tool Accessories, *Grinding & Surface Finishing*, www.lmta.com, Nov. 2014, 72 pages.

* cited by examiner




FIG. 1A




FIG. 1B




FIG. 2

300




FIG. 3

400




FIG. 4




FIG. 5




FIG. 6A




FIG. 6B




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12A




FIG. 12B




FIG. 13A




FIG. 13B




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20A




FIG. 20B




FIG. 20C




FIG. 20D




FIG. 20E




FIG. 21




FIG. 22

SHAPED ABRASIVE PARTICLES AND METHOD OF FORMING SAME

CROSS-REFERENCE TO RELATED APPLICATION(S)

This application is a Continuation-in-Part to U.S. patent application Ser. No. 14/581,220, entitled "COMPOSITE SHAPED ABRASIVE PARTICLES AND METHOD OF FORMING SAME," by Frederic Josseaux, filed Dec. 23, 2014, and claims priority to U.S. Provisional Application No. 62/141,181 entitled "SHAPED ABRASIVE PARTICLES AND METHOD OF FORMING SAME," by Frederic Josseaux and David F. Louapre, filed Mar. 31, 2015, which are assigned to the current assignee hereof and incorporated herein by reference in entirety.

BACKGROUND

Field of the Disclosure

The following is directed to shaped abrasive particles, and more particularly, to composite shaped abrasive particles having certain features and methods of forming such composite shaped abrasive particles.

Description of the Related Art

Abrasive articles incorporating abrasive particles are useful for various material removal operations including grinding, finishing, polishing, and the like. Depending upon the type of abrasive material, such abrasive particles can be useful in shaping or grinding various materials in the manufacturing of goods. Certain types of abrasive particles have been formulated to date that have particular geometries, such as triangular shaped abrasive particles and abrasive articles incorporating such objects. See, for example, U.S. Pat. Nos. 5,201,916; 5,366,523; and 5,984,988.

Previously, three basic technologies that have been employed to produce abrasive particles having a specified shape, which are fusion, sintering, and chemical ceramic. In the fusion process, abrasive particles can be shaped by a chill roll, the face of which may or may not be engraved, a mold into which molten material is poured, or a heat sink material immersed in an aluminum oxide melt. See, for example, U.S. Pat. No. 3,377,660. In sintering processes, abrasive particles can be formed from refractory powders having a particle size of up to 10 micrometers in diameter. Binders can be added to the powders along with a lubricant and a suitable solvent to form a mixture that can be shaped into platelets or rods of various lengths and diameters. See, for example, U.S. Pat. No. 3,079,242. Chemical ceramic technology involves converting a colloidal dispersion or hydrosol (sometimes called a sol) to a gel or any other physical state that restrains the mobility of the components, drying, and firing to obtain a ceramic material. See, for example, U.S. Pat. Nos. 4,744,802 and 4,848,041. Other relevant disclosures on shaped abrasive particles and associated methods of forming and abrasive articles incorporating such particles are available at: <http://www.abel-ip.com/publications/>.

The industry continues to demand improved abrasive materials and abrasive articles.

SUMMARY

According to a first aspect, a method of forming an abrasive particle includes forming a mixture and attaching a

plurality of abrasive particles to at least one surface of the mixture and forming a shaped abrasive particle having a body and the plurality of abrasive particles bonded to at least one surface of the body.

5 In yet another aspect, an abrasive article includes a bond material and a first collection of abrasive particles coupled to the bond material, wherein each particle in the first collection comprises a shaped abrasive particle comprising a body and a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle.

10 In another aspect, an abrasive particle includes a shaped abrasive particle comprising a body; and a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle.

BRIEF DESCRIPTION OF THE FIGURES

The present disclosure may be better understood, and its numerous features and advantages made apparent to those skilled in the art by referencing the accompanying drawings.

20 FIG. 1A includes a portion of a system for forming shaped abrasive particles in accordance with an embodiment.

FIG. 1B includes a portion of the system of FIG. 1 according to an embodiment.

25 FIG. 2 includes a portion of an alternative system for forming shaped abrasive particles in accordance with an embodiment.

FIG. 3 includes an image of an abrasive particle according to an embodiment.

30 FIG. 4 includes a three-dimensional image of an abrasive particle according to an embodiment.

FIG. 5 includes a perspective view illustration of a shaped abrasive particle that may be form the base of an abrasive particle in accordance with an embodiment.

35 FIG. 6A includes a perspective view illustration of a shaped abrasive particle that may be used in accordance with an abrasive particle of an embodiment.

FIG. 6B includes a perspective view illustration of a non-shaped abrasive particle that may be used in accordance with an abrasive particle of an embodiment.

40 FIGS. 7A-7D include illustrations of shaped abrasive particles that may be used in accordance with an abrasive particle of an embodiment.

FIG. 8 includes a cross-sectional image of a shaped abrasive particle according to an embodiment.

FIG. 9 includes a top-down view of a shaped abrasive particle according to an embodiment.

FIG. 10 includes a cross-sectional illustration of a shaped abrasive particle according to an embodiment.

50 FIG. 11 includes cross-sectional image of a shaped abrasive particle according to an embodiment.

FIG. 12A includes a cross-sectional illustration of a coated abrasive article according to an embodiment.

55 FIG. 12B includes a perspective view illustration of a coated abrasive article including an abrasive particle according to an embodiment.

FIG. 13A includes an illustration of a bonded abrasive article according to an embodiment.

60 FIG. 13B includes an illustration of a bonded abrasive article including an abrasive particle according to an embodiment.

FIG. 14 includes an image of a conventional shaped abrasive particle.

65 FIG. 15 includes images of an abrasive particle according to an embodiment.

FIG. 16 includes images of an abrasive particle according to an embodiment.

FIG. 17 includes a plot of force per total area removed for a conventional sample and a representative sample.

FIG. 18 includes a plot of specific grinding energy versus cumulative material removed for three samples of coated abrasive articles.

FIG. 19 includes a plot of specific grinding energy versus cumulative material removed from the workpiece.

FIGS. 20A-20E include images of representative abrasive particles according to embodiments herein.

FIG. 21 includes a plot of force per total area removed from the workpiece according to the single grit grinding test for a conventional samples and representative samples according to embodiments.

FIG. 22 includes a plot of relative performance (% cut) for a conventional sample and representative samples according to embodiments herein.

DETAILED DESCRIPTION

The following is directed to methods of forming shaped abrasive particles, and more particularly composite shaped abrasive particles including shaped abrasive particles and a plurality of abrasive particles overlying at least one surface of the body of the shaped abrasive particle. The abrasive particles of the embodiments herein may be used in various abrasive articles, including for example bonded abrasive articles, coated abrasive articles, and the like. Alternatively, the shaped abrasive particle fractions of the embodiments herein may be utilized in free abrasive technologies, including for example grinding and/or polishing slurries.

The abrasive particles of the embodiments herein may be obtained through various processing methods, including but not limited to, printing, molding, pressing, stamping, casting, extruding, cutting, fracturing, heating, cooling, crystallizing, rolling, embossing, depositing, etching, scoring, drying, and a combination thereof. Particular methods of forming the shaped abrasive particles can include the formation of a mixture, such as a sol-gel, that can be shaped in an opening of a production tooling (e.g., a screen or mold), and formed into a precursor shaped abrasive particle. Screen printing methods of forming shaped abrasive particles are generally described in U.S. Pat. No. 8,753,558. A suitable method of forming shaped abrasive particles according to a conventional molding process is described in U.S. Pat. No. 5,201,916.

According to one particular embodiment, the process of forming the shaped abrasive particles can be a screen printing process. FIG. 1A includes an illustration of a system 150 for forming composite shaped abrasive particles in accordance with one, non-limiting embodiment. The process of forming composite shaped abrasive particles can be initiated by forming a mixture 101 including a ceramic material and a liquid. In particular, the mixture 101 can be a gel formed of a ceramic powder material and a liquid, wherein the gel can be characterized as a shape-stable material having the ability to substantially hold a given shape even in the green (i.e., unfired) state. In accordance with an embodiment, the gel can be formed of the ceramic powder material as an integrated network of discrete particles.

The mixture 101 may contain a certain content of solid material, liquid material, and additives such that it has suitable rheological characteristics for use with the process detailed herein. That is, in certain instances, the mixture can have a certain viscosity, and more particularly, suitable rheological characteristics that form a shape-stable phase of material that can be formed through the process as noted

herein. A dimensionally stable phase of material is a material that can be formed to have a particular shape and substantially maintain the shape for at least a portion of the processing subsequent to forming. In certain instances, the shape may be retained throughout subsequent processing, such that the shape initially provided in the forming process is present in the finally-formed object.

The mixture 101 can be formed to have a particular content of solid material, such as the ceramic powder material. For example, in one embodiment, the mixture 101 can have a solids content of at least about 25 wt %, such as at least about 35 wt %, or even at least about 38 wt % for the total weight of the mixture 101. Still, in at least one non-limiting embodiment, the solids content of the mixture 101 can be not greater than about 75 wt %, such as not greater than about 70 wt %, not greater than about 65 wt %, not greater than about 55 wt %, not greater than about 45 wt %, or not greater than about 42 wt %. It will be appreciated that the content of the solid material in the mixture 101 can be within a range between any of the minimum and maximum percentages noted above.

According to one embodiment, the ceramic powder material can include an oxide, a nitride, a carbide, a boride, an oxycarbide, an oxynitride, and a combination thereof. In particular instances, the ceramic material can include alumina. More specifically, the ceramic material may include a boehmite material, which may be a precursor of alpha alumina. The term "boehmite" is generally used herein to denote alumina hydrates including mineral boehmite, typically being $\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$ and having a water content on the order of 15%, as well as pseudoboehmite, having a water content higher than 15%, such as 20-38% by weight. It is noted that boehmite (including pseudoboehmite) has a particular and identifiable crystal structure, and therefore a unique X-ray diffraction pattern. As such, boehmite is distinguished from other aluminous materials including other hydrated aluminas such as ATH (aluminum trihydroxide), a common precursor material used herein for the fabrication of boehmite particulate materials.

Furthermore, the mixture 101 can be formed to have a particular content of liquid material. Some suitable liquids may include water. In more particular instances, the mixture 101 can have a liquid content of at least about 25 wt % for the total weight of the mixture 101. In other instances, the amount of liquid within the mixture 101 can be greater, such as at least about 35 wt %, at least about 45 wt %, at least about 50 wt %, or even at least about 58 wt %. Still, in at least one non-limiting embodiment, the liquid content of the mixture can be not greater than about 75 wt %, such as not greater than about 70 wt %, not greater than about 65 wt %, not greater than about 62 wt %, or even not greater than about 60 wt %. It will be appreciated that the content of the liquid in the mixture 101 can be within a range between any of the minimum and maximum percentages noted above.

Furthermore, to facilitate processing and forming shaped abrasive particles according to embodiments herein, the mixture 101 can have a particular storage modulus. For example, the mixture 101 can have a storage modulus of at least about 1×10^4 Pa, such as at least about 4×10^4 Pa, or even at least about 5×10^4 Pa. However, in at least one non-limiting embodiment, the mixture 101 may have a storage modulus of not greater than about 1×10^7 Pa, such as not greater than about 2×10^6 Pa. It will be appreciated that the storage modulus of the mixture 101 can be within a range between any of the minimum and maximum values noted above.

5

The storage modulus can be measured via a parallel plate system using ARES or AR-G2 rotational rheometers, with Peltier plate temperature control systems. For testing, the mixture **101** can be extruded within a gap between two plates that are set to be approximately 8 mm apart from each other. After extruding the gel into the gap, the distance between the two plates defining the gap is reduced to 2 mm until the mixture **101** completely fills the gap between the plates. After wiping away excess mixture, the gap is decreased by 0.1 mm and the test is initiated. The test is an oscillation strain sweep test conducted with instrument settings of a strain range between 0.01% to 100%, at 6.28 rad/s (1 Hz), using 25-mm parallel plate and recording 10 points per decade. Within 1 hour after the test completes, the gap is lowered again by 0.1 mm and the test is repeated. The test can be repeated at least 6 times. The first test may differ from the second and third tests. Only the results from the second and third tests for each specimen should be reported.

Furthermore, to facilitate processing and forming shaped abrasive particles according to embodiments herein, the mixture **101** can have a particular viscosity. For example, the mixture **101** can have a viscosity of at least about 4×10^3 Pa s, at least about 5×10^3 Pa s, at least about 6×10^3 Pa s, at least about 8×10^3 Pa s, at least about 10×10^3 Pa s, at least about 20×10^3 Pa s, at least about 30×10^3 Pa s, at least about 40×10^3 Pa s, at least about 50×10^3 Pa s, at least about 60×10^3 Pa s, or at least about 65×10^3 Pa s. In one non-limiting embodiment, the mixture **101** may have a viscosity of not greater than about 100×10^3 Pa s, such as not greater than about 95×10^3 Pa s, not greater than about 90×10^3 Pa s, or even not greater than about 85×10^3 Pa s. It will be appreciated that the viscosity of the mixture **101** can be within a range between any of the minimum and maximum values noted above. The viscosity can be measured in the same manner as the storage modulus as described above.

Moreover, the mixture **101** can be formed to have a particular content of organic materials including, for example, organic additives that can be distinct from the liquid to facilitate processing and formation of shaped abrasive particles according to the embodiments herein. Some suitable organic additives can include stabilizers, binders such as fructose, sucrose, lactose, glucose, UV curable resins, and the like.

Notably, the embodiments herein may utilize a mixture **101** that can be distinct from slurries used in conventional forming operations. For example, the content of organic materials within the mixture **101** and, in particular, any of the organic additives noted above, may be a minor amount as compared to other components within the mixture **101**. In at least one embodiment, the mixture **101** can be formed to have not greater than about 30 wt % organic material for the total weight of the mixture **101**. In other instances, the amount of organic materials may be less, such as not greater than about 15 wt %, not greater than about 10 wt %, or even not greater than about 5 wt %. Still, in at least one non-limiting embodiment, the amount of organic materials within the mixture **101** can be at least about 0.01 wt %, such as at least about 0.5 wt % for the total weight of the mixture **101**. It will be appreciated that the amount of organic materials in the mixture **101** can be within a range between any of the minimum and maximum values noted above.

Moreover, the mixture **101** can be formed to have a particular content of acid or base, distinct from the liquid content, to facilitate processing and formation of shaped abrasive particles according to the embodiments herein. Some suitable acids or bases can include nitric acid, sulfuric acid, citric acid, chloric acid, tartaric acid, phosphoric acid,

6

ammonium nitrate, and ammonium citrate. According to one particular embodiment in which a nitric acid additive is used, the mixture **101** can have a pH of less than about 5, and more particularly, can have a pH within a range between about 2 and about 4.

The system **150** of FIG. 1A, can include a die **103**. As illustrated, the mixture **101** can be provided within the interior of the die **103** and configured to be extruded through a die opening **105** positioned at one end of the die **103**. As further illustrated, extruding can include applying a force **180** (such as a pressure) on the mixture **101** to facilitate extruding the mixture **101** through the die opening **105**. During extrusion within an application zone **183**, a production tool or production tool **151** can be in direct contact with a portion of a belt **109**. The screen printing process can include extruding the mixture **101** from the die **103** through the die opening **105** in a direction **191**. In particular, the screen printing process may utilize the production tool **151** such that, upon extruding the mixture **101** through the die opening **105**, the mixture **101** can be forced into an opening **152** in the production tool **151**.

In accordance with an embodiment, a particular pressure may be utilized during extrusion. For example, the pressure can be at least about 10 kPa, such as at least about 500 kPa. Still, in at least one non-limiting embodiment, the pressure utilized during extrusion can be not greater than about 4 MPa. It will be appreciated that the pressure used to extrude the mixture **101** can be within a range between any of the minimum and maximum values noted above. In particular instances, the consistency of the pressure delivered by a piston **199** may facilitate improved processing and formation of shaped abrasive particles. Notably, controlled delivery of consistent pressure across the mixture **101** and across the width of the die **103** can facilitate improved processing control and improved dimensional characteristics of the shaped abrasive particles.

Referring briefly to FIG. 1B, a portion of the production tool (e.g., screen) **151** is illustrated. As shown, the production tool **151** can include the opening **152**, and more particularly, a plurality of openings **152** extending through the volume of the production tool **151**. In accordance with an embodiment, the openings **152** can have a two-dimensional shape as viewed in a plane defined by the length (l) and width (w) of the screen. The two-dimensional shape can include various shapes such as, for example, polygons, ellipsoids, numerals, Greek alphabet letters, Latin alphabet letters, Russian alphabet characters, complex shapes including a combination of polygonal shapes, and a combination thereof. In particular instances, the openings **152** may have two-dimensional polygonal shapes such as a triangle, a rectangle, a quadrilateral, a pentagon, a hexagon, a heptagon, an octagon, a nonagon, a decagon, and a combination thereof.

As further illustrated, the production tool **151** can have openings **152** that are oriented in a particular manner relative to each other. As illustrated and in accordance with one embodiment, each of the openings **152** can have substantially the same orientation relative to each other, and substantially the same orientation relative to the surface of the production tool **151**. For example, each of the openings **152** can have a first edge **154** defining a first plane **155** for a first row **156** of the openings **152** extending laterally across a lateral axis **158** of the production tool **151**. The first plane **155** can extend in a direction substantially orthogonal to a longitudinal axis **157** of the production tool **151**. However,

it will be appreciated, that in other instances, the openings **152** need not necessarily have the same orientation relative to each other.

Moreover, the first row **156** of openings **152** can be oriented relative to a direction of translation to facilitate particular processing and controlled formation of shaped abrasive particles. For example, the openings **152** can be arranged on the production tool **151** such that the first plane **155** of the first row **156** defines an angle relative to the direction of translation **171**. As illustrated, the first plane **155** can define an angle that is substantially orthogonal to the direction of translation **171**. Still, it will be appreciated that in one embodiment, the openings **152** can be arranged on the production tool **151** such that the first plane **155** of the first row **156** defines a different angle with respect to the direction of translation, including for example, an acute angle or an obtuse angle. Still, it will be appreciated that the openings **152** may not necessarily be arranged in rows. The openings **152** may be arranged in various particular ordered distributions with respect to each other on the production tool **151**, such as in the form of a two-dimensional pattern. Alternatively, the openings may be disposed in a random manner on the production tool **151**.

Referring again to FIG. 1A, after forcing the mixture **101** through the die opening **105** and a portion of the mixture **101** through the openings **152** in the production tool **151**, one or more precursor shaped abrasive particles **123** may be printed on the belt **109** disposed under the production tool **151**. According to a particular embodiment, the precursor shaped abrasive particles **123** can have a shape generally dictated by the shape of the openings **152** and the forming process. Notably, the mixture **101** can be forced through the production tool **151** in rapid fashion, such that the average residence time of the mixture **101** within the openings **152** can be less than about 2 minutes, less than about 1 minute, less than about 40 seconds, or even less than about 20 seconds. In particular non-limiting embodiments, the mixture **101** may be substantially unaltered during printing as it travels through the screen openings **152**, thus experiencing no change in the amount of components from the original mixture, and may experience no appreciable drying in the openings **152** of the production tool **151**. Still, in other instances, the mixture **101** may undergo some drying in the openings **152**, which may facilitate release of the mixture **101** from the openings **152** and may further facilitate formation of certain shape features of the shaped abrasive particles.

Additionally, the system **151** can include a bottom stage **198** within the application zone **183**. During the process of forming shaped abrasive particles, the belt **109** can travel over the bottom stage **198**, which can offer a suitable substrate for forming the mixture **101**.

During operation of the system **150**, the production tool **151** can be translated in a direction **153** while the belt **109** can be translated in a direction **110** substantially similar to the direction **153**, at least within the application zone **183**, to facilitate a continuous printing operation. As such, the precursor shaped abrasive particles **123** may be printed onto the belt **109** and translated along the belt **109** to undergo further processing. It will be appreciated that such further processing can include processes described in the embodiments herein, including for example, shaping, application of other materials (e.g., plurality of abrasive particles), drying, sintering, and the like.

In some embodiments, the belt **109** and/or the production tool **151** can be translated while extruding the mixture **101** through the die opening **105**. As illustrated in the system

100, the mixture **101** may be extruded in a direction **191**. The direction of translation **110** of the belt **109** and/or the production tool **151** can be angled relative to the direction of extrusion **191** of the mixture **101**. While the angle between the direction of translation **110** and the direction of extrusion **191** is illustrated as substantially orthogonal in the system **100**, other angles are contemplated, including for example, an acute angle or an obtuse angle.

The belt **109** and/or the production tool **151** may be translated at a particular rate to facilitate processing. For example, the belt **109** and/or the production tool **151** may be translated at a rate of at least about 3 cm/s. In other embodiments, the rate of translation of the belt **109** and/or the production tool **151** may be greater, such as at least about 4 cm/s, at least about 6 cm/s, at least about 8 cm/s, or even at least about 10 cm/s. Still, in at least one non-limiting embodiment, the belt **109** and/or the production tool **151** may be translated in a direction **110** at a rate of not greater than about 5 m/s, not greater than about 1 m/s, or even not greater than about 0.5 m/s. It will be appreciated that the belt **109** and/or the production tool **151** may be translated at a rate within a range between any of the minimum and maximum values noted above, and moreover, may be translated at substantially the same rate relative to each other. Furthermore, for certain processes according to embodiments herein, the rate of translation of the belt **109** as compared to the rate of extrusion of the mixture **101** in the direction **191** may be controlled to facilitate proper processing.

After the mixture **101** is extruded through the die opening **105**, the mixture **101** may be translated along the belt **109** under a knife edge **107** attached to a surface of the die **103**. The knife edge **107** may define a region at the front of the die **103** that facilitates displacement of the mixture **101** into the openings **152** of the production tool **151**.

Certain processing parameters may be controlled to facilitate formation of particular features of the precursor shaped abrasive particles **123** and the finally-formed shaped abrasive particles described herein. Some exemplary process parameters that can be controlled include a release distance **197**, a viscosity of the mixture, a storage modulus of the mixture, mechanical properties of the bottom stage, geometric or dimensional characteristics of the bottom stage, thickness of the production tool, rigidity of the production tool, a solid content of the mixture, a carrier content of the mixture, a release angle, a translation speed, a temperature, a content of release agent, a pressure exerted on the mixture, a speed of the belt, a drying rate, a drying time, a drying temperature, and a combination thereof.

According to one embodiment, one particular process parameter can include controlling the release distance **197** between a filling position and a release position. In particular, the release distance **197** can be a distance measured in a direction **110** of the translation of the belt **109** between the end of the die **103** and the initial point of separation between the production tool **151** and the belt **109**.

After extruding the mixture **101** into the openings **152** of the production tool **151**, the belt **109** and the production tool **151** may be translated to a release zone **185** where the belt **109** and the production tool **151** can be separated to facilitate the formation of the precursor shaped abrasive particles **123**. In accordance with an embodiment, the production tool **151** and the belt **109** may be separated from each other within the release zone **185** at a particular release angle.

Thereafter, the precursor shaped abrasive particles **123** may be translated through a series of optional zones wherein various treating processes may be conducted. Some suitable

exemplary treating processes can include drying, heating, curing, reacting, radiating, mixing, stirring, agitating, planarizing, calcining, sintering, comminuting, sieving, doping, impregnating, humidifying, application of other abrasive particles to the body of the precursor shaped abrasive particles and a combination thereof. According to one embodiment, the precursor shaped abrasive particles **123** may be translated through an optional shaping zone **113**, wherein at least one exterior surface of the particles may be shaped as described in embodiments herein. Furthermore, the precursor shaped abrasive particles **123** may be translated through an optional application zone **131**, wherein a material, such as a dopant material and/or a plurality of abrasive particles can be applied to at least one exterior surface of the precursor shaped abrasive particles **123** as described in embodiments herein.

After forming precursor shaped abrasive particles **123**, the particles may be translated through any post-forming zone **125**. Various processes may be conducted in the post-forming zone **125**, including treatment of the precursor shaped abrasive particles **123**. In one embodiment, the post-forming zone **125** can include a heating process where the precursor shaped abrasive particles **123** may be dried. Drying may include removal of a particular content of material, including volatiles, such as water. In accordance with an embodiment, the drying process can be conducted at a drying temperature of not greater than about 300° C., such as not greater than about 280° C., or even not greater than about 250° C. Still, in one non-limiting embodiment, the drying process may be conducted at a drying temperature of at least about 50° C. It will be appreciated that the drying temperature may be within a range between any of the minimum and maximum temperatures noted above. Furthermore, the precursor shaped abrasive particles **123** may be translated through the post-forming zone **125** at a particular rate, such as at least about 0.2 feet/min and not greater than about 8 feet/min.

Furthermore, the drying process may be conducted for a particular duration. For example, the drying process may be not greater than about 6 hours, such as not greater than about 5 hours, not greater than about 4 hours, not greater than about 2 hours, or even not greater than about 1 hour. Still, the drying process may be at least about 1 minute, such as at least about 15 minutes or at least about 30 minutes. It will be appreciated that the drying duration may be within a range between any of the minimum and maximum temperatures noted above. For example, in at least one embodiment, the precursor shaped abrasive particles can be dried for a duration of 1 to 10 minutes, which may facilitate intentional fracturing at a predetermined stress concentration point and along a predetermined stress concentration vector.

After the precursor shaped abrasive particles **123** are translated through the post-forming zone **125**, the precursor shaped abrasive particles **123** may be removed from the belt **109**. The precursor shaped abrasive particles **123** may be collected in a bin **127** for further processing.

In accordance with an embodiment, the process of forming shaped abrasive particles may further comprise a sintering process. For certain processes of embodiments herein, sintering can be conducted after collecting the precursor shaped abrasive particles **123** from the belt **109**. Alternatively, the sintering may be a process that is conducted while the precursor shaped abrasive particles **123** are on the belt **109**. Sintering of the precursor shaped abrasive particles **123** may be utilized to densify the particles, which are generally in a green state. In a particular instance, the sintering process can facilitate the formation of a high-temperature phase of

the ceramic material. For example, in one embodiment, the precursor shaped abrasive particles **123** may be sintered such that a high-temperature phase of alumina, such as alpha alumina, is formed. In one instance, a shaped abrasive particle can comprise at least about 90 wt % alpha alumina for the total weight of the particle. In other instances, the content of alpha alumina may be greater such that the shaped abrasive particle may consist essentially of alpha alumina.

In certain instances, another post forming process can include application of moisture to one or more surfaces of the gel mixture while it resides in the openings **152** or after formation of the precursor shaped abrasive particles **123** (i.e., after the mixture is removed from the openings of the production tool). Application of moisture may be referred to as humidification and may be conducted to facilitate the application of a plurality of particles to one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123**. In at least one embodiment, the application of moisture can include the deposition of moisture to one or more surface of the mixture while it resides in the openings **152** of the production tool **151** and/or to the precursor shaped abrasive particles **123**. In another instance, wherein applying moisture can include wetting the at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123** for a sufficient time to change a viscosity of an exterior region of the at least one surface relative to a viscosity at an interior region spaced apart from the exterior region. Moreover, it is noted that the application of moisture may facilitate gelation and sufficient bonding of the surface of the mixture **101** and/or precursor shaped abrasive particles **123** with a plurality of abrasive particles. According to one embodiment, the plurality of abrasive particles can be applied to the surface of the mixture **101** and/or precursor shaped abrasive particles **123** and the water on the surface can facilitate gelation of the material of the abrasive particles and moistened surface for improved bonding. Reference herein to the plurality of abrasive particles will include reference to various types of particles, including but not limited to, green or unsintered abrasive particles, sintered abrasive particles, and like.

The application of moisture can be selective, such that it is applied to at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123**, but may not necessarily be applied to another surface of the mixture **101** and/or precursor shaped abrasive particles **123**. In one embodiment, the application of moisture can be completed by deposition of the moisture, including for example, by spraying moisture onto one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123**. In one embodiment, the application of moisture can include translating the mixture and/or precursor shaped abrasive particles through an environment having a particular moisture content. The humidity and temperature within the environment and the rate at which the mixture and/or precursor shaped abrasive particles **123** are translated through the environment may be controlled to create the particular moisture on at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123**. For example, applying moisture to the at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123** can include directing a gas towards the one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123**. In more particular instances, the process of applying moisture can include directing water vapor and/or steam at the at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123**.

11

In still another embodiment, one or more devices having a particular moisture content may contact one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123** to facilitate the application of moisture. For example, a sponge or other object having a suitable moisture content can contact one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123**.

Still, in another embodiment, another post forming process can include changing the viscosity of the mixture **101** and/or precursor shaped abrasive particles **123**, to facilitate attachment of the plurality of abrasive particles to at least one surface. Changing the viscosity of the mixture can include deposition of a second material on the surface of the mixture **101** and/or precursor shaped abrasive particles **123** or using a process to alter the viscosity of the mixture **101** and/or precursor shaped abrasive particles **123** at an exterior region. For example, in certain instances, changing the viscosity can include application of a tacking material, such as an organic or inorganic adhesive material. One or more of such materials may be selectively deposited on one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123** to facilitate application of a plurality of abrasive particles to the surface.

In another embodiment, changing the viscosity can include application of one or more viscosity modifiers that may increase or decrease the viscosity of the mixture **101** and/or precursor shaped abrasive particles **123** at an exterior region compared to an interior region of the mixture **101** and/or precursor shaped abrasive particles **123** that is spaced apart from the exterior region and is not treated with the viscosity modifier. Such a change in viscosity may be suitable for attachment of the plurality of abrasive particles.

According to one embodiment, the process of forming the abrasive particles can include forming a mixture **101** and/or precursor shaped abrasive particle **123** and attaching a plurality of abrasive particles to at least one surface of the mixture **101** and/or at least one surface of the body of the precursor shaped abrasive particle **123**. In certain instances, the process of attaching can happen in the application zone **131**, wherein one or more application heads **132** can facilitate deposition of the plurality of abrasive particles onto the major exterior surfaces (e.g., the upper surfaces) of the precursor shaped abrasive particles **123**. Various suitable processes for attaching the plurality of abrasive particles can include deposition processes such as blasting, projecting, pressing, gravity coating, molding, stamping, and a combination thereof. Still, it will be appreciated, that the application may happen while the mixture **101** resides in the production tool **151**.

According to one embodiment, the process of attaching the plurality of abrasive particles can include forcibly projecting the plurality of abrasive particles toward at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123**. It will be appreciated that reference herein to attaching the plurality of abrasive particles to at least one surface can include attachment of the plurality of abrasive particles to a surface of the mixture **101** while the mixture is retained in the production tool **151** (e.g., mold or screen) or after the mixture **101** has been removed from the production tool **151** and the precursor shaped abrasive particles **123** have been formed. A portion or all of the mixture **101** and/or precursor shaped abrasive particles **123** can have the plurality of abrasive particles attached thereto. In at least one embodiment, forcibly projecting the plurality of abrasive particles onto the mixture **101** or precursor shaped abrasive particles **123** includes applying a controlled force to a deposition material including a carrier and the plurality of

12

abrasive particles and embedding at least a portion of the plurality of abrasive particles into the surface of the mixture **101** or precursor shaped abrasive particles **123**. For example, the deposition material can include a carrier, which may be a gas. Suitable gaseous materials may include water vapor, steam, an inert gas, air, or a combination thereof.

In at least one embodiment, the humidification of one or more surfaces of the mixture **101** and/or precursor shaped abrasive particles **123** and deposition of the abrasive particles may occur separately, and more specifically, the humidification process may happen before the deposition process. Still, in an alternative embodiment, the humidification process and deposition process may occur simultaneously as a mixture of water vapor and/or steam and the plurality of abrasive particles are directed to the at least one surface of the mixture **101** and/or precursor shaped abrasive particles **123**.

The force or pressure used to project the carrier gas and plurality of abrasive particles may be adjusted to facilitate suitable attachment of the abrasive particles to the surface of the mixture **101** and/or precursor shaped abrasive particles **123**. Notably, the force or pressure may be adapted based on one or more processing parameters, including but not limited to, the viscosity of the surface of the mixture **101** and/or precursor shaped abrasive particles **123**, the median particle size of the plurality of abrasive particles, the content (weight or volume) of the plurality of abrasive particles being projected per unit of time, the humidity of the environment during projecting, the temperature during projecting, the translation speed of the production tool or gel, the desired level of coverage by the plurality of abrasive particles, or a combination thereof.

In at least one embodiment, the process of attaching the plurality of abrasive particles to the bodies of the precursor shaped abrasive particles can occur prior to substantial drying of the body. Notably, in certain instances, some moisture in the precursor shaped abrasive particles may facilitate suitable attachment of the plurality of abrasive particles. According to one embodiment, the process of attachment can occur such that the moisture content (i.e., weight percent of liquid) of the precursor shaped abrasive particle during attachment can be not greater than about 70% different than the moisture content of the mixture **101** when it is placed in the production tool **151**. The percent difference can be calculated according to the formula $[(Mc1 - Mc2) / Mc1] \times 100\%$, where $Mc1$ is the moisture content of the mixture **101** during placement into the production tool **151** and $Mc2$ is the moisture content of the precursor shaped abrasive particle during attachment. In other instances, the moisture content of the precursor shaped abrasive particle during attachment can be not greater than about 60% different, such as not greater than about 50% different, not greater than about 40% different, not greater than about 30% different, not greater than about 20% different, or even not greater than about 10% different than the moisture content of the mixture **101** when it is placed into the production tool **151**. Still, in at least one non-limiting embodiment, the moisture content of the precursor shaped abrasive particle during attachment can be substantially the same or exactly the same as the moisture content of the mixture **101** when it is placed into the production tool **151**.

In at least one embodiment, the process of attaching the plurality of abrasive particles to the bodies of the precursor shaped abrasive particle can include humidifying the surface of the precursor shaped abrasive particle prior to attachment of the abrasive particles. For example, the moisture content at the surface of the precursor shaped abrasive particles can

be increased prior to the attachment process, such that the moisture content can be nearly the same as or higher than the moisture content of the mixture **101** when it is disposed in the production tool **151**.

According to another embodiment, the process of attaching the plurality of abrasive particles to the mixture **101** and/or body of the precursor shaped abrasive particles **123** can include deposition of the mixture **101** onto a layer of abrasive particles including the plurality of shaped abrasive particles. For example, the production tool can be prepared to have a layer of abrasive particles contained on a surface, onto which the mixture **101** is deposited and formed into a precursor shaped abrasive particle, such that the mixture **101** is deposited directly onto the plurality of abrasive particles. In such instances, the process of shaping the mixture **101** into the precursor shaped abrasive particles **123** and the attachment of the plurality of abrasive particles can be completed simultaneously. For example, the upper surface of the belt **109** can be prepared to contain a layer of abrasive particles and the mixture **101** can be extruded into the openings **152** of the production tool **151** and onto the layer of abrasive particles on the upper surface of the belt **109**. The production tool **151** can then be removed from the belt **109** and the precursor shaped abrasive particles **123** can have a plurality of abrasive particles attached to their bottom surface, which was in contact with the belt **109**. It will be appreciated that additional processes can be used to attach the plurality of abrasive particles to other surfaces, including a deposition process that attaches a plurality of abrasive particles to the upper surface of the mixture **101** and/or precursor shaped abrasive particles **123**. It is contemplated that one or more processes can be used to attach a plurality of abrasive particles to one or more surfaces of the mixture **101** and/or body of the precursor shaped abrasive particles **123**, including but not limited to the bottom surface, the upper surface, and side surfaces of the body of the precursor shaped abrasive particles **123**.

In yet another embodiment, the mixture **101** and/or body of the precursor shaped abrasive particles **123** can be placed into a production tool that is translated over a substrate, wherein a plurality of abrasive particles are overlying the surface of the substrate. The substrate can be stamped into the side of the production tool and the mixture **101** and/or precursor shaped abrasive particles **123**, such that the plurality of abrasive particles are deposited and at least partially embedded within the mixture **101** and/or precursor shaped abrasive particles **123**.

According to one embodiment, the plurality of abrasive particles can be applied or bonded to the at least one surface of the body of the mixture **101** and/or precursor shaped abrasive particles **123** as unsintered particles. That is, the plurality of abrasive particles can be a raw material, which is to undergo further processing with the mixture **101** and/or precursor shaped abrasive particle **123** to form a sintered abrasive particle on the surface of the body of the shaped abrasive particle. For example, the plurality of abrasive particles can include a raw material including at least one material of the group of an oxide, a nitride, a carbide, a boride, an oxycarbide, an oxynitride, or a combination thereof. In particular instances, the plurality of abrasive particles can include boehmite or pseudoboehmite material and as noted above. The boehmite or pseudoboehmite material may be processed in the same manner as the mixture, including the addition of seed material, pinning agents, other additives, and the like. In one particular embodiment, the

plurality of abrasive particles include the same material as contained in the mixture used to form the body of the shaped abrasive particle.

In one embodiment, the process can include drying the precursor shaped abrasive particles and plurality of abrasive particles after attaching the plurality of abrasive particles to the precursor shaped abrasive particles. Moreover, it will be appreciated that in certain instances, the process can include calcining the precursor shaped abrasive particle and plurality of abrasive particles after attaching the plurality of abrasive particles to the precursor shaped abrasive particles. Moreover, the process can include sintering the precursor shaped abrasive particle and plurality of abrasive particles after attaching the plurality of abrasive particles to the precursor shaped abrasive particles to form a composite shaped abrasive particle.

FIG. **2** includes an illustration of a portion of a system for use in forming shaped abrasive particles according to an embodiment. Notably, the system **150** of FIG. **2** includes some of the same components as the system **150** of FIG. **1A**, but does not include a belt **109** underlying the tool **151**. Notably, the tool **151** of FIG. **2** can be in the form of a screen, such as illustrated in FIG. **1A**, wherein the cavities **152** extend through the entire thickness of the tool **151**. Still, it will be appreciated that the tool **151** of FIG. **2** may be formed such that the cavities **152** extend for a portion of the entire thickness of the tool **151** and have a bottom surface, such that the volume of space configured to hold and shape the mixture **101** is defined by a bottom surface and side surfaces. All processes described herein in other embodiments may be utilized with the system illustrated in FIG. **2**, including but not limited to drying operations that may facilitate removal of the mixture **101** from the cavities **152** to form precursor shaped abrasive particles. That is, the mixture **101** may undergo some appreciable drying while contained in the cavities **152** of the tool **151**. Moreover, the process of attaching a plurality of abrasive particles to one or more surfaces of the mixture **101** while it resides in the cavities or after it has been removed from the cavities **152** (i.e., on the surfaces of the precursor shaped abrasive particles) may be utilized with the system **150** of FIG. **2**.

The system of FIG. **2** may include one or more components described in U.S. Pat. No. 9,200,187. For example, the system **150** can include a backing plate underlying and abutting the tool **151** during the extrusion of the mixture into the cavities **152** of the tool **151**. The backing plate may allow the cavities **152** to be filled with mixture **101**. The tool **151** can be translated over the backing plate such that the tool abuts the backing plate in the deposition zone when the mixture **101** is being deposited in the cavities **152**, and as the tool **151** is translated away from the deposition zone, the tool **151** is translated away from the backing plate.

The tool can be translated to an ejection zone, where at least one ejection assembly can be configured to direct an ejection material at the mixture **101** contained within the cavities **152** and eject the mixture **101** from the cavities to form precursor shaped abrasive particles. The ejection material may include an aerosol comprising a gas phase component, a liquid phase component, a solid phase component, and a combination thereof.

FIG. **3** includes an image of an abrasive particle according to an embodiment. The abrasive particle can be a composite shaped abrasive particle **300** including a shaped abrasive particle having a body **301** and a plurality of abrasive particles **302** attached to at least one surface **303**, such as a major surface of the body **301** of the shaped abrasive particle. As shown, the shaped abrasive particle can have a

triangular two-dimensional shape as viewed in a plane defined by a length (L) and a width (W) of the body **301**. However, it will be appreciated that the shaped abrasive particles can have other two dimensional shapes, including but not limited to polygons, ellipsoids, numerals, Greek

alphabet characters, Latin alphabet characters, Russian alphabet characters, complex shapes having a combination of polygonal shapes, and a combination thereof.

According to one embodiment, shaped abrasive particle can include a first major surface **303**, a second major surface (e.g., a bottom surface) opposite the first major surface, and a side surface extending between the first and second major surfaces. The plurality of abrasive particles **302** can be bonded to any surface of the body, including for example, the first major **303** of the body **301**. In other instances, the plurality of abrasive particles **302** can be bonded to at least two surfaces of the body. For example, the plurality of abrasive particles **302** can be bonded to at least two major surfaces of the body **301**, such as those surfaces having the greatest surface area compared to all surfaces of the body **301**, which in the particle of FIG. 3 can include the first and second major surfaces. In still other embodiments, the plurality of abrasive particles **302** can be bonded to at least two surfaces of the body **301**, which can include one or more side surfaces. For example, the plurality of abrasive particles **302** can be bonded to an upper surface and a side surface of the body **301**. Alternatively, the plurality of abrasive particles **302** can be bonded to a bottom surface and a side surface of the body **301**. It will be appreciated that in at least one embodiment, the plurality of abrasive particles **302** can be attached to all of the surfaces of the body **301** of the shaped abrasive particle. Still, certain embodiments may utilize selective placement of the abrasive particles, such that certain surfaces (e.g., one or more major surfaces of the body **301**) have a plurality of abrasive particles attached thereto, but one or more other surfaces (e.g., the side surfaces of the body **301**) may be essentially free of the plurality of abrasive particles. A surface that is essentially free of abrasive particles can include a small number of abrasive particles, which may be accidentally deposited or bonded to the surface, but lacks the full coverage of abrasive particles across the entire surface. For example, a surface may include not greater than 10 abrasive particles and be considered essentially free of abrasive particles. In still another instance, a surface can have no abrasive particles bonded to the surface and be essentially free of abrasive particles. Those abrasive particles including a shaped abrasive particle and a plurality of abrasive particles attached to one or more surfaces may be referred to as composite abrasive particles.

In certain instances, controlling the percent coverage of the plurality of abrasive particles on the body of the shaped abrasive particle may facilitate improved forming, deployment, and/or performance of the abrasive particle. For certain abrasive particles of the embodiments herein, the plurality of abrasive particles **302** can cover at least about 1% of the total surface area of the body **301** of the shaped abrasive particle. In other instances, the plurality of abrasive particles **302** covering the exterior surface of the body **301** of the shaped abrasive particle can be greater, such as at least about 5%, at least 10%, at least 20%, at least 30% at least 40% at least 50%, at least 60%, at least 70%, at least 80%, at least 90% at least 95% or even at least 99% of the total surface area of the body **301** of the shaped abrasive particle. Still, in at least one embodiment, the plurality of abrasive particles **302** can cover not greater than 99%, such as not greater than 95%, not greater than 90%, not greater than

85%, not greater than 80%, not greater than 70%, not greater than 60%, not greater than 50%, not greater than 40%, not greater than 30%, not greater than 20%, or even not greater than 10% of the total surface area of the body **301** of the shaped abrasive particle. It will be appreciated that the plurality of abrasive particles **302** can cover a percentage of the total surface area of the body **301** of the shaped abrasive particle within a range including any of the minimum and maximum percentages noted above.

For certain abrasive particles of the embodiments herein, the coverage of the plurality of particles on one surface of the body of the shaped abrasive particle may be controlled to facilitate improved forming, deployment, and/or performance of the abrasive particle. For example, the plurality of abrasive particles **302** can cover at least about 1% of the total surface area of an exterior surface (e.g., first major surface, second major surface, side surface, etc.) of the body of the shaped abrasive particle. In other instances, the percent coverage of the plurality of abrasive particles on a given surface of the body of the shaped abrasive particle can be greater, such as at least about 5%, at least 10%, at least 20%, at least 30% at least 40% at least 50%, at least 60%, at least 70%, at least 80%, at least 90% or even at least 95% or even at least 99% or even 100% of the total surface area of the body **301** of the shaped abrasive particle. Still, in at least one embodiment, the plurality of abrasive particles **302** can cover not greater than 100% such as not greater than 99% or not greater than 95%, not greater than 90%, not greater than 85%, not greater than 80%, not greater than 70%, not greater than 60%, not greater than 50%, not greater than 40%, not greater than 30%, not greater than 20%, or even not greater than 10% of the total surface area of the body **301** of the shaped abrasive particle. It will be appreciated that the plurality of abrasive particles **302** can cover a percentage of the total surface area of the body **301** of the shaped abrasive particle within a range including any of the minimum and maximum percentages noted above. For example, the plurality of abrasive particles can cover at least 1% and not greater than 99% of the total surface area of the first major surface. In yet another embodiment, the plurality of abrasive particles can cover at least 30% and not greater than 99% of the total surface area of the first major surface. In still another embodiment, the plurality of abrasive particles can cover at least 40% and not greater than 99% of the total surface area of the first major surface. According to another aspect, the plurality of abrasive particles can cover at least 80% and not greater than 99% of the total surface area of the first major surface.

For certain abrasive particles of the embodiments herein, the coverage of the plurality of particles on one surface of the body of the shaped abrasive particle may be controlled to facilitate improved forming, deployment, and/or performance of the abrasive particle. For example, in one embodiment, the abrasive particle may include at least 10 particles of the plurality of abrasive particles on a major surface of the body of the shaped abrasive particle. In still other instances, the number of particles of the plurality of abrasive particles on a first major surface of the body can be greater, such as at least 12 or at least 15 or at least 18 or at least 20 or at least 22 or at least 25 or at least 27 or at least 30. Still, depending upon the forming conditions, the average number of particles on a first major surface of the body can be not greater than 500, such as not greater than 400 or not greater than 300 or not greater than 200 or not greater than 100 or not greater than 80 or not greater than 60 or not greater than 50. It will be appreciated that the average number of abrasive particles on the first major surface of the body of the shaped abrasive

particle can be within a range including any of the minimum and maximum values noted above. For example, the average number of abrasive particles can be at least 10 and not greater than 500, such as at least 10 and not greater than 200 or at least 15 and not greater than 200 or at least 20 and not greater than 100. Furthermore, it will be appreciated that such average numbers may be true for any other surfaces of the body of the shaped abrasive particle.

According to one embodiment, the plurality of abrasive particles **302** can account for at least 1 wt % of a total weight of the abrasive particle **300**, such as at least 2 wt %, at least 3 wt %, at least 4 wt %, at least 5 wt %, at least 6 wt %, at least 7 wt %, at least 8 wt %, at least 9 wt %, at least 10 wt %, at least about 20 wt %, at least about 30 wt %, at least about 40 wt %, or even at least about 50 wt %. Still, in a non-limiting embodiment, the plurality of abrasive particles **302** can be not greater than about 80 wt %, such as not greater than about 60 wt %, not greater than about 40 wt %, not greater than about 30 wt %, or even not greater than about 20 wt %, not greater than 10 wt %, not greater than 8 wt %, not greater than 6 wt %, not greater than 5 wt, or not greater than 4 wt % or even not greater than 3 wt % of a total weight of the abrasive particle **300**. It will be appreciated that the plurality of abrasive particles **302** can account for a particular weight percent of the total weight of the abrasive particle within a range including any of the minimum and maximum percentages noted above. It will also be appreciated that such percentages can represent an average value calculated for a plurality of abrasive particles, wherein each of the abrasive particles include a shaped abrasive particle having a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle. Such average values are calculated from a random and statistically relevant sample size of abrasive particles.

The weight percent of the plurality of abrasive particles can be calculated by obtaining a first sample of the particles including a minimum of 300 mg of the abrasive particles having the plurality of abrasive particles bonded to at least one surface. The mass (**M1**) of the particles is measured. The particles are spread on a flat surface providing suitable contrast to accurately count the number of particles (**N**). A camera is used to take a picture of the particles and using suitable imaging software, (e.g., imageJ), the number of coated particles (**N1**) is counted. The average mass per grit (**Mg1**) of the grains with the plurality of abrasive particles is calculated according to the formula $Mg1=M1/N1$. The same process is conducted for a sample of particles without the plurality of abrasive particles (i.e., bare abrasive particles). The average mass per grit (**Mg2**) is calculated for the bare sample. The average weight percentage of the plurality of abrasive particles is then calculated according to the formula $100 \times [(Mg2-Mg1)/Mg1]$.

The plurality of abrasive particles **302** may be selected from a particular type of material to facilitate suitable formation of the composite shaped abrasive particles. For example, the plurality of abrasive particles **302** can include a material from the group of oxides, carbides, nitrides, borides, oxycarbides, oxynitrides, oxyborides, natural minerals, synthetic materials, carbon-based materials, and a combination thereof. In one particular embodiment, the plurality of abrasive particles can include alumina, and more particularly can consist essentially of alpha alumina.

For at least one embodiment, the plurality of abrasive particles **302** can include a material having a particular coefficient of thermal expansion (CTE) relative to the CTE of the body **301** that can facilitate improved forming, deployment, and/or performance of the abrasive particle. For

example the plurality of abrasive particles **302** can have a CTE that is not greater than about 50% different than a CTE of the body **301** of the shaped abrasive particle according to the formula $[(CTE1-CTE2)/CTE1] \times 100\%$, where CTE1 represents the higher CTE value relative to CTE2. In certain instances, the plurality of abrasive particles **302** can have a CTE that is less than the CTE of the body **301**. In another embodiment, the plurality of abrasive particles **302** can have a CTE that is greater than the CTE of the body **301**. Still, the plurality of abrasive particles **302** can have a CTE that is not greater than about 40% different, not greater than about 30% different, not greater than about 20% different, or even not greater than about 10% different compared to the CTE of the body **301**. Still, in one non-limiting embodiment, the CTE of the plurality of abrasive particles **302** may be essentially the same as the CTE of the body **301**. In yet another embodiment, the CTE of the plurality of abrasive particles **302** can be at least about 0.5% different, at least about 1% different, or at least about 3% different compared to the CTE of the body **301**. It will be appreciated that the plurality of abrasive particles can have a difference in CTE relative to the CTE of the body that is within a range including any of the minimum and maximum values noted above. The CTE of the body of the shaped abrasive particle and the plurality of abrasive particles may be measured in the finally-formed abrasive particle after sintering.

According to an embodiment, the plurality of abrasive particles **302** are selected from the group consisting of crushed grains, irregularly shaped grains, elongated gains, agglomerates, aggregates, fine shaped abrasive particles, flakes, and a combination thereof. In one particular instance, the plurality of abrasive particles consists essentially of crush grains, which may have a generally irregular shape. Flakes may be elongated or non-elongated grains that have a very small thickness relative to the width and length of the particle.

Shaped abrasive particles may be formed through particular processes, including molding, printing, casting, extrusion, and the like as described herein. And will be described further herein. In at least one embodiment, at least a portion of the plurality of abrasive particles **302** may include shaped abrasive particles of a significantly finer size compared to the body **301** of the shaped abrasive particle **301**. The shaped abrasive particles included in the plurality of abrasive particles **302** overlying the body **301** of the shaped abrasive particle can have any of the attributes of the shaped abrasive particles defined in the embodiments herein.

The body **301** of the shaped abrasive particle can have a length (**L**), a width (**W**) and a height (**H**), wherein $L \geq W \geq H$. The length may define the longest dimension of the body **301**, and in some instances may be equal to the dimension defining the width. In one embodiment, the width can generally define the second longest dimension of the body **301**, but in certain instances, the width can have the same value as the length. The height may generally define the shortest dimension of the body and may extend in a direction perpendicular to the plane defined by the length and width of the body **301**. According to one particular embodiment, the width can be greater than or equal to the height.

In accordance with an embodiment, the body **301** of the shaped abrasive particle can have an average particle size, as measured by the largest dimension measurable on the body **301** (i.e., the length), of at least about 100 microns. In fact, the body **301** of the shaped abrasive particle can have an average particle size of at least about 150 microns, such as at least about 200 microns, at least about 300 microns, at least about 400 microns, at least about 500 microns, at least

about 500 microns, at least about 600 microns, at least about 800 microns, or even at least about 900 microns. Still, the abrasive particle can have an average particle size that is not greater than about 5 mm, such as not greater than about 3 mm, not greater than about 2 mm, or even not greater than about 1.5 mm. It will be appreciated that the abrasive particle can have an average particle size within a range including any of the minimum and maximum values noted above.

The abrasive grains (i.e., crystallites) contained within the body of the shaped abrasive particles or the plurality of abrasive particles may have an average grain size that is generally not greater than about 100 microns. In other embodiments, the average grain size can be less, such as not greater than about 80 microns, not greater than about 50 microns, not greater than about 30 microns, not greater than about 20 microns, not greater than about 10 microns, not greater than about 1 micron, not greater than about 0.9 microns, not greater than about 0.8 microns, not greater than about 0.7 microns, or even not greater than about 0.6 microns. Still, the average grain size of the abrasive grains contained within the body of the abrasive particles can be at least about 0.01 microns, such as at least about 0.05 microns, at least about 0.06 microns, at least about 0.07 microns, at least about 0.08 microns, at least about 0.09 microns, at least about 0.1 microns, at least about 0.12 microns, at least about 0.15 microns, at least about 0.17 microns, at least about 0.2 microns, or even at least about 0.5 microns. It will be appreciated that the abrasive grains can have an average grain size within a range between any of the minimum and maximum values noted above.

The plurality of abrasive particles **302** may have a particular median particle size relative to one or more dimensions of the body **301** of the shaped abrasive particle. For example, the plurality of abrasive particles **302** can have a median particle size (D50) that can be not greater than the length (L) of the body **301** of the shaped abrasive particle. More particularly, the plurality of abrasive particles **302** can have a median particle size (D50) that is not greater than about 90% of the length (L), such as not greater than about 80% of the length, not greater than about 70% of the length, not greater than about 60% of the length, not greater than about 50% of the length, not greater than about 40% of the length, not greater than about 30% of the length, not greater than about 25% of the length, not greater than about 20% of the length, not greater than about 18% of the length, not greater than about 15% of the length, not greater than about 12% of the length, not greater than about 10% of the length, not greater than about 8% of the length, not greater than about 6% of the length, or even not greater than about 5% of the length of the body **301**. Still, in another non-limiting embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least about 0.1% of the length (L), such as at least about 0.5% of the length, at least about 1% of the length, or even at least about 2% of the length, at least about 3% of the length, at least about 4% of the length, at least about 5% of the length, at least about 6% of the length, at least about 7% of the length, at least about 8% of the length, at least about 9% of the length, at least about 10% of the length, at least about 12% of the length, at least about 15% of the length, at least about 18% of the length, at least about 20% of the length, at least about 25% of the length, or even at least about 30% of the length of the body **301**. It will be appreciated that the plurality of abrasive particles **302** can have a median particle size (D50) that is within a range including any of the minimum and maximum percentages noted above.

According to one particular embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least 0.1% and not greater than about 90% of the length (L) of the body of the shaped abrasive particle, which can be calculated by $[(D50)/(L)] \times 100\%$. In another embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) of at least 0.1% and not greater than about 50% of the length of the body, such as at least 0.1% and not greater than about 20% or at least 0.1% and not greater than about 10% or at least 0.1% and not greater than about 8% or at least 0.1% and not greater than about 6%, or at least 0.1% and not greater than about 5% or even at least 1% and not greater than 5% of the length of the body of the shaped abrasive particle. Moreover, it has been noted in certain instances, that the relative median particle size (D50) of the plurality of abrasive particles **302** compared to the length of the body may impact the percent coverage of the abrasive particles on the body.

In another embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is not greater than about 90% of the width (W), such as not greater than about 80% of the width, not greater than about 70% of the width, not greater than about 60% of the width, not greater than about 50% of the width, not greater than about 40% of the width, not greater than about 30% of the width, not greater than about 25% of the width, not greater than about 20% of the width, not greater than about 18% of the width, not greater than about 15% of the width, not greater than about 12% of the width, not greater than about 10% of the width, not greater than 8% of the width, not greater than 6% of the width, or even not greater than 5% of the width of the body **301**. Still, in another non-limiting embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least about 0.1% of the width (W), such as at least about 0.5% of the width, at least about 1% of the width, at least about 2% of the width, at least about 3% of the width, at least about 4% of the width, at least about 5% of the width, at least about 6% of the width, at least about 7% of the width, at least about 8% of the width, at least about 9% of the width, at least about 10% of the width, at least about 12% of the width, at least about 15% of the width, at least about 18% of the width, at least about 20% of the width, at least about 25% of the width, at least about 30% of the width of the body **301**. It will be appreciated that the plurality of abrasive particles **302** can have a median particle size (D50) that is within a range including any of the minimum and maximum percentages noted above.

According to one particular embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least 0.1% and not greater than about 90% of the width of the body of the shaped abrasive particle, which can be calculated by $[(D50)/(W)] \times 100$. In another embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) of at least 0.1% and not greater than about 50% of the width of the body, such as at least 0.1% and not greater than about 20% or at least 0.1% and not greater than about 10% or at least 0.1% and not greater than about 8% or at least 0.1% and not greater than about 6%, or at least 1% and not greater than about 6% or even at least 1% and not greater than 4% of the width of the body of the shaped abrasive particle. Moreover, it has been noted in certain instances, that the relative median particle size (D50) of the plurality of abrasive particles **302** compared to the width of the body may impact the percent coverage of the abrasive particles on the body.

In another embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is not greater

than about 90% of the height, such as not greater than about 80% of the height, not greater than about 70% of the height, not greater than about 60% of the height, not greater than about 50% of the height, not greater than about 40% of the height, not greater than about 30% of the height, not greater than about 25% of the height, not greater than about 20% of the height, not greater than about 18% of the height, not greater than about 15% of the height, not greater than about 12%, the height, not greater than about 10% of the height, not greater than about 8% of the height, not greater than about 6% of the height, not greater than about 5% of the height of the body **301**. Still, in another non-limiting embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least about 0.1% of the height, such as at least about 0.5% of the height, at least about 1% of the height, at least about 2% of the height, at least about 3% of the height, at least about 4% of the height, at least about 5% of the height, at least about 6% of the height, at least about 7% of the height, at least about 8% of the height, at least about 9% of the height, at least about 10% of the height, at least about 12% of the height, at least about 15% of the height, at least about 18% of the height, at least about 20% of the height, at least about 25% of the height, at least about 30% of the height of the body **301**. It will be appreciated that the plurality of abrasive particles **302** can have a median particle size (D50) that is within a range including any of the minimum and maximum percentages noted above.

According to one particular embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) that is at least 0.1% and not greater than about 90% of the height of the body of the shaped abrasive particle, which can be calculated by $[(D50)/(H)] \times 100$. In another embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) of at least 0.1% and not greater than about 50% of the height of the body, such as at least 0.1% and not greater than about 20% or at least 1% and not greater than about 18% or at least 5% and not greater than about 18% or at least 8% and not greater than about 16% of the height of the body of the shaped abrasive particle. Moreover, it has been noted in certain instances, that the relative median particle size (D50) of the plurality of abrasive particles **302** compared to the height of the body may impact the percent coverage of the abrasive particles on the body.

In accordance with an embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) of not greater than about 1 mm, such as not greater than about 800 microns, not greater than about 500 microns or not greater than 300 microns or not greater than 200 microns or not greater than 100 microns or not greater than 90 microns or not greater than 80 microns or not greater than 70 microns or not greater than 65 microns or not greater than 60 microns or not greater than 50 microns or even not greater than 40 microns. Still, in one non-limiting embodiment, the plurality of abrasive particles **302** can have a median particle size (D50) of at least about 0.1 microns, such as at least about 0.5 microns or at least 1 micron or at least 2 microns or at least 3 microns or at least 5 microns or at least 10 microns or at least 15 microns or at least 20 microns or at least 25 microns or at least 30 microns. It will be appreciated that the abrasive particle can have a median particle size within a range including any of the minimum and maximum values noted above. For example, the plurality of abrasive particles can have a median particle size (D50) of at least 0.1 microns and not greater than 500 microns or at least 0.5 microns and not greater than 100 microns or at least 1 micron and not greater than 65 microns. It has been noted in certain instances, that

the median particle size (D50) of the plurality of abrasive particles **302** may impact the formation, deployment, and/or performance of the abrasive particles.

For at least one embodiment, at least a portion of the abrasive particles of the plurality of abrasive particles can be at least partially embedded in at least one surface the body **301** of the shaped abrasive particle. Moreover, in certain instances, the portion can include a majority of the abrasive particles of the plurality of abrasive particles **302** that can be at least partially embedded in at least one surface of the body **301** of the shaped abrasive particle. According to another embodiment, the portion of the plurality of abrasive particles can be a minority of the particles of the plurality of abrasive particles that are at least partially embedded within at least one surface of the body **301**. It will be appreciated that embedded particles can extend into the volume of the body below an exterior surface of the body **301**, as opposed to particles that are overlying the surface of the body **301**, but may not be embedded and extending into the volume of the body **301** (e.g., particles that are applied as a certain type of coating). Moreover, the feature of the embedded abrasive particles is distinct from patterned surface features, such as grooves or rounded protrusions, wherein the abrasive particles are embedded into the volume of the body of the shaped abrasive particle, and the plurality of abrasive particles have sharp and irregular corners (e.g., in the context of crushed and irregular shaped abrasive particles) protruding from the surface. Without wishing to be tied to a particular theory, it is thought that the sharp and irregular surfaces of the plurality of abrasive particles, as well as the random distribution of the abrasive particles on the surface of the shaped abrasive particle may impact the self-sharpening behavior of the composite abrasive particle, and thus may improve the performance of the abrasive particle and associated abrasive article. The plurality of abrasive particles may also facilitate improved retention of the abrasive particles in certain bond matrix materials, including for example in the bonding layers of a coated abrasive or within the three-dimensional volume of a bond material within a bonded abrasive article.

According to one embodiment, at least one of the abrasive particles of the plurality of abrasive particles can be attached to a surface of the body of the shaped abrasive particle and define an acute contact angle. Notably, the provision of the plurality of abrasive particles according to the processes herein can facilitate the attachment of one or more of the abrasive particles of the plurality abrasive particles to the body in a manner that defines an acute angle. A random sample of abrasive particles can be obtained. Each abrasive particle may be sectioned or ground transverse to the longitudinal axis through the middle half of the body. To obtain a suitable view of the cross-section, such as illustrated in FIG. 10, wherein the body of the shaped abrasive particle **1001** is clearly shown and the plurality of abrasive particles **1002** attached to at least one major surface **1004** are also visible. Each of the abrasive particles can be mounted in an epoxy resin, which is cured and solidified. After mounting each of the abrasive particles in the epoxy resin, a wafer slicing saw can be used to cut out each of the abrasive particles and a portion of the epoxy surrounding each of the abrasive particles, such that discrete samples are formed and include a whole abrasive particle surrounded by a mass of epoxy. Each sample is then polished to remove a portion of the grain and expose the transverse plane used to evaluate the contact area of the grains that exposed. The transverse plane should be smooth such that the perimeter of the

resulting cross-sectional is well defined. If necessary, the resulting cross-sectional plane can be polished to a uniform height.

After completing the foregoing preparation of the samples, each abrasive particle can be mounted and viewed by an optical microscope (e.g., Olympus DSX500) at 10× magnification with a field of view of 2 mm. Using the optical microscope, an image of the cross-section of each abrasive particle is obtained, such as provided in FIG. 11. Using a suitable imaging program, such as ImageJ (available from the National Institute of Health), the contact angle created by abutting surfaces of the abrasive particles and the surface of the body are measured.

Referring to FIG. 11, the abrasive particle 1101 can form a contact angle 1102 with the major surface 1103 of the body 1104. Notably, at least a portion of the abrasive particles create a contact angle with the body that is less than 90 degrees. For example, the abrasive particle contact angle can be less than 88 degrees, such as less than 85 degrees or less than 80 degrees or less than 75 degrees or less than 70 degrees or less than 65 degrees or less than 60 degrees or less than 55 degrees or less than 50 degrees or less than 45 degrees or less than 40 degrees or less than 35 degrees or less than 30 degrees or less than 25 degrees or less than 20 degrees or less than 15 degrees or less than 10 degrees or less than 5 degrees. In yet another embodiment, the abrasive particle contact angle can be at least 1 degree or at least 5 degrees or at least 10 degrees or at least 15 degrees or at least 20 degrees or at least 25 degrees or at least 30 degrees or at least 35 degrees or at least 40 degrees. It will be appreciated that the abrasive particle contact angle can be within a range including any of the minimum and maximum values noted above.

In another embodiment, at least a portion of the plurality of abrasive particles 302 can be bonded directly to at least one surface of the body 301 of the shaped abrasive particle. More particularly, at least a portion of the plurality of abrasive particles 302 can be sinter-bonded to at least one surface of the body 301 of the shaped abrasive particle. In at least one embodiment, all of the abrasive particles of the plurality of abrasive particles 302 can be sinter-bonded to at least one surface of the body 301 of the shaped abrasive particle.

FIG. 4 includes a three-dimensional image of an upper surface of an abrasive particle according to an embodiment. As illustrated, the abrasive particle 400 includes a body 401 having an upper surface 402 with a plurality of abrasive particles attached thereto. As illustrated in the three-dimensional mapping image, the plurality of abrasive particles creates an upper surface having a rough contour with a plurality of randomly arranged peaks and valleys. Such a rough contour may facilitate improved bonding of the abrasive particle in various fixed abrasive articles relative to shaped abrasive particles with smooth surfaces. Moreover, the rough and varied contour of the upper surface 402 may facilitate improved abrasive performance in various fixed abrasives, as a greater number of sharp abrasive surfaces are present as compared to a conventional, smooth surfaced shaped abrasive particle. In certain instances, the existence of the rough contour may limit the need to deploy the abrasive particle in a particular orientation, which is generally the desired approach for conventional shaped abrasive particles, particularly in coated abrasive articles. Still, in other embodiments, it may be advantageous to deploy the abrasive particles in a particular orientation in a fixed abrasive, wherein the one or more surfaces including the

plurality of abrasive particles have a controlled orientation relative to one or more references axes within the fixed abrasive article.

According to one embodiment, the plurality of abrasive particles can be attached to the first major surface and the first major surface can have a surface roughness greater than a surface roughness of another surface (e.g., a side surface) of the body that has fewer abrasive particles attached thereto. In one particular embodiment, the first major surface can include a plurality of abrasive particles bonded thereto and the body can be essentially free of any abrasive particles bonded to the side surface, and in such instances, the surface roughness of the first major surface can be significantly greater than the side surface. Surface roughness can be measured using any suitable techniques, including for example optical metrology techniques. In yet another embodiment, the first major surface can include a plurality of abrasive particles bonded thereto and the body can be essentially free of any abrasive particles bonded to the second major surface, and in such instances, the surface roughness of the first major surface can be significantly greater than the second major surface.

FIG. 5 includes a perspective view illustration of a shaped abrasive particle in accordance with an embodiment. The shaped abrasive particle 500 can include a body 501 including a major surface 502, a major surface 503, and a side surface 504 extending between the major surfaces 502 and 503. As illustrated in FIG. 5, the body 501 of the shaped abrasive particle 500 is a thin-shaped body, wherein the major surfaces 502 and 503 are larger than the side surface 504. Moreover, the body 501 can include an axis 510 extending from a point to a base and through the midpoint 550 on the major surface 502. The axis 510 can define the longest dimension of the major surface extending through the midpoint 550 of the major surface 502, which may be the length or width of the body depending on the geometry, but in the illustrated embodiment of FIG. 5 defines the width. The body 501 can further include an axis 511 defining a dimension of the body 501 extending generally perpendicular to the axis 510 on the same major surface 502, which in the illustrated embodiment of an equilateral triangle defines the length of the body 501. Finally, as illustrated, the body 501 can include a vertical-axis 512, which in the context of thin shaped bodies can define a height (or thickness) of the body 501. For thin-shaped bodies, the length of the axis 510 is equal to or greater than the vertical axis 512. As illustrated, the height 512 can extend along the side surface 504 between the major surfaces 502 and 503 and perpendicular to the plane defined by the axes 510 and 511. It will be appreciated that reference herein to length, width, and height of the abrasive particles may be referenced to average values taken from a suitable sampling size of abrasive particles of a batch of abrasive particles.

The shaped abrasive particles can include any of the features of the abrasive particles of the embodiments herein. For example, the shaped abrasive particles can include a crystalline material, and more particularly, a polycrystalline material. Notably, the polycrystalline material can include abrasive grains. In one embodiment, the body of the abrasive particle, including for example, the body of a shaped abrasive particle can be essentially free of an organic material, including for example, a binder. In at least one embodiment, the abrasive particles can consist essentially of a polycrystalline material.

Some suitable materials for use as abrasive particles can include nitrides, oxides, carbides, borides, oxynitrides, oxyborides, diamond, carbon-containing materials, and a com-

bination thereof. In particular instances, the abrasive particles can include an oxide compound or complex, such as aluminum oxide, zirconium oxide, titanium oxide, yttrium oxide, chromium oxide, strontium oxide, silicon oxide, magnesium oxide, rare-earth oxides, and a combination thereof. In one particular embodiment, the abrasive particles can include at least 95 wt % alumina for the total weight of the body. In at least one embodiment, the abrasive particles can consist essentially of alumina. Still, in certain instances, the abrasive particles can include not greater than 99.5 wt % alumina for the total weight of the body. Moreover, in particular instances, the shaped abrasive particles can be formed from a seeded sol-gel. In at least one embodiment, the abrasive particles of the embodiments herein may be essentially free of iron, rare-earth oxides, and a combination thereof.

In accordance with certain embodiments, certain abrasive particles can be compositional composite articles including at least two different types of grains within the body of the shaped abrasive particle or within the body of the abrasive particles of the plurality of abrasive particles. It will be appreciated that different types of grains are grains having different compositions with regard to each other. For example, the body of the shaped abrasive particle can be formed such that it includes at least two different types of grains, wherein the two different types of grains can be nitrides, oxides, carbides, borides, oxynitrides, oxyborides, carbon-based materials, diamond, naturally occurring minerals, rare-earth-containing materials, and a combination thereof.

FIG. 5 includes an illustration of a shaped abrasive particle having a two-dimensional shape as defined by the plane of the upper major surface 502 or major surface 503, which has a generally triangular two-dimensional shape, such as an equilateral triangle. It will be appreciated that the shaped abrasive particles of the embodiments herein are not so limited and can include other two-dimensional shapes. For example, the shaped abrasive particles of the embodiment herein can include particles having a body with a two-dimensional shape as defined by a major surface of the body from the group of shapes including polygons, irregular polygons, irregular polygons including arcuate or curved sides or portions of sides, ellipsoids, numerals, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, Kanji characters, complex shapes having a combination of polygons shapes, star shapes, shapes with arms extending from a central region (e.g., cross-shaped bodies) and a combination thereof.

It will also be appreciated that the shaped abrasive particles need not be limited to thin shapes defined by only a two-dimensional shape of a major surface, but can include three-dimensional shapes. For example, the body can have a three-dimensional shape selected from the group consisting of a polyhedron, a pyramid, an ellipsoid, a sphere, a prism, a cylinder, a cone, a tetrahedron, a cube, a cuboid, a rhombohedron, a truncated pyramid, a truncated ellipsoid, a truncated sphere, a truncated cone, a pentahedron, a hexahedron, a heptahedron, an octahedron, a nonahedron, a decahedron, a Greek alphabet letter, a Latin alphabet character, a Russian alphabet character, a Kanji character, complex polygonal shapes, irregular shaped contours, a volcano shape, a monostatic shape, and a combination thereof. A monostatic shape is a shape with a single stable resting position. Accordingly, shaped abrasive particles having a monostatic shape can be applied to a substrate and consistently be oriented in the same position, as they have only one stable resting position. For example, shaped abrasive par-

ticles having a monostatic shape may be suitable when applying the particles to a backing via gravity coating, which may be used in the formation of a coated abrasive product. More particularly, the shaped abrasive particles may be mono-monostatic shapes, which describe three dimensional objects having a shape with only one unstable point of balance. According to one particular embodiment, the shaped abrasive particle may have the shape of a gömböc. In another embodiment, the shaped abrasive particle is a monostatic polyhedron with at least four surfaces.

FIG. 6A includes a perspective view illustration of a shaped abrasive particle according to an embodiment. Notably, the shaped abrasive particle 600 can include a body 601 including a surface 602 and a surface 603, which may be referred to as end surfaces 602 and 603. The body can further include surfaces 604, 605, 606, 607 extending between and coupled to the end surfaces 602 and 603. The shaped abrasive particle of FIG. 6A is an elongated shaped abrasive particle having a longitudinal axis 610 that extends along the surface 605 and through the midpoint 640 between the end surfaces 602 and 603. It will be appreciated that the surface 605 is selected for illustrating the longitudinal axis 610, because the body 601 has a generally square cross-sectional contour as defined by the end surfaces 602 and 603. As such, the surfaces 604, 605, 606, and 607 have approximately the same size relative to each other. However in the context of other elongated abrasive particles, wherein the surfaces 602 and 603 define a different shape, for example a rectangular shape, wherein one of the surfaces 604, 605, 606, and 607 may be larger relative to the others, the largest surface of those surfaces defines the major surface, and therefore the longitudinal axis would extend along the largest of those surfaces. As further illustrated, the body 601 can include a lateral axis 611 extending perpendicular to the longitudinal axis 610 within the same plane defined by the surface 605. As further illustrated, the body 601 can further include a vertical axis 612 defining a height of the abrasive particle, wherein the vertical axis 612 can extend in a direction perpendicular to the plane defined by the longitudinal axis 610 and lateral axis 611 of the surface 605.

It will be appreciated that like the thin shaped abrasive particle of FIG. 5, the elongated shaped abrasive particle of FIG. 6A can have various two-dimensional shapes such as those defined with respect to the shaped abrasive particle of FIG. 5. The two-dimensional shape of the body 601 can be defined by the shape of the perimeter of the end surfaces 602 and 603. The elongated shaped abrasive particle 600 can have any of the attributes of the shaped abrasive particles of the embodiments herein.

FIG. 6B includes an illustration of an elongated particle, which is a non-shaped abrasive particle. Shaped abrasive particles may be formed through particular processes, including molding, printing, casting, extrusion, and the like. Shaped abrasive particles are formed such that each particle has substantially the same arrangement of surfaces and edges relative to each other for shaped abrasive particles having the same two-dimensional and three-dimensional shapes. As such, shaped abrasive particles can have a high shape fidelity and consistency in the arrangement of the surfaces and edges relative to other shaped abrasive particles of the group having the same two-dimensional and three-dimensional shape. By contrast, non-shaped abrasive particles can be formed through different process and have different shape attributes. For example, non-shaped abrasive particles are typically formed by a comminution process, wherein a mass of material is formed and then crushed and

sieved to obtain abrasive particles of a certain size. However, a non-shaped abrasive particle will have a generally random arrangement of the surfaces and edges, and generally will lack any recognizable two-dimensional or three dimensional shape in the arrangement of the surfaces and edges around the body. Moreover, non-shaped abrasive particles of the same group or batch generally lack a consistent shape with respect to each other, such that the surfaces and edges are randomly arranged when compared to each other. Therefore, non-shaped grains or crushed grains have a significantly lower shape fidelity compared to shaped abrasive particles.

As further illustrated in FIG. 6B, the elongated abrasive article can be a non-shaped abrasive particle having a body **651** and a longitudinal axis **652** defining the longest dimension of the particle, a lateral axis **653** extending perpendicular to the longitudinal axis **652** and defining a width of the particle. Furthermore, the elongated abrasive particle may have a height (or thickness) as defined by the vertical axis **654**, which can extend generally perpendicular to a plane defined by the combination of the longitudinal axis **652** and lateral axis **653**. As further illustrated, the body **651** of the elongated, non-shaped abrasive particle can have a generally random arrangement of edges **655** extending along the exterior surface of the body **651**.

As will be appreciated, the elongated abrasive particle can have a length defined by longitudinal axis **652**, a width defined by the lateral axis **653**, and a vertical axis **654** defining a height. As will be appreciated, the body **651** can have a primary aspect ratio of length:width such that the length is greater than the width. Furthermore, the length of the body **651** can be greater than or equal to the height. Finally, the width of the body **651** can be greater than or equal to the height **654**. In accordance with an embodiment, the primary aspect ratio of length:width can be at least 1.1:1, at least 1.2:1, at least 1.5:1, at least 1.8:1, at least 2:1, at least 3:1, at least 4:1, at least 5:1, at least 6:1, or even at least 10:1. In another non-limiting embodiment, the body **651** of the elongated shaped abrasive particle can have a primary aspect ratio of length:width of not greater than 100:1, not greater than 50:1, not greater than 10:1, not greater than 6:1, not greater than 5:1, not greater than 4:1, not greater than 3:1, or even not greater than 2:1. It will be appreciated that the primary aspect ratio of the body **651** can be with a range including any of the minimum and maximum ratios noted above. It will be appreciated that not all non-shaped abrasive particles are elongated abrasive particles, and some non-shaped abrasive particles can be substantially equiaxed, such that any combination of the length, width, and height are substantially the same. The non-shaped abrasive particles can be used as the plurality of abrasive particles overlying and bonded to the surface of the shaped abrasive particle. It will be appreciated that the non-shaped abrasive particles may also be used as the body of the abrasive particle to which the plurality of abrasive particles is bonded.

Furthermore, the body **651** of the elongated abrasive particle **650** can include a secondary aspect ratio of width:height that can be at least 1.1:1, such as at least 1.2:1, at least 1.5:1, at least 1.8:1, at least 2:1, at least 3:1, at least 4:1, at least 5:1, at least 8:1, or even at least 10:1. Still, in another non-limiting embodiment, the secondary aspect ratio width:height of the body **651** can be not greater than 100:1, such as not greater than 50:1, not greater than 10:1, not greater than 8:1, not greater than 6:1, not greater than 5:1, not greater than 4:1, not greater than 3:1, or even not greater than 2:1. It will be appreciated the secondary aspect ratio of

width:height can be with a range including any of the minimum and maximum ratios of above.

In another embodiment, the body **651** of the elongated abrasive particle **650** can have a tertiary aspect ratio of length:height that can be at least 1.1:1, such as at least 1.2:1, at least 1.5:1, at least 1.8:1, at least 2:1, at least 3:1, at least 4:1, at least 5:1, at least 8:1, or even at least 10:1. Still, in another non-limiting embodiment, the tertiary aspect ratio length:height of the body **651** can be not greater than 100:1, such as not greater than 50:1, not greater than 10:1, not greater than 8:1, not greater than 6:1, not greater than 5:1, not greater than 4:1, not greater than 3:1, It will be appreciated that the tertiary aspect ratio the body **651** can be with a range including any of the minimum and maximum ratios and above.

The elongated abrasive particle **650** can have certain attributes of the other abrasive particles described in the embodiments herein, including for example, but not limited to, composition, microstructural features (e.g., average grain/crystallite size), hardness, porosity, and the like.

FIG. 7A includes a top view illustration of a shaped abrasive particle according to an embodiment. In particular, the shaped abrasive particle **700** can include a body **701** having the features of other shaped abrasive particles of embodiments herein, including an upper major surface **703** and a bottom major surface (not shown) opposite the upper major surface **703**. The upper major surface **703** and the bottom major surface can be separated from each other by at least one side surface **705**, which may include one or more discrete side surface portions, including for example, a first portion **706** of the side surface **705**, a second portion **707** of the side surface **705**, and a third portion **708** of the side surface **705**. In particular, the first portion **706** of the side surface **705** can extend between a first corner **709** and a second corner **710**. The second portion **707** of the side surface **705** can extend between the second corner **710** and a third corner **711**. Notably, the second corner **710** can be an external corner joining two portions of the side surface **705**. The second corner **710** and a third corner **711**, which are also external corners, are adjacent to each other and have no other external corners disposed between them. Also, the third portion **708** of the side surface **705** can extend between the third corner **711** and the first corner **709**, which are both external corners that are adjacent to each other and have no other external corners disposed between them.

As illustrated, the body **701** can include a first portion **706** including a first curved section **742** disposed between a first linear section **741** and a second linear section **743** and between the external corners **709** and **710**. The second portion **707** is separated from the first portion **706** of the side surface **705** by the external corner **710**. The second portion **707** of the side surface **705** can include a second curved section **752** joining a third linear section **751** and a fourth linear section **753**. Furthermore, the body **701** can include a third portion **708** separated from the first portion **706** of the side surface **705** by the external corner **709** and separated from the second portion **707** by the external corner **711**. The third portion **708** of the side surface **705** can include a third curved section **762** joining a fifth linear section **761** and a sixth linear section **763**.

FIG. 7B includes a top view of a shaped abrasive particle **730** according to an embodiment. The tip sharpness of a shaped abrasive particle, which may be an average tip sharpness, may be measured by determining the radius of a best fit circle on an external corner **731** of the body **732**. For example, turning to FIG. 7B, a top view of the upper major surface **733** of the body **732** is provided. At an external

corner **731**, a best fit circle is overlaid on the image of the body **732** of the shaped abrasive particle **730**, and the radius of the best fit circle relative to the curvature of the external corner **731** defines the value of tip sharpness for the external corner **731**. The measurement may be recreated for each external corner of the body **732** to determine the average individual tip sharpness for a single shaped abrasive particle **730**. Moreover, the measurement may be recreated on a suitable sample size of shaped abrasive particles of a batch of shaped abrasive particles to derive the average batch tip sharpness. Any suitable computer program, such as ImageJ may be used in conjunction with an image (e.g., SEM image or light microscope image) of suitable magnification to accurately measure the best fit circle and the tip sharpness.

The shaped abrasive particles of the embodiments herein may have a particular tip sharpness that may facilitate suitable performance in the fixed abrasive articles of the embodiments herein. For example, the body of a shaped abrasive particle can have a tip sharpness of not greater than 80 microns, such as not greater than 70 microns, not greater than 60 microns, not greater than 50 microns, not greater than 40 microns, not greater than 30 microns, not greater than 20 microns, or even not greater than 10 microns. In yet another non-limiting embodiment, the tip sharpness can be at least 2 microns, such as at least 4 microns, at least 10 microns, at least 20 microns, at least 30 microns, at least 40 microns, at least 50 microns, at least 60 microns, or even at least 70 microns. It will be appreciated that the body can have a tip sharpness within a range between any of the minimum and maximum values noted above.

Another grain feature of shaped abrasive particles is the Shape Index. The Shape Index of a body of a shaped abrasive particle can be described as a value of an outer radius of a best-fit outer circle superimposed on the body, as viewed in two dimensions of a plane of length and width of the body (e.g., the upper major surface or the bottom major surface), compared to an inner radius of the largest best-fit inner circle that fits entirely within the body, as viewed in the same plane of length and width. For example, turning to FIG. 7C the shaped abrasive particle **770** is provided with two circles superimposed on the illustration to demonstrate the calculation of Shape Index. A first circle is superimposed on the body **770**, which is a best-fit outer circle representing the smallest circle that can be used to fit the entire perimeter of the body **770** within its boundaries. The outer circle has a radius (Ro). For shapes such as that illustrated in FIG. 7C, the outer circle may intersect the perimeter of the body at each of the three external corners. However, it will be appreciated that for certain irregular or complex shapes, the body may not fit uniformly within the circle such that each of the corners intersect the circle at equal intervals, but a best-fit, outer circle still may be formed. Any suitable computer program, such as ImageJ may be used in conjunction with an image of suitable magnification (e.g., SEM image or light microscope image) to create the outer circle and measure the radius (Ro).

A second, inner circle can be superimposed on the body **770**, as illustrated in FIG. 7C, which is a best fit circle representing the largest circle that can be placed entirely within the perimeter of the body **770** as viewed in the plane of the length and width of the body **770**. The inner circle can have a radius (Ri). It will be appreciated that for certain irregular or complex shapes, the inner circle may not fit uniformly within the body such that the perimeter of the circle contacts portions of the body at equal intervals, such as shown for the shape of FIG. 7C. However, a best-fit, inner circle still may be formed. Any suitable computer program,

such as ImageJ may be used in conjunction with an image of suitable magnification (e.g., SEM image or light microscope image) to create the inner circle and measure the radius (Ri).

The Shape Index can be calculated by dividing the outer radius by the inner radius (i.e., Shape Index=Ri/Ro). For example, the body **770** of the shaped abrasive particle has a Shape Index of approximately 0.35. Moreover, an equilateral triangle generally has a Shape Index of approximately 0.5, while other polygons, such as a hexagon or pentagon have Shape Index values greater than 0.5. In accordance with an embodiment, the shaped abrasive particles herein can have a Shape Index of at least 0.15, at least 0.20, at least 0.25, at least 0.30, at least 0.35, at least 0.40, at least 0.45, at least about 0.5, at least about 0.55, at least 0.60, at least 0.65, at least 0.70, at least 0.75, at least 0.80, at least 0.85, at least 0.90, at least 0.95. Still, in another non-limiting embodiment, the shaped abrasive particle can have a Shape Index of not greater than 1, such as not greater than 0.98, not greater than 0.95, not greater than 0.90, not greater than 0.85, not greater than 0.80, not greater than 0.75, not greater than 0.70, not greater than 0.65, not greater than 0.60, not greater than 0.55, not greater than 0.50, not greater than 0.45, not greater than 0.40, not greater than 0.35, not greater than 0.30, not greater than 0.25, not greater than 0.20, or even not greater than 0.15. It will be appreciated that the shaped abrasive particles can have a Shape Index within a range between any of the minimum and maximum values noted above.

FIG. 7D includes a top view of a shaped abrasive particle according to another embodiment. The shaped abrasive particle **780** can have a body **781** having the features of other shaped abrasive particles of embodiments herein, including an upper major surface **783** and a bottom major surface (not shown) opposite the upper major surface **783**. The upper major surface **783** and the bottom major surface can be separated from each other by at least one side surface **784**, which may include one or more discrete side surface sections. According to one embodiment, the body **781** can be defined as an irregular hexagon, wherein the body has a hexagonal (i.e., six-sided) two dimensional shape as viewed in the plane of a length and a width of the body **781**, and wherein at least two of the sides, such as sides **785** and **786**, have a different length with respect to each other. Notably, the longest dimension along one of the sides is understood herein to refer to the width of the body **781** and the length of the body is the longest dimension extending through the midpoint of the body **781** from one side of the body to the other (e.g., from a corner to a flat side opposite the corner). Moreover, as illustrated, none of the sides are parallel to each other. And furthermore, while not illustrated, any of the sides may have a curvature to them, including a concave curvature wherein the sides may curve inwards toward the interior of the body **781**.

FIG. 8 includes a cross-sectional view of a portion of an abrasive particle according to an embodiment. As illustrated, the abrasive particle can include a shaped abrasive particle including a body **801** having a first major surface **802**, a second major surface **803**, and side surface **804** and **805** extending between the first and second major surface **802** and **803** as viewed in cross-section. The abrasive particle **800** can further include a plurality of abrasive particles coupled to certain surfaces of the body **801** of the shaped abrasive particle. The plurality of abrasive particles can include one or more portions of particles, which may be differentiated as groups of abrasive particles, wherein the different groups may have at least one abrasive characteristic

that is distinct from each other. Abrasive characteristics can include but is not limited to average particle size, average crystallite size, hardness, toughness, two-dimensional shape, three-dimensional shape, shaped abrasive particles, non-shaped abrasive particles, composition, standing angle, orientation, and a combination thereof. Utilization of different groups may facilitate tailoring of the abrasive particles for a given application. Additionally, different groups may or may not be coupled to different surfaces of the body **801** of the shaped abrasive particle. That is, in one embodiment, the same single surface of the body **801** can include a plurality of groups of abrasive particles. In still other embodiments, the body **801** of the shaped abrasive particle can have different groups of abrasive particles coupled to different surfaces of the body **801**.

In particular, the abrasive particle **800** can include a plurality of abrasive particles including a first group of abrasive particles **810** attached to a portion of the first major surface **802**. The first group of abrasive particles **810** can include fine shaped abrasive particles **811** having an average particle size significantly less than the average particle size of the body **801** of the shaped abrasive particle. The fine shaped abrasive particles can have any of the attributes of other shaped abrasive particles as described in the embodiments herein. In one particular embodiment, the fine shaped abrasive particles can have a two-dimensional shape that is substantially the same as the two dimensional shape of the body of the shaped abrasive particle. Still in another embodiment, the fine shaped abrasive particles can have a two-dimensional shape that is different than the two dimensional shape of the body of the shaped abrasive particle. It will also be appreciated that the fine shaped abrasive particles can have any of the three-dimensional shapes as described herein.

Notably, the fine shaped abrasive particles can have a median particle size relative to the length, width, and/or height of the body **801**. The same relationship noted herein with respect to the median particle size of the plurality of abrasive particles relative to the length, width, or height of the body of the shaped abrasive particles can be true when the plurality of abrasive particles includes fine shaped abrasive particles. The fine shaped abrasive particles have a length \leq width \leq height, wherein the average length of the fine shaped abrasive particles is less than the length of the body of the shaped abrasive particle.

For example, the fine shaped abrasive particles **810** can have an average length of not greater than about 90% of the length of the body **801**, such as or not greater than about 80% of the length or not greater than about 70% of the length or not greater than about 60% of the length or not greater than about 50% of the length or not greater than about 40% of the length or not greater than about 30% of the length or not greater than about 25% of the length or not greater than about 20% of the length or not greater than about 18% of the length or not greater than about 15% of the length or not greater than about 12% of the length or not greater than about 10% of the length or not greater than 8% of the length or not greater than 6% of the length or not greater than 5% of the length of the body **801** of the shaped abrasive particle. In still another non-limiting embodiment, the fine shaped abrasive particles **811** have an average length of at least about 0.1% of the length of the body **801** or at least about 0.5% of the length or at least about 1% of the length or at least about 2% of the length or at least about 3% of the length or at least about 4% of the length or at least about 5% of the length or at least about 6% of the length or at least about 7% of the length or at least about 8% of the length or at least about 9% of the

length or at least about 10% of the length or at least about 12% of the length or at least about 15% of the length or at least about 18% of the length or at least about 20% of the length or at least about 25% of the length or at least about 30% of the length of the body **801** of the shaped abrasive particle. It will be appreciated that the average length of the fine shaped abrasive particles can be within a range between any of the minimum and maximum percentages noted above.

Additionally, the fine shaped abrasive particles can have a particular average width that is less than the length of the body **801** of the shaped abrasive particle. According to one embodiment, the fine shaped abrasive particles **811** can have an average width that is not greater than about 90% of the length of the body **801**, such as not greater than about 80% of the length or not greater than about 70% of the length or not greater than about 60% of the length or not greater than about 50% of the length or not greater than about 40% of the length or not greater than about 30% of the length or not greater than about 25% of the length or not greater than about 20% of the length or not greater than about 18% of the length or not greater than about 15% of the length or not greater than about 12% of the length or not greater than about 10% of the length or not greater than about 8% of the length or not greater than about 6% of the length or not greater than about 5% of the length of the body of the shaped abrasive particle. Still, in another embodiment, the fine shaped abrasive particles **811** can have an average width of at least about 0.1% of the length of the body **801**, such as at least about 0.5% of the length or at least about 1% of the length or at least about 2% of the length or at least about 3% of the length or at least about 4% of the length or at least about 5% of the length or at least about 6% of the length or at least about 7% of the length or at least about 8% of the length or at least about 9% of the length or at least about 10% of the length or at least about 12% of the length or at least about 15% of the length or at least about 18% of the length or at least about 20% of the length or at least about 25% of the length or at least about 30% of the length of the body of the shaped abrasive particle. It will be appreciated that the average width of the fine shaped abrasive particles can be within a range between any of the minimum and maximum percentages noted above.

For yet another embodiment, the fine shaped abrasive particles **811** can have an average height that is less than the length of the body **801** of the shaped abrasive particle. For example, the fine shaped abrasive particles **811** can have an average height that is not greater than about 90% of the length of the body **801**, such as not greater than about 80% of the length or not greater than about 70% of the length or not greater than about 60% of the length or not greater than about 50% of the length or not greater than about 40% of the length or not greater than about 30% of the length or not greater than about 25% of the length or not greater than about 20% of the length or not greater than about 18% of the length or not greater than about 15% of the length or not greater than about 12% of the length or not greater than about 10% of the length or not greater than about 8% of the length or not greater than about 6% of the length or not greater than about 5% of the length of the body **801** of the shaped abrasive particle. Still, in one non-limiting embodiment, the fine shaped abrasive particles **811** can have an average height of at least about 0.01% of the length of the body **801**, such as at least about 0.1% of the length or at least about 0.5% of the length or at least about 1% of the length or at least about 2% of the length or at least about 3% of the length or at least about 4% of the length or at least about 5%

of the length or at least about 6% of the length or at least about 7% of the length or at least about 8% of the length or at least about 9% of the length or at least about 10% of the length or at least about 12% of the length or at least about 15% of the length or at least about 18% of the length or at least about 20% of the length or at least about 25% of the length or at least about 30% of the length of the body **801** of the shaped abrasive particle. It will be appreciated that the average height of the fine shaped abrasive particles can be within a range between any of the minimum and maximum percentages noted above.

FIG. **8**, it will be appreciated that a majority of the plurality of abrasive particles overlying the body **801** can be fine shaped abrasive particles. Moreover, in certain instances, essentially all of the abrasive particles of the plurality of abrasive particles overlying the body **801** can be fine shaped abrasive particles.

The composite shaped abrasive particle **800** can further include a second group of abrasive particles **812** also attached to the first major surface **802** of the body **801**. The second group of abrasive particles **812** can be non-shaped abrasive particles **813**. According to one embodiment, as illustrated in FIG. **8**, at least one surface of the body **801**, such as the first major surface **802** of the abrasive particle **800** can have a blend of two different types of abrasive particles. The first and second groups of abrasive particles **810** and **812** can be placed on the first major surface **802** using any of the techniques described herein. The first and second group of abrasive particles **810** and **812** may be deposited on the first major surface **802** simultaneously or separately.

Moreover, the first group of abrasive particles **810** can have a first average particles size, which in the case of fine shaped abrasive particles can be defined by the average length, and the second group of abrasive particles **812** can have a second average particle size, which in the case of fine shaped abrasive particles can be defined by the average length. In certain instances the first and second average particle sizes can be different from one another. In still another embodiment, the first and second average particle sizes can be substantially the same. The relative sizes of the abrasive particles **811** and **813** of the first and second groups of abrasive particles **810** and **812** can be tailored depending upon the desired application of the abrasive particles.

As further illustrated, abrasive particle **800** can include a third group of abrasive particles **817** that can be coupled to the second major surface **803** of the body **801**. The third group of abrasive particles **817** can include fine shaped abrasive particles **818**, which can have a significantly smaller average particle sized compared to the body **801** of the shaped abrasive particle. The fine shaped abrasive particles **818** can have a different two-dimensional shaped compared to the shaped abrasive particles **811** of the first group of abrasive particles **810**.

Moreover, at least a portion of the fine shaped abrasive particles **818** may be oriented in a standing position relative the surface **803** of the body **801** of the shaped abrasive particle. While the group of abrasive particles **817** is illustrated as shaped abrasive particles, it will be appreciated that it may also include elongated abrasive particles, which may be shaped or non-shaped, and can be oriented in a standing position relative to the surface **803** of the body **801**. According to an embodiment, the standing orientation can be defined by a largest surface (i.e., a major) of the body of a fine shaped abrasive particle being spaced apart from the surface of the body of the shaped abrasive particle. Moreover, the standing orientation of the fine shaped abrasive

particles **818** can be defined by a standing angle **820** between the longitudinal axis **819** of the fine shaped abrasive particle **820** (or elongated abrasive particle, shaped or non-shaped) and the major surface **803** of the body **801**. The standing angle **820** can be at least 5 degrees, such as at least 10 degrees, at least 20 degrees, at least 30 degrees, or at least 40 degrees or at least 50 degree or at least 60 degrees or at least 70 degrees or at least 80 degrees or at least 85 degrees. In at least one embodiment, the fine shaped abrasive particles **818** are in a standing orientation relative to the surface **803** of the body **801** and define a substantially perpendicular standing angle **820** as illustrated in FIG. **8**.

Still, in another embodiment, the group of abrasive particles **817** can include a portion of abrasive particles **830** that are lying flat. In a lying flat orientation, the longitudinal axis of the abrasive particles **831** may be substantially parallel to the surface **803** of the body **801**.

FIG. **9** includes a top down illustration of an abrasive particle according to an embodiment. As illustrated, the abrasive particle **900** can include a shaped abrasive particle having a body **901** and a plurality of abrasive particles **940** overlying and bonded to a major surface **905** of the body **901**. As illustrated, according to one embodiment, the plurality of abrasive particles **940** can be arranged on one or more surfaces of the body **901** in one or more distributions.

As illustrated, in one embodiment, the plurality of abrasive particles **940** may include different groups. For example, the plurality of abrasive particles **940** may include a first group of abrasive particles **902**, which may include fine shaped abrasive particles **903** that can be arranged in a controlled distribution on the surface **905** of the body **901**. The fine shaped abrasive particles **903** can be lying flat relative to the surface **905** of the body **905**. The fine shaped abrasive particles **903** can be arranged in a pattern defined by a plurality of repeating units, wherein each repeating unit of the plurality of repeating units is substantially the same with respect to each other. As illustrated in the embodiment, the fine shaped abrasive particles **903** are arranged in a pattern defined by a substantially triangular repeating unit, as shown by the dotted line. In at least one embodiment, the abrasive particle **900** can be formed such that the fine abrasive particles **903** may extend over a majority or over substantially the entire surface **905** of the body **901** in the controlled distribution as illustrated. It will be appreciated that this may be true of any of the groups of abrasive particles as illustrated herein. Still, in certain instances, one or more groups of abrasive particles may be overlying and bonded to the same surface of the body **901** and may define different distributions and/or orientations relative to each other.

According to another embodiment, the plurality of abrasive particles **940** can include a second group of abrasive particles **910**, which may include fine shaped abrasive particles **911** that can be arranged in a random distribution on the surface **905** of the body **901**. The fine shaped abrasive particles **911** can be in a standing orientation relative to the surface **905** of the body **905**. The fine shaped abrasive particles **911** lack any identifiable repeating unit and thus are arranged in a substantially random distribution compared to each other. It will be appreciated that other types of abrasive particles can be used and other orientation of the abrasive particles may be used. In at least one embodiment, the abrasive particle **900** can be formed such that the fine abrasive particles **911** may extend over a majority or over substantially the entire surface **905** of the body **901** in the random distribution as illustrated.

In yet another embodiment, the plurality of abrasive particles **940** can include a third group of abrasive particles

920, which may include fine shaped abrasive particles 921 that can be arranged in a controlled distribution on the surface 905 of the body 901. The fine shaped abrasive particles 921 can be in a standing orientation relative to the surface 905 of the body 905. As illustrated in the embodiment, the fine shaped abrasive particles 921 can be arranged in a pattern defined by a substantially rectangular repeating unit as shown by the dotted line. In at least one embodiment, the abrasive particle 900 can be formed such that the fine abrasive particles 903 may extend over a majority or over substantially the entire surface 905 of the body 901 in the controlled distribution as illustrated. It will be appreciated that other types of abrasive particles can be used and other orientation of the abrasive particles may be used.

For still another embodiment, the plurality of abrasive particles 940 can include a fourth group of abrasive particles 930, which may include non-shaped abrasive particles 931 that can be arranged in a random distribution on the surface 905 of the body 901. The non-shaped abrasive particles 931 can be in a substantially random arrangement relative to each other. In at least one embodiment, the abrasive particle 900 can be formed such that the non-shaped abrasive particles 931 may extend over a majority or over substantially the entire surface 905 of the body 901 in the random distribution as illustrated.

In at least one embodiment, at least a portion of the plurality of abrasive particles of an abrasive particle can have a coating overlying at least a portion of the exterior surfaces of the abrasive particles. The coating may include a material selected from the group of inorganic, organic, amorphous, crystalline, polycrystalline, ceramic, metal, resin, epoxy, polymer, oxides, carbides, nitrides, borides, carbon-based materials, and a combination thereof.

According to an embodiment, the abrasive particles of the embodiments herein can have a particularly rough and jagged surface. It has been noted by some in the industry that abrasive particles having smooth surfaces and sharp edges provide the best performance. However it has been surprisingly discovered by the Applicants of the present disclosure that grains having a rough surface by virtue of the plurality of abrasive particles attached thereto can have improved performance compared to grains without a plurality of grains attached to one or more surfaces (i.e., grains having a smoother surface).

In at least one particular embodiment, the abrasive particle can include a body of a shaped abrasive particle having a first major surface and a second major surface separated from the first major surface by a side surface, wherein the plurality of abrasive particles are attached to at least the first major surface or the second major surface and the side surface is essentially free of the plurality of abrasive particles. In still other instances, the abrasive particle can include a body of a shaped abrasive particle having a first major surface and a second major surface separated from the first major surface by a side surface, and wherein the plurality of abrasive particles are attached to the first major surface and the second major surface and the side surface is essentially free of the plurality of abrasive particles. Still, it will be appreciated that the plurality of abrasive particles may be overlying and bonded to one or more of the side surface of the body of the shaped abrasive particle.

FIG. 12A includes a cross-sectional illustration of a coated abrasive article incorporating the abrasive particulate material in accordance with an embodiment. Notably, the plurality of abrasive particles on the one or more surfaces of the abrasive particles are not illustrated, but will be appreciated as being present in accordance with embodiments

herein. As illustrated, the coated abrasive 1200 can include a substrate 1201 and a make coat 1203 overlying a surface of the substrate 1201. The coated abrasive 1200 can further include a first type of abrasive particulate material 1205 in the form of a first type of shaped abrasive particle, a second type of abrasive particulate material 1206 in the form of a second type of shaped abrasive particle, and a third type of abrasive particulate material in the form of diluent abrasive particles, which may not necessarily be shaped abrasive particles, and having a random shape. The coated abrasive 1200 may further include size coat 1204 overlying and bonded to the abrasive particulate materials 1205, 1206, 1207, and the make coat 1204.

According to one embodiment, the substrate 1201 can include an organic material, inorganic material, and a combination thereof. In certain instances, the substrate 1201 can include a woven material. However, the substrate 1201 may be made of a non-woven material. Particularly suitable substrate materials can include organic materials, including polymers, and particularly, polyester, polyurethane, polypropylene, polyimides such as KAPTON from DuPont, paper. Some suitable inorganic materials can include metals, metal alloys, and particularly, foils of copper, aluminum, steel, and a combination thereof.

The make coat 1203 can be applied to the surface of the substrate 1201 in a single process, or alternatively, the abrasive particulate materials 1205, 1206, 1207 can be combined with a make coat 1203 material and applied as a mixture to the surface of the substrate 1201. Suitable materials of the make coat 1203 can include organic materials, particularly polymeric materials, including for example, polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and mixtures thereof. In one embodiment, the make coat 1203 can include a polyester resin. The coated substrate can then be heated in order to cure the resin and the abrasive particulate material to the substrate. In general, the coated substrate 1201 can be heated to a temperature of between about 100° C. to less than about 250° C. during this curing process.

Moreover, it will be appreciated that the coated abrasive article can include one or more collections of various types of abrasive particles, including the abrasive particulate materials 1205, 1206, and 1207, which may represent the abrasive particles of the embodiments herein. The embodiments herein can include a fixed abrasive article (e.g., a coated abrasive article) having a first collection of abrasive particles (e.g., abrasive particulate materials 1205) representative of the abrasive particles of the embodiments herein. Any fixed abrasive may further employ a second collection of abrasive particles therein, which may be representative of another type of abrasive particle according to the embodiments herein, which may be distinct in one or more manners from the abrasive particles of the first collection, including but not limited to, one or more abrasive characteristics as described herein. The same features may be utilized in a bonded abrasive article.

The abrasive particulate materials 1205, 1206, and 1207 can include different types of shaped abrasive particles according to embodiments herein. The different types of shaped abrasive particles can differ from each other in composition, two-dimensional shape, three-dimensional shape, size, and a combination thereof as described in the embodiments herein. As illustrated, the coated abrasive 1200 can include a first type of shaped abrasive particle 1205 having a generally triangular two-dimensional shape and a

second type of shaped abrasive particle **1206** having a quadrilateral two-dimensional shape. The coated abrasive **1200** can include different amounts of the first type and second type of shaped abrasive particles **1205** and **1206**. It will be appreciated that the coated abrasive may not necessarily include different types of shaped abrasive particles, and can consist essentially of a single type of shaped abrasive particle. As will be appreciated, the shaped abrasive particles of the embodiments herein can be incorporated into various fixed abrasives (e.g., bonded abrasives, coated abrasive, non-woven abrasives, thin wheels, cut-off wheels, reinforced abrasive articles, and the like), including in the form of blends, which may include different types of shaped abrasive particles, shaped abrasive particles with diluent particles, and the like. Moreover, according to certain embodiments, a batch of particulate material may be incorporated into the fixed abrasive article in a predetermined orientation, wherein each of the shaped abrasive particles can have a predetermined orientation relative to each other and relative to a portion of the abrasive article (e.g., the backing of a coated abrasive).

The abrasive particles **1207** can be diluent particles different than the first and second types of shaped abrasive particles **1205** and **1206**. For example, the diluent particles can differ from the first and second types of shaped abrasive particles **1205** and **1206** in composition, two-dimensional shape, three-dimensional shape, size, and a combination thereof. For example, the abrasive particles **1207** can represent conventional, crushed abrasive grit having random shapes. The abrasive particles **1207** may have a median particle size less than the median particle size of the first and second types of shaped abrasive particles **1205** and **1206**.

After sufficiently forming the make coat **503** with the abrasive particulate materials **1205**, **1206**, **1207** contained therein, the size coat **1204** can be formed to overlie and bond the abrasive particulate material **1205** in place. The size coat **1204** can include an organic material, may be made essentially of a polymeric material, and notably, can use polyesters, epoxy resins, polyurethanes, polyamides, polyacrylates, polymethacrylates, poly vinyl chlorides, polyethylene, polysiloxane, silicones, cellulose acetates, nitrocellulose, natural rubber, starch, shellac, and mixtures thereof.

FIG. **12B** includes a perspective view illustration of a portion of a coated abrasive article including an abrasive particle according to an embodiment. Notably, the illustrated embodiment of FIG. **12B** includes an abrasive article **1230** including an abrasive particle **1231** including a shaped abrasive particle **1232** having a body including a plurality of abrasive particles **1234** bonded to a first major surface **1235** of the body of the shaped abrasive particle. Notably the coated abrasive article includes a backing **1236** having a longitudinal axis **1237** and a lateral axis **1238**. In one embodiment, the abrasive particle **1231** is placed on the backing **1236** and can be bonded on the backing **1236** in a particular orientation using one or more adhesive layers (e.g., a make coat, size coat, etc.) as noted herein. In certain instances, the abrasive particle **1231** can be placed in a controlled orientation on the backing **1236**, such that the orientation of the first major surface **1235** including the plurality of shaped abrasive particles **1234** has a particular orientation relative to the longitudinal axis **1237** and/or lateral axis **1238** of the backing **1236**. For example, in certain instances, such as for the abrasive particle **1232**, the first major surface **1235** including the plurality of abrasive particles **1234** can be oriented substantially perpendicular to the longitudinal axis **1237** and substantially parallel to the lateral axis **1238**. In certain other instances, an alternative

orientation may be desired, including for example, an abrasive particle **1241** having a plurality of abrasive particles **1242** attached to a first major surface **1243** of the body of the shaped abrasive particle **1244**, wherein the particle has a controlled orientation including the first major surface **1243** being substantially perpendicular to the lateral axis **1238** and substantially parallel to the longitudinal axis **1237**. It will be appreciated that the abrasive particles can also have other controlled orientations, such that the orientation of one or more abrasive particles on the backing can define a controlled angle relative to the lateral axis **1238** and/or longitudinal axis **1237**. Moreover, the orientation of the abrasive particles may be controlled depending upon the number and/or type of surfaces of the shaped abrasive particle (i.e., first major surface and/or second major surface and/or side surface) that are covered. Moreover, the coated abrasive article can include one or more group of abrasive particles on the backing **1236**, wherein each group of abrasive particles can have at least one abrasive characteristic that is similar relative to each other. Suitable examples of certain types of abrasive characteristics include type of coating of the plurality of abrasive particles, size of the plurality of abrasive particles, shape of the body of the shaped abrasive particle, composition of the shaped abrasive particle and/or plurality of abrasive particle, orientation, tilt angle, and any of the other features of embodiments detailed herein. Moreover, abrasive particles from different groups on the backing can differ in at least one of the abrasive characteristics noted herein.

FIG. **13A** includes an illustration of a bonded abrasive article incorporating the abrasive particulate material in accordance with an embodiment. As illustrated, the bonded abrasive **1300** can include a bond material **1301**, abrasive particulate material **1302** contained in the bond material, and porosity **1308** within the bond material **1301**. In particular instances, the bond material **1301** can include an organic material, inorganic material, and a combination thereof. Suitable organic materials can include polymers, such as epoxies, resins, thermosets, thermoplastics, polyimides, polyamides, and a combination thereof. Certain suitable inorganic materials can include metals, metal alloys, vitreous phase materials, crystalline phase materials, ceramics, and a combination thereof.

The abrasive particulate material **1302** of the bonded abrasive **1300** can include different types of shaped abrasive particles **1303**, **1304**, **1305**, and **1306**, which can have any of the features of different types of shaped abrasive particles as described in the embodiments herein. Notably, the different types of shaped abrasive particles **1303**, **1304**, **1305**, and **1306** can differ from each other in composition, two-dimensional shape, three-dimensional shape, size, and a combination thereof as described in the embodiments herein.

The bonded abrasive **1300** can include a type of abrasive particulate material **1307** representing diluent abrasive particles, which can differ from the different types of shaped abrasive particles **1303**, **1304**, **1305**, and **1306** in composition, two-dimensional shape, three-dimensional shape, size, and a combination thereof.

The porosity **1308** of the bonded abrasive **1300** can be open porosity, closed porosity, and a combination thereof. The porosity **1308** may be present in a majority amount (vol %) based on the total volume of the body of the bonded abrasive **1300**. Alternatively, the porosity **1308** can be present in a minor amount (vol %) based on the total volume of the body of the bonded abrasive **1300**. The bond material **1301** may be present in a majority amount (vol %) based on the total volume of the body of the bonded abrasive **1300**.

Alternatively, the bond material **1301** can be present in a minor amount (vol %) based on the total volume of the body of the bonded abrasive **1300**. Additionally, abrasive particulate material **1302** can be present in a majority amount (vol %) based on the total volume of the body of the bonded abrasive **1300**. Alternatively, the abrasive particulate material **1302** can be present in a minor amount (vol %) based on the total volume of the body of the bonded abrasive **1300**.

FIG. **13B** includes an illustration of a bonded abrasive article including abrasive particles of the embodiments herein. As illustrated, the bonded abrasive **1350** can include a body **1351** including an abrasive particle **1360** and abrasive particle **1370** contained within the bond matrix material **1352** of the body **1351**. The abrasive particle **1360** can include a shaped abrasive particle **1361** and a plurality of abrasive particles **1362** bonded to at least a first major surface **1363** of the body of the shaped abrasive particle **1361**. Notably, the abrasive particle **1360** can have a particular position within the three dimensional volume of the body **1351** of the bonded abrasive **1350**. Moreover, the abrasive particle **1360** can have a controlled and predetermined orientation relative to a radial axis **1381** and/or lateral axis **1382** of the body **1351**. According to one embodiment, the abrasive particle **1360** can have an orientation that is considered to be lying flat within the body **1351** as the first major surface **1363** of the body of the shaped abrasive particle **1361** is substantially parallel to the radial axis **1381** or substantially parallel to the major surfaces **1354** and **1355** of the body **1351** of the bonded abrasive **1350**. Moreover, the first major surface **1363** of the shaped abrasive particle **1361** can be substantially perpendicular to the lateral axis **1382**. In certain instances, a bonded abrasive may include a portion of abrasive particles within the body in the orientation like the abrasive particle **1360**, which may facilitate improved formation of the bonded abrasive and/or improve performance of the bonded abrasive.

As further illustrated, the abrasive particle **1370** can include a shaped abrasive particle **1371** and a plurality of abrasive particles **1372** bonded to at least a first major surface **1373** of the body of the shaped abrasive particle **1371**. Notably, the abrasive particle **1370** can have a particular position within the three dimensional volume of the body **1351** of the bonded abrasive **1350**. Moreover, the abrasive particle **1370** can have a controlled and predetermined orientation relative to a radial axis **1381** and/or lateral axis **1382** of the body **1351**. According to one embodiment, the abrasive particle **1360** can have an orientation that is considered to be standing upright within the body **1351** as the first major surface **1373** of the body of the shaped abrasive particle **1371** is substantially parallel to the lateral axis **1382** and substantially perpendicular to the major surfaces **1354** and **1355** of the body **1351** of the bonded abrasive **1350**. Moreover, the first major surface **1373** of the shaped abrasive particle **1371** can be substantially perpendicular to the radial axis **1381**. In other instances, the abrasive particle **1370** can be oriented within the body **1351** such that it is tilted with respect to the lateral axis to define a controlled tilt angle. In such situations, the abrasive particle **1371** may have a first major surface that is neither substantially perpendicular to the radial axis **1381** nor substantially parallel to the lateral axis. Such a controlled tilt angle can include any angle between 5 degrees and 85 degrees. As used herein, reference to a substantially parallel or substantially perpendicular orientation is reference to a difference between an axis or plane and a reference axis of not greater than 5 degrees. Moreover, as will be appreciated, the abrasive particles can have various rotational orienta-

tions about the lateral axis **1382** and the radial axis **1381**. When referring to a tilt angle, it will be understood that there may be a radial tilt angle defined as the smallest angle formed between the radial axis **1381** and a radial vector defining the direction of the major surface having the largest component in the radial direction. There may also be a lateral tilt angle defined as the smallest angle formed between the lateral axis **1382** and a vector defining the direction of the major surface with the largest component in the lateral direction.

Many different aspects and embodiments are possible. Some of those aspects and embodiments are described herein. After reading this specification, skilled artisans will appreciate that those aspects and embodiments are only illustrative and do not limit the scope of the present invention. Embodiments may be in accordance with any one or more of the items as listed below.

Items:

Item **1**. An abrasive particle comprising a shaped abrasive particle comprising a body, and a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle.

Item **2**. The abrasive particle of item **1**, wherein the body of the shaped abrasive particle comprises a two-dimensional shape as viewed in a plane defined by a length and a width of the body selected from the group consisting of polygons, ellipsoids, numerals, Greek alphabet characters, Latin alphabet characters, Russian alphabet characters, complex shapes having a combination of polygonal shapes, and a combination thereof.

Item **3**. The abrasive particle of item **1**, wherein the plurality of abrasive particles is bonded to a major surface of the body or wherein the plurality of abrasive particles is bonded to at least two surfaces of the body or wherein the plurality of abrasive particles is bonded to at least two major surfaces of the body.

Item **4**. The abrasive particle of item **1**, wherein a portion of the particles of the plurality of abrasive particles is embedded into the volume of the body of the shaped abrasive particle or wherein a portion of the abrasive particles of the plurality of abrasive particles is embedded within the at least one surface of the body or wherein the plurality of abrasive particles are sinter-bonded to the at least one surface of the body of the shaped abrasive particle or wherein a portion of the abrasive particles of the plurality of abrasive particles are sinter-bonded to the at least one surface of the body of the shaped abrasive particle.

Item **5**. The abrasive particle of item **4**, wherein the portion includes a minority of the particles of the plurality of abrasive particles or wherein the portion includes a majority of the particles of the plurality of abrasive particles.

Item **6**. The abrasive particle of item **1**, wherein the plurality of abrasive particles cover at least 1% of the total surface area of the body or at least 5% or at least 10% or at least 20% or at least 30% or at least 40% or at least 50% or at least 60% or at least about 70% or at least about 80% or at least about 90% or at least about 95%, and wherein the plurality of abrasive particles cover not greater than 95% or not greater than 90% or not greater than 80% or not greater than 60% or not greater than 50% or not greater than 40% or not greater than 30% or the total surface area of the body.

Item **7**. The abrasive particle of item **1**, wherein the body includes a first major surface, a second major surface, and a side surface extending between the first major surface and the second major surface, wherein the plurality of abrasive

particles is bonded to the first major surface and the side surface is essentially free of abrasive particles of the plurality of abrasive particles.

Item 8. The abrasive particle of item 1, wherein the surface of the body including the plurality of abrasive particle comprises a random arrangement of the plurality of abrasive particles on a major surface of the body, and wherein a side surface of the body is essentially free of the plurality of abrasive particles.

Item 9. The abrasive particle of item 1, wherein wherein the body comprises a first major surface and a second major surface separated from the first major surface by a side surface, wherein the plurality of abrasive particles are attached to the first major surface and the first major surface has a surface roughness greater than a surface roughness of the side surface.

Item 10. The abrasive particle of item 1, wherein the plurality of abrasive particles are selected from the group consisting of oxides, carbides, nitrides, borides, oxycarbides, oxynitrides, oxyborides, natural minerals, synthetic materials, carbon-based materials, and a combination thereof.

Item 11. The abrasive particle of item 1, wherein the plurality of abrasive particles are selected from the group consisting of crushed grains, irregularly shaped grains, elongated grains, agglomerates, aggregates, and a combination thereof.

Item 12. The abrasive particle of item 1, wherein the body of the shaped abrasive particle comprises a length \geq width \geq height, and the plurality of abrasive particles comprise a median particle size (D50), and wherein the median particle size (D50) is not greater than the length of the body of the shaped abrasive particle or wherein the median particle size (D50) is not greater than the width of the body of the shaped abrasive particle or wherein the median particle size (D50) is not greater than the height of the body of the shaped abrasive particle.

Item 13. The abrasive particle of item 12, wherein the plurality of abrasive particles comprise a median particle size (D50) of not greater than about 90% of the length of the body or at least about 0.1% of the length of the body.

Item 14. The abrasive particle of item 1, wherein the plurality of abrasive particles comprise at least 1 wt % of a total weight of the abrasive particle or wherein the plurality of abrasive particles comprise not greater than about 80 wt % of a total weight of the abrasive particle.

Item 15. The abrasive particle of item 12, wherein the median particle size (D50) is not greater than the width of the body of the shaped abrasive particle or wherein the plurality of abrasive particles comprise a median particle size (D50) of not greater than about 90% of the width of the body or at least about 0.1% of the width of the body.

Item 16. The abrasive particle of item 1, wherein the plurality of abrasive particles include a material having a CTE that is not greater than about 50% different than a CTE of the body of the shaped abrasive particle.

Item 17. The abrasive particle of item 15, wherein the median particle size (D50) is not greater than the height of the body of the shaped abrasive particle or wherein the plurality of abrasive particles comprise a median particle size (D50) of not greater than about 90% of the height of the body or at least about 0.1% of the height of the body.

Item 18. The abrasive particle of item 1, wherein at least a portion of the plurality of abrasive particles include fine shaped abrasive particles, or wherein essentially all of the plurality of abrasive particles include the fine shaped abrasive particles.

Item 19. The abrasive particle of item 18, wherein the fine shaped abrasive particles have a length \leq width \leq height, wherein the average length of the fine shaped abrasive particles is less than the length of the body of the shaped abrasive particle.

Item 20. The abrasive particle of item 19, wherein fine shaped abrasive particles comprise an average length of not greater than about 90% of the length of the body or at least about 0.1% of the length of the body of the shaped abrasive particle.

Item 21. The abrasive particle of item 19, wherein the fine shaped abrasive particles comprise an average width that is less than the length of the body of the shaped abrasive particle or wherein the fine shaped abrasive particles comprise an average height that is less than the length of the body of the shaped abrasive particle.

Item 22. The abrasive particle of item 19, wherein a portion of the fine shaped abrasive particles are positioned in a standing orientation relative to the surface of the body of the shaped abrasive particle.

Item 23: The abrasive particle of item 1, wherein the plurality of abrasive particles is arranged on the surface of the body in a random distribution.

Item 24. The abrasive particle of item 1, wherein the plurality of abrasive particles are arranged on the surface of the body in a controlled distribution.

Item 25. The abrasive particle of item 24, wherein the controlled distribution includes a pattern defined by a plurality of repeating units, wherein each repeating unit of the plurality of repeating units is substantially the same with respect to each other.

Item 26. The abrasive particle of item 1, wherein a portion of the abrasive particles of the plurality of abrasive particles include a coating comprising a material selected from the group of inorganic, organic, amorphous, crystalline, polycrystalline, ceramic, metal, resin, epoxy, polymer, oxides, carbide, nitride, borides, or a combination thereof.

Item 27. The abrasive particle of item 1, wherein the surface of the body including the plurality of abrasive particle comprises a random arrangement of the plurality of abrasive particles on a major surface of the body, and wherein a side surface of the body is essentially free of the plurality of abrasive particles.

Item 28. The abrasive particle of item 1, wherein the body comprises a first major surface and a second major surface separated from the first major surface by a side surface, wherein the plurality of abrasive particles are attached to at least the first major surface or the second major surface and the side surface is essentially free of the plurality of abrasive particles.

Item 29. The abrasive particle of item 1, wherein the body comprises a first major surface and a second major surface separated from the first major surface by a side surface, wherein the plurality of abrasive particles are attached to the first major surface and the second major surface and the side surface is essentially free of the plurality of abrasive particles.

Item 30. The abrasive particle of item 1, wherein the abrasive particle is incorporated into a fixed abrasive article.

Item 31. The abrasive particle of item 1, further comprising a coated abrasive article including a substrate and the abrasive particle overlying the substrate, wherein the abrasive particle has a predetermined orientation on the coated abrasive defined by an orientation of the at least one surface including the plurality of abrasive particles relative to a longitudinal or lateral axis of the substrate.

Item 32. The abrasive particle of item 1, further comprising a bonded abrasive article including a body including a bond matrix material, wherein the abrasive particle has a predetermined position and orientation within the body defined by a predetermined position and orientation of the at least one surface including the plurality of abrasive particles relative to a longitudinal or lateral axis of the body.

Item 33. An abrasive article comprising: a bond material; and a first collection of abrasive particles coupled to the bond material, wherein each particle in the first collection comprises: a shaped abrasive particle comprising a body; and a plurality of abrasive particles bonded to at least one surface of the body of the shape abrasive particle.

Item 34. A method of forming an abrasive particle comprising forming a mixture and attaching a plurality of abrasive particles to at least one surface of the mixture and forming a shaped abrasive particle having a body and the plurality of abrasive particles bonded to at least one surface of the body.

Item 35. The method of item 34, wherein forming a mixture includes at least one process selected from the group consisting of printing, molding, casting, cutting, ablating, punching, drying, cracking, sintering, humidifying, and a combination thereof.

Item 36. The method of item 34, wherein forming the mixture includes forming a precursor shaped abrasive particle and attaching a plurality of abrasive particles to at least one surface of the precursor shaped abrasive particle.

Item 37. The method of item 34, wherein forming the mixture includes depositing the mixture into an opening of a production tool and attaching a plurality of abrasive particles to at least one surface of the mixture in the opening of the production tool.

Item 38. The method of item 34, wherein the plurality of abrasive particles is attached the body of the mixture prior to substantial drying of the body.

Item 39. The method of item 34, wherein attaching the plurality of abrasive particles includes depositing the plurality of abrasive particles on a surface of the body, wherein depositing includes a process selected from the group consisting of blasting, projecting, pressing, gravity coating, molding, stamping, and a combination thereof.

Item 40. The method of item 34, wherein the mixture is formed on a production tool including a layer of abrasive particles including the plurality of abrasive particles.

Item 41. The method of item 34, wherein the process further comprising applying moisture to at least one surface of the mixture prior to attaching the plurality of abrasive particles.

Item 42. The method item 34, wherein attaching the plurality of abrasive particles includes directing a deposition material at the at least one surface, wherein the deposition material includes the plurality of abrasive particles and a carrier gas.

Item 43. The method item 42, wherein the carrier gas can include water vapor, steam, an inert gas element, and a combination thereof.

Item 44. The method item 34, wherein the mixture is formed on a production tool including a layer of abrasive particles including the plurality of abrasive particles.

Item 45. The method item 34, wherein the process further comprising applying moisture to at least one surface of the mixture prior to attaching the plurality of abrasive particles.

Item 46. The method item 45, wherein applying moisture includes directing a gas towards the at least one surface of the mixture prior to attaching the plurality of abrasive particles.

Item 47. The method item 45, wherein applying moisture includes directing steam at the at least one surface of the mixture in the production tool.

Item 48. The method item 45, wherein applying moisture includes wetting the at least one surface of the mixture for a sufficient time to change a viscosity of an exterior region of the at least one surface relative to a viscosity of the mixture at an interior region spaced apart from the exterior region.

Item 49. The method item 34, wherein the process further comprises changing a viscosity of an exterior region of the body including the at least one surface relative to a viscosity of an interior region of the mixture that is spaced apart from the exterior region, and applying the plurality of abrasive particles to the exterior region of the mixture.

EXAMPLES

Example 1

Three samples of shaped abrasive particles were made and tested for comparison of performance. A first comparative sample (CS1) was a conventional shaped abrasive particle commercially available as 3M984F from 3M Corporation. The body had an average width of 1400 microns and a height of approximately 300 microns. The shaped abrasive particles of Sample CS1 had a rare-earth element doped alpha-alumina composition, an average tip sharpness of approximately 20 microns, an average strength of approximately 606 MPa and an average cross-sectional shape factor of approximately 0.15. FIG. 14 includes an image of a shaped abrasive particle from Sample CS1.

Two samples (Sample S1 and Sample S2) representative of the embodiments herein were formed from a gel mixture including approximately 45-50 wt % boehmite. The boehmite was obtained from Sasol Corp. as Catapal B and modified by autoclaving a 30% by weight mixture of the Catapal B with deionized water and nitric acid. The nitric acid-to-boehmite ratio was approximately 0.025. The mixture was then placed in an autoclave and treated at 100° C. to 250° C. for a time ranging from 5 minutes to 24 hours. The autoclaved Catapal B sol was dried by conventional means. One may also use an alternative boehmite, commercially available as DISPERAL from Sasol Corp. The boehmite was mixed and seeded with 1% alpha alumina seeds relative to the total alumina content of the mixture. The alpha alumina seeds were made by milling of corundum using conventional techniques, described for example in U.S. Pat. No. 4,623,364. The mixture also included 45-50 wt % water and 2.5-4 wt % additional nitric acid, which were used to form the gel mixture. The ingredients were mixed in a planetary mixer of conventional design and mixed under reduced pressure to remove gaseous elements from the mixture (e.g., bubbles).

Sample S1 was formed by hand by depositing the gel into the openings of a stainless steel production tool. The cavities were open to both sides of the production tool, such that they were apertures extending through the entire thickness of the production tool. The cavities or openings of the production tool had an equilateral triangle two-dimensional shape as viewed top down, wherein the length was approximately 2.77 mm, the width was approximately 2.4 mm and the depth was approximately 0.59 mm. The surfaces of the openings in the production tool were coated with a lubricant of olive oil to facilitate removal of the precursor shaped abrasive particles from the production tool.

After depositing the gel, a first side of the mixture was humidified with a sponge while residing in the cavities of the production tool. A plurality of dried, unsintered particles of the same gel mixture used to form the mixture in the production tool were deposited on the humidified surface of the mixture residing in the cavities of the production tool. The plurality of unsintered particles were sieved using a 100 US mesh (ASTM E-11 with openings of 150 microns), such that the maximum particle size of the plurality of unsintered particles was less than 100 US mesh. The plurality of abrasive particles had an absorbed moisture content of approximately 10-15% for the total weight of the particles.

The production tool was then inverted and the opposite side of the gel mixture was humidified with a sponge while residing in the cavities of the production tool. The plurality of abrasive particles were then applied to the humidified surface, such that both major surfaces of the exposed gel mixture in the cavities of the production tool were coated with a plurality of abrasive particles. The excess abrasive particles were removed and the mixture and plurality of abrasive particles were dried in the cavities at approximately 50° C. for 10 minutes using IR lamps and a fan to form precursor abrasive particles. The precursor abrasive particles were removed from the production tool and sintered at approximately 1325° C. for approximately 10 minutes to achieve at least 98% theoretical density. The resulting abrasive particles had a body including a triangular two-dimensional shape including a length of approximately 1550 microns, a width of approximately 1350 microns, and a height of approximately 300 microns. FIGS. 11A and 11B include cross-sectional images of a representative abrasive particle of Sample S1. The abrasive particle of Sample S1 had an average strength of approximately 847 MPa, an average tip sharpness of 20 microns, a Shape Index of approximately 0.5, and an average cross-sectional shape factor of approximately 29%.

Sample S2 was formed using the same gel mixture as noted above for Sample S1. The gel mixture was placed in a die and extruded into openings of a production tool made of PEEK that was translated under the die as described in embodiments herein. The openings in the production tool were the same as described above for the production tool used in Sample S1, except that the production tool had a thickness of approximately 0.54 mm. In a first batch of Sample S2 (Sample Batch S2B1), a plurality of abrasive particles were deposited via gravity on a single side of the gel mixture while it resided in the cavities of the production tool. The plurality of abrasive particles was the same as used in Sample S1. FIG. 15 includes a top-down view and a side view of a representative abrasive particle of Sample Batch S2B1.

In a second batch of Sample S2 (Sample Batch S2B2), a plurality of abrasive particles was deposited on both major surfaces of the mixture while it resided in the cavities of the production tool. For a first major surface, the plurality of abrasive particles was deposited via gravity (e.g., by sprinkling the particles on the production tool and gel mixture in the cavities). For the opposite major surface, the plurality of abrasive particles was contained on a surface that is repeatedly pressed against the bottom surface of the production tool to apply the abrasive particles to the bottom surface of the gel mixture while it resided in the cavities. Thus, a plurality of abrasive particles was applied to both major surfaces of the gel mixture while it resided in the cavities. The plurality of abrasive particles was the same as described in Sample S1. FIG. 16 includes a top-down image and a side view image of an abrasive particle of Sample Batch S2B2.

In both batches of Sample S2, the production tool was translated through a set of rollers that applied pressure to the top and bottom surfaces of the production tool and assisted with imbedding the abrasive particles into the gel mixture while it resided in the cavities.

For both batches of Sample S2, the mixture was dried for approximately 5 minutes at approximately 50-55° C. using an IR lamp and a fan. For both batches of Sample S2, the samples were removed from the production tool and sintered according to the conditions as provided in Sample S1. The abrasive particles of Sample Batch S1B1 had an average tip sharpness of 20 microns, a Shape Index of approximately 0.5, and an average cross-sectional shape factor of approximately 21%. The abrasive particles of Sample Batch S1B2 had an average tip sharpness of 20 microns, a Shape Index of approximately 0.5, and an average cross-sectional shape factor of approximately 30%.

Samples CS1 and S1 were tested according to a single grit grinding test (SGGT) in a major surface orientation and side orientation. In conducting the SGGT, one single shaped abrasive particle is held in a grit holder by a bonding material of epoxy. The shaped abrasive particle is secured in the desired orientation (i.e., major surface orientation or side surface orientation) and moved across a workpiece of 304 stainless steel for a scratch length of 8 inches using a wheel speed of 22 m/s and an initial scratch depth of 30 microns. The shaped abrasive particle produces a groove in the workpiece having a cross-sectional area (AR). For each sample set, each shaped abrasive particle completes 15 passes across the 8 inch length, 10 individual particles are tested for each of the orientation and the results are analyzed. The test measures the tangential force exerted by the grit on the workpiece, in the direction that is parallel to the surface of the workpiece and the direction of the groove, and the net change in the cross-sectional area of the groove from beginning to the end of the scratch length is measured to determine the shaped abrasive particle wear. The net change in the cross-sectional area of the groove for each pass can be measured. For the SGGT, the net cross-sectional area of the groove is defined as the difference between the cross-sectional area of the groove below the surface and the cross-sectional area of the material displaced above the surface. Performance (Ft/A) is defined as the ratio of the tangential force to the net cross-sectional area of the groove.

The SGGT is conducted using two different orientations of the shaped abrasive particles relative to the workpiece. The SGGT is conducted with a first sample set of shaped abrasive particles in a major surface orientation wherein a major surface of each shaped abrasive particle is oriented perpendicular to the grinding direction such that the major surface initiates grinding on the workpiece. The results of the SGGT using the sample set of shaped abrasive particles in a major surface orientation allows for measurement of the grinding efficiency of the shaped abrasive particles in a major surface orientation.

The SGGT is also conducted with a second sample set of shaped abrasive particles in a side surface orientation wherein a side surface of each shaped abrasive particle is oriented perpendicular to the grinding direction such that the side surface initiates grinding of the workpiece. The results of the SGGT test using the sample set of shaped abrasive particles in a side orientation allows for measurement of the grinding efficiency of the shaped abrasive particles in a side orientation.

FIG. 17 includes a plot of force per total area removed from the workpiece for a front orientation (left hand bar) and side orientation (bar on the right) for Sample CS1 and Sample S1. The force per total area removed is a measure of the grinding efficiency of the shaped abrasive particles, with a lower force per total area removed indicating more effi-

cient grinding performance. As illustrated, Sample S1 demonstrated an essentially equivalent performance compared to Sample CS1. This result is quite remarkable considering those of skill in the art have previously disclosed that the most efficient cutting action of abrasive particles is likely to a result from particles having a high shape fidelity marked by sharp edges and smooth surfaces (i.e., like a chisel). See, for example, U.S. Pat. Nos. 4,261,706, 5,603,738 and US Pat. Publ. 20100319269. However, the abrasive particles of the embodiments herein have demonstrated notable performance differences when compared to conventional abrasive particles in light of the noted differences between the abrasive particles and conventional abrasive particles having relatively smooth sides and sharp edges. Notably, the abrasive particles herein have surfaces that are characterized by irregular contours including randomly arranged protrusions and valleys on one or more surfaces of the shaped abrasive particles, which is in contrast to the teachings of the prior art that suggest one should make the surfaces of a shaped abrasive particle smooth and the edges sharp for the best performance.

Abrasive particles Sample Batch S2B1 were formed into coated abrasive articles having the construction, which is provided below. A backing of finished cloth of 18 pounds per ream were obtained and coated with a make formulation including of a phenol formaldehyde as provided in Table 1. The web with the make coat was then followed by an electrostatic deposition process applying 40 pounds per ream of abrasive particles from Sample Batch S2B1. This partial structure of make coated web and grain was then dried in an oven for two hours at 80° C.

TABLE 1

Make Formulation		
Make Formulation Component	Vendor	Percentage
Filler NYAD Wollast 325	NYCO	34%
Wet Witcona 1260	Witco	0.10%
Resin, Single Comp 94-908	Durez	57%
Nalco 2341 Defoamer	Nalco	0.10%
PET-3MP (PTM)	Bruno Bloc	5.70%
Water	—	3.10%

The coated abrasive structures were then coated with 14 pounds per ream of a phenol formaldehyde size coat. The detailed composition of the size coat is presented in Table 2. The web was transported through a drier which had a dry bulb temperature setting of 120° C. for a period of two hours.

TABLE 2

Size Formulation		
Size Formulation Component	Vendor	Percentage
White Dye E-8046	Acrochem Corp	0.70%
Wet Witcona 1260	Witco	0.20%
Solmod Tamol 165A	Rohm & Haas	0.90%
Filler Syn Cryolite	Solvay	42.40%
Resin Single Comp 94-908	Durez	48.30%
Nalco 2341 Defoamer	Nalco	0.10%
PET-3MP Polythiol (PTM)	Bruno Bloc	2.50%
Dye Unisperse Black	Ciba	0.20%
Water	—	4.80%

The coated abrasive sample was then placed into a convection oven to undergo a post curing step in which the oven temperature was 125° C. for 12 hours.

A third sample of a coated abrasive, Sample S3 was also made. The abrasive particles of Sample S3 were made

according to the process used to make the abrasive particles of Sample Batch S2B1, but did not include deposition of a plurality of abrasive particles on the shaped abrasive particles. The construction of the coated abrasive of Sample S3 was the same as for the coated abrasive including the particles of Sample Batch S2B1. Particles of Sample CS1 were tested as a conventional coated abrasive article commercially available at 984F from 3M Corporation.

Each of the three different coated abrasive samples was tested according to the conditions summarized in Table 3. Notably, 2 sample coated abrasives were tested in each case to derive the results.

TABLE 3

Test conditions: Test mode: Dry, straight plunge	
	Constant MRR' = 4 inch ³ /min/inch
	Belt speed (Vs) = 7500 sfpm (38 m/s)
	Work material: 304 ss
	Hardness: 96-104 HRB
	Size: 0.5 × 0.5 × 12 inches
	Contact width: 0.5 in
	Contact Wheel: Steel
Measurements:	Power, Grinding Forces, MRR' and SGE
	Cum MR compared at SGE = 2.4 Hp · min/inch ³

FIG. 18 includes a plot of specific grinding energy versus cumulative material removed (at a material removal rate of 4 inch³/min inch) for each of the samples. It is notable that the coated abrasive utilizing the abrasive particles of the Sample Batch S2B1 performed better than the coated abrasive including the abrasive particles of Sample S3 and was essentially equivalent in performance to the coated abrasive sample including the abrasive particles of Sample CS1.

Example 2

A new sample of abrasive particles (Sample S4) was formed. The shaped abrasive particles of Sample S4 were formed from a gel mixture including approximately 45-50 wt % boehmite. The boehmite was obtained from Sasol Corp. as Catapal B and modified by autoclaving a 30% by weight mixture of the Catapal B with deionized water and nitric acid. The nitric acid-to-boehmite ratio was approximately 0.025 in the autoclave and treated at 100° C. to 250° C. for a time ranging from 5 minutes to 24 hours. The autoclaved Catapal B sol was dried by conventional means. The boehmite was mixed and seeded with 1% alpha alumina seeds relative to the total alumina content of the mixture. The alpha alumina seeds were made by milling of corundum using conventional techniques, described for example in U.S. Pat. No. 4,623,364. The mixture also included 45-50 wt % water and 2.5-4 wt % additional nitric acid, which were used to form the gel mixture. The ingredients were mixed in a planetary mixer of conventional design and mixed under reduced pressure to remove gaseous elements from the mixture (e.g., bubbles).

The gel was then placed in a die and extruded into openings of a production tool translated under the die at a suitable speed relative to the deposition rate such that the openings were sufficiently filled. The cavities were open to both sides of the production tool, such that they were apertures extending through the entire thickness of the production tool. The cavities or openings of the production tool had an equilateral triangle two-dimensional shape as viewed top down, wherein the length was approximately 2.77 mm, the width was approximately 2.4 mm and the depth was approximately 0.60 mm. The production tool had a thickness of approximately 0.60 mm. The surfaces of the openings in the production tool were coated with a lubricant

of canola oil to facilitate removal of the precursor shaped abrasive particles from the production tool.

After depositing of the gel into the openings of the production tool, a plurality of dried, unsintered, particles of the same gel material deposited in the openings were projected at the surface of the gel in the production tool. The plurality of abrasive particles were forcibly ejected toward the gel in the production tool using air as the carrier material at an approximate pressure of 40 psi. The process of applying the plurality of abrasive particles was completed in a container, wherein a vast majority of the excess or unbonded abrasive particles could be captured and recycled for future application processes. The gel was not humidified prior to deposition of the plurality of abrasive particles. Prior to deposition, the plurality of dried, unsintered particles were sieved using a 100 US mesh (ASTM E-11 with openings of 150 microns), such that the maximum particle size of the plurality of unsintered particles was less than 100 US mesh. The plurality of abrasive particles had an absorbed moisture content of approximately 10-15% for the total weight of the particles. Approximately 70% of the precursory shaped abrasive particle had a suitably high coverage of the plurality of dried, unsintered particles on the first major surface.

The excess dried, unsintered particles were removed and the mixture and plurality of abrasive particles were dried in the cavities at approximately 50° C. for 30 seconds using IR lamps and a fan to form precursor abrasive particles. The precursor abrasive particles were removed from the production tool, pre-sintered at 800° C. and sintered at approximately 1320° C. for approximately 15 minutes to achieve 98% theoretical density. The resulting abrasive particles had a body including a triangular two-dimensional shape including a length of approximately 1550 microns, a width of approximately 1350 microns, and a height of approximately 300 microns. The abrasive particle of Sample S4 had an average strength of approximately 20.3 MPa, an average tip sharpness of 30 microns, a Shape Index of approximately 0.5.

Another sample of abrasive particles (Sample CS4) were formed in the same manner as noted above for Sample S4, except that the abrasive particles did not include a plurality of abrasive particles on the surface of the shaped abrasive particles (i.e., unmodified shaped abrasive particles).

Two samples of coated abrasive articles were formed from the abrasive particles of Samples S4 and CS4 to create coated abrasive samples CAS4 and CACS4, respectively. The coated abrasive samples CAS4 and CACS4 were formed in the same manner used to form the coated abrasive samples of Example 1 for Samples CS1 and Sample Batch S2B1.

Each coated abrasive sample was tested according to the test outlined in Table 4 below. Two samples of the coated abrasives were tested in each case to derive the results.

TABLE 4

Test Conditions Test mode Dry, constant depth of cut (rise/fall)	
Measurements:	Constant MRR' = 2.3 inch ³ /min/inch Belt Speed (Vs) = 7500 sfpm (38 m/s) Work Material: 1045 Carbon Steel Hardness: 85-95 HRB Size: 1 × 0.25 inches Contact width: 0.25 inches Contact wheel for belt: Steel wheel Power, MRR' and SGE Cum. MR compared at SGE = 3.2 Hp min/inch ³

FIG. 19 includes a plot of specific grinding energy versus cumulative material removed from the workpiece. As illustrated, Sample CAS4 demonstrates improved cumulative

material removed and lower specific grinding energy, especially near the end of the test, compared to Sample CACS4.

Example 3

Five samples of abrasive particles (S5-1, S5-2, S5-3, S5-4, and S5-5) were formed to investigate the impact of the median particle size of the plurality of abrasive particles on the percent coverage of the abrasive particles on at least one surface of the shaped abrasive particles. Table 5 below summarizes the impact of the median particle size of the plurality of abrasive particles on the percent coverage of the plurality of abrasive particles on a first major surface of a shaped abrasive particle having a generally triangular two-dimensional shape having a length of approximate 1550 μm, a width of approximately 1350 μm, and a height of approximately 320 μm. The abrasive particles were formed in the same manner used to form Sample S4 of Example 2, except that the surfaces of the gel in the production tool were humidified prior to deposition of the plurality of dried, unsintered abrasive particles. The humidification process utilized steam (i.e. a mix of water in the gaseous state and suspended liquid particles) directed at the surfaces of the gel in the production tool.

TABLE 5

Sample ID	D50 of dried unsintered grains	Percentage of particles in the batch having covered
S5-1	125-89 μm	24%
S5-2	89-64 μm	38%
S5-3	64-45 μm	95%
S5-4	45-38 μm	96%
S5-5	76-45 μm	96%

FIGS. 20A-20E include images of the abrasive particles of Samples S5-1, S5-2, S5-3, S5-4, and S5-5, respectively. Notably, the median particle size of the plurality of abrasive particles relative to the size of the shaped abrasive particle had an impact on the percent coverage of the plurality of abrasive particles on the surface of the shaped abrasive particles.

Example 6

Four samples of abrasive particles (Sample S6-1, Sample S6-2, CS1, and Sample S6-3) were tested according to the single grit grinding test, as described in Example 1. Sample S6-1, Sample S6-2, and Sample S6-3 were formed in the same manner as Sample S4 of Example 2, except that Sample S6-1 had an average of 32 abrasive particles bonded to the major surfaces of the bodies of the shaped abrasive particles and Sample S6-2 had an average of 7 abrasive particles bonded to the major surfaces of the bodies of the shaped abrasive particles. Sample S6-3 had no plurality of abrasive particles bonded to the surface of the shaped abrasive particle.

FIG. 21 includes a plot of force per total area removed from the workpiece for a front orientation (left hand bar) and side orientation (bar on the right) for Sample S6-1, S6-2, S6-3, and CS1 (same as provided in Example 1). Surprisingly, Sample S6-2 demonstrated a greater variation in the cutting efficiency in the front orientation compared to Sample S6-1. Sample S6-1 also demonstrated a lower variation in the cutting efficiency compared to Sample S6-3 and CS1 in the front orientation.

51

Example 7

Two samples of abrasive particles were made. A first sample, Sample S7-1 was formed in the same manner used to form Sample S4 of Example 2 except that the surfaces of the gel in the production tool were humidified prior to deposition of the plurality of dried, unsintered abrasive particles. The humidification process utilized steam directed at the surfaces of the gel in the production tool. The plurality of abrasive particles attached to the first major surface of the shaped abrasive particle of Sample S7-1 had not been calcined or sintered. A second sample, Sample S7-2 was formed in the same manner used to form Sample S7-1, except that sintered alpha alumina grains were used for the plurality of abrasive particles attached to a first major surface of the shaped abrasive particles. Sample S7-1 demonstrated significantly better coverage, wherein 90-95% of the particles were suitably covered with the plurality of abrasive particles compared to Sample S7-2, which had only 60-70% of total particles formed with a suitable covering of the plurality of abrasive particles for the first major surface of the shaped abrasive particles. It is theorized that the sintered abrasive particles applied to the surface of the precursor shaped abrasive particles for Sample S7-2 did not bond well to the surface, but the green, unsintered grains applied to the surface of Sample S7-1 had improved bonding as the dried grains could re-gel with the humidified surface of the gel prior to further processing.

Example 8

Two samples of abrasive particles were made. A first sample, Sample S8-1 was formed in the same manner used to form Sample S4 of Example 2. The plurality of abrasive particles attached to the first major surface of the shaped abrasive particle of Sample S8-1 had not been calcined or sintered. A second sample, Sample S8-2 was formed in the same manner used to form Sample S8-1, except that no abrasive particles were deposited on the surfaces of the gel or resulting shaped abrasive particles.

Coated abrasive articles in the form of discs having a diameter of 7 inches were then created using the abrasive particles of Samples S8-1 and S8-2 to create samples CAS8-1 and CAS8-2, respectively. The samples CAS8-1 and CAS8-2 were formed according to the following process:

A make coat formulation as provided in Table 6 below was applied to a fiber backing material available from Sachsenroder having an average thickness of 0.95 mm. The wet laydown weight of the make coat was 9 lbs/ream+/-0.3 lbs and was applied using a two roll coat method using a steel roll over a 65-72 Shore A durometer hard rubber roll.

TABLE 6

Component	% based on Weight
Phenolic Resin (SI HRJ15993)	48.25
Solmod Silane A1100	0.44
Wet Witconate 1260	0.15
Filler NYAD Wollastonite 400	48.25
Water	2.91

The viscosity of the formulation was adjusted using water to a range of 9500 to 10500 cps at 100° F. After the make coat was applied, the abrasive particles of Samples S8-1 and

52

S8-2 were silane treated and applied to the make coat via electrostatic projection. The target grain weight for each of the samples was 55 lbs/ream+/-3 lbs. The particles of each of the samples were pre-heated before projection.

After projecting the particles onto the make coat and backing, the make coat was cured in a festoon oven using the following process: step 1) 42 minutes at 150° F.; step 2) 42 minutes at 170° F.; step 3) 38 minutes at 200° F.; step 4) 43 minutes at 215° F.; and step 5) 23 minutes at 230° F.

After the make coat was cured, a size coat having the formulation provided in Table 7 was applied to the surface of the particles and cured make coat.

TABLE 7

Component	% based on Weight
Phenolic Resin (SI HRJ15993)	53.04
Solmod Tamol 165A	0.84
Air Prod DF70 Defoamer	0.12
Black Pigment	2.41
Filler Syn Cryolite K	42.43
Water	1.16

The formulation of the size coat was adjusted using water to a viscosity range of 5400 to 5600 cps at 100° F. The size coat was applied using the same machine set up as used to apply the make coat. The size is controlled visually versus a known standard including a gap setting for the two roll coater was set at 0.045 inches.

After applying the size coat, the material was cured in a festoon oven using the following process: step 1) 20 minutes at 130° F. and 45% RH; step 2) 20 minutes at 170° F.; step 3) 20 minutes at 190° F.; step 4) 20 minutes at 210° F.; and step 5) 30 minutes at 235° F. The material is then rolled up and cured in a post cure oven for 12 hours at 250° F.

Upon removing the roll from the post cure oven the backing is flexed and re-moisturized by application of water.

Each of the coated abrasive samples were tested according to the conditions summarized below in Table 8.

TABLE 8

Test mode dry, constant force of rotating disc in a linearly traveling workpiece	
Measurements	Constant Force 8 lb
	Disc speed 6000 rpm
	Medium hard backup pad (e.g., rubber)
	Work piece linear speed 15 fpm
	Angle between disc and work piece is 10 degrees
	Work material A36 hot rolled steel
	Contact width 1/8 inch
	Grind time 1 minute intervals
	Grams cut per 1 minute interval
	Grams lost from disc per 1 minute interval
	End point: less than 2 g material removed in the interval

FIG. 22 includes a plot of relative performance (% cut) for Samples CAS8-1 and CAS8-2 relative to a conventional coated abrasive sample, Sample CACS8-3, available as 982C from 3M Corporation. As illustrated, Sample CAS8-1 had essentially the same performance compared to the conventional coated abrasive sample. By contrast, Sample CAS8-2 demonstrated a relative performance of approximately 20% less compared to the conventional sample the Sample CAS8-1.

All values, ratios, percentages and/or quantified data provided herein with respect to an abrasive particle of any embodiment, can also be an average derived from a random

and statistically relevant sample size of representative abrasive particles. For example, with respect to the percent coverage of the plurality of abrasive particles on the body, such percentages can also be calculated from a random and statistically relevant sample size of a batch of abrasive particles. The size of the sample may differ depending upon the size of the batch.

Notably, reference herein to a composition that is “free of” another material (e.g., material Z) may be interpreted as a composition that may have traces or impurity contents of material Z, but such contents do not materially affect the properties of the composition. For example, a material may be “free of” a particular species and such species may be present in an amount of not greater than 0.1% or not greater than 0.01% or not greater than 0.001%. This paragraph is not to be interpreted to narrow any other disclosure in the foregoing embodiments and is intended only to define those instances using the term “free of” Moreover, in instances where a particular species is not expressly identified, Applicants reserve the right to further define the material as being free of said particular species. However, unless the terminology “free of” is expressly recited, such a term cannot be interpreted to narrow those embodiments or claims using inclusive terms, such as “including,” “having,” “comprising,” and the like.

The above-disclosed subject matter is to be considered illustrative, and not restrictive, and the appended claims are intended to cover all such modifications, enhancements, and other embodiments, which fall within the true scope of the present invention. Thus, to the maximum extent allowed by law, the scope of the present invention is to be determined by the broadest permissible interpretation of the following claims and their equivalents, and shall not be restricted or limited by the foregoing detailed description.

The Abstract of the Disclosure is provided to comply with Patent Law and is submitted with the understanding that it will not be used to interpret or limit the scope or meaning of the claims. In addition, in the foregoing Detailed Description, various features may be grouped together or described in a single embodiment for the purpose of streamlining the disclosure. This disclosure is not to be interpreted as reflecting an intention that the claimed embodiments require more features than are expressly recited in each claim. Rather, as the following claims reflect, inventive subject matter may be directed to less than all features of any of the disclosed embodiments. Thus, the following claims are incorporated into the Detailed Description, with each claim standing on its own as defining separately claimed subject matter.

What is claimed is:

1. An abrasive particle comprising:

a shaped abrasive particle comprising a body; and a plurality of abrasive particles bonded to at least one surface of the body of the shaped abrasive particle, wherein the body of the shaped abrasive particle comprises a length>width>height, and the plurality of abrasive particles comprise a median particle size (D50), and wherein the median particle size (D50) is at least 0.1% and not greater than about 20% of the length of the body, at least 0.1% and not greater than about 20% of the width of the body, and at least 0.1% and not greater than about 20% of the height of the body.

2. The abrasive particle of claim 1, wherein the body of the shaped abrasive particle comprises a two-dimensional shape as viewed in a plane defined by a length and a width of the body selected from the first group consisting of regular polygons, irregular polygons, ellipsoids, numerals, Greek alphabet characters, Latin alphabet characters, Rus-

sian alphabet characters, complex shapes having a combination of polygonal shapes, a shape with linear and curved portions, and a combination thereof.

3. The abrasive particle of claim 1, wherein the plurality of abrasive particles is bonded to a major surface of the body.

4. The abrasive particle of claim 1, wherein the plurality of abrasive particles is bonded to at least two surfaces of the body.

5. The abrasive particle of claim 1, wherein the body includes a first major surface, a second major surface, and a side surface extending between the first major surface and the second major surface, wherein the plurality of abrasive particles is bonded to the first major surface and the side surface is essentially free of abrasive particles of the plurality of abrasive particles.

6. The abrasive particle of claim 1, wherein a portion of the abrasive particles of the plurality of abrasive particles is embedded within the at least one surface of the body.

7. The abrasive particle of claim 1, wherein a portion of the abrasive particles of the plurality of abrasive particles is bonded directly to the at least one surface of the body.

8. The abrasive particle of claim 1, wherein a portion of the abrasive particles of the plurality of abrasive particles are sinter-bonded to the at least one surface of the body of the shaped abrasive particle.

9. The abrasive particle of claim 1, wherein the plurality of abrasive particles are selected from the group consisting of oxides, carbides, nitrides, borides, oxycarbides, oxynitrides, oxyborides, natural minerals, synthetic materials, carbon-based materials, and a combination thereof.

10. The abrasive particle of claim 1, wherein the plurality of abrasive particles comprise a median particle size (D50) of at 0.1 microns and not greater than 80 microns.

11. The abrasive particle of claim 1, wherein the surface of the body including the plurality of abrasive particle comprises a random arrangement of the plurality of abrasive particles on a major surface of the body, and wherein a side surface of the body is essentially free of the plurality of abrasive particles.

12. The abrasive particle of claim 1, wherein the abrasive particle is incorporated into a fixed abrasive article.

13. The abrasive particle of claim 1, wherein the shaped abrasive particle comprises alpha alumina.

14. The abrasive particle of claim 1, wherein the shaped abrasive particle is essentially free of a binder.

15. The abrasive particle of claim 12, wherein the abrasive particle has a controlled orientation relative to one or more references axes within the fixed abrasive article.

16. The abrasive particle of claim 12, wherein the fixed abrasive article is a coated abrasive article and wherein the abrasive particle has a predetermined orientation relative to a backing of the coated abrasive article.

17. The abrasive particle of claim 16, wherein the at least one surface of the body has a controlled orientation relative to at least one of a longitudinal axis and a lateral axis of the backing.

18. The abrasive particle of claim 17, wherein the at least one surface of the body is oriented substantially perpendicular to the longitudinal axis and substantially parallel to the lateral axis.

19. The abrasive particle of claim 17, wherein the at least one surface of the body is oriented substantially parallel to the longitudinal axis and substantially perpendicular to the lateral axis.

20. An abrasive particle comprising:
 a shaped abrasive particle comprising a body; and
 a plurality of abrasive particles bonded to at least one
 surface of the body of the shaped abrasive particle,
 wherein the shaped abrasive particle comprises alpha 5
 alumina.

21. The abrasive particle of claim **20**, wherein the body
 includes a first major surface, a second major surface, and a
 side surface extending between the first major surface and
 the second major surface, wherein the plurality of abrasive 10
 particles is sinter-bonded to the first major surface and the
 side surface is essentially free of the plurality of abrasive
 particles.

22. An abrasive particle comprising:
 a shaped abrasive particle comprising a body; and 15
 a plurality of abrasive particles bonded to at least one
 surface of the body of the shaped abrasive particle,
 wherein the abrasive particle is incorporated into a fixed
 abrasive article, and
 wherein the abrasive particle has a controlled orientation 20
 relative to one or more references axes within the fixed
 abrasive article.

23. The abrasive particle of claim **22**, wherein the body
 includes a first major surface, a second major surface, and a
 side surface extending between the first major surface and 25
 the second major surface, wherein the plurality of abrasive
 particles is sinter-bonded to the first major surface and the
 side surface is essentially free of the plurality of abrasive
 particles.

* * * * *

30