


[54] AQUEOUS INK FOR INK JET PRINTING

[75] Inventors: Eiichi Akutsu, Ichikawa; Kakuji Murakami, Shizuoka; Tamotsu Aruga, Numazu, all of Japan

[73] Assignee: Ricoh Company, Limited, Tokyo, Japan

[21] Appl. No.: 179,408

[22] Filed: Apr. 5, 1988



Related U.S. Patent Documents

Reissue of:

[64] Patent No.: 4,581,071
 Issued: Apr. 8, 1986
 Appl. No.: 708,651
 Filed: Mar. 6, 1985

[30] Foreign Application Priority Data

Mar. 22, 1984 [JP] Japan 59-53554

[51] Int. Cl.⁴ C09D 11/00

[52] U.S. Cl. 106/22; 106/20;
 106/23

[58] Field of Search 106/20, 22, 23

[56] References Cited


FOREIGN PATENT DOCUMENTS

3344648 6/1984 Fed. Rep. of Germany .
 3401982 8/1984 Fed. Rep. of Germany .


Primary Examiner—Amelia Burgess Yarbrough
 Attorney, Agent, or Firm—Oblon, Spivak, McClelland,
 Maier & Neustadt

[57] ABSTRACT

An aqueous ink is disclosed, which comprises a first magenta dye having the formula (I), a second magenta dye having the formula (II), a water-soluble organic solvent having a boiling point of 100° C. or higher, water and a preservative and anti-mold agent:



wherein K and R² each represent



(in which R⁵, R⁶, R⁷ and R⁸ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt); R³ and R⁴ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt; and k, l, m and n each represent an integer of 0, 1 or 2.

6 Claims, No Drawings


AQUEOUS INK FOR INK JET PRINTING

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

BACKGROUND OF THE INVENTION


The present invention relates to an aqueous ink for ink jet printing by use of a dot printer and for use with ball point pens and fountain pens.

Conventionally, there is known an aqueous ink for ink jet printing in which a halogenated xanthene-type dye having the following formula (I) is employed:




Although the above dye has an excellent color tone and high solubility in water and polyhydric alcohols, it has the shortcoming that it fades significantly when exposed to light.

There is also known an aqueous ink for ink jet printing in which another xanthene-type dye having the following formula (II) is employed:



wherein R¹ and R² each represent



(in which R⁵, R⁶, R⁷ and R⁸ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt); R³ and R⁴ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt; and k, l, m and n each represent an integer of 0, 1 or 2.

The above dye having the formula (II) does not fade when exposed to light since it has high light resistance, but the color tone is slightly inferior to the first mentioned dye and the solubility in water and polyhydric alcohols is not as high as the first mentioned magenta dye.


Generally, it is preferable that magenta dyes have

high special absorption peaks in a wavelength range of 500 nm to 600 nm. However, most magenta dyes have also spectral absorption in the base of the absorption curves, for instance in the ranges of from 400 nm to 500 nm and from 600 nm to 700 nm and because of such spectral absorption, the color tone of such magenta dyes is not good. A magenta dye having a sharp peak in the first mentioned wavelength range, however, is somehow vulnerable to light and fades easily when exposed to light. Therefore it is not suitable for use as a dye of an ink jet printing ink.

SUMMARY OF THE INVENTION


It is therefore an object of the present invention to provide an aqueous magenta ink for ink jet printing which is particularly improved with respect to the color tone and light resistance as compared with conventional aqueous magenta inks.

According to the present invention, the above object is attained by an aqueous ink comprising a mixture of the previously discussed magenta dyes having the following formulas, a water-soluble organic solvent having a boiling point of 100° C. or higher, water and a preservative and anti-mold agent:



30

wherein R¹ and R² each represent



(in which R⁵, R⁶, R⁷ and R⁸ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt); R³ and R⁴ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt, and k, l, m and n each represent an integer of 0, 1 or 2.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

As mentioned previously, the dye having the formula (I) has high solubility in water and polyhydric alcohols and is excellent in color tone, but has poor light resistance. The dye having the formula (II) has excellent light resistance, but the solubility in water and polyhydric alcohols is not high and the color tone is slightly inferior.

Since the affinity between the dye of the formula (I) and the dye of the formula (II) is high and the dye of the formula (I) is very soluble in water and polyhydric alcohols, a mixture of the dye of the formula (I) and the dye of the formula (II) is highly soluble in water and polyhydric alcohols and significantly resistant to light, possibly because the dye of the formula (II) having high light resistance protects the dye of the formula (I) when

they are mixed. As a result, this mixture is suitable as a magenta dye composition for ink jet printing.

It is preferable that the mixing ratio of the dye of the formula (I) to the dye of the formula (II) in terms of part by weight be (1:3) to (3:1) and the total amount of the two dyes in the aqueous ink according to the present invention be in the range of 2.0 wt. % to 5.0 wt. % of the entire weight of the aqueous ink.

As the water-soluble organic solvent having a boiling point of 100° C. or higher, ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycols (having a molecular weight of about 200, about 300 and about 400) and glycerol and mixtures thereof can be employed. When the boiling point of such organic solvents is below 100° C., the solvents readily evaporate from the ink composition, so that the nozzles are plugged with the solid components of the ink during a non-use period.







As the preservative and anti-mold agents, for example, 2,2-dimethyl-6-acetoxy-dioxane-1,3-dehydrosodium acetate, p-hydroxy benzoic acid butyl ester, potassium sorbate, 2-pyridine thiol-1-oxidesodium salt, anionic surface active agents, Deltop 33 (commercially available from Takeda Chemical Industries Ltd.), and Bioside 880 (commercially available from Taisho Co., Ltd.) can be employed.

Further it is preferable that the pH of the aqueous ink according to the present invention be in the range of about 9.7 to about 10. If the pH is less than 9.7, the ink absorbs a CO₂ gas contained in the air, so that the pH of the ink is decreased and the metallic portions (for instance, made of Ni) of the nozzles are corroded with time.




Specific examples of the dye of the formula (II) for use in the present invention are as follows:

60

65



-continued



By referring to the following examples, the present invention will now be explained in detail.

EXAMPLE 1

A mixture of the following components was prepared:

	Parts by Weight
Magenta dye (I)	2.5
Magenta dye (II)-1	1.0
Glycerol	10
Diethylene glycol	10
Preservative and anti-mold agent (Deltop 33 commercially available from Takoda Chemical Industries, Ltd.)	0.5
Ion-exchanged water	75

To the above mixture, a small amount of sodium carbonate was added so that the pH of the mixture was adjusted to be 10. The mixture was heated to 70° C., stirred at the same temperature for 4 hours and then filtered through a membrane filter with a 0.22 μm mesh, whereby an aqueous ink No. 1 according to the present invention was prepared.

EXAMPLE 2

A mixture of the following components was prepared:

	Parts by Weight
Magenta dye (I)	2.5

-continued

	Parts by Weight
Magenta dye (II)-3	1.5
Glycerol	20
Diethylene glycol	25
Preservative and anti-mold agent (Deltop 33 commercially available from Takoda Chemical Industries, Ltd.)	0.5
Ion-exchanged water	60

To the above mixture, a small amount of sodium hydroxide was added so that the pH of the mixture was adjusted to be 9.7. The mixture was heated to 70° C., stirred at the same temperature for 4 hours and then filtered through a membrane filter with a 0.22 μm mesh, whereby an aqueous ink No. 2 according to the present invention was prepared.

EXAMPLE 3

A mixture of the following components was prepared:

	Parts by Weight
Magenta dye (I)	1.5
Magenta dye (II)-4	1.0
Magenta dye (II)-6	2.0
Glycerol	25
Diethylene glycol	20
Preservative and anti-mold agent (Deltop 33 commercially available from Takoda Chemical Industries, Ltd.)	0.5

-continued

	Parts by Weight
Ion-exchanged water	50

To the above mentioned, a small amount of sodium hydroxide was added so that the pH of the mixture was adjusted to be 9.8. The mixture was heated to 70° C., stirred at the same temperature for 4 hours and then filtered through a membrane filter with a 0.22 μm mesh, whereby an aqueous ink No. 3 according to the present invention was prepared. cl Comparative Example 1

A mixture of the following components was prepared:

	Parts by Weight
Magenta dye (I)	3.5
Glycerol	10
Diethylene glycol	10
Preservative and anti-mold agent (Deltop 33 commercially available from Takoda Chemical Industries, Ltd.	0.5
Ion-exchanged water	75

To the above mixture, a small amount of sodium carbonate was added so that the pH of the mixture was adjusted to be 10. The mixture was heated to 70° C., stirred at the same temperature for 4 hours and then filtered through a membrane filter with a 0.22 μm mesh, whereby a comparative aqueous ink No. 1 was prepared.

Comparative Example 2

A mixture of the following components was prepared:

	Parts by Weight
Magenta Dye (II)-1	3.5
Glycerol	10
Diethylene glycol	10
Preservative and anti-mold agent (Deltop 33 commercially available from Takoda Chemical Industries, Ltd.	0.5
Ion-exchanged water	75

To the above mixture, a small amount of sodium carbonate was added so that the pH of the mixture was adjusted to be 10. The mixture was heated to 70° C., stirred at the same temperature for 4 hours and then filtered through a membrane filter which a 0.22 μm mesh, whereby a comparative aqueous ink No. 2 was prepared.

The thus prepared aqueous inks No. 1 through No. 3 according to the present invention and the comparative aqueous inks No. 1 and No. 1 and No. 2 were subjected to the following tests:

Test 1

100 g of each aqueous ink was filtered through a 0.5 μm mesh membrane filter under a pressure of 2 atm and the time t₁ required to filter the ink through the membrane filter was measured. Each ink, without being filtered, was preserved for 2 months at a cooling and heating cycle of -10° C. for 12 hours and 40° C. for 12 hours. After this preservation test, the ink was filtered through the same membrane filter in the same manner as mentioned above and the time time t₂ required to filter the ink was measured and the increased percentage of the time required for filtering the ink after the preserva-

tion test to the time required for filtering before the preservation test, that is,

$$(t_2 - t_1) / t_1 \times 100\%$$

was calculated.

Test 2

The same aqueous ink was charged in 10 ink jet heads each having one nozzle having a diameter of 40 μm, and was caused to issue from the ink jet heads with a pressure of 3.5 kg/cm² and with vibrations at a frequency of 100 KHz to a sheet of plain paper which was placed at a distance of 30 mm from the nozzles, whereby the first ink-impinging position was determined. The ink was allowed to stand at 40° C., 30% RH for 2 months without being used for subjecting the ink to a non-use test. After this non-use test, the ink was again caused to issue from the 10 ink jet heads to the plain paper under the same conditions as mentioned above, so that the second ejected position was determined. Thus the deviation of the second ink-impinging position from the first ink-impinging position was obtained.

Test 3

The density d₁ of an image printed on the plain paper in the above Test 2 was first measured and the image was exposed to light by a carbon arc lamp at 40° C., 80% RH for 5 hours, so that the image density d₂ of the image exposed to the light was measured. The percentage of the decrease in the image density after the exposure, that is,

$$(d_1 - D_2) / d_1 \times 100\%$$

was obtained.

The results of the above tests are summarized in the following table:

TABLE

Aqueous Ink	Test 1 (%)	Test 2 (μm)	Test 3 (%)
No. 1	4	40	8
No. 2	7	25	6
No. 3	5	18	7
Comp. Ink No. 1	21	23	35
Comp. Ink No. 2	26	145	5

In Test 1, it is preferable that the percentage of the increase in the filtering time be not more than 10%.

In Test 2, it is preferable that the derivation be not more than 100 μm.

In Test 3, it is preferable that the fading ratio be not more than 10%.


The results in the above table indicate that the aqueous inks according to the present invention are far better in the preservability, ejection stability and light resistance than the comparative aqueous inks in which not a combination of the magenta dye of the formula (I) and the magenta dye of the formula (II), but either the magenta dye of the formula (I) or the magenta dye of the formula (II) was employed.

What is claimed is:


1. In an aqueous ink comprising a water-soluble organic solvent having a boiling point of 100° C., or higher, water and a preservative and an anti-mold agent, the improvement comprising a first magenta dye having the formula (I) and a second magenta dye having the formula (II):

11

12



wherein R¹ and R² each represent






(in which R⁵, R⁶, R⁷ and R⁸ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt or a carboxyl group in the form of an alkali metal salt); R³ and R⁴ each represent a lower alkyl group, an amino group, a sulfonic acid group in the form of an alkali metal salt, or a carboxyl group in the form of an alkali metal salt; and k, l, m and n each represent an integer of 0, 1 or 2.






2. An aqueous ink as claimed in claim 1, wherein the mixing ratio of said first magenta dye to the second magenta dye is in the range of (1:3) to (3:1).

3. An aqueous ink as claimed in claim 1, wherein the total amount of said first magenta dye and said second magenta dye is in the range of 2.0 wt. % to 5.0 wt. % of the entire weight of said aqueous ink.


4. An aqueous ink as claimed in claim 1, wherein said second magenta dye is selected from the group consisting of



-continued



and



-continued

5. An aqueous ink as claimed in claim 1, wherein said water-soluble organic solvent is selected from the group consisting of ethylene glycol, diethylene glycol, triethylene glycol, tetraethylene glycol, polyethylene glycols and glycerol and mixtures thereof.

6. An aqueous ink as claimed in claim 1, wherein said

15 preservative and anti-mold agent is selected from the group consisting of 2,2-dimethyl-6-acetoxy-dioxane-1,3-dehydrosodium acetate, p-hydroxy benzoic acid butyl ester, potassium sorbate, 2-pyridine thiol-1-oxidesodium salt and anionic surface active agents.

* * * * *

20

25

30

35

40

45

50

55

60

65


UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : RE 33,155
DATED : January 30, 1990
INVENTOR(S) : Eiichi Akutsu et al

Page 1 of 2

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 1, line 55, Formula II should read:



Column 2, line 45, "special" should read --spectral--.
Column 4, line 41, "entier" should read --entire--;
line 56, "commercialy" should read --commercially--;
line 58, "avaialbe" should read --available--.
Column 7, line 51, "Takoda" should read --Takeda--.
Column 8, line 45, "Takoda" should read --Takeda--;
line 68, "Takoda" should read --Takeda--.
Column 9, line 12, "Comparative Example 1" should be on
a separate line;
Column 9, line 22, "Takoda" should read --Takeda--;
line 43, "Takoda" should read --Takeda--;
line 50, "which" should read --with--;
line 55, delete second appearing "No. 1";
line 66, delete second appearing "time"

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : RE 33,155

Page 2 of 2

DATED : January 30, 1990

INVENTOR(S) : Eiichi Akutsu et al

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 10, line 32, "D₂" should read --d₂--.

**Signed and Sealed this
Thirtieth Day of July, 1991**

Attest:

HARRY F. MANBECK, JR.

Attesting Officer

Commissioner of Patents and Trademarks