

United States Patent [19]

Goward et al.

[11] E

Patent Number: Re. 33,876

[45] Reissued Date of Patent: Apr. 7, 1992

[54] THERMAL BARRIER COATING FOR NICKEL AND COBALT BASE SUPER ALLOYS

[75] Inventors: George W. Goward, Clinton, Conn.;
Delton A. Grey, Scotia, N.Y.;
Richard C. Krutenat, Lowell, Mass.

[73] Assignee: United Technologies Corporation,
Hartford, Conn.

[21] Appl. No.: 419,358

[22] Filed: Oct. 10, 1989

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: 4,248,940
Issued: Feb. 3, 1981
Appl. No.: 811,807
Filed: Jun. 30, 1977

U.S. Applications:

[62] Division of Ser. No. 612,439, Sep. 11, 1975, abandoned.

[51] Int. Cl.⁵ B32B 15/04

[52] U.S. Cl. 428/633; 428/678;
428/679; 428/685

[58] Field of Search 428/610, 632, 633, 678-685,
428/937, 939; 427/34, 405, 419.2, 423

[56] References Cited

U.S. PATENT DOCUMENTS

2,696,662	12/1954	Le Sech	29/195
2,755,210	7/1956	Sutphen et al.	148/16
2,763,919	9/1956	Kempe et al.	29/195
2,775,531	12/1956	Montgomery et al.	117/22
2,937,102	5/1960	Wagner	106/57
2,975,072	3/1961	Bryant et al.	117/68
3,006,782	10/1961	Wheildon, Jr.	117/46
3,031,331	4/1962	Aves, Jr. et al.	117/46
3,091,548	5/1963	Dillon, II	117/70
3,175,920	3/1965	Michael	117/70
3,197,291	7/1965	Michael	29/195
3,269,856	8/1966	Jones	117/70
3,322,515	5/1967	Dittrich et al.	29/191.2
3,410,716	11/1968	Hiltz	117/93.1
3,415,631	12/1968	Ault et al.	29/195
3,481,715	12/1969	Whalen et al.	29/195
3,522,064	7/1970	Valdsaar	106/57
3,542,530	11/1970	Talboom et al.	29/183.5
3,620,808	11/1971	Monroe, Jr.	117/69
3,625,732	12/1971	Nelson	117/43
3,672,849	6/1972	Bredzs et al.	29/195
3,676,085	7/1972	Evans et al.	29/194
3,715,790	2/1973	Reinberger	29/156.5 R
3,719,519	3/1973	Perugini	117/71 M
3,721,534	3/1973	Kubick	29/195
3,726,707	4/1973	Prosser et al.	117/70 C
3,754,903	8/1973	Goward et al.	75/171
3,758,233	9/1973	Cross	416/229
3,777,367	12/1973	Kalagidis	29/597
3,837,894	9/1974	Tucker, Jr.	117/70 A
3,846,159	11/1974	Bornstein et al.	117/71 M
3,864,164	2/1975	Hinchcliffe et al.	117/27
3,872,419	3/1975	Groves et al.	338/25
3,873,347	3/1975	Walker et al.	117/71 M
3,877,961	4/1975	Tank et al.	427/191

3,879,831	4/1975	Rigney et al.	29/182.5
3,890,069	6/1975	Telang et al.	418/178
3,890,456	6/1975	Dils	428/216
3,892,883	7/1975	Leclercq	427/34
3,911,891	10/1975	Dowell	123/191 A
3,927,223	12/1975	Takabatake et al.	427/34
3,928,026	12/1975	Hecht et al.	75/134
3,928,906	12/1975	Good et al.	29/460
3,941,899	3/1976	Kugler	427/34
3,951,612	4/1976	Gates et al.	29/195
3,957,454	5/1976	Bessen	29/194
3,977,660	8/1976	Nakahira	266/265
4,024,617	5/1977	McCormick	29/156.63
4,055,705	10/1977	Stecura et al.	428/633

FOREIGN PATENT DOCUMENTS

1214743 12/1970 United Kingdom .

OTHER PUBLICATIONS

P. W. Schilke, "Advanced Ceramic Seal Program (Phase I)", Apr. 1974.

Proceedings of the 1974 Gas Turbine Materials in the Marine Environment Conference; Fairbanks and Machlin, editors; Jun. 1975; cover page, Table of Contents, Preface.

Ryan et al.; "Development of a Ductile Corrosion Resistant Coating . . .", Jun. 1975; pp. 237, 242-243.

Bessen et al.; "Coating Life Assessment . . ."; Jun. 1975; pp. 259, 270.

Goward; "Coatings and Coating Processing . . ."; Jun. 1975; pp. 277, 286.

Dalal et al.; "Effect of Superalloy Corrosion . . ."; Jun. 1975; p. 297.

Singhal; "Corrosion-Resistant Structural Ceramic Materials . . ."; Jun. 1975; pp. 311, 321.

Schultz; "Laboratory Development of Corrosion Resistant Nickel-Base Superalloys . . ."; Jun. 1975; pp. 335, 344.

Wright; "Development of Dispersion-Strengthened CoCrAl Alloys . . ."; Jun. 1975; p. 357.

Thompson and Kuintzle; "The Effect of Salt Water . . ."; Jun. 1975; pp. 379, 387.

Clelland et al.; "Materials and Coating Developments . . ."; Jun. 1975; pp. 397, 412.

Stetson et al.; "A New Development-Controlled Composition . . ."; Jun. 1975; pp. 457, 464.

(List continued on next page.)

Primary Examiner—John Zimmerman

[57] ABSTRACT

Adherent, thermal shock-resistant protective coatings for nickel base super alloys are obtained by applying to the base metal a thin bond coat of an alloy of chromium aluminum and yttrium with materials selected from the group consisting of iron, cobalt, nickel and nickel-cobalt and applying thereover a continuously graded mixture of this material with a zirconia-based ceramic, the concentration of zirconia-based ceramic increasing from the bond coat to the outer layer. The zirconia ceramic may be stabilized by the addition thereto of amounts of magnesium oxide or other materials.

16 Claims, No Drawings

OTHER PUBLICATIONS

Dapkunas; "Evaluation of Hot-Corrosion Behavior . . ."; Jun. 1975; pp. 481-502.

Manty et al.; "Corrosion Susceptibility Testing . . ."; Jun. 1975; p. 503.

Weinert et al.; "Marine Gas Turbine Diagnostic Testing"; Jun. 1975; pp. 515, 525.

Lowell et al.; "Environmental Effects and Surface Protection . . ."; Jun. 1975; p. 535.

Shores; "The Use of Anodic Polarization in Fused Na₂SO₄ for Estimating Hot Corrosion Rates"; Jun. 1975; pp. 555, 561.

Berkowitz; "Effect of Applied Electrical Potentials . . ."; Jun. 1975; p. 571.

Dapkunas et al.; "Evaluation of the Hot-Corrosion Behavior . . ."; Nov. 1974.

Fairbanks et al.; "High-Rate Sputter Deposition of Protective Coating on Marine Gas Turbine Hot-Section Superalloys"; Jun. 1975; pp. 429-455.

THERMAL BARRIER COATING FOR NICKEL AND COBALT BASE SUPER ALLOYS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

This is a reissue of U.S. Pat. No. 4,248,980, which is a division of application Ser. No. 612,439, filed Sept. 11, 1975, now abandoned.

BACKGROUND OF THE INVENTION

Plasma-sprayed metallic/ceramic thermal barrier coatings utilizing stabilized zirconium oxide are widely used to protect metal components exposed to high temperature conditions and, in general, reduce both the temperature of the base metal and the effects of thermal transients. Such systems are commonly used in combination chambers, transition ducts and after burner liners in gas turbine engines and may also be used in protecting the vane platforms and air foils in various stages.

The most important feature of these coatings is their thermal insulating properties, since the magnitude of reduction in base metal temperature and transient thermal stress is related to the low thermal conductivity of the oxide component and the thickness of the coatings. In general, the desired properties of a practical thermal barrier coating are as follows:

- (a) low thermal conductivity;
- (b) adequate, adherence for resistance to thermal stress spalling, i.e., good interparticle and substrate bonding is required;
- (c) maximum metallurgic integrity and oxidative/hot corrosion resistance of the metallic constituent;
- (d) closest possible thermal expansion match between the ceramic and the substrate alloy;
- (e) adequate stabilization of the desired (cubic zirconia) crystal structure to minimize effects of the non-linear thermal expansion caused by structural transformation; and,
- (f) repairability during manufacturing and after field service.

The current state-of-the-art employs several ceramic-metal systems based on magnesia stabilized zirconia. In general, the base metal is a nickel or cobalt-base superalloy such as Hastelloy X, TD-nickel, or Haynes 188 which is coated with a bond layer of nickel-5% Al or nickel-20% chromium alloy, an intermediate metallic, stabilized zirconia ceramic layer and a top layer of stabilized zirconia. These layers are plasma-sprayed onto the base and the art now recognizes that improved performance and lower application costs can be achieved with nominally continuous grading processing methods by which the concentration of the zirconia is continuously increased from 0, at the interface between the bond layer and the base metal, to substantially 100 percent at the outer surface. Generally, these coatings are applied to a thickness of about 15 mils.

Detailed discussions representative of these various techniques can be found in U.S. Pat. Nos. 3,006,782 dated Oct. 31, 1961, to Wheildon for Oxide Coated Articles With Metal Undercoatings; 2,937,102 dated May 17, 1960, to Wagner for Zirconia Stabilization Control; 3,091,548 dated May 28, 1963, to Dillon for High Temperature Coatings; and 3,522,064 dated July

28, 1970, to Valdsaar for Stabilized Zirconia Containing Niobia and Calcium Oxide.

At present, one of the favored ceramic components is zirconia which can be used either alone or admixed with a material such as magnesium oxide, calcium oxide, yttrium oxide, La_2O_3 , Ce_2O_3 , which are known to stabilize the zirconia in the more desirable cubic form. Accordingly, one of the best means for protecting nickel and cobalt-base superalloys from high temperature environments now known to the art, consists of a zirconia-based ceramic coating which is bonded to the base coating by a nickel-chromium or nickel-aluminum alloy in which the concentration of the ceramic increases either gradually or in discreet increments from the substrate to the outer coating.

While these advanced systems have been found to give good service, failures, when they did occur, were observed to be caused by oxidative degradation of the metallic constituent followed by exfoliation of the outer ceramic layers. Further, when failures did occur, repair of the items has been difficult because of the resistance of the metallic constituent to available acid-stripping solutions. According to this invention, we have found that proper selection of the bond coat metal produces substantial improvements in the performance of the thermal barrier as well as in the ease of repairability of the article.

It is, accordingly, an object of this invention to provide an improved ceramic/metallic thermal barrier coating for nickel and cobalt-base superalloys. This, and other objects of this invention, will be readily apparent from the following description:

DESCRIPTION OF THE INVENTION

According to this invention we have found that the use of an alloy of 10-25% chromium, 10-18% aluminum and less than 1% yttrium with materials selected from the group consisting of cobalt, iron, nickel, and nickel-cobalt as the bond coat and grading metal for a zirconia-base ceramic, produces an unexpected improvement in the thermal resistance of the barrier. These materials are known as MCrAlY alloys and are described in detail in U.S. Pat. Nos. 3,542,530; 3,676,085; 3,754,903 and co-pending application for NiCoCrAlY Ser. No. 469,186 filed May 13, 1974 now U.S. Pat. No. 3,928,026. The concentration of the bond coat and the zirconia is preferably continuously graded from zero percent ceramic at the interface between the base material and the bond coat to 100 percent ceramic at the exposed surface. It should be recognized that while the continuous gradation is clearly the preferred embodiment, one or more layers of discretely increasing concentrations of zirconia can also be employed if equipment for continuous gradation is not available.

The zirconia used in this coating is preferably stabilized in the cubic form by the use of amounts of calcium oxide or magnesium oxide, as known to the art. In addition, the zirconia can also contain other oxides, such as Y_2O_3 and La_2O_3 , which are also known to be permanent cubic stabilizers for zirconia or metastabilizers such as Ce_2O_3 . It is also possible to add antistabilizers such as nickel oxide, zinc oxide and cobalt oxide in admixture with the cubic stabilized zirconia to tailor the characteristics of the ceramic portions with respect to thermal shock resistance by selecting compressive strengths and thermal coefficients of expansion corresponding to the characteristics of the metal substrate. These specific techniques, per se, do not form a part of

the applicants' invention and it should be recognized that the use of the term "zirconia," as hereinafter employed, includes zirconia-based ceramic materials which may be either pure zirconia or zirconia-admixed with one or more additives of which the above are exemplary.

The thermal barrier coatings of this invention can be applied by techniques known to the art using commercially available equipment. With respect to the following examples, the coatings were applied from a Plasmadyne model 1068 minigun using a 106 F45H-1 nozzle, a Plasmadyne model PS-61M 40 kilowatt power supply unit and two Plasmadyne model 1008A powder feeders. One powder feeder contained the bond coat alloy while the other power feeder contained the zirconia, with both feeders being pressurized with argon. By varying the flow rate of the individual power feeders, continuous gradation of the thermal barrier coating was obtained. The choice of the powder size of the materials is not critical and with the equipment used, it was found that the particle size of the metal bond coat alloy was preferably in the range of $-270+400$. This was not critical but merely idiosyncratic to the equipment used in that smaller particle sizes tended to melt too quickly and clog the nozzle of the spray gun.

EXAMPLE 1

Hastelloy X panels were coated with continuous graded nickel chromium plus MgO stabilized zirconia and were subjected to 100 hour and 200 hour static oxidation tests at 1800° F. Metallographic testing of the coating structures after test indicated that the nickel chromium component has substantially oxidized after 100 hours. Another sample was subjected to an oxidation test for one hour at 2000° F. followed by a water quench. Metallographic examination of the coating structure after these treatments showed degraded nickel almost completely oxidized, with cracks running vertically toward the base metal through the coating. Corresponding tests were also performed with Hastelloy X panels coated with 67.5% cobalt, 20% chromium, 12% aluminum, 0.5% yttrium plus 17% MgO stabilized zirconia with coating thicknesses varying between 0.009 to 0.014 inches. Metallographic examination of these samples after completion of the tests corresponding to the above, indicated substantially less oxidation of the bond coat which necessarily leads to a longer expected coating life. Fluidized bed testing of the various samples was also performed in which the specimens were exposed for two minutes at 1800° F. followed by two minutes cooling at room temperature. Using the cobalt, chromium aluminum, yttrium-containing samples, testing was discontinued after 100 cycles with satisfactory adherence of the coating to the substrate alloy and upon metallographic examination, the components showed only partial oxidation. The nickel chromium samples, however, had been completely oxidized.

EXAMPLE 2

The inner surfaces of several full-scale Hastelloy X burner cans from a JT8D-17 gas turbine engine were coated with the continuously graded MgO/ZrO₂-cobalt/chromium/aluminum/yttrium alloy noted above and subjected to experimental engine testing. In an 150 hour endurance test this alloy was substantially better with respect to edge spallation than the conventional 17% MgO/ZrO₂ Ni-20% coating run on another burner in the same test.

While this invention has been described with respect to several specific examples thereof, it should not be construed as being limited thereto. For example, while the preferred embodiment of the invention employs the cobalt, chromium, aluminum, yttrium alloy set forth above, and 17% MgO stabilized ZrO₂, other compositions can be employed by workers skilled-in-the-art. The specific cobalt, chromium, aluminum, yttrium alloy employed in the examples is representative of the broad class of materials consisting of 15-40% chromium, 10-25% aluminum and less than 1% yttrium alloyed with iron, cobalt, nickel, or nickel-cobalt. This general class of materials is described, for example, in U.S. patents cited above. Accordingly, various modifications of this invention may be made by workers skilled-in-the art without departing from the scope of this invention which is limited only by the following claims, wherein:

We claim:

1. [In a] *A thermally protected [superalloy structure] gas turbine engine combustion chamber* which comprises a substrate of a material selected from the group consisting of nickel and cobalt-base superalloys, a metal bond coat on said substrate and an oxide stabilized zirconia-base ceramic thermal barrier coating on said bond coat, [the improvement] wherein said bond coat is an alloy of chromium, aluminum and yttrium with a metal selected from the group consisting of iron, [cobalt,] nickel and a mixture of nickel and cobalt.

2. The [structure] *combustion chamber* of claim 1 wherein said ceramic thermal barrier material is admixed with the bond coat alloy in a manner such that the concentration of the ceramic material increases continuously from the substrate to the finished surface.

3. [The structure of claim 1] *A thermally protected gas turbine engine combustion chamber which comprises a substrate of a material selected from the group consisting of nickel and cobalt-base superalloys, a metal bond coat on said substrate and an oxide stabilized zirconia-base ceramic thermal barrier coating on said bond coat, wherein said bond coat is an alloy of chromium, aluminum and yttrium with a metal selected from the group consisting of iron, cobalt, nickel and a mixture of nickel and cobalt, and wherein said bond coat alloy is 15-40 percent chromium, 10-25 percent aluminum and 0.01-1 percent yttrium.*

4. The [structure] *combustion chamber* of claim 3 wherein said alloy is [a nickel,] chromium, aluminum and yttrium [alloy], with the balance a mixture of nickel and cobalt.

5. The [structure] *combustion chamber* of claim 1 wherein said alloy is [a nickel,] chromium, aluminum and yttrium [alloy], with the balance a mixture of nickel and cobalt.

[6. A coated article of manufacture having a thermal barrier coating system comprising

a substrate selected from the group consisting of nickel-base alloys and cobalt-base alloys,

a bond coating consisting essentially of a material selected from the group consisting of NiCrAlY, CoCrAlY and mixtures thereof covering said substrate, and

a thermal barrier coating consisting essentially of zirconia stabilized with another oxide.]

[7. The thermal barrier coating system of claim 6 wherein said oxide is selected from the group consisting of ZrO₂-Y₂O₃ and ZrO₂-MgO.]

5

[8. The article of claim 6 wherein said bond coating is 15 to 40 percent chromium, 10 to 25 percent aluminum, and 0.01 to 1 percent yttrium.]

[9. A method of coating surfaces of nickel-base and cobalt-base alloys comprising:

a. coating said surfaces with a bond coating consisting essentially of a material selected from the group consisting of NiCrAlY and CoCrAlY and mixtures thereof; and

coating the coated surfaces formed in step (a) with a thermal barrier coating consisting essentially of an oxide stabilized zirconia.]

[10. The method of coating a metal surface as claimed in claim 9 where said oxide is selected from the group consisting of $ZrO_2-Y_2O_3$ and ZrO_2-MgO .]

[11. The method of claim 9 wherein said bond coating is 15 to 40 percent chromium, 10 to 25 percent aluminum and 0.01 to 1 percent yttrium.]

12. A thermally protected gas turbine engine component which comprises a substrate of a nickel base superalloy, a metal bond coat on said substrate and an oxide stabilized

6

zirconia-base ceramic thermal barrier coating on said bond coat, wherein said bond coat is an alloy of chromium, aluminum and yttrium, with the balance of a mixture of nickel and cobalt, and wherein said engine component is selected from the group consisting of combustion chambers, transition ducts, after burner liners, vane platforms and airfoils.

13. The component of claim 12 wherein said bond coat is 15-40 percent chromium, 10-25 percent aluminum, 0.01-1 percent yttrium, with the balance a mixture of nickel and cobalt.

14. The component of claim 13 wherein the concentration of bond coat and zirconia is continuously graded.

15. The component of claim 13 wherein the concentration of bond coat and zirconia is graded such that the engine component is characterized by more than one layer of discretely increasing concentrations of zirconia.

16. The component of claim 13 comprising one layer of 100 percent ceramic of the bond coat.

* * * * *

25

30

35

40

45

50

55

60

65

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : Re. 33,876
DATED : April 7, 1992
INVENTOR(S) : George W. Goward et al.

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 1 lines 20 to 21, delete "combination" and replace it with -- combustion--.

Column 3 line 15, delete "power" and replace it with --powder--.

Column 3 line 17, delete "power" and replace it with --powder--.

Column 3 line 67, insert --Cr-- between "Ni-20%" and "coating".

Claim 12, column 6 line 3, delete "of".

Claim 16, column 6 line 20, delete "of" and replace it with --on--.

Signed and Sealed this
Twenty-third Day of June, 1992

Attest:

DOUGLAS B. COMER

Attesting Officer

Acting Commissioner of Patents and Trademarks