



US00RE34037E

United States Patent [19]

[11] E

Patent Number: **Re. 34,037**

Inoue et al.

[45] Reissued Date of Patent: Aug. 18, 1992

[54] SUPPORT FOR BIOMEDICAL IMPLANT DEVICE

[52] U.S. Cl. 604/93; 604/174, 604/175

[75] Inventors: Masahide Inoue; Takeshi Ichitsuka; Yasuhiko Hirayama; Shozo Koshikawa, all of Tokyo; Tateki Kitaoka, Ichikawa; Nobuo Nakabayashi, Matsudo; Tatsumichi Takeda, Koganei; Osamu Minoo, Miyoshi, all of Japan

[58] Field of Search 604/93, 174, 175, 185, 604/891.1

[73] Assignee: Asahi Kogaku Kogyo K.K., Tokyo, Japan

[56] **References Cited**
U.S. PATENT DOCUMENTS

[21] Appl. No.: 642,582

3,673,612	7/1972	Merrill et al.	604/93 X
3,752,162	8/1973	Newash	604/93
4,479,796	10/1984	Kallok	604/175 X
4,543,088	9/1985	Bootman et al.	604/93
4,610,692	9/1986	Eitenmuller et al.	604/891 X
4,632,670	12/1986	Mueller et al.	604/174
4,798,585	9/1986	Eitenmuller et al.	604/891 X

[22] Filed: Jan. 17, 1991

Primary Examiner—Allen M. Ostrager
Attorney, Agent, or Firm—Sughrue, Mion, Zinn, Macpeak & Seas

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: 4,798,585
Issued: Jan. 17, 1989
Appl. No.: 59,445
Filed: Jun. 8, 1987

[57] **ABSTRACT**

A support for a biomedical implant device in which the support has a surface layer composed of a biocompatible calcium phosphate material such as sintered hydroxyapatite with a porosity of 50-60% and pore size of 0.5-500 micrometers. Preferably, the surface layer is formed with projections or recesses of a few hundred micrometers size.

[30] **Foreign Application Priority Data**

Jun. 6, 1989 [JP] Japan 61-131570

[51] Int. Cl.⁵ A61M 11/00

24 Claims, 4 Drawing Sheets




FIG. 1
PRIOR ART




FIG. 2
PRIOR ART




FIG. 3




FIG. 7




FIG. 8A




FIG. 8B




FIG. 4




FIG. 5




FIG. 6




FIG. 9




FIG. 10



FIG. 11A





FIG. 11B



SUPPORT FOR BIOMEDICAL IMPLANT DEVICE

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a support for retaining biomedical implant devices such as a catheter for peritoneal dialysis, an extracorporeal shunt for hemodialysis, a tube for an ascites recirculation circuit, a drain tube, an air tube for an artificial heart, an electric circuit tube, and drug reservoir to be implanted under the skin. In particular, the present invention relates to a support for such biomedical implant devices that manifests enhanced biocompatibility and which allows them to be retained in the body over a prolonged period without permitting bacterial ingress.

2. Background of the Invention

An example of the support conventionally used to fix a biomedical implant device in the human body is a cuff which is used with a catheter for peritoneal dialysis. As shown in FIG. 1, a catheter 1 is inserted through the skin 10 of the patient, the subcutaneous layer of fat 11, the fascia 12, the muscular tunic 13 and the peritoneum 14. The catheter 1 is retained in the body so as to permit injection or discharging of a dialyzing solution through the catheter 1. In this case, a cuff 2 attached to the catheter 1 is used as a support for functionally retaining the catheter 1 in the body over an extended period and is generally sutured in living tissues at the end of a surgical operation. The cuff 2 is typically made of such materials as knitted or unknitted fabrics of synthetic or natural fibers, plastic or plastic film.

Another prior art biomedical implant device proposed to date is a drug reservoir for subcutaneous implantation. As shown in FIG. 2, a reservoir 15 is implanted below the skin layer 10 and is composed of a drug cell 16. Holes 17 on projections guide a retaining thread (suture). The intended drug is injected into the cell 16 through a silicone or synthetic rubber wall 18. A silicon tube 19 serves as a passage for introducing the drug into the affected site of part of the body such as a blood vessel or muscle. Stability of the retained reservoir 15 is required for a prolonged period in order to allow for periodic supply of the drug into the reservoir through the wall 18 with syringe.

Conventional supports such as cuffs that are formed of cellulosic or synthetic fibers, plastics, titanium or silicone resins show poor biocompatibility and poor adhesion to living tissues because of the nature of their constituent materials. As a result, during prolonged use of biomedical implant devices within the body, they might be displaced in position or bacterial ingress may occur in the gap between the device and the surrounding tissues.

SUMMARY OF THE INVENTION

A general object of the invention is to eliminate the above described problems in a biomedical implant device.

A particular object, therefore, of the present invention is to provide a support for biomedical implant device that affords enhanced adhesion to tissues and al-

lows the implanted biomedical device to be retained stably in the body without permitting bacterial ingress.

Another object of the present invention is to provide a support which, in addition to the enhanced adhesion to surrounding tissues, permits the tissue to be anchored in the support, with subsequent increase in the stability of the support in the body.

A further object of the present invention is to provide a support possessed of increased strength and enhanced adhesion to the biomedical implant device.

These objects are achieved by a biomedical implant device having a support made of a biocompatible calcium phosphate compound as the material of the surface layer. The calcium phosphate material may be porous, thereby allowing anchoring of the tissue. To provide strength, the support is made in multiple layers. The porous or solid support may have in its surface many recesses formed by etching, ion milling or other techniques.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a sketch of a conventional catheter with a cuff in the implanted state.

FIG. 2 is a sketch of a conventional drug reservoir in the subcutaneously implanted state.

FIGS. 3, 7, 8A and 8B and 9 are cross-sectional views of cuffs according to four embodiments of the present invention.

FIGS. 4 to 6 are pictorial representations of supports for biomedical implant device in the state where they adhere to surrounding tissues.

FIG. 10 is a sketch showing a cross section of the surface layer of a cuff according to a fifth embodiment of the present invention.

FIGS. 11A and 11B are a plan and a cross-sectional view, respectively, of a drug reservoir to be implanted under the skin according to a sixth embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The support for biomedical implant device of the present invention is hereinafter described in detail. FIG. 3 shows a cuff 2 prepared in accordance with one embodiment of the present invention. A catheter 1 made of a plastic or some other suitable material is connected to the cuff 2 that is formed of a biocompatible calcium phosphate material such as sintered hydroxyapatite, bioglass or sintered tricalcium phosphate (TCP). The cuff 2 which is formed of sintered hydroxyapatite can be prepared from a hydroxyapatite powder by the following procedure. A hydroxyapatite powder comprising irregularly shaped particles of 0.1–1 μm in average size is blended with a hydroxyapatite powder comprising spherical particles of 2–20 μm in average size. The blend is intimately mixed with water and a blowing agent. The mix is expanded and dried in a thermostatic dryer. A suitable blowing agent is an aqueous solution of hydrogen peroxide or egg albumin.

The so prepared porous hydroxyapatite is machined into a cuff-shaped structure which is fired at a temperature of 1,000°–1,250° C. to produce the intended cuff 2. The cuff has a porosity of 5–60%, preferably 20–40%, with the pore size being adjusted to 0.5–500 μm , preferably 5–200 μm . The value of the porosity is determined by comparing the density of the solid material with that of the porous material. The percentage difference is the porosity and represents generally the volume percent-

age of voids. The cuff 2 is then joined to a catheter 1 which is implanted in the body. Such a cuff exhibits good biocompatibility while it is being gradually fused to surrounding tissues with time. Any bacterial ingress that might occur via the outer surface of the catheter is completely prevented at least by the cuff 2, with the result that the catheter 1 can be stably retained in the body over a prolonged period.

Adjustment of the porosity and pore size of the cuff to the above-specified values ensures spontaneous formation of small voids in its surface with the result that the effective surface area of the cuff 2 is sufficiently increased to provide enhanced adhesion to the surrounding tissues. If the porosity of the cuff is less than 5%, strong adhesion to the surrounding tissues is not attained. If the porosity exceeds 60%, the strength of the cuff 2 is drastically decreased. If the pore size of the cuff is less than 0.5 μm , tissue cells are unable to enter the cuff through voids. If the pore size exceeds 500 μm , the desired anchoring of tissues in the porous structure of the cuff cannot be attained.

FIGS. 4, 5 and 6 show that the adhesion between the cuff and surrounding tissues increases as the porosity of the cuff increases. As can be seen from the comparison of FIG. 4 (20% porosity), FIG. 5 (30% porosity) and FIG. 6 (56% porosity), strong adhesion is imparted by the tissues (colored portion) penetrating into the sintered hydroxy apatite (white portion).

FIGS. 7 shows a cuff according to a second embodiment of the present invention. A catheter 1 is connected to a cuff 2. The surface of the cuff 2 is provided with small projections 3 (5-1,000 μm in height) that are formed by cutting or some other machining technique. The cuff 2 having such small projections 3 on its surface serve as a brake or impediment resisting movement when it is implanted in the body. Therefore, the cuff 2 with the projections 3 allows the catheter 1 to be securely fixed in the body right after it has been implanted by a surgical operation.

FIGS. 8A and 8B show a cuff according to a third embodiment of the present invention. A catheter 1 is connected to a cuff 2 that is provided with holes 3 for facilitating post-operational suturing. Two variations of such a cuff 2 are shown in the two drawings.

FIG. 4 shows a cuff according to a fourth embodiment of the present invention. A catheter 1 is connected to a cuff 2 that is composed of a surface-layer portion 4 and an inner-layer portion 5. The surface-layer portion 4 is formed of a biocompatible calcium phosphate material having a comparatively high porosity. The inner-layer portions 5 is formed of a biocompatible calcium phosphate material having a comparatively low porosity. The inner-layer portion 6 may be formed on other materials such as titanium, alumina and plastics and, if plastic materials are used, greater facility is ensured when connecting the cuff 2 to the catheter 1. The advantage of this fourth embodiment is that the inner-layer portion 6 imparts a greater strength to the cuff 2 so that the catheter 1 can be stably retained within the body.

FIG. 10 shows a cuff according to a fifth embodiment of the present invention. A catheter 1 is connected to a cuff 2 that is prepared from sintered hydroxyapatite which is surface-treated by etching or ion milling to form recesses 7 in its surface having diameters of 0.5-500 μm . The multiple recesses 7 help increase the surface area of the cuff 2 so as to provide further enhanced adhesion to surrounding tissues. The concept of

this embodiment is applicable not only to the case where the cuff 2 has a solid structure but also to the case where it is made of a porous structure. If recesses 7 are formed in the porous surface that has been attained by the sintering described above, the resulting cuff 2 provides not only good adhesion to surrounding tissues but also effective anchoring of the issue in the porous surface of the cuff 2, thereby ensuring greater stability of the catheter in the body.

FIGS. 11A and 11B shows a drug reservoir to be implanted under the skin according to a sixth embodiment of the present invention. Components which are the same as those shown in FIG. 2 are identified by like numerals. The reservoir 15 is surrounded by a casing 20 that has holes 17 for suturing. The casing 20 is formed of a biocompatible calcium phosphate material. Any of the techniques employed in the above-described first to fifth embodiments is applicable to the casing 20 so that it will display sufficient biocompatibility and adhesion to the surrounding tissues to ensure that the reservoir 15 is stably retained in the body over a prolonged period.

As described in the foregoing pages, the support for biomedical implant device of the present invention is made of a biocompatible calcium phosphate material either entirely or at least in the part which is to contact surrounding tissues when the device is implanted in the body. As a result, the support has improved adhesion to the living tissues and allows the implanted biomedical device to be stably retained in the body without permitting bacterial ingress.

What is claimed is:

1. A biomedical implant device for implantation within tissue of a body, comprising: a support having a surface layer to be contacted with said tissue and composed of a biocompatible calcium phosphate material; and a medically operative part at least partially enclosed by said surface layer.

2. A biomedical implant device as recited in claim 1, wherein said calcium phosphate material is sintered hydroxyapatite.

3. A biomedical implant device as recited in claim 1, wherein said calcium phosphate material has a porosity of 5-60%.

4. A biomedical implant device as recited in claim 3 wherein said porosity is in a range of 20-40%.

5. A biomedical implant device as recited in claim 2, wherein said calcium phosphate material has a porosity of 5-60%.

6. A biomedical implant device as recited in claim 1, wherein said calcium phosphate material has a porosity of 5-60% and has voids with an average pore size of 0.5-500 micrometers.

7. A biomedical implant device as recited in claim 6, wherein said average pore size is 5-200 micrometers.

8. A biomedical implant device as recited in claim 2, wherein said calcium phosphate material has a porosity of 5-60% and has voids with an average pore size of 0.5-500 micrometers.

9. A biomedical implant device as recited in claim 8, wherein said average pore size is 5-200 micrometers.

10. A biomedical implant device as recited in claim 1, wherein said support further comprises at least one inner layer inside said surface layer of a material of greater strength than said surface layer.

11. A biomedical implant device as recited in claim 10, wherein said inner layer comprises sintered hydroxyapatite with a porosity significantly less than that of said surface layer.

5

12. A biomedical implant device as recited in claim 1, wherein said surface layer includes a plurality of surface projections having a average height of 5-1000 micrometers.

13. A biomedical implant device as recited in claim 5, wherein said surface layer includes a plurality of surface projections having heights of 5-1000 micrometers.

14. A biomedical implant device as recited in claim 1, wherein said surface layer includes a plurality of surface recesses having diameters of 0.5-500 micrometers.

15. A biomedical implant device as recited in claim 5, wherein said surface layer includes a plurality of surface recesses having diameters of 0.5-500 micrometers.

16. A biomedical implant device as recited in claim 1, wherein said medically operative part comprises a catheter and said support acts as a cuff surrounding said catheter.

17. A biomedical implant device as recited in claim 1, wherein said medically operative part comprises a drug reservoir and said support at least partially covers said drug reservoir.

18. *A biomedical implant device for implantation within the tissues of a body, comprising: a support in the form of a cuff having a surface layer to be contacted with said tissues and composed of a biocompatible calcium phosphate material.*

19. *A biomedical implant device for implantation within the tissues of a body, comprising: a support having a surface layer to be contacted with said tissues and composed of a biocompatible calcium phosphate material, said support being in the form of a catheter cuff, said cuff including*

6

fixing means which, in use, operates to stably retain a catheter within the body.

20. *A drug reservoir device for implantation within the body of a drug recipient, comprising: a drug reservoir, a casing formed of a biocompatible calcium phosphate material and substantially covering at least one surface of said reservoir and being in contact with tissues of the body in use, a drug entry location for receiving quantities of a drug to be delivered to the body, and a drug exit location through which said drug is supplied to the body.*

21. *A biomedical implant device for implantation within the tissues of a body, comprising: a support in the form of a catheter cuff having a surface layer to be contacted with said tissues and composed of a biocompatible calcium phosphate material.*

22. *A biomedical implant device for implantation within the tissues of a body, comprising: a support having a surface layer to be contacted with said tissues and composed of a biocompatible calcium phosphate material, said support being in the form of a cuff, said cuff including fixing means which, in use, operates to stably contact a member to be held in place in the body by said cuff.*

23. *A device as claimed in claim 22, wherein said fixing means includes an interior surface of said cuff.*

24. *A drug reservoir device for implantation within the body of a drug recipient, comprising: a drug reservoir, a casing formed of a biocompatible calcium phosphate material and substantially covering a surface of said reservoir and being in contact with tissues of the body in use, a drug entry location for receiving quantities of a drug to be delivered to the body, and a drug exit location through which said drug is supplied to the body.*

* * * * *

35

40

45

50

55

60

65