



US00RE34904E

United States Patent [19]

[11] E

Patent Number: **Re. 34,904**

Just et al.

[45] Reissued Date of Patent: **Apr. 11, 1995**

[54] **ALKYLARYL HYDROPHOBICALLY MODIFIED CELLULOSE ETHERS**

2,201,663 9/1939 Ellsworth et al. 536/56
2,205,487 6/1940 Meinel et al. 536/56

(List continued on next page.)

[75] Inventors: **Ernst K. Just**, Wilmington, Del.;
Thomas G. Majewicz, Kennett Square, Pa.; **Arjun C. Sau**, Newark, Del.

[73] Assignee: **Hercules Incorporated**, Wilmington, Del.

[21] Appl. No.: **86,872**

[22] Filed: **Jul. 8, 1993**

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: **5,120,838**
Issued: **Jun. 9, 1992**
Appl. No.: **428,912**
Filed: **Oct. 30, 1989**

[51] Int. Cl.⁶ **C08B 11/08; C08B 11/16; C08B 11/187; C08B 11/193**

[52] U.S. Cl. **536/90; 536/93; 536/94; 536/96; 524/43; 524/44; 106/169; 106/170**

[58] Field of Search **536/84, 90, 93, 94, 536/96; 524/43, 44; 106/169, 170**

[56] References Cited

U.S. PATENT DOCUMENTS

T976,002	11/1978	Vanderslice	424/49
1,451,331	4/1923	Dreyfus	536/84
1,483,738	2/1924	Lilienfeld	536/84
1,502,379	7/1924	Dreyfus	536/84
1,683,682	9/1928	Lilienfeld	536/84
1,683,831	9/1928	Lilienfeld	536/84
1,867,050	7/1932	Balle et al.	536/56
1,877,856	9/1932	Hagedorn et al.	536/56
2,067,853	1/1937	Lorand	536/84
2,071,287	2/1937	Lorand	536/56
2,077,066	4/1937	Lorand	536/56
2,087,549	7/1937	Powers et al.	536/84
2,096,114	10/1937	Lorand	536/56
2,098,335	11/1937	Dreyfus	536/84
2,101,032	12/1937	Lorand	536/84
2,102,205	12/1937	Haskins et al.	536/84
2,119,171	5/1938	Lorand	536/58

FOREIGN PATENT DOCUMENTS

0161607	11/1985	European Pat. Off.	.
0384167	8/1990	European Pat. Off.	.
808699	2/1937	France	.
492062	2/1930	Germany	.
494917	4/1930	Germany	.
554877	7/1932	Germany	.
3147434	6/1983	Germany	.
148481	4/1932	Switzerland	.
305946	2/1930	United Kingdom	.
325512	2/1930	United Kingdom	.
346426	4/1931	United Kingdom	.
1242735	8/1971	United Kingdom	.

OTHER PUBLICATIONS

Synthesis, Feb. 1983, pp. 117-119.
English Language Derwent Abstract for European Patent Publication No. 0 161 607.

Primary Examiner—Nathan M. Nutter
Attorney, Agent, or Firm—David Edwards

[57] ABSTRACT

Cellulose ethers are disclosed which have sufficient nonionic substitution to render them water soluble and which are further modified with a C₁₀ to C₂₄ long chain alkylaryl group in an amount between 0.2% by weight and the amount which makes them less than 1% by weight soluble in water. Hydroxyethylcellulose is a preferred water soluble cellulose ether for modification according to the invention. These products exhibit substantially improved viscosifying effects compared to their unmodified cellulose ether counterparts, and provide good leveling and sag resistance in latex paints. Preferred alkylaryl groups are nonylphenyl, dodecylphenyl, and dinonylphenyl. Included are cellulose ethers with spacer groups of various lengths between the alkylaryl group and the connecting group to the cellulose molecule.

47 Claims, No Drawings

U.S. PATENT DOCUMENTS

2,284,282	5/1942	Hentrich et al.	536/84	4,485,211	11/1984	Okamoto	525/51
2,383,361	5/1943	Bass et al.	536/88	4,650,863	3/1987	Felcht et al.	536/90
3,102,912	9/1963	Neracher et al.	564/5	4,663,159	5/1987	Brode, II et al.	424/70
3,941,751	3/1976	Breslow	536/85	4,683,004	7/1987	Goddard	106/170
3,971,627	7/1976	Breslow	536/85	4,684,704	8/1987	Craig	576/200
4,009,329	2/1977	Arney et al.	536/84	4,703,116	10/1987	Solarek et al.	536/111
4,065,319	12/1977	Desmarais	106/93	4,731,162	3/1988	Solarek et al.	536/111
4,076,930	2/1978	Ellingboe et al.	536/1	4,845,175	7/1989	Lo	526/200
4,084,060	4/1978	Glass, Jr. et al.	536/96	4,845,207	7/1989	T'Sas	536/91
4,097,667	6/1978	Holst et al.	536/87	4,902,733	2/1909	Angerer	524/44
4,127,495	11/1978	Swinson	252/89 R	4,954,270	9/1990	Butterworth et al.	536/56
4,228,277	10/1980	Landoll	536/90	4,981,959	1/1991	Diamantoglou	536/56
4,243,802	1/1981	Landoll	536/91	4,981,960	1/1991	Diamantoglou	536/56
4,281,110	7/1981	Blount	536/84	4,994,112	2/1991	Majewicz et al.	106/169
4,286,964	9/1981	Seed	536/43	4,997,935	3/1991	Diamantoglou	536/56
4,485,089	11/1984	Leipold	252/818	5,100,658	3/1992	Bolich, Jr. et al.	536/90
				5,106,609	4/1992	Bolich, Jr. et al.	536/90
				5,140,099	8/1992	Bostrom et al.	536/91

ALKYLARYL HYDROPHOBICALLY MODIFIED CELLULOSE ETHERS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

FIELD OF THE INVENTION

This invention relates to a new class of modified water soluble polymers. Specifically it relates to alkylaryl hydrophobically modified hydroxyethylcellulose, methylcellulose and hydroxypropylcellulose.

BACKGROUND OF THE INVENTION

Nonionic water soluble cellulose ethers are employed in a wide variety of industrial applications, as thickeners, as water retention aids, and as suspension aids in certain polymerization processes, among others. Widely used, commercially available, nonionic cellulose ethers include methylcellulose, hydroxypropylmethylcellulose, hydroxyethylcellulose, hydroxyethylpropylcellulose, hydroxypropylcellulose, and ethylhydroxyethylcellulose.

As is generally the case with high polymers, better thickening efficiency is realized with high molecular weight cellulose ethers. U.S. Pat. Nos. 4,228,277 and 4,243,802 (Landoll) disclose nonionic cellulose ethers of relatively low molecular weight which are capable of producing viscous aqueous solutions in practical concentrations. U.S. Pat. No. 4,845,175 discloses alkylaryl hydrophobically modified hydroxyethylcellulose as a useful material for emulsion polymerization, but contains no disclosure of how to make or use the compounds of the present invention. These products exhibit a relatively high degree of surface activity compared to that of more conventional nonionic water soluble cellulose ethers. These products are nonionic cellulose ethers which are modified by substitution with specified amounts of C₁₀ to C₂₄ alkyl radicals. Such ethers are substituted with an amount of long chain alkyl hydrocarbon radical between about 0.2 weight percent and the amount which renders said cellulose ether less than 1% by weight soluble in water. The base cellulose ether thus modified is preferably one of low to medium molecular weight, i.e., less than about 800,000 and preferably between 20,000 and 500,000, or a Degree of Polymerization (D.P.) of about 75 to 1,800.

Modification of the cellulose ethers with small hydrophobic groups such as ethyl, benzyl and phenylhydroxyethyl groups were not found to effect the property improvements shown by the long chain alkyl hydrophobic modifications. The long chain alkyl cellulose ethers disclosed were useful as stabilizers in emulsion polymerizations, as thickeners in cosmetics, and as flocculants in mineral processing. One particularly good utility was as a thickener in latex paint, where very small amounts of low molecular weight long chain alkyl modified nonionic cellulose ethers outperformed larger quantities of higher molecular weight conventional nonionic cellulosic ethers. The advantages of these products in this particular use are discussed in detail in the Aqualon publication entitled "Natrosol® Plus-Modified Hydroxyethylcellulose-Performance as a Latex Paint Thickener." Specifically, they provide improved paint rheology, excellent spatter resistance,

and good thickening efficiency in a wide variety of latex paint formulations. Paint leveling properties are adequate and better than those obtained with the unmodified base polymer from which they were prepared. However, further improvements in leveling properties would be desirable.


SUMMARY OF THE INVENTION

It is the object of this invention to provide a new class of hydrophobically modified cellulose ethers which give, among other applications, significantly better leveling properties in latex paint formulations than those obtained with the long chain alkyl substituted cellulose ethers of the two previously mentioned patents, without sacrificing the other good performance properties in latex paint applications. This has been achieved by the use of nonionic cellulose ethers having a sufficient degree of nonionic substitution selected from the class consisting of methyl, hydroxyethyl and hydroxypropyl which would cause them to be water soluble, and which are further substituted with alkylaryl hydrocarbon radicals having about 10 to 24 carbon atoms in an amount between about 0.2 weight percent and the amount which renders said cellulose ether less than 1 percent by weight soluble in water. The cellulose ether to be modified is preferably one of low to medium molecular weight, i.e. less than about 800,000 and preferably between about 20,000 and 500,000 (about 75 to 1,800 D.P.) Examples of such alkylaryl modified cellulose ethers are hydroxyethylcelluloses modified with either nonylphenyl, dodecylphenyl, or dinonylphenyl alkylaryl groups containing alkylaryl substitution levels from 0.25 to 2.4 weight percent.

While any nonionic water soluble cellulose ether can be employed as a cellulose ether substrate used to form the products of this invention, the preferred cellulose ether substrate is hydroxyethylcellulose of about 50,000-400,000 molecular weight. The alkylaryl substituent can be attached to the cellulose ether substrate via an ether, ester or urethane linkage. Preferred is the ether linkage, as the reagents currently used to effect etherification are readily obtained, the reaction is similar to that commonly used for the initial etherification, and the reagents are more easily handled than the reagents employed for modification via the other linkages. The resulting linkage is also usually more resistant to further reactions.


DETAILED DESCRIPTION OF THE INVENTION

Although the products of this invention are referred to as being "long chain alkylaryl group modified," it will be recognized that except in the case where modification is effected with an alkyl halide, the modifier is not a simple long chain alkylaryl group. The group is actually a hydroxyalkyl radical in the case of a glycidyl ether, a urethane radical in the case of an isocyanate, or an acyl radical in the case of an acid or acyl chloride. Nonetheless, the terminology "long chain alkylaryl group" is used and the number of carbon atoms refers only to those carbon atoms in the hydrocarbon portion of the modifying molecule. It does not include any carbon atoms in the connecting groups. Thus, hydroxyethylcellulose modified by reaction with nonylphenyl glycidyl ether is termed a C₁₅ hydrophobic group (C₆+C₉) modification of hydroxyethylcellulose.



Similar modifications using [ether] either dodecylphenyl glycidyl ether or dinonylphenyl glycidyl ether would result in C₁₈ and C₂₄ hydrophobes, respectively.

Moreover, there may be additional spacer groups, of various lengths, between the standard connecting group mentioned above and the long chain alkylaryl group. Thus, products with the structure:



$n = 1 \text{ to } 100$

have been prepared, where the hydrophobe group is still considered to be C₁₅.

Methods of preparing mixed ethers of cellulose, i.e. products having more than one etherifying modifier attached to the same cellulose molecule are known to the art. The products of this invention can be prepared via essentially the same methods. The preferred procedure for preparing the mixed ethers of this invention comprises slurrying the nonionic cellulose ether in an inert organic diluent with alkali until swollen, and reacting with about a C₁₀ to C₂₄ alkylaryl glycidyl ether, with agitation and heat, until the reaction is complete. Residual alkali is then actualized, and the product is recovered, washed with inert diluents, and dried. The etherification can also be effected with a C₁₀ to C₂₄ halide, but these are sometimes less reactive, less efficient and more corrosive. Therefore, it is preferred to use the glycidyl ether.

Methods of preparation of alkyl hydrophobically modified cellulose ethers are described in U.S. Pat. No. 4,228,277. In addition, rather than isolating and reacting the dried cellulose ether with the alkylaryl glycidyl ether, it is also possible to conduct the reaction in situ, that is, immediately after the preparation of the base cellulose ether of the proper substitution level, without isolating the cellulose ether. In this variation, the alkylaryl glycidyl ether is added immediately upon completion of the preparation of the cellulose ether, e.g., hydroxyethylcellulose. The reaction mixture is then reacted at an appropriate temperature and time for the


reaction to be completed. In both methods of preparation, it is necessary that conditions be provided to assure that the cellulose ether is swollen to the point that the modifier can react substantially uniformly on all cellulose ether molecular throughout.

The following examples illustrate the practice of this invention, which has industrial application in latex paint

manufacture.

EXAMPLES 1 to 6

Nonylphenyl Glycidyl Ether (NPGE)



The nonylphenyl glycidyl ether used is a commercial product of Wilmington Chemical Company (Heloxy[®] WC-64; 90% pure).

Reaction of NPGE with Hydroxyethylcellulose

Hydroxyethylcellulose was prepared by methods described in U.S. Pat. No. 4,084,060 in a 0.5 gallon CHEMCO stirred autoclave from 121.5 g cellulose; 1,600 ml t-butyl alcohol; 38.9 g sodium hydroxide in 152 ml of water; and 158 g ethylene oxide, at 80° C. Without cooling the reactor, nonylphenyl glycidyl ether (NPGE) dissolved in 20 ml t-butyl alcohol as added and the reactor heated to 110° C. The mixture was kept at 110° C. for 2 hours. The reactor was then cooled to below 40° C. and neutralized to a pH of 7-8. The product was purified by slurrying in 85% aqueous acetone, filtering, reslurrying in 100% acetone, filtering and drying in a laboratory fluid bed dryer. The products were cream colored solids.

Analytical data are given in Table 1.

TABLE 1

Example No.	Grams of nonylphenyl glycidyl ether added	Weight % nonylphenyl modifier	Hydroxyethyl M.S.	1% Brookfield Viscosity (mPa · s)	% Ash as Na ₂ SO ₄
Control A	0	0	4.1	44	6.5
Control B	0	0	5.2	40	5.4
1	9	0.61	4	120	6.2
2	18	0.94	3.1	175	5.0


TABLE 1-continued

Example No.	Grams of nonylphenyl glycidyl ether added	Weight % nonylphenyl modifier	Hydroxyethyl M.S.	1% Brookfield Viscosity (mPa · s)	% Ash as Na ₂ SO ₄
3	18	1.12	4	352	5.6
4	18	1.2	5.2	250	5.6
5	26	1.63	3.1	2120	5.3
6	26	2.42	5.2	2180	5.3

Table 1 illustrates the associative thickener characteristics of alkylaryl hydrophobically modified cellulose ethers to provide enhanced viscosity.



EXAMPLES 7 TO 13

Dodecylphenyl Glycidyl Ether (DDPGE)



The dodecylphenyl glycidyl ether was prepared by a procedure described in U.S. Pat. No. 3,102,912. DDPGE was 80% pure and contained predominately the para isomer.


Dinonylphenyl Glycidyl Ether (DNPGE)



The dinonylphenyl glycidyl ether was prepared by a procedure described in Synthesis, February 1983, pp. 117-119. DNPGE was 99% pure and contained predominately the ortho-para isomer.

【Poly(ethyleneoxy)nonylphenyl Glycidyl Ether】

Poly(ethyleneoxy)_nnonylphenyl Glycidyl Ether (PEONPGE)



The poly(ethyleneoxy)nonylphenyl glycidyl ether was prepared in the same manner as dinonylphenyl glycidyl ether except that poly(ethyleneoxy)_nnonylphenol (Igepal CO630 from GAF) was used instead of dinonylphenol. PEONPGE was 90% pure.

Reaction of DDPGE, DNPGE or PEONPGE with Hydroxyethylcellulose

The dodecylphenyl glycidyl ether (DDPGE) or the dinonylphenyl glycidyl ether (DNPGE) was reacted with hydroxyethylcellulose prepared using the same amounts of ingredients described in examples 1 to 6, except for the amount of alkylaryl glycidyl ether. Poly(ethyleneoxy)_nnonylphenyl glycidyl ether (PEONPGE), 2.1 g, was reacted with 34.5 a HEC, prepared according to examples 1 to 6, in the presence

of 250 ml tert-butyl alcohol (TBA), and 3.6 g sodium hydroxide in 27 g water, at 90° C. for 4½ hours. Neutralization and product workup were similar to the procedures described for examples 1 to 6.

15 The amounts of the glycidyl ethers used and analyses of the products isolated are shown in Table 2.

TABLE 2

Ex-ample No.	Grams of phenyl glycidyl ether added	Weight % Phenyl glycidyl ether modifier	Hydroxyethyl M.S.	1% Brookfield Viscosity (mPa · s)	% Ash as Na ₂ SO ₄
A. Dodecylphenyl glycidyl ether					
7	9.0	0.51	4.0	63	4.9
8	13.57	0.78	3.9	230	5.4
9	18.2	1.00	4.0	550	5.1
B. Dinonylphenyl glycidyl ether					
10	12.0	0.25	4.1	56	4.0
11	18.2	0.46	4.1	135	4.9
12	25.0	0.62	4.1	300	3.6
C. Poly(ethyleneoxy) _n nonylphenyl glycidyl ether					
13	2.1 g/ 34.5 g HEC	~0.5	4.5	44	—

EXAMPLES 14 to 27

35 The products of examples 1 to 13 were used in a semi-gloss white interior all acrylic latex paint formulation (formulation 3; SG-41-3; Aqualon Company Natrosol® Plus booklet, p. 16), substituting these products for the Natrosol® Plus Thickener used in the formulation.

40 Details of the paint properties resulting are given in Table 3. All paints were thickened to a Stormer viscosity of about 90 K.U. Performance parameters are described in the Aqualon Company Natrosol® Plus booklet.

TABLE 3

Ex-ample No.	Thick-ener Sample	Brushing Viscosity (poises)	Spatter	Level-ing	Sag Resistance (mils)	60° Gloss
A. Nonylphenyl Modifier						
14	1	1.3	5	9	10	33.9
15	2	1.1	6	10	12	36.0
16	3	1.0	7	9	17	33.5
17	4	1.1	8	9	13	26.2
18	5	0.8	7	7	16	37.4
19	6	1.0	5	3	24	17.8
B. Dodecylphenyl Modifier						
20	7	1.2	8	9	11	39.8
21	8	1.0	8	8	13	40.2
22	9	1.0	8	5	19	40.0
C. Dinonylphenyl Modifier						
23	10	1.2	9	9	10	39.8

TABLE 3-continued

Ex-ample No.	Thick-ener Sample	Brushing Viscosity (poises)	Spatter	Level-ing	Sag Resistance (mils)	60° Gloss
24	11	1.0	8	8	12	38.9
25	12	0.8	8	8	12	39.1
<u>D. Poly(ethyleneoxy)₉ nonylphenyl Modifier</u>						
26	13	1.2	6	9	10	—
<u>E Control (Natrosol (R) Plus) (Long Chain Alkyl Modifier)</u>						
27		11	9	5	20	31.0

Several unusual effects have been observed to be caused by the products of this invention in latex paint formulations. Relative to a thickener comprises of a long chain alkyl hydrocarbon modifier such as the group in Natrosol® Plus, these alkylaryl modified HEC thickeners showed significantly better leveling properties in paint, with values of 8–10 (compared to a value of 5 for Natrosol® Plus). When the alkylaryl group was nonylphenyl, the paint leveling value increased as the amount of hydrophobic substitution increased, up to a nonylphenyl substitution value of about 1.5 weight percent. At higher amounts of substitution, paint leveling values decreased. Thus, optimum paint leveling was achieved with nonylphenyl substitution amounts of between 0.5 and 1.5 weight percent. Other paint properties such as spatter resistance, brushing viscosity, and gloss were comparable to those obtained with the long chain hydrocarbon alkyl modifier. Sag resistance properties were slightly poorer as the result of the better leveling properties; however, sag values were still within acceptable limits.

In addition, other alkylaryl modifiers, such as dodecylphenyl (C₁₈) and dinonylphenyl (C₂₄) also gave excellent leveling and sag resistance properties—as did cellulose ethers with a long spacer group between the alkylaryl hydrophobic group and a standard connecting group, as in the cellulose ether with a poly(ethyleneoxy)₉nonylphenyl modifier.

EXAMPLE 28

Thickener sample Number 3 from Table 1 was used in a vinyl acrylic paint formulation—specifically, a vinyl acetate/vinyl versatate latex paint formulation. A leveling rating of 6 was obtained, compared to a rating of 3 for Natrosol® Plus.

This example illustrates an improvement in leveling by use of an alkylaryl modified hydroxyethylcellulose, relative to Natrosol® Plus in a different type of latex paint.

What is claimed is:

1. An arylalkyl hydrophobically modified hydroxyethylcellulose useful as an associative thickener in an aqueous protective coating, characterized in that the arylalkyl hydrophobically modified hydroxyethylcellulose provides a leveling value of at least 7 and a sag value of at least 12 and a Stormer Viscosity of at least 85 KU.

2. The arylalkyl hydrophobically modified hydroxyethylcellulose of claim 1 wherein the arylalkyl group is one of the group of nonylphenyl, dodecylphenyl, dinonylphenyl and poly(ethyleneoxy)nonylphenyl.

3. The arylalkyl hydrophobically modified hydroxyethylcellulose of claim 2 having a molecular weight of 20,000 to 400,000.

4. The arylalkyl hydrophobically modified hydroxyethylcellulose of claim 3 having a hydroxyethyl Molar Substitution (M.S.) of 3.0 to 4.5.

5. The arylalkyl hydrophobically modified hydroxyethylcellulose of claim 3 where the arylalkyl substitution ranges from 0.4 to 1.5 weight percent.

6. The arylalkyl hydrophobically modified hydroxyethylcellulose of claim 1, wherein the hydroxyethylcellulose is ethyl group modified.

7. An arylalkyl hydrophobically modified cellulose ether useful as an associative thickener in an aqueous protective coating, characterized in that the arylalkyl hydrophobically modified cellulose ether provides, in an all acrylic semi-gloss latex paint formulation, a leveling value of at least 7, a sag value of at least 12, and a Stormer Viscosity of at least 85 KU.

8. The arylalkyl hydrophobically modified cellulose ether of claim 7, wherein the cellulose ether comprises a water soluble hydroxyalkyl cellulose.

9. The arylalkyl hydrophobically modified cellulose ether of claim 8, wherein the water soluble hydroxyalkyl cellulose comprises a member selected from the group consisting of hydroxyethylcellulose and hydroxypropylcellulose.

10. The arylalkyl hydrophobically modified cellulose ether of claim 9, wherein the water soluble hydroxyalkyl cellulose is hydroxyethylcellulose.

11. The arylalkyl hydrophobically modified cellulose ether of claim 10, wherein the hydroxyethylcellulose is ethyl group modified.

12. The arylalkyl hydrophobically modified cellulose ether of claim 7, wherein the cellulose ether comprises methylcellulose.

13. The arylalkyl hydrophobically modified cellulose ether of claim 7, wherein the arylalkyl comprises about 10 to 24 carbon atoms.

14. The arylalkyl hydrophobically modified cellulose ether of claim 13, wherein the arylalkyl comprises a member selected from the group consisting of nonylphenyl, dodecylphenyl, and dinonylphenyl.

15. The arylalkyl hydrophobically modified cellulose ether of claim 7, wherein the amount of arylalkyl hydrophobe is between about 0.2 weight percent, and the amount which renders the cellulose ether less than 1 percent by weight soluble in water.

16. The arylalkyl hydrophobically modified cellulose ether of claim 15, wherein the amount of arylalkyl hydrophobe is between 0.25 and 2.4 weight percent.

17. The arylalkyl hydrophobically modified cellulose ether of claim 7, comprising a spacer group between the arylalkyl and the cellulose ether.

18. The arylalkyl hydrophobically modified cellulose ether of claim 17, wherein the spacer group comprises 1 to 100 ethyleneoxy units.

19. The arylalkyl hydrophobically modified cellulose ether of claim 7, comprising an ether linkage connecting the arylalkyl hydrophobe and the cellulose ether.

20. The arylalkyl hydrophobically modified cellulose ether of claim 19, wherein the arylalkyl hydrophobe comprises a hydroxyalkyl radical.

21. The arylalkyl hydrophobically modified cellulose ether of claim 20, wherein the hydroxyalkyl radical comprises a hydroxypropyl radical.

22. The arylalkyl hydrophobically modified cellulose ether of claim 21, wherein the arylalkyl hydrophobe comprises a glycidyl ether, reacted with the cellulose ether.

23. The arylalkyl hydrophobically modified cellulose ether of claim 22, comprising a spacer group between the arylalkyl and the ether linkage.

24. The arylalkyl hydrophobically modified cellulose ether of claim 23, wherein the spacer group comprises 1 to 100 ethyleneoxy units.

25. The arylalkyl hydrophobically modified cellulose ether of claim 24, wherein the cellulose ether comprises hydroxyethylcellulose.

26. The arylalkyl hydrophobically modified cellulose ether of claim 25, wherein the hydroxyethylcellulose is ethyl group modified.

27. The arylalkyl hydrophobically modified cellulose ether of claim 26, wherein the arylalkyl comprises nonyl-phenyl.

28. The arylalkyl hydrophobically modified cellulose ether of claim 27, wherein the amount of arylalkyl hydrophobe is between about 0.2 weight percent, and the amount which renders the cellulose ether less than 1 percent by weight solution in water.

29. The arylalkyl hydrophobically modified cellulose ether of claim 28, wherein the amount of arylalkyl hydrophobe is between 0.25 and 2.4 weight percent.

30. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose of claim 1.

31. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose of claim 6.

32. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 7.

33. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 11.

34. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 19.

35. An all acrylic semi-gloss latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 26.

36. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose ether of claim 1.

37. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose of claim 6.

38. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 7.

39. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 11.

40. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 19.

41. A vinyl acrylic latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 26.

42. A latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose of claim 1.

43. A latex paint formulation, comprising the arylalkyl hydrophobically modified hydroxyethylcellulose of claim 6.

44. A latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 7.

45. A latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 11.

46. A latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 19.

47. A latex paint formulation, comprising the arylalkyl hydrophobically modified cellulose ether of claim 26.

* * * * *

40

45

50

55

60

65

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : RE 34,904
DATED : April 11, 1995
INVENTOR(S) : E. K. Just, T. G. Majewicz, and A. C. Sau

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Column 8, line 13 "modified cellulose ether provides,"
should read --modified cellulose ether provides,--

Signed and Sealed this
Eighteenth Day of July, 1995

Attest:



BRUCE LEHMAN

Attesting Officer

Commissioner of Patents and Trademarks