

US00RE36612E

United States Patent [19]

Fukushima et al.

[11] E Patent Number: Re. 36,612

[45] Reissued Date of Patent: Mar. 14, 2000

[54]	MASH SEAM WELDING PROCESS AND
_	MASH SEAM WELDING APPARATUS

[75] Inventors: Toshihiro Fukushima, Chiryu; Masaki

Tanzawa, Toyota, both of Japan

[73] Assignee: Toyota Jidosha Kabushiki Kaisha,

Japan

[21] Appl. No.: **09/236,120**

[22] PCT Filed: Feb. 23, 1996

[86] PCT No.: PCT/JP96/00410

§ 371 Date: Dec. 24, 1996

§ 102(e) Date: **Dec. 24, 1996**

[87] PCT Pub. No.: WO96/26037

PCT Pub. Date: Aug. 29, 1996

Related U.S. Patent Documents

T	•	C
Rei	issue	٥t٠
$\mathbf{I} \mathbf{V} \mathbf{U}$	เออนบ	$\mathbf{O}_{\mathbf{L}}$

[64] Patent No.: 5,789,718
Issued: Aug. 4, 1998
Appl. No.: 08/732,394
Filed: Feb. 23, 1996

[30] Foreign Application Priority Data

		O		č	
Feb.	23, 1995	[JP]	Japan	•••••	7-059786
[51]	Int. Cl. ⁷	•••••	• • • • • • • • • • • • • • • • • • • •		B23K 11/06
[52]	U.S. Cl.	••••	• • • • • • • • • • • • • • • • • • • •	219/83 ; 219/8	1; 219/117.1
[58]	Field of	Searcl	1	23	19/64, 78.01,
		21	9/78.16	5, 82, 83, 84, 102	, 105, 117.1,
					81

[56] References Cited

U.S. PATENT DOCUMENTS

3,313,911	4/1967	Seeloff	219/105
4,160,892	7/1979	Opprecht et al	219/83
4,568,812	2/1986	Panknin et al	219/64

5,042,711	8/1991	Iskenderian et al
5,131,581	7/1992	Geiermann
5,290,990	3/1994	Bischofberger et al 219/82
5,343,010	8/1994	Urech

FOREIGN PATENT DOCUMENTS

63-63575	3/1988	Japan .
3-31074	2/1991	Japan .
3-60874	3/1991	Japan .
3-60873	3/1992	Japan .
5-69151	3/1993	Japan .
5-92273	4/1993	Japan .
6-71452	3/1994	Japan .

OTHER PUBLICATIONS


International Search report dated Jun. 25, 1996 (1 page). Concise Explanation Under Rule 98 (1 page).


Primary Examiner—Gregory Mills
Attorney, Agent, or Firm—Finnegan, Henderson, Farabow,
Garrett & Dunner, L.L.P.


[57] ABSTRACT


Mash seam welding process and apparatus, wherein two plate-like workpieces having different thickness values are fed and guided by a guiding device such that a length W_H of contact of the thick plate-like workpiece with one of two roller electrodes is smaller than a length W_M of contact of the thin plate-like workpiece with the other roller electrode. In this arrangement, the amount of mashing of the thick plate-like workpiece by the roller electrode is made larger than that of the thin plate-like workpiece by the other roller electrode, so that an interface of the two plate-like workpieces is positioned intermediate between the pair of roller electrodes, whereby a weld nugget formed intermediate between the roller electrodes extends across the interface, permitting the weld to have a sufficient strength owing to a nugget ratio, which is a ratio of a width dimension W_N of the weld nugget in the direction of the interface to a width dimension W_G of the interface.

10 Claims, 13 Drawing Sheets











F1G. 3

Re. 36,612








FIG. 6




FIG. 7






FIG. 8


Mar. 14, 2000




F1G. 9





12_H N G 12_M FIG. 11




Mar. 14, 2000














PLATE THICKNESS (mm)	THICKNESS	WELDING CURRENT (KA)	WELDING SPEED (m/min)		
(11111)			10	15	20
0.7×1.0	1.4	26	(1)	(1)	(2)
1.0×1.4	1.4	31	(1)	(1)	(2)
0.7×1.4	2.0	27	(1)	(1)	(2)

n=10





MASH SEAM WELDING PROCESS AND MASH SEAM WELDING APPARATUS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

FIELD OF THE ART

This invention relates to a mash seam welding process and a mash seam welding apparatus for continuously welding together two plate-like workpieces by overlapping the workpieces at their edges and applying a welding current between a pair of roller electrodes while the overlapping edge portions of the two plate-like workpieces are squeezed to be mashed, by and between the pair of roller electrodes.

BACKGROUND TECHNOLOGY

High-speed welding is possible by mash seam welding in which two plate-like workpieces are continuously welded together at their overlapping edge portions while the edge portions are squeezed to be mashed by and between a pair of roller electrodes, with a welding current being applied between the pair of roller electrodes. Since the mash seam welding is suitable for mass production, it is widely employed in production lines for steel plates, automobiles, etc.

In the mash seam welding described above, the two plate-like workpieces are positioned relative to each other by a clamping or guiding device that predetermined portions of the workpieces overlap each other, and the workpieces are fed so that the overlapping portions are squeezed by the pair of roller electrodes. Then, the two plate-like workpieces are continuously welded with a welding current applied between the roller electrodes while the overlapping portions of the workpieces are firmly squeezed and mashed by the roller electrodes.

In such mash seam welding, a so-called "weld nugget" N is formed based on a welding current applied to the pair of 40 roller electrodes, such that the weld nugget N is located in a central part of the thickness of a portion of two plate-like workpieces 12_H , 12_M squeezed by the pair of roller electrodes, as shown in FIG. 10. The formed weld nugget N extends across an interface G of the two plate-like work- 45 pieces 12_H , 12_M , so that the weld may be given a predetermined strength (tensile strength). In FIG. 10, W_G represents a width dimension of the interface G, while W_N represents a width dimension of the weld nugget N in the direction of the interface. The weld strength obtained by the mash seam 50 welding depends upon a ratio W_N/W_G , namely, a nugget ratio R_N , which is the ratio of the width dimension W_N of the weld nugget N to the width dimension W_G of the interface G. The weld strength of the mash seal welding increases as this nugget ratio R_N increases.

Where two plate-like workpieces having different thickness values are welded according to a conventional mash seam welding process, the interface G of the two plate-like workpieces $\mathbf{12}_H$, $\mathbf{12}_M$ mashed by the pair of roller electrodes is formed at a position which is offset from the center of the 60 thickness of the mashed portion in the direction toward the thin plate-like workpiece $\mathbf{12}_M$, as indicated in FIG. 11. However, the weld nugget N is formed at a position intermediate between the pair of roller electrodes, that is, at a central part of the thickness of the mashed portion of the two 65 plate-like workpieces $\mathbf{12}_H$, $\mathbf{12}_M$ squeezed between the pair of roller electrodes. Accordingly, it is difficult to form the weld

2

nugget N in alignment with the interface G of the two plate-like workpieces 12_H , 12_M , and is therefore difficult to obtain the desired weld strength in some cases.

While it is of course possible to increase the nugget ratio R_N indicated above by increasing the amount of the welding current to thereby form a large weld nugget N, an increase in the nugget ratio R_N leads to easy occurrence of cracking on the surfaces of the plate-like workpieces due to enlargement of the weld nugget N which undergoes rapid volumetric expansion. This cracking may develop into rupture in a subsequent press-forming process, for example. In view of this, the application of the mash seam welding is conventionally limited to the workpieces whose thickness ratio is not larger than a predetermined upper limit, for example, about 1.5, and the mash seam welding is not conventionally practiced where the thickness ratio of the workpieces exceeds the upper limit.

On the other hand, there has been proposed a seam welding process in which a shim is superposed on a thinner one of two plate-like workpieces so that the interface G of the two plate-like workpieces is located intermediate between a pair of roller electrodes, as disclosed in JP-A-63-63575. This seam welding process requires the shim as well as the two plate-like workpieces to be clamped by a clamping device adapted to position the two plate-like workpieces relative to each other. Therefore, this process has a drawback that the operation efficiency is inevitably lowered. Further, where the two plate-like workpieces are positioned relative to each other by using guide rollers while the workpieces are fed toward the roller electrodes, there is a drawback that the above seam welding process using the shim cannot be practiced.

The present invention was made in the light of the above background situation. It is therefore an object of the present invention to provide a mash seam welding process and a mash seam welding apparatus, which permit a sufficient weld strength even where two plate-like workpieces have different thicknesses.

DISCLOSURE OF THE INVENTION

The above object may be achieved according to the principle of the present invention, which provides a mash seam welding process continuously welding a first plate-like workpiece and a second plate-like workpiece which has a smaller thickness than the first plate-like workpiece and which overlaps the first plate-like workpiece, by applying a welding current between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a weld nugget at an interface of the two plate-like workpieces while the overlapping portions are squeezed by the pair of roller electrodes, wherein an amount of mashing of the first plate-like workpiece by one of the pair of roller electrodes is made larger than that of the second plate-like workpiece by the other of the pair of roller electrodes.

In the present process in which the amount of mashing of the first thick plate-like workpieces by the first plate-like workpieces is larger than that of the second thin plate-like workpiece, the position of the interface of the two plate-like workpieces is shifted to a position intermediate between the pair of roller electrodes, so that the weld nugget formed at the position intermediate between the pair of roller electrodes extends across the above-indicated interface, permitting a sufficient weld strength.

Preferably, a surface area of contact of the above-indicated one roller electrode with the first plate-like work-piece is made smaller than a surface area of contact of the

other roller electrode with the second plate-like workpiece. This arrangement is advantageous in that the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece, when the pair of plate-like workpieces are squeezed and mashed by 5 the pair of roller electrodes.

It is also preferable that wherein a length of contact of the above-indicated one roller electrode with the first plate-like workpiece in an axial direction of the pair of roller electrodes is made smaller than that of the other roller electrode with the second plate-like workpiece in the axial direction. This arrangement is also advantageous in that the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece, when the pair of plate-like workpieces are squeezed and mashed by 15 the pair of roller electrodes.

It is also preferable that the above-indicated one roller electrode located on the side of the first plate-like workpiece has a smaller diameter than the other roller electrode located on the side of the second plate-like workpiece. This arrangement is advantageous in that the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece, even though the lengths of contact of the pair of roller electrodes with the first and second plate-like workpieces are the same.

It is also preferable that the pair of plate-like workpieces are fed at a speed of 20 m/min. or higher while the plate-like workpieces are squeezed by the above-indicated pair of roller electrodes. In this arrangement in which the welding speed is increased, the contact resistance of the pair of roller electrodes and the two plate-like workpieces is made higher than the specific resistance of the plate-like workpieces, so that the weld nugget formed within the two plate-like workpieces is formed along the interface, with a result of an increase in the nugget ratio, permitting the weld to have a sufficient strength even where the pair of roller electrodes have different surface areas of contact with the two plate-like workpieces having different thickness values.

The above object may also be achieved according to 40 another aspect of the invention, which provides a mash seam welding process of continuously welding a first plate-like workpiece and a second plate-like workpiece which has a smaller thickness than the first plate-like workpiece and which overlaps the first plate-like workpiece, while overlapping portions of the two plate-like workpieces are squeezed a pair of roller electrodes disposed rotatably about respective two parallel axes thereof, the process comprising: a welding step of continuously welding the two plate-like workpieces by applying a welding current between a pair of 50 roller electrodes, to thereby form a weld nugget at an interface of the two plate-like workpieces, while the two plate-like workpieces are squeezed by the pair of roller electrodes; and a preliminary treatment step of reducing the thickness of a welding portion of the first plate-like 55 workpiece, prior to the welding step. In this arrangement, the thickness of the welding portion of the first thick plate-like workpiece is first reduced, so as to reduce the thickness difference with respect to the welding portion of the second thin plate-like workpiece, so that the weld nugget formed at 60 the position intermediate between the pair of roller electrodes extends across the interface of the two plate-like workpieces, permitting the weld to have a sufficient strength.

The above process of the present invention may be suitably practiced by a mash seam welding apparatus for 65 continuously welding a first plate-like workpiece and a second plate-like workpiece which has a smaller thickness

4

than the first plate-like workpiece and which overlaps the first plate-like workpiece, by applying a welding current between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a weld nugget at an interface of the two plate-like workpieces while the overlapping portions are squeezed by the pair of roller electrodes, the apparatus comprising: (a) a pair of roller electrodes disposed rotatably about respective two parallel axes thereof and biased toward each other, the pair of roller electrodes having a same diameter; and (b) a guiding device for guiding the two plate-like workpieces such that the two plate-like workpieces overlap each other with a predetermined lap amount, while the two plate-like workpieces are fed toward the pair of roller electrodes, so that the two plate-like workpieces are squeezed by the pair of roller electrodes such that a surface area of contact of one of the pair of roller electrodes with the first plate-like workpiece is smaller than a surface area of contact of the other of the pair of roller electrodes with the second plate-like workpiece.

In the present apparatus wherein the surface area of contact of one of the above-indicated pair of roller electrodes with the first plate-like workpiece is made smaller than that of the other roller electrode with the second plate-like workpiece, the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece when the pair of plate-like workpieces are squeezed and mashed by the pair of roller electrodes. Accordingly, the position of the interface of the two plate-like workpieces is shifted to a position intermediate between the pair of roller electrodes, so that the weld nugget formed at the position intermediate between the pair of roller electrodes extends across the above-indicated interface, permitting a sufficient weld strength.

Preferably, the guiding device guides the two plate-like workpieces such that a length of contact of the one roller electrode with the first plate-like workpiece in an axial direction of the pair of roller electrodes is smaller than that of the other roller electrode with the second plate-like workpiece in the axial direction. This arrangement is advantageous in that the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece when the pair of plate-like workpieces are squeezed and mashed by the pair of roller electrodes.

In one arrangement of the above preferred form of the apparatus, the pair of roller electrodes have respective outer circumferential contact surfaces and are disposed such that widthwise centerlines of the outer circumferential contact surfaces are substantially aligned with each other, and the guiding device guides the pair of plate-like workpieces such that an edge of the first plate-like workpiece is located between a widthwise end of the outer circumferential contact surface of the one roller electrode on the side of the first plate-like workpiece and the widthwise centerline of the outer circumferential contact surface of the one roller electrode, while an edge of the second plate-like workpiece is located at an widthwise end of the outer circumferential contact surface of the other roller electrode on the side of the first plate-like workpiece.

In another arrangement of the above preferred form of the apparatus, the pair of roller electrodes have respective outer circumferential contact surfaces and are disposed such that widthwise centerlines of the outer circumferential contact surfaces are offset from each other by a predetermined distance in an axial direction thereof, and wherein the guiding device guides the two plate-like workpieces such that a centerline of the overlapping edge portions of the two

plate-like workpieces is substantially aligned with the widthwise centerline of the outer circumferential contact surface of the one of the pair of roller electrodes which is located on the side of the plate-like workpiece having a smaller thickness.

In a further arrangement of the above preferred form of the apparatus, the roller electrode which is located on the side of the plate-like workpiece having a larger thickness has an outer circumferential contact surface having a width dimension smaller than an outer circumferential contact surface of the other of the pair of roller electrodes which is located on the side of the plate-like workpiece having a smaller thickness, the pair of roller electrodes being disposed such that widthwise centerlines of the outer circumferential contact surfaces are substantially aligned with each other, and wherein the guiding device guides the pair of plate-like workpieces such that a centerline of the overlapping edge portions of the two plate-like workpieces is substantially aligned with the widthwise centerlines of the outer circumferential contact surfaces of the roller electrode.

It is also preferable that the one of the pair of roller electrodes located on the side of the first plate-like workpiece has a smaller diameter than the other roller electrode located on the side of the second plate-like workpiece. This arrangement is advantageous in that the amount of mashing of the first thick plate-like workpiece is made larger than that of the second thin plate-like workpiece, even where the guiding device is adapted to guide the pair of plate-like workpieces such that the lengths of contact of the pair of roller electrodes with the first and second plate-like workpieces in the axial direction are equal to each other.

It is also preferable that the apparatus further comprises a feeding device for feeding the pair of plate-like workpieces at a speed of 20 m/min. or higher while the pair of plate-like workpieces are squeezed by the pair of roller electrodes. In 35 this arrangement, the feeding device for feeding the plate-like workpieces permits a high welding speed, and causes a higher resistance of contact of the pair of roller electrodes with the two plate-like workpieces than the specific resistance of the plate-like workpieces, whereby the nugget ratio 40 of the weld nugget formed along the interface of the two plate-like workpieces is increased, advantageously permitting a sufficient weld strength.

The above object may also be achieved according to a further aspect of the invention, which provides a mash seam 45 welding apparatus for continuously welding a first plate-like workpiece and a second plate-like workpiece which has a smaller thickness than the first plate-like workpiece and which overlaps the first plate-like workpiece, while the overlapping portions of the two plate-like workpieces are 50 squeezed by a pair of roller electrodes disposed rotatably about respective two parallel axes thereof, characterized by comprising: a work feeding device for feeding the two plate-like workpieces in one direction; a welding portion for continuously welding the two plate-like workpieces by 55 applying a welding current between a pair of roller electrodes, to thereby form a weld nugget at an interface of the two plate-like workpieces, while the two plate-like workpieces are fed by the work feeding device and squeezed by the pair of roller electrodes; and a preliminary treatment 60 device disposed upstream of the welding portion, for reducing the thickness of a welding portion of the first plate-like workpiece. In this arrangement wherein the thickness of the welding portion of the first thick plate-like workpiece is reduced prior to the welding by the pair of roller electrodes, 65 the thickness difference of the welding portion of the first thick plate-like workpiece with respect to that of the second

6

thin plate-like workpiece is reduced, so that the weld nugget formed intermediate between the pair of roller electrodes extends across the interface of the two plate-like workpieces, advantageously permitting a sufficient weld strength.

BRIEF DESCRIPTION OF THE DRAWINGS

- FIG. 1 is a perspective view schematically showing a manner of feeding plate-like workpieces to explain a mash seam welding process of the present invention;
- FIG. 2 is a plan view explaining an arrangement of guide rollers and retainer rollers used for feeding the plate-like workpieces, to explain the mash seam welding process according to the embodiment of FIG. 1;
- FIG. 3 is a view showing portions of guide members by which the plate-like workpieces are slidably guided, to explain a workpiece guiding step in the embodiment of FIG. 1.
- FIG. 4 is a view explaining a positional relationship between a pair of roller electrodes and the edge portions of the pair of plate-like workpieces pinched by the roller electrodes in a welding step;
- FIG. 5 is a view explaining the position of a weld nugget formed in the welding step in the embodiment of FIG. 1;
- FIG. 6 is view in cross section showing the guide rollers and their vicinity of a seam welding apparatus suitable for practicing the seam welding process of FIG. 1, taken in a plane perpendicular to a feeding direction of the plate-like workpieces;
- FIG. 7 is a view showing in enlargement a portion of the seam welding apparatus of FIG. 6;
- FIG. 8 is a view showing the roller electrodes and their vicinity of the seam welding apparatus of FIG. 6, taken in the plane perpendicular to the feeding direction of the plate-like workpieces;
- FIG. 9 is a partly cut-away view explaining the roller electrodes and their vicinity of the seam welding apparatus of FIG. 6;
- FIG. 10 is a view for explaining a definition of a nugget ratio;
- FIG. 11 is a view explaining the position of a weld nugget generated in a conventional mash seam welding process;
- FIG. 12 is a view corresponding to that of FIG. 4, showing another embodiment of this invention;
- FIG. 13 is a view corresponding to that of FIG. 4, showing another embodiment of this invention;
- FIG. 14 is a side elevational view explaining diameters of a pair of roller electrodes in another embodiment of this invention;
- FIG. 15 is a view corresponding to that of FIG. 4, showing another embodiment of this invention;
- FIG. 16 is a view explaining the position at which a weld nugget is formed in the embodiment of FIG. 15;
- FIG. 17 is a view and a table indicating results of experiments conducted to confirm a range of welding speed in which the embodiment of FIG. 15 is effective;
- FIG. 18 is a view explaining the position at which a weld nugget is formed when the embodiment of FIGS. 1–9 and the embodiment of FIG. 15 are combined; and
- FIG. 19 is a perspective view explaining a preliminary treatment or a preliminary treatment device in another embodiment of this invention.

BEST MODE FOR CARRYING OUT THE INVENTION

There will be described embodiments of this invention in detail referring to the drawings. FIG. 1 through FIG. 5 are

views explaining a seam welding process to be practiced according to this invention, while FIG. 6 through FIG. 9 are views explaining a seam welding apparatus 10 adapted to practice the seam welding process.

In FIGS. 1 and 2, there are shown a pair of left and right plate-like workpieces 12_H , 12_M which are separate plates such as zinc steel plates having given shapes. The plate-like workpiece 12_H has a larger thickness than the plate-like workpiece 12_M . These plate-like workpieces 12_H , 12_M are fed in a predetermined feeding direction B by a plurality of 10 sets of guide rollers 14 (Feeding Step), while the two plate-like workpieces 12_H , 12_M are guided and positioned relative to each other by a pair of upper and lower plate-like guide members 18_U , 18_S in sliding contact with guide surfaces 24_U , 24_S such that edge portions of the plate-like $_{15}$ workpieces 12_H , 12_M overlap each other with a predetermined lap amount (lap width) S (Guiding Step). The thus positioned two plate-like workpieces 12_H , 12_M are squeezed under pressure at their overlapping edge portions, by a pair of upper and lower roller electrodes 20_U , 20_S . In this 20_U condition, an electric current supplied from a power source is applied between the pair of roller electrodes 20_{IJ} , 20_{S} , whereby the two plate-like workpieces 12_H , 12_M are welded together at their overlapping edge portions, along a welding centerline A which is parallel to the feeding direction B and 25 which passes a center of the lap width S of the overlapping edge portions (Welding Step). A set of retainer rollers 16 are disposed on opposite sides of the roller electrodes 20_{T} , 20_{S} , for holding the pair of plate-like workpieces 12_H , 12_M under welding, with a predetermined squeezing force in the direction of thickness of the workpieces, so as to prevent movement of the workpieces away from each other (Holding Step).

Each of the above-indicated sets of guide rollers 14 consists of a pair of upper and lower guide rollers 14_{HU} , 35 14_{HS} disposed to pinch the plate-like workpiece 12_H with a predetermined pinching force in the direction of thickness of the workpiece, and another pair of upper and lower guide rollers 14_{MU} , 14_{MS} disposed to pinch the other plate-like workpiece 12_M with a predetermined pinching force in the 40 direction of thickness of the workpieces. The sets of guide rollers 14 are arranged in the feeding direction B, and include at least one set of guide rollers 14 which are positively driven. Each guide roller 14_{HI} , 14_{HS} , 14_{MI} , 14_{MS} of each set is supported rotatably about a horizontal axis C1 45 which lies in a plane inclined a suitable angle θ with respect to a plane perpendicular to the welding centerline A and which is located above or below the welding centerline A. Each pair of upper and lower guide rollers 14_{HU} and 14_{HS} , or 14_{MU} and 14_{MS} is given a suitable pinching force by a 50 cylinder device 56_H , 56_M described below, for example, such that the pinching force acts on the upper and lower guide rollers in a direction toward each other. The pinching force is determined so as to generate a friction force enough to permit the upper and lower rollers to generate a force 55 consisting of a component for feeding the plate-like workpiece 12_H , 12_M in the feeding direction B and component for moving the workpiece in the direction toward the guide members 18_U , 18_S .

The above-indicated set of retainer rollers 16 consists of 60 a pair of upper and lower retainer rollers 16_{HU} , 16_{HS} which are disposed on one side of the roller electrodes 20_U , 20_S to hold the plate-like workpiece 12_H with a predetermined squeezing force in the direction of thickness of the workpiece, and another pair of upper and lower retainer 65 rollers 16_{MU} , 16_{MS} disposed on the other side of the roller electrodes 20_U , 20_S to hold the other plate-like workpieces

8

 12_M with a predetermined squeezing force in the direction of thickness of the workpiece. Thus, the two pairs of retainer rollers 16 are disposed such that the roller electrodes 20_{II} , 20_s are interposed between the retainer rollers 16. Each pair of upper and lower retainer rollers 16_{HI} and 16_{HS} , or 16_{MI} and 16_{MS} is given a comparatively large squeezing force by a cylinder device similar to the cylinder device 56_H , 56_M described below, for example, such that the squeezing force acts on the upper and lower retainer rollers in a direction toward each other. The squeezing force is determined so as to prevent the edge portions of the pair of plate-like workpieces 12H, 12M under welding from moving away from each other. Each retainer roller 16_{HU} , 16_{HS} , 16_{MU} , 16_{MS} is supported rotatably about a horizontal axis C2 which lies in a plane perpendicular to the welding centerline A and which is located above or below the welding centerline A. The plate-like workpieces 12_H , 12_M under feeding, namely, under welding are retained by the above-indicated squeezing force to prevent the movements of their edge portions away from each other (Holding Step).

Each of the above-indicated pair of roller electrodes 20_U , 20_S is supported rotatably about a horizontal axis C3 which lies in a plane perpendicular to the welding centerline A and which is located above or below the welding centerline A. The pair of roller electrodes 20_U , 20_S is given a comparatively large squeezing force by a cylinder device by a cylinder device 80 described below, for example, such that the squeezing force acts on the roller electrodes in a direction toward each other. The squeezing force is determined so as to permit the overlapping edge portions of the plate-like workpieces 12_H , 12_M to be mashed by an amount enough to reduce the overall lap thickness to the approximate thickness of one of the workpieces 12_H , 12_M . The squeezing portion of the roller electrodes 20_U , 20_S is indicated at P in FIG. 2.

As shown in detail in FIG. 3, the above-indicated platelike guide members 18U, 18S are disposed with a predetermined amount of gap left between mutually opposed end faces thereof, so as to extend along the welding centerline A and between the pair of upper and lower guide rollers 14_{HII} , 14_{HS} for holding the one plate-like workpiece 12_{HS} , and the pair of upper lower guide rollers 14MU, 14MS for holding the other plate-like workpiece 12M, such that the guide members 18U, 18S are spaced apart by a predetermined small distance from the pair of roller electrodes 20_{17} , 20_{5} . The upper guide member 18_{II} has a projecting rail 26_{II} formed at a portion of its end face on the side of the plate-like workpiece 12_M . The projecting rail 26_U has a guide surface 24_{77} for sliding contact with the end face of the plate-like workpiece 12_H . The lower guide member 18_S has a projecting rail 26_s formed at a portion of its end face on the side of the plate-like workpiece 12_H . The projecting rail 26_S has a guide surface 24_S for sliding contact with the end face of the plate-like workpiece 12_{M} .

As shown in FIG. 2, the rotation axis C1 of at least one set (all sets in this embodiment) of the guide rollers 14 disposed on the left and right sides of the guide members 18_U , 18_S is inclined a predetermined small angle θ (1°-3° in this embodiment) with respect to the line perpendicular to the welding centerline A, so that the plate-like workpieces 12_H , 12_M are driven or guided by the guide roller 14 in a direction (in the direction of the driving force F_R described below) which is inclined inwardly by the predetermined angle θ with respect to the feeding direction B.

When the plate-like workpiece 12_M is in abutting contact with the guide surface 24_S , for example, the plate-like workpiece 12_M is fed while it is pressed toward the guide surface 24_S . Similarly, the plate-like workpiece 12_H is fed

while it is pressed toward the guide surface 24_{IJ} . Thus, the pair of plate-like workpieces 12_H , 12_M are positioned relative to each other with their edge portions overlapping over the predetermined lap width S, before the workpieces are squeezed by the upper and lower roller electrodes 20_U , 20_S . In this arrangement, the pair of plate-like workpieces 12_H , 12_M are automatically positioned relative to each other during feeding thereof through a feeding path, even if the workpieces do not have the predetermined relative position when they are introduced into the feeding path. The above- 10 indicated guide members 18_{IJ} , 18_{S} are adapted to guide the plate-like workpieces 12_H , 12_M such that the edge portions of the plate-like workpieces 12_H , 12_M squeezed between the roller electrodes 20_U , 20_S are positioned as indicated in FIG. 4. Namely, the guide members 18_{IJ} , 18_{S} are disposed at the 15 appropriate positions for positioning the workpieces as indicated in FIG. 4. In the guiding step in the present embodiment, the pair of plate-like workpieces 12_H , 12_M are guided and positioned relative to each other by the aboveindicated guide members 18_{IJ} , 18_{S} and the guide rollers 14_{20} disposed on the left and right sides of the guide members 18_{IJ} , 18_{S} , so that the edge portions of these plate-like workpieces 12_H , 12_M may be squeezed by the roller electrodes 20_{IJ} , 20_{S} , as indicated in FIG. 4. In the present embodiment, the above guide members 18_{IJ} , 18_{S} and the 25 guide rollers 14 disposed on the left and right sides of the guide members 18_U , 18_S function as a guiding device.

FIG. 4 shows the overlapping edge portions of the thick plate-like workpiece 12_H and the plate-like workpiece 12_M having a thickness smaller than the plate-like workpiece 30 12_H , which overlapping edge portions are positioned between the roller electrodes 20_U , 20_S which have respective outer circumferential contact surfaces 28_{IJ} , 28_{S} and which are disposed such that widthwise centerlines CL_{IJ} , CL_{S} of the outer circumferential contact surfaces 28_U , 28_S are 35 substantially aligned with each other. The edge of the thick plate-like workpiece 12_H is located between the widthwise end of the outer circumferential contact surface 28U of the one roller electrode 20_U on the side of the plate-like workpiece 12_H and the centerline CL_{IJ} , while the edge of the thin 40 plate-like workpiece 12_M is located at the widthwise end of the outer circumferential contact surface 28_s of the other roller electrode 20_s on the side of the plate-like workpiece 12_H . That is, a length W_H of contact of the one roller electrode 20_{II} with the plate-like workpiece 12_{H} is smaller 45 than a length W_M of contact of the other roller electrode 20_S with the plate-like workpiece 12_{M} . When the edge portions of the plate-like workpiece 12_H and the plate-like workpiece 12_s whose thickness is smaller than the plate-like workpiece 12_H are squeezed between the roller electrodes 20_U , 20_{HS} 50 while these edge portions overlap each other as shown in FIG. 4, the amount of mashing of the thick plate-like workpiece 12_H is larger than that of the thin plate-like workpiece 12_{M} , since the contact surface area of the roller electrode 20_{II} with respect to the plate-like workpiece 12_{H} is 55 smaller than the contact surface area of the roller electrode 20_S with respect to the plate-like workpiece 12_S . Consequently, the interface G of the two plate-like workpieces 12_H , 12_M is formed at a position intermediate between the pair of roller electrodes 20_U , 20_S , whereby the 60 weld nugget N formed is more likely to extend across the above-indicated interface G. Accordingly, the present arrangement results in an increase in the nugget ratio R_N which is the ratio W_N/W_G (ratio of the width W_N of the weld nugget N in the direction of the interface G to the width 65 dimension W_G of the interface G), so that the weld can be given a sufficient strength.

10

The mash seam welding apparatus 10 for practicing the mash seam welding process explained above is constructed as shown in FIGS. 6–9. FIG. 6 is a cross sectional view perpendicular to the feeding direction, showing the guide rollers 14 and their vicinity of the mash seam welding apparatus 10. FIG. 7 is a view showing in enlargement the guide rollers 14 and their vicinity. FIG. 8 is a view explaining an arrangement of the roller electrodes 20_U , 20_S and their vicinity, while FIG. 9 is a partly cut-away view explaining the support structure for the roller electrode 20_U .

Since the guide rollers 14 and the retainer rollers 16 are basically identical in construction to each other, the construction of the guide rollers 14 and the support structure thereof will be described by way of example.

Referring to FIGS. 6 and 7, a base frame 50 extends in the welding direction B, and a pair of posts 52_H , 52_M are disposed upright on the base frame 50. On the upper end faces of the posts 52_H , 52_M , there are provided the guide rollers 14_{HS} , 14_{MS} via base blocks 53_H , 53_M . A top frame 55 is fixed to the base frame 50 through an outer frame 54. To the top frame 55, there are fixed a pair of left and right cylinder devices 56_H , 56_M for giving the pinching forces to the pair of upper and lower guide rollers 14_{HU} , 14_{HS} and the pair of upper and lower guide rollers 14_{MH} , 14_{MS} , respectively. Movable rods 58_H , 58_M extend downward from the cylinder devices 56_H , 56_M , such that the movable rods 58_H , 58_S are movable. To the lower ends of the movable rods 58_H , 58_M , there are fixed movable plates 60_H , 60_M on which the guide rollers 14_{HU} , 14_{MU} .

The set of guide rollers 14_{HS} , 14_{MS} , 14_{HU} , 14_{MU} are provided with respective integrally formed shafts 66 which are supported by respective shaft cases 62_{HS} , 62_{MS} , 62_{HU} , 64_{MU} through bearings 64. The above-indicated shaft cases 62_{HS} , 62_{MS} are fixed to the upper end faces of the posts 52_{H} , 52_{M} , while the above-indicated shaft cases 62_{HU} , 62_{MU} are fixed to the movable plates 60_H , 60_M . The guide rollers 14_{HS} , 14_{MS} are rotatable about the axis C1 located below the welding centerline A while the guide rollers 14_{HU} , 14_{MU} are rotatable about the axis C, located above the welding centerline A. As shown in FIG. 3, the guide members 18_U , 18_S are fixed to the cylinder device 56_H and the post 52_M , respectively, such that the guide members 18_{II} , 18_{S} are disposed with the predetermined amount of gap left between their mutually opposed end faces, and extend between the pair of upper and lower guide rollers 14_{HU} , 14_{HS} for holding the one plate-like workpiece 12_H , and the pair of upper lower guide rollers 14_{MU} , 14_{MS} for holding the other platelike workpiece 12_M , such that the welding centerline A is aligned with the widthwise centers of the opposed end faces of the guide members 18U, 18S.

Each of the shafts 66 of the lower guide rollers 14_{HS} , 14_{MS} is connected to a drive motor 76 through a pair of joints 68, 70, an intermediate shaft 72, and a chain 74. The intermediate shaft 72 is provided for each of the left and right guide rollers 14_{HS} , 14_{MS} of each set of guide rollers 14, and these intermediate shafts 72 are connected to each other by chains and to the drive motor 76, for simultaneous rotation at the same speed. In this arrangement, the lower rollers 14_{HS} , 14_{MS} of the guide rollers 16 are rotated by the drive motor 76 to feed the pair of plate-like workpieces 14HS, 14MS. In the present embodiment, the drive motors 76 function as a driving device for rotating the guide rollers 14. Similar drive motors are used as a driving device for rotating the retainer rollers 16.

The pairs of upper and lower guide rollers 14_{HU} , 14_{HS} , 14_{MU} , 14_{MS} are steel rollers whose outer circumferential

surfaces are covered by an elastic material such as urethane rubber. The pair of guide rollers 14_{HU} , 14_{HS} and the pair of guide rollers 14_{MU} , 14_{MS} are squeezed toward each other by the respective cylinder devices 56_H , 56_M which function as a squeezing force applying device, so that the squeezing forces acting on the guide rollers permit the generation of friction forces enough to generate the component for feeding the pair of plate-like workpieces 12_H , 12_M and the component for forcing the workpieces toward the guide members 18_U , 18_S .

The pair of upper and lower retainer rollers 16_{HU} , 16_{HS} and the pair of upper and lower retainer rollers 16_{MU} , 16_{MS} which constitute one set of retainer rollers 16 are constructed similarly to the guide rollers 14_{HU} , 14_{HS} , 16_{MU} , 14_{MS} , as shown in FIG. 8. The retainer rollers 16 are rotatable about 15 the respective rotation axes C2 described above, and are rotated by the drive motors 76 at the same peripheral speed as the guide rollers 14_{HS} , 14_{MS} . The pair of upper and lower retainer rollers 16_{HU} , 16_{HS} and the pair of upper and lower retainer rollers 16_{MU} , 17_{MS} are steel rollers whose outer 20circumferential surfaces are knurled to increase the generated friction forces in their axial direction, with respect to the plate-like workpieces 12_H , 12_M . The retainer rollers 16_{HS} , 16_{HU} and the retainer rollers 16_{MS} , 16_{MU} are squeezed toward each other by cylinder devices similar to the cylinder 25 devices 56_H , 56_M , which also function as a squeezing force applying device. The squeezing forces given to the retainer rollers 16 are comparatively large permitting the generation of friction forces on their outer circumferential surfaces, so as to prevent the movements of the edge portions of the pair 30 of plate-like workpieces 12_H , 12_M under welding in the directions away from each other.

Auxiliary roller sets 130_{HU} , 130_{HS} , 130_{MU} , 130_{MS} are interposed between the roller electrodes 20_{II} , 20_{S} and the pair of retainer rollers 16_{HU} , 16_{HS} , and between the roller 35 electrodes 20_U , 20_S and the pair of retainer rollers 16_{MU} , 16_{MS} , in the direction perpendicular to the feeding direction B, that is, in the axial direction of the roller electrodes. These auxiliary roller sets 130_{HI} , 130_{HS} , 130_{MI} , 130_{MS} are located so as to press the portions of the workpieces at which the 40 convex deformation F is expected to take place. Described more specifically, the auxiliary roller sets 130_{HS} and 130_{MS} located below the plate-like workpieces 12_H , 12_M are rotatably supported by the end portions of brackets 132_{HS} and 132_{MS} fixed to the base blocks 53_{H} , 53_{M} , while the auxiliary 45 roller sets 130_{HI} and 130_{MI} located above the plate-like workpieces 12_H , 12_M are rotatably supported by the end portions of brackets 132_{HU} and 132_{MU} fixed to the movable plates 60_H , 60_M . The above auxiliary roller sets 130_{HI} , 130_{HS} , 130_{MU} , 130_{MS} are rotatable about axes C4 which are 50 parallel to the rotation axes C3 of the roller electrodes 20_U , 20_S and the axes C2 of the pair of retainer rollers 16_{HU} , 16_{HS} . The plate-like workpieces 12_H , 12_M are pressed with predetermined squeezing forces at their portions laterally adjacent to the roller electrodes 20_U , 20_M , by the upper and 55 lower auxiliary roller sets 130_{HU} , 130_{HS} and the upper and lower auxiliary roller sets 130_{MU} , 130_{MS} .

The pair of roller electrodes 20_U , 20_S have the same diameter, width and construction, as shown in FIG. 8, and only the upper roller electrode 20_U will be explained by 60 reference to FIG. 9, which is a partly cut-away view showing the upper roller electrode 20_U and the support structure of this electrode. As shown in FIG. 9, a cylinder device 80_U is fixed to the above-described top frame 55, for giving the roller electrodes 20_U , 20_S a squeezing force. The cylinder 65 device 80_U is provided with movable rods 82_U extending downward such that the movable rods 82_U are movable. A

12

movable plate 84 is fixed to the ends of the movable rods 82U, and a support block 86 for rotatably supporting the roller electrode 20_{T} is fixed to the movable plate 84.

The roller electrode 20_{T} comprised of a rotary shaft 90_{T} with a flange portion 88_U integrally formed at an axially intermediate part thereof, and a circular electrode disk 96_{II} fastened by a screw 94_{II} to the flange portion 88_{II} together with a pressure plate 92_{T} . The rotary shaft 90_{T} is fitted at its opposite end portions through power supply bushings 98_{IJ} , in a through-hole $\mathbf{100}_U$ formed through the above-indicated support block 86_U , whereby the rotary shaft 90_U is rotatably supported by the support block 86_{II} . The above electrode disk 96_{T} is a highly electrically conductive body formed of a metallic material such as chromium steel, beryllium copper alloy or chromium zirconium copper alloy, which is highly durable with a small amount of wear or damage even in the presence of a comparatively large electric current applied thereto while the metallic material is in contact with the plate-like workpieces 12_H , 12_M . The rotary shaft 90_U , pressure plate 92_U , power supply bushings 98_U and support blocks 86_U are highly electrically conductive bodies formed of a metallic material such as copper alloy or aluminum alloy. The electric current is supplied from the aboveindicated power source 22 to the electrode disk 96_{T} through electric wires not shown, and through the power supply bushings 98, rotary shaft 90_{17} , etc.

A fluid passage 102_U is formed through the above-indicated rotary shaft 90_U such that the fluid passage 102_U is open in the opposite end faces of the rotary shaft 90_U and has an intermediate portion in the form of a circular recess formed in the surface of the flange portion 88_U which contacts the electrode disk 96_U . A pair of hose joints 108_U , 110_U are fixed to the end faces of the rotary shaft 90_U , for connecting the fluid passage 102_U to coolant fluid hoses 104_U , 106_U while permitting the rotary shaft 90U to rotate.

In the mash seam welding apparatus 10 constructed as described above, the plurality of sets of guide rollers 14 and the one set of retainer rollers 16 are continuously rotated by the drive motors 76, so that the pair of plate-like workpieces 12_H , 12_M are fed and positioned relative to each other by the guide rollers 14 and the guide members 18_U , 18_S such that the edge portions of the workpieces overlap each other over the predetermined lap width S. Then, the workpieces are squeezed and mashed by the pair of roller electrodes 20_U , 20_S , and a welding current is simultaneously applied between the roller electrodes 20_U , 20_S , whereby the workpieces are welded at their edge portions as shown in FIG. 5, for example, as described above.

In the present embodiment, the pair of plate-like workpieces 12_H , 12_M are guided in the guiding step by the guiding device (guide rollers 14 and guide members 18_{II} , 18_s), in a manner as shown in FIG. 4, so that the workpieces are introduced between the pair of roller electrodes 20_{II} , 20_{S} . Namely, the pair of plate-like workpieces 12_H , 12_M are guided during feeding thereof such that the length W_H of contact of the one roller electrode 20_U with the plate-like workpiece 12_H is smaller than the length W_M of contact of the other roller electrode 20_s with the plate-like workpiece 12_{M} , in other words, such that the area of contact of the thick plate-like workpiece 12_H with the roller electrode 20_H is smaller than the area of contact of the thin plate-like workpiece 12_M with the roller electrode 20_S . In this arrangement, the amount of mashing of the plate-like workpiece 12_H by the one roller electrode 20_H is larger than that of the plate-like workpiece 12_M by the other roller electrode 20_S . Consequently, the interface G of the two plate-like workpieces 12_H , 12_M is formed at a position intermediate

between the pair of roller electrodes 20_U , 20_S , whereby the weld nugget N formed is more likely to extend across the above-indicated interface G, as shown in FIG. 5. Accordingly, the present arrangement results in an increase in the nugget ratio R_N which is the ratio W_N/W_G (ratio of the width W_N of the weld nugget N in the direction of the interface G to the width dimension W_G of the interface G), so that the weld can be given a sufficient strength.

The present inventors conducted an experiment in which a mash seam welding operation was performed in the following condition, for welding the plate-like workpiece $\mathbf{12}_H$ in the form of a 1.4 mm-thick zinc steel plate and the plate-like workpiece $\mathbf{12}_M$ in the form of a 0.7 mm-thick zinc steel plate: lap width S of the overlapping edge portions of the workpieces $\mathbf{12}_H$, $\mathbf{12}_M$ =1.0 mm; offset distance \mathbf{L}_1 of the welding centerline A from the widthwise centerlines \mathbf{CL}_U , \mathbf{CL}_S of the outer circumferential contact surfaces $\mathbf{28}_U$, $\mathbf{28}_S$ of the roller electrodes $\mathbf{20}_U$, $\mathbf{20}_S$ =2.0 mm; squeezing force acting on the upper and lower roller electrodes $\mathbf{20}_U$, $\mathbf{20}_S$ =9800N (=1000 kgf); welding current=27 kA; and welding speed =20 m/min. In the experiment, the nugget ratio \mathbf{R}_N was 50%, and the weld obtained had a sufficient strength.

It is noted that a guiding device in a conventional mash seam welding apparatus is adapted to guide the plate-like workpieces $\mathbf{12}_{H}$, $\mathbf{12}_{M}$ such that the surface area of contact of the roller electrode $\mathbf{20}_{U}$ with the plate-like workpiece $\mathbf{12}_{H}$ is equal to that of the roller electrode $\mathbf{20}_{S}$ with the plate-like workpiece $\mathbf{12}_{M}$. Although the conventional apparatus permits the weld nugget N to be formed at a position intermediate between the pair of roller electrodes $\mathbf{20}_{U}$, $\mathbf{20}_{S}$, the position of the interface G of the two plate-like workpieces $\mathbf{12}_{H}$, $\mathbf{12}_{M}$ is offset from the weld weld nugget N toward the thin plate-like workpiece $\mathbf{12}_{M}$, as indicated in FIG. $\mathbf{11}$, whereby the nugget ratio \mathbf{R}_{N} is as low as 20%, making it impossible to provide a sufficiently large weld strength.

There will next be described other embodiments of this invention. In the following embodiments, the reference numerals used in the preceding embodiment will be used to identify the corresponding elements, and no description of these elements will be provided.

FIGS. 12 and 13 show the pair of plate-like workpieces 12_H , 12_M which are guided by guiding devices (guide rollers 14 and guide members 18_U , 18_S) and squeezed by the roller electrodes 20_U , 20_S , in other embodiments of this invention.

In the embodiment of FIG. 12, the pair of roller electrodes 20_U , 20_S have the respective outer circumferential contact surfaces 28_U , 28_S which have the same width dimension. However, the roller electrodes 20_U , 20_S are disposed such that the widthwise centerlines CL_U , CL_S of the outer circumferential contact surfaces 28_U , 28_S are offset from each other by a predetermined distance L_2 in the axial direction. Further, the guiding device (guide rollers 14 and guide members 18_U , 18_S) is constructed so as to guide the pair of plate-like workpieces 12_H , 12_M such that the centerline of 55 the lap width S of the overlapping edge portion of the workpieces 12_H , 12_M , that is, the welding centerline A is substantially aligned with the widthwise centerline CL_S of the roller electrode 20_S located on the side of the thin plate-like workpiece 12_M .

In the embodiment of FIG. 13, the the outer circumferential surface 28_U of the roller electrode 20_U on the side of the thick plate-like workpiece 12_H has a smaller width dimension than the outer circumferential contact surface 28_S of the roller electrode 20_S on the side of the thin plate-like 65 workpiece 12_M . The pair of roller electrodes 20_U , 20_S are disposed such that the widthwise centerlines CL_U , CL_S of

14

those outer circumferential contact surfaces 28_U , 28_S are substantially aligned with each other in the axial direction. Further, the guiding device (guide rollers 14 and guide members 18_U , 18_S) is constructed so as to guide the two plate-like workpieces 12_H , 12_M such that the centerline of the lap width S of the overlapping edge portion of the workpieces 12_H , 12_M , that is, the welding centerline A is substantially aligned with the widthwise centerlines CL_U , CL_S of the roller electrodes 20_S , 20_S .

In both of the embodiments of FIGS. 12 and 13, the surface area of contact of the roller electrode 20_U with the thick plate-like workpiece 12_H is made smaller than that of the roller electrode 20_S with the thin plate-like workpiece 12_M . When the pair of plate-like [rollers] workpieces 12_H , [12_S] 12_M are squeezed by the pair of roller electrodes 20_U , 20_S , the amount of mashing of the thick plate-like workpiece 12_H by the roller electrode 20_U is made larger than the amount of mashing of the thin plate-like workpiece 12_M by the roller electrode 20_S . Therefore, the interface G of the two plate-like workpieces 12_H [,] and 12_M is formed at a position intermediate between the pair of roller electrodes, and the nugget ratio R_N is increased, making it possible to provide a sufficient weld strength.

FIG. 14 shows the pair of plate-like workpieces 12_H , 12_S which are guided by guiding devices (guide rollers 14 and guide members 18_{II} , 18_{S}) and squeezed by the roller electrodes 20_{17} , 20_{5} , in another embodiment of this invention. In the embodiment shown in the figure, the outer circumferential surfaces 28_{IJ} , 28_{S} of the pair of roller electrodes 20U, 20S have the same width dimension. However, the roller electrode 20_{T} located on the side of the thick plate-like workpiece 20_H has a smaller diameter than the roller electrode 20_s located on the side of the thin plate-like workpiece 20_{M} . This arrangement is advantageous in that the amount of mashing of the thick plate-like workpiece 12_H is made larger than that of the thin plate-like workpiece 12_M , even though the lengths W_H and W_M of contact of the pair of roller electrodes 20_U , 20_S with the plate-like workpieces 12_H , 12_M in the axial direction of the roller electrodes are equal to each other.

FIG. 15 shows the pair of plate-like workpieces 12_H , 12_S which are guided by guiding devices (guide rollers 14 and guide members 18_{II} , 18_{S}) and squeezed by the roller electrodes 20_{IJ} , 20_{S} , in another embodiment of this invention. In the embodiment shown in the figure, the outer circumferential contact surfaces 28_U , 28_S of the pair of roller electrodes 20_U , 20_S have the same width dimension. These roller electrodes 20_{IJ} , 20_{S} are disposed such that the widthwise centerlines CL_{IJ} , CL_{S} of the outer circumferential contact surfaces 28_{II} , 28_{S} are substantially aligned with each other. The above-indicated guiding device (guide rollers 14 and guide members 18_U , 18_S) is constructed to guide the pair of plate-like workpieces 12_H , 12_M such that the centerline of the lap width S of the overlapping edge portions of the pair of plate-like workpieces 12_H , 12_M , that is, the welding centerline A is substantially aligned with the widthwise centerlines CL_U , CL_S of the pair of roller electrodes 20_U , $20_{\rm S}$. In the present embodiment, the drive motors 76 functioning as a driving device for driving the guide rollers 14 and retainer rollers 16 are arranged to rotate the guide rollers 14 and retainer rollers 16 so that the welding speed, namely, the peripheral speed of the roller electrodes 20_U , 20_S is 20 m/min. or higher.

In the present embodiment, the weld nugget N is formed obliquely along the interface G, as indicated in FIG. 16 by way of example. Accordingly, the nugget ratio R_N is made large permitting a sufficient weld strength, even though the

amount of mashing of the thick plate-like workpiece 12_H is not made larger than that of the thin plate-like workpiece 12_M . This appears to be caused by the specific resistance of the plate-like workpieces 12_H , 12_M which becomes higher than electrical contact resistance between the pair of roller electrodes 20_U , 20_S and the plate-like workpieces 12_H , 12_M .

FIG. 17 shows a relationship between the thickness ratio of the plate-like workpieces 12_H , 12_M and the welding speed, which was obtained by experiments conducted by the present inventors in different conditions, each experiment consisting of ten test operations. In the figure, (1) indicates the case where the nugget ratio R_N is lower than a desired value (40%), while (2) indicates the case where the nugget ratio R_N is higher than the desired value (40%). It will be understood from the table of FIG. 17 that the nugget ratio R_N does not reach the desired value even where the thickness ratio is 1.4 (1:1.4), when the welding speed is 10 m/min. or 15 m/min., while the nugget ratio R_N reaches the desired value even where the thickness ratio is 2.0 (1.2.0), when the welding speed is 20 m/min.

FIG. 18 shows the state of a weld when the welding speed is 20 m/min. or higher in the embodiment of FIGS. 1–9. In this case, the interface G is formed at a position intermediate between the pair of roller electrodes 20_U , 20_S , and the nugget N is formed obliquely along the interface G, whereby the nugget ratio R_N is further increased, leading to an advantage of assuring a sufficient weld strength.

FIG. 19 shows an embodiment provided with a preliminary treatment device for performing a preliminary treatment step of mashing and thinning a welding portion or one 30 edge portion of the thick workpiece 12_H prior to a welding operation. In the embodiment of FIG. 19, the pair of plate-like workpieces 12_H , 12_M are guided relative to each other (Guiding Step) by a plurality of sets of guide rollers 14 and guide members 18_U , 18_S functioning as a guiding device, in the same manner as in the preceding embodiments, such that the edge portions of the workpieces to be welded together overlap each other with a predetermined lap amount S, while the workpieces are fed in the predetermined feeding direction B by conveyors 140, 142, 40 144, guide rollers 14 and retainer rollers 16, which function as a work feeding device. Then, the overlapping edge portions of the thus positioned pair of plate-like workpieces 12_H , 12_M are squeezed at the welding portion by the pair of upper and lower roller electrodes 20_U , 20_S , and are seam- 45 welded (Welding Step) by application of a welding current between the roller electrodes 20_U , 20_S , along the welding centerline A which is parallel to the feeding direction B and which passes the widthwise center of the lap width S of the overlapping edge portions. The pairs of plate-like work- 50 pieces 12_H , 12_M which have been welded together are unloaded by a conveyor 150 and placed in stack on a pallet **152**.

In a feeding path along which the workpieces are fed as described above, there is provided a presser roller device 55 148 consisting of a pair of roller dies 146_U , 146_S for squeezing and thinning the welding portion or edge portion of the thick plate-like workpiece 12_H . The presser roller device 148 is disposed upstream of the roller electrodes 20_U , 20_S , guide rollers 14 and guide members 18_U , 18_S , that is, 60 between the conveyors 140 and 142 provided exclusively for feeding the thick plate-like workpiece 12_H . This presser roller device 148 functions as the preliminary treatment device for thinning the edge portion of the thick plate-like workpiece 12_H prior to the welding operation. In the mash 65 seam welding apparatus according to the present embodiment, the thickness of the welding portion of the

thick plate-like workpiece 12_H is reduced prior to the seam welding by the pair of roller electrodes 20_U , 20_S , so that the thickness difference of the welding portion of the thick plate-like workpiece 12_H with respect to the welding portion of the thin plate-like workpiece 12_M is reduced, whereby the weld nugget N formed at a position intermediate between the pair of roller electrodes 20_U , 20_S extends across the interface G of the two plate-like workpieces 12_H , 12_M , permitting the weld to have a desired strength.

16

While the embodiments of this invention have been explained referring to the drawings, the invention may be otherwise embodied.

In the illustrated embodiments, the plate-like workpiece $\mathbf{12}_{H}$ has a larger thickness than the plate-like workpiece $\mathbf{12}_{M}$, the workpiece $\mathbf{12}_{M}$ may have a thickness larger than the workpiece $\mathbf{12}_{H}$. In this case, too, the surface area of contact of the thick plate-like workpiece with the corresponding roller electrode is made larger than that of the thin plate-like workpiece with the corresponding roller electrode.

While the illustrated embodiments are adapted to seamweld the plate-like workpieces 12_H , 12_M at their edge portions, the plate-like workpieces may be seam-welded at their portions located inwardly from the edge portions.

The embodiment of FIG. 18 is a combination of the embodiment of FIGS. 1–9 and the embodiment of FIG. 16. However, the present invention may be embodied as any combination of the embodiments selected from among the embodiment of FIGS. 1–9, embodiment of FIG. 12, embodiment of FIG. 13, embodiment of FIG. 16 and embodiment of FIG. 19.

While the illustrated embodiments are adapted to seam weld the pair of plate-like workpieces $\mathbf{12}_H$, $\mathbf{12}_M$ while the workpieces are fed in the horizontal direction, the seam welding may be effected while the workpieces are fed in the vertical direction.

Although the embodiment of FIG. 19 uses the presser roller device 148 provided with the pair of roller dies 146_U , 146_S as the preliminary treatment device for thinning the edge portion of the thick plate-like workpiece 12_H , the preliminary treatment device may be a grinding device for thinning the edge portion of the thick plate-like workpiece 12_H by grinding prior to the welding operation.

In the illustrated embodiments, the guide rollers 14 and the retainer rollers 16 include the lower guide rollers 14_{HS} , 14_{MS} and the lower retainer rollers 16_{HS} , 16_{MS} which are located below the plate-like workpieces 12_H , 12_M and which are driven by the drive motors 76. However, the upper guide rollers 14_{HU} , 14_{MU} and the upper retainer rollers 16_{HU} , 16_{MU} are driven by the drive motors 76, or the upper and lower guide and retainer rollers are both driven by the drive motors 76.

While all of the guide rollers 14_{HS} , 14_{MS} are driven by the drive motors 76 in the illustrated embodiments, only the selected ones of these guide rollers may be driven. In the case where the pair of plate-like workpieces 12_H , 12_M can be sufficiently fed by a plurality of sets of guide rollers 14, the set of retainer rollers 16 in the embodiment of FIGS. 1-9 need not be driven.

Further, at least one of the pair of roller electrodes 20_U , 20_S in the embodiment of FIGS. 1–9 may be driven by the electric motor 140 shown in FIG. 19, for example, at a peripheral speed equal to the feeding speed of the pair of plate-like workpieces 12_H , 12_M .

Further, at least one of the pair of roller electrodes 20_U , 20_S in the embodiment of FIGS. 1–9 may be driven by a

drive motor (not shown) at a peripheral speed equal to or higher than the feeding speed of the pair of plate-like workpieces 12_H , 12_M .

In the embodiment of FIGS. 1–9, the guide rollers 14 are inclined by a predetermined angle θ for pressing the pair of 5 plate-like workpieces $\mathbf{12}_{H}$, $\mathbf{12}_{M}$ toward the guide members $\mathbf{18}_{U}$, $\mathbf{18}_{S}$ while the workpieces are fed. However, slant guiding plates may be provided for contact with the outer edges of the pair of plate-like workpieces $\mathbf{12}_{H}$, $\mathbf{12}_{M}$, such that the slant guiding plates approach the guide members $\mathbf{10}_{U}$, $\mathbf{18}_{S}$ as it extends in the feeding direction.

It is to be understood that the foregoing embodiments are provided for illustrative purpose only, and that various changes may be made in the illustrated embodiments, without departing from the spirit of the invention.

We claim:

- 1. A mash seam welding process of continuously welding a first plate-like workpiece and a second plate-like workpiece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second 20 plate-like workpieces, by applying a welding current between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a [weld] welding nugget at an interface of said overlapping portions while said overlapping portions are squeezed by said pair of roller 25 electrodes, wherein a surface area of contact of one of said pair of roller electrodes with said first plate-like workpiece is made smaller than a surface area of contact of the other of said pair of roller electrodes with said second plate-like workpieces, so that an amount of mashing of said first 30 plate-like workpiece by said one [of said pair of] roller electrodes *electrode* is made larger than that of said second plate-like workpiece by [the] said other [of said pair of] roller [electrodes] *electrode*.
- [2. A mash seam welding process according to claim 1 35 wherein a surface area of contact of said one roller electrode with said first plate-like workpiece is made smaller than a surface area of contact of said other roller electrode with said second plate-like workpiece.]
- 3. A mash seam welding process according to claim 1, 40 wherein a length of contact of said one roller electrode with said first plate-like workpiece in an axial direction of said pair of roller electrodes is made smaller than that of said other roller electrode with said second plate-like workpiece in said axial direction.
- 4. A mash seam welding process according to claim 1, wherein said one roller electrode located on the side of said first plate-like workpiece has a smaller diameter than said other roller electrode located on the side of said second plate-like workpiece.
- [5. A mash seam welding process of continuously welding a first plate-like workpiece and a second plate-like workpiece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second plate-like workpieces, by applying a welding current 55 between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a weld nugget at an interface of said overlapping portions while said overlapping portions are squeezed by said pair of roller electrodes, said process comprising:

feeding a pair of plate-like workpieces at a speed of 20 m/min. or higher while said plate-like workpieces are squeezed by said pair of roller electrodes.]

[6. A mash seam welding process of continuously welding a first plate-like workpiece and a second plate-like work- 65 piece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second

plate-like workpieces, while said overlapping portions of said first and second plate-like workpieces are squeezed by a pair of roller electrodes disposed rotatably about respective two parallel axes thereof, said process comprising:

18

- a welding step of continuously welding said first and second plate-like workpieces by applying a welding current between said pair of roller electrodes, to thereby form a weld nugget at an interface of said overlapping portions while said overlapping portions are squeezed by said pair of roller electrodes; and
- a preliminary treatment step of squeezing a welding portion of said first plate-like workpiece between upper and lower roller dies of a presser roller device thereby to reduce the thickness of said welding portion of said first plate-like workpiece, prior to said welding step.]
- 7. A mash seam welding apparatus for continuously welding a first plate-like workpiece and a second plate-like workpiece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second plate-like workpieces, by applying a welding current between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a weld nugget at an interface of said overlapping portions while said overlapping portions are squeezed by said pair of roller electrodes, said mash seam welding apparatus comprising:
 - said pair of roller electrodes being biased toward each other and having a same diameter; and
 - a guiding device for guiding said first and second plate-like workpieces such that said two plate-like workpieces overlap each other with a predetermined lap amount, while said first and second plate-like workpieces are fed toward said pair of roller electrodes, so that said overlapping portions of said first and second plate-like workpieces are squeezed by said pair of roller electrodes such that a surface area of contact of one of said pair of roller electrodes with said first plate-like workpiece is smaller than a surface area of contact of the other of said pair of roller electrodes with said second plate-like workpiece.
- 8. A mash seam welding [process] apparatus according to claim 7, wherein said guiding device guides said first and second plate-like workpieces such that a length of contact of said one roller electrode with said first plate-like workpiece in an axial direction of said pair of roller electrodes is smaller than that of said other roller electrode with said second plate-like workpiece in said axial direction.
- 9. A mash seam welding [process] apparatus according to claim 8, wherein said pair of roller electrodes have respective outer circumferential contact surfaces and are disposed 50 such that widthwise centerlines of said outer circumferential contact [surf aces] surfaces are substantially aligned with each other, and wherein said guiding device guides said first and second plate-like workpieces such that an edge of said first plate-like workpiece is located between a widthwise end of said outer circumferential contact surface of said one roller electrode on the side of said first plate-like workpiece and said widthwise centerline of said outer circumferential contact surface of said one roller electrode, while an edge of said second plate-like workpiece is located at an widthwise 60 end of said outer circumferential contact surface of said other roller electrode on the side of said first plate-like workpiece.
 - 10. A mash seam welding apparatus according to claim 8, wherein said pair of roller electrodes have respective outer circumferential contact surfaces, respectively, and are disposed such that widthwise centerlines of said outer circumferential contact surfaces are offset from each other by a

predetermined distance in an axial direction of said pair of roller electrodes, and wherein said guiding device guides said first and second plate-like workpieces such that a centerline of overlapping edge portions of said first and second plate-like workpieces is substantially aligned with 5 said widthwise centerline of said outer circumferential contact surface of said one roller electrode.

11. A mash seam welding apparatus according to claim 8, wherein said pair of roller electrodes have respective outer circumferential contact surfaces, respectively, said outer 10 circumferential contact surface of said one roller electrode located on the side of said first plate-like workpiece having a smaller width dimension than that of said outer circumferential contact surface of said other roller electrode located on the side of said second plate-like workpiece, said pair of 15 roller electrodes being disposed such that widthwise centerlines of said outer circumferential contact surfaces are substantially aligned with each other, and wherein said guiding device guides said first and second plate-like workpieces such that a centerline of overlapping edge portions of 20 said first and second plate-like workpieces is substantially aligned with said widthwise centerlines of said outer circumferential contact surfaces of said pair of roller electrodes.

[12. A mash seam welding apparatus according to claim 25 7, wherein said one roller electrode located on the side of said first plate-like workpiece has a smaller diameter than said other roller electrode located on the side of said second plate-like workpiece.]

[13. A mash seam welding apparatus according to claim 30 7, further comprising a feeding device for feeding said first and second plate-like workpieces at a speed of 20 m/min. or higher while said first and second plate-like workpieces are squeezed by said first and second roller electrodes.]

14. A mash seam welding apparatus for continuously 35 welding a first plate-like workpiece $[(12_H)]$ and a second plate-like workpiece $[(12_M)]$ having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second plate-like workpieces, by applying a welding current between a pair of roller electrodes [(20)] 40 disposed rotatably about respective axes [(C3)] thereof, to thereby form a weld nugget [(N)] at an interface [(G)] of said overlapping portions while said overlapping portions are squeezed by said pair of roller electrodes, said mash seam welding apparatus comprising:

said pair of roller electrodes being biased toward each other and having a same diameter;

a guiding device for guiding said first and second plate-like workpieces such that said first and second plate-like workpieces overlap each other with a predetermined lap amount, while said first and second plate-like workpieces are fed toward said pair of roller electrodes, so that said overlapping portions of said first and second plate-like workpieces are squeezed by said pair of roller electrodes such that a surface area of contact of one of said pair of roller electrodes with said first plate-like workpiece is made smaller than a surface area of contact of the other of said pair of roller electrodes with said second plate-like workpiece, so that an amount of mashing of said first plate-like workpiece by said one [of said pair of] roller [electrodes] electrode is made larger than that of said second

plate-like workpiece by [the] *said* other [of said pair of] roller [electrodes] *electrode*; and

a feeding device for feeding said first and second platelike workpieces at a speed of 20 m/min. or higher while said overlapping portions are squeezed by said pair of roller electrodes.

[15. A mash seam welding apparatus for continuously welding a first plate-like workpiece and a second plate-like workpiece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second plate-like workpieces, while said overlapping portions of said first and second plate-like workpieces are squeezed by a pair of roller electrodes disposed rotatably about respective two parallel axes thereof, said mash seam welding apparatus comprising:

- a work feeding device for feeding said first and second plate-like workpieces in a predetermined feeding direction;
- a welding portion for continuously welding said first and second plate-like workpieces by applying a welding current between said pair of roller electrodes, to thereby form a weld nugget at an interface of said overlapping portions, while said first and second plate-like workpieces are fed by said work feeding device and squeezed by said pair of roller electrodes; and
- a preliminary treatment device comprising a presser roller device including upper and lower dies disposed upstream of said welding portion, for squeezing the portion of said first plate-like workpiece which overlaps said second plate-like workpiece, between said upper and lower roller dies thereby to reduce the thickness of said portion of said first plate-like workpiece.]

16. A mash seam welding apparatus for continuously welding a first plate-like workpiece and a second plate-like workpiece having a smaller thickness than said first plate-like workpiece, at overlapping portions of said first and second plate-like workpieces, by applying a welding current between a pair of roller electrodes disposed rotatably about respective axes thereof, to thereby form a weld nugget at an interface of said overlapping portions while said overlapping portions are squeezed by said pair of roller electrodes, said mash seam welding apparatus comprising:

said pair of roller electrodes being biased toward each other, one of said pair of roller electrodes located on the side of said first plate-like workpiece having a smaller diameter than that of the other of said pair of roller electrodes located on the side of said second plate-like workpiece; and

a guiding device for guiding said first and second platelike workpieces such that said two plate-like workpieces overlap each other by a predetermined lap amount, while said two plate-like workpieces are fed toward said pair of roller electrodes, so that said overlapping portions of said first and second plate-like workpieces are squeezed by said pair of roller electrodes such that a surface area of contact of said one roller electrode with said first plate-like workpiece is smaller than a surface area of contact of said other roller electrode with said second plate-like workpiece.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE CERTIFICATE OF CORRECTION

PATENT NO .:

Re. 36,612

DATED:

March 14, 2000

INVENTOR(S):

Toshihiro FUKUSHIMA et al.

It is certified that an error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Claim 1, col. 17, line 30, "workpieces" should read --workpiece--.

Claim 9, col. 18, line 59, "an widthwise" should read --a widthwise--.

Signed and Sealed this

Second Day of January, 2001

Attest:

Attesting Officer

Q. TODD DICKINSON

Commissioner of Patents and Trademarks