



US00RE36884E

[54] MANNICH ACRYLAMIDE POLYMERS

[75] Inventors: Joseph J. Kozakiewicz; Sun-Yi Huang, both of Stamford, Conn.

[73] Assignee: Cytec Technology Corp., Wilmington, Del.

[21] Appl. No.: 08/928,148

[22] Filed: Sep. 12, 1997

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: 5,037,881  
Issued: Aug. 6, 1991  
Appl. No.: 07/535,791  
Filed: Jun. 11, 1990

U.S. Applications:

[60] Continuation of application No. 08/274,182, Jul. 12, 1994, abandoned, which is a division of application No. 07/428,730, Oct. 30, 1989, Pat. No. 4,956,399, which is a continuation-in-part of application No. 07/285,927, Dec. 19, 1988, abandoned.

[51] Int. Cl.<sup>7</sup> ..... C08K 7/16; D21H 17/00  
[52] U.S. Cl. .... 524/812; 523/223; 524/801; 524/812; 524/824; 525/328.4; 525/329.4; 525/379; 526/306

[58] Field of Search ..... 523/223; 524/801, 524/812, 829; 525/328.4, 329.4, 379; 526/306

[56] References Cited

U.S. PATENT DOCUMENTS

2,937,143	5/1960	Goren .....	210/728
3,142,638	7/1964	Blaisdell et al. ....	210/695
3,165,465	1/1965	Ray et al. ....	210/727
3,235,490	2/1966	Goren .....	528/488
3,259,569	7/1966	Priesing et al. ....	210/713
3,276,988	10/1966	Williams .....	204/284
3,284,393	11/1966	Vanderhoff et al. ....	524/801
3,380,947	4/1968	Galgoczi et al. ....	523/323
3,536,646	10/1970	Hatch et al. ....	523/319
3,539,535	11/1970	Wisner .....	525/385
3,556,932	1/1971	Coscia et al. ....	524/551
3,624,019	11/1971	Anderson et al. ....	523/336
3,640,897	2/1972	Restaino .....	502/24
3,719,748	3/1973	Manfroy et al. ....	423/544
3,732,184	5/1973	Lindemann et al. ....	524/827
3,734,873	5/1973	Anderson et al. ....	523/336
3,790,529	2/1974	Fujimura et al. ....	525/157
3,840,489	10/1974	Strazdins .....	524/816
3,864,312	2/1975	Suzuki et al. ....	525/157
3,875,097	4/1975	Sedlak .....	524/813
3,875,098	4/1975	Sedlak .....	529/512
3,897,333	7/1975	Field et al. ....	210/734
3,902,958	9/1975	Breen et al. ....	162/164.4
3,917,529	11/1975	Madole et al. ....	210/736
3,929,633	12/1975	Visman et al. ....	210/732
3,956,122	5/1976	Coscia et al. ....	210/734
3,968,037	7/1976	Morgan et al. ....	210/734
3,977,971	8/1976	Quinn et al. ....	210/372
3,979,348	9/1976	Ballweber et al. ....	524/512
4,010,131	3/1977	Phillips et al. ....	523/337
4,021,394	5/1977	Tuka et al. ....	523/336
4,022,741	5/1977	Tuka et al. ....	523/336
4,051,065	9/1977	Venema .....	523/313

4,059,552	11/1977	Zweigle et al. ....	524/555
4,073,763	2/1978	Tai .....	523/337
4,093,542	6/1978	Dahmer et al. ....	524/801
4,110,520	8/1978	Mayajima .....	525/340
4,113,685	9/1978	Hubner et al. ....	524/421
4,113,688	9/1978	Pearson .....	523/324
4,172,066	10/1979	Zweigle et al. ....	523/223
4,172,688	10/1979	Zweigle et al. ....	523/223
4,179,370	12/1979	Hubner et al. ....	210/734
4,245,070	1/1981	Kemp .....	526/75
4,251,410	2/1981	Danner et al. ....	524/512
4,282,928	8/1981	McDonald et al. ....	166/274
4,322,330	3/1982	Merz et al. ....	523/221
4,363,886	12/1982	Lipowski et al. ....	524/801
4,382,864	5/1983	Hashimoto et al. ....	210/727
4,391,932	7/1983	Tai .....	524/801
4,405,728	9/1983	Krebs et al. ....	523/336
4,521,317	6/1985	Candau et al. ....	507/223
4,528,321	7/1985	Allen et al. ....	524/801
4,529,794	7/1985	Sortwell et al. ....	528/449
4,565,836	1/1986	Emerson et al. ....	524/801
4,585,812	4/1986	Field .....	523/221
4,599,379	7/1986	Flesher et al. ....	524/801
4,619,967	10/1986	Emerson et al. ....	524/801
4,681,912	7/1987	Durand et al. ....	524/827
4,702,844	10/1987	Flesher et al. ....	524/555
4,705,640	11/1987	Whittaker .....	523/319
4,720,346	1/1988	Flesher et al. ....	524/922
4,759,856	7/1988	Farrar et al. ....	523/322
4,789,695	12/1988	Farrar et al. ....	523/336

(List continued on next page.)

FOREIGN PATENT DOCUMENTS

1204535	5/1986	Canada .
0102759	11/1984	European Pat. Off. .
0143328	6/1985	European Pat. Off. .
2398762	2/1979	France .
63-218246	9/1988	Japan .
841127	7/1960	United Kingdom .
1153207	5/1969	United Kingdom .
1346596	2/1974	United Kingdom .
1426897	3/1976	United Kingdom .
1489046	10/1977	United Kingdom .
2160879	1/1986	United Kingdom .
2161492	1/1986	United Kingdom .
WO 93/03190	2/1993	WIPO .

OTHER PUBLICATIONS

Principles of Polymerization, George Odian Second Edition, John Wiley & Sons 1981, p. 322.  
Buffle et al. *Environmental Particles*, in Analytical and Physical Chemistry Series, vol. 1, Forward and Contents (1992), pub. by Lewis Publishers  
Candau et al., *Journal of Colloid and Interface Science*, vol. 101, pp. 167–183 (1984).

(List continued on next page.)

Primary Examiner—Peter A. Szekely  
Attorney, Agent, or Firm—Pennie & Edmonds LLP

[57] ABSTRACT

Mannich (alk)acrylamide microparticles are produced at high solids contents without a significant increase in bulk viscosity by inverse microemulsion polymerization and provide superior dewatering characteristics.

27 Claims, No Drawings

U.S. PATENT DOCUMENTS

4,861,499	8/1989	Neff et al. ....	524/555	5,171,781	12/1992	Farrar et al. ....	524/547
4,954,538	9/1990	Dauplaise et al. ....	523/223	5,171,782	12/1992	Candau et al. ....	524/801
4,956,399	9/1990	Kozakiewicz et al. ....	523/223	5,171,808	12/1992	Ryles et al. ....	526/264
4,956,400	9/1990	Kozakiewicz et al. ....	523/323	5,185,061	2/1993	Lowry et al. ....	162/183
4,968,435	11/1990	Neff et al. ....	524/922	OTHER PUBLICATIONS			
5,037,863	8/1991	Kozakiewicz et al. ....	524/827	Miller, <i>The Structure of Polymers</i> , in Polymer Science and			
5,037,881	8/1991	Kozakiewicz et al. ....	524/812	Engineering Series, pp. 334–337 (1966), pub. by Reinhold			
5,041,503	8/1991	Dauplaise et al. ....	523/323	Publishing Corp.			
5,070,133	12/1991	Miyajima ....	524/501	Morgan et al., “How Cationic Polymer Structure Relates to			
5,100,951	3/1992	Fillipo et al. ....	524/801	Dewatering Efficiency of Waste–Activated Sludges”,			
5,104,552	4/1992	Cicchiello et al. ....	210/727	<i>Adv.Chem.Ser.</i> , 187, pp. 235–252, (1980).			
5,132,023	7/1992	Kozakiewicz et al. ....	210/734	Shibahara et al., <i>Chemical Abstracts</i> , 90:7086z (1979).			



## MANNICH ACRYLAMIDE POLYMERS

Matter enclosed in heavy brackets [ ] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

[This] *This reissue application is a continuation of reissue application Ser. No. 08/274,182 filed Jul. 12, 1994, now abandoned which is a divisional of application Ser. No. 07/428,730, filed Oct. 30, 1989, now U.S. Pat. No. 4,956,399, which, in turn, is a CIP of Ser. No. 07/285,927 filed on Dec. 19, 1988, now abandoned.*

This invention relates to high solids inverse microemulsion, Mannich acrylamide polymers and their use as flocculants. More particularly, this invention relates to compositions comprising microparticles containing (alk) acrylamide polymers substituted with tertiary aminomethyl groups and having an average size of from about 200 to about 4000 Å in diameter.

## BACKGROUND OF THE INVENTION

High molecular weight Mannich polyacrylamides (PAMS) are well known and are used in a variety of flocculant applications. A major drawback of Mannich PAMS is their tendency to cross-link. This problem becomes more severe as the polymer solids are increased. Consequently, these polymer are generally made as dilute, aqueous solutions in an attempt to slow down the rate of interpolymer cross-linking. The solids level must also be kept low, particularly for very high molecular weight Mannich PAMS, owing to the ability of these polymers to viscosity water. As a result, solids levels of very high molecular weight Mannich PAMS must generally be well below 10%, and more typically 6% or less so that the solutions can be pumped and handled conveniently.

Several approaches have been tried to overcome these problems. One approach has been to make the Mannich PAMS at the site to use by inverting high solids inverse emulsion PAMS in water containing dialkylamines and formaldehyde. U.S. Pat. No. 4,021,394 and U.S. Pat. No. 4,022,741 describe continuous processes for the preparation of Mannich PAMS which entails inverting an inverse emulsion PAM in a process stream containing formaldehyde and a secondary amine and subjecting the stream to turbulence by in-line mixing to produce a 1–15% aqueous solution of Mannich PAM. This approach, however, suffers from the need to store multiple chemicals on site and from the problems inherent in running chemical reactions at such locations. Another approach has been to prepare dry Mannich PAMS, as described in U.S. Pat. No. 3,864,312; U.S. Pat. No. 3,539,535 and U.S. Pat. No. 3,790,529 or blends of dry PAMS with dry, low-molecular weight Mannich-base forming compounds which, when dissolved in water, react to produce Mannich PAMS, as described in EPO Patent No. 0,210,784. These approaches, in general, suffer from cross-linking problems, the reversibility of the Mannich reaction, the difficulty and length of time required to dissolve high molecular weight polymers, and other problems. Another approach has been to make the Mannich PAM in inverse emulsions, such as described in U.S. Pat. No. 3,979,348; U.S. Pat. No. 4,093,542 and U.S. Pat. No. 4,010,131. While this approach produces a product with substantially higher solids, the average particle size thereof ranges from about 10,000–20,000 Å in diameter, and consequently, cross-linking of the many polymer chains in each particle renders the products less effective. The cross-linking rate can be reduced somewhat by adding fairly large quantities of

stabilizers, such as described in U.S. Pat. No. 4,113,685 and U.S. Pat. No. 4,073,763, but cross-linking continues and the products thus possess a very limited shelf life.

Accordingly, there exists a need for a Mannich acrylamide polymer which can be prepared at high solids levels without extensive interpolymer cross-linking such that it may be economically transported and easily handled by the end user without the need for any on-site preparation. Such a Mannich acrylamide polymer composition would satisfy a long felt need and constitute a notable advance in the art.

Surprisingly, it has now been discovered that Mannich acrylamide polymers, in the form of inverse microemulsions, give superior performance relative to the Mannich acrylamide polymers of the prior art and can be conveniently prepared at high solids content while maintaining a very low bulk viscosity. In contrast to solution and inverse emulsion Mannich acrylamide polymers of the prior art which contain large quantities of polymer molecules in the same aqueous environment, the Mannich acrylamide polymers of the present invention are isolated as individual, or at most, several, polymer molecules in each aqueous microemulsion micelle. Thus, the problem of large scale debilitating interpolymer cross-linking inherent in the solution and inverse emulsion products of the prior art is overcome.

Additionally, in contrast to the high bulk viscosities of the more stable dilute solution acrylamide polymers of the prior art, the novel microemulsion Mannich acrylamide polymers of the present invention can be made at high solids levels while still maintaining an extremely low bulk viscosity.

Even more unexpected with regard to the microemulsion Mannish acrylamide polymers of the instant invention is the fact that even though cross-linking thereof still occurs, the cross-linked polymers are capable of successfully performing as effective flocculants in the dewatering of suspended solids, whereas the cross-linked inverse emulsion and solution Mannich acrylamide polymers fail.

## SUMMARY OF THE INVENTION

According to the present invention, there is provided compositions comprising (alk)acrylamide-containing polymeric microparticles, the (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter. It is preferred that the average particle size range from about 300 to about 2000 Å in diameter and even more preferred that it ranges from about 350 to 1000 Å in diameter. Also provided by the present invention are microemulsions comprising the above-defined modified polymers wherein the polymer solids content is greater than 10 percent, by weight, based on said composition and, preferably, greater than 20 percent, by weight.

The above defined compositions preferably comprise polyacrylamide substituted with said aminomethyl groups.

Also, according to the present invention are provided processes for the preparation of compositions as defined above. In one embodiment, the composition is prepared by

## (a) admixing

- (i) an aqueous solution of at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer;
- (ii) an oil solution comprising at least one hydrocarbon liquid; and
- (iii) an effective amount of surfactant or surfactant mixture so as to form an inverse microemulsion;



- (b) subjecting the inverse microemulsion obtained in step (a) to polymerization conditions;
- (c) reacting the polymerized polymer obtained in step (b) with an effective amount of a formaldehyde and a secondary amine or a complex thereof; and
- (d) optionally, quaternizing the resultant polymer.

In a second embodiment, the composition is prepared by

- (a) reacting
  - (i) at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer; and
  - (ii) formaldehyde and a secondary amine or a complex thereof in aqueous solution to produce a tertiary aminomethyl substituted (alk)acrylamide monomer;
- (b) admixing
  - (i) said aqueous solution of substituted (alk)acrylamide monomer and, optional comonomer obtained in (a);
  - (ii) an oil solution comprising at least one hydrocarbon liquid; and (iii) an effective amount of surfactant or surfactant mixture, so as to form an inverse microemulsion;
- (c) subjecting the inverse microemulsion obtained in step (b) to polymerization conditions; and
- (d) optionally, quaternizing the resultant polymer.

A third embodiment sets forth a process for preparing the composition comprising

- (a) admixing
  - (i) an aqueous solution comprising at (alk)acrylamide monomer and optionally, at least one ethylenically unsaturated comonomer, a formaldehyde and a secondary amine or a complex thereof;
  - (ii) an oil solution comprising at least one hydrocarbon liquid; and
  - (iii) an effective amount of surfactant or surfactant mixture, so as to form an inverse microemulsion;
- (b) subjecting the inverse microemulsion obtained in step (a) to polymerization conditions and allowing the formaldehyde and secondary amine to react with the (alk)acrylamide amide groups; and
- (c) optionally, quaternizing the resultant polymer.

Polymerization, according to the present invention, is carried out by the addition of a polymerization initiator or by subjecting the inverse microemulsion to ultraviolet or ionizing irradiation.

Formaldehydes useful in the practice of this invention are selected from formaldehyde, paraformaldehyde, trioxane or aqueous formalin, etc.

Useful secondary amines are selected from dimethylamine, methylethylamine, diethylamine, amylmethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylamine, ethanolmethylamine, diethanolamine or mixtures thereof.

Especially preferred is a process wherein the formaldehyde comprises formalin and the secondary amine comprises dimethylamine. It is also contemplated to employ a formaldehyde-secondary amine complex such as N,N-dimethylaminomethanol.

The ratio of formaldehyde to amine is not critical and can range from about 10:1 to 1:10, by mole, respectively. It is generally preferred, however, to use a molar ratio as close to 1:1 as practice. A sufficient quantity of the amine and formaldehyde or complex thereof is required to impart at least 1 mole percent of the tertiary aminomethyl groups to the acrylamide polymer.

According to the present invention there are also provided a method of releasing water from a dispersion of suspended

solids which comprises (a) adding to the dispersion from about 10 to about 100,000 parts per million of a composition comprising (meth) acrylamide-containing polymeric microparticles, the (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having a average particle size of from about 200 to about 4000 Å in diameter; and (b) dewatering the mixture of the dispersion of suspended solids and said composition. Dispersions of suspended solids comprising sewage sludge are exemplary.

#### DETAILED DESCRIPTION OF THE INVENTION

Preparation of Mannich acrylamide polymers as small, aqueous, inverse microemulsion droplets or micelles allows the composition to be prepared at a high polymer solids content while substantially eliminating the detrimental interpolymer cross-linking problems inherent in inverse emulsion and solution product forms thereof and while simultaneously maintaining a low product bulk viscosity.

The compositions of this invention comprise (alk)acrylamide-containing polymeric microparticles, the (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter and are generally prepared by an inverse microemulsion polymerization process.

The backbone of the Mannich acrylamide polymers of the present invention may comprise units of such (alk)acrylamides as acrylamide, methacrylamide, ethacrylamide and the like.

The backbones of the Mannich acrylamide polymers of the present invention may also comprise an (alk)acrylamide copolymerized with a cationic or non-ionic, water-soluble, ethylenically unsaturated comonomer in amounts up to about 90%, by weight. Water-soluble, anionic comonomers may also be used in substantially lower amounts.

Useful cationic monomers include diallyl dialkylammonium chlorides, N,N-dialkylaminoalkyl(meth)acrylates, N,N-dialkylaminoalkyl(meth)acrylamides, salts, quaternaries and mixtures thereof.

Anionic monomers useful in the practice of this invention may comprise acrylic or methacrylic acid, fumaric acid, crotonic acid; maleic acid, salts thereof; 2-acrylamido-2-methylpropane sulfonic acid; styrene sulfonic acid and their salts and the like.

Water-soluble, non-ionic monomers, suitable in the practice of this invention, generally comprise N-vinyl pyrrolidone, N,N-dialkylmethacrylamides, hydroxyalkyl methacrylates; N-vinylformamide and the like. Small quantities, i.e. up to about 10%, by weight, of other copolymerizable monomers, such as methyl acrylate; methyl methacrylate; acrylonitrile; vinyl acetate; styrene etc. may also be used.

Formaldehydes suitable for use in this invention, as mentioned above, are selected from formaldehyde; paraformaldehyde; trioxane; aqueous formalin and mixtures thereof. Secondary amines suitable for use in the practice of this invention are selected from those containing from about 2 to about 8 carbon atoms which are aliphatic, cyclic, straight chained or branched.

The compositions of the present invention may be prepared using inverse microemulsion polymerization techniques. Polymerization in microemulsions and inverse microemulsions is known to those skilled in this art. P.



Speiser reported in 1976 and 1977 a process for making spherical "nanoparticles" with diameters less than 800 Å by (1) solubilizing monomers, such as acrylamide and methylenebisacrylamide and other materials, such as drugs in micelles and (2) polymerizing the monomers, see J. Pharm. Sa., 65 (12), 1763 (1976) and U.S. Pat. No. 4,021,364. Both water-in-oil and oil-in-water systems can be used to prepare these nanoparticles. While not specifically called microemulsion polymerization by the author, this prior art process does contain all the features which are currently used to define microemulsion polymerization. These reports also constitute the first examples of polymerization of acrylamide in a microemulsion. Since then, numerous publications reporting polymerization of water-soluble polymers in the inverse phase of microemulsions have appeared, see, for example, U.S. Pat. Nos. 4,521,317 and 4,681,912 and [GB 2162492 A.]GB 2161492 A, incorporated herein by reference.

In general, microemulsion polymerization processes are conducted by (i) preparing a monomer microemulsion by mixing an aqueous solution of monomers with a hydrocarbon liquid containing an appropriate surfactant or surfactant mixture to form an inverse microemulsion consisting of small aqueous monomer droplets dispersed in the continuous oil phase and (ii) subjecting the monomer microemulsion to free radical polymerization.

In order to obtain an inverse microemulsion, it is generally necessary to use particular conditions whose main parameters are as follows: surfactant concentration, HLB of surfactant or surfactant mixture, temperature, nature of the organic phase and composition of the aqueous phase.

Suitable monomers are non-ionic, anionic and cationic and are as defined above. The aqueous monomer solution may contain such conventional additives as are desired. For example, the solution may contain chelating agents to remove polymerization inhibitors, chain-transfer agents, pH adjusters, initiators and other conventional additives.

Essential to the formation of the microemulsion, which may be defined as a transparent and thermodynamically stable solution, comprising two liquids insoluble in each other and a surfactant, in which the micelles are usually 1000 Å or less in diameter, is the selection of appropriate organic phase and surfactant.

The selection of the organic phase has a substantial effect on the minimum surfactant concentration necessary to obtain the inverse microemulsion and may consist of a hydrocarbon or hydrocarbon mixture. Isoparaffinic hydrocarbons or mixtures thereof are the most desirable in order to obtain inexpensive formulations. Typically the organic phase will comprise mineral oil, toluene, fuel oil, kerosene, odorless mineral spirits, mixtures of any of the foregoing and the like.

The ratio by weight of the amounts of aqueous phase and hydrocarbon phase is chosen as high as possible, so as to obtain, after polymerization, a microemulsion of high polymer content. Practically, this ratio may range, for example, from about 0.5 to about 3.1, and usually approximates 1:1.

The one or more surfactants are selected in order to obtain an HLB (Hydrophilic Lipophilic Balance) value ranging from about 8 to about 12. Outside this range, formation of inverse microemulsions generally cannot be attained. In addition to the appropriate HLB value, the concentration of surfactant must be optimized, i.e., sufficient to form an inverse microemulsion. Too low a concentration of surfactant leads to the formation of standard inverse emulsions and too high a concentration results in increased costs and does

not impart any significant benefit. Typical surfactants useful in the practice of this invention may be anionic, cationic or nonionic. Preferred surfactants include sorbitan monooleate, polyoxyethylene (20) sorbitan monooleate, sodium dioctylsulfosuccinate, oleamidopropyldimethyl amine, sodium isostearyl-2-lactate and the like.

Polymerization of the microemulsion may be carried out in any manner known to those skilled in the art. Initiation may be effected with a variety of thermal and redox free radical initiators, including peroxides, e.g. t-butyl peroxide; azo compounds, e.g. azobisisobutyronitrile; inorganic compounds, such as potassium persulfate and redox couples, such as ferrous ammonium sulfate/ammonium persulfate. Initiator addition may be effected any time prior to the actual polymerization per se. Polymerization may also be effected by photochemical irradiation processes, such as ultraviolet irradiation or by ionizing irradiation from a cobalt 60 source.

It is possible to perform the Mannich substitution reaction at various stages in relation to the inverse microemulsion polymerization. The formaldehyde and secondary amine may be added after the inverse microemulsion polymerization of the (alk)acrylamide and then reacted with the resultant polymer to form the tertiary aminomethyl group on the (alk)acrylamide polymer backbone. It is also possible to react the (alk)acrylamide monomer with the formaldehyde and secondary amine prior to the inverse microemulsion formation and before polymerization of the monomers. Also contemplated, is adding the formaldehyde and secondary amine to the aqueous solution prior to polymerizing and then polymerizing the (alk)acrylamide monomer and carrying out the Mannich reaction.

If desired, the Mannich polymers produced by the procedures of the present invention may be quaternized as is known in the art, such as by reacting the Mannich polymers with such quaternizing agents as methyl chloride, dimethyl sulfate, benzyl chloride and the like under known conditions.

The polymers of the present invention can conveniently be employed as flocculants prepared in the form of dilute aqueous solutions. These solutions can be prepared by inverting the microemulsion into water, optionally in the presence of a breaker surfactant, or by recovering the polymer from the microemulsion, such as by stripping or by adding the microemulsion to a solvent which precipitates the polymer, e.g. isopropanol or acetone, filtering off the resultant solids, drying and redispersing in water. The microemulsion can also be stripped to increase the percentage of polymer solids thereof.

Concentrating dispersions of suspended solids is carried out by adding an effective amount of the compositions of this invention, in solution form to the suspension to remove water there to produce an effluent of desired characteristics.

The products of this invention are useful in facilitating a wide range of solid-liquid separation operations. The cationic polymers may be used in the dewatering of biologically treated suspensions, such as sewage and other municipal or industrial sludges, the drainage of cellulosic suspension such as those found in paper production, e.g. paper waste, and the settlement of various inorganic suspensions, i.e. refinery waste, food waste etc.

#### DESCRIPTION OF THE PREFERRED EMBODIMENTS

The following examples illustrate the present invention. They are not to be construed to limit the claims in any manner whatsoever.



Standard Viscosity (SV) is measured by adding 50 gms of a 0.2% aqueous polymer solution to 50 gms of water, stirring the resulting mixture for 5 minutes to completely dissolve the salt, adjusting the pH to 5 and determining the viscosity at 25±0.1° C. using a Brookfield viscometer (LVT model) with UL adapter at 50 rpm. Cationic equivalent (CEQ) is measured by the technique described in J. Chem. Ed., 62 (7), 627 (1985).

EXAMPLE 1

Microemulsion Preparation

100 gms of an aqueous solution (pH=3.5) containing 42.3 gms of acrylamide and 0.02 gm of 2-hydroxyethyl ethylenediaminetriacetic acid are pumped at the rate of 4.4 ml/min into 150 gms of an organic solution containing 128.5 gms of an isoparaffinic solvent having a b. p. of 207°–254° C. (IPS), 21.9 gms of polyoxyethylenesorbitol hepaoleate (PESH) and 7.8 gms of sorbitan sesquioleate (SS). A clear, monomer containing microemulsion is obtained.

0.0424 gms of 2,2,'-azobis-4-methoxy-2,4-dimethylvaleronitrile in 2 mls of ethyl acetate is added to the monomer containing microemulsion which was previously sparged for 40 minutes using nitrogen. Polymerization is conducted at 30° C. The produce is a clear, stable polyacrylamide (PAM) microemulsion (S.V.=3.8 cps).

DMAM Preparation

N,N-dimethyaminomethanol (DMAM) is prepared by slowly adding 7.7 gms of 95 percent paraformaldehyde to a 100 ml flask containing 27.50 gms of a 55 percent aqueous solution of dimethylamine and 6.60 gms of deionized water, keeping the exotherm below 45° C. The resultant DMAM solution is then filtered yielding a clear solution possessing 53.20 gms of DMAM solids.

Mannich PAM Microemulsion Preparation

30.0 gms of the above PAM microemulsion are placed in a suitable reactor. The emulsion is warmed to 30° C. Next 10.0 gms of the DMAM solution prepared above are added to the PAM microemulsion at a rate of 0.08 ml/min. with gentle stirring. The resulting Mannich PAM microemulsion is stored at ambient temperature until use. After 24 hours, the polymer has a CEQ of 5.75 meq/g and S.V. of 2.5 cps.

Free-Drainage Testing

The efficiency of dewatering a typical municipal sludge is determined as follows: 200 gms of sludge are carefully weighed into screw cap jars. Aqueous solutions of Mannich PAM flocculants are prepared by adding the microemulsion (or in the comparative examples, a solution of commercial 14Mannich PAM) to water so that the polymer concentration is 0.2 weight percent. Various doses of the polymer solutions are added to the sludge samples, water is added to bring the total weight to 250 gms, the mixtures are agitated for 90 seconds, the resulting flocculated sludge is poured into a Buchner funnel containing a filter cloth, and the free drainage is determined by measuring the volume of filtrate collected in 10 seconds. The results are set forth in Table 1, below.

TABLE I

MANNICH PAM OF EXAMPLE NO.	DOSE (ml)	FILTRATE (ml)
1	10	100
	12.5	152
	15	158
	17.5	160
	20	140
1C	10	60
	12.5	120
	15	140
	17.5	160
	20	128

C= commercially available product

Table 1 clearly shows the superior performance of the Mannich PAM microemulsion of Example 1 as compared to a typical, commercially available, solution Mannich PAM.

EXAMPLES 2–7

Examples 2–7 describe the preparation of PAM microemulsions which are used for the preparation of a series of Mannich PAM microemulsions.

EXAMPLE 2

To 150 gms of an organic solution containing 128.5g of IPS, 21.9 gms of PESH and 7.8 gms of SS are slowly added 100 gms of a pH 3.5 aqueous solution containing 42.3g of acrylamide and 0.02 gm of N-(2-hydroxyethyl) ethylenediaminetriacetic acid with stirring. The resulting clear, monomer microemulsion is sparged for 40 minutes with nitrogen. 0.0424 gm of 2,2,'-azobis-4-methoxy-2,4 dimethylvaleronitrile in 2 mls of ethyl acetate is then added and the microemulsion polymerized at 30° C. The resulting product is a clear, stable PAM microemulsion having a Standard Viscosity (S.V) of 3.8 cps and a particle size average of 650 Å (median value as measured by transmission electron microscopy).

EXAMPLE 3

The procedure of Example 2 is again followed and produces a polyacrylamide microemulsion with an S.V. of 3.7 cps.

EXAMPLE 4–6

The procedure of Example 2 is used to prepare the PAM microemulsions of Examples 4–6 with the exception that the amount of emulsifier is altered as shown in Table II, below, to vary the resultant PAM microemulsion particle size.

TABLE 2

PAM MICRO- EMULSION	PESH-g	SS-g	PARTICLE SIZE (Å) <sup>a</sup>	S.V. (cps)
Example 4	18.72	6.66	590	3.7
Example 5	15.60	5.55	710	3.5
Example 6	12.48	4.44	960	3.6

<sup>a</sup>as measured by transmission electron microscopy  
S.V. = Standard Viscosity

EXAMPLE 7

Example 7 shows the preparation of a PAM microemulsion with a different emulsifier system.



To 145 gms of an organic solution containing 120 gms of IPS, 14.82 gms of PESH and 11.12 gms of the reaction product of diethanolamine and oleic acid (DOA) are slowly added 100 gms of a pH 3.5 aqueous solution containing 42.3 gms of acrylamide and 0.02 gm of N-(2-hydroxyethyl)-ethylenediaminetriacetic acid with stirring. The resulting clear, monomer containing microemulsion is sparged for 40 minutes with nitrogen. 0.0423 gm of 2,2,'-azobis-4-methoxy2,4-dimethylvaleronitrile in 2 mls of ethyl acetate are then added and the microemulsion is polymerized at 30° C. The resulting product is a clear, stable PAM microemulsion having an S.V. of 3.1 cps.

EXAMPLE 8

Example 8 describes the preparation of dimethylamine/formaldehyde (DMA/CH2O) adducts used to prepare Mannich PAM microemulsions from the PAM microemulsions of Examples 2, 3, 6 and 7.

A. 10.08 gms of 95 percent paraformaldehyde are slowly added to a reaction vessel containing 26.3 gms of a 55 percent aqueous solution of dimethylamine keeping the exotherm below 45° C. The resulting solution is filtered yielding a clear solution.

B. To 30.0 gms of the solution prepared in Example 8A are added 3.05 gms of 100 percent dimethylamine with mixing, bringing the DMA/CH2O ratio from 1/1 to 1.25/1.

EXAMPLES 9-15

Examples 9-15 describe the preparation of Mannich PAM microemulsions with differing amounts of dimethylaminomethyl substitution from the PAM Microemulsions of Examples 2, 3 and 6 and the DMA/CH2O adduct from 8B.

30.0 gms of the PAM microemulsion from Example 2 are placed in a reaction vessel at ambient temperature. To this are slowly added 11.0 gms of the DMA/CH2O adduct from Example 8B, with stirring, yielding a clear, Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water resulting in a Mannich PAM with an S.V. of 3.9 cps and a CEQ of 6.2 meq/g. The identical procedure is used to prepare the Mannich PAM microemulsions of Examples 10-15, which differ only in the amount of DMA/CH2O adduct charged and the PAM microemulsion, as shown in Table 3.

TABLE 3

EXAMPLE	DMA/CH <sub>2</sub> O adduct (g)	PAM MICRO-EMULSION OF EXAMPLE NO.	CEQ (meq/g)	S.V. (cps)
9	11.0	Ex. 2	6.2	3.9
10	6.6	Ex. 2	3.5	4.8
11	4.4	Ex. 2	3.3	4.6
12	2.2	Ex. 2	—	4.1
13	1.1	Ex. 3	—	2.7
14	1.5	Ex. 3	—	2.7
15	11.0	Ex. 6	—	4.1

EXAMPLE 16

Example 16 is a repeat of Example 8A, with the exception being a slight dilution of the clear solution to reduce the adduct concentration. 22.3 gms of 95 percent paraformaldehyde are slowly added to a vessel containing 57.78 gms of a 55 percent aqueous solution of dimethylamine keeping the exotherm below 45° C. The resulting solution is filtered yielding a clear solution. 12.30 gms of deionized water are then added.

EXAMPLES 17-19

Examples 17-19 describe the preparation of Mannich PAM microemulsions from PAM microemulsions of Examples 2, 6 and 7 and with a DMA/CH2O (1/1) adduct.

EXAMPLE 17

30.0 gms of the PAM microemulsion from Example 2 are placed in a vessel at ambient temperature. To this are slowly added 10.0 gms of the DMA/CH2O adduct from Example 16 with stirring, yielding a Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water resulting in a Mannich PAM with an S.V. of 3.7 cps and a CEQ of 5.6 meq/g. The identical procedure is used to prepare the Mannich PAM microemulsions of Examples 18-19 as shown in Table 4, except different PAM microemulsions are used.

TABLE 4

EXAMPLE	DMA/CH <sub>2</sub> O adduct (g)	PAM MICRO-EMULSION OF EXAMPLE NO.	CEQ (meq/g)	S.V. (cps)
18	10.0	Ex. 7	5.1	2.4
19	10.0	Ex. 6	5.4	3.3

EXAMPLE 20

Example 20 describes the preparation of PAM microemulsion via redox initiation.

To 149.64 gms of an organic solution containing 128.5 gms of IPS, 21.9 gms of PESH and 7.8 gms of SS are slowly added 100 gms of a pH 3.0 aqueous solution containing 42.3 gms of acrylamide, 0.00428 gm of sodium bromate and 0.02 gm of N-(2-hydroxyethyl)ethylenediaminetriacetic acid with stirring. The resulting clear, monomer microemulsion is sparged for 40 minutes with nitrogen, SO2 gas is then bubbled into the microemulsion while holding the polymerization temperature at 25° C. The resulting product is a clear, stable PAM microemulsion having an S.V. of 3.58 cps.

EXAMPLES 21-22

30 Examples 21 and 22 show the preparation of a morpholine/formaldehyde adduct and the Mannich 1PAM microemulsion prepared from this adduct.

EXAMPLE 21

10.08 gms of 95 percent paraformaldehyde are slowly added to a reaction vessel containing 27.84 gms of morpholine and 15.45 gms of water keeping the exotherm below 45° C. The resulting solution is filtered yielding a clear solution.

EXAMPLE 22

30.0 gms of the PAM microemulsion from Example 2 are placed in a vessel at ambient temperature. To this are slowly added 11.80 gms of the morpholine/CH2O adduct of Example 21 with stirring yielding a clear, Mannich PAM microemulsion. After approximately 17 days, the microemulsion is inverted into water giving a Mannich PAM solution with an S.V. of 1.4 cps and a CEQ of 3.1 meq/g.

EXAMPLE 23

Example 23 shows the preparation of a Mannich PAM microemulsion where formaldehyde and diethylamine are charged sequentially into the PAM microemulsion.



## 11

30.0 gms of the PAM microemulsion from Example 3 are placed in a vessel at ambient temperature. To this are slowly added 2.85 gms of 37.2 percent aqueous formaldehyde with stirring. Next, 2.56 gms of diethylamine are slowly added to the microemulsion with stirring, yielding a slightly hazy, Mannich PAM microemulsion. After 24 hours, the microemulsion is inverted into water giving a Mannich PAM solution having an S.V. of 2.1 cps and a CEQ of 3.0 meq/g.

## EXAMPLES 24-25

Examples 24 and 25 show the preparation of a diethylamine/dimethylamine/formaldehyde (0.5/0.5/1) adduct and the Mannich PAM microemulsion prepared from this adduct.

## EXAMPLE 24

10.08 gms of 95 percent paraformaldehyde are slowly added to a reaction vessel containing 12.83 gms of a 56 percent aqueous solution of dimethylamine, 11.67 gms of diethylamine and 8.32 gms of water, keeping the exotherm below 45° C. The resulting solution separates into two layers. The bottom layer, which weighs 32.6 gms if shown by NMR to be the desired diethylamine/dimethylamine/formaldehyde (0.5/0.5/1) adduct. This layer is collected and used in Example 25 to prepare a Mannich PAM microemulsion.

## EXAMPLE 25

30.0 gms of the PAM microemulsion from Example 3 are placed in a vessel at ambient temperature. To this is slowly added the diethylamine/dimethylamine/formaldehyde adduct of Example 24 with stirring to yield a clear, Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich PAM with an S.V. of 2.8 cps and a CEQ of 4.04 meq/g.

## EXAMPLES 26-31

Examples 26-28 describe the preparation of PAM copolymer microemulsions using acrylic acid (AA), 2-acrylamido-2-methylpropanesulfonic acid (AMMPS), and diallyl dimethylammonium chloride (DADM), respectively, as the comonomers with acrylamide. Examples 29-31 describe the preparation of Mannich PAM microemulsions from these systems.

## EXAMPLE 26

To 299.3 gms of an organic solution containing 240 gms of IPS, 43.78 gms of PESH and 15.5 gms of SS are slowly added 200 gms of a pH 3.15 aqueous solution containing 80.38 gms of acrylamide, 4.29 gms of acrylic acid and 0.028 gms of N-(2-hydroxyethyl)ethylenediaminetriacetic acid with stirring. The resulting clear monomer microemulsion is sparged for 40 minutes with nitrogen. 0.0424 gm of 2,2, azobis-4-methoxy-2,4-dimethylvaleronitrile, in 2 mls of ethyl acetate, are then added and the microemulsion is polymerized at 30° C. The resulting product is a clear, stable acrylamide-acrylic acid copolymer microemulsion with an S.V. of 3.48 cps.

## EXAMPLE 27

To 150 gms of an organic solution containing 120.0 gms of IPS, 15.0 gms of PESH and 15.0 gms of SS are slowly added 100 gms of a pH 8.5 aqueous solution containing 31.22 gms of acrylamide, 11.18 gms of AMMPS and 0.02

## 12

gm of N-(2-hydroxyethyl)ethylenediaminetriacetic acid with stirring. The resulting monomer microemulsion is sparged for 40 minutes with nitrogen. 1.0 gm of a 4.24 percent solution of 2,2'-azobis(2,4-dimethylpentane) nitrile in ethyl acetate are then added and the microemulsion is polymerized at 50° C. The resulting product is a clear, stable, acrylamide-AMMPS copolymer microemulsion with an S.V. of 3.0 cps.

## EXAMPLE 28

To 137.1 gms of an organic solution containing 120 gms of decane, 14.20 gms of PESH and 2.90 gms of polyoxyethylene sorbitan monooleate (POSO) are slowly added 106.97 gms of an aqueous solution containing 17.23 gms of acrylamide, 25.92 gms of DADM and 0.02 gm of N-(2-hydroxyethyl)-ethylenediaminetriacetic acid with stirring. The resulting clear, monomer microemulsion is sparged for 40 minutes with nitrogen. 0.0424 gm of 2,2'-azobis-4-methoxy-2,4-dimethylvaleronitrile in 0.8 gm of ethyl acetate is then added and the microemulsion is polymerized at 30° C. The resulting product is a clear, stable acrylamide-DADM copolymer microemulsion with an S.V. of 2.3 cps.

## EXAMPLE 29

30.0 gms of the acrylamide/acrylic acid copolymer microemulsion of Example 26 are placed in a vessel at ambient temperature. To this are slowly added a solution of 9.50 gms of the DMA/CH<sub>2</sub>O adduct of Example 16 and 0.36 gm of dimethylamine with stirring yielding a Mannich acrylamide-acrylic acid copolymer microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich copolymer with an S.V. of 4.1 cps and a CEQ of 6.33 meq/g.

## EXAMPLE 30

30.0 gms of the acrylamide/AMMPS copolymer microemulsion of Example 27 are placed in a vessel at ambient temperature. To this are slowly added 7.06 gms of a solution of the DMA/CH<sub>2</sub>O adduct of Example 16 and 0.645 gm of dimethylamine with stirring yielding a Mannich acrylamide-AMMPS copolymer with an S.V. of 1.7 cps and a CEQ of 4.1 meq/g.

## EXAMPLE 31

30.0 gms of the acrylamide/DADM copolymer microemulsion of Example 28 are placed in a vessel at ambient temperature. To this are slowly added 4.06 gms of a solution of the DMA/CH<sub>2</sub>O adduct of Example 16 and 0.41 gm of dimethylamine with stirring yielding a Mannich acrylamide-DADM copolymer microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich copolymer with an S.V. of 2.3 cps and a CEQ of 6.70 meq/g.

## EXAMPLES 32-43

Examples 32-35 describe the preparation of inverse emulsion PAMS with particle sizes of 3600 Å; 6600 Å; 11,400 Å and 20,500 Å which are then converted to Mannich PAM inverse emulsions by reacting them with DMA/CH<sub>2</sub>O (1.25/1 and 1/1) adducts in Examples 36-39 and 40-43, respectively. The products of Examples 17, 19 and 40-43 are then used to determine the effect of particle size on flocculation performance.

## EXAMPLES 32-35

The general procedure used to prepare the inverse emulsion PAMS is as follows: DOA and an A/B/A block copoly-



13

mer of about 5000 m.w. wherein the A units comprise palmitic acid and 12-hydroxystearic acid (1:5) and the B units are polyethyleneoxide (m.w. 1500), hereinafter PHP, are dissolved in low odor paraffin solvent (OPS) to produce an oil solution. An aqueous monomer solution is prepared by dissolving a 52 percent aqueous solution of acrylamide, the disodium salt of ethylenediaminetetraacetic acid (EDTA-2Na) 2,2'-azobis(2-amidinopropane) hydrochloride and Na<sub>2</sub>SO<sub>4</sub> in water, and then adjusting the pH to 3.0–3.5 with 10 percent sulfuric acid. The aqueous monomer solution is then added to the oil solution and emulsified. The resulting inverse emulsion is sparged with nitrogen and then initiated with UV light at 25° C. The polymerization is continued for approximately 3.5 hours. The particle size average is a median value as measured by a Horiba particle size analyzer. The composition of the inverse emulsions and the resulting polymer characteristics are shown below in Table 5.

TABLE 5

	Example 32	Example 33 (C)	Example 34 (C)	Example 35 (C)
OIL PHASE				
OPS	70.8	70.8	70.8	70.8
A/E/A	7.5	7.5	7.5	7.5
PHP	1.25	1.25	1.25	1.25
Acrylamide (52%)	86.6	86.6	86.6	86.6
EDTA.2Na (10%)	0.23	0.23	0.23	0.23
Na <sub>2</sub> SO <sub>4</sub> (1.93%)	3.58	3.58	3.58	3.58
AQUEOUS PHASE				
Azo Cat. (2%)	0.45	1.13	2.25	2.25
Water	94.5	93.8	92.7	92.7
POLYMER				
Conversion. %	97.4	96.0	97.8	98.5
S.V. cps	3.7	3.6	3.1	3.8
Particle size. Å	3.600	6.600	11.400	22.500

\* = all components are given in grams  
S.V. = standard viscosity  
C = comparative

14

EXAMPLE 44

The performance of the Mannich PAM microemulsion of Example 9 is determined by free-drainage sludge dewatering tests as follows: 200 gms of sewage sludge from the Stamford, CT waste treatment plant is carefully weighed into screw cap jars. Aqueous solutions of Mannich PAM flocculant are prepared so that the concentration of polymer is 0.2%. Various doses of the solutions are added to the sludge samples, the sludge is agitated for 90 seconds, the resulting flocculated sludge is poured into a Buchner funnel containing a filter cloth, and the free drainage is determined by measuring the volume of filtrate collected in 10 seconds. The improved performance of Mannich PAM microemulsion from Example 9 (10 days old) compared to a commercially available Mannich PAM is clearly seen in Table 7.

EXAMPLES 36–43

The following is a general description of the method used to prepare the Mannich PAM inverse emulsions of Examples 36–43. 30.0 gms of PAM inverse emulsion from the previous designated example is placed in a vessel at ambient temperature. To this is slowly added a solution of DMA/CH<sub>2</sub>O adduct with stirring yielding a stable Mannich PAM inverse emulsion. After several days, the Mannich PAM inverse emulsion is inverted into water giving a Mannich PAM and the S.V. and the CEQ are determined. The compositions of the examples and the resulting characteristics are shown in Table 6, below.

TABLE 6

Example	Inverse Emul. of Ex. No.	DMA/CH <sub>2</sub> O RATIO	wt. DMA/CH <sub>2</sub> O (g)	Polymer SV (cps)	Polymer CEQ (meq/g)
6	32	1.25	11.0	3.9 (3 days)	5.7
7	33	1.25	11.0	3.8 (3 days)	6.0
8	34	1.25	11.0	3.7 (3 days)	6.3
9	35	1.25	11.0	3.9 (3 days)	5.8
0	32	1.0	10.0	3.9 (2 days)	5.2
1	33	1.0	10.0	3.8 (2 days)	4.9
2	34	1.0	10.0	3.2 (2 days)	5.5
3	35	1.0	10.0	3.9 (2 days)	5.3

TABLE 7

Mannich PAM of Example No.	Dose (ml)	Filtrate (ml)
9	9.5	70
	10.5	108
	11.0	135
	12.5	125
	13.0	125
	15.0	105
9C	11.5	65
	12.5	85



TABLE 7-continued

Mannich PAM of Example No.	Dose (ml)	Filtrate (ml)
	13.0	85
	15.0	98
	16.5	120
	17.5	125
	20.0	120

C= commercially available product

EXAMPLE 45

The significance of particle size on performance is determined by free-drainage testing of the aged (72 day old) microemulsions and inverse emulsions as shown in Table 8, below. The test results clearly show the increase in flocculant dose required as the particle size increases.

TABLE 8

Emulsion of Example No.	Micelle Size (Å)	Aged Polymer SV (cps)	Aged Polymer CEQ (meq/g)
17	650	1.2	5.5
19	960	1.1	5.4
40	3,600	1.2	<0.2
41	6,660	1.1	<0.2
42	10,400	1.1	<0.2
43	20,500	1.1	<0.2

Emulsion of Example No.	Dose (ml)	Filtrate (ml)
17	15	120
	17.5	160
	20	165
	22.5	160
19	15	90
	17.5	145
	20	170
	22.5	180
40	20	100
	22.5	135
	25	180
	30	180
41c	20	55
	30	100
	35	165
	37.5	180
42c	40	185
	30	128
	32.5	148
	35	175
43c	40	185
	30	98
	40	130
	50	175

C= comparative

EXAMPLE 46

The procedure of Example 1 is again followed except that the Mannich PAM microemulsion is subjected to treatment with dimethyl sulfate to quaternize the Mannich PAM. A quaternized polymer is recovered.

EXAMPLE 47

The procedure of Example 1 is again followed except that the acrylamide is replaced by an equivalent amount of methacrylamide. Substantially identical results are achieved.

EXAMPLE 48

The procedure of Example 27 is again followed, except that the AMMPS is replaced by 1-methacryloyl-4-methyl

piperazine. Treatment of the resultant polymer as in Example 30 produces a similar Mannich copolymer.

EXAMPLE 49

To 246.05 grams of an organic solution containing IPS (199.7 gms), PESH (31.6 gms) and SS (13.9 gms) are slowly added 242.5 gms of a pH 3.0 aqueous solution containing acrylamide (109.8 gms) sodium bromate (0.0055 g) and N-(2-hydroxyethyl)-ethylenediaminetriacetic acid (0.10 g) with stirring. The resulting, slightly cloudy, monomer microemulsion is sparged for 40 minutes with nitrogen. SO<sub>2</sub> gas is then bubbled into the resultant microemulsion and the polymerization temperature kept at 55° C. The SO<sub>2</sub> gas is prepared by passing nitrogen gas through a 0.5% sodium metabisulfite solution. The resulting product is a clear, stable, polyacrylamide microemulsion having an S.V. of 2.7 cps.

EXAMPLE 50

A. Paraformaldehyde (92.4 gms, 95%) is slowly added to a suitable vessel containing a dimethylamine (218.4 gms, 60.4% aqueous solution) while keeping the exotherm below 45° C. The resulting solution is allowed to cool with stirring and is then filtered yielding a clear solution.

B. To 70.0 gms of the product of Example 50A are added 17.13 gms of deionized water.

C. To 190.0 gms of the product of Example 50A are added 15.04 qms of dicyanadiamide, 18.62 gms of sodium bisulfite, and 12.86 gms deionized water. The solution is filtered yielding a clear solution.

EXAMPLE 51

150 gms of the PAM microemulsion of Example 49 are placed in a reaction vessel at ambient temperature. To this are slowly added 62.7 gms of the DMA/CH<sub>2</sub>O adduct from Example 50B, with stirring, yielding a hazy, Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich PAM with an S.V. of 2.65 cps and a CEQ of 6.6 meg/g.

EXAMPLE 52

150 gms of the PAM microemulsion of Example 49 are placed in a reaction vessel at ambient temperature. To this are slowly added 62.7 gms of the DMA/CH<sub>2</sub>O adduct from Example 50C, with stirring, yielding a clear, Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich PAM with an S.V. of 2.65 cps and a CEQ of 6.2 meg/g.

EXAMPLE 53

75 gms of the Mannich PAM microemulsion of Example 52 are placed in a pressure reactor mounted on a shaker. To this are added 8.5 gms of methylchloride at ambient temperature over a period of approximately 2 hours, keeping the pressure of the reactor under 30 psi. The resulting product is a clear, stable, quaternized Mannich PAM having an S.V. of 2.1 cps.

EXAMPLE 54

50 gms of the Mannich PAM microemulsion of Example 52 are placed in a pressure reactor mounted on a shaker. To this are added 4.5 gms of methylchloride at ambient temperature over a period of approximately 2 hours, keeping the pressure of the reactor under 30 psi. The resulting product is a clear, stable, quaternized Mannich PAM having an S.V. of 2.2 cps.



EXAMPLE 55

50 gms of the Mannich PAM microemulsion of Example 52 are placed in a pressure reactor mounted on a shaker. To this are added 2.9 gms of methylchloride at ambient temperature over a period of approximately 2 hours, keeping the pressure of the reactor under 30 psi. The resulting product is a clear, stable, quaternized Mannich PAM having an S.V. of 2.4 cps.

EXAMPLE 56

50 gms of the Mannich PAM microemulsion of Example 51 are placed in a pressure reactor mounted on a shaker. To this are added 6.0 gms of methylchloride at ambient temperature over a period of approximately 2 hours, keeping the pressure of the reactor under 30 psi. The resulting product is a clear, stable, quaternized Mannich PAM having an S.V. of 1.8 cps.

EXAMPLE 57

150 gms of the PAM microemulsion of Example 49 are placed in a reaction vessel at ambient temperature. To this are slowly added 25.1 gms of the DMA/CH<sub>2</sub>O adduct from Example 50C, with stirring, yielding a hazy, Mannich PAM microemulsion. After approximately 24 hours, the microemulsion is inverted into water giving a Mannich PAM with an S.V. of 2.65 cps.

EXAMPLE 58

50 gms of the Mannich PAM microemulsion of Example 57 are placed in a pressure reactor mounted on a shaker. To this are added 2.7 gms of methylchloride at ambient temperature over a period of approximately 2 hours, keeping the pressure of the reactor under 30 psi. The resulting product is a clear, stable, quaternized Mannich PAM having an S.V. of 1.4 cps.

EXAMPLE 59

The performance of the quaternized Mannich PAMs of Examples 53–56 and 58 is determined by free drainage sludge dewatering tests as follows: 200 gms of sewage sludge from a municipal waste treatment plant are carefully weighed into jars. Aqueous solutions of the quaternized Mannich PAM flocculant are prepared so that the concentration of polymer is 0.2%. Various doses of the resultant solutions are added to the sludge samples, the sludge agitated for 5 seconds at 300 rpm with an overhead mixer, the resulting flocculated sludge poured into a Buchner funnel containing a filter cloth and the free drainage determined by measuring the milliliters of filtrate collected in 10 seconds. The efficacy of the quaternized polymers (QP) as flocculants is clearly seen in Table 9, below, where they are compared to a commercially available cationic flocculant with similar charge.

TABLE 9

QP of Example	Dosage (lbs/ton)	Filtrate Vol. (ml)
53	3.72	140
	5.58	155
	7.44	155
	9.30	160
54	3.72	140
	5.58	155
	7.44	155

TABLE 9-continued

QP of Example	Dosage (lbs/ton)	Filtrate Vol. (ml)
55	9.30	160
	3.72	145
	5.58	155
	7.44	170
56	9.30	165
	3.72	130
	5.58	155
	7.44	165
58	9.30	170
	3.72	48
	5.58	50
	7.44	60
Comm.	9.30	95
	11.16	110
	13.02	115
	14.88	120
Comm.	16.74	128
	1.86	125
	3.72	140
	5.88	148
Comm.	7.44	148

Comm = Commercially available copolymer of acrylamide and acryloxyethyl-trimethylammonium chloride (45.55).

Following the testing procedure set forth above, (Example 59) except where modified as indicated, other quaternary polymers falling within the scope of the instant invention are tested as flocculants. The results are set forth in Table 10, below.

TABLE 10

QP of Example	Dosage (lbs/ton)	Filtrate Vol. (ml.)	Cake Solids
46 (S.V = 1.2) <sup>1</sup>	Sludge #2		
	25.0	140	21.2
	27.5	148	21.0
	30.0	142	21.5
Comm. <sup>1</sup>	32.5	136	21.1
	22.5	114	19.7
	25.0	142	19.9
	27.5	134	20.6
46 (S.V = 2.0) <sup>2</sup>	Sludge #3		
	40.0	130	10.5
	45.0	126	10.5
	56.0	128	10.7
46 (S.V. = 1.2) <sup>2</sup>	40.0	131	10.2
	45.0	134	10.8
	56.0	134	11.4
	24.0	125	9.1
Comm. <sup>2</sup>	32.0	120	8.3
	40.0	108	8.8
46 (S.V. = 1.45)	Sludge #4		
	1.4	14	**
	2.7	33	37.1
	4.1	65	41.4
Comm.	5.4	80	42.0
	6.8	90	41.3
	1.4	22	**
	2.7	58	39.5
46 (S.V. = 2.0) <sup>3</sup>	4.1	45	32.9
	5.4	37	30.2
46 (S.V. = 2.0) <sup>3</sup>	Sludge #5		
	8.23	160	14.8
	12.35	205	15.3
	16.46	220	15.8
Comm.	20.58	230	16.3
	24.69	230	16.9



TABLE 10-continued

46 (S.V. = 2.4) <sup>3</sup>	8.23	130	14.2	
	12.35	210	15.3	
	16.46	220	16.0	
	20.58	235	16.5	
	24.69	236	16.7	
	Comm <sup>3</sup>	8.23	160	14.1
		10.29	200	14.7
		12.35	208	15.0
		16.46	226	15.1
20.58		214	14.7	
<u>Sludge #6</u>				
53 (S.V. = 2.4)	6.3	134	22.5	
	8.4	158	24.4	
	10.5	152	23.4	
	12.6	160	24.5	
Comm.***	4.2	146	21.2	
	5.3	143	21.2	
	6.3	145	21.5	
	8.4	138	21.1	

Shear		Dosage	Fitrage	Cake
<u>Sludge #7</u>				
46 (S.V. = 2.5)	300 rpm/5 min	10	70	13.1
	300 rpm/10 min	10	85	13.3
	300 rpm/5 min	11.7	98	14.0
	300 rpm/10 min	12.7	88	13.3
	300 rpm/10 min	13.3	95	14.0
Comm.	300 rpm/10 min	15.0	100	14.6
	300 rpm/8 min	6.7	82	12.8
	300 rpm/15 min	6.7	70	13.0
	300 rpm/5 min	8.3	70	12.3
	300 rpm/10 min	8.3	85	13.0
	300 rpm/15 min	8.3	82	13.9
	300 rpm/15 min	10.0	95	13.8
	300 rpm/15 min	11.7	92	12.6
	300 rpm/30 min	11.7	89	14.1

<sup>1</sup>40 sec at 300 rpm agitation  
<sup>2</sup>mixer set at 51 for 10 sec. and 21 for 20 sec  
\*\* not measurable  
<sup>3</sup>350 rpm, 20 sec. agitation  
\*\*\* 500 rpm/15 sec. agitation

The above mentioned patents and publications are incorporated herein by reference.

Many variations of the present invention will suggest themselves to those skilled in this art in light of the above detailed description. For example, instead of employing acrylamide as the (alk)acrylamide monomer; methacrylamide and ethacrylamide may be used. Polymerization may be initiated by any known method such as ionizing radiation in addition to ultraviolet or redox initiation. A wide variety of secondary amines are suitable for use in the Mannich reaction such as piperidine, diethanolamine, dibutylamine and amylmethylaniline; as are a wide variety of formaldehydes, including trioxane.

All such obvious modification are within the full intended scope of the appended claims.

Although the above discussion is directed primarily to the use of (meth)acrylamide-based polymers which before reaction are substantially linear, it is also possible to use lightly to moderately cross-linked (meth)acrylamide-based polymers which can be prepared by adding small amounts of cross-linking monomers, such as methylenebisacrylamide etc., to the aqueous acrylamide monomer solutions of either of the processes described above prior to polymerization.

We claim:

[1. A process for the preparation of a composition comprising (alk)acrylamide-containing polymeric microparticles, said (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter, which aminomethyl groups continually self cross-link the polymer at ambient conditions which comprises:

tuted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter, which aminomethyl groups continually self cross-link the polymer at ambient conditions which comprises:

- (a) admixing
  - (i) an aqueous solution of at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer;
  - (ii) an oil solution comprising at least one hydrocarbon liquid; and
  - (ii) an effective amount of surfactant or surfactant mixture so as to form an inverse microemulsion;
- (b) subjecting the inverse microemulsion obtained in step (a) to polymerization conditions; and
- (c) reacting the polymerized polymer obtained in step (b) with an effective amount of a formaldehyde and a secondary amine or a complex thereof; and
- (d) optionally, quaternizing the resultant polymer.]

[2. A process as defined in claim 1 wherein said aqueous solution of step (a) (i) contains acrylamide.]

[3. A process as defined in claim 1 wherein said polymerization conditions of step (b) comprise introducing a polymerization initiator to said inverse microemulsion.]

[4. A process as defined in claim 1 wherein said formaldehyde is selected from formaldehyde, araformaldehyde, trioxane or aqueous formalin.]

[5. A process as defined in claim 1 wherein said secondary amine is selected from dimethylamine, methylethylamine, diethylamine, amylmethylaniline, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylaniline, diethanolamine or mixtures thereof.]

[6. A process as defined in claim 1 wherein said formaldehyde comprises formalin, and said secondary amine comprises dimethylamine.]

[7. A process for the preparation of a composition comprising (alk)acrylamide-containing polymeric microparticles, said (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter, which aminomethyl groups continually self cross-link the polymer at ambient conditions which comprises:

- (a) reacting
  - (i) at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer; and
  - (ii) formaldehyde and a secondary amine or a complex thereof in aqueous solution to produce a tertiary aminomethyl substituted (alk)acrylamide monomer;
- (b) admixing
  - (i) said aqueous solution of substituted (alk)acrylamide monomer and, optional comonomer obtained in (a);
  - (ii) an oil solution comprising at least one hydrocarbon liquid; and
  - (iii) an effective mount of surfactant or surfactant mixture, so as to form an inverse microemulsion;
- (c) subjecting the inverse microemulsion obtained in step (b) to polymerization conditions; and
- (d) optionally, quaternizing the resultant polymer.]

[8. A process as defined in claim 7 wherein the aqueous solution of step (b)(i) contains substituted acrylamide.]

[9. A process as defined in claim 7 wherein said polymerization conditions of step (c) comprise introducing a polymerization initiator to the inverse microemulsion.]

[10. A process as defined in claim 7 wherein said monomer is reacted with a formaldehyde and a secondary amine.]



## 21

[11. A process as defined in claim 7 wherein said formaldehyde is selected from formaldehyde, paraformaldehyde, trioxane or aqueous formalin.]

[12. A process as defined in claim 7 wherein said secondary amine is selected from dimethylamine, methylethylamine, diethylamine, amylmethylethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylethylamine, diethanolamine or mixtures thereof.]

[13. A process as defined in claim 18 wherein said formaldehyde comprises formalin and said secondary amine comprises dimethylamine.]

[14. A process for the preparation of a composition comprising (alk)acrylamide containing polymeric microparticles, said (alk)acrylamide polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups and having an average particle size of from about 200 to about 4000 Å in diameter, which aminomethyl groups continually self cross-link the polymer at ambient conditions which comprises:

(a) admixing

(i) an aqueous solution comprising at (alk)acrylamide monomer and optionally, at least one ethylenically unsaturated comonomer, a formaldehyde and secondary amine or a complex thereof;

(ii) an oil solution comprising at least one hydrocarbon liquid; and

(iii) an effective amount of surfactant or surfactant mixture, so as to form an inverse microemulsion;

(b) subjecting the inverse microemulsion obtained in step (a) to polymerization conditions and allowing the formaldehyde and secondary amine to react with the (alk)acrylamide amide groups; and

(c) optionally, quaternizing the resultant polymer.]

[15. A process as defined in claim 14 wherein said aqueous solution of step (a)(i) comprises acrylamide.]

[16. A process as defined in claim 14 wherein said polymerization conditions of step (b) comprise introducing a polymerization initiator to the inverse microemulsion.]

[17. A process as defined in claim 14 wherein the aqueous solution of (a)(i) comprises acrylamide, a formaldehyde and a secondary amine.]

[18. A process as defined in claim 14 wherein said formaldehyde is selected from formaldehyde, paraformaldehyde, trioxane or aqueous formalin.]

[19. A process as defined in claim 14 wherein said secondary amine is selected from dimethylamine, diethylamine, methylethylamine, amylmethylethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylethylamine, diethanolamine or mixtures thereof.]

[20. A process as defined in claim 14 wherein said formaldehyde comprises formalin and said secondary amine comprises dimethylamine.]

21. In a process for the preparation of a composition comprising polymer micelles which contain water and (alk)acrylamide-based polymer, said (alk)acrylamide-based polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups which continually self cross-link the polymer at ambient conditions, which process comprises:

a. admixing

i. an aqueous solution of at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer;

ii. an oil solution comprising at least one hydrocarbon liquid; and

iii. an effective amount of surfactant or surfactant mixture so as to form an emulsion;

## 22

b. subjecting the emulsion obtained in step (a) to polymerization conditions; and;

c. reacting the polymerized polymer obtained in step (b) with an effective amount of a formaldehyde and a secondary amine or a complex thereof to substitute said polymer with at least about 1 mole percent of tertiary aminomethyl groups; and

d. optionally, quaternizing the resultant polymer; the improvement comprising including an effective amount of surfactant or surfactant mixture in step (a) iii to form an inverse microemulsion which is subjected to polymerization conditions in step (b); the resultant so produced composition comprising polymer micelles having an average particle size of from about 200 to about 4000 Å in diameter.

22. A process as defined in claim 21 wherein said aqueous solution of step (a)(i) contains acrylamide.

23. A process as defined in claim 21 wherein said polymerization conditions of step (b) comprise introducing a polymerization initiator to said inverse microemulsion.

24. A process as defined in claim 21 wherein said formaldehyde is selected from the group consisting of formaldehyde, paraformaldehyde, trioxane and aqueous formalin.

25. A process as defined in claim 21 wherein said secondary amine is selected from the group consisting of dimethylamine, methylethylamine, diethylamine, amylmethylethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylethylamine, diethanolamine and mixtures thereof.

26. A process as defined in claim 21 wherein said formaldehyde comprises formalin, and said secondary amine comprises dimethylamine.

27. A process as defined in claim 21 wherein said polymer micelles have an average diameter of from about 300 to about 2000 Å.

28. A process as defined in claim 21 wherein said polymer micelles have an average diameter of from about 350 to about 1000 Å.

29. In a process for the preparation of a composition comprising polymer micelles which contain water and (alk)acrylamide-based polymer, said (alk)acrylamide-based polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups which continually self cross-link the polymer at ambient conditions, which process comprises:

a. reacting

i. at least one (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer; and

ii. a formaldehyde and a secondary amine or a complex thereof in aqueous solution to produce a tertiary aminomethyl substituted (alk)acrylamide monomer;

b. admixing

i. an aqueous solution of substituted (alk)acrylamide monomer and optional comonomer obtained in (a);

ii. an oil solution comprising at least one hydrocarbon liquid; and

iii. an effective amount of surfactant or surfactant mixture to form an emulsion;

c. subjecting the emulsion obtained in step (b) to polymerization conditions, and

d. optionally, quaternizing the resultant polymer; the improvement comprising including an effective amount of surfactant or surfactant mixture in step (b) iii to form an inverse microemulsion which is then subjected to



## 23

polymerization conditions in step (c); the resultant so produced composition comprising polymer micelles having an average particle size of from about 200 to about 4000 Å in diameter.

30. A process as defined in claim 29 wherein the aqueous solution of step (a)(i) contains acrylamide.

31. A process as defined in claim 29 wherein said polymerization conditions of step (c) comprise introducing a polymerization initiator to the inverse microemulsion.

32. A process as defined in claim 29 wherein said monomer is reacted with a formaldehyde and a secondary amine.

33. A process as defined in claim 29 wherein said formaldehyde is selected from the group consisting of formaldehyde, paraformaldehyde, trioxane and aqueous formalin.

34. A process as defined in claim 29 wherein said secondary amine is selected from the group consisting of dimethylamine, methylethylamine, diethylamine, amylmethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylamine, diethanolamine and mixtures thereof.

35. A process as defined in claim 29 wherein said formaldehyde comprises formalin and said secondary amine comprises dimethylamine.

36. A process as defined in claim 29 wherein said polymer micelles have an average diameter of from about 300 to about 2000 Å.

37. A process as defined in claim 29 wherein said polymer micelles have an average diameter of from about 350 to about 1000 Å.

38. In a process for the preparation of a composition comprising polymer micelles which contain water and (alk)acrylamide-based polymer, said (alk)acrylamide-based polymer being substituted with at least about 1 mole percent of tertiary aminomethyl groups which continually self cross-link the polymer at ambient conditions, which process comprises:

a. admixing

i. an aqueous solution comprising an (alk)acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer, a formaldehyde and a secondary amine or a complex thereof;

ii. an oil solution comprising at least one hydrocarbon liquid; and

iii. an effective amount of surfactant or surfactant mixture to form an emulsion;

b. subjecting the emulsion obtained in step (a) to polymerization conditions and allowing the formaldehyde and secondary amine to react with (alk)acrylamide amide groups; and

c. optionally, quaternizing the resultant polymer; the improvement comprising including an effective amount of surfactant or surfactant mixture in step (a) iii to form an inverse microemulsion which is then subjected to polymerization conditions in step (b); the resulting composition produced comprising polymer micelles

## 24

having an average particle size of from about 200 to about 4000 Å.

39. A process as defined in claim 38 wherein said aqueous solution of step (a) (i) comprises acrylamide.

40. A process as defined in claim 38 wherein said polymerization conditions of step (b) comprise introducing a polymerization initiator to the inverse microemulsion.

41. A process as defined in claim 38 wherein the aqueous solution of (a) (i) comprises acrylamide, a formaldehyde and a secondary amine.

42. A process as defined in claim 38 wherein said formaldehyde is selected from the group consisting of formaldehyde, paraformaldehyde, trioxane and aqueous formalin.

43. A process as defined in claim 38 wherein said secondary amine is selected from the group consisting of dimethylamine, diethylamine, methylethylamine, amylmethylamine, dibutylamine, dibenzylamine, piperidine, morpholine, ethanolmethylamine, diethanolamine and mixtures thereof.

44. A process as defined in claim 38 wherein said formaldehyde comprises formalin and said secondary amine comprises dimethylamine.

45. A process as defined in claim 38 wherein said polymer micelles have an average diameter of from about 300 to about 2000 Å.

46. A process as defined in claim 38 wherein said polymer micelles have an average diameter of from about 350 to about 1000 Å.

47. A process for the preparation of an inverse microemulsion containing dispersed polymer micelles containing water and an acrylamide-based polymer substituted with at least about 1 mole percent of quaternized tertiary aminomethyl groups which are capable of continually self cross-linking the polymer at ambient conditions, said microemulsion containing greater than 10 percent, by weight, of polymer solids based on said microemulsion and said polymer micelles having average diameters from about 300 to about 2000 Å, which process comprises:

a. admixing

i. an aqueous solution of at least one acrylamide monomer and, optionally, at least one ethylenically unsaturated comonomer;

ii. an oil solution comprising at least one hydrocarbon liquid; and

iii. an effective amount of surfactant or surfactant mixture to form an inverse microemulsion;

b. subjecting the inverse microemulsion obtained in step (a) to polymerization conditions,

c. reacting the polymerized polymer obtained in step (b) with an effective amount of a formaldehyde and a secondary amine or a complex thereof to substitute said polymer with at least about 1 mole percent of tertiary aminomethyl groups; and

a. quaternizing the resultant polymer.

\* \* \* \* \*