



US00RE38021E

(19) **United States**
(12) **Reissued Patent**
Endoh et al.

(10) **Patent Number:** **US RE38,021 E**
(45) **Date of Reissued Patent:** **Mar. 11, 2003**

(54) **ANISOTROPIC MAGNETIC POWDER AND
MAGNET THEREOF AND METHOD OF
PRODUCING SAME**

(75) Inventors: **Minoru Endoh, Kumagaya (JP);
Masaaki Tokunaga, Fukaya (JP)**

(73) Assignee: **Hitachi Metals, Ltd., Tokyo (JP)**

(*) Notice: This patent is subject to a terminal disclaimer.

(21) Appl. No.: **09/985,263**

(22) Filed: **Nov. 2, 2001**

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **5,096,509**
Issued: **Mar. 17, 1992**
Appl. No.: **07/283,910**
Filed: **Dec. 13, 1988**

U.S. Applications:

(62) Division of application No. 07/112,875, filed on Oct. 27, 1987, now Pat. No. 4,983,232.

(30) Foreign Application Priority Data

Jan. 6, 1987 (JP) 62-857
Sep. 10, 1987 (JP) P62-227388

(51) **Int. Cl.**⁷ **H01F 1/057**
(52) **U.S. Cl.** **148/101; 148/104; 148/105;**
75/331; 75/349; 75/352; 75/356; 75/357
(58) **Field of Search** **148/101, 104,**
148/105; 75/331, 349, 352, 356, 357

(56) References Cited

U.S. PATENT DOCUMENTS

4,374,665 A * 2/1983 Koon 148/302
4,402,770 A * 9/1983 Koon 148/302
4,558,077 A 12/1985 Gray et al.
4,601,875 A 7/1986 Yamamoto et al.
4,827,235 A * 5/1989 Inomata et al. 158/302
4,842,656 A * 6/1989 Maines et al. 148/302
4,921,553 A * 5/1990 Tokunga et al. 148/302

FOREIGN PATENT DOCUMENTS

EP 0101552 2/1984

EP	0106948	5/1984	
EP	0125752	11/1984	
EP	0133758	3/1985	
EP	0174735	* 3/1986	
EP	0216254	* 4/1987	
EP	0239031	* 9/1987 148/105
EP	0248981	* 12/1987	
JP	59-46008	3/1984	
JP	59-64733	4/1984	
JP	59-211549	11/1984	
JP	60/100402	6/1985	
JP	60-221549	11/1985	
JP	60-238447	12/1985	
JP	60-243247	* 12/1985	

OTHER PUBLICATIONS

Abstract of Japan Laid-Open No. 61-263,201, Nov. 21, 1986.*
Tokunaga et al., IEEE Tran. on Mag., vol. MAG 23, No. 5, Sep. 1987, pp. 2287-2292.*
1987 Digest of the Intermag conference, Tokyo, Japan, Apr. 14 to 17 p. VII, BCO3 and BCO4.*
Endoh et al., Magnetic Properties and Thermal Stability of Ga Containing Nd-Fe-Co-B Magnets, Japan Met. Assoc., Apr. 1987.*
Hadjipanayis et al., "Cobalt Free Permanent Materials Based On Iron Rare Earth Alloys", J. Appl. Phys., 55(6), Mar. 15, 1984, pp 2073-2077.*

* cited by examiner

Primary Examiner—John P. Sheehan
(74) *Attorney, Agent, or Firm*—Finnegan, Henderson, Farabow, Garrett & Dunner, LLP

(57) ABSTRACT

A the magnetically anisotropic magnetic powder having an average particle size of 1—1000 μm and made from a magnetically anisotropic R-TM-B-Ga or R-TM-B-Ga-M alloy having an average crystal grain size of 0.01—0.5 μm , wherein R represents one or more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B boron, Ga gallium, and M one or more elements selected from the group consisting of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn. This is useful for anisotropic resin-bonded magnet with high magnetic properties.

3 Claims, 1 Drawing Sheet




FIG. 1





FIG. 2



**ANISOTROPIC MAGNETIC POWDER AND
MAGNET THEREOF AND METHOD OF
PRODUCING SAME**

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

This is a division of application Ser. No. 07/112,875, filed Oct. 27, 1987, now U.S. Pat. No. 4,983,232.

BACKGROUND OF THE INVENTION

The present invention relates to a magnetically anisotropic magnetic powder composed of a rare earth element-iron-boron-gallium alloy powder, and a permanent magnet composed of such alloy powder dispersed in a resin, and more particularly to a resin-bonded permanent magnet having good thermal stability composed of a magnetically anisotropic rare earth element-iron-boron-gallium permanent magnet powder having fine crystal grains dispersed in a resin.

Typically conventional rare earth element permanent magnets are SmCo permanent magnets, and Sm₂Co₁₇ permanent magnets. These samarium-cobalt magnets are prepared from ingots produced by melting samarium and cobalt in vacuum or in an inert gas atmosphere. These ingots are pulverized and the resulting powders are pressed in a magnetic field to form green bodies which are in turn sintered and heat-treated to provide permanent magnets.

The samarium-cobalt magnets are given magnetic anisotropy by pressing in a magnetic field as mentioned above. The magnetic anisotropy greatly increases the magnetic properties of the magnets. On the other hand, magnetically anisotropic, resin-bonded samarium-cobalt permanent magnets are obtained by injection-molding a mixture of samarium-cobalt magnet powder produced from the sintered magnet provided with anisotropy and a resin in a magnetic field, or by compression-molding the above mixture in a die.

Thus, resin-bonded samarium-cobalt magnets can be obtained by preparing the sintered magnets having anisotropy, pulverizing them and then mixing them with resins as binders.

Recently, neodymium-iron-boron magnets have been proposed as new rare earth magnets surmounting the samarium cobalt magnets containing samarium which is not only expensive but also unstable in its supply. Japanese Patent Laid-Open Nos. 59-46008 and 59-64733 disclose permanent magnets obtained by forming ingots of neodymium-iron-boron alloys, pulverizing them to fine powders, pressing them in a magnetic field to provide green bodies which are sintered and then heat-treated, like the samarium-cobalt magnets. This production method is called a powder metallurgy method. Also, it was reported to obtain a resin-bonded magnet having magnetic anisotropy by pulverizing an ingot to 0.5–2 μm and then solidifying it with a wax (Appl. Phys. Lett. 48 (10), Mar. 1986, pp.670–672).

With respect to the Nd-Fe-B permanent magnet, GENERAL MOTORS has proposed an alternative method to the above-mentioned powder metallurgy method.

This method comprises melting a mixture of neodymium, iron and boron, rapidly quenching the melt by such a technique as melt spinning to provide fine flakes of the amorphous alloy, the heat-treating the flaky amorphous alloy to generate an Nd₂Fe₁₄B intermetallic compound. The fine flakes of this rapidly-quenched alloy is solidified with a resin binder (Japanese Patent Laid-Open No. 59-211549).

However, the magnetic alloy thus prepared is magnetically isotropic. Then Japanese Patent Laid-Open No. 60-100402 discloses a technique of hot-pressing this isotropic magnetic alloy, and then applying high temperatures and high pressure thereto so that plastic flow takes place partially in the alloy thereby imparting magnetic anisotropy thereto.

The conventional Nd-Fe-B permanent magnets, however, have the following problems.

First, although the above powder metallurgy can provide magnetic anisotropy and magnetic properties of (BH)_{max}=35–45MGOe, the resulting magnets essentially have low Curie temperature, large crystal grain size and poor thermal stability. Accordingly, they cannot be suitably used for motors, etc. which are likely to be used in a high-temperature environment.

Second, although molding is relatively easy by compression molding if rapidly-quenched powder is mixed with a resin, the resulting alloy is isotropic, so that its magnetic properties are inevitably low. For instance, the magnetic properties are (BH)_{max} of 3–5MGOe for those obtained by injection molding and (BH)_{max} of 8–10MGOe for those obtained by compression molding, and further the magnetic properties vary widely depending upon the strength of a magnetic field for magnetizing the alloy. To achieve (BH)_{max} of 8MGOe, the magnetic field should be 50 kOe or so, and it is difficult to magnetize the alloy after assembling for various applications.

In addition, although hot pressing of the rapidly-quenched alloy powder-serves to increase the density of the alloy, eliminating pores from the pressed alloy powder to improve weathering properties thereof, the resulting alloy is [isotropic]isotropic so that it is disadvantageous just like the permanent magnet prepared by mixing rapidly-quenched alloy powder with a resin. (BH)_{max} of the resulting alloy is improved in proportion to the increase in the density, and it can reach 12 MGOe or so. However, it is still impossible to magnetize it after assembling.

By the method of hot-pressing rapidly-quenched alloy powder and then causing plastic flow therein, anisotropy can be achieved like the powder metallurgy method, providing (BH)_{max} of 34–40 MGOe, but annular magnets, for instance, magnet rings of 30 mm in outer diameter, 25 mm in inner diameter and 20 mm in thickness cannot easily be formed because die upsetting should be utilized to provide anisotropy.

Finally, with respect to magnets prepared by pulverizing ingots and solidifying them with wax, powders used are so fine that they are likely to be burned, making it impossible to handle them in the atmosphere. Also since the magnets show a low squareness ratio in the magnetization curve, they cannot have high magnetic properties.

Incidentally, we tried to provide anisotropic resin-bonded magnets by pulverizing anisotropic sintered magnets prepared by the powder metallurgy method, mixing the pulverized particles with resins and molding them while applying a DC magnetic field, but high magnetic properties could not be achieved.

OBJECT AND SUMMARY OF THE INVENTION

Therefore, an object of the present invention is to solve the problems peculiar to the above conventional techniques, thereby providing an anisotropic resin-bonded magnet having good thermal stability and easily magnetizable after assembling, and magnetic powder usable therefor and a method of producing them.

To achieve the above object, the present invention comprises the following technical means.

That is, the object of the present invention has been achieved first by forming magnetically anisotropic magnetic powder having an average crystal grain size of 0.01–0.5 μm from an R-Fe-B-Ga alloy, wherein R represents one or more rare earth elements including Y, Fe may be partially substituted by Co to include an R-Fe-Co-B-Ga alloy, and one or more additional elements (M) selected from Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn may be contained to include an R-Fe-B-Ga-M alloy and an R-Fe-Co-B-Ga-M alloy, second by forming a pressed powder magnet therefrom, and third by forming a resin-bonded magnet from powder of the above alloy having an average particle size of 1–1000 μm .

The present invention is based on our finding that a thermally stable, anisotropic resin-bonded magnet can be obtained from magnetic powder of an average particle size of 1–1000 μm prepared by pulverizing a magnetically anisotropic R-Fe-B-Ga alloy having an average crystal grain size of 0.01–0.5 μm . It has been found that gallium (Ga) is highly effective to improve the thermal stability of the magnet.

Thus, the magnetically anisotropic magnetic powder according to the present invention has an average particle size of 1–1000 μm and is made from a magnetically anisotropic R-TM-B-Ga alloy having an average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B boron and Ga gallium.

The method of producing a magnetically anisotropic magnetic powder according to the present invention comprises the steps of rapidly quenching a melt of an R-TM-B-Ga alloy, wherein R represents one or more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B boron and Ga gallium, to form flakes made of an amorphous or partially crystallized R-TM-B-Ga alloy, pressing these flakes to provide a pressed powder body with a higher density, subjecting it to plastic deformation while heating to form a magnetically anisotropic R-TM-B-Ga alloy having an average crystal grain size of 0.01–0.5 μm , heat-treating it to increase a coercive force thereof, and then pulverizing it.

The method of producing a magnetically anisotropic magnetic powder according to the present invention comprises the steps of rapidly quenching a melt of an R-TM-B-Ga alloy, wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron and Ga gallium, to form flakes of an amorphous or partially crystallized R-TM-B-Ga alloy, pressing the flakes to provide a pressed powder body with a higher density, subjecting it to plastic deformation while heating to provide a magnetically anisotropic R-TM-B-Ga alloy having an average crystal grain size of 0.01–0.5 μm , and then pulverizing it without heat treatment.

The magnetically anisotropic pressed powder magnet according to the present invention is made of magnetically anisotropic R-TM-B-Ga alloy having an average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron and Ga gallium, the magnetically anisotropic R-TM-B-Ga alloy having an axis of easy magnetization aligned in the same direction.

The magnetically anisotropic resin-bonded magnet according to the present invention is composed of 15–40 volume % of a resin binder and balance R-TM-B-Ga alloy powder having an average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron and Ga gallium, the magnetically anisotropic

R-TM-B-Ga alloy having an axis of easy magnetization aligned in the same direction.

The magnetically anisotropic magnetic powder according to the present invention an average particle size of 1–1000 μm and is composed of an R-TM-B-Ga-M alloy powder having average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron, Ga gallium and M one or more elements selected from the group consisting of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn.

The method of producing a magnetically anisotropic magnetic powder according to the present invention comprises the steps of rapidly quenching a melt of an R-TM-B-Ga-M alloy, wherein R represents one or more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B boron, Ga gallium, and M one or more elements selected from the group consisting of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn, to form flakes made of an amorphous or partially crystallized R-TM-B-Ga-M alloy, pressing these flakes to provide a pressed powder body with a higher density, subjecting it to plastic deformation while heating to form a magnetically anisotropic R-TM-B-Ga-M alloy having an average crystal grain size of 0.01–0.5 μm , heat-treating it to increase a coercive force thereof, and then pulverizing it.

The method of producing a magnetically anisotropic magnetic powder according to the present invention comprises the steps of rapidly quenching a melt of an R-TM-B-Ga-M alloy, wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron, Ga gallium, and M one or more elements selected from the group consisting of Nb, W, V, Ta, Si, Al, Zr, Hf, P, C and Zn to form flakes of an amorphous or partially crystallized R-TM-B-Ga-M alloy, pressing the flakes to provide a pressed powder body with a higher density, subjecting it to plastic deformation while heating to provide a magnetically anisotropic R-TM-B-Ga-M alloy having an average crystal grain size of 0.01–0.5 μm , and then pulverizing it without heat treatment.

The magnetically anisotropic pressed powder magnet according to the present invention is made of magnetically anisotropic R-TM-B-Ga-M alloy having an average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B, boron, Ga gallium, and M one or more elements selected from the group consisting of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn, the magnetically anisotropic R-TM-B-Ga-M alloy having an axis of easy magnetization aligned the same direction.

The magnetically anisotropic resin-bonded magnet according to the present invention composed of 15–40 volume % of a resin binder and balance R-TM-B-Ga-M alloy powder having an average crystal grain size of 0.01–0.5 μm , wherein R represents one or more rare earth elements including Y, TM Fe which may be partially substituted by Co, B boron, Ga gallium, and M one or more elements selected from the group consisting of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn, the magnetically anisotropic R-TM-B-Ga-M alloy having an axis of easy magnetization aligned in the same direction.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a graph showing the variation of irreversible loss of flux with heating temperature of the magnets (a), (b) and (c), wherein (a) denotes the magnet prepared by rapid quenching, heat treatment and resin impregnation, (b) the

magnet prepared by rapid quenching, heat treatment and hot pressing, and (c) the magnet prepared by rapid quenching, HIP and die upsetting; and

FIG. 2 is a graph showing the comparison in thermal stability of the anisotropic resin-bonded magnet (a) of Example 8, the anisotropic sintered magnet of $\text{Sm}_2\text{Co}_{17}$ (b) and the anisotropic sintered magnet having the composition of $\text{Nd}_{13}\text{DyFe}_{76.8}\text{Co}_{2.2}\text{B}_6\text{Ga}_{0.9}\text{Ta}_{0.1}$ (c).

DETAILED DESCRIPTION OF THE INVENTION

The above alloy has preferably a composition of 11–18 atomic % of R, 5 atomic % or less of Ga, 4–11 atomic % of B, 30 atomic % or less of Co and balance Fe and inevitable impurities, and further preferably a composition of 11–18 atomic % of R, 0.01–3 atomic % of Ga, 4–11 atomic % of B, 30 atomic % or less of Co and balance Fe and inevitable impurities. This alloy may contain one or more additional elements M selected from Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn. The amount of the additional element M is 3 atomic % or less and more preferably 0.001–3 atomic %. The addition of the additional element M and Ga in combination is effective to further improve the coercive force of the alloy. Of course, the addition of Ga only is effective in some cases.

The R-Fe-B alloy is an alloy containing $\text{R}_2\text{Fe}_{14}\text{B}$ or $\text{R}_2(\text{Fe},\text{Co})_{14}\text{B}$ as a main phase. The composition range desirable for a permanent magnet is as follows:

When R (one or more rare earth elements including Y) is less than 11 atomic %, sufficient iHc cannot be obtained, and when it exceeds 18 atomic %, the Br decreases. Thus, the amount of R is 11–18 atomic %.

When B is less than 4 atomic %, the $[\text{R Fe B}]\text{R}_2\text{Fe}_{14}\text{B}$ phase, a main phase of the magnet is not fully formed, resulting in low Br and iHc. On the other hand, when it exceeds 11 atomic %, a phase undesirable for magnetic properties appears, resulting in low Br. Thus, the amount of B is 4–11 atomic %.

When Co exceeds 30 atomic %, the Curie temperature increases but the anisotropy constant of the main phase decreases, making it impossible to obtain high iHc. Thus, the amount of Co is 30 atomic % or less.

When Ga exceeds 5 atomic %, the saturation magnetization $4\pi\text{I}_s$ and the Curie temperature T_c decrease extremely. Ga is preferably 0.01–3 atomic %, and more preferably 0.05–2 atomic %.

The addition of one or more additional elements of Nb, W, V, Ta, Mo, Si, Al, Zr, Hf, P, C and Zn is effective to further increase the coercive force of the alloy, but when it exceeds 3 atomic %, undesirable decrease in $4\pi\text{I}_s$ and T_c takes place. Preferably, the additional element is 0.001–3 atomic %.

Incidentally, the alloy of the present invention may contain Al contained as an impurity in ferroboration, and further reducing materials and impurities mixed in the reduction of the rare earth element.

In the present invention, when the average crystal grain size of the R-Fe-B-Ga alloy exceeds $0.5\ \mu\text{m}$, its iHc decreases, resulting in an irreversible loss of flux of 10% or more at 160°C . which in turn leads to an extreme decrease in thermal stability. On the other hand, when the average crystal grain size is less than $0.01\ \mu\text{m}$, the formed resin-bonded magnet has a low iHc so that the desired permanent magnet cannot be obtained. Therefore, the average crystal grain size is limited to $0.01\text{--}0.5\ \mu\text{m}$.

An average ratio of an average size (c) of the crystal grains in perpendicular to their C axes to an average size (a) thereof in parallel to their C axes is preferably 2 or more.

To provide an anisotropic resin-bonded magnet with high magnetic properties, the R-Fe-B-Ga alloy to be pulverized is required to have a residual magnetic flux density of 8 kG or more in a particular direction, namely in the direction of anisotropy.

The R-TM-B-Ga or R-TM-B-Ga-M alloy is given anisotropy by pressing or compacting flakes obtained by a rapid quenching method by hot isostatic pressing (HIP) or hot pressing, and then subjecting the resulting pressed body to plastic deformation. One method for giving plastic deformation is die upsetting at high temperatures.

The magnetically anisotropic R-TM-B-Ga or R-TM-B-Ga-M alloy means herein an R-TM-B-Ga or R-TM-B-Ga-M alloy showing anisotropic magnetic properties in which the shape of a $4\pi\text{I-H}$ curve thereof in the second quadrant varies depending upon the direction of magnetization. A pressed powder body produced by the hot isostatic pressing of flakes has usually a residual magnetic flux density of 7.5 kG or less, while by using a R-TM-B-Ga or R-TM-B-Ga-M alloy having a residual magnetic flux density of 8 kG or more, the resulting resin-bonded magnets have higher magnetic properties such as residual magnetic flux density and energy product than isotropic resin-bonded magnets.

The method of producing anisotropic magnetic particles and anisotropic powder or resin-bonded magnets will be explained below.

In the present invention, the alloy flakes are pulverized to $100\text{--}200\ \mu\text{m}$ or so. The coarse powder produced by pulverization is molded at room temperature to obtain a green body. The green body is subjected to hot isostatic pressing or hot pressing at $600^\circ\text{--}750^\circ\text{C}$. to form a compacted block having a relatively small crystal grain size. The block is again subjected to plastic working such as die upsetting at $600^\circ\text{--}800^\circ\text{C}$. to provide an anisotropic flat plate. This is called herein an anisotropic pressed powder magnet. Depending upon applications, this may be used without further treatment or working. It may be heat-treated but the heat treatment can be omitted by adding Ga, because the addition of Ga increases iHc sufficiently enough in some cases.

The more working, the higher anisotropy the resulting alloy has. If necessary, the flat plate may be heat-treated at $600^\circ\text{--}800^\circ\text{C}$. to improve iHc thereof. Pulverization of this flat plate can provide coarse powder for anisotropic resin-bonded magnets.

By plastic working, the anisotropic R-Fe-B-Ga alloy has crystal grains flattened in the C direction. The crystal grains desirably have the ratio of the average size (c) thereof in perpendicular to their C axes to the average size (a) thereof in parallel to the C axes of 2 or more, so that the magnet has a residual magnetic flux density of 8 kG or more. Incidentally, the average crystal grain size is defined herein as a value obtained by averaging the diameters of 30 or more crystal grains, which are converted to spheres having the same volume.

When the plastic working is die upsetting while heating, particularly high magnetic properties can be obtained.

By heat-treating the R-Fe-B magnet which is given anisotropy by the plastic working, it can have an increased coercive force.

The heat treatment temperature is desirably $600\text{--}900^\circ\text{C}$., because when it is less than 600°C ., the coercive force

cannot be increased, and when it is higher than 900° C., the coercive force rather decreases than before the heat treatment.

The heat treatment is conducted for a period of time needed for keeping a sample at a uniform temperature. Taking productivity into consideration, it is 240 minutes or less.

The cooling rate should be 1° C./sec or more. When the cooling rate is less than 1° C./sec, the coercive force decreases before the heat treatment. Incidentally, the term "cooling rate" used herein means an average cooling rate from the heat treatment temperature (° C.) to (heat treatment temperature+room temperature)/2 (° C.). However, the addition of Ga makes the heat treatment unnecessary in some cases, in which the heat treatment is not only unnecessary but also large magnets used for voice coil motors, etc. suffer from substantially no cracking nor oxidation.

In the present invention, an average particle size of the pulverized powder is 1–1000 μm for the following reasons: When it is less than 1 μm , the powder is easily burned, making it difficult to handle it in the air, and when it exceeds 1000 μm , a thin resin-bonded magnet of 1–2 mm in thickness cannot be produced, and also it is not suitable for injection molding.

The pulverization may be carried out by a usual method by a disc mill, a brown mill, an attritor, a ball mill, a vibration mill, a jet mill, etc.

The coarse powder can be blended with a thermosetting resin binder and compression-molded in a magnetic field and then thermally cured to provide an anisotropic resin-bonded magnet of a compression molding type. Further, the coarse powder can be blended with a thermoplastic resin binder and injection-molded in a magnetic field to provide an anisotropic resin-bonded magnet of an injection molding type.

As materials usable as the above binders, thermosetting resins are easiest to use in the case of compression molding. Thermally stable polyamides, polyimides, polyesters, phenol resins, fluorine resins, silicone resins, epoxy resins, etc. may be used. And Al, Sn, Pb and various low-melting point solder alloys may also be used. In the case of injection molding, thermoplastic resins such as ethylene-vinyl, acetate resins, nylons, etc. may be used.

EXAMPLE 1

An $\text{Nd}_{15}\text{Fe}_{77}\text{B}_7\text{Ga}_1$ alloy was prepared by arc melting, and this alloy was formed into thin flakes by a single roll method in an argon atmosphere. The peripheral speed of the roll was 30 m/sec., and the resulting flakes were in irregular shapes of about 30 μm in thickness. And as a result of X-ray diffraction measurement, it was found that they were composed of a mixture of amorphous phases and crystal phases. These thin flakes were pulverized to 32 mesh or finer and then compressed by a die at 6 tons/cm² without applying a magnetic field. The resulting compressed product had a density of 5.8 g/cc. The compressed product body was hot-pressed at 750° C. and 2 tons/cm². The alloy after hot pressing had a density of 7.30 g/cc. Thus, a sufficiently high density was provided by hot pressing. The bulky product or pressed powder body having a higher density was further subjected to die upsetting at 750° C. The height of the sample was adjusted so that a compression ratio was 3.8 before and after the upsetting. That is, $h_0/h=3.8$, wherein h_0 was a height before the upsetting and h a height after the upsetting.

The upset sample was heated in an Ar atmosphere at 750° C. for 60 minutes, and then cooled by water at a cooling rate

of 7° C./sec. The magnetic properties before and after the heat treatment are shown in Table 1.

TABLE 1

	Br (kG)	bHc (kOe)	iHc (kOe)	(BH)max (MGOe)
Before Heat Treatment	11.7	11.0	20	32.2
After Heat Treatment	11.7	11.0	21.0	32.2

The heat-treated sample was pulverized to have a particle size range of 250–500 μm . The resulting magnetic powder was mixed with 16 vol % of an epoxy resin in a dry state, and the resulting powder was molded in a magnetic field of 10 kOe in perpendicular to the direction of compression. Next, by thermally curing it at 120° C. for 3 hours, an anisotropic resin-bonded magnet was obtained. The resulting anisotropic resin-bonded magnet had magnetic properties of Br=7.6 kG, bHc=6.8 kOe, iHc=19.0 kOe and (BH) max=13.5 MGOe when measured at a magnetization intensity of 25 kOe.

For comparison, rapidly quenched thin flakes having the composition of $\text{Nd}_{17}\text{Fe}_{73}\text{B}_8\text{Ga}_2$ was heat-treated at 600° C. for one hour in vacuum, pulverized to 250–500 μm and formed into a resin-bonded magnet in the same manner as above. Incidentally, since this resin-bonded magnet was isotropic, no magnetic field was applied in the compression molding step. The magnetic properties thereof measured at a magnetization intensity of 25 kOe was Br of 6.3 kOe, bHc of 5.2 kOe, iHc of 22.1 kOe and (BH) max of 6.3 MGOe (Comparative Example 1).

It is clear from the above that the [anisotropic]anisotropic resin-bonded magnet of the present invention has better magnetization and higher magnetic properties than the isotropic resin-bonded magnet.

For comparison, an ingot having the composition of $\text{Nd}_{15}\text{Fe}_{77}\text{B}_7\text{Ga}_1$ was pulverized in the same manner as in the above Example, mixed with a binder, molded in a magnetic field and heat-set. The magnetic properties thereof measured at a magnetization strength of 25 kOe were Br of 3.8 kOe and bHc of 0.3 kOe (Comparative Example 2).

Thus, anisotropic resin-bonded magnets prepared from ingots cannot be utilized as practical materials because high iHc cannot be achieved. The results of Example 1 and Comparative Example are summarized in Table 2 below.

TABLE 2

Sample	Average Crystal Grain Size (μm)	Br (KG)	bHc (KOe)	iHc (KOe)	(BH)max (MGOe)	Type
Example 1	0.09	7.6	6.5	19.0	13.5	Anisotropic Resin- Bonded Magnet
Comparative Example 1	0.06	6.3	5.2	22.1	6.8	Isotropic Resin- Bonded Magnet
Comparative Example 2	200	3.8	0.3	0.3	0.5	Anisotropic Resin- Bonded Magnet*

Note:

*Prepared from ingot

EXAMPLE 2

Next, the influence of a compression ratio in die upsetting on final anisotropic resin-bonded magnets will be shown.

With respect to composition and conditions of rapid quenching, hot pressing, molding in a magnetic field in perpendicular to the direction of compression, heat treatment and curing, this Example was the same as Example 1.

The results are shown in Table 3. The magnetic properties shown in Table 3 are values obtained at a magnetization intensity of 25 kOe. As is shown in Table 3, the increase of the compression ratio serves to increase the magnetic properties of the resulting anisotropic resin-bonded magnet.

Incidentally, when the ratio h_0/h was 5.6 or more, cracking appeared in the periphery of the samples after die upsetting, but no influence took place on the final anisotropic resin-bonded magnets of the compression molding type.

TABLE 3

Compression Ratio (ho/h)	Average Crystal Grain Size (μm)	Br (KG)	bHc (KOe)	iHc (KOe)	(BH)max (MGOe)
2.4	0.07	6.4	5.9	21.1	9.0
3.0	0.09	7.3	6.2	19.8	12.5
4.1	0.10	7.9	6.5	18.6	14.1
5.6	0.11	7.9	6.6	17.1	14.0
6.3	0.11	8.0	6.8	16.6	14.1
7.2	0.11	8.1	6.8	15.0	14.4

EXAMPLE 3

Magnetic powder was prepared from an $\text{Nd}_{14}\text{Fe}_{79}\text{B}_6\text{Ga}_1$ alloy in the same manner as in Example 1. The magnetic powder was blended with 33 volume % of EVA to form

pellets. The pellets were injection-molded at 150° C. A test piece produced by the injection molding was in a circular shape of 20 mm in diameter and 10 mm in thickness, and the magnetic field applied during the injection molding was 8 kOe. The magnetic properties of the test piece was Br of nearly 7.1 KG, bHc of nearly 5.8 kOe, iHc of nearly 18.5 kOe and (BH) max of nearly 10.5 MGOe when measured at a magnetization intensity of 25 kOe.

EXAMPLE 4

Anisotropic resin-bonded magnets having the compositions as shown in Table 4 were prepared in the same compression molding method as in Example 1. The magnetic properties measured are shown in Table 4.

Sample Nos. 1-5 show the influence of Nd, Sample Nos. 6-10 show the influence of B, and Sample Nos. 11-19 show the influence of Ga. And Sample Nos. 20-23, 24-27, 28-31, 32-35, 36-39, 40-43, 44-47, 48-51, 52-55, 56-59, 60-63 and 64-67 respectively show the effects of additional elements W, V, Ta, Mo, Si, Al, Zr, Hf, P, C, Zn and Nb.

It is clear from this table that Nd is preferably 11-18 atomic %, boron 4-11 atomic %, Ga 5 atomic % or less and each additional element 3 atomic % or less.

Incidentally, the same effects of Ga and the additional element M were appreciated in the so-called sintering method.

TABLE 4

Sample	Alloy Composition (at. %)					Br (kG)	bHc (kOe)	iHc (kOe)	(BH)max (MGOe)
	Nd	Fe	B	Ga	M				
1*	10	82.5	7	0.5	—	3.0	1.9	15.1	1.2
2	11	81.5	7	0.5	—	5.3	4.0	16.2	5.1
3	15	77.5	7	0.5	—	7.7	6.8	18.4	13.8
4	18	74.5	7	0.5	—	7.0	6.0	19.4	10.8
5*	19	73.5	7	0.5	—	6.8	5.4	19.8	10.3
6*	15	81.5	3	0.5	—	3.0	1.5	7.3	1.3
7	15	80.5	4	0.5	—	4.2	2.0	8.4	2.0
8	15	76.5	8	0.5	—	7.4	6.1	20.0	12.9
9	15	73.5	11	0.5	—	6.9	5.9	21.1	10.8
10*	15	72.5	12	0.5	—	6.7	5.5	21.5	10.5
11*	15	78	7	0	—	8.0	7.1	8.1	14.2
12	15	77.5	7	0.5	—	7.8	7.0	18.4	13.8
13	15	77	7	1.0	—	7.6	6.9	19.4	13.6
14	15	76.5	7	1.5	—	7.4	6.5	22.0	13.0
15	15	76.0	7	2.0	—	7.4	6.4	22.1	12.8
16	15	75.0	7	3.0	—	7.3	6.3	22.0	12.7
17	15	74.0	7	4.0	—	7.2	6.2	22.0	12.4
18	15	73.0	7	5.0	—	7.0	6.0	22.0	11.0
19*	15	72.8	7	5.2	—	6.0	5.7	21.7	8.7
20	15	77.5	7	0.5	0.001 W	7.7	7.0	18.7	13.7
21	15	76.5	7	0.5	1 W	7.5	6.5	20.5	12.5
22	15	74.5	7	0.5	3 W	7.0	6.1	19.6	11.8
23*	15	74.3	7	0.5	3.2 W	5.9	4.2	15.4	7.5
24	15	77.5	7	0.5	0.001 V	7.0	7.0	19.0	14.0
25	15	76.5	7	0.5	1 V	7.6	6.7	23.4	13.4
26	15	74.5	7	0.5	3 V	7.2	6.4	22.8	12.9
27*	15	74.3	7	0.5	3.2 V	6.2	4.8	13.3	8.0
28	15	77.5	7	0.5	0.001 Ta	7.7	6.8	18.7	13.8
29	15	76.5	7	0.5	1 Ta	7.4	6.4	20.1	12.2
30	15	74.5	7	0.5	3 Ta	7.2	6.0	19.8	11.9
31*	15	74.3	7	0.5	3.2 Ta	6.1	4.2	14.4	8.0
32	15	77.5	7	0.5	0.001 Mo	7.7	6.8	18.9	13.5
33	15	76.5	7	0.5	1 Mo	7.5	6.6	22.1	12.5

TABLE 4-continued

Sample	Alloy Composition (at. %)					Br (kG)	bHc (kOe)	iHc (kOe)	(BH)max (MGOe)
	Nd	Fe	B	Ga	M				
34	15	74.5	7	0.5	3 Mo	7.2	6.2	21.8	11.9
35*	15	74.3	7	0.5	3.2 No	6.3	4.2	15.1	8.3
36	15	77.5	7	0.5	0.001 Si	8.0	7.3	19.4	15.2
37	15	76.5	7	0.5	1 Si	7.8	7.1	22.3	14.4
38	15	74.5	7	0.5	3 Si	7.6	6.8	21.0	13.8
39*	15	74.3	7	0.5	3.2 Si	6.3	4.7	15.2	8.7
40	15	77.5	7	0.5	0.001 Al	7.9	7.0	18.7	14.7
41	15	76.5	7	0.5	1 Al	7.6	6.9	21.7	13.7
42	15	74.5	7	0.5	3 Al	7.4	6.6	20.6	12.9
43*	15	74.3	7	0.5	3.2 Al	6.2	4.5	15.0	8.3
44	15	77.5	7	0.5	0.001 Zr	8.2	7.4	19.6	15.5
45	15	76.5	7	0.5	1 Zr	7.9	7.2	22.0	14.3
46	15	74.5	7	0.5	3 Zr	6.8	6.7	20.8	13.2
47*	15	74.3	7	0.5	3.2 Zr	6.1	4.9	14.9	8.7
48	15	77.5	7	0.5	0.001 Hf	7.9	7.0	18.7	14.9
49	15	76.5	7	0.5	1 Hf	7.6	6.8	20.3	14.2
50	15	74.5	7	0.5	3 Hf	7.4	6.4	19.8	12.9
51*	15	74.3	7	0.5	3.2 Hf	6.3	4.7	14.7	8.7
52	15	77.5	7	0.5	0.001 P	7.6	7.0	18.6	13.6
53	15	76.5	7	0.5	1 P	7.4	6.4	20.4	12.4
54	15	74.5	7	0.5	3 P	6.9	5.9	19.7	11.7
55*	15	74.3	7	0.5	3.2 P	5.7	4.1	15.3	7.4
56	15	77.5	7	0.5	0.001 C	7.6	6.8	18.8	13.5
57	15	76.5	7	0.5	1 C	7.4	6.6	21.9	12.5
58	15	74.5	7	0.5	3 C	7.0	6.3	20.8	11.9
59*	15	74.3	7	0.5	3.2 C	6.2	4.2	15.0	8.2
60	15	77.5	7	0.5	0.001 Zn	8.2	7.5	19.8	15.8
61	15	76.5	7	0.5	1 Zn	8.0	7.2	22.8	14.8
62	15	74.5	7	0.5	3 Zn	7.8	6.9	21.4	14.0
63*	15	74.3	7	0.5	3.2 Zn	6.5	4.7	15.3	8.6
64	15	77.5	7	0.5	0.001 Nb	7.8	7.0	18.5	13.9
65	15	76.5	7	0.5	1 Nb	7.6	6.9	21.2	13.0
66	15	74.5	7	0.5	3 Nb	7.4	6.7	20.3	12.4
67*	15	74.3	7	0.5	3.2 Nb	6.1	4.8	14.8	8.5

Note

*Comparative Example

EXAMPLE 5

An alloy having the composition of $\text{Nd}_{14.3}\text{Fe}_{70.7}\text{Co}_{5.1}\text{B}_{6.9}\text{Ga}_{1.7}\text{W}_{1.3}$ was prepared by arc melting, and rapidly quenched by a single roll method. The resulting flaky sample was formed into bulky products by the following three methods:

- Heat-treating at 500° – 700° C., impregnating with an epoxy resin and die molding.
- Heat-treating at 500° – 700° C., and hot pressing.
- Hot isostatic pressing, and die upsetting to produce a flattened product.

The magnetic properties of the resulting samples are shown in Table 5.

TABLE 5

Production Method	Br (kG)	iHc (kOe)	(BH)max (MGOe)	Average Crystal Grain Size (μm)
(a)	6.0	22.6	7.1	0.04
(b)	8.0	20.2	12.6	0.08
(c)	12.4	19.6	36.0	0.12

After heating each sample at various temperatures for minutes, the variation of open flux was measured to investigate the thermal stability of each sample. Incidentally, the sample measured was worked to have a permeance coefficient $P_c = -2$. The results are shown in FIG. 1. It is shown that the upset flat product (c) had a small average crystal grain size and good (BH) max.

EXAMPLE 6

An alloy having the composition of $\text{Nd}_{14.1}\text{Fe}_{73.0}\text{Co}_{3.4}\text{B}_{6.9}\text{Ga}_{1.7}\text{W}_{0.9}$ was prepared by arc melting and then rapidly quenched by a single roll method. The resulting flaky sample was compressed by HIP and upset by a die to provide a flattened product. The resulting bulky sample was pulverized to $80\ \mu\text{m}$ or less, impregnated with an epoxy resin and then molded in a magnetic field. The resulting magnet had magnetic properties of $\text{Br}=7.1\ \text{kG}$, $\text{iHc}=22.0\ \text{kOe}$ and $(\text{BH})\ \text{max}=11.1\ \text{MGOe}$.

EXAMPLE 7

An $\text{Nd}_{15}\text{Fe}_{72.7}\text{Co}_{3.2}\text{B}_7\text{Ga}_3$ alloy was treated in the same manner as in Example 1 to produce magnetic powder. This magnetic powder was blended with an EVA binder to form pellets which were then injection-molded to produce a magnet of 12 mm in inner diameter, 16 mm in outer diameter and 25 mm in height. This magnet had anisotropy in a radial direction, and a sample of $1.5\ \text{mm}\times 1.5\ \text{mm}\times 1.5\ \text{mm}$ was cut out for evaluating its magnetic properties. They were $\text{Br}=6.5\ \text{kG}$, $\text{bHc}=5.8\ \text{kOe}$, $\text{iHc}=24.2\ \text{kOe}$ and $(\text{BH})\ \text{max}=8.5\ \text{MGOe}$.

EXAMPLE 8

An anisotropic resin-bonded magnet of a compression molding type having the composition of $\text{Nd}_{13}\text{DyFe}_{76.8}\text{Co}_{2.2}\text{B}_6\text{Ga}_{0.9}\text{Ta}_{0.1}$ was prepared in the same manner as in Example 1. The magnetic properties of the magnet were Br of nearly 6.6 kG, bHc of nearly 6.2 kOe, iHc

13

of nearly 21.0 kOe and (BH) max of nearly 10.2 MGOe. The magnet had a crystal grain size of 0.11 μm . The magnet was worked to 10 mm in diameter \times 7 mm thick and tested with respect to thermal stability. The results are shown in FIG. 2. For comparison, an anisotropic sintered $\text{Sm}_2\text{Co}_{17}$ magnet and an anisotropic R-Fe-B sintered magnet of the same composition were tested.

It is shown that the anisotropic resin-bonded magnet of the [preent]present invention had better thermal stability than the anisotropic sintered magnets tested as comparative materials.

EXAMPLE 9

Example 1 was repeated except for changing the particle size of magnetic powder to prepare an anisotropic resin-bonded magnet of $\text{Nd}_{14}\text{Fe}_{79}\text{B}_6\text{Ga}_1$. For comparison, an anisotropic sintered magnet of $\text{Nd}_{13}\text{Dy}_2\text{Fe}_{78}\text{B}_7$ was used to investigate the variation of coercive force with particle size. The results are shown in Table 6. It is shown that a sintered body has a coercive force decreased by pulverization, unable to use as a material for resin-bonded magnets, while the magnet of the present invention undergoes substantially no decrease in coercive force by pulverization.

TABLE 6

Powder Size	Coercive Force (kOe)	
	Pulverized Magnet of Present Invention	Pulverized Sintered Magnet
Before Pulverization	21.3	18.8
250–500 μm	21.3	5.7
177–250 μm	21.2	4.2
105–177 μm	21.1	3.6
49–105 μm	21.1	2.8
0–49 μm	21.0	2.1

EXAMPLE 10

Example 1 was repeated except for changing crystal grain size by changing the upsetting temperature to prepare an anisotropic resin-bonded magnet. The results [are shown in Table 7. It is shown]showed that with an average crystal grain size of 0.01 μm to 0.5 μm , good magnetic properties can be achieved.

[TABLE 7

Upsetting Temperature ($^{\circ}\text{C}$.)	Average Crystal Grain Size (μm)	Coercive Force (kOe)				(BH)max (MGOe)
		Br (KG)	bHc (KOe)	iHc (KOe)		
650	0.01	5.7	4.6	8.9	6.9	
750	0.09	7.6	6.5	19.0	13.5	
760	0.17	6.9	6.1	11.5	10.7	
780	0.38	6.5	6.1	10.4	10.1	
800	0.50	6.0	5.8	8.7	8.4	
820	0.80	4.3	3.6	5.2	3.8	

EXAMPLE 11

Example 1 was repeated except for changing the heat treatment time to prepare an upset sample of R-Fe-B-Ga. The results are shown in Table [8]7. It is shown that magnetic properties do not change as long as the heating time at 750 $^{\circ}\text{C}$. is within 240 minutes.

14

TABLE [8]7

Heating Time (min.)	iHc (kOe)	
	Before Heat Treatment	After Heat Treatment
5	21.1	22.2
10	21.3	22.9
30	22.2	22.8
60	21.8	22.3
120	21.7	22.5
240	20.8	21.7
300	22.0	22.8

EXAMPLE 12

Example 1 was repeated except for changing the heat treatment temperature with the heating time of 10 minutes to prepare an upset sample of Nd-Fe-B-Ga. The results are shown in Table [9]8. It is shown that with heat treatment temperature of 600 $^{\circ}$ –900 $^{\circ}\text{C}$., good magnetic properties can be obtained.

TABLE [9]8

Heat Treatment Temperature ($^{\circ}\text{C}$.)	iHc(kOe) after Heat Treatment	
	No Heat Treatment	
500	22.0	15.8
550	16.9	19.8
600	22.8	23.5
650	23.4	22.5
700	21.8	19.0
750	16.0	
800		
850		
900		
950		

EXAMPLE 13

Example 1 was repeated except for changing the cooling method with a constant heating time of 10 minutes to prepare an upset sample of Nd-Fe-B-Ga. The results are shown in Table [10]9. It is shown that with the cooling rate of 1 $^{\circ}\text{C}$./sec. or more, good results are obtained.

TABLE [10]9

Cooling Method	Cooling Rate ($^{\circ}\text{C}$./sec)	Coercive Force (kOe)
Water Cooling	370	23.1
Oil Cooling	180	23.3
Rapid Cooling with Ar	61	23.0
Slow Cooling with Ar	18	22.5
Spontaneous Cooling in Vacuum	4	20.2
Cooling in Furnace	0.3	20.4
Before Heat Treatment	—	21.1

As described above in detail, the magnetic powder for anisotropic resin-bonded magnets containing Ga according to the present invention has excellent magnetizability and small irreversible loss of flux even in a relatively high temperature environment, and are useful for anisotropic resin-bonded magnets which can be magnetized after assembling.

What is claimed is:

1. A method of producing a magnetically anisotropic magnetic powder comprising the steps of rapidly quenching a melt of an R-TM-B-Ga alloy, wherein R represents one or

15

more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B represents boron and Ga represents gallium, to form flakes of an amorphous or partially crystallized R-TM-B-Ga alloy, pressing the flakes to provide a pressed powder body having a higher density, subjecting it to plastic deformation while heating to provide a magnetically anisotropic R-TM-B-Ga alloy, and then pulverizing it.

2. The method of producing magnetically anisotropic magnetic powder according to claim 1, wherein said R-TM-B-Ga alloy consists essentially of 11–18 atomic % of a rare earth element, 4–11 atomic % of boron, 30 atomic % or less of Co, 5 atomic % or less of Ga and balance Fe and inevitable impurities.

16

3. A method of producing a magnetically anisotropic magnetic powder comprising the steps of rapidly quenching a melt of an R-TM-B-Ga-M alloy, wherein R represents one or more rare earth elements including Y, TM represents Fe which may be partially substituted by Co, B represents boron, Ga represents gallium, and M represents one or more elements selected from the group consisting of Nb, W, V, Ta, Si, Al, Zr, Hf, Mo, P, C and Zn to form flakes of an amorphous or partially crystallized R-TM-B-Ga-M alloy, pressing the flakes to have a higher density to provide a pressed powder body, subjecting it to plastic deformation while heating to provide a magnetically anisotropic R-TM-B-Ga-M alloy, and then pulverizing it.

* * * * *