



US00RE38412E

(19) **United States**
(12) **Reissued Patent**
Munter et al.

(10) **Patent Number:** **US RE38,412 E**
(45) **Date of Reissued Patent:** **Feb. 3, 2004**

(54) **COATED SUBSTRATE DRYING SYSTEM WITH MAGNETIC PARTICLE ORIENTATION**

4,508,752 A 4/1985 Takei et al.
4,567,057 A 1/1986 Masuyama et al.
4,874,633 A 10/1989 Komatsu et al.

(List continued on next page.)

(75) Inventors: **John D. Munter**, Oakdale, MN (US);
William B. Kolb, St. Paul, MN (US);
Gary L. Huelsman, St. Paul, MN (US)

FOREIGN PATENT DOCUMENTS

(73) Assignee: **Imation Corp.**, Oakdale, MN (US)

DE 32 40 063 5/1983
DE 40 09 797 A1 10/1991
GB 1 401 041 5/1972
WO WO 97/11328 3/1997

(* Notice: This patent is subject to a terminal disclaimer.

OTHER PUBLICATIONS

(21) Appl. No.: **09/679,446**

Aura Luisa Lopez de Ramos, "Capillary Enhanced Diffusion of CO₂ in Porous Media," A Dissertation Approved for the Discipline of Chemical Engineering, The University of Tulsa, 1993.

(22) Filed: **Sep. 29, 2000**

Prof. Durts, Visuals on Condensation Drying, Erlangen, Germany (Apr. 26, 1996).

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **5,813,133**
Issued: **Sep. 29, 1998**
Appl. No.: **08/888,721**
Filed: **Jul. 7, 1997**

Concus and Finn, "On The Behavior of a Capillary in a Wedge," Proceeding of the National Academy of Science, vol. 63, 292-299 (1968).

Adamson, A.W., "Physical Chemistry of Surfaces," Fourth Edition, John Wiley & Sons, Inc. (1982).

U.S. Applications:

(63) Continuation-in-part of application No. 08/699,522, filed on Sep. 4, 1996, now Pat. No. 5,694,701.

Primary Examiner—Pamela A Wilson

(74) *Attorney, Agent, or Firm*—Eric D. Levinson

(51) **Int. Cl.**⁷ **F26B 3/34**

(52) **U.S. Cl.** **34/248; 34/421; 34/463; 34/469; 34/73**

(58) **Field of Search** 34/248, 421, 463, 34/468, 469, 73; 427/379, 372.2; 118/123, 58, 642; 165/110, 913

(57) **ABSTRACT**


Drying a coated substrate which includes magnetic particles includes a condensing surface spaced from the substrate. This creates a longitudinal gap between the substrate and the condensing surface. Liquid is evaporated from the substrate to create a vapor and the vapor is transported to the condensing surface without requiring applied convection. The vapor is condensed on the condensing surface to create a condensate which is removed from the condensing surface. Removal is performed, using more than gravity, without allowing non-uniformities of the condensate film to occur. The magnetic particles are oriented on the coated substrate by subjecting the coated substrate to a magnetic field created at a location outside of the dryer space.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,494,830 A 5/1924 Cook
3,000,346 A 9/1961 Hnilica, Jr.
3,408,748 A 11/1968 Dunn, Jr.
4,321,757 A 3/1982 van der Blom
4,365,423 A 12/1982 Arter et al.
4,389,797 A 6/1983 Spigarelli et al.
4,413,425 A 11/1983 Candor
4,447,467 A * 5/1984 Oguchi et al. 427/48

97 Claims, 6 Drawing Sheets






US RE38,412 E

Page 2

U.S. PATENT DOCUMENTS

| | | | | | |
|-------------|---------|---------------|----------------|---------|-----------------------------|
| 4,894,927 A | 1/1990 | Ogawa et al. | 5,581,905 A | 12/1996 | Huelsman et al. |
| 4,923,766 A | 5/1990 | Hosoi et al. | 5,721,010 A * | 2/1998 | Hinoki et al. 427/131 |
| 4,926,567 A | 5/1990 | Ogawa | 5,980,697 A * | 11/1999 | Kolb et al. 203/1 |
| 4,951,401 A | 8/1990 | Suzuki et al. | 6,047,151 A * | 4/2000 | Carvalho et al. 34/469 |
| 4,999,927 A | 3/1991 | Durst et al. | 6,134,808 A * | 10/2000 | Yapel et al. 34/421 |
| 5,168,639 A | 12/1992 | Hebels | 6,256,904 B1 * | 7/2001 | Kolb et al. 34/448 |
| 5,448,838 A | 9/1995 | Edmonds | | | |

* cited by examiner






Fig. 4








Fig. 5






Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16

**COATED SUBSTRATE DRYING SYSTEM
WITH MAGNETIC PARTICLE
ORIENTATION**

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

This is a continuation-in-part of U.S. application Ser. No. 08/699,522, filed Sept. 4, 1996, U.S. Pat. No. 5,694,701.

TECHNICAL FIELD

The present invention relates to a method and apparatus for transporting mass and energy and for drying coatings on a substrate. More particularly, the present invention relates to substrate drying with magnetic particle orientation.

BACKGROUND OF THE INVENTION

Drying coated substrates, such as webs, requires supplying energy to the coating and then removing the evaporated liquid. The liquid to be evaporated from the coating can be any liquid including solvents such as organic solvent systems and inorganic systems which include water-based solvent systems. Convection, conduction, radiation, and microwave energy are used to supply energy to coated webs. Applied convection or forced gas flow is used to remove the evaporated liquid. Applied convection is defined as convection produced by the input of power and caused intentionally. It excludes convection caused merely by web movement, natural convection, and other, unavoidable, forces. In some instances where the vapors are non-toxic, such as water evaporation, the vapor is removed by flashing off into the ambient atmosphere.

In conventional drying technology, large volumes of gas, inert or not, are required to remove evaporated liquid from the gas/liquid interface. These dryers require large spaces between the coated web being dried and the top of the drying enclosure to accommodate the large gas flows. Drying is governed at the gas/liquid interface by diffusion, convection, boundary layer air from the moving web and impinging air streams, vapor concentrations, and liquid to vapor change-of-state convection, among other factors. These phenomena occur immediately above the coated web, typically within 15 cm of the surface. Because conventional dryers have a large space above the coated web, and they can only control the average velocity and temperature of the bulk gas stream, they have limited ability to control these phenomena near the gas/liquid interface.

For organic solvent systems, the vapor concentrations in these bulk gas streams are kept low, typically 1–2%, to remain below the flammable limits for the vapor/gas mixture. These large gas flows are intended to remove the evaporated liquid from the process. The expense to enclose, heat, pressurize, and control these gas flows is a major part of the dryer cost. It would be advantageous to eliminate the need for these large gas flows.

These gas streams can be directed to condensation systems to separate the vapors before exhausting, using a large heat exchangers or chilled rolls with wiping blades. These condensation systems are located relatively far from the coated web in the bulk gas flow stream. Due to the low vapor concentration in this gas stream, these systems are large, expensive, and must operate at low temperatures.

It would be advantageous to locate the condensation systems close to the coated substrate where the vapor

concentrations are high. However, conventional heat exchangers would drain the condensed liquid by gravity back onto the coating surface and affect product quality unless they were tilted or had a collection pan. If they had a collection pan they would be isolated from the high concentration web surface. If they were tilted dripping would probably still be a problem. Also, conventional heat exchangers are not planar to follow the web path and control the drying conditions.

U.S. Pat. No. 4,365,423 describes a drying system which uses a foraminous surface above the web being dried to shield the coating from turbulence produced by the large gas flows to prevent mottle. However, this system does not eliminate applied convection, requires using secondary, low efficiency solvent recovery, and has reduced drying rates. Also, because of the reduced drying rates, this patent teaches using this shield for only 5–25% of the dryer length.

German Offenlegungsschrift No. 4009797 describes a solvent recovery system located within a drying enclosure to remove evaporated liquid. A chilled roll with a scraping blade is placed above the web surface and removes the vapors in liquid form. No applied convection removes the evaporated liquid. However, the roll is only in the high vapor concentration near the surface for a short section of the dryer length. This does not provide optimal control of the conditions at the gas/liquid interface. In fact as the roll rotates it can create turbulence near the web surface. Also, this system can not adapt its shape to the series of planar surfaces of the coated web as it travels through the dryer. Therefore, the system can not operate with a small, planar gap to control drying conditions and can not achieve optimum condensing efficiency.

U.K. patent No. 1 401 041 describes a solvent recovery system that operates without the large gas flows required for conventional drying by using heating and condensing plates near the coated substrate. The solvent condenses on the condensing plate and then condensed liquid drains by gravity to a collection device. This apparatus uses only gravity to remove the liquid from the condensing surface. Accordingly, the condensing surface can not be located above the coated substrate since gravity will carry the condensed liquid back onto the coated substrate. In the drawings and discussion (page 3, lines 89–92) the condensing surface is described as vertical or with the coated substrate, coated side facing down, above the condensing surface. Applying a coating to the bottom side of the substrate or inverting the substrate after application of the coating is not the preferred method in industry. Coating in an inverted position and inverting a coated substrate before drying can create coating defects. These limitations greatly reduced the flexibility of the method and entail significant costs to adapt it to standard manufacturing methods. This requirement for vertical or inverted drying is very likely the reason this method has not been adopted or discussed in the industry.

U.K. patent No. 1 401 041 also describes, on page 2 line 126 to page 3 line 20, the problems of this method with growth of the liquid film layer on the condensing surface and droplet formation. Because “the resulting liquid film **14** may increase in thickness towards the lower end of the condenser,” the length of the condensing surface is limited by the buildup and stability of this film layer. Limiting the length of the condensing surface will limit the dryer length or require exiting the drying system with the coating not dried. This has the undesirable effect of losing some of the solvent vapors to the atmosphere, losing control of the drying phenomena, and creating defects. Another limitation is that the distance of the condensing surface from the coated

substrate "can hardly fall below about 5 millimeters" to prevent contacting the condensing liquid film with the substrate, and to prevent droplets from contacting the substrate.

The limitations of this system to vertical or inverted drying, limits in the length of the dryer, and the inability to operate at desired distances from the coated substrate render it inadequate to achieve the desired drying benefits.

Dryers used to dry magnetic coatings also are known. Known systems place a magnetic field generator inside the dryer to orient the magnetic particles within the coating being dried. However, conventional orienting devices inside the dryer disrupt the air flow and impair drying, causing the surface of the product to roughen. As the particles leave a conventional orienting device in the early stages of drying, any components of the magnetic field which are not in the plane of the coating will reorient the particles in a non-preferred direction.

There is a need for a system for drying coated substrates while orienting magnetic particles in the coating, which provides improved control of the conditions near the gas/liquid interface and in which the orientation process does not interfere with the drying. There is also a need for a system that can operate with small gaps adjacent the substrate.

SUMMARY OF THE INVENTION

The invention is a method and apparatus of drying a coated substrate that includes magnetic particles. A condensing surface is spaced from the substrate and substantially corresponds to the path of the substrate in the longitudinal direction. This creates a longitudinal gap between the substrate and the condensing surface. Liquid is evaporated from the substrate to create a vapor and the vapor is transported to the condensing surface without requiring applied convection. The vapor is condensed on the condensing surface to create a condensate, and the condensate is removed from the condensing surface. Removal is performed, using more than gravity, without allowing non-uniformities of the condensate film to occur. The magnetic particles are oriented on the coated substrate by subjecting the coated substrate to a magnetic field created at a location outside of the space between the condensing surface and the coated substrate. The magnetic field can be created by a magnetic field generator.

The magnetic field can be created at various locations: a location separated from the substrate by the condensing surface, a location separated from the condensing surface by the substrate, a location surrounding the substrate, and any combination of these locations.

The magnetic particles can be oriented at the beginning of the evaporating step and holding the magnetic particles in a preferred direction during the evaporating, condensing, transporting, and removing steps.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of the drying and orienting apparatus of the invention.

FIG. 2 is an end view of the apparatus of FIG. 1.

FIG. 3 is a cross-sectional view taken along line 3—3 of FIG. 1.

FIG. 4 is a perspective view of the drying and orienting apparatus according to another embodiment of the invention.

FIG. 5 is an end view of the apparatus of FIG. 4.

FIG. 6 is a perspective view of another embodiment of the drying apparatus.

FIG. 7 is a cross-sectional view of another embodiment of the drying apparatus.

FIG. 8 is a cross-sectional view of another embodiment of the drying apparatus.

FIG. 9 is a cross-sectional view of another embodiment of the drying apparatus.

FIG. 10 is a schematic side view of another embodiment of the drying apparatus.

FIG. 11 is a cross-sectional view of another embodiment of the drying apparatus.

FIG. 12 is a bottom view of a condensing platen according to another embodiment of the invention.

FIG. 13 is a top view of another embodiment of the drying apparatus.

FIG. 14 is a top view of the drying apparatus according to another embodiment of the invention.

FIG. 15 is a side view of another embodiment of the drying apparatus.

FIG. 16 is a schematic side view of the invention showing process variables.

DETAILED DESCRIPTION

The system of this invention is a method and apparatus for transporting mass and energy and for drying coatings on a coated substrate, such as a moving web, with a condensing surface creating a small, controlled-environment gap above the coating surface. Other physical and chemical phenomena that occur during the drying process, such as chemical reactions, curing, the phase changes, can also be affected by the invention. The coated substrate includes magnetic particles, particles which are capable of being attracted or repelled by a magnet, such as ferrous particles used in audio, video, and data storage tape or media. The method and apparatus also orient these particles in a magnetic field as described below.

In the embodiment of FIGS. 1, 2, and 3, drying (heating the liquid to evaporate it to a vapor, transporting the vapor away from the web, condensing the vapor, and transporting the condensed vapor (also known as condensate) away from the web) occurs without requiring the applied gas convection associated with conventional drying methods. This reduces mottle formation associated with many precision coatings and enables drying at increased drying rates. In the embodiment of FIGS. 4—15, at least the removal of the evaporated liquid from the web occurs without requiring applied gas convection. All versions of this system attain improved control of the phenomena occurring near the gas/liquid interface and attain high liquid recovery efficiencies.

All versions use condensation to remove evaporated liquid in a gap which can be substantially planar without requiring applied convection forces, and where ambient and boundary layer convection forces are minimized. The drying system has numerous advantages over the conventional drying technology by creating a small, controlled-environment gap adjacent the coating surface, and by eliminating the requirement for applied convection from the drying mechanism. In some products a chemical reaction or other physical and chemical processes occur in the coating during drying. The drying system functions whether or not these processes are proceeding within the process. The drying system can affect these processes during drying. One example is of moisture-cured polymers dispersed or dissolved in a solvent that can be adversely affected during the drying process due to the presence of humidity in the drying

atmosphere. Because the invention can create a small, controlled environment gap above the coating surface, it is substantially simpler to provide a controlled humidity drying atmosphere to improve the curing of these polymers. By improving control of the drying phenomena and creating a small, controlled environment gap above the coated surface, there are many other applications where other physical and chemical processes occurring during the drying process can benefit.

In an alternative method the drying system can be combined with applied convection, and the applied convection can be produced by forcing gas across the coating, either longitudinally, transversely, or in any other direction. This can provide additional mass transfer or other modification to the atmosphere above the coated surface. This method could be used where applied convection is not a detriment to product properties.

The inventors have found that in drying coated substrates, significant drying improvements and increased drying rates occur when the distance from the condensing surface to the coated substrate is below 5 millimeters. The system of U.K. patent No. 1 401 041 is not practically operable in the range where significant drying control improvements can be made.

Many kinds of condensing structures can be used, such as plates of any type, whether flat or not, porous or not, structured or not, or other shapes such as tubes or fins. The condensing surface structure can combine macro, meso, and micro scale geometries and dimensions. Plates include fixed or moving platens, moving belts with or without liquid scrapers, and similar devices. The condensing structure can be parallel to the web or angled with the web, and can have planar or curved surfaces.

The condensing surface must satisfy three criteria. First, it must be capable of sufficient energy transfer to remove the latent heat of condensation. Second, the condensate must at least partially wet the condensing surface. Third, the condensing surface must prevent the condensed vapor (the condensate) from returning to the coated surface of the web. Associated with a condensing surface is an effective critical condensate film thickness which marks the onset of film non-uniformities. This thickness is a function of the condensing surface material, geometry, dimensions, topology, orientation, configuration, and other factors, as well as the physical properties of the condensate (such as surface tension, density, and viscosity). Another feature of the system is condensate transport and removal. This maintains the condensate film thickness less than the effective critical thickness and can be accomplished by capillary forces, gravitational forces, mechanical forces, or various combinations of these forces.

Capillary force, or capillary pressure, can be described as the resultant of surface tension acting in curved menisci and is governed by the fundamental equation of capillarity known as the Young-LaPlace equation. The Young-LaPlace equation is $\Delta P = \sigma(1/R_1 + 1/R_2)$, where ΔP is the pressure drop across the interface, σ is the surface tension, and R_1 and R_2 are the principal radii of curvature of the interface. Capillarity is discussed in detail in Adamson, A. W. "Physical Chemistry of Surfaces, 4th ed.", John Wiley & Sons, Inc. (1982). FIGS. 1, 2, 4, 5, 9, 10, and 11 show examples of using capillary forces, along with other forces, to remove the condensate from the condensing surface.

Gravitational forces result from the position of the fluid mass in a gravitational field, which is the hydrostatic head. FIGS. 7, 8, 10, and 12 show examples that use gravitational forces, along with other forces, to remove the condensate from the condensing surface.

Other mechanisms can be used to remove the condensed liquid from the condensing surface to prevent the condensed liquid from returning to the substrate. For example, mechanical devices, such as wipers, belts, scrapers, pumping systems, or any combination, can be used to remove the condensed liquid. FIGS. 6, 13, 14, and 15 show examples that use mechanical forces, along with other forces, to remove the condensate from the condensing surface.

FIGS. 1, 2, and 3 show an apparatus using two platens. FIGS. 4 and 5 show an apparatus using one platen. In both versions, one platen has a condensing, liquid-transport surface located a short distance from the coated surface of the web. Distances of less than 15–20 cm are preferred. Distances less than 5 mm yield more advantages. Distances less than 0.5 mm and even distances as low as 0.1 mm and less are attainable.

In FIGS. 1 and 2, the apparatus 10 includes a condensing platen 12, which can be chilled, spaced from a heated platen 14. A solenoid coil 15 surrounds the platens 12, 14. The condensing platen 12 is set to a temperature T_1 , which can be above or below ambient temperature, and the heated platen 14 is set to a temperature T_2 , which can be above or below ambient temperature. The coated web 16 temperature is T_3 . The web position is defined by h_1 and h_2 , the distances between the respective facing surfaces of the web 16 and the condensing and heated platens. FIG. 16 shows the relative locations of these variables. The total gap between the condensing platen and any heating platen, h , is the total of h_1 , h_2 , and the coated web thickness. The web 16, having a coating 18, travels at any speed between the two platens. Alternatively, the web can be stationary and the entire apparatus 10 moves or both the web and apparatus move. The platens are stationary within the apparatus. The heated platen 14 is located on the non-coated side of the web 16, either in contact with the web or with a small gap h_2 between the web and the platen. The condensing platen 12 is located on the coated side of the web 16, with a small gap h_1 between the web and the platen. The condensing platen 12 and the heated platen 14 eliminate the requirement for applied convection forces both above and below the web 16. Drying is controlled by adjusting the temperature T_1 , T_2 , and distances h_1 , h_2 .

The condensing platen 12, which can be stationary or mobile, is placed near the coated surface (such as 10 cm away, 5 cm away, or closer). The arrangement of the platens creates a small gap adjacent the coated web. The gap is substantially constant, which permits small amounts of convergence or divergence. Also, the gap is substantially constant notwithstanding any grooves (discussed below) on the condensing surface. The orientation of the platens is not critical. The condensing platen 12 can be above the web (as shown in FIGS. 1, 2, 4, and 5–9), below the web (with the coating on the bottom surface of the web), and the system can operate with the web vertical or at any other angle, including being tilted around the axis of the direction of web travel.

The heated platen 14 supplies energy without requiring applied convection through the web 16 to the coating 18 to evaporate liquid from the coating 18 to dry the coating. Energy is transferred by a combination of conduction, radiation, and convection achieving high heat transfer rates. This evaporates the liquid in the coating 18 on the web 16. The evaporated liquid from the coating 18 then is transported (using diffusion and convection) across the gap h_1 between the web 16 and the condensing platen 12 and condenses on the bottom surface of the condensing platen 12.

As shown in FIG. 3, the bottom surface of the condensing platen 12 is the condensing surface 22 and has transverse open channels or grooves 24 which use capillary forces to prevent the condensed liquid from returning to the coating by gravity and to move the condensed liquid laterally to edge plates 26. The grooves can be triangular, rectangular, circular, or other more complex shapes or combinations of shapes. The groove material, geometry, and dimensions are designed to accommodate the required mass flow and the physical properties of the condensate, such as surface tension, viscosity, and density.

A specific type of condensing surface is one which has open channels or grooves with corners. This type of capillary condensing surface, shown for example in FIG. 3, is a geometrically specific surface which can be designed with the aid of the Concus-Finn Inequality (Concus P. and Finn R. "On the Behavior of a Capillary Surface in a Wedge," Proceeding of the National Academy of Science, vol. 63, 292-299 (1969)) which is: $\alpha + \theta_s < 90^\circ$, where α is half the included angle of any corner and θ_s is the gas/liquid/solid static contact angle. The static contact angle is governed by the surface tension of the liquid for a given surface material in gas. If the inequality is not satisfied, the interface is bounded; if the inequality is satisfied, the interface does not have a finite equilibrium position and the meniscus is unbounded. In this latter case, the liquid will advance by capillarity indefinitely or to the end of the channel or groove. Cornered grooved surfaces are helpful when the coating liquid has a high surface tension, such as water. Capillary surfaces with corners are discussed in great detail in Lopez de Ramos, A. L., "Capillary Enhanced Diffusion of CO₂ in Porous Media," Ph.D. Dissertation, University of Tulsa (1993).

The grooves 24 also can be longitudinal or in any other direction. If the grooves are in the longitudinal direction, a suitable collection system can be placed at the ends of the grooves to prevent the condensed liquid from falling back to the coated surface 18. This embodiment limits the length of a condensing plate 12 and also limits the minimum gap h_1 .

When the liquid reaches the end of the grooves 24 it intersects with the angle between the edge plates 26 and the condensing surface 22. A liquid meniscus forms and creates a low pressure region which draws the condensate from the condensing surface to at least one edge plate. Gravity overcomes the capillary force in the meniscus and the liquid flows as a film or droplets 28 down the face of the edge plates 26. The edge plates 26 can be used with any condensing surface, not just one having grooves. The droplets 28 fall from each edge plate 26 and can be collected in a collecting device (not shown). For example, a slotted pipe can be placed around the bottom edge of each edge plate 26 to collect the liquid and direct it to a container. The edge plates 26 are shown throughout the application as contacting the ends of the condensing surface of the condensing platens. However, the edge plates can be adjacent the condensing platens without contacting them as long as they are functionally close enough to receive the condensed liquid.

Alternatively, the condensed liquid need not be removed from the platen at all, as long as it is removed from the condensing surface 22, or at least prevented from returning to the web 16. Also, the edge plates 26 are shown as perpendicular to the condensing surface 14, although they can be at other angles with it, and the edge plates 26 can be smooth, grooved, porous, or other materials.

The heated platen 14 and the condensing platen 12 can include internal passageways, such as channels. A heat

transfer fluid can be heated by an external heating system and circulated through the passageways to set the temperature T_2 of the heated platen 14. The same or a different heat transfer fluid can be cooled by an external chiller and circulated through the passageways to set the temperature T_1 of the condensing platen 12. Other mechanisms for heating the platen 14 and cooling the platen 12 can be used.

The apparatus 30 of FIGS. 4 and 5 is similar to that of FIGS. 1-3 except there is no heating platen. In the apparatus 30, the web 16 is heated to evaporate the liquid from the coating by any heating method or combination of heating methods, whether conduction, radiation, microwave, convection, or ambient energy, using any type of heater. This can include but is not limited to a heated drum, radiant heating devices, or forced gas flows. This system can even operate without any applied energy, even outside the dryer, using only ambient energy to evaporate the liquid. The apparatus 30 otherwise operates the same as that of FIGS. 1-3, without requiring applied convection for transport of the evaporated liquid from the web 16 to the condensing surface 22 on the condensing platen 12. The gap h_1 between the coated web 16 and the condensing surface 22 is isolated from the heating devices by any combination of the web 16 and web supports or other barriers. This can isolate the area from any applied convection.

In FIG. 6, the apparatus 32 includes a belt 34 which has the condensing surface 22. The belt 34 substantially corresponds to the shape of the substrate and provides a gap between the substrate and the condensing surface. The belt can be solid or porous and can be made of a variety of materials. The belt is driven by rollers 36 which can provide relative movement between the condensing surface 22 and the substrate 16. Alternatively the condensing surface 22 can be driven to provide no movement relative to the web 16 or it can be driven in the opposite direction of the web 16. Alternatively the entire system can be rotated from the position shown and the belt 34 can be driven substantially transverse to the direction of movement of the web 16. In this method the liquid would be removed beyond the edge of the web 16. Removal of the liquid from the condensing surface 22 is provided by a mechanical wipe 38 which is adjacent to the belt 34. The mechanical wipe 38 removes the liquid from the condensing surface 22 using shear forces and directs it to a suitable collection device 40.

FIGS. 7 and 8 show embodiments of the apparatus where gravity is used to remove the liquid solvent from the condensing surface. The condensing surface 22 is on a plate 42 which is tilted to one transverse side of the web 16 in FIG. 7 and the condensing surface 22 is on one or two plates 44 which are tilted from the center to both transverse sides of the web 16 in FIG. 8. In both cases gravity is used to move the liquid away from the condensing surface. The angle could be centered on the longitudinal centerline of the web or it can be off-center. Capillarity can be combined with gravity.

FIG. 9 is another embodiment where capillary forces remove the liquid from the condensing surface. In this embodiment the condensing plate 46 is a porous or wicking material, such as sintered metal or sponge, which uses capillary forces to transport the liquid solvent. The solvent condenses on the condensing surface 22 and is distributed throughout the condensing plate 46 due to capillary forces. The edge plates 26 adjacent the condensing plate 46 form a capillary surface. A liquid meniscus forms and creates a low pressure region which draws the condensate from the condensing surface to at least one edge plate. Gravity overcomes the capillary force and the liquid flows as a film or droplets down the surface of the edge plate 26.

FIG. 10 shows another embodiment where capillary and gravity forces are used to transport the condensed liquid from the condensing surfaces 22. As shown, condensing surfaces 22 are formed on many surfaces. A condensing platen 48 is tilted to one side or from the center to both sides above the web 16. Thin sheets 50 of material are suspended below the condensing platen 48 and located such that they are slanted away from the horizontal with their lower edge facing the lower edge of the condensing platen 48. As shown, the sheets 50 of material overlap by at least 0.05 cm and are spaced apart in the overlap region by a 0.01–0.25 cm slot. Vapor that condenses on the condensing surfaces 22 will be retained on the surfaces by surface tension. Gravity carries the condensed liquid down each upper surface of the sheets 50 in a cascade effect until the liquid is beyond the edge of the web 16. Liquid that is condensed on the lower surface of the thin sheets 50 will transport to the overlap region and capillary forces created by the slot will draw the liquid into the slot. The liquid will then be transferred to the upper surface of the next sheet 50 and gravity will carry it in a cascade manner to the edge of the substrate. Thus, liquid condensing on the lower surface of the sheets will not form droplets that fall back to the coated substrate. In some cases it is desirable for the liquid to completely fill the slot between the sheets 50 and the condensing platen 48.

FIG. 11 is another embodiment which can combine gravity and capillary forces to transport the liquid from the condensing surface. In this embodiment a porous, slotted, sponge, honeycomb, screened, or otherwise foraminous material 52 is attached to and located below a condensing platen 54. The spacing between the condensing platen 54 and the foraminous material 52, the dimensions of the foramina in the material 52, and the ratio of open area to solid area on the foraminous material 52 are all designed to cause the surface tension forces to retain the liquid on the three condensing surfaces 22. The apparatus is located adjacent to the web 16. Vapor condensing on the condensing surfaces 22 will be retained as liquid in the voids of the foraminous material and in the plate spacing region 56. As liquid is removed from the plate spacing region 56, liquid on the side of the foraminous material 52 facing the web 16 will be transported by capillary forces to fill the void in the plate spacing region 56. Liquid can be removed from the plate spacing region 56 either by gravity, capillary, or mechanical forces. By sloping the condensing platen 54 away from the horizontal in any direction, gravitational forces will remove liquid from the plate spacing region 56 to a point beyond the edge of the web 16. Alternatively, the liquid can be removed from the plate spacing region 56 by positioning at least one edge plate 26 at the edge of the condensing platen 54. The edge plate 26 contacts the condensing platen 54 to form a capillary surface. The edge plates can, in some uses, contact the foraminous material 22. A liquid meniscus forms and creates a low pressure region which draws the condensate toward at least one edge plate. Gravity overcomes the capillary force and the liquid flows as a film or droplets down the surface of the edge plate 26. Also, the condensate can be mechanically pumped out of the plate spacing region 56.

FIG. 12 shows a condensing platen 60 with protruding structures. The condensing platen 60 provides a condensing surface 22 that can substantially correspond to the shape of the web 16. Gravity is used to remove the liquid from the condensing surface 22 by positioning the platen 60 away from horizontal. This tilting from the horizontal can be in any direction, including transverse and parallel to the web 16 path. Without any additional device, the liquid draining from

the condensing surface 22 will, over a short distance (typically less than a meter), build a sufficient film thickness such that the surface tension forces will be incapable of retaining the liquid and the liquid will fall as droplets onto the web 16. Structure having any geometric shape, such as ribs 62, can be positioned on the condensing surface 22 of the condensing platen 60 to limit the buildup of film thickness, and prevent the formation of droplets that fall onto the web 16. The ribs 62 are located diagonally to the slope of the condensing surface 22 to direct the liquid beyond the edge of the web 16 to a suitable collecting device (not shown). They are provided in sufficient number and at a suitable spacing to limit the surface area drained by a specific rib 62 thereby maintaining the film thickness below the critical point for the occurrence of droplet formation. The condensing surface can have grooves that run in the longitudinal web direction.

The apparatus 64 of FIG. 13 mechanically moves the condensing surface and condensed liquid beyond the edge of the web 16 where the liquid is then removed. A condensing platen 66 provides the condensing surface 22 that is located adjacent to the web 16. The platen 66, which can be circular or any other shape, is mechanically rotated so that the liquid that condenses on its condensing surface 22 is transported to an area beyond the edge of the web 16. Removal of the liquid from the condensing surface 22 is provided by a mechanical wipe 68 which is adjacent the condensing surface 22 and anchored to a block 69. The mechanical wipe 68 uses shear forces to remove the liquid from the condensing surface 22 and direct it to a suitable collection device 70. A series of these systems can be located such that they substantially correspond to the shape of the substrate in the longitudinal direction.

FIG. 14 shows an apparatus 72 that uses surface tension to retain the liquid and a mechanical device to remove the liquid from the condensing surface. A condensing platen 74 provides a condensing surface 22 that can substantially correspond to the shape of the web 16. Liquid that condenses on the condensing surface 22 is retained on that surface by surface tension. Removal of the liquid from the condensing surface 22 is provided by one or more mechanical wipes 76 which is adjacent the condensing surface 22. The mechanical wipe 76 can move across the condensing surface 22 transverse to the path of the web 16, parallel to the path of the web 16, or in any other direction. The mechanical wipe 76 uses shear forces to remove the liquid from the condensing surface 22 and direct it to a suitable collection device 78 located below the mechanical wipe 76. The liquid is carried in the collection device 78 beyond the edge of the web 16 where it is transferred away.

FIG. 15 schematically shows an embodiment which uses a pump 80 to remove the condensed liquid from the condensing surface. The pump can be any type of pump, and any other device for creating negative pressure can be used. As also shown in FIG. 15, the condensed liquid can be driven toward the transverse center of the condensing surface before removal, such as by capillarity and gravity.

In another use, the system can first remove fluid from a coated substrate. Then, the system, at a downweb location from the driving location, can be used “in reverse” to add some small portion of moisture or additional reactant to the substrate to modify the coating.

The apparatus can operate outside of a dryer configuration without any applied energy, and with only ambient heat to evaporate the liquid. By controlling the temperature of the condensing surface 22 to be at or near the ambient

temperature, the liquid evaporation will only occur until the vapor concentration in the gap h_1 between the condensing surface and the web **16** is at the saturated concentration as defined by the condensing surface **22** and web **16** temperatures. The liquid that has evaporated will be contained and carried by the viscous drag of the web through the gap h_1 to the exit of the system. Undesirable drying can be reduced and vapor emissions can be isolated from ambient conditions.

The drying system of the invention can be used to reduce or virtually stop the drying of the coating. The rate of drying is a function of the gap height and vapor concentration gradient between the coated surfaces **18** of the web **16** and the condensing surface **22**. For a given gap h_1 , the temperature differential between the web **16** and the condensing surface **22** defines the vapor concentration gradient. The higher the coated surface **18** temperature relative to the condensing surface **22**, the greater the rate of drying. As the temperature of the condensing surface **22** approaches the coated surface **18** temperature, the drying rate will tend to zero. In conventional drying the vapor concentration gradient cannot be controlled without using an expensive inert gas drying system. Some liquid coatings have multiple solvents where one or more of the solvents function to slow down the rate of drying for optimum product properties. By adjusting the coated surface **18** and condensing surface **22** temperatures, the invention can reduce the drying rate and possibly eliminate the requirement of using solvents to retard the drying rate.

The rate of drying is controlled by the height of the gap h_1 and the temperature differential between the coated surface **18** and the condensing surface **22**. Therefore for a given temperature differential, the rate of drying can be controlled by the position of the condensing plate which defines the gap h_1 . Thus by changing the dimensions of the drying system, such as by changing the relative gaps, it is possible to control the rate of drying. Conventional dryers do not have this capability.

Drying some coated webs using applied convection can create mottle patterns in the coatings. Mottle patterns are defects in film coatings that are formed by vapor concentration or gas velocity gradients above the coating which cause non-uniform drying at the liquid surface. Normal room air currents are often sufficient to create these defects. The invention can be used to reduce and control natural convection induced defects, such as mottle, at locations outside the desired drying position. In locations where the coated surface is not in the drying region and would otherwise be exposed to convection from either ambient air currents or from a turbulent boundary layer air due to web movement, the apparatus, with grooves or other liquid transport and removal features, devices, structures or without, can be located adjacent to the coated web **16** separated by a gap h_1 . The location of the condensing plate **12** adjacent the coated web **16** can isolate the ambient air currents from the coating surface. It can also prevent the boundary layer air above the coated surface from becoming turbulent. Accordingly, defects due to convection outside the drying position, such as mottle, can be reduced or eliminated. The apparatus can be operated with condensation and solvent removal similar to FIGS. 4-15, or it can even operate without condensation and solvent removal by raising the condensing surface **22** temperature above the dew point of the vapors in the gap h_1 .

In all embodiments it may be desirable to provide multiple zones of heating and condensing components using multiple pairs. The temperatures and gaps of each pair of

heating and condensing components can be controlled independently of the other pairs. The zones can be spaced from each other or not.

The systems of all of the embodiments use condensation close to the coated web **16** with a small gap between the coating on the web **16** and the condensing surface **22**. There is no requirement for applied convection and there is very little vapor volume. The vapor concentration and convection forces can be controlled by adjusting the web temperature, the gap, and the condensing surface temperature. This provides improved control of the conditions near the gas/liquid interface. Because the plate temperatures and gap can be continuous and constant throughout the drying system, heat and mass transfer rates are more uniformly controlled than with conventional drying systems. All of these factors contribute to improved drying performance. It also improves the efficiency of the condensation vapor recovery systems, providing for liquid recovery at high efficiencies at no additional cost compared to known expensive methods of burning, adsorption, or condensation in a secondary gas stream.

Also, there is less of a concern about the ambient air above the web exploding or being above the flammability limit. In fact, where the gap is very small, such as less than 1 cm, flammability concerns may be eliminated because the entire space above the web has insufficient oxygen to support flammability. Additionally, this system eliminates the need for large gas flows. The mechanical equipment and control system is only 20% of the cost of a conventional air flotation drying system.

Experiments were conducted with 30.5 cm wide platens having transverse grooves. The bottom platen was heated to temperatures in the range of 15° C. through 190° C. with a heat transfer fluid circulated through passageways in the platens. As the heat is transferred to the coating, the liquid in the coating evaporates. The temperatures of the condensing platen was controlled by any suitable method in the range of -10° C. through 65° C. to provide the driving force for vapor transport and condensation. An effective range of the gap h_1 is 0.15-5 cm. Mottle-free coatings were obtained.

In one example, a mottle-prone polymer/MEK solution at 11.5% solids, 2 centipoise, 7.6 micron wet thickness, and 20.3 cm wide was coated. The web was 21.6 cm wide and traveled at a speed of 0.635 m/s. The temperature of the heated platen used to heat the web was controlled at 82° C. The condensing platen temperature was controlled at 27° C. The overall length of the platens was 1.68 m and they were mounted at a 3.4° angle from horizontal with the inlet side at a lower elevation. The inlet to the platens was located 76 cm from the coating application point. The heated platen was separated from the web by a gap of approximately 0.076 cm. The gap h_1 was set at 0.32 cm. The capillary grooves were 0.0381 cm deep with a 0.076 cm peak-to-peak distance, an angle α of 30°, and 0.013 cm land at the top of the grooves. The web was dried mottle-free in the 1.68 m length of the platens although there was some residual solvent in the coating when it left the platens. A conventional dryer would require approximately 9 m to reach the same drying point, requiring the dryer to be more than five times larger.

Other applications for this system include drying adhesives where blister defects are common. Blister defects may be caused by the coating surface forming a dried skin before the rest of the coating has dried, trapping solvent below this skin. With conventional drying, the solvent vapor concentration in the bulk gas is very low because of flammability

limits. If too much heat is applied to the coating, the solvent at the surface will flash very quickly into the low vapor concentration gas stream and will form the skin on the surface. The system of this invention creates a controlled vapor concentration in the space above the web which can reduce the tendency to form a skin on the surface. Other applications are in areas where dryers are run at high solvent concentrations to obtain specific product performance.

This system simplifies the process of subjecting the coating fluid to a magnetic field. Rather than positioning a magnetic field generator within a known dryer, with the present invention the magnetic field generator can be positioned outside of the dryer (outside of apparatus **10, 30**). Locating the magnetic field generator outside of the dryer means that it is outside of the space between the condensing surface and the coated substrate. For example, it could be adjacent (whether spaced from or not) a side of the condensing plate opposite the side with the condensing surface (location separated from the substrate by the condensing surface); it could be adjacent a surface opposite the coated surface of the substrate (separated from the condensing surface by the substrate); or it could be at other locations. At these isolated locations, the magnetic field generator can use bucking fields to orient the magnetic particles. Also, as described below, the magnetic field generator can surround the dryer.

The magnetic field generator can be any of various known devices including permanent magnets and solenoid coils. A solenoid coil **15**, as shown in FIG. **2**, can have coil openings sufficiently large to permit the dryer to fit within the coils. This allows using the magnetic field inside of the coil openings which is uniform at all locations. This obviates any need to precisely locate the coated substrate within the magnetic field; variations in the substrate location will not affect the field through which the substrate passes. The figures schematically show one coil **15**, although a series of 2-10 or any other number of coils can be used. These coils can be individually controlled and lower magnetic field strengths can be used.

This configuration is enabled by the compact nature of the apparatus. This is especially suitable when coating a metal particulate-loaded fluid onto a substrate to make such products as video and audio recording tape, computer and data storage tape, computer diskettes, and the like. Being outside of the apparatus, the magnetic field generators are easily adjustable and maintained.

This setup also improves magnetic output by physically orienting the particles in the direction of recording. One advantage of this is that the magnetic orienting device is outside of the dryer and is non-intrusive (conventional orienting devices inside the dryer disrupt the convection heat and mass transfer (air flow) and orient the particles at a single point or multiple points as the solvent is removed). Because orientation is non-intrusive, it will not affect the solvent removal rates in any way. This allows uniform solvent removal and uniform coating drying while exposing the substrate to the magnetic field. The magnetic particles are easily oriented when the fluid is less viscous at the early stages of drying with this invention. (As the particles leave a conventional orienting device in the early stages of drying, any components of the magnetic field which are not in the plane of the coating will reorient the particles in a non-preferred direction, such as vertical. As the solvent is removed, the viscosity increases, making it difficult for the orienting device to rotate the particles. The particles will not be reoriented when leaving the field or by interparticle forces.)

Another advantage is that because of its small size and increased solvent removal rates, the invention allows orienting particles at the beginning of the dryer. The uniform field holds the particles in the preferred direction as the solvent is removed in a uniform drying environment to such a level that the viscosity is increased to the point that the viscous forces dominate. This prevents undesirable particle disorientation as it leaves the orienting device or from interparticle forces. (Drying at elevated rates in conventional dryers causes the surface of the product to roughen.) Removing the solvent in the controlled environment of the dryer of this invention appears to create smoother surfaces at elevated solvent removal rates. This also improves magnetic output as, for example, the resulting tape will ride closer to the recording head.

Various changes and modifications can be made in the invention without departing from the scope or spirit of the invention. For example, the invention has been described as a method and apparatus for performing magnetic orientation on a web while the web is inside a dryer by locating a magnetic field generator outside of the dryer. Other operations can also be performed on a web inside of a dryer from a device located outside the dryer when the dryer is as compact as the dryer enabled by the present invention. For example, some operations that can be performed include curing such as by UV radiation or electron beam radiation; decontaminating or sterilizing with, for example, a radiation source; and corona treating or light treating (whether through the dryer or through a hole or slot in the dryer plate through which the corona or light can pass). Other operations that do not require physically contacting the web also can be performed from outside of the dryer. Also, magnetic orientation and other operations can be performed outside of other types of dryers.

We claim:

1. A method for drying a coated substrate, wherein the coated substrate comprises magnetic particles, comprising:
 - locating a condensing surface spaced from and facing the substrate which substantially corresponds to the path of the substrate in the longitudinal direction to create a longitudinal gap between the substrate and the condensing surface;
 - evaporating the liquid from the substrate to create a vapor;
 - transporting the vapor to the condensing surface without requiring applied convection;
 - condensing the vapor on the condensing surface to create a condensate;
 - removing, using more than gravity, the condensate from the condensing surface without allowing non-uniformities of the condensate film to occur; and
 - orienting the magnetic particles on the coated substrate by subjecting the coated substrate to a magnetic field between the condensing surface and the coated substrate that is initially created at a location outside of the space between the condensing surface and the coated substrate.
2. The method of claim 1 wherein the orienting step comprises creating the magnetic field at least one of: a first location separated from the substrate by the condensing surface and a second location separated from the condensing surface by the substrate.
3. The method of claim 2 wherein the orienting step comprises creating the magnetic field at locations surrounding the condensing surface and the substrate.
4. The method of claim 1 wherein the orienting step comprises orienting the magnetic particles at the beginning

of the evaporating step and holding the magnetic particles in a preferred direction during the evaporating, condensing, transporting, and removing steps.

5 **5.** The method of claim **1** wherein the removing step comprises at least one of: tilting the condensing surface to at least one transverse side of the coated substrate such that gravity is used to remove the condensate from the condensing surface; and using mechanical shear forces.

6. The method of claim **1** further comprising the step of providing relative movement between the condensing surface and the coated substrate.

7. The method of claim **1** further comprising the step of controlling the rate of drying by controlling the height of the gap and the temperature difference between the coated substrate and the condensing surface.

8. An apparatus for drying a coated substrate, wherein the coated substrate comprises magnetic particles, comprising:

a condensing surface locatable spaced from and facing the substrate which substantially corresponds to the path of the substrate in the longitudinal direction to create a longitudinal gap between the substrate and the condensing surface;

means for evaporating the liquid from the substrate to create a vapor;

means for transporting the vapor to the condensing surface without requiring applied convection;

means for condensing the vapor on the condensing surface to create a condensate;

means for removing, using more than gravity, the condensate from the condensing surface without allowing non-uniformities of the condensate film to occur; and

at least one magnetic field generator located outside of the space between the condensing surface and the coated substrate.

9. The apparatus of claim **8** wherein the magnetic field generator is located at at least one of: a first location separated from the substrate by the condensing surface and a second location separated from the condensing surface by the substrate.

10. The apparatus of claim **9** wherein the magnetic field generator is located at a location surrounding the substrate and the condensing surface such that the substrate passes through the magnetic field generator.

11. The apparatus of claim **8** wherein the magnetic field generator is located at the entrance to the condensing plate.

12. The apparatus of claim **8** wherein the evaporating means comprises a heated plate which supplies heat by conduction to increase the rate of heat transfer compared to conventional drying methods that use convection.

13. The apparatus of claim **8** wherein the removing means comprises at least one of: tilting the condensing surface to at least one transverse side of the coated substrate such that surface tension holds the condensate onto the condensing surface and gravity is used to remove the condensate from the condensing surface; forming the condensing surface of a foraminous material; and a wiper.

14. The apparatus of claim **8** wherein the condensing platen is sloped away from the horizontal in any direction to remove condensate by gravity.

15. The apparatus of claim **8** further comprising a belt, wherein the condensing surface is formed on the belt and means for providing relative movement between the condensing surface on the belt and the coated substrate.

16. The apparatus of claim **8** further comprising means for controlling the rate of drying by controlling the height of the gap and the temperature difference between the coated substrate and the condensing surface.

17. The apparatus of claim **8** further comprising: a plurality of condensing surfaces; wherein the evaporating means comprises a plurality of heaters, and wherein each heater corresponds to a respective condensing surface to form pairs of condensing surfaces and heaters; and means for independently controlling each pair of condensing surface and heater.

18. An apparatus for drying a coating on a substrate, wherein the coating comprises particles in a liquid, the particles being capable of being affected by a magnetic field, the apparatus comprising:

a condensing surface locatable spaced from the substrate along the path of the substrate to create a gap between the substrate and the condensing surface;

means for evaporating the liquid from the coating to create a vapor;

means for condensing the vapor on the condensing surface to create a condensate; and

a magnetic field generator located outside of the space between the condensing surface and the coated substrate for imposing a magnetic field upon the particles in the coating.

19. The apparatus of claim **18** wherein the coated substrate is useful for creating at least one of an audio, video, or data storage medium, wherein the magnetic field generator is configured to magnetically align the particles.

20. A method for drying a coating on a substrate, wherein the coating comprises particles in a liquid, the particles being capable of being affected by a magnetic field, the method comprising the steps of:

locating a condensing surface spaced from the substrate along the path of the substrate to create a gap between the substrate and the condensing surface;

evaporating the liquid from the coating to create a vapor; condensing the vapor on the condensing surface to create a condensate; and

creating a magnetic field from outside of the space between the condensing surface and the coated substrate and imposing the field upon the particles in the coating.

21. The method of claim **20** wherein the coated substrate is useful for creating at least one of an audio, video, or data storage medium, wherein the magnetic field aligns the particles.

22. The method of claim **21** further comprising the step of converting the coated substrate into one of an audio, video, or data storage media product following the evaporating step.

23. A method for drying a coating on a substrate, wherein the coating has particles that can be affected by a magnetic field, comprising:

locating a condensing member adjacent and spaced from the substrate to create a gap between the substrate and a condensing surface of the condensing member;

forming a condensate on the condensing surface from the coating; and

subjecting the coating to a magnetic field created at a location outside the gap.

24. The method of claim **23** wherein the forming step comprises the step of causing vapor to emanate from the coating.

25. The method of claim **24** wherein the forming step comprises the step of heating the coating.

26. The method of claim **23** wherein the forming step comprises the step of evaporating liquid in the coating forming vapor in the gap.

27. The method of claim 26 wherein the liquid comprises a solvent.

28. The method of claim 23 wherein the forming step comprises the step of controlling the temperature of the condensing member.

29. The method of claim 23 wherein the forming step comprises the steps of:

causing vapor to emanate from the coating;

transporting the vapor across the gap to the condensing member; and

condensing the vapor on the condensing surface.

30. The method of claim 23 wherein the subjecting step comprises creating the magnetic field at least at one of a first location separated from the substrate by the condensing member and a second location separated from the condensing member by the substrate.

31. The method of claim 23 wherein the subjecting step comprises providing a magnetic field generator that surrounds the condensing member and the substrate.

32. The method of claim 23 wherein the subjecting step comprises magnetically orienting the particles.

33. The method of claim 32 wherein the forming step comprises the step of evaporating a solvent from the coating, and wherein the orienting step occurs during at least a portion of the evaporating step.

34. The method of claim 23 wherein the method further comprises the step of removing the condensate from the condensing surface.

35. The method of claim 34 wherein the removing step comprises the step of applying at least one of gravitational force, capillary force, and mechanical force to the condensate.

36. The method of claim 35 wherein the step of applying gravitational force comprises the step of configuring the condensing member such that at least a portion of the condensing surface is not horizontal.

37. The method of claim 35 wherein the step of applying capillary force comprises at least one of the steps of configuring the condensing member such that the condensing surface has capillary grooves, configuring the condensing member such that the condensing member comprises a foraminous member, and providing a foraminous member adjacent the condensing surface.

38. The method of claim 35 wherein the step of applying mechanical force comprises at least one of the steps of wiping condensate from the condensing surface and pumping condensate from the condensing surface.

39. The method of claim 23 wherein the condensing member is stationary, wherein the method further comprises the step of transporting the coating and substrate past the condensing member.

40. The method of claim 23 wherein the coating is at a first temperature and the condensing member is at a second temperature lower than the first temperature, and wherein the method further comprises the step of controlling the rate of forming condensate by controlling the temperature difference between the coating and the condensing member.

41. The method of claim 23 wherein the gap has a gap height, and wherein the method further comprises the step of controlling the rate of forming condensate by controlling the gap height.

42. The method of claim 23 wherein the substrate has a first substrate surface and a second substrate surface, wherein the coating is positioned on the first substrate surface, and wherein the condensing surface is adjacent the first substrate surface.

43. An article made using the method of claim 23 comprising one of an audio storage medium, video storage medium, and data storage medium.

44. An apparatus for drying a coating on a substrate, wherein the coating can be affected by a magnetic field, comprising:

a condensing member spaced from the substrate forming a gap between the substrate and a condensing surface of the condensing member;

means for forming a condensate on the condensing surface from the coating; and

at least one magnetic field generator located outside of the gap forming a magnetic field that is imposed upon the coating.

45. The apparatus of claim 44 wherein the magnetic field generator is located at least at one of a first location separated from the substrate by the condensing member and a second location separated from the condensing member by the substrate.

46. The apparatus of claim 44 wherein the magnetic field generator surrounds the substrate and the condensing member.

47. The apparatus of claim 44 wherein the magnetic field generator is located adjacent the condensing member.

48. The apparatus of claim 44 wherein the forming means comprises a heating member that heats the coating causing vapor to emanate from the coating.

49. The apparatus of claim 44 further comprising means for removing condensate from the condensing surface, wherein the removing means comprises at least one of a portion of the condensing surface being tilted, the condensing surface having capillary grooves, the condensing member comprising a foraminous material, a foraminous material adjacent the condensing surface, a wiper; and a pump.

50. The apparatus of claim 44 wherein at least a portion of the condensing surface is tilted around a web travel axis.

51. The apparatus of claim 44 wherein the condensing member comprises a belt and means for moving the belt past the coating.

52. The apparatus of claim 44 further comprising means for controlling the rate of forming condensate by controlling at least one of the height of the gap and a temperature difference between the coating and the condensing surface.

53. The apparatus of claim 44 wherein the condensing member comprises a plurality of condensing members, wherein the forming means comprises a plurality of heating members, wherein each heating member corresponds to a respective condensing member to form pairs of condensing members and heaters; and

means for independently controlling the pairs of condensing members and heaters.

54. An article made using the apparatus of claim 44, comprising one of an audio storage medium, video storage medium, and data storage medium.

55. An apparatus for drying a coating on a substrate, wherein the coating comprises particles that can be affected by a magnetic field, the apparatus comprising:

a condensing member spaced from the substrate along the path of the substrate forming a gap between the substrate and a condensing surface of the condensing member;

a heating member adjacent the condensing member for heating the coating causing vapor to emanate from the coating and condensate to form on the condensing surface; and

a magnetic field generator located outside the gap for imposing a magnetic field upon the particles in the coating.

56. An article made using the apparatus of claim 55 comprising one of an audio storage medium, video storage medium, and data storage medium.

57. A method for drying a coating on a substrate, wherein the coating comprises particles that can be affected by a magnetic field, the method comprising the steps of:

- locating a condensing member spaced from the substrate along the path of the substrate forming a gap between the substrate and a condensing surface of the condensing member;
- heating the coating causing vapor to emanate from the coating;
- condensing vapor emanating from the coating on the condensing surface; and
- creating a magnetic field from outside the gap and imposing the magnetic field upon the particles.

58. The method of claim 57 further comprising the step of converting the coating and substrate into one of an audio storage medium, video storage medium, and data storage medium following the condensing step.

59. A method for drying a coating on a substrate comprising the steps of:

- providing a substrate having a coating thereon, wherein the coating can be affected by a field imposed upon the coating, and wherein the coating has a coating temperature;
- providing a first drying member, wherein the first drying member has a first drying member temperature, wherein the first drying member temperature is less than the coating temperature;
- transporting the substrate adjacent the first drying member forming a gap between the first drying member and the substrate;
- providing a field generator outside the gap; and
- affecting the coating by imposing a field upon the coating with the field generator.

60. The method of claim 59, wherein the field is a magnetic field.

61. The method of claim 60, wherein the field generator comprises at least one of a magnet and a solenoid coil.

62. The method of claim 60, wherein the affecting step comprises orienting particles in the coating.

63. An article made using the method of claim 60, comprising at one of a magnetic audio storage medium, video storage medium, and data storage medium.

64. The method of claim 59, wherein the first drying member is a condensing member for condensing vapor emanating from the coating.

65. The method of claim 64, wherein the condensing member is a chilled plate.

66. The method of claim 59, wherein the first drying member has a shape corresponding to a portion of a path through which the substrate is transported.

67. The method of claim 64, further comprising the step of removing the condensate from the condensing structure.

68. The method of claim 67, wherein the removing step comprises the step of applying at least one of gravitational force, capillary force, and mechanical force to the condensate.

69. The method of claim 59, further comprising the steps of:

- heating the coating to cause vapor to emanate from the coating; and
- condensing vapor emanating from the coating on the first drying member.

70. The method of claim 69, wherein the heating step evaporates liquid in the coating.

71. The method of claim 59, further comprising the step of providing a second drying member for heating the coating to further facilitate drying of the coating.

72. The method of claim 71, wherein the field generator surrounds the substrate and the first and second drying members.

73. The method of claim 59, wherein the coating has a coating temperature, further comprising the step of providing a second drying member positioned relative to the first drying member such that the transporting step causes the substrate to be transported between the first and second drying members, wherein one of the first and second drying members is at a temperature higher than the coating temperature.

74. The method of claim 59, wherein the field is at least one of a magnetic field, curing field, decontaminating field, sterilizing field, light field, ultraviolet light field, electron beam field, corona field, and radiation field.

75. A method for affecting a coating on a substrate comprising the step of:

- providing a condensing member and a field generator along a process path;
- providing a substrate having a coating thereon that can be affected by a field generated by the field generator; and
- transporting the substrate through the process path such that the condensing member is between the field generator and the substrate, wherein the condensing member condenses vapor from the coating and the field generator generates a field that passes through the condensing member to the coating.

76. The method of claim 75 wherein the field generator generates at least one of a magnetic field, curing field, sterilizing field, decontaminating field, light field, ultraviolet light field, electron beam field, radiation field, and corona field.

77. The method of claim 75 wherein the field generator comprises a magnetic field generator.

78. The method of claim 77 wherein the coating comprises particles that can be affected by the magnetic field, and wherein the transporting step causes the magnetic field to orient the particles.

79. The method of claim 77 wherein the field generator comprises at least one of a magnet and a solenoid coil.

80. An article made using the method of claim 77 comprising at least one of a magnetic audio storage medium, video storage medium, and data storage medium.

81. The method of claim 75 wherein the condensing member comprises a chilled platen.

82. The method of claim 75 wherein the coating is at a coating temperature, and wherein the condensing member is at a lower temperature than the coating temperature.

83. The method of claim 82, further comprising the step of controlling the temperature of the condensing member.

84. The method of claim 75, further comprising the step of providing a heating member spaced from the condensing member, wherein the transporting step comprises transporting the substrate between the condensing member and the heating member causing vapor to emanate from the coating.

85. The method of claim 84 wherein the coating is at a coating temperature, wherein the condensing member is at a lower temperature than the coating temperature, and wherein the heating member is at a higher temperature than the coating temperature.

86. The method of claim 85, further comprising the steps of controlling the temperature of the condensing member and controlling the temperature of the heating member.

87. The method of claim 75, further comprising the step of removing condensate from the condensing member using at least one of gravitational force, capillary force, and mechanical force.

88. The method of claim 75, wherein the condensing member has a shape corresponding to a portion of a path through which the substrate is transported.

89. A method for affecting a coating on a substrate, wherein the coating comprises a liquid and particles that can be affected by a field, and wherein the method comprises the steps of:

providing a member spaced from the substrate forming a gap between the substrate and the member;

providing vapor to the gap;

controlling the temperature of the member creating a vapor concentration gradient that achieves one of removing liquid from the coating, preventing removal of liquid from the coating, and adding liquid to the coating; and

subjecting the coating to the field generated by a field generator positioned outside the gap.

90. The method of claim 89 wherein the member comprises a condensing member and the subjecting step comprises orienting the particles to a desired orientation, and wherein the controlling step comprises removing liquid from the coating increasing a viscosity of the coating such that the particles substantially remain in the desired orientation after the subjecting step.

91. The method of claim 89 wherein the field is at least one of a magnetic field, curing field, sterilizing field, decontaminating field, light field, ultraviolet light field, electron beam field, corona field, and radiation field.

92. A method for drying a coating on a first surface of a substrate, wherein the coating has particles that can be affected by a magnetic field, the method comprising the steps of:

providing a condensing member and a heating member spaced from the condensing member to form a substrate path;

providing a magnetic field generator adjacent the substrate path;

transporting the substrate through the substrate path such that the condensing member is adjacent and spaced from the first surface of the substrate forming a gap between the condensing member and the first surface and such that the heating member is adjacent the substrate;

heating the coating with the heating member forming a vapor in the gap from the coating;

condensing the vapor on the condensing member; and subjecting the coating to a magnetic field created outside the gap by the magnetic field generator, wherein the subjecting step comprises magnetically orienting the particles in the coating during at least a portion of the heating and condensing steps to hold the particles in a desired orientation while the coating is being dried.

93. The method of claim 92, wherein the condensing member comprises a chilled platen and the heating member is a heated platen, wherein the transporting step comprises transporting the substrate onto the heated platen.

94. A method for drying a coating on a substrate comprising the steps of:

providing a substrate having a coating thereon, wherein the coating can be affected by a field imposed upon the coating;

providing a first drying member, wherein the first drying member is configured to dry the coating by substantially other than heated air blown onto the coating;

transporting the substrate adjacent the first drying member forming a gap between the first drying member and the substrate;

providing a field generator outside the gap; and

affecting the coating by imposing a field upon the coating with the field generator.

95. The method of claim 94, wherein the first drying member comprises a chilled member.

96. A method for drying a coating on a substrate comprising the steps of:

providing a substrate having a coating thereon, wherein the coating can be affected by a field imposed upon the coating;

providing a first drying member, wherein the first drying member comprises a condenser;

transporting the substrate adjacent the first drying member forming a gap between the first drying member and the substrate;

providing a field generator outside the gap; and

affecting the coating by imposing a field upon the coating with the field generator.

97. The method of claim 96, wherein the condenser comprises a chilled plate.

* * * * *