



US00RE40495E

(19) **United States**
 (12) **Reissued Patent**
Svendsen

(10) **Patent Number:** **US RE40,495 E**
 (45) **Date of Reissued Patent:** **Sep. 9, 2008**

(54) **SUBSTRATE TREATED WITH A BINDER
 COMPRISING POSITIVE IONS**
 (75) Inventor: **Jeffrey S. Svendsen**, Dallas, TX (US)
 (73) Assignee: **Commun-I-Tec, Ltd.**, Dallas, TX (US)
 (21) Appl. No.: **11/075,404**
 (22) Filed: **Mar. 9, 2005**

5,141,803 A 8/1992 Pregozen
 5,213,588 A 5/1993 Wong et al.
 5,252,663 A 10/1993 Chandran et al.
 5,366,732 A * 11/1994 Zigelboim R 424/411
 5,421,898 A * 6/1995 Cavanagh 134/7
 5,435,935 A * 7/1995 Kupneski 252/156

(Continued)

FOREIGN PATENT DOCUMENTS

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **6,667,290**
 Issued: **Dec. 23, 2003**
 Appl. No.: **10/217,294**
 Filed: **Aug. 12, 2002**

U.S. Applications:

(60) Provisional application No. 60/323,573, filed on Sep. 19, 2001.

(51) **Int. Cl.**
C11D 1/62 (2006.01)

(52) **U.S. Cl.** **510/438**; 510/234; 510/237;
 510/238; 510/245; 510/254; 510/363; 510/365;
 510/382; 510/384; 510/391; 510/504

(58) **Field of Classification Search** 510/438,
 510/234, 237, 238, 245, 254, 363, 365, 382,
 510/384, 391, 504

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,702,780 A 2/1955 Lerner
 2,982,682 A 5/1961 Kine et al.
 3,283,357 A * 11/1966 Decker et al. 15/506
 3,786,615 A * 1/1974 Bauer 53/529
 4,002,171 A * 1/1977 Taft 604/364
 4,012,353 A * 3/1977 Chasin et al. 260/29.6
 4,111,922 A * 9/1978 Beede et al. 524/555
 4,151,148 A * 4/1979 Chasin et al. 260/29.6
 4,239,792 A 12/1980 Ludwa
 4,311,479 A * 1/1982 Fenn et al. 8/495
 4,401,712 A 8/1983 Morrison
 4,489,192 A 12/1984 Shih et al.
 4,540,505 A * 9/1985 Frazier 252/106
 4,601,938 A 7/1986 Deacon et al.
 4,666,621 A 5/1987 Clark et al.
 4,675,437 A 6/1987 Knofel et al.
 4,678,704 A * 7/1987 Fellows 442/121
 4,702,947 A * 10/1987 Pall et al. 428/36.4
 4,737,405 A * 4/1988 Bouchette 442/327
 4,740,398 A 4/1988 Bouchette
 4,753,844 A 6/1988 Jones et al.
 4,755,421 A 7/1988 Manning
 4,791,161 A 12/1988 Leising
 4,818,594 A 4/1989 Albien et al.
 4,837,079 A 6/1989 Quantrille et al.
 4,902,503 A 2/1990 Umemura et al.
 4,925,722 A 5/1990 Jeffers et al.
 4,929,498 A * 5/1990 Suskind et al. 442/123
 4,946,617 A * 8/1990 Sheridan et al. 15/104.93
 4,987,632 A 1/1991 Rowe et al.
 5,091,102 A * 2/1992 Sheridan 15/104.93
 5,094,770 A 3/1992 Sheridan et al.

EP 0136649 A2 4/1985
 EP 0141628 A1 5/1985
 EP 0118327 B1 4/1987
 EP 0318258 A2 5/1989
 EP 0412131 B1 2/1991
 EP 0778731 B1 6/1997
 EP 0791362 A3 8/1997
 EP 1059032 A1 12/2000
 EP 1065302 A1 1/2001
 EP 1086648 A1 3/2001
 EP 1167510 A1 1/2002
 EP 1268740 B1 1/2003
 EP 1661586 A1 5/2006
 JP 62-263211 11/1987
 WO WO90/05771 5/1990
 WO WO92/20228 11/1992
 WO WO01/23510 4/2001
 WO WO01/38480 5/2001
 WO WO01/49296 7/2001
 WO WO01/79410 A1 10/2001
 WO WO02/036339 A3 5/2002
 WO WO 02/48296 A2 * 6/2002
 WO WO 02/077048 A2 10/2002
 WO WO03/014284 A1 2/2003
 WO WO03/018732 A1 3/2003
 WO WO 03/048441 A1 6/2003
 WO WO 04/000373 A1 12/2003
 WO WO 04/064876 A2 8/2004
 WO WO 07/016579 2/2007

OTHER PUBLICATIONS

Advertising materials for Quix Plus food service towels, Chicopee and BettyMills.com, 2002 and 2004, with Chicopee Finish Formulation for MEF II Line Only, Jun. 15, 1999.

Rhoplex HA-8 Self-crosslinking Acrylic Emulsion for Textiles, *Textiles and Nonwovens*, Rolm and Haas Company, 1995.

PGI, Polymer Group Inc. letter by Dianne Ellis, dated Jan. 19, 2005.

Primary Examiner—Charles I Boyer

(74) *Attorney, Agent, or Firm*—Steven W. Smith

(57) **ABSTRACT**

An article for sanitizing a surface with a sanitizing solution while maintaining the concentration level of a sanitizer in the sanitizing solution at an effective concentration level. A substrate that absorbs and holds the sanitizing solution is treated with a sanitizer release polymer composition. The substrate may be a woven, nonwoven, or knit fabric, a foam or sponge, or the like. The sanitizer release polymer composition may include a cationic or nonionic surfactant or binder that is operable to maintain the concentration level of the sanitizer at the effective level during prolonged periods of use.

20 Claims, 1 Drawing Sheet


US RE40,495 E

Page 2

U.S. PATENT DOCUMENTS

5,475,903	A	12/1995	Collins et al.		6,936,580	B2	8/2005	Sherry et al.
5,700,742	A	12/1997	Payne		6,986,897	B1 *	1/2006	Roberts et al. 424/402
5,854,147	A	12/1998	Nohr et al.		7,160,846	B2	1/2007	Biering et al.
5,856,290	A *	1/1999	van Buskirk et al.	510/382	2002/0022050	A1	2/2002	Anderson et al.
5,962,001	A *	10/1999	Rose et al.	424/404	2002/0031486	A1 *	3/2002	Lunsmann et al. 424/70.28
5,965,514	A *	10/1999	Wierenga et al.	510/433	2002/0031966	A1	3/2002	Tomarchio et al.
5,968,204	A	10/1999	Wise		2002/0045667	A1	4/2002	Baker, Jr. et al.
5,980,922	A	11/1999	Mackey et al.		2002/0106399	A1	8/2002	Durden
6,001,381	A	12/1999	Gordon et al.		2002/0119207	A1	8/2002	Baker, Jr. et al.
6,013,615	A *	1/2000	Zhou et al.	510/434	2002/0146950	A1	10/2002	Reich
6,015,816	A	1/2000	Kostyniak et al.		2002/0183233	A1	12/2002	Mitra et al.
6,096,469	A *	8/2000	Anderson et al.	430/119	2003/0008591	A1	1/2003	Parsons et al.
6,113,815	A	9/2000	Elfersy et al.		2003/0017194	A1	1/2003	Joerger et al.
6,120,587	A	9/2000	Elfersy et al.		2003/0032352	A1 *	2/2003	Chang et al. 442/102
6,121,165	A	9/2000	Mackey et al.		2003/0060105	A1	3/2003	Puckhaber et al.
6,133,166	A	10/2000	Nissing et al.		2003/0100465	A1	5/2003	Kilkenny et al.
6,136,770	A *	10/2000	Cheung et al.	510/384	2003/0109405	A1	6/2003	Kellar et al.
6,180,584	B1 *	1/2001	Sawan et al.	510/382	2003/0109411	A1	6/2003	Kilkenny et al.
6,239,048	B1 *	5/2001	Wilson et al.	442/123	2003/0113364	A1	6/2003	McAtee et al.
6,270,878	B1	8/2001	Wegele et al.		2003/0125224	A1	7/2003	Seitz, Jr. et al.
6,288,076	B1	9/2001	Kostyniak et al.		2003/0148917	A1	8/2003	Mitra et al.
6,313,049	B1 *	11/2001	Heady et al.	442/123	2003/0176133	A1	9/2003	Walker et al.
6,322,665	B1	11/2001	Sun et al.		2003/0194932	A1	10/2003	Clark et al.
6,340,663	B1	1/2002	Deleo et al.		2003/0199415	A1	10/2003	Mondin
6,376,443	B1	4/2002	Julemont		2003/0211794	A1	11/2003	Shalaby
6,387,856	B1	5/2002	Ofosu-Asante et al.		2003/0216273	A1	11/2003	Mitra et al.
6,395,701	B1	5/2002	Connor et al.		2004/0040107	A1	3/2004	Bolkan et al.
6,399,560	B1	6/2002	Kwon et al.		2004/0043041	A1	3/2004	Baker, Jr. et al.
6,429,261	B1	8/2002	Lang et al.		2004/0062791	A1	4/2004	Branham et al.
6,559,189	B2	5/2003	Baker, Jr. et al.		2004/0072489	A1	4/2004	Wild et al.
6,596,657	B1	7/2003	Shalaby		2004/0106533	A1	6/2004	Mitra et al.
6,596,681	B1	7/2003	Mahieu et al.		2004/0121682	A1	6/2004	Quincy et al.
6,613,729	B1	9/2003	Cole et al.		2004/0137815	A1	7/2004	Ellis et al.
6,635,676	B2	10/2003	Baker, Jr. et al.		2004/0228904	A1	11/2004	Ellis et al.
6,673,761	B2 *	1/2004	Mitra et al.	510/384	2005/0239356	A1	10/2005	Parsons et al.
6,713,156	B1	3/2004	Pauls et al.		2006/0128242	A1	6/2006	Walker et al.
6,716,805	B1	4/2004	Sherry et al.		2006/0128248	A1	6/2006	Elis
6,780,799	B2 *	8/2004	Shalaby	442/123	2006/0166849	A1	7/2006	Kilkenny et al.
6,825,158	B2 *	11/2004	Mitra et al.	510/295	2007/0032151	A1	2/2007	Ellis
6,916,480	B2	7/2005	Anderson et al.					

* cited by examiner



SUBSTRATE TREATED WITH A BINDER COMPRISING POSITIVE IONS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

PRIORITY STATEMENT UNDER 35 U.S.C. §119
(e) & 37 C.F.R. §1.78

This nonprovisional application claims priority based upon the prior U.S. provisional patent application entitled, "Enhanced Sanitizer Release Polymer Composition," application No. 60/323,573, filed Sep. 19, 2001 in the name of Jeffrey Scott Svendsen.

BACKGROUND OF THE INVENTION

1. Technical Field of the Invention

This invention relates to treated substrates containing sanitizer release polymer compositions and, more particularly, to a sanitizing towel treated with an enhanced sanitizer release polymer composition for releasing cationic sanitizers.

2. Description of Related Art

In order to control microbial growth on a surface, a sanitizing solution containing antimicrobials such as sanitizers is applied to the surface with a substrate such as a woven or nonwoven fabric. A sanitizer is a compound that reduces microbial contaminants to safe levels as determined by government Public Health requirements. Currently, the safe level is a 99.999% reduction in the bacterial count.

For the process to be effective, the sanitizing solution must maintain a certain concentration of sanitizer. A serious problem occurs when the woven or nonwoven fabric reduces the concentration of sanitizer in the sanitizing solution. For example, a nonwoven fabric is repeatedly rinsed in a sanitizing solution contained in a bucket, while sanitizing the tabletop surfaces of a restaurant. If the nonwoven fabric is diluting or reducing the effectiveness of the sanitizer in the sanitizing solution, then the tabletop surfaces are not being disinfected. This can lead to an outbreak of pathogenic enteric bacteria, such as nearly all members of the genus *Salmonella* or *E. coli*. Pathogenic enteric bacteria can cause illness, or worse death.

In the field of sanitizers, guidelines exist for the minimum concentration of sanitizer in a sanitizing solution to avoid outbreaks of pathogenic enteric bacteria. The two most common sanitizers in sanitizing solutions are quaternary ammonium compound (QAC)-based or chlorine-based sanitizers. For example, by law, QAC-based sanitizer sanitizing solutions must maintain a concentration level of 200–400 parts per million to achieve the 99.999% reduction in the bacterial count.

Structurally, QACs contain four carbon atoms linked directly to one nitrogen atom through covalent bonds and four alkyl groups. The portion attached to the nitrogen atom by an electrovalent bond may be any anion, but it is usually chloride or bromide to form the salt. The nitrogen atom with the attached alkyl groups forms the positively charged cation portion. Depending on the nature of the R groups, the anion and the number of quaternary nitrogen atoms present, the antimicrobial quaternary ammonium compounds may be classified as monoalkyltrimethyl, monoalkyldimethylbenzyl, heteroaromatic, polysubstituted quaternary, bis-quaternary, or polymeric quaternary ammonium compounds.

A QAC is an ion, that is, a molecule that carries an electric charge. More specifically, a QAC is a cation, that is, an ion that possesses a positive charge. A nonionic molecule is an ion that possesses a neutral charge. An anion is an ion that possesses a negative charge. The charge of a molecule affects that molecule's intermolecular interactions. For example, a cation is attracted to an anion, and a cation repels another cation.

When QACs are applied directly to surfaces, their effect is not long-lasting due to leaching of the compound from the surface. Therefore, frequent applications may be needed to achieve prolonged antimicrobial effects.

The existing woven and nonwoven fabrics used in conjunction with sanitizing solutions to sanitize and disinfect surfaces reduce the concentration of sanitizer in the sanitizing solution rendering the sanitizing solution ineffective. Over a short period of time and under normal use, the existing fabrics reduce the concentration of sanitizer in the sanitizing solution to less than 200 parts per million. The surfaces of woven fabrics are treated with a surfactant to achieve the surface quality desired. A surfactant is a chemical additive that changes the surface attraction between two liquids, or between a liquid and a solid, by changing the surface energy of one or both components. Woven fabrics in common use today with sanitizing solutions are made with anionic surfactants. Nonwoven fabrics are constructed of loose strands of material that are bound together with binders. A binder is an adhesive, applied with a solvent or by melting a softenable plastic, to bond fibers together in a web or one web to another. Nonwoven fabrics in common use today with sanitizing solutions are made with anionic binders and surfactants.

The negative charge of the anionic binders and surfactants utilized in substrates today attracts and bonds the cationic QAC-based sanitizer to the fabric thereby reducing and neutralizing the concentration of sanitizer in the sanitizing solution. Moreover, woven fabrics comprise many interwoven strands of material, thereby creating a large irregular surface area that captures a large number of cationic QACs during use, thereby reducing the concentration of sanitizer in the sanitizing solution. Existing methods to solve this problem are to regularly replace the sanitizing solution or regularly replenish the concentration of sanitizer. However, these existing methods are not without limitations and disadvantages.

These existing methods are time consuming and expensive. Regularly monitoring and replacing or replenishing the sanitizing solution involves considerable employee time and the expense associated with replacing or replenishing the sanitizing solution. Additionally, during busy times in many restaurants, replacement or replenishment of the sanitizing solution is often forgotten, resulting in insufficient levels of microbial reduction.

Therefore, a need has arisen for a sanitizer release polymer composition that is capable of preventing today's fabrics from bonding to the sanitizer. Further, a need has arisen for a substrate that does not bond to or neutralize the sanitizer. The present invention provides such a composition and substrate.

SUMMARY OF THE INVENTION

In one aspect, the present invention is directed to an article for sanitizing a surface utilizing a sanitizing solution that includes a sanitizer at an effective concentration level. The article includes a substrate that absorbs and holds the sanitizing solution, and a composition covering at least a portion of

3

the substrate. The substrate may be, for example, a woven, nonwoven, or knit fabric, a foam or sponge, or other structure suitable for absorbing and holding a sanitizing solution while wiping off a surface. The substrate has a structure that enables a user to wipe the surface with the substrate, thereby applying the sanitizing solution to the surface. The composition is operable to maintain the concentration level of the sanitizer at the effective level.

In another aspect, the present invention is directed to a sanitizing towel utilized to sanitize one of a plurality of areas in a restaurant utilizing a sanitizing solution that includes a sanitizer at an effective concentration level. The sanitizing towel includes a substrate that absorbs and holds the sanitizing solution, and enables a user to apply the sanitizing solution to the surface. The substrate may be selected from the group consisting of woven fabrics, nonwoven fabrics, knit fabrics, and foams. A sanitizer release polymer composition covers at least a portion of the substrate, and is operable to maintain the concentration level of the sanitizer at the effective level. Preferably, the sanitizer release polymer composition comprises at least one cationic surfactant which, in the preferred embodiment, is present in the sanitizer release polymer composition in an amount of about 1 to about 10 weight percent, based on a total weight of the sanitizer release polymer composition. In an alternative embodiment, the sanitizer release polymer composition comprises at least one nonionic surfactant.

In yet another aspect, the present invention is directed to a method of treating a substrate utilized with a sanitizing solution to maintain a sanitizer in the sanitizing solution at an effective concentration level. The method includes the steps of selecting a substrate, selecting a cationic (or nonionic) surfactant for applying to the substrate, and applying the surfactant to the substrate. The surfactant may be a component in a sanitizer release polymer composition in which the surfactant is present in an amount of about 0.1 to about 99 weight percent, based on a total weight of the sanitizer release polymer composition. The composition may be applied to the substrate by diluting the composition with water or an organic solvent, and applying the diluted composition by dip coating, spray coating, or foam coating.

BRIEF DESCRIPTION OF THE DRAWING

The invention will be better understood and its numerous objects and advantages will become more apparent to those skilled in the art by reference to the following drawing, in conjunction with the accompanying specification, in which:

FIG. 1 is a flow chart outlining the steps of a process for manufacturing a treated substrate in accordance with the teachings of the present invention.

DETAILED DESCRIPTION OF EMBODIMENTS

Preferred embodiments of the invention will now be described with reference to various examples of how the invention can best be made and used.

The present invention provides substrate treated with an enhanced sanitizer release polymer composition. The substrate may be any suitable material that can be treated with the enhanced sanitizer release polymer composition, and that will absorb sanitizing solution for wiping and sanitizing surfaces. For example, the substrate may be a woven, nonwoven, or knit fabric, a foam or sponge-like material, or the like. The enhanced sanitizer release polymer composition contains at least one cationic or nonionic surfactant. Optionally, the enhanced sanitizer release polymer composition may contain a co-surfactant. Optionally, the enhanced

4

sanitizer release polymer composition may contain one or more additive agents that functionally and chemically improve the bonding of the cationic surfactant and optional co-surfactant(s) to a particular substrate. Optionally, the enhanced sanitizer release polymer composition may contain one or more fillers. In an alternative embodiment, the enhanced sanitizer release polymer composition contains only nonionic surfactants.

The purpose of any finish, such as a surfactant, is to improve the aesthetic, functional or processing properties of substrates. Surfactants are a class of materials broadly characterized as being made of molecules containing hydrophilic groups adequately separated from hydrophobic groups. The hydrophobic groups have an affinity for the fiber surface. The hydrophilic groups are attached predominantly to the aqueous medium. Existing substrates used in the field of sanitizers use anionic surfactants which have the negative effect of attracting the cationic QAC-based and cationic chlorine-based sanitizers thereby reducing the concentration of sanitizer in the sanitizing solution. The enhanced sanitizer release polymer composition of the present invention achieves its unexpectedly superior sanitizer release properties by preferably using a cationic surfactant that repels the cationic QAC-based and cationic chlorine-based sanitizers and prevents the sanitizer from bonding to the substrate. This enables the substrate to be used repeatedly with the sanitizing solution without significantly reducing the concentration of sanitizer in the sanitizing solution.

As noted, the enhanced sanitizer release polymer composition preferably contains at least one cationic surfactant, and may contain a co-surfactant. Suitable co-surfactants are selected from nonionic, anionic, amphoteric, zwitterionic, and semi-polar surfactants. A combination of cationic surfactants and co-surfactants may also be used. Preferably, the enhanced sanitizer release polymer composition are prepared with either cationic surfactants or a combination of cationic and nonionic surfactants. For nonwoven fabrics, the composition may include cationic binders or a combination of cationic and nonionic binders.

Suitable cationic surfactants include, for example:

- dieicosyldimethyl ammonium chloride;
- didocosyldimethyl ammonium chloride;
- dioctadecyldimethyl ammonium chloride;
- dioctadecyldimethyl ammonium methosulphate;
- ditetradecyldimethyl ammonium chloride and naturally occurring mixtures of above fatty groups, e.g. di(hydrogenated tallow)dimethyl ammonium chloride;
- di(hydrogenated tallow)dimethyl ammonium methosulphate;
- ditallow dimethyl ammonium chloride; and
- dioleyldimethyl ammonium chloride.

Cationic surfactants also include imidazolinium compounds, for example, 1-methyl-1-(tallowylamido)-ethyl-2-tallowyl-4,5-dihydroimidazolinium methosulphate and 1-methyl-1-(palmitoylamido)ethyl-2-octadecyl 4,5-dihydro-imidazolinium methosulphate. Other useful imidazolinium materials are 2-heptadecyl-1-methyl-1(2-stearoylamido)-ethyl-imidazolinium methosulphate and 2-lauryl-1-hydroxyethyl-1-oleyl-imidazolinium chloride.

Further examples of the cationic surfactant include:

- dialkyl (C₁₂-C₂₂)dimethylammonium chloride;
- alkyl(coconut)dimethylbenzylammonium chloride;
- octadecylamine acetate salt;
- tetradecylamine acetate salt;

5

tallow alkylpropylenediamine acetate salt;
 octadecyltrimethylammonium chloride;
 alkyl(tallow)trimethylammonium chloride;
 dodecyltrimethylammonium chlorid;
 alkyl(coconut)trimethylammonium chloride;
 hexadecyltrimethylammonium chloride;
 biphenyltrimethylammonium chloride, alkyl(tallow)-
 imidazoline quaternary salt;
 tetradecylmethylbenzylammonium chloride;
 octadecydimethylbenzylammonium chloride;
 dioleyidimethylammonium chloride;
 polyoxyethylene dodecylmonomethylammonium chlo-
 ride;
 polyoxyethylene alkyl(C₁₂-C₂₂)benzylammonium chlo-
 ride;
 polyoxyethylene laurylmonomethyl ammonium chloride;
 1-hydroxyethyl-2-alkyl(tallow)-imidazoline quaternary
 salt; and
 a silicone cationic surfactant having a siloxane group as a
 hydrophobic group, a fluorine-containing cationic sur-
 factant having a fluoroalkyl group as a hydrophobic
 group.

Anionic surfactants include, for example

from C₈ to C₂₀ alkylbenzenesulfonates;

from C₈ to C₂₀ alkanesulfonates;

from C₈ to C₂₀ alkylsulfates;

from C₈ to C₂₀ alkylsulfosuccinates; and

from C₈ to C₂₀ sulfated ethoxylated alkanols.

Nonionic surfactants include, for example, from C₆ to C₁₂
 alkylphenol ethoxylates, from C₈ to C₂₀ alkanol alkoxyates,
 and block copolymers of ethylene oxide and propylene
 oxide. Optionally, the end groups of polyalkylene oxides can
 be blocked, whereby the free OH groups of the polyalkylene
 oxides can be etherified, esterified, acetalized and/or ami-
 nated. Another modification consists of reacting the free OH
 groups of the polyalkylene oxides with isocyanates. The
 nonionic surfactants also include C₄ to C₁₈ alkyl glucosides
 as well as the alkoxyated products obtainable therefrom by
 alkoxylation, particularly those obtainable by reaction of
 alkyl glucosides with ethylene oxide.

Amphoteric surfactants contain both acidic and basic
 hydrophilic groups. Amphoteric surfactants are preferably
 derivatives of secondary and tertiary amines, derivatives of
 quaternary ammonium, quaternary phosphonium or tertiary
 sulfonium compounds. The cationic atom in the quaternary
 compound can be part of a heterocyclic ring. The amphoteric
 surfactant preferably contains at least one aliphatic group,
 containing about 3 to about 18 carbon atoms.

At least one cationic surfactant is present in the enhanced
 sanitizer release polymer composition in an amount of from
 about 0.1 to about 99 weight percent, preferably from 0.5 to
 50 weight percent, and more preferably from 1 to 10 weight
 percent, based on the total weight of the enhanced sanitizer
 release polymer composition. Preferable surfactants, such as
 the surfactants discussed above, can be obtained from
 Chicopee, Inc. of Dayton, New Jersey, a part of Polymer
 Group Inc. (PGI).

The composition of the additive agents, such as, for
 example, crosslinking or curing agents, that functionally and
 chemically improve the bonding of the cationic surfactant
 and optional co-surfactant to a particular substrate will
 depend on the composition and rheology of the substrate.

FIG. 1 is a flow chart outlining the steps of a process for
 manufacturing a treated substrate which may be utilized as,

6

for example, a restaurant sanitizing towel. At step 10, a suit-
 able cationic (or alternatively, a nonionic) surfactant is
 selected for use in the sanitizer release polymer composi-
 tion. At step 11, it is determined whether or not a
 co-surfactant is also to be utilized in the composition. If not,
 the process moves to step 13. However, if a co-surfactant is
 to be utilized, the process moves to step 12 where a suitable
 co-surfactant is selected from nonionic, anionic, amphoteric,
 zwitterionic, or semi-polar surfactants. At step 13, it is then
 determined whether or not an additive agent is also to be
 utilized in the composition. If not, the process moves to step
 15. However, if an additive agent is to be utilized, the pro-
 cess moves to step 14 where an additive agent such as, for
 example, a cross-linking or curing agent is selected.

At step 15, the concentration of the cationic surfactant is
 preferably adjusted in the composition to a range of 1 to 10
 weight percent, based on the total weight of the enhanced
 sanitizer release polymer composition. The process then
 moves to step 16 where the enhanced sanitizer release poly-
 mer composition is applied to the surface of the substrate. It
 should be understood by one skilled in the art that the bond-
 ing of the enhanced sanitizer release polymer composition to
 a substrate will depend on the composition and rheology of
 the substrate. The enhanced sanitizer release polymer com-
 position of the present invention may be applied to the sur-
 face of the substrate by any suitable method. For example,
 the enhanced sanitizer release polymer composition may be
 diluted with an organic solvent or water, and the resulting
 solution applied to the surface of the substrate by dip
 coating, spray coating or foam coating.

It should be understood by one skilled in the art that the
 bonding of the enhanced sanitizer release polymer composi-
 tion to a substrate will depend on the composition and rheol-
 ogy of the substrate. The enhanced sanitizer release polymer
 of the present invention can be applied to the surface of the
 substrate by any suitable method. For example, the enhanced
 sanitizer release polymer composition may be diluted with
 an organic solvent or water, and the resulting solution may
 be applied to the surface of the substrate to be treated by dip
 coating, spray coating, or foam coating.

Table 1 below summarizes test results obtained with a
 substrate treated with the enhanced sanitizer release polymer
 composition in accordance with the teachings of the present
 invention. The test results show the QAT concentration
 (ppm) of a sanitizing solution that was utilized with different
 substrates over a four-hour period. The results for each sub-
 strate are compared with the QAT concentration of a control
 solution that was not used during the test period.

TABLE 1

	Control	Invention	Generic 2 oz FST	Terry Cloth	Linen
After first Use	203	203	177	180	174
After 1 hour	202	197	159	147	130
After 2 hours	202	203	133	119	88
After 4 hours	203	203	124	91	62

It can be readily seen that the inventive substrate and com-
 position maintained the QAT concentration at the original
 level throughout the four-hour test period, matching the con-
 trol solution which was not used. Traditional substrates such
 as the generic 2-oz Food Service Towel (FST), the Terry
 cloth, and the linen all substantially reduced the QAT con-
 centration of the sanitizing solution during the test period.

It is thus believed that the composition of the present invention will be apparent from the foregoing description. Although the invention has been described with reference to certain exemplary arrangements, it is to be understood that the forms of the invention shown and described are to be treated as preferred embodiments. Various changes, substitutions and modifications can be realized without departing from the scope of the invention as defined in the following claims.

What is claimed is:

1. [An article for sanitizing a surface utilizing a sanitizing solution that includes a sanitizer comprising positively charged ions at an effective concentration level, said article comprising:

a substrate that absorbs and holds the sanitizing solution, said substrate having a structure that enables a user to wipe the surface with the substrate, thereby applying the sanitizing solution to the surface; and

an adhesive binder that binds together the structure of the substrate, said binder including positively or neutrally charged ions that provide the substrate with a predominantly positive or neutral charge that prevents the substrate from neutralizing the positively charged ions in the sanitizer when the sanitizer is subsequently applied to the substrate, thereby maintaining the concentration level of the sanitizer at the effective level.] *An article for sanitizing a surface utilizing a sanitizing solution that includes a sanitizer comprising positively charged ions at an effective concentration level, said article comprising:*

a plurality of substrate components; and

a cationic adhesive binder composition that binds together the substrate components into a substrate that absorbs and holds the sanitizing solution, said cationic binder providing the substrate with a predominantly positive charge that prevents the substrate from neutralizing the positively charged ions in the sanitizer when the sanitizer is subsequently applied to the substrate, thereby maintaining the concentration level of the sanitizer at the effective level.

2. [The article of claim 1 wherein the article is further treated with a cationic surfactant applied to the surface of the substrate.] *The article of claim 1 wherein the article is further treated with a cationic surfactant applied to the surface of the substrate.*

3. The article of claim 1 wherein the binder includes the positively or neutrally charged ions in an amount of about 0.1 to about 99 weight percent, based on a total weight of the binder.] *The article of claim 2 wherein the cationic surfactant includes positively charged ions in an amount of about 0.1 to about 99 weight percent, based on a total weight of the surfactant.*

4. [The article of claim 3 wherein the binder includes the positively or neutrally charged ions in an amount of about 0.5 to about 50 weight percent, based on a total weight of the binder.] *The article of claim 3 wherein the cationic surfactant includes positively charged ions in an amount of about 0.5 to about 50 weight percent, based on a total weight of the surfactant.*

5. [The article of claim 4 wherein the binder includes the positively or neutrally charged ions in an amount of about 1 to about 10 weight percent, based on a total weight of the binder.] *The article of claim 4 wherein the cationic surfactant includes positively charged ions in an amount of about 1 to about 10 weight percent, based on a total weight of the surfactant.*

6. [The article of claim 2 wherein the cationic surfactant is selected from the group consisting of:

dieicosyldimethyl ammonium chloride;
didocosyldimethyl ammonium chloride;

dioctadecyldimethyl ammonium chloride;
dioctadecyldimethyl ammonium methosulphate;
ditetradecyldimethyl ammonium chloride and naturally occurring mixtures of fatty groups;
di(hydrogenated tallow)dimethyl ammonium methosulphate;
ditallow dimethyl ammonium chloride; and
dioleyldimethyl ammonium chloride.] *The article of claim 2 wherein the cationic surfactant is selected from the group consisting of:*

dieicosyldimethyl ammonium chloride;
didocosyldimethyl ammonium chloride;
dioctadecyldimethyl ammonium chloride;
dioctadecyldimethyl ammonium methosulphate;
ditetradecyldimethyl ammonium chloride and naturally occurring mixtures of fatty groups;
di(hydrogenated tallow)dimethyl ammonium methosulphate;
ditallow dimethyl ammonium chloride; and
dioleyldimethyl ammonium chloride.

7. [The article of claim 2 wherein the article is also treated with a co-surfactant selected from the group consisting of:

a nonionic surfactant;
an anionic surfactant;
an amphoteric surfactant;
a zwitterionic surfactant; and

a semi-polar surfactant.] *The article of claim 2 wherein the article is also treated with a co-surfactant selected from the group consisting of:*

a nonionic surfactant;
an anionic surfactant;
an amphoteric surfactant;
a zwitterionic surfactant; and
a semi-polar surfactant.

8. [The article of claim 7 wherein the amphoteric surfactant is selected from the group consisting of:

derivatives of secondary and tertiary amines;
derivatives of quaternary ammonium;
quaternary phosphonium; and

tertiary sulfonium compounds.] *The article of claim 7 wherein the amphoteric surfactant is selected from the group consisting of:*

derivatives of secondary and tertiary amines;
derivatives of quaternary ammonium;
quaternary phosphonium; and
tertiary sulfonium compounds.

9. [The article of claim 2 wherein the cationic surfactant includes at least one additive agent that provides for improved bonding of the cationic surfactant to the substrate.] *The article of claim 2 wherein the cationic surfactant includes at least one additive agent that provides for improved bonding of the cationic surfactant to the substrate.*

10. [The article of claim 1 wherein the binder also includes at least one filler.] *The article of claim 2 wherein the cationic surfactant also includes at least one filler.*

11. [The article of claim 2 wherein the article is also treated with at least one nonionic co-surfactant selected from the group consisting of:

C₆ to C₁₂ alkylphenol ethoxylates;
C₈ to C₂₀ alkanol alkoxyates;
block copolymers of ethylene oxide and propylene oxide;

9

C₄ to C₁₈ alkyl glucosides; and alkoxyated products obtainable from C₄ to C₁₈ alkyl glucosides by alkoxylation.] *The article of claim 2 wherein the article is also treated with at least one nonionic co-surfactant selected from the group consisting of:*

C₆ to C₁₂ alkylphenol ethoxylates;

C₈ to C₂₀ alkanol alkoxyates;

block copolymers of ethylene oxide and propylene oxide;

C₄ to C₁₈ alkyl glucosides; and

alkoxyated products obtainable from C₄ to C₁₈ alkyl glucosides by alkoxylation.

12. [The article of claim 1 wherein the article is further treated with a nonionic surfactant applied to the surface of the substrate.] *The article of claim 1 wherein the article is further treated with a nonionic surfactant applied to the surface of the substrate.*

13. [The article of claim 12 wherein the nonionic surfactant is selected from the group consisting of:

C₈ to C₁₂ alkylphenol ethoxylates;

C₈ to C₂₀ alkanol alkoxyates;

block copolymers of ethylene oxide and propylene oxide;

C₄ to C₁₈ alkyl glucosides; and

alkoxyated products obtainable from C₄ to C₁₈ alkyl glucosides by alkoxylation.] *The article of claim 12 wherein the nonionic surfactant is selected from the group consisting of:*

C₈ to C₁₂ alkylphenol ethoxylates;

C₈ to C₂₀ alkanol alkoxyates;

block copolymers of ethylene oxide and propylene oxide;

C₄ to C₁₈ alkyl glucosides; and

alkoxyated products obtainable from C₄ to C₁₈ alkyl glucosides by alkoxylation.

14. [The article of claim 1 wherein the substrate is a nonwoven fabric comprising a multiplicity of strands of material that are bound together by the adhesive binder.] *The article of claim 1 wherein the substrate is a nonwoven fabric comprising a multiplicity of strands of material that are bound together by the adhesive cationic binder.*

15. [The article of claim 1 wherein the substrate is selected from the group consisting of woven fabrics, nonwoven fabrics, knit fabrics, and foams.] *The article of claim 1 wherein the substrate is selected from the group consisting of woven fabrics, nonwoven fabrics, knit fabrics, and foams.*

16. [The article of claim 15 wherein the article is a sanitizing towel utilized to sanitize one of a plurality of areas in a restaurant.] *The article of claim 15 wherein the article is a sanitizing towel utilized to sanitize one of a plurality of areas in a restaurant.*

17. [A method of manufacturing a substrate, said substrate being utilized with a sanitizing solution that includes a sanitizer comprising positively charged ions, said method comprising the steps of:

selecting an adhesive binder comprising predominantly positively or neutrally charged ions; and

applying the binder to a plurality of loose strands of material to bind the strands together into a web-like structure forming the substrate;

whereby, when the substrate is utilized with the sanitizing solution, the positively or neutrally charged ions in the binder prevent the substrate from neutralizing the positively charged ions in the sanitizer.] *A combination for sanitizing a surface, said combination comprising:*

a liquid sanitizing solution that includes a sanitizer comprising positively charged ions at an effective concentration level; and

10

a substrate that absorbs and holds the sanitizing solution, said substrate comprising:

a plurality of substrate components; and

a cationic adhesive binder composition that binds together the substrate components to form the substrate, said cationic binder composition providing the substrate with a predominantly positive charge that prevents the substrate from neutralizing the positively charged ions in the sanitizer when the sanitizer is subsequently applied to the substrate, thereby maintaining the concentration level of the positively charged ions in the sanitizer at the effective level.

18. [The method of claim 17 wherein the step of selecting a substrate includes selecting a substrate from the group consisting of woven fabrics, nonwoven fabrics, knit fabrics, and foams.] *The combination of claim 17 wherein the sanitizer in the sanitizing solution is a quaternary ammonium compound (QAC)-based sanitizer.*

19. [The method of claim 17 further comprising applying a cationic surfactant to the surface of the substrate, said cationic surfactant being selected from the group consisting of:

dieicosyldimethyl ammonium chloride;

didocosyldimethyl ammonium chloride;

dioctadecyldimethyl ammonium chloride;

dioctadecyldimethyl ammonium methosulphate;

ditetradecyldimethyl ammonium chloride and naturally occurring mixtures of fatty groups;

di(hydrogenated tallow)dimethyl ammonium methosulphate;

ditallow dimethyl ammonium chloride; and

dioleyldimethyl ammonium chloride.] *The combination of claim 17, wherein the substrate is further treated with a cationic surfactant applied to the surface of the substrate.*

20. [The method of claim 19 wherein the step of applying the cationic surfactant to the surface of the substrate includes the steps of:

mixing a composition in which the cationic surfactant is present in an amount of about 0.1 to about 99 weight percent, based on a total weight of the composition; and

applying the composition to the substrate.] *A method of manufacturing an article for sanitizing surfaces, said article being utilized with a sanitizing solution that includes a sanitizer comprising positively charged ions, said method comprising the steps of:*

selecting a plurality of substrate components;

selecting a cationic adhesive binder composition; and

utilizing the cationic adhesive binder composition to bind together the substrate components into a substrate for absorbing and holding the sanitizing solution, said cationic binder composition providing the substrate with a predominantly positive charge;

whereby, when the article is subsequently utilized with the sanitizing solution, the positively charged substrate prevents the article from neutralizing the positively charged ions in the sanitizer.

[21. The method of claim 20 wherein the step of mixing a composition includes mixing a composition in which the cationic surfactant is present in an amount of about 1 to about 10 weight percent, based on a total weight of the composition.]

[22. The method of claim 20 wherein the step of applying the composition to the substrate includes the steps of:

diluting the composition with an organic solvent; and

dip coating the substrate in the diluted composition.]

11

[23. The method of claim 20 wherein the step of applying the composition to the substrate includes the steps of:

diluting the composition with an organic solvent; and

spray coating the substrate with the diluted composition.]

[24. The method of claim 20 wherein the step of applying the composition to the substrate includes the steps of:

diluting the composition with an organic solvent; and

foam coating the substrate with the diluted composition.]

[25. The method of claim 20 wherein the step of applying the composition to the substrate includes the steps of:

diluting the composition with water; and

dip coating the substrate in the diluted composition.]

[26. The method of claim 20 wherein the step of applying the composition to the substrate includes the steps of:

diluting the composition with water; and

spray coating the substrate with the diluted composition.]

[27. The method of claim 20 wherein the step of applying the composition to the substrate includes the step of:

diluting the composition with water; and

foam coating the substrate with the diluted composition.]

[28. The method of claim 20 further comprising the steps of:

selecting a nonionic co-surfactant for use with the cationic surfactant in the composition; and

mixing the nonionic co-surfactant with the cationic surfactant to form the composition.]

[29. The method of claim 20 further comprising the steps of:

selecting an additive agent for use with the cationic surfactant in the composition, said additive agent being operable to improve bonding of the cationic surfactant to the substrate; and

mixing the additive agent with the cationic surfactant to form the composition.]

[30. A combination for sanitizing a surface, said combination comprising:

a liquid sanitizing solution that includes a sanitizer comprising positively charged ions at an effective concentration level;

a substrate that absorbs and holds the sanitizing solution, said substrate having a structure that enables a user to wipe the surface with the substrate, thereby applying the sanitizing solution to the surface; and

12

an adhesive binder that binds together the structure of the substrate, said binder including positively or neutrally charged ions that provide the substrate with a predominantly positive or neutral charge that prevents the substrate from neutralizing the positively charged ions in the sanitizer when the sanitizer is subsequently applied to the substrate, thereby maintaining the concentration level of the sanitizer at the effective level.]

[31. The combination of claim 30 wherein the sanitizer in the sanitizing solution is a quaternary ammonium compound (QAC)-based sanitizer.]

[32. A combination for sanitizing a surface, said combination comprising:

a liquid sanitizing solution that includes a sanitizer comprising positively charged ions at an effective concentration level; and

a cationic or nonionic substrate that absorbs and holds the sanitizing solution, said substrate having a structure that enables a user to wipe the surface with the substrate, thereby applying the sanitizing solution to the surface, said substrate having a cationic surfactant bonded to the surface of the substrate during manufacturing to provide the substrate with a predominantly positive or neutral charge, thereby preventing the substrate from neutralizing the positively charged ions in the sanitizer when the sanitizer is subsequently applied to the substrate.]

[33. A method of manufacturing an article for sanitizing surfaces, said article being utilized with a sanitizing solution that includes a sanitizer comprising positively charged ions, said method comprising the steps of:

selecting a substrate for the article having a structure suitable for absorbing and holding the sanitizing solution during use;

selecting a cationic surfactant comprising predominantly positively charged ions; and

bonding the cationic surfactant to the surface of the substrate to provide the substrate with a predominantly positive or neutral charge;

whereby, when the article is subsequently utilized with the sanitizing solution, the positively or neutrally charged substrate prevents the article from neutralizing the positively charged ions in the sanitizer.]

* * * * *