

US00RE44036E

(19) **United States**
(12) **Reissued Patent**
McCord

(10) **Patent Number:** **US RE44,036 E**
(45) **Date of Reissued Patent:** **Mar. 5, 2013**

(54) **LEAD FREE BARIUM SULFATE
ELECTRICAL INSULATOR AND METHOD
OF MANUFACTURE**
(76) Inventor: **Stuart J. McCord**, Westford, MA (US)
(21) Appl. No.: **13/332,667**
(22) Filed: **Dec. 21, 2011**

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **7,638,783**
Issued: **Dec. 29, 2009**
Appl. No.: **11/595,786**
Filed: **Nov. 10, 2006**

U.S. Applications:

(63) Continuation-in-part of application No. 10/850,931,
filed on May 22, 2004, now abandoned.

(51) **Int. Cl.**
G21F 3/00 (2006.01)
G21F 1/10 (2006.01)
(52) **U.S. Cl.** **250/515.1**; 250/492.21; 250/492.3;
378/203; 252/478
(58) **Field of Classification Search** 250/515.1,
250/492.21, 492.3; 378/203; 252/478
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,118,413 A * 5/1938 Mesick, Jr. et al. 378/121
3,328,338 A * 6/1967 Parish 523/457
3,473,028 A * 10/1969 Curry 378/193
4,157,476 A * 6/1979 O'Connor 378/203
4,485,838 A * 12/1984 Shoji et al. 164/462
4,619,963 A * 10/1986 Shoji et al. 524/439
4,938,233 A * 7/1990 Orrison, Jr. 128/849
4,957,943 A * 9/1990 McAllister et al. 521/64

5,190,990 A * 3/1993 Eichmiller 523/137
5,360,666 A * 11/1994 Eichmiller 428/327
5,443,775 A * 8/1995 Brannon 264/143
5,548,125 A * 8/1996 Sandbank 250/519.1
5,665,808 A * 9/1997 Bilsbury et al. 524/439
5,719,352 A * 2/1998 Griffin 102/517
5,730,664 A * 3/1998 Asakura et al. 473/373
6,048,379 A * 4/2000 Bray et al. 75/229
6,166,390 A * 12/2000 Quapp et al. 250/506.1
6,310,355 B1 * 10/2001 Cadwalader 250/515.1
6,487,273 B1 * 11/2002 Takenaka et al. 378/142
6,548,570 B1 * 4/2003 Lange 523/137
6,644,853 B1 * 11/2003 Kantor et al. 378/203
6,674,838 B1 * 1/2004 Barrett 378/125
6,722,665 B1 * 4/2004 Burkhart et al. 277/637
6,740,260 B2 * 5/2004 McCord 252/511
7,079,624 B1 * 7/2006 Miller et al. 378/119
7,638,783 B2 * 12/2009 McCord 250/515.1
8,022,116 B2 * 9/2011 Coppens et al. 523/136
8,263,952 B1 * 9/2012 McCord 250/492.21
8,308,986 B1 * 11/2012 Stuart 252/478
2003/0168637 A1 * 9/2003 McCord 252/500


* cited by examiner

Primary Examiner — Jack Berman
(74) *Attorney, Agent, or Firm* — Marian J. Furst

(57) **ABSTRACT**

A high voltage insulator and radiation shield made of barium sulfate composite having a polymer matrix and barium sulfate therein. The device may be made by casting. By means of use of various combinations of barium sulfate, other radiologically resistant materials, polymers, and third components, the physical, radiological and electrical properties of the finished products may be tailored to achieve desired properties. In addition, the invention teaches that radiation shielding, insulators, and combined radiation shield/insulators may be fashioned from the composite. A wide range of production methods may be employed, including but not limited to liquid resin casting.

14 Claims, 2 Drawing Sheets







Fig. 1

Fig. 2



**LEAD FREE BARIUM SULFATE
ELECTRICAL INSULATOR AND METHOD
OF MANUFACTURE**

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

CROSS-REFERENCE TO RELATED
APPLICATIONS

The application is a continuation-in-part of U.S. utility patent application No. 10/850,931 filed May 22, 2004 now abandoned in the name of the same inventor, Stuart McCord, and entitled LEAD FREE BARIUM SULFATE COMPOSITE, and claims the priority and benefit of that earlier application and all related applications, the entire disclosures of which are incorporated herein by this reference.

FIELD OF THE INVENTION

This invention relates to generally to X-ray and Ion beam electrical insulators and particularly to polymer-metal-precursor composite insulators in which the metal-precursor component is barium sulfate.

BACKGROUND OF THE INVENTION

X-ray and gamma ray sources are presently being used in a wide array of medical and industrial machinery, and the breadth of such use expands from year to year. [Consumer] Consumers tend to notice medical and dental X-ray machines, but in addition to these applications there are baggage screening machines, CAT scan machines, non-destructive industrial inspection machinery and ion implantation machines used in the manufacture of silicon wafer computer chips. All require that high voltage generated within the device be contained, and furthermore that radiation be contained and directed. In particular, the ion implantation machinery increased in the 1980's and 1990's with the silicon chip boom.

In the past, lead itself or lead-polymer composites were used to make electrical insulator items. But there are numerous problems with the use of lead. One problem with lead is that it is toxic and thus subject to increasingly stringent legal controls. Another issue is that lead may not have the mechanical or electrical properties desired for a given application. Lead has been used in various forms in wide range of applications: machined, as a solid casting, as a solid encased within a matrix such as a polymer matrix, or as a filler. As a filler, it may be lead particles, tribasic lead-sulfate or lead-oxide particles or particles of a specified shape or size, or as a mixture with other materials such as tin. Tungsten shielding, or polymer-tungsten shielding has also been used. Examples of all of these methods may be found in the prior art.

In general, polymer-metal composites are materials having a polymer matrix containing particles of a metal compound intermixed therein. The polymer may advantageously have plastic properties allowing for ease of manufacture, but a wide variety of polymers are known for use in such composites. In the prior art, lead has been a particularly favored material for its density and ease of working. Tungsten has been favored more recently, despite cost concerns. Three

characteristics in particular which make such materials desirable are electrical non-conductivity, radiological shielding ability, and high density.

There is a growing list of applications for which polymer-metal composite materials are either required or advantageous. Ion implantation machine source insulators, X-ray tube insulation, radioisotope housings, other castings and housings could benefit from the properties of polymer-metal composite materials. In the case of typical high voltage insulators for ion implantation machinery, a thick walled generally round or cylindrical part is created out of lead or polymer-lead-oxide ranging from an inch to several feet or more in long dimension and weighing anywhere up to 500 pounds. Wall thickness may range from 1/2 inch to several inches. Such parts must resist high voltages, shield against x-ray or gamma ray emission and hold a high vacuum state when connected to the vacuum chamber. High voltage X-ray shielding for X-ray tube insulators is generally thinner (often 0.070 inch thickness), generally smaller, and of different shape, having an aperture for the X-ray beam, but once again must offer high voltage insulation and radiation protection. The lead in such devices obviously presents an environmental challenge to manufacture, use and disposal.

In the processing of lead precursor filled plastics known in the art, specialized facilities, handling procedures, training and safety equipment must be used to protect the employees from the lead precursor they handle. Lead-based dust is a particular concern, being airborne and inhalable. Such dust may be generated during mixing, molding, deflashing, machining and finishing of final products such as insulators or shields, to say nothing of earlier stages of mining, smelting and refining of lead and the final disposal of the used product at the end of its useful life. Even during the life span of the product, it is illegal to sand, machine, alter or use the product in any way that will generate dust. All such processes must be carried out at special lead handling sites, and all waste dust from any of these processes must be collected in accordance with OSHA regulations and transported to hazardous waste land fills in accordance with OSHA and DES guidelines.

Various radio-opaque agents are known which are used for diverse applications. Importantly, however, certain families of compounds are disfavored as having many of the same issues as lead and lead oxides. For example, the barium family of compounds are almost without exception subject to regulation due to their toxic nature. It is not previously known to use such barium family compounds in amounts greater than 10% by volume, since the structures in which they are emplaced are radio-opaque, not radiation barriers.

Internalized by law into the manufacturing process, such safety issues dramatically increase the cost of such products, which in turn increases other medical or industrial costs.

One recent invention to deal with this issue is TUNGSTEN-PRECURSOR COMPOSITE, for which application Ser. No. 10/095,350 filed Mar. 9, 2002 in the name of the same inventor, Stuart J. McCord [was filed and has been allowed], issued on May 25, 2004 as U.S. Pat. No. 6,740,260 B2. This invention addresses material and cost concerns of tungsten shielding by proposing the use of tungsten precursor materials which testing reveals to have favorable properties. However, an entire range of desirable properties is not attainable with a single family of compounds, and so additional compounds may be desirable in order to expand the range of properties which may be attained in a lead-free shield device. Cost, of course, is one issue. Availability is another, as are actual material properties. During prosecution of that patent, U.S. Pat. No. 5,548,125 issued to Sandback (RADIATION PROTECTIVE GLOVE) and U.S. Pat. No. 4,957,943 issued

to McAllister et al. (PARTICLE-FILLED MICROPOROUS MATERIALS) were cited by the examiner prior to allowance. However, the glove patent, for example, teaches a flexible material most likely to be extruded.

Other prior art cited includes U.S. Pat. No. 3,473,028 issued to Curry for X-RAY TUBE HOUSEING CONSISTING OF A DIELECTRIC MATERIAL WITH AN ELECTRICALLY CONDUCTIVE LINER, issued Oct. 14, 1969. The device disclosed is neither annular nor composed of truncated cone shapes. Much more importantly, it teaches towards use of a specific dielectric material and thus teaches away from the material of the invention, and for that reason may not be combined with prior art showing the materials of the present invention.

U.S. Pat. No. 5,443,775 to Brannon on Aug. 22, 1995 for PROCESS FOR PREPARING PIGMENTED THERMOPLASTIC POLYMER COMPOSITIONS AND LOW SHRINKING THERMOSETTING RESIN MOLDING COMPOSITION is directed towards making of desirable colors and refractive properties in polymer products and is thus not relevant prior art for the present invention.

U.S. Pat. No. 4,938,233 issued to Orrison, Jr. for RADIATION SHIELD on Jul. 3, 1990 teaches a flexible radiation shield not manufacturable by casting and not having thick walls suitable for high voltage insulation. Since the device teaches flexibility, it teaches away from thick walls and thus cannot be combined with a device having useful high voltage insulation properties (i.e. having thick walls).

U.S. Pat. No. 7,079,624 to Miller et al for X-RAY TUBE AND METHOD OF MANUFACTURE, granted Jul. 18, 2006, teaches a device having an entirely different configuration, and teaches away from barium sulfate in a polymer matrix.

Another attempt to deal with the issue of environmental lead contamination may be found in U.S. Pat. No. 6,048,379 issued Apr. 11, 2000 to Bray et al for "HIGH DENSITY COMPOSITE MATERIAL". This patent teaches the use of tungsten powder, a binder and a polymer to provide a composite material offering a density high enough for use as ammunition. As stated, a serious issue with the use of tungsten is that of cost. Tungsten metal is quite expensive in comparison to lead. For example, tungsten-composite materials may cost as much as \$20 per pound.

U.S. Pat. Nos. 5,730,664, 5,719,352, and 5,665,808, respectively issued to Asakura, Griffin, Bilsbury all disclose metal-polymer composites for projectiles, respectively golf balls and shot pellets. Other patents from the same art (projectiles) also propose non-toxic materials.

In the actual radiation shielding art itself, various patents propose polymer-metal composites of various forms.

EcoMASS (a registered trademark of the PolyOne Corporation) is a combination of tungsten metal and nylon and elastomer compounds used for shielding, apparently based upon the Bray '379 patent related to ammunition and thus developed specifically in response to military/sporting needs for non-toxic ammunition. It does not teach that materials other than tungsten may be used, thus limiting the range of characteristics of the final product. For example, tungsten is electrically conductive and thus is not normally suitable for insulators. As mentioned earlier, this material also faces cost limitations. In addition, this material has manufacturing limitations in terms of thickness and size of the final item.

U.S. Pat. No. 4,619,963 issued Oct. 28, 1986 to Shoji et al for "RADIATION SHIELDING COMPOSITE SHEET MATERIAL" teaches a lead-tin fiber and resin shield, as does

U.S. Pat. No. 4,485,838 issued Dec. 4, 1984 to the same inventors. Obviously the lead inclusion leads to toxicity and thus regulation questions.

U.S. Pat. No. 6,310,355 issued Oct. 30, 2001 to Cadwalader for "LIGHTWEIGHT RADIATION SHIELD SYSTEM" teaches a flexible matrix having a radiation attenuating material and at least one void.

U.S. Pat. No. 6,166,390 issued Dec. 26, 2000 to Quapp et al for "RADIATION SHIELDING COMPOSITION" teaches a concrete composite material.

U.S. Pat. No. 5,360,666 issued Nov. 1, 1994 and U.S. Pat. No. 5,190,990 issued Mar. 2, 1993 to Eichmiller for "DEVICE AND METHOD FOR SHIELDING HEALTHY TISSUE DURING RADIATION THERAPY" teach a radiation shield for the human body comprising an elastomeric material and certain mixtures (see the summary of the invention) of various metals in the form of spherical particles.

Various metals might be explored for lead replacement. In such cases, it is natural enough to skip metals having families which are generally considered toxic or too expensive, and to skip those generally used in radio-opaque applications rather than radiological blocking applications. Thus, it would be natural to skip the barium family of compounds, since these are highly regulated.

It would be preferable to explore the use of other materials which are non-toxic and thus considerably safer than lead or certain available alternatives.

SUMMARY OF THE INVENTION

General Summary

The present invention teaches a novel lead-free plastic material that may act as a replacement for lead or lead oxide filled plastics, particularly in the role of electrical insulators in radiation devices. The present invention teaches a polymer-barium sulfate composite comprising a plastic matrix having barium sulfate materials within it as "filler" at an increased percentage of the total volume. The properties of barium sulfate are favorable and unexpected for a number of reasons. The use as an electrical insulator and materials for rigid radiation shields is unexpected due to the fact that most other members of the family are toxic and thus subject to environmental regulation, thus reducing or eliminating the key reason for lead replacement in any case. It is further unexpected in that barium sulfate is normally used in "radio-opaque" applications such as medical X-ray procedures, and it not normally considered a suitable material for actual higher density electrical insulators of radiation shielding and similar applications.

The new material allows a wider range of function and use when compared with previous methods using a single metal, lead, or a lead and polymer composite.

The present invention further teaches the use of binders, fibers, and secondary fillers in the polymer-barium sulfate composite in order to further broaden the range of achievable desirable physical, radiological and/or electrical properties.

The present invention importantly teaches casting of the device as a process of manufacture.

Summary in Reference to Claims

It is a first aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure comprising:

- a first truncated cone section and a second truncated cone section;
- the two truncated cone sections secured together at their respective bases by an overlap joint;

5

an interior space defined by the two truncated cones sections;
 the first and second truncated cone sections having walls, the walls made of a material comprising:
 a) a polymer matrix and
 b) barium sulfate within the polymer matrix in an approximate amount of at least 10% by volume;
 a first transmission port passing through at least one wall;
and
 a second electrical port passing through at least one [walls] wall.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure further comprising an X-ray tube disposed within the hollow body.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure, further comprising at least one oil port passing through the walls.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure wherein the polymer matrix comprises at least one member selected from the following group: epoxy, polyester, polyurethane, silicone rubber, bismaleimides, polyimides, vinyl esters, urethane hybrids, polyurea elastomer, phenolics, cyanates, cellulose, fluoro-polymer, ethylene inter-polymer alloy elastomer, ethylene vinyl acetate, nylon, polyetherimide, polyester elastomer, polyester sulfone, polyphenyl amide, polypropylene, polyvinylidene fluoride, acrylic, homopolymers, acetates, copolymers, acrylonitrile-butadienestyrene] *butadienestyrene*, fluoropolymers, ionomers, polyamides, polyamideimides, polyacrylates, polyether ketones, polyaryl-sulfones, polybenzimidazoles, polycarbonates, polybutylene, terephthalates, polyether sulfones, thermoplastic polyimides, thermoplastic polyurethanes, polyphenylene sulfides, polyethylene, polypropylene, polysulfones, polyvinylchlorides, [styrene] *styrene* acrylonitriles, polystyrenes, polyphenylene, ether blends, styrene maleic anhydrides, allyls, aminos, polyphenylene oxide, and combinations thereof.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure wherein the polymer matrix comprises epoxy resin in an approximate amount of 50% to 70% by volume.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure further comprising:

c) a third material.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure wherein the third material comprises at least one member selected from the following group: electrically insulating materials, binders, high density materials and combinations thereof.

It is another aspect, advantage, objective and embodiment of the invention to provide a high voltage insulating radiation enclosure wherein the third material comprises at least one member selected from the following group: tungsten, lead, platinum, gold, silver, tantalum, calcium carbonate, hydrated alumina, tabular alumina, silica, glass beads, glass fibers, magnesium oxide/sulfate, wollastonite, stainless steel fibers, copper, carbonyl iron, iron, molybdenum, nickel and combinations thereof.

It is another aspect, advantage, objective and embodiment of the invention to provide an electrical insulator for an ion source, the insulator comprising:

6

a generally annular body having a diameter of at least 6 inches;
 the body having at least one vacuum sealing surface dimensioned and configured to
 provide a tight seal;
 at least one alignment pin projecting from the vacuum sealing surface of the insulator;
 at least one metal insert secured to the body;
 the body made of a material comprising:
 a. a polymer matrix and
 b. barium sulfate within the polymer matrix in an approximate amount of at least 35% by volume.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties, the method comprising:

- a) mixing uncured liquid polymers with desired percentages of powdered barium sulfate;
- b) blending the mixture in high shear vacuum mixers for a first predetermined time;
- c) placing the material into a mold having a generally annular body cavity having a diameter of at least 6 inches, the body cavity having at least one vacuum sealing surface;
- d) placing the material into an autoclave;
- e) curing it at a first temperature and first pressure for a first time.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the step a) further comprises use of epoxy polymers.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties further comprising at step a) mixing powdered hydrated alumina.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the step of mixing further comprises use of a single blade mixer.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the step of placing the mixture into a mold further comprises vacuum casting the mixture in the mold.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the step of placing the mixture into a mold further comprises pouring the mixture into the mold.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the step of placing the mixture into a mold further comprises injecting the mixture into the mold.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the first temperature comprises a range from at least 70 degrees F. to 400 degrees F.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high voltage insulator having radiation shielding properties wherein the first time comprises a range from at least two hours to 24 hours.

It is another aspect, advantage, objective and embodiment of the invention to provide a method of producing a high

voltage insulator having radiation shielding properties wherein the first pressure comprises at least 50 to 250 psi.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of a first embodiment of an ion source insulator according to the present invention.

FIG. 2 is a cross-sectional perspective view of an X-ray box made with the material of the present invention.

DETAILED DESCRIPTION

The present invention teaches novel lead-free electrical insulators of a cast plastic material that may act as replacements for lead or lead oxide filled plastics, particularly in radiation [device] devices. The presently preferred embodiment and best mode presently contemplated of the invention teaches a high voltage electrical insulator for ion implanter machines and a high voltage insulator for X-ray tube enclosures, both made of a cast polymer-barium sulfate composite comprising a high density plastic matrix having barium sulfate materials within it as filler. It is not presently known to use such barium family compounds in amounts greater than 10% by volume, since the structures in which they are emplaced in prior art are flexible and radio-opaque, not cast insulators with radiation shielding properties.

Barium sulfate is a white, soluble and somewhat heavy compound normally used in paper manufacture. It is also administered prior to X-ray of patients, either as a liquid or for marking of items inserted into the patient: in either case, [it's] its radio-opaque properties are used for internal navigation and diagnosis of [patient's] patients after the relatively low radiation exposure of such patients.

By teaching the use of barium sulfate, the range of materials which may be used instead of the single metal lead is increased and thus the breadth of the properties which may be achieved is increased, another benefit of the invention. In particular, when compared to lead-composites:

- a. Barium sulfate consists of a combination of the barium atom, a sulfur atom, and four oxygen atoms, having properties such as a high electrical resistance, an average atomic weight of approximately 233.4, a density of roughly 4.25-4.5 grams/centimeter cubed and thus the reasonably good radiation shielding properties that are partially dependent thereon. While it does not actually meet lead oxide in terms of radiation shielding ability, it can be used in applications previously having a lower percentage of lead oxide, for example, an application having a 14% (v/v) lead component could be replaced by a component having a 35% to 45% barium sulfate component.
- b. Barium sulfate offers commercial advantages over tungsten metal and even over lead oxide. While a tungsten-composite may cost \$20[\$] per pound to manufacture, and even lead oxide is roughly \$1.00/lb, barium sulfate is roughly \$0.30/lb at current prices, thus offering a similar or lower price. In addition, handling and manufacturing costs may be lower due to differing environmental requirements.
- c. Barium sulfate [offer] offers environmental advantages over lead composites. While lead causes adverse consequences after ingestion, barium sulfate does not. While lead is subject to very stringent regulations as laid out in the BACKGROUND OF THE INVENTION, barium sulfate is not.
- d. Barium sulfate is an unexpected choice in lead replacement applications, due to the fact that barium sulfate is

the only commonly available form of barium which is not itself an environmental hazard. Thus, replacing lead in a metal-composite application with barium carbonates, nitrates, oxides, etc, would appear to be pointless in terms of avoiding hazardous material regulations, as these substances are subject to such regulation. Barium sulfate itself is relatively harmless, even being used for the infamous "barium milkshake" given to patients suffering ulcers or other gastrointestinal disorders. The barium liquid coats the interior of the GI tract and thus provides contrast during an X-ray examination of the patient.

The present invention may be manufactured by casting with thermosetting materials and/or thermoplastic materials. In general, higher filler loadings may be advantageously employed.

The polymers, plastics and resins which may be advantageously employed in the present invention are too numerous for a complete list, however, a partial and exemplary list includes epoxy, polyester, polyurethane, silicone rubber, bis-maleimides, polyimides, vinylesters, urethane hybrids, polyurea elastomer, phenolics, cyanates, cellulose, fluoro-polymer, ethylene inter-polymer alloy elastomer, ethylene vinyl acetate, nylon, polyetherimide, polyester elastomer, polyester sulfone, polyphenyl amide, polypropylene, polyvinylidene fluoride, acrylic, homopolymers, acetates, copolymers, acrlonitrile-butadiene-[stryrene] styrene, fluoupolymers, ionimers, polyamides, polyamide-imides, polyacrylates, polyether ketones, polyaryl-sulfones, polybenzimidazoles, polycarbonates, polybutylene, terephthalates, polyether sulfones, thermoplastic polyimides, thermoplastic polyurethanes, polyphenylene sulfides, polyethylene, polypropylene, polysulfones, polyvinylchlorides, [stryrene] styrene acrylonitriles, polystyrenes, polyphenylene, ether blends, styrene maleic anhydrides, allyls, aminos, and polyphenylene oxide. Numerous variations and equivalents are possible.

The invention is not limited to a single matrix component and a single barium sulfate composite, on the contrary multiple components may be included, for example, copolymers may be used or other mixtures of matrix elements. As another example, in tailoring of the physical properties of the composition, a blend of more than one shielding compound (such as a blend of barium sulfate and tungsten, tungsten-precursor, lead compounds, etc.) may be used.

In addition, the invention supports addition to the mixture of secondary fillers, binders, fibers and other components. As examples, additional electrically insulating materials, strengthening materials, materials to provide a uniform composition or bind other components, and/or density increasing materials may be used. A more specific list of examples includes such materials as tungsten metal, calcium carbonate, hydrated alumina, tabular alumina, silica, glass beads, glass fibers, magnesium oxide, wollastonite, stainless steel fibers, copper, carbonyl iron, steel, iron, molybdenum, and/or nickel.

In addition, the composite material of the present invention is susceptible to a wide range of processing methods both for creation of the material and creation of items incorporating the material. In addition to casting, other techniques including molding, aggregation, machining, liquid resin casting, transfer molding, injection molding, compression molding, extrusion, pultrusion, centrifugal molding, calendering, filament winding, and other methods of handling are possible. Additionally, the composite of the invention may advantageously be worked with known equipment such as molds and machine tools, thus avoiding costs associated with re-equip-

ping production facilities. Furthermore, since the material contains no lead, significant cost and time savings may be realized and burdensome regulations regarding lead may be properly avoided during these processes.

In theory, the material may be substituted for lead oxide shielding on a basis of approximately 3.5 to 1. Thus, for typical lead oxide shielding of 0.070 inches thickness, a replacement may be manufactured at a ratio of 3.5 to 1 in thickness. In the case of liquid resin casting, this increased thickness further allows easier molding.

EXAMPLE I

A first formulation and embodiment of the invention was derived from barium sulfate, epoxy resin and hydrated alumina. The formulation comprised 57% by volume of an epoxy resin (438 Novolac/HHPA curative, a trademark and product of the Dow Corporation), 35% barium sulfate (catalog no. RS-22BS-35) and 8% hydrated alumina. 12 inch square plates of 0.25 inch thickness were vacuum cast and examined. Test panels were machined from the plates.

The test item was compared to an equivalent lead-epoxy plate with a 14% vol/vol percentage.

The cast plate was of good quality and very producible.

Machined panels were of good quality, strength and durability.

Material density was 0.085 lb/cubic inch, equivalent.

Electrical testing showed the material to be a good insulator:

Dielectric strength was 300 volts/mil per D-149,

Arc resistance was 130 seconds per D-150.

Shielding effectiveness was equivalent to lead oxide composite items.

Despite being a barium compound, the material is non-toxic, thus despite expectations, it may be used in lead replacement roles without excessive environmental regulation.

The dielectric strength was equal to the 14% lead item (300 volts/mil in both cases), and the arc resistance was approximately double that of the lead test item. This is an important factor in calculating MTBF for items made with the materials, as one source of failures is failure under arc, leading to carbon paths on the surface. Since the carbon paths are conductive, the item is rendered quickly unusable and the equipment in which it is used (micro-chip production, for example) must be shut down, interrupting manufacturing, therapy, etc.

EXAMPLE II

A second test item was produced, using a second formulation and embodiment of the invention derived from barium sulfate and epoxy resin. The formulation comprised 60% by volume of an epoxy resin (438 Novolac/HHPA curative, a trademark and product of the Dow Corporation) and 40% barium sulfate. 12 inch square plates of 0.25 inch thickness were vacuum cast and examined. Test panels were machined from the plates.

The cast plate was of good quality and very producible.

Machined panels were of good quality, strength and durability.

Electrical testing showed the material to be a good insulator.

Material density was 0.093 lb/cubic inch, equivalent.

Shielding effectiveness was equivalent to lead oxide composite items.

In summary of the test results, it can be seen that for applications requiring high resistivity and high arc resistance,

barium sulfate composites may be advantageously used to achieve the desired properties. While the two tests both utilized epoxy resin, the present invention is not so limited, neither to the specific epoxy resin used nor to epoxy resin in general. Applicant reiterates that the examples presented are only examples: further development will produce numerous other materials with a wide range of characteristics, components, and methods of production.

Two examples of an application of the composite are presented below, that of [a] an ion implantation device source insulator, and [a] an high voltage insulating X-ray box, though the invention is not so limited.

It can also be seen that for applications requiring high shielding ability (such as X-ray source shielding in the medical field) the invention may be formulated to provide a shielding ability sufficient for lead replacement.

Without undue experimentation higher density formulations may be produced on demand by mixing additional secondary fillers into the composition. While use of lead would under some circumstances be self-defeating, lead, tungsten, platinum, gold, iridium, silver, tantalum, and similar materials may be used. Alternatively, the barium sulfate volumetric percentage may be increased by use of injection molding, compression molding or transfer molding as permitted by materials handling techniques. As demonstrated by the example using hydrated alumina, other properties such as electrical resistivity/conductivity, workability, ductility, density, and so on may also be adjusted by use of secondary fillers, binders, and other agents in the composition.

Thus it is apparent that a wide variety of products may be produced, as the characteristics of the barium sulfate composite of the present invention may be tailored depending upon the desired end characteristics. In addition, the environmental contamination engendered by the product is of a different order of magnitude than that produced by products containing lead.

An exemplary list of embodiments which may advantageously be produced using the material of the present invention includes X-ray tube insulators, apertures and enclosures, X-ray tube high-voltage insulators and enclosures, X-ray tube high voltage apertures, X-ray tube high voltage encapsulation devices, high voltage insulating radioactive shielding containers and other medical X-ray and gamma ray housings. Industrially, an exemplary list of embodiments in which the composition of the invention may advantageously be incorporated include ion source insulators for ion implantation machinery and other devices for insulating, isolating, directing or shielding any radiation producing device. As stated, these lists are exemplary only and embodiments of the invention may be utilized within the art field of radiation shielding in a broad range of equivalent ways.

FIG. 1 is a perspective view of an embodiment of an ion source electrical insulator according to the present invention. Ion source insulator 2 is generally annular in shape so as to allow to pass therethrough an ion implantation beam such as those used in the creation of microchip wafers. Such a device may advantageously have a desirable combination of radiation shielding ability, electrical resistivity/conductivity, physical parameters and other characteristics as are allowed by use of the polymer-barium sulfate composite of the present invention.

In use, the device may be placed directly against the ion source and/or may be placed around the ion stream at later points, for example, after magnetic devices which may focus, re-direct or otherwise alter the ion beam, or in any other location in which radiation or electrical charges may need to be blocked. Vacuum sealing surfaces 10 may facilitate provi-

11

sion of a tight seal. Alignment pin 20, one of several possible, may be used to assure proper alignment, the number and arrangement of pins obviously allows proper alignment to be assured in as many degrees of freedom as must be restricted. Metallic inserts 30 allow attachment of the device to the overall structure of the ion implanter device, medical device, or other device to which it belongs. The inserts have internal threads (not shown) allowing easy bolting to the larger machine of which the invention will be a part or a retrofit. Such features may be produced by molding, inserts, machining, or other means suitable for use with polymer materials as are known in the art. One additional desirable quality is that these features may be created "on demand" as requested by end users of the item.

Surface convolutions 40 may be used to provide additional properties such as to increase surface distance/area in order to prevent electrical arcing, to locally increase shielding or insulation, fit with other components of the overall system and so on.

While the exemplary ion source insulator is quite simple, such devices may be complex, having a much greater depth, having a much greater thickness, having multiple grooves and ridges and so on. Items created using the composite of the present invention need not be annular nor even circular but may be any shape as required. The range of sizes in such insulators is quite broad: from 1 inch to 20 or more inches tall, diameters from 6 to 40 inches, wall thicknesses which might be from 1/2 inch thick up to 3 inches thick and weights anywhere from under 1 pound to over 500 pounds.

The material of the device may be a barium sulfate composite as discussed previously.

As another example, FIG. 2 teaches one example of a high voltage insulating and X-ray shielding enclosure or box. X-ray shielding insulators are typically of an extremely wide range of shapes and sizes: cylinders, three dimensional conic sections, prisms, regular and irregular solids and composite shapes. A typical "box" might be irregular, 16 inches on a side and have a weight from 1 to 30 pounds. The thickness of the walls may be even greater than that of industrial ion source insulators.

The enclosure 102 shown in cross-sectional perspective in FIG. 2 is a composite of two truncated conical sections, but is an example only. It contains X-ray tube 104, having plating 106 and emitting X-ray beam 108 by means of an emission port dimensioned and configured to allow the X-ray beam to pass therethrough.

Enclosure/box 102 has a number of features required to allow X-ray tube 104 to function properly. Enclosure 102 has thick walls 110 of the desired composite material: on a 3.5 to 1 replacement basis, the walls may be approximately 3.5 times as thick as a corresponding lead oxide product, but at reduced cost. Oil cooling port 120 and electrical port 130 allow oil and electrical connections to the interior of the box. Overlap joint 140 is designed to prevent radiation leakage from the joint during the case manufacture.

While the exemplary ion source insulator is quite simple, such devices may be complex, having a much greater depth, having a much greater thickness, having multiple grooves and ridges and so on. Items created using the composite of the present invention need not be annular nor even circular but may be any shape as required. The range of sizes in such insulators is quite large: from 1 inch to 20 or more inches tall, diameters from 6 to 40 inches, wall thicknesses which might be from 1/2 inch thick up to 3 inches thick and weights anywhere from under 1 pound to over 500 pounds.

High voltage insulating X-ray shielding enclosures are typically of an even wider range of shapes and sizes, cylin-

12

ders, three dimensional conic sections, prisms, regular and irregular solids and composite shapes. A typical "box" might be irregular, 16 inches on a side and have a weight from 1 to 30 pounds. The thickness of the walls may be even greater than that of industrial ion source insulators.

In short, regardless of shape or size of the item to be made the present invention may be adapted to any radioactive/ion/gamma ray/x-ray shielding application without undue experimentation and without departing from the scope of the invention. Formulations other than those specifically provided may be employed without departing from the scope of the invention.

The method of the invention, a process for producing a high voltage insulator having radiation shielding properties, may have the following steps:

TABLE I

- | | |
|----|--|
| A) | mixing uncured liquid epoxy polymers with desired percentages of powdered barium sulfate and powdered hydrated alumina. |
| B) | blending the mixture in high shear single blade vacuum mixers for a first predetermined time. |
| C) | Pouring, injecting or vacuum casting the material in a mold having a generally annular body cavity having a diameter of at least 6 inches, the body cavity having at least one vacuum sealing surface. |
| D) | Placing the material into an autoclave. |
| E) | Curing the mold and material therein at a temperature in a range from at least 70 degrees F. to 400 degrees F. for a period depending upon the size, configuration and exact choice of materials, the time ranging from at least two hours to 24 hours, at a pressure ranging from at least 50 to 250 psi. |

This is in contrast to methods of creating thin and flexible radiation barriers, which do not involve casting.

This disclosure is provided to allow practice of the invention by those skilled in the art without undue experimentation, including the best mode presently contemplated and the presently preferred embodiment. Nothing in this disclosure is to be taken to limit the scope of the invention, which is susceptible to numerous alterations, equivalents and substitutions without departing from the scope and spirit of the invention. The scope of the invention is to be understood from the appended claims.

What is claimed is:

[1. A high voltage insulating radiation enclosure comprising:

a first truncated cone section and a second truncated cone section;

the two truncated cone sections secured together at their respective bases by an overlap joint;

an interior space defined by the two truncated cones sections;

the first and second truncated cone sections having walls, the walls made of a material comprising:

a) a polymer matrix and

b) barium sulfate within the polymer matrix in an approximate amount of at least 10% by volume;

a first emission port passing through at least one wall;

a second electrical port passing through at least one walls.]

[2. The high voltage insulating radiation enclosure of claim 1, further comprising an X-ray tube disposed within the hollow body.]

[3. The high voltage insulating radiation enclosure of claim 1, further comprising at least one oil port passing through the walls.]

[4. The high voltage insulating radiation enclosure of claim 1, wherein the polymer matrix comprises at least one member selected from the following group: epoxy, polyester, polyurethane, silicone rubber, bismaleimides, polyimides, vinyl-

ers, urethane hybrids, polyurea elastomer, phenolics, cyanates, cellulose, fluoro-polymer, ethylene inter-polymer alloy elastomer, ethylene vinyl acetate, nylon, polyetherimide, polyester elastomer, polyester sulfone, polyphenyl amide, polypropylene, polyvinylidene flouride, acrylic, homopolymers, acetates, copolymers, acrylonitrile-butadiene-styrene, flouropolymers, ionimers, polyamides, polyamide-imides, polyacrylates, polyether ketones, polyaryl-sulfones, polybenzimidazoles, polycarbonates, polybutylene, terephthalates, polyether sulfones, thermoplastic polyimides, thermoplastic polyurethanes, polyphenylene sulfides, polyethylene, polypropylene, polysulfones, polyvinylchlorides, styrene acrylonitriles, polystyrenes, polyphenylene, ether blends, styrene maleic anhydrides, allyls, aminos, polyphenylene oxide, and combinations thereof.]

[5. The high voltage insulating radiation enclosure of claim 1, wherein the polymer matrix comprises epoxy resin in an approximate amount of 50% to 70% by volume.]

[6. The high voltage insulating radiation enclosure of claim 1, further comprising:

c) a third material.]

[7. The high voltage insulating radiation enclosure of claim 6, wherein the third material comprises at least one member selected from the following group: electrically insulating materials, binders, high density materials and combinations thereof.]

[8. The high voltage insulating radiation enclosure of claim 6, wherein the third material comprises at least one member selected from the following group: tungsten, lead, platinum, gold, silver, tantalum, calcium carbonate, hydrated alumina, tabular alumina, silica, glass beads, glass fibers, magnesium oxide/sulfate, wollastonite, stainless steel fibers, copper, carbonyl iron, iron, molybdenum, nickel and combinations thereof.]

9. An electrical insulator for an ion source, the insulator comprising:

a generally annular body having a diameter of at least 6 inches;

the body having at least one vacuum sealing surface dimensioned and configured to provide a tight seal;

[at least one alignment pin projecting from the vacuum sealing surface of the insulator;]

at least one metal insert secured to the body;

the body made of a material comprising:

a. a polymer matrix and

b. barium sulfate within the polymer matrix in an approximate amount of at least 35% by volume.

10. The electrical insulator of claim 9, further comprising at least one element selected from alignment pins projecting from the vacuum sealing surface of the insulator, metal inserts secured to the body, and combinations thereof.

11. The electrical insulator of claim 9, further comprising a third material selected from the group consisting of electrically insulating materials, binders, high density materials, and combinations thereof.

12. The electrical insulator of claim 11, wherein the third material comprises at least one member selected from the group of tungsten, lead, platinum, gold, silver, tantalum, calcium carbonate, hydrated alumina, tabular alumina, silica, glass beads, glass fibers, magnesium oxide/sulfate, wollastonite, stainless steel fibers, copper, carbonyl iron, iron, molybdenum, nickel and combinations thereof.

13. The electrical insulator of claim 9, wherein the polymer matrix comprises at least one member selected from the following group: epoxy, polyester, polyurethane, silicone rubber, bismaleimides, polyimides, vinyl esters, urethane hybrids, polyurea elastomer, phenolics, cyanates, cellulose,

fluoro-polymer, ethylene inter-polymer alloy elastomer, ethylene vinyl acetate, nylon, polyetherimide, polyester elastomer, polyester sulfone, polyphenyl amide, polypropylene, polyvinylidene flouride, acrylic, homopolymers, acetates, copolymers, acrylonitrile-butadiene-styrene, flouropolymers, ionimers, polyamides, polyamide-imides, polyacrylates, polyether ketones, polyaryl-sulfones, polybenzimidazoles, polycarbonates, polybutylene, terephthalates, polyether sulfones, thermoplastic polyimides, thermoplastic polyurethanes, polyphenylene sulfides, polyethylene, polypropylene, polysulfones, polyvinylchlorides, styrene acrylonitriles, polystyrenes, polyphenylene, ether blends, styrene maleic anhydrides, allyls, aminos, polyphenylene oxide, and combinations thereof.

14. The electrical insulator of claim 9, wherein the polymer matrix comprises epoxy resin in an approximate amount between about 50% and about 70% by volume.

15. A high voltage insulating radiation enclosure comprising:

a first truncated cone section and a second truncated cone section;

the two truncated cone sections secured together at their respective bases by an overlap joint;

an interior space defined by the two truncated cone sections;

the first and second truncated cone sections having walls, the walls made of a material comprising:

a) a polymer matrix; and

b) barium sulfate within the polymer matrix in an approximate amount of at least 10% by volume;

a first emission port passing through at least one wall; and a second electrical port passing through at least one wall.

16. The high voltage insulating radiation enclosure of claim 15, further comprising an X-ray tube disposed within the hollow body.

17. The high voltage insulating radiation enclosure of claim 15, further comprising at least one oil port passing through at least one wall.

18. The high voltage insulating radiation enclosure of claim 15, wherein the polymer matrix comprises at least one member selected from the following group: epoxy, polyester, polyurethane, silicone rubber, bismaleimides, polyimides, vinyl esters, urethane hybrids, polyurea elastomer, phenolics, cyanates, cellulose, fluoro-polymer, ethylene inter-polymer alloy elastomer, ethylene vinyl acetate, nylon, polyetherimide, polyester elastomer, polyester sulfone, polyphenyl amide, polypropylene, polyvinylidene flouride, acrylic, homopolymers, acetates, copolymers, acrylonitrile-butadiene-styrene, flouropolymers, ionimers, polyamides, polyamide-imides, polyacrylates, polyether ketones, polyaryl-sulfones, polybenzimidazoles, polycarbonates, polybutylene, terephthalates, polyether sulfones, thermoplastic polyimides, thermoplastic polyurethanes, polyphenylene sulfides, polyethylene, polypropylene, polysulfones, polyvinylchlorides, styrene acrylonitriles, polystyrenes, polyphenylene, ether blends, styrene maleic anhydrides, allyls, aminos, polyphenylene oxide, and combinations thereof.

19. The high voltage insulating radiation enclosure of claim 15, wherein the polymer matrix comprises epoxy resin in an approximate amount of 50% to 70% by volume.

20. The high voltage insulating radiation enclosure of claim 15, further comprising:

c) a third material.

21. The high voltage insulating radiation enclosure of claim 20, wherein the third material comprises at least one

15

member selected from the following group: electrically insulating materials, binders, high density materials and combinations thereof.

22. The high voltage insulating radiation enclosure of claim 20, wherein the third material comprises at least one member selected from the following group: tungsten, lead, platinum, gold, silver, tantalum, calcium carbonate, hydrated

16

alumina, tabular alumina, silica, glass beads, glass fibers, magnesium oxide/sulfate, wollastonite, stainless steel fibers, copper, carbonyl iron, molybdenum, nickel and combinations thereof.

* * * * *