



US00RE46549E

(19) **United States**
(12) **Reissued Patent**
Minn et al.

(10) **Patent Number:** **US RE46,549 E**
(45) **Date of Reissued Patent:** **Sep. 12, 2017**

(54) **INTEGRATED CIRCUIT CHIP HAVING ANTI-MOISTURE-ABSORPTION FILM AT EDGE THEREOF AND METHOD OF FORMING ANTI-MOISTURE-ABSORPTION FILM**

(58) **Field of Classification Search**
CPC H01L 2924/00; H01L 2924/00014; H01L 21/304; H01L 21/3043
USPC 257/208, 529, 620, E21.237, E21.238, 257/E21.599; 438/460, 462
See application file for complete search history.

(71) Applicant: **Conversant Intellectual Property Management Inc., Ottawa (CA)**

(56) **References Cited**

(72) Inventors: **Eun-Young Minn, Gyeonggi-do (KR); Young-Hoon Park, Gyeonggi-do (KR); Chi-Hoon Lee, Gyeonggi-do (KR); Hyo-Dong Ban, Gyeonggi-do (KR)**

U.S. PATENT DOCUMENTS

5,017,512 A 5/1991 Takagi
5,025,300 A * 6/1991 Billig et al. 357/51
5,296,745 A 3/1994 Shirai et al.
(Continued)

(73) Assignee: **Conversant Intellectual Property Management Inc., Ottawa (CA)**

FOREIGN PATENT DOCUMENTS

JP Hei 9-69571 11/1997 21/82

(21) Appl. No.: **14/025,203**

Primary Examiner — Kenneth J Whittington

(22) Filed: **Sep. 12, 2013**

(74) *Attorney, Agent, or Firm* — Conversant IP Management Corp.

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **6,566,735**
Issued: **May 20, 2003**
Appl. No.: **09/715,372**
Filed: **Nov. 17, 2000**

(57) **ABSTRACT**

An integrated circuit chip having an anti-moisture-absorption film at the edge thereof and a method of forming the anti-moisture-absorption film are provided. In the integrated circuit chip which has predetermined devices inside and whose uppermost layer is covered with a passivation film, a trench is formed by etching interlayer dielectric films to a predetermined depth along the perimeter of the integrated circuit chip to be adjacent to the edge of the integrated circuit chip and an anti-moisture-absorption film is formed to fill the trench or is formed on the sidewall of the trench to a predetermined thickness, in order to prevent moisture from seeping into the edge of the integrated circuit chip. Moisture is effectively prevented from seeping into the edge of the chip by forming the anti-moisture-absorption film at the edge of the chip using the conventional processes of manufacturing the integrated circuit chip without an additional process.



(30) **Foreign Application Priority Data**

Nov. 26, 1999 (KR) 10-1999-0052997

(51) **Int. Cl.**
H01L 23/544 (2006.01)
H01L 23/26 (2006.01)
H01L 23/31 (2006.01)

(52) **U.S. Cl.**
CPC *H01L 23/26* (2013.01); *H01L 23/3178* (2013.01); *H01L 2924/0002* (2013.01); *H01L 2924/19041* (2013.01)

9 Claims, 11 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

5,414,297 A * 5/1995 Morita et al. 257/620
5,665,655 A * 9/1997 White 438/584
5,686,171 A * 11/1997 Vokoun B81C 1/00873
257/E21.599
5,789,302 A * 8/1998 Mitwalsky et al. 438/462
5,827,759 A * 10/1998 Froehner et al. 438/132
5,841,182 A * 11/1998 Linn H01L 21/2007
257/532
5,879,966 A 3/1999 Lee et al. 438/132
5,936,296 A * 8/1999 Park et al. 257/529
5,990,537 A * 11/1999 Endo et al. 257/529
6,316,287 B1 * 11/2001 Zandman et al. 438/113
6,365,521 B1 * 4/2002 Shubert H01L 23/3171
257/529

* cited by examiner

FIG. 1 (PRIOR ART)




FIG. 2 (PRIOR ART)




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 3F




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 6A




FIG. 6B





FIG. 6C



1

**INTEGRATED CIRCUIT CHIP HAVING
ANTI-MOISTURE-ABSORPTION FILM AT
EDGE THEREOF AND METHOD OF
FORMING ANTI-MOISTURE-ABSORPTION
FILM**

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue; a claim printed with strikethrough indicates that the claim was canceled, disclaimed, or held invalid by a prior post-patent action or proceeding.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an integrated circuit chip and a method of manufacturing the same, and more particularly, to a structure at the edge of an integrated circuit chip and a method of forming the same.

2. Description of the Related Art

A plurality of integrated circuit chips are generally simultaneously formed on one wafer. The completed chips are sawed one by one and are packaged. Referring to FIG. 1 which is a plan view showing part of the surface of a wafer on which a plurality of integrated circuit chips are formed, chips 10 are formed on the wafer at predetermined intervals using the same process. The chips 10 are separated from each other by scribe lines 20 which define spaces for sawing the chips 10.

Referring to FIG. 2 which is an enlarged sectional view taken along the line 2—2 of FIG. 1, metal interconnections 40 and a contact 60 are formed in the chip 10. Interlayer dielectric films 30 are interposed between the metal interconnections 40. The uppermost part is covered with a passivation film 50. Also, since the area occupied by the scribe lines 20 is not generally used as a device, only interlayer dielectric films 30 and a passivation film 50 exist. However predetermined circuit patterns 45 referred to as a test element group (TEG) may be formed in order to estimate the characteristics of a device which is being designed in advance. Also, trenches 70 are formed at the boundaries of the chips 10 and the scribe lines 20. This is for cutting the passivation film 50, since mechanical shock generated when the chips are sawed along the center of the scribe line 20 and separated from each other is transmitted to the chip 10 through the passivation film 50 formed of silicon nitride, which is a hard material. The shock is strong if there is no trench 70, thus causing cracks to occur in the passivation film 50 and the device under the passivation film 50 of the chip 10. The trench 70 is formed in an etching process also used to form a fuse opening (not shown) of the chip 10 without in order to reduce the number of processes. The wafer is sawed along the center of the scribe line 20 and divided into separate chips. In FIG. 2, the part between dotted lines 80 is sawed and removed. The entire width of the scribe line 20 is generally between about 100 and 120 μm . The width of the sawed and removed part (the part between dotted lines 80) is generally between about 30 and 60 μm .

In general, before the completed chips 10 are sawed, the reliability of the wafer shown in FIG. 2 is tested at a temperature of between 100 and 150° C., a humidity of between 80 and 100%, and a pressure of between 1.5 and 3 atm, in order to estimate whether the completed integrated

2

circuit chips operate in a stable condition at a high temperature, a high humidity, and a high pressure.

The interlayer dielectric films 30 exposed on the sidewalls of the trenches 70 located at the edges of the chips 10 are usually formed of silicon oxide such as boron phosphorous silicate glass (BPSG), phosphorous silicate glass (PSG), spin on glass (SOG), tetra ethyl ortho silicate (TEOS), and undoped silicate glass (USG), which have an excellent planarization characteristic. However, the BPSG, the PSG, the SOG, and the TEOS, which include a high concentration of impurities such as boron greater than or equal to 5 weight % and phosphorous greater than or equal to 4 weight %, are vulnerable to moisture. Furthermore, in order to prevent changes in the characteristics of the device, the interlayer dielectric films 30 are formed at a low temperature. Therefore, when moisture seeps into interfaces between the interlayer dielectric films 30 vulnerable to moisture while test the reliability of the device, the metal interconnections 40 formed of tungsten or aluminum and the contact 60 in an adjacent peripheral circuit erode and the interfaces between the interlayer dielectric films 30 or the interfaces between the interlayer dielectric films 30 and the metal interconnections 40 are peeled from each other, or cracks occur in the interfaces between the interlayer dielectric films 30 or the interfaces between the interlayer dielectric films 30 and the metal interconnections 40. Accordingly, the reliability of the device severely deteriorates.

Similar problems occur in the fuse opening (not shown) in the chip 10. In order to solve the problems in the fuse opening, a method of forming an anti-moisture-absorption film with a moisture-proof material on the sidewall of the fuse opening (U.S. Pat. No. 5,879,966) and a method of forming a ring-shaped guard ring which surrounds the fuse opening (Japanese Patent Publication No. Hei 9-69571) are provided. However, when using these methods, it is necessary to add process steps. Also, such methods have not been provided with respect to the edges of the chips.

SUMMARY OF THE INVENTION

To solve the above problem, it is an object of the present invention to provide an integrated circuit chip having a structure capable of preventing moisture from seeping into the edge of the chip.

It is another object of the present invention to provide a method of forming an anti-moisture-absorption film capable of preventing moisture from seeping into the edge of a chip without an additional process.

In accordance with the present invention, an integrated circuit chip is provided with a plurality of devices formed in the integrated circuit chip. A passivation film is formed on the integrated circuit chip. A trench is formed at a predetermined depth along the perimeter of the integrated circuit chip adjacent to the edge of the integrated circuit chip. An anti-moisture-absorption film is formed in the trench at a predetermined thickness. The anti-moisture-absorption film prevents moisture from seeping into the edge of the integrated circuit chip.

The trench can be formed by etching interlayer dielectric films of the device to the predetermined depth. The anti-moisture-absorption film can be formed on a sidewall of the trench.

The anti-moisture-absorption film can be formed by extending the passivation film at least to the sidewall of the trench.

The anti-moisture-absorption film may comprise a conductive layer pattern which fills the trench or is formed on

the sidewall of the trench to a predetermined thickness and a passivation film extended so as to cover the conductive layer pattern.

In accordance with the invention, there is also provided a method of forming an anti-moisture-absorption film at a boundary between an integrated circuit chip and a scribe line, in a wafer on which a plurality of integrated circuit chips are formed by interposing the scribe line. In the method of forming the anti-moisture-absorption film, predetermined devices, a lower interconnection layer, and an insulating layer on the lower interconnection layer are formed in an area where the chips are formed by sequentially stacking predetermined material layer and interlayer dielectric films on the wafer. A contact hole which exposes the lower interconnection layer is formed in a predetermined position of the chip by etching the insulating layer on the lower interconnection layer, and a trench is formed to a predetermined depth by etching interlayer dielectric films stacked at the boundary between the chip and the scribe line at the same time. After forming a conductive layer by depositing a conductive material which will form an upper interconnection layer of the integrated circuit chip on the entire surface of the wafer on which the contact hole and the trench are formed, the upper interconnection layer and a contact are formed in the chip by patterning the conductive layer and the conductive material is removed inside and around the trench at the same time. The passivation film is formed by depositing a moisture-proof material on the entire surface of the wafer on which the upper interconnection layer is formed. The anti-moisture-absorption film is formed with the passivation film formed inside the trench by removing part of the passivation film at the boundary between the chip and the scribe line.

According to one embodiment of the present invention, an anti-moisture-absorption film is formed with a conductive material film left on the sidewall of the trench or inside the trench when the conductive material layer, which will form the upper interconnection layer, is patterned and the passivation film on the conductive material layer.

In one embodiment, an etching stop film is formed under the lower interconnection layer by extending a predetermined material layer which forms the device of the integrated circuit chip having etching selectivity with respect to interlayer dielectric films to be etched in order to form the trench before forming the lower interconnection layer and the interlayer dielectric films are etched until the etching stop film is exposed, so that the trench can be formed.

According to the present invention, moisture is prevented from seeping into the edge of a chip by forming an anti-moisture-absorption film on the sidewall of a trench formed at the edge of an integrated circuit chip or inside the trench.

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing and other objects, features and advantages of the invention will be apparent from the following more particular description of preferred embodiments of the invention, as illustrated in the accompanying drawings in which like reference characters refer to the same parts throughout the different views. The drawings are not necessarily to scale emphasis instead being placed upon illustrating the principles of the invention.

FIG. 1 is a plan view showing part of the surface of a wafer on which a plurality of integrated circuit chips are formed.

FIG. 2 is an enlarged sectional view taken along the line 2—2 of FIG. 1.

FIGS. 3A through 3F are sectional views showing processes of forming an anti-moisture-absorption film at the edge of an integrated circuit chip according to an embodiment of the present invention and the structure of the chip edge formed thereby.

FIGS. 4A through 4C are sectional views showing a structure in which an anti-moisture-absorption film is formed at the edge of an integrated circuit chip according to another embodiment of the present invention.

FIGS. 5A through 5F are sectional views showing processes of forming an anti-moisture-absorption film at the edge of an integrated circuit chip according to still another embodiment of the present invention and the structure of the chip edge formed thereby.

FIGS. 6A through 6C are sectional views showing a structure in which the anti-moisture-absorption film is formed at the edge of the integrated circuit chip according to still another embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention now will be described more fully with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. In the drawings, it will also be understood that when a layer is referred to as being on another layer or substrate, it can be directly on the other layer or substrate, or intervening layers may also be present. Also, each of interlayer dielectric films is described to have a single-layered structure, however, can have a structure where multi-layered interlayer dielectric films are stacked. The thickness or length of layers are exaggerated for clarity.

FIGS. 3A through 3F are sectional views showing processes of forming an anti-moisture-absorption film at the edge of an integrated circuit chip according to an embodiment of the present invention and the structure of the chip edge formed thereby. Chip areas and scribe lines of only one side are shown in FIGS. 3A through 3F unlike in FIG. 2. The chip areas and the scribe lines of only one side are shown in other embodiments.

Referring to FIG. 3A, a trench is formed at the boundary between a chip and a scribe line. Material layer patterns 110 which form a predetermined device are formed in the chip on a substrate or an interlayer dielectric film 100. Predetermined material layer patterns 112 can be simultaneously formed in the scribe line for a test element group (TEG). Here, since the characteristic part of the present invention is the boundary between the chip and the scribe line, a detailed description of a device or material layer patterns formed inside the chip and in the center of the scribe line excluding the boundary will be omitted. In the case of a memory device, the respective memory cells and a peripheral circuit for driving the respective memory cells are generally formed inside the chip.

After forming an interlayer dielectric film 120, a lower interconnection layer 130 of the chip is formed. The lower interconnection layer 130 is formed by depositing a conductive material, for example, a metal such as tungsten or aluminum, on the entire surface of the interlayer dielectric film 120 (a barrier metal layer may be included under a metal layer when the metal is used) and patterning the metal in a desired interconnection pattern.

A contact hole 150 is formed by depositing an interlayer dielectric film 140 such as a silicon oxide film on the entire surface of the resultant on the lower interconnection layer 130 to a thickness of between 5,000 and 10,000 Å and by

5

etching the interlayer dielectric film **140** in a portion where a contact is to be formed. A trench **152** is simultaneously formed at the boundary between the chip and the scribe line. To be specific, the contact hole **150** which exposes the lower interconnection layer **130** is formed in the chip, and the trench **152** is formed at the boundary between the chip and the scribe line at the same time by forming a photoresist pattern (not shown) which exposes the portions of the interlayer dielectric film **140** to be etched and plasma etching the interlayer dielectric film **140** formed of the silicon oxide using CF_4 having a flow rate of between 35 and 50 sccm and CHF_3 having a flow rate of between 35 and 50 sccm as etching gases, and flowing Ar having a flow rate of between 300 and 450 sccm, at a pressure of between 300 and 500 mTorr, and at an RF power of between 1,100 and 1,400 W, for between 100 and 150 seconds. The width of the trench **152** is about several μm .

A conductive material layer **160** which fills the contact hole **150** is formed and the conductive material layer **160** is also formed in the trench **152**, as shown in FIG. 3B, when the conductive material, for example, a metal such as tungsten or aluminum, is deposited on the entire surface of the resultant of FIG. 3A to a thickness of between 6,500 and 10,000 Å in order to form an upper interconnection layer on the entire surface of the resultant structure.

Referring to FIG. 3C, the conductive material layer **160** is patterned. As a result, an upper interconnection layer **164** including a contact is formed in the chip and the conductive material is completely removed inside and around the trench **152**. At this time, an interconnection pattern **162** can be formed in the scribe line, if necessary.

Referring to FIG. 3D, a passivation film **170** used as the anti-moisture-absorption film is formed on the uppermost layer of the chip and the sidewall of the trench **152**. The interlayer dielectric film **120** is exposed in the center of the bottom of the trench **152**, since part of the passivation film **170** is removed.

In order to form the structure shown in FIG. 3D, a moisture-proof film such as a silicon nitride film, a silicon oxide film which is not doped with impurities or is doped with a low concentration of impurities, or a compound film of the above films is formed on the entire surface of the resultant structure of FIG. 3C. In the present embodiment, the silicon oxide film which is not doped with impurities is deposited to a thickness of between 1,000 and 2,000 Å. The silicon nitride film is deposited on the silicon oxide film to a thickness of between 5,000 and 10,000 Å. As a result, an interface between the interlayer dielectric films **120** and **140**, which is exposed on the sidewall of the trench **152** and can be a moisture-absorption path, is covered with the passivation film **170**. Accordingly, the moisture-absorption path is blocked by the passivation film **170**.

A chip edge structure is completed by removing part of the passivation film **170**, thus exposing the interlayer dielectric film **120** so that mechanical shock is not transmitted through the passivation film **170** when the wafer is sawed along the center of the scribe line. The interlayer dielectric film **120** is exposed at the bottom of the trench **152** in a process of exposing the upper interconnection layer **164** by etching the passivation film **170** in order to form a bonding pad (not shown) for wire bonding, so that an additional process is not needed. The interlayer dielectric film **120** is exposed in the center of the trench **152** and the bonding pad (not shown) in which the upper interconnection layer **164** is exposed is formed in a predetermined position of the chip by performing a photolithography process. To be specific, a photoresist pattern (not shown) is formed to expose a portion

6

in which the bonding pad is to be formed and the center of the trench **152**, and the passivation film **170** formed by stacking the silicon oxide film and the silicon nitride film is plasma etched using CF_4 having a flow rate of between 65 and 90 sccm and O_2 having a flow rate of between 10 and 25 sccm as etching gases, and flowing Ar having a flow rate of between 80 and 110 sccm, at a pressure of between 300 and 500 mTorr, and at an RF power of between 1,000 and 1,300 W, for between 60 and 95 seconds.

When the reliability of the integrated circuit chip is tested at a high temperature, a high humidity, and a high pressure in the state that the anti-moisture-absorption film is formed of the passivation film **170** on the sidewall of the trench **152**, moisture is prevented from seeping into the sidewall of the trench formed at the boundary between the chip and the scribe line, unlike in the conventional technology. Accordingly, reliable integrated circuit chips are obtained.

When the chips are sawed along the center of the scribe lines after the reliability of the integrated circuit chips tested, the right side of a dotted line **200** is cut and removed and the chip on the left side of the dotted line **200** is divided into separate chips.

FIG. 3E is a modification of the present embodiment. The position where part of a passivation film **172** is removed in FIG. 3E is different from the position where part of the passivation film **170** is removed in FIG. 3D. Meanwhile it is probable that a small amount of moisture will seep into the interface between the interlayer dielectric film **120** exposed to the bottom of the trench **152** and the passivation film **170** in the structure shown in FIG. 3D. However, the seeping of moisture is completely prevented in the structure shown in FIG. 3E.

FIG. 3F is another modification of the present invention, in which a passivation film **174** fills a trench **154**. Here, the width of the trench **154** is formed to be equal to or less than twice the thickness of the passivation film **174** so that the passivation film **174** fills the trench **154**. In the structure shown in FIG. 3F, it is possible to completely prevent the seeping of moisture like in the structure shown in FIG. 3E.

FIGS. 4A through 4C are sectional views showing the structure of the edge of a chip according to another embodiment of the present invention. Conductive material patterns **166**, **167**, and **168** which are formed of the same material as the upper interconnection layer **164** in the chip are left inside the trench or on the sidewall of the trench in the present embodiment, unlike in the embodiment described above in connection with FIGS. 3A through 3F.

In order to form the structure shown in FIG. 4A, in the step corresponding to FIG. 3C of the embodiment of FIGS. 3A through 3F, the conductive material is not completely removed inside and around the trench **156** when the upper interconnection layer **164** is formed and is left on the sidewall of the trench **156**. The structure shown in FIG. 4A is obtained through the same process as the embodiment of FIGS. 3A through 3F described with reference to FIG. 3D. The width of the trench **156** is made wider than the width of the trench **152** shown in FIG. 3A, considering the thickness of the conductive material pattern **166** left on the sidewall of the trench **156**.

The edge of the chip having the structure shown in FIG. 4B is a modification of the present embodiment, in which the conductive material pattern **167** is left on the sidewall and the bottom of the trench **156**. The part of the passivation film **172** is removed in a portion on the scribe line side adjacent to the trench **156**.

The structure shown in FIG. 4C is another modification of the present embodiment, in which the conductive material

pattern **168** fills the trench **154**. In order to form the edge of the chip having the structure shown in FIG. **4C**, after the width of the trench **154** is formed to be equal to or less than twice the thickness of the conductive material layer **168** so that the conductive material layer **168** fills the trench **154**, the conductive material layer **168** which fills the trench **154** is left when the upper interconnection layer **164** of the chip is formed, like in the structure shown in FIG. **3F** of the embodiment of FIGS. **3A** through **3F**.

In FIGS. **4A** through **4C**, the upper interconnection layer **164** is described as being separated from the conductive material patterns **166**, **167**, and **168** left on the sidewalls of the trench **156** or inside the trench **154**. However, the upper interconnection layer **164** does not need to be separated from the conductive material patterns **166**, **167**, and **168** unless there is an electrical influence such that the conductive material patterns **166**, **167**, and **168** on the sidewalls of the trenches or inside the trenches are connected to other elements. This is true of the embodiment of FIGS. **6A** through **6C** described below in detail.

In the present embodiment, it is possible to prevent moisture from seeping into the edge of the chip since the interface between the interlayer dielectric films **120** and **140** which becomes the moisture-absorption path is not exposed.

FIGS. **5A** through **5F** are sectional views showing processes of forming the anti-moisture-absorption film at the edge of the chip according to a third embodiment of the present invention and the structure of the chip edge formed thereby. The third embodiment is different from the first embodiment of FIGS. **3A** through **3F** only in that an etching stop film is formed with a predetermined material layer **190** which forms a device in the chip under the lower interconnection layer **130**, so as to easily control the depth to which the interlayer dielectric films **140** and **122** are etched in order to form the trench **152**.

Referring to FIG. **5A**, the material layer patterns **110** which form a predetermined device are formed on the substrate or the interlayer dielectric film **100** and the interlayer dielectric film **120** is formed on the material layer pattern **110**, like in FIG. **3A**. The predetermined material layer **190** which forms the device in the chip is formed on the interlayer dielectric film **120** to be extended to the scribe line. The material layer **190** can be formed of polycrystalline silicon which is doped with impurities, which forms the upper electrode of a memory cell capacitor when the device formed in the chip is a DRAM device. The material layer **190** can be formed of other interconnections and a material having etching selectivity with respect to the interlayer dielectric films **122** and **140** which is generally formed of the silicon oxide thereon. It is not necessary that the material layer **190** must be formed of the conductive material.

After forming the lower interconnection layer **130** by interposing the interlayer dielectric film **122** on the material layer **190** which will become the etching stop film and forming the interlayer dielectric film **140** on the lower interconnection layer **130**, the trench **152** is formed together with the contact hole **150** of the chip and at the boundary between the chip and the scribe line as described in FIG. **3A**. The contact hole **150** and the trench **152** are etched to have different depths, however, they can be simultaneously formed by etching until both the lower interconnection layer **130** and the etching stop film **190** are exposed. Therefore, it is possible to etch the trench **152** to a uniform depth.

As shown in FIG. **5B**, the conductive material layer **160** is formed by depositing the conductive material which will form the upper interconnection layer of the chip on the entire surface of the resultant of FIG. **5A**.

As shown in FIG. **5C**, a predetermined interconnection pattern **162** in the scribe line and in the upper interconnection layer **164** of the chip are formed by patterning the conductive material layer **160**, and the conductive material is completely removed inside and around the trench **152**. Also, the material layer **190** exposed by removing the conductive material in the trench **152** is removed. Here, the conductive material layer **160** and the material layer **190** exposed at the bottom of the trench **152** can be removed by two-step etching using an etching gas or an etching solution. However, it is convenient to remove the conductive material layer **160** and the material layer **190** used as the etching stop film by successively etching the conductive material layer **160** and the material layer **190** using an etching gas or etching solution having low etching selectivity with respect to the two materials which form the conductive material layer **160** and the material layer **190**. Namely, when the conductive material layer **160** and the material layer **190** are formed of aluminum and polycrystalline silicon, respectively, polycrystalline silicon reacts with aluminum due to heat generated when aluminum is deposited and reflowed, thus being metalized (it is possible to observe by a scanning electron microscope that polycrystalline silicon is metalized). Therefore, metalized polycrystalline silicon is removed by plasma etching aluminum using BCl_3 having a flow rate of between 35 and 60 sccm and Cl_2 having a flow rate of between 30 and 50 sccm as etching gases, and flowing N_2 having a flow rate of between 10 and 25 sccm, and at a pressure of between 100 and 250 mTorr, an RF power of between 300 and 700 W, for between 100 and 160 seconds.

Meanwhile, the exposed material layer **190** which was used as the etching stop film may not be removed, so that it remains on the bottom of the trench **152**, unless there is an influence to other elements, as in the embodiment of FIGS. **6A** through **6C** described below in detail.

The structure shown in FIG. **5D** is obtained through the process described with reference to FIG. **3D**.

The edge of the chip and the anti-moisture-absorption film having the structures shown in FIGS. **5E** and **5F** are modifications of the present embodiment. A description of the modifications will be omitted since the modifications are different from the modifications described with reference to FIGS. **3E** and **3F** only in that the material layer **190** used as the etching stop film (which is etched later and comes to have the form denoted by reference numeral **192**) is used.

According to the present embodiment, it is possible to prevent moisture from seeping into the edge of the chip since the anti-moisture-absorption film is formed at the edge of the chip and to easily control the depth to which the trench is etched in the process of forming the anti-moisture-absorption film.

FIGS. **6A** through **6C** are sectional views showing the structures of the edge of the chip and the anti-moisture-absorption film according to a fourth embodiment of the present invention. The structure of the present embodiment is obtained by combining the structure of the second embodiment of FIGS. **4A** through **4C** with the structure of the third embodiment of FIGS. **5A** through **5F**. The etching stop film **190** is used during the etching of the trench and the conductive material patterns **166**, **167**, and **168** which are formed of the same material as the upper interconnection layer **164** in the chip are left inside the trenches **156** and **154**. Since the method of forming the edge of the chip according to the present embodiment is obtained by combining the method of the second embodiment of FIGS. **4A** through **4C** with the method of the third embodiment of FIGS. **5A**

through 5F in which the etching stop film 190 is used, a description thereof will be omitted.

As mentioned above, according to the present invention, reliable integrated circuit chips are obtained by preventing moisture from seeping into the edges of the chips when the reliability of the integrated circuit chips are tested. In particular, according to the present invention, the anti-moisture-absorption film is formed at the edge of the chip using conventional process steps used in manufacturing integrated circuit chips without an additional process.

While this invention has been particularly shown and described with reference to preferred embodiments thereof, it will be understood by those skilled in the art that various changes in form and details may be made therein without departing from the spirit and scope of the invention as defined by the appended claims.

What is claimed is:

1. An integrated circuit device, comprising:

an integrated circuit chip;

a plurality of devices formed in the integrated circuit chip;

a scribe line formed at and defining the perimeter of the integrated circuit chip, said scribe line being used in separating the integrated circuit chip from other integrated circuit chips;

a passivation film formed on the integrated circuit chip;

a trench at a predetermined depth along the perimeter of the integrated circuit chip adjacent to the edge of the integrated circuit chip, the trench being formed at the scribe line at the perimeter of the integrated circuit chip, the predetermined depth being such that a boundary between multiple [layers] *interlayer dielectric films* of the integrated circuit device intersects a sidewall of the trench; [and]

an etching stop film formed under at least one of said multiple interlayer dielectric films, such that the bottom of said trench corresponding to said predetermined depth is formed within said one of said multiple interlayer dielectric films; and

an anti-moisture-absorption film in the trench at a predetermined thickness, said anti-moisture-absorption film covering the boundary between the multiple [layers] *interlayer dielectric films* such that moisture is prevented from seeping into the edge of the integrated circuit chip.

2. The integrated circuit device of claim 1, wherein the anti-moisture-absorption film is formed on the sidewall of the trench.

3. The integrated circuit device of claim 1, wherein the trench is etched into at least one interlayer dielectric film of the integrated circuit chip.

4. The integrated circuit device of claim [1] 9, wherein the anti-moisture-absorption film is formed by extending the passivation film at least to a sidewall of the trench.

5. The integrated circuit device of claim 1, wherein the anti-moisture-absorption film comprises a conductive layer pattern which fills the trench to a predetermined thickness and a passivation film extended so as to cover the conductive layer pattern.

6. The integrated circuit device of claim 5, wherein the conductive pattern is formed of the same material as an uppermost interconnection layer of the integrated circuit chip.

7. The integrated circuit device of claim 1, wherein the anti-moisture-absorption film comprises a conductive layer pattern which is formed on the sidewall of the trench to a predetermined thickness and a passivation film extended so as to cover the conductive layer pattern.

8. *The integrated circuit device of claim 1, wherein the anti-moisture absorption film comprises a conductive anti-moisture absorption film.*

9. *The integrated circuit device of claim 1, wherein the anti-moisture absorption film comprises an insulative anti-moisture absorption film.*

* * * * *