

US00RE47570E

(19) **United States**
(12) **Reissued Patent**
Limb et al.

(10) **Patent Number:** **US RE47,570 E**
(45) **Date of Reissued Patent:** **Aug. 13, 2019**

(54) **STRESSED SUBSTRATES FOR TRANSIENT ELECTRONIC SYSTEMS**

(58) **Field of Classification Search**
CPC ... H03K 19/17768; H01L 21/64; H01L 21/71;
H01L 23/44; H01L 27/00
(Continued)

(71) Applicant: **Palo Alto Research Center**
Incorporated, Palo Alto, CA (US)

(56) **References Cited**

(72) Inventors: **Scott J. H. Limb**, Palo Alto, CA (US);
Gregory L. Whiting, Boulder, CO
(US); **Sean R. Garner**, Redwood City,
CA (US); **JengPing Lu**, Fremont, CA
(US); **Dirk De Bruyker**, San Jose, CA
(US)

U.S. PATENT DOCUMENTS

3,397,278 A 8/1968 Pomerantz
3,601,114 A 8/1971 Cook
(Continued)

FOREIGN PATENT DOCUMENTS

DE 102004015546 10/2005
WO WO2001043228 6/2001

(73) Assignee: **Palo Alto Research Center**
Incorporated, Palo Alto, CA (US)

OTHER PUBLICATIONS

Apr. 13, 2018, File History for U.S. Appl. No. 15/220,221.
(Continued)

(21) Appl. No.: **15/726,944**

(22) Filed: **Oct. 6, 2017**

Primary Examiner — Tuan H Nguyen
(74) *Attorney, Agent, or Firm* — Hollingsworth Davis,
LLC

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **9,154,138**
Issued: **Oct. 6, 2015**
Appl. No.: **14/052,348**
Filed: **Oct. 11, 2013**


(51) **Int. Cl.**
H01L 21/64 (2006.01)
H01L 21/71 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 21/71** (2013.01); **H03K 19/17768**
(2013.01); **H01L 21/64** (2013.01); **H01L 27/00**
(2013.01)

(57) **ABSTRACT**

A stressed substrate for transient electronic systems (i.e., electronic systems that visually disappear when triggered to do so) that includes one or more stress-engineered layers that store potential energy in the form of a significant internal stress. An associated trigger mechanism is also provided that, when triggered, causes an initial fracture in the stressed substrate, whereby the fracture energy nearly instantaneously travels throughout the stressed substrate, causing the stressed substrate to shatter into multiple small (e.g., micron-sized) pieces that are difficult to detect. The internal stress is incorporated into the stressed substrate through strategies similar to glass tempering (for example through heat or chemical treatment), or by depositing thin-film layers with large amounts of stress. Patterned fracture features are optionally provided to control the final fractured

(Continued)



particle size. Electronic systems built on the substrate are entirely destroyed and dispersed during the transience event.

25 Claims, 7 Drawing Sheets

(51) **Int. Cl.**

H01L 23/14 (2006.01)

H01L 27/00 (2006.01)

H03K 19/177 (2006.01)

(58) **Field of Classification Search**

USPC 257/414, 417; 438/130

See application file for complete search history.

(56)

References Cited

U.S. PATENT DOCUMENTS

3,666,967	A	5/1972	Keister et al.	
3,673,667	A	7/1972	Loewenstein et al.	
3,882,323	A	5/1975	Smolker	
4,102,664	A	7/1978	Dumbaugh, Jr.	
4,139,359	A	2/1979	Johnson et al.	
4,598,274	A *	7/1986	Holmes	340/550
4,673,453	A	6/1987	Georgi	
5,374,564	A	12/1994	Bruel	
7,002,517	B2	2/2006	Nougeim	
7,153,758	B2	12/2006	Hata et al.	
7,554,085	B2 *	6/2009	Lee	250/338.4
7,880,248	B1	2/2011	Pham et al.	
8,130,072	B2	3/2012	De Bruyker et al.	
9,154,138	B2	10/2015	Limb et al.	
9,294,098	B2	3/2016	Shah et al.	
9,356,603	B2	5/2016	Limb et al.	
9,577,047	B2	2/2017	Chua et al.	
9,630,870	B2	4/2017	Zhao et al.	
9,780,044	B2	10/2017	Limb et al.	
2004/0031966	A1	2/2004	Forrest	
2004/0222500	A1	11/2004	Aspar et al.	
2005/0061032	A1	3/2005	Yoshizawa	
2005/0084679	A1	4/2005	Sglavo et al.	
2005/0176573	A1	8/2005	Thoma et al.	
2006/0138798	A1	6/2006	Oehrlein	
2006/0270190	A1	11/2006	Nastasi et al.	
2007/0113886	A1	5/2007	Arao et al.	
2008/0029195	A1	2/2008	Lu	
2008/0311686	A1	12/2008	Morral et al.	
2009/0086170	A1	4/2009	El-ghoury et al.	
2010/0035038	A1	2/2010	Barefoot et al.	
2010/0133641	A1	6/2010	Kim	
2010/0225380	A1	9/2010	Hsu et al.	
2011/0048756	A1	3/2011	Shi et al.	
2011/0089506	A1 *	4/2011	Hoofman	G06F 21/87 257/417
2011/0183116	A1	7/2011	Hung et al.	
2012/0052252	A1	3/2012	Kohli et al.	
2012/0135177	A1	5/2012	Comejo et al.	

2012/0135195	A1	5/2012	Glaesemann et al.	
2012/0196071	A1	8/2012	Comejo et al.	
2012/0288676	A1	11/2012	Sondergard et al.	
2013/0037308	A1	2/2013	Wang et al.	
2013/0082383	A1	4/2013	Aoya	
2013/0140649	A1 *	6/2013	Rogers et al.	257/414
2013/0192305	A1	8/2013	Black et al.	
2014/0091374	A1	4/2014	Assefa et al.	
2014/0103957	A1	4/2014	Fritz et al.	
2014/0266946	A1	9/2014	Billy et al.	
2014/0300520	A1	10/2014	Nguyen et al.	
2014/0323968	A1 *	10/2014	Rogers et al.	604/113
2015/0001733	A1	1/2015	Karhade et al.	
2015/0044445	A1	2/2015	Garner et al.	
2015/0076677	A1	3/2015	Ebefors et al.	
2015/0089977	A1	4/2015	Li	
2015/0102852	A1	4/2015	Limb et al.	
2015/0121964	A1	5/2015	Zhao et al.	
2015/0229028	A1	8/2015	Billy et al.	
2015/0318618	A1	11/2015	Chen et al.	
2015/0348940	A1	12/2015	Woychik	
2015/0358021	A1	12/2015	Limb et al.	
2015/0372389	A1	12/2015	Chen et al.	
2016/0122225	A1	5/2016	Wada et al.	
2016/0137548	A1	5/2016	Cabral, Jr. et al.	
2017/0036942	A1	2/2017	Abramov et al.	
2017/0217818	A1	8/2017	Dumenil et al.	
2017/0292546	A1	10/2017	Limb et al.	
2018/0005963	A1	1/2018	Limb et al.	
2018/0033577	A1	2/2018	Whiting et al.	
2018/0033742	A1	2/2018	Chua et al.	

OTHER PUBLICATIONS

Dec. 6, 2017, Search Report for EP App. No. 17182802.3 dated Dec. 6, 2017, 9 pages.

Apr. 5, 2018, EP Search Report for EP App. No. 17194476.2 dated Apr. 5, 2018, 9 pages.

U.S. Appl. No. 15/299,385, filed Oct. 20, 2016, Chua et al.

U.S. Appl. No. 15/629,506, filed Jun. 21, 2017, Limb et al.

Jan. 4, 2018, EP Search Report dated Jan. 4, 2018 for EP App. No. 17182800.7, 14 pages.

Feb. 13, 2018, File History for EP App. No. 17163445.4 as retrieved from the EP Patent Office electronic file system on Feb. 13, 2018, 74 pages.

Feb. 13, 2018, File History for U.S. Appl. No. 14/796,440.

Feb. 13, 2018, File History for U.S. Appl. No. 15/220,221.

Feb. 13, 2018, File History for U.S. Appl. No. 15/220,164.

Feb. 14, 2018, File History for U.S. Appl. No. 15/629,506.

Feb. 13, 2018, File History for U.S. Appl. No. 15/092,313.

File History for U.S. Appl. No. 15/092,313.

File History for U.S. Appl. No. 15/220,164.

File History for U.S. Appl. No. 15/220,221.

File History for U.S. Appl. No. 15/629,506.

File History for U.S. Appl. No. 15/689,566.

File History for U.S. Appl. No. 16/025,573.

File History for U.S. Appl. No. 16/033,783.

* cited by examiner




FIG. 1

FIG. 2(A)




FIG. 2(B)




FIG. 2(C)




FIG. 2(D)




FIG. 2(E)




FIG. 3(A)




FIG. 3(B)




FIG. 3(C)




FIG. 3(D)




FIG. 3(E)




FIG. 4(A)




FIG. 4(B)




FIG. 4(C)




FIG. 4(D)




FIG. 4(E)




FIG. 5(A)




FIG. 5(B)




FIG. 5(C)




FIG. 5(D)




FIG. 5(E)




FIG. 5(F)




FIG. 5(G)




FIG. 6(A)




FIG. 6(B)




FIG. 6(C)




FIG. 6(D)




FIG. 6(E)




FIG. 6(F)




FIG. 6(G)




FIG. 7(A)




FIG. 7(B)




FIG. 7(C)




FIG. 7(D)





FIG. 7(E)



STRESSED SUBSTRATES FOR TRANSIENT ELECTRONIC SYSTEMS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue; a claim printed with strikethrough indicates that the claim was canceled, disclaimed, or held invalid by a prior post-patent action or proceeding.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH AND DEVELOPMENT

This invention was made with Government support under Contract No. HR0011-14-C-0013 (G017.3765) awarded by defense Advanced Research Projects Agency. The Government has certain rights in this invention.

This is an application for reissue of U.S. Pat. No. 9,154,138.

FIELD OF THE INVENTION

This invention relates to transient electronic systems, and in particular to substrates used in transient electronic systems.

BACKGROUND OF THE INVENTION

Large area sensing is critical for a variety of military, ecological and commercial interests and has historically been served through the use of centralized long-range sensors. However, rapid improvements in miniaturization of electronic systems have significantly improved the capabilities of small sensor devices. These micro-sensors have the potential to create "large N" distributed networks with advantages in operational adaptability, non-traditional sensing modalities that are only possible with close proximity, increased sensitivity and knowledge extraction through networked intelligence.

While distributed network systems have remarkable promise, their realistic use is limited by risks associated with their accumulation in the environment, detection and defeat, and exploitation due to inability to maintain positive control (unlike centralized long-range sensors).

The phrase "transient electronics" refers to a relatively new family of electronic devices that disappear (disaggregate and disperse) within a set period of time, making them ideally suited for distributed network systems. Conventional transient electronic systems typically rely on the use of soluble substrates and electronic materials (such as silk). When placed into solvent (typically water), these conventional substrates and electronics slowly dissolve into solution. As such, a distributed network system made up of conventional transient electronic devices can be expected to "disappear" over a relatively short amount of time (e.g., after periodic rainfall).

Although the conventional transient electronic approaches achieve the goal of causing the electronics to "disappear" after use, the long dissolution period required to achieve complete disaggregation and dispersal make the conventional approaches unfit for discrete (e.g., military) applications that require rapid and complete disaggregation upon command. Moreover, the conventional approaches utilize materials that are not compatible with existing inte-

grated circuit fabrication and assembly techniques, requiring the development of new IC fabrication processes at significant cost.

What is needed is a substrate for transient electronics that is compatible with existing IC fabrication techniques, and achieves complete, on-command disaggregation of the electronic circuitry formed thereon.

SUMMARY OF THE INVENTION

The present invention is directed to a stressed substrate for transient electronic systems that utilizes one or more stress-engineered layers to store potential energy in the form of residual, self-equilibrating internal stresses, and an associated transient event triggering mechanism that, upon receiving a trigger signal, generates an initial fracture that causes the stressed substrate to suddenly and catastrophically release the stored potential energy in a manner that completely disaggregates ("powderizes") the stressed substrate into micron-sized particulates (i.e., 100 μm across) using a mechanism similar to that captured in a Prince Rupert's Drop. The stressed substrate is stable enough to support either mounted or fabricated electronics thereon. In one embodiment, the stressed substrate comprises a suitable semiconductor material (e.g., SiO_2) that is compatible with existing IC fabrication techniques. The stress-engineered layers include at least one tensile layer and at least one compressive layer that are operably attached together such that release of the potential energy powderizes the stressed substrate and any electronic devices disposed thereon. The transient event triggering system is connected to the stressed substrate, and includes an actuating mechanism that controls release of the potential energy, i.e., by generating an initial fracture in the stressed substrate upon receipt of a trigger signal (e.g., an externally delivered current pulse or a radio frequency signal). The present invention thus facilitates the production of transient electronic systems that reliably disappear (powderize) in a significantly shorter amount of time than is possible using conventional (e.g., soluble substrate) approaches. Moreover, because the stressed substrate is compatible with low-cost existing IC fabrication techniques, the present invention facilitates the production of transient electronic systems having custom-fabricated IC devices and/or the incorporation of high-performance off-the-shelf electronic devices with minimal (or potentially without any) modification to core IC fabrication process.

According to alternative exemplary embodiments, stressed substrates are fabricated either by depositing stress-engineered substrate layers using, for example, plasma vapor deposition techniques in which the deposition parameters (i.e., temperature or pressure) are varied such that the layers collectively contain a significant inbuilt stress gradient, or by post-treating the substrate material using strategies similar to glass tempering (e.g., by way of ion-exchange, heat or chemical treatment). In some cases, the stress-engineered substrate layers are sequentially deposited on top of each other inside a sacrificial mold that is later removed (i.e., such that the stressed substrate is entirely formed by the deposited stress-engineered substrate layers). In other cases, the stress-engineered layers are formed over a central core substrate. In each case, the stressed substrate includes at least one tensile stress layer having a residual tensile stress and at least one compressive stress layer having a residual compressive stress, where the compressive stress layer is operably integrally connected to the tensile stress layer such that residual tensile and compressive stresses are self-equilibrating (i.e., such that the laminated structure is stable), and

3

such that the residual tensile and compressive stresses are sufficient to cause complete powderization of the substrate upon application of a triggering force (i.e., an initial fracture) by way of a suitable trigger mechanism (e.g., one of a resistive heat element, a chemical reaction element, and a mechanical pressure element).

According to an aspect of the present invention, transient electronic systems are fabricated by forming a stressed substrate using the methods mentioned above, and then disposing (i.e., fabricating or mounting) one or more electronic elements and one or more trigger mechanisms on the stressed substrate. According to alternative embodiments, the electronic devices are attached to the stressed substrate using various techniques. In one exemplary embodiment, already-formed microelectronic circuit “chips” are attached to the substrate using a bonding method (such as using sealing glasses or anodic bonding) that allows crack propagation to destroy the adhered chips. That is, during the transience event, not only will the substrate fracture into small difficult to detect particles, but the bonded microelectronic devices will also fracture into small particulates as well. The final particle size after triggering is based upon factors such as the stress profile and substrate thickness. In one embodiment, the IC chip is thinned and/or patterned to provide fracture points (features) that assist in controlling the final fractured particle size (i.e., the fracture features are formed such that, when the substrate is powderized by release of the stored potential energy, the substrate fractures along the patterned fracture features. In another embodiment, standard thin-film fabrication (e.g., photolithographic or inkjet printing) techniques are used to fabricate the electronic devices directly into and/or on the stressed substrate such that, upon triggering, the energy released by the stressed substrate destroys the thin, brittle functional layers and all electronics formed thereon.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other features, aspects and advantages of the present invention will become better understood with regard to the following description, appended claims, and accompanying drawings, where:

FIG. 1 is a top side perspective view showing a transient electronic device produced in accordance with an exemplary embodiment of the present invention;

FIGS. 2(A), 2(B), 2(C), 2(D) and 2(E) are simplified cross-sectional side views showing the production of a stressed substrate according to an embodiment of the present invention;

FIGS. 3(A), 3(B), 3(C), 3(D) and 3(E) are simplified cross-sectional side views showing the production of a stressed substrate according to another embodiment of the present invention;

FIGS. 4(A), 4(B), 4(C), 4(D) and 4(E) are simplified cross-sectional side views showing the production of a stressed substrate according to another embodiment of the present invention;

FIGS. 5(A), 5(B), 5(C), 5(D), 5(E), 5(F) and 5(G) are cross-sectional side views showing a transient electronic device produced in accordance with another embodiment of the present invention;

FIGS. 6(A), 6(B), 6(C), 6(D), 6(E), 6(F) and 6(G) are cross-sectional side views showing a transient electronic device produced in accordance with another embodiment of the present invention; and

4

FIGS. 7(A), 7(B), 7(C), 7(D) and 7(E) are cross-sectional side views showing a transient electronic device produced in accordance with another embodiment of the present invention.

DETAILED DESCRIPTION OF THE DRAWINGS

The present invention relates to an improvement in transient electronic devices. The following description is presented to enable one of ordinary skill in the art to make and use the invention as provided in the context of a particular application and its requirements. As used herein, directional terms such as “upper”, “upward”, “lower”, “downward”, are intended to provide relative positions for purposes of description, and are not intended to designate an absolute frame of reference. Various modifications to the preferred embodiment will be apparent to those with skill in the art, and the general principles defined herein may be applied to other embodiments. Therefore, the present invention is not intended to be limited to the particular embodiments shown and described, but is to be accorded the widest scope consistent with the principles and novel features herein disclosed.

FIG. 1 is a simplified diagram including perspective views showing a transient electronic device **100** in a pre-transience “whole” state (i.e., device **100(t0)** shown in the middle portion of FIG. 1) and a post-transience “powderized” state (i.e., device **100(t1)** shown in the lower portion of FIG. 1). Referring to the middle of FIG. 1, in the pre-transience state (e.g., immediately after production), transient electronic device **100(t0)** generally includes an integrated circuit (functional) layer **120** and a trigger mechanism **130** that are disposed on a stressed substrate **110**, which is characterized as shown in the bubble at the upper portion of FIG. 1. Functional layer **120** of device **100(t0)** includes one or more electronic elements **122** that perform a prescribed useful function (e.g., sensor operations) up until the transient event. As described in additional detail below, trigger mechanism **130** initiates the transient event, e.g., by generating an initial fracture F_0 (shown in the bubble immediately below device **100(t0)**). As depicted by device **100(t1)**, the initial fracture propagates through stressed substrate **110** and the associated structures, causing the device to undergo powderization (i.e., fragmentation into tiny particles **101**, one of which is depicted in the bubble located in the lowermost portion of FIG. 1).

Referring to device **100(t0)** and to the bubble located in the uppermost portion of FIG. 1, stressed substrate **110** is a wafer-like structure including at least one tensile stress layer **110-1** having a residual tensile stress and at least one compressive stress layer **110-2** having a residual compressive stress. Tensile stress layer **110-1** and compressive stress layer **110-2** (collectively referred to herein as “stress-engineered layers”) are operably integrally connected together such that residual tensile and compressive stresses are self-equilibrating and produce a stress gradient (e.g., indicated by the simplified stress graph shown at the right of the bubble). As set forth in additional detail below, the stress-engineered layers **110-1** and **110-2** are fabricated either by post-treating a substrate material using strategies similar to glass tempering (e.g., by way of heat or chemical treatment), or by depositing the substrate layers using, for example chemical, vapor deposition techniques in which the deposition parameters (i.e., temperature, pressure, chemistry) are varied such that the layers collectively contain a significant inbuilt stress gradient. Note that the arrangement of stress-engineered layers **110-1** and **110-2** indicated in the upper

bubble is not intended to be limiting in that one or more non-stressed substrate layers may be disposed between the two stress-engineered layers, and in that the stress gradient is not necessarily linear.

Referring to the middle of FIG. 1, functional layer **120** includes a suitable base layer **121** preferably formed using a semiconductor material (e.g., SiO_2) that is compatible with existing IC fabrication techniques, and one or more electronic elements **122** that are fabricated on and in base layer **121** that perform one or more designated (e.g., sensor) operations. As described in additional detail below, functional layer **120** is operably attached to the stressed substrate **110** such that release of the potential energy powderizes both stressed substrate **110** and functional layer **120**, along with any electronic devices disposed thereon.

Referring to the lower-middle portion of FIG. 1, trigger mechanism **130** serves to initiate a transient event that controls the release of potential energy stored in stressed substrate **110** in response to a suitable trigger signal TS (e.g., an externally delivered current pulse or a radio frequency signal). As indicated in the middle bubble of FIG. 1, trigger mechanism **130** is disposed on substrate **110** and constructed such that the transient event is initiated, for example, by generating an initial fracture F_0 . As indicated in the middle bubble, this initial fracture F_0 is propagated by way of secondary fractures F_p that travel rapidly throughout stressed substrate **110**, whereby the potential energy stored in stressed substrate **110** is suddenly and catastrophically released in a manner that completely disaggregates (powderizes) the stressed substrate into micron-sized particulates **101** (i.e., having length L, width W, and height H dimensions that are less than approximately $100\ \mu\text{m}$ across, as illustrated in the bubble located at the bottom of FIG. 1).

According to an aspect of the present invention, the mechanism by which transient device **100** is powderized during the above-described transient event is similar to that associated with a Prince Rupert's Drop. A Prince Rupert's Drop is formed by simply dropping a bead of molten glass into water, cooling the surface of the drop much more rapidly than the bulk during solidification. This leads to compressive stress on the surface of the glass and tensile stress within the bulk. The resulting glass is very strong as the surface stress resists cracking, however the tail is thin enough that it can be broken; when this is done the elastic strain energy within the drop is released rapidly (fracture propagation steps are $>1000\ \text{ms}^{-1}$) and the drop is shattered into powder. The disaggregation of stressed substrate **110** in response to a transient event trigger signal TS is similar to that of a Prince Rupert's Drop, and hence the terms "powderize" and "powderization" are defined herein to describe a disaggregation event similar to that associated with a Prince Rupert's Drop.

Referring to the lower portion of FIG. 1, by utilizing suitable device fabrication techniques and trigger mechanisms (some of which are described below), the above-mentioned transient event facilitates the controlled nearly instantaneous powderization of the entirety of device **100** (t1) (i.e., functional layer **120**) into particles of $100\ \mu\text{m}$ or smaller that are not discernible by the human eye at greater than 50 cm viewing distance. That is, by storing sufficient potential energy in stressed substrate **110** to powderize functional layer **120**, and by providing trigger mechanism **130** for releasing the potential energy on command, the present invention facilitates the production of transient electronic devices **100** that reliably essentially disappear on command and in a significantly shorter amount of time than is possible using conventional (e.g., soluble substrate)

approaches. Moreover, because stressed substrate **110** is compatible with low-cost existing IC fabrication techniques, the present invention facilitates the production of transient electronic systems having custom-fabricated IC devices and/or the incorporation of high-performance off-the-shelf electronic devices with minimal (or potentially without any) modification to core IC fabrication process.

Various methods may be used to generate stressed substrate **110** utilized in transient electronic device **100** (shown in FIG. 1). A first approach to forming stressed substrates involves thin film sputter deposition. In thin film sputter deposition, generally two distinct regimes can be identified leading to very different film morphology and characteristics, and result in either compressive or tensile stress. Metals are often used because of functionality (e.g., electrical properties), their structural qualities (e.g., ductility), and the fact that a conductive sputter target allows for a simple, high yield, glow discharge DC magnetron sputtering process. However, stress-engineered metal oxides and glasses (silicon oxides) can be sputtered as well; these insulating or semiconducting films can be sputter deposited by either radiofrequency (RF) sputtering or by reactive sputtering in a mixed inert/reactive gas plasma (e.g. argon/oxygen). The assignee of the present invention has generated films of stress engineered vanadium oxide using the latter method, for use as temperature sensitive micro-probes. In addition, relatively thick oxide films have been sputter deposited and stress engineered in order to minimize intrinsic stress.

To achieve reliable powderization yielding fragmentation particulates $\leq 100\ \mu\text{m}$ in any lateral dimension, the presently preferred methodology for generating stressed substrates involves adapting stress-engineered thin film fabrication techniques with ion-exchange tempering to create optimal stress profiles in glass (SiO_2) substrates. The presently preferred stressed substrate fabrication methodologies are set forth in the exemplary embodiments described below with reference to FIGS. 2(A) to 2(E), 3(A) to 3(E), and 4(A) to 4(E).

FIGS. 2(A) to 2(E) illustrate a first methodology in which a stressed substrate **110A** is built up by patterned SiO_2 stressed substrates generated entirely using plasma vapor deposition (PVD) techniques. This methodology provides a high degree of control over the specific stress profile generated in the stressed substrate, and introduces a completely new way to create tempered glass, with continuous control over glass formulation and morphology through the thickness dimension of the stressed substrate. Referring to FIG. 2(A), a wafer **200** (e.g., silicon or other material) is coated with a release layer **210**, most likely a metal. In FIG. 2(B), a thick liftoff mask **220** is then patterned on release layer **210** such that mask **220** defines an opening **222**. Note that wafer **200**, release layer **210** and mask **220** form a sacrificial structure. Referring to FIGS. 2(C) and 2(D), PVD processing is then used to create the stress engineered layers **110A-1** and **110A-2** in opening **222**, placing stresses in the deposited substrate material **230-1** and **230-2**, for example, by altering the process parameters (e.g., using different temperatures T1 and T2 and/or pressures P1 and P2). Finally, as indicated in FIG. 2(E), the mask is then lifted off, and stressed substrate **110A** is singulated (removed) from the remaining sacrificial structure by underetching the release layer.

FIGS. 3(A) to 3(E) illustrate a second methodology in which a stressed substrate **110B** is built up by patterned SiO_2 on a thin glass core using PVD techniques. This methodology avoids a possible drawback to the first methodology (i.e., that the thick PVD processing proves unreliable), but in a similar manner provides a high degree of control over the

specific stress profile generated in the stressed substrate. Referring to FIG. 3(A), the process begins using a substantially unstressed glass core substrate **110B-0** having a thickness T_0 in the range of 25 μm and 100 μm . Suitable glass core substrates are currently produced by Schott North America, Inc. of Elmsford, N.Y., USA). Referring to FIGS. 3(B) to 3(E), SiO_2 is then deposited on alternating sides of core substrate **110B-0** via PVD using methods similar to those described above. Specifically, FIG. 3(B) shows the deposition of material **230-1** in a manner that forms stress-engineered layer **110B-11** on core substrate **110B-0**. FIG. 3(C) shows the deposition of material **230-2** in a manner that forms stress-engineered layer **110B-21** on an opposite side of core substrate **110B-0**. FIG. 3(C) shows the subsequent deposition of material **230-1** in a manner that forms stress-engineered layer **110B-12** on core layer **110B-11**, and FIG. 3(E) shows the deposition of material **230-2** in a manner that forms stress-engineered layer **110B-22** layer **110B-21**. FIG. 3(E) shows completed stressed substrate **110B** including core substrate (central, substantially unstressed layer) **110B-0** with stress-engineered layers **110B-11**, **110B-12**, **110B-21** and **110B-22** formed thereon. A possible drawback to this methodology is that, because core substrate **110B-0** is freestanding and the deposited stress-engineered layers have high stress, each stress-engineered layer must be made thin enough that no de-bonding or cracking occurs, and that core substrate **110B-0** is not caused to flex excessively. One possible approach will be to construct a custom fixture that can rotate the samples inside the deposition chamber during PVD. Another possible challenge will be developing suitable surface preparation and deposition process parameters so that good film adhesion is achieved.

FIGS. 4(A) to 4(E) illustrate a third methodology in which a stressed substrate **110C** is produced by subjecting a core substrate to one of an ion-exchange tempering treatment, a chemical treatment and a thermal treatment. Specifically, FIGS. 4(A) to 4(E) illustrate an exemplary ion-exchange tempering treatment during which various stress profiles are introduced in a core substrate via molten-salt ion exchange. FIG. 4(A) shows a core substrate **110C-0** over a vat **250** containing a molten-salt solution **255**. FIG. 4(B) shows core substrate **110C-0** immediately after submersion in molten-salt solution **255**, FIG. 4(C) shows core substrate **110C-0** after a first time period of submersion in molten-salt solution **255** in which a first stress-engineered layer **110C-1** is formed, and FIG. 4(D) shows the structure after a second time period of submersion in molten-salt solution **255** in which a second stress-engineered layer **110C-2** is formed on first stress-engineered layer **110C-1**. FIG. 4(E) shows completed stressed substrate **100C** including central core substrate **110C-0** and stress-engineered layers **110C-1** and **110C-2**.

According to a fourth methodology, a hybrid of the above second and third methods is employed in which diced, thin glass core substrates are ion-exchange tempered, and then multiple layers of SiO_2 are deposited on the tempered substrates to further increase the induced stresses. This combined approach has the advantage that much higher central tension values should be attainable by varying the parameters of the ion exchange or the thickness of the layering materials and their relative stress mismatch.

FIGS. 5(A) to 5(F) depict the fabrication and subsequent actuation of a transient electronic device **100D** according to another embodiment of the present invention.

FIG. 5(A) depicts a stressed substrate **110D** produced in accordance with any of the methodologies mentioned above.

FIGS. 5(B) and 5(C) depict the formation of a trigger mechanism **130D** on stressed substrate **110D** according to a currently preferred embodiment. Trigger mechanism **130D** is electrical, and more specifically utilizes a heating element to generate local heating in response to an applied electrical pulse. As indicated in these figures, trigger mechanism **130D** is constructed by forming a wide/thicker lower resistance electrodes **132D** (shown in FIG. 5(B)), and then forming a resistive, thin, narrow resistor structure **135D** (shown in FIG. 5(C)) between electrodes **132D**, where resistor structure **135D** is formed using a material that is capable of sustaining high temperature (e.g., a metal such as tungsten). Trigger mechanism **130D** is fabricated directly onto stressed substrate **110D** using standard microfabrication techniques (vapor deposition and photo-patterning) or simply through shadow-masked evaporation. The mechanism of fracture generated by trigger mechanism **130D** is hoop stress generated as the portion of stressed substrate **110D** heated by resistor structure **135D** expands. Simulation of such triggering mechanisms indicate that 0.5 ms after the current pulse is applied, tensile hoop stresses in the range of 100-150 MPa are present below the resistor structure—this would be sufficient to initiate fracture in almost any traditionally tempered glass. These simulation results show that large surface tensile stresses can be obtained with a modest amount of current and energy. In this example, based on resistance estimates using properties for tungsten, the current is approximately 70 mA, and the voltage developed across the resistor is about 80 mV. These amounts are well within the capabilities of currently available small-form-factor batteries.

FIG. 5(D) depicts the disposition of an IC device **120D** on stressed substrate **110D** according to a currently preferred embodiment. The preferred circuit proxy is a bare single-crystal silicon chip, thinned via CMP to realistic thicknesses. The inventors do not believe that the lack of CMOS processing layers changes the mechanical properties of the proxy chip significantly compared to actual chips. The key to achieving fragmentation of this type of chip is coupling the propagating cracks from stressed substrate **110D** into the silicon of IC chip **120D**. This process can be viewed as a competition between two possible outcomes: a crack can propagate upward into the silicon, or make a sharp turn and instead propagate through the bond region, leading to de-bonding. To exceed the ratio needed for a glass/silicon bond, a low-melting-point sealing glass **125D** is utilized to secure IC **120D** to stressed substrate **110D**. Alternatively, an anodic, eutectic and adhesive bonding is used to secure IC **120D** to stressed substrate **110D**.

FIGS. 5(E) to 5(G) illustrate the subsequent completion and actuation of transient electronic device **100D**. FIG. 5(E) depicts completed device **100D** formed by stressed substrate **110D**, IC chip (functional substrate or layer) **120D**, and triggering mechanism **130D**. FIGS. 5(F) and 5(G) show the subsequent controlled destruction (disaggregation) of device **100D**, with FIG. 5(F) depicting device **100D(t0)** during the transmission of a radio-frequency trigger signal RF-TS to triggering mechanism **130D**, which in turn generates an initial fracture F_0 in stressed substrate **110E** by way of localized heating, and FIG. 5(G) depicting the subsequent powdered device **100D(t1)** caused by the propagation of fractures throughout the various structures, thereby forming particles **101E(t1)**.

In addition to the localized heating approach described in the previous embodiment, other trigger mechanisms may be utilized to generate the initial fracture required to generate powderization of the stressed substrate. For example, suit-

able triggering mechanisms may be produced that generate localized fracturing using by initiating a chemical reaction on the surface of the stressed substrate, or by applying a localized mechanical pressure (e.g., using a piezoelectric element) to the stressed stressed substrate.

FIGS. 6(A) to 6(G) depict the fabrication and actuation of a transient electronic device **100E** according to another embodiment of the present invention in which defects sites are created to promote fracturing.

FIGS. 6(A) to 6(C) depict the generation of IC chips **120E** having the requisite feature features. FIG. 6(A) depicts a “normal” semiconductor (e.g., monocrystalline silicon) functional substrate **121F** during an established low-cost, high-volume (e.g., CMOS) fabrication process in which electronic elements are produced on upper surface **121F**. FIG. 6(B) depicts functional substrate **121E** after lower surface **121L** is subject to polishing (i.e., to reduce the substrate thickness), and the generation of patterned fracture features **125E** by laser beams **260** directed onto lower surface **121L** from a laser ablation tool using known laser-scoring techniques. Alternatively, a process similar to “stealth dicing” technology developed by Hamamatsu Photonics K.K. of Japan may be used, in which a laser focus internal to the silicon creates defects which promote crack-
ing. FIG. 6(C) shows subsequent dicing cuts **D** applied to segment the wafer into individual IC die **120E**.

FIGS. 6(D) to 6(G) illustrate the subsequent completion of transient electronic device **100E** using IC die **120E**. FIG. 6(D) depicts mounting IC die (functional substrate) **120E** on stressed substrate **110E**, which is produced in accordance with any of the methodologies mentioned above, by way of a sealing glass **127E** (or an anodic bond) in the manner described above. FIG. 6(E) depicts completed device **100E** formed by stressed substrate **110E**, IC chip (functional substrate or layer) **120E**, and a triggering mechanism **130E** formed in accordance with any of the embodiments mentioned above. FIGS. 6(F) and 6(G) show the subsequent controlled destruction (disaggregation) of device **100E**, with FIG. 6(F) depicting device **100E(t0)** during the transmission of trigger signal RF-TS to triggering mechanism **130E**, which in turn generates an initial fracture F_0 in stressed substrate **110E** according to one of the mechanisms mentioned above, and FIG. 6(G) depicting the subsequent powdered device **100E(t1)** caused by the propagation of fractures throughout the various structures, thereby forming particles **101E(t1)**. The resulting patterned fracture features (grooves) **125E** should have a much higher defect density than the base polished silicon, so cracks are expected to readily form at these features, whereby fragmentation (i.e., the size of particles **101E(t1)**) is controlled through the spacing of these defects.

FIGS. 7(A) to 7(C) depict the fabrication and actuation of a transient electronic device **100F** according to another exemplary embodiment of the present invention in which a thin-film polysilicon and/or amorphous silicon proxy is used to form electronic elements directly on a stressed substrate **100F**. FIG. 7(A) depicts a stressed substrate **110F** produced in accordance with any of the methodologies mentioned above with a base functional layer **120F** (e.g., polycrystalline or amorphous silicon) formed thereon, FIG. 7(B) depicts the subsequent generation of electronic elements **122** in and on base functional layer **120E-1** by way of existing large area electronic ink-jet print processes, and FIG. 7(C) depicts the subsequent generation of a triggering mechanism **130F** according to any of the embodiments mentioned above, thereby completing device **100F**. FIGS. 7(D) and 7(E) show the subsequent controlled destruction (disaggre-

gation) of device **100F**, with FIG. 7(D) depicting device **100F(t0)** during the transmission of trigger signal RF-TS to triggering mechanism **130F**, which in turn generates an initial fracture F_0 in stressed substrate **110F** according to one of the mechanisms mentioned above, and FIG. 7(E) depicting the subsequent powdered device **100F(t1)** caused by the propagation of fractures throughout the various structures, thereby forming particles **101F(t1)**. This embodiment may be useful, for example, if for some reason the single-crystal approach fails. That is, thin film circuitry **122F** represents a way to reach near-COTS-level performance with stressed substrates **110F**. If processed correctly, thin film silicon layer **120F** forms a bond to stressed substrate **110F** that is similar to that of the stressed substrate material (e.g., glass). Furthermore, polysilicon and amorphous silicon are weaker than single-crystal silicon, and existing thin-film printing processes allow very thin layers to be formed and processed as the functional materials directly on the stressed substrate (rather than requiring a thicker single-crystal silicon substrate as support between the transient substrate and the functional materials). For these reasons, this approach presents a relatively low risk path to demonstrating silicon circuit proxies on stressed substrates. However, there are challenges associated with this approach as well. For example, there are multiple handling and processing steps that will expose the substrates to stresses and thermal gradients that could inadvertently trigger fragmentation, so custom processing may need to be developed.

Although the present invention has been described with respect to certain specific embodiments, it will be clear to those skilled in the art that the inventive features of the present invention are applicable to other embodiments as well, all of which are intended to fall within the scope of the present invention.

The invention claimed is:

1. A transient electronic device comprising:

a stressed substrate including at least one tensile stress layer having a residual tensile stress and at least one compressive stress layer having a residual compressive stress and being operably integrally connected to the at least one tensile stress layer such that *the* residual tensile and compressive stresses are self-equilibrating; and

a trigger mechanism attached to the stressed substrate and [including means for generating] *configured to generate* an initial fracture in said stressed substrate, wherein said residual tensile and compressive stresses are sufficient to generate secondary fractures in response to said initial fracture that propagate [throughout] *through* said stressed substrate[, whereby said stressed substrate is powdered].

2. The transient electronic device of claim 1, further comprising a functional layer including one or more electronic elements, wherein the functional layer is bonded to the stressed substrate such that the secondary fractures propagate into said functional layer[, whereby said functional layer is powdered substantially simultaneously with said stressed substrate].

3. The transient electronic device of claim 2, wherein the functional [substrate] layer comprises silicon, and wherein the one or more electronic elements are integrally fabricated on the functional layer.

4. The transient electronic device of claim 1, wherein said stressed substrate further comprises a central, substantially unstressed layer.

11

5. The transient electronic device of claim 1, wherein said trigger mechanism [comprises one of means for applying resistive heating to] *is configured to heat* said stressed substrate, [means for initiating] *initiate* a chemical reaction in said stressed substrate, [and means for applying] *or apply* a mechanical pressure to said stressed [stressed] substrate to generate the initial fracture.

6. The transient electronic device of claim 2, wherein at least one of said functional layer and said substrate comprises a plurality of patterned fracture features formed such that[, when said substrate is powderized by release of said potential energy,] said substrate fractures along said plurality of patterned fracture features *in response to the initial fracture*.

7. The transient electronic device of claim 2, wherein said functional layer comprises one or more IC chips attached to the stressed substrate layer such that said IC chips [are powderized upon release of the potential energy] *fracture in response to the initial fracture*.

8. The transient electronic device of claim 7, wherein said IC chips are attached to the stressed *substrate* layer by one of a sealing glass and an anodic bond.

9. The transient electronic device of claim 1, wherein said functional layer comprises one or more thin-film electronic elements disposed directly on said stressed substrate.

10. A method for manufacturing a transient electronic device comprising:

forming a stressed substrate including at least one tensile stress layer having a residual tensile stress and at least one compressive stress layer having a residual compressive stress and being operably integrally connected to the at least one tensile stress layer such that residual tensile and compressive stresses are self-equilibrating; and

disposing a trigger mechanism *configured to generate an initial fracture in the stressed substrate* and one or more electronic elements on the stressed substrate.

11. The method of claim 10, wherein forming stressed substrate comprises depositing one or more substrate materials while varying applied process conditions such that the deposited substrate material forms a plurality of layer portions collectively forming a stress gradient.

12. The method of claim 11, wherein forming the stressed substrate comprises depositing said one or more substrate materials onto a sacrificial structure and then removing said [one or more] sacrificial structure.

13. The method of claim 11, wherein forming stressed substrate comprises depositing said one or more substrate materials onto a core substrate.

14. The method of claim 10, wherein forming stressed substrate comprises subjecting a core substrate to one of an ion-exchange tempering treatment, a chemical treatment and a thermal treatment.

12

15. The method of claim 10, wherein disposing said one or more electronic elements comprises fabricating said one or more electronic elements on a functional substrate and then attaching said functional substrate to said stressed substrate.

16. The method of claim 15, wherein fabricating said one or more electronic elements comprises forming said one or more electronic elements using a photolithographic semiconductor fabrication process flow.

17. The method of claim 15, wherein attaching said functional substrate to said stressed substrate comprises using one of a sealing glass and an anodic bond.

18. The method of claim 15, further comprising forming a plurality of patterned fracture features in said functional substrate.

19. The method of claim 10, wherein disposing said one or more electronic elements comprises forming said one or more electronic elements directly on the stressed substrate.

20. The method of claim 19, wherein forming said one or more electronic elements directly on the stressed substrate comprises printing one or more thin film electronic elements on the stressed substrate.

21. A method comprising:

actuating a trigger mechanism attached to a stressed substrate, the stressed substrate including at least one tensile stress layer having a residual tensile stress and at least one compressive stress layer having a residual compressive stress and being operably integrally connected to the at least one tensile stress layer such that the residual tensile and compressive stresses are self-equilibrating; and

generating an initial fracture in said stressed substrate in response to actuating the trigger mechanism, wherein the residual tensile and compressive stresses of the stressed substrate are sufficient to generate secondary fractures in response to the initial fracture, the secondary fractures propagating through the stressed substrate.

22. The method of claim 21, further comprising receiving a trigger signal, wherein actuating the trigger mechanism occurs in response to receiving the trigger signal.

23. The method of claim 22, wherein receiving the trigger signal comprises receiving a current pulse or a radio frequency signal.

24. The method of claim 21, wherein generating the initial fracture comprises heating the stressed substrate, initiating a chemical reaction in the stressed substrate, or applying mechanical pressure to the stressed substrate.

25. The method of claim 21, wherein the secondary fractures that propagate through the stressed substrate break a functional layer bonded to the stressed substrate.

* * * * *