

US00RE49097E

(19) **United States**
(12) **Reissued Patent**
Kahlbaugh et al.

(10) **Patent Number:** **US RE49,097 E**
(45) **Date of Reissued Patent:** ***Jun. 7, 2022**

(54) **FILTER MEDIUM AND STRUCTURE**

(71) Applicant: **Donaldson Company, Inc.,**
Minneapolis, MN (US)

(72) Inventors: **Brad E. Kahlbaugh**, Bloomington, MN (US); **Keh B. Dema**, Johnson City, TN (US); **Linda M. Olson**, Savage, MN (US); **Joe Israel**, St. Louis Park, MN (US); **Derek O. Jones**, Andover, MN (US); **Gregory L. LaVallee**, Monticello, MN (US); **Michael A. Madden**, Woodbury, MN (US); **Chuanfang Yang**, Eden Prairie, MN (US); **Robert M. Rogers**, Minnetonka, MN (US); **Paul L. Kojetin**, Rosemount, MN (US); **Timothy D. Sporre**, Brooklyn Park, MN (US)

(73) Assignee: **Donaldson Company, Inc.,**
Minneapolis, MN (US)

(*) Notice: This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/678,393**

(22) Filed: **Nov. 8, 2019**

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **7,314,497**
Issued: **Jan. 1, 2008**
Appl. No.: **11/267,958**
Filed: **Nov. 4, 2005**

U.S. Applications:

(63) Continuation of application No. 15/626,614, filed on Jun. 19, 2017, now Pat. No. Re. 47,737, which is an application for the reissue of Pat. No. 7,314,497.

(60) Provisional application No. 60/650,051, filed on Feb. 4, 2005, provisional application No. 60/625,439, filed on Nov. 5, 2004.

(51) **Int. Cl.**
B01D 39/20 (2006.01)
B01D 46/00 (2022.01)
B01D 46/10 (2006.01)
B01D 46/24 (2006.01)
B01D 46/52 (2006.01)

(52) **U.S. Cl.**
CPC **B01D 39/2024** (2013.01); **B01D 39/2089** (2013.01); **B01D 46/0068** (2013.01); **B01D 46/10** (2013.01); **B01D 46/2411** (2013.01); **B01D 46/521** (2013.01); **B01D 2275/10** (2013.01)

(58) **Field of Classification Search**
CPC .. B01D 39/2024; B01D 46/10; B01D 46/521; B01D 46/0068; B01D 46/2411; B01D 39/2089; B01D 2275/10; B01D 2239/0216; B01D 2239/0283; B01D 2239/06; B01D 2239/065; B01D 2239/12;

B01D 2239/1208; B01D 2239/1216;
B01D 2239/1225; B01D 2239/1233;
B01D 2239/1266; B01D 39/00; B01D 46/00

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

431,108 A	7/1890	Cowley
657,860 A	9/1900	Cummings
2,764,602 A	9/1956	Ahlbrecht
2,764,603 A	9/1956	Ahlbrecht
2,801,706 A	8/1957	Asker
2,803,656 A	8/1957	Ahlbrecht
3,019,127 A	1/1962	Czerwonka et al.
3,073,735 A	1/1963	Till et al.
3,147,064 A	9/1964	Brown
3,252,270 A	5/1966	Pall et al.
3,255,131 A	6/1966	Ahlbrecht
3,279,151 A	10/1966	Kauer, Jr. et al.
3,303,621 A	2/1967	Hill
3,448,038 A	6/1969	Pall et al.
3,450,755 A	6/1969	Ahlbrecht
3,505,794 A	4/1970	Nutter et al.
3,589,956 A	6/1971	Kranz et al.
3,595,731 A	7/1971	Davies et al.
3,616,160 A	10/1971	Wincklhofer et al.
3,616,183 A	10/1971	Brayford et al.
3,620,819 A	11/1971	Croce
3,639,195 A	2/1972	Sanders
3,653,181 A	4/1972	Becker
3,676,242 A	7/1972	Prentice
3,705,480 A	12/1972	Wireman
3,714,763 A	2/1973	Suzuki
3,728,848 A	4/1973	Vest, Jr.
3,744,256 A	7/1973	Cobb et al.
3,826,067 A	7/1974	Wilder et al.
3,841,953 A	10/1974	Lohkamp et al.
3,849,241 A	11/1974	Butin et al.

(Continued)

FOREIGN PATENT DOCUMENTS

AU	2005304879	5/2006
CN	1364095	8/2002

(Continued)

OTHER PUBLICATIONS

“Physical Properties and Compositions Testing Table”, U.S. Pat. No. 5,580,459 Examples, Dec. 10, 2012, (1 page)—previously presented by Patent Owner in parent reissue U.S. Appl. No. 15/626,614.*

(Continued)

Primary Examiner — Norca L. Torres Velazquez

(74) *Attorney, Agent, or Firm* — Mueting Raasch Group

(57) **ABSTRACT**

Thermoplastic bicomponent binder fiber can be combined with other media, fibers and other filtration components to form a thermally bonded filtration media. The filtration media can be used in filter units. Such filter units can be placed in the stream of a mobile fluid and can remove a particulate load from the mobile stream. The unique combination of media fiber, bicomponent binder fiber and other filtration additives and components provide a filtration media having unique properties in filtration applications.

70 Claims, No Drawings

US RE49,097 E

Page 2

(56)

References Cited

U.S. PATENT DOCUMENTS

3,878,014 A	4/1975	Melead	4,684,576 A	8/1987	Tabor et al.
3,891,417 A	6/1975	Wade	4,688,511 A	8/1987	Gerlach et al.
3,900,648 A	8/1975	Smith	4,689,057 A	8/1987	Gasper
3,917,448 A	11/1975	Wood	4,713,285 A	12/1987	Klein
3,934,238 A	1/1976	Pavlou	4,726,817 A	2/1988	Roger
3,937,860 A	2/1976	Gusman et al.	4,729,371 A	3/1988	Krueger et al.
3,971,373 A	7/1976	Braun	4,732,809 A	3/1988	Harris, Jr. et al.
3,972,694 A *	8/1976	Head 95/285	4,734,208 A	3/1988	Pall et al.
3,998,988 A	12/1976	Shimomai et al.	4,753,730 A	6/1988	Maurer
4,042,522 A	8/1977	Falk	4,759,782 A	7/1988	Miller et al.
4,045,350 A	8/1977	Kupf et al.	4,764,189 A	8/1988	Yanagawa et al.
4,047,914 A	9/1977	Hansen et al.	4,765,812 A	8/1988	Homonoff et al.
4,069,158 A	1/1978	Bertocchio et al.	4,765,915 A *	8/1988	Diehl 210/767
4,069,244 A	1/1978	Mueller	4,807,619 A	2/1989	Dyrud et al.
4,079,675 A	3/1978	Beumel, Jr.	4,814,033 A	3/1989	Spearman et al.
4,088,726 A	5/1978	Cumbers	4,816,224 A	3/1989	Vogel et al.
4,090,967 A	5/1978	Falk	4,836,931 A	6/1989	Spearman et al.
4,100,324 A	7/1978	Anderson et al.	4,838,903 A	6/1989	Thomaides et al.
4,102,785 A	7/1978	Head et al.	4,838,905 A	6/1989	Billiet et al.
4,111,815 A	9/1978	Walker et al.	4,840,838 A	6/1989	Wyss
4,160,059 A	7/1979	Samejima	4,868,032 A *	9/1989	Eian et al. 428/198
4,161,422 A	7/1979	Lawson et al.	4,874,666 A	10/1989	Kubo et al.
4,161,590 A	7/1979	Mueller	4,886,058 A	12/1989	Brostrom et al.
4,161,602 A	7/1979	Mueller	4,889,764 A *	12/1989	Chenoweth et al. 442/342
4,169,754 A	10/1979	Perrotta	4,904,385 A	2/1990	Wessling et al.
4,177,141 A	12/1979	Nakamura et al.	4,910,064 A	3/1990	Sabee
4,189,338 A	2/1980	Ejima et al.	4,911,789 A *	3/1990	Rieunier et al. 162/156
4,196,027 A	4/1980	Walker et al.	4,917,714 A	4/1990	Kinsley, Jr.
4,210,540 A	7/1980	Perrotta	4,919,753 A	4/1990	Johnson et al.
4,211,819 A	7/1980	Kunimune et al.	4,933,129 A	6/1990	Huykman
4,227,904 A	10/1980	Kasmak, Jr. et al.	4,983,434 A	1/1991	Sassa
4,231,768 A	11/1980	Seibert et al.	5,022,964 A	6/1991	Crane et al.
4,234,655 A	11/1980	Kunimune et al.	5,027,781 A	7/1991	Lewis
4,239,278 A	12/1980	Skilliter	5,034,040 A	7/1991	Walcott et al.
4,239,516 A	12/1980	Klein	5,042,468 A	8/1991	Lambert
4,254,731 A	3/1981	Taylor	5,045,210 A	9/1991	Chen et al.
4,267,016 A	5/1981	Okazaki et al.	5,057,368 A	10/1991	Largman et al.
4,269,888 A	5/1981	Ejima et al.	5,066,538 A	11/1991	Huykman
4,272,318 A	6/1981	Walker et al.	5,068,141 A	11/1991	Kubo et al.
4,274,914 A	6/1981	Keith et al.	5,080,791 A	1/1992	Sims
4,309,475 A	1/1982	Hoffman, Jr.	5,082,476 A	1/1992	Kahlbaugh et al.
4,318,774 A	3/1982	Powell et al.	5,087,278 A	2/1992	Suzuki
4,321,108 A	3/1982	Goddard et al.	5,089,119 A	2/1992	Day et al.
4,327,936 A	5/1982	Sekiguchi	5,092,911 A	3/1992	Williams et al.
4,370,152 A	1/1983	Luper	5,104,537 A	4/1992	Stifelman et al.
4,388,086 A	6/1983	Bauer et al.	5,108,827 A	4/1992	Gessner
4,423,995 A	1/1984	Karis	5,110,330 A	5/1992	Loughran
4,429,001 A	1/1984	Kolpin et al.	5,131,387 A	7/1992	French et al.
4,443,233 A	4/1984	Moran	5,135,792 A	8/1992	Hogan
4,457,974 A	7/1984	Summers	5,147,553 A	9/1992	Waite
4,460,642 A	7/1984	Errede et al.	5,147,721 A	9/1992	Baron et al.
4,487,617 A	12/1984	Dienes et al.	5,160,582 A	11/1992	Takahashi
4,500,384 A	2/1985	Tomioka et al.	5,167,764 A	12/1992	Nielsen et al.
4,501,598 A	2/1985	Long	5,167,765 A	12/1992	Nielsen et al.
RE31,849 E	3/1985	Klein	5,190,569 A	3/1993	McGrath
4,504,289 A	3/1985	Waller et al.	5,190,812 A *	3/1993	Joseph et al. 442/350
4,516,994 A	5/1985	Kocher	5,208,098 A	5/1993	Stover
4,536,440 A	8/1985	Berg	5,212,131 A	5/1993	Belding
4,545,789 A	10/1985	Lato	5,238,474 A	8/1993	Kahlbaugh et al.
4,548,624 A	10/1985	Waller	5,246,474 A	9/1993	Greatorex
4,551,378 A	11/1985	Carey, Jr.	5,246,772 A	9/1993	Manning
4,552,603 A	11/1985	Harris, Jr. et al.	5,275,743 A	1/1994	Miller et al.
4,555,430 A	11/1985	Mays	5,283,106 A *	2/1994	Seiler et al. 428/198
4,579,774 A	4/1986	Kuwazuru et al.	5,284,704 A	2/1994	Kochesky et al.
4,597,218 A	7/1986	Friemel et al.	5,284,997 A	2/1994	Spearman et al.
4,604,205 A *	8/1986	Ayers 210/497.2	5,286,802 A	2/1994	Uesugi et al.
4,610,678 A	9/1986	Weisman et al.	5,290,449 A	3/1994	Heagle et al.
4,627,863 A	12/1986	Klein	5,302,443 A	4/1994	Manning et al.
4,650,506 A	3/1987	Barris et al.	5,307,796 A	5/1994	Kronzer et al.
4,657,804 A	4/1987	Mays et al.	5,328,758 A	7/1994	Markell et al.
4,659,467 A	4/1987	Spearman	5,332,426 A	7/1994	Tang et al.
4,661,132 A	4/1987	Thornton et al.	5,334,446 A	8/1994	Quantrille et al.
4,676,807 A	6/1987	Miller	5,336,286 A	8/1994	Alexander et al.
4,677,929 A	7/1987	Harris	5,342,418 A	8/1994	Jesse
4,681,801 A *	7/1987	Eian et al. 442/361	5,344,698 A	9/1994	Rock et al.
			5,354,603 A *	10/1994	Errede et al. 442/361
			5,364,456 A	11/1994	Kahlbaugh et al.
			5,366,631 A	11/1994	Adiletta
			5,380,580 A	1/1995	Rogers et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

5,405,682 A	4/1995	Shawyer et al.	5,935,883 A	8/1999	Pike
5,415,676 A	5/1995	Tokar et al.	5,948,344 A	9/1999	Cusick et al.
5,423,892 A	6/1995	Kahlbaugh et al.	5,952,092 A	9/1999	Groeger et al.
5,436,980 A	7/1995	Weeks et al.	5,952,252 A *	9/1999	Shawver et al. 442/407
5,454,945 A	10/1995	Spearman	5,954,962 A	9/1999	Adiletta
5,456,982 A	10/1995	Hansen et al.	5,965,091 A	10/1999	Navarre et al.
5,458,960 A	10/1995	Nieminen et al.	5,965,468 A *	10/1999	Marmon et al. 442/340
5,468,572 A	11/1995	Zguris et al.	5,972,166 A	10/1999	Helwig et al.
5,472,467 A *	12/1995	Pfeffer 55/488	5,972,477 A	10/1999	Kim et al.
5,478,466 A	12/1995	Heilmann et al.	5,972,808 A	10/1999	Groeger et al.
5,486,410 A	1/1996	Groeger et al.	5,976,998 A	11/1999	Sandor et al.
5,508,079 A	4/1996	Grant et al.	5,981,410 A *	11/1999	Hansen et al. 442/361
5,508,093 A	4/1996	Mehdorn	5,989,432 A	11/1999	Gildersleeve et al.
5,509,340 A	4/1996	Kawamura	5,989,688 A	11/1999	Barge et al.
5,545,453 A	8/1996	Grant	5,993,501 A	11/1999	Cusick et al.
5,545,475 A	8/1996	Korleski	5,993,905 A	11/1999	Sheehan
5,565,062 A	10/1996	Nass et al.	5,993,943 A	11/1999	Bodaghi et al.
5,575,832 A	11/1996	Boyd	6,007,608 A	12/1999	Johnson
5,580,459 A	12/1996	Powers et al.	6,007,898 A	12/1999	Kim et al.
5,581,647 A	12/1996	Onishi et al.	6,013,587 A	1/2000	Truong et al.
5,584,784 A	12/1996	Wu	6,024,782 A *	2/2000	Freund et al. 96/154
5,597,654 A	1/1997	Scholz et al.	6,041,782 A	3/2000	Angadjivand et al.
5,603,747 A	2/1997	Matuda et al.	6,045,597 A	4/2000	Choi
5,605,746 A	2/1997	Groeger et al.	6,048,379 A	4/2000	Bray et al.
5,607,490 A	3/1997	Taniguchi et al.	6,071,419 A	6/2000	Beier et al.
5,607,735 A *	3/1997	Brown 428/36.1	6,071,641 A	6/2000	Zguris et al.
5,614,283 A	3/1997	Potnis et al.	6,077,391 A	6/2000	Gironi
5,616,408 A *	4/1997	Oleszczuk et al. 442/346	6,099,726 A	8/2000	Gembolis et al.
5,620,641 A	4/1997	Berger	6,103,181 A	8/2000	Berger
5,620,785 A *	4/1997	Watt et al. 428/219	6,103,643 A	8/2000	Forsten
5,633,082 A	5/1997	Berger	6,110,249 A	8/2000	Medcalf et al.
5,638,569 A	6/1997	Newell	6,114,262 A	9/2000	Groh et al.
5,643,467 A	7/1997	Romanco	6,136,058 A *	10/2000	Miller 55/524
5,643,653 A *	7/1997	Griesbach et al. 428/120	6,139,595 A	10/2000	Herman et al.
5,645,057 A *	7/1997	Watt et al. 128/206.12	6,143,049 A	11/2000	Gieseke et al.
5,645,689 A	7/1997	Ruf et al.	6,143,441 A	11/2000	Zguris
5,645,690 A	7/1997	Cox, Jr.	6,146,436 A	11/2000	Hollingsworth et al.
5,652,048 A	7/1997	Haynes et al.	6,152,120 A	11/2000	Julazadeh
5,662,728 A *	9/1997	Groeger 96/153	6,156,682 A	12/2000	Fletemier et al.
5,665,235 A *	9/1997	Gildersleeve et al. 210/503	6,156,842 A	12/2000	Hoenig et al.
5,667,562 A	9/1997	Midkiff	6,165,572 A *	12/2000	Kahlbaugh et al. 428/36.1
5,669,949 A	9/1997	Dudrey et al.	6,169,045 B1	1/2001	Pike et al.
5,672,399 A *	9/1997	Kahlbaugh et al. 428/36.1	6,171,355 B1	1/2001	Gieseke et al.
5,672,415 A *	9/1997	Sawyer et al. 428/219	6,171,369 B1 *	1/2001	Schultink et al. 95/57
5,677,058 A	10/1997	Neal et al.	6,171,684 B1 *	1/2001	Kahlbaugh et al. 428/212
5,679,042 A	10/1997	Varona	6,174,603 B1	1/2001	Berger
5,681,469 A	10/1997	Barboza	6,183,536 B1	2/2001	Schultink et al.
5,705,119 A	1/1998	Takeuchi et al.	6,186,992 B1	2/2001	Roe et al.
5,709,735 A *	1/1998	Midkiff et al. 96/17	6,187,073 B1	2/2001	Gieseke et al.
5,711,878 A	1/1998	Ogata et al.	6,190,768 B1	2/2001	Turley et al.
5,721,180 A	2/1998	Pike et al.	6,197,709 B1 *	3/2001	Tsai et al. 442/347
5,728,187 A *	3/1998	Kern et al. 55/486	6,200,669 B1 *	3/2001	Marmon et al. 428/198
5,728,298 A	3/1998	Hamlin	6,203,713 B1	3/2001	Tanny
5,753,002 A	5/1998	Glucksman	6,241,886 B1	6/2001	Kitagawa et al.
5,755,963 A	5/1998	Sugiura et al.	6,251,224 B1	6/2001	Dong
5,779,847 A	7/1998	Groeger	6,264,044 B1 *	7/2001	Meyering et al. 210/490
5,783,505 A	7/1998	Duckett	6,267,252 B1	7/2001	Amsler
5,785,725 A *	7/1998	Cusick et al. 55/382	6,267,843 B1	7/2001	Helwig et al.
5,792,711 A	8/1998	Roberts	6,290,739 B1	9/2001	Gieseke et al.
5,795,835 A	8/1998	Bruner et al.	6,300,261 B1	10/2001	Young et al.
5,800,586 A	9/1998	Cusick et al.	6,301,887 B1	10/2001	Gorel et al.
5,800,587 A	9/1998	Kahlbaugh	6,306,539 B1	10/2001	Zguris
5,800,884 A	9/1998	D'Anna et al.	6,316,107 B1	11/2001	Lubnin et al.
5,804,286 A *	9/1998	Quantrille et al. 428/198	6,322,604 B1	11/2001	Midkiff
5,820,646 A	10/1998	Gillingham et al.	6,330,883 B1	12/2001	Berger
5,837,018 A	11/1998	Goerg	6,351,078 B1	2/2002	Wang et al.
5,837,627 A	11/1998	Halabisky et al.	6,352,947 B1	3/2002	Haley et al.
5,840,245 A	11/1998	Coombs et al.	6,355,076 B2	3/2002	Gieseke et al.
5,853,439 A	12/1998	Gieseke et al.	6,355,079 B1	3/2002	Sorvari et al.
5,883,439 A	3/1999	Saitoh	6,364,976 B2	4/2002	Fletemier et al.
5,885,390 A	3/1999	Alkire et al.	6,365,001 B1	4/2002	Helwig et al.
5,885,696 A	3/1999	Groeger	6,371,977 B1	4/2002	Bumbarger et al.
5,911,213 A	6/1999	Ahlborn et al.	6,372,004 B1	4/2002	Schultink et al.
5,932,104 A	8/1999	Kawamura	6,384,369 B1	5/2002	Stenersen et al.
5,935,879 A	8/1999	Helwig et al.	6,395,153 B1	5/2002	Matousek et al.
			6,406,789 B1	6/2002	McDaniel et al.
			6,409,785 B1	6/2002	Smithies et al.
			6,409,787 B1	6/2002	Smithies et al.
			6,419,721 B1	7/2002	Hunter

(56)

References Cited

U.S. PATENT DOCUMENTS

6,419,839 B1	7/2002	Cox et al.	6,875,249 B2	4/2005	Gogins
6,420,626 B1	7/2002	Erspamer et al.	6,878,191 B2	4/2005	Escaffre et al.
6,428,610 B1 *	8/2002	Tsai et al. 96/15	6,878,193 B2	4/2005	Kasmak, Jr.
6,440,192 B2	8/2002	Guerin et al.	6,883,321 B2	4/2005	Fornof
6,458,456 B1	10/2002	Zainiev et al.	6,900,148 B2	5/2005	Yoneda et al.
6,471,740 B2	10/2002	Kobayashi et al.	6,916,752 B2	7/2005	Berrigan et al.
6,478,953 B2	11/2002	Spearman et al.	6,918,939 B2	7/2005	Dworatzek et al.
6,479,147 B2	11/2002	Lubnin et al.	6,923,182 B2	8/2005	Angadjivand et al.
6,488,811 B1	12/2002	Dong	6,924,028 B2	8/2005	Chung et al.
6,492,183 B1	12/2002	Perman et al.	6,926,961 B2 *	8/2005	Roth 428/364
6,495,286 B2	12/2002	Zguris et al.	6,936,554 B1	8/2005	Singer
6,495,656 B1	12/2002	Haile et al.	6,939,386 B2 *	9/2005	Sato et al. 55/524
6,497,950 B1	12/2002	Haile et al.	6,939,492 B2	9/2005	Jackson et al.
6,503,447 B1	1/2003	Mondjian et al.	6,942,711 B2	9/2005	Faulkner et al.
6,511,774 B1	1/2003	Tsukuda et al.	6,955,708 B1	10/2005	Julos et al.
6,514,306 B1	2/2003	Rohrbach et al.	6,955,775 B2	10/2005	Chung et al.
6,517,612 B1	2/2003	Crouch et al.	6,962,615 B2	11/2005	Staudenmayer et al.
6,517,725 B2	2/2003	Spearman et al.	6,966,940 B2	11/2005	Krisko et al.
6,521,012 B2	2/2003	Lamon et al.	6,991,113 B2	1/2006	Nakajima
6,521,321 B2 *	2/2003	Kahlbaugh et al. 428/181	6,997,208 B2	2/2006	Mack
6,528,439 B1	3/2003	Stokes et al.	7,008,144 B2	3/2006	McGinn
6,530,366 B2	3/2003	Geiger et al.	7,008,465 B2	3/2006	Graham et al.
6,530,969 B2	3/2003	Gieseke et al.	7,011,011 B2	3/2006	Jessberger et al.
6,540,801 B2	4/2003	Gieseke et al.	7,017,563 B2	3/2006	Dworatzek et al.
6,541,114 B2	4/2003	Katou et al.	7,029,516 B2 *	4/2006	Campbell et al. 95/90
6,547,860 B2	4/2003	Buchwald et al.	7,033,410 B2	4/2006	Hilpert et al.
6,551,608 B2	4/2003	Yao	7,033,493 B2	4/2006	McGarvey et al.
6,555,489 B1 *	4/2003	Pfeffer 442/390	7,037,569 B2	5/2006	Curro et al.
6,576,034 B2 *	6/2003	Berger 55/527	7,049,254 B2 *	5/2006	Bansal et al. 442/347
6,579,342 B2	6/2003	Wang et al.	7,070,640 B2	7/2006	Chung et al.
6,585,808 B2	7/2003	Burban et al.	7,081,145 B2	7/2006	Gieseke et al.
6,588,641 B2	7/2003	Pritie	7,090,715 B2	8/2006	Chung et al.
6,602,311 B2	8/2003	Berger	7,094,270 B2 *	8/2006	Schultink et al. 55/486
6,607,997 B1	8/2003	Cox et al.	7,115,150 B2	10/2006	Johnson et al.
6,613,704 B1 *	9/2003	Arnold et al. 442/361	7,125,470 B2	10/2006	Graef et al.
6,616,723 B2 *	9/2003	Berger 55/527	7,163,349 B2	1/2007	Politicchio et al.
6,624,099 B1	9/2003	Shah	7,174,612 B2	2/2007	Ortega et al.
6,627,252 B1	9/2003	Nanjundiah et al.	7,182,537 B2	2/2007	Politicchio et al.
H2086 H	10/2003	Amsler	7,182,804 B2	2/2007	Gieseke et al.
6,645,388 B2	11/2003	Sheikh-Ali	7,267,789 B2	9/2007	Chhabra et al.
6,646,179 B1	11/2003	Melius et al.	7,278,542 B2	10/2007	Dussaud et al.
6,649,547 B1	11/2003	Arnold et al.	7,288,338 B2	10/2007	Zguris
6,652,614 B2	11/2003	Gieseke et al.	7,309,372 B2	12/2007	Kahlbaugh et al.
6,653,381 B2	11/2003	Thames et al.	7,314,497 B2	1/2008	Kahlbaugh et al.
6,673,864 B2	1/2004	Patel et al.	7,329,623 B2	2/2008	Kinn et al.
6,682,576 B1	1/2004	Kiyotani et al.	7,520,994 B2	4/2009	Dong et al.
6,682,809 B2	1/2004	Van Rheenen	7,717,975 B2	5/2010	Kalayci et al.
6,695,148 B2	2/2004	Homonoff et al.	7,737,224 B2	6/2010	Willis et al.
6,705,270 B1	3/2004	Rau et al.	7,772,456 B2	8/2010	Zhang et al.
6,706,086 B2	3/2004	Emig et al.	7,896,941 B2	3/2011	Choi
6,723,142 B2	4/2004	Emerson et al.	7,918,913 B2	4/2011	Kalayci et al.
6,723,149 B2	4/2004	Ernst et al.	7,985,344 B2	7/2011	Dema et al.
6,723,669 B1 *	4/2004	Clark et al. 442/347	8,021,455 B2	9/2011	Adamek et al.
6,726,751 B2	4/2004	Sause et al.	8,021,457 B2	9/2011	Dema et al.
6,740,142 B2	5/2004	Buettner et al.	8,021,547 B2	9/2011	Hukki
6,743,273 B2	6/2004	Chung et al.	8,057,567 B2	11/2011	Webb et al.
6,758,873 B2	7/2004	Gieseke et al.	8,096,290 B2	1/2012	Karlsson
6,770,356 B2	8/2004	O'Donnell et al.	8,177,875 B2	5/2012	Rogers et al.
6,792,925 B2	9/2004	Dworatzek et al.	8,267,681 B2	9/2012	Hemant et al.
6,797,377 B1	9/2004	DeLucia et al.	8,268,033 B2	9/2012	Rogers et al.
6,815,383 B1	11/2004	Arnold	8,277,529 B2	10/2012	Rogers et al.
6,818,037 B2	11/2004	Tamaka et al.	8,404,014 B2	3/2013	Israel et al.
6,821,321 B2 *	11/2004	Chinn et al. 96/108	8,460,424 B2	6/2013	Rogers et al.
6,821,672 B2	11/2004	Zguris	8,512,435 B2	8/2013	Rogers et al.
6,830,656 B2	12/2004	Kinsley, Jr. et al.	8,641,796 B2	2/2014	Rogers et al.
6,835,311 B2	12/2004	Koslow	9,795,906 B2	10/2017	Rogers et al.
6,848,866 B1	2/2005	McGinn	9,885,154 B2	2/2018	Gupta et al.
6,849,330 B1	2/2005	Morin et al.	10,610,813 B2 *	4/2020	Rogers B01D 46/0068
6,852,148 B2	2/2005	Gieseke et al.	2001/0000375 A1 *	4/2001	Kobayashi et al. 55/502
6,858,057 B2	2/2005	Healey	2001/0033932 A1	10/2001	Katou et al.
6,860,917 B2	3/2005	Henrichsen et al.	2002/0007167 A1	1/2002	Dan et al.
6,866,692 B2	3/2005	Emerson et al.	2002/0013111 A1 *	1/2002	Dugan et al. 442/335
6,872,431 B2 *	3/2005	Kahlbaugh et al. 428/36.1	2002/0016120 A1	2/2002	Nagano et al.
6,872,674 B2	3/2005	Williams et al.	2002/0083690 A1 *	7/2002	Emig et al. 55/382
6,874,641 B2	4/2005	Clary	2002/0106478 A1	8/2002	Hayase et al.
			2002/0116910 A1 *	8/2002	Berger 55/258
			2002/0092423 A1	9/2002	Gillingham et al.
			2002/0121194 A1 *	9/2002	Buchwald et al. 96/66
			2002/0127939 A1 *	9/2002	Hwo et al. 442/347

(56)

References Cited

FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS					
2002/0148776	A1	10/2002	Cousart et al.	CN	1543520 A
2002/0148876	A1	10/2002	Pritie	CN	101098741
2002/0193030	A1	12/2002	Yao et al.	CN	101934172
2003/0008214	A1	1/2003	Zguris	DE	101947400
2003/0019193	A1 *	1/2003	Chinn et al. 55/486	DE	4344819
2003/0022575	A1 *	1/2003	Yoneda et al. 442/104	DE	202005020566
2003/0039815	A1	2/2003	Roth	EP	0451554
2003/0082979	A1	5/2003	Bean et al.	EP	0465203
2003/0084788	A1 *	5/2003	Fraser, Jr. 95/285	EP	0904819
2003/0087568	A1	5/2003	Kinn et al.	EP	1036585
2003/0089092	A1 *	5/2003	Bause et al. 55/524	EP	1 141 454 A1
2003/0096549	A1	5/2003	Ortega et al.	EP	0844861
2003/0099576	A1	5/2003	Li et al.	EP	1 378 283 B1
2003/0106294	A1	6/2003	Chung et al.	EP	1 179 673 A3
2003/0109190	A1 *	6/2003	Geel 442/342	EP	1179673
2003/0139110	A1 *	7/2003	Nagaoka et al. 442/347	EP	1171495
2003/0145569	A1 *	8/2003	Sato et al. 55/524	EP	1118632
2003/0148691	A1 *	8/2003	Pelham et al. 442/347	EP	1141454
2003/0150820	A1	8/2003	Dussaud et al.	EP	1378283
2003/0211069	A1	11/2003	Deckner et al.	EP	1827649
2003/0211799	A1	11/2003	Yao et al.	EP	1894609
2004/0038014	A1	2/2004	Schaefer et al.	EP	1938883
2004/0116026	A1	6/2004	Kubose et al.	EP	2308579
2004/0134355	A1 *	7/2004	Kasmak, Jr. 96/154	EP	2311542
2004/0192141	A1 *	9/2004	Yang et al. 442/342	EP	2311543
2004/0211400	A1	10/2004	Basset	EP	1 827 649 B1
2004/0221436	A1	11/2004	Ortega et al.	EP	2 311 542 B1
2004/0242108	A1	12/2004	Russell et al.	EP	2 311 543 B1
2004/0255783	A1	12/2004	Graham et al.	EP	2 308 579 B1
2005/0000876	A1	1/2005	Knight	EP	3138621
2005/0026526	A1	2/2005	Verdegan et al.	GB	1532076
2005/0109683	A1	5/2005	Joyce et al.	JP	55117615
2005/0130031	A1	6/2005	Zguris	JP	57099716
2005/0160711	A1 *	7/2005	Yang 55/524	JP	58205520
2005/0210844	A1 *	9/2005	Kahlbaugh et al. 55/486	JP	60025521
2005/0211232	A1	9/2005	Dushek et al.	JP	62-079822
2005/0214188	A1 *	9/2005	Rohrbach et al. 423/237	JP	63126955
2005/0215965	A1	9/2005	Schmidt et al.	JP	64-014399
2005/0233665	A1 *	10/2005	Groten et al. 442/340	JP	H03270703
2006/0009106	A1 *	1/2006	Nishimura et al. 442/404	JP	H06-126112
2006/0086344	A1	4/2006	Karlsson	JP	06-218210
2006/0094320	A1	5/2006	Chen et al.	JP	06233909
2006/0096263	A1	5/2006	Kahlbaugh et al.	JP	H06-218210 A
2006/0096932	A1 *	5/2006	Dema et al. 210/767	JP	H07-031677
2006/0101796	A1 *	5/2006	Kern et al. 55/524	JP	7265640
2006/0121811	A1 *	6/2006	Mangold et al. 442/392	JP	08196829
2006/0137317	A1 *	6/2006	Bryner et al. 55/528	JP	08206421
2006/0207932	A1 *	9/2006	Hajek et al. 210/502.1	JP	H08-323121 A
2006/0230731	A1 *	10/2006	Kalayci et al. 55/486	JP	09000841
2006/0242933	A1 *	11/2006	Webb et al. 55/486	JP	H09-095893 A
2006/0246798	A1	11/2006	Reneker et al.	JP	H09-192423
2006/0266701	A1	11/2006	Dickerson et al.	JP	10046486
2007/0039300	A1	2/2007	Kahlbaugh et al.	JP	10156116
2007/0062855	A1	3/2007	Chase et al.	JP	10161962
2007/0210008	A1	9/2007	Sprenger et al.	JP	10165731
2007/0227359	A1	10/2007	Choi	JP	H11-216316
2008/0035103	A1	2/2008	Barris et al.	JP	H11-309315
2008/0073296	A1	3/2008	Dema et al.	JP	2000-202235 A
2008/0245037	A1	10/2008	Rogers et al.	JP	2000-246097 A
2009/0044702	A1	2/2009	Adamek et al.	JP	2002-046201 A
2009/0050578	A1	2/2009	Israel et al.	JP	2002085918
2009/0266759	A1	10/2009	Green et al.	JP	2002177718
2010/0187171	A1	7/2010	Gupta	JP	2003290617 A
2010/0187712	A1	7/2010	Gupta et al.	JP	2003325411
2011/0154790	A1	6/2011	Israel et al.	JP	2004002176
2011/0215046	A1	9/2011	Rogers et al.	JP	2004017041 A
2011/0309012	A1	12/2011	Rogers	JP	2004-066737 A
2012/0210689	A1	8/2012	Rogers et al.	JP	2004160328
2012/0312738	A1	12/2012	Rogers et al.	JP	2004160361
2013/0008846	A1	1/2013	Rogers et al.	JP	2004188355
2014/0197094	A1	7/2014	Rogers et al.	JP	2004255230
2017/0225105	A1	8/2017	Rogers et al.	JP	2004305853
				JP	2006-055735
				JP	2006512530
				JP	2008518770 A
				JP	2008518772 A
				JP	5340598 B2

(56)

References Cited

FOREIGN PATENT DOCUMENTS

KP	10165731	6/1998
KR	19950011179	9/1995
KR	19990030043	4/1999
KR	19990030043 A	4/1999
RU	2389529	5/2010
WO	1989/003716	1/1989
WO	89/03716 A1	5/1989
WO	1993010881	6/1993
WO	1994005396	3/1994
WO	9513856	5/1995
WO	1997041167	11/1997
WO	199748846	12/1997
WO	9803716	1/1998
WO	1999047211	9/1999
WO	0032854	6/2000
WO	2000032295	6/2000
WO	2000059969	10/2000
WO	2001003802	1/2001
WO	0107143	2/2001
WO	200110929	2/2001
WO	2001041898	6/2001
WO	0147618	7/2001
WO	0185824	11/2001
WO	2001085824	11/2001
WO	0245098	6/2002
WO	2003013732	2/2003
WO	2003080904	10/2003
WO	2003080905	10/2003
WO	2003013732	1/2004
WO	2004089509	10/2004
WO	2005005696	1/2005
WO	2005005704	1/2005
WO	2005075054	8/2005
WO	2005082488	9/2005
WO	2005083240	9/2005
WO	2005120678	12/2005
WO	2006052656	5/2006
WO	2006052732	5/2006
WO	2006052732	6/2006
WO	2006089063	8/2006
WO	2007133403	11/2007
WO	2007133403	1/2008
WO	2008103821	8/2008
WO	2008103821	10/2008
WO	2009088647	7/2009

OTHER PUBLICATIONS

Hutten, Section 6.7 "Solidity and Porosity," in Handbook of Non-woven Filter Media. Elsevier, Oxford, UK; 2007. Cover page, publisher's page, and pp. 250-253.*

ASTM D 737-04 "Standard Test Method for Air Permeability of Textile Fabrics", Jan. 2005, ASTM International, West Conshohocken, Pennsylvania, 5 pages.

ASTM D 737-96 "Standard Test Method for Air Permeability of Textile Fabrics", Apr. 1996, ASTM International, West Conshohocken, Pennsylvania, 5 pages.

"Chinese Office Action", for Chinese Application No. 200580046000.4, corresponding to U.S. Appl. No. 11/591,330, dated May 24, 2012, (pp. 12) Including English translation.

"Chinese Office Action", for Chinese Application No. 200580046000.4, corresponding to U.S. Appl. No. 11/591,330, dated Nov. 22, 2011, (pp. 12) Including English translation.

"Cost Effective Emissions Solutions for Diesel Engines", Donaldson Company brochure, 2004, 4 pages.

Dahiya, A et al., "Dry-Laid Nonwovens", <http://www.engr.utk.edu/mse/pages/Textiles/Dry%20Laid%20Nonwovens.htm>, (Apr. 2004), 10 pages.

"European Office Action", from the European Patent Office in EP Patent Application No. 06720573.2-1213, corresponding to U.S. Appl. No. 11/883,690, dated May 13, 2011, (pp. 3).

"Examiner's Pre-Review Report", for Japanese Patent Application No. 2007-540069, dated Feb. 8, 2013 (4 pages).

"Examiner Report", from CA Application No. 2586636, dated Feb. 8, 2012 (pp. 1-5).

"Extended European Search Report", from EP Application No. 07119967.3, corresponding to U.S. Appl. No. 11/381,010, dated May 6, 2008, pp. 1-6.

"Extended European Search Report", from EP Application No. 10010697.0, dated Mar. 9, 2011, pp. 1-4.

"Extended European Search Report", dated Mar. 3, 2011, in co-pending European Patent Application 10010698.8 (4 pages).

"File History", for co-pending U.S. Appl. No. 10/892,538, filed Nov. 5, 2004, entitled "Filter Media and Structure" (History occurring after May 18, 2011 IDS Filing: 49 pages).

"File History", for co-pending U.S. Appl. No. 10/982,538, filed Nov. 5, 2004, entitled "Filter Media and Structure" (History occurring after May 18, 2011 IDS Filing: 49 pages).

"File History", for co-pending U.S. Appl. No. 11/381,010, filed May 1, 2006, entitled "Filter Medium and Breather Filter Structure", (325 pages).

"File History", for co-pending U.S. Appl. No. 11/986,377, filed Nov. 20, 2007, entitled "High Strength, High Capacity Filter Media and Structure", (275 pages).

"File History", for co-pending U.S. Appl. No. 12/694,913, filed Jan. 27, 2010, entitled "Fibrous Media", (188 pages).

"File History", for co-pending U.S. Appl. No. 12/694,935, filed Jan. 27, 2010, entitled "Method and Apparatus for Forming a Fibrous Media", (183 pages).

"File History", for co-pending US. Appl. No. 11/381,010, filed May 1, 2006, entitled "Filter Medium and Breather Filter Structure" (History occurring after May 18, 2011 IDS Filing: 51 Pages).

"File History", for co-pending US. Appl. No. 11/381,010, filed May 1, 2006, entitled "Filter Medium and Breather Filter Structure" (History occurring after Aug. 31, 2011 IDS Filing: 39 Pages).

"File History", for co-pending US. Appl. No. 11/986,377, filed Nov. 20, 2007, entitled "High Strength, High Capacity Filter Media and Structure" (History occurring after May 18, 2011 IDS Filing: 9 pages).

"File History", for co-pending U.S. Appl. No. 12/694,935, filed Jan. 27, 2010, entitled "Method and Apparatus for Forming a Fibrous Media" (History occurring after May 18, 2011 IDS Filing: 86 pages).

"File History", for co-pending US. Appl. No. 12/694,935, filed Jan. 27, 2010, entitled "Method and Apparatus for Forming a Fibrous Media" (History occurring after Aug. 31, 2011 IDS Filing: 58 pages).

"File History", for co-pending US. Appl. No. 12/694,913, filed Jan. 27, 2010, entitled "Fibrous Media" (History occurring after May 18, 2011 IDS Filing: 63 pages).

"File History", for co-pending US. Appl. No. 12/694,913, filed Jan. 27, 2010, entitled "Fibrous Media" (History occurring after Aug. 31, 2011 IDS Filing: 13 pages).

"Filter Bag", Nonwoven Industry, Mar. 1992, vol. 23, No. 3, pp. 5 and 68.

"Filtration—Daiwabo and Kyowa Jointly Produce Microfiber Filter", Nonwovens Markets Feb. 14, 1992, vol. 7, No. 4, p. 5.

"Final Office Action", from JP Application No. 2007-540069, corresponding to US. Appl. No. 11/267,958, dated Jul. 2, 2012, (pp. 4).

"Final Office Action", from JP Application No. 2007-540069, corresponding to US. Appl. No. 11/267,958, dated Jul. 22, 2011, (pp. 18) Including English translation.

"Final Office Action", Final Office Action from KR Application No. 10-2007-7012741, dated Feb. 21, 2013, 8 pgs.

"Final Rejection", for Japanese Application No. 2011-233239, dated Apr. 5, 2013 (7 pages).

"First Office Action", for Chinese Application No. 201010255252.0, corresponding to U.S. Appl. No. 11/381,010, dated May 25, 2011, (pp. 16) Including English translation.

"First Office Action", for Chinese Application No. 201010255270.9, corresponding to U.S. Appl. No. 11/267,958, dated Aug. 25, 2011, (pp. 14) Including English translation.

(56)

References Cited

OTHER PUBLICATIONS

"2.2 The Fourdrinier", http://www.paper.org.uk/papertech/data/unit_03/2_mechanical_methods/2-2_fourdrinier . . . Sep. 24, 2007, 7 pages.

Frautmann, P et al., "High Performance Nanofibre Coated Filter Media for Engine Intake Air Filtration", *Filtration*, vol. 6, No. 1, pp. 53-56 (2006).

Hagewood, J. , "Bicomponent Filtration: Variable Capacity Continuous Extended Area Filter", *International Fiber Journal* Feb. 1998, vol. 14, No. 1, pp 58-67.

Hansen, L et al., "Water Absorption and Mechanical Properties of Electrospun Structured Hydrogels", *Journal of Applied Polymer Science*, vol. 95, pp. 427 -434 (2005).

"HEPA & 95% DOP Panel Filters", Donaldson Company Torit brochure, 2004, 4 pages.

Hinds, W, *Aerosol Technology Properties, Behavior, and Measurement of Airborne Particles*, Second Edition, (Copyright 1999), 3 pages.

Hutten, *Handbook of Nonwoven Filter Media*, 2007, pp. 114-115 and 247.

"Japanese Office Action", from JP Application No. 2011233239, dated Jul. 30, 2012, (pp. 1-2).

Ko, F et al., "Electrospinning of Continuous Carbon Nanotube-Filled Nanofiber Yarns", *Adv. Mater.*, vol. 15, No. 14, pp. 1161-1165, (Jul. 17, 2003).

"Korean Office Action", from KR Application No. 10-2007-7012741, dated Jul. 19, 2012, (pp. 1-27), including English translation.

Lennox-Kerr, "Advances in Textiles Technology", *International Newsletters Ltd.*, UK Sep. 2003 , vol. 153, 3 pages.

"Migration of Superabsorbent Polymer (SAP) Media Downstream of Filtration", *Velcron Filters, Inc. Service Bulletin*, May 2007, <http://www.velcon.com/doc/Vol6-Npl-05.21.07.pdf>.

"Non-Final Office Action", dated May 3, 2012 in co-pending U.S. Appl. No. 11/884,743, "Aerosol Separator" (31 pages).

"Non-Final Office Action", dated Jul. 19, 2011 in co pending U.S. Appl. No. 11/883,690, "Aerosol Separator; and Method" (14 pages).

"Non-Final Office Action", dated Oct. 28, 2011 in co-pending U.S. Appl. No. 13/110,148, "Filter Medium and Structure" (30 pages).

"Non-Final Office Action", dated Apr. 28, 2011 in co pending U.S. Appl. No. 11/381,010, "Filter Medium and Breather Filter Structure" (30 pages).

"Non-Final Office Action", dated Jun. 29, 2012 in co-pending U.S. Appl. No. 13/461,228, 18 pages.

"Non-Final Office Action", dated Dec. 22, 2011 in co-pending U.S. Appl. No. 13/222,063, "Filter Medium and Structure" (24 pages).

"Non-Final Office Action", dated Jan. 7, 2013 in co-pending U.S. Appl. No. 13/591,699, "Filter Medium and Breather Filter Structure," pp. 1-58 (58 pages).

"Notice of Allowance", from JP Application No. 2009147316, dated Apr. 11, 2011, (pp. 1-8).

"Notice of Allowance", for Mexico Application No. MX/a/2010/008502, dated Apr. 23, 2013 (2 pages).

"Notice of Allowance", dated Aug. 31, 2011 in co-pending U.S. Appl. No. 11/381,010, "Filter Medium and Breather Filter Structure" (6 pages).

"Notice of Allowance", dated Jan. 17, 2012 in co-pending U.S. Appl. No. 11/883,690, "Aerosol Separator; and Method" (26 pages).

"Notice of Allowance", dated May 7, 2012 in co-pending U.S. Appl. No. 13/110,148, "Filter Medium and Structure" (11 pages).

"Notice of Allowance", dated Jun. 25, 2012 in co-pending U.S. Appl. No. 13/222,063, "Filter Medium and Structure," (10 pages).

"Notice of Allowance Received", dated Nov. 26, 2012 in co-pending U.S. Appl. No. 11/884,743, "Aerosol Separator," (60 pages).

"Notice of Allowance", from U.S. Appl. No. 13/591,669, dated May 16, 2013, 20 pages.

"Office Action", for Chinese Application No. 2005800460004, dated Feb. 21, 2011, (10 pages), including English translation.

"PCT International Search Report and Written Opinion", from International Application No. PCT/US2005/039793, corresponding to U.S. Appl. No. 10/982,538, dated Mar. 23, 2006, pp. 1-11.

"PCT International Search Report and Written Opinion", from International Application No. PCT/US2007/00963, corresponding to U.S. Appl. No. 11/381,010, dated Nov. 21, 2007, pp. 1-14.

"PCT International Search Report and Written Opinion", from International Application No. PCT/U82008/054574, corresponding to U.S. Appl. No. 12/036,022, dated Aug. 29, 2008, pp. 1-11.

"PCT Written Opinion", from International Application No. PCT/US2005/039971 (WO2006052732), pp. 1-4.

"PCT Written Opinion", from International Application No. PCT/US2005/039793 (WO 2006052656), corresponding to U.S. Appl. No. 10/982,538, pp. 1-6.

"PCT Written Opinion", from International Application No. PCT/US2007/09963 (WO 2007133403), corresponding to U.S. Appl. No. 11/381,010, pp. 1-7.

"PCT Written Opinion", from International Application No. PCT/US2008/054574 (WO 2008103821), corresponding to U.S. Appl. No. 12/036,022, pp. 1-5.

"Physical Properties and Compositions Testing Table", U.S. Pat. No. 5,580,459 Examples, Dec. 10, 2012, (1 page).

Puurinen, "Multilayering of Fine Paper With 30 Layer Headbox and Roll and Blade Gap Former", *Helsinki University of Technology, Laboratory of Paper Technolo Reports, Series A19* May 14, 2004, pp. 1-54.

"Response to Chinese Office Action", dated Aug. 25, 2011 Filed in the Chinese Patent Office on Nov. 29, 2011 for Chinese Patent Application No. 201010255270.9, corresponding to U.S. Appl. No. 11/267,958, (pp. 15).

"Response to Chinese Office Action", dated Mar. 8, 2011 Filed in the Chinese Patent Office on Jul. 11, 2011 for Chinese Patent Application No. 200580046000.4, corresponding to U.S. Appl. No. 11/267,958, (pp. 25).

"Response to Chinese Office Action", dated May 25, 2011 Filed in the Chinese Patent Office on Nov. 29, 2011 for Chinese Patent Application No. 201010255252.0, corresponding to U.S. Appl. No. 11/267,958, (pp. 18).

"Response to Chinese Office Action", dated Nov. 22, 2011 Filed in the Chinese Patent Office on Jan. 18, 2012 for Chinese Patent Application No. 200580046000.4 corresponding to U.S. Appl. No. 11/267,958, (pp. 15).

"Response to Office Communication", Response to European Examination Report, dated Jul. 19, 2011, Filed in the European Patent Office on Oct. 11, 2011 for EP Patent Application No. 07119965.7, corresponding to U.S. Appl. No. 13/222,063, (pp. 48).

"Second Office Action", for Chinese Application No. 201010255252.0, corresponding to U.S. Appl. No. 11/381,010, dated Jun. 19, 2012 pp. 20) Including English translation.

"Second Office Action", for Chinese Application No. 201010255270.9, corresponding to U.S. Appl. No. 11/267,958, dated May 17, 2012, (pp. 19) Including English translation.

"Second Office Action", from CA Application No. 2586636, dated May 23, 2012 (pp. 1-4).

"Third Office Action", from CN Application No. 201010255252.0, dated Jan. 29, 2013, 10 pages.

"Three-Dimensional Structure Incorporates Heterofil Fibre and Carbon Beads", *Nonwovens Report, International* Oct. 1995 , No. 295, pp. 8-9.

Trautmann, P et al., "High Performance Nanofibre Coated Filter Media for Engine Intake Air Filtration", *Filtration*, vol. 6, No. 1, pp. 53-56 (2006) (9 pages).

Zhao, R., "An Investigation of Bicomponent Polypropylene/Poly(ethylene Terephthalate) Melt Blown Microfiber Nonwovens, A Dissertation", *Front Cover* Dec. 2001, pp. i-xix, pp. 1-207, 3 information pages.

Decision of the Opposition Division, Grounds for the Decision, & Annex to the Communication in EP2311542, dated Jan. 22, 2018, 29 pages.

Preparation for Oral Proceedings & Annex in EP2308579, dated Sep. 13, 2017, 7 pages.

(56)

References Cited

OTHER PUBLICATIONS

Decision of the Opposition Division, Grounds for the Decision, & Annex to the Communication in EP2308579, dated Apr. 6, 2018, 28 pages.

Donaldson Company Torit® brochure entitled “HEPA & 95% DOP Panel Filters”, 4 pages (2004).

Donaldson Company brochure entitled “Cost Effective Emissions Solutions for Diesel Engines”, 4 pages (2004).

* cited by examiner

FILTER MEDIUM AND STRUCTURE

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue; a claim printed with strikethrough indicates that the claim was canceled, disclaimed, or held invalid by a prior post-patent action or proceeding.

[RELATED APPLICATION] *RELATED APPLICATIONS*

[This application claims priority under 35 U.S.C. §119(e) to U.S. provisional application Ser. Nos. 60/625,439 filed Nov. 5, 2004 and 60/650,051 filed Feb. 4, 2005, incorporated by reference herein.]

This application is a continuation reissue application of U.S. Reissue application Ser. No. 15/626,614, filed Jun. 19, 2017, and is an application for reissue of U.S. Pat. No. 7,314,497, which issued from U.S. patent application Ser. No. 11/267,958 on Jan. 1, 2008, and which claims the benefit of U.S. Application No. 60/625,439 filed Nov. 5, 2004, and U.S. Application No. 60/650,051 filed Feb. 4, 2005.

FIELD OF THE INVENTION

The invention relates to a formed layer, a filtration medium or media, and a filter having strength, compressibility and high capacity for particulate removal from a moving fluid (air, gas, or liquid) stream. The filter and filter medium comprises a non-woven web made suitable for particulate removal from mobile liquids and gases using permeability, efficiency, loading and other filtration parameters. The invention relates to non-woven media layers obtaining sufficient tensile strength, wet strength, burst strength and other properties to survive the common operating conditions, such as variation in flow rate, temperature, pressure and particulate loading while removing substantial particulate loads from the fluid stream. The invention further relates to filter structures comprising one or more layers of the particulate removing media with other layers of similar or dissimilar media. These layers can be supported on a porous or perforate support and can provide mechanical stability during filtering operations. These structures can be formed into any of many filter forms such as panels, cartridge, inserts, etc. This disclosure relates to media layers and to methods of filtration of gas and aqueous or non-aqueous liquids. Gaseous streams can include both air and industrial waste gasses. Liquids can include water, fuels, oil, hydraulics, and others. The disclosure also relates to systems and methods for separating entrained particulate from the gas or liquid. The invention also relates to hydrophobic fluids (such as oils or an aqueous oil emulsion or other oil mixture) that are entrained as aerosols, from gas streams (for example airborne aerosol or aerosols in crankcase gases). Preferred arrangements also provide for filtration of other fine contaminants, for example carbon material, from the gas streams. Methods for conducting the separations are also provided.

BACKGROUND OF THE INVENTION

Non-woven webs for many end uses, including filtration media, have been manufactured for many years. Such structures can be made from bicomponent or core shell materials are disclosed in, for example, Winckelhofer et al., U.S. Pat.

No. 3,616,160; Sanders, U.S. Pat. No. 3,639,195; Perrotta, U.S. Pat. No. 4,210,540; Gessner, U.S. Pat. No. 5,108,827; Nielsen et al., U.S. Pat. No. 5,167,764; Nielsen et al., U.S. Pat. No. 5,167,765; Powers et al., U.S. Pat. No. 5,580,459; Berger, U.S. Pat. No. 5,620,641; Hollingsworth et al., U.S. Pat. No. 6,146,436; Berger, U.S. Pat. No. 6,174,603; Dong, U.S. Pat. No. 6,251,224; Amsler, U.S. Pat. No. 6,267,252; Sorvari et al., U.S. Pat. No. 6,355,079; Hunter, U.S. Pat. No. 6,419,721; Cox et al., U.S. Pat. No. 6,419,839; Stokes et al., U.S. Pat. No. 6,528,439; Amsler, U.S. Pat. No. H2,086, U.S. Pat. No. 5,853,439; U.S. Pat. No. 6,171,355; U.S. Pat. No. 6,355,076; U.S. Pat. No. 6,143,049; U.S. Pat. No. 6,187,073; U.S. Pat. No. 6,290,739; and U.S. Pat. No. 6,540,801; U.S. Pat. No. 6,530,969. This application incorporates by reference PCT Publication WO 01/47618 published on Jul. 5, 2001, and PCT Publication WO 00/32295 published on Jun. 8, 2000. Such structures have been applied and made by both air laid and wet laid processing and have been used in fluid, both gaseous and air and aqueous and non-aqueous liquid filtration applications, with some degree of success. In this regard we have found that the non-woven webs that are used for particulate removal from mobile fluids often suffer from a number of disadvantages.

Many attempts to obtain such non-woven structures with suitable perforate supports have been made. In many melt blown materials and layers made with thermal lamination techniques, the resulting structures often obtain incorrect pore sizes, reduced efficiency, reduced permeability, lack of strength or other problems rendering the media or filter structure insufficient for useful fluid filtration applications.

A substantial need exists for filtration media, filter structures and filtration methods that can be used for removing particulate materials from fluid streams, and in particular gaseous streams such as air, aqueous, and non-aqueous liquids such as lubricating oils and hydraulic fluids. The invention provides such media, filtration structures and methods and provides a unique media or media layer combinations that achieve substantial permeability, high media strength, substantial efficiency and long filtration life.

Certain gas streams, such as blow-by gases from the crankcase of diesel engines, carry substantial amounts of entrained oils therein, as aerosol. The majority of the oil droplets within the aerosol are generally within the size of 0.1-5.0 microns. In addition, such gas streams also carry substantial amounts of fine contaminant, such as carbon contaminants. Such contaminants generally have an average particle size of about 0.5-3.0 microns. It is preferred to reduce the amount of such contaminants in these systems. A variety of efforts have been directed to the above types of concerns. The variables toward which improvements are desired generally concern the following:

- (a) size/efficiency concerns; that is, a desire for good efficiency of separation while at the same time avoidance of a requirement for a large separator system;
- (b) cost/efficiency; that is, a desire for good or high efficiency without the requirement of substantially expensive systems; (c) versatility; that is, development of systems that can be adapted for a wide variety of applications and uses, without significant re-engineering; and, (d) cleanability/regeneratability; that is, development of systems which can be readily cleaned (or regenerated) if such becomes desired, after prolonged use.

BRIEF DESCRIPTION OF THE INVENTION

We have found a filter medium or media and a unique filter structure capable of efficiently removing particulate

from a mobile fluid stream under a variety of conditions. The medium of the invention combines high strength with excellent filtration properties. The invention comprises a thermally bonded sheet, filter medium or filter containing a shaped or formed medium. Combining substantial proportions of an organic or inorganic media fiber, a bicomponent thermoplastic binder fiber, optionally a resin binder, a secondary fiber or other filtration materials in a formed layer makes these sheet materials. The use of the bicomponent fiber enables the formation of a media layer or filter element that can be formed with no separate resin binder or with minimal amounts of a resin binder that substantially reduces or prevents film formation from the binder resin and also prevents lack of uniformity in the media or element due to migration of the resin to a particular location of the media layer. The use of the bicomponent fiber permits reduced compression, improves solidity, increases tensile strength and improves utilization of media fiber such as glass fiber and other fine fiber materials added to the media layer or filter element. Media fiber is that fiber that provides filtration properties to the media such as controllable pore size, permeability and efficiency. Further, the bicomponent fiber obtains improved processability during furnish formulation, sheet or layer formation and downstream processing including thickness adjustment, drying, cutting and filter element formation. These components combine in various proportions to form a high strength material having substantial filtration capacity, permeability and filtration lifetime. The media of the invention can maintain, intact, filtration capacity for substantial periods of time at substantial flow rates and substantial efficiency.

We have found a filter media and a unique filter structure capable of removing particulate from a fluid stream. The media comprises a thermally bonded sheet, media, or filter made by combining a substantial proportion of a media fiber and a bicomponent thermoplastic binder fiber. The media can comprise glass fiber, a fiber blend of differing fiber diameters, a binder resin and a bicomponent thermoplastic binder fiber. Such a media can be made with optional secondary fibers and other additive materials. These components combine to form a high strength material having substantial flow capacity, permeability and high strength. The media of the invention can maintain intact filtration capacity at high pressure for a substantial period of time. The media and filter operate at substantial flow rate, high capacity and substantial efficiency.

A first aspect of the invention comprises a filtration media or medium having a thermally bonded non-woven structure.

A second aspect of the invention comprises a bilayer, tri layer or multilayer (4-20, 4-64 or 4-100 layers) filtration medium or media. In one embodiment, the medium comprises the mobile fluid passing first through one layer comprising a loading layer and subsequently through another layer comprising an efficiency layer. A layer is a region of the material containing a different fibrous structure that may be attained by changing the amount of fiber, the sizes or amount of different fibers used, or by changing the process conditions. Layers may be made separately and combined later or simultaneously.

A third aspect of the invention comprises a filter structure. The structure can comprise a media layer or can comprise a 2 to 100 filtration media layer of the invention. Such layers can comprise a loading layer filtration media of the invention, and an efficiency layer filtration media of the invention or combinations thereof also combined with other filtration layers, support structures and other filter components.

A fourth aspect having high filtration performance comprises a depth loading media that does not compress or tear when subjected to application conditions or conversion processes. Such media can have low solidity as a result of relatively large spacing bicomponent and filter fiber.

A fifth aspect of the invention comprises a method of filtering the mobile fluid phase having a particulate load using the filtration aspects of the invention. The pervious support structure can support the media under the influence of fluid under pressure passing through the media and support. The mechanical support can comprise additional layers of the perforate support, wire support, a high permeability scrim or other support. This media commonly is housed in a filter element, panel, cartridge or other unit commonly used in the filtration of non-aqueous or aqueous liquids.

An additional aspect of the invention comprises a method of filtering with preferred crankcase ventilation (CCV) filters. It particularly concerns use of advantageous filter media, in arrangements to filter crankcase gases. The preferred media is provided in sheet form from a wet laid process. It can be incorporated into filter arrangements, in a variety of ways, for example by a wrapping or coiling approach or by providing in a panel construction. According to the present disclosure, filter constructions for preferred uses to filter blow-by gases from engine crankcases are provided. Example constructions are provided. Also provided are preferred filter element or cartridge arrangements including the preferred type of media. Further, methods are provided.

Medium materials of the invention can be used in a variety of filter applications including pulse clean and non-pulse cleaned filters for dust collection, gas turbines and engine air intake or induction systems; gas turbine intake or induction systems, heavy duty engine intake or induction systems, light vehicle engine intake or induction systems; vehicle cabin air; off road vehicle cabin air, disk drive air, photocopier-toner removal; HVAC filters in both commercial or residential filtration applications. Paper filter elements are widely used forms of surface loading media. In general, paper elements comprise dense mats of cellulose, synthetic or other fibers oriented across a gas stream carrying particulate material. The paper is generally constructed to be permeable to the gas flow, and to also have a sufficiently fine pore size and appropriate porosity to inhibit the passage of particles greater than a selected size therethrough. As the gases (fluids) pass through the filter paper, the upstream side of the filter paper operates through diffusion and interception to capture and retain selected sized particles from the gas (fluid) stream. The particles are collected as a dust cake on the upstream side of the filter paper. In time, the dust cake also begins to operate as a filter, increasing efficiency.

In general, the invention can be used to filter air and gas streams that often carry particulate material entrained therein. In many instances, removal of some or all of the particulate material from the stream is necessary for continued operations, comfort or aesthetics. For example, air intake streams to the cabins of motorized vehicles, to engines for motorized vehicles, or to power generation equipment; gas streams directed to gas turbines; and, air streams to various combustion furnaces, often include particulate material therein. In the case of cabin air filters it is desirable to remove the particulate matter for comfort of the passengers and/or for aesthetics. With respect to air and gas intake streams to engines, gas turbines and combustion furnaces, it is desirable to remove the particulate material

5

because it can cause substantial damage to the internal workings to the various mechanisms involved. In other instances, production gases or off gases from industrial processes or engines may contain particulate material therein. Before such gases can be, or should be, discharged through various downstream equipment or to the atmosphere, it may be desirable to obtain a substantial removal of particulate material from those streams. In general, the technology can be applied to filtering liquid systems. In liquid filtering techniques, the collection mechanism is believed to be sieving when particles are removed through size exclusion. In a single layer the efficiency is that of the layer. The composite efficiency in a liquid application is limited by the efficiency of the single layer with the highest efficiency. The liquids would be directed through the media according to the invention, with particulates therein trapped in a sieving mechanism. In liquid filter systems, i.e. wherein the particulate material to be filtered is carried in a liquid, such applications include aqueous and non-aqueous and mixed aqueous/non-aqueous applications such as water streams, lube oil, hydraulic fluid, fuel filter systems or mist collectors. Aqueous streams include natural and man-made streams such as effluents, cooling water, process water, etc. Non-aqueous streams include gasoline, diesel fuel, petroleum and synthetic lubricants, hydraulic fluid and other ester based working fluids, cutting oils, food grade oil, etc. Mixed streams include dispersions comprising water in oil and oil in water compositions and aerosols comprising water and a non-aqueous component.

The media of the invention comprises an effective amount of a bicomponent binder fiber. "Bicomponent fiber" means a thermoplastic material having at least one fiber portion with a melting point and a second thermoplastic portion with a lower melting point. The physical configuration of these fibers is typically in a "side-by-side" or "sheath-core" structure. In side-by-side structure, the two resins are typically extruded in a connected form in a side-by-side structure. One could also use lobed fibers where the tips have lower melting point polymer. "Glass fiber" is fiber made using glass of various types. The term "secondary fibers" can include a variety of different fibers from natural synthetic or specialty sources. Such fibers are used to obtain a thermally bonded media sheet, media, or filter, and can also aid in obtaining appropriate pore size, permeability, efficiency, tensile strength, compressibility, and other desirable filter properties. The medium of the invention is engineered to obtain the appropriate solidity, thickness, basis weight, fiber diameter, pore size, efficiency, permeability, tensile strength, and compressibility to obtain efficient filtration properties when used to filter a certain mobile stream. Solidity is the solid fiber volume divided by the total volume of the filter medium, usually expressed as a percentage. For example, the media used in filtering a dust-laden air stream can be different from a media used for filtering a water or oil aerosol from an air stream. Further, the media used to remove particulates from a liquid stream can be different than a media used to remove particulates from an gaseous stream. Each application of the technology of the invention obtains from a certain set of operating parameters as discussed below.

The media of the invention can be made from a media fiber. Media fibers include a broad variety of fibers having the correct diameter, length and aspect ratio for use in filtration applications. One preferred media fiber is a glass fiber. A substantial proportion of glass fiber can be used in the manufacture of the media of the invention. The glass fiber provides pore size control and cooperates with the

6

other fibers in the media to obtain a media of substantial flow rate, high capacity, substantial efficiency and high wet strength. The term glass fiber "source" means a glass fiber composition characterized by an average diameter and aspect ratio that is made available as a distinct raw material. Blends of one or more of such sources do not read on single sources.

We have found that by blending various proportions of bicomponent and media fiber that substantially improved strength and filtration can be obtained. Further, blending various fiber diameters can result in enhanced properties. Wet laid or dry laid processes can be used. In making the media of the invention, a fiber mat is formed using either wet or dry processing. The mat is heated to melt thermoplastic materials to form the media by internally adhering the fibers. The bicomponent fiber used in the media of the invention permits the fiber to fuse into a mechanically stable sheet, media, or filter. The bicomponent fiber having a thermally bonding exterior sheath causes the bicomponent fiber to bind with other fibers in the media layer. The bicomponent fiber can be used with an aqueous or solvent based resin and other fibers to form the medium.

In the preferred wet laid processing, the medium is made from an aqueous furnish comprising a dispersion of fibrous material in an aqueous medium. The aqueous liquid of the dispersion is generally water, but may include various other materials such as pH adjusting materials, surfactants, defoamers, flame retardants, viscosity modifiers, media treatments, colorants and the like. The aqueous liquid is usually drained from the dispersion by conducting the dispersion onto a screen or other perforated support retaining the dispersed solids and passing the liquid to yield a wet paper composition. The wet composition, once formed on the support, is usually further dewatered by vacuum or other pressure forces and further dried by evaporating the remaining liquid. After liquid is removed, thermal bonding takes place typically by melting some portion of the thermoplastic fiber, resin or other portion of the formed material. The melt material binds the component into a layer.

The media of this invention can be made on equipment of any scale from laboratory screens to commercial-sized papermaking. For a commercial scale process, the bicomponent mats of the invention are generally processed through the use of papermaking-type machines such as commercially available Fourdrinier, wire cylinder, Stevens Former, Roto Former, Inver Former, Venti Former, and inclined Delta Former machines. Preferably, an inclined Delta Former machine is utilized. The general process involves making a dispersion of bicomponent fibers, glass fibers, or other medium material in an aqueous liquid, draining the liquid from the resulting dispersion to yield a wet composition, and adding heat to form, bond and dry the wet non-woven composition to form the useful medium.

DETAILED DESCRIPTION OF THE INVENTION

The media of the invention relates to a composite, non-woven, air laid or wet laid media having formability, stiffness, tensile strength, low compressibility, and mechanical stability for filtration properties; high particulate loading capability, low pressure drop during use and a pore size and efficiency suitable for use in filtering fluids. Preferably, the filtration media of the invention is typically wet laid and is made up of randomly oriented array of media fiber, such as a glass fiber, and a bicomponent fiber. These fibers are bonded together using the bicomponent fiber and sometimes

with the addition of a binder resin to the invention. The media that can be used in the filters and methods of the invention contain an inorganic fiber, a bicomponent binder fiber, a binder and other components. The media fiber of the invention can include organic fibers such as natural and synthetic fibers including polyolefin, polyester, nylon, cotton, wool, etc. fibers. The media fiber of the invention can include inorganic fiber such as glass, metal, silica, polymeric fibers, and other related fibers.

The preferred filter structure of the invention comprises at least one media layer of the invention supported on a mechanically stable perforate support structure. The media and support are often packaged in a panel, cartridge or other filter format. The media layer can have a defined pore size for the purpose of removing particulates from fluid streams having a particle size of about 0.01 to 100 micrometers, from gas streams containing liquids in the form of a mist having droplet size of about 0.01 to 100 micrometers, from aqueous streams having a particle size of about 0.1 to 100 micrometers from non-aqueous streams having a particle size of about 0.05 to 100 micrometers or from fuel, lubricant or hydraulic streams having a particle size of about 0.05 to 100 micrometers.

Mechanical attributes are important for filter media including wet and dry tensile strength, burst strength, etc. Compressibility characteristic is important. Compressibility is the resistance (i.e.) to compression or deformation in the direction of fluid flow through the media. This must be sufficient to maintain a material's thickness and thereby maintain its pore structure and filtration flow and particulate removal performance. Many high efficiency wet laid materials using conventional resin saturation, melt blown materials, and other air laid materials lack this compressive strength and collapse under pressure. This is especially a problem with liquid filters, but can also be a problem with gas filters. In addition, media that are pleated must have sufficient tensile strength for processing into a finished filter with an integrated pleated structure. For example, pleating, corrugating, winding, threading, unwinding, laminating, coating, ultrasonically welding, dimpling or various other rolled goods operations. Materials without sufficient tensile strength may break during these processes.

Compressive strength is defined here as the percent change in thickness when the pressure applied during thickness measurement is increased. Compressive strengths typical of the materials made by the invention are as follows:

Compressive strength when pressure varied from 1.25 lb-in⁻² to 40 lb-in⁻²: 8% to 40%

Compressive strength when pressure varied from 0.125 lb-in⁻² to 0.625 lb-in⁻²: 10% to 20%

Tensile strength is defined here as the peak load is typically expressed as a peak load per unit width of dry media when running a force deflection test. The tensile strength will usually vary with sheet orientation. The orientation of interest for rolled goods operations is the machine direction. The range of machine direction tensile strength for these bicomponent sheets is from about 2 lb/(in width) to about 40 lb/(in width) or 5 lb/(in width) to about 35 lb/(in width). This will obviously vary with thickness and quantity of bicomponent fibers.

A filter with a gradient structure where the media pores become smaller on the downstream side is often helpful. In other words, the porous structure becomes continuously denser going from upstream to downstream side. As a result, the particles or contaminants to be filtered are able to penetrate to varying depths dependent on particle size. This causes the particles or contaminants to be distributed

throughout the depth of the filter material, reducing the build up of pressure drop, and extending the life of the filter.

In other cases, for example, when filtering oil or water mists out of gas streams, it is often advantageous to use a filter with a gradient structure where the media pores become larger on the downstream side. In other words, the porous structure becomes less dense going from the upstream to downstream side. Generally, this results in less fiber surface area in the downstream regions. As a result, the captured droplets are forced to come together and coalesce into larger droplets. At the same time, these downstream regions are more open and allow the now larger droplets to drain from the filter material. These types of gradient structures may be made in a single layer by stratifying the finer fibers either downstream or upstream, or by forming and combining several discrete layers by applying a series of differing furnishes. Often, when combining discrete layers, the laminating techniques result in loss of useful filtration surface area. This is true of most adhesive laminating systems performed by coating one surface with adhesive and then contacting the layers together, whether this is done in a homogeneous coating or in a dot pattern. The same is true of point-bonded material using ultrasonic bonding. A unique feature when using bicomponent fibers in the filter sheet or material is the bicomponent not only bonds the fibers of individual layers together, but can also act to bond the layers together. This has been accomplished in conventional heat lamination as well as through pleating.

The filter media of the present invention is typically suited for high efficiency filtration properties such that fluids, including air and other gasses, aqueous and non-aqueous fuel, lubricant, hydraulic or other such fluids can be rapidly filtered to remove contaminating particulates.

Pressure-charged diesel engines often generate "blow-by" gases, i.e., a flow of air-fuel mixture leaking past pistons from the combustion chambers. Such "blow-by gases" generally comprise a gas phase, for example air or combustion off gases, carrying therein: (a) hydrophobic fluid (e.g., oil including fuel aerosol) principally comprising 0.1-5.0 micron droplets (principally, by number); and, (b) carbon contaminant from combustion, typically comprising carbon particles, a majority of which are about 0.1-10 microns in size. Such "blow-by gases" are generally directed outwardly from the engine block, through a blow-by vent. Herein when the term "hydrophobic" fluids is used in reference to the entrained liquid aerosol in gas flow, reference is meant to non-aqueous fluids, especially oils. Generally such materials are immiscible in water. Herein the term "gas" or variants thereof, used in connection with the carrier fluid, refers to air, combustion off gases, and other carrier gases for the aerosol. The gases may carry substantial amounts of other components. Such components may include, for example, copper, lead, silicone, aluminum, iron, chromium, sodium, molybdenum, tin, and other heavy metals. Engines operating in such systems as trucks, farm machinery, boats, buses, and other systems generally comprising diesel engines, may have significant gas flows contaminated as described above. For example, flow rates can be about 2-50 cubic feet per minute (cfm), typically 5 to 10 cfm. In such an aerosol separator in for example a turbocharged diesel engine, air is taken to the engine through an air filter, cleaning the air taken in from the atmosphere. A turbo pushes clean air into engine. The air undergoes compression and combustion by engaging with pistons and fuel. During the combustion process, the engine gives off blow-by gases. A filter arrangement is in gas flow communication with engine and cleans the blow-by gases that are returned to the air intake or

induction system. The gasses and air is again pulled through by the turbo and into the engine. The filter arrangement in gas flow communication is used for separating a hydrophobic liquid phase from a gaseous stream (sometimes referred to herein as a coalescer/separator arrangement) is provided. In operation, a contaminated gas flow is directed into the coalescer/separator arrangement. Within the arrangement, the fine oil phase or aerosol phase (i.e., hydrophobic phase) coalesces. The arrangement is constructed so that as the hydrophobic phase coalesces into droplets, it will drain as a liquid such that it can readily be collected and removed from the system. With preferred arrangements as described herein below, the coalescer or coalescer/separator, especially with the oil phase in part loaded thereon, operates as a filter for other contaminant (such as carbon contaminant) carried in the gas stream. Indeed, in some systems, as the oil is drained from the system, it will provide some self-cleaning of the coalescer because the oil will carry therein a portion of the trapped carbon contaminant. The principles according to the present disclosure can be implemented in single stage arrangements or multistage arrangements. In many of the figures, multistage arrangements are depicted. In the general descriptions, we will explain how the arrangements could be varied to a single stage arrangement, if desired.

We have found, in one embodiment, that two filter media of this description can be combined in one embodiment. A loading layer and an efficiency layer can be used, each of said layers having distinct structures and filtration properties, to form a composite layer. The loading layer is followed in a fluid pathway by an efficiency layer. The efficiency layer is a highly efficient layer having suitable porosity, efficiency, permeability and other filtration characteristics to remove any remaining harmful particulate from the fluid stream as the fluid passes through the filter structure. The loading filtration media of the invention has a basis weight of about 30 to about 100 g-m⁻². The efficiency layer has a basis weight of about 40 to about 150 g-m⁻². The loading layer has an average pore size of about 5 to about 30 micrometers. The efficiency layer has a pore size smaller than the loading layer that ranges from about 0.5 to about 3 micrometers. The loading layer has a permeability that ranges from about 50 to 200 ft-min⁻¹. The efficiency layer has a permeability of about 5 to 30 ft-min⁻¹. The loading layer or the efficiency layer of the invention has a wet bursting strength of greater than about 5 lb-in⁻², typically about 10 to about 25 lb-in⁻². The combined filtration layer has a permeability of about 4 to 20 ft-min⁻¹; a wet burst strength of 10 to 20 lb-in⁻² and a basis weight of 100 to 200 g-m⁻².

Various combinations of polymers for the bicomponent fiber may be useful in the present invention, but it is important that the first polymer component melt at a temperature lower than the melting temperature of the second polymer component and typically below 205° C. Further, the bicomponent fibers are integrally mixed and evenly dispersed with the pulp fibers. Melting of the first polymer component of the bicomponent fiber is necessary to allow the bicomponent fibers to form a tacky skeletal structure, which upon cooling, captures and binds many of the secondary fibers, as well as binds to other bicomponent fibers.

In the sheath-core structure, the low melting point (e.g., about 80 to 205° C.) thermoplastic is typically extruded around a fiber of the higher melting (e.g., about 120 to 260° C.) point material. In use, the bicomponent fibers typically have a fiber diameter of about 5 to 50 micrometers often about 10 to 20 micrometers and typically in a fiber form generally have a length of 0.1 to 20 millimeters or often have a length of about 0.2 to about 15 millimeters. Such fibers can

be made from a variety of thermoplastic materials including polyolefins (such as polyethylenes, polypropylenes), polyesters (such as polyethylene terephthalate, polybutylene terephthalate, PCT), nylons including nylon 6, nylon 6,6, nylon 6,12, etc. Any thermoplastic that can have an appropriate melting point can be used in the low melting component of the bicomponent fiber while higher melting polymers can be used in the higher melting "core" portion of the fiber. The cross-sectional structure of such fibers can be, as discussed above, the "side-by-side" or "sheath-core" structure or other structures that provide the same thermal bonding function. One could also use lobed fibers where the tips have lower melting point polymer. The value of the bicomponent fiber is that the relatively low molecular weight resin can melt under sheet, media, or filter forming conditions to act to bind the bicomponent fiber, and other fibers present in the sheet, media, or filter making material into a mechanically stable sheet, media, or filter.

Typically, the polymers of the bicomponent (core/shell or sheath and side-by-side) fibers are made up of different thermoplastic materials, such as for example, polyolefin/polyester (sheath/core) bicomponent fibers whereby the polyolefin, e.g. polyethylene sheath, melts at a temperature lower than the core, e.g. polyester. Typical thermoplastic polymers include polyolefins, e.g. polyethylene, polypropylene, polybutylene, and copolymers thereof, polytetrafluoroethylene, polyesters, e.g. polyethylene terephthalate, polyvinyl acetate, polyvinyl chloride acetate, polyvinyl butyral, acrylic resins, e.g. polyacrylate, and polymethylacrylate, polymethylmethacrylate, polyamides, namely nylon, polyvinyl chloride, polyvinylidene chloride, polystyrene, polyvinyl alcohol, polyurethanes, cellulosic resins, namely cellulosic nitrate, cellulosic acetate, cellulosic acetate butyrate, ethyl cellulose, etc., copolymers of any of the above materials, e.g. ethylene-vinyl acetate copolymers, ethyleneacrylic acid copolymers, styrene-butadiene block copolymers, Kraton rubbers and the like. Particularly preferred in the present invention is a bicomponent fiber known as 271P available from DuPont. Others fibers include FIT 201, Kuraray N720 and the Nichimen 4080 and similar materials. All of these demonstrate the characteristics of cross-linking the sheath poly upon completion of first melt. This is important for liquid applications where the application temperature is typically above the sheath melt temperature. If the sheath does not fully crystallize then the sheath polymer will remelt in application and coat or damage downstream equipment and components.

Media fibers are fibers that can aid in filtration or in forming a structural media layer. Such fiber is made from a number of both hydrophilic, hydrophobic, oleophilic, and oleophobic fibers. These fibers cooperate with the glass fiber and the bicomponent fiber to form a mechanically stable, but strong, permeable filtration media that can withstand the mechanical stress of the passage of fluid materials and can maintain the loading of particulate during use. Such fibers are typically monocomponent fibers with a diameter that can range from about 0.1 to about 50 micrometers and can be made from a variety of materials including naturally occurring cotton, linen, wool, various cellulosic and proteinaceous natural fibers, synthetic fibers including rayon, acrylic, aramide, nylon, polyolefin, polyester fibers. One type of secondary fiber is a binder fiber that cooperates with other components to bind the materials into a sheet. Another type a structural fiber cooperates with other components to increase the tensile and burst strength the materials in dry and wet conditions. Additionally, the binder fiber can include fibers made from such polymers as polyvinyl chlo-

ride, polyvinyl alcohol. Secondary fibers can also include inorganic fibers such as carbon/graphite fiber, metal fiber, ceramic fiber and combinations thereof. Depending on application, the media or medium of the invention can comprise a wide variety of amount of secondary binder fiber. Amounts used in different media examples can be 5 to 50 wt %, 10 to 40 wt %, 0.1 to 10 wt %, 0 to 20 wt % or 13 to 50 wt %.

Thermoplastic fibers include, but are not limited to, polyester fibers, polyamide fibers, polypropylene fibers, copolyetherester fibers, polyethylene terephthalate fibers, polybutylene terephthalate fibers, polyetherketoneketone (PEKK) fibers, polyetheretherketone (PEEK) fibers, liquid crystalline polymer (LCP) fibers, and mixtures thereof. Polyamide fibers include, but are not limited to, nylon 6, 66, 11, 12, 612, and high temperature "nylons" (such as nylon 46) including cellulosic fibers, polyvinyl acetate, polyvinyl alcohol fibers (including various hydrolysis of polyvinyl alcohol such as 88% hydrolyzed, 95% hydrolyzed, 98% hydrolyzed and 99.5% hydrolyzed polymers), cotton, viscose rayon, thermoplastic such as polyester, polypropylene, polyethylene, etc., polyvinyl acetate, polylactic acid, and other common fiber types. The thermoplastic fibers are generally fine (about 0.5-20 denier diameter), short (about 0.1-5 cm long), staple fibers, possibly containing precompounded conventional additives, such as antioxidant, stabilizers, lubricants, tougheners, etc. In addition, the thermoplastic fibers may be surface treated with a dispersing aid. The preferred thermoplastic fibers are polyamide and polyethylene terephthalate fibers, with the most preferred being polyethylene terephthalate fibers. The preferred media fiber comprises a glass fiber used in media of the present invention include glass types known by the designations: A, C, D, E, Zero Boron E, ECR, AR, R, S, S-2, N, and the like, and generally, any glass that can be made into fibers either by drawing processes used for making reinforcement fibers or spinning processes used for making thermal insulation fibers. Such fiber is typically used as a diameter about 0.1 to 10 micrometers and an aspect ratio (length divided by diameter) of about 10 to 10000. These commercially available fibers are characteristically sized with a sizing coating. Such coatings cause the otherwise ionically neutral glass fibers to form and remain in bundles. Glass fiber in diameter less than about 1 micron is not sized.

Large diameter chopped glass is sized.

Manufacturers of glass fibers commonly employ sizes such as this. The sizing composition and cationic antistatic agent eliminates fiber agglomeration and permits a uniform dispersion of the glass fibers upon agitation of the dispersion in the tank. The typical amount of glass fibers for effective dispersion in the glass slurry is within the range of 50% to about 90%, and most preferably about 50-80%, by weight of the solids in the dispersion. Blends of glass fibers can substantially aid in improving permeability of the materials. We have found that combining a glass fiber having an average fiber diameter of about 0.3 to 0.5 micrometer, a glass fiber having an average fiber diameter of about 1 to 2 micrometers, a glass fiber having an average fiber diameter of about 3 to 6 micrometers, a glass fiber with a fiber diameter of about 6 to 10 micrometers, and a glass fiber with a fiber diameter of about 10 to 100 micrometers in varying proportions can substantially improve permeability. We believe the glass fiber blends obtain a controlled pore size resulting in a defined permeability in the media layer. Binder resins can typically comprise water-soluble or water sensitive polymer materials. Its polymer materials are typically provided in either dry form or aqueous dispersions. Such

useful polymer materials include acrylic polymers, ethylene vinyl acetate polymers, ethylene vinyl polyvinyl alcohol, ethylene vinyl alcohol polymers, polyvinyl pyrrolidone polymers, and natural gums and resins useful in aqueous solution.

We have surprisingly found that the media of the invention have a surprising thermal property. The media after formation and thermal bonding at or above the melt temperature of the lower melting portion of the bicomponent fiber, can be used at temperatures above that melting temperature. Once thermally formed, the media appears to be stable at temperatures at which the media should lose mechanical stability due to the softening or melting of the fiber. We believe that there is some interaction in the bonded mass that prevents the melting of the fiber and the resulting failure of the media. Accordingly, the media can be used with a mobile gaseous or liquid phase at a temperature equal to or 10 to 100° F. above the melt temperature of the lower melting portion of the bicomponent fiber. Such applications include hydraulic fluid filtration, lubricant oil filtration, hydrocarbon fuel filtration, hot process gas filtration, etc.

Binder resins can be used to help bond the fiber into a mechanically stable media layer. Such thermoplastic binder resin materials can be used as a dry powder or solvent system, but are typically aqueous dispersions (a latex or one of a number of lattices) of vinyl thermoplastic resins. A resinous binder component is not necessary to obtain adequate strength for the papers of this invention, but can be used. Resin used as binder can be in the form of water soluble or dispersible polymer added directly to the paper making dispersion or in the form of thermoplastic binder fibers of the resin material intermingled with the aramid and glass fibers to be activated as a binder by heat applied after the paper is formed. Resins include vinyl acetate materials, vinyl chloride resins, polyvinyl alcohol resins, polyvinyl acetate resins, polyvinyl acetyl resins, acrylic resins, methacrylic resins, polyamide resins, polyethylene vinyl acetate copolymer resins, thermosetting resins such as urea phenol, urea formaldehyde, melamine, epoxy, polyurethane, curable unsaturated polyester resins, polyaromatic resins, resorcinol resins and similar elastomer resins. The preferred materials for the water soluble or dispersible binder polymer are water soluble or water dispersible thermosetting resins such as acrylic resins, methacrylic resins, polyamide resins, epoxy resins, phenolic resins, polyureas, polyurethanes, melamine formaldehyde resins, polyesters and alkyd resins, generally, and specifically, water soluble acrylic resins, methacrylic resins, polyamide resins, that are in common use in the papermaking industry. Such binder resins typically coat the fiber and adhere fiber to fiber in the final non-woven matrix. Sufficient resin is added to the furnish to fully coat the fiber without causing film over of the pores formed in the sheet, media, or filter material. The resin can be added to the furnish during papermaking or can be applied to the media after formation.

The latex binder used to bind together the three-dimensional non-woven fiber web in each non-woven layer or used as the additional adhesive, can be selected from various latex adhesives known in the art. The skilled artisan can select the particular latex adhesive depending upon the type of cellulosic fibers that are to be bound. The latex adhesive may be applied by known techniques such as spraying or foaming. Generally, latex adhesives having from 15 to 25% solids are used. The dispersion can be made by dispersing the fibers and then adding the binder material or dispersing the binder material and then adding the fibers. The dispersion can, also, be made by combining a dispersion of fibers with a disper-

sion of the binder material. The concentration of total fibers in the dispersion can range from 0.01 to 5 or 0.005 to 2 weight percent based on the total weight of the dispersion. The concentration of binder material in the dispersion can range from 10 to 50 weight percent based on the total weight of the fibers.

Non-woven media of the invention can contain secondary fibers made from a number of both hydrophilic, hydrophobic, oleophilic, and oleophobic fibers. These fibers cooperate with the glass fiber and the bicomponent fiber to form a mechanically stable, but strong, permeable filtration media that can withstand the mechanical stress of the passage of fluid materials and can maintain the loading of particulate during use. Secondary fibers are typically monocomponent fibers with a diameter that can range from about 0.1 to about 50 micrometers and can be made from a variety of materials including naturally occurring cotton, linen, wool, various cellulosic and proteinaceous natural fibers, synthetic fibers including rayon, acrylic, aramide, nylon, polyolefin, polyester fibers. One type of secondary fiber is a binder fiber that cooperates with other components to bind the materials into a sheet. Another type of secondary fiber is a structural fiber that cooperates with other components to increase the tensile and burst strength the materials in dry and wet conditions. Additionally, the binder fiber can include fibers made from such polymers as polyvinyl chloride, polyvinyl alcohol. Secondary fibers can also include inorganic fibers such as carbon/graphite fiber, metal fiber, ceramic fiber and combinations thereof.

The secondary thermoplastic fibers include, but are not limited to, polyester fibers, polyamide fibers, polypropylene fibers, copolyetherester fibers, polyethylene terephthalate fibers, polybutylene terephthalate fibers, polyetherketoneketone (PEKK) fibers, polyetheretherketone (PEEK) fibers, liquid crystalline polymer (LCP) fibers, and mixtures thereof. Polyamide fibers include, but are not limited to, nylon 6, 66, 11, 12, 612, and high temperature "nylons" (such as nylon 46) including cellulosic fibers, polyvinyl acetate, polyvinyl alcohol fibers (including various hydrolysis of polyvinyl alcohol such as 88% hydrolyzed, 95% hydrolyzed, 98% hydrolyzed and 99.5% hydrolyzed polymers), cotton, viscose rayon, thermoplastic such as polyester, polypropylene, polyethylene, etc., polyvinyl acetate, polylactic acid, and other common fiber types. The thermoplastic fibers are generally fine (about 0.5-20 denier diameter), short (about 0.1-5 cm long), staple fibers, possibly containing precompounded conventional additives, such as antioxidant, stabilizers, lubricants, tougheners, etc. In addition, the thermoplastic fibers may be surface treated with a dispersing aid. The preferred thermoplastic fibers are polyamide and polyethylene terephthalate fibers, with the most preferred being polyethylene terephthalate fibers.

Fluoro-organic wetting agents useful in this invention for addition to the fiber layers are organic molecules represented by the formula



wherein R_f is a fluoroaliphatic radical and G is a group which contains at least one hydrophilic group such as cationic, anionic, nonionic, or amphoteric groups. Nonionic materials are preferred. R_f is a fluorinated, monovalent, aliphatic organic radical containing at least two carbon atoms. Preferably, it is a saturated perfluoroaliphatic monovalent organic radical. However, hydrogen or chlorine atoms can be present as substituents on the skeletal chain. While radicals containing a large number of carbon atoms may function adequately, compounds containing not more than


about 20 carbon atoms are preferred since large radicals usually represent a less efficient utilization of fluorine than is possible with shorter skeletal chains. Preferably, R_f contains about 2 to 8 carbon atoms.

The cationic groups that are usable in the fluoro-organic agents employed in this invention may include an amine or a quaternary ammonium cationic group which can be oxygen-free (e.g., $-\text{NH}_2$) or oxygen-containing (e.g., amine oxides). Such amine and quaternary ammonium cationic hydrophilic groups can have formulas such as $-\text{NH}_2$, $-(\text{NH}_3)\text{X}$, $-(\text{NH}(\text{R}^2)_2)\text{X}$, $-(\text{NH}(\text{R}^2)_3)\text{X}$, or $-\text{N}(\text{R}^2)_2 \rightarrow \text{O}$, where x is an anionic counterion such as halide, hydroxide, sulfate, bisulfate, or carboxylate, R^2 is H or C_{1-18} alkyl group, and each R^2 can be the same as or different from other R^2 groups. Preferably, R^2 is H or a C_{1-16} alkyl group and X is halide, hydroxide, or bisulfate.

The anionic groups which are usable in the fluoro-organic wetting agents employed in this invention include groups which by ionization can become radicals of anions. The anionic groups may have formulas such as $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{OSO}_3\text{M}$, $-\text{PO}_3\text{HM}$, $-\text{OPO}_3\text{M}_2$, or $-\text{OPO}_3\text{HM}$, where M is H, a metal ion, $(\text{NR}^1_4)^+$, or $(\text{SR}^1_4)^+$, where each R^1 is independently H or substituted or unsubstituted $\text{C}_1\text{-C}_6$ alkyl. Preferably M is Na^+ or K^+ . The preferred anionic groups of the fluoro-organo wetting agents used in this invention have the formula $-\text{COOM}$ or $-\text{SO}_3\text{M}$. Included within the group of anionic fluoroorganic wetting agents are anionic polymeric materials typically manufactured from ethylenically unsaturated carboxylic mono- and diacid monomers having pendent fluorocarbon groups appended thereto. Such materials include surfactants obtained from 3M Corporation known as FC-430 and FC-431.

The amphoteric groups which are usable in the fluoro-organic wetting agent employed in this invention include groups which contain at least one cationic group as defined above and at least one anionic group as defined above.

The nonionic groups which are usable in the fluoro-organic wetting agents employed in this invention include groups which are hydrophilic but which under pH conditions of normal agronomic use are not ionized. The nonionic groups may have formulas such as $-\text{O}(\text{CH}_2\text{CH}_2)_x\text{OH}$ where x is greater than 1, $-\text{SO}_2\text{NH}_2$, $-\text{SO}_2\text{NHCH}_2\text{CH}_2\text{OH}$, $-\text{SO}_2\text{N}(\text{CH}_2\text{CH}_2\text{H})_2$, $-\text{CONH}_2$, $-\text{CONHCH}_2\text{CH}_2\text{OH}$, or $-\text{CON}(\text{CH}_2\text{CH}_2\text{OH})_2$. Examples of such materials include materials of the following structure:



wherein n is 2 to 8 and m is 0 to 20.


Other fluoro-organic wetting agents include those cationic fluorochemicals described, for example in U.S. Pat. Nos. 2,764,602; 2,764,603; 3,147,064 and 4,069,158. Such amphoteric fluoro-organic wetting agents include those amphoteric fluorochemicals described, for example, in U.S. Pat. Nos. 2,764,602; 4,042,522; 4,069,158; 4,069,244; 4,090,967; 4,161,590 and 4,161,602. Such anionic fluoro-organic wetting agents include those anionic fluorochemicals described, for example, in U.S. Pat. Nos. 2,803,656; 3,255,131; 3,450,755 and 4,090,967.

There are numerous methods of modifying the surface of the fibers. Fibers that enhance drainage can be used to manufacture the media. Treatments can be applied during the manufacture of the fibers, during manufacture of the media or after manufacture of the media as a post treatment. Numerous treatment materials are available such as fluorochemicals or silicone containing chemicals that increase the

contact angle. One example would be DuPont Zonyl fluorochemicals such as 8195. Numerous fibers incorporated into filter media can be treated to enhance their drainage capability. Bicomponent fibers composed of polyester, polypropylene or other synthetic polymers can be treated. Glass fibers, synthetic fibers, ceramic, or metallic fibers can also be treated. We are utilizing various fluorochemicals such as DuPont #8195, #7040 and #8300. The media grade is composed of 50% by mass DuPont 271P bicomponent fiber cut 6 mm long, 40% by weight DuPont Polyester 205 WSD cut 6 mm, and 10% by mass Owens Corning DS-9501-11W Advantex cut to 6 mm. This media grade was produced using the wet laid process on an inclined wire which optimizes the distribution of the fibers and uniformity of the media. The media is being post treated in media or element

form with a dilute mixture of Zonyl incorporating a fugitive wetting agent (isopropyl alcohol), and DI water. The treated, wrapped element pack is dried and cured at 240 F to remove the liquid and activate the fluorochemical.

Examples of such materials are DuPont Zonyl FSN and DuPont Zonyl FSO nonionic surfactants. Another aspect of additives that can be used in the polymers of the invention include low molecular weight fluorocarbon acrylate materials such as 3M's Scotchgard material having the general structure:



wherein X is —F or —CF₃ and n is 1 to 7.

The following table sets forth the useful parameters of the layers of the invention:

TABLE 1

Fluid	Contaminant	Layer	Bicomponent Fiber	Bicomponent Fiber	Glass Fiber	Glass Fiber		
			%	Diameter Micrometer	%	Diameter Micrometer		
Air	Industrial Mist	1, 2 or more	20-80	5-15	80-20	0.1-5		
Air	Industrial Mist	1	50	13.0	50	1.6		
			50	5-15	80-20	1.6		
				14.0	12.5	1.5		
Air	Industrial Mist	1	20-80	5-15	80-20	1.5		
				14.0	50			
Air	Diesel Engine Crankcase Blowby	1	20-80	5-15	0	11		
					14.0	10		
Air	Diesel Engine Crankcase Blowby	1	10-30	5-15	35-50	0.4-3.4		
					12			
Diesel Engine	Soot	1	1-40	5-15	60-99	0.1-5		
		2	20	12.0	80	0.32-0.51		
Lube Oil		3 or more	20	12.0	80	0.43		
			20	12.0	80	0.32		
			50	10-14	30-50	0.2-0.8		
Diesel fuel	Particulate	2	50-65	10-14	25-50	0.4-1		
		3	50-70	10-14	13-33	1.0-1.5		
		4	50	10-14	0-50	2.6		
		1, 2, 3, 4 or more	20-80	5-15	80-20	0.1-5		
Hydraulic	Particulate	2,	50	12.0	50	0.8-2.6		
		3,	50	12.0	33	1		
		4 or more	50	12.0	33	0.8		
		50	12.0	50	0.51			
		80-98	10-15	3-12	0.5-2			
Air	Particulate	1 or 2	80-98	10-15	3-12	0.5-2		
Air	Particulate	1	90	12.0	10	0.6		
Air	Particulate	1	95	12.0	5	0.6		
Air	Particulate	1	97	12.0	3	0.6		
Fluid	Contaminant	Secondary Fiber	Secondary Fiber	Basis Weight	Thickness			
			Diameter		mm			
		%	Micrometer	g-m ⁻²	0.125 lb-in ⁻²	0.625 lb-in ⁻²	1.5 lb-in ⁻²	
Air	Industrial Mist	0-10		20-80	0.2-0.8	0.2-0.8	0.2-0.8	
		0.1-10		62.3	0.510	0.430	0.410	
Air	Industrial Mist			128.2	1.27	.993	.892	
				122.8	1.14	.922	.833	
Air	Diesel Engine	5-50%	0.5-15	20-80	0.2-0.8	0.2-0.8	0.2-0.8	
		10-40%	10-15	65.7	0.690	0.580	.530	
Air	Diesel Engine	Blowby	Poly					
		20-55	7-13	134			0.69	
		15-25	Latex resin					
Diesel Engine	Soot	0-20		10-50			0.2-0.8	
		17		40			0.3	

TABLE 1-continued

Lube Oil		17		32			0.25
		0		28			0.2
Diesel fuel	Particulate	10-15	10	30-50	0.18-0.31		
		13-50	12-14				
		17	17				
Hydraulic	Particulate		10-20	10-50			0.2-0.8
			18	32			0.23
			18	37			0.26
				39			0.25
				34			0.18
Air	Particulate			40-350			0.2-2
Air	Particulate			45			0.25
Air	Particulate			110			0.51
Air	Particulate			300			1.02

Fluid	Contaminant	Compressibility % change from 0.125 lb-inch ⁻² to 0.5 lb-inch ⁻²	Solidity at 0.125 lb- inch ⁻² %	Perm ft- min ⁻¹	MD Fold Tensile lb/(in width)	Mean Pore Size Micrometer	3160 DOP Efficiency 10.5 fpm % at 0.3 Micrometer
Air	Industrial	15	2-10	50-500	5-15	5-20	5-25
	Mist		6.9	204	3.9	17.8	12.0
Air	Industrial	22	5.6	68	6.9	15.6	26.3
	Mist						
Air	Industrial	19	6	50	8.6	14.4	39.7
	Mist						
Air	Diesel	14	6.7	50-300	5-15	5-20	5-20
	Engine						
	Crankcase			392	2.6	43	6.0
	Blowby						
Air	Diesel			33			
	Engine						
	Crankcase						
	Blowby						
Diesel	Particulate			6-540		1.5-41	
fuel							
Diesel	Soot		2-10	0.1-30		0.5-10	
Engine			4	7		2	
Lube			5	6		1.2	
Oil			6	4		1	
Hydrau- lic	Particulate			5-200		0.5-30	
				180		19	
				94		6.9	
				23		2.6	
				6.7		0.94	
Air	Particulate		10-25	20-200		10-30	
Air	Particulate		13	180		26	
Air	Particulate		17	90		33	
Air	Particulate		22	30		12	

We have found improved technology of enhanced internal bond between fiber and fiber of the filter media. Bicomponent fiber can be used to form a fiber layer. During layer formation, a liquid resin can be used. In the resin saturation process of the media, the liquid binding resin can migrate to the outer sides of the filter media making the internal fibers of the media unbonded relatively. During the pleating process, the unbonded regions cause degrading media stiffness and durability and excessive manufacturing scrap. Bicomponent and homopolymer binder fibers were used in this invention to enhance the internal bonding between fiber and fiber of the filter media. Bicomponent fibers are coextruded with two different polymers in the cross section; they can be concentric sheath/core, eccentric sheath/core or side-by-side, etc.

The bicomponent fibers used in this work are concentric sheath/core:

TJ04CN Teijin Ltd. (Japan) 2.2 DTEX×5 mm sheath core PET/PET

3380 Unitika Ltd. (Japan) 4.4 DTEX×5 mm sheath core PET/PET

The homopolymer binder fiber 3300 sticks at 130° C. and has the dimension of 6.6 DTEX×5 mm. The sheath melting temperatures of TJ04CN and 3380 are at 130° C.; and the core melting temperatures of these binder fibers are at 250° C. Upon heating, the sheath fiber component begins to melt and spread out, attaching itself in the fiber matrix; and the core fiber component remains in the media and functions to improve the media strength and flexibility. Unpressed handsheets were made in the Corporate Media Lab at Donaldson. Also pressed handsheets were made and pressed at 150° C. (302° F.) for 1 minute. In the Description of the Invention, some codes and furnish percentages of the handsheets and the internal bond strength test results will be presented. Results show that the Teijin and Unitika binder fibers would improve internal bond strengths in the synthetic media.

Eight furnish formulations were created in this work. Below are the information about the furnish formulations. Johns Manville 108B and Evanite 710 are glass fibers. Teijin TJ04CN, Unitika 3380, and Unitika 3300 are binder fibers. Polyester LS Code 6 3025-LS is made by MiniFibers, Inc.

Furnish	Fibers	% of Furnish	Weight (g)
Example 1	Johns Manville 108B	40	1.48
	Unitika 3300	17.5	0.6475
	Polyester LS Code 6 3025-LS	42.5	1.5725
Example 2	Evanite 710	40	1.48
	Unitika 3300	10	0.37
	Polyester LS Code 6 3025-LS	50	1.85
Example 3	Evanite 710	40	1.48
	Unitika 3300	15	0.555
	Polyester LS Code 6 3025-LS	45	1.665
Example 4	Evanite 710	40	1.48
	Unitika 3300	17.5	0.6475
	Polyester LS Code 6 3025-LS	42.5	1.5725
Example 5	Evanite 710	40	1.48
	Unitika 3300	20	0.74
	Polyester LS Code 6 3025-LS	40	1.48
Example 6	Evanite 710	40	1.48
	Polyester LS Code 6 3025-LS	60	2.22
Example 7	Evanite 710	40	1.48
	Teijin TJ04CN	17.5	0.6475
	Polyester LS Code 6 3025-LS	42.5	1.5725
Example 8	Evanite 710	40	1.48
	Unitika 3380	17.5	0.6475
	Polyester LS Code 6 3025-LS	42.5	1.5725

The handsheet procedure includes an initial weigh out of the individual fibers. About six drops of Emerhurst 2348 was placed into a 100 mls. of water and set aside. About 2 gallons of cold clean tap water was placed into a 5 gallon container with 3 mls. of the Emerhurst solution and mixed. The synthetic fibers were added and allowed to mix for at least 5 minutes before adding additional fibers. Fill the Waring blender with water ½ to ¾ add 3 mls. of 70% sulfuric acid. Add the glass fibers. Mix on the slowest speed for 30 seconds. Add to the synthetic fibers in the pail. Mix for an additional 5 minutes. Add the binder fibers to the container. Clean and rinse the dropbox out prior to using. Insert handsheet screen and fill to the first stop. Remove air trapped under the screen by jerking up on the plunger. Add the furnish to the dropbox, mix with the plunger, and drain. Vacuum of the handsheet with the vacuum slot. If no pressing is required, remove the handsheet from the screen and dry at 250.

Pressed Handsheets at 100 psi

Below are the physical data of the pressed handsheets that were made during Sep. 1, 2005 to Sep. 14, 2005 based on the above furnish formulations. The handsheets were pressed at 100 psi.

Sample ID	Example 1	Example 2 #1	Example 2 #2	Example 3 #1
BW (g) (8 × 8 sample)	3.52	3.55	3.58	3.55
Thickness (inch)	0.019	0.022	0.023	0.022
Perm (cfm)	51.1	93.4	90.3	85.8
Internal Bond	56.5	25.8	26.4	39

Sample ID	Example 3 #2	Example 4 #1	Example 4 #2	Example 5 #1
BW (g) (8 × 8 sample)	3.54	3.41	3.45	3.6
Thickness (inch)	0.02	0.017	0.018	0.022
Perm (cfm)	81.3	59.4	64.1	93.1
Internal Bond	46.2	40.6	48.3	42.2

-continued

Sample ID	Example 5 #2	Example 6 #1	Example 6 #2	Example 7 #1
BW (g) (8 × 8 sample)	3.51	3.56	3.56	3.63
Thickness (inch)	0.021	0.021	0.02	0.021
Perm (cfm)	89.4	109.8	108.3	78.9
Internal Bond	49.4	3.67	No Value	28.2

Sample ID	Example 7 #2	Example 8 #1	Example 8 #2
BW (g) (8 × 8 sample)	3.54	3.41	3.45
Thickness (inch)	0.02	0.017	0.018
Perm (cfm)	81.3	59.4	64.1
Internal Bond	46.2	40.6	48.3

Handsheet without having Unitika 3300 were made. Results from Examples 6 #1 and 6 #2 showed that the handsheets without having Unitika 3300 had poor internal bond strengths.

The internal bond data show that the bond strengths will be at optimum with the presence of 15%-20% of Unitika 3300 in the furnish.

Results from Examples 4 #1, 4 #2, 7 #1, 7 #2, 8 #1, and 8 #2 show that Unitika 3300 works better than Teijin TJ04CN and Unitika 3380 in creating internal bond strengths in the handsheets.

	Useful	Preferred	More Preferred
Basis Wt. (g) (8" × 8" sample)	3 to 4	3.2 to 3.6	3.3 to 3.3
Thickness (in)	0.02	0.017	0.018
Perm (cfm)	81.3	59.4	64.1
Internal Bond	46.2	40.6	48.3

Unpressed Handsheets

Two handsheet Samples 4 #3 and 4 #4 were made without pressed. After being dried in the photodrier; the samples were put in the oven for 5 minutes at 300° F.

Sample ID	Example 4 #3	Example 4 #4
BW (g) (8" × 8" sample)	3.53	3.58
Thickness (inch)	0.029	0.03
Perm (cfm)	119.8	115.3
Internal Bond	17.8	19.8

Compared to Samples 4 #1 and 4 #2 (pressed handsheet), the unpressed samples 4 #3 and 4 #4 were having much lower internal bond strengths.

Pressed Handsheets at 50 psi

Two handsheet Samples 4 #5 and 4 #6 were made and pressed at 50 psi. Below are the physical properties of the handsheets.

Sample ID	Example 4 #5	Example 4 #6
BW (g) (8" × 8" sample)	3.63	3.65
Thickness (inch)	0.024	0.023
Perm (cfm)	91.4	85.8
Internal Bond	33.5	46

21

Results of Examples 4 #1-4 #6 show that binders are more effective with pressing.

Pressed and Saturated Handsheets

Two handsheet Examples 4 #7 and 6 #3 were made. First, the handsheets were dried in the photodrier; then were saturated in the solution of 95% Rhoplex TR-407 (Rohm & Haas) and 5% Cymel 481 (Cytec) on dry resin basis. Then the handsheets were pressed at 100 psi and tested. Below are the physical properties of the saturated handsheets. Results show that the resin solution may decrease the internal bond strengths

Sample ID	Example 4 #7	Example 6 #3
BW (g) (8" × 8" sample)	3.57	3.65
Final BW (g) (8" × 8" sample)	4.43	4.62
Pick-up percent (%)	24.1	26.6
Thickness (inch)	0.019	0.022
Perm (cfm)	64.9	67.4
Internal Bond	32.3	No Value

Results show that the Teijin TJ04CN, Unitika 3380 and Unitika 3300 binder fibers would improve internal bond strengths in the synthetic media and Unitika 3300 works best among the binder fibers. Handsheets without having Unitika 3300 had poor internal bond strengths. Handsheets were having optimum bond strengths with the presence of 15%-20% of Unitika 3300 in the furnish. Pressed handsheets were having higher internal bond strengths than unpressed handsheets. The latex resin does not provide internal bond strengths to polyester fibers. Latex resin may be used in conjunction with the binder fibers but the binder fibers would yield more effective internal bond strengths without latex resin.

The sheet media of the invention are typically made using papermaking processes. Such wet laid processes are particularly useful and many of the fiber components are designed for aqueous dispersion processing. However, the media of the invention can be made by air laid processes that use similar components adapted for air laid processing. The machines used in wet laid sheet making include hand laid sheet equipment, Fourdrinier papermaking machines, cylindrical papermaking machines, inclined papermaking machines, combination papermaking machines and other machines that can take a properly mixed paper, form a layer or layers of the furnish components, remove the fluid aqueous components to form a wet sheet. A fiber slurry containing the materials are typically mixed to form a relatively uniform fiber slurry. The fiber slurry is then subjected to a wet laid papermaking process. Once the slurry is formed into a wet laid sheet, the wet laid sheet can then be dried, cured or otherwise processed to form a dry permeable, but real sheet, media, or filter. Once sufficiently dried and processed to filtration media, the sheets are typically about 0.25 to 1.9 millimeter in thickness, having a basis weight of about 20 to 200 or 30 to 150 g-m⁻². For a commercial scale process, the bicomponent mats of the invention are generally processed through the use of papermaking-type machines such as commercially available Fourdrinier, wire cylinder, Stevens Former, Roto Former, Inver Former, Venti Former, and inclined Delta Former machines. Preferably, an inclined Delta Former machine is utilized. A bicomponent mat of the invention can be prepared by forming pulp and glass fiber slurries and combining the slurries in mixing tanks, for example. The amount of

22

water used in the process may vary depending upon the size of the equipment used. The furnish may be passed into a conventional head box where it is dewatered and deposited onto a moving wire screen where it is dewatered by suction or vacuum to form a non-woven bicomponent web. The web can then be coated with a binder by conventional means, e.g., by a flood and extract method and passed through a drying section which dries the mat and cures the binder, and thermally bonds the sheet, media, or filter. The resulting mat may be collected in a large roll.

The medium or media can be formed into substantially planar sheets or formed into a variety of geometric shapes using forms to hold the wet composition during thermal bonding. The media fiber of the invention includes glass, metal, silica, polymer and other related fibers. In forming shaped media, each layer or filter is formed by dispersing fibers in an aqueous system, and forming the filter on a mandrel with the aid of a vacuum. The formed structure is then dried and bonded in an oven. By using a slurry to form the filter, this process provides the flexibility to form several structures; such as, tubular, conical, and oval cylinders.

Certain preferred arrangements according to the present invention include filter media as generally defined, in an overall filter construction. Some preferred arrangements for such use comprise the media arranged in a cylindrical, pleated configuration with the pleats extending generally longitudinally, i.e. in the same direction as a longitudinal axis of the cylindrical pattern. For such arrangements, the media may be imbedded in end caps, as with conventional filters. Such arrangements may include upstream liners and downstream liners if desired, for typical conventional purposes. Permeability relates to the quantity of air (ft³-min⁻¹-ft⁻² or ft min⁻¹) that will flow through a filter medium at a pressure drop of 0.5 inches of water. In general, permeability, as the term is used is assessed by the Frazier Permeability Test according to ASTM D737 using a Frazier Permeability Tester available from Frazier Precision Instrument Co. Inc., Gaithersburg, Md. or a TexTest 3300 or TexTest 3310 available from Advanced Testing Instruments Corp (ATI), 243 East Black Stock Rd. Suite 2, Spartanburg, S.C. 29301, (864)989-0566, www.atincorporation.com. Pore size referred to in this disclosure means mean flow pore diameter determined using a capillary flow porometer instrument like Model APP 1200 AEXSC sold by Porus Materials, Inc., Cornell University Research Park, Bldg. 4.83 Brown Road, Ithaca, N.Y. 14850-1298, 1-800-825-5764, www.pmiapp.com.

Preferred crankcase ventilation filters of the type characterized herein include at least one media stage comprising wet laid media. The wet laid media is formed in a sheet form using wet laid processing, and is then positioned on/in the filter cartridge. Typically the wet laid media sheet is at least used as a media stage stacked, wrapped or coiled, usually in multiple layers, for example in a tubular form, in a serviceable cartridge. In use, the serviceable cartridge would be positioned with the media stage oriented for convenient drainage vertically. For example, if the media is in a tubular form, the media would typically be oriented with a central longitudinal axis extending generally vertically.

As indicated, multiple layers, from multiple wrappings or coiling, can be used. A gradient can be provided in a media stage, by first applying one or more layers of wet laid media of first type and then applying one or more layers of a media (typically a wet laid media) of a different, second, type. Typically when a gradient is provided, the gradient involves use of two media types which are selected for differences in efficiency. This is discussed further below.

Herein, it is important to distinguish between the definition of the media sheet used to form the media stage, and the definitions of the overall media stage itself. Herein the term "wet laid sheet," "media sheet" or variants thereof, is used to refer to the sheet material that is used to form the media stage in a filter, as opposed to the overall definition of the total media stage in the filter. This will be apparent from certain of the following descriptions.

Secondly, it is important to understand that a media stage can be primarily for coalescing/drainage, for both coalescing/drainage and particulate filtration, or primarily for particulate filtration. Media stages of the type of primary concern herein, are at least used for coalescing/drainage, although they typically also have particulate removal function and may comprise a portion of an overall media stage that provides for both coalescing/drainage and desired efficiency of solid particulate removal.

In the example arrangement described above, an optional first stage and a second stage were described in the depicted arrangements. Wet laid media according to the present descriptions can be utilized in either stage. However typically the media would be utilized in a stage which forms, in the arrangements shown, the tubular media stages. In some instances when materials according to the present disclosure are used, the first stage of media, characterized as the optional first stage hereinabove in connection with the figures, can be avoided entirely, to advantage.

The media composition of the wet laid sheets used to form a stage in a filter is provided in a form having a calculated pore size (X-Y direction) of at least 10 micron, usually at least 12 micron. The pore size is typically no greater than 60 micron, for example within the range of 12-50 micron, typically 15-45 micron. The media is formulated to have a DOP % efficiency (at 10.5 fpm for 0.3 micron particles), within the range of 3-18%, typically 5-15%. The media can comprise at least 30% by weight, typically at least 40% by weight, often at least 45% by weight and usually within the range of 45-70% by weight, based on total weight of filter material within the sheet, bi-component fiber material in accord with the general description provided herein. The media comprises 30 to 70% (typically 30-55%), by weight, based on total weight of fiber material within the sheet, of secondary fiber material having average largest cross-sectional dimensions (average diameters is round) of at least 1 micron, for example within the range of 1 to 20 micron. In some instances it will be 8-15 micron. The average lengths are typically 1 to 20 mm, often 1-10 mm, as defined. This secondary fiber material can be a mix of fibers. Typically polyester and/or glass fibers are used, although alternatives are possible. Typically and preferably the fiber sheet (and resulting media stage) includes no added binder other than the binder material contained within the bi-component fibers. If an added resin or binder is present, preferably it is present at no more than about 7% by weight of the total fiber weight, and more preferably no more than 3% by weight of the total fiber weight. Typically and preferably the wet laid media is made to a basis weight of at least 20 lbs. per 3,000 square feet (9 kg/278.7 sq. m.), and typically not more than 120 lbs. per 3,000 square feet (54.5 kg/278.7 sq. m.). Usually it will be selected within the range of 40-100 lbs. per 3,000 sq. ft. (18 kg-45.4 kg/278.7 sq. m.). Typically and preferably the wet laid media is made to a Frazier permeability (feet per minute) of 40-500 feet per minute (12-153 meters/min.), typically 100 feet per minute (30 meters/min.). For the basis weights on the order of about 40 lbs./3,000 square feet-100 lbs./3,000 square feet (18-45.4 kg/278.7 sq. meters), typical permeabilities would be about 200-400 feet

per minute (60-120 meters/min.). The thickness of the wet laid media sheet(s) used to later form the described media stage in the filter at 0.125 psi (8.6 millibars) will typically be at least 0.01 inches (0.25 mm) often on the order of about 0.018 inch to 0.06 inch (0.45-1.53 mm); typically 0.018-0.03 inch (0.45-0.76 mm).

Media in accord with the general definitions provided herein, including a mix of bi-component fiber and other fiber, can be used as any media stage in a filter as generally described above in connection with the figures. Typically and preferably it will be utilized to form the tubular stage. When used in this manner, it will typically be wrapped around a center core of the filter structure, in multiple layers, for example often at least 20 layers, and typically 20-70 layers, although alternatives are possible. Typically the total depth of the wrapping will be about 0.25-2 inches (6-51 mm), usually 0.5-1.5 (12.7-38.1 mm) inches depending on the overall efficiency desired. The overall efficiency can be calculated based upon the number of layers and the efficiency of each layer. For example the efficiency at 10.5 feet per minute (3.2 m/min) for 0.3 micron DOP particles for media stage comprising two layers of wet laid media each having an efficiency of 12% would be 22.6%, i.e., $12\% + 0.12 \times 88$.

Typically enough media sheets would be used in the final media stage to provide the media stage with overall efficiency measured in this way of at least 85%, typically 90% or greater. In some instances it would be preferred to have the efficiency at 95% or more. In the context the term "final media stage" refers to a stage resulting from wraps or coils of the sheet(s) of wet laid media.

In crankcase ventilation filters, a calculated pore size within the range of 12 to 80 micron is generally useful. Typically the pore size is within the range of 15 to 45 micron. Often the portion of the media which first receives gas flow with entrained liquid for designs characterized in the drawings, the portion adjacent the inner surface of tubular media construction, through a depth of at least 0.25 inch (6.4 mm), has an average pore size of at least 20 microns. This is because in this region, a larger first percentage of the coalescing/drainage will occur. In outer layers, in which less coalescing drainage occur, a smaller pore size for more efficient filtering of solid particles, may be desirable in some instances. The term X-Y pore size and variants thereof when used herein, is meant to refer to the theoretical distance between fibers in a filtration media. X-Y refers to the surface direction versus the Z direction which is the media thickness. The calculation assumes that all the fibers in the media are lined parallel to the surface of the media, equally spaced, and ordered as a square when viewed in cross-section perpendicular to the length of the fibers. The X-Y pore size is a distance between the fiber surface on the opposite corners of the square. If the media is composed of fibers of various diameters, the d^2 mean of the fiber is used as the diameter. The d^2 mean is the square root of the average of the diameters squared. It has been found that it is useful to have calculated pore sizes on the higher end of the preferred range, typically 30 to 50 micron, when the media stage at issue has a total vertical height, in the crankcase ventilation filter of less than 7 inches (178 mm); and, pore sizes on the smaller end, about 15 to 30 micron, are sometimes useful when the filter cartridge has a height on the larger end, typically 7-12 inches (178-305 mm). A reason for this is that taller filter stages provide for a higher liquid head, during coalescing, which can force coalesced liquid flow, under gravity, downwardly through smaller pores, during drainage. The smaller pores, of course, allow for

25

higher efficiency and fewer layers. Of course in a typical operation in which the same media stage is being constructed for use in a variety of filter sizes, typically for at least a portion of the wet laid media used for the coalescing/ drainage in initial separation, an average pore size of about 30-50 microns will be useful.

Solidity is the volume fraction of media occupied by the fibers. It is the ratio of the fibers volume per unit mass divided by the media's volume per unit mass. Typical wet laid materials preferred for use in media stages according to the present disclosure, especially as the tubular media stage in arrangements such as those described above in connection with the figures, have a percent solidity at 0.125 psi (8.6 millibars) of under 10%, and typically under 8%, for example 6-7%. The thickness of media utilized to make media packs according to the present disclosure, is typically measured using a dial comparator such as an Ames #3W (BCA Melrose MA) equipped with a round pressure foot, one square inch. A total of 2 ounces (56.7 g) of weight is applied across the pressure foot. Typical wet laid media sheets useable to be wrapped or stacked to form media arrangements according to the present disclosure, have a thickness of at least 0.01 inches (0.25 mm) at 0.125 psi (8.6 millibars), up to about 0.06 inches (1.53 mm), again at 0.125 psi (8.6 millibars). Usually, the thickness will be 0.018-0.03 inch (0.44-0.76 mm) under similar conditions.

Compressibility is a comparison of two thickness measurements made using the dial comparator, with compressibility being the relative loss of thickness from a 2 ounce (56.7 g) to a 9 ounce (255.2 g) total weight (0.125 psi-0.563 psi or 8.6 millibars-38.8 millibars). Typical wet laid media (at about 40 lbs/3,000 square feet (18 kg/278.7 sq. m) basis weight) useable in wrappings according to the present disclosure, exhibit a compressibility (percent change from 0.125 psi to 0.563 psi or 8.6 millibars-38.8 millibars) of no greater than 25%, and typically 12-16%.

The media of the invention have a preferred DOP efficiency at 10.5 ft/minute for 0.3 micron particles for layers or sheets of wet laid media. This requirement indicates that a number of layers of the wet laid media will typically be required, in order to generate an overall desirable efficiency for the media stage of typically at least 85% or often 90% or greater, in some instances 95% or greater. In general, DOP efficiency is a fractional efficiency of a 0.3 micron DOP particle (dioctyl phthalate) challenging the media at 10 fpm. A TSI model 3160 Bench (TSI Incorporated, St. Paul, Minn.) can be used to evaluate this property. Model dispersed particles of DOP are sized and neutralized prior to challenging the media. The wet laid filtration media accomplishes strength through utilization of added binders. However this comprises the efficiency and permeability, and increases solidity. Thus, as indicated above, the wet laid media sheets and stages according to preferred definitions herein typically include no added binders, or if binder is present it is at a level of no greater than 7% of total fiber weight, typically no greater than 3% of total fiber weight. Four strength properties generally define media gradings: stiffness, tensile, resistance to compression and tensile after fold. In general, utilization of bi-component fibers and avoidance of polymeric binders leads to a lower stiffness with a given or similar resistance to compression and also to good tensile and tensile after fold. Tensile strength after folding is important, for media handling and preparation of filter cartridges of the type used in many crankcase ventilation filters. Machine direction tensile is the breaking strength of a thin strip of media evaluated in the machine direction (MD). Reference is to Tappi 494. Machine direc-

26

tion tensile after fold is conducted after folding a sample 180° relative to the machine direction. Tensile is a function of test conditions as follows: sample width, 1 inch (25.4 mm); sample length, 4 inch gap (101.6 mm); fold-1 inch (25.4 mm) wide sample 180° over a 0.125 inch (3.2 mm) diameter rod, remove the rod and place a 10 lb. weight (4.54 kg) on the sample for 5 minutes. Evaluate tensile; pull rate-2 inches/minute (50.8 mm/minute).

EXAMPLE 9

Example 9, EX1051, is a sheet material useable for example, as a media phase in a filter and can be used in layers to provide useable efficiencies of overall filtration. The material will drain well and effectively, for example when used as a tubular media construction having a height of 4 inches-12 inches (100-300.5 mm). The media can be provided in multiple wrappings, to generate such a media pack. The media comprises a wet laid sheet made from a fiber mix as follows: 50% by wt. DuPont polyester bi-component 271P cut to 6 mm length; 40% by wt. DuPont polyester 205 WSD, cut to 6 mm length; and 10% by wt. Owens Corning DS-9501-11W Advantex glass fibers, cut to 6 mm. The DuPont 271P bi-component fiber is an average fiber diameter of about 14 microns. The DuPont polyester 205 WSD fiber has an average fiber diameter of about 12.4 microns. The Owens Corning DS-9501-11W has an average fiber diameter of about 11 microns. The material was made to a basis weight of about 40.4 lbs./3,000 sq. ft. The material had a thickness at 0.125 psi, of 0.027 inches and at 0.563 psi of 0.023 inches. Thus, the total percent change (compressibility) from 0.125 to 0.563 psi, was only 14%. At 1.5 psi, the thickness of the material was 0.021 inches. The solidity of the material at 0.125 psi was 6.7%. The permeability (frazier) was 392 feet per minute. The MD fold tensile was 2.6 lbs./inch width. The calculated pore size, X-Y direction, was 43 microns. The DOP efficiency of 10.5 feet per minute per 0.43 micron particles, was 6%.

EXAMPLE 10

Example 10, EX1050, was made from a fiber mixture comprising 50% by weight DuPont polyester bi-component 271P cut to 6 mm length; and 50% by weight Lauscha B50R microfiber glass. The microfiber glass had lengths on the order of about 3-6 mm. Again, the DuPont polyester bi-component 271P had an average diameter of 14 microns. The Lauscha B50R had an average diameter of 1.6 microns and a d^2 mean of 2.6 microns.

The sample was made to a basis weight of 38.3 lbs./3,000 square feet. The thickness of the media at 0.125 psi, 0.020 inches and at 0.563 psi was 0.017 inches. Thus the percent changed from 0.125 psi to 0.563 psi was 15%, i.e., 15% compressibility. At 1.5 psi, the sample had a thickness of 0.016 inches. The solidity of the material measured at 0.125 psi was 6.9%. The permeability of the material was about 204 feet/minute. The machine direction fold tensile was measured at 3.9 lbs/inch width. The calculated pore size X-Y direction was 18 microns. The DOP efficiency at 10.5 ft/minute for 0.3 micron particles, was 12%. The material would be effective when used as a layer or a plurality of layers to polish filtering. Because of its higher efficiency, it can be used alone or in multiple layers to generate high efficiency in the media.

EXAMPLE 11

Example 11, EX 1221, is a sheet material useable for example, as a media phase in a filter and can be used in

layers to provide usable efficiencies for overall filtration. The material will not drain as well as either example 9 or 10 but will exhibit much higher efficiency. It is useful for mist applications where load rate is lower and element construction allows for a pleated construction of higher pleat height, such as 10 inches. The media was made from a fiber mixture comprising 50% by weight DuPont polyester bi-component 271P cut to 6 mm length; and 12.5% by weight Lauscha B50R microfiber glass and 37.5% Lauscha B26R. The microfiber glass had lengths on the order of about 3-6 mm. Again, the DuPont polyester bi-component 271P had an average diameter of 14 microns. The Lauscha B50R had an average diameter of 1.6 microns and a d^2 mean of 2.6 microns.

The sample was made to a basis weight of 78.8 lbs./3,000 square feet. The thickness of the media at 0.125 psi, 0.050 inches and at 0.563 psi was 0.039 inches. Thus the percent changed from 0.125 psi to 0.563 psi was 22%, i.e., 22% compressibility. At 1.5 psi, the sample had a thickness of 0.035 inches. The solidity of the material measured at 0.125 psi was 5.6%. The permeability of the material was about 68 feet/minute. The machine direction fold tensile was measured at 6.8 lbs./inch width. The calculated pore size X-Y direction was 16 microns. The DOP efficiency at 10.5 ft/minute for 0.3 micron particles, was 26%. The material would be effective when used as a layer or a plurality of layers to polish filtering. Because of its higher efficiency, it can be used alone or in multiple layers to generate high efficiency in the media.

Increased hydrophilic modification of the surface characteristics of the fibers in media, such as increasing the contact angle, should enhance water binding and the drainage capability of the filtration media and thus the performance of a filter (reduced pressure drop and improved mass efficiency). Various fibers are used in the design of for example filtration media used for low pressure filters such as mist filters or others (less than 1 psi terminal pressure drop). One method of modifying the surface of the fibers is to apply a surface treatment such as a fluorochemical or silicone containing material, 0.001 to 5% or about 0.01 to 2% by weight of the media. We anticipate modifying the surface characteristics of the fibers in a wet laid layer that can include bicomponent fibers, other secondary fiber such as a synthetic, ceramic or metal fibers with and without additional resin binder at about 0.001 to 7% by weight when used. The resulting media would be incorporated into filter element structures with a thickness generally greater than 0.05 inches often about 0.1 to 0.25 inches. The media would have larger XY pore size than conventional air media, generally greater than 10 often about 15 to 100 micron, and would be composed of larger size fibers, generally greater than 6 micron although in certain cases small fibers could be used to enhance efficiency. The use of surface modifiers should allow the construction of media with smaller XY pore sizes than untreated media, thereby increasing efficiency with the use of small fibers, reduce the thickness of the media for more compact elements, and reduce the equilibrium pressure drop of the element.

In the case of mist filtration, the system must be designed to drain the collected liquids; otherwise element life is uneconomically short. Media in both prefilter and primary element are positioned so that the liquid can drain from the media. The primary performance properties for these two elements are: initial and equilibrium fractional efficiency, pressure drop, and drainage ability. The primary physical properties of the media are thickness, solidity, and strength.

The elements are typically aligned vertically which enhances the filter's capability to drain. In this orientation, any given media composition will exhibit a equilibrium liquid height which will be a function of the XY pore size, fiber orientation, and the interaction of the liquid with the fibers' surface, measured as contact angle. The collection of liquid in the media will increase the height to a point balanced with the drainage rate of liquid from the media. Any portion of the media that is plugged with draining liquid would not be available for filtration thus increasing pressure drop and decreasing efficiency across the filter. Thus it is advantageous to minimize the portion of the element that retains liquid.

The three media factors effecting drainage rate, XY pore size, fiber orientation, and interaction of the liquid being drained with the fiber's surface, can all be modified to minimize the portion of the media that is plugged with liquid. The XY pore size of the element can be increased to enhance the drainage capability of the media but this approach has the effect of reducing the number of fibers available for filtration and thus the efficiency of the filter. To achieve target efficiency, a relatively thick element structure may be needed, typically greater than 0.125 inches, due to the need for a relatively large XY pore size. The fibers can be oriented with the vertical direction of the media but this approach is difficult to achieve in a manufacturing scenario. The interaction of the liquid being drained with the surface of the fibers can be modified to enhance the drainage rate. This invention disclosure supports this approach.

In one application, crank case filtration applications, small oil particle mists are captured, collect in the element and eventually drain from the element back into the engine's oil sump. Filtration systems installed on the crank case breather of diesel engines can be composed of multiple elements, a pre filter that removes large particles generally greater than 5 microns and a primary filter that removes the bulk of the residual contamination. The primary element can be composed of single or multiple layers of media. The composition of each layer can be varied to optimize efficiency, pressure drop and drainage performance.

Due to filtration system size constraints, the pre and primary elements must be designed for equilibrium fractional efficiency. Equilibrium fractional efficiency is defined as the element's efficiency once the element is draining liquid at a rate equal to the collection rate. The three performance properties, initial and equilibrium fractional efficiency, pressure drop, and drainage ability, are balanced against the element's design to achieve optimum performance. Thus, as an example, short elements in a high liquid loading environment must be designed to drain at a relatively fast rate.

Filtration performance (relative low pressure drop, high efficiency and the capability to drain) coupled with space requirements necessitates short elements composed of relatively thick, open media. As an example the small Spiracle element would be a vertically positioned cylinder of filtration media with an ID of 2" and thickness of 0.81 inches. The height of the media available for filtration would be only 4.72".

Various element configurations are being evaluated. The pre filter is composed of two layers of dry laid high loft polyester media. The primary element is composed of multiple wraps of EX 1051, 42 to 64 layers dependent on the available OD dimensions. Structures such as 32 wraps of EX 1051 and 12 wraps of EX 1050 separated with expanded metal have been evaluated. Various basis weights can be used to achieve equivalent element thickness. The elements

are being tested in standard engine blow-by filter housings, reverse flow (cylindrical elements with the flow from the inside-out). Modifications to the housings are anticipated to enhance oil drainage. It is also envisioned that the primary element could be an inner wrap. Other pre and primary element media configurations are anticipated such as dry laid VTF, use of other dry laid media grades utilizing bicomponent fibers or other combinations of fibers using the wet laid process.

This same approach can be used in applications where height restrictions are not as stringent but the drainage rate of the media is of primary concern. As an example, Industrial Air Filtration utilizes media collecting mist particles generated from the cooling fluids used in machine tool cutting. In this case the height of the media positioned in the vertical direction is 10 inches to greater than 30 inches. Thus a smaller XY pore size can be used but enhanced drainage will improve the performance of the element, equilibrium efficiency and pressure drop. We have evaluated a second media grade. The media grade, EX 1050, is composed of 50% by mass DuPont Polyester bicomponent 271P cut 6 mm and 50% by mass Lauscha B50R microfiber glass (see attached media physicals). Additional grades of media incorporating small microfiber glass have been evaluated.

It is anticipated that some combination of fiber size, solidity resulting in an XY pore size coupled with surface modification will yield superior performance where as a much smaller XY pore size will yield inferior performance.

The media's performance was evaluated in element form. Multiple wraps of EX 1051-40 media, approximately 42, were wound around a center core. Two layers of a pre filter, EN 0701287, a dry laid latex impregnated media composed

of large polyester fibers and large pores were cut out as a circle and placed on one end of the center core. Both ends were potted and the element was positioned in a housing so that challenge air was directed through the prefilter then into the inside of the wrapped core and through the media to the outside of the cylinder.

Challenge oil, Mallinckrodt N.F. 6358 mineral oil, is created using either a Laskin and/or TSI atomizer. Both the number of nozzles and air pressure is varied to generate particles and maintain mass flow. A 2/1 mass ratio between the Laskin and TSI atomizers is produced to evaluate small and medium size CCV elements. Both nozzles are used to match expected particle distributions exhibited in diesel engine crank case ventilation.

The element evaluations were initiated at the high/high test condition without any presoaking, to model worse case field conditions. Every 24 hours of operation a mass balance is conducted to determine element efficiency. The flow and oil feed rate condition is maintained until the element has achieved equilibrium, defined when the mass of oil drained equals the mass of oil captured (>95% of equilibrium). A pressure drop/flow curve is then obtained by obtaining DP at various flows.

Under low flow and flux (2 cfm and 7.4 gm/hr/sq ft), the equilibrium pressure drop for a small size diesel engine crank case ventilation element (ID: 2 inches of water, OD: 3.62" media height 5.25") utilizing untreated EX 1051-40 media (~42 wraps of 40 lb/3,000 sq ft) was 1.9" of water. Equilibrium mass efficiency of 92.7%. A media treated with approximately 2.5% Zonly 7040, a fluorochemical, and used to construct an equivalent element exhibited an equilibrium pressure drop of 2.7" of water but a mass efficiency of 98.8%.

Wet Laid Mist Media						
Units	Composition	Fiber size,	Basis Weight	Thickness		
		average diameter	lb/3000 sq ft	inches, 0.125 psi	inches, 0.563 psi	inches, 1.5 psi
Example 10,	50% by mass DuPont Polyester bicomponent 271P cut 6 mm, 50% by mass Lauscha B50R microfiber glass	271P: 14 microns, B50R: 1.6 microns (2.5 um d ² mean)	38.3	0.020	0.017	0.016
Example 9	50% by mass DuPont Polyester bicomponent 271P cut 6 mm, 40% by mass DuPont Polyester 205 WSD cut 6 mm, 10% by mass Owens Corning DS-9501-11W Advantex cut to 6 mm	271P: 14 microns, 205 WSD: 12.4 microns DS-9501-11W: 11 microns	40.4	0.027	0.023	0.021
Example 11	50% by mass DuPont Polyester bicomponent 271P cut 6 mm, 12.5% by mass Lauscha B50R microfiber glass and 37.5% by mass Lauscha B26R	271P: 14 microns, B50R: 1.6 microns (2.5 um d ² mean) B26R: 1.5 micron (1.95)	78.8	0.050	0.039	0.035
Range Produced		20 to 120				

-continued

Wet Laid Mist Media						
Units	Compressability % change from 0.125 oz to 0.563 psi	Solidity at 0.125 psi %	Perm fpm	MD Fold Tensile lb/in width	Calculated Pore Size, X-Y direction microns	3160 DOP Efficiency @ 10.5 fpm % at 0.3 um
Example 10	15	6.9	204	3.9	18	12.0
Example 9	14	6.7	392	2.6	43	6.0
Example 11	22	5.6	68	6.9	16	26.3
Range Produced						

In one embodiment of the invention, the filtration medium or media is comprised of a thermally bonded sheet. The sheet is comprised of about 20 to 80 wt % of a bicomponent binder fiber and about 20 to 80 wt % of a glass fiber. The bicomponent binder fiber has a diameter of about 5 to 50 micrometers and a length of about 0.1 to 15 cm. The glass fiber has a diameter of about 0.1 to 30 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.2 to 50 mm, a solidity of about 2 to 25%, a basis weight of about 10 to 1000 g-m⁻², a pore size of about 0.5 to 100 micrometers and a permeability of about 5 to 500 ft-min⁻¹. The media is comprised of about 0.1 to 10 wt % of a binder resin. The media is comprised of about 0.5 to 15 wt % of a secondary fiber. One example of the secondary fiber would be a glass fiber wherein the glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 3 to 30 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a liquid filtration medium comprised of a thermally bonded sheet. The thermally bonded sheet is comprised of about 10 to 90 wt % of a bicomponent binder fiber and about 10 to 90 wt % of a media fiber. The bicomponent binder fiber has a diameter of about 5 to 50 micrometers and a length of about 0.1 to 15 cm. The media fiber has a diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 2 to 200 g-m⁻², a pore size of about 0.2 to 50 micrometers and a permeability of about 2 to 200 ft-min⁻¹. The media fiber is comprised of a secondary fiber. The media fiber is comprised of a glass fiber. The glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 10 to 50 micrometers. The media is comprised of about 0.1 to 25 wt % of a binder resin. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

A method of the invention embodies filtering a liquid stream, where the method is comprised of placing a filter unit into the steam and retaining particulate entrained in the filter in the stream using filter media within the filter unit. The filter media is comprised of a thermally bonded sheet. The thermally bonded sheet is comprised of about 10 to 90 wt % of a bicomponent binder fiber and about 10 to 90 wt % of a media fiber. The bicomponent binder fiber has a

diameter of about 5 to 50 micrometers and a length of about 0.1 to 15 cm. The media fiber has a diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 2 to 200 g-m⁻², a pore size of about 0.2 to 50 micrometers and a permeability of about 2 to 200 ft-min⁻¹. The liquid to be filtered may be either an aqueous liquid or a non-aqueous liquid. The media is comprised of about 0.1 to 25 wt % of a binder resin. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a gaseous filtration medium for removing mist from air comprising a thermally bonded sheet. The thermally bonded sheet is comprised of about 20 to 80 wt % of a bicomponent binder fiber and about 20 to 80 wt % of a media fiber. The bicomponent binder fiber has a diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm. The media fiber has a fiber diameter of about 0.1 to 20 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 20 to 100 grams-m⁻², a pore size of about 5 to 20 micrometers, an efficiency of 5 to 25% at 10.5 fpm. and a permeability of about 5 to 500 ft-min⁻¹. The media comprises about 0.1 to 10 wt % of a secondary fiber having a fiber diameter of 0.1 to 15 microns. One example of the media fiber is a glass fiber. The glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 10 to 50 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a gaseous filtration medium for removing particulate from air comprising a thermally bonded sheet. The thermally bonded sheet is comprised of about 80 to 98 wt % of a bicomponent binder fiber and about 2 to 20 wt % of a media fiber. The bicomponent binder fiber has a diameter of about 10 to 15 micrometers and a fiber length of about 0.1 to 15 cm. The media fiber has a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.1 to 2 mm, a solidity of about 10 to 25%, a basis weight of about 40 to 400 grams-m⁻², a pore size of about 10 to 30 micrometers and a permeability of about 20 to 200 ft-min⁻¹. The media comprises a secondary fiber. One example of the media fiber is a glass fiber. The glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5

micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 10 to 50 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a gaseous filtration medium for removing entrained liquid from blow comprising a thermally bonded sheet. The thermally bonded sheet is comprised of about 20 to 80 wt % of a bicomponent binder fiber and about 0.5 to 15 wt % of a media fiber or a secondary fiber. The bicomponent binder fiber has a diameter of about 5 to 15 micrometers and a fiber length of about 5 to 15 cm. The media fiber has a fiber diameter of about 0.5 to 15 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.1 to 2 mm, a solidity of about 1 to 10%, a basis weight of about 20 to 80 grams-m⁻², a pore size of about 5 to 50 micrometers, and a permeability of about 50 to 500 ft-min⁻¹. The media comprises a secondary fiber. One example of the media fiber is a glass fiber. The glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 10 to 50 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a filtration medium for filtering lubricant oil comprising a thermally bonded sheet. The sheet is comprised of about 1 to 40 wt % of a bicomponent binder fiber and about 60 to 99 wt % of a glass fiber. The bicomponent binder fiber has a diameter of about 5 to 15 micrometers and a length of about 0.1 to 15 cm. The glass fiber has a diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.2 to 2 mm, a solidity of about 2 to 10%, a basis weight of about 10 to 50 g-m⁻², a pore size of about 0.5 to 10 micrometers and a permeability of about 0.1 to 30 ft-min⁻¹. The media is comprised of a binder resin. One example of the media fiber would be a glass fiber wherein the glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 3 to 30 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

In one embodiment of the invention, the invention is a filtration medium for filtering hydraulic oil comprising a thermally bonded sheet. The sheet is comprised of about 20 to 80 wt % of a bicomponent binder fiber and about 80 to 20 wt % of a glass fiber. The bicomponent binder fiber has a diameter of about 5 to 15 micrometers and a length of about 0.1 to 15 cm. The glass fiber has a diameter of about 0.1 to 2 micrometers and an aspect ratio of about 10 to 10,000. The media has a thickness of about 0.2 to 2 mm, a basis weight of about 40 to 350 g-m⁻², a pore size of about 0.5 to 30 micrometers and a permeability of about 5 to 200 ft-min⁻¹. The media is comprised of a binder resin. One example of the media fiber would be a glass fiber wherein the glass fiber is selected from one or two or more sources of glass fiber where the average diameter of the glass fiber is of about 0.1 to 1 micrometers, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, or 3 to 30 micrometers. The media is comprised of a single layer or two or more layers. The media is comprised of about 0.01 to 10 wt % of a fluoro-organic agent.

A method of the invention embodies filtering a heated fluid. The method is comprised of passing a mobile fluid phase containing a contaminant through a filter medium, the medium having a thickness of about 0.2 to 50 mm, the medium comprising a thermally bonded sheet, and removing the contaminant. The sheet is comprised of about 20 to 80 wt % of a biocomponent binder fiber and about 20 to 80 wt % of a glass fiber. The bicomponent binder fiber has a first component with a melting point and a second component with a lower melting point. The bicomponent binder fiber has a diameter of about 5 to 50 micrometers and a length of about 0.1 to 15 cm. The glass fiber has a diameter of about 0.1 to 30 micrometers and an aspect ratio of about 10 to 10,000. The media has a solidity of about 2 to 25%, a basis weight of about 10 to 1000 g-m⁻², a pore size of about 0.5 to 100 micrometers and a permeability of about 5 to 500 ft-min⁻¹, the mobile fluid phase having a temperature greater than the melting point of the second component. In one embodiment of the method described the fluid is a gas or liquid. In one embodiment of the method described the liquid is an aqueous liquid, fuel, lubricant oil or hydraulic fluid. In one embodiment of the method described, the contaminant is a liquid or solid.

While the invention has been described in connection with specific embodiments thereof, it will be understood that it is capable of further modifications and this application is intended to cover any variations, uses, or adaptations of the invention following, in general, the principles of the invention and including such departures from the present disclosure as come with known or customary practice within the art to which the invention pertains and as may be applied to the essential features hereinbefore set forth and as follows in scope of the appended claims.

We claim:

1. A filtration medium comprising a thermally bonded sheet, the sheet comprising:

- (a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm; [and]
- (b) an effective amount of a glass fiber having a fiber diameter of about 0.1 to 30 micrometers, an aspect ratio of about 10 to 10,000 to obtain a pore size of about 0.5 to [100] 30 micrometers and a permeability of about 5 to 500 ft-min⁻¹; and

(c) a binder resin,

wherein the [media] medium has a thickness of about 0.2 to [50] 1.9 mm, a solidity of about 2 to 25%, a basis weight of about 10 to 1000 g-m⁻².

2. The medium of claim 1 wherein the [media] medium comprises about 0.1 to 10 wt % of a binder resin.

3. The medium of claim 1 wherein the [media] medium comprises about 0.5 to 15 wt % of a secondary fiber.

4. The medium of claim 3 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, 3 to 30 micrometers and combinations of two or more sources thereof.

5. The medium of claim 1 comprising two or more layers.

6. The medium of claim 1 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

7. The medium of claim 1, wherein the bicomponent binder fiber comprises a blend of two or more fibers having different average diameters.

35

8. The medium of claim 1, wherein the bicomponent binder fiber comprises a blend of two or more fibers comprising different materials.

9. The medium of claim 8 wherein the different materials comprise two or more of a vinyl acetate polymer, poly(vinyl chloride), polyvinyl alcohol, polyvinyl acetate, polyvinyl acetyl, acrylic polymer, methacrylic polymer, polyamide, polyethylene vinyl acetate copolymer, urea phenol resin, urea formaldehyde resin, a polyolefin, a polyester, a nylon, polytetrafluoroethylene, polyvinyl chloride acetate, polyvinyl butyral, polyvinylidene chloride, polystyrene, a cellulosic resin, or blends or copolymers thereof.

10. A liquid filtration medium comprising a thermally bonded sheet, the sheet comprising:

- (a) about 10 to 90 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm; [and]
- (b) about 10 to 90 wt % of a media fiber having a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000; and

(c) binder resin,

wherein the [media] medium has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 2 to 200 g-m⁻², a pore size of about 0.2 to [50] 30 micrometers and a permeability of about 2 to 200 ft-min⁻¹.

11. The medium of claim 10 wherein the [media] medium comprises a secondary fiber.

12. The medium of claim 10 wherein the media fiber comprises a glass fiber.

13. The medium of claim [12] wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to [7] 5 micrometers, 1 to [10] 5 micrometers, 10 to 50 micrometers and combinations of two or more sources thereof.

14. The medium of claim 10 [also] comprising [a] 0.1 to 25 wt % of [a] binder resin.

15. The medium of claim 10 comprising two or more layers.

16. The medium of claim 10 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

17. A method of filtering a liquid stream, the method comprising:

- (a) placing a filter unit into the stream and
- (b) retaining particulate entrained in the filter in the stream using filter media within the filter unit, the filter media comprising a thermally bonded sheet comprising:
 - (i) about 10 to 90 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm; [and]
 - (ii) about 10 to 90 wt % of a media fiber having a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000; and

(c) binder resin,

wherein the [medium] filter media has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25 %, a basis weight of about 2 to 200 g-m⁻², a pore size of about 0.2 to [50] 30 micrometers and a permeability of about 2 to 200 ft-min⁻¹.

18. The method of claim 17 wherein the liquid is an aqueous liquid.

19. The method of claim 17 wherein the liquid is a non-aqueous liquid.

36

[20. The method of claim 19 wherein the medium also comprises 0.1 to 25 wt % of a binder resin.]

21. The method of claim 17 comprising two or more layers.

22. A gaseous filtration medium for removing mist from air comprising a thermally bonded sheet, the sheet comprising:

- (a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm;
- (b) about 20 to 80 wt % of a media fiber having a fiber diameter of about 0.1 to 20 micrometers and an aspect ratio of about 10 to 10,000; and

(c) binder resin,

wherein the [media] medium has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 20 to 200 grams-m⁻², a pore size of about 5 to [100] 30 micrometers and a permeability of about 5 to 500 ft-min⁻¹.

23. The medium of claim 22 wherein the [media] medium comprises about 0.1 to 10 wt % of a secondary fiber having a fiber diameter of 0.1 to 15 [microns] micrometers.

24. The medium of claim 22 wherein the media fiber comprises a glass fiber.

25. The medium of claim 24 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, 10 to [50] 20 micrometers and combinations of two or more sources thereof.

26. The medium of claim 22 comprising two or more layers.

27. The medium of claim 22 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

28. A gaseous filtration medium for removing particulate from air comprising a thermally bonded sheet, the sheet comprising:

- (a) about 80 to 98 wt % of a bicomponent binder fiber having a fiber diameter of about 10 to 15 micrometers and a fiber length of about 0.1 to 15 cm;
- (b) about 2 to 20 wt % of a media fiber having a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000; and

(c) binder resin,

wherein the [media] medium has a thickness of about 0.1 to 2 mm, a solidity of about 10 to 25%, a basis weight of about 40 to 400 grams-m⁻², a pore size of about 10 to 30 micrometers and a permeability of about 20 to 200 ft-min⁻¹.

29. The medium of claim 28 wherein the [media] medium comprises a secondary fiber.

30. The medium of claim 28 wherein the media fiber comprises a glass fiber.

31. The medium of claim 30 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to [7] 5 micrometers, 1 to [10] 5 micrometers, 10 to 50 micrometers and combinations of two or more sources thereof.

32. The medium of claim 28 comprising two or more layers.

33. The medium of claim [28] 30 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

37

34. A gaseous filtration medium for removing an entrained liquid from blow-by gases comprising a thermally bonded sheet, the sheet comprising:

- (a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 15 micrometers and a fiber length of about 5 to 15 cm;
- (b) about 0.5 to 15 wt % of a media fiber or a secondary fiber having a fiber diameter of about 0.5 to 15 micrometers and an aspect ratio of about 10 to 10,000; and
- (c) binder resin,

wherein the [media] medium has a thickness of about 0.1 to 2 mm, a solidity of about [1] 2 to 10%, a basis weight of about 20 to 80 grams-m⁻², a pore size of about 5 to [50] 30 micrometers and a permeability of about 50 to 500 ft-min⁻¹.

35. The medium of claim 34 wherein the [media] medium comprises a secondary fiber.

36. The medium of claim 34 wherein the media fiber comprises a glass fiber.

37. The medium of claim 36 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about [0.1] 0.5 to 1 micrometer, [0.3] 0.5 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, 10 to [50] 15 micrometers and combinations of two or more sources thereof.

38. The medium of claim 34 comprising two or more layers.

39. The medium of claim [37] 34 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

40. A filtration medium for filtering a lubricant oil comprising a thermally bonded sheet, the sheet comprising:

- (a) about 1 to 40 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 15 micrometers and a fiber length of about 0.1 to 15 cm; and
- (b) about 60 to 99 wt % of a glass fiber having a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000;

wherein the [media] medium has a thickness of about 0.2 to 2 mm, a solidity of about 2 to 10%, a basis weight of about 10 to 50 g-m⁻², a pore size of about 0.5 to 10 micrometers and a permeability of about 0.1 to 30 ft-min⁻¹.

41. The medium of claim 40 wherein the [media] medium comprises a binder resin.

[42. The medium of claim 40 wherein the media fiber comprises a glass fiber.]

43. The medium of claim [42] 40 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to [7] 5 micrometers, 1 to [10] 5 micrometers[, 3 to 30 micrometers] and combinations of two or more sources thereof.

44. The medium of claim 40 comprising two or more layers.

45. The medium of claim [44] 40 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

46. A filtration medium for filtering a hydraulic oil comprising a thermally bonded sheet, the sheet comprising:

- (a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 15 micrometers and a fiber length of about 0.1 to 15 cm; [and]

38

- (b) about 80 to 20 wt % of a media fiber having a fiber diameter of about 0.1 to 2 micrometers and an aspect ratio of about 10 to 10,000; and

(c) binder resin,

wherein the [media] medium has a thickness of about 0.2 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 40 to 350 g-m⁻², a pore size of about 0.5 to 30 micrometers and a permeability of about 5 to 200 ft-min⁻¹.

[47. The medium of claim 46 wherein the media comprises a binder resin.]

48. The medium of claim 46 wherein the media fiber comprises a glass fiber.

49. The medium of claim 48 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to [5] 2 micrometers, 0.75 to [7] 2 micrometers, 1 to [10] 2 micrometers[, 3 to 30 micrometers] and combinations of two or more sources thereof.

50. The medium of claim 46 comprising two or more layers.

51. The medium of claim 46 wherein the [media] medium contains a secondary thermoplastic binder fiber and is substantially free of a residue from an aqueous binder resin.

[52. A method of filtering a heated fluid, the method comprises the steps of:

- (a) passing a mobile fluid phase containing a contaminant through a filter medium, the medium having a thickness of about 0.2 to 50 mm, the medium comprising a thermally bonded sheet, the sheet comprising:
 - (i) about 20 to 80 wt % of a bicomponent binder fiber having a first component with a melting point and a second component with a lower melting point, the fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm; and
 - (ii) about 20 to 80 wt % of a glass fiber having a fiber diameter of about 0.1 to 30 micrometers and an aspect ratio of about 10 to 10,000;

wherein the media has a solidity of about 2 to 25%, a basis weight of about 10 to 1000 g-m⁻², a pore size of about 0.5 to 100 micrometers and a permeability of about 5 to 500 ft-min⁻¹, the mobile fluid phase having a temperature greater than the melting point of the second component; and (b) removing the contaminant.]

[53. The method of claim 52 wherein the fluid is a gas.]

[54. The method of claim 52 wherein the contaminant is a liquid.]

[55. The method of claim 52 wherein the contaminant is a solid.]

[56. The method of claim 52 wherein the fluid is a liquid.]

[57. The method of claim 52 wherein the liquid is an aqueous liquid.]

[58. The method of claim 52 wherein the liquid is a fuel.]

[59. The method of claim 52 wherein the liquid is a lubricant oil.]

[60. The method of claim 52 wherein the liquid is a hydraulic fluid.]

61. A filtration medium comprising a thermally bonded sheet, the sheet comprising:

- (a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm[:];
- (b) binder resin comprising an effective medium bonding amount of a secondary binder fiber, the [fiber] binder resin comprising a thermoplastic resin; and

39

(c) about 20 to 80 wt % of a glass fiber having a fiber diameter of about 0.1 to 30 micrometers and an aspect ratio of about 10 to 10,000;

wherein the [media] *medium* has a thickness of about 0.2 to [50] 1.9 mm, a solidity of about 2 to 25%, a basis weight of about 10 to 1000 g-m⁻², a pore size of about 0.5 to [100] 30 micrometers and a permeability of about 5 to 500 ft-min⁻¹.

62. The medium of claim 61 wherein the [media] *medium* comprises about 0.1 to 10 wt % of [a] binder resin.

63. The medium of claim 61 wherein the [media] *medium* comprises an effective amount of the secondary binder fiber to bind the sheet and the [media] *medium* is substantially free of a residue from an aqueous binder resin.

64. The medium of claim 61 wherein the [media] *medium* comprises 0.5 to 15 wt % of the secondary binder fiber and the [media] *medium* is substantially free of a residue from an aqueous binder resin.

65. The medium of claim 63 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, 3 to 30 micrometers and combinations of two or more sources thereof.

66. The medium of claim 61 comprising two or more layers.

67. A liquid filtration medium comprising a thermally bonded sheet, the sheet substantially free of a residue from an aqueous binder resin, the sheet comprising:

(a) about 10 to 90 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm;

(b) *binder resin comprising* an effective medium [binding] *bonding* amount of a secondary binder fiber, the [fiber] *binder resin* comprising a thermoplastic resin; and

(c) about 10 to 90 wt % of a media fiber having a fiber diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000;

wherein the [media] *medium* has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 2 to 200 g-m⁻², a pore size of about 0.2 to [50] 30 micrometers and a permeability of about 1 to 200 ft-min⁻¹.

68. The medium of claim 67 wherein the [media] *medium* comprises about 0.5 to 15 wt % of the secondary binder fiber and the media fiber comprises a glass fiber.

69. The medium of claim 68 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to [7] 5 micrometers, 1 to [10] 5 micrometers, [10 to 50 micrometers] and combinations of two or more sources thereof.

70. The medium of claim 67 comprising two or more layers.

71. A method of filtering a liquid stream, the method comprising:

(a) placing a filter unit comprising the medium of claim 67 into the stream; and

(b) retaining particulate entrained within the filter *unit* from the stream using *the* filter [media] *medium* within the filter unit.

72. A gaseous filtration medium for removing mist from air comprising a thermally bonded sheet, the sheet substantially free of a residue from an aqueous binder resin, the sheet comprising:

40

(a) about 20 to 80 wt % of a bicomponent binder fiber having a fiber diameter of about 5 to 50 micrometers and a fiber length of about 0.1 to 15 cm;

(b) *binder resin comprising* an effective medium bonding amount of a secondary binder fiber, the [fiber] *binder resin* comprising a thermoplastic resin; and

(c) about 20 to 80 wt % of a media fiber with a diameter of about 0.1 to 20 micrometers and an aspect ratio of about 10 to 10,000;

wherein the [media] *medium* has a thickness of about 0.1 to 2 mm, a solidity of about 2 to 25%, a basis weight of about 20 to 200 g-m⁻², a pore size of about 5 to 20 micrometers and a permeability of about 5 to 500 ft-min⁻¹.

73. The medium of claim 72 wherein the secondary binder fiber is present in an effective amount to bind the sheet and the fiber has a fiber diameter of about 0.1 to 15 [microns] *micrometers*.

74. The medium of claim 72 wherein the [media] *medium* comprises about 0.5 to 15 wt % of the secondary binder fiber having a diameter of about 0.1 to 15 [microns] *micrometers* and the media fiber comprises a glass fiber.

75. The medium of claim 74 wherein the glass fiber is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75 to 7 micrometers, 1 to 10 micrometers, 10 to [50] 15 micrometers and combinations of two or more sources thereof.

76. A method of filtering a gaseous stream, the method comprising:

(a) placing a filter unit comprising the medium of claim 72 into the stream; and

(b) retaining particulate entrained within the filter *unit* from the stream using *the* filter [media] *medium* within the filter unit.

77. A gaseous filtration medium for removing particulate from air comprising a thermally bonded sheet, the sheet substantially free of a residue from an aqueous binder resin, the sheet comprising:

(a) about 80 to 98 wt % of a bicomponent binder fiber having a fiber diameter of about 10 to 15 micrometers and a fiber length of about 0.1 to 15 cm;

(b) *binder resin comprising* an effective medium bonding amount of a secondary binder fiber, the [fiber] *binder resin* comprising a thermoplastic resin; and

(c) about 2 to 20 wt % of a media fiber with a diameter of about 0.1 to 5 micrometers and an aspect ratio of about 10 to 10,000;

wherein the [media] *medium* has a thickness of about 0.1 to 2 mm, a solidity of about 10 to 25%, a basis weight of about 40 to 400 g-m⁻², a pore size of about 10 to 30 micrometers and a permeability of about 20 to 200 ft-min⁻¹.

78. The medium of claim 77 wherein the secondary binder fiber is present in an effective amount to bind the sheet and the fiber has a fiber diameter of 0.1 to 15 [microns] *micrometers*.

79. The medium of claim 77 wherein the secondary binder fiber is present in an amount of about 0.01 to 10 wt % and the fiber has a fiber diameter of 0.1 to 15 [microns] *micrometers*.

80. The medium of claim 79 wherein the *media fiber* comprises glass fiber *and* is selected from [the] sources comprising an average fiber diameter of about 0.1 to 1 micrometer, 0.3 to 2 micrometers, 0.5 to 5 micrometers, 0.75

to [7] 5 micrometers, 1 to [10] 5 micrometers[, 10 to 50 micrometers] and combinations of two or more sources thereof.

81. The medium of claim 77 comprising two or more layers.

5

82. A method of filtering a gaseous stream, the method comprising:

(a) placing a filter unit comprising the medium of claim 77 into the stream and

(b) retaining particulate entrained within the filter *unit* 10 from the stream using *the* filter [media] *medium* within the filter unit.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : RE49,097 E
APPLICATION NO. : 16/678393
DATED : June 7, 2022
INVENTOR(S) : Brad E. Kahlbaugh et al.

Page 1 of 2

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On the Title Page

In References Cited item (56), the date '9/2002' for 2002/0092423 A1 should read --7/2002--.

In the Claims

In Claim 1 Line 49, '25%' should read --25 %--.

In Claim 10 Line 24, '25%' should read --25 %--.

In Claim 22 Line 17, '25%' should read --25 %--.

In Claim 28 Line 48, '25%' should read --25 %--.

In Claim 33 Line 64, '[28]' should read --28--.

In Claim 33 Line 64, '30' should read --[30]--.

In Claim 34 Line 12, '10%' should read --10 %--.

In Claim 40 Line 43, '10%' should read --10 %--.

In Claim 46 Line 5, '25%' should read --25 %--.

In Claim 61 Line 5, '25%' should read --25 %--.

In Claim 67 Line 42, '25%' should read --25 %--.

Signed and Sealed this
Sixth Day of June, 2023



Katherine Kelly Vidal
Director of the United States Patent and Trademark Office

CERTIFICATE OF CORRECTION (continued)
U.S. Pat. No. RE49,097 E

Page 2 of 2

In Claim 72 Line 11, '25%' should read --25 %--.

In Claim 77 Line 52, '25%' should read --25 %--.