

US00RE49307E

(19) **United States**
(12) **Reissued Patent**
Ellison et al.

(10) **Patent Number:** **US RE49,307 E**
(45) **Date of Reissued Patent:** ***Nov. 22, 2022**

(54) **ALKALI-DOPED AND ALKALI-FREE
BOROALUMINOSILICATE GLASS**

(71) Applicant: **CORNING INCORPORATED**,
Corning, NY (US)

(72) Inventors: **Adam James Ellison**, Corning, NY
(US); **Jason Sanger Frackenhohl**,
Corning, NY (US); **John Christopher
Mauro**, Corning, NY (US); **Douglas
Miles Noni, Jr.**, Horseheads, NY (US);
Natesan Venkataraman, Painted Post,
NY (US)

(73) Assignee: **Corning Incorporated**, Corning, NY
(US)

(*) Notice: This patent is subject to a terminal dis-
claimer.

(21) Appl. No.: **16/902,663**

(22) Filed: **Jun. 16, 2020**

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **10,000,409**
Issued: **Jun. 19, 2018**
Appl. No.: **15/478,571**
Filed: **Apr. 4, 2017**

U.S. Applications:

(62) Division of application No. 14/455,332, filed on Aug.
8, 2014, now Pat. No. 9,643,884.

(Continued)

(51) **Int. Cl.**
B32B 17/06 (2006.01)
C03C 3/091 (2006.01)

(Continued)

(52) **U.S. Cl.**
CPC **H01Q 1/38** (2013.01); **H01Q 1/2283**
(2013.01); **H01Q 9/0407** (2013.01); **H01Q**
15/0013 (2013.01)

(58) **Field of Classification Search**
CPC C03C 3/095; C03C 13/046; C03C 3/11;
C03C 3/093; C03C 3/118; B32B 17/06;
C03B 17/02
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,008,841 A 11/1961 Tiede
3,673,049 A 6/1972 Giffen et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 1531007 A 9/2004
CN 1807308 A 7/2006
(Continued)

OTHER PUBLICATIONS

European Patent Application No. 14755493.5 Office Action dated
Oct. 2, 2018; 6 pages; European Patent Office.

(Continued)


Primary Examiner — Carlos N Lopez

(74) *Attorney, Agent, or Firm* — Russell S. Magaziner

(57) **ABSTRACT**

Alkali-doped boroaluminosilicate glasses are provided. The glasses include the network formers SiO₂, B₂O₃, and Al₂O₃. The glass may, in some embodiments, have a Young's modulus of less than about 65 GPa and/or a coefficient of thermal expansion of less than about 40×10⁻⁷/° C. The glass may be used as a cover glass for electronic devices, a color filter substrate, a thin film transistor substrate, or an outer clad layer for a glass laminate.

32 Claims, 2 Drawing Sheets



Related U.S. Application Data

(60) Provisional application No. 61/866,272, filed on Aug. 15, 2013.

(51) **Int. Cl.**
C03B 17/06 (2006.01)
H01Q 1/38 (2006.01)
H01Q 1/22 (2006.01)
H01Q 9/04 (2006.01)
H01Q 15/00 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,737,294	A	6/1973	Dumbaugh et al.
3,746,526	A	7/1973	Giffon
3,849,097	A	11/1974	Giffon et al.
3,931,438	A	1/1976	Beall et al.
4,102,664	A	7/1978	Dumbaugh, Jr.
4,214,886	A	7/1980	Shay et al.
4,350,532	A	9/1982	Randklev
4,554,259	A	11/1985	Franklin et al.
5,116,787	A	5/1992	Dumbaugh, Jr.
5,342,426	A	8/1994	Dumbaugh, Jr.
5,348,916	A	9/1994	Kushitani et al.
5,489,558	A	2/1996	Moffatt et al.
5,559,060	A	9/1996	Dumbaugh et al.
5,785,726	A	7/1998	Dorfeld et al.
5,801,109	A	9/1998	Nishizawa et al.
5,811,361	A	9/1998	Miwa
5,824,127	A	10/1998	Bange et al.
5,851,939	A	12/1998	Miwa
6,096,670	A	8/2000	Lautenschlaeger et al.
6,128,924	A	10/2000	Bange et al.
6,169,047	B1	1/2001	Nishizawa et al.
6,287,674	B1	9/2001	Verlinden et al.
6,319,867	B1	11/2001	Chacon et al.
6,329,310	B1	12/2001	Peuchert et al.
6,417,124	B1	7/2002	Peuchert et al.
6,465,381	B1	10/2002	Lautenschlaeger et al.
6,468,933	B1	10/2002	Narita et al.
6,537,937	B1	3/2003	Nishizawa et al.
6,680,266	B1	1/2004	Peuchert et al.
6,707,526	B2	3/2004	Peuchert et al.
RE38,959	E	1/2006	Kohli
6,992,030	B2	1/2006	Paulson
7,153,797	B2	12/2006	Peuchert
7,157,392	B2	1/2007	Peuchert et al.
7,201,965	B2	4/2007	Gulati et al.
7,323,426	B2	1/2008	Aitken
7,323,427	B2	1/2008	Wolff et al.
7,470,642	B2	12/2008	Fechner et al.
7,514,149	B2	4/2009	Bocko et al.
7,534,734	B2	5/2009	Ellison
7,635,521	B2	12/2009	Aitken et al.
7,696,113	B2	4/2010	Ellison
7,763,559	B2	7/2010	Kurachi et al.
8,007,913	B2	8/2011	Coppola et al.
8,129,299	B2	3/2012	Kishimoto et al.
8,349,751	B2	1/2013	Nagai et al.
8,445,394	B2	5/2013	Aitken et al.
8,497,220	B2	7/2013	Murata
8,697,590	B2	4/2014	Li et al.
8,796,165	B2	8/2014	Ellison et al.
8,835,335	B2	9/2014	Murata et al.
9,023,421	B2	5/2015	Nakashima
9,096,462	B2	8/2015	Li
9,266,769	B2	2/2016	Aitken et al.
9,346,705	B2	5/2016	Kiczenski et al.
9,512,030	B2	12/2016	Mauro
9,643,884	B2 *	5/2017	Ellison C03B 17/02
10,000,409	B2	6/2018	Ellison et al.
10,112,865	B2	10/2018	Kiczenski et al.
10,399,890	B2 *	9/2019	Mauro B32B 17/06
2001/0034293	A1	10/2001	Peuchert et al.

2001/0034294	A1	10/2001	Peuchert et al.
2002/0013210	A1	1/2002	Peuchert et al.
2002/0032117	A1	3/2002	Peuchert et al.
2002/0151426	A1	10/2002	Murata et al.
2003/0087746	A1	5/2003	Ritter et al.
2003/0129417	A1	7/2003	Chen et al.
2004/0209758	A1	10/2004	Peuchert et al.
2006/0003884	A1	1/2006	Nishizawa et al.
2006/0242996	A1	11/2006	Deangelis et al.
2007/0158317	A1	7/2007	Brix et al.
2007/0190338	A1	8/2007	Aitken et al.
2007/0190340	A1	8/2007	Coppola et al.
2007/0213194	A1	9/2007	Abensour et al.
2008/0194394	A1	8/2008	Lecomte
2008/0206494	A1	8/2008	Kurachi et al.
2009/0129061	A1	5/2009	Fechner et al.
2010/0048016	A1	2/2010	Izumi et al.
2010/0084016	A1	4/2010	Aitken et al.
2010/0151210	A1	6/2010	Shimatani
2010/0292068	A1	11/2010	Takaya et al.
2010/0300536	A1	12/2010	Aitken et al.
2011/0207594	A1	8/2011	Niida et al.
2011/0240499	A1	10/2011	Taniguchi et al.
2011/0318555	A1	12/2011	Bookbinder et al.
2011/0318561	A1	12/2011	Murata et al.
2012/0015150	A1	1/2012	Suzuki
2012/0063479	A1	3/2012	Li et al.
2012/0088648	A1	4/2012	Ellison et al.
2012/0135226	A1	5/2012	Bookbinder et al.
2012/0135852	A1	5/2012	Ellison et al.
2012/0135853	A1	5/2012	Amin et al.
2012/0141668	A1	6/2012	Nakashima
2012/0282450	A1	11/2012	Kawaguchi et al.
2012/0308803	A1	12/2012	Dejneka et al.
2013/0037105	A1	2/2013	Aitken et al.
2013/0330599	A1	12/2013	Kroll et al.
2014/0049708	A1	2/2014	Murata et al.
2014/0242375	A1	8/2014	Mauro et al.
2014/0335331	A1	11/2014	Ellison et al.
2014/0342897	A1	11/2014	Amin et al.
2015/0037552	A1	2/2015	Mauro
2015/0037553	A1	2/2015	Mauro
2015/0051060	A1	2/2015	Ellison et al.
2015/0140299	A1	5/2015	Ellison et al.
2016/0174301	A1	6/2016	Comte et al.
2018/0339932	A1	11/2018	Qian et al.
2020/0055769	A1	2/2020	Schwall et al.
2020/0102241	A1	4/2020	Miyasaka et al.

FOREIGN PATENT DOCUMENTS

CN	101092280	A	12/2007
CN	101243020	A	8/2008
CN	101400613	A	4/2009
CN	102417295	A	4/2012
CN	102448901	A	5/2012
CN	103249689	A	8/2013
DE	102005019958	A1	11/2006
DE	102008005857	A1	7/2009
FR	2905694	A1	3/2008
JP	60-036349	A	2/1985
JP	63-011543	A	1/1988
JP	01-201041	A	8/1989
JP	07-010598	A	1/1995
JP	07-277763	A	10/1995
JP	07-300336	A	11/1995
JP	08-295530	A	11/1996
JP	09-156953	A	6/1997
JP	2719504	B2	2/1998
JP	10-139467	A	5/1998
JP	2000-001331	A	1/2000
JP	2001-172041	A	6/2001
JP	2001151534	A	6/2001
JP	2002-003240	A	1/2002
JP	2002-029775	A	1/2002
JP	2003-054984	A	2/2003
JP	2003-335548	A	11/2003
JP	2004-002062	A	1/2004
JP	2004075494	A	3/2004

(56)

References Cited**FOREIGN PATENT DOCUMENTS**

JP	2004-168597	A	6/2004
JP	2004-189535	A	7/2004
JP	2005-089286	A	4/2005
JP	2005-263628	A	9/2005
JP	2006-188406	A	7/2006
JP	2006-213595	A	8/2006
JP	2007-246365	A	9/2007
JP	2008-522950	A	7/2008
JP	2008-308375	A	12/2008
JP	2008-308376	A	12/2008
JP	2009-525943	A	7/2009
JP	2010-509180	A	3/2010
JP	2010-215463	A	9/2010
JP	2001151534		3/2011
JP	2011-093728	A	5/2011
JP	2011-162413	A	8/2011
JP	2012-111692	A	6/2012
JP	2012-528072	A	11/2012
JP	2013-530123	A	7/2013
SU	1377250	A1	2/1988
TW	1252844	B	4/2006
WO	8902877		4/1989
WO	8902877	A1	4/1989
WO	2008/149021	A2	12/2008
WO	2011/136027	A1	11/2011
WO	2012/074953	A1	6/2012
WO	2012/147615	A1	11/2012
WO	2013/020128	A1	2/2013
WO	2013/065648	A1	5/2013
WO	2013/130700	A1	9/2013
WO	2013130718		9/2013
WO	2013130718	A1	9/2013
WO	2014/182753	A1	11/2014
WO	2019/119341	A1	6/2019
WO	2019/181707	A1	9/2019
WO	2019/233290	A1	12/2019
WO	2019/233291	A1	12/2019

OTHER PUBLICATIONS

English Translation of KR1020167006450 Office Action dated Jul. 20, 2020; 8 Pages; Korean Patent Office.

Mauro, "Statistics of Modifier Distributions in Mixed Network Glasses," J. Chem. Phys. 138, 12A522 (2013).

U.S. Appl. No. 17/221,926 Office Action dated Jun. 23, 2021; 44 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926, Response to Office Action dated Jul. 8, 2021; 14 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926 Notice of Allowance dated Sep. 27, 2021; 7 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926 Examiner Initiated Summary Record dated Aug. 30, 2021; 5 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926, Final Office Action dated Aug. 10, 2021; 11 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926, Response to Office Action dated Aug. 12, 2021; 4 pages; U.S. Patent Office.

U.S. Appl. No. 17/221,926, Response to Office Action dated Sep. 7, 2021; 5 pages; U.S. Patent Office.

Korean Patent Application No. 10-2016-7006353, Notice of Allowance dated May 12, 2021, 4 pages (2 pages of English Translation and 2 pages of Original Document), Korean Patent Office.

Ellison et al.; U.S. Appl. No. 61/821,426; "Alkali-Free Phosphoborosilicate Glass;" May 2013; 24 pages.

Ellison et al.; U.S. Appl. No. 61/866,272; "Alkali-Doped and Alkali-Free Boroaluminosilicate Glass;" Aug. 2013; 23 pages.

English Translation of CN201480054310.X First Office Action dated Mar. 17, 2017, China Patent Office.

English Translation of JP2014560016 Office Action dated Oct. 25, 2016; 3 pages; Japanese Patent Office.

English Translation of JP2016534765 Office Action dated May 8, 2018; 4 pages; Japanese Patent Office.

European Patent Application No. 14753438.2; Office Action dated Jan. 13, 2021; 5 pages; European Patent Office.

European Patent Application No. 13710680.3 Office Action dated Dec. 8, 2017; 4 Pages; European Patent Office.

European Patent Application No. 14755493.5 Decision to grant a European patent dated Feb. 11, 2021; 2 Pages; European Patent Office.

European Patent Office; International Search Report; dated Mar. 6, 2015; pp. 1-4.

International Preliminary Report on Patentability; PCT/US2014/050486; dated Feb. 23, 2016.

International Search Report and Written Opinion of the International Searching Authority; PCT/US13/28177; dated Jul. 16, 2013; 10 Pages; European Patent Office.

International Search Report and Written Opinion of the International Searching Authority; PCT/US2014/037043; dated Aug. 13, 2014; 11 Pages; European Patent Office.

International Search Report and Written Opinion of the International Searching Authority; PCT/US2014/050486; dated Mar. 6, 2015.

International Search Report and Written Opinion, dated Jul. 16, 2013, pp. 1-11, International Patent Application No. PCT/US2013/028177, European Patent Office, The Netherlands.

John C. Mauro; "Statistics of modifier distributions in mixed network glasses"; The Journal of Chemical Physics 138 (2013); pp. 12A522-1-12A522-8.

Korean Patent Application No. 10-2015-7033782; Office Action dated Mar. 30, 2021; 4 Pages; Korean Patent Office.

Mauro et al.; U.S. Appl. No. 61/604,839; "Low CTE Alkali-Free Boroaluminosilicate Glass Compositions and Glass Articles Comprising the Same;" Feb. 2012; 25 pages.

Orlov A.D., Razrabotka Sostavov i Tekhnologii Tugoplavkikh Elektrovakuumnykh Stekol Volframovoi Gruppy. Thesis. Moskva, 1991.

PCT/US2014/037043 International Preliminary Report on Patentability dated Nov. 19, 2015.

PCT/US2014/037043 Search Report dated Aug. 13, 2014.

Shigeki Morimoto; "Phase separation and crystallization in the system SiO₂-Al₂O₃-P₂O₅-B₂O₃-Na₂O glasses"; Journal of Non-Crystalline Solids 352 (2006); pp. 756-760.

Korean Patent Application No. 10-2016-7006450, Office Action dated May 22, 2021, 5 pages (2 pages of English Translation and 3 pages of Original Document), Korean Patent Office.

Chinese Patent Application No. 202110371219.2, Office Action, dated Jul. 1, 2022, 5 pages, Chinese Patent Office.

PCT/US2014/050279 Search report dated Oct. 29, 2014—Cited as EP Search Report.

* cited by examiner

FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E





FIG. 2F



ALKALI-DOPED AND ALKALI-FREE BOROALUMINOSILICATE GLASS

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue; a claim printed with strikethrough indicates that the claim was canceled, disclaimed, or held invalid by a prior post-patent action or proceeding.

This application is a *reissue application of U.S. application Ser. No. 15/478,571, filed Apr. 4, 2017, which is a divisional application of U.S. application Ser. No. 14/455,332, filed on Aug. 8, 2014, now issued as U.S. Pat. No. 9,643,884, which claims the benefit of priority under 35 U.S.C. § 119 of U.S. Provisional Application Ser. No. 61/866,272, filed [on] Aug. 15, 2013, the content of which is relied upon and incorporated herein by reference in its entirety.*

BACKGROUND

The disclosure relates to glasses that do not contain alkali metals or their oxides. More particularly, the disclosure relates to glasses that either contain low levels of alkali metals and/or alkali metal oxides or are alkali-doped and alkali-free and are formable by down-draw processes such as slot-draw and fusion-draw techniques. Even more particularly, the disclosure relates to glasses that either contain low levels of alkali metals and/or alkali metal oxides or are alkali-doped and alkali-free and can be formed into a clad layer for a glass laminate.

SUMMARY

Alkali-doped boroaluminosilicate glasses are provided. The glasses include the network formers SiO_2 , B_2O_3 , and Al_2O_3 . The glass may, in some embodiments, have a Young's modulus of less than about 65 GPa and/or a coefficient of thermal expansion, averaged over a temperature range from about 20° C. to about 300° C., of less than about $40 \times 10^{-7}/^\circ\text{C}$. The glass may be used as a cover glass for electronic devices, a color filter substrate, a thin film transistor substrate, or an outer clad layer for a glass laminate.

Accordingly, one aspect of the disclosure is to provide a glass comprising from about 50 mol % to about 70 mol % SiO_2 ; from about 5 mol % to about 20 mol % Al_2O_3 ; from about 12 mol % to about 35 mol % B_2O_3 ; up to about 5 mol % MgO ; up to about 12 mol % CaO ; and up to about 5 mol % SrO , wherein the sum of alkali metal oxide modifiers is less than or equal to about 1 mol %.

A second aspect of the disclosure is to provide a glass comprising SiO_2 , B_2O_3 , and Al_2O_3 . The sum of alkali metal oxide modifiers in the glass is less than or equal to about 1 mol %. The glass is substantially free of P_2O_5 , and has at least one of a Young's modulus of less than about 65 GPa, a coefficient of thermal expansion, averaged over a temperature range from about 20° C. to about 300° C., of less than about $40 \times 10^{-7}/^\circ\text{C}$., and a Knoop scratch threshold of at least about 15 N (Newtons).

A third aspect of the disclosure is to provide a glass laminate comprising a core glass and a clad glass laminated onto an outer surface of the core glass. The clad glass layer comprises SiO_2 , B_2O_3 , and Al_2O_3 and the sum of alkali

metal oxide modifiers in the clad layer glass is less than or equal to about 1 mol %. The clad glass has a first coefficient of thermal expansion, averaged over a temperature range from about 20° C. to about 300° C., of less than about $40 \times 10^{-7}/^\circ\text{C}$. and the core glass has a second coefficient of thermal expansion, averaged over a temperature range from about 20° C. to about 300° C., that is greater than the first coefficient of thermal expansion.

A fourth aspect of the disclosure is to provide a method of making a glass. The method comprises: providing a glass melt, the glass melt comprising SiO_2 , B_2O_3 , and Al_2O_3 , wherein the sum of alkali metal oxide modifiers in the glass is less than or equal to about 1 mol %; and down-drawing the glass melt to form the glass.

These and other aspects, advantages, and salient features will become apparent from the following detailed description, the accompanying drawings, and the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic cross-sectional view of a glass laminate; and

FIGS. 2A, 2B, 2C, 2D, 2E, and 2F are photographs of Knoop scratch test results for a glass sample.

DETAILED DESCRIPTION

In the following description, like reference characters designate like or corresponding parts throughout the several views shown in the figures. It is also understood that, unless otherwise specified, terms such as “top,” “bottom,” “outward,” “inward,” and the like are words of convenience and are not to be construed as limiting terms. In addition, whenever a group is described as comprising at least one of a group of elements and combinations thereof, it is understood that the group may comprise, consist essentially of, or consist of any number of those elements recited, either individually or in combination with each other. Similarly, whenever a group is described as consisting of at least one of a group of elements or combinations thereof, it is understood that the group may consist of any number of those elements recited, either individually or in combination with each other. Unless otherwise specified, a range of values, when recited, includes both the upper and lower limits of the range as well as any ranges therebetween. As used herein, the indefinite articles “a,” “an,” and the corresponding definite article “the” mean “at least one” or “one or more,” unless otherwise specified. It also is understood that the various features disclosed in the specification and the drawings can be used in any and all combinations.

As used herein, the terms “glass article” and “glass articles” are used in their broadest sense to include any object made wholly or partly of glass. Unless otherwise specified, all compositions are expressed in terms of mole percent (mol %). Coefficients of thermal expansion (CTE) are expressed in terms of $10^{-7}/^\circ\text{C}$. and represent a value measured over a temperature range from about 20° C. to about 300° C., unless otherwise specified.

It is noted that the terms “substantially” and “about” may be utilized herein to represent the inherent degree of uncertainty that may be attributed to any quantitative comparison, value, measurement, or other representation. These terms are also utilized herein to represent the degree by which a quantitative representation may vary from a stated reference without resulting in a change in the basic function of the subject matter at issue. Thus, a glass that is “substantially free of alkali metal oxides” or “substantially free of P_2O_5 ”

3

is one in which such oxides are not actively added or batched into the glass, but may be present in very small amounts as contaminants.

Referring to the drawings in general and to FIG. 1 in particular, it will be understood that the illustrations are for the purpose of describing particular embodiments and are not intended to limit the disclosure or appended claims thereto. The drawings are not necessarily to scale, and certain features and certain views of the drawings may be shown exaggerated in scale or in schematic in the interest of clarity and conciseness.

Described herein are glasses and glass articles made therefrom that comprise the network formers SiO_2 , B_2O_3 , and Al_2O_3 , and, in some embodiments, have low (i.e., less than about $40 \times 10^{-7}/^\circ\text{C}$.) coefficients of thermal expansion (CTE). In some embodiments, the glasses are intentionally lightly doped with less than about 1 mol % of alkali metals or alkali metal oxides to lower the resistivity of the glass melt and avoid "fire-through" of refractory containment and processing structures. In other embodiments, the glasses are free of alkali metals and alkali metal oxides (also referred to herein as "alkali metal oxide modifiers"). In some embodiments, these glasses also have low values of Young's modulus and shear modulus to improve the intrinsic or native damage resistance of the glass.

In some embodiments, the glasses described herein are formable by down-draw processes that are known in the art, such as slot-draw and fusion-draw processes. The fusion draw process is an industrial technique that has been used for the large-scale manufacture of thin glass sheets. Compared to other flat glass manufacturing techniques, such as the float or slot draw processes, the fusion draw process yields thin glass sheets with superior flatness and surface quality. As a result, the fusion draw process has become the dominant manufacturing technique in the fabrication of thin glass substrates for liquid crystal displays, as well as for cover glass for personal electronic devices such as notebooks, entertainment devices, tables, laptops, and the like.

The fusion draw process involves the flow of molten glass over a trough known as an "isopipe," which is typically made of zircon or another refractory material. The molten glass overflows the top of the isopipe from both sides, meeting at the bottom of the isopipe to form a single sheet where only the interior of the final sheet has made direct contact with the isopipe. Since neither exposed surface of the final glass sheet has made contact with the isopipe material during the draw process, both outer surfaces of the glass are of pristine quality and do not require subsequent finishing.

In order to be fusion drawable, a glass must have a sufficiently high liquidus viscosity (i.e., the viscosity of a molten glass at the liquidus temperature). In some embodiments, the glasses described herein have a liquidus viscosity of at least about 100 kilopoise (kpoise), in other embodiments, at least about 120 kpoise, and in still other embodiments, these glasses have a liquidus viscosity of at least about 300 kpoise. In those instances in which the alkali-doped and alkali-free glass is used as a clad layer in a glass laminate and the viscosity behavior of the core glass with respect to temperature is approximately the same as that of the clad glass, the liquidus viscosity of the clad glass may be greater than or equal to about 70 kPoise.

Traditional fusion draw is accomplished using a single isopipe, resulting in a homogeneous glass product. The more complicated laminate fusion process makes use of two isopipes to form a laminated sheet comprising a core glass composition surrounded on either (or both) side by outer

4

clad layers. One of the main advantages of laminate fusion is that when the coefficient of thermal expansion of the clad glass is less than that of the core glass, the CTE difference results in a compressive stress in the outer clad layer. This compressive stress increases the strength of the final glass product without the need for ion exchange treatment. Unlike ion exchange, this strengthening can be achieved without the use of alkali ions in the glass.

Accordingly, in some embodiments, the alkali-doped and alkali-free glasses described herein may be used to form a glass laminate, schematically shown in FIG. 1. Glass laminate 100 comprises a core glass 110 surrounded by a clad glass 120 or "clad layer" formed from the alkali-doped and alkali-free glass described herein. The core glass 110 has a CTE that is greater than that of the alkali-doped and alkali-free glass in the clad layer 120. The core glass may, in some embodiments, be an alkali aluminosilicate glass. In one non-limiting example, the core glass is an alkali aluminosilicate glass having the composition 66.9 mol % SiO_2 , 10.1 mol % Al_2O_3 , 0.58 mol % B_2O_3 , 7.45 mol % Na_2O , 8.39 mol % K_2O , 5.78 mol % MgO , 0.58 mol % CaO , 0.2 mol % SnO_2 , 0.01 mol % ZrO_2 , and 0.01 mol % Fe_2O_3 , with a strain point of 572°C ., an anneal point of 629°C ., a softening point of 888°C ., and $\text{CTE}=95.5 \times 10^{-7}/^\circ\text{C}$.

When employed as a clad glass in a laminated product, the alkali-doped and alkali-free glass compositions described herein can provide high compressive stresses to the clad layer. The CTE of low alkali metal oxide/alkali-doped and alkali-free fusion-formable glasses described herein are generally in the range of about $40 \times 10^{-7}/^\circ\text{C}$ or less and, in some embodiments, in the range of about $35 \times 10^{-7}/^\circ\text{C}$ or less. When such a glass is paired with, for example, an alkali aluminosilicate glass (e.g., Gorilla® Glass, manufactured by Corning Incorporated) having a CTE of $90 \times 10^{-7}/^\circ\text{C}$., the expected compressive stress in the clad glass can be calculated using the elastic stress equations given below in which subscripts 1 and 2 refer to the core glass and the clad glass, respectively:

$$\sigma_2 = \frac{E_1(e_2 - e_1)}{\left(\frac{E_1}{E_2}(1 - \nu_2)\right) + \left(\frac{2t_2}{t_1}(1 - \nu_1)\right)}$$

and

$$\sigma_1 = -\frac{2t_2}{t_1}\sigma_2$$

where E is Young's modulus, ν is Poisson's ratio, τ is the glass thickness, σ is the stress, and $e_2 - e_1$ is the difference in thermal expansion between the clad glass and the core glass. Using the same elastic modulus and Poisson's ratio for the clad glass and core glass further simplifies the above equations.

To calculate the difference in thermal expansion between the clad glass and core glass, it is assumed that the stress sets in below the strain point of the softer glass of the clad and core. The stresses in the clad glass can be estimated using these assumptions and the equations above. For typical display-like glass with a CTE of $30 \times 10^{-7}/^\circ\text{C}$ as the clad glass and an alkali aluminosilicate core glass with CTE of $90 \times 10^{-7}/^\circ\text{C}$., overall thicknesses in the range of 0.5-1.0 mm and clad glass thickness of 10-100 μm , the compressive stress of the clad glass is estimated to be in a range from about 200 MPa to about 315 MPa. In some embodiments, the glasses described herein have coefficients of thermal expansion of less than about $40 \times 10^{-7}/^\circ\text{C}$ and, in some

embodiments, less than about $35 \times 10^{-7}/^{\circ}\text{C}$. For these glasses, the compressive stress of the clad glass layer would be at least about 40 MPa, and in other embodiments, at least about 80 MPa.

The alkali-doped and alkali-free glasses described herein have especially low coefficients of thermal expansion. In some embodiments, the CTE of the glass is less than less than about $40 \times 10^{-7}/^{\circ}\text{C}$. and, in other embodiments, is less than about $35 \times 10^{-7}/^{\circ}\text{C}$. When paired with a core glass having a higher CTE, the glasses described herein provide a high level of compressive stress in the clad layers of the final laminated glass product. This increases the strength of the glass laminate product. Room-temperature compressive stresses of at least about 40 MPa and, in some embodiments, at least about 80 MPa are attainable by using the glasses disclosed herein in the clad layer of the laminate. When used as a clad layer, the liquidus viscosity requirements of the glasses described herein may be lowered. In those embodiments where the viscosity behavior of the core glass with respect to temperature is approximately the same as (i.e., “matched with”) that of the clad glass, the liquidus viscosity of the clad glass may be greater than or equal to about 70 kPoise.

The alkali-doped and alkali-free glasses have values of Young’s modulus and shear modulus that are significantly less than those of other commercially available fusion-drawn glasses. In some embodiments, the Young’s modulus is less than about 65 gigapascals (GPa) and, in still other embodiments, less than about 60 GPa. The low elastic moduli provide these glasses with a high level of intrinsic damage resistance.

In some embodiments, the glasses described herein consist essentially of or comprise: from about 50 mol % to about 70 mol % SiO_2 (i.e., $50 \text{ mol \%} \leq \text{SiO}_2 \leq 70 \text{ mol \%}$); from about 5 mol % to about 20 mol % Al_2O_3 (i.e., $5 \text{ mol \%} \leq \text{Al}_2\text{O}_3 \leq 20 \text{ mol \%}$); from about 12 mol % to about 35 mol % B_2O_3 (i.e., $12 \text{ mol \%} \leq \text{B}_2\text{O}_3 \leq 35 \text{ mol \%}$); up to about 5 mol % MgO (i.e., $0 \text{ mol \%} \leq \text{MgO} \leq 5 \text{ mol \%}$); up to about 12 mol % CaO (i.e., $0 \text{ mol \%} \leq \text{CaO} \leq 12 \text{ mol \%}$); and up to about 5 mol % SrO (i.e., $0 \text{ mol \%} \leq \text{SrO} \leq 5 \text{ mol \%}$), wherein the sum of the alkali metal oxide modifiers is less than or equal to 0.1 mol % (i.e., $0 \text{ mol \%} \leq \text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O} \leq 0.1 \text{ mol \%}$). In some embodiments, 4 mol % $\leq \text{MgO} + \text{CaO} + \text{SrO} \leq \text{Al}_2\text{O}_3 + 1 \text{ mol \%}$. In certain embodiments, the glass is substantially free of, or contains 0 mol %, P_2O_5 and/or alkali metal oxide modifiers.

The glass may further include up to about 0.5 mol % Fe_2O_3 (i.e., $0 \text{ mol \%} \leq \text{Fe}_2\text{O}_3 \leq 0.5 \text{ mol \%}$); up to about 0.2 mol % ZrO_2 (i.e., $0 \text{ mol \%} \leq \text{ZrO}_2 \leq 0.2 \text{ mol \%}$); and, optionally, at least one fining agent such as SnO_2 , CeO_2 , As_2O_3 , Sb_2O_5 , Cl^- , F^- , or the like. The at least one fining agent may, in some embodiments, include up to about 0.7 mol % SnO_2 (i.e., $0 \text{ mol \%} \leq \text{SnO}_2 \leq 0.5 \text{ mol \%}$); up to about 0.7 mol % CeO_2 up to about 0.5 mol % (i.e., $0 \text{ mol \%} \leq \text{CeO}_2 \leq 0.7 \text{ mol \%}$); As_2O_3 (i.e., $0 \text{ mol \%} \leq \text{As}_2\text{O}_3 \leq 0.5 \text{ mol \%}$); and up to about 0.5 mol % Sb_2O_3 (i.e., $0 \text{ mol \%} \leq \text{Sb}_2\text{O}_3 \leq 0.5 \text{ mol \%}$).

In particular embodiments, the glasses consist essentially of or comprise: from about 55 mol % to about 70 mol % SiO_2 (i.e., $55 \text{ mol \%} \leq \text{SiO}_2 \leq 70 \text{ mol \%}$); from about 6 mol % to about 10 mol % Al_2O_3 (i.e., $6 \text{ mol \%} \leq \text{Al}_2\text{O}_3 \leq 10 \text{ mol \%}$); from about 18 mol % to about 30 mol % B_2O_3 (i.e., $18 \text{ mol \%} \leq \text{B}_2\text{O}_3 \leq 30 \text{ mol \%}$); up to about 3 mol % MgO (i.e., $0 \text{ mol \%} \leq \text{MgO} \leq 3 \text{ mol \%}$); from about 2 mol % up to about 10 mol % CaO (i.e., $2 \text{ mol \%} \leq \text{CaO} \leq 10 \text{ mol \%}$); and up to about 3 mol % SrO (i.e., $0 \text{ mol \%} \leq \text{SrO} \leq 3 \text{ mol \%}$), wherein the sum of the alkali metal oxide modifiers is less than or equal to 1 mol (i.e., $0 \text{ mol \%} \leq \text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O} \leq 1 \text{ mol \%}$). In some embodiments, the total amount of MgO , CaO , and SrO in the

glasses described herein is greater than or equal to about 4 mol % and less than or equal to the amount of Al_2O_3 present in the glass (i.e., $4 \text{ mol \%} \leq \text{MgO} + \text{CaO} + \text{SrO} \leq \text{Al}_2\text{O}_3$). In some embodiments, the total amount of alkali and alkaline earth oxides in the glasses described herein is greater than or equal to about 4 mol % and less than or equal to the amount of Al_2O_3 present in the glass (i.e., $4 \text{ mol \%} \leq \text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O} + \text{MgO} + \text{CaO} + \text{SrO} \leq \text{Al}_2\text{O}_3$). In certain embodiments, the glass is free of P_2O_5 .

The glass may further include up to about 0.2 mol % ZrO_2 (i.e., $0 \text{ mol \%} \leq \text{ZrO}_2 \leq 0.2 \text{ mol \%}$), up to about 0.2 mol % Fe_2O_3 (i.e., $0 \text{ mol \%} \leq \text{Fe}_2\text{O}_3 \leq 0.2 \text{ mol \%}$) and at least one fining agent such as SnO_2 , CeO_2 , As_2O_3 , Sb_2O_5 , Cl^- , F^- , or the like. The at least one fining agent may, in some embodiments, include up to about 0.2 mol % SnO_2 (i.e., $0 \text{ mol \%} \leq \text{SnO}_2 \leq 0.2 \text{ mol \%}$).

Compositions and of non-limiting examples of these glasses are listed in Table 1. Each of the oxide components of these glasses serves a function. Silica (SiO_2) is the primary glass forming oxide, and forms the network backbone for the molten glass. Pure SiO_2 has a low CTE and is alkali metal-free. Due to its extremely high melting temperature, however, pure SiO_2 is incompatible with the fusion draw process. The viscosity curve is also much too high to match with any core glass in a laminate structure. In some embodiments, the amount of SiO_2 in the glasses described herein ranges from about 50 mol % to about 70 mol %. In other embodiments, the SiO_2 concentration ranges from about 55 mol % to about 70 mol %.

In addition to silica, the glasses described herein comprise the network formers Al_2O_3 and B_2O_3 to achieve stable glass formation, low CTE, low Young’s modulus, low shear modulus, and to facilitate melting and forming. By mixing all four of these network formers in appropriate concentrations, it is possible achieve stable bulk glass formation while minimizing the need for network modifiers such as alkali or alkaline earth oxides, which act to increase CTE and modulus. Like SiO_2 , Al_2O_3 contributes to the rigidity to the glass network. Alumina can exist in the glass in either fourfold or fivefold coordination. In some embodiments, the glasses described herein comprise from about 5 mol % to about 12 mol % Al_2O_3 and, in particular embodiments, from about 6 mol % to about 10 mol % Al_2O_3 .

Boron oxide (B_2O_3) is also a glass-forming oxide that is used to reduce viscosity and thus improves the ability to melt and form glass. B_2O_3 can exist in either threefold or fourfold coordination in the glass network. Threefold coordinated B_2O_3 is the most effective oxide for reducing the Young’s modulus and shear modulus, thus improving the intrinsic damage resistance of the glass. Accordingly, the glasses described herein, in some embodiments, comprise from about 12 mol % up to about 35 mol % B_2O_3 and, in other embodiments, from about 18 mol % to about 30 mol % B_2O_3 .

Alkaline earth oxides (MgO , CaO , and SrO), like B_2O_3 , also improve the melting behavior of the glass. However, they also act to increase CTE and Young’s and shear moduli. In some embodiments, the glasses described herein comprise up to about 5 mol % MgO , up to about 12 mol % CaO , and up to about 5 mol % SrO and, in other embodiments, up to about 3 mol % MgO , from about 2 mol % up to about 10 mol % CaO , and up to about 3 mol % SrO . In order to ensure that the vast majority of B_2O_3 in the glass is in the threefold coordinated state and thus obtain a high native scratch resistance, $(\text{MgO}) + (\text{CaO}) + (\text{SrO}) \leq (\text{Al}_2\text{O}_3) + 1 \text{ mol \%}$ in some embodiments, or, in other embodiments, $(\text{MgO}) + (\text{CaO}) + (\text{SrO}) \leq (\text{Al}_2\text{O}_3)$.

The glass may also include at least one fining agent such as SnO₂, CeO₂, As₂O₃, Sb₂O₅, Cl⁻, F³¹, or the like in small concentrations to aid in the elimination of gaseous inclusions during melting. In some embodiments, the glass may comprise up to about 0.7 mol % SnO₂, up to about 0.7 mol % CeO₂, up to about 0.5 mol % As₂O₃, and/or up to about 0.5 mol % Sb₂O₃. In other embodiments, at least one fining agent may comprise up to about 0.2 mol % SnO₂.

A small amount of ZrO₂ may also be introduced by contact of hot glass with zirconia-based refractory materials in the melter, and thus monitoring its level in the glass may be important to judging the rate of tank wear over time. The glass, may in some embodiments, include up to about 0.1 mol % ZrO₂. The glass may further comprise low concentrations of Fe₂O₃, as this material is a common impurity in batch materials. In some embodiments, the glass may include up to about 0.5 mol % Fe₂O₃ and, in other embodiments, up to about 0.2 mol % Fe₂O₃.

TABLE 1

Exemplary compositions of glasses.						
mol %						
	1	2	3	4	5	6
SiO ₂	67.11	65.75	65.82	65.79	65.81	65.63
Al ₂ O ₃	9.90	9.49	9.46	9.41	9.39	9.36
B ₂ O ₃	13.30	15.44	15.43	15.60	15.65	15.94
Na ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
K ₂ O	0.02	0.02	0.02	0.02	0.02	0.01
MgO	0.39	0.39	0.39	0.39	0.21	0.19
CaO	8.92	8.72	8.73	8.66	8.75	8.64
SrO	0.21	0.07	0.02	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.07	0.05	0.05	0.05	0.08	0.11
ZrO ₂	0.03	0.02	0.03	0.03	0.03	0.05
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00
	7	8	9	10	11	12
SiO ₂	66.14	66.35	66.59	66.45	67.24	67.51
Al ₂ O ₃	9.17	8.81	8.38	8.01	7.66	7.45
B ₂ O ₃	15.81	16.27	16.90	17.72	17.60	17.87
Na ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
K ₂ O	0.02	0.01	0.01	0.01	0.01	0.01
MgO	0.19	0.18	0.17	0.17	0.15	0.00
CaO	8.47	8.17	7.75	7.39	7.07	6.90
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.10	0.10	0.09	0.12	0.12	0.11
ZrO ₂	0.04	0.05	0.04	0.07	0.08	0.08
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00
	13	14	15	16	17	18
SiO ₂	67.54	67.48	67.41	66.80	67.49	67.38
Al ₂ O ₃	7.32	7.27	7.27	7.20	7.23	7.22
B ₂ O ₃	17.94	18.11	18.17	18.94	18.19	18.29
Na ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
K ₂ O	0.01	0.01	0.01	0.01	0.01	0.01
MgO	0.15	0.15	0.15	0.15	0.15	0.15
CaO	6.79	6.75	6.76	6.67	6.71	6.73
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.10	0.10	0.10	0.09	0.09	0.09
ZrO ₂	0.08	0.06	0.06	0.07	0.06	0.06
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00

TABLE 1-continued

Exemplary compositions of glasses.						
mol %						
	19	20	21	22	23	24
SiO ₂	66.56	64.20	61.34	59.18	60.52	60.66
Al ₂ O ₃	7.39	7.46	8.17	8.08	8.25	8.24
B ₂ O ₃	18.75	20.87	22.04	24.39	22.71	22.60
Na ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
K ₂ O	0.01	0.01	0.01	0.01	0.01	0.01
MgO	0.16	0.15	0.17	0.17	0.18	0.18
CaO	6.91	7.06	7.92	7.90	8.07	8.04
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.10	0.11	0.17	0.13	0.12	0.12
ZrO ₂	0.06	0.07	0.11	0.07	0.07	0.08
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00
	25	26	27	28	29	30
SiO ₂	58.20	60.20	60.27	58.75	60.33	60.32
Al ₂ O ₃	8.53	8.12	8.08	7.87	8.09	8.07
B ₂ O ₃	24.88	23.24	23.30	25.21	23.19	23.22
Na ₂ O	0.04	0.04	0.04	0.03	0.03	0.03
K ₂ O	0.01	0.02	0.01	0.01	0.01	0.01
MgO	0.26	0.30	1.95	2.55	3.04	3.16
CaO	7.89	7.77	6.14	5.36	5.08	4.96
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.11	0.16	0.11	0.11	0.12	0.12
ZrO ₂	0.07	0.12	0.08	0.08	0.09	0.09
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00
	31	32	33	34	35	36
SiO ₂	58.80	60.59	60.69	61.01	60.98	59.86
Al ₂ O ₃	7.89	8.16	8.24	8.27	8.29	8.12
B ₂ O ₃	25.23	23.43	23.85	23.85	23.96	25.52
Na ₂ O	0.03	0.03	0.04	0.04	0.04	0.05
K ₂ O	0.01	0.01	0.01	0.01	0.01	0.01
MgO	3.19	3.44	3.67	3.84	3.89	3.84
CaO	4.64	4.09	3.26	2.72	2.56	2.34
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.11	0.12	0.11	0.13	0.13	0.12
ZrO ₂	0.10	0.10	0.10	0.11	0.12	0.12
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00
	31	32	33	34	35	36
SiO ₂	58.80	60.59	60.69	61.01	60.98	59.86
Al ₂ O ₃	7.89	8.16	8.24	8.27	8.29	8.12
B ₂ O ₃	25.23	23.43	23.85	23.85	23.96	25.52
Na ₂ O	0.03	0.03	0.04	0.04	0.04	0.05
K ₂ O	0.01	0.01	0.01	0.01	0.01	0.01
MgO	3.19	3.44	3.67	3.84	3.89	3.84
CaO	4.64	4.09	3.26	2.72	2.56	2.34
SrO	0.01	0.01	0.01	0.01	0.01	0.01
BaO	0.00	0.00	0.00	0.00	0.00	0.00
SnO ₂	0.11	0.12	0.11	0.13	0.13	0.12
ZrO ₂	0.10	0.10	0.10	0.11	0.12	0.12
Fe ₂ O ₃	0.01	0.01	0.01	0.01	0.01	0.01
Total	100.00	100.00	100.00	100.00	100.00	100.00

The high amount of boron present provides the glass with a high level of intrinsic or “native” scratch resistance without chemical strengthening by ion exchange. Scratch resistance is determined by Knoop scratch threshold testing. In Knoop threshold testing, a mechanical tester holds a Knoop diamond in which a glass is scratched at increasing loads to determine the onset of lateral cracking; i.e., sus-

tained cracks that are greater than twice the width of the original scratch/groove. This onset of lateral cracking is defined as the "Knoop Scratch Threshold." The glasses described herein have a minimum Knoop scratch threshold of about 15 N (Newtons). In some embodiments, the Knoop scratch threshold is at least 20 N and, in other embodiments, at least about 25 N.

Photographs of Knoop scratch test results for glass sample 25 in Table 1 are shown in FIGS. 2A-2F. The glass was not ion exchanged prior to testing. At loads of up to 26 N (FIGS. 2A-2D), no lateral cracking associated with the original scratch **200** is observed. Lateral cracking **202** is observed at a load of 28 N (FIG. 2E), but the degree of lateral cracking **212** is less than twice the width of the original scratch **202**. The Knoop Scratch Threshold for the glass is reached at a load of 30 N (FIG. 2F), as the lateral observed cracking **214** is greater than twice the width of the original scratch **204**.

In comparison to the glasses described herein, other alkaline earth borosilicate glasses (Eagle XG® Glass, manufactured by Corning Incorporated) exhibit a Knoop Scratch Threshold of 8-10 N, and ion exchanged alkali aluminosilicate glasses (Gorilla® Glass and Gorilla® Glass 3, manufactured by Corning Incorporated) exhibit Knoop Scratch Thresholds of 3.9-4.9 N and 9.8-12 N, respectively.

A method of making the glasses described herein is also provided the method includes providing a glass melt comprising SiO_2 , B_2O_3 , and at least one of Al_2O_3 and P_2O_5 , wherein the glass melt is substantially free of alkali metal oxide modifiers, and down-drawing the glass melt to form the glass. In some embodiments, the step of down-drawing the glass comprises slot-drawing the glass melt and, in other embodiments, fusion-drawing the glass melt.

In certain embodiments, the method further includes providing a core glass melt and fusion drawing the core glass melt to form a core glass having a coefficient of thermal expansion that is less than the coefficient of thermal expansion of the clad glass. The clad glass melt is then fusion drawn to form the clad glass layer, thereby surrounding the core glass. The clad glass layer is under a compressive stress of at least about 40 MPa and, in some embodiments, at least about 80 MPa.

Being substantially free of alkali metals, the glasses described herein are suitable for use in thin film transistor (TFT) display applications. These applications require an alkali-doped and alkali-free interface, since the presence of alkali ions poisons the thin film transistors. Thus, ion exchanged alkali-containing glasses are unsuitable for such applications. Glass laminates that employ the alkali-doped and alkali-free glasses described herein as a clad layer provide a strengthened glass product combined with an interface that is either alkali-doped and alkali-free or doped with a low level (<1 mol %) alkali metals or alkali metal oxides. In some embodiments, the alkali-doped and alkali-free glasses also have high annealing and strain points to reduce thermal compaction, which is desirable for TFT display substrates. The glasses described herein may also be used in color filter substrates, cover glasses, or touch interfaces in various electronic devices.

While typical embodiments have been set forth for the purpose of illustration, the foregoing description should not be deemed to be a limitation on the scope of the disclosure or appended claims. Accordingly, various modifications, adaptations, and alternatives may occur to one skilled in the art without departing from the spirit and scope of the present disclosure or appended claims.

The invention claimed is:

1. A glass, the glass comprising:

about 50 mol % to about 70 mol % SiO_2 ;

about 6 mol % to about 10 mol % Al_2O_3 ;

about 18 mol % to about 30 mol % B_2O_3 ;

up to about 5 mol % MgO ;

up to about 10 mol % CaO ;

up to about 5 mol % SrO ; and

0.01 mol % to about 0.5 mol % Fe_2O_3 ,

wherein $\text{MgO}+\text{CaO}+\text{SrO}\leq\text{Al}_2\text{O}_3$, and a sum of alkali metal oxide modifiers is less than or equal to about 1 mol %.

2. The glass of claim 1, wherein $4\text{ mol \%}\leq\text{MgO}+\text{CaO}+\text{SrO}\leq\text{Al}_2\text{O}_3$.

3. The glass of claim 1, wherein the glass has a Young's modulus of less than about 65 GPa.

4. The glass of claim 3, wherein the Young's modulus is less than about 60 GPa.

5. The glass of claim 1, wherein the glass has a coefficient of thermal expansion of less than about $40\times 10^{-7}/^\circ\text{C}$.

6. The glass of claim 5, wherein the coefficient of thermal expansion is less than about $35\times 10^{-7}/^\circ\text{C}$.

7. The glass of claim 1, wherein the glass further comprises at least one of SnO_2 , CeO_2 , As_2O_3 , Sb_2O_5 , Cl^- , and F^- .

8. The glass of claim 1, wherein the glass comprises at least one of:

up to about 0.7 mol % SnO_2 ;

up to about 0.7 mol % CeO_2 ;

up to about 0.5 mol % As_2O_3 ; and

up to about 0.5 mol % Sb_2O_5 .

9. The glass of claim 1, wherein the glass comprises:

about 55 mol % to about 70 mol % SiO_2 ;

greater than 6 mol % to about 10 mol % Al_2O_3 ;

about 18 mol % to about 30 mol % B_2O_3 ;

up to about 3 mol % MgO ;

up to about 10 mol % CaO ; and

up to about 3 mol % SrO .

10. The glass of claim 9, wherein the glass comprises up to about 0.2 mol % SnO_2 .

11. The glass of claim 10, wherein the glass forms a clad layer in a glass laminate, the glass laminate comprising a core glass and having a coefficient of thermal expansion that is greater than a coefficient of thermal expansion of the clad layer.

12. The glass of claim 11, wherein the clad layer is under a compressive stress of at least about 40 MPa.

13. The glass of claim 1, wherein the glass has a liquidus viscosity of at least 100 kpoise.

14. The glass of claim 1, wherein the glass is drawdownable.

15. The glass of claim 1, wherein the glass comprises up to about 0.1 mol % ZrO_2 .

16. The glass of claim 1, wherein the glass is free of alkali metal oxide modifiers.

17. The glass of claim 1, wherein the glass has a Knoop scratch threshold of at least 15 N.

18. The glass of claim 17, wherein the glass has a Knoop scratch threshold of at least 20 N.

19. The glass of claim 1, wherein the glass forms at least a portion of a color filter substrate, a thin film transistor substrate, a cover glass, or a touch interface.

20. The glass of claim 1, wherein the glass comprises 0 mol % BaO .

21. A glass, comprising:

$55\text{ mol \%}\leq\text{SiO}_2\leq 70\text{ mol \%}$;

$6\text{ mol \%}\leq\text{Al}_2\text{O}_3\leq 10\text{ mol \%}$;

11

- 18 mol % $\leq B_2O_3 \leq 30$ mol %;
 0 mol % $< MgO \leq 5$ mol %;
 0 mol % $< CaO \leq 12$ mol %;
 0 mol % $< SrO$, wherein 4 mol % $\leq (MgO + CaO + SrO) \leq (Al_2O_3 + 1 \text{ mol } \%)$; and
 0 mol % $\leq (Li_2O + Na_2O + K_2O) \leq 0.1$ mol %.
22. The glass of claim 21, wherein 4 mol % $\leq (MgO + CaO + SrO) \leq Al_2O_3$.
23. The glass of claim 22, wherein 4 mol % $\leq (Li_2O + Na_2O + K_2O + MgO + CaO + SrO) \leq Al_2O_3$.
24. The glass of claim 21, wherein 55 mol % $\leq SiO_2 \leq 64.20$ mol %.
25. The glass of claim 24, wherein 20.87 mol % $\leq B_2O_3 \leq 30$ mol %.
26. The glass of claim 21, where a majority of the B_2O_3 in the glass is in a threefold coordinated state.
27. A glass, comprising:
 55 mol % $\leq SiO_2 \leq 70$ mol %;
 6 mol % $\leq Al_2O_3 \leq 10$ mol %;

12

- 20.87 mol % $\leq B_2O_3 \leq 30$ mol %;
 4 mol % $\leq (MgO + CaO + SrO) \leq Al_2O_3$; and
 0 mol % $\leq (Li_2O + Na_2O + K_2O) \leq 0.1$ mol %.
28. The glass of claim 27, wherein 4 mol % $\leq (Li_2O + Na_2O + K_2O + MgO + CaO + SrO) \leq Al_2O_3$.
29. The glass of claim 27, where a majority of the B_2O_3 in the glass is in a threefold coordinated state.
30. A glass, comprising:
 55 mol % $\leq SiO_2 \leq 64.20$ mol %;
 6 mol % $\leq Al_2O_3 \leq 10$ mol %;
 18 mol % $\leq B_2O_3 \leq 30$ mol %;
 4 mol % $\leq (MgO + CaO + SrO) \leq Al_2O_3$; and
 0 mol % $\leq (Li_2O + Na_2O + K_2O) \leq 0.1$ mol %.
31. The glass of claim 30, wherein 4 mol % $\leq (Li_2O + Na_2O + K_2O + MgO + CaO + SrO) \leq Al_2O_3$.
32. The glass of claim 30, where a majority of the B_2O_3 in the glass is in a threefold coordinated state.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : RE49,307 E
APPLICATION NO. : 16/902663
DATED : November 22, 2022
INVENTOR(S) : Adam James Ellison et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On the Title Page

On page 3, in item (56), in Column 2, under “Other Publications”, Line 49, delete “Al.sub.20” and insert -- Al.sub.2O --.

In the Claims

In Column 10, Lines 50-51, in Claim 14, delete “downdrawable.” and insert -- down-drawable. --.

Signed and Sealed this
Twenty-eighth Day of February, 2023



Katherine Kelly Vidal
Director of the United States Patent and Trademark Office