



US00RE49523E

(19) **United States**
(12) **Reissued Patent**
Tyagi et al.

(10) **Patent Number: US RE49,523 E**
(45) **Date of Reissued Patent: May 9, 2023**

(54) **INTEGRAL POLYETHYLENE TEREPHTHALATE GRIDS, THE METHOD OF MANUFACTURE, AND USES THEREOF**

(58) **Field of Classification Search**
CPC Y10T 428/249921; B29K 2067/003
See application file for complete search history.

(71) Applicant: **TENSAR CORPORATION**, Atlanta, GA (US)

(56) **References Cited**

(72) Inventors: **Manoj Kumar Tyagi**, Fayetteville, GA (US); **William Stanley Shelton**, Lithonia, GA (US)

U.S. PATENT DOCUMENTS

4,374,798 A 2/1983 Mercer
4,590,029 A 5/1986 Mercer

(73) Assignee: **TENSAR CORPORATION, LLC**, Alpharetta, GA (US)

(Continued)

(21) Appl. No.: **15/880,932**

FOREIGN PATENT DOCUMENTS

(22) Filed: **Jan. 26, 2018**

DE 698 17 607 6/2004
GB 2 266 540 11/1993
WO WO 99/28563 6/1999

Related U.S. Patent Documents

Reissue of:

OTHER PUBLICATIONS

(64) Patent No.: **9,249,552**
Issued: **Feb. 2, 2016**
Appl. No.: **12/449,379**
PCT Filed: **Feb. 5, 2008**
PCT No.: **PCT/US2008/001481**
§ 371 (c)(1),
(2) Date: **May 3, 2010**
PCT Pub. No.: **WO2008/097523**
PCT Pub. Date: **Aug. 14, 2008**

Ward, I.M., "Mechanical Properties of Solid Polymers," Wiley Interscience, New York, 1971.

Primary Examiner — Timothy J. Kugel

(74) *Attorney, Agent, or Firm* — Jacobson Holman PLLC

U.S. Applications:

(57) **ABSTRACT**


(60) Provisional application No. 60/899,658, filed on Feb. 6, 2007.

An integral polymer grid with a plurality of interconnected, oriented polyethylene terephthalate strands and an array of openings therein is made from a polyethylene terephthalate sheet-like starting material having holes or depressions therein that form the openings when the sheet-like material is uniaxially or biaxially stretched. The grid has a higher tensile strength to weight ratio and a higher creep reduced strength to weight ratio than corresponding ratios associated with a grid made from a non-polyethylene terephthalate starting material.

(51) **Int. Cl.**
B29C 55/02 (2006.01)
E02D 17/20 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **E02D 17/00** (2013.01); **B29C 55/04** (2013.01); **B29C 55/12** (2013.01); **B29D 28/00** (2013.01);
(Continued)

36 Claims, 15 Drawing Sheets



(51) **Int. Cl.**

E02D 17/00 (2006.01)
B29C 55/04 (2006.01)
B29C 55/12 (2006.01)
B29D 28/00 (2006.01)
E02D 31/00 (2006.01)
B29K 67/00 (2006.01)

(52) **U.S. Cl.**

CPC *E02D 17/202* (2013.01); *E02D 31/004*
(2013.01); *B29K 2067/003* (2013.01); *Y10T*
428/24273 (2015.01); *Y10T 428/249921*
(2015.04)

(56)

References Cited

U.S. PATENT DOCUMENTS

4,743,486	A	5/1988	Mercer et al.	
4,756,946	A	7/1988	Mercer	
4,837,387	A *	6/1989	van de Pol 442/185
5,419,659	A	5/1995	Mercer B65D 71/504 405/302.7
6,312,198	B1	11/2001	Van Vliet et al.	
6,572,718	B2	6/2003	Heerten et al. B29C 66/526 156/73.6
2005/0112372	A1 *	5/2005	Rolland et al. C08J 5/18 428/364
2007/0003710	A1	1/2007	Lynch et al.	

* cited by examiner

FIG. 1




FIG. 2

CPET 3mm#1, 60% Loading




FIG. 3

CPET 3mm#2, 70% Loading






FIG. 4
PRIOR ART



Comparative creep curves under 40% of ultimate load for
 (1) nonwoven needled polypropylene fabric; (2) woven
 polypropylene fabric; (3) nonwoven needled fabric;
 (4) nonwoven thermal bonded polypropylene fabric.

FIG. 5
PRIOR ART



Creep curves for (1) polypropylene, (2) polyamide,
(3) polyester filaments.

FIG. 6

Table 1
Test Results

Variant	Pk load Newtons (N)	Test Specimen X-sectional area (mm ²)	Specific Tensile Strength (N/mm ²)	Comments
HOPEUS21-2	1328	68.66	22.31	HDPE unstretched, 21mm wide, 1.84mm thick same as above.
HOPEUS21-1	1311	57.4	22.8	
HOPEUS-2	2457	101.1	24.3	HDPE unstretched, 38.5mm wide, 1.84mm thick 3/8"-5/8" diablo punch, 4:1 heat set
HOPEUS-1	1417	9.277	152.74	
HOPEUS247-1	1154	7.06	163.4	20mm strip stretched 4:1 38.5mm strip (2.8mm thick) stretched 4:1 unstretched 38.5mm wide sample
HOPEUS20-1	1228	11.29	108.8	
HOPEUS-1	2175	20.99	105.6	38.5mm wide stretched 5.5:1 10:1 draw from 70.84mm ² X-section
APETUS385	4672	70.84	64.98	
APETUS21-1	2409	39.28	61.33	3/8"-5/8" diablo punch, stretched 4:1, sample from TD rib (SR 4.5:1) 3/8"-5/8" diablo punch, stretched 4:1, sample from punched rib (SR 2.25:1)
APETS385-3	1188	15.47	78.8	
APETS247-2	635	7.31	73.18	5:1 draw length 158mm between drawn ribs along md. Circle punched 5:1 draw Rib length 46mm 5:1 draw Rib length 121mm. Circle punched
APETS247-1	688	12.59	54.48	
APETS20-1	482	8.84	54.52	5.68:1 draw blushed while due to being orientated such that it became crystallized temp. 60degrees centigrade came as above.
APETS10-1a-1-1	176	3.125	66.32	
APETCS-R-1	432	6.58	65.8	CPET (1/4 inch thick crystalline PET from modern plaetice), dogbone shape sample CPET punched with 3/8"-5/8" diablo punch, stretched at 153 C, 15 min soak, ratio 2.35:1 CPET, dogbone, 3.58:1 draw 85degrees centigrade at 8min. dogbone shape sample
APETCS-C-1	401	7.33	54.7	
APETS20-C1	2438	13.45	181.8	4:1 First specimen pulled out of grips, did not brk. Second specimen eventually elipped but after the clamping force had been increased to the maximum system psig. Also after reaching the 9503 newton load.
APETS20-C2	2419	13.89	174.1	
CPETUS	21789	276.8	78.7	Specimen 2 broke at 11,023 newtons but data not used.
CPETS	8091	42.8	189	
CPETS2	19188	75.47	254.4	4.25:1 @125degrees centigrade Circle punch
PETGUS-1	12516	245.65	50.95	
PETGS-1	1608	20.82	77.8	3.1:1 DR. stretched on 4/12/06 at 125degrees centigrade. 4.4:1 @160 degrees centigrade tested on 4/20 and 4/21/08
CPETS3-205-1	8,503	26.22	197	
CPETS3-20-1	4013	24.68	162.6	3.27:1 140degrees centigrade. . spd change=0.148mpm data 4-14-06
CPETS3-205-2	8483	29.42	288	
CPETS3-205-3	8693	24.55	354	mini-dogbone samples, 40mm gauge length, 180 C in hot-box, 16 min, 5.3:1
CPETS-3-205-4.25:1	8923	26.57	373.6	
CPETS-CP-R-1	1933	6.55	295	4.17:1
CPETS3-230-1	2095	10.66	198.6	
CPETS3-203-1	2482	6.95	357	4.17:1
QT2-R-3	2436	8.9	301	
CPETS3-205-1	2104	10.28	205	3.27:1 140degrees centigrade. . spd change=0.148mpm data 4-14-06
QT2-R-6	1577	4.11	384	




FIG. 8

Table 2

Representative Specific Strength of Different Samples

<u>Sample</u>	<u>Description</u>	<u>N/mm2</u>	<u>Comments</u>
HDPE 1	Unstretched	23	2.9 mm thick
HDPE 2	Punched/Stretched	163	2.9 mm thick
APET 1	Unstretched	61	3 mm thick
APET 2	Punched/Stretched	63	3 mm thick
APET 3	Punched/Stretched/Crystallized	178	3 mm thick
CPET1	Unstretched	78	6 mm thick
CPET 2	Punched/Stretched	254	6 mm thick
CPET 3	Unstretched	63	3 mm thick
CPET 4	Punched/Stretched	373	3 mm thick
CPET 5	mini dog bone_stretched	384	3 mm thick
PETG 1	Unstretched	51	3 mm thick
PETG 2	Punched/Stretched	78	3 mm thick

FIG. 10

Effect of Stretch Ratio on Specific Strength

CPET 3mm

<u>Stretch Ratio</u>	<u>Specific Strength (N/mm2)</u>
3.1	197
3.27	205
4.17	301
4.4	357
5.3	384

FIG. 9




FIG. 11




FIG. 12

CPET 55 mil (1.4 mm) Stretch Ratio 4.25:1 Rig#24




FIG. 13
PRIOR ART

Comparison of Some Basic Properties of Different Polymers Used to Produce Staple Fibers, Continuous Filaments, and Oriented Tapes That are Candidates for Use in Geotextiles*

Polymer property	PA	N6	N6.6	PET	PP	LDPE	HDPE
Density, kg m^{-3}	1450	1140	1140	1380	900-910	920-930	940-960
Crystallinity, %	90	60	60	30-40	60-70	40-55	60-80
T_g , °C	340	30-60	30-60	75	-15 to 10	-100	-100
T_m , °C	550	215-220	250	250-260	160-165	110-120	125-135
Water adsorption at 20°C, 65% RH	0-4	0-4	0-4	0-4	0	0	0
Tensile strength (dry), N mm^{-2}	2760	700-900	700-900	800-1200	400-600	80-250	350-600
Breaking strain (dry), %	2.6	18-25	15-28	8-15	10-40	20-80	10-45
Tensile strength (wet), N mm^{-2}	—	600-800	600-800	800-1200	400-600	80-250	350-600
Breaking strain (wet), %	—	20-30	18-30	8-15	10-40	20-80	10-15

*Key: PA, para-aramid (e.g., Kevlar 49); N6, nylon 6; N6.6, nylon 6.6; PET, polyester; PP, polypropylene; LDPE, low-density polyethylene (used primarily as a bonding/encapsulating polymer); HDPE, high-density polyethylene; T_g , second-order transition temperature; T_m , melting temperature.

FIG. 14 PRIOR ART

Relative Chemical Resistance of Fiber-Forming Polymers Used
in Geotextiles^a

Polymer	Nylon		PET		PP		PE	
	A	B	A	B	A	B	A	B
Chemical								
Dilute acid	2	1	3	2	3	3	3	3
Concentrated acid	1	0	1	0	3	2	3	2
Dilute alkali	3	2	3	1	3	3	3	3
Concentrated alkali	1	0	1	0	3	3	3	3
Salt (brine)	3	3	3	3	3	3	3	3
Mineral oil	3	3	3	3	2	1	2	1
UV	2	1	2	1	1	0	1	0
UV (stabilized)	3	2	3	2	3	2	3	2
Heat (dry), 100°C	3	2	3	3	3	2	3	1
Steam, 100°C	3	2	1	0	1	0	1	0
Moisture absorption	3	3	3	3	3	3	3	3
Creep tendency	3	2	3	3	2	1	2	1

Key: A, short-term, installation; B, long-term, use; PET, polyester; PP, polypropylene; PE, polyethylene; 0, no resistance; 1, moderate resistance; 2, passable resistance; 3, good resistance.

FIG. 15 PRIOR ART

**Results of Various Geotextile Fabric Tensile Tests
(Expressed as Percentage of Strength at Zero Time Exposure)^a**

Exposure time (days)	PP woven	PVC woven	PET needled nonwoven	PP needled nonwoven	PET heatset nonwoven	PP heatset nonwoven
(a) Tap water, pH = 7						
0	100	100	100	100	100	100
1	97	100	100	83	96	102
4	86	92	100	83	104	102
7	95	110	100	110	110	101
14	100	98	97	93	96	92
28	91	110	97	100	93	90
42	91	110	100	100	100	106
63	95	99	100	92	110	99
96	100	110	100	98	97	96
120	103	109	110	110	94	93
(b) CaO solution, pH = 10						
0	100	100	100	100	100	100
1	96	99	100	98	100	105
4	93	99	100	100	110	126
7	110	120	99	100	110	97
14	97	110	99	100	94	92
28	110	110	99	100	90	102
42	110	120	93	90	95	111
63	110	130	92	100	92	105
96	110	120	94	100	94	99
120	100	110	91	100	94	92
(c) CaO solution, pH = 12						
0	100	100	100	100	100	100
1	110	110	97	89	91	111
4	96	120	95	87	94	92
7	110	110	96	100	95	86
14	110	110	94	99	88	114
28	100	110	92	93	92	101
42	96	100	74	94	86	85
63	100	110	73	85	82	104
96	98	100	70	92	80	110
120	97	100	70	110	80	89




FIG. 16

**INTEGRAL POLYETHYLENE
TEREPHTHALATE GRIDS, THE METHOD
OF MANUFACTURE, AND USES THEREOF**

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue; a claim printed with strikethrough indicates that the claim was canceled, disclaimed, or held invalid by a prior post-patent action or proceeding.

CROSS-REFERENCE TO RELATED
APPLICATION

This application is a national stage of PCT/US08/001481 filed Feb. 5, 2008 and published in English, which claims the benefit of priority to U.S. Provisional Application for Patent No. 60/899,658 filed Feb. 6, 2007, hereby incorporated by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates generally to integral polymer geogrids and other oriented grids used for structural or construction reinforcement purposes. More particularly, the present invention relates to such integral polymer grids made from homopolymer and copolymer polyethylene terephthalate ("PET") in order to achieve a higher tensile strength to weight ratio and a higher creep reduced strength to weight ratio.

This invention also relates to the method of producing such integral PET grids. Lastly, the present invention relates to the use of such integral PET grids for soil reinforcement and methods of such reinforcement.

For the purpose of this invention, the terms "integral PET grid" and "integral PET grids" are intended to include integral polyethylene terephthalate geogrids and other integral polyethylene terephthalate grid structures made by orienting (stretching) starting materials in the form of sheets or the like having holes or depressions made or formed therein.

2. Description of the Prior Art

Polymeric integral grid structures having mesh openings defined by various geometric patterns of substantially parallel, orientated strands and junctions therebetween, such as geogrids, have been manufactured for over 25 years. Such grids are manufactured by extruding an integrally cast sheet which is subjected to a defined pattern of holes or depressions followed by the controlled uniaxial and biaxial orientation of the sheet into strands and junctions defined by mesh openings formed by the holes or depressions. Orienting the sheet in either the uniaxial or biaxial direction develops strand tensile strength and modulus in the corresponding direction. These integral oriented polymer grid structures can be used for retaining or stabilizing particulate material of any suitable form, such as soil, earth, sand, clay, gravel, etc. and in any suitable location, such as on the side of a road or other cutting or embankment, beneath a road surface, runway surface, etc.

Various shapes and patterns of holes have been experimented with to achieve higher levels of strength to weight ratio, or to achieve faster processing speeds during the manufacturing process. Orientation is accomplished under controlled temperatures and strain rates. Some of the variables in this process include draw ratio, molecular weight,

molecular weight distribution, and degree of branching or cross linking of the polymer. As a result of the orientation process, the finished product has a much higher tensile modulus and a highly reduced creep sensitivity.

The manufacture and use of such geogrid and other integral polymer grid structures can be accomplished by well-known techniques. As described in detail in U.S. Pat. No. 4,374,798 to Mercer et al. ("Production of Plastic Mesh Structure"), U.S. Pat. No. 5,419,659 to Mercer et al. ("Plastic Material Mesh Structure"), U.S. Pat. No. 4,590,029 to Mercer et al. ("Molecularly Orienting Plastics Material"), U.S. Pat. No. 4,743,486 to Mercer and Martin ("Product and Method of Producing a Plastics Material Mesh Structure"), and U.S. Pat. No. 4,756,946 to Mercer ("Plastic Material Mesh Structure"), a starting polymeric sheet material is first extruded and then punched to form the requisite defined pattern of holes or depressions.

As disclosed in the aforesaid patents, the starting sheet material is uniplanar or substantially uniplanar. As further described in the aforesaid patents, the uniplanar or substantially uniplanar punched starting material can be stretched only in the machine direction whereby the polymeric material between the punched holes is stretched to form highly molecularly oriented parallel strands interconnected by parallel transverse bars substantially at right angles to the strands. The stretching is continued so that the molecular orientation extends into the mostly unoriented transverse bar, which forms the junctions between the aligned strands. This uniaxial stretching of the punched starting material forms a uniaxial integral mesh structure, or uniaxial integral geogrid. The uniaxial integral geogrid is substantially uniplanar and has a plurality of highly oriented parallel strands that are interconnected by partially oriented junctions in the transverse bar, all substantially symmetrical about a median plane. The highly oriented parallel strands and the parallel transverse bars form an array of longitudinal openings between the parallel strands.

As further described in the aforesaid patents, when the substantially uniplanar starting material is biaxially stretched, i.e., first in the machine direction and then in the transverse direction, the stretching forms a biaxial integral mesh structure, or biaxial integral geogrid. The biaxial integral geogrid is also substantially uniplanar and has a plurality of highly oriented strands interconnected by partially oriented junctions, all substantially symmetrical about a median plane. The highly oriented strands and the partially oriented junctions define an array of mesh openings in the biaxial integral geogrid.

When imparting the high molecular orientation to the strands of the biaxial integral geogrid during the biaxial stretching, the molecular orientation is caused to extend into the junctions and around the crotch of the partially oriented junctions between adjacent oriented strands.

It is intended that the present invention be applicable to all integral PET grids regardless of the method of forming the starting material or orienting the starting material into the geogrid or grid structure. The subject matter of the foregoing patents is expressly incorporated into this specification by reference as if the patents were set forth herein in their entireties. These patents are cited as illustrative, and are not considered to be inclusive, or to exclude other techniques known in the art for the production of integral polymer grid materials.

Traditionally, the polymeric materials used in the production of integral grids have been high molecular weight homopolymer or copolymer polypropylene, and high density, high molecular weight polyethylene. Various additives,

3

such as ultraviolet light inhibitors, carbon black, processing aids, etc., are added to these polymers to achieve desired effects in the finished product.

While the conventional polypropylene and polyethylene materials exhibit generally satisfactory properties, it is structurally and economically advantageous to produce a grid material having a higher tensile strength to weight ratio and a higher creep reduced strength to weight ratio.

Creep is the process by which the dimensions of a material change with time, while subjected to a sustained or variable load. See, e.g., FIGS. 4 and 5. FIG. 4 illustrates comparative creep curves for various conventional polymeric geotextile materials such as polypropylene and polyester under loading of 40% ultimate strength. FIG. 5 shows representative creep curves for filaments of various polymers.

The creep behavior of a synthetic material is a function not only of polymer type and physical structure, but also of factors such as geometric structure (e.g., woven, nonwoven, integral grid, etc.), surrounding medium, environmental temperature, presence of any micro or macro damage, and aging.

With regard to the temperature factor, polymers creep significantly when exposed to stress above their glass transition temperature, T_g . This means that high density polyethylene ("HDPE") and polypropylene ("PP"), with a T_g of -120°C . and -18°C ., respectively, creep substantially more at ambient temperature than does PET, which has a T_g of 69°C .

Another method of manufacturing grids employs weaving or knitting technology. High tenacity filaments of either PET or polypropylene are twisted together to form yarn. These yarns are either woven or knitted into open structured fabric and then coated with a protective coating to provide protection to the core yarns. The protective coating can be, for example, polyvinyl chloride (PVC), a bituminous substance, or latex. The primary difference between products manufactured using this technology and the aforementioned integral grids is that the woven or knitted products have flexible junctions with considerably low junction strength. Some examples of such grids are the geogrids manufactured by companies such as Merex, Huesker, and Strata. FIG. 13 of the drawings summarizes basic properties of various polymers typically used to produce staple fibers, continuous filaments, and oriented tapes.

Still another method of manufacturing grids uses highly oriented ribs or straps of polyester. The ribs are processed in a welding device in which cross machine direction ribs are introduced and welded together forming dimensional apertures. An example of such a grid is the Secugrid® manufactured by NAUE GmbH & Co. The junction strength of products manufactured using this method tends to fall between that of integral grids and woven/knit grids.


Therefore, a need exists for an integral polymer material that not only is suitable for use in geogrid service, but that exhibits a higher tensile strength to weight ratio and a higher creep reduced strength to weight ratio than those values associated with conventional geogrid materials.

SUMMARY OF THE INVENTION

Polyethylene terephthalate ("PET") is an attractive polymer for use in soil reinforcement projects because it is a relatively low cost commodity polymer, demonstrates high tenacity and low creep behavior, and is fairly resistant to naturally occurring chemicals in soil.

4

As is evident from its structural formula (below), PET is a much bulkier molecule than polyethylene:



The PET molecule is planar, as required by resonance, but the main chains are not planar due to rotation about the C—O bond. The stiffening action of the p-phenylene group leads to a high melting point and good fiber forming properties.

Accordingly, it is an object of the present invention to produce an integral geogrid or other grid structure from a polyethylene terephthalate starting material according to known process methods, such as those described in the aforementioned U.S. Pat. Nos. 4,374,798, 5,419,659, 4,590,029, 4,743,486, 4,756,946, as well as many other patents.

As indicated above, high density polyethylene and polypropylene, with a T_g of -120°C . and -18°C ., respectively, creep substantially more at ambient temperature than does polyethylene terephthalate, which has a T_g of 69°C . In PET, since the T_g is much higher than ambient temperature, creep is largely attributable to steric reorganization of the tightly packed non-crystalline region polymer chain segments, which results in little or no chain slippage.

As a result, a PET material is characterized by a higher creep reduced strength to weight ratio than that of conventional geogrid materials. That is, since PET exhibits much lower creep than does, for example, HDPE, the PET can be used at up to about 70% of ultimate tensile strength, but HDPE only up to about 40%. Accordingly, for an integral geogrid material possessing a specified creep value, an integral PET grid will weigh substantially less than a geogrid using a conventional geogrid material, such as HDPE or PP.

In addition, a PET material is characterized by a higher tensile strength to weight ratio than that of conventional geogrid materials. For example, at comparable stretch ratios, crystalline PET ("CPET") exhibits almost double the specific strength of HDPE.

Therefore, another object of the present invention is to provide an integral polymer grid made from homopolymer and copolymer polyethylene terephthalate that is characterized by both a higher tensile strength to weight ratio and a higher creep reduced strength to weight ratio than those values associated with integral polymer grids made of conventional geogrid materials.

In addition to the aforementioned structural advantages, PET exhibits good resistance to salts, organic acids, organic solvents, oxidizing agents, reducing agents, and petroleum components, including bitumen often found in soil and related materials. As a result, the integral PET grid according to the present invention is especially attractive for use in soil reinforcement service.

Therefore, still another object of the present invention is to provide an integral polymer grid made from homopolymer and copolymer polyethylene terephthalate that exhibits good resistance to various agents encountered in soil reinforcement service.

These together with other objects and advantages which will become subsequently apparent reside in the details of construction and operation as more fully hereinafter described, reference being had to the accompanying drawings forming a part hereof, wherein like reference numbers

refer to like parts throughout. The accompanying drawings are intended to illustrate the invention, but are not necessarily to scale.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a sample of a crystalline polyethylene terephthalate (CPET) grid according to one embodiment of the present invention in which the starting sheet was uniaxially stretched to a stretch ratio of 3.1:1.

FIG. 2 is a creep test chart showing a creep curve for a CPET sample, initially 3 mm thick, which is uniaxially stretched to a stretch ratio of 5.3:1 and suspended under 60% loading.

FIG. 3 is a creep test chart showing a creep curve for a CPET sample, also initially 3 mm thick, which is uniaxially stretched to a stretch ratio of 5.3:1, but suspended under 70% loading.

FIG. 4 is a graph illustrating comparative creep curves for various polymeric geotextile materials under loading of 40% ultimate strength.

FIG. 5 is a graph illustrating representative creep curves for filaments of various polymers.

FIG. 6 is a table summarizing the tensile test results of the various polymeric samples tested.

FIG. 7 is a chart illustrating the specific strength of the samples shown in FIG. 6.

FIG. 8 is a table summarizing the specific strength of certain representative samples shown in FIG. 7.

FIG. 9 is a chart summarizing the specific strength of the representative samples shown in FIG. 8.

FIG. 10 is a table summarizing the effect of the stretch ratio on the specific strength of a PET sample.

FIG. 11 is a graph depicting the effect of the stretch ratio on the specific strength summarized in FIG. 10.

FIG. 12 is a creep test chart showing a creep curve for a CPET sample, initially 1.4 mm thick, which is stretched to a stretch ratio of 4.25:1 and suspended under 60% loading.

FIG. 13 is a table summarizing basic properties of various polymers typically used to produce staple fibers, continuous filaments, and oriented tapes.

FIG. 14 is a table summarizing the relative chemical resistance of various fiber-forming polymers used in geotextiles.

FIG. 15 is a table summarizing the effect of pH on the tensile strength of various geotextile polymers.

FIG. 16 illustrates a substantially uniplanar biaxial integral geogrid as shown for a composite of FIGS. 3 and 5 of U.S. Pat. No. 4,374,798.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Although only preferred embodiments of the invention are explained in detail, it is to be understood that the invention is not limited in its scope to the details of construction and arrangement of components set forth in the following description or illustrated in the drawings. The invention is capable of other embodiments and of being practiced or carried out in various ways.

Also, in describing the preferred embodiments, terminology will be resorted to for the sake of clarity. It is intended that each term contemplates its broadest meaning as understood by those skilled in the art, and includes all technical equivalents which operate in a similar manner to accomplish a similar purpose.

In order to understand the behavior and properties of the PET material, and to establish the parameters of using PET to make integral grids, instead of HDPE, standard commercially available extruded sheets of PET were procured.

Three types of PET sheets were used: amorphous PET ("APET"), crystalline PET ("CPET"), and PET glycol ("PETG").

Punched samples for each of the three types of PET sheet were prepared with standard sheet punches such as those used to manufacture HDPE UX products sold by the Tensar International Corporation, Inc. (hereinafter "Tensar") (Atlanta, Ga.), the assignee of the instant provisional application for patent. For example, FIG. 1 shows a CPET starting sheet sample prepared using a punch (1.53"x0.375") and uniaxially stretched to a stretch ratio of 3.1:1.

The punched sheet uniaxial stretching was performed on a Tensar laboratory stretcher. Tensar carried out initial laboratory work in accordance with the present invention by stretching narrow strips, i.e., from 2 mm to 4 mm wide, of PET and HDPE to establish the temperature and stretch ratio conditions under which the testing would be conducted. The temperature range was established to be between 100° C. and 240° C., and the stretch ratio range to be between 2:1 and 10:1. These temperature and stretch ratio conditions were then used during stretching of the approximately 8"x10" punched samples.

For high temperature stretching, i.e., above 160° C., an Instron "Hot-Box" was installed on an Instron Model 1125 tensile testing machine. Standard "dog bone"-shaped samples of CPET, having an initial thickness of 3 mm, were heated to, and then conditioned at, 180° C. for 15 minutes. The heat-conditioned samples were then uniaxially stretched in the lab stretcher in accordance with standard stretching protocols used by Tensar. The samples were stretched to the maximum stretch ratio that was allowed by the size of the Hot-Box, i.e., a ratio of 5.3:1. These 5.3:1 samples were then tested for both tensile and creep properties.

The unstretched and stretched strips and ribs from the 8"x10" samples were tested for tensile properties on an Instron Model 1125 tensile testing machine using serrated pneumatic grips. The testing grips were padded with cardboard and/or sandpaper to prevent slippage and edge break. The tensile data was normalized for the difference in sheet thickness between the HDPE and the PET by dividing the tensile results by the initial cross-sectional area of the test specimen (i.e., the resultant tensile data has the units of N/mm²). This normalization enabled a material-to-material comparison without the need to standardize the physical dimensions of the test specimens.

Finally, a strength to basis weight comparison was made between standard Tensar HDPE UX products and the 8"x10" PET punched and stretched samples.

For creep testing, the 5.3:1 stretch ratio samples were suspended under a load at room temperature in a quality control laboratory. One sample was suspended under a load corresponding to 60% of ultimate tensile strength (FIG. 2), and a second sample was suspended under a load corresponding to 70% of ultimate tensile strength (FIG. 3).

Tensile strength test data associated with the aforementioned 5.3:1 stretch ratio samples is presented in FIGS. 6 and 7. A summary of representative data from FIGS. 6 and 7 is presented in FIGS. 8 and 9. FIG. 8 presents representative specific strength values for each type of polymer at unstretched and maximum stretch ratio conditions.

Since the 3 mm thick CPET starting sheet provided the maximum specific strength among the samples summarized in FIGS. 6-8, samples of the 3 mm CPET starting sheet were

uniaxially stretched at various ratios of from 3.1:1 to 5.3:1. These results are shown in FIGS. 10 and 11. From this data it is evident that for the 3 mm CPET starting sheet there exists a substantially linear relationship between stretch ratio and specific tensile strength (see FIG. 11).

As is evident from the results presented herein, CPET is a good candidate for the manufacture of extruded and uniaxially stretched integral grids because of a higher specific strength and better creep characteristics. At comparable stretch ratios, CPET exhibits almost double the specific strength of HDPE. That is, as is evident from FIG. 8, sample HDPE 2 (initial thickness of 2.9 mm) has a specific strength of 163 N/mm², while sample CPET 4 (initial thickness of 3 mm) has a specific strength of 373 N/mm².

Since APET starting sheets crystallize during the heated stretching operation, APET starting sheets can achieve a specific strength similar to that of HDPE. But, the required crystallization associated with the heated stretching of APET starting sheets makes the process slow and more expensive. Hence, CPET starting sheets are clearly preferred for the present invention.

The PETG starting sheets did not show any significant difference between unstretched and stretched samples even at a stretch ratio of 8.5:1.

As is evident from FIGS. 2 and 3, the first 5600 hrs of creep data show that there is minimal strain associated with the CPET samples. That is, the strain is only 0.78% at 60% loading, and 1.34% at 70% loading.

Another test demonstrated the ability to prepare a grid from a CPET sheet having an initial thickness of 1.4 mm. The sample was first punched, then stretched to a stretch ratio of 4.25:1, and finally placed under a loading of 60% of ultimate tensile strength. As is evident from FIG. 12, creep data for the 1.4 mm sample for the first 2000 hours shows a strain of only about 2.4%.

The inventive polymer mesh structure has been described herein primarily in the context of being one that is uniaxially oriented, i.e., as being produced via uniaxial stretching of the punched starting material so as to form a uniaxial integral mesh structure.

However, in yet another possible embodiment of the invention, the polymer mesh structure is one that is biaxially oriented. That is, in this embodiment of the invention, the substantially uniplanar starting material is biaxially stretched, i.e., first in the machine direction and then in the transverse direction, so as to form a biaxial integral mesh structure. As indicated above in the Background section, such a biaxial orientation method is disclosed in certain of the above-described patents, such as U.S. Pat. No. 4,374,798 to Mercer et al. ("Mercer '798"). See, for example, FIG. 16 of the instant application, which illustrates a substantially uniplanar biaxial integral geogrid as shown for a composite of FIGS. 3 and 5 of the Mercer '798 patent. Accordingly, the instant invention is also directed to a biaxially oriented mesh structure having the polyethylene terephthalate integral geogrid.

While the integral PET grid according to the present invention exhibits the above-described advantageous characteristics, PET in general can be susceptible to hydrolysis during wet processing and in end use. PET is hydrolyzed by certain acids and by all strong bases, including some organic bases. The factors that can affect this hydrolysis include carboxyl end group ("CEG"), molecular weight, crystallinity, orientation, surface area, temperature, pH level, and the presence of cations. See FIG. 14, which summarizes the relative chemical resistance of various fiber-forming poly-

mers used in geotextiles, and FIG. 15, which summarizes the effect of pH on the tensile strength of various geotextile polymers.

For example, one literature source has proposed that PET hydrolysis is proportional to the square root of the CEG concentration. I. M. Ward, Mechanical Properties of Solid Polymers, Wiley Interscience, New York, 1971. Molecular weight inversely affects the CEG concentration. Hence, a higher molecular weight PET will be less susceptible to hydrolysis. Orientation can also lessen the hydrolytic effect in that it reduces the diffusion rate of the penetrant.

Thus, while there are no specific additives that can retard hydrolysis in PET materials, one or more of the aforementioned variables of CEG, molecular weight, crystallinity, orientation, surface area, temperature, pH, and the presence of cations can be manipulated to improve resistance to hydrolysis.

The foregoing is considered as illustrative only of the principles of the invention. Further, since numerous modifications and changes may readily occur to those skilled in the art, it is not desired to limit the invention to the exact construction and operation described and shown.

What is claimed is:

1. A polymer mesh structure comprising a substantially uniplanar integral geogrid having a plurality of highly oriented strands interconnected by partially oriented junctions forming an array of openings in said geogrid, said integral geogrid formed of polyethylene terephthalate and having (a) a tensile strength per unit of cross-sectional area of from approximately 63N/mm² to approximately 384N/mm² and (b) a creep strain at 60% loading which starts out at about 0.75% and does not exceed about 1.00% after 10,000 hours loading.

2. The polymer mesh structure according to claim 1, wherein the highly oriented polyethylene terephthalate strands have been uniaxially or biaxially stretched.

3. The polymer mesh structure according to claim 1, wherein the polyethylene terephthalate is a homopolymer or a copolymer.

4. The polymer mesh structure according to claim 1, wherein the polyethylene terephthalate is selected from the group consisting of amorphous polyethylene terephthalate, crystalline polyethylene terephthalate, and polyethylene terephthalate glycol.

5. The polymer mesh structure according to claim 1, wherein the plurality of highly oriented polyethylene terephthalate strands includes oriented transverse strands and oriented longitudinal strands interconnected by partially oriented polyethylene terephthalate junctions.

6. The polymer mesh structure according to claim 1, wherein the integral geogrid is configured for structural or construction reinforcement purposes.

7. The polymer mesh structure according to claim 1, wherein the plurality of highly oriented polyethylene terephthalate strands are aligned in a longitudinal array by unilateral stretching and each aligned pair of the highly oriented strands are interconnected by a partially oriented polyethylene terephthalate junction aligned in a transverse bar.

8. The polymer mesh structure according to claim 1, wherein the polyethylene terephthalate has a creep strain at 70% loading which starts out at about 0.75% and does not exceed about 1.50% after 10,000 hours loading.

9. A starting material for making an integral polymer geogrid comprising a homogeneous polyethylene terephthalate substantially uniplanar material having holes or depressions therein that provide highly oriented polyethylene tere-

phthalate strands interconnected by partially oriented junctions forming an array of grid openings, when the substantially uniplanar material is uniaxially or biaxially stretched,

said integral polymer geogrid having (a) a tensile strength to weight ratio of from approximately 63N/mm² to approximately 384N/mm² and (b) a creep strain at 60% loading which starts out at about 0.75% and does not exceed about 1.00% after 10,000 hours loading.

10. The starting material according to claim 9, wherein the polyethylene terephthalate is crystalline polyethylene terephthalate.

11. The starting material according to claim 9, wherein the substantially uniplanar starting material has an initial thickness of at least 1.4 mm.

12. The starting material according to claim 11, wherein the substantially uniplanar starting material has an initial thickness of at least 3 mm.

13. The starting material according to claim 12, wherein the stretched substantially uniplanar starting material exhibits a substantially linear relationship between a stretch ratio and a specific tensile strength.

14. The starting material according to claim 9, wherein the polyethylene terephthalate has a creep strain at 70% loading which starts out at about 0.75% and does not exceed about 1.50% after 10,000 hours loading.

15. A soil construction comprising a mass of particulate material strengthened by embedding therein a polymer mesh structure as claimed in claim 1.

16. A method of strengthening a mass of particulate material, comprising embedding in the mass of particulate material a polymer mesh structure as claimed in claim 1.

17. A method of making a polymer mesh structure, comprising orienting a substantially uniplanar homogeneous polyethylene terephthalate starting material having holes or depressions therein into an integral geogrid having a plurality of highly oriented[.] polyethylene terephthalate strands interconnected by partially oriented junctions to configure the holes or depressions as mesh openings,

said integral geogrid having (a) a tensile strength per unit of cross-sectional area of from approximately 63N/mm² to approximately 384N/mm² and (b) a creep strain at 60% loading which starts out at about 0.75% and does not exceed about 1.00% after 10,000 hours loading.

18. The method according to claim 17, wherein the substantially uniplanar polyethylene terephthalate starting material is oriented by uniaxial or biaxial stretching.

19. The method according to claim 17, wherein the polyethylene terephthalate is crystalline polyethylene terephthalate.

20. The method according to claim 19, wherein the substantially uniplanar polyethylene terephthalate starting material has an initial thickness of at least 3 mm.

21. The method according to claim 17, further comprising a step of manipulating a variable associated with the polyethylene terephthalate to improve resistance of the integral [geogrid] geogrid to hydrolysis, the variable being selected from the group consisting of carboxyl end group, molecular weight, crystallinity, orientation, surface area, temperature, pH, and cation presence.

22. The method according to claim 17, wherein the polyethylene terephthalate has a creep strain at 70% loading which starts out at about 0.75% and does not exceed about 1.50% after 10,000 hours loading.

23. A method of providing a stabilized soil construction, comprising:

[uniaxially] uniaxially or biaxially stretching a crystalline polyethylene terephthalate substantially uniplanar starting material having holes or depressions therein to form an integral geogrid having a plurality of highly oriented polyethylene terephthalate strands interconnected by partially oriented junctions which define a plurality of grid openings,

said integral polymer geogrid having (a) a tensile strength per unit of cross-sectional area of from approximately 63N/mm² to approximately 384N/mm² and (b) a creep strain at 60% loading which starts out at about 0.75% and does not exceed about 1.00% after 10,000 hours loading; and

embedding the integral geogrid in a mass of particulate material.

24. The method according to claim 23, wherein the polyethylene terephthalate has a creep strain at 70% loading which starts out at about 0.75% and does not exceed about 1.50% after 10,000 hours loading.

25. *A substantially uniplanar integral geogrid formed by uniaxially or biaxially stretching and orienting a substantially uniplanar sheet-like material having an array of perforations or indentations, said substantially uniplanar integral geogrid comprising:*

a plurality of interconnected, oriented strands and partially oriented junctions having an array of openings therebetween, with the substantially uniplanar sheet-like material and the substantially uniplanar integral geogrid being made of polyethylene terephthalate.

26. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate substantially uniplanar sheet-like material is biaxially stretched and oriented to form the polyethylene terephthalate substantially uniplanar integral geogrid having molecularly oriented longitudinal strands and molecularly oriented transverse strands interconnected by the partially oriented junctions which define generally square or rectangular grid openings.*

27. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate is a homopolymer or a copolymer.*

28. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate is selected from the group consisting of amorphous polyethylene terephthalate, crystalline polyethylene terephthalate, and polyethylene terephthalate glycol.*

29. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate substantially uniplanar sheet-like material is uniaxially stretched and oriented to form a generally square or rectangular grid of substantially parallel oriented strands and a set of substantially parallel bars generally at right angles to the strands, wherein an end of each of the strands is oriented into adjacent ones of said parallel bars.*

30. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate substantially uniplanar sheet-like material has an initial thickness of at least about 1.4 mm.*

31. *The substantially uniplanar integral geogrid according to claim 25, wherein the polyethylene terephthalate strands include substantially transversely oriented strands interconnected by substantially longitudinally oriented strands.*

32. *A starting material for making a substantially uniplanar integral geogrid, said starting material comprising:*
a substantially uniplanar sheet-like material having holes or depressions therein that provides a plurality of

interconnected, oriented strands and partially oriented junctions having an array of openings therebetween when the substantially uniplanar sheet-like material is uniaxially or biaxially stretched, with the substantially uniplanar sheet-like material being made of polyethylene terephthalate. 5

33. *The starting material according to claim 32, wherein the stretched polyethylene terephthalate substantially uniplanar sheet-like material exhibits a substantially linear relationship between a stretch ratio and a specific tensile strength.* 10

34. *A method of making a substantially uniplanar integral geogrid, said method comprising:*

stretching and orienting a substantially uniplanar sheet-like material having holes or depressions therein to provide a plurality of interconnected, oriented strands and partially oriented junctions, and to configure the holes or depressions as geogrid openings, with the substantially uniplanar sheet-like material and the substantially uniplanar integral geogrid being made of polyethylene terephthalate. 15 20

35. *The method according to claim 34, wherein the polyethylene terephthalate substantially uniplanar sheet-like starting material is oriented by uniaxial or biaxial stretching.* 25

36. *The method according to claim 34, wherein the polyethylene terephthalate is crystalline polyethylene terephthalate.*

* * * * *